



(43) International Publication Date
18 October 2012 (18.10.2012)

WIPO | PCT

(10) International Publication Number
WO 2012/139223 A1

(51) International Patent Classification:

A61K 9/10 (2006.01) *A61K 9/00* (2006.01)
A61K 38/18 (2006.01) *A61P 17/02* (2006.01)
A61K 47/30 (2006.01) *A61P 19/08* (2006.01)
A61K 47/34 (2006.01)

(21) International Application Number:

PCT/CA2012/050234

(22) International Filing Date:

11 April 2012 (11.04.2012)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/474,049 11 April 2011 (11.04.2011) US

(71) Applicant (for all designated States except US): **INDUCE BIOLOGICS INC.** [CA/CA]; 66 Avenue Road, Unit 3, Toronto, Ontario M5R 3N8 (CA).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **CLOKIE, Cameron M.L.** [CA/CA]; 40 Blyth Hill Road, Toronto, Ontario M4N 3L7 (CA). **PEEL, Sean A.F.** [CA/CA]; 2188 Munn's Avenue, Oakville, Ontario L6H 3T8 (CA).

(74) Agents: **CHARI, Santosh K.** et al.; Blake, Cassels & Graydon LLP, Box 25, Commerce Court West, 199 Bay Street, Suite 4000, Toronto, Ontario M5L 1A9 (CA).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report (Art. 21(3))
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments (Rule 48.2(h))

(54) Title: SYSTEM AND METHOD FOR MULTIPHASIC RELEASE OF GROWTH FACTORS

(57) Abstract: A system for multiphasic delivery of at least one growth factor at a treatment site comprises a delivery vehicle for releasing at least one growth factor in an initial release profile and a carrier for releasing at least one growth factor in a sustained release profile. The initial release profile releases at least one growth factor over a period of hours to days, wherein the growth factor is released in a large amount initially, with the remainder being released in progressively lower amounts. The sustained release profile releases at least one growth factor over a period of days to weeks, wherein the growth factor is released at a generally constant amount over such period. The system of the invention is particularly suited for applications on bioimplants. The invention also comprises methods and kits for multiphasic delivery of at least one growth factor.



WO 2012/139223 A1

1 **SYSTEM AND METHOD FOR MULTIPHASIC RELEASE OF GROWTH FACTORS**

2 **CROSS REFERENCE TO PRIOR APPLICATIONS**

3 **[0001]** This application claims priority under the Paris Convention from US Application
4 Number 61/474,049, filed on April 11, 2011, the entire contents of which are incorporated
5 herein by reference.

6 **FIELD OF THE INVENTION**

7 **[0002]** This invention relates to systems and methods for releasing biological
8 substances. In particular, the invention relates to the release of growth factors associated
9 with bioimplants. More particularly, the invention provides a system and method for
10 producing a multiphasic release profile of at least one growth factor to improve the
11 performance of the bioimplant.

12 **BACKGROUND OF THE INVENTION**

13 **[0003]** Growth factors (GFs) are peptides and proteins that stimulate the growth and/or
14 differentiation of cells via the interaction of the GFs with specific cell surface receptors.
15 Growth factors play an integral role in the repair and regeneration of tissues and exogenous
16 application of GFs can be used to stimulate the repair of various tissues and organs
17 including bone, cartilage, skin and mucosa and to enhance repair of tissues through the
18 stimulation of angiogenesis at the repair site.

19 **[0004]** The transforming growth factor beta (TGF β) superfamily of secreted growth and
20 differentiation factors in mammals has over 30 members. These dimeric proteins are
21 characterized by a conserved seven cystine knot-based structure. They regulate the
22 proliferation, differentiation and migration of many cell types, and have important roles in
23 morphogenesis, organogenesis, tissue maintenance and wound healing. The TGF β
24 superfamily of growth factors can be subdivided into several subfamilies including the
25 transforming growth factor beta subfamily, the bone morphogenetic protein (BMP) and
26 growth and differentiation factor (GDF) family (also called the BMP subfamily), and the
27 inhibin and activin subfamily.

28 **[0005]** The BMP subfamily of the TGF β superfamily comprises at least twenty proteins,
29 including BMP-2, BMP-3 (also known as osteogenin), BMP-3b (also known as growth and
30 differentiation factor 10, GDF-10), BMP-4, BMP-5, BMP-6, BMP-7 (also known as
31 osteogenic protein-1, OP-1), BMP-8 (also known as osteogenic protein-2, OP-2), BMP-9,
32 BMP-10, BMP-11 (also known as growth and differentiation factor 8, GDF-8, or myostatin),

1 BMP-12 (also known as growth and differentiation factor 7, GDF-7), BMP-13 (also known as
2 growth and differentiation factor 6, GDF-6), BMP-14 (also known as growth and
3 differentiation factor 5, GDF-5), and BMP-15 (for a review, see e.g., Azari et al. Expert Opin
4 Invest Drugs 2001;10:1677-1686).

5 **[0006]** BMPs have been shown to stimulate matrix synthesis in chondroblasts; stimulate
6 alkaline phosphatase activity and collagen synthesis in osteoblasts, induce the differentiation
7 of early mesenchymal progenitors into osteogenic cells (osteoiduction), regulate
8 chemotaxis of monocytes and mesenchymal cells, and regulate the differentiation of neural
9 cells (for a review, see e.g., Azari et al. Expert Opin Invest Drugs 2001;10:1677-1686 and
10 Hoffman et al. Appl. Microbiol. Biotech 2001;57:294-308).

11 **[0007]** One of the many functions of BMP proteins is to induce cartilage, bone, and
12 connective tissue formation in vertebrates. The most osteoinductive members of the BMP
13 subfamily are BMP-2, BMP-4, BMP-6, BMP-7, BMP-8 and BMP-9 (see, e.g., Hoffman et al.,
14 Appl. Microbiol Biotech 2001, 57-294-308; Yeh et al., J Cellular Biochem., 2005; 95-173-188;
15 and Boden, Orthopaedic Nursing 2005,24:49-52). This osteoinductive capacity of BMPs has
16 long been considered very promising for a variety of therapeutic and clinical applications,
17 including fracture repair; spine fusion; treatment of skeletal diseases, regeneration of skull,
18 mandibular, and bone defects; and in oral and dental applications such as dentogenesis and
19 cementogenesis during regeneration of periodontal wounds, extraction socket grafting,
20 alveolar ridge augmentation , and sinus augmentation. Currently, recombinant human BMP-
21 2 sold as INFUSE® by Medtronic FDA approved for use in spinal fusion surgery, for repair of
22 fracture non-unions and for use in oral surgery, while and recombinant human BMP-7 sold
23 as OP-1® by Stryker is approved as an alternative to autograft in recalcitrant long bone
24 nonunion and for revision posterolateral (intertransverse) lumbar spine fusions, where
25 autograft and bone marrow harvest are not feasible or are not expected to promote fusion

26 **[0008]** Other recombinant growth factors that have been used exogenously to enhance
27 bone repair include various TGFβs (see Clokie & Bell, J. Craniofacial Surg. 2003, 14:268-
28 77), members of the fibroblast growth factor superfamily (FGFs) (see Kawaguchi et al.,
29 (2007) J. Orthopaedic Res. 25(4): 480-487), members of the platelet derived growth factor
30 superfamily (PDGFs) (see Hollinger et al., 2008 JBJs 90(s1):48-54), and vascular
31 endothelial growth factor (VEGF) (Street et al., 2002 PNAS 99:9656-61)

32 **[0009]** For these growth factors to be effective they must be active and available at a
33 sufficient concentration at the time when critical densities of the appropriate responsive cells

1 are present in the repair site. The short half-life, thermal instability, sensitivity to proteases
2 and/or solubility of the GFs requires their administration in combination with a carrier to
3 achieve this requirement.

4 **[0010]** A number of carriers have been evaluated for the delivery of GFs. These include
5 fibrous collagen sponges, gelatin hydrogels, fibrin gels, heparin, reverse phase polymers
6 such as the poloxamers, scaffolds composed of poly-lactic acid (PLA), poly-glycolic acid
7 (PGA) or their co-polymers (PLGA), heparin-conjugated PLGA scaffolds, and inorganic
8 materials such as calcium phosphates. For example the bioimplant (GEM-21S®) which is
9 used for periodontal regeneration uses beta tricalcium phosphate (β -TCP) as the carrier for
10 rhPDGF-BB (see <http://www.ostehealth.com/GEM21S.aspx>).

11 **[0011]** However, these carriers are of limited effectiveness, due to loss of growth factor
12 activity when associated with the carrier, inefficient release of the GF at the implantation site,
13 and/or poor protection from proteolysis and degradation. For example the bioimplant
14 Infuse® uses a type I collagen sponge as the carrier for rhBMP-2. The rhBMP-2 is released
15 in a burst from the carrier and the half life of the BMP within the wound site is 1-3 days (Winn
16 et al., 1998, Adv. Drug Del. Rev. 31:303; Friess et. al., 1999, Intl. J. Pharm., 187:91). By the
17 time the mesenchymal stem cells which regenerate bone have migrated into the wound site
18 only fractions of a percent of the original amount of BMP loaded is present to stimulate these
19 cells to make bone. The current solution to ensure an effective level of BMP remaining at
20 these later times is to significantly increase the amount of BMP that is initially loaded. These
21 increased doses increase the risk of complications including bone formation beyond the
22 implant site, autoimmune responses and potentially cancer. Further this dramatically
23 increases the cost of the implant.

24 **[0012]** Therefore, a need exists in the art for materials and methods which release
25 growth factors with a profile which minimizes the amount of growth factor that needs to be
26 loaded to achieve the required therapeutic effect.

27 **[0013]** One strategy is to encapsulate the GF in a biodegradable polymeric matrix that
28 releases the GF with a sustained release profile over many days. For example BMPs have
29 been combined with poly-lactic acid (PLA) or poly-lactic co-glycolic acid (PLGA) to produce
30 sustained release profiles. However the incorporation of the BMP in the PLA or PLGA can
31 denature the BMP reducing its activity and it is difficult to manipulate the release profile to
32 optimize the effectiveness of the bioimplant. Further the degradation rate of these carriers is
33 typically such that large amounts of GF remain locked away long after healing is complete.

1 **[0014]** Another strategy is to chemically immobilize the GF directly onto the carrier retain
2 it at the implant site. However this may also result in partial or complete loss of activity of
3 the GF, and restricts the GF activity such that only those cells directly in contact with the
4 carrier are able to interact with the GF and respond (see Steinmuller-Nethl, D. et al.,
5 Biomaterials, 2006, 27: 4547-56) which is not desirable as the effect is limited to the
6 immediate interface with the carrier and not throughout the wound site.

7 **[0015]** In nature during wound healing multiple GF are present within the wound site and
8 surrounding tissue at varying concentrations at different times. For example, immediately
9 following bone fracture, platelets at the injury site will initially release large amounts of
10 PDGF, with a sharp decline in protein levels within the fracture site over the following days
11 (see Tyndall et al., Clinical Orthopaedics and Related Research, 2003, 408: 319–330).
12 Conversely BMP-2 is expressed at all stages of the fracture healing process (see Rasubala
13 et al. British Journal of Oral and Maxillofacial Surgery, 2003, 41: 173–178). The
14 concentration of these growth factors is estimated to be orders of magnitude lower than
15 those used during therapeutic application of exogenous GF due to matching of the
16 concentration to the cellular requirements and synergistic effects of the multiple growth
17 factors. Producing a system that allows the delivery of growth factors with multiphasic
18 release profiles and the release of multiple growth factors with different release profiles
19 would permit the use of bioimplants with GF release profiles that more closely mimic GF
20 release during the natural healing process than current bioimplants that release a single
21 growth factor in a burst or with sustained release.

22 **[0016]** This background information is provided for the purpose of making known
23 information believed by the applicant to be of possible relevance to the present invention.
24 No admission is necessarily intended, nor should be construed, that any of the preceding
25 information constitutes prior art against the present invention.

26 **SUMMARY OF THE INVENTION**

27 **[0017]** The present invention provides, in one aspect, a system, method and kit for the
28 multiphasic release of at least one growth factor at, for example a treatment site. For this
29 purpose, the system of the invention may be provided as a bioimplant or the like. In one
30 aspect, the method of the invention delivers at least one growth factor in an initial release
31 followed by the delivery of at least one growth factor in a "sustained release profile". The
32 invention utilizes a delivery system for the initial release and a carrier for the sustained
33 release.

1 **[0018]** In one aspect, the same growth factor is released in the initial and sustained
2 release profiles. In another aspect, different growth factors are released, with a first growth
3 factor released in an initial profile and a second growth factor released in a sustained
4 release profile. As will be known to persons skilled in the art, the release of two different
5 growth factors in such differing manners is believed to more closely mimic the natural growth
6 factor release system at a treatment site.

7 **[0019]** In accordance with one aspect of the invention, there is provided a carrier that
8 provides a sustained release of at least one growth factor, combined with a delivery vehicle
9 that provides an initial release of at least one growth factor. The combination of the carrier
10 and the delivery vehicle results in a multiphasic release profile of the growth factor(s).

11 **[0020]** In preferred embodiments the growth factor ("GF") is a member of the
12 transforming growth factor beta (TGF β) superfamily. In particularly preferred embodiments
13 the growth factor is a bone morphogenetic protein (BMP).

14 **[0021]** In one aspect of the present invention, the carrier ("CAR") is formed of calcium
15 phosphate particles dispersed within a polymer scaffold or matrix. In one aspect, the
16 scaffold or matrix is further coated with a hydroxyapatite layer.

17 **[0022]** In one embodiment the at least one growth factor is/are applied as a liquid to the
18 calcium particles and are then lyophilized onto the particles before combining with the
19 polymer matrix.

20 **[0023]** In another aspect of the present invention the carrier is formed by mixing one or
21 more calcium phosphate powders with a liquid solution containing at least one growth factor
22 to produce a calcium phosphate cement. In one aspect, the cement is then ground into
23 particles.

24 **[0024]** In preferred embodiments the delivery vehicle is a reverse phase polymer. In
25 particularly preferred embodiments the reverse phase polymer is a poloxamer, more
26 particularly poloxamer 407 (also called Pluronic™ F127).

27 **[0025]** As indicated above, in one aspect, the carrier and the delivery vehicle are
28 adapted to release the same growth factor while in another aspect, the carrier and delivery
29 vehicle are adapted to release different growth factors. In yet another aspect of the
30 invention, the carrier and delivery vehicle are each adapted to release combinations of two
31 or more growth factors, with the combination released by each being the same or different.

1 **[0026]** Thus, in one aspect, the invention provides a system for multiphasic release of
2 growth factors at a treatment site, the system comprising:

- 3 - a delivery vehicle comprising at least one first growth factor; and
- 4 - a carrier comprising at least one second growth factor;
- 5 - wherein:
 - 6 - the delivery vehicle is adapted to release the at least one first growth factor in
 - 7 an initial release profile over a first time period;
 - 8 - the carrier is adapted to release the at least one second growth factor in a
 - 9 sustained release profile over a second time period.

10 **[0027]** In another aspect, the invention provides a method of multiphasic release of
11 growth factors, the method comprising:

- 12 - delivering at least one first growth factor with an initial release profile;
- 13 - delivering at least one second growth factor in a sustained release profile.

14 **[0028]** In a further aspect, the invention provides a kit for multiphasic delivery of growth
15 factors, the kit comprising:

- 16 - a delivery vehicle component;
- 17 - at least one first growth factor associated with the delivery vehicle;
- 18 - a carrier component; and
- 19 - at least one second growth factor associated with the carrier.

20 **BRIEF DESCRIPTION OF THE DRAWINGS**

21 **[0029]** The invention will now be described with reference to the appended figures,
22 which are briefly described below.

23 **[0030]** Figure 1 illustrates a sustained release profile exhibited by the carrier of the
24 invention.

25 **[0031]** Figure 2 illustrates the initial release profile exhibited by the delivery vehicle of
26 the invention.

27 **[0032]** Figure 3 illustrates differing release profiles based on an amount of growth factor
28 in the delivery vehicle and carrier. A multiphasic release profile is observed when growth
29 factors are incorporated into both the delivery vehicle and carrier (50-50).

30 **[0033]** Figure 4 illustrates the *in vivo* activity of the bioimplants where a growth factor is
31 released as shown in Figure 3 according to the method of the invention.

1 **[0034]** Figure 5 illustrates the formation of new bone (Bone) onto calcium phosphate
2 particles (CaP) when a bioimplant produced according to the method of the invention was
3 implanted into a mouse.

4 **[0035]** Figure 6 illustrates the histological appearance of the new bone (Bone) formed
5 on a carrier (Carrier) when bioimplant produced according to the method of the invention
6 was implanted into a mouse

7 **[0036]** Figure 7 illustrates a short sustained growth factor release profile produced by a
8 carrier produced according to the method of the invention

9 **[0037]** Figure 8 illustrates how a sustained release profile can be altered by changing
10 the properties of the carrier produced according to the method of the invention

11 **DETAILED DESCRIPTION OF THE INVENTION**

12 **[0038]** Growth factors (GF) play an integral role in the repair and regeneration of tissues
13 and exogenous GFs can be used to stimulate the repair of various tissues and organs. For
14 exogenous growth factors to be effective in stimulating repair they must be retained at the
15 site requiring repair, and be protected from inactivation, sequestration or degradation. To
16 achieve this carriers are used. However the release of growth factors from these carriers is
17 not ideal and cannot be easily modified. The current invention is based on the discovery that
18 the multiphasic release of growth factors from a bioimplant increases the efficacy of the
19 implant.

20 **[0039]** The present inventors have developed methods and materials for enhancing the
21 efficacy of, for example, bioimplants by improving the release kinetics or release profile of
22 growth factors at sites of implantation, while maintaining the activity of the growth factors. In
23 one aspect, the present invention provides a growth factor delivery system and method
24 comprising a carrier containing at least one growth factor, combined with a delivery vehicle
25 also containing at least one growth factor. The at least one growth factor released by the
26 carrier and delivery vehicle may be the same or different.

27 **[0040]** The system and method of the invention can be used for a variety of therapeutic
28 and clinical applications, including: fracture repair; bone grafts; spine fusion; and
29 regeneration of skull, mandibular, and bone defects. For such applications, the system of
30 the invention is preferably provided on, or in the form of a bioimplant.

1 **[0041] Definitions**

2 **[0042]** Unless defined otherwise below, all technical and scientific terms used herein
3 have the same meaning as commonly understood by one of ordinary skill in the art to which
4 this invention belongs.

5 **[0043]** As used herein the term “bioimplant” refers to a material which is suitable for
6 implantation and contains an exogenous growth or biologically active factor. As discussed
7 further herein, the system of the present invention is preferably used by applying same to a
8 bioimplant. The bioimplant is then provided within a body of a subject wherein the system
9 releases at least one growth factor in a multiphasic release profile.

10 **[0044]** As used herein the term “growth factor” refers to peptides and proteins that
11 stimulate the growth and/or differentiation of cells via the interaction of the GFs with specific
12 cell surface receptors. Examples of growth factors include the bone morphogenetic proteins
13 (BMPs), transforming growth factor beta (TGF β), the insulin-like growth factors (IGF), the
14 fibroblast growth factors (FGFs), platelet derived growth factor (PDGF) and vascular
15 endothelial growth factor. In preferred embodiments the growth factors are BMPs.

16 **[0045]** By “recombinant” is meant a protein produced by a transiently transfected, stably
17 transfected, or transgenic host cell or animal as directed by an expression construct
18 containing the cDNA for that protein. The term “recombinant” also encompasses
19 pharmaceutically acceptable salts of such a polypeptide

20 **[0046]** As used herein, the term “polypeptide” or “protein” refers to a polymer of amino
21 acid monomers that are alpha amino acids joined together through amide bonds.
22 Polypeptides are therefore at least two amino acid residues in length, and are usually longer.
23 Generally, the term “peptide” refers to a polypeptide that is only a few amino acid residues in
24 length. A polypeptide, in contrast with a peptide, may comprise any number of amino acid
25 residues. Hence, the term polypeptide included peptides as well as longer sequences of
26 amino acids.

27 **[0047]** As used herein, the terms “bone morphogenetic protein” or “bone morphogenic
28 protein” or “BMP” are used interchangeably and refer to any member of the bone
29 morphogenetic protein (BMP) subfamily of the transforming growth factor beta (TGF β)
30 superfamily of growth and differentiation factors, including BMP-2, BMP-3 (also known as
31 osteogenin), BMP-3b (also known as growth and differentiation factor 10, GDF-10), BMP-4,
32 BMP-5, BMP-6, BMP-7 (also known as osteogenic protein-1, OP-1), BMP-8 (also known as

osteogenic protein-2, OP-2), BMP-9, BMP-10, BMP-11 (also known as growth and differentiation factor 8, GDF-8, or myostatin), BMP-12 (also known as growth and differentiation factor 7, GDF-7), BMP-13 (also known as growth and differentiation factor 6, GDF-6), BMP-14 (also known as growth and differentiation factor 5, GDF-5), and BMP-15.

[0048] The terms “bone morphogenetic protein” and “BMP” also encompass allelic variants of BMPs, function conservative variants of BMPs, and mutant BMPs that retain BMP activity. The BMP activity of such variants and mutants may be confirmed by any of the methods well known in the art (see the section Assays to measure BMP activity, below) or as described in Example 1

[0049] In preferred embodiments, the BMP is BMP-2, BMP-4, BMP-5, BMP-6, BMP-7, BMP-8 or BMP-9. In particularly preferred embodiments the BMP is BMP-2, BMP-4 or BMP-7.

[0050] In preferred embodiments the BMP is a mammalian BMP (e.g., mammalian BMP-2 or mammalian BMP-7). In particularly preferred embodiments, the BMP is a human BMP (hBMP) (e.g. hBMP-2 or hBMP-7).

[0051] As used herein the term “scaffold” refers to a material whose purpose is to provide a structure which supports cell adhesion, migration and ingrowth into a tissue repair site.

[0052] As used herein the term “carrier” refers to a material comprising single or multiple components and is adapted to release at least one growth factor at a treatment site in a “sustained release” profile over a period of time. In one aspect, the period of time taken by the carrier to release the at least one growth factor is between several days and several weeks. Preferably, the carrier is adapted to release the at least one growth factor over a period of weeks.

[0053] In preferred embodiments the carrier also acts as a scaffold or matrix. As discussed above, in one aspect of the invention, the carrier is formed of calcium phosphate particles dispersed within a macroporous polymer scaffold or matrix. In one aspect, the scaffold or matrix is further coated with a hydroxyapatite layer. In one embodiment the at least one growth factor is applied as a liquid to the calcium particles and are then lyophilized onto the particles before combining with the polymer matrix.

1 **[0054]** As used herein the term “delivery vehicle” refers to a material which comprises or
2 contains at least one growth factor and is adapted to release the at least one growth factor at
3 a treatment site in an initial release profile over a time period. In one aspect, the material
4 forming the delivery vehicle is in the form of a gel. In one aspect, the period of time taken by
5 the delivery vehicle to release the at least one growth factor is between several hours and
6 several days. In a preferred embodiment of the invention, the delivery vehicle releases the
7 majority of the at least one growth factor in an “initial release” or “initial release profile” that
8 lasts a period of hours. Preferably, the delivery vehicle is adapted to release at least 80% of
9 the growth factor(s) contained therein (or associated therewith) within a period of 72 hours.

10 **[0055]** In preferred embodiments the delivery vehicle is a reverse phase polymer. As
11 used herein the term “reverse phase” refers to the property whereby the polymer undergoes
12 a reversible temperature dependent transition from a liquid to a gel. In one aspect the
13 transition temperature is between 15°C and 37°C. Preferably the transition temperature is
14 between 15°C and 25°C. As would be known to persons skilled in the art, “normal phase”
15 materials increase their viscosity with a decline in temperature. In contrast, reverse phase
16 materials show a decline in viscosity as the temperature drops below their transition
17 temperature.

18 **[0056]** In particularly preferred embodiments the reverse phase polymer is a poloxamer,
19 more particularly Pluronic™ F127 (also known as poloxamer 407).

20 **[0057]** As used herein the term “sustained release” or “sustained release profile” refers
21 to the release of at least one growth factor, by the carrier, over a period of several days or
22 weeks with the amount released over an initial period being similar to or less than the
23 amount released over the same period after several days or weeks of implantation.
24 Preferably, a sustained release profile lasts at least one week. As will be understood by
25 persons skilled in the art, typically, the amount of growth factor released in a sustained
26 release profile over the first three days will be less than the amount released over the
27 following seven days.

28 **[0058]** As used herein the term “initial release” or “initial release profile” refers to the
29 initial release, by the delivery vehicle, of a large amount of at least one growth factor
30 followed by progressively smaller amounts released over a period of hours or days. In one
31 aspect, an initial release profile results in the delivery of at least 80% of the loaded growth
32 factor(s) within a period of roughly 72 hours. An initial release profile is illustrated in Figure
33 2.

1 **[0059]** As used herein the term “multiphasic release” refers to an initial release of the at
2 least one growth factor over an initial period of time, followed by “sustained” release of the at
3 least one growth factor over a second period of time. Preferably, the initial period of time is
4 roughly several hours and the second period of time is roughly several days to weeks. Such
5 a release profile may also be referred to as “biphasic release” since it occurs in two stages.
6 In preferred embodiments, the initial release is provided by the delivery system of the
7 invention and the “sustained” release is provided by the carrier of the invention.

8 **[0060]** In one aspect of the invention, the delivery vehicle component comprises at least
9 10% and not more than 50% of the total amount of growth factor(s) delivered by the system
10 of the invention and the carrier component comprises at least 50% of the total amount of
11 growth factor(s) delivered by the system.

12 **[0061]** **Assays to measure BMP activity**

13 **[0062]** Assays to characterize *in vitro* and *in vivo* function of recombinant BMPs are well
14 known in the art, (see, e.g., U.S. Patent No. 4,761,471; U.S. Patent No. 4,789,732; U.S.
15 Patent No. 4,795,804; U.S. Patent No. 4,877,864; U.S. Patent No. 5,013,649; U.S. Patent
16 No. 5,166,058; U.S. Patent No. 5,618,924; U.S. Patent No. 5,631,142; U.S. Patent No.
17 6,150,328; U.S. Patent No. 6,593,109; Clokie and Urist, *Plast. Reconstr. Surg.* 2000;
18 105:628-637; Kirsch et al., *EMBO J* 2000; 19:3314-3324; Vallejo et al., *J. Biotech.* 2002;
19 94:185-194; Peel et al., *J. Craniofacial. Surg.* 2003; 14:284-291; and Hu et al., *Growth*
20 *Factors*, 2004; 22:29-33).

21 **[0063]** Such assays include: *in vivo* assays to quantify osteoinductive activity of a BMP
22 following implantation (e.g., into hindquarter muscle or thoracic area) into a rodent (e.g. a rat
23 or a mouse) (see, for example, U.S. Patent No. 4,761,471; U.S. Patent No. 4,789,732; U.S.
24 Patent No. 4,795,804; U.S. Patent No. 4,877,864; U.S. Patent No. 5,013,649; U.S. Patent
25 No. 5,166,058; U.S. Patent No. 5,618,924; U.S. Patent No. 5,631,142; U.S. Patent No.
26 6,150,328; U.S. Patent No. 6,503,109; Kawai and Urist., *Clin. Orthop. Relat. Res.*, 1988;
27 222:262-267; Clokie and Urist, *Plast. Reconstr. Surg.*, 2000; 105:628-637; and Hu et al.,
28 *Growth Factors*, 2004; 22:29-33); *in vivo* assays to quantify activity of a BMP to regenerate
29 skull trephine defects in mammals (e.g., rats, dogs, or monkeys) (see, for example, U.S.
30 Patent No. 4,761,471 and U.S. Patent No. 4,789,732); *in vitro* assays to quantify activity of a
31 BMP to induce proliferation of *in vitro* cultured cartilage cells (see, for example, U.S. Patent
32 No. 4,795,804); *in vitro* assays to quantify activity of a BMP to induce alkaline phosphatase
33 activity in *in vitro* cultured muscle cells (e.g., C2C12 cells, ATCC Number CRL-1772) or

bone marrow stromal cells (e.g., murine W-20 cells, ATCC Number CRL-2623) (see, for example, U.S. Patent No. 6,593,109; Ruppert et al., Eur J Biochem 1996;237:295-302; Kirsch et al., EMBO J, 2000;19:3314-3324; Vallejo et al., J Biotech, 2002;94:185-194; Peel et al., J Craniofacial Surg., 2003;14:284-291; and Hu et al., Growth Factors, 2004;22:29-33); *in vitro* assays to quantify activity of a BMP to induce FGF-receptor 2 (FGFR3) expression in cultured mesenchymal progenitor cell lines (e.g., murine C3H10T1-2 cells) (see, for example, Vallejo et al. J Biotech 2002;94:185-194); *in vitro* assays to quantify activity of a BMP to induce proteoglycan synthesis in chicken limb bud cells (see, for example, Ruppert et al., Eur J Biochem 1996;237:295-302); and *in vitro* assays to quantify activity of a BMP to induce osteocalcin treatment in bone marrow stromal cells (e.g., murine W-20 cells; ATCC Number CRL-2623) (see, for example, U.S. Patent No. 6,593,109).

[0064] Assays to measure BMP binding and release

[0065] Various assays can be used to measure binding and release of recombinant BMP from a carrier. For example, the amount of recombinant BMP protein can be quantified by any of the techniques well known in the art, including dot blots, immunoassay (e.g., enzyme linked immunosorbent assays, ELISA), measurement of the increase in radioactivity present in the release buffer when the bioimplant incorporates radiolabeled BMP and chromatography (e.g., high pressure liquid chromatography, HPLC and ion-exchange chromatography).

[0066] Such methods are well known in the art (See for example, Harlow and Lane, Using Antibodies: A Laboratory Manual, Cold Spring Harbor Laboratory Press. 1999; Gosling, ed., Immunoassays: A Practical Approach, Oxford University Press. 2000; Oliver, ed., HPLC of Macromolecules: A Practical Approach., Oxford University Press, 1998; Millner, ed., High Resolution Chromatography: A Practical Approach. Oxford University Press, 1999; Hockfield et al., Selected Methods for Antibody and Nucleic Acid Probes. Cold Spring Harbor Laboratory Press. 1993; Gore, ed., Spectrophotometry and Spectrofluorimetry: A Practical Approach. Oxford University Press, 2000).

[0067] For example, protocols for radioimmunoassay analysis of BMP proteins have been described (see, for example, U.S. Patent No. 4,857,456). For example, protocols for immunoblot analysis of BMP proteins have been described (see, for example, Wang et al. Proc Natl Acad Sci USA 1990; 87:2220-2224). For example, ELISA kits for the quantitation of protein levels of human, rat, or mouse BMP-2 are commercially available, for example, from R&D Systems (catalog #DBP200, PDBP200, or SBP200). For example, ELISA kits for

1 the quantitation of protein levels of human BMP-7 are commercially available, for example,
2 from R&D Systems (catalog #DY354 or DY354E).

3 **[0068] Kits**

4 **[0069]** In one aspect, the invention provides a kit for containing the system described
5 herein. In one embodiment, the kit comprises the necessary components for making the
6 delivery vehicle and the carrier as well as the needed growth factors. That is, the kit of the
7 invention would comprise the necessary components for making the delivery vehicle and the
8 carrier as well as at least one growth factor associated with the delivery vehicle and at least
9 one growth factor associated with the carrier.

10 **[0070]** Preferably, the delivery vehicle and the associated growth factor(s) are
11 maintained in separate containers, to be combined at the time of use. This would be
12 particularly preferable in cases where the delivery vehicle may comprise a liquid or a gel. In
13 such case, the associated growth factor(s) may be kept in a separate container as a
14 lyophilized powder. At the time of use, the growth factor(s), in powder form, may be
15 combined with the liquid or gel delivery vehicle.

16 **[0071]** The kit preferably comprises a further container comprising the carrier onto which
17 may be loaded or coated the associated growth factor(s). In one embodiment, the carrier
18 material may also be maintained separate from the associated growth factor(s).

19 **[0072]** In a preferred embodiment, the kit of the invention would comprise at least three
20 containers for each of the following: 1) the delivery vehicle component; 2) the at least one
21 first growth factor (i.e. the growth factor(s) associated with the delivery vehicle); and, 3) the
22 carrier and the least one second growth factor (i.e. the growth factor(s) associated with the
23 carrier). In use, the at least one second growth factor, in powder form, is combined with the
24 liquid or gel form delivery vehicle and the mixture is then applied to the carrier onto which the
25 at least one second growth factor was pre-loaded.

26 **[0073]** In one aspect, the kit of the invention may comprise any necessary reagents
27 and/or instructions and/or vessels as may be needed.

28 **[0074] EXAMPLES**

29 **[0075]** The present invention will now be described by means of the following examples.
30 These examples illustrate the novel findings by the inventors that a multiphasic release
31 profile of a growth factor, such as rhBMP-2 produced by loading part of the BMP within a

1 carrier that releases BMP with a sustained release and part of the BMP within a delivery
2 vehicle that releases BMP with an initial release is more effective than carriers that only
3 produce a burst release or a sustained release.

4 **[0076]** As will be obvious to one skilled in the art it is possible to place one growth factor
5 within the carrier and a different growth factor within the delivery vehicle, resulting in different
6 release profiles of each growth factor.

7 **[0077]** It will be understood that the examples provided herein are intended solely to
8 illustrate the present invention and not to limit the scope of the invention in any way.
9 Likewise, the invention is not limited to any particular preferred embodiments described
10 herein. Indeed, many modifications and variations of the invention may be apparent to those
11 skilled in the art upon reading the present specification. The invention is therefore to be
12 limited only by the terms of the appended claims, along with the full scope of equivalents to
13 which the claims are entitled.

14 **[0078]** **EXAMPLE 1: Manufacture of a sustained release composite carrier**
15 **containing BMP by encapsulation in PLGA.**

16 **[0079]** This example demonstrates how to form a carrier containing rhBMP-2 and which
17 releases the growth factor in a sustained release profile.

18 **[0080]** **Materials and Methods**

19 **[0081]** PLGA 75/25 with inherent viscosity of 1.33 dL/g (MW = 205,000-210,000) was
20 purchased from Birmingham Polymers Inc. (Birmingham, AL). Tetracalcium phosphate
21 (TTCP) was obtained from Taihei Chemical Industrial Co. (Osaka, Japan) and dicalcium
22 phosphate anhydrous (DCPA) and dimethyl sulfoxide (DMSO) were obtained from Sigma
23 Chemical Co. (MO, USA). Sugar particles were purchased from Tate & Lyle North America
24 Inc. (Toronto, Canada).

25 **[0082]** Resorbable calcium phosphate particles were prepared by mixing equimolar
26 TTCP and DCPA with deionized distilled water (ddH₂O) at 100% relative humidity for 24 h.
27 The reactant was ground and sieved through 45 µm sieve.

28 **[0083]** Recombinant human BMP-2 (rhBMP-2, Induce Biologics Inc) in was prepared in
29 formulation buffer (1.5mg/ml, pH 4.5; 5 mm glutamic acid, 2.5% glycine, 0.5% sucrose and
30 0.01% Tween™ 80 with ddH₂O). The protein solution was added to vials containing CaP
31 powder and agitated for at least 15 minutes. The powder was then frozen and lyophilized.

1 [0084] Particles with (CaP-BMP) or without (CaP) BMP were then used to make CaP
2 particulate-PLGA scaffold blocks by phase-inversion/particle leaching as follows: PLGA was
3 dissolved in DMSO at a concentration of 11.5% (w/v). To this solution, the CaP and CaP-
4 BMP particles were thoroughly mixed according to a CaP/PLGA ratio of 2:1 (w/w). Sugar
5 crystals with size ranges of 0.85–1.18mm were dispersed in the CaP/PLGA and the mixture
6 was solidified at -18°C in a mold. The PLGA was precipitated and the sugar crystals
7 leached out by soaking in three changes of ddH₂O.

8 [0085] A layer of hydroxyapatite was deposited onto and throughout the macroporous
9 composite scaffolds as follows: dry PLGA/CaP cylinders, measuring 2mm in diameter and
10 2mm in length, were pre-wetted in 70% ethanol and immersed in 60 ml of 3xSBF for a period
11 of 9 days at 37°C. SBF was prepared as follows: to 1.8L of ddH₂O under vigorous stirring
12 the following salts were added sequentially 29.711g NaCl, 2.206g CaCl₂·2H₂O, 10ml 1M
13 HCl, 0.852 Na₂HPO₄. The final volume was brought to 2L. The SBF solution was changed
14 daily. Following coating, the 3PCC samples were rinsed in ddH₂O and air dried.

15 [0086] This resulted in the formation of a macroporous composite carrier (3PS) that is
16 able to release rhBMP-2 with a sustained release profile over at least seven days. These
17 results are illustrated in Figure 1.

18 [0087] **EXAMPLE 2: Manufacture of a sustained release carrier containing BMP by**
19 **encapsulation in a calcium phosphate cement**

20 [0088] The present example demonstrates how to form a calcium phosphate cement
21 (CPC) carrier containing rhBMP-2 that has a sustained release profile.

22 [0089] **Materials and Methods**

23 [0090] Tetracalcium phosphate (TTCP) was obtained from Taihei Chemical Industrial
24 Co. (Osaka, Japan) and dicalcium phosphate anhydrous (DCPA) was obtained from Sigma
25 Chemical Co. Macroporous biphasic calcium phosphate granules (Eclipse) were purchased
26 from Citagenix (Laval Qc, Canada). Recombinant human BMP-2 (rhBMP-2, Induce
27 Biologics Inc) was prepared in formulation buffer (1.5mg/ml, pH 4.5; 5 mM glutamic acid,
28 2.5% glycine, 0.5% sucrose and 0.01% Tween™ 80 with ddH₂O).

29 [0091] Resorbable calcium phosphate cement particles were prepared by mixing
30 equimolar TTCP and DCPA with rhBMP-2 solution. The reactant was ground and sieved
31 through a 300 and 100 µm sieve and particles between 100 and 300µm, retained.

1 [0092] This resulted in the formation of calcium phosphate cement carrier particles into
2 which the rhBMP-2 was incorporated. Upon implantation into an animal BMP is released in
3 a sustained manner over a period of at least several weeks.

4 [0093] To produce a CPC based sustained release carrier that also acted as a
5 macroporous scaffold CPC particles (0.1 to 0.3mm) were mixed macroporous calcium
6 phosphate granules (1-2mm) in a 1:1 ratio (w/w).

7 [0094] **EXAMPLE 3: Manufacture of a sustained release carrier containing BMP by**
8 **use of a coating that binds BMP.**

9 [0095] The present example demonstrates how to form a carrier that has a sustained
10 release profile by applying a BMP binding coating. One such method is to coat a scaffold
11 with an antibody or BMP binding protein as described in our co-pending application number
12 US Application No. 13/002,444 (the entire content of which is incorporated herein by
13 reference).

14 [0096] **Materials and Methods**

15 [0097] Purified polyclonal rabbit anti-human BMP-2 antibodies were purchased from Cell
16 Sciences, (Canton MA., Cat #PA0025). Macroporous biphasic calcium phosphate (BCP)
17 granules (Eclipse) were purchased from Citagenix (Laval, Qc, Canada.)

18 [0098] Sterile BCP granules were weighed out in a biosafety cabinet and placed in
19 sterile TPP tubes (Mandel Scientific, Guelph ON, Canada). The antibody solution was
20 diluted in phosphate buffered saline to final concentration of 150, 300 and 600ng of antibody
21 in 1ml PBS, filter sterilized and applied to the scaffold at a 1:1 v/v ratio. The samples were
22 agitated for at least 15 minutes at room temperature, before being frozen and lyophilized.
23 BMP solution was then applied to the granules, allowed to soak for 15 minutes at room
24 temperature and then frozen and re-lyophilized.

25 [0099] This resulted in the formation of a BCP granules coated with antibody that bound
26 and slowly released the rhBMP-2 in a sustained fashion.

27 [00100] The amount of rhBMP-2 that can be bound can be increased by increasing the
28 amount of antibody used. The rate of release can be increased by using antibodies with
29 lower affinity or avidity.

1 **[00101] EXAMPLE 4: Production of a BMP containing delivery vehicle using F127**

2 **[00102]** The present example demonstrates how to prepare a delivery vehicle containing
3 rhBMP-2 using F127.

4 **[00103] Materials and Methods**

5 **[00104]** Poloxamer was prepared as follows: 100ml of distilled water was chilled to 4°C
6 and various amounts of poloxamer 407 were added slowly with stirring over a period of
7 several hours, until all the solid prill was dissolved making a final solution ranging between
8 12 and 33%. The poloxamer solution was then sterilized in an autoclave (121°C, 20
9 minutes, 30psi). Following sterilization, the poloxamer solution was kept at 4°C until use.

10 **[00105]** Lyophilized recombinant human BMP-2 powder (rhBMP-2, Induce Biologics Inc)
11 was added to the poloxamer solution and was slowly mixed.

12 **[00106]** Alternatively rhBMP-2 was added from solution (1mg/ml, pH 4.5; 5 mm glutamic
13 acid, 2.5% glycine, 0.5% sucrose and 0.01% Tween 80) at a 1/10 or 1/20 ratio (v/v).

14 **[00107]** This resulted in the formation of a delivery vehicle that released more than 80%
15 of the rhBMP -2 over the first two days (as illustrated in Figure 2).

16 **[00108] EXAMPLE 5: Production of a bioimplant with a multiphasic release profile**

17 **[00109]** The present example demonstrates how to form a 3PS-F127 bioimplant
18 containing rhBMP-2 that releases the rhBMP-2 with a multiphasic release profile.

19 **[00110] Materials and Methods**

20 **[00111]** The 3PS carrier (as described in Example 1) containing 0, 4.55 or 9.1µg of
21 rhBMP-2 per 5mg of carrier was prepared and stored in Eppendorf tubes. A delivery vehicle
22 containing 0, 4.55 or 9.1µg of rhBMP-2 in 45.5µl F127 (prepared as described in Example 4)
23 was stored in Eppendorf tubes at 4°C. Immediately prior to use, the F127 was pipetted onto
24 the 3PS carrier and the carrier was mixed into the delivery vehicle.

25 **[00112]** This 3PS-F127 bioimplant was then used to measure BMP release *in vitro* and
26 bone formation activity *in vivo* as described below.

27 **[00113]** The ratios of carrier to delivery vehicle can be varied to produce gel (1:1 ratio v:v)
28 or putties (2:1 ratio v:v). Further the ratio of BMP to carrier or the particle size of the carrier

1 can be varied to alter the sustained release profile. Finally the amount of rhBMP-2 in the
2 carrier and the delivery vehicle can be varied to alter the amount of rhBMP-2 released
3 initially over the first few hours compared to amount released over the following weeks.

4 **[00114] EXAMPLE 6: An *in vitro* assay for release of BMPs from bioimplants.**

5 **[00115]** The present example describes how to measure the release of rhBMP-2 from the
6 various bioimplants described in Examples 1 to 5.

7 **[00116] Materials & Methods**

8 **[00117]** Bioimplants containing known amounts of rhBMP-2 prepared as in Examples 1 to
9 5 were transferred to Eppendorf tubes. The total amount of rhBMP-2 used was 9.1µg of
10 rhBMP-2 per 5mg of carrier and 45.5µl of F127, or 20µg of rhBMP-2 to 10mg of carrier to
11 100µl of F127.

12 **[00118]** Samples were then incubated under agitation with a 1 ml solution of release
13 buffer comprising phosphate buffered saline (PBS) + 1% BSA at 37°C. The buffer was
14 removed and replaced with fresh release buffer after various times (e.g. 1, 2, 5, 7 and 10
15 days) and the collected solutions were stored with 1.5 ml vials at -20°C for further analysis.

16 **[00119]** The amount of BMP-2 released into the buffer was measured using a commercial
17 ELISA (Quantikine™ hBMP-2 ELISA, RnD Systems). The ELISA was carried out according
18 to the manufacturer's instructions.

19 **[00120] Results**

20 **[00121]** No BMP was detectable in release buffer collected from any of the bioimplants
21 which had not been loaded with BMP. The carrier samples which had been loaded with
22 rhBMP-2 demonstrated a sustained release of rhBMP-2 over the period of the study, while
23 samples in the delivery vehicle alone were released in an "initial release profile".

24 **[00122]** When the carrier and delivery vehicle were combined, various release profiles
25 were obtained depending on which component the BMP was loaded into. When 100% of
26 the rhBMP-2 (9.1µg) was loaded within the 3PS (5mg) carrier which was then mixed with
27 33% F127 (45.5µl), the BMP release profile matched the sustained pattern, where the
28 amount of BMP released over the first 2 days was 5ng, between days 3 and 5 it was 8ng
29 and between days 5 and 7 it was 10ng (Figure 3; 100-0).

1 [00123] When 100% of the rhBMP-2 (9.1µg) was loaded within 33% F127 (45.5µl) and
2 then was then mixed with the 3PS carrier (5mg) which had no BMP within it, the BMP was
3 released where the amount of BMP released over the first 1 day was 2363ng, over the
4 second day was 381ng and then 12ng on the third day (Figure 3; 0-100).

5 [00124] When the BMP was distributed between the carrier and the delivery vehicle the
6 bioimplant demonstrated a biphasic release profile, with an intermediate initial release
7 followed by sustained release of BMP (Figure 3; 50-50).

8 [00125] **EXAMPLE 7: An *in vitro* assay to test the activity of released BMPs.**

9 [00126] The present example describes how to determine whether the rhBMP-2 released
10 from the bioimplants retains its activity. To demonstrate that the released rhBMP is
11 biologically active, responsive cells can be cultured in with the releasate and their response
12 to the growth factor measured. Such assays are known in the art (see Peel et al., J.
13 Craniofac. Surg. 2003, 14:284-291).

14 [00127] Materials & Methods

15 [00128] Materials with or without rhBMP-2 as described in Examples 1 to 5 were
16 prepared. Releasates were prepared as described in Example 3 except the buffer was
17 alpha minimal essential medium with 15% fetal bovine serum and antibiotics
18 (aMEM+15%FBS+AB)

19 [00129] C2C12 cells were seeded into 24 well tissue culture plates at 0.5×10^5 cells/ml,
20 1ml alpha MEM+15%FBS per well. After various periods between 24 and 72 hours the
21 media was removed and the various releasates were applied. Negative controls included
22 C2C12 cells cultured with fresh aMEM+15%FBS+AB. Positive controls included C2C12
23 cells incubated with aMEM+15%FBS+AB containing 25, 50 and 100ng/ml rhBMP-2. After
24 48 hours the cells were lysed in 1 ml cell lysis buffer (Cellytic Sigma Aldrich) and the alkaline
25 phosphatase (ALP) activity of the cell lysates measured using the para-nitrophenol
26 phosphate assay (Sigma Aldrich). The cell protein content of the lysates was measured
27 using Coomassie Plus Reagent (Fisher) and was used to normalize ALP activity to the
28 number of cells in each well.

29 [00130] Generally, to determine whether there has been any loss in activity of the BMP
30 when associated with the carrier or delivery vehicle, a standard activity curve of ALP/PTN
31 results for rhBMP-2 standards which have not been associated with the carrier or delivery

vehicle is determined. The concentration of active rhBMP-2 in the releasates can be determined from this standard curve and this is expressed as a percentage of the total the amount of rhBMP-2 present in the releasates as determined by ELISA.

[00131] EXAMPLE 8: Evaluation of osteoinductive activity of multiphasic BMP implants

[00132] The present example describes how to determine the osteoinductive activity of BMP containing bioimplants *in vivo*. To evaluate the ability of bioimplants to induce bone formation the mouse muscle pouch assay was used. In this model the bioimplant is placed in a muscle pouch made in the hind limbs of the mouse and the size of the induced bone formed is proportional to the amount of BMP tested. Such assays are known in the art (see for example Barr et al., Oral Surg. Oral Med. Oral Pathol. Oral Radiol. Endod., 2010; 109:531-40.)

[00133] Materials and Methods

[00134] Bioimplants were prepared as described in Examples 1 and 5. Under anesthesia bilateral pouches were made in the thigh muscles of the hind limbs of male CD-1 mice aged 37-42 days, by blunt dissection. The bioimplants were then placed into sterile gelatin capsules which had been placed into the muscle pouch. The muscle was pulled together and the skin closed with Mitchel clips.

[00135] The animals were euthanized on post-op day 28. The hind limbs were harvested and fixed with 10% buffered formalin. Following fixation, the specimens were imaged using a microCT scanner (General Electric Healthcare eXplore™ Locus SP). Samples were scanned and reconstructed using the manufactures software at a resolution of 59µm. Following image reconstruction, a region of interest (ROI) was determined. This area encompassed all areas containing the bioimplant induced bone. These can be easily distinguished from the skeletal bones based on location and density.

[00136] In order to analyze the quantity and quality of bone within the ROI, the voxels of the mCT images were segmented into bone and non-bone phases. Segmentation was achieved by determining a threshold value for the voxel grayscale at which the voxel was counted as bone. The total volume (TV), bone volume (BV), mineral density of the total volume (TV-MD), mineral density of the bone volume (BV-MD), mineral content of the total volume (TV-MC), mineral content of the bone volume (BV-MC) and bone volume fraction (BVF) of the ROI were determined for each sample. Values were adjusted for the presence

of calcium due to the carrier by using an upper threshold value that selected only carrier and subtracting it from the values obtained using a lower threshold which included carrier plus new bone (see Humber et al., Oral Surgery, Oral Medicine, Oral Pathology, Oral Radiology, and Endodontology. 2010. 109:372-384).

[00137] Following completion of the microCT analysis, the specimens were either embedded in spurs resin or decalcified in formic acid and embedded in wax. Resin embedded samples were evaluated by backscatter SEM while wax embedded samples were cut and stained with hematoxylin and eosin (H&E) and examined by light microscopy to evaluate the tissue types present at the implantation site.

[00138] Results

[00139] A carrier and a delivery vehicle were combined as described in Example 5.

[00140] MicroCT analysis showed that bioimplants with all of the BMP within the 3PS carrier, which had a sustained BMP release profile, produced the smallest ossicles of bone (Figure 4; 100-0), bioimplants with all of the BMP within the F127 delivery vehicle, which had a burst BMP release profile produced intermediate sized ossicles (Figure 4; 0-100), while bioimplants with 50% of the BMP loaded into the carrier and 50% loaded into the delivery vehicle, which had a multiphasic BMP release profile, produced the largest ossicles of bone (Figure 4; 50-50).

[00141] Backscatter SEM showed that by 28 days bone formed throughout the bioimplant and onto the calcium phosphate particulate that had been incorporated into the PLGA (Figure 5). Histology confirmed the tissue formed was bone (Figure 6).

[00142] **EXAMPLE 9: An in vivo assay for release of BMPs from bioimplants**

[00143] The present example describes how to measure the release of rhBMP-2 from the various bioimplants described in Examples 1, 2, 3, 4 or 5 following implantation into an animal. Methods to do this are well known in the art. For example see Uludag et al. J Biomed Mater Res, 46, 193–202, 1999.

[00144] Materials & Methods

[00145] Recombinant hBMP-2 is radiolabeled with Iodine125 (I-125) by Perkin Elmer. The radiolabelled rhBMP-2 (hot) is mixed with unlabeled rhBMP-2 (cold) to produce a hot cold mixture of 1:100.

1 [00146] Bioimplants containing known amounts of rhBMP-2 are prepared as in Examples
2 1 to 5. These bioimplants are then implanted into animals as described in Example 8. At
3 various times the animals are sacrificed and the implant site is dissected out. The dissected
4 tissue is then weighed, and the amount of radioactivity determined using a gamma counter.

5 [00147] To determine whether the counts are associated with protein, the tissue is
6 homogenized in 0.5ml PBS+0.5% BSA. Two mls of ice cold 10% trichloroacetic acid are
7 added to the homogenate and is then held for at least 1 hour at 4°C. The homogenate is
8 then centrifuged and the supernatant removed. The radioactivity of the precipitate is then
9 measured using a gamma counter.

10 [00148] The radioactivity associated with implants is corrected for the decay and the total
11 amount of BMP remaining in the implant is estimated.

12 [00149] **EXAMPLE 10: Production of a carrier with a short sustained release profile**

13 [00150] The present example describes means of producing a carrier that releases a
14 growth factor with a short sustained release profile.

15 [00151] Materials & Methods

16 [00152] Macroporous biphasic calcium phosphate (BCP) granules (Eclipse) were
17 purchased from Citagenix (Laval, Qc, Canada.) Recombinant human BMP-2 (rhBMP-2,
18 Induce Biologics Inc) was prepared in formulation buffer (1.5mg/ml, pH 4.5; 5 mm glutamic
19 acid, 2.5% glycine, 0.5% sucrose and 0.01% Tween™ 80 with ddH2O).

20 [00153] Sterile rhBMP-2 solution was incubated with sterile BCP granules at a ratio of
21 9.1µg per 5mg or 4.55µg per 5mg (BMP per BCP) for 15 minutes under shaking. The
22 samples were then frozen and lyophilized aseptically.

23 [00154] Following lyophilization the carriers were weighed into 5mg aliquots and placed in
24 sterile epindorf tubes. Some tubes had 33% F127 (45.5µl added). The BMP release profile
25 was then determined as described in Example 6.

26 [00155] Results

27 [00156] Carriers that were not coated with F127 (BCP) showed a burst release profile
28 with the largest amount of BMP released over the first day and then decreasing amounts of
29 BMP released at each subsequent time point. Mixing the BCP within the F127 (BCP-Pol)

1 resulted in a short sustained release profile where similar amount of BMP were collected
2 each day over the first 4 days (Figure 7).

3 **[00157] EXAMPLE 11: Altering the sustained release profile of the carrier**

4 **[00158]** The present example describes a means of altering the release profile from a
5 carrier.

6 **[00159] Materials & Methods**

7 **[00160]** PLGA with differing inherent viscosities and molecular weights were purchased
8 from Birmingham Polymers Inc. (Birmingham, AL). Carriers were then made using these
9 PLGAs as described in Example 1. The BMP release profile from these carriers was
10 determine according to the method of Example 6.

11 **[00161] Results**

12 **[00162]** All carriers produced sustained release profiles. However the amount of BMP
13 released differed depending on the viscosity/molecular weight of the PLGA used. The
14 carriers made with low viscosity PLGA (Pol-1) released more rhBMP-2 than those using the
15 high viscosity (Pol-2) PLGA over the 12 week duration of the study (Figure 8).

16

17

WHAT IS CLAIMED IS:

1. A system for multiphasic release of growth factors at a treatment site, the system comprising:
 - a delivery vehicle comprising at least one first growth factor; and
 - a carrier comprising at least one second growth factor;- wherein:
 - the delivery vehicle is adapted to release the at least one first growth factor in an initial release profile over a first time period;
 - the carrier is adapted to release the at least one second growth factor in a sustained release profile over a second time period.
2. The system according to claim 1, wherein the delivery vehicle comprises a polymer.
3. The system according to claim 2, wherein the polymer is a reverse phase polymer or a block co-polymer.
4. The system according to claim 3, wherein the polymer is a poloxamer.
5. The system according to claim 4, wherein the polymer is poloxamer 407.
6. The system according to claim 1, wherein the carrier comprises a plurality of particles dispersed within a polymeric matrix and wherein the particles contain the at least one second growth factor on the surfaces thereof.
7. The system according to claim 6, wherein the particles comprise calcium phosphate particles.
8. The system according to claim 6 or 7, wherein the polymeric matrix comprises polylactic acid (PLA) or polylactic-co-glycolic acid (PLGA).
9. The system according to any one of claims 1 to 8, wherein the first time period comprises hours or days.

10. The system according to any one of claims 1 to 9, wherein the second time period comprises days or weeks.
11. The system according to any one of claims 1 to 10, wherein the at least one first growth factor and the at least one second growth factor are the same.
12. The system according to any one of claims 1 to 10, wherein the at least one first growth factor and the at least one second growth factor are the different.
13. The system according to any one of claims 1 to 12, wherein the first and second growth factor are growth factors of the transforming growth factor beta superfamily.
14. The system according to claim 13, wherein the first and second growth factors are: bone morphogenetic proteins (BMPs), transforming growth factor beta, insulin-like growth factors (IGFs), fibroblast growth factors (FGFs), platelet derived growth factors (PDGFs) or vascular endothelial growth factors (VEGFs).
15. The system according to claim 14, wherein the at least one first and second growth factors are BMPs.
16. The system according to claim 15, wherein the at least one first and second growth factors are BMP-2 or BMP-7.
17. The system according to any one of claims 1 to 16, wherein the delivery vehicle delivers at least 10% of the total amount of the growth factors and the carrier delivers at least 50% of the total amount of the growth factors.
18. A bioimplant comprising the growth factor release system according to any one of claims 1 to 17.
19. A method of multiphasic release of growth factors, the method comprising:
 - delivering at least one first growth factor in an initial release profile;
 - delivering at least one second growth factor in a sustained release profile.

20. The method according to claim 19, wherein the at least one first growth factor is delivered by a delivery vehicle and said at least one second growth factor is delivered by a carrier.
21. The method according to claim 19 or 20, wherein the at least one first growth factor and the at least one second growth factor are the same.
22. The method according to any one of claims 19 to 21, wherein the at least one first growth factor and the at least one second growth factor are different.
23. The method according to any one of claims 19 to 22, wherein the at least one first and second growth factors are growth factors of the transforming growth factor beta superfamily.
24. The method according to claim 23, wherein the at least one first and second growth factors are: bone morphogenetic proteins (BMPs), transforming growth factor beta, insulin-like growth factors (IGFs), fibroblast growth factors (FGFs), platelet derived growth factors (PDGFs) or vascular endothelial growth factors (VEGFs).
25. The method according to claim 24, wherein the at least one first and second growth factors are BMPs.
26. The method according to claim 25, wherein the at least one first and second growth factors are BMP-2 or BMP-7.
27. The method according to any one of claims 18 to 26, wherein the delivery vehicle delivers at least 10% of the total amount of the growth factors and the carrier delivers at least 50% of the total amount of the growth factors.
28. A kit for multiphasic delivery of growth factors, the kit comprising:
- a delivery vehicle component;
 - at least one first growth factor associated with the delivery vehicle;
 - a carrier component; and
 - at least one second growth factor associated with the carrier.

29. The kit according to claim 28, wherein the delivery vehicle and the carrier components are in separate containers.
30. The kit according to claim 29, wherein the delivery vehicle and the at least one first growth factor are provided in separate containers.
31. The kit according to any one of claims 28 to 30, wherein the carrier and the at least one second growth factor are combined in a single container and wherein the at least one second growth factor is loaded or coated on the carrier component.
32. The kit according to any one of claims 28 to 31, wherein the delivery vehicle comprises a polymer.
33. The kit according to claim 32, wherein the polymer is a reverse phase polymer or a block co-polymer.
34. The kit according to claim 33, wherein the polymer is a poloxamer.
35. The kit according to claim 34, wherein the polymer is poloxamer 407.
36. The kit according to claim 28, wherein the carrier comprises a plurality of particles dispersed within a polymeric matrix and wherein the particles contain the at least one second growth factor on the surfaces thereof.
37. The kit according to claim 36, wherein the particles comprise calcium phosphate particles.
38. The kit according to claim 36 or 37, wherein the polymeric matrix comprises polylactic acid (PLA) or polylactic-co-glycolic acid (PLGA).
39. The kit according to any one of claims 28 to 38, wherein the at least one first growth factor and the at least one second growth factor are the same.
40. The kit according to any one of claims 28 to 38, wherein the at least one first growth factor and the at least one second growth factor are different.

41. The kit according to any one of claims 28 to 40, wherein the first and second growth factor are growth factors of the transforming growth factor beta superfamily.
42. The kit according to claim 41, wherein the first and second growth factors are: bone morphogenetic proteins (BMPs), transforming growth factor beta, insulin-like growth factors (IGFs), fibroblast growth factors (FGFs), platelet derived growth factors (PDGFs) or vascular endothelial growth factors (VEGFs).
43. The kit according to claim 42, wherein the first and second growth factors are BMPs.
44. The kit according to claim 43, wherein the first and second growth factors are BMP-2 or BMP-7.
45. The kit according to any one of claims 28 to 44, wherein the at least one first growth factor comprises at least 10% of the total amount of growth factors provided in the kit and the at least one second growth factor comprises at least 50% of the total amount of growth factors provided in the kit.




Figure 1




Figure 2




Figure 3




Figure 4




Figure 5




Figure 6




Figure 7




Figure 8

INTERNATIONAL SEARCH REPORT

International application No.
PCT/CA2012/050234

A. CLASSIFICATION OF SUBJECT MATTER

IPC: **A61K 9/10** (2006.01) , **A61K 38/18** (2006.01) , **A61K 47/30** (2006.01) , **A61K 47/34** (2006.01) ,
A61K 9/00 (2006.01) , **A61P 17/02** (2006.01) (more IPCs on the last page)
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

A61K 9/10, A61K 38/18, A61K 47/30, A61K 47/34, A61K 9/00, A61P 17/02, A61P 19/08

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic database(s) consulted during the international search (name of database(s) and, where practicable, search terms used)
Canadian Patent Database, EPODOC. growth factor, BMP, morphogen, PLGA, lacti*, calcium, poloxamer, protein, pluronic, copolymer, Induce Biologics, klokie, peel

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2010/0021518 A (SCIFERT) 28 January 2010 (28-01-2010) paragraphs [0031], [0039]-[0044], [0052], [0082], [0085].	1-45
Y	WO 2010/000061 A1 (CLOKIE et al) 07 January 2010 (07-01-2010) paragraphs [0074]-[0075].	1-45
Y	WO2006/093808A1 (ZAMORA et al) 08 September 2006 (08-09-2006) pages 46-50, claims 1, 3, 5.	1-45

☐ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents :	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier application or patent but published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

31 July 2012 (31-07-2012)

Date of mailing of the international search report

08 August 2012 (08-08-2012)

Name and mailing address of the ISA/CA
Canadian Intellectual Property Office
Place du Portage I, C114 - 1st Floor, Box PCT
50 Victoria Street
Gatineau, Quebec K1A 0C9
Facsimile No.: 001-819-953-2476

Authorized officer

ADAM MACKENZIE (819) 994-6514

INTERNATIONAL SEARCH REPORT
Information on patent family members

International application No.
PCT/CA2012/050234

Patent Document Cited in Search Report	Publication Date	Patent Family Member(s)	Publication Date
US2010021518A1	28 January 2010 (28-01-2010)	None	
WO2010000061A1	07 January 2010 (07-01-2010)	AU2009200540A1 CA2653866A1 EP2310062A1 US2011182911A1	21 January 2010 (21-01-2010) 03 January 2010 (03-01-2010) 20 April 2011 (20-04-2011) 28 July 2011 (28-07-2011)
WO2006093808A1	08 September 2006 (08-09-2006)	AU2006216676A1 CA2598688A1 CA2599134A1 EP1855703A1 EP1855706A2 EP1855706A4 JP2008531505A JP4897708B2 US7528105B1 US2006205652A1 US7671012B2 US2010298218A1 US8101570B2 US2006024347A1 US2008227696A1 US2009111743A1 WO2006004868A2 WO2006004868A3 WO2006091727A2 WO2006091727A3	31 August 2006 (31-08-2006) 31 August 2006 (31-08-2006) 08 September 2006 (08-09-2006) 21 November 2007 (21-11-2007) 21 November 2007 (21-11-2007) 28 March 2012 (28-03-2012) 14 August 2008 (14-08-2008) 14 March 2012 (14-03-2012) 05 May 2009 (05-05-2009) 14 September 2006 (14-09-2006) 02 March 2010 (02-03-2010) 25 November 2010 (25-11-2010) 24 January 2012 (24-01-2012) 02 February 2006 (02-02-2006) 18 September 2008 (18-09-2008) 30 April 2009 (30-04-2009) 12 January 2006 (12-01-2006) 01 February 2007 (01-02-2007) 31 August 2006 (31-08-2006) 01 March 2007 (01-03-2007)

A61P 19/08 (2006.01)