





(86) Date de dépôt PCT/PCT Filing Date: 2010/10/28
 (87) Date publication PCT/PCT Publication Date: 2011/05/05
 (45) Date de délivrance/Issue Date: 2021/11/23
 (85) Entrée phase nationale/National Entry: 2012/05/01
 (86) N° demande PCT/PCT Application No.: US 2010/054422
 (87) N° publication PCT/PCT Publication No.: 2011/053677
 (30) Priorité/Priority: 2009/11/02 (US61/257,261)

(51) Cl.Int./Int.Cl. *D21H 27/00* (2006.01),
A61F 13/15 (2006.01), *D04H 13/00* (2006.01)
 (72) Inventeurs/Inventors:
BARNHOLTZ, STEVEN LEE, US;
TROKHAN, PAUL DENNIS, US;
BARKEY, DOUGLAS JAY, US;
YOUNG, CHRISTOPHER MICHAEL, US;
SUER, MICHAEL DONALD, US
 (73) Propriétaire/Owner:
THE PROCTER & GAMBLE COMPANY, US
 (74) Agent: WILSON LUE LLP

(54) Titre : PLI DE STRUCTURE FIBREUSE CALANDREE AYANT UNE DISTRIBUTION DE VOLUME DE PORES
 (54) Title: CALENDERED FIBROUS STRUCTURE PLY WITH PORE VOLUME DISTRIBUTION



(57) Abrégé/Abstract:

Fibrous structures that exhibit a pore volume distribution such that at least 25% and/or at least 43% of the total pore volume present in the fibrous structures exists in pores of radii of from 91µm to 140µm, and to methods for making such fibrous structures are provided.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
5 May 2011 (05.05.2011)

PCT

(10) International Publication Number
WO 2011/053677 A1

- (51) International Patent Classification:
D21H 27/00 (2006.01) *D04H 13/00* (2006.01)
A61F 13/15 (2006.01)
- (21) International Application Number:
PCT/US2010/054422
- (22) International Filing Date:
28 October 2010 (28.10.2010)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
61/257,261 2 November 2009 (02.11.2009) US
- (71) Applicant (for all designated States except US): **THE PROCTER & GAMBLE COMPANY** [US/US]; One Procter & Gamble Plaza, Cincinnati, Ohio 45202 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **BARNHOLTZ, Steven, Lee** [US/US]; 5835 Olympia Fields Court, West Chester, Ohio 45069 (US). **TROKHAN, Paul, Dennis** [US/US]; 1356 Warvel Road, Hamilton, Ohio 45013 (US). **BARKEY, Douglas, Jay** [US/US]; 964 Airymeadows Drive, Hamilton Township, Ohio 45039 (US). **YOUNG, Christopher, Michael** [US/US]; 6975 Bramble Hill Drive, Cincinnati, Ohio 45227 (US). **SUER, Michael, Donald** [US/US]; 5470 Longlake Court, Cincinnati, Ohio 45247 (US).

- (74) Common Representative: **THE PROCTER & GAMBLE COMPANY**; c/o Eileen L. Hughett, Global Patent Services, 299 East Sixth Street, Sycamore Building, 4th Floor, Cincinnati, Ohio 45202 (US).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:
— with international search report (Art. 21(3))

[Continued on next page]

(54) Title: FIBROUS STRUCTURES AND METHODS FOR MAKING SAME




Fig. 1

(57) Abstract: Fibrous structures that exhibit a pore volume distribution such that at least 25% and/or at least 43% of the total pore volume present in the fibrous structures exists in pores of radii of from 91µm to 140µm, and to methods for making such fibrous structures are provided.



WO 2011/053677 A1

WO 2011/053677 A1 

— *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments (Rule 48.2(h))*

CALENDERED FIBROUS STRUCTURE PLY WITH PORE VOLUME DISTRIBUTION

FIELD OF THE INVENTION

The present invention relates to fibrous structures and more particularly to fibrous structures that exhibit a pore volume distribution such that at least 25% and/or at least 43% of the total pore volume present in the fibrous structures exists in pores of radii of from $91\mu\text{m}$ to $140\mu\text{m}$, and to methods for making such fibrous structures.

BACKGROUND OF THE INVENTION

Consumers of fibrous structures, especially paper towels, require absorbency properties (such as absorption capacity and/or rate of absorption) in their fibrous structures. The pore volume distribution present in the fibrous structures impacts the absorbency properties of the fibrous structures. In the past, some fibrous structures exhibit pore volume distributions that optimize the absorption capacity others exhibit pore volume distributions that optimize the rate of absorption. To date, no known fibrous structures balance the properties of absorption capacity with rate of absorption and surface drying via the pore volume distribution exhibited by the fibrous structures.

Known fibrous structures exhibit various pore volume distributions. For example, a currently marketed wood pulp-based paper towel exhibits a substantially uniform pore volume distribution. In another example, a currently marketed wipe product has significantly more than 55% of its total pore volume present in the wipe product that exists in pores of radii of less than $100\mu\text{m}$. In yet another example, a currently marketed non-textile washcloth has significantly more than 55% of its total pore volume present in the wipe product that exists in pores of radii of greater than $200\mu\text{m}$.

The problem faced by formulators is how to produce fibrous structures that have a pore volume distribution that balances the absorbency properties (i.e., absorption capacity and rate of absorption and surface drying) that satisfies the consumers' needs.

Accordingly, there is a need for fibrous structures that exhibit a pore volume distribution such that at least 25% and/or at least 43% of the total pore volume present in the fibrous structures exists in pores of radii of from $91\mu\text{m}$ to about $140\mu\text{m}$, and for methods for making such fibrous structures.

SUMMARY OF THE INVENTION

The present invention solves the problem identified above by fulfilling the needs of the consumers by providing fibrous structures that exhibit a novel pore volume distribution and methods for making such fibrous structures.

In one example of the present invention, a fibrous structure comprising a plurality of filaments, wherein the fibrous structure exhibits a pore volume distribution such that at least 43% and/or at least 45% and/or at least 50% and/or at least 55% and/or at least 60% and/or at least 75% of the total pore volume present in the fibrous structures exists in pores of radii of from 91 μ m to about 140 μ m as determined by the Pore Volume Distribution Test Method described herein, is provided.

In another example of the present invention, a fibrous structure comprising a non-random, repeating pattern of microregions, wherein the fibrous structure exhibits a pore volume distribution such that at least 25% and/or at least 30% and/or at least 43% and/or at least 45% and/or at least 50% and/or at least 60% and/or at least 75% of the total pore volume present in the fibrous structures exists in pores of radii of from 91 μ m to 140 μ m as determined by the Pore Volume Distribution Test Method described herein, is provided.

In still another example of the present invention, a method for making a fibrous structure, the method comprising the step of combining a plurality of filaments to form a fibrous structure that exhibits a pore volume distribution such that at least 43% and/or at least 45% and/or at least 50% and/or at least 55% and/or at least 60% and/or at least 75% of the total pore volume present in the fibrous structure exists in pores of radii of from 91 μ m to 140 μ m as determined by the Pore Volume Distribution Test Method, is provided.

In even still another example of the present invention, a method for making a fibrous structure, the method comprising the step of combining a plurality of filaments on a collection device capable of forming a non-random, repeating pattern of microregions in the fibrous structure to form a fibrous structure comprising a non-random, repeating pattern of microregions, wherein the fibrous structure exhibits a pore volume distribution such that at least 25% and/or at least 30% and/or at least 43% and/or at least 45% and/or at least 50% and/or at least 60% and/or at least 75% of the total pore volume present in the fibrous structures exists in pores of radii of from 91 μ m to 140 μ m as determined by the Pore Volume Distribution Test Method described herein, is provided.

In yet another example of the present invention, a sanitary tissue product comprising a fibrous structure according to the present invention is provided.

Accordingly, the present invention provides fibrous structures that solve the problems described above by providing fibrous structures that exhibit a pore volume distribution such that at least 25% and/or at least 43% of the total pore volume present in the fibrous structure exists in pores of radii of from $91\mu\text{m}$ to $140\mu\text{m}$, and to methods for making such fibrous structures.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a Pore Volume Distribution graph of various fibrous structures, including a fibrous structure according to the present invention, showing the Ending Pore Radius of from $1\mu\text{m}$ to $1000\mu\text{m}$ and the Capacity of Water in Pores;

Fig. 2 is a Pore Volume Distribution graph of various fibrous structures, including a fibrous structure according to the present invention, showing the Ending Pore Radius of from $1\mu\text{m}$ to $400\mu\text{m}$ and the Capacity of Water in Pores;

Fig. 3 is a schematic representation of an example of a fibrous structure according to the present invention;

Fig. 4 is a schematic, cross-sectional representation of Fig. 3 taken along line 4-4;

Fig. 5 is a scanning electromicrophotograph of a cross-section of another example of fibrous structure according to the present invention;

Fig. 6 is a schematic representation of another example of a fibrous structure according to the present invention;

Fig. 7 is a schematic, cross-sectional representation of another example of a fibrous structure according to the present invention;

Fig. 8 is a schematic, cross-sectional representation of another example of a fibrous structure according to the present invention;

Fig. 9 is a schematic representation of an example of a process for making a fibrous structure according to the present invention;

Fig. 10 is a schematic representation of an example of a patterned belt for use in a process according to the present invention; and

Fig. 11 is a schematic representation of an example of a filament-forming hole and fluid-releasing hole from a suitable die useful in making a fibrous structure according to the present invention.

DETAILED DESCRIPTION OF THE INVENTION

Definitions

“Fibrous structure” as used herein means a structure that comprises one or more filaments and/or fibers. In one example, a fibrous structure according to the present invention means an orderly arrangement of filaments and/or fibers within a structure in order to perform a function. In another example, a fibrous structure according to the present invention is a nonwoven.

Non-limiting examples of processes for making fibrous structures include known wet-laid papermaking processes and air-laid papermaking processes. Such processes typically include steps of preparing a fiber composition in the form of a suspension in a medium, either wet, more specifically aqueous medium, or dry, more specifically gaseous, i.e. with air as medium. The aqueous medium used for wet-laid processes is oftentimes referred to as a fiber slurry. The fibrous slurry is then used to deposit a plurality of fibers onto a forming wire or belt such that an embryonic fibrous structure is formed, after which drying and/or bonding the fibers together results in a fibrous structure. Further processing the fibrous structure may be carried out such that a finished fibrous structure is formed. For example, in typical papermaking processes, the finished fibrous structure is the fibrous structure that is wound on the reel at the end of papermaking, and may subsequently be converted into a finished product, e.g. a sanitary tissue product.

The fibrous structures of the present invention may be homogeneous or may be layered. If layered, the fibrous structures may comprise at least two and/or at least three and/or at least four and/or at least five layers.

The fibrous structures of the present invention may be co-formed fibrous structures.

“Co-formed fibrous structure” as used herein means that the fibrous structure comprises a mixture of at least two different materials wherein at least one of the materials comprises a filament, such as a polypropylene filament, and at least one other material, different from the first material, comprises a solid additive, such as a fiber and/or a particulate. In one example, a co-formed fibrous structure comprises solid additives, such as fibers, such as wood pulp fibers and/or absorbent gel materials and/or filler particles and/or particulate spot bonding powders and/or clays, and filaments, such as polypropylene filaments.

“Solid additive” as used herein means a fiber and/or a particulate.

“Particulate” as used herein means a granular substance or powder.

“Fiber” and/or “Filament” as used herein means an elongate particulate having an apparent length greatly exceeding its apparent width, i.e. a length to diameter ratio of at least

about 10. For purposes of the present invention, a "fiber" is an elongate particulate as described above that exhibits a length of less than 5.08 cm (2 in.) and a "filament" is an elongate particulate as described above that exhibits a length of greater than or equal to 5.08 cm (2 in.).

Fibers are typically considered discontinuous in nature. Non-limiting examples of fibers include wood pulp fibers and synthetic staple fibers such as polyester fibers.

Filaments are typically considered continuous or substantially continuous in nature. Filaments are relatively longer than fibers. Non-limiting examples of filaments include meltblown and/or spunbond filaments. Non-limiting examples of materials that can be spun into filaments include natural polymers, such as starch, starch derivatives, cellulose and cellulose derivatives, hemicellulose, hemicellulose derivatives, chitin, chitosan, polyisoprene (*cis* and *trans*), peptides, polyhydroxyalkanoates, and synthetic polymers including, but not limited to, thermoplastic polymer filaments comprising thermoplastic polymers, such as polyesters, nylons, polyolefins such as polypropylene filaments, polyethylene filaments, polyvinyl alcohol and polyvinyl alcohol derivatives, sodium polyacrylate (absorbent gel material) filaments, and copolymers of polyolefins such as polyethylene-octene, and biodegradable or compostable thermoplastic fibers such as polylactic acid filaments, polyvinyl alcohol filaments, and polycaprolactone filaments. The filaments may be monocomponent or multicomponent, such as bicomponent filaments.

In one example of the present invention, "fiber" refers to papermaking fibers. Papermaking fibers useful in the present invention include cellulosic fibers commonly known as wood pulp fibers. Applicable wood pulps include chemical pulps, such as Kraft, sulfite, and sulfate pulps, as well as mechanical pulps including, for example, groundwood, thermomechanical pulp and chemically modified thermomechanical pulp. Chemical pulps, however, may be preferred since they impart a superior tactile sense of softness to tissue sheets made therefrom. Pulps derived from both deciduous trees (hereinafter, also referred to as "hardwood") and coniferous trees (hereinafter, also referred to as "softwood") may be utilized. The hardwood and softwood fibers can be blended, or alternatively, can be deposited in layers to provide a stratified web. U.S. Pat. No. 4,300,981 and U.S. Pat. No. 3,994,771 disclose

layering of hardwood and softwood fibers. Also applicable to the present invention are fibers derived from recycled paper, which may contain any or all of the above categories as well as other non-fibrous materials such as fillers and adhesives used to facilitate the original papermaking.

In addition to the various wood pulp fibers, other cellulosic fibers such as cotton linters, rayon, lyocell and bagasse can be used in this invention. Other sources of cellulose in the form of fibers or capable of being spun into fibers include grasses and grain sources.

“Sanitary tissue product” as used herein means a soft, low density (i.e. < about 0.15 g/cm³) web useful as a wiping implement for post-urinary and post-bowel movement cleaning (toilet tissue), for otorhinolaryngological discharges (facial tissue), and multi-functional absorbent and cleaning uses (absorbent towels). Non-limiting examples of suitable sanitary tissue products of the present invention include paper towels, bath tissue, facial tissue, napkins, baby wipes, adult wipes, wet wipes, cleaning wipes, polishing wipes, cosmetic wipes, car care wipes, wipes that comprise an active agent for performing a particular function, cleaning substrates for use with implements, such as a Swiffer[®] cleaning wipe/pad. The sanitary tissue product may be convolutedly wound upon itself about a core or without a core to form a sanitary tissue product roll.

In one example, the sanitary tissue product of the present invention comprises a fibrous structure according to the present invention.

The sanitary tissue products of the present invention may exhibit a basis weight between about 10 g/m² to about 120 g/m² and/or from about 15 g/m² to about 110 g/m² and/or from about 20 g/m² to about 100 g/m² and/or from about 30 to 90 g/m². In addition, the sanitary tissue product of the present invention may exhibit a basis weight between about 40 g/m² to about 120 g/m² and/or from about 50 g/m² to about 110 g/m² and/or from about 55 g/m² to about 105 g/m² and/or from about 60 to 100 g/m².

The sanitary tissue products of the present invention may exhibit a total dry tensile strength of at least 59 g/cm (150 g/in) and/or from about 78 g/cm (200 g/in) to about 394 g/cm (1000 g/in) and/or from about 98 g/cm (250 g/in) to about 335 g/cm (850 g/in). In addition, the sanitary tissue product of the present invention may exhibit a total dry tensile strength of at least 196 g/cm (500 g/in) and/or from about 196 g/cm (500 g/in) to about 394 g/cm (1000 g/in) and/or from about 216 g/cm (550 g/in) to about 335 g/cm (850 g/in) and/or from about 236 g/cm (600 g/in) to about 315 g/cm (800 g/in). In one example, the sanitary tissue product exhibits a total dry tensile strength of less than about 394 g/cm (1000 g/in) and/or less than about 335 g/cm (850 g/in).

In another example, the sanitary tissue products of the present invention may exhibit a total dry tensile strength of at least 196 g/cm (500 g/in) and/or at least 236 g/cm (600 g/in) and/or at least 276 g/cm (700 g/in) and/or at least 315 g/cm (800 g/in) and/or at least 354 g/cm (900

g/in) and/or at least 394 g/cm (1000 g/in) and/or from about 315 g/cm (800 g/in) to about 1968 g/cm (5000 g/in) and/or from about 354 g/cm (900 g/in) to about 1181 g/cm (3000 g/in) and/or from about 354 g/cm (900 g/in) to about 984 g/cm (2500 g/in) and/or from about 394 g/cm (1000 g/in) to about 787 g/cm (2000 g/in).

The sanitary tissue products of the present invention may exhibit an initial total wet tensile strength of less than about 78 g/cm (200 g/in) and/or less than about 59 g/cm (150 g/in) and/or less than about 39 g/cm (100 g/in) and/or less than about 29 g/cm (75 g/in).

The sanitary tissue products of the present invention may exhibit an initial total wet tensile strength of at least 118 g/cm (300 g/in) and/or at least 157 g/cm (400 g/in) and/or at least 196 g/cm (500 g/in) and/or at least 236 g/cm (600 g/in) and/or at least 276 g/cm (700 g/in) and/or at least 315 g/cm (800 g/in) and/or at least 354 g/cm (900 g/in) and/or at least 394 g/cm (1000 g/in) and/or from about 118 g/cm (300 g/in) to about 1968 g/cm (5000 g/in) and/or from about 157 g/cm (400 g/in) to about 1181 g/cm (3000 g/in) and/or from about 196 g/cm (500 g/in) to about 984 g/cm (2500 g/in) and/or from about 196 g/cm (500 g/in) to about 787 g/cm (2000 g/in) and/or from about 196 g/cm (500 g/in) to about 591 g/cm (1500 g/in).

The sanitary tissue products of the present invention may exhibit a density (measured at 95 g/in²) of less than about 0.60 g/cm³ and/or less than about 0.30 g/cm³ and/or less than about 0.20 g/cm³ and/or less than about 0.10 g/cm³ and/or less than about 0.07 g/cm³ and/or less than about 0.05 g/cm³ and/or from about 0.01 g/cm³ to about 0.20 g/cm³ and/or from about 0.02 g/cm³ to about 0.10 g/cm³.

The sanitary tissue products of the present invention may be in the form of sanitary tissue product rolls. Such sanitary tissue product rolls may comprise a plurality of connected, but perforated sheets of fibrous structure, that are separably dispensable from adjacent sheets. In one example, one or more ends of the roll of sanitary tissue product may comprise an adhesive and/or dry strength agent to mitigate the loss of fibers, especially wood pulp fibers from the ends of the roll of sanitary tissue product.

The sanitary tissue products of the present invention may comprises additives such as softening agents, temporary wet strength agents, permanent wet strength agents, bulk softening agents, lotions, silicones, wetting agents, latexes, especially surface-pattern-applied latexes, dry strength agents such as carboxymethylcellulose and starch, and other types of additives suitable for inclusion in and/or on sanitary tissue products.

“Weight average molecular weight” as used herein means the weight average molecular weight as determined using gel permeation chromatography according to the protocol found in Colloids and Surfaces A. Physico Chemical & Engineering Aspects, Vol. 162, 2000, pg. 107-121.

“Basis Weight” as used herein is the weight per unit area of a sample reported in lbs/3000 ft² or g/m².

“Machine Direction” or “MD” as used herein means the direction parallel to the flow of the fibrous structure through the fibrous structure making machine and/or sanitary tissue product manufacturing equipment.

“Cross Machine Direction” or “CD” as used herein means the direction parallel to the width of the fibrous structure making machine and/or sanitary tissue product manufacturing equipment and perpendicular to the machine direction.

“Ply” as used herein means an individual, integral fibrous structure.

“Plies” as used herein means two or more individual, integral fibrous structures disposed in a substantially contiguous, face-to-face relationship with one another, forming a multi-ply fibrous structure and/or multi-ply sanitary tissue product. It is also contemplated that an individual, integral fibrous structure can effectively form a multi-ply fibrous structure, for example, by being folded on itself.

“Total Pore Volume” as used herein means the sum of the fluid holding void volume in each pore range from 1μm to 1000μm radii as measured according to the Pore Volume Test Method described herein.

“Pore Volume Distribution” as used herein means the distribution of fluid holding void volume as a function of pore radius. The Pore Volume Distribution of a fibrous structure is measured according to the Pore Volume Test Method described herein.

As used herein, the articles “a” and “an” when used herein, for example, "an anionic surfactant" or "a fiber" is understood to mean one or more of the material that is claimed or described.

All percentages and ratios are calculated by weight unless otherwise indicated. All percentages and ratios are calculated based on the total composition unless otherwise indicated.

Unless otherwise noted, all component or composition levels are in reference to the active level of that component or composition, and are exclusive of impurities, for example, residual solvents or by-products, which may be present in commercially available sources.

Fibrous Structure

It has surprisingly been found that the fibrous structures of the present invention exhibit a pore volume distribution unlike pore volume distributions of other known structured and/or textured fibrous structures.

The fibrous structures of the present invention may comprise a plurality of filaments, a plurality of solid additives, such as fibers, and a mixture of filaments and solid additives.

As shown in Figs. 1 and 2, examples of fibrous structures according to the present invention as represented by the plot for the Inventive Sample exhibit a pore volume distribution such that at least 43% of the total pore volume present in the fibrous structure exists in pores of radii of from $91\mu\text{m}$ to about $140\mu\text{m}$.

The range of $91\mu\text{m}$ to $140\mu\text{m}$ is explicitly identified on the graph of Fig. 2. It should be noted that the value for the ending pore radius for the range of $91\mu\text{m}$ to $140\mu\text{m}$ is plotted at the ending pore radius; namely, $140\mu\text{m}$. This data is also supported by the values present in Table 1 below.

Such fibrous structures have been found to exhibit consumer-recognizable beneficial absorbent capacity and surface drying. In one example, the fibrous structures comprise a plurality of solid additives, for example fibers. In another example, the fibrous structures comprise a plurality of filaments. In yet another example, the fibrous structures comprise a mixture of filaments and solid additives, such as fibers.

As shown in Fig. 2, the examples of fibrous structures according to the present invention as represented by the plot for the Inventive Sample may exhibit a bi-modal pore volume distribution such that the fibrous structure exhibits a pore volume distribution such that the at least 43% of the total pore volume present in the fibrous structure exists in pores of radii of from $91\mu\text{m}$ to $140\mu\text{m}$ and at least 2% and/or at least 5% and/or at least 10% of the total pore volume present in the fibrous structure exists in pores of radii of less than about $100\mu\text{m}$ and/or less than about $80\mu\text{m}$ and/or less than about $50\mu\text{m}$ and/or from about $1\mu\text{m}$ to about $100\mu\text{m}$ and/or from about $5\mu\text{m}$ to about $75\mu\text{m}$ and/or $10\mu\text{m}$ to about $50\mu\text{m}$.

A fibrous structure according to the present invention exhibiting a bi-modal pore volume distribution as described above provides beneficial absorbent capacity and absorbent rate as a result of the larger radii pores and beneficial surface drying as a result of the smaller radii pores.

Figs. 3 and 4 show schematic representations of an example of a fibrous structure in accordance with the present invention. As shown in Figs. 3 and 4, the fibrous structure 10 may be a co-formed fibrous structure. The fibrous structure 10 comprises a plurality of filaments 12, such as polypropylene filaments, and a plurality of solid additives, such as wood pulp fibers 14.

The filaments 12 may be randomly arranged as a result of the process by which they are spun and/or formed into the fibrous structure 10. The wood pulp fibers 14, may be randomly dispersed throughout the fibrous structure 10 in the x-y plane. The wood pulp fibers 14 may be non-randomly dispersed throughout the fibrous structure in the z-direction. In one example (not shown), the wood pulp fibers 14 are present at a higher concentration on one or more of the exterior, x-y plane surfaces than within the fibrous structure along the z-direction.

Fig. 5 shows a cross-sectional, SEM microphotograph of another example of a fibrous structure 10a in accordance with the present invention shows a fibrous structure 10a comprising a non-random, repeating pattern of microregions 15a and 15b. The microregion 15a (typically referred to as a “pillow”) exhibits a different value of a common intensive property than microregion 15b (typically referred to as a “knuckle”). In one example, the microregion 15b is a continuous or semi-continuous network and the microregion 15a are discrete regions within the continuous or semi-continuous network. The common intensive property may be caliper. In another example, the common intensive property may be density.

As shown in Fig. 6, another example of a fibrous structure in accordance with the present invention is a layered fibrous structure 10b. The layered fibrous structure 10b comprises a first layer 16 comprising a plurality of filaments 12, such as polypropylene filaments, and a plurality of solid additives, in this example, wood pulp fibers 14. The layered fibrous structure 10b further comprises a second layer 18 comprising a plurality of filaments 20, such as polypropylene filaments. In one example, the first and second layers 16, 18, respectively, are sharply defined zones of concentration of the filaments and/or solid additives. The plurality of filaments 20 may be deposited directly onto a surface of the first layer 16 to form a layered fibrous structure that comprises the first and second layers 16, 18, respectively.

Further, the layered fibrous structure 10b may comprise a third layer 22, as shown in Fig. 6. The third layer 22 may comprise a plurality of filaments 24, which may be the same or different from the filaments 20 and/or 16 in the second 18 and/or first 16 layers. As a result of the addition of the third layer 22, the first layer 16 is positioned, for example sandwiched, between the second layer 18 and the third layer 22. The plurality of filaments 24 may be deposited directly onto a surface of the first layer 16, opposite from the second layer, to form the layered fibrous structure 10b that comprises the first, second and third layers 16, 18, 22, respectively.

As shown in Fig. 7, a cross-sectional schematic representation of another example of a fibrous structure in accordance with the present invention comprising a layered fibrous structure

10c is provided. The layered fibrous structure 10c comprises a first layer 26, a second layer 28 and optionally a third layer 30. The first layer 26 comprises a plurality of filaments 12, such as polypropylene filaments, and a plurality of solid additives, such as wood pulp fibers 14. The second layer 28 may comprise any suitable filaments, solid additives and/or polymeric films. In one example, the second layer 28 comprises a plurality of filaments 34. In one example, the filaments 34 comprise a polymer selected from the group consisting of: polysaccharides, polysaccharide derivatives, polyvinylalcohol, polyvinylalcohol derivatives and mixtures thereof.

In another example of a fibrous structure in accordance with the present invention, instead of being layers of fibrous structure 10c, the material forming layers 26, 28 and 30, may be in the form of plies wherein two or more of the plies may be combined to form a fibrous structure. The plies may be bonded together, such as by thermal bonding and/or adhesive bonding, to form a multi-ply fibrous structure.

Another example of a fibrous structure of the present invention in accordance with the present invention is shown in Fig. 8. The fibrous structure 10d may comprise two or more plies, wherein one ply 36 comprises any suitable fibrous structure in accordance with the present invention, for example fibrous structure 10 as shown and described in Figs. 3 and 4 and another ply 38 comprising any suitable fibrous structure, for example a fibrous structure comprising filaments 12, such as polypropylene filaments. The fibrous structure of ply 38 may be in the form of a net and/or mesh and/or other structure that comprises pores that expose one or more portions of the fibrous structure 10d to an external environment and/or at least to liquids that may come into contact, at least initially, with the fibrous structure of ply 38. In addition to ply 38, the fibrous structure 10d may further comprise ply 40. Ply 40 may comprise a fibrous structure comprising filaments 12, such as polypropylene filaments, and may be the same or different from the fibrous structure of ply 38.

Two or more of the plies 36, 38 and 40 may be bonded together, such as by thermal bonding and/or adhesive bonding, to form a multi-ply fibrous structure. After a bonding operation, especially a thermal bonding operation, it may be difficult to distinguish the plies of the fibrous structure 10d and the fibrous structure 10d may visually and/or physically be a similar to a layered fibrous structure in that one would have difficulty separating the once individual plies from each other. In one example, ply 36 may comprise a fibrous structure that exhibits a basis weight of at least about 15 g/m² and/or at least about 20 g/m² and/or at least about 25 g/m² and/or at least about 30 g/m² up to about 120 g/m² and/or 100 g/m² and/or 80 g/m² and/or 60 g/m² and the plies 38 and 42, when present, independently and individually, may comprise

fibrous structures that exhibit basis weights of less than about 10 g/m^2 and/or less than about 7 g/m^2 and/or less than about 5 g/m^2 and/or less than about 3 g/m^2 and/or less than about 2 g/m^2 and/or to about 0 g/m^2 and/or 0.5 g/m^2 .

Plies 38 and 40, when present, may help retain the solid additives, in this case the wood pulp fibers 14, on and/or within the fibrous structure of ply 36 thus reducing lint and/or dust (as compared to a single-ply fibrous structure comprising the fibrous structure of ply 36 without the plies 38 and 40) resulting from the wood pulp fibers 14 becoming free from the fibrous structure of ply 36.

The fibrous structures of the present invention may comprise any suitable amount of filaments and any suitable amount of solid additives. For example, the fibrous structures may comprise from about 10% to about 70% and/or from about 20% to about 60% and/or from about 30% to about 50% by dry weight of the fibrous structure of filaments and from about 90% to about 30% and/or from about 80% to about 40% and/or from about 70% to about 50% by dry weight of the fibrous structure of solid additives, such as wood pulp fibers.

The filaments and solid additives of the present invention may be present in fibrous structures according to the present invention at weight ratios of filaments to solid additives of from at least about 1:1 and/or at least about 1:1.5 and/or at least about 1:2 and/or at least about 1:2.5 and/or at least about 1:3 and/or at least about 1:4 and/or at least about 1:5 and/or at least about 1:7 and/or at least about 1:10.

The fibrous structures of the present invention and/or any sanitary tissue products comprising such fibrous structures may be subjected to any post-processing operations such as embossing operations, printing operations, tuft-generating operations, thermal bonding operations, ultrasonic bonding operations, perforating operations, surface treatment operations such as application of lotions, silicones and/or other materials and mixtures thereof.

Non-limiting examples of suitable polypropylenes for making the filaments of the present invention are commercially available from Lyondell-Basell and Exxon-Mobil.

Any hydrophobic or non-hydrophilic materials within the fibrous structure, such as polypropylene filaments, may be surface treated and/or melt treated with a hydrophilic modifier. Non-limiting examples of surface treating hydrophilic modifiers include surfactants, such as Triton X-100TM. Non-limiting examples of melt treating hydrophilic modifiers that are added to the melt, such as the polypropylene melt, prior to spinning filaments, include hydrophilic modifying melt additives such as VW351 and/or S-1416 commercially available from Polyvel, Inc. and IrgasurfTM commercially available from Ciba. The hydrophilic modifier may be associated with the

hydrophobic or non-hydrophilic material at any suitable level known in the art. In one example, the hydrophilic modifier is associated with the hydrophobic or non-hydrophilic material at a level of less than about 20% and/or less than about 15% and/or less than about 10% and/or less than about 5% and/or less than about 3% to about 0% by dry weight of the hydrophobic or non-hydrophilic material.

The fibrous structures of the present invention may include optional additives, each, when present, at individual levels of from about 0% and/or from about 0.01% and/or from about 0.1% and/or from about 1% and/or from about 2% to about 95% and/or to about 80% and/or to about 50% and/or to about 30% and/or to about 20% by dry weight of the fibrous structure. Non-limiting examples of optional additives include permanent wet strength agents, temporary wet strength agents, dry strength agents such as carboxymethylcellulose and/or starch, softening agents, lint reducing agents, opacity increasing agents, wetting agents, odor absorbing agents, perfumes, temperature indicating agents, color agents, dyes, osmotic materials, microbial growth detection agents, antibacterial agents and mixtures thereof.

The fibrous structure of the present invention may itself be a sanitary tissue product. It may be convolutedly wound about a core to form a roll. It may be combined with one or more other fibrous structures as a ply to form a multi-ply sanitary tissue product. In one example, a co-formed fibrous structure of the present invention may be convolutedly wound about a core to form a roll of co-formed sanitary tissue product. The rolls of sanitary tissue products may also be coreless.

To further illustrate the fibrous structures of the present invention, Table 1 sets forth the average pore volume distributions of known and/or commercially available fibrous structures and a fibrous structure in accordance with the present invention.

Table 1

Pore Radius (μm)	Huggies®	Huggies® Wash Cloth	Duramax™	Concert EBT.055. 1010 TBAL (no filaments)	LBAL-DUNI embossed (no filaments)	Bounty® (no filaments)	Comparative Example	Invention
1	0	0	0	0	0	0	0	0
2.5	19.25	29.6	32.4	33.65	34.4	31.1	15.85	30.05
5	11.65	16.1	17.85	18.1	18.25	17.6	7.95	29.95
10	11.7	12.6	28.5	14.4	14.75	32.8	6.45	21.15
15	7.95	7.05	101.7	8.65	8.5	52.3	3.2	9.4
20	7.15	4.65	62.7	6.45	6.4	36.7	2.45	6.2

30	31.35	6.45	91.55	9.1	9.55	54	3.65	8.65
40	110.4	5.5	82.1	26.3	127.25	47.8	3.4	9.3
50	133.05	6.5	77.35	65.95	71.4	43.6	4.6	66
60	200.1	96.55	70.5	74.7	59.95	38.9	6.55	82.9
70	302.45	144.85	61.65	70.25	69.05	36.3	11.3	77.2
80	336.9	132.35	56.05	102.05	95.05	33.9	63.15	101.65
90	250.9	150.8	49.3	174.05	150.1	33	128	141.1
100	160.15	162.8	48.3	293	232.9	32.2	129.25	223.4
120	172.8	394.1	95.6	693.4	464.15	64.7	306.05	653.2
140	85.1	451.7	89.5	162.55	176.45	68.5	521.95	269.05
160	54	505.45	76.6	19.35	49.6	74.8	613.35	50.35
180	37.3	509.7	63.45	10.15	24.3	78.5	243.3	19.6
200	30.15	450.95	50	8.2	18.55	89.2	69.15	14.45
225	28.2	409.15	51.6	8.5	18.95	134.4	32.55	15.7
250	22.85	245.2	44	7.5	16.25	149.8	20.6	16.4
275	22.15	144.1	40.25	2.7	14.9	157.9	13.75	15
300	18.4	101.3	35.95	10.05	13.75	125.7	7.9	14.55
350	29.95	153.2	60.7	10.9	25.4	145	24.45	24.45
400	24.25	141.7	59.25	9.65	26.65	52.4	17.55	18.25
500	45.6	271.15	266.45	15.75	116.85	56	31.05	30.45
600	34.3	230.95	291.9	14.5	71.3	23.9	27.95	27.25
800	46.65	261.6	162.4	24.3	34.25	34.9	32.6	58.15
1000	38.75	112.55	29.15	24.9	30.35	24.9	25.55	45.75
Total	2273.45	5158.6	2196.75	1919.05	1999.25	1770.8	2373.55	2079.55
91-140 µm	18.39%	19.55%	10.62%	59.87%	43.69%	9.34%	40.33%	55.1%

Method For Making A Fibrous Structure

A non-limiting example of a method for making a fibrous structure according to the present invention is represented in Fig. 9. The method shown in Fig. 9 comprises the step of mixing a plurality of solid additives 14 with a plurality of filaments 12. In one example, the solid additives 14 are wood pulp fibers, such as SSK fibers and/or Eucalyptus fibers, and the filaments 12 are polypropylene filaments. The solid additives 14 may be combined with the filaments 12, such as by being delivered to a stream of filaments 12 from a hammermill 42 via a solid additive spreader 44 to form a mixture of filaments 12 and solid additives 14. The filaments 12 may be created by meltblowing from a meltblow die 46. The mixture of solid additives 14 and filaments 12 are collected on a collection device, such as a belt 48 to form a fibrous structure 50. The collection device may be a patterned and/or molded belt that results in the fibrous structure exhibiting a surface pattern, such as a non-random, repeating pattern of microregions. The molded belt may have a three-dimensional pattern on it that gets imparted to the fibrous structure

50 during the process. For example, the patterned belt 52, as shown in Fig. 10, may comprise a reinforcing structure, such as a fabric 54, upon which a polymer resin 56 is applied in a pattern. The pattern may comprise a continuous or semi-continuous network 58 of the polymer resin 56 within which one or more discrete conduits 60 are arranged.

In one example of the present invention, the fibrous structures are made using a die comprising at least one filament-forming hole, and/or 2 or more and/or 3 or more rows of filament-forming holes from which filaments are spun. At least one row of holes contains 2 or more and/or 3 or more and/or 10 or more filament-forming holes. In addition to the filament-forming holes, the die comprises fluid-releasing holes, such as gas-releasing holes, in one example air-releasing holes, that provide attenuation to the filaments formed from the filament-forming holes. One or more fluid-releasing holes may be associated with a filament-forming hole such that the fluid exiting the fluid-releasing hole is parallel or substantially parallel (rather than angled like a knife-edge die) to an exterior surface of a filament exiting the filament-forming hole. In one example, the fluid exiting the fluid-releasing hole contacts the exterior surface of a filament formed from a filament-forming hole at an angle of less than 30° and/or less than 20° and/or less than 10° and/or less than 5° and/or about 0°. One or more fluid releasing holes may be arranged around a filament-forming hole. In one example, one or more fluid-releasing holes are associated with a single filament-forming hole such that the fluid exiting the one or more fluid releasing holes contacts the exterior surface of a single filament formed from the single filament-forming hole. In one example, the fluid-releasing hole permits a fluid, such as a gas, for example air, to contact the exterior surface of a filament formed from a filament-forming hole rather than contacting an inner surface of a filament, such as what happens when a hollow filament is formed.

In one example, the die comprises a filament-forming hole positioned within a fluid-releasing hole. The fluid-releasing hole 62 may be concentrically or substantially concentrically positioned around a filament-forming hole 64 such as is shown in Fig. 11.

After the fibrous structure 50 has been formed on the collection device, such as a patterned belt, the fibrous structure 50 may be calendered, for example, while the fibrous structure is still on the collection device. In addition, the fibrous structure 50 may be subjected to post-processing operations such as embossing, thermal bonding, tuft-generating operations, moisture-imparting operations, and surface treating operations to form a finished fibrous structure. One example of a surface treating operation that the fibrous structure may be subjected to is the surface application of an elastomeric binder, such as ethylene vinyl acetate (EVA),

latexes, and other elastomeric binders. Such an elastomeric binder may aid in reducing the lint created from the fibrous structure during use by consumers. The elastomeric binder may be applied to one or more surfaces of the fibrous structure in a pattern, especially a non-random, repeating pattern of microregions, or in a manner that covers or substantially covers the entire surface(s) of the fibrous structure.

In one example, the fibrous structure 50 and/or the finished fibrous structure may be combined with one or more other fibrous structures. For example, another fibrous structure, such as a filament-containing fibrous structure, such as a polypropylene filament fibrous structure may be associated with a surface of the fibrous structure 50 and/or the finished fibrous structure. The polypropylene filament fibrous structure may be formed by meltblowing polypropylene filaments (filaments that comprise a second polymer that may be the same or different from the polymer of the filaments in the fibrous structure 50) onto a surface of the fibrous structure 50 and/or finished fibrous structure. In another example, the polypropylene filament fibrous structure may be formed by meltblowing filaments comprising a second polymer that may be the same or different from the polymer of the filaments in the fibrous structure 50 onto a collection device to form the polypropylene filament fibrous structure. The polypropylene filament fibrous structure may then be combined with the fibrous structure 50 or the finished fibrous structure to make a two-ply fibrous structure – three-ply if the fibrous structure 50 or the finished fibrous structure is positioned between two plies of the polypropylene filament fibrous structure like that shown in Fig. 6 for example. The polypropylene filament fibrous structure may be thermally bonded to the fibrous structure 50 or the finished fibrous structure via a thermal bonding operation.

In yet another example, the fibrous structure 50 and/or finished fibrous structure may be combined with a filament-containing fibrous structure such that the filament-containing fibrous structure, such as a polysaccharide filament fibrous structure, such as a starch filament fibrous structure, is positioned between two fibrous structures 50 or two finished fibrous structures like that shown in Fig. 8 for example.

In still another example, two plies of fibrous structure 50 comprising a non-random, repeating pattern of microregions may be associated with one another such that protruding microregions, such as pillows, face inward into the two-ply fibrous structure formed.

The process for making fibrous structure 50 may be close coupled (where the fibrous structure is convolutedly wound into a roll prior to proceeding to a converting operation) or directly coupled (where the fibrous structure is not convolutedly wound into a roll prior to proceeding to a converting operation) with a converting operation to emboss, print, deform,

surface treat, or other post-forming operation known to those in the art. For purposes of the present invention, direct coupling means that the fibrous structure 50 can proceed directly into a converting operation rather than, for example, being convolutedly wound into a roll and then unwound to proceed through a converting operation.

The process of the present invention may include preparing individual rolls of fibrous structure and/or sanitary tissue product comprising such fibrous structure(s) that are suitable for consumer use.

Non-limiting Example of Process for Making a Fibrous Structure of the Present Invention:

A 20%:27.5%:47.5%:5% blend of Lyondell-Basell PH835 polypropylene : Lyondell-Basell Metocene TMMF650W polypropylene : Exxon-Mobil PP3546 polypropylene : Polyvel S-1416 wetting agent is dry blended, to form a melt blend. The melt blend is heated to 475°F through a melt extruder. A 15.5 inch wide Biax TM12 row spinnerette with 192 nozzles per cross-direction inch, commercially available from Biax TMFiberfilm Corporation, is utilized. 40 nozzles per cross-direction inch of the 192 nozzles have a 0.018 inch inside diameter while the remaining nozzles are solid, i.e. there is no opening in the nozzle. Approximately 0.19 grams per hole per minute (ghm) of the melt blend is extruded from the open nozzles to form meltblown filaments from the melt blend. Approximately 375 SCFM of compressed air is heated such that the air exhibits a temperature of 395°F at the spinnerette. Approximately 475 g / minute of Golden Isle TM(from Georgia Pacific) 4825 semi-treated SSK pulp is defibrillated through a hammermill to form SSK wood pulp fibers (solid additive). Air at 85-90°F and 85% relative humidity (RH) is drawn into the hammermill. Approximately 1200 SCFM of air carries the pulp fibers to a solid additive spreader. The solid additive spreader turns the pulp fibers and distributes the pulp fibers in the cross-direction such that the pulp fibers are injected into the meltblown filaments in a perpendicular fashion through a 4 inch x 15 inch cross-direction (CD) slot. A forming box surrounds the area where the meltblown filaments and pulp fibers are commingled. This forming box is designed to reduce the amount of air allowed to enter or escape from this commingling area; however, there is an additional 4 inch x 15 inch spreader opposite the solid additive spreader designed to add cooling air. Approximately 1000 SCFM of air at approximately 80°F is added through this additional spreader. A forming vacuum pulls air through a collection device, such as a patterned belt, thus collecting the commingled meltblown filaments and pulp fibers to form a fibrous structure comprising a pattern of non-random, repeating microregions. The fibrous structure formed by this process comprises about 75% by dry fibrous structure weight of pulp and about 25% by dry fibrous structure weight of meltblown filaments.

Optionally, a meltblown layer of the meltblown filaments can be added to one or both sides of the above formed fibrous structure. This addition of the meltblown layer can help reduce the lint created from the fibrous structure during use by consumers and is preferably performed prior to any thermal bonding operation of the fibrous structure. The meltblown filaments for the exterior layers can be the same or different than the meltblown filaments used on the opposite layer or in the center layer(s).

The fibrous structure may be convolutedly wound to form a roll of fibrous structure. The end edges of the roll of fibrous structure may be contacted with a material to create bond regions.

TEST METHODS

Unless otherwise indicated, all tests described herein including those described under the Definitions section and the following test methods are conducted on samples that have been conditioned in a conditioned room at a temperature of $73^{\circ}\text{F} \pm 4^{\circ}\text{F}$ (about $23^{\circ}\text{C} \pm 2.2^{\circ}\text{C}$) and a relative humidity of $50\% \pm 10\%$ for 2 hours prior to the test. Samples conditioned as described herein are considered dry samples (such as "dry fibrous structures") for purposes of this invention. Further, all tests are conducted in such conditioned room.

Pore Volume Distribution Test Method

Pore Volume Distribution measurements are made on a TRI/Autoporosimeter (TRI/Princeton Inc. of Princeton, NJ). The TRI/Autoporosimeter is an automated computer-controlled instrument for measuring pore volume distributions in porous materials (e.g., the volumes of different size pores within the range from 1 to 1000 μm effective pore radii). Complimentary Automated Instrument Software, Release 2000.1, and Data Treatment Software, Release 2000.1 is used to capture, analyze and output the data. More information on the TRI/Autoporosimeter, its operation and data treatments can be found in *The Journal of Colloid and Interface Science* 162 (1994), pgs 163-170.

As used in this application, determining Pore Volume Distribution involves recording the increment of liquid that enters a porous material as the surrounding air pressure changes. A sample in the test chamber is exposed to precisely controlled changes in air pressure. The size (radius) of the largest pore able to hold liquid is a function of the air pressure. As the air pressure increases (decreases), different size pore groups drain (absorb) liquid. The pore volume of each group is equal to this amount of liquid, as measured by the instrument at the corresponding pressure. The effective radius of a pore is related to the pressure differential by the following relationship.

$$\text{Pressure differential} = [(2) \gamma \cos\theta] / \text{effective radius}$$

where γ = liquid surface tension, and Θ = contact angle.

Typically pores are thought of in terms such as voids, holes or conduits in a porous material. It is important to note that this method uses the above equation to calculate effective pore radii based on the constants and equipment controlled pressures. The above equation assumes uniform cylindrical pores. Usually, the pores in natural and manufactured porous materials are not perfectly cylindrical, nor all uniform. Therefore, the effective radii reported here may not equate exactly to measurements of void dimensions obtained by other methods such as microscopy. However, these measurements do provide an accepted means to characterize relative differences in void structure between materials.

The equipment operates by changing the test chamber air pressure in user-specified increments, either by decreasing pressure (increasing pore size) to absorb liquid, or increasing pressure (decreasing pore size) to drain liquid. The liquid volume absorbed at each pressure increment is the cumulative volume for the group of all pores between the preceding pressure setting and the current setting.

In this application of the TRI/Autoporosimeter, the liquid is a 0.2 weight % solution of octylphenoxy polyethoxy ethanol (Triton X-100 from Union Carbide Chemical and Plastics Co. of Danbury, CT.) in distilled water. The instrument calculation constants are as follows: ρ (density) = 1 g/cm³; γ (surface tension) = 31 dynes/cm; $\cos\Theta = 1$. A 0.22 μ m Millipore Glass Filter (Millipore Corporation of Bedford, MA; Catalog # GSWP09025) is employed on the test chamber's porous plate. A plexiglass plate weighing about 24 g (supplied with the instrument) is placed on the sample to ensure the sample rests flat on the Millipore Filter. No additional weight is placed on the sample.

The remaining user specified inputs are described below. The sequence of pore sizes (pressures) for this application is as follows (effective pore radius in μ m): 1, 2.5, 5, 10, 15, 20, 30, 40, 50, 60, 70, 80, 90, 100, 120, 140, 160, 180, 200, 225, 250, 275, 300, 350, 400, 500, 600, 800, 1000. This sequence starts with the sample dry, saturates it as the pore settings increase (typically referred to with respect to the procedure and instrument as the 1st absorption).

In addition to the test materials, a blank condition (no sample between plexiglass plate and Millipore Filter) is run to account for any surface and/or edge effects within the chamber. Any pore volume measured for this blank run is subtracted from the applicable pore grouping of the test sample. This data treatment can be accomplished manually or with the available TRI/Autoporosimeter Data Treatment Software, Release 2000.1.

Percent (%) Total Pore Volume is a percentage calculated by taking the volume of fluid in the specific pore radii range divided by the Total Pore Volume. The TRI/Autoporosimeter outputs the volume of fluid within a range of pore radii. The first data obtained is for the "2.5 micron" pore radii which includes fluid absorbed between the pore sizes of 1 to 2.5 micron radius. The next data obtained is for "5 micron" pore radii, which includes fluid absorbed between the 2.5micron and 5 micron radii, and so on. Following this logic, to obtain the volume held within the range of 91-140 micron radii, one would sum the volumes obtained in the range titled "100 micron", "110 micron", "120 micron", "130 micron", and finally the "140 micron" pore radii ranges. For example, % Total Pore Volume 91-140 micron pore radii = (volume of fluid between 91-140 micron pore radii) / Total Pore Volume

The dimensions and values disclosed herein are not to be understood as being strictly limited to the exact numerical values recited. Instead, unless otherwise specified, each such dimension is intended to mean both the recited value and a functionally equivalent range surrounding that value. For example, a dimension disclosed as "40 mm" is intended to mean "about 40 mm."

All documents cited in the Detailed Description of the Invention are not to be construed as an admission that it is prior art with respect to the present invention. To the extent that any meaning or definition of a term in this document conflicts with any meaning or definition of the same term in a document cited herein, the meaning or definition assigned to that term in this document shall govern.

While particular embodiments of the present invention have been illustrated and described, it would be obvious to those skilled in the art that various other changes and modifications can be made without departing from the invention described herein.

What is claimed is:

1. A fibrous structure comprising a calendered fibrous structure ply comprising from 10% to 70% by dry weight of the fibrous structure of a plurality of first filaments and from 30% to 90% by dry weight of the fibrous structure of a plurality of solid additives, wherein at least one of the solid additives comprises a wood pulp fiber that is randomly dispersed throughout the calendered fibrous structure ply such that the calendered fibrous structure ply exhibits a pore volume distribution such that at least 43% of the total pore volume present in the calendered fibrous structure ply exists in pores of radii of from 91 μm to 140 μm as measured according to the Pore Volume Distribution Test Method and wherein the fibrous structure comprises a surface comprising a layer of a plurality of second filaments present at a basis weight of greater than 0 to less than 10 g/m^2 .
2. The fibrous structure according to Claim 1 wherein the calendered fibrous structure ply exhibits a pore volume distribution such that at least 45% of the total pore volume present in the fibrous structure ply exists in pores of radii of from 91 μm to 140 μm as measured according to the Pore Volume Distribution Test Method.
3. The fibrous structure according to Claim 1 or 2 wherein the plurality of first filaments comprises a thermoplastic polymer.
4. The fibrous structure according to Claim 3 wherein the thermoplastic polymer is polypropylene, polyethylene, polyester, polylactic acid, polyhydroxyalkanoate, polyvinyl alcohol, polycaprolactone or mixtures thereof.
5. The fibrous structure according to Claim 1 or 2 wherein the plurality of first filaments comprises a natural polymer.

6. The fibrous structure according to Claim 1 or 2 wherein the plurality of first filaments comprises a polymer, wherein the polymer is starch, cellulose, hemicellulose or mixtures thereof.
7. The fibrous structure according to any one of Claims 1 to 6 wherein the plurality of second filaments comprises a thermoplastic polymer.
8. The fibrous structure according to any one of Claims 1 to 7 wherein the calendered fibrous structure ply comprises at least a bi-modal pore volume distribution as measured according to the Pore Volume Distribution Test Method.
9. The fibrous structure according to Claim 8 wherein at least 2% of the total pore volume present in the calendered fibrous structure ply exists in pores of radii of less than 100 μm as measured according to the Pore Volume Distribution Test Method.
10. The fibrous structure according to Claim 9 wherein at least 2% of the total pore volume present in the calendered fibrous structure ply exists in pores of radii of less than 80 μm as measured according to the Pore Volume Distribution Test Method.
11. The fibrous structure according to Claim 10 wherein at least 2% of the total pore volume present in the calendered fibrous structure ply exists in pores of radii of less than 50 μm as measured according to the Pore Volume Distribution Test Method.
12. The fibrous structure according to any one of Claims 1 to 11 wherein the wood pulp fiber is Southern Softwood Kraft pulp fiber, Northern Softwood Kraft pulp fiber, Eucalyptus pulp fiber, or Acacia pulp fibers.

13. The fibrous structure according to any of Claims 1 to 12 wherein the plurality of second filaments comprises a thermoplastic polymer is polypropylene, polyethylene, polyester, polylactic acid, polyhydroxyalkanoate, polyvinyl alcohol, polycaprolactone or mixtures thereof.

14. A sanitary tissue product comprising the fibrous structure according to any one of Claims 1 to 13.

15. The sanitary tissue product according to Claim 14 wherein the sanitary tissue product is a paper towel, bath tissue, facial tissue, napkin, baby wipe, adult wipe, wet wipe, cleaning wipe, polishing wipe, cosmetic wipe, car care wipe, wipe that comprises an active agent for performing a particular function, or cleaning substrate for use with implements.

16. A method for making the fibrous structure comprising a calendered fibrous structure ply according to Claim 1 wherein the method comprises the steps of combining from 10% to 70% by dry weight of the fibrous structure of a plurality of first filaments and from 30% to 90% by dry weight of the fibrous structure of a plurality of solid additives, wherein at least one of the solid additives comprises a wood pulp fiber, on a patterned belt to form a fibrous structure ply and then calendering the fibrous structure ply to form a calendered fibrous structure ply.

17. The method according to Claim 16 wherein the plurality of first filaments comprises a thermoplastic polymer.

18. The method according to Claim 16 or 17 wherein the plurality of first filaments comprises polypropylene filaments.

19. The method according to Claim 16 wherein the plurality of first filaments comprises a natural polymer.

20. The method according to any one of Claims 16 to 19 wherein the wood pulp fiber is Southern Softwood Kraft pulp fiber, Northern Softwood Kraft pulp fiber, Eucalyptus pulp fiber, or Acacia pulp fibers.

1/8




Fig. 1

2/8




Fig. 2

3/8




Fig. 3




Fig. 4

4/8




Fig. 5

5/8




Fig. 6




Fig. 7




Fig. 8

6/8




Fig. 9

7/8




Fig. 10

8/8




Fig. 11

