

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
2 April 2009 (02.04.2009)

PCT

(10) International Publication Number
WO 2009/042841 A2

- (51) International Patent Classification:
A61L 17/04 (2006.01) A61B 17/04 (2006.01)
- (21) International Application Number:
PCT/US2008/077813
- (22) International Filing Date:
26 September 2008 (26.09.2008)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/975,758 27 September 2007 (27.09.2007) US
- (71) Applicant (for all designated States except US): AN-GIOTECH PHARMACEUTICALS, INC. [CA/CA]; 1618 Station Street, Vancouver, British Columbia V6A 1B6 (CA).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): HERRMANN, Robert, A. [US/CA]; 1508-1082 Seymour St., Vancouver, British Columbia V6B 1X9 (CA). GORALTCHOUK, Alexei [CA/CA]; #314 8880 Jones Road, Richmond, British Columbia V6Y 3Z1 (CA). DRUBETSKY, Lev [CA/CA]; 2948 Waterford Pl., Coquitlam, British Columbia V5E 2S9 (CA).
- (74) Agents: PHINNEY, David, D. et al.; P.O. Box 2840, Suite 201, 101 West North Bend Way, North Bend, Washington 98045 (US).

- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))
- of inventorship (Rule 4.17(iv))

Published:

- without international search report and to be republished upon receipt of that report

(54) Title: SELF-RETAINING SUTURES INCLUDING TISSUE RETAINERS HAVING IMPROVED STRENGTH




Fig. 1A

(57) Abstract: An embodiment of a suture for use in a surgical procedure applied to tissue comprises an elongated body having a first end and a second end, and a plurality of retainers arranged along a portion of the elongated body. The retainers substantially yield to motion of the elongated body within the tissue when the elongated body is drawn at the first end and resist motion of the elongated within the tissue when the elongated body is drawn at the second end. The retainers include an upper surface and a lower surface, the upper surface extending from a periphery of the elongated body and the lower surface having at least two facets.

WO 2009/042841 A2

SELF-RETAINING SUTURES INCLUDING TISSUE RETAINERS HAVING IMPROVED STRENGTH

TECHNICAL FIELD

[0001] The present invention relates generally to methods and devices for joining or positioning bodily tissue in surgical and cosmetic applications.

BACKGROUND

[0002] Sutures are commonly used for closing or binding together wounds in human or animal tissue, such as skin, muscles, tendons, internal organs, nerves, and blood vessels. Sutures can be formed from non-absorbable material such as silk, nylon, polypropylene, or cotton, or alternatively sutures can be formed from bio-absorbable material such as, but not limited to, homopolymers and/or copolymers of glycolide, lactide, p-dioxanone and ϵ -caprolactone.

[0003] A suture can include retainers protruding from the suture periphery and arranged to allow passage of the self-retaining suture when drawn in one direction (with respect to the direction of protrusion of the retainer) through tissue but resist movement of the self-retaining suture when drawn in the opposite direction. Retainers can reduce slippage of the suture at least in a direction along the suture and can optionally obviate knotting of the suture.

[0004] Single-directional self-retaining sutures can include an end that is pointed to allow penetration and passage through tissue when drawn by the end and an opposite end that includes an anchor for engaging tissue at the initial insertion point to limit movement of the suture. Alternatively, bi-directional self-retaining sutures can include retainers grouped and extending in one direction along one portion of the suture and opposing retainers grouped and extending in an opposing direction along another portion of the suture. When implanted so that both groups of retainers are engaging tissue, the retainers can resist movement of the suture through tissue in either direction.

[0005] A surgeon may use a surgical needle with an attached suture (which can be a smooth monofilament or can be a multi-filament) to pierce the tissue alternately on opposing faces of a wound to sew the wound closed. Techniques for placement of self-retaining sutures in tissue to close or bind together wounds can include threading the self-retaining suture in straight-line patterns such as zig-zag, and curvilinear patterns such as alpha, sinusoidal, and corkscrew. A surgeon may also use self-retaining sutures to position and support tissue where there is no wound in procedures such as cosmetic surgery of the face, neck, abdominal or thoracic region among others.

BRIEF DESCRIPTION OF THE DRAWINGS

[0006] Further details of the present invention are explained with the help of the attached drawings in which:

[0007] FIG. 1A is a side view of a suture in accordance with the prior art including a retainer protruding generally at an angle in a direction along an axis of the suture.

[0008] FIG. 1B is a perspective view of the suture of FIG. 1A.

[0009] FIG. 2A is a side view of an embodiment of a suture including a retainer wherein an apex of a cut forming the retainer is enlarged to distribute applied stress applied across a larger surface, reducing concentration of the stress.

[0010] FIG. 2B is a perspective view of the suture of FIG. 1A.

[0011] FIG. 3 is a side view of an improperly formed retainer.

[0012] FIG. 4A is a side view of an embodiment of a suture including a retainer wherein the retainer has a lower surface having two converging faces.

[0013] FIG. 4B is a front view of the embodiment of FIG. 4A.

[0014] FIG. 4C is a front view of an alternative embodiment of a suture including a retainer wherein the retainer has a lower surface having two converging faces.

[0015] FIG. 5A top perspective view of a blade configuration for forming the retainer of the suture of FIGS. 4A and 4B.

[0016] FIG. 5B top perspective view of a blade configuration for forming the retainer of the suture of FIG. 4C.

[0017] FIG. 6A is a side view of an alternative embodiment of a suture including a retainer with material added to a surface of the retainer.

[0018] FIG. 6B is a top view of the suture of FIG. 6A including a retainer with material added to a surface of the retainer.

[0019] FIG. 7A is a side view of a suture including a plurality of retainers protruding from approximately the same tangent along a periphery of the suture, and spaced so that the retainers overlap a preceding retainer or are overlapped by a subsequent retainer along the suture.

[0020] FIG. 7B is a side view of a suture including a pair of retainers protruding from approximately the same tangent along a periphery of the suture. The pair of retainers is spaced a distance along the suture.

[0021] FIG. 7C is an exploded diagram illustrating relative size of tissue and related structures.

DETAILED DESCRIPTION

[0022] Self-retaining sutures used in surgical techniques such as wound closure and tissue positioning can provide improved results where the retainers of the sutures provide increased resistance to movement opposite the path of insertion (also referred to hereinafter as “pull-out strength”). Pull-out strength can vary with factors such as retainer geometry, relative positioning of the retainers along the suture, the type of tissue into which the suture is implanted, the surgical or cosmetic technique applied for implantation of the suture, the strength of the core suture, and application for which the suture is used. For example, suture performance may be identified with reference to tissue type, with different sutures being qualified for use in surgical procedures targeting specific tissue. Different tissues will accept favorably different configurations, spacing, and geometries of the retainers. Suturing muscle in an abdomen, for example, can be substantially different from sewing fatty tissue or skin tissue. Sutures can be labeled to identify appropriate procedures and tissue.

[0023] Self-retaining suture refers to a suture that may not require a knot in order to maintain its position into which it is deployed during a surgical procedure. Such self-retaining sutures generally include a retaining element or tissue retainer.

[0024] Tissue retainer refers to a suture element having a retainer body projecting from the suture body and a retainer end adapted to penetrate tissue. Each retainer is adapted to resist movement of the suture in a direction other than the direction in which the suture is deployed into the tissue by the surgeon, by being oriented to substantially face the deployment direction (i.e. the retainers lie flat when pulled in the deployment direction; and open or “fan out” when pulled in a direction contrary to the deployment direction). As the tissue-penetrating end of each retainer faces away from the deployment direction when moving through tissue during deployment, the tissue retainers should generally avoid catching or grabbing tissue during this phase. Once the self-retaining suture has been deployed, a force exerted in another direction (often substantially opposite to the deployment direction) causes the retainers to be displaced from their deployment positions (i.e. resting substantially along the suture body), forces the retainer ends to open (or “fan out”) from the suture body in a manner that catches and penetrates into the surrounding tissue, and results in tissue being caught between the retainer and the suture body; thereby “anchoring” or affixing the self retaining suture in place. By way of example only, tissue retainer or retainers can include hooks, projections, barbs, darts, extensions, bulges, anchors, protuberances, spurs, bumps, points, cogs, tissue engagers, tractions means, surface roughness, surface irregularities, surface defects, edges, facets and the like.

[0025] FIG. 1A is a side view and FIG. 1B is a perspective view of a suture 100 in accordance with the prior art including a retainer 102 protruding from a periphery of the suture 100. Retainers can have myriad geometric shapes, for example pyramidal and conical. The retainer 102 is formed when a cutting edge (not shown) is brought into contact with the suture 100 so that the cutting edge 102 penetrates the periphery of the suture 100. The cutting edge forms a

wedge cut 106 having an apex 104 at a termination point of the cutting edge's penetration. The retainer 102 is urged apart from the suture 100 so that the retainer 102 is gapped to form a retainer channel opening x from the periphery of the suture 100 from which the retainer 102 is separated. The apex 104 likely includes a small radius of curvature defined largely by a rounding of the cutting edge. For example, the cutting edge may be a knife blade including rounding inherent in a structure subjected to abrasion forces, or for example the cutting edge may be a wire having a circular cross-section with a diameter. It can be desirable for the cutting edge to have an extremely small radius of curvature (i.e., to be as sharp as practicable) so that the periphery of the suture is penetrated cleanly. The extremely small rounding of the cutting edge results in a sharp apex 104, which produces an unfavorably high stress concentration.

[0026] In a common surgical or cosmetic procedure, the suture of FIGS. 1A and 1B may be threaded or otherwise inserted into tissue and drawn in the direction of a first end 108. The force of the tissue pressing against the suture 100 causes the retainer 102 to substantially collapse and yield to movement of the suture through the tissue. If the suture 100 is drawn in the direction of a second, opposite end 110, the edge of the retainer 102 grabs the tissue and resists movement. Additional force applied to the suture 100 can increase the retainer channel opening x , causing a high stress concentration at the apex 104. This results in an increased probability of fracture initiation and propagation at the apex resulting in suture failure.

[0027] Referring to FIGS. 2A and 2B, an embodiment of a self-retaining suture 200 in accordance with the present invention can include a retainer 202 formed by a cut 206 with an apex 204 radius of curvature larger than a radius of curvature of the cutting blade (not shown). In a preferred embodiment, the radius of curvature of the apex 204 can range from 0.1 to 0.25 times the retainer channel opening x , although in other embodiments the radius of curvature of the apex 204 can be smaller than $0.1x$ or larger than $0.25x$ (e.g., $0.5x$). Stress reduction at the apex of the cut can be achieved by increasing a radius of curvature at the apex 204 of the cut 206. Embodiments of methods

in accordance with the present invention can be applied to form sutures within the periphery of the suture have an apex larger than the cutting blade. Alternatively, the apex geometry can be non-circular (i.e. the groove terminating in a flat face, a multi-faced facet, or any other given geometric shape or combination thereof).

[0028] In an embodiment of a method, a heated cutting edge such as a blade or wire can penetrate the periphery of the suture, heating the suture material as the knife cuts. The temperature and contact time can be varied to achieve the most desirable curvature of the apex. Preferably, the cutting edge can be heated to a temperature between the melting temperature of the suture material and the decomposition temperature of the suture material. For example, polyethylene terephthalate can have a melting temperature of about 260°C and a decomposition temperature of about 350°C, some polyglycolic acid homopolymers can have a melting temperature of about 180°C and a decomposition temperature of about 225°C, some types of nylon can have a melting temperature of about 250°C and a decomposition temperature of about 375°C, and polydioxanone can have a melting temperature of about 90°C and a decomposition temperature of about 175°C. It should be noted that these temperature characteristics are exemplary, and melting and decomposition temperatures may vary within a class of materials. For example, nylon melting and decomposition temperatures can vary substantially based on the chemical composition.

[0029] In an alternative embodiment of a method of increasing the radius of curvature of the apex, a first cutting edge can form the retainer (and cut), and a second heated edge or blunt heated dye can be subsequently positioned within the cut. A still further embodiment of a method of increasing the radius of curvature of the apex can comprise a two-step cut, whereby a first cutting edge (e.g., a knife blade or wire) having an edge with a first radius of curvature penetrates the periphery of the suture to cause a cut, followed by a second cutting edge having an edge with a second, larger radius of curvature to widen the apex of the cut. The temperature, radius of curvature of the dye, pressure

applied during forming and contact time can be varied to achieve the most desirable curvature.

[0030] A common technique for forming retainers on sutures includes feeding or drawing the suture across a pulley (also called an anvil). As the suture twists, a cutting edge slices across the suture, forming retainers. Twisting the suture may or may not affect the mechanical properties of the suture along an unaltered periphery of the suture and/or at the retainer. In an alternative embodiment, a method of forming a suture including retainers having a cut with a radius of curvature larger than a cutting edge can include feeding or drawing a suture from a feed spool to a take-up spool that are spinning at a matched angular velocity. A cutting edge is heated to a temperature sufficient to melt a material with which the suture is formed, and the cutting edge is rotated across the surface of the suture to form the retainers. The cutting edge can be heated by any known technique for heating small precision tools, to a temperature sufficient to cause a desired melting of the suture material without causing undesired stretching, mechanical deformation or excessive diameter reduction. For example, a conductive blade or wire can be heated by resistive heating to a temperature of approximately 200 degrees C. Alternatively, where achievable, one or both of the cutting edge and the suture can be heated by a laser, directed gas, flame or torch so that when the cutting edge penetrates the suture to form a retainer, a local temperature near the apex of the cut is sufficient to achieve a desired geometric result. Where a laser is used to heat the suture, a polymer or copolymer comprising the suture can be doped to absorb the wavelengths of the laser. The area to which the heating source is directed can be as small as 10 nanometers across.

[0031] Referring to FIG. 3, a cut 304 caused by a cutting edge with intent to form a retainer is shown that is generally non-protruding from the periphery of the suture 300. Such a result can occur where a material has insufficient plasticity and is predominantly deformed in the elastic region during retainer cutting. A retainer formed in such a material will tend to lay flat rather than

“stand up” by protruding from the periphery. A retainer that fails to protrude from the periphery is less likely to catch the tissue in which it is arranged. Mechanical properties of the specific suture material are considered in order to form a retainer geometry having preferred characteristics. A retainer formed in a material having undesirably high elasticity can have an improved protrusion from the periphery of the suture by annealing the local suture material at least at the base of a retainer site. Annealing the base of the retainer causes polymer chains to realign themselves and relieves internal stresses in a polymer. During cutting, these residual stresses may cause the retainers to lay flat. Relieving the residual stresses at the base of the retainer by annealing can allow the retainers to protrude from the periphery of the suture.

[0032] To anneal a polymer, the polymer is heated to a temperature above some crystallization temperature for an amount of time to change its microstructure, and then cooled at a given rate to retain or obtain a different microstructure. For example, the crystallization temperature for polydioxanone is about 40°C, while a crystallization temperature for a copolymer of glycolide ϵ -caprolactone in a 72/28 ratio is about 75°C. Sutures are typically formed from extruded polymer and are annealed after extrusion to relieve some of the alignment of polymer chains, to recover some elongation, and to drive out residual solvents. The sutures can subsequently be heated in an oven over a period of time to sterilize the sutures. Some annealing can occur during sterilization; although where sutures are sterilized using techniques employing relatively low temperatures (such as sterilization by ethylene oxide) the annealing is typically not effective in reducing internal stresses. The semi-crystalline structure that results from processing provides a suture with mixed properties including high yield strength and acceptable malleability.

[0033] In a preferred embodiment, annealing of the cut retainer is achieved by local heating of the retainer at the base of the retainer while the retainer is protruding to a generally desired degree. Local heating of the retainer can be achieved (as described above with reference to increasing a radius of curvature of the apex) by heating the cutting edge to a sufficient temperature. As

mentioned above, a cutting edge can be heated by resistive heating, or by other conductive or convective means. Alternatively, the retainer can be heated by heated gas (such as hot nitrogen gas), a flame, a torch or some other heat source. It is proposed that heating with a cutting edge at a sufficient temperature (e.g., 200 degrees C) for 4-5 milliseconds, and cooling by ambient temperature, can result in a sufficiently protruding retainer. Alternatively, the retainer can be actively cooled. For example, a Peltier device is a device for electrically controlling temperature that can be miniaturized to suit small features.

[0034] Referring to FIGS. 4A and 4B, an alternative embodiment of a self-retaining suture 400 in accordance with the present invention can include a retainer 402 with an upper surface 412 extending from a periphery 410 of the elongated body and a lower surface 414 having at least two facets 416. As seen in the front view of FIG. 4B, the retainer can have a roughly pie-slice (i.e., wedge) shape. The increased cross-section moment of inertia (also known as the second moment of area) of the retainer improves strength, and can improve resistance to the tendency of a retainer to fold back on itself and yield to movement of the suture through the tissue, as described above. This retainer further reduces stress concentrations along the lower surface of the retainer and the suture when compared with the retainers of FIG. 1A. The retainer need not be shaped as a perfect wedge, but rather preferably has at least two facets to improve resistance to back bending. Thus, for example in FIGS. 4C and 5B, a suture 600 is shown having a retainer 602 having a roughly trapezoidal shape, with three facets 616.

[0035] Referring to FIG. 5A, an embodiment of a method of forming a retainer 402 in a suture 400 such as shown in FIGS. 4A and 4B is illustrated. A V-shape cutting edge 420 can be formed arranging two blades 422,424 in proximity to form a desired cutting angle α and resembling a V. Preferably, the blades 422,424 can be placed close to each other at a cutting angle α of 90°, although the blades 422,424 can be arranged to form an obtuse or acute angle where desired. The cutting edge 420 can optionally be heated to provide local

heating to the base of the retainer 402 while cutting the suture 400, thereby annealing the base of the retainer 402 and/or increasing a radius of curvature at apex 404 or the interface of the lower surface 414 of the retainer 402 and the suture 400. In a preferred embodiment, the cutting edge 420 can comprise sapphire blades. Sapphire blades are ceramic blades typically having an edge radius one or two magnitudes lower than an edge radius of a steel blade. Further, sapphire blades generally maintain their mechanical characteristics over the temperature ranges desirable for annealing polymer and co-polymer materials. Maintaining mechanical characteristics (i.e., geometry of a cut produced) can be desired where the retainers are extremely small and therefore sensitive to small changes. Further, sapphire blades are more abrasion resistant than, for example, typical steel blades, providing more repeatable results over long term use. Further, sapphire blades can be sharpened more effectively than steel blades. In another embodiment of this invention the V-shaped blade can have any of its surfaces be convex or concave to allow for the selection of an appropriate final retainer design, either maximizing the moment of inertia of the retainer or the remaining cross sectional area of the suture.

[0036] In an embodiment, the suture 400 can be spooled or otherwise fed or drawn in a direction z after extrusion at a generally constant speed, in a non-twisting path. For manufacturing a one-direction retainer suture, a cutting edge 420 can be arranged in each of four quadrants of a circle. The cutting edge 420 can comprise the sapphire blades that oscillate in a direction z so that the cutting edge 420 alternately penetrates the suture 420 and pulls away from a cut. As mentioned, the cutting edge 420 is heated to both cut and anneal the retainer 402 simultaneously, causing the retainer 402 to protrude from the periphery of the suture 400. The cutting edge can be oscillated by a cam device, for example.

[0037] To heat the cutting edge 420, the sapphire blades can be mounted or otherwise place in conductive communication with a copper heating plate 430. The copper plate 430 can heat the cutting edge 420 through conduction to a

temperature above the crystallization temperature of the suture material. For example, where the suture material is a copolymer of glycolide ϵ -caprolactone the cutting edge can be heated to about 200°C. The temperature of the cutting edge can be maintained in a temperature range to provide satisfactory results. The cutting edge 420 is generally in conductive proximity to the retainer 402 for generally from four to five milliseconds. In this embodiment, heating the retainer at 200°C for four to five milliseconds is sufficient to anneal the base of the retainer so that the retainer protrudes from the periphery of the suture. It may be desirable to cause sufficient contact to melt the suture at the apex, thereby increasing a radius of curvature of the apex. The retainers are cooled by the ambient conditions of the environment (generally room temperature) or through directed cooling to provide a desired degree of strand alignment (crystallinity) in the material. Alternatively, the sapphire blades can be heated by a laser beam directed through the sapphire blades. An efficiency of this technique can depend on the absorption of the suture material.

[0038] Referring to FIG. 5B, a cutting edge 620 includes two sapphire blades 624 having some finite distance between the cutting surfaces, resulting in a suture 600 having a retainer 602 resembling the retainer 602 of FIG. 4B. Further, an alternative heating plate 630 is shown contacting the surface of the blades 624 rather than contacting the back edge of the blades 624.

[0039] For manufacturing a two-direction retainer suture, a cutting edge can be arranged in each of four quadrants of a circle in each of two directions of protrusion/penetration, resulting in eight cutting edges. The cutting edge can comprise the sapphire blades that oscillate so that the cutting edge alternately penetrates the suture and pulls away from the cut. As mentioned, the cutting edge is optionally heated to both cut and anneal the retainer simultaneously, causing the retainer to protrude from the periphery of the suture.

[0040] In other embodiments of methods of forming retainers in sutures in accordance with the present invention, other retainer arrangements can be produced. For example, a cutting edge can be arranged in each of three zones to form retainers extending from three circumferential locations along the

suture. Alternatively, one or more cutting edges can be rotated so that the retainers are arranged in a helical fashion along the suture. Retainer patterns can be formed to suit a surgical or cosmetic procedure or application, and the properties of the material at the location of the procedure or application.

[0041] Referring to FIGS. 6A and 6B, a still further embodiment of a self-retaining suture 500 in accordance with the present invention can include a retainer 502 having supplementary material 540 on an upper surface 512 of the retainer 502. The supplementary material 540 can increase the mass of the retainer 502 to improve strength and improve resistance to the tendency of the retainer 502 to fold back on itself and yield to movement of the suture 500 through the tissue, as described above. The supplementary material 540 can comprise a polymer or copolymer that is the same material used to form the suture 502, or a polymer or copolymer material different from the material used to form the suture 500. Alternatively, the supplementary material 540 can be some other material (preferably biocompatible with the tissue in which it is implanted) that can be made to adhere to the upper surface 512 of the retainer 500. Such materials can include metals, ceramics, polymers, composites, or a combination thereof. Preferably, the supplementary material can comprise a material that is stiffer and stronger than the material with which the suture is formed (i.e., the material can have an increased Young's modulus and/or an increased yield strength and ultimate tensile strength). The supplementary material 540 can be formed or deposited before the cutting edge forms the retainer 502 or alternatively the supplementary material 540 can be formed subsequent to forming the protruding retainer 502; however, the supplementary material 540 is generally confined to the surface of the retainer 502. Preferably the supplementary material 540 increases a mean thickness of the retainer up to twice the thickness of the retainer without the supplementary material.

[0042] In an embodiment, a printer can be used to precisely deposit the supplementary material 540 on the location where the retainer 502 is or will be formed. The printer can be, for example, a dot matrix style printer having a wire or pin that runs back and forth along the suture and prints by impact, striking

the location where the retainer is or will be formed to cause the supplementary material to be deposited. Alternatively, some other printing technique can be applied, such as techniques resembling inkjet printing techniques. In still other embodiments, the supplementary material can be deposited or formed using some technique other than printing, such as brush coating, spray coating, selective dip coating, curtain coating, etc.

[0043] It is noted that embodiments of sutures in accordance with the present invention can further be impregnated, coated, or otherwise associated with medicine, hormones, drugs, etc., to deliver the associated material to the surgical location. Such associated treatments can be released as the suture material is absorbed into the body. For example, polydioxanone (specifically poly(p-dioxanone)) is a biopolymer that loses most of its strength within six to eight weeks and begins to absorb in about three to four months, and is therefore a longer-term degradable. Polyglycolide and ϵ -caprolactone, which are degraded primarily by hydrolysis, dissolve generally in a shorter timeframe than polydioxanone. In such embodiments, the associated material can assist in healing wounds closed with the sutures, or alternatively, the suture itself can serve primarily as a vehicle for delivering the associated material over a period of bio-absorption.

[0044] FIG. 7A is a side view of a suture 600 including a plurality of retainers 602 protruding from approximately the same tangent along a periphery of the suture 600, and spaced so that the retainers overlap a preceding retainer 602 or overlapped by a subsequent retainer 602 along the suture 600. FIG. 7B is a side view of a suture 700 including a pair of retainers 702 protruding from approximately the same position along the circumference of the suture, the pair of retainers 702 spaced a distance, L , along the suture 700. As the retainers 700 are arranged closer together (i.e., L is reduced) so that the retainers approach a point of overlapping (as shown in FIG. 7A), the target location of the surgical or cosmetic procedure can begin to "see" the retainers as a continuous surface, so that the retainers fail to grab or interfere with suture movement through the target location in a direction opposite the direction of insertion. The

degree of overlap or proximity that results in undesirable retainer performance can vary depending on tissue type. Referring to FIG. 7C, for example, when retainers grab or interfere with suture movement through muscle, the retainer commonly grabs or interferes with bundles of muscle, rather than microfibers. On the other hand, when retainers grab or interfere with suture movement through collagen, the retainers typically grab or interfere with collagen fibers (collagen fibrils are tropocollagens packed into an organized overlapping bundle, while collagen fibers are bundles of fibrils). Collagen fibers can have diameters approaching 10 μm . An acceptable proximity or overlap of retainers can generally be proportional to the size of the structure in which the retainers are placed, so that closely arranged retainers are generally acceptable for tissue and structure comprised of microfibers or other small structures, for example. Generally, longer spacing between retainers (i.e., where distance L is large) is appropriate for tissues with relatively larger structures that can support the retainer. In addition, the distance between retainers L can be a function of the strength of the tissue. Overall, a stronger tissue can accommodate a larger retainer distance L and a weaker tissue can accommodate a shorter retainer distance L. Another way to view the dependence of the distance L on the tissue is that a length of tissue equal to L resists the hold of a single retainer. Failure can occur either if the retainer or the tissue opposing the retainer fails. If the distance between retainers L is increasingly small the force which the tissue can withstand also becomes small, whereas if the distance between retainers L is increasingly large the force that the tissue can withstand is excessively large. An equilibrium case L would be such that the force that the tissue (length L) can withstand is equal to the force it takes to bend back or break off the retainer. This distance L is a function of the type of tissue where the suture is used. As such, this translates into the amount of retainers per length of suture being optimized for each particular type of tissue.

[0045] The foregoing description of the present invention has been presented for purposes of illustration and description. It is not intended to be exhaustive or to limit the invention to the precise forms disclosed. Many

modifications and variations will be apparent to practitioners skilled in this art. The embodiments were chosen and described in order to best explain the principles of the invention and its practical application, thereby enabling others skilled in the art to understand the invention for various embodiments and with various modifications as are suited to the particular use contemplated. It is intended that the scope of the invention be defined by the following claims and their equivalents.

Claims:

1. A suture for use in a procedure applied to tissue comprising:
an elongated body having a first end and a second end; and
a plurality of retainers arranged along a portion of the elongated body;
wherein the retainers substantially yield to motion of the elongated body within the tissue when the elongated body is drawn in a first direction and resist motion of the elongated within the tissue when the elongated body is drawn in a second direction opposite the first direction; and
wherein the retainers include an upper surface and a lower surface, the upper surface extending from a periphery of the elongated body and the lower surface having at least two facets.
2. The suture of claim 1, wherein one or both of the elongated body and the plurality of retainers includes an associated material to be delivered to the tissue.
3. The suture of claim 2, wherein the associated material is one or more of a hormone, a drug, and medicine.
4. The suture of claim 1, wherein the plurality of retainers is a first set and the portion of the elongated body is a first portion; and further comprising:
a second set including a plurality of retainers arranged along a second portion of the elongated body;
wherein the retainers substantially yield to motion of the elongated body within the tissue when the elongated body is drawn at the second end and resist motion of the elongated within the tissue when the elongated body is drawn at the first end; and
wherein the retainers of the second set include an upper surface and a lower surface, the upper surface extending from a periphery of the elongated body and the lower surface having at least two facets.

5. A method of forming one or more retainers in a suture having an elongated body with a first end and a second end for use in a surgical procedure applied to tissue comprising:

urging the elongated body;

oscillating a cutting edge so that the cutting edge alternately penetrates the elongated body and exits the elongated body, wherein the cutting edge includes a first blade and a second blade arranged to form an angle;

wherein the cutting edge forms one or more retainers so that the one or more retainers substantially yield to motion of the elongated body within the tissue when the elongated body is drawn at the first end and resist motion of the elongated within the tissue when the elongated body is drawn at the second end.

6. The method of claim 5, further comprising:

heating the cutting edge so that the one or more retainers are annealed.

7. The method of claim 6, wherein the cutting edge is heated to approximately 200°C.

8. The method of claim 5, wherein the first blade and the second blade comprise sapphire.

9. A suture for use in a procedure applied to tissue comprising:

an elongated body having a first end and a second end; and

a plurality of retainers arranged along a portion of the elongated body;

wherein the retainers substantially yield to motion of the elongated body within the tissue when the elongated body is drawn at the first end and resist motion of the elongated within the tissue when the elongated body is drawn at the second end; and

wherein the retainers include an upper surface and a lower surface formed by a cutting edge, the upper surface extending from a periphery of the

elongated body and the lower surface joining the elongated body at an apex having a radius of curvature larger than a radius of curvature of the cutting edge.

10. The suture of claim 9, wherein one or both of the elongated body and the plurality of retainers includes an associated material to be delivered to the tissue.

11. The suture of claim 10, wherein the associated material is one or more of a hormone, a drug, and medicine.

12. The suture of claim 9, wherein the radius of curvature of the apex is 0 to 0.5 times the retainer channel opening length.

13. The suture of claim 9, wherein the radius of curvature of the apex is 0.1 to 0.25 times the retainer channel opening length.

14. The suture of claim 9, wherein the plurality of retainers is a first set, the portion of the elongated body is a first portion, and the cutting edge is a first cutting edge; and further comprising:

a second set including a plurality of retainers arranged along a second portion of the elongated body;

wherein the retainers substantially yield to motion of the elongated body within the tissue when the elongated body is drawn at the second end and resist motion of the elongated within the tissue when the elongated body is drawn at the first end; and

wherein the retainers of the second set include an upper surface and a lower surface defined by a second cutting edge, the upper surface extending from a periphery of the elongated body and the lower surface joining the elongated body at an apex having a radius of curvature larger than a radius of curvature of the second cutting edge.

15. A method of forming one or more retainers in a suture for use in a surgical procedure applied to tissue comprising:

urging an elongated body having a first end and a second end ;

heating a cutting edge to a temperature that distorts the elongated body;

and

oscillating the cutting edge so that the cutting edge alternately penetrates the elongated body and exits the elongated body;

wherein the cutting edge forms the one or more retainers so that the one or more retainers substantially yield to motion of the elongated body within the tissue when the elongated body is drawn at the first end and resist motion of the elongated within the tissue when the elongated body is drawn at the second end; and

wherein the cutting edge forms the one or more retainers to include an upper surface and a lower surface defined by a cutting edge, the upper surface extending from a periphery of the elongated body and the lower surface joining the elongated body at an apex having a radius of curvature larger than a radius of curvature of the cutting edge.

16. The method of claim 15, further comprising:

annealing the one or more retainers with the cutting edge.

17. The method of claim 16, wherein the one or more retainers are annealed by heating the cutting edge within the range of 100-250°C









18. The method of claim 15, wherein the radius of curvature of the apex is 0 to 0.5 times the retainer channel opening length.

19. The suture of claim 15, wherein the radius of curvature of the apex is 0.1 to 0.25 times the retainer channel opening length.

20. The suture of claim 1, wherein the lower surface is one of V-shaped, rectangular-shaped, and trapezoidal-shaped.
21. A system to form a retainer in a suture for use in a procedure applied to tissue comprising:
a cutting edge including a first blade and a second blade arranged at an angle relative to the first blade;
a mechanism to oscillate the cutting edge; and
a heater connected with the cutting edge to heat the cutting edge.
22. The system of claim 21, wherein the first blade and the second blade are sapphire blades.
23. The system of claim 21, wherein the first blade and the second blade are one of metallic blades and ceramic blades.
24. The system of claim 21, wherein the first blade and the second blade are substantially in contact and the second blade is arranged at 90° relative to the first blade.
25. The system of claim 21, wherein the heater is a copper plate that conducts heat to the cutting edge.
26. The system of claim 21, wherein the mechanism to oscillate the cutting edge is a cam.

27. A suture for use in a procedure applied to tissue comprising:
an elongated body having a first end and a second end; and
a plurality of retainers arranged along a portion of the elongated body;
wherein the retainers substantially yield to motion of the elongated body
within the tissue when the elongated body is drawn at the first end and
resist motion of the elongated within the tissue when the elongated body
is drawn at the second end; and
wherein the retainers include an upper surface and a lower surface formed
by a cutting edge, and
wherein the upper surface includes a supplementary material formed on at
least a portion of the upper surface.
28. The suture of claim 27, wherein the supplementary material is deposited by
a printing technique.
29. The suture of claim 27, wherein the supplementary material has
substantially the same material properties as the elongated body.
30. The suture of claim 27, wherein the supplementary material has one or both
of higher yield strength and higher Young's Modulus than the elongated body.
31. A suture for use in a procedure applied to tissue comprising:
an elongated body having a first end and a second end; and
a plurality of retainers arranged along a portion of the elongated body;
wherein the retainers substantially yield to motion of the elongated body
within the tissue when the elongated body is drawn at the first end and
resist motion of the elongated within the tissue when the elongated body
is drawn at the second end; and
wherein a spacing distance is formed between retainers arranged at a
position along a circumference of the elongated body, the spacing
distance being a function of the tissue strength and composition.

1/4






Fig. 5B




Fig. 5A




Fig. 6A




Fig. 6B




Fig. 7A




Fig. 7B




Fig. 7C