



US009379285B2

(12) **United States Patent**  
**Kim**

(10) **Patent No.:** **US 9,379,285 B2**  
(45) **Date of Patent:** **Jun. 28, 2016**

(54) **LIGHT EMITTING DEVICE HAVING UNDOPED GAN LAYER**

(71) Applicant: **LG INNOTEK CO., LTD.**, Seoul (KR)

(72) Inventor: **Tae Yun Kim**, Gwangju (KR)

(73) Assignee: **LG INNOTEK CO., LTD.**, Seoul (KR)

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/643,777**

(22) Filed: **Mar. 10, 2015**

(65) **Prior Publication Data**

US 2015/0187994 A1 Jul. 2, 2015

**Related U.S. Application Data**

(63) Continuation of application No. 14/206,468, filed on Mar. 12, 2014, now Pat. No. 9,000,462, which is a continuation of application No. 13/589,974, filed on Aug. 20, 2012, now Pat. No. 8,692,269, which is a continuation of application No. 13/046,520, filed on Mar. 11, 2011, now Pat. No. 8,258,525, which is a continuation of application No. 12/107,256, filed on Apr. 22, 2008, now Pat. No. 7,928,454.

(30) **Foreign Application Priority Data**

Apr. 23, 2007 (KR) ..... 10-2007-0039534

(51) **Int. Cl.**

**H01L 33/32** (2010.01)

**H01L 33/12** (2010.01)

**H01L 21/02** (2006.01)

(52) **U.S. Cl.**

CPC ..... **H01L 33/325** (2013.01); **H01L 33/12** (2013.01); **H01L 33/32** (2013.01); **H01L 21/0254** (2013.01); **H01L 21/0262** (2013.01)

(58) **Field of Classification Search**

CPC ..... H01L 33/325; H01L 33/32; H01L 33/12; H01L 21/0254; H01L 21/0262

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

6,121,638 A 9/2000 Rennie et al.  
6,875,627 B2 4/2005 Bour et al.

(Continued)

FOREIGN PATENT DOCUMENTS

KR 10-2006-0007123 A 1/2006  
KR 102006-0072444 A 6/2006

(Continued)

OTHER PUBLICATIONS

A machine generated English translation of KR 10-0785374.

(Continued)


*Primary Examiner* — William Coleman

(74) *Attorney, Agent, or Firm* — Birch, Stewart, Kolasch & Birch, LLP

(57) **ABSTRACT**

Disclosed is a light emitting device. A light emitting device comprises a plurality of N-type semiconductor layers including a first N-type semiconductor layer and a second N-type semiconductor layer on the first N-type semiconductor layer, an active layer on the second N-type semiconductor layer, and a P-type semiconductor layer on the active layer, wherein the first N-type semiconductor layer comprises a Si doped Nitride layer and the second N-type semiconductor layer comprises a Si doped Nitride layer, and wherein the first and second N-type semiconductor layers have a Si impurity concentration different from each other.

**20 Claims, 1 Drawing Sheet**



(56)

**References Cited**

2009/0242874 A1 10/2009 Biwa et al.

U.S. PATENT DOCUMENTS

FOREIGN PATENT DOCUMENTS

7,067,838 B1 6/2006 Sato et al.  
7,501,299 B2 3/2009 Wong et al.  
7,501,664 B2 \* 3/2009 Yoo ..... H01L 33/12  
257/190  
7,663,138 B2 2/2010 Fujikura  
8,030,639 B2 10/2011 Lee  
8,692,269 B2 4/2014 Kim  
2007/0152207 A1 7/2007 Yen et al.  
2007/0152232 A1 7/2007 Kobayakawa et al.  
2008/0048172 A1 2/2008 Muraki et al.  
2008/0142781 A1 6/2008 Lee

KR 10-0785374 B1 12/2007  
TW 536844 B 6/2003  
WO WO 2006/009372 A1 1/2006  
WO WO 2006/068375 A1 6/2006

OTHER PUBLICATIONS

A machine generated English translation of TW 536844.

\* cited by examiner

FIG.1





FIG.2



## LIGHT EMITTING DEVICE HAVING UNDOPED GAN LAYER

### CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a continuation of co-pending U.S. application Ser. No. 14/206,468, filed on Mar. 12, 2014, which is a continuation of U.S. application Ser. No. 13/589,974, filed on Aug. 20, 2012, (now U.S. Pat. No. 8,692,269, issued on Apr. 8, 2014), which is a continuation of U.S. application Ser. No. 13/046,520, filed on Mar. 11, 2011, (now U.S. Pat. No. 8,258,525, issued on Sep. 4, 2012), which is a continuation of U.S. application Ser. No. 12/107,256, filed on Apr. 22, 2008 (now U.S. Pat. No. 7,928,454, issued on Apr. 19, 2011), which claims priority under 35 U.S.C. §119 of Korean Patent Application No. 10-2007-0039534, filed on Apr. 23, 2007, the entire contents of which are hereby incorporated by reference and for which priority is claimed under 35 U.S.C. §120.

### BACKGROUND OF THE INVENTION

#### Field of the Invention

The embodiment relates to a light emitting diode and a method for manufacturing the same.

A light emitting diode is formed by sequentially stacking a buffer layer, an unintentionally doped GaN layer (Un-GaN layer), an N-type GaN layer, an active layer, and a P-type GaN layer on a substrate.

The light emitting diode has a characteristic in which electrons are inserted into holes on the active layer to emit light if power is applied to the N-type GaN layer and the P-type GaN layer.

Meanwhile, since the substrate has a lattice constant different from that of the N-type GaN layer, dislocation may occur, and the buffer layer and the Un-GaN layer reduce a difference between lattice constants of the substrate and the GaN layer.

However, the buffer layer and the Un-GaN layer have a limitation in the reduction of the difference of the lattice constants, and the dislocation density may be increased due to the Un-GaN layer.

### SUMMARY OF THE INVENTION

The embodiment provides a light emitting device and a method for manufacturing the same.

The embodiment provides a light emitting device and a method for manufacturing the same, capable of reducing dislocation density.

The embodiment provides a light emitting device and a method for manufacturing the same, capable of reducing lattice mismatching, thereby improving a light emitting characteristic.

According to the embodiment, a light emitting device comprises a plurality of N-type semiconductor layers including a first N-type semiconductor layer and a second N-type semiconductor layer on the first N-type semiconductor layer; an active layer on the second N-type semiconductor layer; and a P-type semiconductor layer on the active layer, wherein the first N-type semiconductor layer comprises a Si doped Nitride layer and the second N-type semiconductor layer comprises a Si doped Nitride layer, and wherein the first and second N-type semiconductor layers have a Si impurity concentration different from each other.

According to the embodiment, a light emitting device comprises a plurality of N-type semiconductor layers including a first N-type semiconductor layer and a second N-type semiconductor layer on the first N-type semiconductor layer; an active layer on a first portion of the second N-type semiconductor layer; a P-type semiconductor layer on the active layer, a first electrode on a second portion of the second N-type semiconductor layer; and a second electrode on the P-type semiconductor layer, wherein the first N-type semiconductor layer comprises a Si doped Nitride layer and the second N-type semiconductor layer comprises a Si doped Nitride layer, and wherein the first and second N-type semiconductor layers have a Si impurity concentration different from each other.

According to the embodiment, a light emitting device comprises a substrate; a first N-type semiconductor layer including a GaN layer on the substrate; a second N-type semiconductor layer including a GaN layer on the first N-type semiconductor layer; an undoped GaN layer on the second N-type semiconductor layer; an active layer on the undoped GaN layer; and a P-type GaN layer on the active layer, wherein the first and second N-type semiconductor layers have a Si impurity concentration different from each other.

### BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a view used to explain a light emitting diode according to the first embodiment; and

FIG. 2 is a view used to explain a light emitting diode according to the second embodiment.

### DETAILED DESCRIPTION OF THE INVENTION

In the description of the embodiments, when layers (films), regions, patterns, or elements are described in that they are formed on or under substrates, layers (films), regions, or patterns, it means that they are formed directly or indirectly on or under the substrates, layers (films), regions, or patterns.

The thickness and size of each layer shown in the drawings can be simplified or exaggerated for the purpose of convenience or clarity. In addition, the elements may have sizes different from those shown in drawings in practice.

Hereinafter, a light emitting diode and a method for manufacturing the same with reference to accompanying drawings.

FIG. 1 is a view used to explain a light emitting diode according to a first embodiment.

The light emitting diode according to the first embodiment comprises a substrate **10**, a buffer layer **20**, a first Un-GaN layer **31**, a first N-type GaN layer **32**, a second Un-GaN layer **33**, a second N-type GaN layer **34**, an active layer **40**, a P-type GaN layer **50**, and an ohmic electrode layer **60**. A first electrode layer **70** is formed on the second N-type GaN layer **34**, and a second electrode layer **80** is formed on the ohmic electrode layer **60**.

As shown in FIG. 1, the light emitting diode according to the first embodiment includes the first and second Un-GaN layers **31** and **33** and the first and second N-type GaN layers **32** and **34**, which are alternatively and repeatedly stacked on the buffer layer **20**.

As shown in FIG. 1, the Un-GaN layer and the N-type GaN layer are repeated twice.

According to the first embodiment, the first N-type GaN layer **32** is formed between the first and second Un-GaN layers **31** and **33**, thereby preventing the occurrence of a dislocation density due to the first and second Un-GaN layers **31** and **33**. According to the first embodiment, a plurality of Un-GaN layers are provided, in which each Un-GaN layer is

thinner than an Un-GaN layer provided in a single layer structure of the Un-GaN layer and an N-type GaN layer according to the related art. Similarly, each N-type GaN layer may be thin a conventional N-type GaN layer.

In other words, the increase of dislocation density occurring as the Un-GaN layer becomes thick is prevented by forming a plurality of thin Un-GaN layers.

For example, the first and second Un-GaN layer **31** and **33** may have thicknesses in the range of 0.50  $\mu\text{m}$  to 1  $\mu\text{m}$ , and the first and second N-type GaN layers **32** and **34** may have thicknesses in the range of 1  $\mu\text{m}$  to 1.5  $\mu\text{m}$ .

According to the first embodiment, the dislocation density of the first and second N-type GaN layers **32** and **34** is reduced as the N-type GaN layers become close to the active layer **40**, that is, distant from the buffer layer **20**.

To this end, the first and second Un-GaN layers **31** and **33** and the first and second N-type GaN layers **32** and **34** are formed in a chamber having a higher temperature and a lower pressure while reducing the amount of TMGa flowed into the chamber as the Un-GaN layers and the N-type GaN layers are close to the active layer **40**.

Further, since a dislocation density may be increased as the concentration of impurities is increased in the first and second N-type GaN layers **32** and **34**, the concentration of N-type impurities is decreased as the N-type GaN layers become close to the active layer **40**.

FIG. 2 is a view used to explain a light emitting diode according to a second embodiment.

The light emitting diode according to the second embodiment comprises a substrate **10**, a buffer layer **20**, a first Un-GaN layer **31**, a first N-type GaN layer **32**, a second Un-GaN layer **33**, a second N-type GaN layer **34**, a third Un-GaN layer **35**, a third N-type GaN layer **36**, an active layer **40**, a P-type GaN layer **50**, and an ohmic electrode layer **60**. A first electrode layer **70** is formed on the third N-type GaN layer **36**, and a second electrode layer **80** is formed on the ohmic electrode layer **60**.

As shown in FIG. 2, the light emitting diode according to the second embodiment has the first, second, and third Un-GaN layers **31**, **33**, and **35** and the first, second, and third N-type GaN layers **32**, **34**, and **36** alternatively stacked on the buffer layer **20**.

As shown in FIG. 2, the Un-GaN layers and the N-type GaN layers are repeated three times.

Although it is not shown, the Un-GaN layers and the N-type GaN layers may be repeated four times according to another embodiment.

According to the second embodiment, the first and second N-type GaN layers **32** and **34** are alternately provided in relation to the first second, and third Un-GaN layers **31**, **33**, and **35**, thereby preventing the increase of dislocation density by the first, second, and third Un-GaN layers **31**, **33**, and **35**. According to the second embodiment, a plurality of Un-GaN layers are provided. In this case, the first, second, and third Un-GaN layers **31**, **33**, and **35** are thinner than an Un-GaN layer provided in a single layer structure of the Un-GaN layer and an N-type GaN layer according to the related art. Similarly, the first, second, and third N-type GaN layers **32**, **34**, and **36** may be thin a conventional N-type GaN layer.

In other words, the increase of dislocation density occurring as the Un-GaN layer becomes thick is prevented by forming a plurality of thin Un-GaN layers.

For example, the first, second, and third Un-GaN layers **31**, **33**, and **35** may have thicknesses in the range of 0.3  $\mu\text{m}$  to 0.6  $\mu\text{m}$ , and the first, second, and third N-type GaN layers **32**, **34**, and **36** may have thicknesses in the range of 0.5  $\mu\text{m}$  to 1  $\mu\text{m}$ .

According to the second embodiment, the dislocation density of the N-type GaN layer is reduced as the N-type GaN layer becomes close to the active layer **40**, that is, distant from the buffer layer **20**.

To this end, the Un-GaN layer and the N-type GaN layer are formed in a chamber having a higher temperature and a lower pressure while reducing an amount of TMGa flowed into the chamber as the Un-GaN layer and the N-type GaN layer are close to the active layer **40**.

Further, since a dislocation density may be increased as the concentration of impurities is increased in the first, second, and third N-type GaN layers **32**, **34**, and **36**, the concentration of N-type impurities is decreased as the N-type GaN layers become close to the active layer **40**.

As described above, in the light emitting diode according to the embodiments, a plurality of thin Un-GaN layers are provided, and the N-type GaN layers are provided between the Un-GaN layers in order to prevent the increase of dislocation density caused by the layers. Accordingly, the increase of the dislocation density in the Un-GaN layer can be prevented due to the N-type GaN layer.

In addition, the light emitting diode according to the embodiments is provided such that dislocation density is decreased as the N-type GaN layer becomes close to the active layer **40**.

Accordingly, the dislocation density of the N-type GaN layer in contact with the active layer **40** is decreased so that the light emitting characteristic of the light emitting diode can be improved.

Hereinafter, a method for manufacturing the light emitting diode according to the embodiment will be described in detail with reference to FIG. 2.

The buffer layer **20** is formed on the substrate **10**. For example, the substrate **10** includes at least one of  $\text{Al}_2\text{O}_3$ , Si, SiC, GaAs, ZnO, and MgO.

The buffer layer **20** is used to reduce a difference between lattice constants of the substrate **10** and the GaN layer stacked on the substrate **10**. For example, the buffer layer **20** may have a stacking structure such as  $\text{AlInN}/\text{GaN}$ ,  $\text{In}_x\text{Ga}_{1-x}\text{N}/\text{GaN}$ , or  $\text{Al}_x\text{In}_y\text{Ga}_{1-x-y}\text{N}/\text{In}_x\text{Ga}_{1-x}\text{N}/\text{GaN}$ .

For example, the buffer layer **20** may be grown by flowing TMGa and TMIn at a flow rate of  $3 \times 10^5$  Mol/min into the chamber, in which the substrate **10** is positioned, and flowing TMAI at a flow rate of  $3 \times 10^6$  Mol/min into the chamber together with hydrogen gas and ammonia gases.

The first Un-GaN layer **31**, the first N-type GaN layer **32**, the second Un-GaN layer **33**, the second N-type GaN layer **34**, the third Un-GaN layer **35**, the third N-type GaN layer **36** are sequentially formed on the buffer layer **20**. The first, second, and third Un-GaN layers **31**, **33**, and **35** and the first, second, and third N-type GaN layer **32**, **34**, and **36** may be formed through a metal-organic vapor chemical deposition (MOCVD) process.

First, the first Un-GaN layer **31** is formed on the buffer layer **20**. For example, the first Un-GaN layer **31** may be formed by flowing  $\text{NH}_3$  ( $3.7 \times 10^{-2}$  Mol/min) and TMGa ( $2.9 \times 10^{-4}$ - $3.1 \times 10^{-4}$  Mol/min) gas in a state in which the chamber is adjusted to have internal pressure of 500 Torr to 700 Torr and the internal temperature in the range of 1040° C. to 1050° C.

Then, the first N-type GaN layer **32** is formed on the first Un-GaN layer **31**. For example, the first N-type GaN layer **32** is formed by flowing  $\text{NH}_3$  ( $3.7 \times 10^{-2}$  Mol/min), TMGa ( $2.9 \times 10^{-4}$ - $3.1 \times 10^{-4}$  Mol/min), a  $\text{SiH}_4$  gas including N-type impurities such as Si in a state in which a chamber is adjusted to have an internal pressure of 500 Torr to 700 Torr and an internal temperature the temperature in the range of 1040° C. to 1050° C.

In this case, the first N-type GaN layer **32** may have a dislocation density of  $10^{10}/\text{cm}^2$  or less. In addition, Si may be implanted into the first N-type GaN layer **32** with the concentration of  $7 \times 10^{18}/\text{cm}^2$ .

The second Un-GaN layer **33** is formed on the first N-type GaN layer **32**. The second Un-GaN layer **33** is formed by flowing a less amount of TMGa gas in a chamber with a lower pressure under a higher temperature as compared with the process of performing the first Un-GaN layer **31**.

For example, the second Un-GaN layer **33** may be formed by flowing  $\text{NH}_3$  ( $3.7 \times 10^{-2}$  Mol/min) and TMGa ( $1.9 \times 10^{-4}$ – $2.1 \times 10^{-4}$  Mol/min) gas in a state in which a chamber is adjusted to have an internal pressure of 300 Torr to 500 Torr and an internal temperature in the range of 1050° C. to 1060° C.

The second N-type GaN layer **34** is formed on the second Un-GaN layer **33**. The second N-type GaN layer **34** is formed by flowing a less amount of a TMGa gas and an  $\text{SiH}_4$  gas in a chamber with a lower pressure under a higher temperature as compared with the process of performing the first N-type GaN layer **32**.

For example, the second N-type GaN layer **34** may be formed by flowing  $\text{NH}_3$  ( $3.7 \times 10^{-2}$  Mol/min), TMGa ( $1.9 \times 10^{-4}$ – $2.1 \times 10^{-4}$  Mol/min), and a  $\text{SiH}_4$  gas including N-type impurities such as Si in a state in which a chamber is adjusted to have an internal pressure of 300 Torr to 500 Torr and an internal in the range of 1050° C. to 1060° C.

In this case, the second N-type GaN layer **34** may have the dislocation density of  $10^9/\text{cm}^2$  or less. In addition, Si may be implanted into the second N-type GaN layer **34** with the concentration of  $5 \times 10^{18}/\text{cm}^2$ .

The third Un-GaN layer **35** is formed on the second N-type GaN layer **34**. The third Un-GaN layer **35** is formed by flowing a less amount of a TMGa gas in a chamber with a lower pressure under a higher temperature as compared with the process of performing the second Un-GaN layer **33**.

For example, the third Un-GaN layer **35** may be formed by flowing  $\text{NH}_3$  ( $3.7 \times 10^{-2}$  Mol/min) and TMGa ( $1.4 \times 10^{-4}$ – $1.6 \times 10^{-4}$  Mol/min) gas in a state in which a chamber is adjusted to have an internal pressure of 200 Torr to 300 Torr and an internal temperature in the range of 1060° C. to 1070° C.

The third N-type GaN layer **36** is formed on the third Un-GaN layer **35**. The third N-type GaN layer **36** is formed by flowing a less amount of a TMGa gas and an  $\text{SiH}_4$  gas in a chamber with a lower pressure under a higher temperature as compared with the process of performing the second N-type GaN layer **34**.

For example, the third N-type GaN layer **36** may be formed by flowing  $\text{NH}_3$  ( $3.7 \times 10^{-2}$  Mol/min), TMGa ( $1.4 \times 10^{-4}$ – $1.6 \times 10^{-4}$  Mol/min), and a  $\text{SiH}_4$  gas including N-type impurities such as Si in a state in which a chamber is adjusted to have an internal pressure of 200 Torr to 300 Torr and an internal temperature in the range of 1060° C. to 1070° C.

In this case, the third N-type GaN layer **36** may have the dislocation density of  $10^8/\text{cm}^2$  or less. In addition, Si may be implanted into the third N-type GaN layer **36** with the concentration of  $3 \times 10^{18}/\text{cm}^2$ .

The active layer **40** is formed on the third N-type GaN layer **36**. For example, the active layer **40** may have a multi-quantum well structure including InGaN/GaN which is grown at a nitrogen gas atmosphere by flowing TMGa and TMIn into the chamber.

The P-type GaN layer **50** is formed on the active layer **40**. For example, the P-type GaN layer **50** may be grown by supplying TMGa ( $7 \times 10^{-6}$  Mol/min), TMAI ( $2.6 \times 10^{-5}$  Mol/min),  $(\text{EtCp}_2\text{Mg})\{\text{Mg}(\text{C}_2\text{H}_5\text{C}_5\text{H}_4)_2\}$  ( $5.2 \times 10^{-7}$  Mol/min), and  $\text{NH}_3$  ( $2.2 \times 10^{-1}$  Mol/min using hydrogen as a carrier gas.

The ohmic electrode layer **60** is formed on the P-type GaN layer **50**. For example, the ohmic electrode layer **60** includes at least one of ITO, CTO,  $\text{SnO}_2$ , ZnO,  $\text{RuO}_x$ ,  $\text{TiO}_x$ ,  $\text{IrO}_x$ , and  $\text{Ga}_x\text{O}_x$ .

After the above stacking structure is formed, a mask layer (not shown) is formed on the ohmic electrode **60**. The ohmic electrode layer **60**, the P-type GaN layer **50**, the active layer **40**, and the third N-type GaN layer **36** are selectively etched so that a portion of the third N-type GaN layer **36** is exposed upward.

The first electrode layer **70** is formed on the third N-type GaN layer **36**, and the second electrode layer **80** is formed on the ohmic electrode layer **60**.

Accordingly, the light emitting diode according to the embodiments can be manufactured.

In the light emitting diode and the method for manufacturing the same according to the embodiments, the Un-GaN layer and the N-type GaN layer are alternatively stacked, thereby reducing the dislocation density on the N-type GaN layer adjacent to the active layer.

Further, in the light emitting diode and the method for manufacturing the same according to the embodiments, a plurality of Un-GaN layers and N-type GaN layers are provided. In this case, the Un-GaN layers and the N-type GaN layers are formed by reducing an amount of TMGa flowed into the chamber while increasing the temperature of a chamber and reducing the pressure of the chamber step by step. Accordingly, the dislocation density of the N-type GaN layer adjacent to the active layer may be more reduced.

In the light emitting diode and the method for manufacturing the same according to the embodiments, a plurality of Un-GaN layers and a plurality of N-type GaN are formed. In this case, the N-type GaN layer is formed by reducing an amount of N-type impurities step by step. Accordingly, the dislocation density of the N-type GaN layer adjacent to the active layer can be more reduced.

Any reference in this specification to “one embodiment,” “an embodiment,” “example embodiment,” etc., means that a particular feature, structure, or characteristic described in connection with the embodiment is included in at least one embodiment of the invention. The appearances of such phrases in various places in the specification are not necessarily all referring to the same embodiment. Further, when a particular feature, structure, or characteristic is described in connection with any embodiment, it is submitted that it is within the purview of one skilled in the art to effect such feature, structure, or characteristic in connection with other ones of the embodiments.

Although embodiments have been described with reference to a number of illustrative embodiments thereof, it should be understood that numerous other modifications and embodiments can be devised by those skilled in the art that will fall within the spirit and scope of the principles of this disclosure. More particularly, various variations and modifications are possible in the component parts and/or arrangements of the subject combination arrangement within the scope of the disclosure, the drawings and the appended claims. In addition to variations and modifications in the component parts and/or arrangements, alternative uses will also be apparent to those skilled in the art.

What is claimed is:

1. A light emitting device comprising:

a substrate;

a first undoped GaN layer on the substrate;

a first n-type semiconductor layer on the first undoped GaN layer;

7

a second undoped GaN layer on the first n-type semiconductor layer;  
 a second n-type semiconductor layer on the second undoped GaN layer;  
 an active layer on the second n-type semiconductor layer;  
 a p-type semiconductor layer on the active layer;  
 an ohmic electrode layer on the p-type semiconductor layer; and  
 a second electrode on the p-type semiconductor layer.

2. The light emitting device according to claim 1, further comprising a third undoped GaN layer on the second n-type semiconductor layer.

3. The light emitting device according to claim 1, wherein the first n-type semiconductor layer has a Si impurity concentration different from that of the second n-type semiconductor layer, and wherein the Si concentration of the first n-type semiconductor layer is greater than that of the second n-type semiconductor layer.

4. The light emitting device according to claim 1, wherein the first n-type semiconductor layer is thicker than the first undoped GaN layer.

5. The light emitting device according to claim 1, wherein the first n-type semiconductor layer is thicker than the second undoped GaN layer.

6. The light emitting device according to claim 1, further comprising a first electrode on a first portion of the first n-type semiconductor layer.

7. The light emitting device according to claim 1, wherein the ohmic electrode layer is directly disposed on the p-type semiconductor layer.

8. The light emitting device according to claim 2, further comprising a third n-type semiconductor layer on the third undoped GaN layer.

9. The light emitting device according to claim 8, wherein the first n-type semiconductor layer has a Si impurity concentration different from that of the second n-type semiconductor layer, and wherein the Si concentration of the first n-type semiconductor layer is greater than that of the third n-type semiconductor layer.

10. The light emitting device according to claim 8, wherein a Si concentration of the second n-type semiconductor layer is greater than that of the third n-type semiconductor layer.

8

11. A light emitting device comprising:

a substrate;  
 a first undoped GaN layer on the substrate;  
 a first n-type semiconductor layer on the first undoped GaN layer;  
 a second undoped GaN layer on the first n-type semiconductor layer;  
 a second n-type semiconductor layer on the second undoped GaN layer;  
 an active layer on the second n-type semiconductor layer;  
 a p-type semiconductor layer on the active layer; and  
 a first electrode on the p-type semiconductor layer, wherein the first n-type semiconductor layer is thicker than the first undoped GaN layer.

12. The light emitting device according to claim 11, further comprising an ohmic electrode layer on the p-type semiconductor layer.

13. The light emitting device according to claim 11, wherein the first n-type semiconductor layer is thicker than the second undoped GaN layer.

14. The light emitting device according to claim 11, further comprising a second electrode on a first portion of the first n-type semiconductor layer.

15. The light emitting device according to claim 11, further comprising a third undoped GaN layer on second n-type semiconductor layer.

16. The light emitting device according to claim 11, wherein a Si concentration of the first n-type semiconductor layer is different from that of the second n-type semiconductor layer.

17. The light emitting device according to claim 12, wherein the ohmic electrode layer is directly disposed on the p-type semiconductor layer.

18. The light emitting device according to claim 15, further comprising a third n-type semiconductor layer on the third undoped GaN layer.

19. The light emitting device according to claim 18, wherein a Si concentration of the first n-type semiconductor layer is greater than that of the third n-type semiconductor layer.

20. The light emitting device according to claim 16, wherein the Si concentration of the first n-type semiconductor layer is greater than that of the second n-type semiconductor layer.

\* \* \* \* \*