

(12) PATENT
(19) AUSTRALIAN PATENT OFFICE

(11) Application No. **AU 199955000 B2**
(10) Patent No. **762568**

(54) Title
Tinting plastic articles

(51)⁶ International Patent Classification(s)
D06P 005/20 G02C 007/02
D06P 003/36

(21) Application No: 199955000 (22) Application Date: 1999 . 09 . 02

(87) WIPO No: WO00/14325

(30) Priority Data

(31) Number	(32) Date	(33) Country
2246505	1998 . 09 . 03	CA

(43) Publication Date : 2000 . 03 . 27
(43) Publication Journal Date : 2000 . 05 . 18
(44) Accepted Journal Date : 2003 . 06 . 26

(71) Applicant(s)
Christophe U. Ryser

(72) Inventor(s)
Christophe U. Ryser

(74) Agent/Attorney
GRIFFITH HACK,GPO Box 1285K,MELBOURNE VIC 3001

(56) Related Art
GB 2270576

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



55 000/49

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : D06P 5/20, 3/36, G02C 7/02	A1	(11) International Publication Number: WO 00/14325 (43) International Publication Date: 16 March 2000 (16.03.00)
(21) International Application Number: PCT/CA99/00803 (22) International Filing Date: 2 September 1999 (02.09.99) (30) Priority Data: 2,246,505 3 September 1998 (03.09.98) CA (71)(72) Applicant and Inventor: RYSER, Christophe, U. [CA/CA]; Apartment 1622, 4998 de Maisonneuve Ouest, Westmount, Québec H3Z 1N2 (CA). (74) Agents: MURPHY, Kevin, P. et al.; Swabey Ogilvy Renault, Suite 1600, 1981 McGill College Avenue, Montreal, Québec H3A 2Y3 (CA).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: TINTING PLASTIC ARTICLES (57) Abstract Plastic articles, especially plastic optical lenses are tinted by immersing the plastic article in an aqueous dispersion of tinting agent and exposing the dispersion and immersed article to microwave radiation to bring the dispersion to ebullition; the ebullition is maintained for at least 2 seconds with transfer of tinting agent from the dispersion to the article to tint the article; the tinted article is removed from the dispersion and rinsed with water. The method achieves tinting in significantly shorter times than conventional methods and employs water-based dispersions thereby avoiding emission of vapors of organic solvents.		

- 1 -

TINTING PLASTIC ARTICLES

TECHNICAL BACKGROUND

This invention relates to a method of tinting a plastic article;
the invention is especially concerned with tinting plastic optical lenses,
5 especially ophthalmic lenses, for use in spectacles and other eye wear, to
provide a colour tint or ultraviolet (UV) light transmission inhibiting tint.

BACKGROUND ART

Tinting of optical lenses for spectacles and sunglasses is
widely employed either to apply an aesthetic, fashion oriented coloured tint
10 to eye wear or to apply a tint which functions to block or inhibit
transmission of ultraviolet light in eye wear, while additionally providing a
desired aesthetic or fashionable appearance.

Current techniques for tinting optical lenses involve
immersing the lens in a bath comprising solution or dispersion of a tinting
15 dye or pigment which is heated to a temperature typically of 75 to 85°C and
maintained well below boiling temperature. The heating is achieved by
heat exchange, wherein pots containing the tinting dye or pigment are
surrounded by a heat transfer fluid which may be a silicone oil or other heat
transfer oil. Typically it takes about 60 minutes to heat the bath from room
20 temperature to 75 to 85°C by this conventional technique. The lenses are
inserted into the hot bath, typically by means of a lens holder which
maintains the lens in an upright or vertical disposition.

As the temperature of the lens rises in the hot bath, the
surface pores of the lens open and dye or pigment penetrates to effect
25 tinting. Opening of the surface pores and initial tinting typically takes 5
minutes, but in order to achieve a dark sunglass tint colour, the lens
typically needs to be maintained immersed in the hot bath for 15 minutes or
more, and in particular up to 45 minutes for a dark tint.

- 2 -

Different optical plastics are employed in lens manufacture. Some optical plastics are tintable, having surface pores which will receive a tinting dye or pigment, for example, diethylene glycol bis(allyl carbonate) known as CR-39. Other optical plastics such as polycarbonates are not-
5 tintable or are difficult to tint.

In some cases optical lenses are provided with a thin, hard surface coating, typically about 2 microns, these hard surface coatings permit tinting but conventional tinting techniques require long tinting times, for example, several hours. Hard surface coatings may be, for
10 example, of vinyl polyester or polysiloxane.

These hard surface coatings do permit tinting of optical lenses of non-tintable plastic, but as indicated above long tinting times are required. These hard surface coatings are also employed, in some cases, on otherwise tintable lenses such as CR-39 lenses, rendering such lenses more
15 difficult to tint.

These prior techniques employ low energy dye pigments available for optical use, which pigments disintegrate within a few hours if exposed to temperatures of 95°C or higher.

U.S. Patent 5,560,751 describes another conventional
20 technique in which a thin liquid coating of a tinting solution is formed on a surface of a lens by spinning the lens at 1000 to 2000 rpm while applying the tinting solution dropwise to the lens surface, whereafter the resulting coated lens is heated causing the dye in the coating to be absorbed.

Canadian Patent Specification 2,095,703 describes a method
25 for producing a photochromic plastic lens in which the lens is immersed in a high boiling organic solvent bath containing the dye and exposed to microwave heating, typically for about 6 minutes, whereafter the lens was allowed to soak in the hot bath for about 15 minutes.

The use of organic solvents is costly and use of hot solvents requires special handling facilities and equipment to avoid or minimize escape of vapors of the hot solvents into the atmosphere with the consequent hazards to the environment and to personnel involved in the tinting operation.

It is thus desirable to develop tinting techniques which avoid the use of hot organic solvents, while at the same time shortening the time required for tinting and avoiding the need for special or costly equipment.

SUMMARY OF THE INVENTION

The invention seeks to provide a tinting method in which tinting is achieved in short times.

The invention further seeks to provide a tinting method which avoids the need for costly equipment or handling facilities and employs water-based materials.

In accordance with the invention there is provided a method for tinting a tintable plastic optical lens, said lens being of thermoplastic or a thermoset plastic and said method involving:

- i) immersing a tintable thermoplastic or thermoset plastic optical lens in an aqueous dispersion of a tinting agent, said dispersion and lens being supported on a rotatable platform, and said tinting agent being a high energy dye or a UV dye which withstands temperature of 90°C to 135°C;
- ii) exposing said aqueous dispersion with said immersed optical lens to microwave radiation to bring said dispersion to a quiescent boil, while rotating said platform;
- iii) maintaining said quiescent boil for a time period of at least about 2 seconds, while rotating said platform, with transfer of

- iv) tinting agent from said dispersion to said optical lens to effect tinting;
- v) removing the resulting tinted optical lens from said dispersion; and
- 5 vi) rinsing the tinted optical lens with water to remove residual dispersion.

DETAILED DESCRIPTION OF THE INVENTION

i) Plastic Articles

The invention is applicable to tintable plastic articles
10 generally, especially small articles, but has particular application to plastic

optical lenses employed in eye wear, more especially, spectacles, sunglasses and protective eye wear, such as eye shields and goggles.

It is to be understood that "tintable plastic articles" in the context of the invention, contemplates articles such as lenses which are either of a plastic which is itself tintable, or have a surface coating which is tintable.

The tinting method may be employed to provide a tint of a desired colour, for aesthetic or fashion reasons, or to provide a protective tint effective to reduce, inhibit or block transmission of ultraviolet light through the lens, or for both of these functions.

Typical plastics for eye wear are well established in the eye wear industry and include poly(methyl methacrylate), cellulose acetates, polyvinyl chloride, polyurethanes, polycarbonate and diethylene glycol bis(allyl carbonate).

Within this class of plastics, diethylene glycol bis(allyl carbonate) referred to in the trade as CR-39 is widely employed as a tintable optical lens, both for use in producing a tinted lens of a desired colour and shade, and also for producing lenses with a protective UV tint.

Polycarbonates are also widely employed as optical lens plastic.

ii) Tinting Method

a) Pretreatment

The method of the invention is applied to clean lenses and, if necessary, the lenses are subjected to a preliminary cleansing operation. If lenses are being re-tinted or it is desired to change an existing tint, the existing tint is first removed using a technique similar to that of the invention but with a water-based tint removal solution instead of the aqueous dispersion of dye.

In the tint removal operation the tinted lens is immersed in an aqueous solution of a surfactant effective for removal of the tint under the operating conditions.

5 The solution of surfactant is first exposed to microwave radiation until the solution boils quietly; the tinted lens is immersed in the hot boiling solution and boiling is maintained to liberate the tinting dye from the lens. The operation is continued until the dye is removed from the lens.

10 The lens is removed from the solution and washed and the aqueous solution containing liberated tinting agent is reused for removal of tint in other lenses or is discarded.

A clean lens which is to be tinted is suitably surface conditioned by immersing the lens in an aqueous solution of a surfactant which is effective to reduce or lower surface tension on the surfaces of the lens, such that the tinting dispersion uniformly coats the surfaces of the lens
15 when the lens is immersed in the tinting dispersion.

One suitable surfactant for this purpose is that available under the Trade-mark KIRALON-OL from BASF, however, other suitable surfactants can be readily identified by trial and experiment.

20 The surface conditioning can be carried out at room temperature; suitably the lens is immersed in the aqueous solution of surfactant for 10 to 40, preferably 15 to 30 seconds, removed and rinsed with water.

It is found that if the surface conditioning is not carried, in
25 some cases the tint produced is not homogeneous.

b) Tinting

In order to tint the lens, an aqueous dispersion of a dye or pigment is selected for the desired colour of tint. The aqueous dispersion is

housed in a container and the lens is immersed in the dispersion; the lens may be supported by a lens holder which leaves the major faces of the lens fully exposed or may be placed on the floor of the container with a positive side of the lens, i.e., the convex face of the lens uppermost. In this way, both major faces of the lens, i.e., the concave face and the convex face are exposed to the aqueous dispersion; the dispersion and the immersed lens are heated by microwave energy in a microwave oven until the dispersion reaches ebullition, and preferably a quiescent or non-violent boil.

After the boiling state is reached, the lens is maintained in the boiling dispersion for a predetermined time to achieve a desired level of tint.

The dye or pigment in the hot dispersion penetrates the surface pores of the lens, and thus dye or pigment is transferred to the lens across the major surfaces of the lens. The surface pores may be in a coating on the surface of the plastic lens or in the surface defined by the plastic from which the lens is manufactured.

Suitably the container housing the dispersion is supported on a turntable in the microwave oven, which defines a rotating platform. Rotation of the turntable supporting the container of dispersion ensures a uniform heating and uniform temperature throughout the dispersion, which in turn results in a uniform transfer of dye to the lens surfaces. Rotation of the turntable is typically at 2 to 10 rpm, more usually 4 to 8 rpm.

It is found preferable to maintain the exposure of the dispersion and lens to the microwave radiation, on a continuous basis, throughout the tinting. Microwave ovens have different heating operations, some of which provide continuous microwave radiation in a heating cycle, and others of which provide microwave radiation in an interrupted or

- 7 -

discontinuous manner in which the microwave radiation is interrupted or discontinued periodically in a heating cycle.

It has been found that use of a continuous exposure to microwave radiation provides faster tinting than the use of an interrupted or
5 discontinuous exposure. Furthermore, the use of continuous microwave radiation is found to be especially important in the case of lenses which are more difficult to tint, such as high index or polycarbonate lens. In these cases the use of continuous microwave radiation resulted in faster tinting and darker tints than could be achieved with discontinuous microwave
10 radiation.

The time for the aqueous dispersion to reach boiling at particular microwave oven operating parameters for a particular microwave oven are predetermined by trial. Likewise the time of immersion of a lens in the dispersion, to reach a desired level of tinting is predetermined by
15 trial.

Immersion times for different levels of tinting may be predetermined by trial for specific operating parameters of a specific microwave oven to provide a table of immersion times and tinting levels, to which reference may be made when a lens is to be tinted.

20 In general a typical 800 watt power microwave oven at high power will bring 120 ml of aqueous dispersion, having the lens immersed therein, to boiling temperature in about 60 seconds. The boiling is maintained for a time depending on the level of tinting desired. In the case of an uncoated CR-39 lens, tinting is complete in 2 to 60 seconds.
25 Typically, a 2 second immersion produces a tinted lens with 10% absorption of visible light, a 30 second immersion produces 50% absorption and a 60 second immersion produces 72% absorption. Other

12-09-2000

- 8 -

levels of absorption are achieved by shortening or lengthening the immersion time, a longer time producing a darker tint.

On completion of the tinting, the microwave heating is discontinued, the lens is removed from the hot dispersion and rinsed with
 5 water to remove residual dispersion.

The lens is preferably removed immediately from the dispersion at termination of the heating, and continued soaking in the dispersion is avoided. If the lens is left soaking in the dispersion, the tinting by the hot dispersion will continue, even if at a slower rate so that
 10 the desired level of tinting may be exceeded.

The dispersion may be used repeatedly to tint further lenses until it is depleted in dye.

Since the dispersion reaches the boiling stage rapidly, it is not necessary to maintain it at boiling in between tinting operations. Thus by
 15 allowing the dispersion to cool in between tinting operations, exposure of the dispersion to high temperatures is reduced whereby the life of the dye is maintained. In addition the short tinting times required by the method of the invention also result in prolongation of the life of the dye in the dispersion.

20 In the case of lenses of non-tintable plastic and which have a thin, hard coating which permits tinting, for example, polycarbonate lenses or high index lenses, which have a hard coating of, for example, a vinyl ester or a polysiloxane, the tinting may take up to 12 minutes of immersion in the boiling dispersion, but this is still markedly faster than with
 25 conventional tinting techniques where tinting requires upwards of 45 minutes and frequently several hours.

Furthermore, employing the method of the invention to apply UV tints of the benzophenone class, it has been found that the tinting

dispersion has a significantly longer reheat life than when the tinting dispersion is employed in the conventional methods.

In the conventional method, even though operated at lower temperatures, the benzophenone UV tints are found to degrade significantly after only 6 to 8 cycles of heating, cooling and re-heating; the degradation is such that the dispersion will no longer function and must be discarded. This degradation occurs whether the 6 to 8 cycles are over a short or a long period of time.

Employing the method of the present invention with benzophenone tints, however, the degradation does not occur even after 70 cycles of heating, cooling and reheating, even through higher heating temperatures are involved.

The reason for this result is unclear, but one theory is that the exposure to microwave radiation or the presence of the surfactant contribute to the stability.

In the present invention it is found that the dispersion can be employed until it is substantially depleted in tinting agent, and the tinting agent is not degraded.

The method of the invention achieves tinting in times that are at least 10 to 20 times shorter than in currently employed techniques, and the tinting dispersion can be employed repeatedly until it is depleted of tinting agent.

c) Tinting Dispersion

The aqueous dispersion of tinting agent suitably contains the dye or pigment and a surfactant to stabilize the dispersion.

The tinting agent is an organic dye or pigment, in particular, a high energy tinting dye or pigment or UV dye which withstands temperatures of 90°C to 135°C without significant degradation.

One suitable class of tinting dyes is the azo dyes available under the Trade-mark CIBACET from Ciba-Geigy Dyes Ltd. A suitable class of UV dye is the benzophenones available under the Trade-mark UVINUL of BASF.

5 Particular UV dyes of this class include 2,2',4,4'-tetrahydroxy benzophenone, benzophenone-6, benzoorsorcinol, oxybenzone and sulisobenzene.

The azo dyes are available in red, blue and yellow and these three primary colours can be employed to make a full range of colours,
10 employing appropriate proportions of the three primary colours.

In the preparation of the aqueous tinting dispersion weighed amounts of a tinting agent or agents are employed to provide a desired colour, and the dyes are blended with water, preferably luke warm water; suitably the dye is added slowly to the water during mixing or blending.
15 An anti-foaming agent may be added as foaming occurs and finally a surfactant is added to stabilize the dispersion. Suitable surfactants include those derived from castor oil, for example, the ethoxylated castor oil surfactants available under the Trade-mark ALKAMULS from Rhone-Poulenc, especially Alkalmuls EP-620 which is castor oil ethoxylated (30).

20 Typically the dispersion is produced as a concentrate which is diluted for use.

EXAMPLES

Example 1

A red tinting dispersion was produced as follows:

25 Step 1)

4 litres of luke warm water were added to a high speed blender and the blender was operated at medium speed;

Step 2)

100 gms of powder red dye (CIBACET from Ciba-Geigy Dyes Ltd.) was added slowly into the water while the blender continued to operate at medium speed;

5 Step 3)

During the blending of the dye and water, foaming occurred; at this stage 2 ml of Antifoam 1520-US from Dow Corning was added and the foaming receded within seconds;

Step 4)

10 The blending was continued after completion of the addition of the dye, and 19 ml of a surfactant ALKAMULS EL-620 of Rhone-Poulenc was added, to stabilize the resulting dispersion;

Step 5)

15 The dispersion was blended for a further 5 minutes at high speed; thereafter 120 ml portions of the resulting dispersion concentrate were diluted with 880 ml of water to produce 1 liter of tinting dispersion.

Example 2

A surface conditioner was produced by blending 7 gms of Kiralon-ol in 1000 ml of water.

20 120 ml of the surface conditioner was placed in a container jar and a stainless steel grill was placed on the floor of the jar. Three CR-39 cleaned lenses were immersed in the surface conditioner, being supported by the grill at room temperature, for 10 to 30 seconds; the lenses were removed and rinsed with water.

25 The rinsed lenses were submerged in a portion of the tinting dispersion of Example 1 and placed on the turntable of an 800 watt microwave oven and the oven was set at high power with the timer at 2 minutes and 30 seconds, and the turntable rotating at about 6 rpm; when

boiling was observed, the lenses were maintained in the boiling dispersion for 2, 30 and 60 seconds respectively. The lenses were thus removed at 2, 30 and 60 seconds respectively and rinsed with water.

The following visible light absorption levels were noted in
5 the three lenses employing a UV and visible light transmission meter -

<u>Time</u>	<u>Absorption</u>
2 sec.	10%
30 sec.	50%
60 sec.	72%

10 Example 3

The existing tint on a polycarbonate lens was removed as follows:

10 gms of a surfactant RHODAFAC RS-610 of Rhone-Poulenc was mixed with 1000 ml of water; the tinted polycarbonate lens
15 was immersed in a portion of the surfactant solution in a container with a negative (concave) face of the lens facing down and supported by a stainless steel grill on the floor of the container.

The container was placed in an 800 watt microwave oven and the power was set on high; after boiling commenced it was allowed to
20 continue until the dye was removed from the tinted lens. The lens was removed and rinsed with water.

A UV dye was applied to the lens as follows:

Step 1)

22.5g of UVINOL D50, a 2,2',4,4'-tetrahydroxy
25 benzophenone was dissolved in 1 litre of methanol to form a concentrate. An aqueous solution of surfactant was formed by blending 7 g of a surfactant KIRALON OL and 4 g of surfactant ALKAMULS EL-620 in

620 litres of water. The UVINOL concentrate was added slowly to the aqueous solution under agitation to produce the UV dye dispersion.

Step 2)

The lens was submerged in 120 ml of the UV dye dispersion
5 in a container, the container was placed on the turntable of an 800 watt microwave oven and the oven was operated at high power, when boiling was observed the lens was maintained in the boiling UV dye dispersion for 2 minutes. The container was removed from the oven and the lens was removed from the UV dye dispersion, allowed to cool to room temperature
10 and rinsed with water.

UV transmission readings with a UV-meter at 400 nm was less than 3%.

It was found that the UV dye dispersion could be re-used repeatedly until the UV dye content of the dispersion was exhausted.

15 The invention provides a simple, low cost method of tinting plastic optical lenses and other plastic articles. Tinting is completed in much shorter times than with prior tinting procedures, and the equipment employed was readily available. Since the water-based compositions do not emit organic solvent vapors at the boiling temperature employed,
20 environmental concerns are satisfied.

THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:

1. A method for tinting a tintable plastic optical lens, said lens being of thermoplastic or a thermoset plastic and said method involving:
 - i) immersing a tintable thermoplastic or thermoset plastic optical lens in an aqueous dispersion of a tinting agent, said dispersion and lens being supported on a rotatable platform, and said tinting agent being a high energy dye or a UV dye which withstands temperatures of 90°C to 135°C;
 - ii) exposing said aqueous dispersion with said immersed optical lens to microwave radiation to bring said dispersion to a quiescent boil, while rotating said platform,
 - iii) maintaining said quiescent boil for a time period of at least about 2 seconds, while rotating said platform, with transfer of tinting agent from said dispersion to said optical lens to effect tinting,
 - iv) removing the resulting tinted optical lens from said dispersion; and
 - v) rinsing the tinted optical lens with water to remove residual dispersion.
2. A method according to claim 1, wherein said tinting agent is a high-energy dye which withstands temperatures of 90°C to 135°C.
3. A method according to claim 1, wherein said tinting agent is a UV dye capable of producing a tint which reduces ultra violet light transmission.

4. A method as claimed in either claim 1 or 2, wherein said time period for maintaining a quiescent boil is between 2 to 120 seconds.

5. A method as claimed in claim 4, wherein said time period for maintaining a quiescent boil is between 2 to 60 seconds.

6. A method as claimed in any one of claims 1, 2, 4 or 5, including a step, prior to step i) of surface conditioning said optical lens.

10 7. A method as claimed in claim 6, wherein said step of surface conditioning involves immersing said optical lens in an aqueous solution of a surfactant capable of reducing surface tension of said optical lens such that in step iii) dye is uniformly transferred to said optical lens from said dispersion across the surface of the optical lens.

15 8. A method as claimed in any one of the preceeding claims, wherein said aqueous dispersion contains a surfactant.

20 9. A method as claimed in any one of the preceeding claims, wherein said optical lens is of a thermoset plastic.

10. A method as claimed in any one of claims 1 to 8, wherein said lens is of diethylene glycol bis(allyl)carbonate.

25 11. A method as claimed in any one of claims 1 to 3, wherein said optical lens is of a thermoplastic polycarbonate and said time period for maintaining a quiescent boil is between 2 seconds and 12 minutes.

12. A method as claimed in any one of claims 1, 2, 3 or 11,
further including a step, prior to step i), of surface conditioning said optical
lens by immersing said optical lens in an aqueous solution of a surfactant
effective to reduce surface tension of said optical lens such that in step iii)
5 dye is uniformly transferred to said optical lens from said dispersion across
the surface of the optical lens; and said dispersion in step i) contains a
surfactant.

13. A method as claimed in any one of the preceeding claims,
10 wherein at completion of tinting in step iii), said tinted optical lens is
immediately removed from the dispersion in step iv), and rinsed in step v).

14. A method as claimed in claim 13, wherein at completion of
tinting in step iii) said microwave radiation is terminated to discontinue
15 said quiescent boil of said dispersion.

15. A method as claimed in any one of the preceeding claims,
wherein said rotatable platform is a turntable in a microwave oven and said
dispersion with said immersed optical lens is housed in a container
20 supported on said turntable for rotation therewith.

16. A method as claimed in any one of the preceeding claims,
wherein said aqueous dispersion and optical lens are exposed to said
microwave radiation, continuously, in steps ii) and iii).

25

17. A method as claimed in any one of the preceeding claims,
wherein said platform is rotated at 2 to 10 rpm during steps ii) and iii).

18. A method according to claim 17, wherein said platform is rotated at 4 to 8 rpm during steps ii) and iii).

19. A method for tinting a tintable plastic optical lens
5 substantially as herein described with reference to any one of the examples.

Dated this 13th day of January 2003

CHRISTOPHE U RYSER

By their Patent Attorneys

10 GRIFFITH HACK

Fellows Institute of Patent and

Trade Mark Attorneys of Australia

15