



(11) (21) (C) **2,048,966**  
(22) 1991/08/12  
(43) 1992/02/14  
(45) 2000/04/25

(72) Klaiber, Adolf August, DE

(73) SOLUTIA INC., US

(51) Int.Cl.<sup>5</sup> E04F 15/10

(30) 1990/08/13 (9017703.1) GB

(54) **UTILISATION DE PVB RECUPERES DANS LA FABRICATION  
DE REVETEMENT DE PLANCHER**

(54) **USE OF RECOVERED PVB IN THE MANUFACTURE OF  
FLOORING**

(57) Floorings and flooring compositions containing a plasticised, preferably recovered, PVB resin are disclosed. In a more preferred aspect of the technology, the floorings and the corresponding compositions contain a major amount of a second compatible resin such as a non-plasticised PVB, and also a major amount of a composition inert filler. The floorings made in accordance with the technology herein can contain substantially reduced levels of chlorine.

06-12(9080)A

A B S T R A C T

5 Floorings and flooring compositions containing a plasticised, preferably recovered, PVB resin are disclosed. In a more preferred aspect of the technology, the floorings and the corresponding compositions contain a major amount of a second compatible resin such as a non-plasticised PVB, and also a major amount of a composition inert filler. The floorings made in accordance with the technology herein can contain substantially reduced levels of chlorine.

USE OF RECOVERED PVB  
IN THE MANUFACTURE OF FLOORING

This invention relates to the use of recovered plasticised poly-  
5 vinyl butyral ( PVB ) as a raw material component for the manu-  
facture of flooring material, to new flooring compositions com-  
prising recovered plasticised PVB and to flooring comprising  
recovered plasticised PVB.

Hereinafter the term "flooring" means synthetic flooring in the  
10 form of a finished product; "flooring composition" and "flooring  
material", mean compounded and processed product, generated from  
a raw materials mixture comprising a resin or mixture of resins  
with possibly other adjuvants, which is used in the manufacture  
of "flooring". The terms "flooring composition" and "flooring  
15 material" are used interchangeably.

Steadily increasing quantities of various resinous materials used  
in all areas of industry, environmental awareness and concern as  
shown by national and international regulations concerning the  
disposal of difficultly biodegradable material, and technical  
20 difficulties encountered in the recovery of such resinous mater-  
ials, have created the need for efficient and economically  
acceptable recycling of resinous materials.

Plasticised PVB is one of the resinous materials for which no  
appropriate recycling was available so far. Plasticised PVB is  
25 used in large quantities, mainly as interlayer in laminated  
safety glass for windows in buildings and windscreens for cars.  
For economical and environmental reasons, the glass from lamin-  
ated safety glass is recovered by conventional techniques, for  
example, by crushing, grinding and milling of the scrap lamin-  
30 ated glass which provokes the release, from the PVB interlayer,  
of the small glass particles. The glass so recovered is  
recycled.



The residual PVB is recovered as a resinous mass comprising various kinds of adjuvants and contaminants. Due to a lack of appropriate recycling possibilities, large quantities of recovered PVB resin had to be disposed of by conventional approaches inclusive of incineration and landfill.

PVB is a complex resin which may be manufactured, depending upon its application and other extrinsic factors, with large variations with respect to structural features and composition.

10 Differences in kind of PVB resin can, for example, relate to

- differences in molecular weight,
- differences in contents of hydroxyl, butyral and residual ester groups,
- differences in type and contents of plasticiser,
- 15 - differences in other various adjuvants.

Unless indicated to the contrary, the percent (%) indications hereinafter stand for percent-by-weight (% wt).

A typical PVB resin may have a molecular weight range, according to the Staudinger equation, of about 30.000 to 600.000, for example from about 40.000 to 250.000, a range of about 12% to 20%, for example about 16% to 20%, hydroxyl groups, calculated as polyvinyl alcohol, and a range of 0% to about 3% residual ester groups calculated as polyvinyl acetate.

Many different compounds, well known in the art, may be used as plasticisers for PVB. Typical ones are, for example, di-n-hexyl-adipate, butylbenzylphthalate, 3-ethyleneglycol ethyl-butyrate, dioctyladipate and tetraethyleneglycol heptanoate.

The contents of the plasticisers in PVB may vary largely, for example from about 5% to about 50% by weight.

Synthetic flooring has gained widespread commercial acceptance and is made from various flooring compositions which may comprise all sorts of resins or mixtures of resins. A major component of many  
5 current synthetic flooring compositions is polyvinyl chloride (PVC) which can be applied in various forms such as, e.g. plasticised PVC and PVC foam. As a matter of fact, PVC is virtually the sole polymer which is widely used in flooring materials.

For environmental and other reasons, there is an on-going effort  
10 to develop adequate resin compositions for flooring with a substantially reduced chlorine content.

Flooring materials have to fulfil several technical criteria such as, for example, abrasion and scuff resistance, stain resistance, a good balance between hardness and flexibility, compatibility  
15 with additional adjuvants such as, for example, plasticisers, fillers, UV-stabilisers, pigments and colouring agents, flame retardants and antistatic agents, the possibility of its easily industrially processing, and an economically attractive raw materials cost.

20 While floorings such as tiles are frequently made as a monolayer, multilayer executions containing the various layers made from different compositions exhibiting different in-use properties, can also be used.

A typical multilayer flooring can contain, for example, seen from  
25 the bottom to the top, a PVC-foam layer, a coloured interface, a transparent PVC-wear layer and possibly an extra top-wear layer of polyurethane or poly(meth)acrylates. This flooring can optionally be combined with a form stabilising element such as, for example, a layer of plasticised PVC impregnated with a  
30 glassfiber mat. The flooring can also be provided with a backing layer of e.g. PVC foam or a textile mat.



It is an object of this invention to provide an environmentally, industrially and economically acceptable recycling for recovered plasticised PVB.

- 5 A further object of the invention relates to new flooring compositions which can be manufactured and further processed to new floorings at conditions comparable to conventional floorings. Still another object of this invention is to provide flooring compositions and floorings with substantially reduced levels of  
10 chlorine-containing components.

The foregoing and other objects of the invention can now be met by using recovered plasticised PVB according to the invention herein.

- 15 In detail, recovered plasticised PVB is used as a low cost, high quality raw material in the manufacture of flooring compositions with the additional advantage that such flooring compositions and floorings made therefrom contain substantially reduced chlorine levels.

- 20 In one aspect of the invention, it has been discovered that recovered plasticised PVB can be used as a raw material component, preferably as the major raw material component, for the manufacture of flooring material.

- 25 In a preferred aspect of the invention, a resin mixture comprising from about 95% to about 25% of recovered plasticised PVB resin and from about 5% to 75% of another compatible resin is used. In a more preferred aspect of the invention, the recovered PVB represents from about 95% to 60% whereas the compatible resin represents from about 5% to 40%. In another preferred aspect, a  
30 resin mixture comprising from about 90% to 80% recovered plasticised PVB and from about 10% to 20% of another compatible resin is used.

In still another preferred aspect of the invention the compatible resin is selected among compatible resins which are substantially free of plasticiser.

- 5 The invention also relates to flooring compositions, and to floorings made therefrom, comprising recovered plasticised PVB or mixtures of recovered plasticised PVB and a compatible resin as described hereinbefore.

10 The kind of recovered PVB is not critical to the working of the invention. Suitable flooring compositions are obtained with recovered plasticised PVB of different kinds and from different manufacturing origins, as well as with mixtures of different kinds of recovered PVBs.

15 The kind and contents of plasticiser in the recovered PVB is not critical neither to the working of the invention. Suitable compositions are obtained from recovered PVB resins which contain different kinds of plasticisers as well as from mixtures of recovered PVBs containing two or more different plasticisers.

20 By "another compatible resin" is meant any resin or mixture of two or more resins which, under known processing conditions of raw materials mixtures for flooring, is capable of forming together with the recovered PVB an adequate flooring composition.

25 The compatible resin can be selected from commercially available resins including homopolymers and copolymers such as, for example, PVB, PVC, PVA's (polyvinyl acetates), PEVA (polyethylvinylacetate), PVF (polyvinylformal), e.g. Formvar<sup>®</sup>, (registered trademark of Monsanto), NBR (nitrilebutadiene rubber), and the like.



5 The compatible resin can be a plasticised resin, containing additive levels of plasticiser, e.g. up to about 40% expressed on the compatible resin. Since, however, a considerable amount of plasticiser in the flooring composition will generally originate from the recovered plasticised PVB, the utilisation of a compatible resin with low plasticiser contents, e.g. below about 15%, is preferred. In one preferred embodiment herein, a compatible resin which is substantially free of plasticiser is used.

10 A particularly preferred compatible resin for flooring compositions and flooring according to the invention is non-plasticised PVB such as, for example Butvar B 72® (Trademark of Monsanto Company).

15 Accordingly, for a given quality of recovered PVB, the selection with respect to kind and ratio of compatible resin is made such that the resulting flooring material will meet the manufacturing criteria, in particular hardness.

20 The appropriate ratio of recovered plasticised PVB/compatible resin can be determined experimentally according to known techniques, for example by carrying out laboratory-scale manufacturing runs under standardised processing conditions. Resin mixtures comprising varying ratios of recovered PVB /compatible resin can be used, wherein in addition the compatible resin can be varied. The results of the measurements of selected physico-chemical properties, (e.g. hardness, low-temperature flexibility, 25 water uptake) of the obtained flooring material can serve for the optimisation, on a routine basis, of the choice of kind and level of the resin components and, in a similar way of the other adjuvants, of the resins mixtures.



In the compositions of the invention the plasticiser level, expressed by reference to the total resin level (100%), may vary from about 5% to 50 %. Preferably the plasticiser level varies  
5 from about 15% to 40%; most preferably from about 20% to 30 %.

The compositions of the invention may also comprise one or more adjuvants commonly used in flooring material such as fillers, pigments, colouring agents, UV-stabilisers, antistatic agents and flame retardants. Such adjuvants are, for example, used for their  
10 established functionality in the art-established levels.

Some adjuvants can originate from the recovered PVB. The qualitative and quantitative adjuvant selection can be optimised routinely with the aid of known techniques, e.g. small-scale manufacturing runs and comparative testing of the end-product.

15 Recovered PVB can also contain common contaminants such as sand and remaining glass particles. During the processing steps of the PVB recovery and the manufacturing of the flooring material, these glass particles generally have become minute and act in fact, as does also sand, as a filler, and do not adversely affect  
20 to any substantial extent the use of recovered PVB.

While the level of these minute glass particles is relatively low, e.g. frequently below 2%, larger quantities up to 5% or even up to 10% can be used. The contents of other contaminants, such as e.g. sand, is low, usually below about 5 %, preferable below  
25 about 2%. The levels of glass particles and sand or other contaminants are expressed by reference to the total resin level (100%) of the flooring composition.

Recovered PVB containing various kinds of adjuvants and contaminants such as e.g. plasticiser, glass, sand and others, can in the  
30 context of the invention herein be used as a raw material.

However, the recovered PVB has to be substantially free of rubber and metal parts.

5 The preferred compositions of the invention comprising recovered plasticised PVB and non-plasticised PVB can contain higher filler contents than current flooring material from plasticised PVC. The total filler contents, composed of one or more kinds of fillers, may be up to about 150%, expressed by reference to the total resin contents. Preferably the filler level varies from 10 about 40% to 120%. The fillers are well-established in the art. Preferred fillers are, for example, calcium carbonate, barium sulfate and aluminium trihydrate.

15 Scrap of flooring and recovered flooring made according to this invention can also be used as a source of recovered plasticised PVB.

20 The compositions of the invention comprising recovered plasticised PVB and a compatible resin, such as a non-plasticised PVB, can be routinely processed on existing equipment used for the manufacture of PVC flooring, such as for example, Banbury mixing rolls, Auma calenders (laminating rolls systems), press moulds, extrusion moulding equipment, and hot melt roll calenders.

25 The compositions of the invention are suitable for the manufacture of flooring in monolayer form, e.g. as tiles, and can also be used as a constructing element, e.g. as wear layer, in multilayer floorings.

The flooring materials of the invention can optionally be combined with other conventional flooring elements such as, e.g. dimension stabilising elements, backing elements, foamed resin layers, adhesive layers and top wear layers.



In still another aspect of the invention the major resin components of the flooring compositions are preferably substantially chlorine-free and the flooring materials and floorings manufactured therefrom consequently contain substantially reduced chlorine contents as compared to current synthetic floorings. This applies in particular to flooring material and flooring made from a mixture of recovered PVB and non-plasticised PVB.

The invention is illustrated by the following example :

- 10 To 100 parts of a mixture of 85% plasticised PVB, recovered from scrap laminated glass and containing about 30% plasticiser, and 15% non-plasticised PVB (Butvar B72®); are added 100 parts of crystalline calcium carbonate filler. Optionally additive levels of 3% of pigments and stabilisers are added. The mixture is  
15 compounded on a Banbury mixer at 120° to 130°C, i.e. about 15° to 20°C below the temperature normally required for PVC processing, and further processed into flooring by conventional techniques. For example, via calender rolls a sheet of monolayer flooring is manufactured which is subsequently cut into tiles, or installed  
20 in sheetings.

Alternatively, the compounded product can be processed in the form of granules which by e.g. press-mould technique are further processed into tiles. The compounded product can, alternatively, be processed into a film, which via an Auma rolls system and  
25 subsequent cutting can be processed into multilayer tiles.

Measurements made by standard techniques on monolayer tiles manufactured according to the above gave the following results:

- |    |   |                                      |  |
|----|---|--------------------------------------|--|
|    | - | low-temperature flexibility (-19°C): | good                                   |
|    | - | Shore-A-Hardness                     | : good (95 to 97)                      |
| 30 | - | dimensional stability                | : good (no shrinkage)                  |
|    | - | water pick-up                        | : no problem (0.9%)                    |
|    | - | abrasion resistance                  | : significantly better than PVC tiles. |
|    | - | scuff resistance (manual test)       | : good.                                |



THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. Use of recovered plasticised polyvinylbutyral (PVB) resin as raw material component for the manufacture of flooring material.
2. Use of recovered PVB according to claim 1 in a resin mixture comprising 95% to 25% by weight recovered plasticised PVB resin and 5% to 75% by weight of another compatible resin.
3. Use of recovered PVB according to claim 2 wherein the resin mixture comprises from 95% to 60% by weight of recovered plasticised PVB and from 5 to 40% by weight of the compatible resin.
4. Use of recovered PVB according to claim 3 wherein the resin mixture comprises from 90% to 80% by weight of recovered plasticised PVB and from 10% to 20% by weight of the compatible resin.
5. Use according to any of claims 1 to 4 wherein the compatible resin is selected from PVB, PVC, PVA's (polyvinylacetates), PEVA (polyethylvinylacetate), PVF (polyvinylformal), or NBR (nitrilebutadiene rubber).
6. Use according to claim 5 wherein the compatible resin is non-plasticised PVB.
7. Use according to any of claims 1 to 6 wherein the resin mixture comprises one or more adjuvants selected from known filling agents, pigments, colouring agents, UV-stabilising agents, antistatic agents and flame retarding agents.

8. Use according to any of claims 1 to 7 wherein the major resin components of the flooring composition are substantially chlorine-free.
- 5 9. Use according to any of claims 1 to 8 for the manufacture of flooring material in the form of a monolayer or as a wear layer for a multilayer flooring.
- 10 10. Use according to any of claims 1 to 8 wherein the flooring materials are combined with one or more of the elements selected from dimension stabilising elements, backing elements, foamed resin layers, adhesive layers and top-wear layers.
11. A flooring composition comprising recovered plasticised PVB resin.
- 15 12. The flooring composition according to claim 11, obtainable by known processing techniques from the resin mixture as defined in any of claims 2 to 8.
- 20 13. A flooring composition containing a resin component, and if desired additives inclusive of plasticisers and fillers, characterised in, that the resin component is represented by a mixture of (i) from about 95% to 25% by weight of plasticised PVB containing, expressed by reference to said PVB (100%), from about 5% to 50% of a plasticiser; and (ii) from about 5% to 75% by weight of a compatible resin.
- 25 14. The flooring composition in accordance with claim 13 which in addition contains a composition-inert filler in a level up to about 150%, preferably from about 40% to about 120%, expressed by reference to the resins content (100%).

15. The flooring composition according to claims 13 or 14 wherein the compatible resin is substantially free of chlorine said compatible resin being present in a level of from about 5% to 40% by weight.
16. The flooring composition according to claim 15 wherein the resin components are represented by a mixture of recovered plasticised PVB and non-plasticised PVB.
17. The flooring composition according to claims 14 to 16 wherein the plasticised PVB component represents from 95% to 60% by weight, said PVB component containing, expressed by reference to said PVB (100%), from about 5% to about 50% of the plasticiser, from about 5% to about 40% by weight of the compatible resin and from about 40% to 120%, expressed by reference to the resins content (100%) of the composition-inert filler.
18. A flooring comprising recovered plasticised PVB resin.
19. The flooring according to claim 18 obtainable from the composition as defined in any of claims 12 to 17.
20. The flooring according to claim 19 wherein the resin mixture contains the recovered plasticised PVB and the non-plasticised PVB as defined in any of claims 12 to 17.
21. Use of recovered plasticised polyvinylbutyral (PVB) resin as raw material component for the manufacture of flooring material, in a resin mixture comprising 95% to 25% by weight recovered plasticised PVB resin and 5% to 75% by weight of another compatible resin.



22. Use of recovered PVB according to claim 21 wherein the resin mixture comprises from 95% to 60% by weight of recovered plasticised PVB and from 5 to 40% by weight of the compatible resin.
23. Use of recovered PVB according to claim 22 wherein the resin mixture comprises from 90% to 80% by weight of recovered plasticised PVB and from 10% to 20% by weight of the compatible resin.
24. Use according to any of claims 21 to 23 wherein the compatible resin is selected from PVB, PVC, PVA's (polyvinylacetates), PEVA (polyethylvinylacetate), PVF (polyvinylformal), or NBR (nitrilebutadiene rubber).
25. Use according to claim 24 wherein the compatible resin is non-plasticised PVB.
26. Use according to any of claims 21 to 25 wherein the resin mixture comprises one or more adjuvants selected from known filling agents, pigments, colouring agents, UV-stabilising agents, antistatic agents and flame retarding agents.
27. Use according to any of claims 21 to 26 wherein the major resin components of the flooring composition are substantially chlorine-free.
28. Use according to any of claims 21 to 27 for the manufacture of flooring material in the form of a monolayer or as a wear layer for a multilayer flooring.
29. Use according to any of claims 21 to 27 wherein the flooring materials are combined with one or more of the elements selected from dimension

stabilising elements, backing elements, foamed resin layers, adhesive layers and top-wear layers.

30. A flooring composition comprising recovered plasticised PVB resin, said resin comprising 95% to 25% by weight recovered plasticised PVB resin and 5% to 75% by weight of another compatible resin.
31. The flooring composition according to claim 30, obtainable by known processing techniques from the resin mixture as defined in any of claims 22 to 27.
32. Use of recovered plasticised polyvinylbutyral (PVB) resin as raw material component for the manufacture of flooring material wherein said plasticised PVB resin is that recovered from laminated safety glass.
33. Use of recovered PVB according to claim 32 in a resin mixture comprising 95% to 25% by weight recovered plasticised PVB resin and 5% to 75% by weight of another compatible resin.
34. Use of recovered PVB according to claim 33 wherein the resin mixture comprises from 95% to 60% by weight of recovered plasticised PVB and from 5 to 40% by weight of the compatible resin.
35. Use of recovered PVB according to claim 34 wherein the resin mixture comprises from 90% to 80% by weight of recovered plasticised PVB and from 10% to 20% by weight of the compatible resin.
36. Use according to any of claims 32 to 35 wherein the compatible resin is selected from PVB, PVC, PVA's (polyvinylacetates), PEVA (polyethylvinylacetate), PVF (polyvinylformal), or NBR (nitrilebutadiene

rubber).

37. Use according to claim 36 wherein the compatible resin is non-plasticised PVB.
38. Use according to any of claims 32 to 37 wherein the resin mixture comprises one or more adjuvants selected from known filling agents, pigments, colouring agents, UV-stabilising agents, antistatic agents and flame retarding agents.
39. Use according to any of claims 32 to 38 wherein the major resin components of the flooring composition are substantially chlorine-free.
40. Use according to any of claims 32 to 38 for the manufacture of flooring material in the form of a monolayer or as a wear layer for a multilayer flooring.
41. Use according to any of claims 32 to 38 wherein the flooring materials are combined with one or more of the elements selected from dimension stabilising elements, backing elements, foamed resin layers, adhesive layers and top-wear layers.
42. A flooring composition comprising recovered plasticised PVB resin, wherein said plasticised PVB resin is that recovered from laminated safety glass.
43. The flooring composition according to claim 42, obtainable by known processing techniques from the resin mixture as defined in any of claims 33 to 39.



44. A flooring composition containing a resin component, and if desired additives inclusive of plasticisers and fillers, characterised in, that the resin component is represented by a mixture of (i) from about 95% to 25% by weight of plasticised PVB containing, expressed by reference to said PVB (100%), from about 5% to 50% of a plasticiser; and (ii) from about 5% to 75% by weight of a compatible resin, said plasticised PVB being recovered from laminated safety glass.
45. The flooring composition in accordance with claim 44 which in addition contains a composition-inert filler in a level up to about 150%, preferably from about 40% to about 120%, expressed by reference to the resins content (100%).
46. The flooring composition according to claims 44 or 45 wherein the compatible resin is substantially free of chlorine said compatible resin being present in a level of from about 5% to 40% by weight.
47. The flooring composition according to claim 46 wherein the resin components are represented by a mixture of recovered plasticised PVB and non-plasticised PVB.
48. The flooring composition according to claims 45 to 47 wherein the plasticised PVB component represents from 95% to 60% by weight, said PVB component containing, expressed by reference to said PVB (100%), from about 5% to about 50% of the plasticiser, from about 5% to about 40% by weight of the compatible resin and from about 40% to 120%, expressed by reference to the resins content (100%) of the composition-inert filler.

49. A flooring comprising recovered plasticised PVB resin, said plasticised PVB resin is that recovered from laminated safety glass.
50. The flooring according to claim 18 obtainable from the composition as defined in any of claims 43 to 48.
51. The flooring according to claim 50 wherein the resin mixture contains the recovered plasticised PVB and the non-plasticised PVB as defined in any of claims 43 to 48.
52. Use of recovered plasticised polyvinylbutyral (PVB) resin as raw material component for the manufacture of flooring material, wherein said plasticised PVB resin is that recovered from laminated safety glass containing minute glass particles at a level greater than 0% up to 10% by weight based on total resin content of the flooring material.
53. Use of recovered PVB according to claim 52 in a resin mixture comprising 95% to 25% by weight recovered plasticised PVB resin and 5% to 75% by weight of another compatible resin.
54. Use of recovered PVB according to claim 53 wherein the resin mixture comprises from 95% to 60% by weight of recovered plasticised PVB and from 5 to 40% by weight of the compatible resin.
55. Use of recovered PVB according to claim 54 wherein the resin mixture comprises from 90% to 80% by weight of recovered plasticised PVB and from 10% to 20% by weight of the compatible resin.
56. Use according to any of claims 52 to 55 wherein the compatible resin is selected from PVB, PVC, PVA's (polyvinylacetates), PEVA

(polyethylvinylacetate), PVF (polyvinylformal), or NBR (nitrilebutadiene rubber).

57. Use according to claim 56 wherein the compatible resin is non-plasticised PVB.
58. Use according to any of claims 52 to 57 wherein the resin mixture comprises one or more adjuvants selected from known filling agents, pigments, colouring agents, UV-stabilising agents, antistatic agents and flame retarding agents.
59. Use according to any of claims 52 to 58 wherein the major resin components of the flooring composition are substantially chlorine-free.
60. Use according to any of claims 52 to 59 for the manufacture of flooring material in the form of a monolayer or as a wear layer for a multilayer flooring.
61. Use according to any of claims 52 to 59 wherein the flooring materials are combined with one or more of the elements selected from dimension stabilising elements, backing elements, foamed resin layers, adhesive layers and top-wear layers.
62. A flooring composition comprising recovered plasticised PVB resin, wherein said plasticised PVB resin is that recovered from laminated safety glass containing minute glass particles at a level greater than 0% and up to 10% by weight based on total resin content of the flooring composition.
63. The flooring composition according to claim 62, obtainable by known processing techniques from the resin mixture as defined in any of claims 53



to 59.

64. A flooring composition containing a resin component, and if desired additives inclusive of plasticisers and fillers, characterised in, that the resin component is represented by a mixture of (i) from about 95% to 25% by weight of plasticised PVB containing, expressed by reference to said PVB (100%), from about 5% to 50% of a plasticiser; and (ii) from about 5% to 75% by weight of a compatible resin, wherein said plasticised PVB resin is that recovered from laminated safety glass containing minute glass particles at a level greater than 0% up to 10% by weight based on total resin content of the flooring material.
65. The flooring composition in accordance with claim 64 which in addition contains a composition-inert filler in a level up to about 150%, preferably from about 40% to about 120%, expressed by reference to the resins content (100%).
66. The flooring composition according to claims 64 or 65 wherein the compatible resin is substantially free of chlorine said compatible resin being present in a level of from about 5% to 40% by weight.
67. The flooring composition according to claim 66 wherein the resin components are represented by a mixture of recovered plasticised PVB and non-plasticised PVB.
68. The flooring composition according to claims 65 to 67 wherein the plasticised PVB component represents from 95% to 60% by weight, said PVB component containing, expressed by reference to said PVB (100%), from about 5% to about 50% of the plasticiser, from about 5% to about 40% by weight of the compatible resin and from about 40% to 120%,

expressed by reference to the resins content (100%) of the composition-inert filler.

69. A flooring comprising recovered plasticised PVB resin, wherein said plasticised PVB resin is that recovered from laminated safety glass containing minute glass particles at a level greater than 0% up to 10% by weight based on total resin content of the flooring material.
70. The flooring according to claim 69 obtainable from the composition as defined in any of claims 63 to 68.
71. The flooring according to claim 70 wherein the resin mixture contains the recovered plasticised PVB and the non-plasticised PVB as defined in any of claims 63 to 68.

72. Use according to any one of claims 2 to 5, 13 to 15, 21 to 24, 30, 33 to 36, 44 to 46, 53 to 56 and 64 to 66 wherein the compatible resin is PVC.