

(12) **United States Patent**
Kurata et al.

(10) **Patent No.:** **US 10,438,982 B2**
(45) **Date of Patent:** **Oct. 8, 2019**

(54) **METHOD FOR MANUFACTURING SEMICONDUCTOR DEVICE INCLUDING STEP OF SIMULTANEOUS FORMATION OF PLURALITY OF CONTACT OPENINGS**

(71) Applicant: **Semiconductor Energy Laboratory Co., Ltd.**, Kanagawa-ken (JP)

(72) Inventors: **Motomu Kurata**, Kanagawa (JP); **Ryota Hodo**, Kanagawa (JP); **Yuta Iida**, Kanagawa (JP)

(73) Assignee: **Semiconductor Energy Laboratory Co., Ltd.** (JP)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 188 days.

(21) Appl. No.: **15/082,633**

(22) Filed: **Mar. 28, 2016**

(65) **Prior Publication Data**
US 2016/0293732 A1 Oct. 6, 2016

(30) **Foreign Application Priority Data**
Mar. 30, 2015 (JP) 2015-069654

(51) **Int. Cl.**
H01L 21/768 (2006.01)
H01L 27/146 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC .. **H01L 27/14621** (2013.01); **H01L 21/76802** (2013.01); **H01L 27/1207** (2013.01);
(Continued)

(58) **Field of Classification Search**
CPC H01L 21/76802
(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,731,856 A 3/1998 Kim et al.
5,744,864 A 4/1998 Cillessen et al.
(Continued)

FOREIGN PATENT DOCUMENTS

CN 001254948 A 5/2000
CN 001290922 A 4/2001
(Continued)

OTHER PUBLICATIONS

Asakuma, N. et al., "Crystallization and Reduction of Sol-Gel-Derived Zinc Oxide Films by Irradiation With Ultraviolet Lamp," Journal of Sol-Gel Science and Technology, 2008, vol. 26, pp. 181-184.

(Continued)


Primary Examiner — Hsin Yi Hsieh

(74) *Attorney, Agent, or Firm* — Husch Blackwell LLP

(57) **ABSTRACT**

A minute transistor is provided. A transistor with low parasitic capacitance is provided. A transistor having high frequency characteristics is provided. A semiconductor device including the transistor is provided. A semiconductor device includes a first opening, a second opening, and a third opening which are formed by performing first etching and second etching. By the first etching, the first insulator is etched for forming the first opening, the second opening, and the third opening. By the second etching, the first metal oxide, the second insulator, the third insulator, the fourth insulator, the second metal oxide, and the fifth insulator are etched for forming the first opening; the first metal oxide, the second insulator, and the third insulator are etched for forming the second opening; and the first metal oxide is etched for forming the third opening.

18 Claims, 66 Drawing Sheets



(51)	Int. Cl.		8,995,174 B2	3/2015	Koyama
	<i>H01L 29/423</i>	(2006.01)	9,209,795 B2	12/2015	Okamoto et al.
	<i>H01L 29/49</i>	(2006.01)	9,705,001 B2	7/2017	Yamazaki
	<i>H01L 29/66</i>	(2006.01)	9,829,761 B2	11/2017	Kimura
	<i>H01L 29/786</i>	(2006.01)	10,256,347 B2	4/2019	Yamazaki
	<i>H01L 27/12</i>	(2006.01)	2001/0046027 A1	11/2001	Tai et al.
	<i>H01L 27/1156</i>	(2017.01)	2002/0056838 A1	5/2002	Ogawa
	<i>H01L 21/8258</i>	(2006.01)	2002/0132454 A1	9/2002	Ohtsu et al.
	<i>H01L 27/06</i>	(2006.01)	2003/0189401 A1	10/2003	Kido et al.
	<i>H01L 23/00</i>	(2006.01)	2003/0218222 A1	11/2003	Wager, III et al.
			2004/0038446 A1	2/2004	Takeda et al.
			2004/0127038 A1	7/2004	Carcia et al.
(52)	U.S. Cl.		2005/0017302 A1	1/2005	Hoffman
	CPC	<i>H01L 27/1225</i> (2013.01); <i>H01L 27/1248</i>	2005/0199959 A1	9/2005	Chiang et al.
		(2013.01); <i>H01L 27/1259</i> (2013.01); <i>H01L</i>	2006/0035452 A1	2/2006	Carcia et al.
		<i>29/42384</i> (2013.01); <i>H01L 29/4908</i> (2013.01);	2006/0043377 A1	3/2006	Hoffman et al.
		<i>H01L 29/66969</i> (2013.01); <i>H01L 29/78648</i>	2006/0091793 A1	5/2006	Baude et al.
		(2013.01); <i>H01L 21/8258</i> (2013.01); <i>H01L</i>	2006/0108529 A1	5/2006	Saito et al.
		<i>24/32</i> (2013.01); <i>H01L 24/48</i> (2013.01); <i>H01L</i>	2006/0108636 A1	5/2006	Sano et al.
		<i>24/73</i> (2013.01); <i>H01L 27/0629</i> (2013.01);	2006/0110867 A1	5/2006	Yabuta et al.
		<i>H01L 27/1156</i> (2013.01); <i>H01L 27/14627</i>	2006/0113536 A1	6/2006	Kumomi et al.
		(2013.01); <i>H01L 2029/42388</i> (2013.01); <i>H01L</i>	2006/0113539 A1	6/2006	Sano et al.
		<i>2224/32225</i> (2013.01); <i>H01L 2224/48227</i>	2006/0113549 A1	6/2006	Den et al.
		(2013.01); <i>H01L 2224/48463</i> (2013.01); <i>H01L</i>	2006/0113565 A1	6/2006	Abe et al.
		<i>2224/73265</i> (2013.01); <i>H01L 2924/181</i>	2006/0169973 A1	8/2006	Isa et al.
		(2013.01)	2006/0170111 A1	8/2006	Isa et al.
			2006/0197092 A1	9/2006	Hoffman et al.
			2006/0208977 A1	9/2006	Kimura
			2006/0228974 A1	10/2006	Thelss et al.
(58)	Field of Classification Search		2006/0231882 A1	10/2006	Kim et al.
	USPC	438/104	2006/0238135 A1	10/2006	Kimura
	See application file for complete search history.		2006/0244107 A1	11/2006	Sugihara et al.
			2006/0284171 A1	12/2006	Levy et al.
			2006/0284172 A1	12/2006	Ishii
(56)	References Cited		2006/0292777 A1	12/2006	Dunbar
	U.S. PATENT DOCUMENTS		2007/0024187 A1	2/2007	Shin et al.
	6,255,130 B1	7/2001 Kim	2007/0046191 A1	3/2007	Saito
	6,294,274 B1	9/2001 Kawazoe et al.	2007/0052025 A1	3/2007	Yabuta
	6,333,229 B1	12/2001 Furukawa et al.	2007/0054507 A1	3/2007	Kaji et al.
	6,563,174 B2	5/2003 Kawasaki et al.	2007/0090365 A1	4/2007	Hayashi et al.
	6,673,683 B1	1/2004 Sheu et al.	2007/0108446 A1	5/2007	Akimoto
	6,674,495 B1	1/2004 Hong et al.	2007/0152217 A1	7/2007	Lai et al.
	6,727,522 B1	4/2004 Kawasaki et al.	2007/0172591 A1	7/2007	Seo et al.
	6,841,831 B2	1/2005 Hanafi et al.	2007/0187678 A1	8/2007	Hirao et al.
	7,049,190 B2	5/2006 Takeda et al.	2007/0187760 A1	8/2007	Furuta et al.
	7,061,014 B2	6/2006 Hosono et al.	2007/0194379 A1	8/2007	Hosono et al.
	7,064,346 B2	6/2006 Kawasaki et al.	2007/0252928 A1	11/2007	Ito et al.
	7,105,868 B2	9/2006 Nause et al.	2007/0272922 A1	11/2007	Kim et al.
	7,190,421 B2	3/2007 Hong et al.	2007/0287296 A1	12/2007	Chang
	7,211,825 B2	5/2007 Shih et al.	2008/0006877 A1	1/2008	Mardilovich et al.
	7,220,991 B2	5/2007 Hong et al.	2008/0038882 A1	2/2008	Takechi et al.
	7,282,782 B2	10/2007 Hoffman et al.	2008/0038929 A1	2/2008	Chang
	7,297,977 B2	11/2007 Hoffman et al.	2008/0050595 A1	2/2008	Nakagawara et al.
	7,323,356 B2	1/2008 Hosono et al.	2008/0073653 A1	3/2008	Iwasaki
	7,385,224 B2	6/2008 Ishii et al.	2008/0083950 A1	4/2008	Pan et al.
	7,402,506 B2	7/2008 Levy et al.	2008/0106191 A1	5/2008	Kawase
	7,411,209 B2	8/2008 Endo et al.	2008/0128689 A1	6/2008	Lee et al.
	7,453,065 B2	11/2008 Saito et al.	2008/0129195 A1	6/2008	Ishizaki et al.
	7,453,087 B2	11/2008 Iwasaki	2008/0166834 A1	7/2008	Kim et al.
	7,462,862 B2	12/2008 Hoffman et al.	2008/0182358 A1	7/2008	Cowdery-Corvan et al.
	7,468,304 B2	12/2008 Kaji et al.	2008/0224133 A1	9/2008	Park et al.
	7,501,293 B2	3/2009 Ito et al.	2008/0254569 A1	10/2008	Hoffman et al.
	7,674,650 B2	3/2010 Akimoto et al.	2008/0258139 A1	10/2008	Ito et al.
	7,675,062 B2	3/2010 Hong et al.	2008/0258140 A1	10/2008	Lee et al.
	7,732,819 B2	6/2010 Akimoto et al.	2008/0258141 A1	10/2008	Park et al.
	7,872,722 B2	1/2011 Kimura	2008/0258143 A1	10/2008	Kim et al.
	7,883,943 B2	2/2011 Miyairi et al.	2008/0296568 A1	12/2008	Ryu et al.
	8,130,354 B2	3/2012 Kimura	2009/0068773 A1	3/2009	Lai et al.
	8,421,068 B2	4/2013 Yamazaki et al.	2009/0073325 A1	3/2009	Kuwabara et al.
	8,421,069 B2	4/2013 Yamazaki et al.	2009/0114910 A1	5/2009	Chang
	8,547,771 B2	10/2013 Koyama	2009/0134399 A1	5/2009	Sakakura et al.
	8,780,307 B2	7/2014 Kimura	2009/0152506 A1	6/2009	Umeda et al.
	8,809,853 B2	8/2014 Saito et al.	2009/0152541 A1	6/2009	Maekawa et al.
	8,829,528 B2	9/2014 Yamazaki et al.	2009/0278122 A1	11/2009	Hosono et al.
	8,940,638 B2	1/2015 Hoshino et al.	2009/0280600 A1	11/2009	Hosono et al.
	8,941,113 B2	1/2015 Takeuchi et al.	2009/0302473 A1	12/2009	Shibata et al.
	8,964,156 B2	2/2015 Kimura	2010/0065844 A1	3/2010	Tokunaga
			2010/0092800 A1	4/2010	Itagaki et al.
			2010/0109002 A1	5/2010	Itagaki et al.

(56)

References Cited

U.S. PATENT DOCUMENTS

2012/0025191	A1	2/2012	Yamazaki
2012/0051119	A1	3/2012	Yamazaki et al.
2013/0120702	A1	5/2013	Yamazaki et al.
2014/0302670	A1	10/2014	Kasahara
2014/0339540	A1	11/2014	Takemura
2015/0187814	A1	7/2015	Miyairi et al.
2015/0214256	A1	7/2015	Miyairi
2015/0270402	A1	9/2015	Endo et al.
2015/0280691	A1	10/2015	Koyama
2015/0303200	A1	10/2015	Yuki
2016/0013312	A1	1/2016	Fujimoto
2017/0263651	A1*	9/2017	Tochibayashi H01L 23/5226
2018/0088425	A1	3/2018	Kimura
2018/0375498	A1	12/2018	Koyama

FOREIGN PATENT DOCUMENTS

EP	1 737 044	A1	12/2006
EP	2 226 847	A2	9/2010
JP	60-198861	A	10/1985
JP	63-210022	A	8/1988
JP	63-210023	A	8/1988
JP	63-210024	A	8/1988
JP	63-215519	A	9/1988
JP	63-239117	A	10/1988
JP	63-265818	A	11/1988
JP	05-251705	A	9/1993
JP	08-264794	A	10/1996
JP	11-505377		5/1999
JP	2000-044236	A	2/2000
JP	2000-150900	A	5/2000
JP	2002-076356	A	3/2002
JP	2002-289859	A	10/2002
JP	2003-086000	A	3/2003
JP	2003-086808	A	3/2003
JP	2004-103957	A	4/2004
JP	2004-273614	A	9/2004
JP	2004-273732	A	9/2004
JP	2012-049514	A	3/2012
JP	2012-257187		12/2012
JP	2014-240833		12/2014
JP	2014-241407		12/2014
TW	200834197		8/2008
TW	201212162		3/2012
TW	201442242		11/2014
WO	WO 2004/114391	A1	12/2004
WO	WO 2012/017843	A1	2/2012
WO	WO 2014/142333	A1	9/2014

OTHER PUBLICATIONS

Asaoka, Y. et al., "29.1: Polarizer-Free Reflective LCD Combined With Ultra Low-Power Driving Technology," SID Digest '09: SID International Symposium Digest of Technical Papers, May 31, 2009, pp. 395-398.

Chern, H.N. et al., "An Analytical Model for the Above-Threshold Characteristics of Polysilicon Thin-Film Transistors," IEEE Transactions on Electron Devices, Jul. 1, 1995, vol. 42, No. 7, pp. 1240-1246.

Cho, D-H. et al., "21.2: Al and Sn-Doped Zinc Indium Oxide Thin Film Transistors for AMOLED Back-Plane," SID Digest '09: SID International Symposium Digest of Technical Papers, May 31, 2009, pp. 280-283.

Clark, S.J. et al., "First Principles Methods Using CASTEP," Zeitschrift für Kristallographie, 2005, vol. 220, pp. 567-570.

Coates, D. et al., "Optical Studies of the Amorphous Liquid-Cholesteric Liquid Crystal Transition: The 'Blue Phase'," Physics Letters, Sep. 10, 1973, vol. 45A, No. 2, pp. 115-116.

Costello, M.J. et al., "Electron Microscopy of a Cholesteric Liquid Crystal and Its Blue Phase," Physical Review. A, May 1, 1984, vol. 29, No. 5, pp. 2957-2959.

Dembo, H. et al., "RFCPUS on Glass and Plastic Substrates Fabricated by TFT Transfer Technology," IEDM 05: Technical Digest of International Electron Devices Meeting, Dec. 5, 2005, pp. 1067-1069.

Fortunato, E.M.C. et al., "Wide-Bandgap High-Mobility ZnO Thin-Film Transistors Produced at Room Temperature," Applied Physics Letters, Sep. 27, 2004, vol. 85, No. 13, pp. 2541-2543.

Fung, T.C. et al., "2-D Numerical Simulation of High Performance Amorphous In—Ga—Zn—O TFTs for Flat Panel Displays," AM-FPD '08 Digest of Technical Papers, Jul. 2, 2008, pp. 251-252, The Japan Society of Applied Physics.

Godo, H. et al., "P-9: Numerical Analysis on Temperature Dependence of Characteristics of Amorphous In—Ga—Zn-Oxide TFT," SID Digest '09: SID International Symposium Digest of Technical Papers, May 31, 2009, pp. 1110-1112.

Godo, H. et al., "Temperature Dependence of Characteristics and Electronic Structure for Amorphous In—Ga—Zn-Oxide TFT," AM-FPD '09 Digest of Technical Papers, Jul. 1, 2009, pp. 41-44.

Hayashi, R. et al., "42.1: Invited Paper: Improved Amorphous In—Ga—Zn—O TFTs," SID Digest '08: SID International Symposium Digest of Technical Papers, May 20, 2008, vol. 39, pp. 621-624.

Hirao, T. et al., "Novel Top-Gate Zinc Oxide Thin-Film Transistors (ZnO TFTs) for AMLCDs," Journal of the Society for Information Display, 2007, vol. 15, No. 1, pp. 17-22.

Hosono, H. et al., "Working Hypothesis to Explore Novel Wide Band Gap Electrically Conducting Amorphous Oxides and Examples," Journal of Non-Crystalline Solids, 1996, vol. 198-200, pp. 165-169.

Hosono, H., "68.3: Invited Paper: Transparent Amorphous Oxide Semiconductors for High Performance TFT," SID Digest '07: SID International Symposium Digest of Technical Papers, 2007, vol. 38, pp. 1830-1833.

Hsieh, H-H. et al., "P-29: Modeling of Amorphous Oxide Semiconductor Thin Film Transistors and Subgap Density of States," SID Digest '08: SID International Symposium Digest of Technical Papers, May 20, 2008, vol. 39, pp. 1277-1280.

Ikeda, T. et al., "Full-Functional System Liquid Crystal Display Using CG-Silicon Technology," SID Digest '04: SID International Symposium Digest of Technical Papers, 2004, vol. 35, pp. 860-863.

Janotti, A. et al., "Native Point Defects in ZnO," Physical Review. B, Oct. 4, 2007, vol. 76, No. 16, pp. 165202-1-165202-22.

Janotti, A. et al., "Oxygen Vacancies in ZnO," Applied Physics Letters, 2005, vol. 87, pp. 122102-1-122102-3.

Jeong, J.K. et al., "3.1: Distinguished Paper: 12.1-Inch WXGA AMOLED Display Driven by Indium-Gallium-Zinc Oxide TFTs Array," SID Digest '08: SID International Symposium Digest of Technical Papers, May 20, 2008, vol. 39, No. 1, pp. 1-4.

Jin, D-U. et al., "65.2: Distinguished Paper: World-Largest (6.5") Flexible Full Color Top Emission AMOLED Display on Plastic Film and Its Bending Properties," SID Digest '09: SID International Symposium Digest of Technical Papers, May 31, 2009, pp. 983-985.

Kanno, H. et al., "White Stacked Electrophosphorescent Organic Light-Emitting Devices Employing MoO₃ as a Charge-Generation Layer," Advanced Materials, 2006, vol. 18, No. 3, pp. 339-342.

Kikuchi, H. et al., "39.1: Invited Paper: Optically Isotropic Nano-Structured Liquid Crystal Composites for Display Applications," SID Digest '09: SID International Symposium Digest of Technical Papers, May 31, 2009, pp. 578-581.

Kikuchi, H. et al., "62.2: Invited Paper: Fast Electro-Optical Switching in Polymer-Stabilized Liquid Crystalline Blue Phases for Display Application," SID Digest '07: SID International Symposium Digest of Technical Papers, 2007, vol. 38, pp. 1737-1740.

Kikuchi, H. et al., "Polymer-Stabilized Liquid Crystal Blue Phases," Nature Materials, Sep. 2, 2002, vol. 1, pp. 64-68.

Kim, S. et al., "High-Performance Oxide Thin Film Transistors Passivated by Various Gas Plasmas," 214th ECS Meeting, 2008, No. 2317, ECS.

Kimizuka, N. et al., "SPINEL, YbFe₂O₄, and Yb₂Fe₃O₇ Types of Structures for Compounds in the In₂O₃ and Sc₂O₃—A₂O₃—BO Systems [A: Fe, Ga, or Al; B: Mg, Mn, Fe, Ni, Cu, or Zn] at temperatures Over 1000° C.," Journal of Solid State Chemistry, 1985, vol. 60, pp. 382-384.

(56)

References Cited

OTHER PUBLICATIONS

- Kimizuka, N. et al., "Syntheses and Single-Crystal Data of Homologous Compounds, $\text{In}_2\text{O}_3(\text{ZnO})_m$ ($m=3, 4, \text{ and } 5$), $\text{InGaO}_3(\text{ZnO})_3$, and $\text{Ga}_2\text{O}_3(\text{ZnO})_m$ ($m=7, 8, 9, \text{ and } 16$) in the $\text{In}_2\text{O}_3\text{—ZnGa}_2\text{O}_4\text{—ZnO}$ System," *Journal of Solid State Chemistry*, Apr. 1, 1995, vol. 116, No. 1, pp. 170-178.
- Kitzerow, H-S. et al., "Observation of Blue Phases in Chiral Networks," *Liquid Crystals*, 1993, vol. 14, No. 3, pp. 911-916.
- Kurokawa, Y. et al., "UHF RFCPUS on Flexible and Glass Substrates for Secure RFID Systems," *Journal of Solid-State Circuits*, 2008, vol. 43, No. 1, pp. 292-299.
- Lany, S. et al., "Dopability, Intrinsic Conductivity, and Nonstoichiometry of Transparent Conducting Oxides," *Physical Review Letters*, Jan. 26, 2007, vol. 98, pp. 045501-1-045501-4.
- Lee, H.N. et al., "Current Status of, Challenges to, and Perspective View of AM-OLED," *IDW '06: Proceedings of the 13th International Display Workshops*, Dec. 7, 2006, pp. 663-666.
- Lee, J-H. et al., "World's Largest (15-Inch) XGA AMLCD Panel Using IGZO Oxide TFT," *SID Digest '08: SID International Symposium Digest of Technical Papers*, May 20, 2008, vol. 39, pp. 625-628.
- Lee, M-H. et al., "15.4: Excellent Performance of Indium-Oxide-Based Thin-Film Transistors by DC Sputtering," *SID Digest '09: SID International Symposium Digest of Technical Papers*, May 31, 2009, pp. 191-193.
- Li, C. et al., "Modulated Structures of Homologous Compounds $\text{InMO}_3(\text{ZnO})_m$ ($M=\text{In,Ga}$; $m=\text{Integer}$) Described by Four-Dimensional Superspace Group," *Journal of Solid State Chemistry*, 1998, vol. 139, pp. 347-355.
- Masuda, S. et al., "Transparent Thin Film Transistors Using ZnO as an Active Channel Layer and Their Electrical Properties," *Journal of Applied Physics*, Feb. 1, 2003, vol. 93, No. 3, pp. 1624-1630.
- Meiboom, S. et al., "Theory of the Blue Phase of Cholesteric Liquid Crystals," *Physical Review Letters*, May 4, 1981, vol. 46, No. 18, pp. 1216-1219.
- Miyasaka, M., "SUFTLA Flexible Microelectronics on Their Way to Business," *SID Digest '07: SID International Symposium Digest of Technical Papers*, 2007, vol. 38, pp. 1673-1676.
- Mo, Y-G. et al., "Amorphous Oxide TFT Backplanes for Large Size AMOLED Displays," *IDW '08: Proceedings of the 6th International Display Workshops*, Dec. 3, 2008, pp. 581-584.
- Nakamura, M. et al., "The Phase Relations in the $\text{In}_2\text{O}_3\text{—Ga}_2\text{ZnO}_4\text{—ZnO}$ System at 1350°C ," *Journal of Solid State Chemistry*, Aug. 1, 1991, vol. 93, No. 2, pp. 298-315.
- Nakamura, M., "Synthesis of Homologous Compound with New Long-Period Structure," *NIRIM Newsletter*, Mar. 1, 1995, vol. 150, pp. 1-4.
- Nomura, K. et al., "Amorphous Oxide Semiconductors for High-Performance Flexible Thin-Film Transistors," *Japanese Journal of Applied Physics*, 2006, vol. 45, No. 5B, pp. 4303-4308.
- Nomura, K. et al., "Carrier Transport in Transparent Oxide Semiconductor with Intrinsic Structural Randomness Probed Using Single-Crystalline $\text{InGaO}_3(\text{ZnO})_5$ Films," *Applied Physics Letters*, Sep. 13, 2004, vol. 85, No. 11, pp. 1993-1995.
- Nomura, K. et al., "Room-Temperature Fabrication of Transparent Flexible Thin-Film Transistors Using Amorphous Oxide Semiconductors," *Nature*, Nov. 25, 2004, vol. 432, pp. 488-492.
- Nomura, K. et al., "Thin-Film Transistor Fabricated in Single-Crystalline Transparent Oxide Semiconductor," *Science*, May 23, 2003, vol. 300, No. 5623, pp. 1269-1272.
- Nowatari, H. et al., "60.2: Intermediate Connector With Suppressed Voltage Loss for White Tandem OLEDs," *SID Digest '09: SID International Symposium Digest of Technical Papers*, May 31, 2009, vol. 40, pp. 899-902.
- Oba, F. et al., "Defect Energetics in ZnO: A Hybrid Hartree-Fock Density Functional Study," *Physical Review. B*, 2008, vol. 77, pp. 245202-1-245202-6.
- Oh, M.S. et al., "Improving the Gate Stability of ZnO Thin-Film Transistors With Aluminum Oxide Dielectric Layers," *Journal of the Electrochemical Society*, 2008, vol. 155, No. 12, pp. H1009-H1014.
- Ohara, H. et al., "21.3: 4.0 in. QVGA AMOLED Display Using In—Ga—Zn-Oxide TFTs With a Novel Passivation Layer," *SID Digest '09: SID International Symposium Digest of Technical Papers*, May 31, 2009, pp. 284-287.
- Ohara, H. et al., "Amorphous In—Ga—Zn-Oxide TFTs with Suppressed Variation for 4.0 inch QVGA AMOLED Display," *AM-FPD '09 Digest of Technical Papers*, Jul. 1, 2009, pp. 227-230. The Japan Society of Applied Physics.
- Orita, M. et al., "Amorphous Transparent Conductive Oxide $\text{InGaO}_3(\text{ZnO})_m$ ($m<4$): a Zn_{4s} Conductor," *Philosophical Magazine*, 2001, vol. 81, No. 5, pp. 501-515.
- Orita, M. et al., "Mechanism of Electrical Conductivity of Transparent InGaZnO_4 ," *Physical Review. B*, Jan. 15, 2000, vol. 61, No. 3, pp. 1811-1816.
- Osada, T. et al., "15.2: Development of Driver-Integrated Panel using Amorphous In—Ga—Zn-Oxide TFT," *SID Digest '09: SID International Symposium Digest of Technical Papers*, May 31, 2009, pp. 184-187.
- Osada, T. et al., "Development of Driver-Integrated Panel Using Amorphous In—Ga—Zn-Oxide TFT," *AM-FPD '09 Digest of Technical Papers*, Jul. 1, 2009, pp. 33-36.
- Park, J-S. et al., "Amorphous Indium-Gallium-Zinc Oxide TFTs and Their Application for Large Size AMOLED," *AM-FPD '08 Digest of Technical Papers*, Jul. 2, 2008, pp. 275-278.
- Park, J.S. et al., "Dry Etching of ZnO Films and Plasma-Induced Damage to Optical Properties," *Journal of Vacuum Science & Technology B*, Mar. 1, 2003, vol. 21, No. 2, pp. 800-803.
- Park, J-S. et al., "Electronic Transport Properties of Amorphous Indium-Gallium-Zinc Oxide Semiconductor Upon Exposure to Water," *Applied Physics Letters*, 2008, vol. 92, pp. 072104-1-072104-3.
- Park, J.C. et al., "High Performance Amorphous Oxide Thin Film Transistors with Self-Aligned Top-Gate Structure," *IEDM 09: Technical Digest of International Electron Devices Meeting*, Dec. 7, 2009, pp. 191-194.
- Park, J-S. et al., "Improvements in the Device Characteristics of Amorphous Indium Gallium Zinc Oxide Thin-Film Transistors by Ar Plasma Treatment," *Applied Physics Letters*, Jun. 26, 2007, vol. 90, No. 26, pp. 262106-1-262106-3.
- Park, S. et al., "Challenge to Future Displays: Transparent AM-OLED Driven by PEALD Grown ZnO TFT," *IMID '07 Digest*, 2007, pp. 1249-1252.
- Park, Sang-Hee et al., "42.3: Transparent ZnO Thin Film Transistor for the Application of High Aperture Ratio Bottom Emission AM-OLED Display," *SID Digest '08: SID International Symposium Digest of Technical Papers*, May 20, 2008, vol. 39, pp. 629-632.
- Prins, M.W.J. et al., "A Ferroelectric Transparent Thin-Film Transistor," *Applied Physics Letters*, Jun. 17, 1996, vol. 68, No. 25, pp. 3650-3652.
- Sakata, J. et al., "Development of 4.0-in. AMOLED Display With Driver Circuit Using Amorphous In—Ga—Zn-Oxide TFTs," *IDW '09: Proceedings of the 16th International Display Workshops*, 2009, pp. 689-692.
- Son, K-S. et al., "42.4L: Late-News Paper: 4 Inch QVGA AMOLED Driven by the Threshold Voltage Controlled Amorphous GIZO ($\text{Ga}_2\text{O}_3\text{—In}_2\text{O}_3\text{—ZnO}$) TFT," *SID Digest '08: SID International Symposium Digest of Technical Papers*, May 20, 2008, vol. 39, pp. 633-636.
- Takahashi, M. et al., "Theoretical Analysis of IGZO Transparent Amorphous Oxide Semiconductor," *IDW '08: Proceedings of the 15th International Display Workshops*, Dec. 3, 2008, pp. 1637-1640.
- Tsuda, K. et al., "Ultra Low Power Consumption Technologies for Mobile TFT-LCDs," *IDW '02: Proceedings of the 9th International Display Workshops*, Dec. 4, 2002, pp. 295-298.
- Ueno, K. et al., "Field-Effect Transistor on SrTiO_3 With Sputtered Al_2O_3 Gate Insulator," *Applied Physics Letters*, Sep. 1, 2003, vol. 83, No. 9, pp. 1755-1757.

(56)

References Cited

OTHER PUBLICATIONS

Van de Walle, C.G., "Hydrogen as a Cause of Doping in Zinc Oxide," Physical Review Letters, Jul. 31, 2000, vol. 85, No. 5, pp. 1012-1015.

* cited by examiner

FIG. 1A




FIG. 1B




FIG. 1C




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 3A




FIG. 3B

FIG. 3C




FIG. 4A




FIG. 4B




FIG. 4C




FIG. 5A




FIG. 5B




FIG. 5C




FIG. 5D




FIG. 5E




FIG. 5F




FIG. 6A




FIG. 6B




FIG. 7A




FIG. 7B




FIG. 7C




FIG. 7D




FIG. 8A




FIG. 8B




FIG. 8C




FIG. 8D




FIG. 9A




FIG. 9B




FIG. 9C




FIG. 10A




FIG. 10B




FIG. 11




FIG. 12A




FIG. 12B

FIG. 12C




FIG. 13A




FIG. 13B

FIG. 13C




FIG. 14A




FIG. 14B

FIG. 14C




FIG. 15A




FIG. 15B




FIG. 15C




FIG. 16A




FIG. 16B




FIG. 16C




FIG. 17A




FIG. 17B




FIG. 17C




FIG. 18A




FIG. 18B





FIG. 18C








FIG. 20A




FIG. 20B




FIG. 20C




FIG. 21A




FIG. 21B




FIG. 21C




FIG. 22A




FIG. 22B




FIG. 22C




FIG. 23A




FIG. 23B




FIG. 23C




FIG. 24A




FIG. 24B




FIG. 24C




FIG. 25A




FIG. 25B




FIG. 25C




FIG. 26A




FIG. 26B




FIG. 26C




FIG. 28A




FIG. 28B

FIG. 28C




FIG. 29A




FIG. 29B

FIG. 29C




FIG. 30A




FIG. 30B

FIG. 30C




FIG. 31A




FIG. 31B




FIG. 31C




FIG. 32A




FIG. 32B




FIG. 32C




FIG. 33A




FIG. 33B




FIG. 33C




FIG. 34A




FIG. 34B




FIG. 34C




FIG. 35A




FIG. 35B




FIG. 35C




FIG. 36A




FIG. 36B




FIG. 36C




FIG. 37A




FIG. 37B




FIG. 37C




FIG. 38A




FIG. 38B




FIG. 38C




FIG. 39A




FIG. 39B




FIG. 39C




FIG. 40A




FIG. 40B




FIG. 40C




FIG. 41A




FIG. 41B

FIG. 41C




FIG. 42A




FIG. 42B




FIG. 42C




FIG. 43A




FIG. 43B




FIG. 43C




FIG. 44A




FIG. 44B




FIG. 44C




FIG. 45A




FIG. 45B

FIG. 45C




FIG. 46A




FIG. 46B

FIG. 46C




FIG. 47A




FIG. 47B

FIG. 47C




FIG. 48A





FIG. 48B






FIG. 49




FIG. 50

FIG. 51A




FIG. 51B




FIG. 51C




FIG. 51D




FIG. 51E




FIG. 51F




FIG. 52




FIG. 54A 200




FIG. 54B




FIG. 55A




FIG. 55B




FIG. 56A




FIG. 56B




FIG. 57A




FIG. 57B




FIG. 58




FIG. 59A




FIG. 59B




FIG. 59C




FIG. 60A




FIG. 60B




FIG. 61




FIG. 62A




FIG. 62B




FIG. 63A




FIG. 63B




FIG. 63C




FIG. 63D




FIG. 63E




FIG. 64A




FIG. 64B




FIG. 64C




FIG. 64D




FIG. 65A




FIG. 65B




FIG. 65C




FIG. 66A




FIG. 66B




FIG. 66C




FIG. 66D





FIG. 66E



FIG. 66F



METHOD FOR MANUFACTURING SEMICONDUCTOR DEVICE INCLUDING STEP OF SIMULTANEOUS FORMATION OF PLURALITY OF CONTACT OPENINGS

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to, for example, a transistor, a semiconductor device, and manufacturing methods thereof. The present invention relates to, for example, a display device, a light-emitting device, a lighting device, a power storage device, a memory device, a processor, and an electronic device. The present invention relates to a method for manufacturing a display device, a liquid crystal display device, a light-emitting device, a memory device, and an electronic device. The present invention relates to a driving method of a semiconductor device, a display device, a liquid crystal display device, a light-emitting device, a memory device, and an electronic device.

Note that one embodiment of the present invention is not limited to the above technical field. The technical field of one embodiment of the invention disclosed in this specification and the like relates to an object, a method, or a manufacturing method. In addition, one embodiment of the present invention relates to a process, a machine, manufacture, or a composition of matter.

In this specification and the like, a semiconductor device generally means a device that can function by utilizing semiconductor characteristics. A display device, a light-emitting device, a lighting device, an electro-optical device, a semiconductor circuit, and an electronic device include a semiconductor device in some cases.

2. Description of the Related Art

In recent years, a transistor including an oxide semiconductor has attracted attention. An oxide semiconductor can be formed by a sputtering method or the like, and thus can be used for a semiconductor of a transistor in a large display device. In addition, the transistor including an oxide semiconductor is advantageous in reducing capital investment because part of production equipment for a transistor including amorphous silicon can be retrofitted and utilized.

It is known that a transistor including an oxide semiconductor has an extremely low leakage current in an off state. For example, a low-power-consumption CPU utilizing a characteristic of low leakage current of the transistor including an oxide semiconductor is disclosed (see Patent Document 1).

Furthermore, a method for manufacturing a transistor including an oxide semiconductor in which a gate electrode is embedded in an opening is disclosed (see Patent Documents 2 and 3).

REFERENCE

Patent Document

- [Patent Document 1] Japanese Published Patent Application No. 2012-257187
- [Patent Document 2] Japanese Published Patent Application No. 2014-241407
- [Patent Document 3] Japanese Published Patent Application No. 2014-240833

SUMMARY OF THE INVENTION

An object is to provide a minute transistor. Another object is to provide a transistor with low parasitic capacitance.

Another object is to provide a transistor having high frequency characteristics. Another object is to provide a transistor with favorable electrical characteristics. Another object is to provide a transistor having stable electrical characteristics. Another object is to provide a transistor having low off-state current. Another object is to provide a novel transistor. Another object is to provide a semiconductor device including the transistor. Another object is to provide a semiconductor device that operates at high speed. Another object is to provide a novel semiconductor device. Another object is to provide a module including any of the above semiconductor devices. Another object is to provide an electronic device including any of the above semiconductor devices or the module.

Note that the descriptions of these objects do not disturb the existence of other objects. In one embodiment of the present invention, there is no need to achieve all the objects. Other objects will be apparent from and can be derived from the description of the specification, the drawings, the claims, and the like.

(1) One embodiment of the present invention is a method for manufacturing a semiconductor device including a first insulator, a second insulator over the first insulator, a first conductor embedded in the second insulator, a third insulator over the second insulator and the first conductor, a first metal oxide over the third insulator, a fourth insulator over the first metal oxide, a fifth insulator over the fourth insulator, an oxide semiconductor over the fifth insulator, a second conductor and a third conductor over the oxide semiconductor, a sixth insulator over the fourth insulator, the second conductor, the third conductor, and the oxide semiconductor, a seventh insulator over the sixth insulator, a fourth conductor over the seventh insulator, a second metal oxide over the sixth insulator and the fourth conductor, an eighth insulator over the second metal oxide, a first opening reaching the first conductor through the eighth insulator, the second metal oxide, the seventh insulator, the sixth insulator, the fourth insulator, the first metal oxide, and the third insulator, a second opening reaching the second conductor through the eighth insulator, the second metal oxide, the seventh insulator, and the sixth insulator, and a third opening reaching the fourth conductor through the eighth insulator and the second metal oxide. The method includes the following steps: forming a fifth conductor over the eighth insulator; forming a ninth insulator over the fifth conductor; forming a resist mask over the ninth insulator by a lithography method; etching part of the ninth insulator and part of the fifth conductor to form a hard mask layer including the ninth insulator and the fifth conductor; and performing first etching and second etching using the hard mask layer as a mask to form the first opening, the second opening, and the third opening. In the first etching, the eighth insulator is etched for forming the first opening, the second opening, and the third opening. In the second etching, the second metal oxide, the seventh insulator, the sixth insulator, the fourth insulator, the first metal oxide, and the third insulator are etched for forming the first opening; the second metal oxide, the seventh insulator, and the sixth insulator are etched for forming the second opening; and the second metal oxide is etched for forming the third opening.

(2) Another embodiment of the present invention is the method for manufacturing a semiconductor device described in (1) where the first conductor, the second conductor, the third conductor, and the fourth conductor comprise a same conductive material.

(3) Another embodiment of the present invention is the method for manufacturing a semiconductor device described

in (1) or (2) where the first conductor, the second conductor, the third conductor, the fourth conductor, and the fifth conductor comprise a same conductive material.

(4) Another embodiment of the present invention is the method for manufacturing a semiconductor device described in any one of (1) to (3) where in the first etching step, an etching rate of the ninth insulator is lower than that of the eighth insulator.

(5) Another embodiment of the present invention is the method for manufacturing a semiconductor device described in any one of (1) to (4) where in the first etching step, an etching rate of the second metal oxide is lower than that of the eighth insulator.

(6) Another embodiment of the present invention is the method for manufacturing a semiconductor device described in any one of (1) to (5) where in the second etching step, an etching rate of the fourth conductor is lower than etching rates of the first metal oxide film and the second metal oxide film.

(7) Another embodiment of the present invention is a method for manufacturing a semiconductor device including a first insulator, a second insulator over the first insulator, a first conductor embedded in the second insulator, a third insulator over the second insulator and the first conductor, a first metal oxide over the third insulator, a fourth insulator over the first metal oxide, a fifth insulator over the fourth insulator, an oxide semiconductor over the fifth insulator, a second conductor and a third conductor over the oxide semiconductor, a sixth insulator over the fourth insulator, the second conductor, the third conductor, and the oxide semiconductor, a seventh insulator over the oxide semiconductor, an eighth insulator over the seventh insulator, a fourth conductor over the eighth insulator, a ninth insulator over the sixth insulator, the seventh insulator, the eighth insulator, and the fourth conductor, a second metal oxide over the ninth insulator, a tenth insulator over the second metal oxide, a first opening reaching the first conductor through the tenth insulator, the second metal oxide, the ninth insulator, the sixth insulator, the fourth insulator, the first metal oxide, and the third insulator, a second opening reaching the second conductor through the tenth insulator, the second metal oxide, the ninth insulator, and the sixth insulator, and a third opening reaching the fourth conductor through the tenth insulator, the second metal oxide, and the ninth insulator. The method includes the following steps: forming a fifth conductor over the tenth insulator; forming an eleventh insulator over the fifth conductor; forming a resist mask over the eleventh insulator by a lithography method; etching part of the eleventh insulator and part of the fifth conductor to form a hard mask layer including the eleventh insulator and the fifth conductor; and performing first etching and second etching using the hard mask layer as a mask to form the first opening, the second opening, and the third opening. In the first etching, the tenth insulator is etched for forming the first opening, the second opening, and the third opening. In the second etching, the second metal oxide, the ninth insulator, the sixth insulator, the fourth insulator, the first metal oxide, and the third insulator are etched for forming the first opening; the second metal oxide, the ninth insulator, and the sixth insulator are etched for forming the second opening; and the second metal oxide and the ninth insulator are etched for forming the third opening.

(8) Another embodiment of the present invention is the method for manufacturing a semiconductor device described in (7) where the first conductor, the second conductor, the third conductor, and the fourth conductor comprise a same conductive material.

(9) Another embodiment of the present invention is the method for manufacturing a semiconductor device described in (7) or (8) where the first conductor, the second conductor, the third conductor, the fourth conductor, and the fifth conductor comprise a same conductive material.

(10) Another embodiment of the present invention is the method for manufacturing a semiconductor device described in any one of (7) to (9) where in the first etching step, an etching rate of the eleventh insulator is lower than that of the tenth insulator.

(11) Another embodiment of the present invention is the method for manufacturing a semiconductor device described in any one of (7) to (10) where in the first etching step, an etching rate of the second metal oxide is lower than that of the tenth insulator.

(12) Another embodiment of the present invention is the method for manufacturing a semiconductor device described in any one of (7) to (11) where in the second etching step, an etching rate of the fourth conductor is lower than etching rates of the first metal oxide film and the second metal oxide film.

Note that in the method for manufacturing a semiconductor device of one embodiment of the present invention, the oxide semiconductor may be replaced with another semiconductor.

A minute transistor can be provided. Alternatively, a transistor with low parasitic capacitance can be provided. Alternatively, a transistor having high frequency characteristics can be provided. Alternatively, a transistor with favorable electrical characteristics can be provided. Alternatively, a transistor with stable electrical characteristics can be provided. Alternatively, a transistor with low off-state current can be provided. Alternatively, a novel transistor can be provided. Alternatively, a semiconductor device including the transistor can be provided. Alternatively, a semiconductor device which can operate at high speed can be provided. Alternatively, a novel semiconductor device can be provided. A module including any of the above semiconductor devices can be provided. An electronic device including any of the above semiconductor devices or the module can be provided.

Note that the description of these effects does not disturb the existence of other effects. One embodiment of the present invention does not necessarily achieve all the effects listed above. Other effects will be apparent from and can be derived from the description of the specification, the drawings, the claims, and the like.

BRIEF DESCRIPTION OF THE DRAWINGS

In the accompanying drawings:

FIGS. 1A to 1C are a top view and cross-sectional views of a transistor of one embodiment of the present invention;

FIGS. 2A to 2C are a top view and cross-sectional views of a transistor of one embodiment of the present invention;

FIGS. 3A to 3C are a top view and cross-sectional views of a transistor of one embodiment of the present invention;

FIGS. 4A to 4C are a top view and cross-sectional views of a transistor of one embodiment of the present invention;

FIGS. 5A to 5F are cross-sectional views each illustrating part of a transistor of one embodiment of the present invention;

FIGS. 6A and 6B are cross-sectional views each illustrating a transistor of one embodiment of the present invention;

FIGS. 7A to 7D are Cs-corrected high-resolution TEM images of a cross section of a CAAC-OS and a cross-sectional schematic view of a CAAC-OS;

FIGS. 8A to 8D are Cs-corrected high-resolution TEM images of a plane of a CAAC-OS;

FIGS. 9A to 9C show structural analysis of a CAAC-OS and a single crystal oxide semiconductor by XRD;

FIGS. 10A and 10B show electron diffraction patterns of a CAAC-OS;

FIG. 11 shows a change in crystal part of an In—Ga—Zn oxide induced by electron irradiation;

FIGS. 12A to 12C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 13A to 13C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 14A to 14C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 15A to 15C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 16A to 16C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 17A to 17C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 18A to 18C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 19A to 19C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 20A to 20C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 21A to 21C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 22A to 22C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 23A to 23C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 24A to 24C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 25A to 25C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 26A to 26C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 27A to 27C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 28A to 28C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 29A to 29C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 30A to 30C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 31A to 31C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 32A to 32C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 33A to 33C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 34A to 34C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 35A to 35C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 36A to 36C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 37A to 37C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 38A to 38C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 39A to 39C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 40A to 40C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 41A to 41C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 42A to 42C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 43A to 43C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 44A to 44C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 45A to 45C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 46A to 46C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 47A to 47C are a top view and cross-sectional views illustrating a method for manufacturing a transistor of one embodiment of the present invention;

FIGS. 48A and 48B are each a circuit diagram of a memory device of one embodiment of the present invention;

FIG. 49 is a cross-sectional view of a semiconductor device of one embodiment of the present invention;

FIG. 50 is a cross-sectional view of a semiconductor device of one embodiment of the present invention;

FIGS. 51A to 51F are cross sectional views and circuit diagrams of a semiconductor device of one embodiment of the present invention;

FIG. 52 is a block diagram of a CPU of one embodiment of the present invention;

FIG. 53 is a circuit diagram of a memory element of one embodiment of the present invention;

FIGS. 54A and 54B are plan views of imaging devices;

FIGS. 55A and 55B are plan views of pixels of an imaging device;

FIGS. 56A and 56B are cross-sectional views of an imaging device;

FIGS. 57A and 57B are cross-sectional views of imaging devices;

FIG. 58 illustrates a configuration example of an RF tag;

FIGS. 59A to 59C are a circuit diagram, a top view, and a cross-sectional view of a semiconductor device of one embodiment of the present invention;

FIGS. 60A and 60B are a circuit diagram and a cross-sectional view of a semiconductor device of one embodiment of the present invention;

FIG. 61 illustrates a display module;

FIGS. 62A and 62B are perspective views illustrating a cross-sectional structure of a package using a lead frame interposer;

FIGS. 63A to 63E each illustrate an electronic device of one embodiment of the present invention;

FIGS. 64A to 64D each illustrate an electronic device of one embodiment of the present invention;

FIGS. 65A to 65C each illustrate an electronic device of one embodiment of the present invention; and

FIGS. 66A to 66F illustrate application examples of an RF tag of one embodiment of the present invention.

DETAILED DESCRIPTION OF THE INVENTION

Hereinafter, embodiment of the present invention will be described in detail with the reference to the drawings. However, the present invention is not limited to the description below, and it is easily understood by those skilled in the art that modes and details disclosed herein can be modified in various ways. Further, the present invention is not construed as being limited to description of the embodiments and the examples. In describing structures of the present invention with reference to the drawings, common reference numerals are used for the same portions in different drawings. Note that the same hatched pattern is applied to similar parts, and the similar parts are not especially denoted by reference numerals in some cases.

Note that the size, the thickness of films (layers), or regions in drawings is sometimes exaggerated for simplicity.

In this specification, for example, when the shape of an object is described with the use of a term such as “diameter”, “grain size (diameter)”, “dimension”, “size”, or “width”, the term can be regarded as the length of one side of a minimal cube where the object fits, or an equivalent circle diameter of a cross section of the object. The term “equivalent circle diameter of a cross section of the object” refers to the diameter of a perfect circle having the same area as that of the cross section of the object.

A voltage usually refers to a potential difference between a given potential and a reference potential (e.g., a ground potential (GND) or a source potential). A voltage can be referred to as a potential and vice versa.

Note that the ordinal numbers such as “first” and “second” in this specification are used for convenience and do not denote the order of steps or the stacking order of layers. Therefore, for example, description can be made even when “first” is replaced with “second” or “third”, as appropriate. In addition, the ordinal numbers in this specification and the like are not necessarily the same as those which specify one embodiment of the present invention.

Note that an impurity in a semiconductor refers to, for example, elements other than the main components of the semiconductor. For example, an element with a concentration of lower than 0.1 atomic % is an impurity. When an

impurity is contained, the density of states (DOS) may be formed in a semiconductor, the carrier mobility may be decreased, or the crystallinity may be decreased, for example. In the case where the semiconductor is an oxide semiconductor, examples of an impurity which changes characteristics of the semiconductor include Group 1 elements, Group 2 elements, Group 14 elements, Group 15 elements, and transition metals other than the main components; specifically, there are hydrogen (included in water), lithium, sodium, silicon, boron, phosphorus, carbon, and nitrogen, for example. In the case of an oxide semiconductor, oxygen vacancy may be formed by entry of impurities such as hydrogen. Further, in the case where the semiconductor is a silicon film, examples of an impurity which changes characteristics of the semiconductor include oxygen, Group 1 elements except hydrogen, Group 2 elements, Group 13 elements, and Group 15 elements.

Note that the channel length refers to, for example, a distance between a source (source region or source electrode) and a drain (drain region or drain electrode) in a region where a semiconductor (or a portion where a current flows in a semiconductor when a transistor is on) and a gate electrode overlap with each other or a region where a channel is formed in a top view of the transistor. In one transistor, channel lengths in all regions are not necessarily the same. In other words, the channel length of one transistor is not limited to one value in some cases. Therefore, in this specification, the channel length is any one of values, the maximum value, the minimum value, or the average value in a region where a channel is formed.

The channel width refers to, for example, the length of a portion where a source and a drain face each other in a region where a semiconductor (or a portion where a current flows in a semiconductor when a transistor is on) and a gate electrode overlap with each other, or a region where a channel is formed. In one transistor, channel widths in all regions are not necessarily the same. In other words, the channel width of one transistor is not limited to one value in some cases. Therefore, in this specification, the channel width is any one of values, the maximum value, the minimum value, or the average value in a region where a channel is formed.

Note that depending on transistor structures, a channel width in a region where a channel is actually formed (hereinafter referred to as an effective channel width) is different from a channel width shown in a top view of a transistor (hereinafter referred to as an apparent channel width) in some cases. For example, in a transistor having a three-dimensional structure, an effective channel width is greater than an apparent channel width shown in a top view of the transistor, and its influence cannot be ignored in some cases. For example, in a miniaturized transistor having a three-dimensional structure, the proportion of a channel formation region formed in a side surface of a semiconductor is increased in some cases. In that case, an effective channel width obtained when a channel is actually formed is greater than an apparent channel width shown in the top view.

In a transistor having a three-dimensional structure, an effective channel width is difficult to measure in some cases. For example, estimation of an effective channel width from a design value requires an assumption that the shape of a semiconductor is known. Therefore, in the case where the shape of a semiconductor is not known accurately, it is difficult to measure an effective channel width accurately.

Therefore, in this specification, in a top view of a transistor, an apparent channel width that is a length of a portion

where a source and a drain face each other in a region where a semiconductor and a gate electrode overlap with each other is referred to as a surrounded channel width (SCW) in some cases. Furthermore, in this specification, in the case where the term “channel width” is simply used, it may denote a surrounded channel width and an apparent channel width. Alternatively, in this specification, in the case where the term “channel width” is simply used, it may denote an effective channel width in some cases. Note that the values of a channel length, a channel width, an effective channel width, an apparent channel width, a surrounded channel width, and the like can be determined by obtaining and analyzing a cross-sectional TEM image and the like.

Note that in the case where field-effect mobility, a current value per channel width, and the like of a transistor are obtained by calculation, a surrounded channel width may be used for the calculation. In that case, the values may be different from those calculated using an effective channel width in some cases.

Note that in this specification, the description “A has a shape such that an end portion extends beyond an end portion of B” may indicate, for example, the case where at least one of end portions of A is positioned on an outer side of at least one of end portions of B in a top view or a cross-sectional view. Thus, the description “A has a shape such that an end portion extends beyond an end portion of B” can be read as the description “one end portion of A is positioned on an outer side of one end portion of B in a top view,” for example.

In this specification, the term “parallel” indicates that the angle formed between two straight lines is greater than or equal to -10° and less than or equal to 10° , and accordingly also includes the case where the angle is greater than or equal to -5° and less than or equal to 5° . The term “perpendicular” indicates that the angle formed between two straight lines is greater than or equal to 80° and less than or equal to 100° , and accordingly also includes the case where the angle is greater than or equal to 85° and less than or equal to 95° .

In this specification, the trigonal and rhombohedral crystal systems are included in the hexagonal crystal system.

Embodiment 1

<Transistor Structure 1>

A structure of a transistor included in a semiconductor device of one embodiment of the present invention will be described below.

FIGS. 1A to 1C are a top view and cross-sectional views of a semiconductor device of one embodiment of the present invention. FIG. 1A is the top view, and FIGS. 1B and 1C are the cross-sectional views taken along dashed-dotted lines A1-A2 and A3-A4 in FIG. 1A, respectively. Note that for simplification of the drawing, some components are not illustrated in the top view in FIG. 1A.

In FIGS. 1B and 1C, the transistor includes an insulator 401 over a substrate 400; an insulator 301 over the insulator 401; an insulator 302 over the insulator 301 and conductors 310a and 310b which are in openings of the insulator 301; an electron trap layer 303 over the insulator 302; an insulator 402 over the electron trap layer 303; an insulator 406a over the insulator 402; a semiconductor 406b over the insulator 406a; conductors 416a1 and 416a2 each having a region in contact with a top surface of the semiconductor 406b; an insulator 406c having regions in contact with the top of the insulator 402, side surfaces of the insulator 406a, the top surface and side surfaces of the semiconductor 406b, a top

surface and side surfaces of the conductor 416a1, and a top surface and side surfaces of the conductor 416a2; an insulator 412 over the insulator 406c; a conductor 404 overlapping with the semiconductor 406b with the insulator 412 positioned therebetween; an insulator 408 over the insulator 412 and the conductor 404; an insulator 410 over the insulator 408; a first opening reaching the conductor 310b through the insulators 410, 408, 412, 406c, and 402, the electron trap layer 303, and the insulator 302; a second opening reaching the conductor 416a1 through the insulators 410, 408, 412, and 406c; a third opening reaching the conductor 416a2 through the insulators 410, 408, 412, and 406c; a fourth opening reaching the conductor 404 through the insulators 410 and 408; a conductor 433, a conductor 431, a conductor 429, and a conductor 437 that are embedded in the first opening, the second opening, the third opening, and the fourth opening, respectively; a conductor 434 over the insulator 410, which includes a region in contact with the conductor 433; a conductor 432 over the insulator 410, which includes a region in contact with the conductor 431; a conductor 430 over the insulator 410, which includes a region in contact with the conductor 429; and a conductor 438 over the insulator 410, which includes a region in contact with the conductor 437.

The cross sections of the openings in one embodiment of the present invention are described with reference to FIGS. 5A to 5C. FIGS. 5A to 5C are enlarged cross sectional views of the openings of the transistor shown in FIGS. 1A to 1C. FIG. 5A is an enlarged view of the first opening. FIG. 5B is an enlarged view of the second opening. FIG. 5C is an enlarged view of the fourth opening. Note that in FIGS. 5A to 5C, the insulator 410 is thin in its thickness direction for convenience of explanation.

Although the openings in FIGS. 1B and 1C have straight cross sections, the openings each may have a shape in which the opening diameter of a layer is larger than those of layers positioned thereover and thereunder or larger than that of a layer positioned thereover or thereunder, or a shape with a smaller part (constricted part) than those of layers positioned thereover and thereunder or larger than that of a layer positioned thereover or thereunder as illustrated in FIGS. 5A to 5C. In the first opening in FIG. 5A, the opening diameter of each of the insulators 410, 412, 402, and 302 is larger than those of layers positioned thereover and thereunder or that of a layer positioned thereover or thereunder. In other words, the opening diameter of each of the insulators 408 and 406c and the electron trap layer 303 is smaller than those of layers positioned thereover and thereunder. In other words, the opening of each of the insulator 408, the insulator 406c, and the electron trap layer 303 is constricted. In the second opening in FIG. 5B, the opening diameter of each of the insulators 410 and 412 is larger than those of layers positioned thereover and thereunder or that of a layer positioned thereunder. In other words, the opening diameter of each of the insulators 408 and 406c is smaller than those of layers positioned thereover and thereunder or that of a layer positioned thereover. In other words, the opening of each of the insulators 408 and 406c is constricted. In the fourth opening in FIG. 5C, the opening diameter of the insulator 410 is larger than that of a layer positioned thereunder. In other words, the opening diameter of the insulator 408 is smaller than that of a layer positioned thereover. In other words, the opening of the insulator 408 is constricted. Such shapes are obtained in some cases when etching rates of the insulators 410, 412, 402, and 302 are higher than those of the insulator 408, the insulator 406a, and the electron trap layer 303.

In a bottom part of the opening in FIG. 5B, part of the top surface of the conductor **416a1** is dented. The reason for this is because the time needed for forming the first opening and the time needed for forming the second opening are different from each other, the conductor **416a1** is over-etched, that is, the conductor **416a1** is partly etched until the first opening is formed after the second opening is formed. Similarly, in a bottom part of the opening in FIG. 5C, part of the top surface of the conductor **404** is dented. The reason for this is because the time needed for forming the first opening and the time needed for forming the fourth opening are different from each other, the conductor **404** is over-etched, that is, the conductor **404** is partly etched until the first opening is formed after the fourth opening is formed. Note that in FIGS. 5A to 5C, examples are illustrated in which the opening diameter of a layer is larger than those of layers positioned thereover and thereunder or the conductor has a dented portion; however, the size of the expanded portion of the opening and the dented portion of the conductive film are not limited to those examples.

Note that the semiconductor **406b** includes a region **407** in which the top surface of the semiconductor **406b** is in contact with the conductors **416a1** and **416a2**.

In the transistor, the conductor **404** functions as a first gate electrode. Furthermore, the conductor **404** can have a stacked structure including a conductor that hardly allows oxygen to pass therethrough. For example, when the conductor that hardly allows oxygen to pass therethrough is formed as a lower layer, an increase in the electric resistance value due to oxidation of the conductor **404** can be prevented. The insulator **412** functions as a gate insulator.

The conductors **416a1** and **416a2** function as a source electrode and a drain electrode of the transistor. The conductors **416a1** and **416a2** each can have a stacked structure including a conductor that hardly allows oxygen to pass therethrough. For example, when the conductor that hardly allows oxygen to pass therethrough is formed as an upper layer, an increase in the electric resistance value due to oxidation of the conductors **416a1** and **416a2** can be prevented. Note that the electric resistance values of the conductors can be measured by a two-terminal method or the like.

The resistance of the semiconductor **406b** can be controlled by a potential applied to the conductor **404**. That is, conduction or non-conduction between the conductors **416a1** and **416a2** can be controlled by the potential applied to the conductor **404**.

As illustrated in FIGS. 1B and 1C, the top surface of the semiconductor **406b** is in contact with the conductors **416a1** and **416a2**. In addition, the insulator **406a** and the semiconductor **406b** can be electrically surrounded by an electric field of the conductor **404** functioning as the first gate electrode. A structure in which a semiconductor is electrically surrounded by an electric field of a gate electrode is referred to as a surrounded channel (s-channel) structure. Therefore, a channel is formed in the entire semiconductor **406b** (bulk) in some cases. In the s-channel structure, a large amount of current can flow between a source and a drain of the transistor, so that an on-state current can be increased. In addition, since the insulator **406a** and the semiconductor **406b** are surrounded by the electric field of the conductor **404**, an off-state current can be decreased.

The conductor **310a** functions as a second gate electrode. The conductor **310a** can be a multilayer film containing a conductor that hardly allows oxygen to pass therethrough. When the conductor **310a** is a multilayer film including a conductive film that hardly allows oxygen to pass there-

through, a reduction in conductivity caused by oxidation of the conductor **310a** can be prevented. The insulator **302**, the electron trap layer **303**, and the insulator **402** function as a second gate insulating film. The threshold voltage of the transistor can be controlled by a potential applied to the conductor **310a**. In addition, by the potential applied to the conductor **310a**, electrons are injected to the electron trap layer **303** and thus the threshold voltage of the transistor can be controlled. The first gate electrode and the second gate electrode electrically connected to each other can increase the on-state current. Note that the function of the first gate electrode and that of the second gate electrode may be interchanged.

FIG. 6A illustrates an example in which the first gate electrode and the second gate electrode are electrically connected. In an opening reaching the conductor **404** through the insulator **410**, a conductor **440** is embedded, and a top surface of the conductor **440** is electrically connected to a conductor **444** formed over the insulator **410**. In an opening reaching a conductor **310c** through the insulator **410**, the insulator **408**, the insulator **412**, the insulator **406c**, the insulator **402**, the electron trap layer **303**, and the insulator **302**, the conductor **442** is embedded, and a top surface of the conductor **442** and the conductor **444** are electrically connected. That is, the conductor **404** functioning as the first gate electrode is electrically connected to the conductor **310c** functioning as the second gate electrode through the conductors **440**, **444**, and **442**.

Note that the transistor is surrounded by an insulator which has a function of blocking oxygen and impurities such as hydrogen, whereby stable electrical characteristics can be obtained. For example, as the insulator **408**, an insulator which has a function of blocking oxygen and impurities such as hydrogen may be used.

An insulator which has a function of blocking oxygen and impurities such as hydrogen may be formed to have a single-layer structure or a stacked-layer structure including an insulator containing, for example, boron, carbon, nitrogen, oxygen, fluorine, magnesium, aluminum, silicon, phosphorus, chlorine, argon, gallium, germanium, yttrium, zirconium, lanthanum, neodymium, hafnium, or tantalum.

Furthermore, for example, the insulator **408** may be formed using a metal oxide such as aluminum oxide, magnesium oxide, gallium oxide, germanium oxide, yttrium oxide, zirconium oxide, lanthanum oxide, neodymium oxide, hafnium oxide, or tantalum oxide; silicon nitride oxide; or silicon nitride. Note that the insulator **408** preferably contains aluminum oxide. For example, when the insulator **408** is formed using plasma including oxygen, oxygen can be added to the insulator **412** serving as a base layer of the insulator **408**. The added oxygen becomes excess oxygen in the insulator **412**. When the insulator **408** contains aluminum oxide, entry of impurities such as hydrogen into the semiconductor **406b** can be inhibited. Furthermore, when the insulator **408** contains aluminum oxide, for example, outward diffusion of excess oxygen added to the insulator **412** described above can be reduced.

The insulator **401** may be formed using, for example, aluminum oxide, magnesium oxide, silicon nitride oxide, silicon nitride, gallium oxide, germanium oxide, yttrium oxide, zirconium oxide, lanthanum oxide, neodymium oxide, hafnium oxide, or tantalum oxide. Note that the insulator **401** preferably includes aluminum oxide or silicon nitride. For example, when the insulator **401** includes aluminum oxide or silicon nitride, entry of impurities such as hydrogen into the semiconductor **406b** can be inhibited.

Furthermore, when the insulator **401** includes aluminum oxide or silicon nitride, for example, outward diffusion of oxygen can be reduced.

The insulator **301** may be formed to have, for example, a single-layer structure or a stacked-layer structure including an insulator containing boron, carbon, nitrogen, oxygen, fluorine, magnesium, aluminum, silicon, phosphorus, chlorine, argon, gallium, germanium, yttrium, zirconium, lanthanum, neodymium, hafnium, or tantalum. For example, the insulator **301** preferably includes silicon oxide or silicon oxynitride.

The electron trap layer **303** may be formed to have, for example, a single-layer structure or a stacked-layer structure including an insulator or a metal oxide film containing boron, carbon, nitrogen, oxygen, fluorine, magnesium, aluminum, silicon, phosphorus, chlorine, argon, gallium, germanium, yttrium, zirconium, lanthanum, neodymium, hafnium, or tantalum. For example, the electron trap layer **303** preferably contains silicon nitride, hafnium oxide, or aluminum oxide.

The insulators **302** and **402** may each be formed to have, for example, a single-layer structure or a stacked-layer structure including an insulator containing boron, carbon, nitrogen, oxygen, fluorine, magnesium, aluminum, silicon, phosphorus, chlorine, argon, gallium, germanium, yttrium, zirconium, lanthanum, neodymium, hafnium, or tantalum. For example, the insulator **402** preferably contains silicon oxide or silicon oxynitride.

Note that the insulator **410** preferably includes an insulator with a low dielectric constant. For example, the insulator **410** preferably includes silicon oxide, silicon oxynitride, silicon nitride oxide, silicon nitride, silicon oxide to which fluorine is added, silicon oxide to which carbon is added, silicon oxide to which carbon and nitrogen are added, porous silicon oxide, a resin, or the like. Alternatively, the insulator **410** preferably has a stacked structure of a resin and silicon oxide, silicon oxynitride, silicon nitride oxide, silicon nitride, silicon oxide to which fluorine is added, silicon oxide to which carbon is added, silicon oxide to which carbon and nitrogen are added, or porous silicon oxide. When silicon oxide or silicon oxynitride, which is thermally stable, is combined with a resin, the stacked-layer structure can have thermal stability and a low dielectric constant. Examples of the resin include polyester, polyolefin, polyamide (e.g., nylon or aramid), polyimide, polycarbonate, and acrylic.

The insulator **412** may be formed to have, for example, a single-layer structure or a stacked-layer structure including an insulator containing boron, carbon, nitrogen, oxygen, fluorine, magnesium, aluminum, silicon, phosphorus, chlorine, argon, gallium, germanium, yttrium, zirconium, lanthanum, neodymium, hafnium, or tantalum. For example, the insulator **412** preferably includes silicon oxide or silicon oxynitride.

Note that the insulator **412** preferably contains an insulator with a high dielectric constant. For example, the insulator **412** preferably includes gallium oxide, hafnium oxide, oxide including aluminum and hafnium, oxynitride including aluminum and hafnium, oxide including silicon and hafnium, oxynitride including silicon and hafnium, or the like. The insulator **412** preferably has a stacked-layer structure including silicon oxide or silicon oxynitride and an insulator with a high dielectric constant. Because silicon oxide and silicon oxynitride have thermal stability, combination of silicon oxide or silicon oxynitride with an insulator with a high dielectric constant allows the stacked-layer structure to be thermally stable and have a high dielectric

constant. For example, when an aluminum oxide, a gallium oxide, or a hafnium oxide of the insulator **412** is on the insulator **406c** side, entry of silicon included in the silicon oxide or the silicon oxynitride into the semiconductor **406b** can be suppressed. When silicon oxide or silicon oxynitride is on the insulator **406c** side, for example, trap centers might be formed at the interface between aluminum oxide, gallium oxide, or hafnium oxide and silicon oxide or silicon oxynitride. The trap centers can shift the threshold voltage of the transistor in the positive direction by trapping electrons in some cases.

Each of the conductors **416a1** and **416a2** may be formed to have a single-layer structure or a stacked-layer structure including a conductor containing, for example, one or more kinds of boron, nitrogen, oxygen, fluorine, silicon, phosphorus, aluminum, titanium, chromium, manganese, cobalt, nickel, copper, zinc, gallium, yttrium, zirconium, molybdenum, ruthenium, platinum, silver, indium, tin, tantalum, and tungsten. Alternatively, a film of an alloy or compound containing the above element may be used: a conductor containing aluminum, a conductor containing copper and titanium, a conductor containing copper and manganese, a conductor containing indium, tin, and oxygen, a conductor containing titanium and nitrogen, or the like may be used.

Each of the conductors **310a**, **310b**, **310c**, **404**, **429**, **430**, **431**, **432**, **433**, **434**, **437**, **438**, **440**, **442**, and **444** may be formed to have, for example, a single-layer structure or a stacked-layer structure including a conductor containing one or more kinds of boron, nitrogen, oxygen, fluorine, silicon, phosphorus, aluminum, titanium, chromium, manganese, cobalt, nickel, copper, zinc, gallium, yttrium, zirconium, molybdenum, ruthenium, silver, indium, tin, tantalum, and tungsten. Alternatively, a film of an alloy or compound containing the above element may be used: a conductor containing aluminum, a conductor containing copper and titanium, a conductor containing copper and manganese, a conductor containing indium, tin, and oxygen, a conductor containing titanium and nitrogen, or the like may be used.

Each of the conductors **429**, **430**, **431**, **432**, **433**, **434**, **437**, and **438** may be formed to have a single-layer structure or a stacked-layer structure including a conductor containing, for example, one or more kinds of boron, nitrogen, oxygen, fluorine, silicon, phosphorus, aluminum, titanium, chromium, manganese, cobalt, nickel, copper, zinc, gallium, yttrium, zirconium, molybdenum, ruthenium, silver, indium, tin, tantalum, and tungsten. Alternatively, a film of an alloy or compound containing the above element may be used: a conductor containing aluminum, a conductor containing copper and titanium, a conductor containing copper and manganese, a conductor containing indium, tin, and oxygen, a conductor containing titanium and nitrogen, or the like may be used.

As the semiconductor **406b**, an oxide semiconductor is preferably used. However, silicon (including strained silicon), germanium, silicon germanium, silicon carbide, gallium arsenide, aluminum gallium arsenide, indium phosphide, gallium nitride, an organic semiconductor, or the like can be used in some cases.

The insulator **406a** and the insulator **406c** are desirably oxides including one or more, or two or more elements other than oxygen included in the semiconductor **406b**. However, silicon (including strained silicon), germanium, silicon germanium, silicon carbide, gallium arsenide, aluminum gallium arsenide, indium phosphide, gallium nitride, an organic semiconductor, or the like can be used in some cases.

<Transistor Structure 2>

A transistor having a structure different from that in FIGS. 1A to 1C will be described with reference to FIGS. 2A to 2C. FIGS. 2A to 2C are a top view and cross-sectional views of a semiconductor device of one embodiment of the present invention. FIG. 2A is the top view, and FIGS. 2B and 2C are the cross-sectional views taken along dashed-dotted lines A1-A2 and A3-A4 in FIG. 2A, respectively. Note that for simplification of the drawing, some components are not illustrated in the top view in FIG. 2A.

As illustrated in FIGS. 2A to 2C, the transistor has a structure different from that in FIGS. 1A to 1C in that the conductor 404 functioning as the first gate electrode does not have a region overlapping with the conductors 416a1 and 416a2 functioning as the source electrode and the drain electrode.

Since the conductor 404 functioning as the first gate electrode does not have the region overlapping with the conductors 416a1 and 416a2 functioning as the source electrode and the drain electrode, parasitic capacitance is not generated between the conductor 404 functioning as the gate electrode and the conductor 416a1 or the 416a2 functioning as the source electrode or the drain electrode, which is favorable for high-speed operation of the transistor. In addition, this structure can prevent leakage current between the conductor 404 functioning as the first gate electrode and the conductor 416a1 or 416a2 functioning as the source electrode or the drain electrode. For the other components as those in FIGS. 1A to 1C, refer to the above description.

<Transistor Structure 3>

A transistor having a structure different from that in FIGS. 2A to 2C will be described with reference to FIGS. 3A to 3C. FIGS. 3A to 3C are a top view and cross-sectional views of a semiconductor device of one embodiment of the present invention. FIG. 3A is the top view, and FIGS. 3B and 3C are the cross-sectional views taken along dashed-dotted lines A1-A2 and A3-A4 in FIG. 3A, respectively. Note that for simplification of the drawing, some components are not illustrated in the top view in FIG. 3A.

As illustrated in FIGS. 3A to 3C, the transistor has a structure different from that in FIGS. 2A to 2C in that it does not include the conductors 416a1 and the 416a2 functioning as the source electrode and the drain electrode, and includes: regions 407a1 and 407a2 functioning as a source region and a drain region; an opening reaching the insulator 406a through the insulator 410, the insulator 408, the insulator 412, the region 407a1, and the semiconductor 406b; and an opening reaching the insulator 406a through the insulator 410, the insulator 408, the insulator 412, the region 407a2, and the semiconductor 406b. For the other components, refer to the above description.

<Transistor Structure 4>

A transistor having a structure different from that in FIGS. 1A to 1C will be described with reference to FIGS. 4A to 4C. FIGS. 4A to 4C are a top view and cross-sectional views of a semiconductor device of one embodiment of the present invention. FIG. 4A is the top view, and FIGS. 4B and 4C are the cross-sectional views taken along dashed-dotted lines A1-A2 and A3-A4 in FIG. 4A, respectively. Note that for simplification of the drawing, some components are not illustrated in the top view in FIG. 4A.

In FIGS. 4B and 4C, the transistor includes the insulator 401 over the substrate 400; the insulator 301 over the insulator 401; the insulator 302 over the insulator 301 and conductors 310a and 310b which are in the openings of the insulator 301; the electron trap layer 303 over the insulator 302; the insulator 402 over the electron trap layer 303; the

insulator 406a over the insulator 402; the semiconductor 406b over the insulator 406a; the conductors 416a1 and 416a2 each having the region in contact with the top surface of the semiconductor 406b; the insulator 410 in contact with the top surfaces of the conductors 416a1 and 416a2; the insulator 406c in contact with the top surface of the semiconductor 406b; the insulator 412 over the insulator 406c; the conductor 404 over the semiconductor 406b with the insulators 412 and 406c positioned therebetween; an insulator 418 over the insulator 410, the conductor 404, the insulator 412, and the conductor 404; the insulator 408 over the insulator 418; an insulator 428 over the insulator 408; the first opening reaching the conductor 310b through the insulators 428, 408, 418, 410, and 402, the electron trap layer 303, and the insulator 302; the second opening reaching the conductor 416a1 through the insulators 428, 408, 418, and 410; the third opening reaching the conductor 416a2 through the insulators 428, 408, 418, and 410; the fourth opening reaching the conductor 404 through the insulators 428, 408, and 418; the conductor 433, the conductor 431, the conductor 429, and the conductor 437 that are embedded in the first opening, the second opening, the third opening, and the fourth opening, respectively; the conductor 434 over the insulator 428, which includes a region in contact with the conductor 433; the conductor 432 over the insulator 428, which includes a region in contact with the conductor 431; the conductor 430 over the insulator 428, which includes a region in contact with the conductor 429; and the conductor 438 over the insulator 428, which includes a region in contact with the conductor 437.

The cross sections of the openings in one embodiment of the present invention are described with reference to FIGS. 5D to 5F. FIGS. 5D to 5F are enlarged cross sectional views of the openings of the transistor shown in FIGS. 4A to 4C. FIG. 5D is an enlarged view of the first opening. FIG. 5E is an enlarged view of the second opening. FIG. 5F is an enlarged view of the fourth opening. Note that in FIGS. 5D to 5F, the insulator 410 is thin in its thickness direction for convenience of explanation.

Although the openings in FIGS. 4B and 4C have straight cross sections, the openings each may have a shape in which the opening diameter of a layer is larger than those of layers positioned thereover and thereunder or larger than that of a layer positioned thereover or thereunder, or a shape with a smaller part (constricted part) than those of layers positioned thereover and thereunder or larger than that of a layer positioned thereover or thereunder as illustrated in FIGS. 5D to 5F. In the first opening in FIG. 5D, the opening diameter of each of the insulators 428, 418, 410, 402, and 302 is larger than those of layers positioned thereover and thereunder or that of a layer positioned thereover or thereunder. In other words, the opening diameter of each of the insulator 408 and the electron trap layer 303 is smaller than those of layers positioned thereover and thereunder. In other words, the opening diameter of each of the insulator 408 and the electron trap layer 303 is constricted. In the second opening in FIG. 5E, the opening diameter of each of the insulators 428, 418, and 410 is larger than those of layers positioned thereover and thereunder or that of a layer positioned thereover or thereunder. In other words, the opening diameter of the insulator 408 is smaller than those of layers positioned thereover and thereunder. In other words, the opening of the insulator 408 is constricted. In the fourth opening in FIG. 5F, the opening diameter of each of the insulator 428 and the insulator 418 is larger than that of a layer positioned thereover or thereunder. In other words, the opening diameter of the insulator 408 is smaller than those of layers positioned thereover and

thereunder. In other words, the opening of the insulator **408** is constricted. Such shapes are obtained in some cases when etching rates of the insulators **428**, **418**, **410**, **402**, and **302** are higher than those of the insulator **408** and the electron trap layer **303**.

In a bottom part of the opening in FIG. 5E, part of the top surface of the conductor **416a1** is dented. The reason for this is because the time needed for forming the first opening and the time needed for forming the second opening are different from each other, the conductor **416a1** is over-etched, that is, the conductor **416a1** is partly etched until the first opening is formed after the second opening is formed. Similarly, in a bottom part of the opening in FIG. 5F, part of the top surface of the conductor **404** is dented. The reason for this is because the time needed for forming the first opening and the time needed for forming the fourth opening are different from each other, the conductor **404** is over-etched, that is, the conductor **404** is partly etched until the first opening is formed after the fourth opening is formed. Note that in FIGS. 5D to 5F, examples are illustrated in which the opening diameter of a layer is larger than those of layers positioned thereover and thereunder or the conductor has a dented portion; however, the size of the expanded portion of the opening and the dented portion of the conductive film are not limited to those examples.

Note that the semiconductor **406b** includes the region **407** in which the top surface of the semiconductor **406b** is in contact with the conductors **416a1** and **416a2**.

In the transistor, the conductor **404** functions as the first gate electrode. Furthermore, the conductor **404** can have the stacked structure including a conductor that hardly allows oxygen to pass therethrough. For example, when the conductor that hardly allows oxygen to pass therethrough is formed as a lower layer, an increase in the electric resistance value due to oxidation of the conductor **404** can be prevented. The insulator **412** functions as the gate insulator.

The conductors **416a1** and **416a2** function as the source electrode and the drain electrode of the transistor. The conductors **416a1** and **416a2** each can have the stacked structure including a conductor that hardly allows oxygen to pass therethrough. For example, when the conductor that hardly allows oxygen to pass therethrough is formed as an upper layer, an increase in the electric resistance value due to oxidation of the conductors **416a1** and **416a2** can be prevented.

The resistance of the semiconductor **406b** can be controlled by a potential applied to the conductor **404**. That is, conduction or non-conduction between the conductors **416a1** and **416a2** can be controlled by the potential applied to the conductor **404**.

In the transistor, the region functioning as a gate electrode is formed in a self-aligned manner so as to fill the opening in the insulator **410** and others. Such a transistor can be also referred to as a TGSA s-channel FET.

In FIG. 4B, the length of the region of the bottom surface of the conductor **404** functioning as a gate electrode facing the top surface of the semiconductor **406b** with the insulator **412** and the insulator **406c** positioned therebetween is defined as a gate line width. The gate line width can be smaller than the width of the opening reaching the semiconductor **406b** in the insulator **410**. That is, the gate line width can be smaller than the minimum feature size. Specifically, the gate line width can be greater than or equal to 5 nm and less than or equal to 60 nm, preferably greater than or equal to 5 nm and less than or equal to 30 nm.

When an electric field from the gate electrode is blocked by other conductors, switching characteristics of the tran-

sistor may be degraded. In the transistor, the positional relationship between the conductor **404** and the conductors **416a1** and **416a2** is changed by the thicknesses of the insulator **406c** and the insulator **412**. That is, the relationship between the thicknesses of the conductors **416a1** and **416a2** functioning as the source electrode and the drain electrode and the thickness of the insulator **412** functioning as the gate insulating film affects electrical characteristics of the transistor.

In FIG. 4B, when the thickness of the insulator **412** in a region between the conductors **416a1** and **416a2** is smaller than that of the conductor **416a1** or **416a2**, an electric field from the gate electrode is applied to the entire channel formation region, making the operation of the transistor favorable. The thickness of the insulator **412** in the region between the conductors **416a1** and **416a2** is smaller than or equal to 30 nm, preferably smaller than or equal to 10 nm.

The transistor can have a structure in which the conductor **416a1** or **416a2** has a small thickness. An end portion of the conductor **416a1** has a region facing the conductor **404** with the insulator **406c** and the insulator **412** positioned therebetween; furthermore, an end portion of the conductor **416a2** has a region facing the conductor **404** with the insulator **406c** and the insulator **412** positioned therebetween; however, the area of these regions can be small. Thus, parasitic capacitance of these regions in the transistor is reduced.

The conductor **310a** functions as the second gate electrode. The conductor **310a** can be the multilayer film including a conductive film that hardly allows oxygen to pass therethrough. The use of the multilayer film including a conductive film that hardly allows oxygen to pass therethrough can prevent a decrease in conductivity due to oxidation of the conductor **310a**. The insulator **302**, the electron trap layer **303**, and the insulator **402** function as the second gate insulating film. The threshold voltage of the transistor can be controlled by a potential applied to the conductor **310a**. Furthermore, by the potential applied to the conductor **310a**, electrons are injected to the electron trap layer **303** and thus the threshold voltage of the transistor can be controlled. The first gate electrode and the second gate electrode are electrically connected to each other, whereby a high on-state current can be obtained. Note that the functions of the first gate electrode and the second gate electrode may be replaced with each other.

FIG. 6B illustrates an example in which the first gate electrode and the second gate electrode are electrically connected. In the opening reaching the conductor **404** through the insulators **428**, **408**, and **418**, the conductor **440** is embedded, and a top surface of the conductor **440** is electrically connected to the conductor **444** formed over the insulator **428**. In the opening reaching the conductor **310c** through the insulators **428**, **408**, **418**, **410**, and **402**, the electron trap layer **303**, and the insulator **302**, the conductor **442** is embedded, and the top surface of the conductor **442** and the conductor **444** are electrically connected. That is, the conductor **404** functioning as the first gate electrode is electrically connected to the conductor **310c** functioning as the second gate electrode through the conductors **440**, **444**, and **442**.

The insulators **418** and **428** may each be formed to have, for example, a single-layer structure or a stacked-layer structure including an insulator containing boron, carbon, nitrogen, oxygen, fluorine, magnesium, aluminum, silicon, phosphorus, chlorine, argon, gallium, germanium, yttrium, zirconium, lanthanum, neodymium, hafnium, or tantalum.

For example, the insulator **301** preferably contains silicon oxide or silicon oxynitride. For the other components, refer to the above description.

In Embodiment 1, one embodiment of the present invention has been described. Other embodiments of the present invention are described in Embodiments 2 to 14. Note that one embodiment of the present invention is not limited to the above examples. That is, since various embodiments of the present invention are disclosed in Embodiment 1 and Embodiments 2 to 14, one embodiment of the present invention is not limited to a specific embodiment. For example, an example in which a channel formation region of a transistor includes an oxide semiconductor, an example in which a transistor includes an oxide semiconductor, and the like are described as one embodiment of the present invention; however, one embodiment of the present invention is not limited to these examples. Depending on circumstances or conditions, various transistors of embodiments of the present invention may include various semiconductors. Depending on circumstances or conditions, transistors of embodiments of the present invention may include, for example, at least one of silicon, germanium, silicon germanium, silicon carbide, gallium arsenide, aluminum gallium arsenide, indium phosphide, gallium nitride, and an organic semiconductor. Alternatively, depending on circumstances or conditions, various transistors of embodiments of the present invention do not necessarily include an oxide semiconductor, for example.

At least part of this embodiment can be implemented in combination with any of the embodiments described in this specification as appropriate.

Embodiment 2

<Structure of Oxide Semiconductor>

A structure of an oxide semiconductor is described below.

An oxide semiconductor is classified into a single crystal oxide semiconductor and a non-single-crystal oxide semiconductor. Examples of a non-single-crystal oxide semiconductor include a c-axis aligned crystalline oxide semiconductor (CAAC-OS), a polycrystalline oxide semiconductor, a nanocrystalline oxide semiconductor (nc-OS), an amorphous-like oxide semiconductor (a-like OS), and an amorphous oxide semiconductor.

From another perspective, an oxide semiconductor is classified into an amorphous oxide semiconductor and a crystalline oxide semiconductor. Examples of a crystalline oxide semiconductor include a single crystal oxide semiconductor, a CAAC-OS, a polycrystalline oxide semiconductor, and an nc-OS.

It is known that an amorphous structure is generally defined as being metastable and unfixed, and being isotropic and having no non-uniform structure. In other words, an amorphous structure has a flexible bond angle and a short-range order but does not have a long-range order.

This means that an inherently stable oxide semiconductor cannot be regarded as a completely amorphous oxide semiconductor. Moreover, an oxide semiconductor that is not isotropic (e.g., an oxide semiconductor that has a periodic structure in a microscopic region) cannot be regarded as a completely amorphous oxide semiconductor. Note that an a-like OS has a periodic structure in a microscopic region, but at the same time has a void and has an unstable structure. For this reason, an a-like OS has physical properties similar to those of an amorphous oxide semiconductor.

<CAAC-OS>

First, a CAAC-OS is described.

A CAAC-OS is one of oxide semiconductors having a plurality of c-axis aligned crystal parts (also referred to as pellets).

In a combined analysis image (also referred to as a high-resolution TEM image) of a bright-field image and a diffraction pattern of a CAAC-OS, which is obtained using a transmission electron microscope (TEM), a plurality of pellets can be observed. However, in the high-resolution TEM image, a boundary between pellets, that is, a grain boundary is not clearly observed. Thus, in the CAAC-OS, a reduction in electron mobility due to the grain boundary is less likely to occur.

A CAAC-OS observed with TEM is described below. FIG. 7A shows a high-resolution TEM image of a cross section of the CAAC-OS that is observed from a direction substantially parallel to the sample surface. The high-resolution TEM image is obtained with a spherical aberration corrector function. The high-resolution TEM image obtained with a spherical aberration corrector function is particularly referred to as a Cs-corrected high-resolution TEM image. The Cs-corrected high-resolution TEM image can be obtained with, for example, an atomic resolution analytical electron microscope JEM-ARM200F manufactured by JEOL Ltd.

FIG. 7B is an enlarged Cs-corrected high-resolution TEM image of a region (1) in FIG. 7A. FIG. 7B shows that metal atoms are arranged in a layered manner in a pellet. Each metal atom layer has a configuration reflecting unevenness of a surface over which the CAAC-OS is formed (hereinafter, the surface is referred to as a formation surface) or a top surface of the CAAC-OS, and is arranged parallel to the formation surface or the top surface of the CAAC-OS.

As shown in FIG. 7B, the CAAC-OS has a characteristic atomic arrangement. The characteristic atomic arrangement is denoted by an auxiliary line in FIG. 7C. FIGS. 7B and 7C prove that the size of a pellet is greater than or equal to 1 nm or greater than or equal to 3 nm, and the size of a space caused by tilt of the pellets is approximately 0.8 nm. Therefore, the pellet can also be referred to as a nanocrystal (nc). Furthermore, the CAAC-OS can also be referred to as an oxide semiconductor including c-axis aligned nanocrystals (CANC).

Here, according to the Cs-corrected high-resolution TEM images, the schematic arrangement of pellets **5100** of a CAAC-OS over a substrate **5120** is illustrated by such a structure in which bricks or blocks are stacked (see FIG. 7D). The part in which the pellets are tilted as observed in FIG. 7C corresponds to a region **5161** shown in FIG. 7D.

FIG. 8A shows a Cs-corrected high-resolution TEM image of a plane of the CAAC-OS observed from a direction substantially perpendicular to the sample surface. FIGS. 8B, 8C, and 8D are enlarged Cs-corrected high-resolution TEM images of regions (1), (2), and (3) in FIG. 8A, respectively. FIGS. 8B, 8C, and 8D indicate that metal atoms are arranged in a triangular, quadrangular, or hexagonal configuration in a pellet. However, there is no regularity of arrangement of metal atoms between different pellets.

Next, a CAAC-OS analyzed by X-ray diffraction (XRD) is described. For example, when the structure of a CAAC-OS including an InGaZnO₄ crystal is analyzed by an out-of-plane method, a peak appears at a diffraction angle (2θ) of around 31° as shown in FIG. 9A. This peak is derived from the (009) plane of the InGaZnO₄ crystal, which indicates that crystals in the CAAC-OS have c-axis alignment,

and that the c-axes are aligned in a direction substantially perpendicular to the formation surface or the top surface of the CAAC-OS.

Note that in structural analysis of the CAAC-OS by an out-of-plane method, another peak may appear when 2θ is around 36° , in addition to the peak at 2θ of around 31° . The peak at 2θ of around 36° indicates that a crystal having no c-axis alignment is included in part of the CAAC-OS. It is preferable that in the CAAC-OS analyzed by an out-of-plane method, a peak appear when 2θ is around 31° and that a peak not appear when 2θ is around 36° .

On the other hand, in structural analysis of the CAAC-OS by an in-plane method in which an X-ray beam is incident on a sample in a direction substantially perpendicular to the c-axis, a peak appears when 2θ is around 56° . This peak is attributed to the (110) plane of the InGaZnO_4 crystal. In the case of the CAAC-OS, when analysis (ϕ scan) is performed with 2θ fixed at around 56° and with the sample rotated using a normal vector of the sample surface as an axis (ϕ axis), as shown in FIG. 9B, a peak is not clearly observed. In contrast, in the case of a single crystal oxide semiconductor of InGaZnO_4 , when ϕ scan is performed with 2θ fixed at around 56° , as shown in FIG. 9C, six peaks that are derived from crystal planes equivalent to the (110) plane are observed. Accordingly, the structural analysis using XRD shows that the directions of a-axes and b-axes are irregularly oriented in the CAAC-OS.

Next, a CAAC-OS analyzed by electron diffraction is described. For example, when an electron beam with a probe diameter of 300 nm is incident on a CAAC-OS including an InGaZnO_4 crystal in a direction parallel to the sample surface, a diffraction pattern (also referred to as a selected-area transmission electron diffraction pattern) shown in FIG. 10A can be obtained. In this diffraction pattern, spots derived from the (009) plane of an InGaZnO_4 crystal are included. Thus, the electron diffraction also indicates that pellets included in the CAAC-OS have c-axis alignment and that the c-axes are aligned in a direction substantially perpendicular to the formation surface or the top surface of the CAAC-OS. Meanwhile, FIG. 10B shows a diffraction pattern obtained in such a manner that an electron beam with a probe diameter of 300 nm is incident on the same sample in a direction perpendicular to the sample surface. As shown in FIG. 10B, a ring-like diffraction pattern is observed. Thus, the electron diffraction also indicates that the a-axes and b-axes of the pellets included in the CAAC-OS do not have regular alignment. The first ring in FIG. 10B is considered to be derived from the (010) plane, the (100) plane, and the like of the InGaZnO_4 crystal. The second ring in FIG. 10B is considered to be derived from the (110) plane and the like.

As described above, the CAAC-OS is an oxide semiconductor with high crystallinity. Entry of impurities, formation of defects, or the like might decrease the crystallinity of an oxide semiconductor. This means that the CAAC-OS has small amounts of impurities and defects (e.g., oxygen vacancies).

Note that the impurity means an element other than the main components of the oxide semiconductor, such as hydrogen, carbon, silicon, or a transition metal element. For example, an element (specifically, silicon or the like) having higher strength of bonding to oxygen than a metal element included in an oxide semiconductor extracts oxygen from the oxide semiconductor, which results in disorder of the atomic arrangement and reduced crystallinity of the oxide semiconductor. A heavy metal such as iron or nickel, argon, carbon dioxide, or the like has a large atomic radius (or

molecular radius), and thus disturbs the atomic arrangement of the oxide semiconductor and decreases crystallinity.

The characteristics of an oxide semiconductor having impurities or defects might be changed by light, heat, or the like. Impurities contained in the oxide semiconductor might serve as carrier traps or carrier generation sources, for example. Furthermore, oxygen vacancies in the oxide semiconductor serve as carrier traps or serve as carrier generation sources when hydrogen is captured therein.

The CAAC-OS having small amounts of impurities and oxygen vacancies is an oxide semiconductor with low carrier density (specifically, lower than $8 \times 10^{11}/\text{cm}^3$, preferably lower than $1 \times 10^{11}/\text{cm}^3$, further preferably lower than $1 \times 10^{10}/\text{cm}^3$, and is higher than or equal to $1 \times 10^{-9}/\text{cm}^3$). Such an oxide semiconductor is referred to as a highly purified intrinsic or substantially highly purified intrinsic oxide semiconductor. A CAAC-OS has a low impurity concentration and a low density of defect states. Thus, the CAAC-OS can be referred to as an oxide semiconductor having stable characteristics.

<nc-OS>

Next, an nc-OS is described.

An nc-OS has a region in which a crystal part is observed and a region in which it is difficult to observe a crystal part clearly in a high-resolution TEM image. In most cases, the size of a crystal part included in the nc-OS is greater than or equal to 1 nm and less than or equal to 10 nm, or greater than or equal to 1 nm and less than or equal to 3 nm. Note that an oxide semiconductor including a crystal part whose size is greater than 10 nm and less than or equal to 100 nm is sometimes referred to as a microcrystalline oxide semiconductor. In a high-resolution TEM image of the nc-OS, for example, it is difficult to observe a crystal grain boundary clearly in some cases. Note that there is a possibility that the origin of the nanocrystal is the same as that of a pellet in a CAAC-OS. Therefore, a crystal part of the nc-OS may be referred to as a pellet in the following description.

In the nc-OS, a microscopic region (for example, a region with a size greater than or equal to 1 nm and less than or equal to 10 nm, in particular, a region with a size greater than or equal to 1 nm and less than or equal to 3 nm) has a periodic atomic arrangement. There is no regularity of crystal orientation between different pellets in the nc-OS. Thus, the orientation of the whole film is not ordered. Accordingly, the nc-OS cannot be distinguished from an a-like OS or an amorphous oxide semiconductor, depending on an analysis method. For example, when the nc-OS is analyzed by an out-of-plane method using an X-ray beam having a diameter larger than the size of a pellet, a peak that shows a crystal plane does not appear. Furthermore, a diffraction pattern like a halo pattern is observed when the nc-OS is subjected to electron diffraction using an electron beam with a probe diameter (e.g., 50 nm or larger) that is larger than the size of a pellet. Meanwhile, spots appear in a nanobeam electron diffraction pattern of the nc-OS when an electron beam having a probe diameter close to or smaller than the size of a pellet is applied. Moreover, in a nanobeam electron diffraction pattern of the nc-OS, regions with high luminance in a circular (ring) pattern are shown in some cases. Also in a nanobeam electron diffraction pattern of the nc-OS, a plurality of spots are shown in a ring-like region in some cases.

Since there is no regularity of crystal orientation between the pellets (nanocrystals) as mentioned above, the nc-OS can also be referred to as an oxide semiconductor including random aligned nanocrystals (RANC) or an oxide semiconductor including non-aligned nanocrystals (NANC).

The nc-OS is an oxide semiconductor that has high regularity as compared with an amorphous oxide semiconductor. Therefore, the nc-OS is likely to have a lower density of defect states than an a-like OS and an amorphous oxide semiconductor. Note that there is no regularity of crystal orientation between different pellets in the nc-OS. Therefore, the nc-OS has a higher density of defect states than the CAAC-OS.

<a-Like OS>

An a-like OS has a structure between those of the nc-OS and the amorphous oxide semiconductor.

In a high-resolution TEM image of the a-like OS, a void may be observed. Furthermore, in the high-resolution TEM image, there are a region where a crystal part is clearly observed and a region in which a crystal part is not observed.

The a-like OS has an unstable structure because it contains a void. To verify that an a-like OS has an unstable structure as compared with a CAAC-OS and an nc-OS, a change in structure caused by electron irradiation is described below.

An a-like OS (referred to as Sample A), an nc-OS (referred to as Sample B), and a CAAC-OS (referred to as Sample C) are prepared as samples subjected to electron irradiation. Each of the samples is an In—Ga—Zn oxide.

First, a high-resolution cross-sectional TEM image of each sample is obtained. The high-resolution cross-sectional TEM images show that all the samples have crystal parts.

Note that which part is regarded as a crystal part is determined as follows. It is known that a unit cell of an InGaZnO₄ crystal has a structure in which nine layers including three In—O layers and six Ga—Zn—O layers are stacked in the c-axis direction. The distance between the adjacent layers is equivalent to the lattice spacing on the (009) plane (also referred to as d value). The value is calculated to be 0.29 nm from crystal structural analysis. Accordingly, a portion where the lattice spacing between lattice fringes is greater than or equal to 0.28 nm and less than or equal to 0.30 nm is regarded as a crystal part of InGaZnO₄. Each of lattice fringes corresponds to the a-b plane of the InGaZnO₄ crystal.

FIG. 11 shows change in the average size of crystal parts (at 22 points to 45 points) in each sample. Note that the crystal part size corresponds to the length of a lattice fringe. FIG. 11 indicates that the crystal part size in the a-like OS increases with an increase in the cumulative electron dose. Specifically, as shown by (1) in FIG. 11, a crystal part of approximately 1.2 nm (also referred to as an initial nucleus) at the start of TEM observation grows to a size of approximately 2.6 nm at a cumulative electron dose of 4.2×10^8 e⁻/nm². In contrast, the crystal part size in the nc-OS and the CAAC-OS shows little change from the start of electron irradiation to a cumulative electron dose of 4.2×10^8 e⁻/nm². Specifically, as shown by (2) and (3) in FIG. 11, the average crystal sizes in an nc-OS and a CAAC-OS are approximately 1.4 nm and approximately 2.1 nm, respectively, regardless of the cumulative electron dose.

In this manner, growth of the crystal part in the a-like OS is induced by electron irradiation. In contrast, in the nc-OS and the CAAC-OS, growth of the crystal part is hardly induced by electron irradiation. Therefore, the a-like OS has an unstable structure as compared with the nc-OS and the CAAC-OS.

The a-like OS has a lower density than the nc-OS and the CAAC-OS because it contains a void. Specifically, the density of the a-like OS is higher than or equal to 78.6% and lower than 92.3% of the density of the single crystal oxide semiconductor having the same composition. The density of

each of the nc-OS and the CAAC-OS is higher than or equal to 92.3% and lower than 100% of the density of the single crystal oxide semiconductor having the same composition. Note that it is difficult to deposit an oxide semiconductor having a density of lower than 78% of the density of the single crystal oxide semiconductor.

For example, in the case of an oxide semiconductor having an atomic ratio of In:Ga:Zn=1:1:1, the density of single crystal InGaZnO₄ with a rhombohedral crystal structure is 6.357 g/cm³. Accordingly, in the case of the oxide semiconductor having an atomic ratio of In:Ga:Zn=1:1:1, the density of the a-like OS is higher than or equal to 5.0 g/cm³ and lower than 5.9 g/cm³. For example, in the case of the oxide semiconductor having an atomic ratio of In:Ga:Zn=1:1:1, the density of each of the nc-OS and the CAAC-OS is higher than or equal to 5.9 g/cm³ and lower than 6.3 g/cm³.

Note that there is a possibility that an oxide semiconductor having a certain composition cannot exist in a single crystal structure. In that case, single crystal oxide semiconductors with different compositions are combined at an adequate ratio, which makes it possible to calculate density equivalent to that of a single crystal oxide semiconductor with the desired composition. The density of a single crystal oxide semiconductor having the desired composition can be calculated using a weighted average according to the combination ratio of the single crystal oxide semiconductors with different compositions. Note that it is preferable to use as few kinds of single crystal oxide semiconductors as possible to calculate the density.

As described above, oxide semiconductors have various structures and various properties. Note that an oxide semiconductor may be a multilayer film including two or more of an amorphous oxide semiconductor, an a-like OS, an nc-OS, and a CAAC-OS, for example.

An oxide which can be used as the insulator 406a, the semiconductor 406b, the insulator 406c, or the like is described.

The semiconductor 406b is an oxide semiconductor containing indium, for example. The oxide semiconductor 406b can have high carrier mobility (electron mobility) by containing indium, for example. The semiconductor 406b preferably contains an element M. The element M is preferably aluminum, gallium, yttrium, tin, or the like. Other elements can be used as the element M are boron, silicon, titanium, iron, nickel, germanium, zirconium, molybdenum, lanthanum, cerium, neodymium, hafnium, tantalum, tungsten, and the like. Note that two or more of the above elements may be used in combination as the element M. The element M is an element having high bonding energy with oxygen, for example. The element M is an element whose bonding energy with oxygen is higher than that of indium. The element M is an element that can increase the energy gap of the oxide semiconductor, for example. Furthermore, the semiconductor 406b preferably contains zinc. When the oxide semiconductor contains zinc, the oxide semiconductor is easily crystallized, in some cases.

Note that the semiconductor 406b is not limited to the oxide semiconductor containing indium. The semiconductor 406b may be, for example, an oxide semiconductor which does not contain indium and contains zinc, an oxide semiconductor which does not contain indium and contains gallium, or an oxide semiconductor which does not contain indium and contains tin, e.g., a zinc tin oxide, a gallium tin oxide, or a gallium oxide.

For the semiconductor 406b, an oxide with a wide energy gap may be used, for example. For example, the energy gap

of the semiconductor **406b** is greater than or equal to 2.5 eV and less than or equal to 4.2 eV, preferably greater than or equal to 2.8 eV and less than or equal to 3.8 eV, and further preferably greater than or equal to 3 eV and less than or equal to 3.5 eV.

For example, the insulator **406a** and the insulator **406c** are oxides including one or more, or two or more elements other than oxygen included in the semiconductor **406b**. Since the insulator **406a** and the insulator **406c** each include one or more, or two or more elements other than oxygen included in the semiconductor **406b**, an interface state is less likely to be formed at the interface between the insulator **406a** and the semiconductor **406b** and the interface between the semiconductor **406b** and the insulator **406c**.

The case where the insulator **406a**, the semiconductor **406b**, and the insulator **406c** contain indium is described. In the case of using an In-M-Zn oxide as the insulator **406a**, when a summation of In and M is assumed to be 100 atomic %, the proportions of In and M are preferably set to be less than 50 atomic % and greater than 50 atomic %, respectively, further preferably less than 25 atomic % and greater than 75 atomic %, respectively. In the case of using an In-M-Zn oxide as the semiconductor **406b**, when the summation of In and M is assumed to be 100 atomic %, the proportions of In and M are preferably set to be greater than 25 atomic % and less than 75 atomic %, respectively, further preferably greater than 34 atomic % and less than 66 atomic %, respectively. In the case of using an In-M-Zn oxide as the insulator **406c**, when the summation of In and M is assumed to be 100 atomic %, the proportions of In and M are preferably set to be less than 50 atomic % and greater than 50 atomic %, respectively, further preferably less than 25 atomic % and greater than 75 atomic %, respectively. Note that the insulator **406c** may be an oxide that is a type the same as that of the insulator **406a**.

As the semiconductor **406b**, an oxide having an electron affinity higher than those of the insulators **406a** and **406c** is used. For example, as the semiconductor **406b**, an oxide having an electron affinity higher than those of the insulators **406a** and **406c** by 0.07 eV or higher and 1.3 eV or lower, preferably 0.1 eV or higher and 0.7 eV or lower, further preferably 0.15 eV or higher and 0.4 eV or lower is used. Note that the electron affinity refers to an energy gap between the vacuum level and the bottom of the conduction band.

An indium gallium oxide has a small electron affinity and a high oxygen-blocking property. Therefore, the insulator **406c** preferably includes an indium gallium oxide. The gallium atomic ratio [Ga/(In+Ga)] is, for example, higher than or equal to 70%, preferably higher than or equal to 80%, further preferably higher than or equal to 90%.

Note that the insulator **406a** and/or the insulator **406c** may be gallium oxide. For example, when gallium oxide is used as the insulator **406c**, leakage current between the conductor **404** and the conductor **416a1** or the conductor **416a2** can be reduced. In other words, the off-state current of the transistor can be reduced.

At this time, when a gate voltage is applied, a channel is formed in the semiconductor **406b** having the highest electron affinity in the insulator **406a**, the semiconductor **406b**, and the insulator **406c**.

Here, in some cases, there is a mixed region of the insulator **406a** and the semiconductor **406b** between the insulator **406a** and the semiconductor **406b**. Furthermore, in some cases, there is a mixed region of the semiconductor **406b** and the insulator **406c** between the semiconductor **406b** and the insulator **406c**. The mixed region has a low

density of interface states. For that reason, the stack of the insulator **406a**, the semiconductor **406b**, and the insulator **406c** has a band structure where energy at each interface and in the vicinity of the interface is changed continuously (continuous junction).

At this time, electrons move mainly in the semiconductor **406b**, not in the insulator **406a** and the insulator **406c**. Thus, when the interface state density at the interface between the insulator **406a** and the semiconductor **406b** and the interface state density at the interface between the semiconductor **406b** and the insulator **406c** are decreased, electron movement in the semiconductor **406b** is less likely to be inhibited and the on-state current of the transistor can be increased.

In the case where the transistor has an s-channel structure, a channel is formed in the whole of the semiconductor **406b**. Therefore, as the semiconductor **406b** has a larger thickness, a channel region becomes larger. In other words, the thicker the semiconductor **406b** is, the larger the on-state current of the transistor is. For example, the semiconductor **406b** has a region with a thickness greater than or equal to 10 nm, preferably greater than or equal to 20 nm, more preferably greater than or equal to 40 nm, further preferably greater than or equal to 60 nm, still further preferably greater than or equal to 100 nm. Note that the semiconductor **406b** has a region with a thickness of, for example, less than or equal to 300 nm, preferably less than or equal to 200 nm, or more preferably less than or equal to 150 nm because the productivity of the semiconductor device including the transistor might be decreased. In some cases, when the channel formation region is reduced in size, electrical characteristics of the transistor with a smaller thickness of the semiconductor **406b** may be improved. Therefore, the semiconductor **406b** may have a thickness less than 10 nm.

Moreover, the thickness of the insulator **406c** is preferably as small as possible to increase the on-state current of the transistor. The thickness of the insulator **406c** is less than 10 nm, preferably less than or equal to 5 nm, more preferably less than or equal to 3 nm, for example. Meanwhile, the insulator **406c** has a function of blocking entry of elements other than oxygen (such as hydrogen and silicon) included in the adjacent insulator into the semiconductor **406b** where a channel is formed. For this reason, it is preferable that the insulator **406c** have a certain thickness. The thickness of the insulator **406c** is greater than or equal to 0.3 nm, preferably greater than or equal to 1 nm, further preferably greater than or equal to 2 nm, for example. The insulator **406c** preferably has an oxygen blocking property to suppress outward diffusion of oxygen released from the insulator **402** and the like.

To improve reliability, preferably, the thickness of the insulator **406a** is large and the thickness of the insulator **406c** is small. For example, the insulator **406a** has a region with a thickness, for example, greater than or equal to 10 nm, preferably greater than or equal to 20 nm, further preferably greater than or equal to 40 nm, still further preferably greater than or equal to 60 nm. When the thickness of the insulator **406a** is made large, a distance from an interface between the adjacent insulator and the insulator **406a** to the semiconductor **406b** in which a channel is formed can be large. Since the productivity of the semiconductor device including the transistor might be decreased, the insulator **406a** has a region with a thickness, for example, less than or equal to 200 nm, preferably less than or equal to 120 nm, further preferably less than or equal to 80 nm.

For example, silicon in the oxide semiconductor might serve as a carrier trap or a carrier generation source. Therefore, the silicon concentration of the semiconductor **406b** is

preferably as low as possible. For example, a region in which the concentration of silicon which is measured by secondary ion mass spectrometry (SIMS) is lower than 1×10^{19} atoms/cm³, preferably lower than 5×10^{18} atoms/cm³, or further preferably lower than 2×10^{18} atoms/cm³ is provided between the semiconductor **406b** and the insulator **406a**. A region with a silicon concentration lower than 1×10^{19} atoms/cm³, preferably lower than 5×10^{18} atoms/cm³, further preferably lower than 2×10^{18} atoms/cm³ which is measured by SIMS is provided between the semiconductor **406b** and the insulator **406c**.

It is preferable to reduce the concentration of hydrogen in the insulator **406a** and the insulator **406c** in order to reduce the concentration of hydrogen in the semiconductor **406b**. The insulator **406a** and the insulator **406c** each have a region in which the concentration of hydrogen measured by SIMS is lower than or equal to 2×10^{20} atoms/cm³, preferably lower than or equal to 5×10^{19} atoms/cm³, further preferably lower than or equal to 1×10^{19} atoms/cm³, still further preferably lower than or equal to 5×10^{18} atoms/cm³. It is preferable to reduce the concentration of nitrogen in the insulator **406a** and the insulator **406c** in order to reduce the concentration of nitrogen in the semiconductor **406b**. The insulator **406a** and the insulator **406c** each have a region in which the concentration of nitrogen measured by SIMS is lower than 5×10^{19} atoms/cm³, preferably lower than or equal to 5×10^{18} atoms/cm³, further preferably lower than or equal to 1×10^{18} atoms/cm³, still further preferably lower than or equal to 5×10^{17} atoms/cm³.

Note that when copper enters the oxide semiconductor, an electron trap might be generated. The electron trap might shift the threshold voltage of the transistor in the positive direction. Therefore, the concentration of copper on the surface of or in the semiconductor **406b** is preferably as low as possible. For example, the semiconductor **406b** preferably has a region in which the copper concentration is lower than or equal to 1×10^{19} atoms/cm³, lower than or equal to 5×10^{18} atoms/cm³, or lower than or equal to 1×10^{18} atoms/cm³.

The above three-layer structure is an example. For example, a two-layer structure without the insulator **406a** or the insulator **406c** may be employed. Alternatively, a four-layer structure in which any one of the insulators or the semiconductors described as examples of the insulator **406a**, the semiconductor **406b**, and the insulator **406c** is provided below or over the insulator **406a** or below or over the insulator **406c** may be employed. Alternatively, an n-layer structure (n is an integer of 5 or more) may be employed in which any one of the insulators or the semiconductors described as examples of the insulator **406a**, the semiconductor **406b**, and the insulator **406c** is provided at two or more of the following positions: over the insulator **406a**, below the insulator **406a**, over the insulator **406c**, and below the insulator **406c**.

As the substrate **400**, an insulator substrate, a semiconductor substrate, or a conductor substrate may be used, for example. As the insulator substrate, a glass substrate, a quartz substrate, a sapphire substrate, a stabilized zirconia substrate (e.g., an yttria-stabilized zirconia substrate), or a resin substrate is used, for example. As the semiconductor substrate, a single material semiconductor substrate of silicon, germanium, or the like or a compound semiconductor substrate containing silicon carbide, silicon germanium, gallium arsenide, indium phosphide, zinc oxide, or gallium oxide as a material is used, for example. A semiconductor substrate in which an insulator region is provided in the above semiconductor substrate, e.g., a silicon on insulator (SOI) substrate or the like is used. As the conductor sub-

strate, a graphite substrate, a metal substrate, an alloy substrate, a conductive resin substrate, or the like is used. A substrate including a metal nitride, a substrate including a metal oxide, or the like is used. An insulator substrate provided with a conductor or a semiconductor, a semiconductor substrate provided with a conductor or an insulator, a conductor substrate provided with a semiconductor or an insulator, or the like is used. Alternatively, any of these substrates over which an element is provided may be used. As the element provided over the substrate, a capacitor, a resistor, a switching element, a light-emitting element, a memory element, or the like is used.

Alternatively, a flexible substrate may be used as the substrate **400**. As a method for providing the transistor over a flexible substrate, there is a method in which the transistor is formed over a non-flexible substrate and then the transistor is separated and transferred to the substrate **400** which is a flexible substrate. In that case, a separation layer is preferably provided between the non-flexible substrate and the transistor. As the substrate **400**, a sheet, a film, or a foil containing a fiber may be used. The substrate **400** may have elasticity. The substrate **400** may have a property of returning to its original shape when bending or pulling is stopped. Alternatively, the substrate **400** may have a property of not returning to its original shape. The substrate **400** has a region with a thickness of, for example, greater than or equal to 5 μm and less than or equal to 700 μm , preferably greater than or equal to 10 μm and less than or equal to 500 μm , more preferably greater than or equal to 15 μm and less than or equal to 300 μm . When the substrate **400** has a small thickness, the weight of the semiconductor device including the transistor can be reduced. When the substrate **400** has a small thickness, even in the case of using glass or the like, the substrate **400** may have elasticity or a property of returning to its original shape when bending or pulling is stopped. Therefore, an impact applied to the semiconductor device over the substrate **400**, which is caused by dropping or the like, can be reduced. That is, a durable semiconductor device can be provided.

For the substrate **400** which is a flexible substrate, metal, an alloy, resin, glass, or fiber thereof can be used, for example. The flexible substrate **400** preferably has a lower coefficient of linear expansion because deformation due to an environment is suppressed. The flexible substrate **400** is formed using, for example, a material whose coefficient of linear expansion is lower than or equal to $1 \times 10^{-3}/\text{K}$, lower than or equal to $5 \times 10^{-5}/\text{K}$, or lower than or equal to $1 \times 10^{-5}/\text{K}$. Examples of the resin include polyester, polyolefin, polyamide (e.g., nylon or aramid), polyimide, polycarbonate, and acrylic. In particular, aramid is preferably used for the flexible substrate **400** because of its low coefficient of linear expansion.

At least part of this embodiment can be implemented in combination with any of the embodiments described in this specification as appropriate.

Embodiment 3

<Method 1 for Manufacturing Transistor>

A method for manufacturing the transistor of the present invention in FIGS. 1A to 1C will be described below with reference to FIGS. 12A to 12C, FIGS. 13A to 13C, FIGS. 14A to 14C, FIGS. 15A to 15C, FIGS. 16A to 16C, FIGS. 17A to 17C, FIGS. 18A to 18C, FIGS. 19A to 19C, FIGS. 20A to 20C, FIGS. 21A to 21C, FIGS. 22A to 22C, FIGS. 23A to 23C, FIGS. 24A to 24C, FIGS. 25A to 25C, FIGS. 26A to 26C, FIGS. 27A to 27C, and FIGS. 28A to 28C.

First, the substrate **400** is prepared.

Then, the insulator **401** is formed. The insulator **401** may be formed by a sputtering method, a chemical vapor deposition (CVD) method, a molecular beam epitaxy (MBE) method, a pulsed laser deposition (PLD) method, an atomic layer deposition (ALD) method, or the like.

Note that CVD methods can be classified into a plasma enhanced CVD (PECVD) method using plasma, a thermal CVD (TCVD) method using heat, a photo CVD method using light, and the like. Moreover, the CVD method can include a metal CVD (MCVD) method and a metal organic CVD (MOCVD) method depending on a source gas.

In the case of a PECVD method, a high quality film can be obtained at relatively low temperature. Furthermore, a TCVD method does not use plasma and thus causes less plasma damage to an object. For example, a wiring, an electrode, an element (e.g., transistor or capacitor), or the like included in a semiconductor device might be charged up by receiving electric charges from plasma. In that case, accumulated electric charges might break the wiring, electrode, element, or the like included in the semiconductor device. Such plasma damage is not caused in the case of using a TCVD method, and thus the yield of a semiconductor device can be increased. In addition, since plasma damage does not occur in the deposition by a TCVD method, a film with few defects can be obtained.

An ALD method also causes less plasma damage to an object. An ALD method does not cause plasma damage during deposition, so that a film with few defects can be obtained.

Unlike in a deposition method in which particles ejected from a target or the like are deposited, in a CVD method and an ALD method, a film is formed by reaction at a surface of an object. Thus, a CVD method and an ALD method enable favorable step coverage almost regardless of the shape of an object. In particular, an ALD method enables excellent step coverage and excellent thickness uniformity and can be favorably used for covering a surface of an opening with a high aspect ratio, for example. On the other hand, an ALD method has a relatively low deposition rate; thus, it is sometimes preferable to combine an ALD method with another deposition method with a high deposition rate such as a CVD method.

When a CVD method or an ALD method is used, composition of a film to be formed can be controlled with a flow rate ratio of the source gases. For example, by the CVD method or the ALD method, a film with a desired composition can be formed by adjusting the flow ratio of a source gas. Moreover, with a CVD method or an ALD method, by changing the flow rate ratio of the source gases while forming the film, a film whose composition is continuously changed can be formed. In the case where the film is formed while changing the flow rate ratio of the source gases, as compared to the case where the film is formed using a plurality of deposition chambers, time taken for the deposition can be reduced because time taken for transfer and pressure adjustment is omitted. Thus, semiconductor devices can be manufactured with improved productivity.

Next, the insulator **301** is formed over the insulator **401**. The insulator **301** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like.

Then, a groove is formed in the insulator **301** so as to reach the insulator **401**. Examples of the groove include a hole and an opening. In forming the groove, wet etching may be employed; however, dry etching is preferably employed in terms of microfabrication. The insulator **401** is preferably

an insulator that functions as an etching stopper film used in forming the groove by etching the insulator **301**. For example, in the case where a silicon oxide film is used as the insulator **301** in which the groove is to be formed, the insulator **401** is preferably formed using a silicon nitride film, an aluminum oxide film, or a hafnium oxide film.

After the formation of the groove, a conductor to be the conductors **310a** and **310b** is formed. The conductor to be the conductors **310a** and **310b** desirably includes a conductor that is less likely to transmit oxygen. For example, tantalum nitride, tungsten nitride, or titanium nitride can be used. Alternatively, a stacked-layer film formed using the conductor and tantalum, tungsten, titanium, molybdenum, aluminum, copper, or a molybdenum-tungsten alloy can be used. The conductors to be the conductor **310a** and **310b** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like.

Next, chemical mechanical polishing (CMP) is performed to remove the conductor to be the conductors **310a** and **310b** that are located over the insulator **301**. Consequently, the conductors **310a** and **310b** remain only in the groove, whereby a wiring layer with a flat top surface can be formed.

Next, the insulator **302** is formed over the insulator **301** and the conductors **310a** and **310b**. The insulator **302** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. The electron trap layer **303** is formed over the insulator **302**. It is preferable that the electron trap layer **303** hardly allow impurities such as oxygen and hydrogen to pass there-through. It is preferable to use, for example, a silicon nitride film, an aluminum oxide film, or a hafnium oxide film. The electron trap layer **303** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like.

Next, the insulator **402** is formed over the electron trap layer **303**. The insulator **402** can be formed by a sputtering method, a CVD method, an MBE method, an ALD method, or the like. Next, treatment to add oxygen to the insulator **402** may be performed. Examples of the treatment for adding oxygen to the insulator **402** include ion implantation and plasma treatment. Note that oxygen added to the insulator **402** is excess oxygen.

Next, an insulator **406a_1** is formed over the insulator **402**. The insulator **406a_1** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like.

Next, treatment to add oxygen to the insulator **406a_1** may be performed. Examples of the treatment for adding oxygen to the insulator **406a_1** include ion implantation and plasma treatment. Note that oxygen added to the insulator **406a_1** is excess oxygen. Oxygen is preferably added to a layer corresponding to the insulator **406a_1**. Next, a semiconductor **406b_1** is formed over the insulator **406a_1**.

Next, first heat treatment is preferably performed. The first heat treatment can be performed at a temperature higher than or equal to 250° C. and lower than or equal to 650° C., preferably higher than or equal to 450° C. and lower than or equal to 600° C., further preferably higher than or equal to 520° C. and lower than or equal to 570° C. The first heat treatment is performed in an inert gas atmosphere or an atmosphere containing an oxidizing gas at 10 ppm or more, 1% or more, or 10% or more. The first heat treatment may be performed under a reduced pressure. Alternatively, the first heat treatment may be performed in such a manner that heat treatment is performed in an inert gas atmosphere, and then another heat treatment is performed in an atmosphere containing an oxidizing gas at 10 ppm or more, 1% or more,

or 10% or more in order to compensate desorbed oxygen. By the first heat treatment, crystallinity of the semiconductor **406b_1** can be increased and impurities such as hydrogen and water can be removed, for example. Alternatively, in the first heat treatment, plasma treatment using oxygen may be performed under a reduced pressure. The plasma treatment containing oxygen is preferably performed using an apparatus including a power source for generating high-density plasma using microwaves, for example. Alternatively, a power source for applying a radio frequency (RF) to a substrate side may be provided. The use of high-density plasma enables high-density oxygen radicals to be produced, and application of the RF to the substrate side allows oxygen radicals generated by the high-density plasma to be efficiently introduced into the semiconductor **406b_1**. Alternatively, after plasma treatment using an inert gas with the apparatus, plasma treatment using oxygen in order to compensate released oxygen may be performed.

Next, a conductor **414** is formed over the semiconductor **406b_1**. The conductor **414** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like (see FIGS. **12A** to **12C**).

Next, the conductor **414** is processed by a photolithography method or the like to form a conductor **415** (see FIGS. **13A** to **13C**).

Then, the insulator **406a_1**, the semiconductor **406b_1**, and the conductor **415** are processed by a lithography method or the like to form a multilayer film including the insulator **406a**, the semiconductor **406b**, and the conductors **416a1** and **416a2**. Here, a top surface of the semiconductor to be the semiconductor **406b** is damaged when the conductor is formed, whereby the region **407** is formed. The region **407** includes a region in which the resistance of the semiconductor **406b** is reduced; thus, contact resistance between the conductor **415** and the semiconductor **406b** is reduced. Note that when the multilayer film is formed, the insulator **402** is also subjected etching to have a thinned region in some cases. That is, the insulator **402** may have a protruding portion in a region in contact with the multilayer film (see FIGS. **14A** to **14C**).

In the lithography method, first, a resist is exposed to light through a photomask. Next, a region exposed to light is removed or left using a developing solution, so that a resist mask is formed. Then, etching through the resist mask is conducted. As a result, the conductor, the semiconductor, the insulator, or the like can be processed into a desired shape. The resist mask is formed by, for example, exposure of the resist to light using KrF excimer laser light, ArF excimer laser light, extreme ultraviolet (EUV) light, or the like. Alternatively, a liquid immersion technique may be employed in which a portion between a substrate and a projection lens is filled with liquid (e.g., water) to perform light exposure. An electron beam or an ion beam may be used instead of the above-mentioned light. Note that a photomask is not necessary in the case of using an electron beam or an ion beam. Note that dry etching treatment such as etching or wet etching treatment can be used for removal of the resist mask. Alternatively, wet etching treatment is performed after dry etching treatment. Further alternatively, dry etching treatment is performed after wet etching treatment.

As a dry etching apparatus, a capacitively coupled plasma (CCP) etching apparatus including parallel plate type electrodes can be used. The capacitively coupled plasma etching apparatus including the parallel plate type electrodes may have a structure in which a high-frequency power source is applied to one of the parallel plate type electrodes. Alternatively,

the capacitively coupled plasma etching apparatus may have a structure in which different high-frequency power sources are applied to one of the parallel plate type electrodes. Alternatively, the capacitively coupled plasma etching apparatus may have a structure in which high-frequency power sources with the same frequency are applied to the parallel plate type electrodes. Alternatively, the capacitively coupled plasma etching apparatus may have a structure in which high-frequency power sources with different frequencies are applied to the parallel plate type electrodes. Alternatively, a dry etching apparatus including a high-density plasma source can be used. As the dry etching apparatus including a high-density plasma source, an inductively coupled plasma (ICP) etching apparatus can be used, for example.

Next, the insulator **406c** is formed. The insulator **406c** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. Then, the insulator **412** is formed over the insulator **406c**. The insulator **412** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like.

Next, a conductor to be the conductor **404** is formed. The conductor to be the conductor **404** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. Then, the conductor to be the conductor **404** is processed by a lithography method or the like to form the conductor **404** (see FIGS. **15A** to **15C**).

Next, the insulator **408** is formed. The insulator **408** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. An aluminum oxide film is preferably formed as the insulator **408** using plasma containing oxygen, so that oxygen in the plasma can be added to a top surface of the insulator **412** as excess oxygen.

Next, the insulator **410** is formed over the insulator **408**. The insulator **410** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. Alternatively, the insulator **410** can be formed by a spin coating method, a dipping method, a droplet discharging method (such as an ink jet method), a printing method (such as screen printing or offset printing), a doctor knife method, a roll coater method, a curtain coater method, or the like.

The insulator **410** may be formed to have a flat top surface. For example, the top surface of the insulator **410** may have flatness immediately after the film formation. Alternatively, for example, the insulator **410** may have flatness by removing the insulator and the like from the top surface after the film formation so that the top surface of the insulator **410** becomes parallel to a reference surface such as a rear surface of the substrate. Such treatment is referred to as planarization treatment. As the planarization treatment, for example, chemical mechanical polishing (CMP) treatment, dry etching treatment, or the like can be performed. However, the top surface of the insulator **410** is not necessarily flat (see FIGS. **16A** to **16C**).

A method for forming the first to fourth openings are described below in detail.

First, a conductor **417a** is formed over the insulator **410**. The conductor **417a** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. Next, an insulator **419a** is formed over the conductor **417a**. The insulator **419a** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like (see FIGS. **17A** to **17C**).

Next, a resist mask **420** is formed over the insulator **419a** by a lithography method or the like. Although not shown, the resist mask **420** may be formed in such a manner that an organic coating film is formed over the insulator **419a** and then a lithography method or the like is performed on the organic coating film. Formation of the organic coating film between the insulator **419a** and the resist mask **420** may improve adhesion between the insulator **419a** and the resist mask **420** with the organic coating film interposed therebetween (see FIGS. **18A** to **18C**).

Next, first processing is performed by dry etching using the resist mask as a mask until the insulator **419a** reaches a top surface of the conductor **417a**, whereby the insulator **419** is formed. In the case where the organic coating film is formed over the insulator **419a**, the organic coating film is processed by dry etching or the like before the first processing. Examples of a gas to be used for the processing of the organic coating film include a C_4F_6 gas, a C_2F_8 gas, a CF_4 gas, a SF_6 gas, and a CHF_3 gas.

As a gas for the first processing, for example, a C_4F_6 gas, a C_2F_8 gas, a CF_4 gas, a SF_6 gas, a CHF_3 gas, or the like can be used alone or in combination. Alternatively, an oxygen gas, a helium gas, an argon gas, a hydrogen gas, or the like can be added to any of the above gases as appropriate. As a dry etching apparatus used for the processing of the organic coating film and the processing of the insulator **419**, any of the above-described dry etching apparatuses can be used; however, a dry etching apparatus in which high-frequency power sources with different frequencies are connected to the parallel-plate electrodes is preferably used (see FIGS. **19A** to **19C**).

Next, second processing is performed by dry etching until the conductor **417a** reaches the top surface of the insulator **410**, whereby the conductor **417** is formed. As a gas for the dry etching, for example, a C_4F_6 gas, a C_2F_8 gas, a CF_4 gas, a SF_6 gas, a CHF_3 gas, a Cl_2 gas, a BCl_3 gas, a $SiCl_4$ gas, or the like can be used alone or in combination. Alternatively, an oxygen gas, a helium gas, an argon gas, a hydrogen gas, or the like can be added to any of the above gases as appropriate. At this time, the resist mask **420** is eliminated by the etching in some cases. As a dry etching apparatus, the dry etching apparatuses used in the first processing may be used. Through the above steps, a hard mask including the conductor **417** and the insulator **419** is formed (see FIGS. **20A** to **20C**).

Note that the hard mask may be one layer formed only using the conductor **417**. In that case, the second processing is performed after the formation of the resist mask **420** over the conductor **417** by a lithography method or the like. By the second processing, the resist mask **420** is eliminated by the etching in some cases. Alternatively, without the hard mask, only the resist mask **420** or a two-layer mask including the organic coating film and the resist mask **420** may be used.

Next, third processing is performed on the insulator **410** until the first opening, the second opening, the third opening, and the fourth opening reach the top surface of the insulator **408** using the hard mask including the conductor **417** and the insulator **419** as a mask. As a gas for the dry etching, a gas similar to that used in the first processing can be used. As a dry etching apparatus, an apparatus similar to that used in the first processing can be used.

When the top surface of the insulator **410** is flat, the first to fourth openings differ in thickness in the insulator **410**. The order of thickness from the largest to the smallest is the first opening, the fourth opening, and the second and third openings.

That is, in the third processing, the insulator **410** in the second and third openings is etched to reach the insulator **408** first; then, the insulator **410** in the fourth opening is etched to reach the insulator **408**; lastly, the insulator **410** in the first opening is etched to reach the insulator **408**. In other words, the insulator **408** in the second opening, the third opening, and the fourth opening are over-etched in the period of time until the first opening reaches the insulator **408** after the second opening, the third opening, and the fourth opening reach the insulator **408**.

In the conditions for the third processing, the etching rate of the insulator **408** is set lower than that of the insulator **410**. In other words, by setting the ratio of the etching rate of the insulator **410** to the etching rate of the insulator **408** high, the progress of the etching of the insulator **408** in the second and third openings can be minimized. The ratio between the etching rate of the insulator **408** and the etching rate of the insulator **410** is set to 1:5 or more, preferably, 1:10 or more (see FIGS. **21A** to **21C**).

Next, fourth processing is performed on the insulator **408** by dry etching until the first opening, the second opening, and the third opening reach the insulator **412** and the fourth opening reaches the conductor **404**.

Then, fifth processing is performed on the insulator **412** by dry etching until the first opening, the second opening, and the third opening reach the insulator **406c**. The fourth opening has reached the conductor **404** by the fourth processing, and the conductor **404** in the fourth opening is over-etched by the fifth processing (see FIGS. **22A** to **22C**).

Next, sixth processing is performed on the insulator **406c** by dry etching until the first opening reaches the insulator **402**, and the second and third openings reach the conductors **416a1** and **416a2**. The fourth opening has reached the conductor **404** by the fourth processing, and the conductor **404** in the fourth opening is further over-etched by the sixth processing.

Next, seventh processing is performed on the insulator **402** by dry etching until the first opening reaches the electron trap layer **303**. The second and third openings have reached the conductors **416a1** and **416a2** by the sixth processing, and the conductor **416a1** and conductor **416a2** in the second and third openings are over-etched by the seventh processing. The fourth opening has reached the conductor **404** by the fourth processing and the conductor **404** in the fourth opening is further over-etched by the seventh processing (FIGS. **23A** to **23C**).

Next, eighth processing is performed on the electron trap layer **303** by dry etching until the first opening reaches the insulator **302**. The second and third openings have reached the conductors **416a1** and **416a2** by the sixth processing, and the conductors **416a1** and **416a2** in the second and third openings are over-etched by the eighth processing. The fourth opening has reached the conductor **404** by the fourth processing, and the conductor **404** in the fourth opening is further over-etched by the eighth processing.

Next, ninth processing is performed on the insulator **302** by dry etching until the first opening reaches the conductor **310b**. The second and third openings have reached the conductors **416a1** and **416a2** by the sixth processing, and the conductors **416a1** and **416a2** in the second and third openings are further over-etched by the ninth processing. The fourth opening has reached the conductor **404** by the fourth processing, and the conductor **404** in the fourth opening is further over-etched by the ninth processing.

The fourth to ninth processing can be performed in the same conditions. As the gas used for the dry etching, a gas similar

to that used in the first processing can be used. As a dry etching apparatus, an apparatus similar to that used in the first processing can be used.

In the conditions of the fourth to ninth processing, the ratio of the etching rates of the insulator **408** and the electron trap layer **303** is set higher than the etching rates of the conductors **404**, **416a1**, **416a2**, and **310b**, so that the progress of the etching of the conductors **404**, **416a1**, and **416a2** due to the over-etching can be suppressed. The etching rates of the conductors **404**, **416a1**, **416a2**, and **310b** are set to 1, and the etching rates of the insulator **408** and the electron trap layer **303** are set to 5 or more, preferably 10 or more.

Furthermore, in the conditions of the third to ninth processing, by making the ratio of the etching rates of the insulator **410**, the insulator **408**, the insulator **412**, the insulator **406c**, the insulator **402**, the electron trap layer **303**, and the insulator **302** to the etching rates of the insulator **419** and the conductor **417** as a hard mask high, the change in the shapes of the insulator **419** and the conductor **417** as the hard mask can be prevented, and defects in the shapes of the openings can be prevented. Specifically, upper portions of the openings can be prevented from extending. The etching rates of the insulator **419** and the conductor **417** are set to 1, and etching rates of the insulator **410**, the insulator **408**, the insulator **412**, the insulator **406c**, the insulator **402**, the electron trap layer **303**, and the insulator **302** are set to 5 or more, preferably 10 or more.

Note that the first to ninth processing can be successively performed using the same dry etching apparatus. Alternatively, when the dry etching apparatus includes a plurality of etching chambers, the first to ninth processing can be performed without exposure to air in each processing. Thus, corrosion or contamination of the substrate, attachment of dust to the substrate, or the like can be prevented; alternatively, productivity can be improved, which is preferable.

For example, when the dry etching apparatus has two etching chambers, after the first processing and the second processing are successively performed in a first chamber, the substrate is moved to a second chamber, and the third to ninth processing may be successively performed. It is preferable that different chambers be used depending on the kinds of the gases to be used in the etching (e.g., when a gas containing chlorine and a gas containing fluorine are used), because stable etching rates, and the like are obtained. Alternatively, the first to ninth processing can be performed in the first chamber and the second chamber in parallel. The parallel processing is preferable because productivity can be improved. Through the above steps, the first opening, the second opening, the third opening, and the fourth opening can be formed (see FIGS. **24A** to **24C**).

Then, a conductor **422a** is formed. The conductor **422a** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. The conductor **422a** is formed so as to fill the opening formed in the insulator **410** and others. Therefore, a CVD method (a MCVD method, in particular) is preferred. A multi-layer film of a conductor formed by an ALD method or the like and a conductor formed by a MCVD method is preferred in some cases to increase adhesion between the insulator **410** and the conductor formed by a MCVD method. For example, a multi-layer film in which titanium nitride and tungsten are stacked in this order is used (see FIGS. **25A** to **25C**).

Next, first CMP treatment is performed until the conductor **422a** reaches a top surface of the insulator **419**, whereby the conductor **422** is formed (see FIGS. **26A** to **26C**).

Next, second CMP processing is performed until the conductor **422**, the insulator **419**, and the conductor **417** reach the top surface of the insulator **410**. Accordingly, the conductor **433**, the conductor **431**, the conductor **429**, and the conductor **437** are embedded in the first opening, the second opening, the third opening, and the fourth opening, respectively (see FIGS. **27A** to **27C**).

Next, a conductor is formed over the insulator **410**, the conductor **433**, the conductor **431**, the conductor **429**, and the conductor **437**, and partly etched by a lithography method, whereby the conductor **434**, the conductor **432**, the conductor **430**, and the conductor **438** are formed. Through the above steps, the transistor in FIGS. **1A** to **1C** can be formed (see FIGS. **28A** to **28C**).

<Method 2 for Manufacturing Transistor>

A method for manufacturing a transistor in FIGS. **4A** to **4C** of one embodiment of the present invention is described below with reference to FIGS. **29A** to **29C**, FIGS. **30A** to **30C**, FIGS. **31A** to **31C**, FIGS. **32A** to **32C**, FIGS. **33A** to **33C**, FIGS. **34A** to **34C**, FIGS. **35A** to **35C**, FIGS. **36A** to **36C**, FIGS. **37A** to **37C**, FIGS. **38A** to **38C**, FIGS. **39A** to **39C**, FIGS. **40A** to **40C**, FIGS. **41A** to **41C**, FIGS. **42A** to **42C**, FIGS. **43A** to **43C**, FIGS. **44A** to **44C**, FIGS. **45A** to **45C**, FIGS. **46A** to **46C**, and FIGS. **47A** to **47C**. Note that the process up to the formation of the conductor **414** is similar to that in Method **1** for manufacturing a transistor (see FIGS. **29A** to **29C**).

Next, the insulator **406a_1**, the semiconductor **406b_1**, and the conductor **414** are processed by a lithography method or the like, whereby the multi-layer film including the insulator **406a**, the semiconductor **406b**, and the conductor **415** is formed. Here, a top surface of the semiconductor **406b_1** is damaged when the conductor **414** is formed, whereby the region **407** is formed. Since the region **407** includes a region where the resistance of the semiconductor **406b** is reduced, the contact resistance between the conductor **415** and the semiconductor **406b** is reduced. Note that when the multilayer film is formed, the insulator **402** is also subjected etching to have a thinned region in some cases. That is, the insulator **402** may have a protruding portion in a region in contact with the multilayer film (see FIGS. **30A** to **30C**).

Next, an insulator **410a** is formed. The insulator **410a** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. Alternatively, the insulator **410a** can be formed by a spin coating method, a dipping method, a droplet discharging method (such as an ink-jet method), a printing method (such as screen printing or offset printing), a doctor knife method, a roll coater method, a curtain coater method, or the like.

The insulator **410a** may be formed to have a flat top surface. For example, the top surface of the insulator **410a** may have flatness immediately after the film formation. Alternatively, for example, the insulator **410a** may have flatness by removing the insulator and the like from the top surface after the film formation so that the top surface of the insulator **410a** becomes parallel to a reference surface such as a rear surface of the substrate. Such treatment is referred to as planarization treatment. As the planarization treatment, for example, CMP treatment, dry etching treatment, or the like can be performed. However, the top surface of the insulator **410a** is not necessarily flat.

Next, the resist mask **411** is formed over the insulator **410a** by a lithography method or the like. Here, in order to improve the adhesion between the top surface of the insulator **410a** and the resist mask **411**, for example, an organic coating film may be provided between the insulator **410a**

and the resist mask **411**. Alternatively, a single layer of a conductor or a stacked layer of a conductor and an insulator is formed over the insulator **410a** to form a hard mask by a lithography method (see FIGS. **31A** to **31C**).

Next, the first processing is performed by dry etching or the like until the insulator **410a** reaches the insulator **402**, whereby the insulator **410** is formed. At that time, etching is performed until the insulator **402** reaches the electron trap layer **303** in some cases. As a gas for the dry etching in the first processing, for example, a C_4F_6 gas, a CF_4 gas, a SF_6 gas, a CHF_3 gas, or the like can be used. Alternatively, an oxygen gas, a helium gas, an argon gas, a hydrogen gas, or the like can be added to any of the above gases as appropriate. Here, a C_4F_6 gas to which an oxygen gas is added is preferably used. As a dry etching apparatus, any of the above-described dry etching apparatuses can be used; however, a dry etching apparatus in which high-frequency power sources with different frequencies are connected to parallel-plate electrodes is preferably used.

Next, the conductor **415** is subjected to the second processing using dry etching or the like so as to be separated into the conductor **416a1** and the conductor **416a2**. As a gas for the dry etching in the second processing, for example, a C_4F_6 gas, a CF_4 gas, a SF_6 gas, a Cl_2 gas, a BCl_3 gas, a $SiCl_4$ gas, and the like can be used alone or in combination. Alternatively, an oxygen gas, a helium gas, an argon gas, or a hydrogen gas can be added to any of the above gases as appropriate. Here, a combination of a CF_4 gas, a Cl_2 gas, and an oxygen gas is preferably used. As a dry etching apparatus, the above-described dry etching apparatuses for the first processing may be used.

At this time, the semiconductor **406b** has an exposed region. Here, the exposed region of the semiconductor **406b**, which is the region **407**, is removed by the second processing in some cases (see FIGS. **32A** to **32C**).

When the first processing and the second processing are each performed by dry etching, an impurity such as the residual components of the etching gas is attached to the exposed region of the semiconductor **406b** in some cases. For example, when a chlorine-based gas is used as an etching gas, chlorine and the like are attached in some cases. Furthermore, when a hydrocarbon-based gas is used as an etching gas, carbon, hydrogen, and the like are attached in some cases. When the substrate is exposed to air after the second processing, the exposed region of the semiconductor **406b** and the like corrode in some cases. Thus, plasma treatment using an oxygen gas is preferably performed successively after the second processing because the impurity can be removed and corrosion of the exposed region of the semiconductor **406b** and the like can be prevented.

Alternatively, the impurity may be reduced by cleaning treatment using diluted hydrofluoric acid or the like or cleaning treatment using ozone or the like, for example. Note that different types of cleaning treatment may be combined. In such a manner, the exposed region of the semiconductor **406b**, i.e., a channel formation region has high resistance.

Meanwhile, in the region **407** where the conductors **416a1** and **416a2** and the top surface of the semiconductor **406b** overlap with each other, a value of contact resistance between the conductors **416a1** and **416a2** and the semiconductor **406b** is preferably decreased; thus, favorable transistor characteristics can be obtained.

Next, an insulator to be the insulator **406c** is formed, and an insulator to be the insulator **412** is formed over the insulator to be the insulator **406c**. The insulator to be the insulator **406c** and the insulator to be the insulator **412** can

be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. The insulator to be the insulator **406c** and the insulator to be the insulator **412** are formed to have a uniform thickness along bottom and side surfaces of an opening formed in the insulator **410**, the conductor **416a1**, and the conductor **416a2**. Therefore, the ALD method is preferably used.

Next, the conductor to be the conductor **404** is formed. The conductor to be the conductor **404** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. The conductor to be the conductor **404** is formed so as to fill the opening formed in the insulator **410** and the like. Therefore, a CVD method (an MCVD method, in particular) is preferred. A multi-layer film of a conductor deposited by an ALD method or the like and a conductor deposited by a CVD method is preferred in some cases to increase adhesion between the insulator **410** and the conductor formed by a MCVD method. For example, the multi-layer film where titanium nitride and tungsten are formed in this order may be used.

Next, the conductor to be the conductor **404**, the insulator to be the insulator **412**, and the insulator to be the insulator **406c** are polished and flattened by CMP or the like from the top surface of the conductor to be the conductor **404** so as to reach the top surface of the insulator **410**. Accordingly, the conductor **404** functioning as the gate electrode can be formed in a self-aligned manner without using a lithography method. Furthermore, the insulator **412** and the insulator **406c** are formed.

The conductor **404** functioning as the gate electrode can be formed without considering alignment accuracy of the conductor **404** functioning as the gate electrode and the conductors **416a1** and **416a2** functioning as the source electrode and the drain electrode; as a result, the area of the semiconductor device can be reduced. Furthermore, because the lithography process is not necessary, improvement in productivity due to simplification of the process is expected (see FIGS. **33A** to **33C**).

Next, the insulator **418** is formed over the insulator **410**, the insulator **412**, and the insulator **406c**. The insulator **418** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. Then, the insulator **408** is formed over the insulator **418**. The insulator **408** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. An aluminum oxide film is preferably formed as the insulator **408** using plasma containing oxygen, so that oxygen in the plasma can be added to the top surface of the insulator **418** as excess oxygen.

Second heat treatment may be performed at any time after the formation of the insulator to be the insulator **408**. By the second heat treatment, the excess oxygen contained in the insulator **418** is moved to the semiconductor **406b** through the insulator **410**, the insulator **402**, and the insulator **406a**. Furthermore, the excess oxygen contained in the insulator **418** is moved to the semiconductor **406b** through the insulator **412** and/or the insulator **406c**. Since excess oxygen is moved to the semiconductor **406b** by passing two paths as described above, defects (oxygen vacancies) in the semiconductor **406b** can be reduced.

Note that the second heat treatment may be performed at a temperature such that excess oxygen (oxygen) in the insulator **418** is diffused to the semiconductor **406b**. For example, the description of the first heat treatment may be referred to for the second heat treatment. The second heat treatment is preferably performed at a temperature lower than that of the first heat treatment. The second heat treat-

ment is preferably performed at a temperature lower than that of the first heat treatment by higher than or equal to 20° C. and lower than or equal to 150° C., preferably higher than or equal to 40° C. and lower than or equal to 100° C. Accordingly, superfluous release of excess oxygen (oxygen) from the insulator **402** can be inhibited. Note that in the case where heating at the time of formation of the layers doubles as the second heat treatment, the second heat treatment is not necessarily performed.

Next, the insulator **428** is formed over the insulator **408**. The insulator **428** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like (see FIGS. **34A** to **34C**).

A method for forming the first to fourth openings according to one embodiment of the present invention will be described below in detail.

First, the conductor **417a** is formed over the insulator **428**. The conductor **417a** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. The insulator **419a** is formed over the conductor **417a**. The insulator **419a** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like (see FIGS. **35A** to **35C**).

Next, the resist mask **420** is formed over the insulator **419a** by a lithography method or the like. Although not shown, the resist mask **420** may be formed in such a manner that an organic coating film is formed over the insulator **419a** and then a lithography method or the like is performed on the organic coating film. Formation of the organic coating film between the insulator **419a** and the resist mask **420** may improve adhesion between the insulator **419a** and the resist mask **420** with the organic coating film interposed therebetween (see FIGS. **36A** to **36C**).

Next, the first processing is performed by dry etching or the like until the insulator **419a** reaches a top surface of the conductor **417a**, whereby the insulator **419** is formed. In the case where the organic coating film is formed over the insulator **419a**, the organic coating film is processed by dry etching or the like before the first processing. Examples of gases to be used for the processing of the organic coating film include a C₄F₆ gas, a C₂F₈ gas, a CF₄ gas, a SF₆ gas, and a CHF₃ gas.

As a gas for the first processing, for example, a C₄F₆ gas, a C₂F₈ gas, a CF₄ gas, a SF₆ gas, a CHF₃ gas, or the like can be used alone or in combination. Alternatively, an oxygen gas, a helium gas, an argon gas, a hydrogen gas, or the like can be added to any of the above gases as appropriate. As a dry etching apparatus used for the processing of the organic coating film and the processing of the insulator **419**, any of the above-described dry etching apparatuses can be used; however, a dry etching apparatus in which high-frequency power sources with different frequencies are connected to the parallel-plate electrodes is preferably used (see FIGS. **37A** to **37C**).

Next, the second processing is performed by dry etching until the conductor **417a** reaches the top surface of the insulator **428**, whereby the conductor **417** is formed. As a gas for the dry etching, for example, a C₄F₆ gas, a C₂F₈ gas, a CF₄ gas, a SF₆ gas, a CHF₃ gas, a Cl₂ gas, a BCl₃ gas, a SiCl₄ gas, or the like can be used alone or in combination. Alternatively, an oxygen gas, a helium gas, an argon gas, a hydrogen gas, or the like can be added to any of the above gases as appropriate. At this time, the resist mask **420** is eliminated by the etching in some cases. As a dry etching apparatus, the dry etching apparatuses used in the first processing may be used. Through the above steps, a hard

mask including the conductor **417** and the insulator **419** is formed (see FIGS. **38A** to **38C**).

Note that the hard mask may be one layer formed only using the conductor **417**. In that case, the second processing is performed after the formation of the resist mask **420** over the conductor **417a** by a lithography method or the like. By the second processing, the resist mask **420** is eliminated by the etching in some cases. Alternatively, without the hard mask, only the resist mask **420** or a two-layer mask including the organic coating film and the resist mask **420** may be used.

Next, the third processing is performed on the insulator **428** by dry etching until the first opening, the second opening, the third opening, and the fourth opening reach the top surface of the insulator **408** using the hard mask including the conductor **417** and the insulator **419** as a mask. As a gas for the dry etching, a gas similar to that used in the first processing can be used. As a dry etching apparatus, an apparatus similar to that used in the first processing can be used (see FIGS. **39A** to **39C**).

Next, the fourth processing is performed on the insulator **408** by dry etching until the first opening, the second opening, the third opening, and the fourth opening reach the top surface of the insulator **418**.

Next, the fifth processing is performed on the insulator **418** by dry etching until the first to third openings reach the insulator **410** and the fourth opening reaches the conductor **404**.

Next, the sixth processing is performed on the insulator **410** by dry etching until the first opening, the second opening, and the third opening reach the insulator **402**, the conductor **416a1**, and the conductor **416a2**, respectively. The insulator **410** is not included in the fourth opening, and the conductor **404** is over-etched by the sixth processing since the fourth opening has already reached the conductor **404** by the fifth processing (see FIGS. **40A** to **40C**).

Since the insulator **410** has a flat top surface by CMP treatment or the like, the first opening and the second and third openings differ in thickness in the insulator **410**. The order of thickness from the largest to the smallest is the first opening, and the second and third openings. Note that the insulator **410** is not included in the fourth opening.

That is, in the sixth processing, the insulator **410** in the second and third openings is etched to reach the conductors **416a1** and **416a2** first; then, the insulator **410** in the first opening is etched to reach the insulator **402**. In other words, the conductors **416a1** and **416a2** in the second and third openings are over-etched in the period of time after the second opening and the third opening reach the conductors **416a1** and **416a2** respectively and until the first opening reaches the insulator **402**. Alternatively, the conductor **404** in the fourth opening is over-etched during the sixth processing.

Next, the seventh processing is performed on the insulator **402** and the electron trap layer **303** by dry etching until the first opening reaches the insulator **302**. Since the second and third openings have reached the conductors **416a1** and **416a2** by the sixth processing, the conductors **416a1** and **416a2** are further over-etched by the seventh processing. Since the fourth opening has reached the conductor **404** by the fifth processing, the conductor **404** is over-etched by the seventh processing (see FIGS. **41A** to **41C**).

Next, the eighth processing is performed on the insulator **302** by dry etching until the first opening reaches the conductor **310b**. Since the second opening and the third opening have reached the conductors **416a1** and **416a2** by the sixth processing, the conductors **416a1** and **416a2** are

41

further over-etched by the eighth processing. Since the fourth opening has reached the conductor **404** by the fifth processing, the conductor **404** is over-etched by the eighth processing (see FIGS. **42A** to **42C**).

The fourth to eighth processing can be performed in the same conditions. As a gas used for the dry etching, a gas similar to that used in the first processing can be used. As a dry etching apparatus, an apparatus similar to that used in the first processing can be used.

In the conditions of the fourth to eighth processing, the ratio of the etching rates of the insulator **408** and the electron trap layer **303** is set higher than the etching rates of the conductors **404**, **416a1**, **416a2**, and **310b**, so that the progress of the etching of the conductors **404**, **416a1**, and **416a2** due to the over-etching can be suppressed. The etching rates of the conductors **404**, **416a1**, **416a2**, and **310b** are set to 1, and the etching rates of the insulator **408** and the electron trap layer **303** are set to 5 or more, preferably 10 or more.

Furthermore, in the conditions of the third to eighth processing, by making the ratio of the etching rates of the insulator **428**, the insulator **418**, the insulator **408**, the insulator **410**, the insulator **402**, the electron trap layer **303**, and the insulator **302** to the etching rates of the insulator **419** and the conductor **417** as a hard mask high, the change in the shapes of the insulator **419** and the conductor **417** as the hard mask can be prevented, and defects in the shapes of the openings can be prevented. Specifically, upper portions of the openings can be prevented from extending. The etching rates of the insulator **419** and the conductor **417** are set to 1, and etching rates of the insulator **428**, the insulator **418**, the insulator **408**, the insulator **410**, the insulator **402**, the electron trap layer **303**, and the insulator **302** are set to 5 or more, preferably 10 or more.

Next, the conductor **422a** is formed. The conductor **422a** can be formed by a sputtering method, a CVD method, an MBE method, a PLD method, an ALD method, or the like. The conductor **422a** is formed so as to fill the opening formed in the insulator **410** and others. Therefore, a CVD method (a MCVD method, in particular) is preferred. A multi-layer film of a conductor formed by an ALD method or the like and a conductor formed by a CVD method is preferred in some cases to increase adhesion between the insulator **410** and the like and the conductor formed by a MCVD method. For example, a multi-layer film including titanium nitride and tungsten in this order is used (see FIGS. **43A** to **43C**).

Next, the first CMP treatment is performed until the conductor **422a** reaches the top surface of the insulator **419**, whereby the conductor **422** is formed (see FIGS. **44A** to **44C**).

Next, the second CMP processing is performed until the conductor **422**, the insulator **419**, and the conductor **417** reach the top surface of the insulator **428**. Accordingly, the conductor **433**, the conductor **431**, the conductor **429**, and the conductor **437** are embedded in the first opening, the second opening, the third opening, and the fourth opening, respectively (see FIGS. **45A** to **45C**).

Next, the conductor is formed over the insulator **428**, the conductor **433**, the conductor **431**, the conductor **429**, and the conductor **437**, and partly etched by a lithography method, whereby the conductor **434**, the conductor **432**, the conductor **430**, and the conductor **438** are formed. Through the above steps, the transistor in FIGS. **4A** to **4C** can be formed (see FIGS. **46A** to **46C**).

As described above, when the insulator **410** is formed, the first processing is performed by dry etching until the insulator **410a** reaches the insulator **402**, whereby the insulator

42

410 is formed. At that time, the etching is performed until the insulator **402** reaches the electron trap layer **303** in some cases. The transistor in that case has a structure shown in FIGS. **47A** to **47C**. At least part of this embodiment can be implemented in combination with any of the embodiments described in this specification as appropriate.

Embodiment 4

<Memory Device 1>

An example of a semiconductor device (memory device) which includes the transistor of one embodiment of the present invention, which can retain stored data even when not powered, and which has an unlimited number of write cycles is shown in FIGS. **48A** and **48B**.

The semiconductor device illustrated in FIG. **48A** includes a transistor **3200** using a first semiconductor, a transistor **3300** using a second semiconductor, and a capacitor **3400**. Note that any of the above-described transistors can be used as the transistor **3300**.

The transistor **3300** is preferably a transistor with a low off-state current. For example, a transistor using an oxide semiconductor can be used as the transistor **3300**. Since the off-state current of the transistor **3300** is low, stored data can be retained for a long period at a predetermined node of the semiconductor device. In other words, power consumption of the semiconductor device can be reduced because refresh operation becomes unnecessary or the frequency of refresh operation can be extremely low.

In FIG. **48A**, a first wiring **3001** is electrically connected to a source of the transistor **3200**. A second wiring **3002** is electrically connected to a drain of the transistor **3200**. A third wiring **3003** is electrically connected to one of the source and the drain of the transistor **3300**. A fourth wiring **3004** is electrically connected to the gate of the transistor **3300**. The gate of the transistor **3200** and the other of the source and the drain of the transistor **3300** are electrically connected to one electrode of the capacitor **3400**. A fifth wiring **3005** is electrically connected to the other electrode of the capacitor **3400**.

The semiconductor device in FIG. **48A** has a feature that the potential of the gate of the transistor **3200** can be retained, and thus enables writing, retaining, and reading of data as follows.

Writing and retaining of data are described. First, the potential of the fourth wiring **3004** is set to a potential at which the transistor **3300** is on, so that the transistor **3300** is turned on. Accordingly, the potential of the third wiring **3003** is supplied to a node FG where the gate of the transistor **3200** and the one electrode of the capacitor **3400** are electrically connected to each other. That is, a predetermined electric charge is supplied to the gate of the transistor **3200** (writing). Here, one of two kinds of electric charges providing different potential levels (hereinafter referred to as a low-level electric charge and a high-level electric charge) is supplied. After that, the potential of the fourth wiring **3004** is set to a potential at which the transistor **3300** is off, so that the transistor **3300** is turned off. Thus, the electric charge is held at the node FG (retaining).

Since the off-state current of the transistor **3300** is low, the electric charge of the node FG is retained for a long time.

Next, reading of data is described. An appropriate potential (a reading potential) is supplied to the fifth wiring **3005** while a predetermined potential (a constant potential) is supplied to the first wiring **3001**, whereby the potential of the second wiring **3002** varies depending on the amount of electric charge retained in the node FG. This is because in

the case of using an n-channel transistor as the transistor **3200**, an apparent threshold voltage $V_{th,H}$ at the time when the high-level electric charge is given to the gate of the transistor **3200** is lower than an apparent threshold voltage $V_{th,L}$ at the time when the low-level electric charge is given to the gate of the transistor **3200**. Here, an apparent threshold voltage refers to the potential of the fifth wiring **3005** which is needed to make the transistor **3200** be in "on state." Thus, the potential of the fifth wiring **3005** is set to a potential V_0 which is between $V_{th,H}$ and $V_{th,L}$, whereby electric charge supplied to the node FG can be determined. For example, in the case where the high-level electric charge is supplied to the node FG in writing and the potential of the fifth wiring **3005** is $V_0 (>V_{th,H})$, the transistor **3200** is brought into "on state." In the case where the low-level electric charge is supplied to the node FG in writing, even when the potential of the fifth wiring **3005** is $V_0 (<V_{th,L})$, the transistor **3200** still remains in "off state." Thus, the data retained in the node FG can be read by determining the potential of the second wiring **3002**.

Note that in the case where memory cells are arrayed, it is necessary that data of a desired memory cell be read in read operation. The fifth wiring **3005** of memory cells from which data is not read may be supplied with a potential at which the transistor **3200** is turned off regardless of the electric charge supplied to the node FG, that is, a potential lower than $V_{th,H}$, whereby only data of a desired memory cell can be read. Alternatively, the fifth wiring **3005** of the memory cells from which data is not read may be supplied with a potential at which the transistor **3200** is brought into "on state" regardless of the electric charge supplied to the node FG, that is, a potential higher than $V_{th,L}$, whereby only data of a desired memory cell can be read.

<Structure 1 of Semiconductor Device>

FIG. **49** is a cross-sectional view of the semiconductor device in FIG. **48A**. The semiconductor device shown in FIG. **49** includes the transistor **3200**, the transistor **3300**, and the capacitor **3400**. The transistor **3300** and the capacitor **3400** are provided over the transistor **3200**. Although an example where the transistor illustrated in FIGS. **1A** to **1C** is used as the transistor **3300** is shown, a semiconductor device of one embodiment of the present invention is not limited thereto. The description of the above transistor is referred to as appropriate.

The transistor **3200** illustrated in FIG. **49** is a transistor using a semiconductor substrate **450**. The transistor **3200** includes a region **474a** in the semiconductor substrate **450**, a region **474b** in the semiconductor substrate **450**, an insulator **462**, and a conductor **454**.

In the transistor **3200**, the regions **474a** and **474b** have a function as a source region and a drain region. The insulator **462** has a function as a gate insulator. The conductor **454** has a function as a gate electrode. Therefore, resistance of a channel formation region can be controlled by a potential applied to the conductor **454**. In other words, conduction or non-conduction between the region **474a** and the region **474b** can be controlled by the potential applied to the conductor **454**.

For the semiconductor substrate **450**, a single-material semiconductor substrate of silicon, germanium, or the like or a compound semiconductor substrate of silicon carbide, silicon germanium, gallium arsenide, indium phosphide, zinc oxide, gallium oxide, or the like may be used, for example. A single crystal silicon substrate is preferably used as the semiconductor substrate **450**.

For the semiconductor substrate **450**, a semiconductor substrate including impurities imparting n-type conductivity

is used. However, a semiconductor substrate including impurities imparting p-type conductivity may be used as the semiconductor substrate **450**. In that case, a well including impurities imparting the n-type conductivity may be provided in a region where the transistor **3200** is formed. Alternatively, the semiconductor substrate **450** may be an i-type semiconductor substrate.

The top surface of the semiconductor substrate **450** preferably has a (110) plane. Thus, on-state characteristics of the transistor **3200** can be improved.

The regions **474a** and **474b** are regions including impurities imparting the p-type conductivity. Accordingly, the transistor **3200** has a structure of a p-channel transistor.

Note that although the transistor **3200** is illustrated as a p-channel transistor, the transistor **3200** may be an n-channel transistor.

Note that the transistor **3200** is separated from an adjacent transistor by the region **460** and the like. The region **460** is an insulating region.

The semiconductor device illustrated in FIG. **49** includes an insulator **464**, an insulator **466**, an insulator **468**, an insulator **470**, an insulator **472**, an insulator **475**, the insulator **402**, the insulator **410**, the insulator **418**, the insulator **408**, the insulator **428**, an insulator **465**, an insulator **467**, an insulator **469**, an insulator **498**, a conductor **480a**, a conductor **480b**, a conductor **480c**, a conductor **478a**, a conductor **478b**, a conductor **478c**, a conductor **476a**, a conductor **476b**, a conductor **476c**, a conductor **479a**, a conductor **479b**, a conductor **479c**, a conductor **477a**, a conductor **477b**, a conductor **477c**, a conductor **484a**, a conductor **484b**, a conductor **484c**, a conductor **484d**, a conductor **483a**, a conductor **483b**, a conductor **483c**, a conductor **483d**, a conductor **483e**, a conductor **483f**, a conductor **485a**, a conductor **485b**, a conductor **485c**, a conductor **485d**, a conductor **487a**, a conductor **487b**, a conductor **487c**, a conductor **488a**, a conductor **488b**, a conductor **488c**, a conductor **490a**, a conductor **490b**, a conductor **489a**, a conductor **489b**, a conductor **491a**, a conductor **491b**, a conductor **491c**, a conductor **492a**, a conductor **492b**, a conductor **492c**, a conductor **494**, a conductor **496**, the insulator **406a**, the semiconductor **406b**, and the insulator **406c**.

The insulator **464** is provided over the transistor **3200**. The insulator **466** is over the insulator **464**. The insulator **468** is over the insulator **466**. The insulator **470** is placed over the insulator **468**. The insulator **472** is placed over the insulator **470**. The insulator **475** is placed over the insulator **472**. The transistor **3300** is provided over the insulator **475**. The insulator **418** is provided over the transistor **3300**. The insulator **408** is provided over the insulator **418**. The insulator **428** is provided over the insulator **408**. The insulator **465** is over the insulator **428**. The capacitor **3400** is provided over the insulator **465**. The insulator **469** is provided over the capacitor **3400**.

The insulator **464** includes an opening reaching the region **474a**, an opening reaching the region **474b**, and an opening reaching the conductor **454**, in which the conductor **480a**, the conductor **480b**, and the conductor **480c** are embedded, respectively.

In addition, the insulator **466** includes an opening reaching the conductor **480a**, an opening reaching the conductor **480b**, and an opening reaching the conductor **480c**, in which the conductor **478a**, the conductor **478b**, and the conductor **478c** are embedded, respectively.

In addition, the insulator **468** includes an opening reaching the conductor **478a**, an opening reaching the conductor **478b**, and an opening reaching the conductor **478c**, in which

the conductor **476a**, the conductor **476b**, and the conductor **476c** are embedded, respectively.

The conductor **479a** in contact with the conductor **476a**, the conductor **479b** in contact with the conductor **476b**, and the conductor **479c** in contact with the conductor **476c** are over the insulator **468**. The insulator **472** includes an opening reaching the conductor **479a** through the insulator **470**, an opening reaching the conductor **479b** through the insulator **470** and an opening reaching the conductor **479c** through the insulator **470**. In the openings, the conductor **477a**, the conductor **477b**, and the conductor **477c** are embedded.

The insulator **475** includes an opening overlapping with the channel formation region of the transistor **3300**, an opening reaching the conductor **477a**, an opening reaching the conductor **477b**, an opening reaching the conductor **477c**, and an opening reaching the insulator **472**. In the openings, the conductor **484a**, the conductor **484b**, the conductor **484c**, and the conductor **484d** are embedded.

The conductor **484d** may have a function as a bottom gate electrode of the transistor **3300**. Alternatively, for example, electrical characteristics such as the threshold voltage of the transistor **3300** may be controlled by application of a constant potential to the conductor **484d**. Further alternatively, for example, the conductor **484d** and the top gate electrode of the transistor **3300** may be electrically connected to each other. Thus, the on-state current of the transistor **3300** can be increased. A punch-through phenomenon can be suppressed; thus, stable electrical characteristics in the saturation region of the transistor **3300** can be obtained.

In addition, the insulator **402** includes an opening reaching the conductor **484a**, an opening reaching the conductor **484b**, and an opening reaching the conductor **484c**.

The insulator **428** includes an opening reaching the conductor **484a** through the insulator **408**, the insulator **418**, the insulator **410**, and the insulator **402**, an opening reaching the conductor **484c** through the insulator **408**, the insulator **418**, the insulator **410**, and the insulator **402**, two openings reaching a conductor of one of the source electrode and the drain electrode of the transistor **3300** through the insulator **408**, the insulator **418**, and the insulator **410**, an opening reaching a conductor of the gate electrode of the transistor **3300** through the insulator **408** and the insulator **418** and an opening reaching the conductor **484b** through the insulator **408**, the insulator **418**, the insulator **410**, and the insulator **402**. In the openings, the conductor **483a**, the conductor **483b**, the conductor **483c**, the conductor **483e**, the conductor **483f**, and the conductor **483d** are embedded.

The conductor **485a** in contact with the conductors **483a** and **483e**, the conductor **485b** in contact with the conductor **483b**, the conductor **485c** in contact with the conductor **483c** and the conductor **483f**, and the conductor **485d** in contact with the conductor **483d** are over the insulator **428**. The insulator **465** has an opening reaching the conductor **485a**, an opening reaching the conductor **485b**, and an opening reaching the conductor **485c**. In the openings, the conductor **487a**, the conductor **487b**, and the conductor **487c** are embedded.

The conductor **488a** in contact with the conductor **487a**, the conductor **488b** in contact with the conductor **487b**, and the conductor **488c** in contact with the conductor **487c** are over the insulator **465**. In addition, the insulator **467** includes an opening reaching the conductor **488a** and an opening reaching the conductor **488b**. In the openings, the conductor **490a** and the conductor **490b** are embedded. The conductor **488c** is in contact with the conductor **494** which is one of the electrodes of the capacitor **3400**.

The conductor **489a** in contact with the conductor **490a** and the conductor **489b** in contact with the conductor **490b** are over the insulator **467**. The insulator **469** includes an opening reaching the conductor **489a**, an opening reaching the conductor **489b**, and an opening reaching the conductor **496** which is the other of the electrodes of the capacitor **3400**. In the openings, the conductor **491a**, the conductor **491b**, and the conductor **491c** are embedded.

The conductor **492a** in contact with the conductor **491a**, the conductor **492b** in contact with the conductor **491b**, and the conductor **492c** in contact with the conductor **491c** are over the insulator **469**.

The insulators **464**, **466**, **468**, **470**, **472**, **475**, **402**, **410**, **408**, **428**, **465**, **467**, **469**, and **498** may each be formed to have, for example, a single-layer structure or a stacked-layer structure including an insulator containing boron, carbon, nitrogen, oxygen, fluorine, magnesium, aluminum, silicon, phosphorus, chlorine, argon, gallium, germanium, yttrium, zirconium, lanthanum, neodymium, hafnium, or tantalum. The insulator **401** may be formed of, for example, aluminum oxide, magnesium oxide, silicon oxide, silicon oxynitride, silicon nitride oxide, silicon nitride, gallium oxide, germanium oxide, yttrium oxide, zirconium oxide, lanthanum oxide, neodymium oxide, hafnium oxide, or tantalum oxide.

The insulator that has a function of blocking oxygen and impurities such as hydrogen is preferably included in at least one of the insulators **464**, **466**, **468**, **470**, **472**, **475**, **402**, **410**, **408**, **428**, **465**, **467**, **469**, and **498**. When an insulator that has a function of blocking oxygen and impurities such as hydrogen is placed near the transistor **3300**, the electrical characteristics of the transistor **3300** can be stable.

An insulator with a function of blocking oxygen and impurities such as hydrogen may have a single-layer structure or a stacked-layer structure including an insulator containing, for example, boron, carbon, nitrogen, oxygen, fluorine; magnesium, aluminum, silicon, phosphorus, chlorine, argon, gallium, germanium, yttrium, zirconium, lanthanum, neodymium, hafnium, or tantalum.

Each of the conductors **480a**, **480b**, **480c**, **478a**, **478b**, **478c**, **476a**, **476b**, **476c**, **479a**, **479b**, **479c**, **477a**, **477b**, **477c**, **484a**, **484b**, **484c**, **484d**, **483a**, **483b**, **483c**, **483d**, **483e**, **483f**, **485a**, **485b**, **485c**, **485d**, **487a**, **487b**, **487c**, **488a**, **488b**, **488c**, **490a**, **490b**, **489a**, **489b**, **491a**, **491b**, **491c**, **492a**, **492b**, **492c**, **494**, and **496** may have a single-layer structure or a stacked-layer structure including a conductor containing, for example, one or more kinds of boron, nitrogen, oxygen, fluorine, silicon, phosphorus, aluminum, titanium, chromium, manganese, cobalt, nickel, copper, zinc, gallium, yttrium, zirconium, molybdenum, ruthenium, silver, indium, tin, tantalum, and tungsten. An alloy or a compound may be used, for example, and a conductor containing aluminum, a conductor containing copper and titanium, a conductor containing copper and manganese, a conductor containing indium, tin, and oxygen, a conductor containing titanium and nitrogen, or the like may be used.

An oxide semiconductor is preferably used as the semiconductor **406b**. However, silicon (including strained silicon), germanium, silicon germanium, silicon carbide, gallium arsenide, aluminum gallium arsenide, indium phosphide, gallium nitride, an organic semiconductor, or the like can be used in some cases.

As the insulator **406a** and the insulator **406c**, oxides containing one or more, or two or more elements other than oxygen included in the semiconductor **406b** are preferably used. However, silicon (including strained silicon), germanium, silicon germanium, silicon carbide, gallium arsenide,

aluminum gallium arsenide, indium phosphide, gallium nitride, an organic semiconductor, or the like can be used in some cases.

The source or drain of the transistor **3200** is electrically connected to the conductor that is one of the source electrode and the drain electrode of the transistor **3300** through the conductor **480a**, the conductor **478a**, the conductor **476a**, the conductor **479a**, the conductor **477a**, the conductor **484a**, the conductor **483a**, the conductor **485a**, and the conductor **483e**. The conductor **454** that is the gate electrode of the transistor **3200** is electrically connected to the conductor that is the other of the source electrode and the drain electrode of the transistor **3300** through the conductor **480c**, the conductor **478c**, the conductor **476c**, the conductor **479c**, the conductor **477c**, the conductor **484c**, the conductor **483c**, the conductor **485c**, and the conductor **483f**.

The capacitor **3400** includes one of the source electrode and the drain electrode of the transistor **3300**, the conductor **494** electrically connected to one of the electrodes of the capacitor **3400** through the conductor **483c**, the conductor **485c**, the conductor **487c**, and the conductor **488c**, the insulator **498**, the conductor **496** that is the other electrode of the capacitor **3400**. The capacitor **3400** is preferably formed above or below the transistor **3300** because the semiconductor can be reduced in size.

For the structures of other components, the description of FIGS. **4A** to **4C** and the like can be referred to as appropriate.

A semiconductor device in FIG. **50** is the same as the semiconductor device in FIG. **49** except the structure of the transistor **3200**. Therefore, the description of the semiconductor device in FIG. **49** is referred to for the semiconductor device in FIG. **50**. Specifically, in the semiconductor device in FIG. **50**, the transistor **3200** is a FIN-type transistor. The effective channel width is increased in the FIN-type transistor **3200**, whereby the on-state characteristics of the transistor **3200** can be improved. In addition, since contribution of the electric field of the gate electrode can be increased, the off-state characteristics of the transistor **3200** can be improved. Note that the transistor **3200** may be a p-channel transistor or an n-channel transistor.

Although an example in which the transistor **3300** is over the transistor **3200** and the capacitor **3400** is over the transistor **3300** is illustrated in this embodiment, one or more transistors including a semiconductor similar to that included in the transistor **3300** may be provided over the transistor **3200**. With such a structure, the degree of integration of the semiconductor device can be further increased.

<Memory Device 2>

The semiconductor device in FIG. **48B** is different from the semiconductor device in FIG. **48A** in that the transistor **3200** is not provided. Also in this case, data can be written and retained in a manner similar to that of the semiconductor device in FIG. **48A**.

Reading of data in the semiconductor device in FIG. **48B** is described. When the transistor **3300** is turned on, the third wiring **3003** which is in a floating state and the capacitor **3400** are electrically connected to each other, and the charge is redistributed between the third wiring **3003** and the capacitor **3400**. As a result, the potential of the third wiring **3003** is changed. The amount of change in potential of the third wiring **3003** varies depending on the potential of the one of the electrode of the capacitor **3400** (or the charge accumulated in the capacitor **3400**).

For example, the potential of the third wiring **3003** after the charge redistribution is $(C_B \times V_{B0} + C \times V) / (C_B + C)$, where V is the potential of the one electrode of the capacitor **3400**,

C is the capacitance of the capacitor **3400**, C_B is the capacitance component of the third wiring **3003**, and V_{B0} is the potential of the third wiring **3003** before the charge redistribution. Thus, it can be found that, assuming that the memory cell is in either of two states in which the potential of the one electrode of the capacitor **3400** is V_1 and V_0 ($V_1 > V_0$), the potential of the third wiring **3003** in the case of retaining the potential V_1 ($= (C_B \times V_{B0} + C \times V_1) / (C_B + C)$) is higher than the potential of the third wiring **3003** in the case of retaining the potential V_0 ($= (C_B \times V_{B0} + C \times V_0) / (C_B + C)$).

Then, by comparing the potential of the third wiring **3003** with a predetermined potential, data can be read.

In this case, a transistor including the first semiconductor may be used for a driver circuit for driving a memory cell, and a transistor including the second semiconductor may be stacked over the driver circuit as the transistor **3300**.

When including a transistor using an oxide semiconductor and having a low off-state current, the semiconductor device described above can retain stored data for a long time. In other words, refresh operation becomes unnecessary or the frequency of the refresh operation can be extremely low, which leads to a sufficient reduction in power consumption. Moreover, stored data can be retained for a long time even when power is not supplied (note that a potential is preferably fixed).

Further, in the semiconductor device, high voltage is not needed for writing data and deterioration of elements is less likely to occur. Unlike in a conventional nonvolatile memory, for example, it is not necessary to inject and extract electrons into and from a floating gate; thus, a problem such as deterioration of an insulator is not caused. That is, the semiconductor device of one embodiment of the present invention does not have a limit on the number of times data can be rewritten, which is a problem of a conventional nonvolatile memory, and the reliability thereof is drastically improved. Furthermore, data is written depending on the state of the transistor (on or off), whereby high-speed operation can be achieved. At least part of this embodiment can be implemented in combination with any of the embodiments described in this specification as appropriate.

Embodiment 5

<Structure 2 of Semiconductor Device>

In this embodiment, an example of a circuit including the transistor of one embodiment of the present invention is described with reference to drawings.

<Cross-Sectional Structure>

FIGS. **51A** and **51B** are cross-sectional views of a semiconductor device of one embodiment of the present invention. In FIG. **51A**, X1-X2 direction represents a channel length direction, and in FIG. **51B**, Y1-Y2 direction represents a channel width direction. The semiconductor device illustrated in FIGS. **51A** and **51B** includes a transistor **2200** containing a first semiconductor material in a lower portion and a transistor **2100** containing a second semiconductor material in an upper portion. In FIGS. **51A** and **51B**, an example is illustrated in which the transistor illustrated in FIGS. **4A** to **4C** is used as the transistor **2100** containing the second semiconductor material.

Here, the first semiconductor material and the second semiconductor material are preferably materials having different band gaps. For example, the first semiconductor material can be a semiconductor material other than an oxide semiconductor (examples of such a semiconductor material include silicon (including strained silicon), germanium, silicon germanium, silicon carbide, gallium arsenide, aluminum

gallium arsenide, indium phosphide, gallium nitride, and an organic semiconductor), and the second semiconductor material can be an oxide semiconductor. A transistor using a material other than an oxide semiconductor, such as single crystal silicon, can operate at high speed easily. In contrast, a transistor using an oxide semiconductor and described in the above embodiment as an example has excellent sub-threshold characteristics and a minute structure. Furthermore, the transistor can operate at a high speed because of its high switching speed and has low leakage current because of its low off-state current.

The transistor **2200** may be either an n-channel transistor or a p-channel transistor, and an appropriate transistor may be used in accordance with a circuit. Furthermore, the specific structure of the semiconductor device, such as the material or the structure used for the semiconductor device, is not necessarily limited to those described here except for the use of the transistor of one embodiment of the present invention which uses an oxide semiconductor.

FIGS. **51A** and **51B** illustrate a structure in which the transistor **2100** is provided over the transistor **2200** with an insulator **2201**, an insulator **2207**, and an insulator **2208** provided therebetween. A plurality of wirings **2202** are provided between the transistor **2200** and the transistor **2100**. Furthermore, wirings and electrodes provided over and under the insulators are electrically connected to each other through a plurality of plugs **2203** embedded in the insulators. An insulator **2204** covering the transistor **2100** and a wiring **2205** over the insulator **2204** are provided.

The stack of the two kinds of transistors reduces the area occupied by the circuit, allowing a plurality of circuits to be highly integrated.

Here, in the case where a silicon-based semiconductor material is used for the transistor **2200** provided in a lower portion, hydrogen in an insulator provided in the vicinity of the semiconductor film of the transistor **2200** terminates dangling bonds of silicon; accordingly, the reliability of the transistor **2200** can be improved. Meanwhile, in the case where an oxide semiconductor is used for the transistor **2100** provided in an upper portion, hydrogen in an insulator provided in the vicinity of the semiconductor film of the transistor **2100** becomes a factor of generating carriers in the oxide semiconductor; thus, the reliability of the transistor **2100** might be decreased. Therefore, in the case where the transistor **2100** using an oxide semiconductor is provided over the transistor **2200** using a silicon-based semiconductor material, it is particularly effective that the insulator **2207** having a function of preventing diffusion of hydrogen is provided between the transistors **2100** and **2200**. The insulator **2207** makes hydrogen remain in the lower portion, thereby improving the reliability of the transistor **2200**. In addition, since the insulator **2207** suppresses diffusion of hydrogen from the lower portion to the upper portion, the reliability of the transistor **2100** also can be improved.

The insulator **2207** can be, for example, formed using aluminum oxide, aluminum oxynitride, gallium oxide, gallium oxynitride, yttrium oxide, yttrium oxynitride, hafnium oxide, hafnium oxynitride, or yttria-stabilized zirconia (YSZ).

Furthermore, a blocking film having a function of preventing diffusion of hydrogen is preferably formed over the transistor **2100** to cover the transistor **2100** including an oxide semiconductor film. For the blocking film, a material that is similar to that of the insulator **2207** can be used, and in particular, an aluminum oxide film is preferably used. Using the aluminum oxide film, excess oxygen can be added to the insulator under the aluminum oxide film in the

deposition, and the excess oxygen moves to the oxide semiconductor layer of the transistor **2100** by heat treatment, which has an effect of repairing a defect in the oxide semiconductor layer. The aluminum oxide film has a high shielding (blocking) effect of preventing penetration of both oxygen and impurities such as hydrogen and moisture. Thus, by using the aluminum oxide film as the blocking film covering the transistor **2100**, release of oxygen from the oxide semiconductor film included in the transistor **2100** and entry of water and hydrogen into the oxide semiconductor film can be prevented. Note that as the block film, the insulator **2204** having a stacked-layer structure may be used, or the block film may be provided under the insulator **2204**.

Note that the transistor **2200** can be a transistor of various types without being limited to a planar type transistor. For example, the transistor **2200** can be a fin-type transistor, a tri-gate transistor, or the like. An example of a cross-sectional view in this case is shown in FIGS. **51E** and **51F**. An insulator **2212** is provided over a semiconductor substrate **2211**. The semiconductor substrate **2211** includes a projecting portion with a thin tip (also referred to a fin). Note that an insulator may be provided over the projecting portion. The insulator functions as a mask for preventing the semiconductor substrate **2211** from being etched when the projecting portion is formed. The projecting portion does not necessarily have the thin tip; a projecting portion with a cuboid-like projecting portion and a projecting portion with a thick tip are permitted, for example. A gate insulator **2214** is provided over the projecting portion of the semiconductor substrate **2211**, and a gate electrode **2213** is provided over the gate insulator **2214**. Source and drain regions **2215** are formed in the semiconductor substrate **2211**. Note that here is shown an example in which the semiconductor substrate **2211** includes the projecting portion; however, a semiconductor device of one embodiment of the present invention is not limited thereto. For example, a semiconductor region having a projecting portion may be formed by processing an SOI substrate.

At least part of this embodiment can be implemented in combination with any of the embodiments described in this specification as appropriate.

Embodiment 6

CMOS Circuit

A circuit diagram in FIG. **51C** shows a configuration of a so-called CMOS circuit in which a p-channel transistor **2200** and an n-channel transistor **2100** are connected to each other in series and in which gates of them are connected to each other.

Analog Switch

A circuit diagram in FIG. **51D** shows a configuration in which sources of the transistors **2100** and **2200** are connected to each other and drains of the transistors **2100** and **2200** are connected to each other. With such a configuration, the transistors can function as a so-called analog switch. At least part of this embodiment can be implemented in combination with any of the embodiments described in this specification as appropriate.

<CPU>

A CPU including a semiconductor device such as any of the above-described transistors or the above-described memory device is described below.

FIG. 52 is a block diagram illustrating a configuration example of a CPU including any of the above-described transistors as a component.

The CPU illustrated in FIG. 52 includes, over a substrate 1190, an arithmetic logic unit (ALU) 1191, an ALU controller 1192, an instruction decoder 1193, an interrupt controller 1194, a timing controller 1195, a register 1196, a register controller 1197, a bus interface 1198, a rewritable ROM 1199, and a ROM interface 1189. A semiconductor substrate, an SOI substrate, a glass substrate, or the like is used as the substrate 1190. The ROM 1199 and the ROM interface 1189 may be provided over a separate chip. Needless to say, the CPU in FIG. 52 is just an example of a simplified structure, and an actual CPU may have a variety of structures depending on the application. For example, the CPU may have the following configuration: a structure including the CPU illustrated in FIG. 52 or an arithmetic circuit is considered as one core; a plurality of the cores are included; and the cores operate in parallel. The number of bits that the CPU can process in an internal arithmetic circuit or in a data bus can be 8, 16, 32, or 64, for example.

An instruction that is input to the CPU through the bus interface 1198 is input to the instruction decoder 1193 and decoded therein, and then, input to the ALU controller 1192, the interrupt controller 1194, the register controller 1197, and the timing controller 1195.

The ALU controller 1192, the interrupt controller 1194, the register controller 1197, and the timing controller 1195 conduct various controls in accordance with the decoded instruction. Specifically, the ALU controller 1192 generates signals for controlling the operation of the ALU 1191. While the CPU is executing a program, the interrupt controller 1194 processes an interrupt request from an external input/output device or a peripheral circuit depending on its priority or a mask state. The register controller 1197 generates an address of the register 1196, and reads/writes data from/to the register 1196 depending on the state of the CPU.

In the CPU illustrated in FIG. 52, a memory cell is provided in the register 1196. For the memory cell of the register 1196, any of the above-described transistors, the above-described memory device, or the like can be used.

In the CPU illustrated in FIG. 52, the register controller 1197 selects operation of retaining data in the register 1196 in accordance with an instruction from the ALU 1191. That is, the register controller 1197 selects whether data is held by a flip-flop or by a capacitor in the memory cell included in the register 1196. When data holding by the flip-flop is selected, a power supply voltage is supplied to the memory cell in the register 1196. When data holding by the capacitor is selected, the data is rewritten in the capacitor, and supply of the power supply voltage to the memory cell in the register 1196 can be stopped.

FIG. 53 is an example of a circuit diagram of a memory element that can be used as the register 1196. A memory element 1200 includes a circuit 1201 in which stored data is volatile when power supply is stopped, a circuit 1202 in which stored data is nonvolatile even when power supply is stopped, a switch 1203, a switch 1204, a logic element 1206, a capacitor 1207, and a circuit 1220 having a selecting function. The circuit 1202 includes a capacitor 1208, a transistor 1209, and a transistor 1210. Note that the memory

element 1200 may further include another element such as a diode, a resistor, or an inductor, as needed.

Here, the above-described memory device can be used as the circuit 1202. When supply of a power supply voltage to the memory element 1200 is stopped, GND (0 V) or a potential at which the transistor 1209 in the circuit 1202 is turned off continues to be input to a gate of the transistor 1209. For example, the gate of the transistor 1209 is grounded through a load such as a resistor.

Shown here is an example in which the switch 1203 is a transistor 1213 having one conductivity type (e.g., an n-channel transistor) and the switch 1204 is a transistor 1214 having a conductivity type opposite to the one conductivity type (e.g., a p-channel transistor). A first terminal of the switch 1203 corresponds to one of a source and a drain of the transistor 1213, a second terminal of the switch 1203 corresponds to the other of the source and the drain of the transistor 1213, and conduction or non-conduction between the first terminal and the second terminal of the switch 1203 (i.e., the on/off state of the transistor 1213) is selected by a control signal RD input to a gate of the transistor 1213. A first terminal of the switch 1204 corresponds to one of a source and a drain of the transistor 1214, a second terminal of the switch 1204 corresponds to the other of the source and the drain of the transistor 1214, and conduction or non-conduction between the first terminal and the second terminal of the switch 1204 (i.e., the on/off state of the transistor 1214) is selected by the control signal RD input to a gate of the transistor 1214.

One of a source and a drain of the transistor 1209 is electrically connected to one of a pair of electrodes of the capacitor 1208 and a gate of the transistor 1210. Here, the connection portion is referred to as a node M2. One of a source and a drain of the transistor 1210 is electrically connected to a line which can supply a low power supply potential (e.g., a GND line), and the other thereof is electrically connected to the first terminal of the switch 1203 (the one of the source and the drain of the transistor 1213). The second terminal of the switch 1203 (the other of the source and the drain of the transistor 1213) is electrically connected to the first terminal of the switch 1204 (the one of the source and the drain of the transistor 1214). The second terminal of the switch 1204 (the other of the source and the drain of the transistor 1214) is electrically connected to a line which can supply a power supply potential VDD. The second terminal of the switch 1203 (the other of the source and the drain of the transistor 1213), the first terminal of the switch 1204 (the one of the source and the drain of the transistor 1214), an input terminal of the logic element 1206, and one of a pair of electrodes of the capacitor 1207 are electrically connected to each other. Here, the connection portion is referred to as a node M1. The other of the pair of electrodes of the capacitor 1207 can be supplied with a constant potential. For example, the other of the pair of electrodes of the capacitor 1207 can be supplied with a low power supply potential (e.g., GND) or a high power supply potential (e.g., VDD). The other of the pair of electrodes of the capacitor 1207 is electrically connected to the line which can supply a low power supply potential (e.g., a GND line). The other of the pair of electrodes of the capacitor 1208 can be supplied with a constant potential. For example, the other of the pair of electrodes of the capacitor 1208 can be supplied with a low power supply potential (e.g., GND) or a high power supply potential (e.g., VDD). The other of the pair of electrodes of the capacitor 1208 is electrically connected to the line which can supply a low power supply potential (e.g., a GND line).

The capacitor **1207** and the capacitor **1208** are not necessarily provided as long as the parasitic capacitance of the transistor, the line, or the like is actively utilized.

A control signal WE is input to a first gate (first gate electrode) of the transistor **1209**. As for each of the switch **1203** and the switch **1204**, a conduction state or a non-conduction state between the first terminal and the second terminal is selected by the control signal RD which is different from the control signal WE. When the first terminal and the second terminal of one of the switches are in the conduction state, the first terminal and the second terminal of the other of the switches are in the non-conduction state.

A signal corresponding to data retained in the circuit **1201** is input to the other of the source and the drain of the transistor **1209**. FIG. **53** illustrates an example in which a signal output from the circuit **1201** is input to the other of the source and the drain of the transistor **1209**. The logic value of a signal output from the second terminal of the switch **1203** (the other of the source and the drain of the transistor **1213**) is inverted by the logic element **1206**, and the inverted signal is input to the circuit **1201** through the circuit **1220**.

In the example of FIG. **53**, a signal output from the second terminal of the switch **1203** (the other of the source and the drain of the transistor **1213**) is input to the circuit **1201** through the logic element **1206** and the circuit **1220**; however, one embodiment of the present invention is not limited thereto. The signal output from the second terminal of the switch **1203** (the other of the source and the drain of the transistor **1213**) may be input to the circuit **1201** without its logic value being inverted. For example, in the case where the circuit **1201** includes a node in which a signal obtained by inversion of the logic value of a signal input from the input terminal is retained, the signal output from the second terminal of the switch **1203** (the other of the source and the drain of the transistor **1213**) can be input to the node.

In FIG. **53**, the transistors included in the memory element **1200** except for the transistor **1209** can each be a transistor in which a channel is formed in a film formed using a semiconductor other than an oxide semiconductor or in the substrate **1190**. For example, the transistor can be a transistor whose channel is formed in a silicon film or a silicon substrate. Alternatively, all the transistors in the memory element **1200** may be a transistor in which a channel is formed in an oxide semiconductor. Further alternatively, in the memory element **1200**, a transistor in which a channel is formed in an oxide semiconductor can be included besides the transistor **1209**, and a transistor in which a channel is formed in a layer including a semiconductor other than an oxide semiconductor or the substrate **1190** can be used for the rest of the transistors.

As the circuit **1201** in FIG. **53**, for example, a flip-flop circuit can be used. As the logic element **1206**, for example, an inverter or a clocked inverter can be used.

In a period during which the memory element **1200** is not supplied with the power supply voltage, the semiconductor device of one embodiment of the present invention can retain data stored in the circuit **1201** by the capacitor **1208** which is provided in the circuit **1202**.

The off-state current of a transistor in which a channel is formed in an oxide semiconductor is extremely low. For example, the off-state current of a transistor in which a channel is formed in an oxide semiconductor is significantly lower than that of a transistor in which a channel is formed in silicon having crystallinity. Thus, when the transistor is used as the transistor **1209**, a signal held in the capacitor **1208** is retained for a long time also in a period during which the power supply voltage is not supplied to the memory

element **1200**. The memory element **1200** can accordingly retain the stored content (data) also in a period during which the supply of the power supply voltage is stopped.

Since the above-described memory element performs pre-charge operation with the switch **1203** and the switch **1204**, the time required for the circuit **1201** to retain original data again after the supply of the power supply voltage is restarted can be shortened.

In the circuit **1202**, a signal retained by the capacitor **1208** is input to the gate of the transistor **1210**. Therefore, after supply of the power supply voltage to the memory element **1200** is restarted, the signal retained by the capacitor **1208** can be converted into the one corresponding to the state (the on state or the off state) of the transistor **1210** to be read from the circuit **1202**. Consequently, an original signal can be accurately read even when a potential corresponding to the signal retained by the capacitor **1208** varies to some degree.

By using the above-described memory element **1200** for a memory device such as a register or a cache memory included in a processor, data in the memory device can be prevented from being lost owing to the stop of the supply of the power supply voltage. Further, shortly after the supply of the power supply voltage is restarted, the memory element can be returned to the same state as that before the power supply is stopped. Therefore, the power supply can be stopped even for a short time in the processor or one or a plurality of logic circuits included in the processor. Accordingly, power consumption can be suppressed.

Although the memory element **1200** is used in a CPU in this embodiment, the memory element **1200** can also be used in an LSI such as a digital signal processor (DSP), a custom LSI, or a programmable logic device (PLD), and a radio frequency (RF) tag.

At least part of this embodiment can be implemented in combination with any of the embodiments described in this specification as appropriate.

Embodiment 8

<Imaging Device>

FIG. **54A** is a top view illustrating an example of an imaging device **200** of one embodiment of the present invention. The imaging device **200** includes a pixel portion **210** and peripheral circuits for driving the pixel portion **210** (a peripheral circuit **260**, a peripheral circuit **270**, a peripheral circuit **280**, and a peripheral circuit **290**). The pixel portion **210** includes a plurality of pixels **211** arranged in a matrix with p rows and q columns (p and q are each a natural number greater than or equal to 2). The peripheral circuit **260**, the peripheral circuit **270**, the peripheral circuit **280**, and the peripheral circuit **290** are each connected to a plurality of pixels **211**, and a signal for driving the plurality of pixels **211** is supplied. In this specification and the like, in some cases, "a peripheral circuit" or "a driver circuit" indicates all of the peripheral circuits **260**, **270**, **280**, and **290**. For example, the peripheral circuit **260** can be regarded as part of the peripheral circuit.

The imaging device **200** preferably includes a light source **291**. The light source **291** can emit detection light P1.

The peripheral circuit includes at least one of a logic circuit, a switch, a buffer, an amplifier circuit, and a converter circuit. The peripheral circuit may be formed over a substrate where the pixel portion **210** is formed. Alternatively, a semiconductor device such as an IC chip may be used as part or the whole of the peripheral circuit. Note that as the peripheral circuit, one or more of the peripheral circuits **260**, **270**, **280**, and **290** may be omitted.

As illustrated in FIG. 54B, the pixels 211 may be provided to be inclined in the pixel portion 210 included in the imaging device 200. When the pixels 211 are obliquely arranged, the distance between pixels (pitch) can be shortened in the row direction and the column direction. Accordingly, the quality of an image taken with the imaging device 200 can be improved.

<Configuration Example 1 of Pixel>

The pixel 211 included in the imaging device 200 is formed with a plurality of subpixels 212, and each subpixel 212 is combined with a filter which transmits light with a specific wavelength band (color filter), whereby data for achieving color image display can be obtained.

FIG. 55A is a top view showing an example of the pixel 211 with which a color image is obtained. The pixel 211 illustrated in FIG. 55A includes the subpixel 212 provided with a color filter that transmits light with a red (R) wavelength band (also referred to as a subpixel 212R), a subpixel 212 provided with a color filter that transmits light with a green (G) wavelength band (also referred to as a subpixel 212G), and a subpixel 212 provided with a color filter that transmits light with a blue (B) wavelength band (also referred to as a subpixel 212B). The subpixel 212 can function as a photosensor.

The subpixel 212 (the subpixel 212R, the subpixel 212G, and the subpixel 212B) is electrically connected to a wiring 231, a wiring 247, a wiring 248, a wiring 249, and a wiring 250. In addition, the subpixel 212R, the subpixel 212G, and the subpixel 212B are connected to respective wirings 253 which are independent from one another. In this specification and the like, for example, the wiring 248 and the wiring 249 that are connected to the pixel 211 in the n-th row are referred to as a wiring 248[n] and a wiring 249[n], respectively. For example, the wiring 253 connected to the pixel 211 in the m-th column is referred to as a wiring 253[m]. Note that in FIG. 55A, the wirings 253 connected to the subpixel 212R, the subpixel 212G, and the subpixel 212B in the pixel 211 in the m-th column are referred to as a wiring 253[m]R, a wiring 253[m]G, and a wiring 253[m]B. The subpixels 212 are electrically connected to the peripheral circuit through the above wirings.

The imaging device 200 has a structure in which the subpixel 212 is electrically connected to the subpixel 212 in an adjacent pixel 211 that is provided with a color filter that transmits light with the same wavelength band as the subpixel 212, via a switch. FIG. 55B shows a connection example of the subpixels 212: the subpixel 212 in the pixel 211 arranged in an n-th (n is an integer greater than or equal to 1 and less than or equal to p) row and an m-th (m is an integer greater than or equal to 1 and less than or equal to q) column and the subpixel 212 in the adjacent pixel 211 arranged in an (n+1)-th row and the m-th column. In FIG. 55B, the subpixel 212R arranged in the n-th row and the m-th column and the subpixel 212R arranged in the (n+1)-th row and the m-th column are connected to each other via a switch 201. The subpixel 212G arranged in the n-th row and the m-th column and the subpixel 212G arranged in the (n+1)-th row and the m-th column are connected to each other via a switch 202. The subpixel 212B arranged in the n-th row and the m-th column and the subpixel 212B arranged in the (n+1)-th row and the m-th column are connected to each other via a switch 203.

The color filter used in the subpixel 212 is not limited to red (R), green (G), and blue (B) color filters, and color filters that transmit light of cyan (C), yellow (Y), and magenta (M) may be used. By provision of the subpixels 212 that sense

light with three different wavelength bands in one pixel 211, a full-color image can be obtained.

The pixel 211 including the subpixel 212 provided with a color filter transmitting yellow (Y) light may be provided, in addition to the subpixels 212 provided with the color filters transmitting red (R), green (G), and blue (B) light. The pixel 211 including the subpixel 212 provided with a color filter transmitting blue (B) light may be provided, in addition to the subpixels 212 provided with the color filters transmitting cyan (C), yellow (Y), and magenta (M) light. When the subpixels 212 sensing light with four different wavelength bands are provided in one pixel 211, the reproducibility of colors of an obtained image can be increased.

For example, in FIG. 55A, in regard to the subpixel 212 sensing light in a red wavelength band, the subpixel 212 sensing light in a green wavelength band, and the subpixel 212 sensing light in a blue wavelength band, the pixel number ratio (or the light receiving area ratio) thereof is not necessarily 1:1:1. For example, it is possible to employ the Bayer arrangement, in which the ratio of the number of pixels (the ratio of light-receiving areas) is set to red:green:blue=1:2:1. Alternatively, the pixel number ratio (the ratio of light receiving area) of red and green to blue may be 1:6:1.

Although the number of subpixels 212 provided in the pixel 211 may be one, two or more subpixels are preferably provided. For example, when two or more subpixels 212 sensing light in the same wavelength band are provided, the redundancy is increased, and the reliability of the imaging device 200 can be increased.

When an infrared (IR) filter that transmits infrared light and absorbs or reflects visible light is used as the filter, the imaging device 200 that senses infrared light can be achieved.

Furthermore, when a neutral density (ND) filter (dark filter) is used, output saturation which occurs when a large amount of light enters a photoelectric conversion element (light-receiving element) can be prevented. With a combination of ND filters with different dimming capabilities, the dynamic range of the imaging device can be increased.

Besides the above-described filter, the pixel 211 may be provided with a lens. An arrangement example of the pixel 211, a filter 254, and a lens 255 is described with cross-sectional views in FIGS. 56A and 56B. With the lens 255, the photoelectric conversion element can receive incident light efficiently. Specifically, as illustrated in FIG. 56A, light 256 enters a photoelectric conversion element 220 through the lens 255, the filter 254 (a filter 254R, a filter 254G, and a filter 254B), a pixel circuit 230, and the like which are provided in the pixel 211.

However, part of the light 256 indicated by arrows might be blocked by some wirings 257 as indicated by a region surrounded with dashed-dotted lines. Thus, a preferable structure is such that the lens 255 and the filter 254 are provided on the photoelectric conversion element 220 side as illustrated in FIG. 56B, whereby the photoelectric conversion element 220 can efficiently receive the light 256. When the light 256 enters the photoelectric conversion element 220 from the photoelectric conversion element 220 side, the imaging device 200 with high sensitivity can be provided.

As the photoelectric conversion element 220 illustrated in FIGS. 56A and 56B, a photoelectric conversion element in which a p-n junction or a p-i-n junction is formed may be used.

The photoelectric conversion element 220 may be formed using a substance that has a function of absorbing a radiation and generating electric charges. Examples of the substance

that has a function of absorbing a radiation and generating electric charges include selenium, lead iodide, mercury iodide, gallium arsenide, cadmium telluride, and cadmium zinc alloy.

For example, when selenium is used for the photoelectric conversion element **220**, the photoelectric conversion element **220** can have a light absorption coefficient in a wide wavelength range, such as visible light, ultraviolet light, infrared light, X-rays, and gamma rays.

One pixel **211** included in the imaging device **200** may include the subpixel **212** with a first filter in addition to the subpixel **212** illustrated in FIGS. **56A** and **56B**.
<Configuration Example 2 of Pixel>

An example of a pixel including a transistor using silicon and a transistor using an oxide semiconductor according to one embodiment of the present invention is described below.

FIGS. **57A** and **57B** are each a cross-sectional view of an element included in an imaging device.

The imaging device illustrated in FIG. **57A** includes a transistor **351** including silicon over a silicon substrate **300**, transistors **353** and **354** which include an oxide semiconductor and are stacked over the transistor **351**, and a photodiode **360** provided in a silicon substrate **300** and including an anode **361** and a cathode **362**. The transistors and the photodiode **360** are electrically connected to various plugs **370** and wirings **371**. In addition, an anode **361** of the photodiode **360** is electrically connected to the plug **370** through a low-resistance region **363**.

The imaging device includes a layer **305** including the transistor **351** provided on the silicon substrate **300** and the photodiode **360** provided in the silicon substrate **300**, a layer **320** which is in contact with the layer **305** and includes the wirings **371**, a layer **331** which is in contact with the layer **320** and includes the transistors **353** and **354**, and a layer **340** which is in contact with the layer **331** and includes a wiring **372** and a wiring **373**.

Note that in the example of cross-sectional view in FIG. **57A**, a light-receiving surface of the photodiode **360** is provided on the side opposite to a surface of the silicon substrate **300** where the transistor **351** is formed. With the structure, an optical path can be obtained without the influence by the transistors or wirings, and therefore, a pixel with a high aperture ratio can be formed. Note that the light-receiving surface of the photodiode **360** can be the same as the surface where the transistor **351** is formed.

In the case where a pixel is formed with use of transistors using an oxide semiconductor, the layer **305** may include the transistor using an oxide semiconductor. Alternatively, the layer **305** may be omitted, and the pixel may include only transistors using an oxide semiconductor.

In addition, in the cross-sectional view in FIG. **57A**, the photodiode **360** in the layer **305** and the transistor in the layer **331** can be formed so as to overlap with each other. Thus, the degree of integration of pixels can be increased. In other words, the resolution of the imaging device can be increased.

An imaging device shown in FIG. **57B** includes a photodiode **365** in the layer **340** and over the transistor. In FIG. **57B**, the layer **305** includes the transistor **351** and a transistor **352** using silicon, the layer **320** includes the wiring **371**, the layer **331** includes the transistors **353** and **354** using an oxide semiconductor layer, the layer **340** includes the photodiode **365**. The photodiode **365** includes a semiconductor layer **366**, a semiconductor layer **367**, and a semiconductor layer **368**, and is electrically connected to the wiring **373** and a wiring **374** through the plug **370**.

The element structure shown in FIG. **57B** can increase the aperture ratio.

Alternatively, a PIN diode element formed using an amorphous silicon film, a microcrystalline silicon film, or the like may be used as the photodiode **365**. In the photodiode **365**, an n-type semiconductor layer **368**, an i-type semiconductor layer **367**, and a p-type semiconductor layer **366** are stacked in this order. The i-type semiconductor layer **367** is preferably formed using amorphous silicon. The p-type semiconductor layer **366** and the n-type semiconductor layer **368** can each be formed using amorphous silicon, microcrystalline silicon, or the like which includes a dopant imparting the corresponding conductivity type. A photodiode in which the photodiode **365** is formed using amorphous silicon has high sensitivity in a visible light wavelength region, and therefore can easily sense weak visible light.

Here, an insulator **380** is provided between the layer **305** including the transistor **351** and the photodiode **360** and the layer **331** including the transistors **353** and **354**. However, there is no limitation on the position of the insulator **380**.

Hydrogen in an insulator provided in the vicinity of a channel formation region of the transistor **351** terminates dangling bonds of silicon; accordingly, the reliability of the transistor **351** can be improved. In contrast, hydrogen in the insulator provided in the vicinity of the transistor **353**, the transistor **354**, and the like becomes one of factors generating a carrier in the oxide semiconductor. Thus, the hydrogen may cause a reduction of the reliability of the transistor **354**, the transistor **354**, and the like. Therefore, in the case where the transistor using an oxide semiconductor is provided over the transistor using a silicon-based semiconductor, it is preferable that the insulator **380** having a function of blocking hydrogen be provided between the transistors. When the hydrogen is confined below the insulator **380**, the reliability of the transistor **351** can be improved. In addition, the hydrogen can be prevented from being diffused from a part below the insulator **380** to a part above the insulator **380**; thus, the reliability of the transistor **353**, the transistor **354**, and the like can be increased. It is preferable to form the insulator **381** over the transistors **353** and **354** because oxygen diffusion can be prevented in the oxide semiconductor.

At least part of this embodiment can be implemented in combination with any of the embodiments described in this specification as appropriate.

Embodiment 9

<RF Tag>

In this embodiment, an RF tag that includes the transistor described in the above embodiments or the memory device described in the above embodiment is described with reference to FIG. **58**.

The RF tag of this embodiment includes a memory circuit, stores necessary data in the memory circuit, and transmits and receives data to/from the outside by using contactless means, for example, wireless communication. With these features, the RF tag can be used for an individual authentication system in which an object or the like is recognized by reading the individual information, for example. Note that the RF tag is required to have extremely high reliability in order to be used for this purpose.

A configuration of the RF tag will be described with reference to FIG. **58**. FIG. **58** is a block diagram illustrating a configuration example of an RF tag.

As shown in FIG. 58, an RF tag 800 includes an antenna 804 which receives a radio signal 803 that is transmitted from an antenna 802 connected to a communication device 801 (also referred to as an interrogator, a reader/writer, or the like). The RF tag 800 includes a rectifier circuit 805, a constant voltage circuit 806, a demodulation circuit 807, a modulation circuit 808, a logic circuit 809, a memory circuit 810, and a ROM 811. A transistor having a rectifying function included in the demodulation circuit 807 may be formed using a material which enables a reverse current to be low enough, for example, an oxide semiconductor. This can suppress the phenomenon of a rectifying function becoming weaker due to generation of a reverse current and prevent saturation of the output from the demodulation circuit. In other words, the input to the demodulation circuit and the output from the demodulation circuit can have a relation closer to a linear relation. Note that data transmission methods are roughly classified into the following three methods: an electromagnetic coupling method in which a pair of coils is provided so as to face each other and communicates with each other by mutual induction, an electromagnetic induction method in which communication is performed using an induction field, and a radio wave method in which communication is performed using a radio wave. Any of these methods can be used in the RF tag 800 described in this embodiment.

Next, a structure of each circuit will be described. The antenna 804 exchanges the radio signal 803 with the antenna 802 which is connected to the communication device 801. The rectifier circuit 805 generates an input potential by rectification, for example, half-wave voltage doubler rectification of an input alternating signal generated by reception of a radio signal at the antenna 804 and smoothing of the rectified signal with a capacitor provided in a later stage in the rectifier circuit 805. Note that a limiter circuit may be provided on an input side or an output side of the rectifier circuit 805. The limiter circuit controls electric power so that electric power which is higher than or equal to certain electric power is not input to a circuit in a later stage if the amplitude of the input alternating signal is high and an internal generation voltage is high.

The constant voltage circuit 806 generates a stable power supply voltage from an input potential and supplies it to each circuit. Note that the constant voltage circuit 806 may include a reset signal generation circuit. The reset signal generation circuit is a circuit which generates a reset signal of the logic circuit 809 by utilizing rise of the stable power supply voltage.

The demodulation circuit 807 demodulates the input alternating signal by envelope detection and generates the demodulated signal. Further, the modulation circuit 808 performs modulation in accordance with data to be output from the antenna 804.

The logic circuit 809 analyzes and processes the demodulated signal. The memory circuit 810 holds the input data and includes a row decoder, a column decoder, a memory region, and the like. Further, the ROM 811 stores an identification number (ID) or the like and outputs it in accordance with processing.

Note that the decision whether each circuit described above is provided or not can be made as appropriate as needed.

Here, the memory circuit described in the above embodiment can be used as the memory circuit 810. Since the memory circuit of one embodiment of the present invention can retain data even when not powered, the memory circuit can be favorably used for an RF tag. Furthermore, the

memory circuit of one embodiment of the present invention needs power (voltage) needed for data writing significantly lower than that needed in a conventional nonvolatile memory; thus, it is possible to prevent a difference between the maximum communication range in data reading and that in data writing. Furthermore, it is possible to suppress malfunction or incorrect writing which is caused by power shortage in data writing.

Since the memory circuit of one embodiment of the present invention can be used as a nonvolatile memory, it can also be used as the ROM 811. In this case, it is preferable that a manufacturer separately prepare a command for writing data to the ROM 811 so that a user cannot rewrite data freely. Since the manufacturer gives identification numbers before shipment and then starts shipment of products, instead of putting identification numbers to all the manufactured RF tags, it is possible to put identification numbers to only good products to be shipped. Thus, the identification numbers of the shipped products are in series and customer management corresponding to the shipped products is easily performed.

This embodiment can be combined as appropriate with any of the other embodiments in this specification.

Embodiment 10

<Display Device>

A display device of one embodiment of the present invention is described below with reference to FIGS. 59A and FIGS. 60A and 60B.

Examples of a display element provided in the display device include a liquid crystal element (also referred to as a liquid crystal display element) and a light-emitting element (also referred to as a light-emitting display element). The light-emitting element includes, in its category, an element whose luminance is controlled by a current or voltage, and specifically includes, in its category, an inorganic electroluminescent (EL) element, an organic EL element, and the like. A display device including an EL element (EL display device) and a display device including a liquid crystal element (liquid crystal display device) are described below as examples of the display device.

Note that the display device described below includes in its category a panel in which a display element is sealed and a module in which an IC such as a controller is mounted on the panel.

The display device described below refers to an image display device or a light source (including a lighting device). The display device includes any of the following modules: a module provided with a connector such as an FPC or TCP; a module in which a printed wiring board is provided at the end of TCP; and a module in which an integrated circuit (IC) is mounted directly on a display element by a COG method.

FIGS. 59A to 59C illustrate an example of an EL display device of one embodiment of the present invention. FIG. 59A is a circuit diagram of a pixel in an EL display device. FIG. 59B is a top view showing the whole of the EL display device. FIG. 59C is a cross-sectional view taken along part of dashed-dotted line M-N in FIG. 59B.

FIG. 59A illustrates an example of a circuit diagram of a pixel used in an EL display device.

Note that in this specification and the like, it might be possible for those skilled in the art to constitute one embodiment of the invention even when portions to which all the terminals of an active element (e.g., a transistor or a diode), a passive element (e.g., a capacitor or a resistor), or the like are connected are not specified. In other words, one embodi-

61

ment of the invention can be clear even when connection portions are not specified. Further, in the case where a connection portion is disclosed in this specification and the like, it can be determined that one embodiment of the invention in which a connection portion is not specified is disclosed in this specification and the like, in some cases. Particularly in the case where the number of portions to which a terminal is connected might be more than one, it is not necessary to specify the portions to which the terminal is connected. Therefore, it might be possible to constitute one embodiment of the invention by specifying only portions to which some of terminals of an active element (e.g., a transistor or a diode), a passive element (e.g., a capacitor or a resistor), or the like are connected.

Note that in this specification and the like, it might be possible for those skilled in the art to specify the invention when at least the connection portion of a circuit is specified. Alternatively, it might be possible for those skilled in the art to specify the invention when at least a function of a circuit is specified. In other words, when a function of a circuit is specified, one embodiment of the present invention can be clear. Further, it can be determined that one embodiment of the present invention whose function is specified is disclosed in this specification and the like. Therefore, when a connection portion of a circuit is specified, the circuit is disclosed as one embodiment of the invention even when a function is not specified, and one embodiment of the invention can be constituted. Alternatively, when a function of a circuit is specified, the circuit is disclosed as one embodiment of the invention even when a connection portion is not specified, and one embodiment of the invention can be constituted.

The EL display device illustrated in FIG. 59A includes a switching element 743, a transistor 741, a capacitor 742, and a light-emitting element 719.

Note that FIG. 59A and the like each illustrate an example of a circuit structure; therefore, a transistor can be provided additionally. In contrast, for each node in FIG. 59A and the like, it is possible not to provide an additional transistor, switch, passive element, or the like.

A gate of the transistor 741 is electrically connected to one terminal of the switching element 743 and one electrode of the capacitor 742. A source of the transistor 741 is electrically connected to the other electrode of the capacitor 742 and one electrode of the light-emitting element 719. A power supply potential VDD is supplied to a drain of the transistor 741. The other terminal of the switching element 743 is electrically connected to a signal line 744. A constant potential is supplied to the other electrode of the light-emitting element 719. The constant potential is a ground potential GND or a potential lower than the ground potential GND.

It is preferable to use a transistor as the switching element 743. When the transistor is used as the switching element, the area of a pixel can be reduced, so that the EL display device can have high resolution. As the switching element 743, a transistor formed through the same step as the transistor 741 can be used, so that EL display devices can be manufactured with high productivity. Note that as the transistor 741 and/or the switching element 743, the transistor illustrated in FIGS. 4A to 4C can be used, for example.

FIG. 59B is a top view of the EL display device. The EL display device includes a substrate 700, a substrate 750, a sealant 734, a driver circuit 735, a driver circuit 736, a pixel 737, and an FPC 732. The sealant 734 is provided between the substrate 700 and the substrate 750 so as to surround the pixel 737, the driver circuit 735, and the driver circuit 736.

62

Note that the driver circuit 735 and/or the driver circuit 736 may be provided outside the sealant 734.

FIG. 59C is a cross-sectional view of the EL display device taken along part of dashed-dotted line M-N in FIG. 59B.

FIG. 59C illustrates a structure of the transistor 741 including an insulator 712a over the transistor 700; a conductor 704a; an insulator 706a that is over the insulator 712a and the conductor 704a and partly overlaps with the conductor 704a; a semiconductor 706b over the insulator 706a; conductors 716a1 and 716a2 in contact with a top surface of the semiconductor 706b; an insulator 710 over the conductors 716a1 and 716a2; an insulator 706c over the semiconductor 706b; an insulator 718b over the insulator 706c; and a conductor 714a that is over the insulator 718b and overlaps with the semiconductor 706b. Note that the structure of the transistor 741 is just an example; the transistor 741 may have a structure different from that illustrated in FIG. 59C.

In the transistor 741 illustrated in FIG. 59C, the conductor 704a functions as a gate electrode, the insulator 712a functions as a gate insulator, the conductor 716a1 functions as a source electrode, the conductor 716a2 functions as a drain electrode, the insulator 718b functions as a gate insulator, and the conductor 714a functions as a gate electrode. Note that in some cases, electrical characteristics of the insulator 706a, the semiconductor 706b, and the insulator 706c change if light enters the insulator 706a, the semiconductor 706b, and the insulator 706c. To prevent this, it is preferable that one or more of the conductor 704a, the conductor 716a1, the conductor 716a2, and the conductor 714a have a light-blocking property.

FIG. 59C illustrates a structure of the capacitor 742 including an insulator 706d that is over a conductor 704b and partly overlaps with the conductor 704b; a semiconductor 706e over the insulator 706d; conductors 716a3 and 716a4 in contact with a top surface of the semiconductor 706e; the insulator 710 over the conductors 716a3 and 716a4; an insulator 706f over the semiconductor 706e; the insulator 718b over the insulator 706f; and a conductor 714b that is over the insulator 718b and overlaps with the semiconductor 706e.

In the capacitor 742, the conductor 704b functions as one electrode and the conductor 714b functions as the other electrode.

Thus, the capacitor 742 can be formed using a film of the transistor 741. The conductor 704a and the conductor 704b are preferably conductors of the same kind, in which case the conductor 704a and the conductor 704b can be formed through the same step. Furthermore, the conductor 714a and the conductor 714b are preferably conductors of the same kind, in which case the conductor 714a and the conductor 714b can be formed through the same step.

The capacitor 742 illustrated in FIG. 59C has a large capacitance per area occupied by the capacitor. Therefore, the EL display device illustrated in FIG. 59C has high display quality. Note that the structure of the capacitor 742 is just an example and may be different from that illustrated in FIG. 59C.

An insulator 728 is provided over the transistor 741 and the capacitor 742, and an insulator 720 is provided over the insulator 728. Here, the insulator 728 and the insulator 720 may have an opening reaching the conductor 716a1 that functions as the source electrode of the transistor 741. A conductor 781 is provided over the insulator 720. The conductor 781 may be electrically connected to the transistor 741 through the opening in the insulator 728 and the insulator 720.

A partition wall **784** having an opening reaching the conductor **781** is provided over the conductor **781**. A light-emitting layer **782** in contact with the conductor **781** through the opening provided in the partition wall **784** is provided over the partition wall **784**. A conductor **783** is provided over the light-emitting layer **782**. A region where the conductor **781**, the light-emitting layer **782**, and the conductor **783** overlap with one another functions as the light-emitting element **719**.

So far, examples of the EL display device are described. Next, an example of a liquid crystal display device is described.

FIG. **60A** is a circuit diagram showing a structural example of a pixel of the liquid crystal display device. A pixel illustrated in FIG. **60A** includes a transistor **751**, a capacitor **752**, and an element (liquid crystal element) **753** in which a space between a pair of electrodes is filled with a liquid crystal.

One of a source and a drain of the transistor **751** is electrically connected to a signal line **755**, and a gate of the transistor **751** is electrically connected to a scan line **754**.

One electrode of the capacitor **752** is electrically connected to the other of the source and the drain of the transistor **751**, and the other electrode of the capacitor **752** is electrically connected to a wiring for supplying a common potential.

One electrode of the liquid crystal element **753** is electrically connected to the other of the source and the drain of the transistor **751**, and the other electrode of the liquid crystal element **753** is electrically connected to a wiring to which a common potential is supplied. The common potential supplied to the wiring electrically connected to the other electrode of the capacitor **752** may be different from that supplied to the other electrode of the liquid crystal element **753**.

Note the description of the liquid crystal display device is made on the assumption that the top view of the liquid crystal display device is similar to that of the EL display device. FIG. **60B** is a cross-sectional view of the liquid crystal display device taken along dashed-dotted line M-N in FIG. **59B**. In FIG. **60B**, the FPC **732** is connected to the wiring **733a** via the terminal **731**. Note that the wiring **733a** may be formed using the same kind of conductor as the conductor of the transistor **751** or using the same kind of semiconductor as the semiconductor of the transistor **751**.

For the transistor **751**, the description of the transistor **741** is referred to. For the capacitor **752**, the description of the capacitor **742** is referred to. Note that the structure of the capacitor **752** in FIG. **60B** corresponds to, but is not limited to, the structure of the capacitor **742** in FIG. **59C**.

Note that in the case where an oxide semiconductor is used as the semiconductor of the transistor **751**, the off-state current of the transistor **751** can be extremely small. Therefore, an electric charge held in the capacitor **752** is unlikely to leak, so that the voltage applied to the liquid crystal element **753** can be maintained for a long time. Accordingly, the transistor **751** can be kept off during a period in which moving images with few motions or a still image are/is displayed, whereby power for the operation of the transistor **751** can be saved in that period; accordingly a liquid crystal display device with low power consumption can be provided. Furthermore, the area occupied by the capacitor **752** can be reduced; thus, a liquid crystal display device with a high aperture ratio or a high-resolution liquid crystal display device can be provided.

An insulator **721** is provided over the transistor **751** and the capacitor **752**. The insulator **721** has an opening reaching

the transistor **751**. A conductor **791** is provided over the insulator **721**. The conductor **791** is electrically connected to the transistor **751** through the opening in the insulator **721**.

An insulator **792** functioning as an alignment film is provided over the conductor **791**. A liquid crystal layer **793** is provided over the insulator **792**. An insulator **794** functioning as an alignment film is provided over the liquid crystal layer **793**. A spacer **795** is provided over the insulator **794**. A conductor **796** is provided over the spacer **795** and the insulator **794**. A substrate **797** is provided over the conductor **796**.

Owing to the above-described structure, a display device including a capacitor occupying a small area, a display device with high display quality, or a high-resolution display device can be provided.

For example, in this specification and the like, a display element, a display device, a light-emitting element, or a light-emitting device includes at least one of an electroluminescence (EL) element (e.g., an EL element including organic and inorganic materials, an organic EL element, or an inorganic EL element), an LED (e.g., a white LED, a red LED, a green LED, or a blue LED), a transistor (a transistor that emits light depending on current), an electron emitter, a liquid crystal element, electronic ink, an electrophoretic element, a grating light valve (GLV), a plasma display panel (PDP), a display element using micro electro mechanical systems (MEMS), a digital micromirror device (DMD), a digital micro shutter (DMS), an interferometric modulator display (IMOD) element, a MEMS shutter display element, an optical-interference-type MEMS display element, an electrowetting element, a piezoelectric ceramic display, a display element including a carbon nanotube, and the like. Other than the above, display media whose contrast, luminance, reflectivity, transmittance, or the like is changed by electrical or magnetic effect may be included.

Note that examples of display devices having EL elements include an EL display. Examples of a display device including an electron emitter include a field emission display (FED), an SED-type flat panel display (SED: surface-conduction electron-emitter display), and the like. Examples of display devices including liquid crystal elements include a liquid crystal display (e.g., a transmissive liquid crystal display, a transreflective liquid crystal display, a reflective liquid crystal display, a direct-view liquid crystal display, or a projection liquid crystal display). Examples of a display devices having electronic ink or an electrophoretic element include electronic paper. In the case of a transreflective liquid crystal display or a reflective liquid crystal display, some of or all of pixel electrodes function as reflective electrodes. For example, some or all of pixel electrodes are formed to contain aluminum, silver, or the like. In such a case, a memory circuit such as an SRAM can be provided under the reflective electrodes, leading to lower power consumption.

Note that in the case of using an LED, graphene or graphite may be provided under an electrode or a nitride semiconductor of the LED. Graphene or graphite may be a multilayer film in which a plurality of layers are stacked. As described above, provision of graphene or graphite enables easy formation of a nitride semiconductor thereover, such as an n-type GaN semiconductor including crystals. Furthermore, a p-type GaN semiconductor including crystals or the like can be provided thereover, and thus the LED can be formed. Note that an MN layer may be provided between the n-type GaN semiconductor including crystals and graphene or graphite. The GaN semiconductors included in the LED may be formed by MOCVD. Note that when the graphene

65

is provided, the GaN semiconductors included in the LED can also be formed by a sputtering method.

This embodiment can be combined as appropriate with any of the other embodiments in this specification.

Embodiment 11

In this embodiment, a display module using a semiconductor device of one embodiment of the present invention is described with reference to FIG. 61.

<Display Module>

In a display module 6000 in FIG. 61, a touch panel 6004 connected to an FPC 6003, a display panel 6006 connected to an FPC 6005, a backlight unit 6007, a frame 6009, a printed board 6010, and a battery 6011 are provided between an upper cover 6001 and a lower cover 6002. Note that the backlight unit 6007, the battery 6011, the touch panel 6004, and the like are not provided in some cases.

The semiconductor device of one embodiment of the present invention can be used for, for example, the display panel 6006 and an integrated circuit mounted on a printed circuit board.

The shapes and sizes of the upper cover 6001 and the lower cover 6002 can be changed as appropriate in accordance with the sizes of the touch panel 6004 and the display panel 6006.

The touch panel 6004 can be a resistive touch panel or a capacitive touch panel and may be formed to overlap with the display panel 6006. A counter substrate (sealing substrate) of the display panel 6006 can have a touch panel function. A photosensor may be provided in each pixel of the display panel 6006 so that an optical touch panel function is added. An electrode for a touch sensor may be provided in each pixel of the display panel 6006 so that a capacitive touch panel function is added.

The backlight unit 6007 includes a light source 6008. The light source 6008 may be provided at an end portion of the backlight unit 6007 and a light diffusing plate may be used.

The frame 6009 protects the display panel 6006 and also functions as an electromagnetic shield for blocking electromagnetic waves generated from the printed board 6010. The frame 6009 may function as a radiator plate.

The printed board 6010 has a power supply circuit and a signal processing circuit for outputting a video signal and a clock signal. As a power source for supplying power to the power supply circuit, an external commercial power source or the battery 6011 provided separately may be used. Note that the battery 6011 is not necessary in the case where a commercial power source is used.

The display module 6000 can be additionally provided with a member such as a polarizing plate, a retardation plate, or a prism sheet.

This embodiment can be combined as appropriate with any of the other embodiments and an example in this specification.

Embodiment 12

<Package Using a Lead Frame Interposer>

FIG. 62A is a perspective view illustrating a cross-sectional structure of a package using a lead frame interposer. In the package illustrated in FIG. 62A, a chip 551 corresponding to the semiconductor device of one embodiment of the present invention is connected to a terminal 552 over an interposer 550 by wire bonding. The terminal 552 is placed on a surface of the interposer 550 on which the chip 551 is mounted. The chip 551 may be sealed by a mold resin

66

553, in which case the chip 551 is sealed such that part of each of the terminals 552 is exposed.

FIG. 62B illustrates the structure of a module of an electronic device (mobile phone) in which a package is mounted on a circuit board. In the module of the mobile phone in FIG. 62B, a package 602 and a battery 604 are mounted on a printed wiring board 601. The printed wiring board 601 is mounted on a panel 600 including a display element by an FPC 603.

This embodiment can be combined as appropriate with any of the other embodiments in this specification.

Embodiment 13

In this embodiment, electronic devices and lighting devices of one embodiment of the present invention will be described with reference to drawings.

<Electronic Device>

Electronic devices and lighting devices can be fabricated using the semiconductor device of one embodiment of the present invention. In addition, highly reliable electronic devices and lighting devices can be fabricated using the semiconductor device of one embodiment of the present invention. Furthermore, electronic devices and lighting devices including touch sensors with improved detection sensitivity can be fabricated using the semiconductor device of one embodiment of the present invention.

Examples of electronic devices include a television set (also referred to as a television or a television receiver), a monitor of a computer or the like, a digital camera, a digital video camera, a digital photo frame, a mobile phone (also referred to as a mobile phone device), a portable game machine, a portable information terminal, an audio reproducing device, a large game machine such as a pinball machine, and the like.

In the case of having flexibility, the electronic device or lighting device of one embodiment of the present invention can be incorporated along a curved inside/outside wall surface of a house or a building or a curved interior/exterior surface of a car.

Furthermore, the electronic device of one embodiment of the present invention may include a secondary battery. It is preferable that the secondary battery be capable of being charged by non-contact power transmission.

As examples of the secondary battery, a lithium ion secondary battery such as a lithium polymer battery (lithium ion polymer battery) using a gel electrolyte, a lithium ion battery, a nickel-hydride battery, a nickel-cadmium battery, an organic radical battery, a lead-acid battery, an air secondary battery, a nickel-zinc battery, and a silver-zinc battery can be given.

The electronic device of one embodiment of the present invention may include an antenna. When a signal is received by the antenna, the electronic device can display an image, data, or the like on a display portion. When the electronic device includes a secondary battery, the antenna may be used for contactless power transmission.

FIG. 63A illustrates a portable game machine including a housing 7101, a housing 7102, a display portion 7103, a display portion 7104, a microphone 7105, speakers 7106, an operation key 7107, a stylus 7108, and the like. The semiconductor device of one embodiment of the present invention can be used for an integrated circuit, a CPU, or the like incorporated in the housing 7101. When the light-emitting device according to one embodiment of the present invention is used as the display portion 7103 or 7104, it is possible to provide a user-friendly portable game machine with

67

quality that hardly deteriorates. Although the portable game machine illustrated in FIG. 63A includes two display portions, the display portion 7103 and the display portion 7104, the number of display portions included in the portable game machine is not limited to two.

FIG. 63B illustrates a smart watch, which includes a housing 7302, a display portion 7304, operation buttons 7311 and 7312, a connection terminal 7313, a band 7321, a clasp 7322, and the like. The semiconductor device of one embodiment of the present invention can be used for display portion 7304 or a memory, a CPU, or the like incorporated in the housing 7302.

FIG. 63C illustrates a portable information terminal, which includes a display portion 7502 incorporated in a housing 7501, operation buttons 7503, an external connection port 7504, a speaker 7505, a microphone 7506, a display portion 7502, and the like. The semiconductor device of one embodiment of the present invention can be used for a mobile memory, a CPU, or the like incorporated in the housing 7501. Note that the display portion 7502 is small- or medium-sized but can perform full high vision, 4 k, or 8 k display because it has greatly high definition; therefore, a significantly clear image can be obtained.

FIG. 63D illustrates a video camera, which includes a first housing 7701, a second housing 7702, a display portion 7703, operation keys 7704, a lens 7705, a joint 7706, and the like. The operation keys 7704 and the lens 7705 are provided for the first housing 7701, and the display portion 7703 is provided for the second housing 7702. The first housing 7701 and the second housing 7702 are connected to each other with the joint 7706, and the angle between the first housing 7701 and the second housing 7702 can be changed with the joint 7706. Images displayed on the display portion 7703 may be switched in accordance with the angle at the joint 7706 between the first housing 7701 and the second housing 7702. The imaging device in one embodiment of the present invention can be provided in a focus position of the lens 7705. The semiconductor device of one embodiment of the present invention can be used for an integrated circuit, a CPU, or the like incorporated in the first housing 7701.

FIG. 63E illustrates a digital signage including a display portion 7922 provided on a utility pole 7921. The display device of one embodiment of the present invention can be used for a control circuit of the display portion 7922.

FIG. 64A illustrates a notebook personal computer, which includes a housing 8121, a display portion 8122, a keyboard 8123, a pointing device 8124, and the like. The semiconductor device of one embodiment of the present invention can be used for a CPU, a memory, or the like incorporated in the housing 8121. Note that the display portion 8122 is small- or medium-sized but can perform 8 k display because it has greatly high definition; therefore, a significantly clear image can be obtained.

FIG. 64B is an external view of an automobile 9700. FIG. 64C illustrates a driver's seat of the automobile 9700. The automobile 9700 includes a car body 9701, wheels 9702, a dashboard 9703, lights 9704, and the like. The semiconductor device of one embodiment of the present invention can be used in a display portion and a control integrated circuit of the automobile 9700. For example, the semiconductor device of one embodiment of the present invention can be used in display portions 9710 to 9715 illustrated in FIG. 64C.

The display portion 9710 and the display portion 9711 are display devices or input/output devices provided in an automobile windshield. The display device or input/output device of one embodiment of the present invention can be a

68

see-through display device or input/output device, through which the opposite side can be seen, by using a light-transmitting conductive material for its electrodes. Such a see-through display device or input/output device does not hinder driver's vision during the driving of the automobile 9700. Therefore, the display device or input/output device of one embodiment of the present invention can be provided in the windshield of the automobile 9700. Note that in the case where a transistor or the like for driving the display device or input/output device is provided in the display device or input/output device, a transistor having light-transmitting properties, such as an organic transistor using an organic semiconductor material or a transistor using an oxide semiconductor, is preferably used.

The display portion 9712 is a display device provided on a pillar portion. For example, an image taken by an imaging unit provided in the car body is displayed on the display portion 9712, whereby the view hindered by the pillar portion can be compensated. The display portion 9713 is a display device provided on the dashboard. For example, an image taken by an imaging unit provided in the car body is displayed on the display portion 9713, whereby the view hindered by the dashboard can be compensated. That is, by displaying an image taken by an imaging unit provided on the outside of the automobile, blind areas can be eliminated and safety can be increased. Displaying an image to compensate for the area which a driver cannot see, makes it possible for the driver to confirm safety easily and comfortably.

FIG. 64D illustrates the inside of a car in which a bench seat is used as a driver seat and a front passenger seat. A display portion 9721 is a display device or input/output device provided in a door portion. For example, an image taken by an imaging unit provided in the car body is displayed on the display portion 9721, whereby the view hindered by the door can be compensated. A display portion 9722 is a display device provided in a steering wheel. A display portion 9723 is a display device provided in the middle of a seating face of the bench seat. Note that the display device can be used as a seat heater by providing the display device on the seating face or backrest and by using heat generation of the display device as a heat source.

The display portion 9714, the display portion 9715, and the display portion 9722 can display a variety of kinds of information such as navigation data, a speedometer, a tachometer, a mileage, a fuel meter, a gearshift indicator, and air-condition setting. The content, layout, or the like of the display on the display portions can be changed freely by a user as appropriate. The information listed above can also be displayed on the display portions 9710 to 9713, 9721, and 9723. The display portions 9710 to 9715 and 9721 to 9723 can also be used as lighting devices. The display portions 9710 to 9715 and 9721 to 9723 can also be used as heating devices.

FIG. 65A illustrates an external view of a camera 8000. The camera 8000 includes a housing 8001, a display portion 8002, an operation button 8003, a shutter button 8004, a connection portion 8005, and the like. A lens 8006 can be put on the camera 8000.

The connection portion 8005 includes an electrode to connect with a finder 8100, which is described below, a stroboscope, or the like.

Although the lens 8006 of the camera 8000 here is detachable from the housing 8001 for replacement, the lens 8006 may be included in a housing.

Images can be taken at the touch of the shutter button **8004**. In addition, images can be taken at the touch of the display portion **8002** which serves as a touch panel.

The display device or input/output device of one embodiment of the present invention can be used in the display portion **8002**.

FIG. **65B** shows the camera **8000** with the finder **8100** connected.

The finder **8100** includes a housing **8101**, a display portion **8102**, a button **8103**, and the like.

The housing **8101** includes a connection portion for the camera **8000** and the connection portion **8005**, and the finder **8100** can be connected to the camera **8000**. The connection portion includes an electrode, and an image or the like received from the camera **8000** through the electrode can be displayed on the display portion **8102**.

The button **8103** has a function of a power button, and the display portion **8102** can be turned on and off with the button **8103**.

The semiconductor device of one embodiment of the present invention can be used for an integrated circuit and an image sensor included in the housing **8101**.

Although the camera **8000** and the finder **8100** are separate and detachable electronic devices in FIGS. **65A** and **65B**, the housing **8001** of the camera **8000** may include a finder having the display device or input/output device of one embodiment of the present invention.

FIG. **65C** illustrates an external view of a head-mounted display **8200**.

The head-mounted display **8200** includes a mounting portion **8201**, a lens **8202**, a main body **8203**, a display portion **8204**, a cable **8205**, and the like. The mounting portion **8201** includes a battery **8206**.

Power is supplied from the battery **8206** to the main body **8203** through the cable **8205**. The main body **8203** includes a wireless receiver or the like to receive video data, such as image data, and display it on the display portion **8204**. In addition, the movement of the eyeball and the eyelid of a user can be captured by a camera in the main body **8203** and then coordinates of the points the user looks at can be calculated using the captured data to utilize the eye of the user as an input means.

The mounting portion **8201** may include a plurality of electrodes to be in contact with the user. The main body **8203** may be configured to sense current flowing through the electrodes with the movement of the user's eyeball to recognize the direction of his or her eyes. The main body **8203** may be configured to sense current flowing through the electrodes to monitor the user's pulse. The mounting portion **8201** may include sensors, such as a temperature sensor, a pressure sensor, or an acceleration sensor so that the user's biological information can be displayed on the display portion **8204**. The main body **8203** may be configured to sense the movement of the user's head or the like to move an image displayed on the display portion **8204** in synchronization with the movement of the user's head or the like.

The semiconductor device of one embodiment of the present invention can be used for an integrated circuit included in the main body **8203**.

At least part of this embodiment can be implemented in combination with any of the embodiments described in this specification as appropriate.

Embodiment 14

In this embodiment, application examples of an RF tag using the semiconductor device of one embodiment of the present invention will be described with reference to FIGS. **66A** to **66F**.

<Application Examples of RF Tag>

The RF tag is widely used and can be provided for, for example, products such as bills, coins, securities, bearer bonds, documents (e.g., driver's licenses or resident's cards, see FIG. **66A**), vehicles (e.g., bicycles, see FIG. **66B**), packaging containers (e.g., wrapping paper or bottles, see FIG. **66C**), recording media (e.g., DVD or video tapes, see FIG. **66D**), personal belongings (e.g., bags or glasses, see FIG. **66E**), foods, plants, animals, human bodies, clothing, household goods, medical supplies such as medicine and chemicals, and electronic devices (e.g., liquid crystal display devices, EL display devices, television sets, or cellular phones), or tags on products (see FIGS. **66E** and **66F**).

An RF tag **4000** of one embodiment of the present invention is fixed to a product by being attached to a surface thereof or embedded therein. For example, the RF tag **4000** is fixed to each product by being embedded in paper of a book, or embedded in an organic resin of a package. Since the RF tag **4000** of one embodiment of the present invention can be reduced in size, thickness, and weight, it can be fixed to a product without spoiling the design of the product. Furthermore, bills, coins, securities, bearer bonds, documents, or the like can have an identification function by being provided with the RF tag **4000** of one embodiment of the present invention, and the identification function can be utilized to prevent counterfeiting. Moreover, the efficiency of a system such as an inspection system can be improved by providing the RF tag of one embodiment of the present invention for packaging containers, recording media, personal belongings, foods, clothing, household goods, electronic devices, or the like. Vehicles can also have higher security against theft or the like by being provided with the RF tag of one embodiment of the present invention.

As described above, by using the RF tag including the semiconductor device of one embodiment of the present invention for each application described in this embodiment, power for operation such as writing or reading of data can be reduced, which results in an increase in the maximum communication distance. Moreover, data can be held for an extremely long period even in the state where power is not supplied; thus, the RF tag can be preferably used for application in which data is not frequently written or read.

This embodiment can be combined as appropriate with any of the other embodiments in this specification.

This application is based on Japanese Patent Application serial no. 2015-069654 filed with Japan Patent Office on Mar. 30, 2015, the entire contents of which are hereby incorporated by reference.

What is claimed is:

1. A method for manufacturing a semiconductor device: the semiconductor device comprising:
 - a first insulator;
 - a second insulator over the first insulator;
 - a first conductor embedded in the second insulator;
 - a third insulator over the second insulator and the first conductor;
 - a first metal oxide over the third insulator;
 - a fourth insulator over the first metal oxide;
 - a fifth insulator over the fourth insulator;
 - an oxide semiconductor over the fifth insulator;
 - a second conductor and a third conductor over the oxide semiconductor;
 - a sixth insulator over the fourth insulator, the second conductor, the third conductor, and the oxide semiconductor;
 - a seventh insulator over the sixth insulator;
 - a fourth conductor over the seventh insulator;

71

a second metal oxide over the sixth insulator and the fourth conductor;

an eighth insulator over the second metal oxide;

a first opening reaching the first conductor through the eighth insulator, the second metal oxide, the seventh insulator, the sixth insulator, the fourth insulator, the first metal oxide, and the third insulator;

a second opening reaching the second conductor through the eighth insulator, the second metal oxide, the seventh insulator, and the sixth insulator; and

a third opening reaching the fourth conductor through the eighth insulator and the second metal oxide, the method comprising the steps of:

forming a fifth conductor over the eighth insulator;

forming a ninth insulator over the fifth conductor;

forming a resist mask over the ninth insulator by a lithography method;

etching part of the ninth insulator and part of the fifth conductor to form a hard mask layer including the ninth insulator and the fifth conductor; and

performing first etching and second etching using the hard mask layer as a mask to form the first opening, the second opening, and the third opening,

wherein in the first etching, the eighth insulator is etched for forming the first opening, the second opening, and the third opening, and

wherein in the second etching, the second metal oxide, the seventh insulator, the sixth insulator, the fourth insulator, the first metal oxide, and the third insulator are etched for forming the first opening, the second metal oxide, the seventh insulator, and the sixth insulator are etched for forming the second opening, and the second metal oxide is etched for forming the third opening.

2. The method for manufacturing a semiconductor device according to claim 1, wherein the first conductor, the second conductor, the third conductor, and the fourth conductor comprise a same conductive material.

3. The method for manufacturing a semiconductor device according to claim 1, wherein the first conductor, the second conductor, the third conductor, the fourth conductor, and the fifth conductor comprise a same conductive material.

4. The method for manufacturing a semiconductor device according to claim 1, wherein in the first etching step, an etching rate of the ninth insulator is lower than an etching rate of the eighth insulator.

5. The method for manufacturing a semiconductor device according to claim 1, wherein in the first etching step, an etching rate of the second metal oxide is lower than an etching rate of the eighth insulator.

6. The method for manufacturing a semiconductor device according to claim 1, wherein in the second etching step, an etching rate of the fourth conductor is lower than etching rates of the first metal oxide and the second metal oxide.

7. A method for manufacturing a semiconductor device comprising the steps of:

forming a first insulator;

forming a first conductor embedded in the first insulator;

forming a second insulator over the first insulator and the first conductor;

forming a third insulator over the second insulator;

forming an oxide semiconductor over the third insulator;

forming a second conductor and a third conductor over the oxide semiconductor;

forming a fourth insulator over the third insulator, the second conductor, the third conductor, and the oxide semiconductor;

forming a fifth insulator over the fourth insulator;

72

forming a fourth conductor over the fifth insulator;

forming a metal oxide over the fifth insulator and the fourth conductor;

forming a sixth insulator over the metal oxide;

forming a fifth conductor over the sixth insulator;

forming a seventh insulator over the fifth conductor;

forming a resist mask over the seventh insulator by a lithography method;

etching part of the seventh insulator and part of the fifth conductor to form a hard mask layer including the seventh insulator and the fifth conductor; and

performing first etching and second etching using the hard mask layer as a mask to form a first opening, a second opening, and a third opening,

wherein the first opening reaches the first conductor, wherein the second opening reaches the second conductor,

wherein the third opening reaches the fourth conductor, wherein in the first etching, the sixth insulator is etched for forming the first opening, the second opening, and the third opening,

wherein in the second etching, the metal oxide, the fifth insulator, the fourth insulator, and the second insulator are etched for forming the first opening, the metal oxide, the fifth insulator, and the fourth insulator are etched for forming the second opening, and the metal oxide is etched for forming the third opening, and

wherein the first conductor has a stacked structure of a first conductive layer comprising tungsten and a second conductive layer comprising tantalum nitride over the first conductive layer.

8. The method for manufacturing a semiconductor device according to claim 7, wherein the first conductor, the second conductor, the third conductor, and the fourth conductor comprise a same conductive material.

9. The method for manufacturing a semiconductor device according to claim 7, wherein the first conductor, the second conductor, the third conductor, the fourth conductor, and the fifth conductor comprise a same conductive material.

10. The method for manufacturing a semiconductor device according to claim 7, wherein in the first etching step, an etching rate of the seventh insulator is lower than an etching rate of the sixth insulator.

11. The method for manufacturing a semiconductor device according to claim 7, wherein in the first etching step, an etching rate of the metal oxide is lower than an etching rate of the sixth insulator.

12. The method for manufacturing a semiconductor device according to claim 7, wherein in the second etching step, an etching rate of the fourth conductor is lower than an etching rate of the metal oxide.

13. A method for manufacturing a semiconductor device: the semiconductor device comprising:

a first insulator;

a second insulator over the first insulator;

a first conductor embedded in the second insulator;

a third insulator over the second insulator and the first conductor;

a first metal oxide over the third insulator;

a fourth insulator over the first metal oxide;

an oxide semiconductor over the fourth insulator;

a second conductor and a third conductor over the oxide semiconductor;

a fifth insulator over the oxide semiconductor, the second conductor and the third conductor;

a fourth conductor over the fifth insulator;
 a second metal oxide over the fifth insulator and the fourth conductor;
 a sixth insulator over the second metal oxide;
 a first opening reaching the first conductor through the sixth insulator, the second metal oxide, the fifth insulator, the fourth insulator, the first metal oxide, and the third insulator;
 a second opening reaching the second conductor through the sixth insulator, the second metal oxide, and the fifth insulator; and
 a third opening reaching the fourth conductor through the sixth insulator and the second metal oxide, the method comprising the steps of:
 forming a fifth conductor over the sixth insulator;
 forming a seventh insulator over the fifth conductor;
 forming a resist mask over the seventh insulator by a lithography method;
 etching part of the seventh insulator and part of the fifth conductor to form a hard mask layer including the seventh insulator and the fifth conductor; and
 performing first etching and second etching using the hard mask layer as a mask to form the first opening, the second opening, and the third opening,
 wherein in the first etching, the sixth insulator is etched for forming the first opening, the second opening, and the third opening, and
 wherein in the second etching, the second metal oxide, the fifth insulator, the fourth insulator, the first metal oxide,

and the third insulator are etched for forming the first opening, the second metal oxide, and the fifth insulator are etched for forming the second opening, and the second metal oxide is etched for forming the third opening.
14. The method for manufacturing a semiconductor device according to claim **13**, wherein the first conductor, the second conductor, the third conductor, and the fourth conductor comprise a same conductive material.
15. The method for manufacturing a semiconductor device according to claim **13**, wherein the first conductor, the second conductor, the third conductor, the fourth conductor, and the fifth conductor comprise a same conductive material.
16. The method for manufacturing a semiconductor device according to claim **13**, wherein in the first etching step, an etching rate of the seventh insulator is lower than an etching rate of the sixth insulator.
17. The method for manufacturing a semiconductor device according to claim **13**, wherein in the first etching step, an etching rate of the second metal oxide is lower than an etching rate of the sixth insulator.
18. The method for manufacturing a semiconductor device according to claim **13**, wherein in the second etching step, an etching rate of the fourth conductor is lower than etching rates of the first metal oxide and the second metal oxide.

* * * * *