



(11) (21) (C) **2,151,217**
(22) 1995/06/07
(43) 1995/12/09
(45) 2000/09/26

(72) Nishikawa, Chiharu, JP

(72) Ohba, Jun, JP


(73) Taiko Refractories Co., Ltd., JP

(51) Int.Cl.⁶ C04B 35/10

(30) 1994/06/08 (6-151462) JP

(54) **MATERIAU REFRACTAIRE COULABLE**

(54) **CASTABLE REFRACTORY MATERIAL**



(57) The castable refractory material comprising as binders, per 100 parts by weight of solid components, (a) 10-30 parts by weight of water-inactive, fine refractory powder, which is a mixture of fine refractory powder having an average diameter of 0.2-0.6 μm and fine refractory powder having an average diameter of 1-10 μm at a ratio of 1:2-2:1; (b) 2-7 parts by weight (as an effective amount) of alumina cement having an average diameter of 3-8 μm , cement clinker minerals thereof comprising $\text{CaO}\cdot\text{Al}_2\text{O}_3$ and $\text{CaO}\cdot 2\text{Al}_2\text{O}_3$, with $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$, if any, in such an amount that a diffraction intensity index of the $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$ at a lattice plane distance D of 2.68 \AA is 1 or less assuming that the diffraction intensity index of the $\text{CaO}\cdot\text{Al}_2\text{O}_3$ at a lattice plane distance D of 2.96 \AA is 100; and (c) 0.4-3 parts by weight of fine amorphous silica powder having an average diameter of 0.5 μm or less; the balance of the solid components being substantially refractory aggregate and refractory powder.



ABSTRACT OF THE DISCLOSURE

The castable refractory material comprising as binders, per 100 parts by weight of solid components, (a) 10-30 parts by weight of water-inactive, fine refractory powder, which is a mixture of fine refractory powder having an average diameter of 0.2-0.6 μm and fine refractory powder having an average diameter of 1-10 μm at a ratio of 1:2-2:1; (b) 2-7 parts by weight (as an effective amount) of alumina cement having an average diameter of 3-8 μm , cement clinker minerals thereof comprising $\text{CaO}\cdot\text{Al}_2\text{O}_3$ and $\text{CaO}\cdot 2\text{Al}_2\text{O}_3$, with $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$, if any, in such an amount that a diffraction intensity index of the $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$ at a lattice plane distance D of 2.68 \AA is 1 or less assuming that the diffraction intensity index of the $\text{CaO}\cdot\text{Al}_2\text{O}_3$ at a lattice plane distance D of 2.96 \AA is 100; and (c) 0.4-3 parts by weight of fine amorphous silica powder having an average diameter of 0.5 μm or less; the balance of the solid components being substantially refractory aggregate and refractory powder.

CASTABLE REFRACTORY MATERIAL

BACKGROUND OF THE INVENTION

The present invention relates to a castable refractory material mainly used for linings of vessels such as tundishes and ladles for molten steel, etc.

Refractories are damaged mainly by melting and peeling. With respect to the melting, the castable refractory material can be provided with an improved resistance to the melting by using highly pure starting materials or by using fine powder serving to make the structures of the refractory concretes denser. However, no effective solutions have been found yet to the peeling of linings from ladles for molten steel, etc. due to mechanical spalling. The term "mechanical spalling" used herein means, for instance, cracking or peeling caused by mechanical impact to remove slag, metals or coating materials, etc. attached to the surfaces of the tundishes, etc. after casting. In addition, the linings are subjected to thermal expansion during operations, but they are restrained by outside iron shells. Accordingly, stress is likely to be generated in the refractory linings, causing the peeling of the refractory linings. Particularly since there is a temperature gradient in the refractory linings of the melt vessels from the inner surfaces to the outer surfaces, peeling is likely to take place due to stress concentration in a region which is subjected to a temperature at which the strength of the lining materials is drastically decreased.

It may be contemplated to prevent the peeling of linings by increasing the strength of the lining materials. However, since the castable refractory material is not burned before casting unlike

refractory bricks, ceramic bonding cannot be relied on as a force to prevent the peeling.

Japanese Patent Laid-Open No. 54-113617 discloses a high-strength, unshaped refractory material comprising a refractory material based on alumina-silica, 0.5-12 weight % of an alumina cement containing 70% or more of alumina, and 1.0-8.0 weight % of fine amorphous silica flour having an apparent average diameter of 3 μm or less, based on the total amount thereof. In this refractory material, the silica flour and the alumina cement are used to achieve high strength. However, sufficient strength cannot be achieved at a low temperature unless the silica flour and the alumina cement are added in such large amounts as to damage the corrosion resistance.

Japanese Patent Laid-Open No. 57-172181 discloses a castable refractory material for linings of vessels for molten metals containing 0.5-4.0 weight % of refractory clay and 0.5-2.0 weight % of ultra-fine silica flour having an average diameter of at least 0.1 μm , based on the total amount thereof. In this refractory material, silica flour and alumina cement are used in desired amounts from the viewpoint of corrosion resistance. However, sufficient strength cannot be achieved yet.

Large amounts of alumina cement, etc. are used to achieve high strength in these references. This is due to the fact that sufficient consideration has not been made on the properties of alumina cement and the particle size distribution of binder-constituting materials, particularly fine refractory powder of alumina, etc.

Apart from the above, it is known that various fine refractory powders are added to increase a packing density, thereby improving physical strength. For instance, Japanese Patent

Publication No. 58-33195 discloses a castable refractory material comprising a refractory material containing 5-30 weight % of ultra-fine powder having a particle size of 10 μm or less without binder clay, a dispersant and an agglomeration agent such as gelatin, casein, vegetable rubber, cellulose paste, PVA, etc., the refractory material being one or more selected from the group consisting of oxides, carbides, nitrides, silicides, borides and carbonaceous materials. The oxides include alumina, magnesia, silica, etc. However, this reference fails to teach that refractory powder having different sizes should be added to castable refractory materials to achieve high strength.

To withstand a mechanical impact from outside and a stress caused by thermal expansion, it is preferable that the refractory concretes have a modulus of rupture of 120 kgf/cm^2 or more and a crushing strength of 700 kgf/cm^2 or more at a temperature of 110°C or higher.

OBJECT AND SUMMARY OF THE INVENTION

An object of the present invention is to provide a castable refractory material having excellent corrosion resistance and capable of showing strength to such a level as to withstand mechanical spalling, etc.

Thus, the castable refractory material of the present invention comprises as binders for exhibiting strength, per 100 parts by weight of solid components:

- (a) 10-30 parts by weight of fine refractory powder inactive to water, the fine refractory powder being a mixture of fine refractory powder having an average diameter of 0.2-0.6 μm and fine refractory powder having an average diameter of 1-10 μm at a mixing ratio of 1:2-2:1;

(b) 2-7 parts by weight (as an effective amount) of alumina cement having an average diameter of 3-8 μm , cement clinker minerals of the alumina cement comprising $\text{CaO}\cdot\text{Al}_2\text{O}_3$ and $\text{CaO}\cdot 2\text{Al}_2\text{O}_3$, with $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$, if any, in such an amount that a diffraction intensity index of the $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$ at a lattice plane distance D of 2.68 Å is 1 or less assuming that the diffraction intensity index of the $\text{CaO}\cdot\text{Al}_2\text{O}_3$ at a lattice plane distance D of 2.96 Å is 100; and

(c) 0.4-3 parts by weight of fine amorphous silica powder
10 having an average diameter of 0.5 μm or less; the balance of the solid components being substantially refractory aggregate and refractory powder.

Another aspect of the present invention provides a method of lining a vessel for molten steel, by using the material as defined above.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a graph showing the relation between the mixing ratio of fine alumina powder having different sizes and flowability expressed by viscosity.

20 DETAILED DESCRIPTION OF THE INVENTION

In the castable refractory material of the present invention, the binders for exhibiting high strength comprises fine refractory powder inactive to water (hereinafter referred

2151217

to as "water-inactive, fine refractory powder"), alumina cement and fine amorphous silica powder, and the remaining solid components are substantially refractory aggregate and refractory powder. Detailed descriptions will be made on each component.

[1] Water-inactive fine refractory powder

To increase the strength of the refractory concretes, water-inactive, fine refractory powder are required as materials

mainly constituting the binders to provide as dense a refractory concrete structure as possible. A typical example of such water-inactive, fine refractory powder is alumina, and the fine refractory powder of alumina has a particle size which differs stepwise
5 depending on their production stages. Accordingly, to make the filling or packing structure of the refractory concrete dense, fine refractory powder of different sizes should be combined at appropriate proportions, because fine refractory powder of a single size fails to provide a sufficiently dense structure to the refractory
10 concrete. Here, the term "single size" means that the particle size distribution of the fine refractory powder used has a single sharp peak, and the term "different sizes" means that the particle size distribution of the fine refractory powder used has two or more separate peaks.

15 The first important feature of the present invention is that the fine refractory powder used should be a mixture of fine refractory powder having an average diameter of 0.2-0.6 μm and fine refractory powder having an average diameter of 1-10 μm at a mixing ratio of 1:2-2:1.

20 When the average diameter of the fine refractory powder is more than 10 μm , the fine refractory powder hardly contributes to an increase in the strength of the refractory concretes. On the other hand, when the average diameter of the fine refractory powder is less than 0.2 μm , the agglomeration of the fine refractory powder
25 becomes larger, failing to achieve sufficient dispersion and thus strength. Since the lower limit (1 μm) of the average diameter of the larger refractory powder is sufficiently larger than the upper limit (0.6 μm) of the average diameter of the smaller refractory powder, the smaller refractory powder is well dispersed in gaps

between the larger refractory powder. This is considered to contribute high densities of the refractory concretes produced from the castable refractory material of the present invention.

With respect to the mixing ratio of 1:2-2:1, its criticality is proved by experiments shown in Fig. 1, which shows a viscosity of a mixture of fine alumina powder having an average diameter of 4 μm and fine alumina powder having an average diameter of 0.3 μm , the mixture further containing 0.3 % (outer percentage) of sodium hexametaphosphate as a dispersant and 25% (outer percentage) of water. In Fig. 1, "A" denotes the fine alumina powder having an average diameter of 4 μm , and "B" denotes the fine alumina powder having an average diameter of 0.3 μm . It is evident from Fig. 1 that the viscosity of the mixture of the fine alumina powder of different sizes is minimum in a mixing ratio ranging from 2:1 to 1:2 with 1:1 at center. Also, when a suspension is prepared from the mixture of the fine alumina powder having different average diameters (diameter distributions), the suspension has a small sedimentation volume in this mixing ratio range, thereby providing the resultant refractory concrete with a well packed structure.

When the percentage of the water-inactive, fine refractory powder is less than 10 parts by weight, sufficient strength cannot be achieved in the resultant refractory concretes. On the other hand, when the percentage of the water-inactive, fine refractory powder exceeds 30 parts by weight, the percentage of the fine refractory powder becomes excessive, resulting in an undesirably increased porosity of the refractory concretes.

The water-inactive, fine refractory powder may be alumina, chromia, spinel, titania, etc. or mixtures thereof, which may be selected depending on applications. Alumina is preferable

particularly in the case of the linings of vessels such as tundishes and ladles for steel melt which are required to have high corrosion resistance.

[2] Alumina cement

5 It is required that the alumina cement is uniformly dispersed in the densely packed water-inactive, fine refractory powder. After dispersion, the alumina cement is gradually dissolved and diffused in water to precipitate a hydrate thereof which fills
10 refractory concretes exhibit such a strength that cannot be achieved with physical agglomeration depending on the packing density of the fine refractory powder.

When the alumina cement has an average diameter of less than 3 μm , it is rapidly dissolved in water since it is extremely
15 active to water, thereby not only consuming a dispersant in a short period of time, but also being hard to deflocculate in water due to high agglomeration force. On the other hand, when the average diameter of the alumina cement exceeds 8 μm , the amount of the alumina cement necessary for achieving sufficient strength increases,
20 resulting in the deterioration of corrosion resistance.

The clinker minerals of the alumina cement generally include $\text{CaO}\cdot\text{Al}_2\text{O}_3$, $\text{CaO}\cdot 2\text{Al}_2\text{O}_3$ and $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$. Since
25 $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$ is active to water, thereby preventing the uniform dispersion of the alumina cements. If the alumina cement including $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$ is used, a large amount of alumina cement is necessary to achieve high strength because of forming secondary particles of cement powder. In addition, the secondary particles tend to form voids in the refractory concretes after drying and heating, they decrease the strength of the refractory concretes in a temperature

range lower than a temperature at which ceramic bonding takes place. As a result, the resultant refractory concretes suffer from peeling.

Accordingly, the alumina cement should not contain
5 $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$, or the amount of $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$, if any, should be as small as possible. The determination of the amount of $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$ is carried out by powder X-ray diffractometry, and the diffraction intensity index of a main peak (lattice plane distance $D = 2.68 \text{ \AA}$) of $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$ should be 1 or less, assuming that the diffraction
10 intensity index of a main peak (lattice plane distance $D = 2.96 \text{ \AA}$) of $\text{CaO}\cdot\text{Al}_2\text{O}_3$ is 100. Also, the CaO content in the alumina cement is desirably 25 weight % or less, and more desirably 10-25 weight %.

Commercially available high-grade alumina cement usually contains free $\alpha\text{-Al}_2\text{O}_3$ in addition to cement minerals (cement
15 clinker minerals). Therefore, the CaO content in the high-grade alumina cement varies depending on the mineral composition of the cement clinker and free $\alpha\text{-Al}_2\text{O}_3$ content. Since the total amount of CaO derived from the cement used for the castable refractories has a great influence on the strength and corrosion resistance of the
20 refractory concrete, it should be prescribed in a definite range. The effective amount (W_{eff}) of alumina cement required in the castable refractories is determined herein with respect to the alumina cement containing 25 weight % of CaO. As a result, it has been found that the effective amount of (W_{eff}) of alumina cement should be 2-7 parts by
25 weight in the castable refractory material of the present invention. Assuming that the alumina cement (commercially available alumina cement) containing "X" weight % of CaO is used, the amount (W) of alumina cement can be calculated by the formula: $W = (25 \times W_{\text{eff}}) / X$

When the effective amount of the alumina cement is less than 2 parts by weight, sufficient strength cannot be achieved in the resultant refractory concretes. On the other hand, when the effective amount of the alumina cement is more than 7 parts by weight, the corrosion resistance of the resultant refractory concretes is deteriorated.

The alumina cement may contain up to 5 weight %, preferably less than 2 weight %, as a total amount based on the alumina cement, of impurities such as Fe_2O_3 , SiO_2 , TiO_2 , etc.

10 [3] Fine amorphous silica powder

The fine amorphous silica powder having an average diameter of 0.5 μm or less can react with Ca^{2+} ions dissolved from the alumina cement into water to form a gel hydrate of $\text{CaO-SiO}_2\text{-H}_2\text{O}$, etc., whereby they are effective to achieve high bonding strength.

15 Fine powder exhibiting bonding strength by such a chemical reaction is amorphous silica, while crystalline silica, chromia and alumina fail to exhibit such effects. Further, when the fine amorphous silica powder is substantially spherical, it can show high packing state due to a bearing effect, thereby effectively improving strength. The preferred average diameter of the fine amorphous silica powder is 0.1-0.4 μm .

When the fine amorphous silica powder is less than 0.4 parts by weight, sufficient strength cannot be achieved in the resultant refractory concretes. On the other hand, when the fine amorphous silica powder is more than 3 parts by weight, the corrosion resistance of the resultant refractory concretes is deteriorated, and excessive sintering and thus excessive shrinkage take place at a high temperature of 1300°C or higher, whereby the resultant refractory concretes suffer from poor resistance to thermal

spalling. Also, the excessive shrinkage leads to the expansion of shrinkage cracks in an actual lining, thereby resulting in soaking of molten metal into shrinkage cracks, which leads to a decrease in a service lives of vessel linings. The preferred amount of the fine
5 amorphous silica powder is 0.5-2.5 parts by weight.

[4] Refractory aggregate and refractory powder

The castable refractory material also comprises refractory aggregate and refractory powder. The refractory aggregate and refractory powder may be alumina, magnesia, spinel, chromia,
10 bauxite, etc., or mixtures thereof.

[5] Other components

The castable refractory materials of the present invention may further contain set control additives, dispersants, plasticizers, reinforcing materials (steel fibers, etc.), materials resistant to steam
15 spalling such as aluminum powder, organic fibers, etc.

The present invention will be explained more specifically by Examples and Comparative Examples below without intention of restricting the scope of the present invention defined in the claims attached hereto.

20 **Examples 1-3, Comparative Examples 1-7**

Five types of alumina cement A, B, C, D and E shown in Table 1 were mixed with refractory aggregate, fine alumina powder, amorphous silica powder, sodium hexametaphosphate and water in formulations as shown in Table 2, and each of the resultant mixtures
25 was vibration-cast into a mold and cured. Each of the resultant refractory concretes was measured with respect to modulus of rupture, crushing strength and corrosion resistance. The corrosion resistance was determined from the amount of refractory concretes eroded (simply "erosion depth") at 1700°C for 5 hours by using a slag

for a steel melt ladle in a rotating erosion test. The test results of the refractory concretes are also shown in Table 2.

Table 1

5

<u>Type of Alumina Cement</u>	<u>A</u>	<u>B</u>	<u>C</u>	<u>D</u>	<u>E</u>
Chemical Composition (weight %) ⁽¹⁾					
CaO	24	25	24	24	18
Al ₂ O ₃	74	74	74	74	80
Fe ₂ O ₃	0.2	0.2	0.2	0.2	0.05
SiO ₂	0.3	0.4	0.3	0.3	0.05
TiO ₂	0.05	0.05	0.05	0.05	tr ⁽²⁾
Mineral Composition (weight %) ⁽³⁾					
α-Al ₂ O ₃	25	27	25	25	42
CaO·Al ₂ O ₃	70	70	70	70	54
CaO·2Al ₂ O ₃	5	-(4)	5	5	4
12CaO·7Al ₂ O ₃	-(4)	3	-(4)	-(4)	-(4)
Diffraction Intensity Index					
CaO·2Al ₂ O ₃ ⁽⁵⁾	32	0	32	32	25
12CaO·7Al ₂ O ₃ ⁽⁶⁾	0	2	0	0	0
Average Diameter (μm)	5	5	2	10	5

Note: (1) The chemical composition of alumina cement expressed by weight %, based on the total amount of the alumina cement.

(2) Trace amount.

10

(3) The mineral composition of alumina cement expressed by weight %, based on the total amount of the alumina cement.

(4) Not detected.

(5) Diffraction intensity index of a main peak of CaO·2Al₂O₃, assuming that the diffraction intensity index of a main

peak of $\text{CaO}\cdot\text{Al}_2\text{O}_3$ is 100.

- (6) Diffraction intensity index of a main peak of $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$, assuming that the diffraction intensity index of a main peak of $\text{CaO}\cdot\text{Al}_2\text{O}_3$ is 100.

5

Table 2

<u>No.</u>	<u>Example</u>			<u>Comparative Example</u>						
	<u>1</u>	<u>2</u>	<u>3</u>	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>	<u>5</u>	<u>6</u>	<u>7</u>
<u>Composition (parts by weight)</u>										
Alumina 6-1 mm ⁽¹⁾	40	40	40	40	40	40	40	40	40	40
Alumina 1-0 mm ⁽²⁾	30	30	30	30	30	30	30	30	30	30
Magnesia 1-0 mm ⁽³⁾	5	5	5	5	5	5	5	5	5	5
Fine Alumina Powder										
A ⁽⁴⁾	10	8	5	6	10	6	12	10	6	7
B ⁽⁵⁾	10	10	10	10	10	10	10	10	10	10
Alumina Cement										
A	4	6	-	8	-	-	-	-	-	-
B	-	-	-	-	4	8	-	-	-	-
C	-	-	-	-	-	-	-	4	8	-
D	-	-	-	-	-	-	-	-	-	7
E	-	-	9	-	-	-	2	-	-	-
W _{eff} ⁽⁶⁾	3.84	5.76	6.48	7.68	3.84	7.68	1.44	3.84	7.68	6.72
Amorphous Silica ⁽⁷⁾	1	1	1	1	1	1	1	1	1	1
(NaPO ₃) ₆ ⁽⁸⁾	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Water ⁽⁹⁾	5.0	5.0	5.2	5.3	5.1	5.3	4.9	5.4	5.8	5.5

Table 2 (Continued)

<u>No.</u>	<u>Example</u>			<u>Comparative Example</u>						
	<u>1</u>	<u>2</u>	<u>3</u>	<u>1</u>	<u>2</u>	<u>3</u>	<u>4</u>	<u>5</u>	<u>6</u>	<u>7</u>
<u>Properties of Refractory Concretes</u>										
Modulus of Rapture ⁽¹⁰⁾										
at 110°C	150	155	165	170	60	110	40	60	90	80
at 700°C	155	160	162	160	38	65	30	40	60	85
at 1000°C	170	175	180	185	105	130	70	60	90	135
Crushing Strength ⁽¹⁰⁾										
at 110°C	750	775	800	835	380	465	290	395	480	465
at 700°C	945	950	955	960	395	490	350	355	410	490
at 1000°C	1050	1065	1080	1085	585	680	425	450	505	695
Erosion Depth (mm)	8	9	10	21	14	24	14	14	27	17

Note: (1) Aggregate having a diameter ranging from 6 mm to 1 mm.

5 (2) Aggregate having a diameter ranging from 1 mm to 0 mm.

(3) Aggregate having a diameter ranging from 1 mm to 0 mm.

(4) Average diameter = 4 μm.

(5) Average diameter = 0.3 μm.

(6) Effective amount of alumina cement expressed by the

10 following formula:

$$W_{\text{eff}} = \frac{X}{25} \cdot W,$$

wherein W_{eff} : effective amount of alumina cement,

W: total amount of alumina cement, and

X: CaO content (weight %).

15 (7) Amorphous silica powder having an average diameter of 0.3 μm.

(8) Sodium hexametaphosphate (outer percentage).

(9) Outer percentage.

(10) Unit: kgf/cm².

Comments on each Comparative Example are as follows.

5

- Com. Ex. 1 Large amount of cement, poor corrosion resistance.
 Com. Ex. 2 Containing $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$, poor strength.
 Com. Ex. 3 Large amount of cement.
 Com. Ex. 4 Low value of W_{eff} , poor strength.
 Com. Ex. 5 Fine cement powder, poor strength.
 Com. Ex. 6 Large amount of cement.
 Com. Ex. 7 Coarse cement powder, poor strength.

The refractory concretes of Examples 1 and 2 containing alumina cement A (average diameter: 4 μm) had a high strength and an excellent corrosion resistance. On the other hand, the refractory concrete of Comparative Example 1 to which an excessive amount (W_{eff} : more than 7) of alumina cement was added suffered from the deterioration of corrosion resistance. The refractory concretes of Comparative Examples 2 and 3 containing alumina cement B having a large $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$ content failed to show sufficient strength. The refractory concrete of Example 3 containing 9 parts by weight of alumina cement E (average diameter: 4 μm) also had an excellent corrosion resistance, because of the W_{eff} value between 2 and 7.

The refractory concrete of Comparative Example 4 failed to show sufficient strength, because of the W_{eff} value less than 2. The refractory concretes of Comparative Examples 5 and 6 containing alumina cement C having a small average diameter (2 μm) and the refractory concrete of Comparative Example 7 containing alumina

cement D having a large average diameter (10 μm) also failed to show sufficient strength.

Examples 4-7, Comparative Examples 8-12

5 With the proportions of fine alumina powder having different sizes and the fine amorphous silica powder changed, refractory concretes were prepared in the same manner as in Example 1. The formulations and test results of modulus of rupture, crushing strength and permanent linear change by thermal expansion are shown in Table 3.

10

Table 3

<u>No.</u>	<u>Example</u>				<u>Comparative Example</u>				
	<u>4</u>	<u>5</u>	<u>6</u>	<u>7</u>	<u>8</u>	<u>9</u>	<u>10</u>	<u>11</u>	<u>12</u>
<u>Composition (parts by weight)</u>									
Alumina 6-1 mm ⁽¹⁾	40	40	40	40	40	40	40	40	40
Alumina 1-0 mm ⁽²⁾	44.5	30	30	20.5	39.5	15.5	30	30	30
Magnesia 1-0 mm ⁽³⁾	5	5	5	5	5	5	5	5	5
Fine Alumina Powder									
A ⁽⁴⁾	5	7.5	13.5	15	3	15	0	20	10
B ⁽⁵⁾	5	13	7.5	15	3	20	20	0	10
Alumina Cement A	7	2	2	2	7	2	5	5	2
Amorphous Silica ⁽⁶⁾	2.5	2.5	2.5	2.5	2.5	2.5	1	1	4
(NaPO ₃) ₆ ⁽⁷⁾	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Water ⁽⁸⁾	4.9	4.8	4.8	5.3	5.0	6.0	6.0	6.2	4.6

Table 3 (Continued)

<u>No.</u>	<u>Example</u>				<u>Comparative Example</u>				
	<u>4</u>	<u>5</u>	<u>6</u>	<u>7</u>	<u>8</u>	<u>9</u>	<u>10</u>	<u>11</u>	<u>12</u>
<u>Properties of Refractory Concretes</u>									
Modulus of Rapture ⁽⁹⁾									
at 110°C	125	135	130	145	90	80	60	70	145
at 700°C	120	135	135	150	85	70	55	65	140
at 1000°C	140	155	150	160	120	125	115	135	175
Crushing Strength ⁽⁹⁾									
at 110°C	675	705	690	720	490	455	425	430	730
at 700°C	685	720	710	745	510	485	420	460	730
at 1000°C	720	790	780	805	530	505	495	625	970
Permanent Linear Change (%) ⁽¹⁰⁾	-0.2	-0.2	-0.2	-0.1	-0.2	-0.2	+0.1	+0.3	-0.8

Note: (1)-(5): Same as (1)-(5) in Table 2.

5 (6)-(9): Same as (7)-(10) in Table 2.

(10): Permanent linear change by heating at 1500°C for 3 hrs.

Comments on each Comparative Example are as follows.

Com. Ex. 8 Small amount of fine alumina powder; poor strength.

Com. Ex. 9 Large amount of fine alumina powder; poor strength.

Com. Ex. 10 Fine alumina powder A or B was used; poor strength.

Com. Ex. 11 Fine alumina powder A or B was used; poor strength.

Com. Ex. 12 Large shrinkage, soaking of molten metal.

10

The refractory concretes of Examples 4, 5, 6 and 7 showed high strength. However, the refractory concrete of Comparative

Example 8, to which a small amount (6 parts by weight) of fine alumina powder was added, failed to achieve sufficient strength. Also, the refractory concrete of Comparative Example 9, to which a large amount (35 parts by weight) of fine alumina powder was added, failed to achieve sufficient strength, because of increase in the water amount required for good workability.

When fine alumina powder A and fine alumina powder B were added alone as in Comparative Examples 10 and 11, the amount of water added also increased, failing to achieve high strength. The refractory concrete of Comparative Example 12 containing a large amount of fine amorphous silica powder showed large shrinkage by heating at a high temperature. Thus, the refractory concrete of Comparative Example 12 suffered from cracks due to shrinkage, resulting in soaking of molten metal into the shrinkage cracks.

As described above, the castable refractory material of the present invention shows a high strength at a temperature of 110°C or higher and does not suffer from a decrease in a strength at a high temperature up to 1300°C. Accordingly, it can withstand mechanical impact from outside and stress generated by thermal expansion. Thus, it can show a drastically improved resistance to damage due to peeling.

THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. A castable refractory material comprising as binders for exhibiting high strength, per 100 parts by weight of solid components:
 - (a) 10-30 parts by weight of fine refractory powder inactive to water, the fine refractory powder being a mixture of fine refractory powder having an average diameter of 0.2 - 0.6 μm and fine refractory powder having an average diameter of 1-10 μm at a mixing ratio by weight of 1:2-2:1.
 - (b) 2-7 parts by weight (as an effective amount) of alumina cement having an average diameter of 3-8 μm , cement clinker minerals of the alumina cement comprising $\text{CaO}\cdot\text{Al}_2\text{O}_3$ and $\text{CaO}\cdot 2\text{Al}_2\text{O}_3$ without $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$ or with $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$ in such an amount that a diffraction intensity index of a main peak of the $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$ at a lattice plane distance D of 2.68 Å as measured by powder X-ray diffractometry is 1 or less, assuming that the diffraction intensity index of a main peak of the $\text{CaO}\cdot\text{Al}_2\text{O}_3$ at a lattice plane distance D of 2.96 Å is 100; and
 - (c) 0.4-3 parts by weight of fine amorphous silica powder

having an average diameter of 0.5 μm or less; the balance of the solid components being substantially refractory aggregate and refractory powder.

2. The castable refractory material according to claim 1, wherein the alumina cement (b) contains 25 weight % or less of CaO.

3. The castable refractory material according to claim 1 or 2, wherein the fine amorphous silica powder (c) is substantially spherical.

4. The castable refractory material according to any one of claims 1 - 3, wherein the water-inactive, fine refractory powder (a) is of a material selected from the group consisting of alumina, chromina, spinel, titania and mixtures thereof.

5. The castable refractory material according to any one of claims 1 - 4, wherein the material of the refractory aggregate and refractory powder is selected from the group consisting of alumina, magnesia, spinel, chromia, bauxite and mixtures thereof.

6. The castable refractory material according to any one of the claims 1 - 5, containing no $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$.

7. A castable refractory material to be used as a binder for lining vessels for molten steel, by mixing with water, which material comprises, per 100 parts by weight of solid components:

(a) 10 - 30 parts by weight of fine refractory powder inactive to water, the fine refractory powder being selected from the group consisting of alumina, chromia, spinel, titania and mixtures thereof and being a mixture of the fine refractory powder having an average diameter of $0.2 - 0.6 \mu\text{m}$ and the fine refractory powder having an average diameter of $1 - 10 \mu\text{m}$ at a mixing ratio by weight of 1:2-2:1.

(b) 2-7 parts by weight (as an effective amount) of alumina cement having an average diameter of $3 - 8 \mu\text{m}$ and comprising free $\alpha\text{-Al}_2\text{O}_3$ and cement clinker minerals, wherein the cement clinker minerals contain $\text{CaO}\cdot\text{Al}_2\text{O}_3$ and $\text{CaO}\cdot 2\text{Al}_2\text{O}_3$ and may further contain $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$, provided that when $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$ is contained, the amount of $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$ is such that a diffraction intensity index of a main peak of $12\text{CaO}\cdot 7\text{Al}_2\text{O}_3$ at a lattice

plane distance D of 2.68 Å as measured by powder X-ray diffractometry is 1 or less assuming that the diffraction intensity index of a main peak of CaO·Al₂O₃ at a lattice plane distance D of 2.96 Å is 100; and wherein the effective amount W_{eff} is obtained from the equation;

$$W = (25 \times W_{\text{eff}}) / X$$

[wherein W is an actual amount (parts by weight) of the alumina cement and

X is the content (weight %) of CaO in the alumina cement],

(c) 0.4-3 parts by weight of fine amorphous silica powder having an average diameter of 0.5 μm or less, and

(d) the balance being substantially refractory aggregate or refractory powder.

8. The castable refractory material according to claim 7, wherein the refractory aggregate or refractory powder (d) is each selected from the group consisting of alumina, magnesia, spinel, chromia, bauxite and mixtures thereof.

9. The castable refractory material according to claim 7

or 8, which further comprises at least one other component selected from the group consisting of set control additives, dispersants, plasticizers, reinforcing materials and materials resistant to steam spalling.

10. The castable refractory material according to claim 9, which comprises a hexametaphosphate as the dispersant.


11. A method of lining a vessel for molten steel, which comprises:

mixing uniformly the material as defined in any one of claims 1 through 10 with water, to form a refractory concrete, and applying the resulting concrete as a lining onto a surface of the vessel and allowing the concrete to cure.

SMART & BIGGAR
OTTAWA, CANADA

PATENT AGENTS

FIG. 1



Patent Agents
Smart & Biggar

