



(86) **Date de dépôt PCT/PCT Filing Date:** 2015/01/31
(87) **Date publication PCT/PCT Publication Date:** 2015/08/06
(45) **Date de délivrance/Issue Date:** 2019/04/30
(85) **Entrée phase nationale/National Entry:** 2016/07/26
(86) **N° demande PCT/PCT Application No.:** US 2015/014011
(87) **N° publication PCT/PCT Publication No.:** 2015/117047
(30) **Priorités/Priorities:** 2014/01/31 (US61/934,697);
2015/01/30 (US14/611,167)


(51) **Cl.Int./Int.Cl.** *E21B 10/20* (2006.01),
E21B 10/08 (2006.01), *E21B 10/46* (2006.01)

(72) **Inventeurs/Inventors:**
NGUYEN, DON Q., US;
POTEET, CARL E., US;
SULLIVAN, ERIC C., US;
BRADFORD, JOHN F., US;
BLACKMAN, MARK P., US;
MASSEY, ALAN J., US;
RICKS, GREGORY L., US

(73) **Propriétaire/Owner:**
BAKER HUGHES INCORPORATED, US

(74) **Agent:** MARKS & CLERK

(54) **Titre : TREPAN HYBRIDE DE DUREE DE VIE ACCRUE**
(54) **Title: HYBRID DRILL BIT HAVING INCREASED SERVICE LIFE**



(57) **Abrégé/Abstract:**

A method of improving the service life of a drill bit comprises creating a weldment between load bearing portions of the drill bit where the weldment has a preselected root gap greater than about 25 mils and a preselected root face greater than about 25 mils, and where the weldment has a material property greater than the materials being joined.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau




(43) International Publication Date
6 August 2015 (06.08.2015)

(10) International Publication Number
WO 2015/117047 A1

- (51) International Patent Classification:
E21B 10/00 (2006.01) *E21B 10/46* (2006.01)
- (21) International Application Number:
PCT/US2015/014011
- (22) International Filing Date:
31 January 2015 (31.01.2015)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
61/934,697 31 January 2014 (31.01.2014) US
14/611,167 30 January 2015 (30.01.2015) US
- (71) Applicant: **BAKER HUGHES INCORPORATED**
[US/US]; 2001 Rankin Road, Houston, Texas 77073 (US).
- (72) Inventors: **NGUYEN, Don Q.**; 11503 Springshire Dr., Houston, Texas 77066 (US). **POTEET, Carl E.**; c/o Baker Hughes Incorporated, 2001 Rankin Road, Houston, Texas 77073 (US). **SULLIVAN, Eric C.**; c/o Baker Hughes Incorporated, 2001 Rankin Road, Houston, Texas 77073 (US). **BRADFORD, John F.**; 26 Gate Hill Drive, The Woodlands, Texas 77381 (US). **BLACKMAN, Mark P.**; 28714 Binefield Street, Spring, Texas 77386 (US). **MASSEY, Alan J.**; 8103 Dorcrest, Houston, Texas 77070 (US).
- (74) Agent: **DEAVER, Albert B., Jr.**; Three Riverway, Suite 900, Houston, Texas 77056 (US).
- (81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: HYBRID DRILL BIT HAVING INCREASED SERVICE LIFE



(57) Abstract: A method of improving the service life of a drill bit comprises creating a weldment between load bearing portions of the drill bit where the weldment has a preselected root gap greater than about 25 mils and a preselected root face greater than about 25 mils, and where the weldment has a material property greater than the materials being joined.

WO 2015/117047 A1



Published:

— *with international search report (Art. 21(3))*

— *with information concerning one or more priority claims
considered void (Rule 26bis.2(d))*

Hybrid Drill Bit Having Increased Service Life

[0001] BACKGROUND OF THE INVENTION

Field of the Invention. The present inventions relate generally to earth-boring drill bits having one or more modules or subassemblies attached to the bit body.

[0002] DESCRIPTION OF THE RELATED ART.

[0003] U.S. Patent No. 4,156,123 discloses "Segments of a rock bit are secured together by electron-beam welding. The segments are slightly spaced apart prior to welding by a thin shim of alloying metal such as titanium which improves ductility of the weld and is a strong carbide-former during welding. The shim is positioned between adjacent segments in the region of the crown or dome of the bit. The resulting welded interface is a fine-grain stress-relieved structure with good ductility and resistance to cracking."

[0004] U.S. Patent No. 4,866,245 discloses "A method is shown for manufacturing rotary rock bits. The method reduces the effect of stresses in the area of the radial weld seams by providing a channel in the interior of the bit which intersects the root region of each weld, providing a generous radius for the root region of each radial weld."

[0005] The inventions disclosed and taught herein are directed to improved methods for attaching drill bit modules or subassemblies to bit bodies to improve the service life thereof.

[0006] BRIEF SUMMARY OF THE INVENTION

[0007] As one of many summaries of the inventions disclosed herein, a method of increasing the service life of a modular drill bit is disclosed, comprising selecting a root gap dimension greater than about 25 mils (; selecting a root face dimension greater than about 25 mils; establishing a root gap having the selected root gap dimension between a drill bit module and a drill bit body; and creating a multi-pass weldment between the module and the body having the selected root gap and root face dimensions and from weldment material having at least one material property greater than the same material property of the materials being joined.

[0008] As another of the many possible summaries of the inventions disclosed herein, a modular drill bit having improved service life is disclosed, comprising a multi-pass weldment joining at least one module to a drill bit body; the weldment having a preselected root gap dimension greater than about 25 mils and a preselected root face dimension greater than about 25 mils; and the weldment having at least one mechanical property greater than the same mechanical property of the materials being joined.

[0009] As another of the many possible summaries of the inventions disclosed herein, a method of manufacturing a drill bit is disclosed, comprising: selecting a root gap dimension of between 25 mils and 60 mils; selecting a root face dimension equal to or less than the selected root gap dimension; establishing a root gap having the selected root gap dimension between a drill bit module and a drill bit body; and creating a multi-pass weldment between the drill bit module and the drill bit body having the selected root gap and root face dimensions and from weldment material having at least one material property greater in value than a same material property of materials being joined, wherein the root face dimension is less than a dimension between the drill bit module and the drill bit body.

[0010] As another of the many possible summaries of the inventions disclosed herein, a modular drill bit is disclosed, comprising: a weldment joining at least one module to a drill bit body; the weldment having a preselected root gap dimension of between 25 mils and 60 mils and a preselected root face dimension greater than 25 mils and equal to or less than the selected root gap dimension; and the weldment having at least one material property greater in value than a material property of materials being joined, wherein the root face dimension is less than a dimension between the at least one module and the drill bit body.

[0011] As another of the many possible summaries of the inventions disclosed herein, a hybrid drill bit is disclosed, comprising: a bit body having at least one cutter blade and at least one portion formed in the bit body and configured to receive a roller cutter assembly leg; the roller cutter assembly leg attached to the bit body at the at least one portion with at least one threaded fastener; a multi-pass weldment

joining the roller cutter assembly to the bit body and formed with a weldment interpass temperature of 300°F or less; the weldment having a preselected root gap dimension greater than 25 mils and a preselected root face dimension greater than 25 mils and equal to or less than the selected root gap dimension; and the weldment having a tensile strength greater than a tensile strength of either a material of the bit body or a material of the roller cutter assembly.

[0012] BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

[0013] The following figures form part of the present specification and are included to further demonstrate certain aspects of the present invention. The invention may be better understood by reference to one or more of these figures in combination with the detailed description of specific embodiments presented herein.

[0014] FIG. 1 illustrates a drill bit having fixed PDC cutters and roller cone sub-assemblies.

[0015] FIG. 2 illustrates a roller cone subassembly being located in a corresponding slot.

[0016] FIG. 3 illustrates a cross-sectional view of a roller cone subassembly located in a corresponding slot.

[0017] FIG. 4 illustrates a subassembly-to-body weldment according to the present inventions.

[0018] FIG. 5, 6 and 7 illustrate alternate embodiments of weldment according to the present inventions.

[0019] While the inventions disclosed herein are susceptible to various modifications and alternative forms, only a few specific embodiments have been shown by way of example in the drawings and are described in detail below. The figures and detailed descriptions of these specific embodiments are not intended to limit the breadth or scope of the inventive concepts or the appended claims in any manner. Rather, the figures and detailed written descriptions are provided to illustrate the inventive

concepts to a person of ordinary skill in the art and to enable such person to make and use the inventive concepts.

[0020] DETAILED DESCRIPTION

[0021] The Figures described above and the written description of specific structures and functions below are not presented to limit the scope of what Applicants have invented or the scope of the appended claims. Rather, the Figures and written description are provided to teach any person skilled in the art to make and use the inventions for which patent protection is sought. Those skilled in the art will appreciate that not all features of a commercial embodiment of the inventions are described or shown for the sake of clarity and understanding. Persons of skill in this art will also appreciate that the development of an actual commercial embodiment incorporating aspects of the present inventions will require numerous implementation-specific decisions to achieve the developer's ultimate goal for the commercial embodiment. Such implementation-specific decisions may include, and likely are not limited to, compliance with system-related, business-related, government-related and other constraints, which may vary by specific implementation, location and from time to time. While a developer's efforts might be complex and time-consuming in an absolute sense, such efforts would be, nevertheless, a routine undertaking for those of skill in this art having benefit of this disclosure. It must be understood that the inventions disclosed and taught herein are susceptible to numerous and various modifications and alternative forms. Lastly, the use of a singular term, such as, but not limited to, "a," is not intended as limiting of the number of items. Also, the use of relational terms, such as, but not limited to, "top," "bottom," "left," "right," "upper," "lower," "down," "up," "side," and the like are used in the written description for clarity in specific reference to the Figures and are not intended to limit the scope of the invention or the appended claims.

[0022] We have created an earth boring drill bit and a manufacturing method for a drill bit that improves the service life thereof. This manufacturing method is especially applicable to drill bits comprising one or more roller cone subassemblies mated or joined to a bit body, but is not so limited in its application or utility. For example, and without limitation, this manufacturing method may be successfully employed on hybrid style bits having one or more integral fixed blades with PDC

cutters thereon and one or more roller cone sub-assemblies attached to the bit body. As is known in the art, attaching roller cone sub-assemblies to bit bodies is technically challenging in that service failures often originate or occur at attachment points or are caused or enhanced by the attachment method employed. The present inventions provide an improved method of attaching sub-assemblies to bit bodies and comprise creating a weldment, such as a multi-pass weldment, having a higher strength, such as tensile strength, yield strength, fatigue strength and/or toughness, than the base metal(s) and the weldment having a root gap and root face defined by a predetermined or preselected set-off or gap between the bit body and the sub-assembly. While the use of a higher strength weldment may be generally considered a detriment in that it may create a stress concentration or discontinuity at the interface between the higher strength weldment and the lower strength base metal (e.g., the heat affected zone) that may exacerbate crack initiation or stress corrosion, it is believed that combining the higher strength weldment with the predetermined root gap and/or root face of the present invention establishes a synergistic balance of strength and reduced stress concentration that either alone would not create.

[0023] Referring now to FIG. 1, a hybrid drill bit 100 is illustrated as comprising a shank portion or section 102, which is threaded or otherwise configured at its upper extent for connection into a drillstring (not shown). At the lower extent of shank portion 102, a generally cylindrical receptacle 104 is formed. Receptacle 104 receives a correspondingly shaped and dimensioned cylindrical portion 106 at the upper extent of a bit body portion 108. Shank 102 and body 108 portions are joined together by inserting the cylindrical portion 106 at the upper extent of body portion 108 into the cylindrical receptacle 104 in the lower extent of shank 102. The receptacle 104 may be, for example, a Class 2 female thread that engages with a mating male thread at the upper extent of the body 108. The circular seam or joint may then be continuously bead welded to secure the two portions or sections together. Receptacle 104 and upper extent 106 need not be cylindrical, but could be other shapes that mate together, or could be a sliding or running fit relying on the weld for strength. Alternatively, the joint could be strengthened by a close interference fit between upper extent 108 and receptacle 104. Tack welding around, and/or fully welding, the seam also can be employed. Additionally, other embodiments may have the shank 102 and body 108 integrally formed.

[0024] A bit leg or head 110 (three are shown in FIG. 1) is received in an axially extending slot 112 (again, there is a slot 112 for each leg or head 110). The slot 112 may be dovetailed (and leg 110 correspondingly shaped) so that only axial sliding of leg 110 is permitted and leg 110 resists radial removal from slot 112. Alternately, other forms of centering or alignment structures may be employed between leg 110 and slot 112, such as but not limited to fasteners, such as bolts. Still further, no centering or alignment structure may be needed or employed.

[0025] As shown, a plurality (e.g., four) of fasteners 114 and washers may secure each leg 110 in slot 112 so that leg 110 is secured against axial motion in and removal from slot 112. While FIG. 1 illustrates bolts, it will be understood that any type of fastener, including threaded studs, may be employed. A rolling cutter 116 is secured on a bearing associated with each leg 112 by a ball lock and seal assembly 118. The apertures in leg 110 through which fasteners 114 extend may be oblong and/or oversized, to permit the axial and/or radial positioning of leg 110 within slot 112 during manufacture, which in turn permits selection of the relative projection of the cutting elements on each rolling cutter. A lubricant compensator assembly 120 is also carried by each leg 110 and supplies lubricant to the bearing assembly and compensates for pressure variations in the lubricant during drilling operations. At least one nozzle 122 is received and retained in the bit body portion 108 to direct a stream of drilling fluid from the interior of bit 100 to selected locations proximate the cutters and blades of the bit. The slots 112 preferably have a pair of adjacent opposing sides 124. As will be discussed in further detail below, the sides 124 may be straight, inclined or relieved. A third side 126, which may be curved or flat, connects the two opposing sides 124.

[0026] Conventionally, the leg 110 fits into slot 112 with typical or conventional manufacturing tolerances (e.g., between about 5 and 15 mils), or may be pressed into place using an interference fit. Thereafter, a welded joint is established along the leg-to-slot interface to lock the roller cone subassembly to the body.

[0027] As illustrated in FIG. 2, roller cone assembly 200 is being placed into slot 112 and leg side 224 will be adjacent slot side 124. Also shown are fastener holes 202 in subassembly 200 and corresponding threaded receptacles 204 in slot 112. FIG. 3 illustrates a cross sectional view of a roller cone subassembly 110 located in slot 112. Also shown is fixed blade 300.

[0028] FIG. 4 illustrates a cut away view of leg 110 in slot 112 and having a multi pass weldment 400 according to the present invention. FIG. 4 shows that the leg side 124 is spaced apart from slot side 224 by a distance "x," which is referred to herein as the root gap of weldment 400. FIG. 4 also shows that the weldment root 402 may have a face dimension of "y," which is referred to herein as the root face of weldment 400. Also shown is weldment crown 404 formed between the leg side 124 and a relieved portion in the slot 112 / body 108. It will be appreciated that not all weldments 400 between the leg and slot will exhibit a root gap or a root face. For example, in interference fit systems there likely will be no root gap or root face component of the weldment. For conventional tolerance systems, the root gap and root face, to the extent such exist, likely will be inconsistent in dimension and existence. It is believed that creating a leg-to-slot weldment in interference and conventional tolerance systems causes residual stresses to exist in and adjacent the weld area, which residual stresses impair the service life of the drill bit. In addition, the inconsistency in size and existence of root gap and root face are believed to diminish the service life of a drill bit.

[0029] With reference again to FIG. 4, the present invention comprises using a predetermined or preselected root gap dimension "x" and/or a predetermined or preselected root face dimension "y" that function synergistically with the weldment material and/or with the weld procedure to improve the service life of the drill bit. It is preferred that the root gap "x" generally be wider than conventional manufacturing tolerances create and most preferably greater than about 25 mils (0.025 inch). Preferably, the root gap will be between about 25 and about 90 mils, and most preferably between about 30 and about 60 mils. Similarly, it is preferred that the root face "y" be between about 25 and about 90 mils, and most preferably greater than about 25 mils. It has been found that establishing a root gap and/or a root face for the weldment 400 of about these dimensions diminishes the residual stress field in

and adjacent weldment 400. It is preferred, but not required, that the relationship between the root gap and the root face is "square," meaning that their dimensional values are substantially the same. However, the inventions disclosed herein contemplate that the relationship between root gap and root can be other than square. For out-of-square relationships, it is preferred, but not required, that the root gap dimension be greater than the root face dimension. As an example, for a drill bit manufactured with 0.045 inch welding wire having a tensile strength of 100ksi, the root gap and the root face were set at the wire diameter (i.e., 45 mils), according to the present invention..

[0030] It has further been found that creating a weldment having at least one material property greater than the corresponding material property of the base material(s) in conjunction with a predetermined root gap and/or root face results in a surprising increase in the service life of the drill bit compared to conventionally manufactured bits. For example, and without limitation, if the bit body material has a tensile strength of about 60-70 ksi and the leg material (or roller cone subassembly material) has a tensile strength of about 80-85 ksi, it is presently preferred to establish a weldment from material having a tensile strength of about 100-110 ksi, or anywhere from about 15% to 85% greater strength.

[0031] As an example of one implementation of the present invention, a threebladed hybrid bit body was fabricated from AISI 8620 material having three roller cone assembly slots. The roller cone legs or heads were fabricated from AISI 4715 material. The legs were located in the corresponding slot and threaded fasteners were used to locate the legs at the desired projection and location to establish the desired root gap of 45 mils $\pm$ 5 mils. Once the legs were fastened in position, the assembly was preheated to about 150°F, but not less than about 75°F. Once the assembly was preheated, a U-shaped multi pass weldment was created between the roller cone leg and bit body at the leg-to-slot interface, such as illustrated in FIG. 4. The welding process was a MIG (or GMAW) process using AWS 5.28 grade ER100S filler wire with a diameter of 35 mils. The welding current was set between about 180 and about 230 amps at a voltage of about 24 to about 28 volts. The shielding gas was a mixture of Argon with about 10% to about 15% Carbon Dioxide at a flow rate of about 35 to about 45 cubic feet per hour. The root gap weldment was laid down in

a single pass with an interpass temperature not exceeding about 300°F. Thereafter, multiple passes were laid down to create the final weldment with the weldment interpass temperatures not exceeding about 300°F.

[0032] While the previous discussion is an example of an actual embodiment, it will be appreciated that the inventions may be implemented in many other embodiments. For example, and without limitation, preheating is not required, but may be desired for large assemblies. When used, preheating may range from about ambient to about 150°F and up to about 400°F. The preheat temperature may be limited by elastomeric components in the bit or other temperature limited components. The weldment interpass temperature(s) may range between about 150°F and about 400°F, depending on the material properties (such as heat treatment) of the materials. Also, other forms of welding, such as stick or SMAW welding, may be used.

[0033] FIG. 5 illustrates an alternate implementation of the present invention, in which the leg 110 is relieved both above 504 and below 502 the root gap / root face area. FIG. 6 illustrates another embodiment in which only relief 502 below the root gap is utilized. FIG. 7 illustrates still another embodiment in which a localized area of relief 700 is created immediately below the root gap.

[0034] Having now the benefit of the details of our invention, it will be understood and appreciated drill bit modules or subassemblies, such as, but not limited to roller cone subassemblies, may be attached or fixed to the bit body using the predetermined root gap and/or root face spacing in conjunction with higher strength weldment. It is not necessary to use fasteners or other permanent centering or alignment structures in conjunction with this invention, as the unique weldment alone is sufficient to improve drill bit service life. However, as noted above, one or more fasteners or centering/alignment structures may be beneficial during the manufacturing process to hold the module in position during welding. Alternately, consumable or non-consumable inserts or spacers may be utilized to establish and/or maintain the predetermined root gap or root face spacing.

[0035] While embodiments have been described with multi pass weldments, single pass weldments may be utilized where appropriate based on the materials being welded, the size of the parts, and the welding process being utilized. Indeed, other material joining process may be used with this invention, such as, but not limited to amorphous diffusion bonding.

[0036] Other and further embodiments utilizing one or more aspects of the inventions described above can be devised without departing from the spirit of Applicant's invention. Further, the various methods and embodiments of the methods of manufacture and assembly of the system, as well as location specifications, can be included in combination with each other to produce variations of the disclosed methods and embodiments. Discussion of singular elements can include plural elements and vice-versa.

[0037] The order of steps can occur in a variety of sequences unless otherwise specifically limited. The various steps described herein can be combined with other steps, interlineated with the stated steps, and/or split into multiple steps. Similarly, elements have been described functionally and can be embodied as separate components or can be combined into components having multiple functions.

[0038] The inventions have been described in the context of preferred and other embodiments and not every embodiment of the invention has been described. Obvious modifications and alterations to the described embodiments are available to those of ordinary skill in the art. The disclosed and undisclosed embodiments are not intended to limit or restrict the scope or applicability of the invention conceived of by the Applicants, but rather, in conformity with the patent laws, Applicants intend to fully protect all such modifications and improvements that come within the scope or range of equivalent of the following claims.

What is claimed is:

1. A method of manufacturing a drill bit, comprising:
selecting a root gap dimension of between 25 mils and 60 mils;
selecting a root face dimension equal to or less than the selected root gap dimension;
establishing a root gap having the selected root gap dimension between a drill bit module and a drill bit body; and
creating a multi-pass weldment between the drill bit module and the drill bit body having the selected root gap and root face dimensions and from weldment material having at least one material property greater in value than a same material property of materials being joined,
wherein the root face dimension is less than a dimension between the drill bit module and the drill bit body.
2. The method of claim 1, wherein the root gap dimension is between 30 mils and 50 mils.
3. The method of claim 1 or 2, wherein the root face dimension is between 25 mils and 60 mils and is equal to or less than the root gap dimension.
4. The method of any one of claims 1 to 3, wherein the material property is tensile strength.
5. The method of any one of claims 1 to 3, wherein the material property is fatigue strength.
6. The method of any one of claims 1 to 5, further comprising forming in the drill bit body a cavity configured to receive the drill bit module and establish the selected root gap and root face dimension.
7. The method of claim 6, further comprising locating the drill bit module in the drill bit body prior to creating the weldment, adjusting the drill bit module in

the cavity to establish a desired projection and attaching the drill bit module to the drill bit body with at least one threaded fastener.

8. The method of claim 6 or 7, further comprising placing the drill bit module in the cavity, and positioning the drill bit module in the cavity to establish the root gap.

9. The method of claim 8, wherein positioning the drill bit module in the cavity to establish the root gap comprises moving the drill bit module in at least one of an axial direction and a radial direction.

10. The method of any one of claims 1 to 9, further comprising maintaining a weldment interpass temperature of less than 400°F.

11. The method of claim 10, further comprising maintaining a weldment interpass temperature of 300°F.

12. A modular drill bit, comprising:
a weldment joining at least one module to a drill bit body;
the weldment having a preselected root gap dimension of between 25 mils and 60 mils and a preselected root face dimension greater than 25 mils and equal to or less than the selected root gap dimension; and
the weldment having at least one material property greater in value than a material property of materials being joined,
wherein the root face dimension is less than a dimension between the at least one module and the drill bit body.

13. The bit of claim 12, wherein the root gap dimension is between 30 mils and 50 mils.

14. The bit of claim 12 or 13, wherein the root face dimension is between 25 mils and 60 mils.

15. The bit of any one of claims 12 to 14, wherein the material property is tensile strength.
16. The bit of any one of claims 12 to 14, wherein the material property is fatigue strength.
17. The bit of any one of claims 12 to 16, further comprising a cavity formed in the drill bit body and configured to receive the module and establish the preselected root gap and root face dimensions.
18. The bit of claim 17, wherein the cavity is configured to allow at least one of axial and radial positioning of the at least one module prior to the weldment.
19. The bit of any one of claims 12 to 18, further comprising a weldment interpass temperature of less than 400°F.
20. The bit of claim 19, further comprising a weldment interpass temperature of 300°F.
21. A hybrid drill bit, comprising:
a bit body having at least one cutter blade and at least one portion formed in the bit body and configured to receive a roller cutter assembly leg;
the roller cutter assembly leg attached to the bit body at the at least one portion with at least one threaded fastener;
a multi-pass weldment joining the roller cutter assembly to the bit body and formed with a weldment interpass temperature of 300°F or less;
the weldment having a preselected root gap dimension greater than 25 mils and a preselected root face dimension greater than 25 mils and equal to or less than the selected root gap dimension; and
the weldment having a tensile strength greater than a tensile strength of either a material of the bit body or a material of the roller cutter assembly.




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7

