

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

0 031 997
B1

(12)

EUROPEAN PATENT SPECIFICATION

(46) Date of publication of patent specification: **28.12.83**

(51) Int. Cl.³: **C 08 F 2/08**

(21) Application number: **80304319.9**

(22) Date of filing: **01.12.80**

(54) **Polymerisation process for production of polymer microparticles of high refractive index and coating compositions containing them..**

(30) Priority: **21.12.79 GB 7944210**

(43) Date of publication of application:
15.07.81 Bulletin 81/28

(45) Publication of the grant of the patent:
28.12.83 Bulletin 83/52

(84) Designated Contracting States:
AT BE DE FR GB IT NL SE

(56) References cited:
FR - A - 2 304 622
GB - A - 941 305
GB - A - 1 231 614

(73) Proprietor: **IMPERIAL CHEMICAL INDUSTRIES PLC**
Imperial Chemical House Millbank
London SW1P 3JF (GB)

(72) Inventor: **Backhouse, Alan James**
Monks Wood Monks Close St. Mary's Hill
South Ascot Berkshire (GB)
Inventor: **Hunt, Patrick Arthur**
5, Monk's Rise
Welwyn Garden City Hertfordshire (GB)
Inventor: **Thorne, Stephen James**
49 Luker Avenue
Henley-On-Thames Berkshire (GB)

(74) Representative: **Wood, Dennis John Cecil et al,**
Imperial Chemical Industries PLC Legal
Department: Patents PO Box 6
Welwyn Garden City Herts, AL7 1HD (GB)

EP 0 031 997 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European patent convention).

Production of polymer microparticles and coating compositions containing them

This invention relates to a process for making polymer microparticles, and to coating compositions containing the particles.

The preparation of polymeric microparticles and their incorporation into coating compositions comprising a film-forming polymer have been described, for example in British Patents Nos. 967,051; 1,242,051; 1,451,948 and 1,538,151, in United States Patent No. 4,025,474, in German Offenlegungsschriften 2818093, 2818094, 2818095, 2818100, 2818102 and in European Patent Applications Nos. 78300095 and 78300419. In certain of these publications the particles in question are referred to as "microgel" particles, in which case the polymer of which the particles are composed is crosslinked to a greater or lesser extent and thereby rendered insoluble in any inert liquid diluent in which the film-forming polymer of the coating composition may be carried (although it may be swollen by that diluent). In other instances, the microparticles may be non-crosslinked and retain their identity in the coating composition by reason of the polymer of which they are composed being inherently insoluble in the diluent.

Such microparticles are conveniently made by processes of dispersion polymerisation of monomers in suitable liquids in the presence of polymeric stabilisers for the particles of polymer which are formed. The microparticles are thereby sterically stabilised against flocculation or aggregation, in the manner described in "Dispersion Polymerisation in Organic Media", ed. K. E. J. Barrett (John Wiley, 1975) and in many patent specifications such as British Specifications Nos. 934,038; 941,305; 1,052,241; 1,122,397; 1,143,404 and 1,231,614.

Two types of such dispersion polymerisation process may be distinguished. In the first, which is described in British Patent No. 1,451,948 referred to above, microgel particles are formed as a minor product of a dispersion polymerisation of ethylenically unsaturated monomers in the presence of a so-called "multifunctional" stabiliser. This stabiliser possesses the molecular structural features which are common to all sterically stabilising entities, namely a polymeric component of the molecule which is solvated by the continuous phase of the dispersion and another component which associates with the disperse phase; however, it possesses in addition a plurality of groupings which are capable of copolymerising with the monomers undergoing dispersion polymerisation. The main result of using such a stabiliser, as described more generally in British Patent Specification No. 1,231,614, is that the stabiliser becomes covalently linked to the disperse polymer, but a further consequence is that, whilst the greater part of the polymer formed as the disperse phase is non-crosslinked, a small part of it becomes cross-linked through the intervention of the copolymerisable groups in the stabiliser. By adding to the dispersion thus obtained a sufficient amount of an active solvent for the non-crosslinked disperse polymer, there can be produced a solution-type coating composition in which the non-crosslinked polymer constitutes the main film-forming material but in which the crosslinked microgel remains as insoluble, discrete and sterically stabilised particles. It is, however, difficult by this method to control the relative proportions of microgel and of non-crosslinked polymer which are produced, and also to control the molecular weight of the latter polymer (which may be desirable in order to optimise its film-forming properties) without adversely affecting the yield of microgel. Furthermore it is, of course, inevitable that microgel made in this way will have essentially the same monomer composition as that of the non-crosslinked polymer.

In the second method of making microparticles, which is described in British Patent Specification No. 1,538,151 and in the published German and European specifications referred to earlier, the particles are produced essentially as the sole disperse material; here crosslinking is achieved through the expedient of having present in the monomer charge being polymerised pairs of comonomers carrying mutually chemically reactive groups (in addition to the copolymerisable groups) by reaction of which groups covalent cross-links between the polymer chains may be generated. A variety of combinations of mutually reactive groups has been proposed, for example epoxy and carboxyl, amine and carboxyl, epoxide and carboxylic anhydride, amine and carboxylic anhydride, hydroxyl and carboxylic anhydride, amine and carboxylic acid chloride, alkylene-imine and carboxyl, and organo-alkoxysilane and carboxyl. Since the microparticles made by this procedure are not accompanied by significant amounts of other polymeric products, they can conveniently be incorporated into coating compositions based on film-forming resins of any desired type and in any desired proportion.

One class of coating composition to which polymeric microparticles can with advantage be added is that based upon solutions of thermosetting acrylic resins; these are of particular interest for the painting of car bodies and other metal structures which can tolerate stoving at relatively high temperatures following application of the composition, whereby the composition is converted to a hard, insoluble coating through reaction of the resin with a crosslinking agent such as a melamine-formaldehyde resin. It is common practice to include in the monomers, from which these thermosetting acrylic resins are derived, a proportion of up to 40% by weight of styrene. This is done for two main reasons: firstly, because of the significantly higher refractive index of polystyrene as compared with that of most unmodified polymers of acrylic or methacrylic acid esters (1.59 and 1.46—1.49 respectively), the incorporation of styrene gives rise to a higher reflectance of light at the air-polymer interface and

hence enhances the apparent gloss of the coating; secondly, copolymers containing some styrene show improved flow during the stoving operation in comparison with methyl methacrylate homopolymers. On the other hand, a practical upper limit, of about 50% by weight of total monomers, is set to the proportion of styrene by the strong ultra-violet light absorption properties of the latter and the consequent adverse effect on exterior durability of coatings containing it.

A general consideration affecting the incorporation of polymeric microparticles into coating compositions is that unless the refractive index of the micro-particulate polymer is fairly closely matched to that of the main film-forming resin, there will be scattering of light at the boundary between the two polymer phases and the coating film will appear cloudy. This will, of course, be of little consequence in compositions containing light-scattering pigments such as titanium dioxide, but in coloured compositions of a deep hue containing light-absorbing pigments, particularly coloured metallic compositions containing a low level of aluminium flake, and above all in unpigmented compositions intended for the production of clear coatings, it can be a serious defect. Where a thermosetting copolymer contains a significant proportion of styrene, incorporation of micro-particles consisting essentially of polymethyl methacrylate will have this undesirable result; the problem tends to be accentuated by the fact that the melamine-formaldehyde resins which are most commonly used as crosslinking agents in such systems themselves have relatively high refractive indices (in the region of 1.52).

When microgel particles are produced by the first of the two dispersion polymerisation techniques described above, it follows that the microgel polymer will always have approximately the same monomer composition as the main film-forming polymer which is produced along with it, so that the above-mentioned refractive index problem does not arise. A disadvantage of this first-described technique additional to those already mentioned is, however, that the very polymers which it is desired to use as the main film-former in many clear-coat compositions and compositions of high solids content are not readily prepared by non-aqueous dispersion polymerisation. For a variety of reasons, such polymerisation is most conveniently carried out in low polarity organic liquids, in particular aliphatic hydrocarbons, and, whilst polymers based wholly or overwhelmingly upon methyl methacrylate are practically insoluble in these liquids, copolymers containing other monomers, such as styrene, in significant proportions may be appreciably soluble in them. This may make it difficult to obtain initially a stable dispersion of the copolymer.

The foregoing discussion has considered the problems which arise where the main film-forming polymer is of the addition type, i.e. is one derived from ethylenically unsaturated monomers. However, the same need to match the refractive index of the microgel particles to that of the film-former may arise in the case of the use of certain alkyd or polyester resins in the latter capacity, more specifically those alkyd resins which are derived in part from aromatic starting materials, such as phthalic anhydride, and which in consequence have relatively high refractive indices. Here again, there may be used as crosslinking agents melamine-formaldehyde resins also having high refractive indices.

The evident way out of the difficulty, whatever the nature of the film-forming polymer into which the microgel polymer is incorporated, is to make microgel polymer which contains a substantial proportion of styrene by the second of the two dispersion polymerisation methods referred to. However, as indicated above, the dispersion polymerisation of styrene in an aliphatic hydrocarbon using free radical catalysts presents certain other problems: the polymerisation proceeds slowly and the polymer formed is heavily swollen by the hydrocarbon at the polymerisation temperature normally employed, so that a coarse particle-size dispersion results (see "Dispersion Polymerisation in Organic Media", ed. K. E. J. Barrett: John Wiley, London, 1975: pages 231—214). These problems are encountered equally in the case of monomer mixtures containing a substantial proportion of styrene, for example greater than 20% by weight.

We have now found that dispersion polymerisation of such monomer mixtures can be carried out without these difficulties if the monomer mixture contains, in addition to styrene, a specified derivation of maleic acid or fumaric acid.

According to the present invention we provide a process for the production of addition polymer microparticles, comprising the dispersion polymerisation in an aliphatic hydrocarbon liquid of an ethylenically unsaturated monomer mixture which gives rise to a polymer or copolymer insoluble in the hydrocarbon liquid and which comprises (i) up to 50% by weight of styrene or a substituted derivative thereof and (ii) up to 50% by weight of a derivative of maleic acid or fumaric acid which is soluble in the hydrocarbon liquid at the temperature of polymerisation, the polymerisation being carried out in the presence in the hydrocarbon liquid of a steric dispersion stabiliser the molecule of which comprises at least one polymeric component which is solvated by the hydrocarbon liquid and at least one other component which is not solvated by the liquid and is capable of associating with the polymer produced.


Any derivative of maleic acid or fumaric acid which is soluble in the aliphatic hydrocarbon liquid is suitable for use in the process of the invention. This solubility requirement excludes maleic acid and fumaric acid themselves, and also maleic anhydride, but a variety of compounds derived from these, for example through the medium of the carboxyl groups, are suitable. A preferred type of derivative is one containing in the molecule at least one aromatic group, since the presence of the aromatic nucleus

0 0 3 1 9 9 7

provides an enhancement of the refractive index of the microparticle additional to that afforded by the copolymerised styrene or styrene derivative.

One class of derivative of maleic acid or fumaric acid containing at least one aromatic nucleus which is especially suitable is the class of N-aryl-substituted maleimides of the general formula

5



10


where Ar is an aromatic radical which may contain a single benzene nucleus or two or more connected or fused benzene nuclei and which may optionally carry other substituent groups. Such compounds are in general soluble in aliphatic hydrocarbons. Examples of members of this class include N-phenylmaleimide, N-o-tolylmaleimide, N-m-tolylmaleimide, N-p-tolylmaleimide, N-o-biphenylmaleimide, N-p-biphenylmaleimide, N-p-(tert-butyl)phenylmaleimide, N-p-dodecylphenylmaleimide, N- α -naphthylmaleimide, N- β -naphthylmaleimide, N-o-chlorophenylmaleimide, N-m-chlorophenylmaleimide, N-p-chlorophenylmaleimide, N-p-methoxyphenylmaleimide, N-2-methyl-4-chlorophenylmaleimide, N-2-methoxy-5-chlorophenylmaleimide, N-4-phenoxyphenylmaleimide, N-4-phenylcarboxyphenylmaleimide, N-4-(o-chlorophenoxy)phenylmaleimide, N-2,5-dichlorophenylmaleimide, N-2,5-dimethoxyphenylmaleimide and N-2,4,5-trichlorophenylmaleimide. Any of the foregoing substances may be made by the processes described in British Patent Specifications Nos, 1,040,907 and 1,041,027.

15

20

Another class of derivative of maleic acid or fumaric acid containing at least one aromatic nucleus which is soluble in aliphatic hydrocarbons and is suitable for use according to the invention is the class of diesters of maleic acid or fumaric acid of the structure

25




30

where either X or Y, or both, is an aromatic radical which may contain a single benzene nucleus or two or more connected or fused benzene nuclei and which may optionally carry other substituent groups. Examples of members of this class include diphenylmaleate, methyl phenyl maleate, dibenzylmaleate, di(o-chlorobenzyl)maleate, di(p-chlorobenzyl)maleate, benzyl methyl maleate, dinaphthyl maleate, bis(di-phenyl)maleate, diphenyl fumarate, methyl phenyl fumarate and other fumaric esters corresponding to the foregoing maleic esters.

35

Yet another class of suitable, aliphatic hydrocarbon-soluble derivative of maleic acid or fumaric acid comprises the diesters of those acids of the structure

40



45

where R and R¹, which may be the same or different, are alkyl radicals containing two or more carbon atoms. Examples of compounds of this class include diethyl maleate, diethyl fumarate, dibutyl maleate, dibutyl fumarate, dioctyl maleate, dioctyl fumarate, di-isooctyl maleate, di-isooctyl fumarate, dicyclohexyl maleate and dicyclohexyl fumarate.

50

Of the above-described derivatives of maleic acid and fumaric acid, those most preferred for use in the present process are the N-arylsubstituted maleimides, in particular N-o-chlorophenylmaleimide.

Derivatives of styrene which may be employed according to the invention instead of, or in addition to, styrene itself include α -methylstyrene, o-, m- and p-vinyltoluenes, p-tert-butylstyrene and o-, m- and p-chlorostyrenes.

55

As defined above, the addition polymer microparticles are insoluble in the aliphatic hydrocarbon liquid and consequently precipitate out therefrom as they are formed during the dispersion polymerisation; the particles are maintained in a state of stable dispersion by the steric stabiliser present. In solubility of the microparticles may be achieved in either of two ways. Firstly, the choice of the monomers from which the microparticulate polymer is derived may be such that the polymer is inherently insoluble in the hydrocarbon liquid. In this case, the monomer mixture to be polymerised will usually include one or more ethylenically unsaturated monomers in addition to the monomers specified above. Such monomers may in particular be the acrylic monomers, that is to say the alkyl esters of acrylic acid or methacrylic acid, such as methyl methacrylate, ethyl methacrylate, propyl methacrylate, butyl methacrylate, lauryl methacrylate, ethyl acrylate, butyl acrylate, hexyl acrylate, n-octylacrylate, 2-ethylhexyl acrylate, nonyl acrylate, lauryl acrylate and cetostearyl acrylate. Furthermore, there may be included other "neutral" monomers not of the acrylic type, for example vinyl acetate, vinyl propionate or

60

65

acrylonitrile. Secondly, insolubility of the microparticles may be achieved by introducing a sufficient degree of crosslinking into a polymer which, if it were not crosslinked, would actually be soluble in the aliphatic hydrocarbon. Such crosslinking can be effected, for example, by including in the monomers to be polymerised a monomer which is difunctional or polyfunctional with respect to the polymerisation reaction, such as an acrylic or methacrylic ester of a diol or polyol, e.g. ethylene glycol dimethacrylate or trimethylolpropane trimethacrylate, or a difunctional or polyfunctional vinyl aromatic compound, e.g. divinylbenzene. Alternatively, crosslinking may be achieved by including in the monomers to be polymerised pairs of monomers containing functional groupings which are mutually reactive by a condensation reaction. Examples of such pairs of monomers include epoxy group-containing and carboxyl group-containing monomers, such as glycidyl methacrylate and methacrylic acid or glycidyl acrylate and acrylic acid; or hydroxymethylamino- or alkoxymethylamino-group-containing and carboxyl group-containing monomers. As a further alternative, crosslinking may be brought about by carrying out the polymerisation of the monomers in the presence of a reactive amino resin which is insoluble in the aliphatic hydrocarbon liquid, the monomers in this case including at least one bearing a group capable of reacting with the amino resin, such as a hydroxyl or a carboxyl group.

Where insolubility of the microparticles is achieved through crosslinking, by whichever method, it is preferred that the degree of crosslinking should not be greater than that necessary to render the polymer insoluble. As in the case of non-crosslinked microparticles, the monomer mixture to be polymerised may here include additionally one or more ethylenically unsaturated monomers not bearing functional groups, such as the acrylic monomers and others listed above.

In those cases where the crosslinking of the microparticles is effected by means of a difunctional or polyfunctional comonomer, or by means of a pair of comonomers carrying mutually condensible groups, as mentioned above, it is preferred that the monomer mixture which is polymerised in the process of the invention comprises:—

- (i) from 10% to 40% by weight of styrene or a homologue thereof;
- (ii) from 2% to 30% by weight of the maleic acid or fumaric acid derivative as hereinabove defined;
- (iii) from 0.2% to 10% by weight of crosslinking monomer;
- (iv) from 20% to 87.8% of one or more other ethylenically unsaturated monomers not falling within any of the categories (i), (ii) or (iii), the total monomers being 100%. The expression "crosslinking monomer" above refers to either a single comonomer or the combination of two mutually reactive comonomers, as the case may be.

In the case where crosslinking of the microparticles arises from use of a functional comonomer in conjunction with a reactive amino resin, the preferred monomer mixture comprises:—

- (i) from 10% to 40% by weight of styrene or a homologue thereof;
- (ii) from 2% to 30% by weight of the maleic or fumaric acid derivative as hereinbefore defined;
- (iii) from 1% to 20% by weight of a hydroxyl group-containing monomer;
- (iv) from 1% to 5% by weight of a carboxyl group-containing monomer;
- (v) from 5% to 86% by weight of one or more other ethylenically unsaturated monomers not falling within any of the categories (i) to (iv), the total monomers being 100%,

and the amount of the amino resin is from 0.5% to 20% of the total weight of the monomer mixture.

Aliphatic hydrocarbon liquids which are suitable for use in the process of the invention include hexane, heptane and commercially available petroleum fractions of various boiling point ranges; the latter may contain minor proportions of aromatic hydrocarbons.

The steric stabiliser used in the process, as defined above, is an amphipathic substance such as is conventionally employed in non-aqueous dispersion polymerisation procedures (see "Dispersion Polymerisation in Organic Media" ed. K. E. J. Barrett, John Wiley & Sons, 1975). The type of stabilising agent preferred for use in the invention is a block or graft copolymer containing two types of polymeric component; one type consists, as stated above, of polymer chains which are solvatable by the dispersion liquid and the other type consists of polymer chains of different polarity from the first type which accordingly are not solvatable by that liquid and are capable of becoming anchored to the polymer microparticles.

A particularly useful form of such a stabilising agent is a graft copolymer comprising a polymer backbone, which is the non-solvatable or "anchor" component, and a plurality of solvatable polymer chains pendant from the backbone. Specific examples of such graft copolymers include those in which the backbone is an acrylic polymer chain, derived predominantly from methyl methacrylate, and the pendant chains are residues of poly(12-hydroxy-stearic acid) which are readily solvatable by an aliphatic hydrocarbon medium. These copolymers may be made, for example, by first reacting poly(12-hydroxystearic acid) with glycidyl acrylate or glycidyl methacrylate, whereby the terminal —COOH group in the polymeric acid is converted to an ester derivative containing a polymerisable unsaturated grouping, and then copolymerising that derivative with methyl methacrylate, optionally together with minor proportions of other copolymerisable monomers. By employing acrylic acid or methacrylic acid as

such minor comonomers, it is possible to introduce carboxyl groups into the backbone chain of the graft copolymer with beneficial results inasmuch as the backbone is thereby rendered more polar than it is if composed of methyl methacrylate units alone. This increased polarity causes the backbone to be even less solvatable by a non-polar diluent such as an aliphatic hydrocarbon, and in consequence enhances the force whereby it becomes anchored to the microparticles.

Further details concerning suitable stabilising agents, and concerning dispersion polymerisation in general, are given in the reference quoted above and in the patent literature, for example in British Specifications Nos. 941,305; 1,052,241; 1,122,397 and 1,231,614.

The inclusion in the mixture to be polymerised of the derivative of maleic acid or fumaric acid as defined above has two advantageous consequences. Firstly, it increases the rate of polymerisation as compared with monomer mixtures containing styrene but not containing one of the derivatives in question; the quality of the polymer dispersion obtained is thereby improved. Secondly, as already mentioned, where the derivatives themselves contain one or more aromatic nuclei in the molecule, these lead to further enhancement of the refractive index of the disperse polymer beyond that due to the styrene incorporated; consequently the amount of styrene required, in order to achieve a given level of refractive index, can be reduced.

Polymer microparticles made by the process described above may be incorporated into any coating composition based on a film-forming polymer or resin.

Thus according to a further aspect of the present invention there is provided a coating composition comprising a liquid diluent and film-forming constituents which comprise:—

- (i) a film-forming polymer,
- (ii) polymer microparticles made by the process hereinbefore defined.

Any of the film-forming resins conventionally used in the coating compositions may be employed. The resin may be of either the crosslinking or the non-crosslinking type, that is to say the coating composition may be either thermosetting or thermoplastic in nature.

One class of coating composition of interest is that of the thermosetting acrylic resins, including those which are known to be useful in compositions intended for automotive applications. Such resins are typically derived from one or more acrylic esters such as methyl methacrylate, ethyl methacrylate, propyl methacrylate, butyl methacrylate, ethyl acrylate, butyl acrylate and 2-ethylhexyl acrylate, together with suitable other monomers carrying functional groups whereby the resin can subsequently be crosslinked through reaction with an amino resin, such as acrylic acid, methacrylic acid, hydroxyethyl acrylate, hydroxyethyl methacrylate, 2-hydroxypropyl acrylate, 2-hydroxypropyl methacrylate, N-(alkoxymethyl)acrylamides and N-(alkoxymethyl)methacrylamides (where the alkoxy groups may be, for example, a butoxy group), glycidyl acrylate and glycidyl methacrylate. Such functional monomers typically constitute from 5% to 30% by weight of the total acrylic resin. The acrylic resin may also include minor proportions of other, copolymerised monomers such as vinyl acetate, vinyl propionate and acrylonitrile. In particular, as is common practice where resins for automotive use are concerned, they may include also from 5% to 40% by weight, based on the total resin, of styrene; the present invention is especially valuable in these circumstances, on account of the enhancement of the refractive index of the resin which the presence of the styrene brings about. These thermosetting acrylic resins may be crosslinked in conventional fashion, after application of the composition to a substrate, by the action of heat in conjunction with an amino resin crosslinking agent also present in the composition. The crosslinking agent may be any of the known materials of this type, that is to say a condensate of formaldehyde with a nitrogenous compound such as melamine, urea or benzoguanamine, or such a condensate in which a substantial proportion of the methylol groups present have been etherified by reaction with a lower alcohol, in particular butanol. The amount of the crosslinking agent is typically from 20% to 50% of the weight of the thermosetting acrylic resin taken.

Instead of being a thermosetting acrylic resin, the film-forming material in the coating composition may be a thermoplastic acrylic resin derived from any of the monomers referred to above but excluding those carrying functional groups.

As a further alternative, the film-forming material may be an alkyd resin derived in the usual way by the condensation of one or more polyhydric alcohols and one or more polycarboxylic acids and incorporating the residues of a drying oil or semi-drying oil fatty acid, whereby the resin cures by means of an autoxidation polymerisation mechanism. Yet again, it may be a polyester derived from similar polyfunctional starting materials but not incorporating any autoxidisable residues, in which case curing of the resin is effected by reaction of residual hydroxyl and/or carboxyl groups therein with an amino resin crosslinking agent.

In certain cases, the continued stability of the polymer microparticles after their incorporation into a coating composition may be enhanced if the microparticles as described above are further associated, before their introduction into the composition, with a further, essentially non-crosslinked, polymer which is soluble in the continuous phase liquid, or diluent, of the composition and which is also compatible with the film-forming polymer present therein. This non-crosslinked polymer, which may be referred to as "auxiliary" polymer, is most conveniently brought into association with the microparticles

by following up the dispersion polymerisation process, after conversion of monomer and crosslinking, if any, are complete, directly with the polymerisation of further monomer, from which the auxiliary polymer is to be derived, in the original aliphatic hydrocarbon medium and in the presence of the original dispersion stabiliser (although further stabiliser may be added, if desired). Monomers from which the auxiliary polymer may be derived include the acrylic monomers and other "neutral" monomers referred to above in connection with the microparticles proper, but crosslinking monomers are, of course, omitted. It will be apparent to those skilled in the art which monomers to use in order to produce a non-crosslinked polymer having the required solubility characteristics.

The proportion of the polymer microparticles which is incorporated into the coating composition can vary widely, depending upon the nature of the microparticles and of the main film-forming material respectively, and upon the effect which it is desired to achieve. Thus, different proportions may be required in a particular case according to whether the microparticles are introduced in order to modify the rheological properties of the coating composition and hence influence its flow characteristics when applied to a substrate, or whether they are incorporated in order to modify the mechanical properties of the coating film after application.

The coating composition may, when appropriate, incorporate a suitable catalyst for the crosslinking reaction between the film-forming material and a cross-linking agent, for example an acid-reacting compound such as acid butyl maleate, acid butyl phosphate or p-toluene sulphonic acid. Alternatively the catalytic action may be supplied by the incorporation of free acid groups in the film-forming material, for example by the use of acrylic acid or methacrylic acid as a comonomer in the preparation of a crosslinkable acrylic polymer.

The coating composition may contain one or more pigments. As already mentioned, the invention is of particular interest in connection with compositions which contain pigments of a light-absorbing character (as contrasted with those which scatter light), including such compositions which additionally contain aluminium flakes and are intended for the production of "glamour metallic" type finishes on car bodies. The invention is, however, of greatest benefit with respect to non-pigmented, "clear" compositions which are normally applied over lightly pigmented metallic-type basecoats. In this case, the possibility according to the invention of matching the refractive index of the polymer microparticles exactly to that of the film-forming resin, and thus preserving the high clarity of the unmodified resin, is a very significant advantage.

The selection of the precise monomer formulation to be used in making polymer microparticles according to the invention, in order to match the refractive index of a particular film-forming resin, is a matter of simple experimentation which can be carried out without difficulty by a person skilled in the coating polymer art.

The invention is illustrated but not limited by the following Examples in which parts, ratios and percentages are by weight.

Examples 1—5 and Comparative Examples A—C

To a vessel fitted with stirrer, thermometer, reflux condenser and provision for adding a liquid feed to the returning condensate there was charged:

Aliphatic hydrocarbon (boiling range 170—210°C; aromatic content 5%)	10.355 parts
Hexane	2.536 parts
Heptane	13.561 parts

The vessel and charge were purged with inert gas and then raised to reflux temperature (100°C). The following premixed ingredients were added over a short period of time:

Methyl methacrylate	0.833 part
Methacrylic acid	0.017 part
Azodiisobutyronitrile	0.066 part
Graft copolymer stabiliser (33% solution, as described below)	0.310 part

The contents of the vessel were then held under reflux for 30 minutes to form a 'seed' dispersion, after which the following premixed ingredients were fed into the hydrocarbon returning from the condenser at a uniform rate over a period of 3 hours:—

Monomer mixture, as given in detail below	16.145 parts
Azodiisobutyronitrile	0.212 part
Graft copolymer stabiliser (33% solution, as described below)	3.330 parts
Dimethylaminoethanol	0.031 part

After completion of the monomer feed, the reaction mixture was maintained under reflux for 3 hours.

The monomer mixtures used in the feed stage in these Examples and Comparative Examples had the compositions indicated in the accompanying Table I; the first figure in each case is the amount in

0031 997

parts by weight and the second figure (in parentheses) indicates the weight percentage of the monomer in question in the total feed stage monomer mixture.

In each case, a fine, stable dispersion of crosslinked polymer microparticles was obtained. The dispersions had solids contents in the range 38—40%, (determined by evaporation at 150°C for 1
5 hour) and insoluble gel contents in the range 21—31%. The volume average particle size of the microparticles was measured in each case by their Brownian motion and autocorrelation of laser light: the sizes found are also recorded in Table I. Prior to being cooled from the reaction temperature, each dispersion was diluted finally with 12.549 parts of xylene.

The graft copolymer stabiliser solution used in the above procedure was obtained as follows. 12-
10 Hydroxystearic acid was self-condensed to an acid value of about 31—34 mg KOH/g (corresponding to a molecular weight of 1650—1800) and then reacted with an equivalent amount of glycidyl methacrylate. The resulting unsaturated ester was copolymerised at a weight ratio of 2:1 with a mixture of methyl methacrylate and acrylic acid in the proportions of 95:5. The copolymer was used as a 33% solution in a mixture of aliphatic hydrocarbon, toluene and ethyl acetate in the ratio of 74:14:12.
15

20

25

30

35

40

45

50

55

60

65

TABLE I

Example no.	1	2	3	4	5	A	B	C
Methyl methacrylate	8.606 (53.3)	8.606 (53.3)	8.606 (53.3)	8.606 (53.3)	8.606 (53.3)	15.823 (98.0)	10.979 (68.0)	7.750 (48.0)
Styrene	4.844 (30.0)	7.844 (30.0)	4.844 (30.0)	4.844 (30.0)	4.844 (30.0)	—	5.099 (30.0)	8.498 (50.0)
Glycidyl methacrylate	0.161 (1.00)	0.161 (1.00)	0.161 (1.00)	0.161 (1.00)	0.161 (1.00)	0.161 (1.00)	0.161 (1.00)	0.161 (1.00)
Methacrylic acid	0.161 (1.00)	0.161 (1.00)	1.616 (1.00)	0.161 (1.00)	0.161 (1.00)	0.161 (1.00)	0.161 (1.00)	0.161 (1.00)
Diethyl-fumarate	2.373 (14.7)	—	—	—	—	—	—	—
Dibutyl-maleate	—	2.373 (14.7)	—	—	—	—	—	—
Diiso-octyl maleate	—	—	2.373 (14.7)	—	—	—	—	—
Dibenzyl maleate	—	—	—	2.373 (14.7)	—	—	—	—
N-o-Chlorophenyl maleimide	—	—	—	—	2.373 (14.7)	—	—	—
Volume average particle size, nm	250	260	270	290	260	270	570	470

The results of particle size determination given in Table I illustrate the fact that the use of styrene as a comonomer, in the absence of a maleic acid or fumaric acid derivative as required according to the present invention, leads to the production of relatively coarse particles in dispersion, which in turn cause the dispersion to sediment out rapidly on storage. The process of the invention, on the other hand, yields dispersions of similar particle size to those obtained with acrylic monomers only (i.e. omitting styrene).

Example 6 and Comparative Examples D—G

Thermosetting acrylic coating compositions were prepared by blending a melamine-formaldehyde resin with an acrylic solution polymer having the composition: styrene 42.5%, butyl methacrylate 21.25%, butyl acrylate 21.25%, hydroxyethyl methacrylate 14.0% and acrylic acid 1%, together with (in all cases except one) insoluble micro particles prepared as described in one of the preceding Examples or Comparative Examples. Details of the particular microparticles used and of the proportion of the three constituents taken are given in the accompanying Table II; the amounts stated are in each case parts by weight based on 100% non-volatile material. Each blend was then thinned with a 1:1 mixture of butyl acetate and xylene to a spraying viscosity of 50—60 seconds (measured in a BS.B3 cup at 25°C), and sprayed on to glass panels which were afterwards stoved for 30 minutes at 127°C. The appearance of the resulting film was then noted: the results are recorded also in Table II.

TABLE II

Example no.	6	D	E	F	G
M/F resin	30	30	30	30	30
Acrylic polymer	60	60	60	60	70
Microparticles	10	—	—	—	—
from:					
Example 4					
Comp. Ex. A	—	10	—	—	—
" " B	—	—	10	—	—
" " C	—	—	—	10	—
Appearance of film	clear	very cloudy	slightly cloudy	clear	clear

The above results demonstrated that the inherent clarity of the cured acrylic film (Comparative Example G) is lost if microparticles which are not matched to its refractive index are introduced, i.e. microparticles containing a zero or low proportion of styrene (Comparative Examples D & E). Clarity of the film is maintained if the microparticles contain a high proportion of styrene (Comparative Example F) but this, as is demonstrated by the results presented in the previous group of Examples, is done at the expense of the microparticles being of a coarse size and consequently prone to settlement from dispersion. In contrast, the use of styrene in conjunction with a maleic acid or fumaric acid derivative according to the invention, as shown by Example 6, enables clarity of the film to be preserved without such accompanying drawbacks.

Examples 7—8 and Comparative Example H

(a) To a vessel fitted with stirrer, thermometer, reflux condenser and Dean and Stark separator there was charged:

Aliphatic hydrocarbon (boiling range 140—156°C; zero aromatic content)	25.735 parts
Methyl methacrylate	1.341 parts
Methacrylic acid	0.026 part
Azodiisobutyronitrile	0.107 part
Graft copolymer stabiliser (33% solution, as described below)	0.497 part

The vessel and charge were purged with inert gas and the temperature raised to 100°C and maintained there for 30 minutes in order to produce a 'seed' polymer dispersion. The following pre-mixed ingredients were then fed into the vessel at a uniform rate over a period of 3 hours, maintaining the temperature at 100°C with stirring:

Monomer, as given in detail below	19.877 parts
Hydroxyethyl acrylate	1.130 parts
Hexamethoxymethylmelamine	1.130 parts
Methacrylic acid	0.451 part
Azodiisobutyronitrile	0.140 part
Graft copolymer stabiliser (33% solution, as described below)	4.664 parts
Aliphatic hydrocarbon, (as described above)	11.320 parts

0031 997

The reaction mixture was then held at 100°C for a further period of 30 minutes, after which the temperature was raised to 140—145°C when recycling of distillate commenced; these conditions were maintained for 2 hours, during which 1.2 parts of water were removed at the separator. The contents of the vessel were then cooled to give a fine dispersion of crosslinked microparticles. The dispersions had solids contents in the range 38—39% and insoluble gel contents in the range 31—32%.

The graft copolymer stabiliser used in the foregoing procedure was obtained as follows: 12-hydroxystearic acid was self-condensed to an acid value of about 31—34 mg KOH/g (corresponding to a molecular weight of 1650—1800) and was then reacted with an equivalent amount of glycidyl methacrylate. The resulting unsaturated ester was copolymerised with methyl methacrylate and glycidyl methacrylate in the weight ratios 49:46:5 respectively, and the copolymer thus obtained was finally reacted with methacrylic acid and p-nitrobenzoic acid in the presence of a tertiary amine catalyst, in the proportions of 0.070 part of methacrylic acid and 0.019 part of p-nitrobenzoic acid for every 100 parts of the copolymer.

(b) To a vessel fitted as described in step (a) above, but fitted with provision for adding a liquid feed into the recycling distillate, there was charged 66.418 parts of the dispersion obtained in step (a). The dispersion was heated to 145°C to establish recycling of distillate, and the following premixed ingredients were then fed in via the returning distillate at a steady rate over a period of 3 hours:

	Reaction product of poly(12-hydroxystearic acid) and glycidyl methacrylate, (50% solution in aliphatic hydrocarbon, boiling range 136—165°C)	14.982 parts
	Hydroxyethyl acrylate	1.972 parts
	Methacrylic acid	0.394 part
	Styrene	5.193 parts
	Methyl methacrylate	3.943 parts
	Di-tert-butyl peroxide	0.394 part
	Graft copolymer stabiliser (33% solution, as described in (a), above)	5.984 parts

When the feed was complete, the reaction mixture was held at recycle temperature for 3 hours. The resulting dispersions of crosslinked microparticles, modified with non-crosslinked auxiliary polymer, had solids contents in the range 47—48% and insoluble gel contents in the range 29—30%.

The monomer used in the feed stage of step (a) of the above procedure in these Examples and Comparative Example had the compositions shown in the accompanying Table III; the first figure in each case represents the parts by weight of each monomer taken, the second figure (in parentheses) the weight percentage of the monomer in question in the total monomers used in the feed stage.

TABLE III

Example no.	7	8	H
Methyl methacrylate	16.283 (72.0)	15.085 (66.8)	19.877 (88.0)
N-o-Chlorophenyl-maleimide	2.396 (10.6)	2.396 (10.6)	—
Styrene	1.198 (5.3)	2.396 (10.6)	—

Examples 9—10 and Comparative Example J

Air-drying alkyd coating compositions were prepared by blending 90 parts of a 52% tall oil-modified alkyd resin from pentaerythritol, p-tert-butylbenzoic acid, benzoic acid and phthalic anhydride with 10 parts of insoluble microparticles prepared as described in one of Examples 7 or 8 or Comparative Example H. Each blend was thinned to a viscosity of 24 seconds (measured in a B.S. B3 cup at 25°C) with a solvent consisting of aliphatic hydrocarbon, boiling range 138—165°C, 95 parts, nonanol 5 parts, and mixed terpene alcohols 1 part. The blends were sprayed on to glass panels, allowed to dry overnight and the appearance of the resulting film then noted. The particular microparticles used, and the film appearance in each case are recorded in Table IV below.

TABLE IV


Example no.	9	10	J
Microparticles from	Ex. 7	Ex. 8	Comp. Ex. H
Appearance of film	slightly cloudy	clear	very cloudy

Claims

1. A process for the production of addition polymer microparticles, comprising the dispersion polymerisation in an aliphatic hydrocarbon liquid of an ethylenically unsaturated monomer mixture
 5 which gives rise to a polymer or copolymer insoluble in the hydrocarbon liquid and which comprises (i) up to 50% by weight of styrene or a substituted derivative thereof and (ii) up to 50% by weight of a derivative of maleic acid or fumaric acid which is soluble in the hydrocarbon liquid at the temperature of polymerisation, the polymerisation being carried out in the presence in the hydrocarbon liquid of a
 10 steric dispersion stabiliser the molecule of which comprises at least one polymeric component which is solvated by the hydrocarbon liquid and at least one other component which is not solvated by the liquid and is capable of associating with the polymer produced.

2. A process as claimed in claim 1, wherein the derivative of maleic acid or fumaric acid contains in the molecule at least one aromatic group.


3. A process as claimed in claim 2, wherein the derivative is an N-aryl-substituted maleimide of
 15 the general formula



where R is an aromatic radical which may contain a single benzene nucleus or two or more connected or fused benzene nuclei.

4. A process as claimed in claim 3, wherein the derivative is N-o-chlorophenylmaleimide.

5. A process as claimed in claim 2, wherein the derivative is a diester of maleic acid or fumaric acid of the structure



where either X or Y, or both, is an aromatic radical which may contain a single benzene nucleus or two or more connected or fused benzene nuclei.

6. A process as claimed in claim 5, wherein the derivative is dibenzyl maleate.

7. A process as claimed in any one of claims 1 to 6 for preparing crosslinked polymer
 35 microparticles, wherein the monomer mixture being polymerised comprises:—

- (i) from 10% to 40% by weight of styrene or a homologue thereof;
 (ii) from 2% to 30% by weight of a maleic acid or fumaric acid derivative which is soluble in the hydrocarbon liquid at the temperature of polymerisation;
 40 (iii) from 0.2% to 10% by weight of crosslinking monomer which is a single comonomer or the combination of two mutually reactive comonomers;
 (iv) from 20% to 87.8% of one or more other ethylenically unsaturated monomers not falling within any of the categories (i), (ii) or (iii), the total monomers being 100%.

8. A process as claimed in any one of claims 1 to 6 for preparing crosslinked polymer
 45 microparticles, wherein the monomer mixture being polymerised comprises:

- (i) from 10% to 40% by weight of styrene or a homologue thereof;
 (ii) from 2% to 30% by weight of a maleic or fumaric acid derivative which is soluble in the hydrocarbon liquid at the temperature of polymerisation;
 60 (iii) from 1% to 20% by weight of a hydroxyl group-containing monomer;
 (iv) from 1% to 5% by weight of carboxyl group-containing monomer;
 (v) from 5% to 86% by weight of one or more other ethylenically unsaturated monomers not falling within any of the categories (i) to (iv), the total monomers being 100%

55 and the monomer mixture being polymerised in the presence of from 0.5% to 20%, based on the monomer mixture, of a reactive amino resin.

9. A process as claimed in any one of claims 1 to 8, wherein the stabilising agent is a graft copolymer comprising an acrylic polymer backbone, which is non-solvatable by the hydrocarbon liquid, and a plurality of chains pendant from the backbone which are residues of poly(12-hydroxystearic acid) and which are solvatable by the hydrocarbon liquid.

10. A coating composition comprising a liquid diluent and film-forming constituents which comprise:—

- (i) a film-forming polymer;
 65 (ii) polymer microparticles made by the process as claimed in any one of claims 1 to 9.

11. A coating composition as claimed in claim 10, wherein the polymer microparticles have been associated, before their introduction into the composition, with an essentially non-crosslinked polymer which is soluble in the liquid diluent of the composition and is compatible with the film-forming polymer.

5


Patentansprüche

1. Verfahren zur Herstellung von Additionspolymermikroteilchen durch Dispersionspolymerisation eines äthylenisch ungesättigten Monomergemischs in einer aliphatischen Kohlenwasserstoffflüssigkeit, welches Monomergemisch ein in der Kohlenwasserstoffflüssigkeit unlösliches Polymer oder Copolymer ergibt und (i) bis zu 50 Gew.-% Styrol oder eines substituierten Derivats davon und (ii) bis zu 50 Gew.-% eines Maleinsäure- oder Fumarsäurederivats, das in der Kohlenwasserstoffflüssigkeit bei der Polymerisationstemperatur löslich ist, enthält, wobei die Polymerisation in Gegenwart eines sterischen Dispersionsstabilisators in der Kohlenwasserstoffflüssigkeit ausgeführt wird, welcher Dispersionsstabilisator im Molekül mindestens eine polymere Komponente, die durch die Kohlenwasserstoffflüssigkeit solvatisiert wird, und mindestens eine weitere Komponente, die durch die Flüssigkeit nicht solvatisiert wird und sich mit dem gegildeten Polymer assoziieren kann, enthält.

2. Verfahren nach Anspruch 1, bei welchem das Maleinsäure- oder Fumarsäurederivat im Molekül mindestens eine aromatische Gruppe enthält.

3. Verfahren nach Anspruch 2, bei welchem das Derivat ein N-aryl-substituiertes Maleimid der allgemeinen Formel

25




ist, worin R für ein aromatisches Radikal steht, das einen einzigen Benzolkern oder zwei oder mehr miteinander verbundene oder kondensierte Benzolkerne enthalten kann.

4. Verfahren nach Anspruch 3, bei welchem das Derivat aus N-o-Chlorophenylmaleimid besteht.

5. Verfahren nach Anspruch 2, bei welchem das Derivat aus einem Diester von Maleinsäure oder Fumarsäure der Struktur

35



besteht, worin X und/oder Y für ein aromatisches Radikal steht, das einen einzigen Benzolkern oder zwei oder mehr miteinander verbundene oder kondensierte Benzolkerne enthalten kann.

6. Verfahren nach Anspruch 5, bei welchem das Derivat aus Dibenzylmaleat besteht.

7. Verfahren nach einem der Ansprüche 1 bis 6 zur Herstellung von vernetzten Polymermikroteilchen, bei welchem das zu polymerisierende Monomergemisch folgendes enthält:

45

- (i) 10 bis 40 Gew.-% Styrol oder eines Homologen davon;
- (ii) 2 bis 30 Gew.-% eines Maleinsäure- oder Fumarsäurederivats, das in der Kohlenwasserstoffflüssigkeit bei der Polymerisationstemperatur löslich ist;
- (iii) 0,2 bis 10 Gew.-% eines Vernetzungsmonomers, das ein einzelnes Comonomer oder eine Kombination aus zwei gegenseitig reaktiven Comonomeren ist;
- (iv) 20 bis 87,8% ein oder mehrerer weiterer äthylenisch ungesättigter Monomere, die nicht in die Kategorien (i), (ii) oder (iii) fallen,

50

wobei die gesamten Monomere 100% ausmachen.

55

8. Verfahren nach einem der Ansprüche 1 bis 6 zur Herstellung von vernetzten Polymermikroteilchen, bei welchem das zu polymerisierende Monomergemisch folgendes enthält:

- (i) 10 bis 40 Gew.-% Styrol oder eines Homologen davon;
- (ii) 2 bis 30 Gew.-% eines Maleinsäure- oder Fumarsäurederivats, das in der Kohlenwasserstoffflüssigkeit bei der Polymerisationstemperatur löslich ist;
- (iii) 1 bis 20 Gew.-% eines Hydroxylgruppen enthaltenden Monomers;
- (iv) 1 bis 5 Gew.-% eines Carboxylgruppen enthaltenden Monomers;
- (v) 5 bis 86 Gew.-% ein oder mehrerer weiterer äthylenisch ungesättigter Monomere, die nicht in die Kategorien (i) bis (iv) fallen,

65

wobei die gesamten Monomere 100% ausmachen und wobei das Monomergemisch in Gegenwart von 0,5 bis 20%, bezogen auf das Monomergemisch, eines reaktiven Aminoharzes polymerisiert wird.

9. Verfahren nach einem der Ansprüche 1 bis 8, bei welchem das Stabilisierungsmittel ein Pfropfcopolymer ist, das ein durch die Kohlenwasserstoffliquidität nicht solvatisierbares Acrylpolymergerüst und eine Vielzahl von Gerüst abstehender Ketten, welche Reste von Poly-(12-Hydroxystearinsäure) darstellen und durch die Kohlenwasserstoffliquidität solvatisierbar sind, enthält.

10. Beschichtungszusammensetzung, welche ein flüssiges Verdünnungsmittel und filmbildende Bestandteile enthält, nämlich:

- (i) ein filmbildendes Polymer;
 (ii) Polymermikroteilchen, die durch das Verfahren nach einem der Ansprüche 1 bis 9 hergestellt worden sind.


11. Beschichtungszusammensetzung nach Anspruch 10, bei welcher die Polymermikroteilchen vor ihrer Einführung in die Zusammensetzung mit einem im wesentlichen nichtvernetzenden Polymer, das in dem flüssigen Verdünnungsmittel der Zusammensetzung löslich und mit dem filmbildenden Polymer verträglich ist, assoziiert worden sind.

20 Revendications

1. Procédé de production de microparticules de polymère d'addition, comprenant la polymérisation en dispersion, dans un liquide hydrocarboné aliphatique, d'un mélange de monomères éthyléniquement insaturés qui donne naissance à un polymère ou copolymère insoluble dans le liquide hydrocarboné et qui comprend (i) jusqu'à 50% en poids de styrène ou d'un dérivé substitué de celui-ci et (ii) jusqu'à 50% en poids d'un dérivé d'acides maléique ou d'acide fumarique qui est soluble dans le liquide hydrocarboné à la température de polymérisation, la polymérisation étant exécutée en présence, dans le liquide hydrocarboné, d'un stabilisant de dispersion stérique dont la molécule comprend au moins un constituant polymère qui est solvate par le liquide hydrocarboné et un autre constituant qui n'est pas solvate par le liquide et est capable de s'associer au polymère formé.

2. Procédé suivant la revendication 1, dans lequel le dérivé d'acide maléique ou d'acide fumarique contient au moins un radical aromatique dans la molécule.


3. Procédé suivant la revendication 2, dans lequel le dérivé est un maléimide N-aryl-substitué de formule générale



où Ar est un radical aromatique qui peut contenir un noyau de benzène unique ou deux ou plusieurs noyaux de benzène assemblés ou condensés.

4. Procédé suivant la revendication 3, dans lequel le dérivé est le N-o-chlorophénylmaléimide.

5. Procédé suivant la revendication 2, dans lequel le dérivé est un diester d'acide maléique ou d'acide fumarique de formule:



où X et/ou Y sont un radical aromatique qui peut contenir un noyau de benzène unique ou deux ou plusieurs noyaux de benzène assemblés ou condensés.

6. Procédé suivant la revendication 5, dans lequel le dérivé est le maléate de dibenzyle.

7. Procédé suivant l'une quelconque des revendications 1 à 6 de préparation de microparticules de polymère réticulé, dans lequel le mélange des monomères qui est polymérisé comprend:

- (i) 10 à 40% en poids de styrène ou d'un homologue de celui-ci;
 (ii) 2 à 30% en poids d'un dérivé d'acide maléique ou d'acide fumarique qui est soluble dans le liquide hydrocarboné à la température de polymérisation;
 (iii) 0,2 à 10% en poids d'un monomère de réticulation qui est un comonomère unique ou la combinaison de deux comonomères mutuellement réactifs;
 (iv) 20 à 87,8% en poids d'un ou plusieurs autres monomères éthyléniquement insaturés n'étrant dans aucune des catégories (i), (ii) et (iii), le total des monomères étant de 100%.

0031 997

8. Procédé suivant l'une quelconque des revendications 1 à 6 de préparation de microparticules de polymère réticulé, dans lequel le mélange des monomères qui est polymérisé comprend:

- (i) 10 à 40% en poids de styrène ou d'un homologue de celui-ci;
- 5 (ii) 2 à 30% en poids d'un dérivé d'acide maléique ou d'acide fumarique qui est soluble dans le liquide hydrocarboné à la température de polymérisation;
- (iii) 1 à 20% en poids d'un monomère contenant un radical hydroxyle;
- (iv) 1 à 5% en poids d'un monomère contenant un radical carboxyle;
- 10 (v) 5 à 86% en poids d'un ou plusieurs autres monomères éthyléniquement insaturés n'appartenant à aucune des catégories (i) à (iv), le total des monomères étant de 100%,

et le mélange des monomères étant polymérisé en présence de 0,5 à 20%, sur base du mélange des monomères, d'une résine aminoplaste réactive.

9. Procédé suivant l'une quelconque des revendications 1 à 8, dans lequel l'agent stabilisant est un copolymère greffé comprenant un squelette polymère acrylique qui est non solvatable par le liquide hydrocarboné et plusieurs chaînes pendantes portées par le squelette qui sont des résidus d'acide poly(12-hydroxystéarique) et qui sont solvatables par le liquide hydrocarboné.

10. Composition de revêtement comprenant un diluant liquide et des constituants filmogènes qui comprend:

- 20 (i) un polymère filmogène;
- (ii) des microparticules de polymère obtenues par un procédé suivant l'une quelconque des revendications 1 à 9.

25 11. Composition de revêtement suivant la revendication 10, dans laquelle les microparticules de polymère ont été associées, avant leur introduction dans la composition, à un polymère essentiellement non réticulé qui est soluble dans le diluant liquide de la composition et qui est compatible avec le polymère filmogène.

30

35

40

45

50

55

60

65