



(43) International Publication Date  
18 September 2014 (18.09.2014)

WIPO | PCT

(10) International Publication Number  
**WO 2014/138976 A1**

(51) International Patent Classification:

*C08L 1/02* (2006.01) *C08J 5/18* (2006.01)  
*C08J 3/20* (2006.01) *C08K 5/42* (2006.01)

(21) International Application Number:

PCT/CA2014/050219

(22) International Filing Date:

12 March 2014 (12.03.2014)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/777,203 12 March 2013 (12.03.2013) US

(71) Applicant: **CELLUFORCE INC.** [CA/CA]; Suite 1501,  
625 Président-Kennedy Avenue, Montréal, Québec H3A  
1K2 (CA).

(72) Inventors: **HAMAD, Wadood Yasser**; 109-2040 West  
12th Avenue, Vancouver, British Columbia V6J 2G2 (CA).  
**ATIFI, Siham**; 216-3428 Wesbrook Mall, Vancouver,  
British Columbia V6T 1Z4 (CA). **BERRY, Richard Mi-**  
**chael**; 68 Du Domaine, Notre-Dame-De-L'Ile-Perrot,  
Québec J7V 7P2 (CA).

(74) Agent: **NORTON ROSE FULBRIGHT CANADA**  
**LLP/S.E.N.C.R.L., S.R.L.**; Suite 2500, 1 place Ville-Mar-  
ie, Montreal, Québec H3B 1R1 (CA).

(81) Designated States (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AL, AM,  
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,  
BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,  
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,  
HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR,  
KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME,  
MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ,  
OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA,  
SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM,  
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM,  
ZW.

(84) Designated States (unless otherwise indicated, for every  
kind of regional protection available): ARIPO (BW, GH,  
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ,  
UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,  
TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK,  
EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV,  
MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,  
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,  
KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: FLEXIBLE NANOCRYSTALLINE CELLULOSE (NCC) FILMS WITH TUNABLE OPTICAL AND MECHANICAL PROPERTIES

(57) Abstract: This invention describes development of a novel flexible film comprising nanocrystalline cellulose (NCC), or cellulose nanocrystals (CNC), and a controlled amount of a suitable zwitterionic (amphoteric) surfactant. The films are iridescent and have a high level of structural integrity, where mechanical properties can be engineered to suit the end applications. Flexible NCC films can be used in a multitude of applications, for instance, electrostatic shielding, gas barrier, hard coatings, printing.



WO 2014/138976 A1

## **FLEXIBLE NANOCRYSTALLINE CELLULOSE (NCC) FILMS WITH TUNABLE OPTICAL AND MECHANICAL PROPERTIES**

### **FIELD OF THE DISCLOSURE**

This invention describes development of a novel flexible film comprising nanocrystalline cellulose (NCC), or cellulose nanocrystals (CNC), and a controlled amount of a suitable zwitterionic (amphoteric) surfactant.

### **BACKGROUND OF THE DISCLOSURE**

Nanocrystalline cellulose (NCC), also referred to as cellulose nanocrystals (CNC), is extracted as a colloidal suspension by (typically sulfuric) acid hydrolysis of lignocellulosic materials, such as bacteria, cotton, or wood pulp. NCC is comprised of cellulose, a linear polymer of  $\beta(1\rightarrow4)$  linked D-glucose units, whose chains are arranged to form crystalline and amorphous domains.

Colloidal suspensions of cellulose crystallites form a chiral nematic structure upon reaching a critical concentration. Hydrogen bonding between the cellulose chains can stabilize the local structure in NCC, and plays a key role in the formation of crystalline domains. The iridescence of NCC self-assemblies is typically characterized by the finger-print patterns, where the patch work of bright and dark regions is typical of spherulitic behavior of fibrillar crystals in which the molecules are packed with their axes perpendicular to the fibrillar axis.

### **SUMMARY OF THE DISCLOSURE**

In one aspect, there is provided a NCC-surfactant adduct comprising NCC and one or more zwitterionic surfactant; wherein said one or more zwitterionic surfactant is adsorbed onto said NCC.

In one aspect, there is provided a process for preparing a NCC-surfactant adduct comprising providing a suspension of NCC in an aqueous medium; adding one or more zwitterionic surfactant and contacting said NCC and said zwitterionic surfactant to form the NCC-surfactant adduct, and purifying the NCC-surfactant adduct.

In one aspect, there is provided a process for preparing a film comprising providing a suspension of NCC-surfactant adduct as defined herein in an aqueous medium; and substantially or completely removing said aqueous medium to produce said film.

## BRIEF DESCRIPTION OF THE FIGURES

FIG. 1 illustrates chiral nematic organization of flexible NCC films at different surfactant (DMAPS) ratios. Top left is pure NCC, top right is a film with NCC:DMAPS = 1:0.1, bottom left NCC:DMAPS = 1:0.4, and bottom right NCC:DMAPS = 1:1.

FIG. 2 is UV-Vis measurements of cast NCC films at different DMAPS ratios.

FIG. 3 is CD measurements of cast NCC films at different DMAPS ratios.

FIG. 4 illustrates the mechanical response of NCC films containing different DMAPS ratios.

FIG. 5 illustrates the mechanical response of NCC films containing similar amounts of DMAPS but prepared at different pH.

FIG. 6 illustrates zwitterion-NCC (NCC:DMAPS = 1:1) films prepared according to this disclosure but purified using HCl and EtOH. Films are transparent with no chiral nematic organization.

## DETAILED DESCRIPTION OF THE EMBODIMENTS

Nanocrystalline cellulose (NCC), or cellulose nanocrystals (CNC), is characterized by high crystallinity (between 85 and 97%, typically greater than 90%) approaching the theoretical limit of the cellulose chains (Hamad W. Y., and Hu, T. Q., *Can. J. Chem. Eng.* 88: 392-402, 2010). NCC can further be characterized by a degree of polymerization (DP) in the range  $90 \leq DP \leq 110$ , and 3.7-6.7 sulphate groups per 100 anhydroglucose units (Hamad W. Y., and Hu, T. Q., *Can. J. Chem. Eng.* 88: 392-402, 2010). The crystallites have aspect ratios between 10 and 20 (Hamad W. Y., and Hu, T. Q., *Can. J. Chem. Eng.* 88: 392-402, 2010). Their physical dimensions depend on the raw material used in the extraction, which ranges between 5-15 nm in cross-section and 100-150 nm in length for bleached kraft pulp. These charged crystallites can be suspended in water, or other solvents if appropriately compatibilized, or self-

assemble to form solid materials by air, spray- or freeze-drying. Hydrogen bonding between cellulose chains can stabilize the local structure in NCC, and plays a key role in the formation of crystalline domains. Crystallinity strongly influences the physical and chemical behaviour of NCC. For example, the crystallinity of NCC directly influences the accessibility for chemical derivatization, swelling and water-binding properties.

When NCC particles self-assemble upon evaporation of water, they form brittle films. These films retain the chiral nematic structure of the liquid crystalline phase. Owing to their brittle nature, the films are rendered unsuitable for applications whereby NCC may be applied as a structurally integral film or coating. The current invention discloses a novel way to overcome the brittle feature of typical NCC films.

The novel NCC films retain their unique chiral nematic structure (FIG. 1), but, in addition, have superbly improved strength, stiffness and toughness. The films are iridescent and have a high level of structural integrity, where mechanical properties can be engineered to suit the end applications. Flexible NCC films can be used in a multitude of applications, for instance, electrostatic shielding, gas barrier, hard coatings, printing.

In an aspect, aqueous suspensions of NCC are heated and mixed with a desired amount of a suitable amphoteric surfactant, for example, a zwitterionic surfactant. Amphoteric, or zwitterionic, surfactants have both cationic and anionic centres attached to the same molecule. The cationic part is typically based on primary, secondary, or tertiary amines or quaternary ammonium cations. The anionic part can be more variable and include sulfonates.

Examples of zwitterionic surfactants that can be used to adsorb to the anionic sulfated NCC include, but are not limited to: 3-(N,N-dimethylmyristylammonio)-propanesulfonate, 3-(N,N-dimethylpalmitylammonio)-propanesulfonate, 3-(N,N-dimethyloctadecylammonio)-propanesulfonate, N-dodecyl-N,N-dimethyl-3-ammonio-1-propanesulfonate, 3-(decyldimethylammonio)propanesulfonate, 3-(N,N-dimethyloctylammonio)propanesulfonate, and 3-[N,N-dimethyl(3-palmitoylamino)propyl]ammonio]-propanesulfonate. In one embodiment, the surfactant is 3-(N,N-Dimethylmyristylammonio)propanesulfonate (DMAPS).

The suitable zwitterionic surfactant can have a Critical Micelle Concentration (CMC), i.e., maximum monomer concentration, between 0.01 and 40 mM; and an aggregation number, or average number of monomers in a micelle, in the range 10 to 200. Ideally, CMC should be in the range 0.1 to 0.4 mM and the aggregation number around 80. Experiments to determine the aggregation number are known in the art, for example by using a luminescent probe, quencher and a known concentration of surfactant.

In one embodiment, the zwitterionic surfactant-to-NCC mass ratio used in the process and NCC-surfactant described herein can range from 0.1:1 to 1:1, and lower ratios in the range of 0.01:1 are also possible.

### Examples

#### Reaction:

40 g of aqueous NCC suspension was mixed with 110 g of deionized (DI) water and sonicated for 10 min at 60% max power in a Fisher Sonic Dismembrator. The NCC solids contents in the suspension were 2 %. The NCC suspension was heated to 80 °C, and a zwitterionic surfactant, 3-(N,N-Dimethylmyristylammonio)propanesulfonate (DMAPS) suspension was added with vigorous stirring to produce suspensions with the following NCC:DMAPS mass ratios: 1:0.1, 1:0.41 and 1:1. The mixture was continuously stirred for 2 hours at 80 °C.

#### Purification:

After completion of the reaction, the clear suspension was mixed with a disintegrator for 1 min and dialyzed against DI water until reaching a stable conductivity value. The dialyzed suspension was further sonicated for 10 min at 60% max. power.

#### Alternative purification:

In another preparation, the purification procedure was modified as follows. After completion of the reaction between NCC and the surfactant, the suspension was precipitated by adding HCl (37%) until reaching pH = 1. A very viscous (gel-like) suspension was formed, and the suspension was centrifuged once at 4000 rpm for 30 min. The precipitated paste was subsequently washed with EtOH and further centrifuged at 4000 rpm for 30 min. This was repeated twice.

The purified paste was re-dispersed in DI water and air dried.

### Physico-Chemical Characteristics

The size of baseline NCC and DMAPS-NCC particles was determined by photon correlation spectroscopy (Zetasizer 3000, Malvern Instruments, UK), which uses dynamic laser light scattering. NCC particles size was found to be  $50.5 \pm 0.4$  nm, and that of NCC-DMAPS  $51.8 \pm 1.3$  nm in the case of NCC:DMAPS = 1:0.41, and  $53.2 \pm 1.7$  nm for NCC:DMAPS = 1:1.

Once the reaction is complete and purified, as described above, NCC-DMAPS films are prepared by evaporation or casting. Any suitable film preparation method is contemplated.


Examining Table 1 it is possible to correlate the amount of zwitterionic surfactant (DMAPS) determined gravimetrically with the nitrogen and sulfur contents from elemental analysis. For samples B and D, where the ratio of NCC-to-DMAPS was 1-to-0.41 the nitrogen content was practically identical within the margin of error associated with elemental measurements, namely, 0.58 and 0.61 %, respectively. When the NCC-to-DMAPS ratio is increased to 1-to-1 (sample C, Table 1), the nitrogen content was found to be 1.51 %. The typical nitrogen content in pure NCC (Control, Table 1) was less than 0.3 %. Table 1 further indicates successful ionic adsorption of the zwitterionic surfactant to NCC surface by examining the sulfur content. For samples B, C, and D, the sulfur content was 1.69, 3.63, and 1.44 %, respectively. The sulfur content is typically 0.68 % for NCC extracted using sulfuric acid hydrolysis (Control, Table 1). It is apposite to note that sample A, with NCC:DMAPS = 1:0.1, has a gravimetric weight determination of DMAPS less than 5 % and a corresponding less than 0.3 % nitrogen content, as well as 0.64 % sulfur. Samples A, B and C (Table 1) were prepared with sodium (Na)-form NCC, whereas sample D (which has similar ratio of NCC:DMAPS to sample B) was prepared with protonated (H)-form NCC. This indicates that any form of sulfated nanocrystalline cellulose, or cellulose nanocrystals, can be reacted with the zwitterionic surfactant to generate flexible, iridescent NCC films.

Table 1: Elemental and conductivity data for NCC films prepared at different zwitterionic surfactant ratios.

| NCC:DMAPS | pH | Conductivity | DMAPS | C | H | N | S |
|-----------|----|--------------|-------|---|---|---|---|
|-----------|----|--------------|-------|---|---|---|---|

|         | Mass Ratio |      | ( $\mu\text{S}.\text{cm}^{-1}$ ) | (wt.%) | (%)  | (%)  | (%)  | (%)  |
|---------|------------|------|----------------------------------|--------|------|------|------|------|
| A       | 1:0.1      | 4.03 | 103                              | <5     | 37.9 | 5.65 | <0.3 | 0.64 |
| B       | 1:0.41     | 4.17 | 79                               | 22     | 43.5 | 6.70 | 0.58 | 1.69 |
| C       | 1:1        | 4.23 | 75                               | 53     | 46.7 | 7.74 | 1.51 | 3.63 |
| D       | 1:0.41     | 3.04 | 319                              | 19     | 43.1 | 6.66 | 0.61 | 1.44 |
| Control | 1:0        | 6.9  | 377                              | 0      | 40.2 | 5.99 | <0.3 | 0.68 |

NCC obtained from sulfuric acid hydrolysis of lignocellulosic materials contains (negative) sulfate groups on the surface. A suitable zwitterionic surfactant, as in 3-(N,N-dimethylmyristylammonio)-propanesulfonate, DMAPS, contains both negative ( $\text{SO}_3^-$ ) and positive ( $\text{N}^+$ ) charges. It is believed that the  $\text{N}^+$  from the surfactant (such as DMAPS) is adsorbed to the  $\text{SO}_3^-$  (i.e. sulfonates replacing the C-6 hydroxy of D-glucose) on the NCC surface, resulting in a net negative charge onto the NCC-DMAPS complex as shown in the scheme below:



Wherein the dotted lines represent an ionic interaction, R1 and R2 are  $\beta(1\rightarrow4)$  linked D-glucose units present in cellulose. Although each sulfonate in the scheme above is linked to a surfactant molecule, it is not intended to mean that all glucose will have such ionic linking. The number of such surfactant molecule will depend on the concentration and nature of surfactant used.

Like pure NCC, NCC treated with zwitterionic surfactants could be deposited onto an anode when a suitable electrical current was passed through an aqueous suspension of NCC or NCC-DMAPS complexes.

NCC treated with zwitterionic surfactants essentially remains hydrophilic. It is therefore dispersible in polar protic solvents, like water, and some polar aprotic solvents, like N,N-dimethylformamide (DMF), but not in non-polar solvents, like toluene or chloroform.

#### Optical and Mechanical Properties

The micelles of the zwitterionic surfactant act as small springs adsorbed onto the NCC surface. However, the NCC crystals are unperturbed, and as such retain their chiral nematic characteristic. Cast NCC films, at different ratios of NCC-to-DMAPS are characteristically chiral nematic in nature, as is pure NCC. The chiral pitch for NCC films having different zwitterion ratios ranges from 4.3 to 5.6  $\mu\text{m}$ , which is typical for pure NCC films. Measurements carried out on the various NCC films described hereinbefore, using UV-Vis and circular dichroism (CD) techniques, revealed a shift towards higher wavelengths as the zwitterionic surfactant ratios were increased relative to pure NCC (Figs. 2 and 3). This indicates the ability to tune the optical response of NCC films by controlling the amount of zwitterionic surfactant adsorbed onto the NCC surface.

While the chiral nematic characteristics of NCC films treated with zwitterionic surfactant are maintained and can be tailored by controlling the amount of surfactant used, the mechanical properties of the resulting films are greatly affected. The zwitterionic surfactants, as described above, act as small springs adsorbed onto the NCC surface via ionic linkages. The tensile strength, stiffness, toughness and stretch of the resulting NCC films are controlled via the use of zwitterionic surfactant (Fig. 4).

For NCC-to-DMAPS ratio equals 1:0.1 (sample A in Table 1), the NCC film is very strong resulting in an ultimate tensile strength of 63 MPa and maximum strain just below 1 % (Fig. 4). As the zwitterionic surfactant-to-NCC ratio is increased to parity (sample C in Table 1), the response of the NCC film becomes characteristically elastic-plastic, and the film is highly flexible (Fig. 4). The ultimate tensile strength and maximum strain average values are 13 MPa and 1.2 %, respectively. These are significantly stronger and more flexible films than could be obtained with, for instance, graphene/polyaniline composite paper or graphene paper (Wang, D. W, Li, F., Zhao, J., Ren, W., Chen, Z. G., Tan, J., Wu, Z. S., Gentle, I., Lu, G. Q., Cheng, H. M., "Fabrication of graphene/polyaniline composite paper *via in situ* anodic electropolymerization for high-performance flexible electrode," *ACS Nano* 3: 1745-1752 (2009). For graphene/polyaniline composite paper and graphene paper, it has been reported that the tensile strength was 12.6 and 8.8 MPa, and maximum strain, 0.11 and 0.08 %, respectively.

It is apposite to note that the pH of the NCC:DMAPS suspension affects the resulting mechanical response of cast NCC films. Samples B and D (Table 1) have similar NCC:DMAPS ratios, but different pH: 4.17 and 3.04, respectively. The tensile strength and strain of the more acidic film (sample D) were significantly lowered relative to the less acidic film (sample B) (Fig. 5).

Moreover, the incorporation of zwitterionic surfactant in the preparation of NCC films can modulate the hardness of resulting films. NCC is a typically hard material, whose hardness averages around 0.25 GPa (hardness is measured with a 25 gf load for 15 sec, and the values are converted from Vickers hardness to GPa). Gold has a typical hardness of 0.22 GPa, polystyrene 0.18 GPa, and nickel 0.64 GPa. Sample A (Table 1) measured a hardness of 0.36 GPa, and sample B 0.19 GPa, whereas sample C (NCC:DMAPS = 1:1) was too soft to record a measurement. It is evident that, in addition to the tensile strength and toughness properties, the hardness of NCC films can be calibrated and tailored using suitable amounts of zwitterionic surfactants to meet the needs of specific applications.

The prepared zwitterion-treated NCC films according to this disclosure (NCC:DMAPS = 1:1) but purified against HCl and EtOH (rather than dialysis; refer to Purification section above) were clear transparent films, with no chiral (iridescent) characteristics—i.e., the chiral nematic structure is disrupted by using hydrochloric acid and subsequent washing with ethanol (Fig. 6).

NCC treated with zwitterionic surfactants essentially remains hydrophilic. It is therefore dispersible in polar protic solvents, like water, and some polar aprotic solvents, like N,N-dimethylformamide (DMF), but not in non-polar solvents, like toluene or chloroform.

While the disclosure has been described in connection with specific embodiments thereof, it is understood that it is capable of further modifications and that this application is intended to cover any variation, use, or adaptation of the disclosure following, in general, the principles of the disclosure and including such departures from the present disclosure that come within known, or customary practice within the art to which the disclosure pertains and as may be applied to the essential features hereinbefore set forth, and as follows in the scope of the appended claims.

## Claims

1. A NCC-surfactant adduct comprising NCC and one or more zwitterionic surfactant; wherein said one or more zwitterionic surfactant is adsorbed onto said NCC.
2. The NCC-surfactant adduct of claim 1, wherein said surfactant has a CMC from 0.01 and 40 mM and an aggregation number from 10 to 200.
3. The NCC-surfactant adduct of claim 1, comprising a NCC:surfactant mass ratios of 1:0.01 to 1:1.
4. The NCC-surfactant adduct of any one of claims 1 to 3, wherein said NCC is the sodium (Na)-form NCC.
5. The NCC-surfactant adduct of any one of claims 1 to 3, wherein said NCC is the protonated (H)-form NCC.
6. The NCC-surfactant adduct of any one of claims 1 to 4, wherein said NCC-surfactant adduct has chiral nematic characteristics.
7. The NCC-surfactant adduct of claim 5, wherein said NCC-surfactant adduct has no chiral nematic characteristics.
8. A process for preparing a NCC-surfactant adduct comprising providing a suspension of NCC in an aqueous medium; adding one or more zwitterionic surfactant and contacting said NCC and said zwitterionic surfactant to form the NCC-surfactant adduct, and purifying the NCC-surfactant adduct.
9. The process of claim 8 wherein said suspension of NCC-surfactant adduct is prepared by mixing an aqueous NCC suspension in deionized water, optionally heating said NCC suspension, and mixing said NCC suspension and a zwitterionic surfactant to produce said suspension of NCC-surfactant adduct.
10. The process of claim 8 or 9, comprising a NCC: surfactant mass ratios of 1:0.01 to 1:1.

11. The process of any one of claims 8 to 10 wherein said surfactant is comprising a primary, secondary, or tertiary amines or quaternary ammonium cationic part and a sulfonate anionic part.
12. The process of any one of claims 8 to 10 wherein said surfactant is selected from 3-(N,N-dimethylmyristylammonio)-propanesulfonate, 3-(N,N-dimethylpalmitylammonio)-propanesulfonate, 3-(N,N-dimethyloctadecylammonio)-propanesulfonate, N-dodecyl-N,N-dimethyl-3-ammonio-1-propanesulfonate, 3-(decyldimethylammonio)propanesulfonate, 3-(N,N-dimethyloctylammonio)propanesulfonate, and 3-[N,N-dimethyl(3-palmitoylamino)propyl]ammonio]-propanesulfonate.
13. The process of any one of claims 8 to 12, wherein said step of purifying is comprising dialyzing NCC-surfactant adduct in deionized water until reaching a stable conductivity value.
14. The process of any one of claims 8 to 12, wherein said step of purifying is comprising precipitating said NCC-surfactant adduct by adding an acid.
15. A process for preparing a film comprising providing a suspension of NCC-surfactant adduct in an aqueous medium; and substantially or completely removing said aqueous medium to produce said film.
16. The process of claim 15 wherein said step of substantially or completely removing said aqueous medium is further comprising a step of casting said suspension of NCC-surfactant adduct.
17. A film prepared by the process of claim 15 or 16.
18. The film of claim 17 for use in one or more of electrostatic shielding, gas barrier, hard coatings and printing applications.




Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6

# INTERNATIONAL SEARCH REPORT

International application No.

**PCT/CA2014/050219**

## A. CLASSIFICATION OF SUBJECT MATTER

IPC: **C08L 1/02** (2006.01), **C08J 3/20** (2006.01), **C08J 5/18** (2006.01), **C08K 5/42** (2006.01)

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC: **C08L 1/02** (2006.01), **C08J 3/20** (2006.01), **C08J 5/18** (2006.01), **C08K 5/42** (2006.01)

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic database(s) consulted during the international search (name of database(s) and, where practicable, search terms used)  
CAPLus, internet, keywords, zwitterion(ic), surfactant, amphoteric, cellulose, ncc, cnc, film

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

| Category* | Citation of document, with indication, where appropriate, of the relevant passages                                                                                                                                                                            | Relevant to claim No. |
|-----------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------------------|
| A         | DI: US2010/0162926 A1 (THOMSON, S ET AL.) 1 July 2010 (01-07-2010)                                                                                                                                                                                            | 1-18                  |
| A         | DHAR, N ET AL., "Interactions of nanocrystalline cellulose with an oppositely charged surfactant in aqueous medium." Colloids and Surfaces A:Physiochemical and Engineering Aspects, vol 415, available online 19 September 2012 (19-09-2012), pages 310-319. | 1-18                  |
| A         | ALILA, S ET AL., "Adsorption of a Cationic surfactant onto Cellulosic Fibers I. Surface charge Effects." Langmuir, vol 21, available online 26 July 2005 (07-26-2005), pages 8106-8113.                                                                       | 1-18                  |
| A         | PENG, B., "Interactions between surfactants and polymer-grafted nanocrystalline cellulose." Colloids and Surfaces A:Physiochemical and Engineering Aspects, vol 421, available online 8 January 2013 (08-01-1013), pages 142-149.                             | 1-18                  |
| T         | LV, W ET AL., "Preparation of hemocompatible cellulosic paper based on P(DMAPS)-functionalized surface." Colloids and Surfaces B: Biointerfaces, Abstract only, vol 116, 1 April 2014 (01-04-2014), pages 537-543.                                            | 1-18                  |

 Further documents are listed in the continuation of Box C.

 See patent family annex.

|                                      |                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                               |                          |                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                          |
|--------------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| *<br>"A"<br>"E"<br>"L"<br>"O"<br>"P" | Special categories of cited documents:<br>document defining the general state of the art which is not considered to be of particular relevance<br>earlier application or patent but published on or after the international filing date<br>document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another claim or other special reason (as specified)<br>document referring to an oral disclosure, use, exhibition or other means<br>document published prior to the international filing date but later than the priority date claimed | "T"<br>"X"<br>"Y"<br>"&" | later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention<br>document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone<br>document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art<br>document member of the same patent family |
|--------------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|

Date of the actual completion of the international search  
20 May 2014 (20-05-2014)

Date of mailing of the international search report  
02 June 2014 (02-06-2014)

Name and mailing address of the ISA/CA  
Canadian Intellectual Property Office  
Place du Portage I, C114 - 1st Floor, Box PCT  
50 Victoria Street  
Gatineau, Quebec K1A 0C9  
Facsimile No.: 001-819-953-2476

Authorized officer  
  
Rebecca Gardner (819) 956-4117

## INTERNATIONAL SEARCH REPORT

International application No.

**PCT/CA2014/050219****Box No. II Observations where certain claims were found unsearchable (Continuation of item 2 of the first sheet)**

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claim Nos.:  
because they relate to subject matter not required to be searched by this Authority, namely:
  
2. ☒ Claim Nos.: 1-18  
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:  
The above claims do not clearly and concisely define the subject matter for which protection is sought, and thus fail to comply with Article 6 of the PCT. By the same token, the subject matter encompassed by said claims has not been clearly and completely disclosed in the description, such that the application does not comply with Article 5 of the PCT. See extra sheet for further details.
  
3. ☐ Claim Nos.:  
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

**Box No. III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)**

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying additional fees, this Authority did not invite payment of additional fees.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claim Nos.:
  
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claim Nos.:

**Remark on Protest**

- ☐ The additional search fees were accompanied by the applicant's protest and, where applicable, the payment of a protest fee.
- ☐ The additional search fees were accompanied by the applicant's protest but the applicable protest fee was not paid within the time limit specified in the invitation.
- ☐ No protest accompanied the payment of additional search fees.

## Continuation of Box No. II

Claims 1-18 do not clearly define the matter for which protection is sought, and thus fail to comply with Article 6 of the PCT. The expression zwitterionic surfactant results in genera that encompass a very broad range of compounds, such that it is not clear what exact compounds fall within the scope of these claims. Furthermore, the application only provides adequate disclosure within the meaning of Article 5 of the PCT as to the utility of the compounds appearing in the examples of the description, such that a search beyond this scope is not possible. Consequently, the search has only been established for the parts of the application which appear to be clear and supported, namely 3-(N, N-Dimethylmyristylammonio)propanesulfonate (DMAPS).

**INTERNATIONAL SEARCH REPORT**  
Information on patent family members

International application No.  
**PCT/CA2014/050219**

| Patent Document<br>Cited in Search Report | Publication<br>Date       | Patent Family<br>Member(s)                   | Publication<br>Date                                                                         |
|-------------------------------------------|---------------------------|----------------------------------------------|---------------------------------------------------------------------------------------------|
| US2010162926A1                            | 01 July 2010 (01-07-2010) | US2010162926A1<br>US8273174B2<br>US8293003B1 | 01 July 2010 (01-07-2010)<br>25 September 2012 (25-09-2012)<br>23 October 2012 (23-10-2012) |
| <hr/>                                     |                           |                                              |                                                                                             |