



(43) International Publication Date
16 June 2016 (16.06.2016)

(10) International Publication Number
WO 2016/094199 A1

- (51) International Patent Classification:
C09D 183/08 (2006.01)
- (21) International Application Number:
PCT/US2015/063852
- (22) International Filing Date:
4 December 2015 (04.12.2015)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
62/088,750 8 December 2014 (08.12.2014) US
- (71) Applicant: **3M INNOVATIVE PROPERTIES COMPANY** [US/US]; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).
- (72) Inventors: **YANG, Yu**; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US). **GIBNEY, Katherine A.**; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US). **IYER, Suresh S.**; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US). **HAUGAN, Ingrid N.**; 749 Oakwood Drive, New Brighton, Minnesota 55112 (US). **JARIWALA, Chetan P.**; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US). **ZHANG, Yifan**; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).
- (74) Agents: **KOKKO, Kent S.**, et al.; 3M Center, Office of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))

Published:

- with international search report (Art. 21(3))

(54) Title: COMPOUNDS COMPRISING MODIFIED DIORGANOSILOXANE POLYMERS

(57) Abstract: Modified poly(diorganosiloxanes), compositions, and articles comprising the same. The modified poly(diorganosiloxanes) can be soluble or dispersable in aqueous media. The articles can have modified poly(diorganosiloxanes) affixed thereto.



WO 2016/094199 A1

COMPOUNDS COMPRISING MODIFIED DIORGANOSILOXANE POLYMERS

TECHNICAL FIELD

Compounds comprising modified poly(diorganosiloxanes) are disclosed. Compositions and articles comprising such compounds are also disclosed.


BACKGROUND

Polymers such as polydiorganosiloxanes can be hydrophobic. However, their use can be limited because they cannot be affixed to some substrates, and also can have minimal solubility and dispersibility in aqueous media.

Some polydiorganosiloxanes are described in WO 2007/075317 (Leir et al.), WO 2007/075802 (Sherman et al.), US 5,026,890 (Webb et al.), US 5,276,122 (Akoi et al.), US 5,214,119 (Leir et al.), and US 7,501,184 (Leir et al.)

SUMMARY

A compound can have the chemical structure of Formula (I)



(I)

wherein:

POLY is a poly(diorganosiloxane);

L₁ and L₂ are independently a covalent bond, alkylene, aralkylene, alkenylene, alkynylene, or arylene;

L₃ and L₄ are independently alkylene, aralkylene, alkenylene, alkynylene, or arylene,

m is independently represents the charge on the N atom, which is 0 or 1⁺;

and either:

R₁ is H, CH₂CH(OH)R^a-Si(R₅)₃, or R^d-R^e, and

R₂ is absent, H, CH₂CH(OH)R^a-Si(R₅)₃, or R^d-R^e;

or

5 R₁ and R₂ are covalently bound to one another, and are together alkylene, aralkylene, alkenylene, alkynylene, arylene, or any of the preceding substituted with hydroxy;

R₃ is independently hydroxy, alkoxy, or alkyl, provided that at least one R₃ is either hydroxy or alkoxy.

R^a is alkylene or R^b-O-R^c,

10 R^b is alkylene,

R^c is alkylene,

R^d is alkylene,

R^e is Si(R₅)₃, SO₃H or a salt thereof, or CO₂H or a salt thereof,

15 and R₅ is alkyl, alkoxy, or hydroxy, with the proviso that at least one R₅ is alkoxy or hydroxy.

Compositions containing such compounds are also described.

Articles, particularly glass articles, having such compounds affixed thereto are also described.

DETAILED DESCRIPTION

20 Throughout this disclosure, singular forms such as “a,” “an,” and “the” are often used for convenience; however, it should be understood that the singular forms are meant to include the plural unless the singular alone is explicitly specified or is clearly indicated by the context.

25 Some terms used in this application have special meanings, as defined herein. All other terms will be known to the skilled artisan, and are to be afforded the meaning that a person of skill in the art at the time of the invention would have given them.

30 “Independently,” when used in reference to the identify of one or more variable elements, means that each occurrence of any of the variable elements may have the same or different identity, within the specified limitations, regardless of the identity of any other occurrence of the reference element. Thus, if there are two occurrences of element “E,” and element E can be independently selected from identity A or identity B, each of the two occurrences of E can be either A or B, in any combination (e.g., AA, AB, BA, or BB)

“Alkyl” refers to a monovalent aliphatic hydrocarbon radical. Alkyl radicals can have any number of carbon atoms. Many alkyl groups are from C₁ to C₃₀. Some alkyl radicals can be C₁ or greater, such as C₂ or greater, C₄ or greater, C₆ or greater, or C₈ or greater. Some alkyl radicals can be C₂₂ or smaller, C₁₆ or smaller, C₁₂ or smaller, C₈ or smaller, or C₄ or smaller.

5 Unless otherwise indicated, any alkyl radicals can independently be linear, branched, cyclic, or a combination thereof (e.g., a cyclic alkyl can also have a linear or branched component.) Exemplary alkyl radicals include methyl, ethyl, propyl, isopropyl, *n*-butyl, *t*-butyl, *sec*-butyl, *iso*-butyl, 2-ethyl hexyl, *iso*-octyl, dodecyl, hexadecyl, behenyl, and the like.

10 “Aryl” refers to a monovalent aromatic radical. An aryl radicals can include only carbon and hydrogen or may also include one or more heteroatoms, such as one or more of oxygen, nitrogen, and sulfur. Aryl radicals can have aromatic rings with three or more atoms, four or more atoms, or five or more atoms. Aryl radicals can have rings with ten or fewer atoms, eight or fewer atoms, seven or fewer atoms, or six or fewer atoms. Exemplary aryl radicals include phenyl, furanyl, naphthyl, anthracenyl, and the like. Phenyl is a common
15 aryl substituent.

“Aralkyl” refers to a monovalent radical including an alkyl component and an aryl component. Aralkyl radicals can have a total of or six or more carbon atoms, seven or more carbon atoms, eight or more carbon atoms, nine or more carbon atoms, or ten or more carbon atoms. Aralkyl radicals can have a total of twenty-two or fewer carbon atoms, sixteen or
20 fewer carbon atoms, twelve or fewer carbon atoms, ten or fewer carbon atoms, eight or fewer carbon atoms, seven or fewer carbon atoms, or six or fewer carbon atoms. Exemplary aralkyl radicals include xylyl, toluenyl, and the like.

“Alkenyl” refers to a monovalent unsaturated hydrocarbon radical having one or more carbon-carbon double bonds. Many alkenyl radicals are from C₂ to C₃₀. Some alkenyl
25 radicals can be C₂ or greater, such as C₃ or greater, C₄ or greater, C₆ or greater, C₈ or greater, or C₁₀ or greater. Some alkenyl radicals can be C₂₂ or smaller, C₁₆ or smaller, C₁₂ or smaller, C₈ or smaller, or C₄ or smaller. Unless otherwise indicated, any alkenyl radical can be monounsaturated or polyunsaturated alkenyl. Exemplary alkenyl radicals include linoleyl, oleyl, myristoyl, palmitoyl, hexadecatrienyl, eicosatrienyl, eicosapentaenyl, arachidonyl,
30 docosadienyl, adrenyl, and the like.

“Alkynyl” refers to a monovalent unsaturated hydrocarbon radical having one or more carbon-carbon triple bonds. In addition to the one or more carbon-carbon triple bonds,

alkynyl radicals can also have one or more carbon-carbon double bonds. Many alkyl radicals are from C₂ to C₃₀. Alkynyl radicals can be, for example, C₂ or greater, C₃ or greater, C₄ or greater, C₆ or greater, C₈ or greater, or C₁₀ or greater. Alkynyl radicals can be, for example, C₂₂ or fewer, C₁₆ or fewer, C₁₂ or fewer, C₈ or fewer, or C₄ or fewer.

5 “Alkylene” refers to an aliphatic hydrocarbon diradical. Many alkylene diradicals are from C₁ to C₃₀. Alkylene diradicals can be C₁ or greater, C₂ or greater, C₃ or greater, C₄ or greater, C₆ or greater, or C₈ or greater. Alkylene diradicals can be C₂₂ or smaller, C₁₆ or smaller, C₁₂ or smaller, C₁₀ or smaller, or C₈ or smaller. Unless otherwise indicated, any alkylene can be linear, branched or cyclic or a combination thereof (e.g., having both a cyclic
10 component and a linear component.) Exemplary alkylene groups include methylene, ethylene, propyl, isopropylene, *n*-butylene, *t*-butylene, *sec*-butylene, *iso*-butylene, 2-ethyl hexylene, *iso*-octylene, dodecylene, hexadecylene, behenylene, and the like.

 “Alkenylene” refers to an unsaturated hydrocarbon diradical having one or more carbon-carbon double bonds. Many alkenylene diradicals are from C₂ to C₃₀. Alkenylene diradicals
15 can be C₂ or greater, C₃ or greater, C₄ or greater, C₆ or greater or C₈ or greater. Alkenylene diradicals can be C₂₂ or smaller, C₁₈ or smaller, C₁₆ or smaller, C₁₂ or smaller, C₁₀ or smaller, C₈ or smaller, or C₆ or smaller. Unless otherwise indicated, alkenylene diradicals can be monounsaturated or polyunsaturated, and can be linear, branched, cyclic, or a combination thereof (e.g., having both a cyclic component and a linear component.) Exemplary
20 alkenylene groups include linoleylene, oleylene, myristoylene, palmitoylene, hexadecatrienylene, eicosatrienylene, eicosapentaenylene, arachidonylene, docosadienylene, adrenylene, and the like.

 “Alkynylene” refers to an unsaturated hydrocarbon diradical having one or more carbon-carbon triple bonds. Alkynylene diradicals can also have one or more carbon-carbon double
25 bonds. Many alkynylene diradicals are from C₁ to C₃₀. Alkynylene diradicals can be C₂ or greater, C₃ or greater, C₄ or greater, C₆ or greater or C₈ or greater. Alkynylene diradicals can be C₂₂ or smaller, C₁₈ or smaller, C₁₆ or smaller, C₁₂ or smaller, C₁₀ or smaller, C₈ or smaller, or C₆ or smaller. Unless otherwise indicated, alkynylene diradicals can be monounsaturated or polyunsaturated, and can be linear, branched, cyclic, or a combination thereof (e.g., having
30 both a cyclic component and a linear component.)

 “Arylene” refers to an aromatic diradical. Arylene diradicals can have aromatic rings with three or more atoms, four or more atoms, or five or more atom. Arylene diradicals can

have rings with ten or fewer atoms, eight or fewer atoms, seven or fewer atoms, or six or fewer atoms. Suitable aryls include phenylene, furanylene, piperidylene, naphthylene, and the like. Phenylene is a common arylene diradical.

“Aralkylene” refers to a diradical including an alkyl component and an aryl component. Aralkylene diradicals can have a total of three or more carbon atoms, four or more carbon atoms, five or more carbon atoms, six or more carbon atoms or seven or more carbon atoms. Aralkylene diradicals can have a total of twenty-two or fewer carbon atoms, sixteen or fewer carbon atoms, twelve or fewer carbon atoms, ten or fewer carbon atoms, eight or fewer carbon atoms, seven or fewer carbon atoms, or six or fewer carbon atoms. Aralkylene groups include xylylene, toluenylene, and the like.

“Alkoxy” refers to a radical having the formula -O-ALK, wherein ALK is alkyl. The alkyl can include any alkyl, for example, any alkyl group referenced in the definition of “alkyl,” herein. The alkyl portion of an alkoxy substituent can independently be linear, branched, cyclic, or a combination thereof (e.g., a cyclic alkyl can also have a linear or branched component.) Examples of alkoxys include methoxy, ethoxy, propoxy, isopropoxy, n-butoxy, t-butoxy, sec-butoxy, iso-butoxy, 2-ethyl hexoxy, *iso*-octoxy, dodecoxy, hexadecoxy, and the like. Particular examples include methoxy and ethoxy.

“Hydroxy” refers to a radical having the formula -OH.

“Carbonyl alkoxy” refers to a radical having the formula -C(O)OALK, wherein OALK is alkoxy. The alkoxy can be any alkoxy, such as those referred to under the definition of “alkoxy,” herein.

“Carbonyl alkyl” refers to a radical having the formula -C(O)ALK, wherein ALK is alkyl. The alkyl can be any alkyl, such as those referred to under the definition of “alkyl,” herein.

“Carbonyl hydroxyl” refers to a radical having the formula -C(O)OH.

“Alkylene carbonyl alkyl” refers to a radical having the formula -ALK-C(O)-ALKYL, wherein ALK is alkylene and ALKYL is alkyl. The carbonyl alkyl substituent radical can be any carbonyl alkyl substituent radical, such as those referred to in the definition of “carbonyl alkyl,” herein.

“Amino” refers to a radical with the formula -N^c(H)_p(R')_q, wherein each R' is independently alkyl, alkenyl, alkyl, aryl, or alkaryl, any of which can be optionally substituted, p+q is 2 or 3, and c represents the charge on the nitrogen atom, which is either 0 or 1⁺. Typically, each R' is alkyl. When p+q is 2, c is 0; when p+q is 3, c is 1⁺. Amino

“Amido” refers to a radical having the formula $-C(O)N(H)_r(R')_s$, wherein each R' is independently alkyl, alkenyl, alkyl, aryl, or alkaryl, any of which can be optionally substituted, and r+s is 2. Typically, each R' is alkyl.

“Sulphydryl” refers to a radical having the formula -SH.

“PDMS” refers to “polydimethylsiloxane,” a polymer having the repeat unit $-\text{OSi}(\text{CH}_3)_2-$, that is, a polydiorganosiloxane wherein each occurrence of G is methyl. When not specified, the end groups of PDMS can vary; typical endgroups include trimethylsilyl groups and hydroxy groups, as well as terminating groups, quenching groups, and chain transfer groups.

$$\text{POLY} \left(\begin{array}{c} \text{HN} \text{---} \text{C}(=\text{O}) \text{---} \text{L}_2 \text{---} \text{C}(=\text{O}) \text{---} \text{HN} \text{---} \text{L}_3 \text{---} \text{N}^m \text{---} \text{L}_4 \text{---} \text{Si}(\text{R}_3)_3 \\ | \qquad \qquad \qquad | \qquad \qquad \qquad | \qquad \qquad \qquad | \\ \text{L}_1 \text{---} \text{C}(=\text{O}) \qquad \qquad \text{C}(=\text{O}) \qquad \qquad \text{R}_1 \qquad \qquad \text{R}_2 \end{array} \right) \quad (I)$$

In Formula (I):

POLY is a poly(diorganosiloxane);

L₁ and L₂ are independently a covalent bond, alkylene, aralkylene, alkenylene, alkynylene, or arylene;

5 L₃ and L₄ are independently alkylene, aralkylene, alkenylene, alkynylene, or arylene;

m represents the charge on the N atom, which is 0 or 1⁺;

and either:

R₁ is H, CH₂CH(OH)R^a-Si(R₅)₃, or R^d-R^e, and

R₂ is absent, H, CH₂CH(OH)R^a-Si(R₅)₃, or R^d-R^e;

10 or

R₁ and R₂ are covalently bound to one another, and are together alkylene, aralkylene, alkenylene, alkynylene, arylene, or any of the preceding substituted with hydroxy;

R₃ is independently hydroxy, alkoxy, or alkyl, provided that at least one R₃ is either hydroxy or alkoxy.

15 R^a is alkylene or R^b-O-R^c,

R^b is alkylene,


R^c is alkylene,

R^d is alkylene,

R^e is Si(R₅)₃, SO₃H or a salt thereof, or CO₂H or a salt thereof,

20 and R₅ is alkyl, alkoxy, or hydroxy, with the proviso that at least one R₅ is alkoxy or hydroxy.

In many cases, compounds of Formula (I) feature an L₂ that is a covalent bond. Such compounds are compounds of Formula (Ia).




25 (Ia)

Compounds of Formula (I) and (Ia) can be useful in that they have siloxane groups Si(R₃)₃, which allow them to be affixed to glass, for example, as a coating on glass. Such coatings can impart one or more of hydrophobicity, water repellency, and ink repellency to the glass.

In compounds of Formula (I) or (Ia), POLY can be any suitable divalent radical of a poly(diorganosiloxane), which is a polymer having the repeat unit $-\text{Si}(\text{G})_2\text{O}-$, wherein each occurrence of G is independently an organic moiety. Exemplary poly(diorganosiloxanes) include, for example poly(dialkylsiloxane) wherein each G is alkyl, poly(diarylsiloxane) wherein each G is aryl, or poly(alkylaryl siloxane) wherein one G is alkyl and the other is aryl. Poly(dialkylsiloxanes) include poly(di C₁ to C₂₂ alkylsiloxane), poly(di C₁ to C₁₂ alkylsilane), poly(di C₈-C₂₂ alkylsiloxane), for example, poly(di C₁₂-C₁₈ alkylsiloxane), as well as poly(di C₁ to C₄ alkylsiloxane). The alkyl groups in a poly(dialkylsiloxane) can be the same or different. An exemplary poly(dialkylsiloxane) is PDMS. A poly(diarylsiloxane) can be any suitable poly(diarylsiloxane). Exemplary poly(diarylsiloxanes) include poly(diphenylsiloxane). Other exemplary poly(diorganosiloxanes) include poly(alkyl aryl siloxanes) wherein some organic groups are alkyl and other organic groups are aryl. In such poly(diorganosiloxanes), the alkyl and aryl groups can be the same or different. Exemplary alkyl and aryl groups include those discussed above with respect to poly(dialkylsiloxane) and poly(diarylsiloxane).

The poly(diorganosiloxane) can have any appropriate molecular weight. The molecular weight, such as the number average molecular weight, will depend on both the chemical identity of the monomer or monomers that constitute the poly(diorganosiloxane) and on the degree of polymerization, such as the number average degree of polymerization. In many cases, the number average degree of polymerization can be 10 or greater, 15 or greater, 20 or greater, 25 or greater, 30 or greater, 35 or greater, 40 or greater, 45 or greater, 50 or greater, 55 or greater, or 60 or greater. In any of those cases, the number average degree of polymerization can be no more than 300, no more than 250, no more than 200, no more than 175, no more than 150, no more than 125, no more than 100, no more than 95, no more than 90, no more than 85, no more than 80, no more than 75, or no more than 70.

The compound of Formula (I) or (Ia) can be prepared from a poly(diorganosiloxane) having an amine endgroup. Such poly(diorganosiloxanes) have been described, for example, in US 3,890,269 (Ray), US 4,661,577 (Jo Lane et al.), US 5,026,890 (Webb et al.), US 5,276,122 (Aoki et al.), US 5,214,119 (Leir et al.), US 5,461,134 (Leir et al.), US 5,512,650 (Leir et al.), US 6,355,759 (Sherman et al.), and US 7,501,184 (Leir et al.). Also, such polydiorganosiloxanes are commercially available from Shin-Etsu Chemicals (Tokyo, Japan) and Gelest (Morrisville, PA). Exemplary poly(diorganosiloxanes) with amine end-groups can have the structure of Formula (II).




(II)

In Formula (II), L₁ can be a covalent bond to POLY. Alternatively, L₁ can be alkylene, aralkylene, alkenylene, alkynylene, or arylene. In many cases, L₁ is alkylene, such as C₁ to C₁₆ alkylene, C₁ to C₁₂ alkylene, C₁ to C₈ alkylene, or C₁ to C₄ alkylene. In some cases, L₁ is propylene. When L₁ is aralkylene, the alkylene portion of the aralkylene can be any suitable alkylene, such as C₁ to C₁₆ alkylene, C₁ to C₁₂ alkylene, C₁ to C₈ alkylene, or C₁ to C₄ alkylene. The arylene portion can be any suitable arylene, such as phenylene, naphthylene, anthrylene, pyridylene, pyrrolylene, or thionylene. When L₁ is aralkylene, the alkenylene can be any suitable alkenylene, for example C₁ to C₁₆ aralkenylene, C₁ to C₁₂ aralkenylene, C₁ to C₈ aralkenylene, or C₁ to C₄ aralkenylene. When L₁ is arylene, it can be any suitable arylene, such as arylene with five atoms, six atoms, eight atoms, ten atoms, and the like. Phenylene is a typical arylene.

In many cases, L₁ is alkylene. The alkylene can be linear. The alkylene can be C₁ or greater, such as C₂ or greater, C₄ or greater, C₆ or greater, or C₈ or greater. The alkylene can be C₂₂ or smaller, C₁₆ or smaller, C₁₂ or smaller, C₈ or smaller, or C₄ or smaller. An exemplary alkylene is *n*-propylene.

The poly(diorganosiloxane) with amine end-groups of Formula (II) can react with a diacid or synthetic equivalent thereof of Formula (III) according to Reaction Scheme 1 to form an intermediate compound of Formula (IV).

Reaction Scheme 1



In Formula (III) L₂ can be any suitable linking group, such as a covalent bond, alkylene, aralkylene, alkenylene, alkynylene, or arylene. When L₂ is alkylene, the alkylene can be any suitable alkylene, such as C₁ to C₂₂ alkylene, C₁ to C₁₆ alkylene, C₁ to C₁₂ alkylene, C₁ to C₈ alkylene, or C₁ to C₄ alkylene. When L₂ is aralkylene, the alkylene portion of the aralkylene can be any suitable alkylene, such as C₁ to C₂₂ alkylene, C₁ to C₁₆ alkylene, C₁ to C₁₂ alkylene, C₁ to C₈ alkylene, or C₁ to C₄ alkylene. The arylene portion can be any suitable arylene, such as phenylene, naphthylene, anthrylene, pyridylene, furanylene, or

pyrrolylene. When L₂ is alkenylene, the alkenylene can be any suitable alkyenylene, for example C₂ to C₁₆ alkenylene, C₂ to C₁₂ alkenylene, C₂ to C₈ alkenylene, or C₂ to C₄ alkenylene. When L₂ is alkynylene, it can be any suitable alkynylene, such as C₂ to C₁₆ alkynylene, C₂ to C₁₂ alkynylene, C₂ to C₈ alkynylene, or C₂ to C₄ alkynylene. When L₂ is arylene, it can be any suitable arylene, such as arylene with five atoms, six atoms, eight atoms, ten atoms, and the like. Phenylene is a typical arylene.

The nature of L₂ will depend on the identity of the compound of Formula (III). For example, when the compound of Formula (III) is oxalic acid or a synthetic equivalent thereof, L₂ is a covalent bond. When the compound of Formula (III) is malonic acid or a synthetic equivalent thereof, L₂ is methylene. The compound of Formula (III) can also be, for example and without limitation, succinic acid, glutaric acid, adipic acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, or a synthetic equivalent of any of the foregoing. Thus L₂ can be, for example, ethylene, *n*-propylene, *n*-butylene, *n*-pentylene, *n*-hexylene, *n*-heptylene, or *n*-octylene. When L₂ is arylene, it can be, for example, phenylene, in which case the compound of Formula (III) is ortho-, iso-, or terephthalic acid, or synthetic equivalents thereof. L₂ can also be alkenylene, such as C₂ alkenylene, in which case the compound of Formula (III) can be maleic acid or fumaric acid, or synthetic equivalents thereof.

Most commonly, the compound of Formula (III) is oxalic acid or an oxalate. In such cases, L₂ is a covalent bond.

In the compounds of Formulas (III) and (IV), A can independently be hydroxy, alkoxy, haloalkoxy, halogen, such as chlorine, bromine, or iodine, or a leaving group, such as the leaving groups discussed below. Thus, the reaction of Reaction Scheme 1 can use a dicarboxylic acid form of the compound of Formula (III), in which case both instances of A are hydroxy. While this is acceptable, it can be convenient to instead use synthetic equivalents of the dicarboxylic acid. Such synthetic equivalents can be easier to handle or more reactive towards the amine endgroups of the poly(diorganosiloxane) than the dicarboxylic acid. Synthetic equivalents include acid chlorides and acid bromides, as well as esters such as methyl and ethyl esters. Acid chlorides and acid bromides have the structure of Formula (III) wherein A is Cl or Br, respectively. They can be obtained commercially or synthesized by reaction of the dicarboxylic acid with a suitable reagent, such as thionyl chloride, thionyl bromide, phosphorous pentachloride, phosphorous pentabromide, and similar reagents. Esters can also be obtained commercially or by reaction of the dicarboxylic acid with a suitable alcohol, such as methanol or ethanol, under esterification conditions, for

example, in the presence of an acid or base catalyst. Exemplary esters include alkyl esters, wherein A is alkoxy, and haloalkyl esters, wherein A is haloalkoxy, most commonly fluoroalkoxy such as OCF_3 . A can also be haloaryloxy or haloalkaryloxy. A can also be other suitable leaving groups, such as triflate, mesylate, and the like. Examples of A include OH, Cl, Br, alkoxy, such as methoxy or ethoxy, OCF_3 , and triflate. Most commonly, an ester is employed, wherein A is alkoxy. The alkoxy is most often C_1 - C_4 alkoxy, such as methoxy or ethoxy.


When both instances of A are ethoxy and L_2 is a covalent bond, the compound of Formula (III) is diethyl oxalate.

The reaction of Reaction Scheme 1 can take place under any conditions suitable for amidation, that is, the formation of amides. In many cases, contacting the compounds of Formula (II) and Formula (III) with stirring at ambient temperature is sufficient. The compound of Formula (III) can be added in stoichiometric excess in order to facilitate high yields and to minimize the formation of oligomers and polymers. In such cases, excess compound of Formula (III) can be present in the product, and removal of such excess compound can be desirable in some circumstances. In some, a catalyst can be added to facilitate the reaction. The catalyst can be an acid or base, such as an Arrhenius acid or base. Most commonly, when a catalyst is used, it is an Arrhenius acid, typically a mineral acid. Suitable mineral acids include hydrochloric acid, hydrobromic acid, phosphoric acid, nitric acid, nitrous acid, and sulfuric acid. Alternatively, a strong base such as sodium methoxide, sodium borohydride, methyl lithium, or butyllithium can be used to facilitate the reaction. The strong base can deprotonate the primary amine in Formula (II), thereby increasing the reactivity of the compound of Formula (II) with the compound of Formula (III).

An inert solvent can be used in some cases. The inert solvent is typically one that does not react under amidation conditions. Exemplary inert solvents include ethers, ketones, and aromatic solvents, such as diethyl ether, acetone, methyl ethyl ketone, toluene, and benzene. The inert solvent is not required because the reaction can be conducted neat. Neat reactions are particularly convenient because it is not necessary to remove solvent in order to obtain pure product. However, byproducts can be produced during the reaction. Removal of such byproducts can be desirable in some circumstances. When removal of such byproducts is desirable, it can be accomplished by any suitable method. Suitable methods, which include column chromatography and distillation, can be selected depending on the nature of the byproduct.

In many cases, the reaction of Reaction Scheme 1 can be accomplished without the use of solvent and at ambient temperature, especially when the compound of Formula (III) is an acid chloride, acid bromide, or ester. In such cases, the compounds of Formulas (II) and (III) can be mixed and allowed to stir at ambient temperature for one to three days. For example, when diethyl oxylate is used as the compound of Formula (III), the ethyl oxylate can be added to the compound of Formula (II) without the use of solvent and the reaction can proceed to completion after stirring for two days at ambient temperature.

The product of the reaction between the compounds of Formulas (II) and (III) is an intermediate compound of Formula (IV).




(IV)

In the intermediate compound of Formula (IV), POLY, L₁ and L₂ come from the compounds of Formulas (II) and (III), and therefore are defined in the same manner as in the compounds of Formulas (II) and (III). Notably, while A in Formula (IV) is defined the same way as in the compound of Formula (III), the A in Formula (IV) need not be the same as either A in Formula (III). This is because it is possible for one or more A in Formula (III) to be hydrolyzed from its original form, for example, to hydroxy, during the reaction of Reaction Scheme 1, particularly if A in Formula (III) is chlorine or bromine. Thus, there can be more than one type of intermediate compound of Formula (IV) present after the reaction of compounds of Formulas (II) and (III).

The intermediate compound of Formula (IV) can further react with a compound of Formula (V) according to Reaction Scheme 2 to provide a compound of Formula (VI).

Reaction Scheme 2



In the compound of Formula (V), L₃ can be any suitable linking group, such as alkylene, aralkylene, alkenylene, alkynylene, or. When L₃ is alkylene, the alkylene can be any suitable alkylene, such as C₁ to C₁₆ alkylene, C₁ to C₁₂ alkylene, C₁ to C₈ alkylene, or C₁ to C₄ alkylene. When L₃ is aralkylene, the alkylene portion of the aralkylene can be any suitable alkylene, such as C₁ to C₁₆ alkylene, C₁ to C₁₂ alkylene, C₁ to C₈ alkylene, or C₁ to C₄ alkylene. The arylene portion can be any suitable arylene, such as phenylene, naphthylene, anthrylene, pyridylene, furanylene, pyrrolylene, or thionylene. When L₃ alkenylene, the alkenylene can be any suitable alkenylene, for example C₂ to C₁₆ alkenylene, C₂ to C₁₂ alkenylene, C₂ to C₈ alkenylene, or C₂ to C₄ alkenylene. When L₃ is alkynylene, the alkynylene can be any suitable alkynylene, for example C₂ to C₁₆ alkynylene, C₂ to C₁₂ alkynylene, C₂ to C₈ alkynylene, or C₂ to C₄ alkynylene. When L₃ is arylene, it can be any suitable arylene, such as the arylenes discussed above with respect to aralkylenes.

In some cases, L₃ is alkylene, such as C₁ to C₈ or C₁ to C₆ alkylene. In such cases, L₃ is often ethylene.

In the compound of Formula (V), L₄ can be any suitable linking group, such as alkylene, aralkylene, alkenylene, alkynylene, or arylene. When L₄ is alkylene, the alkylene can be any suitable alkylene, such as C₁ to C₂₂, alkylene, C₁ to C₁₆ alkylene, C₁ to C₁₂ alkylene, C₁ to C₈ alkylene, or C₁ to C₄ alkylene. When L₄ is aralkylene, the alkylene portion of the aralkylene can be any suitable alkylene, such as C₁ to C₂₂ alkylene, C₁ to C₁₆ alkylene, C₁ to C₁₂ alkylene, C₁ to C₈ alkylene, or C₁ to C₄ alkylene. The arylene portion of the aralkylene can be any suitable arylene, such as phenylene, naphthylene, anthrylene, pyridylene, furanylene, pyrrolylene, thionylene, or acridylene. When L₄ is alkenylene, the alkenylene can be any suitable alkenylene, for example C₂ to C₁₆ alkenylene, C₂ to C₁₂ alkenylene, C₂ to C₈ alkenylene, or C₂ to C₄ alkenylene. When L₄ is alkynylene, it can be any suitable alkynylene,

such as C₂ to C₁₆ alkynylene, C₂ to C₁₂ alkynylene, C₂ to C₈ alkynylene, or C₂ to C₄ alkynylene. When L₄ is arylenylene, it can be any suitable arylenylene, such as the arylenylenes discussed above with respect to aralkylenes.


In some cases, L₄ is alkylene, such as C₁ to C₂₂, C₁ to C₁₆, C₁ to C₁₂, C₁ to C₈, C₁ to C₄ alkylene. Particular examples are propylene and butylene.

R₃ in Formula (V) can be independently alkyl, hydroxy or alkoxy. At least one instance of R₃ is either hydroxy or alkoxy, because at least one hydroxy or alkoxy group is needed to allow the compound to bond with glass. When an R₃ is alkyl, it can be any suitable alkyl such as C₁ to C₁₆ alkyl, C₁ to C₁₂ alkyl, C₁ to C₈ alkyl, or C₁ to C₄ alkyl. When an R₃ is alkoxy, it can be any suitable alkoxy such as C₁ to C₁₆ alkoxy, C₁ to C₁₂ alkoxy, C₁ to C₈ alkoxy, or C₁ to C₄ alkoxy. Ethoxy and methoxy are common.

In many cases in the compound of Formula (V), L₃ and L₄ are alkylene and each R₃ is alkoxy. In such cases, the compound of Formula (V) is N-[(trialkoxysilyl)alkyl]alkylenediamine. An exemplary N-[(trialkoxysilyl)alkyl]alkylenediamine is N-[3-trimethoxysilyl]propyl]ethylenediamine.

In the compound of Formula (VI), POLY, L₁ and L₂ come from the compounds of Formulas (II) and (III), and are defined in the same manner as in those compounds. L₃ and L₄ come from the compound of Formula (V), and are defined in the same manner as in Formula (V).


The reaction between the compound of Formula (IV) and the compound of Formula (V) as shown in Reaction Scheme 2 can be carried out under the same amidation conditions discussed herein with reference to the reaction between the poly(diorganosiloxane) of Formula (II) and the compound of Formula (III) as shown in Reaction Scheme 1. The reaction can be selective in that the reaction can occur only at the primary amine of the compound of Formula (V), for example a N-[(trialkoxysilyl)alkyl]alkylenediamine such as N-[3-(trimethoxysilyl)propyl]ethylenediamine, to the exclusion of any reaction occurring at the secondary amine. Thus, a single product of Formula (VI) can be formed wherein the secondary amine of the compound of Formula (V) remains a secondary amine in Formula (VI), where it can be available for further reaction.



(VI)

Notably, the compound of Formula (VI) is a compound of Formula (I) wherein R₁ is H, R₂ is absent, and m is 0. If desired, the secondary amine in the compound of Formula (VI) can react with any suitable molecule, particularly molecules bearing one or more leaving groups, in order to form a tertiary amine or quaternary ammonium having, for example, one or more of an R₁ that is not H and an R₂ that is not absent.


When L₂ is a covalent bond, the compound of Formula (VI) is a compound of Formula (VIa).




(VIa)

R₁ and, when it is not absent, R₂, can be covalently bound to the amine by any suitable reaction. For example, a compound having an electrophilic group or a good leaving group can react with the amine by way of a nucleophilic substitution reaction.

When R₂ is not absent, then R₁ and R₂ can either be separate groups or they can be covalently bound to one another such that R₁ and R₂ together with the nitrogen atom to which they both attached combine to form a ring structure. In the former case, when R₁ and R₂ are both present as separate groups, the compound of Formula (VI) can be a compound of Formula (VIb), and the compound of Formula (VIa) can be a compound of Formula (VIc).



(VIb)



(VIc)

In the later case, when R₁ and R₂ are covalently bound to each other, R₁ and R₂ together can be alkylene, aralkylene, alkenylene, alkynylene, arylene, or any of the preceding substituted with hydroxy. In such situations, the charge, m, on the amine nitrogen is 1⁺. This charge can improve the water solubility or dispersibility of the compounds. Water solubility or dispersibility can be beneficial in that it can allow the compound to be present as solutions or dispersions in aqueous media.

When R₁ and R₂ together are alkylene or alkylene substituted with hydroxy, the alkylene can be any suitable alkylene, such as C₂ to C₁₆ alkylene, C₂ to C₁₂ alkylene, C₂ to C₈ alkylene, or C₂ to C₄ alkylene. C₃ alkylene is common, in which case R₁ and R₂ together with the nitrogen atom to which they are bound form a four membered ring. The hydroxy can be covalently bonded to any carbon atom in the ring. When the ring is a four membered ring R₁ and R₂ together form propylene and the hydroxy is typically bonded to the 2-carbon, i.e., the carbon atom that is not covalently bonded to the nitrogen atom.

When R₁ and R₂ together form aralkylene or aralkylene substituted with hydroxy, the alkylene portion of the aralkylene can be any suitable alkylene, such as C₁ to C₁₆ alkylene, C₁ to C₁₂ alkyl, C₁ to C₈ alkylene, or C₁ to C₄ alkylene. The arylene portion can be any suitable arylene, such as phenylene, naphthylene, anthrylene, pyridylene, furanylene, pyrrolylene, or thionylene. The hydroxy substituent, if present, can be at any location on the aralkylene, but is typically on the alkylene portion of the aralkylene.

When R₁ and R₂ together form alkenylene or alkenylene substituted with hydroxy, the alkenylene can be any suitable alkenylene, for example C₂ to C₁₆ alkenylene, C₂ to C₁₂ alkenylene, C₂ to C₈ alkenylene, or C₂ to C₄ alkenylene. When the hydroxy substituent is present it can be located at any suitable portion of the alkenylene, such as at a vinyl carbon, an allyl carbon, or another carbon.

When R₁ and R₂ together form alkynylene or alkynylene substituted with hydroxy, the alkynylene can be any suitable alkynylene, such as C₂ to C₁₆ alkynylene, C₂ to C₁₂ alkynylene, C₂ to C₈ alkynylene, or C₂ to C₄ alkynylene. When a hydroxy substituent is present, it can be located at any suitable carbon in the alkynylene, such as alpha to one or more alkynes, beta to one or more alkynes, or at any other carbon.


When R₁ and R₂ together form arylene or substituted arylene, the arylene can be any suitable arylene, such as the arylenes discussed above with respect to aralkylenes. When a hydroxy is present, it can be located at any suitable location on the arylene.

Compounds of Formula (VI) or (VIa) can be converted to compounds of Formula (I) or (Ia), respectively, wherein R₁ and R₂ are covalently bound together by any suitable chemical

reaction. Typical chemical reactions involve reaction of the secondary amine in Formula (VI) with a molecule having two electrophilic leaving groups. Examples of suitable leaving groups, which may be the same or different, include chloride, bromide, iodide, methylsulfonate, trifluoromethanesulfonate, tosylate, and mesylate. Other functional groups that can react with the secondary amine to form structures where R₁ and R₂ are covalently bound to one another include glycidyl groups.

When R₁ and R₂ are covalently bound together to form an alkylene, aralkylene, alkenylene, or alkynylene, the alkylene, aralkylene, alkenylene, or alkynylene can be substituted with hydroxy. Hydroxy substituents can occur when R₁ and R₂ together are formed by reaction of a compound of Formula (I) with an epoxide bearing a leaving group. When the epoxide contains an alkylene diradical, the resulting compound will be alkylene substituted with hydroxide; likewise when the epoxide contains an aralkylene, alkenylene or alkynylene diradical, the resulting compound will contain an aralkylene, alkenylene, or alkynylene, respectively, substituted with hydroxide. An example of such a reaction is illustrated in Reaction Scheme 3, which shows the reaction of a compound of Formula (VI) with an alkylene bearing epoxide of Formula (VII) to form a compound of Formula (VIII).

Reaction Scheme 3



In the compound of Formula (VII), ALK is alkylene, such as C₁ to C₂₂ alkylene, C₁ to C₁₈ alkylene, C₁ to C₈ alkylene, or C₁ to C₄ alkylene. When the compound of Formula (VII) is epichlorohydrin, ALK is methylene. Other examples of ALK include ethylene, propylene, and butylene.


In the compound of Formula (VIII), ALK has the same definition as in the compound of Formula (VII). Compounds of Formula (VIII) can be water soluble or dispersible, and are often water soluble.

In the compound of Formula (VII), LG is a leaving group. Any suitable leaving group can be used. Exemplary leaving groups include chloride, bromide, iodide, methylsulfonate,

trifluoromethanesulfonate, tosylate, and mesylate. When the compound of Formula (VII) is epichlorohydrin, LG is chloride.


In the compound of Formula (VIII), which is the product of Reaction Scheme 3, L₁, L₂, L₃, L₄, POLY, and R₃ are defined as discussed herein with reference to the compounds of Formula (II) through Formula (VII). The charge on the amine nitrogen, m, is 1⁺.

L₂ in the compound of Formula (VIII) can be a covalent bond. In such cases, the compound of Formula (VIII) is a compound of Formula (VIIIa).




(VIIIa)

ALK in the compound of Formula (VIIIa) can be methylene. In such cases, the compound of Formula (VIIIa) is a compound of Formula (VIIIb).



(VIIIb)

L₁ in the compound of Formula (VIIIb) can be alkylene, for example, propylene. In such cases the compound of Formula (VIIIb) is a compound of Formula (VIIIc).




(VIIIc)

Returning to the compounds of Formulas (I) and (Ia), when R₁ and R₂ are not covalently bound to one another, R₁ can be H, CH₂CH(OH)R^a-Si(R₅)₃ or R^d-R^e, and R₂ can be absent, H, CH₂CH(OH)R^a-Si(R₅)₃ or R^d-R^e. When R₁ is H and R₂ is absent, the amine is a secondary amine having a charge, m, of 0. Examples of such a compound include the compounds of Formula (VI) and (VIa). When R₁ is not H and R₂ is neither absent nor H, then the amine is a tertiary amine having a charge, m, of 1⁺. Examples of such compounds include compounds of Formulas (VIb) and (VIc). Similarly if both R₁ and R₂ are present such that one is H and

one is not H, the amine is a protonated tertiary amine and bears a charge, m , of 1^+ . As discussed above, this charge can be beneficial because it often increases the water solubility or dispersibility of the compound of Formula (I) or (Ia).


When R_1 is $\text{CH}_2\text{CH}(\text{OH})\text{R}^a\text{-Si}(\text{R}_5)_3$, R^a is alkylene or R^bOR^c . A compound of Formula (I) or Formula (Ia) bearing this type of R_1 can be formed by reaction of the secondary amine of Formula (VI) with a compound of Formula (IX).



R^a in the compound of Formula (IX) can be alkylene. In such cases, R^a can be C_1 or greater, C_2 or greater, C_3 or greater, C_4 or greater, C_6 or greater, C_8 or greater, or C_{10} or greater. R^a can also be C_{22} or smaller, C_{16} or smaller, C_{12} or smaller, C_8 or smaller, or C_4 or smaller. More commonly, R^a is $\text{R}^b\text{-O-R}^c$. In such cases, each of R^b and R^c can independently be alkylene, wherein the alkylene is C_1 or greater, C_2 or greater, C_3 or greater, C_4 or greater, C_6 or greater, C_8 or greater, or C_{10} or greater. R^b and R^c can also independently be C_{22} or smaller, C_{16} or smaller, C_{12} or smaller, C_8 or smaller, or C_4 or smaller.

Each R_5 can independently be alkyl, alkoxy, or hydroxy, with the proviso that at least one R_5 is alkoxy or hydroxy. When R_5 is alkyl, it can be C_1 or greater, C_2 or greater, C_3 or greater, C_4 or greater, C_6 or greater, C_8 or greater, or C_{10} or greater. The alkyl can also be C_{22} or smaller, C_{16} or smaller, C_{12} or smaller, C_8 or smaller, or C_4 or smaller. Most commonly the alkyl is ethyl or methyl. When R_5 is alkoxy, the alkyl portion of the alkoxy can be C_1 or greater, C_2 or greater, C_3 or greater, C_4 or greater, C_6 or greater, C_8 or greater, or C_{10} or greater. The alkyl portion of the alkoxy can be C_{22} or smaller, C_{16} or smaller, C_{12} or smaller, C_8 or smaller, or C_4 or smaller. Most commonly, the alkyl portion of the alkoxy is ethyl or methyl. In such cases, the alkoxy is ethoxy or methoxy.

A specific example of an R_1 of this type is $\text{CH}_2\text{CH}(\text{OH})(\text{CH}_2)\text{O}(\text{CH}_2)_3\text{Si}(\text{R}_5)_3$. In this example, R^a is R^bOR^c , R^b is methylene and R^c is propylene. An even more specific example is $\text{CH}_2\text{CH}(\text{OH})(\text{CH}_2)\text{O}(\text{CH}_2)_3\text{Si}(\text{OMe})_3$. In this example, R^a is R^bOR^c , R^b is methylene, R^c is propylene, and each R_5 is methoxy. A compound of Formula (I) or Formula (Ia) bearing this type of R_1 can be formed by reaction of the secondary amine of Formula (Ia) bearing this type of R_1 can be formed by reaction of the secondary amine of Formula (VI) with a compound of Formula (IXa).



(IXa)

R_1 can also be R^d-R^e . In such cases, R^d is alkylene. The alkylene can be C_1 or greater, C_2 or greater, C_3 or greater, C_4 or greater, C_6 or greater, C_8 or greater, or C_{10} or greater. It can also be C_{22} or smaller, C_{16} or smaller, C_{12} or smaller, C_8 or smaller, or C_4 or smaller.

5 Examples of R^d include ethylene, n-propylene, and n-butylene.

R^e is $Si(R_5)_3$, SO_3H or a salt thereof, or CO_2H or a salt thereof wherein R_5 is defined as above. When a salt is used, it can be any suitable salt. Suitable salts include salts of alkaline metals, salts of alkaline earth metals, and ammonium salts. Common alkaline metals include sodium and potassium. Common alkaline earth metals include magnesium and calcium.

10 Salts of ammonium and alkaline metals are most common.


A compound Formula (I) or Formula (Ia) bearing this type of R_1 group wherein R^e is SO_3H or a salt hereof can be formed by reaction of the secondary amine of Formula (VI) with a sulfone, for example, a compound of Formula (X). This reaction can be carried out by stirring the amine of Formula (VI) with the compound of Formula (X) at ambient
15 temperature. Moderate heating, for example, to $60^\circ C$, can be applied if necessary.



(X)

In the compound of Formula (X), R^d is defined as discussed above with respect to R_1 .

20 A specific example of a compound of Formula (X) wherein R^d is propylene is the compound of Formula (Xa).




(Xa)

A compound of Formula (I) or Formula (Ia) bearing this type of R_1 group wherein R^e is a CO_2H or a salt thereof can be formed using lactones that correspond to the sulfones of Formulas (X) or (Xa). Such lactones can be, for example, a compound of Formula (Xb) or Formula (Xc).




(Xb)



(Xc)


A compound of Formula (I) or Formula (Ia) bearing this type of R_1 group wherein R^e is a $Si(R_5)_3$ can be formed by reaction of the secondary amine of Formula (VI) with a compound of Formula (XI).



(XI)


In the compound of Formula (XI), LG' is a leaving group. Any suitable leaving group can be used. Exemplary leaving groups include chloride, bromide, iodide, methylsulfonate, trifluoromethanesulfonate, tosylate, and mesylate.

An example of a compound of Formula (XI) wherein R^d is propylene and LG is chloride is the compound of Formula (XIa).



(XIa)


When R_1 is not H, reaction of the compound of Formula (VI) to covalently bond to R_1 converts the secondary amine of Formula (VI) to a tertiary amine, as shown in the compound of Formula (XII).



(XII)


In the compound of Formula (XII), POLY, L_1 , L_2 , L_3 , L_4 , R_1 , R_2 , and R_3 are defined as above with respect to Formula (I), except that R_1 is not H and R_2 is absent.

An example of a compound of Formula (XII) that can be formed from the compound of Formula (Ia), that is, wherein L_2 is a covalent bond, is the compound of Formula (XIIa).



(XIIa)


A compound of Formula (XII) or Formula (XIIa) can be used without further chemical modification. One example of such a compound is the compound of Formula (XIII). In the
 5 compound of Formula (XIII), R₁ is CH₂CH(OH)R^aSi(R₅)₃



(XIII)


In some compounds of Formula (XIII), L₁ and L₃ are independently alkylene.

10 When L₃ is ethylene, the compound of Formula (XIII) is a compound of Formula (XIIIa).




(XIIIa)

When L₁ in the compound of Formula (XIIIa) is propylene, the compound of Formula (XIIIa) is a compound of Formula (XIIIb).




(XIIIb)

In the compound of Formula (XIIIb), R^a can be $\text{R}^b\text{-O-R}^c$, in which case the compound of Formula (XIIIb) is the compound of Formula (XIIIc).



(XIIIc)

When L_4 is propylene, R^b is methylene, and R^c is propylene, then the compound of Formula (XIIIc) is the compound of Formula (XIIId).



(XIIId)

In certain cases of any of the compounds of Formulas (XIII), (XIIIa), (XIIIb), (XIIIc), and (XIIId), each R_3 can be alkoxy, such as methoxy or ethoxy.


The tertiary amine in the compound of any of Formulas (XIII), (XIIIa), (XIIIb), (XIIIc), can be further reacted to form a compound of Formula (I) or (Ia) wherein R_2 is not absent.

For example, a compound of Formula (XII) or (XIIa) can be protonated by reaction with an

acid, such as hydrochloric acid, sulfuric acid, nitric acid, phosphoric acid, acetic acid, and the like, to form a compound of Formula (I) or Formula (Ia) wherein R₂ is H.

Compounds of Formula (I) or (Ia) wherein R₂ is neither absent or H can also be formed. For example, a compound of Formula (XII), Formula (XIIa), or any of the compounds of Formulas (XIII), (XIIIa), (XIIIb), (XIIIc), and (XIId), can react with a compound of any of Formulas (IX), (IXa), (X), (Xa), (XI), or (XIa) to form a covalent bond to an R₂ group that is derived from which ever compound of Formulas (IX), (IXa), (X), (Xa), (XI), or (XIa) is used. In this case, the charge on the amine nitrogen, m, is 1⁺.


Exemplary compounds wherein R₂ is neither H nor absent include compounds of Formulas (XIV).



(XIV)


In the compound of Formula (XIV), R₁ is CH₂CH(OH)(CH₂)₃Si(R₅)₃, and R₂ is R^d-R^e. Compounds of Formula (XIV) can be formed by reacting any compound of Formula (XIII) with any compound of Formulas (X), (Xa), (XI) or (XIa) using the same reaction conditions described above with respect to reactions for forming compounds of Formula (XIII)

When L₁ in the compound of Formula (XIVa) is propylene, the compound of Formula (XIVa) is a compound of Formula (XIVb). Compounds of Formula (XIVb) can be formed by reacting compounds of Formula (XIIIb) with compounds of Formulas (X), (Xa), (XI) or (XIa) using the same reaction conditions described above with respect to reactions for forming compounds of Formula (XIII).




(XIVa)

In the compound of Formula (XIVa), R^a can be R^b-O-R^c , in which case the compound of Formula (XIVa) is the compound of Formula (XIVb). Compounds of Formula (XIVb) can be formed by reacting compounds of Formula (XIIIb) with compounds of Formulas (X), (Xa), (XI), or (XIa) using the same reaction conditions described above with respect to reactions for forming compounds of Formula (XIII).




(XIVb)

When R^e in compound (XIVb) is SO_3H or a salt thereof, $Si(R_5)_3$, the compound of Formula (XIVb) is a compound of Formula (XV). Such compounds can be formed by the reaction of a compound of Formula (XIIIc) with compounds of Formulas (X) or (Xa) using the same reaction conditions described above with respect to reactions for forming compounds of Formula (XIII).




(XV)

In some compounds of Formula (XV), R^a is R^bOR^c . Such compounds have a structure of Formula (XVa).




(XVa)

An exemplary compound of Formula (XVa) wherein R^b is methylene, R^b is ethylene, R^c and R^d are both propylene, L_4 is butylene, and each instance of R_3 and R_3 is OMe. Such compounds have a structure of Formula (XVb).




When R^e in compound (XIVb) is $\text{Si}(R_5)_3$, the compound of Formula (XIVb) is a compound of Formula (XVI). Such compounds can be formed by the reaction of a compound of Formula (XIIIc) with compounds of Formulas (XI) or (XIa) using the same reaction conditions described above with respect to reactions for forming compounds of


10 Formula (XIII).



In some compounds of Formula (XVI), R^a is $R^b\text{OR}^c$. Such compounds have a structure of Formula (XVIa).



An exemplary compound of Formula (XVIa) wherein R^b is methylene, R^c and R^d are both propylene, L_4 is propylene, and each R_3 and R_5 is methoxy. Such compounds have a structure of Formula (XVIb).



(XVIb)

Modified poly(diorganosiloxanes) such as those described herein can have a variety of uses. For example, the compounds can be useful to form modified surfaces that repel water, as evidenced by an increased contact angle of water with the modified surfaces. In addition, the compounds can be ink repellent. Thus, the compounds can modify surfaces to resist soiling and weathering. The surfaces that can be modified include glass and ceramic surfaces. Such surfaces can be modified by way of a covalent bond between the modified poly(diorganosiloxane) and the glass or ceramic surface.

One or more modified poly(diorganosiloxanes) can be present in a composition. The composition can be an aqueous solution or aqueous dispersion. An alcohol, such as one or more of methanol, ethanol, and isopropanol, can also be included. The alcohol can increase the solubility or dispersibility of the compounds. Importantly, an alcohol is not required because the compounds often have sufficient water solubility or dispersibility without the addition of alcohol.

The composition can additionally comprise one or more surfactants. Such surfactants can be ionic surfactants or non-ionic surfactants. Ionic surfactants can be anionic surfactants, cationic surfactants, or zwitterionic surfactants. Exemplary surfactants include stearate salt, sodium lauryl sulfate, ammonium lauryl sulfate, sodium laureth sulfate, polysorbate-20, polysorbate-80, lauryl glucoside, laureth glucoside, disodium lauryl sulfosuccinate, cocamidopropyl betaine, and alpha-olefin sulfonate. In some cases, the one or more surfactants are at least two surfactants. Such surfactants can be particularly useful when the composition is a cleaning composition. In use, such cleaning composition can be applied to a surface, such as a glass surface, and then wiped off. The modified poly(diorganosiloxane) can remain bound to the glass surface by way of the siloxane groups.

Other suitable ingredients can also be included in the composition. Examples of ingredients that can be suitable, depending on the intended use, include fragrance, colorant, cleaning agent, tonicity adjusting agent, and pH adjusting agent.


The glass article can have one or more modified poly(diorganosiloxanes) according to this description affixed thereto. Exemplary glass articles can include slides, windows, billboards, walls, lenses, such as eyeglass lenses, prisms, mirrors, and cook tops.

Automobiles can comprise at least one glass element. A compound as described herein can be affixed to one or more of the at least one glass elements.

Listing of Exemplary Embodiments

Particular embodiments are discussed below to assist in understanding the invention, and are not to be construed as limiting. None of the particular features discussed in these embodiments is required, unless otherwise specified. The embodiments discussed below are illustrative; other embodiments are also envisioned.

Embodiment 1 is a compound having the chemical structure of Formula (I)



(I)

In Formula (I):

POLY is a poly(diorganosiloxane);

L₁ and L₂ are independently a covalent bond, alkylene, aralkylene, alkenylene, alkynylene, or arylene;

L₃ and L₄ are independently alkylene, aralkylene, alkenylene, alkynylene, or arylene;

m is independently represents the charge on the N atom, which is 0 or 1⁺;

and either:

R₁ is H, CH₂CH(OH)R^a-Si(R₅)₃, or R^d-R^e, and

R₂ is absent, H, CH₂CH(OH)R^a-Si(R₅)₃, or R^d-R^e;

or

R₁ and R₂ are covalently bound to one another, and are together alkyl, aralkyl, alkenyl, alkynyl, aryl, or any of the preceding substituted with hydroxy;

R₃ is independently hydroxy, alkoxy, or alkyl, provided that at least one R₃ is either hydroxy or alkoxy.

R^a is alkylene or R^b-O-R^c,

R^b is alkylene,

R^c is alkylene,

R^d is alkylene,

R^e is Si(R₅)₃, SO₃H or a salt thereof, or CO₂H or a salt thereof,

R₅ is

and R₅ is alkyl, alkoxy, or hydroxy, with the proviso that at least one R₅ is alkoxy or hydroxy.

Embodiment 2 is a compound of embodiment 1, wherein poly(diorganosiloxane) is a poly(dialkylsiloxane), poly(diarylsiloxane), or Poly(alkyl aryl siloxane).

Embodiment 3 is a compound of any of the preceding embodiments, wherein the poly(dialkylsiloxane) is a poly(di C₁ to C₂₂ alkylsiloxane).

Embodiment 4 is a compound of any of the preceding embodiments, wherein the poly(dialkylsiloxane) is a poly(di C₁ to C₄ alkylsiloxane).

Embodiment 5 is a compound of any of the preceding embodiments, wherein the poly(diorganosiloxane) is PDMS.

Embodiment 6 is a compound of any of embodiments 1 or 2, wherein the poly(diarylsiloxane) is a poly(diphenylsiloxane).

Embodiment 7 is a compound of any of the preceding embodiments, wherein the poly(diorganosiloxane) has a number average degree of polymerization that is greater than 10.

Embodiment 8 is a compound of any of the preceding embodiments, wherein the poly(diorganosiloxane) has a number average degree of polymerization that is greater than 15.

Embodiment 9 is a compound of any of the preceding embodiments, wherein the poly(diorganosiloxane) has a number average degree of polymerization that is greater than 20.

5 Embodiment 10 is a compound of any of the preceding embodiments, wherein the poly(diorganosiloxane) has a number average degree of polymerization that is greater than 30.

Embodiment 11 is a compound of any of the preceding embodiments, wherein the poly(diorganosiloxane) has a number average degree of polymerization that is greater than 40.

10 Embodiment 12 is a compound of any of the preceding embodiments, wherein the poly(diorganosiloxane) has a number average degree of polymerization that is greater than 50.

15 Embodiment 13 is a compound of any of the preceding embodiments, wherein the poly(diorganosiloxane) has a number average degree of polymerization that is no greater than 300.

Embodiment 14 is a compound of any of the preceding embodiments, wherein the poly(diorganosiloxane) has a number average degree of polymerization that is no greater than 200.

20 Embodiment 15 is a compound of any of the preceding embodiments, wherein the poly(diorganosiloxane) has a number average degree of polymerization that is no greater than 100.

Embodiment 16 is a compound of any of the preceding embodiments, wherein the poly(diorganosiloxane) has a number average degree of polymerization that is no greater than 85.

25 Embodiment 17 is a compound of any of the preceding embodiments, wherein the poly(diorganosiloxane) has a number average degree of polymerization that is no greater than 75.

Embodiment 18 is a compound of any of the preceding embodiments, wherein L₁ is a covalent bond or alkylene.

30 Embodiment 19 is a compound of embodiment 18, wherein L₁ is C₁ to C₁₆ alkylene.

Embodiment 20 is a compound of embodiment 19, wherein L₁ propylene.

Embodiment 21 is a compound of any of the preceding embodiments, wherein L₂ is a covalent bond or alkylene.

Embodiment 22 is a compound of any of the preceding embodiments, wherein L₂ is a covalent bond.

Embodiment 23 is a compound of any of embodiments 1-21, wherein L₂ is alkylene.

Embodiment 24 is a compound of embodiment 23, wherein the alkylene is C₁ to C₂₂ alkylene.

Embodiment 25 is a compound of embodiment 24, wherein the alkylene is C₁ to C₄ alkylene.

Embodiment 26 is a compound of any of the preceding embodiments, wherein L₃ is alkylene or alkenylene.

Embodiment 27 is a compound of embodiment 26, wherein L₃ is alkylene.

Embodiment 28 is a compound of embodiment 27, wherein L₃ is C₁ to C₁₆ alkylene.

Embodiment 29 is a compound of embodiment 28, wherein L₃ is C₁ to C₄ alkylene.

Embodiment 30 is a compound of embodiment 29, wherein L₃ is ethylene.

Embodiment 31 is a compound of any of the preceding embodiments, wherein L₄ is alkylene or alkenylene.


Embodiment 32 is a compound of embodiment 31, wherein L₄ is alkylene.

Embodiment 33 is a compound of embodiment 32, wherein L₄ is C₁ to C₂₂ alkylene.

Embodiment 34 is a compound of embodiment 33, wherein L₄ is C₁ to C₄ alkylene.

Embodiment 35 is a compound of embodiment 34, wherein L₄ is propylene.

Embodiment 36 is a compound any of the preceding embodiments, wherein the compound has the structure of Formula (VI)



Embodiment 37 is a compound of any of embodiments 1-35, wherein R₁ and R₂ are covalently bound to one another.


Embodiment 38 is a compound of embodiment 37, wherein R₁ and R₂ together are C₁ to C₄ alkylene or C₁ to C₄ alkylene substituted with hydroxy.

Embodiment 39 is a compound of embodiment 38, wherein R₁ and R₂ are together are C₁ to C₄ alkylene substituted with hydroxy.

5 Embodiment 40 is a compound of embodiment 39, wherein the alkylene or substituted alkylene is propylene or propylene substituted with hydroxy.

Embodiment 41 is a compound of embodiment 40, wherein the propylene substituted with hydroxy is substituted on the carbon that is not bound to a nitrogen atom.

10 Embodiment 42 is a compound of embodiment 37, wherein the compound has a structure of Formula (VIII)



(VIII)

wherein ALK is alkylene.

Embodiment 43 is a compound of embodiment 42, wherein ALK is C₁ to C₈ alkylene.

15 Embodiment 44 is a compound of embodiment 43, wherein ALK is C₁ to C₄ alkylene.

Embodiment 45 is a compound of embodiment 44, wherein ALK is methylene.

Embodiment 46 is a compound of any of embodiments 1-35, wherein

R₁ is H, CH₂CH(OH)R^a-Si(R₅)₃, or R^d-R^e, and

R₂ is absent, H, CH₂CH(OH)R^a-Si(R₅)₃, or R^d-R^e.

20 Embodiment 47 is a compound of embodiment 46, wherein R₁ is H.

Embodiment 48 is a compound of any of embodiments 1-46, wherein R₁ is CH₂CH(OH)R^a-Si(R₅)₃.

Embodiment 49 is a compound of embodiment 48, wherein R^a is alkylene.

Embodiment 50 is a compound of embodiment 49, wherein R^a is R^b-O-R^c.

25 Embodiment 51 is a compound of embodiment 50, wherein R^b is C₁ to C₈ alkylene.

Embodiment 52 is a compound of embodiment 51, wherein R^b is methylene.

Embodiment 53 is a compound of any of embodiments 49-52, wherein R^c is C₁ to C₈ alkylene.

Embodiment 54 is a compound of any of embodiments 49- 53, wherein R^c is propylene.

Embodiment 55 is a compound of embodiment 49-54, wherein each R₃ is alkoxy.

5 Embodiment 56 is a compound of embodiment 55, wherein each alkoxy is methoxy or ethoxy.

Embodiment 57 is a compound of any of embodiments 1-46, wherein R₁ is R^d-R^e.

Embodiment 58 is a compound of embodiment 57, wherein R^d is C₁ to C₈ alkylene.

Embodiment 59 is a compound of embodiment 58, wherein R^d is propylene.

10 Embodiment 60 is a compound of any of embodiments 57-59, wherein R^e is S(O)₃H or a salt thereof.

Embodiment 61 is a compound of any of embodiments 57-59, wherein R^e is Si(R₅)₃.

Embodiment 62 is a compound of embodiment 61, wherein R₅ is alkoxy.

Embodiment 63 is a compound of embodiments 62, wherein the alkoxy is methoxy or ethoxy.

15 Embodiment 64 is a compound of any of embodiments 57-59, wherein R^e is CO₂H or a salt thereof.

Embodiment 65 is a compound of any preceding embodiment, wherein R₂ is absent

Embodiment 66 is a compound of any of embodiments 1-64, wherein R₂ is H.

20 Embodiment 67 is a compound of any of embodiments 1-64, wherein R₂ is CH₂CH(OH)R^a-Si(R₅)₃.

Embodiment 68 is a compound of embodiment 67, wherein R^a is alkylene.

Embodiment 69 is a compound of embodiment 68, wherein R^a is R^b-O-R^c.

Embodiment 70 is a compound of embodiment 69, wherein R^b is C₁ to C₈ alkylene.

Embodiment 71 is a compound of embodiment 70, wherein at least one R^b methylene.

25 Embodiment 72 is a compound of any of embodiments 69-71, wherein R^c is C₁ to C₈ alkylene.

Embodiment 73 is a compound of any of embodiments 69-72, wherein R^c is propylene.

Embodiment 74 is a compound of any of embodiments 67-73, wherein each R₅ is alkoxy.

Embodiment 75 is a compound of embodiment 74, wherein each alkoxy is methoxy or ethoxy.

Embodiment 76 is a compound of any of embodiments 1-64, wherein R₂ is R^d-R^e.

5 Embodiment 77 is a compound of embodiment 76, wherein R^d is C₁ to C₈ alkylene.

Embodiment 78 is a compound of embodiment 77, wherein R^d is propylene.

Embodiment 79 is a compound of any of embodiments 76-78, wherein R^e is S(O)₃H or a salt thereof.


Embodiment 80 is a compound of any of embodiments 76-78, wherein R^e is Si(R₅)₃.

10 Embodiment 81 is a compound of embodiment 80, wherein R₅ is alkoxy.

Embodiment 82 is a compound of embodiment 81, wherein the alkoxy is methoxy or ethoxy.


Embodiment 83 is a compound of any of embodiments 76-78 wherein R_e is CO₂H or a salt thereof

15 Embodiment 84 is a compound of any of embodiments 1-64, wherein the compound has a structure of Formula (XII)




(XII).

20 Embodiment 85 is a compound of any of embodiments 1-64 or 67-83, wherein the compound has a structure of Formula (XIIa)




(XIIa).

Embodiment 86 is a compound of any of embodiments 1-64 or 67-84, wherein the compound has a structure of Formula (XIII)




(XIII).

- 5 Embodiment 87 is a compound of embodiment 86, wherein the compound has a structure of Formula (XIIIa)




(XIIIa).

- 10 Embodiment 88 is a compound of embodiment 87, wherein the compound has a structure of Formula (XIIIb)




(XIIIb).

- 15 Embodiment 89 is a compound of embodiment 88, wherein the compound has a structure of Formula (XIIIc).




(XIIIc).

Embodiment 90 is a compound of embodiment 89, wherein the compound has a structure of Formula (XIIIId)



(XIIIId).


Embodiment 91 is a compound of any of embodiments 1-64 or 67-85, wherein the compound has a structure of Formula (XIV)



(XIV).

Embodiment 92 is a compound of embodiment 85, wherein L4 is alkylene.


Embodiment 93 is a compound of any of embodiments 1-35, wherein the compound has a structure of Formula (XIVb)



(XIVb).

Embodiment 94 is a compound of embodiment 85, wherein the compound has a structure of Formula (XIVc)


5



(XIVc).


Embodiment 95 is a compound of any of embodiments 1-64 or 67-94, wherein the compound has a structure of Formula (XV)

10




(XV).

Embodiment 96 is a compound of embodiment 95, wherein the compound has a structure of Formula (XVa)




(XVa).

Embodiment 97 is a compound of embodiment 96, wherein the compound has a structure of Formula (XVb)




(XVb).

Embodiment 98 is a compound of embodiment 85, wherein the compound has a structure of Formula (XVI)




(XVI).

Embodiment 99 is a compound of embodiment 98, wherein the compound has a structure of Formula (XVIa)



(XVIa).

Embodiment 100 is a compound of embodiment 99, wherein the compound has a structure of Formula (XVIb)



(XVIb).

Embodiment 101 is a compound of any of embodiments 84-99, wherein each R₃ is hydroxy or alkoxy.

Embodiment 102 is a compound of embodiments 101, wherein each R₃ is alkoxy or hydroxy.

Embodiment 103 is a compound of embodiments 102, wherein each R₃ is alkoxy.

Embodiment 104 is a compound of any of embodiments 102-103, wherein the alkoxy is methoxy or ethoxy.

Embodiment 105 is a composition comprising an aqueous solution of a compound of any of the preceding embodiments.

Embodiment 106 is a composition comprising an aqueous dispersion of a compound of any of embodiments 1-104.

Embodiment 107 is a composition of any of embodiments 105-106, further comprising an alcohol.

Embodiment 108 is the composition of embodiment 107, wherein the alcohol is selected from methanol, ethanol, and isopropanol.

Embodiment 109 is a composition of any of embodiments 105-108, further comprising one or more surfactants.

Embodiment 110 is a composition of embodiment 109, wherein the one or more surfactants include at least one of a stearate salt, sodium lauryl sulfate, ammonium lauryl sulfate, sodium laureth sulfate, polysorbate-20, polysorbate-80, lauryl glucoside, laureth glucoside, disodium lauryl sulfosuccinate, cocamidopropyl betaine, and alpha-olefin sulfonate.

5 Embodiment 111 is a composition of any of embodiments 109-110, wherein the one or more surfactants comprise at least two surfactants.

Embodiment 112 is the composition of any of embodiments 105-111, further comprising one or more of fragrance, colorant, cleaning agent, tonicity adjusting agent, and pH adjusting agent.

10 Embodiment 113 is an article having a compound of any of embodiments 1-104 affixed thereto.

Embodiment 114 is an article of embodiment 113, wherein the article comprises glass.

Embodiment 115 is an article of embodiment 114, wherein the glass is a slide, a window, a billboard, a wall, a lens, a prism, a mirror, or a cooktop.

15 Embodiment 116 is an automobile comprising at least one glass element, wherein a compound of any of embodiments 1-104 is affixed to one or more of the at least one glass element.

EXAMPLES

20 Materials List

N-[3-(trimethoxysilyl)propyl]ethylenediamine, 96%: Alfa Aesar (Ward Hill, MA, USA)

Glycidol trimethoxy silane: synthesized

Diethyl oxalate, 99%: Alfa Aesar (Ward Hill, MA, USA)

Zn(CF₃SO₃)₂, 98%: Alfa Aesar (Ward Hill, MA, USA)

25 1,3-propane sulfone, 99%: Alfa Aesar (Ward Hill, MA, USA)

Epichlorohydrin, 99%: Alfa Aesar (Ward Hill, MA, USA)

(3-chloropropyl)triethoxysilane: TCI (Portland, OR, USA)

Amine-terminated polydimethylsiloxane (M_n of 5104): Gelest (Maidstone, Kent, UK)

Ethyl octadecanedioate: Sigma-Aldrich (St. Louis, MO, USA)


30 Sodium methoxide (25 wt % in methanol): Sigma-Aldrich (St. Louis, MO, USA)

Methanesulfonyl chloride, 98%: Alfa Aesar (Ward Hill, MA, USA)

Preparatory Example 1

Di-amine terminated PDMS (1020.8 g, number average molecular weight 5104 g/mol)) was added to a 2L flask with a mechanical stirrer. Diethyloxalate (118.1 g) was added dropwise over 30 minutes. When the reaction mixture appeared homogenous, stirring was stopped and the reaction was allowed to rest for one day. Distillation of methanol and excess diethyloxalate gave the product of Reaction Scheme 3 as a clear liquid.


Reaction Scheme 3



Example 1


The product of Preparatory Example 1 (212 g) was mixed with N-[3-(trimethoxysilyl)propyl]ethylenediamine (19.45 g) and stirred at ambient temperature overnight. Evaporation of methanol provided a compound of Formula (XVI) as shown by Reaction Scheme 4.

Reaction Scheme 4




Example 2

The compound of Formula (XVI) (56.6 g), glycidyl trimethoxysilane (4.9 g), and $\text{Zn}(\text{CF}_3\text{SO}_3)_2$ (0.02 g) were stirred at room temperature for 48 hours, providing a compound of Formula (XVII) as shown in Reaction Scheme 5.

Reaction Scheme 5**Example 3**


- 5 The compound of Formula (XVII) (12.26 g) was mixed with 1, 3-propanesulfone (2.49 g) and stirred for 48 hours, providing a compound of Formula (XVIII)



10


Example 4

The compound of Formula (XVII) (33.8 g) was mixed with (3-chloropropyl)triethoxysilane (4.92 g) and stirred at 60° C for 48 hours, providing the product of Formula (XIX).



Example 5


The product of Preparatory Example 1 (16.2 g) was mixed with N-[3-(trimethoxysilyl)propyl]ethylenediamine (1.44 g) at 50° C for five hours and then allowed to cool to ambient temperature. Epichlorohydrin (0.6 g) was added and the mixture was stirred for two days at ambient temperature, providing the compound of Formula (XX).



Preparatory Example 1 and Examples 1-5 demonstrate that modified poly(diorganosiloxane) compounds can be synthesized under mild conditions. The reactions can be carried out at ambient temperatures or under mild heating.

Comparative Example 1

Ethyl heptadecanoate (26.8 g), N-[3-(trimethoxysilyl)propyl]ethylenediamine (19 g), and sodium methoxide (0.86 g, 25% in methanol) were stirred in toluene (45 g) at 50° C for 15 hours. The reaction mixture was cooled to room temperature. Epichlorohydrin (3.93 g) was added and stirred for two days. Evaporation of solvent provided the compound of Formula (XXI).



Examples 6-9 and Comparative Example 2


Solutions were formed of 0.1 g of one of the compounds of Formula (XVII), (XVIII), (XIX), (XX), or (XXI), 1 g of isopropyl alcohol, 9.2 g of reverse osmosis water, and sufficient concentrated hydrochloric acid to reach a pH of 2. Each solution was wiped onto a cleaned glass microscope slide with a clean polyester cloth to coat the slide. The coated slides were cured either by allowing the slide to sit at ambient temperature until completely dry (RT curing), or heating to 120° C for 15 minutes (heat curing). The contact angles, θ_A and θ_R , of water and hexadecane were measured. Ink repellency was tested by drawing a line with a felt tipped marker and observing any discontinuity of the line. The results are summarized in Table 1.

Example	Compound	Curing	Water		Hexadecane		Ink Repellancy
			θ_A	θ_R	θ_A	θ_R	
6	(XVII)	RT	100	58	40	30	Discontinued line and dots
		Heat	105	82	38	31	Discontinued line and dots
7	(XVIII)	RT	105	79	37	28	Discontinued line and dots
		Heat	101	83	35	29	Discontinued line and dots
8	(XIX)	RT	103	82	37	30	Discontinued line and dots
		Heat	106	86	36	32	Discontinued line and dots
9	(XX)	RT	110	78	41	28	Discontinued dots
		Heat	104	75	36	31	Discontinued dots
Comparative 2	(XXI)	RT	76	34	16	11	Solid line with small patches
		Heat	89	47	19	10	Solid line with small patches

The results shown in Table 1 demonstrate that the modified poly(diorganosiloxane) compounds provide a water and ink repellent coating. By comparison, a similar compound having a long chain alkane instead of a poly(diorganosiloxane) (Compound XXI, Comparative Examples 1 and 2) does not provide any of these advantages.

What is claimed is:

1 A compound having the chemical structure of Formula (I)



(I)

5 wherein:

POLY is a poly(diorganosiloxane);

L₁ and L₂ are independently a covalent bond, alkylene, aralkylene, alkenylene, alkynylene, or arylene;

L₃ and L₄ are independently alkylene, aralkylene, alkenylene, alkynylene, or arylene;

10 m is independently represents the charge on the N atom, which is 0 or 1⁺;

and either:

R₁ is H, CH₂CH(OH)R^a-Si(R₅)₃, or R^d-R^e, and

R₂ is absent, H, CH₂CH(OH)R^a-Si(R₅)₃, or R^d-R^e;

or

15 R₁ and R₂ are covalently bound to one another, and are together alkylene, aralkylene, alkenylene, alkynylene, arylene, or any of the preceding substituted with hydroxy;

R₃ is independently hydroxy, alkoxy, or alkyl, provided that at least one R₃ is either hydroxy or alkoxy.

R^a is alkylene or R^b-O-R^c,

20 R^b is alkylene,


R^c is alkylene,

R^d is alkylene,

R^e is Si(R₅)₃, SO₃H or a salt thereof, or CO₂H or a salt thereof,


and R₅ is alkyl, alkoxy, or hydroxy, with the proviso that at least one R₅ is alkoxy or
25 hydroxyl.

2. A compound of claim 1, wherein the poly(dialkylsiloxane) is a poly(di C₁ to C₂₂ alkylsiloxane).
3. A compound of any of the preceding claims, wherein the poly(diorganosiloxane) is PDMS.
4. A compound of any of the preceding claims, wherein L₁ is alkylene.
5. A compound of any of the preceding claims, wherein L₂ is a covalent bond or alkylene.
6. A compound of any of the preceding claims, wherein L₃ is alkylene.
7. A compound of any of the preceding claims, wherein L₄ alkylene.
8. A compound any of the preceding claims, wherein the compound has the structure of Formula (VI)



(VI)


9. A compound of any of claims 1-7, wherein the compound has a structure of Formula (VIII)



(VIII)


wherein ALK is alkylene.

10. A compound of claim 9, wherein ALK is methylene.
11. A compound of any of claims 1-7, wherein the compound has the structure of Formula (XIII)




(XIII).

12. A compound of any of claims 1-7, wherein the compound has the structure of Formula (XIV)



(XIV).

13. A compound of any of claims 1-7 or 11, wherein the compound has the structure of Formula (XV)



(XV).

14. A composition comprising an aqueous solution or dispersion of a compound of any of the preceding claims.

15. An article having a compound of any of the preceding claims affixed thereto.

INTERNATIONAL SEARCH REPORT

International application No

PCT/US2015/063852

A. CLASSIFICATION OF SUBJECT MATTER

INV. C09D183/08

ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C09D C08G C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2007/148475 A1 (SHERMAN AUDREY A [US] ET AL) 28 June 2007 (2007-06-28) paragraphs [0091] - [0093] examples prep 1, prep 3 -----	1-15
X	US 2007/148474 A1 (LEIR CHARLES M [US] ET AL) 28 June 2007 (2007-06-28) examples prep 1-5, 1-20 -----	1-15
X	US 2008/318058 A1 (SHERMAN AUDREY A [US] ET AL) 25 December 2008 (2008-12-25) examples 1-3 -----	1-15
X	US 2008/318057 A1 (SHERMAN AUDREY A [US] ET AL) 25 December 2008 (2008-12-25) examples prep 1-2, 1-7 ----- -/--	1-15



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

9 February 2016

Date of mailing of the international search report

16/02/2016

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Queste, Sébastien

INTERNATIONAL SEARCH REPORT

International application No

PCT/US2015/063852

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2011/230633 A1 (FERENZ MICHAEL [DE] ET AL) 22 September 2011 (2011-09-22) example 1 claim 8 -----	1-15

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2015/063852

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2007148475	A1	28-06-2007	AT 501204 T 15-03-2011
		CN 101346448 A 14-01-2009	
		EP 1963456 A2 03-09-2008	
		JP 4955701 B2 20-06-2012	
		JP 2009521569 A 04-06-2009	
		KR 20080080321 A 03-09-2008	
		US 2007148475 A1 28-06-2007	
		US 2008187750 A1 07-08-2008	
		US 2008199620 A1 21-08-2008	
		US 2011189421 A1 04-08-2011	
		US 2012295025 A1 22-11-2012	
		US 2013288053 A1 31-10-2013	
		WO 2007075802 A2 05-07-2007	
US 2007148474	A1	28-06-2007	AT 504620 T 15-04-2011
		CN 101346414 A 14-01-2009	
		EP 1963404 A1 03-09-2008	
		JP 5266061 B2 21-08-2013	
		JP 2009521545 A 04-06-2009	
		KR 20080078683 A 27-08-2008	
		US 2007148474 A1 28-06-2007	
		US 2009133832 A1 28-05-2009	
		US 2011092638 A1 21-04-2011	
		US 2014050872 A1 20-02-2014	
		US 2014370243 A1 18-12-2014	
		WO 2007075317 A1 05-07-2007	
US 2008318058	A1	25-12-2008	CN 101687998 A 31-03-2010
		EP 2167567 A1 31-03-2010	
		JP 5351148 B2 27-11-2013	
		JP 2010530920 A 16-09-2010	
		TW 200909482 A 01-03-2009	
		US 2008318058 A1 25-12-2008	
		US 2012027976 A1 02-02-2012	
		US 2013109828 A1 02-05-2013	
		US 2014094584 A1 03-04-2014	
		US 2015197675 A1 16-07-2015	
		WO 2009002681 A1 31-12-2008	
US 2008318057	A1	25-12-2008	CN 101687997 A 31-03-2010
		EP 2162485 A1 17-03-2010	
		JP 5199346 B2 15-05-2013	
		JP 2010530919 A 16-09-2010	
		KR 20100050467 A 13-05-2010	
		TW 200906917 A 16-02-2009	
		US 2008318057 A1 25-12-2008	
		US 2010163809 A1 01-07-2010	
		US 2011123798 A1 26-05-2011	
		US 2011263798 A1 27-10-2011	
		US 2012175566 A1 12-07-2012	
		US 2013225768 A1 29-08-2013	
		WO 2009002611 A1 31-12-2008	
US 2011230633	A1	22-09-2011	CA 2732357 A1 22-08-2011
		CN 102167830 A 31-08-2011	
		DE 102010002178 A1 25-08-2011	
		EP 2365021 A1 14-09-2011	
		JP 5683316 B2 11-03-2015	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2015/063852

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
		JP 2011168782 A	01-09-2011
		US 2011230633 A1	22-09-2011
