

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
15 January 2004 (15.01.2004)


PCT

(10) International Publication Number
WO 2004/005372 A1

- (51) International Patent Classification⁷: **C08G 64/12**, (74) Agents: **WINTER, Catherine, J.** et al.; General Electric Company, 3135 Easton Turnpike W3C, Fairfield, CT 06431 (US).
C07C 233/56, 231/02, 69/36
- (21) International Application Number: PCT/US2002/021433 (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZM, ZW.
- (22) International Filing Date: 5 July 2002 (05.07.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (71) Applicant: **GENERAL ELECTRIC COMPANY** (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
[US/US]; 1 River Road, Schenectady, NY 12345 (US).
- (72) Inventors: **PICKETT, James, Edward**; 4331 Buckingham Drive, Schenectady, NY 12304 (US). **SICLOVAN, Tiberiu, Mircia**; 1455 Dorwaldt Boulevard #5-9, Schenectady, NY 12308 (US). **SURIANO, Joseph, Anthony**; 35 Gloucester Street, Clifton Park, NY 12065 (US). **BRUNELLE, Daniel, Joseph**; 4 Woods Edge, Burnt Hills, NY 12027 (US).
- Published:
— with international search report

[Continued on next page]

(54) Title: WEATHERABLE POLYCARBONATES COMPRISING OXANILIDE STRUCTURAL UNITS, METHOD, AND ARTICLES MADE THEREFROM



(57) Abstract: In one embodiment the present invention is a polycarbonate comprising structural units derived from at least one dihydric phenol, a carbonate precursor, and at least one member selected from the group consisting of an oxanilide-comprising compound, an oxamate-comprising compound, and mixtures thereof. In another embodiment the present invention is a method for making a polycarbonate comprising structural units derived from at least one dihydric phenol and at least one member selected from the group consisting of an oxanilide-comprising compound, an oxamate-comprising compound, and mixtures thereof, which comprises the step of contacting under reactive conditions at least one dihydric phenol, a carbonate precursor, and at least one member selected from the group consisting of an oxanilide-comprising compound, an oxamate-comprising compound, and mixtures thereof. In still another embodiment the present invention is an article comprising a polycarbonate comprising oxanilide structural units. In still another embodiment the present invention is a method for making a symmetrical or unsymmetrical oxanilide-comprising dihydric phenol which comprises the step of contacting at least one aromatic amine bearing a hydroxy group with a diaryl oxalate or a dialkyl oxalate bearing alkyl groups each substituted with at least one electron-withdrawing group. In still another embodiment the present invention is a method for making an oxamate-comprising monohydric phenol which comprises the step of contacting an aromatic amine bearing a hydroxy group with a diaryl oxalate or a dialkyl oxalate bearing alkyl groups each substituted with at least one electron-withdrawing group.

WO 2004/005372 A1



For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.


WEATHERABLE POLYCARBONATES COMPRISING OXANILIDE STRUCTURAL UNITS, METHOD, AND ARTICLES MADE THEREFROM

BACKGROUND OF THE INVENTION

The present invention is directed to polycarbonate polymers which are resistant to weathering. More particularly, the present invention is directed to polycarbonate polymers comprising oxanilide structural units, methods for producing them, and articles made therefrom.

Polycarbonates are a widely employed class of polymers, in part because of their excellent physical properties including high impact strength. However, the resistance of polycarbonates to change upon exposure to weather phenomena (generally termed "weatherability") is not ideal. In particular, long term color stability is a problem as polycarbonates are subject to yellowing, which detracts from the transparency and attractiveness of the polymers. Yellowing of polycarbonates is caused largely by the action of ultraviolet radiation, which is why such yellowing is frequently referred to as "photoyellowing". Numerous means for suppressing photoyellowing and other detrimental phenomena associated with weathering have been employed and proposed. Many of these involve incorporation in polycarbonate compositions of ultraviolet absorbing compounds (UVA's). For the most part, UVA's are low molecular weight compounds and they must be employed at relatively low levels, typically up to no more than about 1% by weight, to avoid degradation of the physical properties of the polymer such as impact strength and high temperature properties as reflected in heat distortion temperature. A long-felt need exists for polycarbonate compositions with effective resistance to weathering which do not require the addition of low molecular weight UVA's.

An example of a typical UVA is an oxanilide-comprising compound available under the tradename SANDUVOR VSU from Clariant Corporation and having the formula (I) :



Commonly assigned U.S. Patent No. 5,847,196 discloses a synthesis of mono- and difunctional oxanilides containing aromatic hydroxy functionality. However, the oxanilides made by the method taught therein are themselves highly colored. Also, there is no teaching therein of polycarbonates which might be derived from such oxanilides. There is a need for a method for preparing oxanilides containing aromatic hydroxy functionality which produces oxanilides with little or no color, which can be used to prepare essentially colorless, transparent polycarbonates.

SUMMARY OF THE INVENTION

After diligent experimentation the present inventors have discovered polycarbonates comprising oxanilide structural units which are essentially colorless and which exhibit excellent weatherability. Thus, in one embodiment the present invention is a polycarbonate comprising structural units derived from at least one dihydric phenol, a carbonate precursor, and at least one member selected from the group consisting of an oxanilide-comprising compound, an oxamate-comprising compound, and mixtures thereof. In another embodiment the present invention is a method for making a polycarbonate comprising structural units derived from at least one dihydric phenol and at least one member selected from the group consisting of an oxanilide-comprising compound, an oxamate-comprising compound, and mixtures thereof, which comprises the step of contacting under reactive conditions at least one dihydric phenol, a carbonate precursor, and at least one member selected from the group consisting of an oxanilide-comprising compound, an oxamate-comprising compound, and mixtures thereof. In still another embodiment the present invention is an article comprising a polycarbonate comprising oxanilide structural units. In still another embodiment the present invention is a method for making a symmetrical or unsymmetrical oxanilide-comprising dihydric phenol which comprises the step of

contacting at least one aromatic amine bearing a hydroxy group with a diaryl oxalate or a dialkyl oxalate bearing alkyl groups each substituted with at least one electron-withdrawing group. In still another embodiment the present invention is a method for making an oxanilide-comprising monohydric phenol which comprises the step of contacting an aromatic amine bearing a hydroxy group with a diaryl oxalate or a dialkyl oxalate bearing alkyl groups each substituted with at least one electron-withdrawing group. Various other features, aspects, and advantages of the present invention will become more apparent with reference to the following description and appended claims.

BRIEF DESCRIPTION OF THE DRAWINGS


FIGURE 1 shows the ultraviolet spectra for the bis(phenyl carbonate) derivative of compound (V) and the monophenyl carbonate derivative of compound (VIII).

FIGURE 2 shows change in yellowing index (delta YI) upon exposure to ultraviolet radiation for plaques of bisphenol-A polycarbonate compared to plaques comprising bisphenol-A polycarbonate with an overlayer of polycarbonate comprising bisphenol-A and oxanilide structural units.


FIGURE 3 shows change in color (delta E) upon exposure to ultraviolet radiation for plaques of bisphenol-A polycarbonate compared to plaques comprising bisphenol-A polycarbonate with an overlayer of polycarbonate comprising bisphenol-A and oxanilide structural units.

DETAILED DESCRIPTION OF THE INVENTION

Oxanilide-comprising compounds in various embodiments of the present invention include oxanilide-comprising dihydric phenols of formula (II) :



wherein D and D¹ are each independently a divalent aromatic radical. In various embodiments D and D¹ independently have the structure of formula (III) ;



wherein A¹ represents an aromatic group such as phenylene, biphenylene, naphthylene, etc. E may be an alkylene or alkylidene group including, but not limited to, methylene, ethylene, ethylidene, propylene, propylidene, isopropylidene, butylene, butylidene, isobutylidene, amylene, amylidene, isoamylidene. When E is an alkylene or alkylidene group, it may also consist of two or more alkylene or alkylidene groups connected by a moiety different from alkylene or alkylidene, such as an aromatic linkage; a tertiary amino linkage; an ether linkage; a carbonyl linkage; a silicon-containing linkage; or a sulfur-containing linkage including, but not limited to, sulfide, sulfoxide, sulfone; or a phosphorus-containing linkage including, but not limited to, phosphinyl, phosphonyl. In addition, E may be a cycloaliphatic group including, but not limited to, cyclopentylidene, cyclohexylidene, 3,3,5-trimethylcyclohexylidene, methylcyclohexylidene, 2-[2.2.1]-bicycloheptylidene, neopentylidene, cyclopentadecylidene, cyclododecylidene, adamantylidene; a sulfur-containing linkage, such as sulfide, sulfoxide or sulfone; a phosphorus-containing linkage, such as phosphinyl or phosphonyl; an ether linkage; a carbonyl group; a tertiary nitrogen group; or a silicon-containing linkage such as silane or siloxy. R¹ represents hydrogen or a monovalent hydrocarbon group such as alkyl, aryl, aralkyl, alkaryl, or cycloalkyl. In various embodiments a monovalent hydrocarbon group of R¹ may be halogen-substituted, particularly fluoro- or chloro-substituted, for example as in dichloroalkylidene. Y¹ may be an inorganic atom including, but not limited to, halogen (fluorine, bromine, chlorine, iodine); an inorganic group including, but not limited to, nitro; an organic group including, but not limited to, a monovalent hydrocarbon group such as alkyl, aryl, aralkyl, alkaryl, or cycloalkyl, or an oxy group such as OR², wherein R² is a monovalent hydrocarbon group such as alkyl, aryl,


aralkyl, alkaryl, or cycloalkyl; it being only necessary that Y^1 be inert to and unaffected by the reactants and reaction conditions used to prepare a polycarbonate. The letter "m" represents any integer from and including zero through the number of positions on A^1 available for substitution; "p" represents an integer from and including zero through the number of positions on E available for substitution; "t" represents an integer equal to at least one; "s" is either zero or one; and "u" represents any integer including zero.

In the context of the present invention alkyl radicals or groups are typically those containing from 1 to about 18 carbon atoms, and include branched alkyl radicals and straight chain alkyl radicals. Some illustrative non-limiting examples of these alkyl radicals include methyl, ethyl, propyl, isopropyl, butyl, tertiary-butyl, pentyl, neopentyl, and hexyl. Cycloalkyl radicals or groups are typically those containing from 3 to about 12 ring carbon atoms. Some illustrative non-limiting examples of these cycloalkyl radicals include cyclobutyl, cyclopentyl, cyclohexyl, methylcyclohexyl, cycloheptyl. Aryl radicals or groups are typically those containing from 6 to 12 ring carbon atoms. Some illustrative non-limiting examples of these aryl radicals include phenyl, biphenyl, naphthyl. Typical aralkyl and alkaryl radicals or groups are those containing from 7 to about 24 carbon atoms. These include, but are not limited to, benzyl, ethylphenyl, phenylbutyl, phenylpropyl, propylphenyl, and phenylethyl.

When more than one Y substituent is present as represented by formula (III) above, they may be the same or different. When more than one R^1 substituent is present, they may be the same or different. Where "s" is zero in formula (III) and "u" is not zero, the aromatic rings are directly joined with no intervening alkylidene or other bridge. The positions of the hydroxyl groups and Y^1 on the aromatic residues A^1 can be varied in the ortho, meta, or para positions and the groupings can be in vicinal, asymmetrical or symmetrical relationship, where two or more ring carbon atoms of the aromatic residue are substituted with Y^1 and hydroxyl groups.


In one embodiment D and D^1 of formula (II) are the same and the compound is a symmetrical oxanilide-comprising dihydric phenol. In another embodiment D and D^1

of formula (II) are different and the compound is an unsymmetrical oxanilide-comprising dihydric phenol. In a particular embodiment oxanilide-comprising dihydric phenols of formula (II) include those of formula (IV) :




wherein R^3 is an alkylene, alkylidene, or cycloaliphatic group including, but not limited to, methylene, ethylene, ethylidene, propylene, propylidene, isopropylidene, butylene, butylidene, isobutylidene, amylene, amylidene, isoamylidene, cyclopentylidene, cyclohexylidene, 3,3,5-trimethylcyclohexylidene, methylcyclohexylidene, 2-[2.2.1]-bicycloheptylidene, neopentylidene, cyclopentadecylidene, cyclododecylidene, adamantylidene, dichloroalkylidene; R^4 is halogen, bromo, chloro, alkyl, aryl, aralkyl, alkaryl, cycloalkyl, or OR^2 , wherein R^2 is a monovalent hydrocarbon group such as alkyl, aryl, aralkyl, alkaryl, or cycloalkyl; and "x" represents any integer from and including zero through the number of positions on the aromatic ring available for substitution. When present, any R^4 substituent may be ortho or meta to the heteroatom-aromatic ring linkage. In another particular embodiment R^3 in formula (IV) is isopropylidene and "x" is zero, which compound is N,N'-bis[4-[1-(4-hydroxyphenyl)-1-methylethyl]phenyl]-ethanediamide, also referred to herein as compound (V).

Oxanilide-comprising compounds in various embodiments of the present invention also include oxanilide-comprising monohydric phenols of formula (VI) :




wherein D and D^1 are each independently a divalent aromatic radical and R^5 is hydrogen or a monovalent hydrocarbon group such as alkyl, aryl, aralkyl, alkaryl, or cycloalkyl; an inorganic atom including, but not limited to, halogen (fluorine,

bromine, chlorine, iodine); an inorganic group including, but not limited to, nitro; or an oxy group such as OR^2 , wherein R^2 is a monovalent hydrocarbon group such as alkyl, aryl, aralkyl, alkaryl, or cycloalkyl; it being only necessary that R^5 be inert to and unaffected by the reactants and reaction conditions used to prepare a polycarbonate. In various embodiments D and D^1 each independently have the structure of formula (III) ;



wherein A^1 , Y^1 , E, R^1 , m, p, t, s, and u have the same definition and scope as defined hereinabove.


In a particular embodiment oxanilide-comprising monohydric phenols of formula (VI) include those of formula (VII) :



wherein R^3 is an alkylene, alkylidene, or cycloaliphatic group including, but not limited to, methylene, ethylene, ethylidene, propylene, propylidene, isopropylidene, butylene, butylidene, isobutylidene, amylene, amylidene, isoamylidene; cyclopentylidene, cyclohexylidene, 3,3,5-trimethylcyclohexylidene, methylcyclohexylidene, 2-[2.2.1]-bicycloheptylidene, neopentylidene, cyclopentadecylidene, cyclododecylidene, adamantylidene, dichloroalkylidene; R^4 and R^5 are each independently halogen, bromo, chloro, alkyl, aryl, aralkyl, alkaryl, cycloalkyl, or OR^2 , wherein R^2 is a monovalent hydrocarbon group such as alkyl, aryl, aralkyl, alkaryl, or cycloalkyl; and "x" and "j" represent any integer from and including zero through the number of positions on the aromatic ring available for

substitution. When present, any R^4 substituent may be ortho or meta to the heteroatom-aromatic ring linkage, and any R^5 substituent may be ortho, meta, or para to the heteroatom-aromatic ring linkage. In another particular embodiment R^3 in formula (VII) is isopropylidene; "j" is zero; "x" is one; and R^5 is OCH_2CH_3 ortho to the heteroatom-aromatic ring linkage, which compound is sometimes referred to hereinafter as compound (VIII) or as N-[4-[1-(4-hydroxyphenyl)-1-methylphenyl]-N'-1-[2-ethoxyphenyl)]-ethanediamide.

In various embodiments the present invention also includes oxamate-comprising monohydric phenols of formula (IX) :



wherein D is a divalent aromatic radical with the same definition and scope as defined hereinabove and R^6 is a monovalent hydrocarbon group such as alkyl, aryl, aralkyl, alkaryl, or cycloalkyl, which may be optionally substituted with an electron-withdrawing group including, but not limited to, halogen, chloro, fluoro, nitro, carboxy, trihaloacetyl, and trifluoroacetyl. Illustrative examples for R^6 include, but are not limited to, phenyl, methyl salicyl, 2-chlorophenyl, 2-nitrophenyl, 2-trifluoroacetylphenyl, 2-fluorophenyl, ethyl, butyl, chloroethyl, and trifluoroethyl. In particular embodiments D is a residue derived from the compound 2-(4-aminophenyl)-2-(4'-hydroxyphenyl)propane and R^6 is ethyl, butyl, or trifluoroethyl.

Methods of making oxanilide-comprising compounds of the present invention include those methods known in the art. In one embodiment at least one aromatic amine is contacted with a difunctional oxalic acid derivative under reactive conditions. Aromatic amines suitable for making oxanilide-comprising dihydric phenols of formula (II) include, but are not limited to, those with the structure $H_2N-D-OH$ and H_2N-D^1-OH , wherein D and D^1 have the definition and scope given hereinabove. Aromatic amines suitable for making oxanilide-comprising monohydric phenols of formula (VI) include, but are not limited to, those with the structure H_2N-D-R^5 and H_2N-D^1-OH , wherein D, D^1 , and R^5 have the definition and scope given hereinabove.

Representative examples of aromatic amines include, but are not limited to, aniline, phenetidine, 3-aminophenol, 4-aminophenol, and 2-(4-aminophenyl)-2-(4'-hydroxyphenyl)propane. Suitable difunctional oxalic acid derivatives include, but are not limited to, oxalic acid, oxalyl chloride, oxalic acid diesters and oxalic acid monoester-monoacid chlorides. In particular embodiments suitable difunctional oxalic acid derivatives include, but are not limited to, oxalic acid diaryl esters and dialkyl esters, such as diethyl oxalate and dibutyl oxalate, and oxalic acid monoalkylester-monoacid chlorides, such as ethyl oxalyl chloride. Catalysts, such as a Lewis acids, are known in the art to enhance the reaction rate of an aromatic amine in reaction with a difunctional oxalic acid derivative, and a catalyst may optionally be present in any reaction to prepare oxanilide-comprising compounds.

In one embodiment two equivalents of a single aromatic amine may react in one or more steps with a difunctional oxalic acid derivative to provide a symmetrical oxanilide-comprising compound. In another embodiment one equivalent each of two different aromatic amines may react in separate steps with a difunctional oxalic acid derivative to provide an unsymmetrical oxanilide-comprising compound. In another embodiment one equivalent of an aromatic amine may react with a difunctional oxalic acid derivative to provide an unsymmetrical oxamate-comprising compound. In a particular embodiment two equivalents of a single aromatic amine react in one or more steps with a difunctional oxalic acid derivative to provide a symmetrical oxanilide-comprising dihydric phenol. In another particular embodiment one equivalent each of two different aromatic amines may react in separate steps with a difunctional oxalic acid derivative to provide either an unsymmetrical oxanilide-comprising dihydric phenol or an oxanilide-comprising monohydric phenol (for example, if only one of the aromatic amines bears a hydroxy group). In another particular embodiment one equivalent of an aromatic amine may react with a difunctional oxalic acid derivative to provide an oxamate-comprising monohydric phenol.


The synthesis of symmetrical oxanilide-comprising dihydric phenols by reaction of aromatic amines with dialkyl oxalate under the conditions taught in U.S. Patent No. 5,847,196 gives dark-colored compounds unsuitable for use in making essentially

colorless, transparent polycarbonates. In contrast, the present inventors have unexpectedly discovered that the reaction of aromatic amines with oxalate diesters bearing either aryl groups, including, but not limited to, phenyl, methyl salicyl, 2-chlorophenyl, 2-nitrophenyl, 2-trifluoroacetylphenyl, 2-fluorophenyl; or alkyl groups substituted with electron-withdrawing groups, including, but not limited to, fluoro or chloro, may be performed at lower temperature and provides both symmetrical and unsymmetrical dihydric and monohydric oxanilide-comprising phenols with little or no color, which can be used to prepare essentially colorless, transparent polycarbonates. Although the invention is not dependent upon any theory of operation, it is believed that the use of a lower temperature in the synthesis of oxanilide-comprising phenols may be a factor in decreasing color formation. Thus, in one embodiment the present invention is a method for making symmetrical oxanilide-comprising dihydric phenols which comprises the step of contacting an aromatic amine bearing a hydroxy group with a diaryl oxalate or a dialkyl oxalate bearing alkyl groups each substituted with at least one electron-withdrawing group. In another embodiment the present invention is a method for making unsymmetrical oxanilide-comprising dihydric phenols which comprises the steps of contacting an aromatic amine bearing a hydroxy group with a diaryl oxalate or a dialkyl oxalate bearing alkyl groups each substituted with at least one electron-withdrawing group, followed by contacting the oxamate intermediate with a second aromatic amine bearing a hydroxy group and different from said first aromatic amine. In still another embodiment the present invention is a method for making oxanilide-comprising monohydric phenols which comprises the steps of contacting an aromatic amine with a diaryl oxalate or a dialkyl oxalate bearing alkyl groups each substituted with at least one electron-withdrawing group, followed by contacting the oxamate intermediate with a second aromatic amine different from said first aromatic amine, wherein only one aromatic amine bears a hydroxy group. In still another embodiment the present invention is a method for making oxamate-comprising monohydric phenols which comprises the step of contacting an aromatic amine bearing a hydroxy group with a diaryl oxalate or a dialkyl oxalate bearing alkyl groups each substituted with at least one electron-withdrawing group.


In one embodiment the temperature of reaction for contacting an aromatic amine with a diaryl oxalate or a dialkyl oxalate bearing alkyl groups each substituted with at least one electron-withdrawing group is in a range of between about 30°C and about 150°C; in another embodiment in a range of between about 30°C and about 100°C; and in still another embodiment in a range of between about 30°C and about 75°C. These same temperature ranges also apply when contacting an aromatic amine with an oxamate intermediate. Illustrative diaryl oxalates include, but are not limited to, diphenyl oxalate, bis(2-chlorophenyl)oxalate, bis(2-nitrophenyl)oxalate, and bis(2-fluorophenyl)oxalate. Illustrative dialkyl oxalates bearing alkyl groups each substituted with at least one electron-withdrawing group include, but are not limited to, bis(trifluoroethyl)oxalate and bis(chloroethyl)oxalate.

In another embodiment the present invention comprises polycarbonates which comprise oxanilide-comprising structural units. In a particular embodiment polycarbonates of the present invention comprise structural units derived from at least one oxanilide-comprising compound, at least one dihydric phenol and a carbonate precursor. Polycarbonates comprising oxanilide structural units may be made by any known method. Representative methods include, but are not limited to, solution methods, interfacial methods, melt methods, transesterification methods, solid-state methods, and redistribution methods, and combinations thereof. In one embodiment polycarbonates comprising oxanilide structural units may be made through combining at least one compound comprising at least one oxanilide moiety with at least one dihydric phenol and a carbonate precursor under reactive conditions.

Suitable dihydric phenols for preparing polycarbonates include those represented by the formula X :







wherein D is a divalent aromatic radical. In various embodiments D has the structure of formula (III) ;



wherein A^1 , Y^1 , E , R^1 , m , p , t , s , and u have the same definition and scope as defined hereinabove.


Some illustrative, non-limiting examples of dihydric phenols of formula (X) include the dihydroxy-substituted aromatic hydrocarbons disclosed by name or formula (generic or specific) in U.S. Patent 4,217,438. In various embodiments of the invention dihydric phenols include 6-hydroxy-1-(4'-hydroxyphenyl)-1,3,3-trimethylindane, 4,4'-(3,3,5-trimethylcyclohexylidene)diphenol; 1,1-bis(4-hydroxy-3-methylphenyl)cyclohexane; 2,2-bis(4-hydroxyphenyl)propane (commonly known as bisphenol-A); 2,2-bis(4-hydroxy-3,5-dimethylphenyl)propane; 2,2-bis(4-hydroxy-3-methylphenyl)propane; 2,2-bis(4-hydroxy-3-ethylphenyl)propane; 2,2-bis(4-hydroxy-3-isopropylphenyl)propane; 2,4'-dihydroxydiphenylmethane; bis(2-hydroxyphenyl)methane; bis(4-hydroxy-phenyl)methane; bis(4-hydroxy-5-nitrophenyl)methane; bis(4-hydroxy-2,6-dimethyl-3-methoxyphenyl)methane; 1,1-bis(4-hydroxyphenyl)ethane; 1,1-bis(4-hydroxy-2-chlorophenyl)ethane; 2,2-bis(3-phenyl-4-hydroxyphenyl)-propane; bis(4-hydroxyphenyl)cyclohexylmethane; 2,2-bis(4-hydroxyphenyl)-1-phenylpropane; hydroquinone, resorcinol; C_{1-3} alkyl-substituted resorcinols.

Suitable dihydric phenols also include those containing indane structural units such as represented by the formula (XI), which compound is 3-(4-hydroxyphenyl)-1,1,3-trimethylindan-5-ol, and by the formula (XII), which compound is 1-(4-hydroxyphenyl)-1,3,3-trimethylindan-5-ol :



Suitable dihydric phenols also include those containing spirobiindane

structural units such as represented by the formula (XIII) :



wherein each R^{20} is independently selected from monovalent hydrocarbon radicals and halogen radicals; each R^{21} , R^{22} , R^{23} , and R^{24} is independently C_{1-6} alkyl; each R^{25} and R^{26} is independently H or C_{1-6} alkyl; and each n is independently selected from positive integers having a value of from 0 to 3 inclusive. The monovalent hydrocarbon radicals represented by R^{20} include alkyl radicals, cycloalkyl radicals, aryl radicals, aralkyl radicals, and alkaryl radicals, as already defined hereinabove. In various embodiments the halogen radicals represented by R^{20} are fluorine, chlorine and bromine.

In the dihydric phenol compound of formula (XIII) when more than one R^{20} substituent is present they may be the same or different. The relative positions of the hydroxyl groups and R^{20} on the aromatic nuclear residues may be varied in the ortho or meta positions. The position of each hydroxy group is independently at any unsubstituted site on each of the aromatic rings. In one embodiment each hydroxy group is independently in positions 5 or 6 and 5' or 6' of each aromatic ring. In another embodiment each hydroxy group is in position 6 and 6' of each aromatic ring.

In various embodiments, each R^{20} is independently selected from chlorine, bromine, and lower alkyl radicals containing from 1 to about 5 carbon atoms, each R^{21} , R^{22} , R^{23} , and R^{24} is independently C_{1-6} alkyl; each R^{25} and R^{26} is independently H or C_{1-6} alkyl; and each n is independently 0 to 3. In some embodiments, each R^{20} is

independently selected from chlorine and lower alkyl radicals containing from 1 to about 3 carbon atoms, each R^{21} , R^{22} , R^{23} , and R^{24} is independently C_{1-2} alkyl; each R^{25} and R^{26} is independently H or C_{1-2} alkyl; and each n is independently 0 to 2. In other embodiments, each R^{21} , R^{22} , R^{23} , and R^{24} is methyl; each R^{25} and R^{26} is H; and each n is 0.

In one embodiment a spiro dihydric phenol for forming polycarbonates suitable for use in the present invention is 6,6'-dihydroxy-3,3,3',3'-tetramethyl-1,1'-spirobiindane (sometimes known as "SBI"), in which n in formula (XIII) is 0 and the linkages with the rest of the polymer molecule are in a specific position on the aromatic rings.

In various embodiments the carbonate precursor for preparing polycarbonates include at least one carbonyl halide, carbonate ester or haloformate. The carbonyl halides which can be employed herein are carbonyl chloride, carbonyl bromide and mixtures thereof. Typical carbonate esters which may be employed herein include, but are not limited to, diaryl carbonates, including, but not limited to, diphenylcarbonate, di(halophenyl)carbonates, di(chlorophenyl)carbonate, di(bromophenyl)carbonate, di(trichlorophenyl)carbonate, di(tribromophenyl)carbonate; di(alkylphenyl)carbonates, di(tolyl)carbonate; di(naphthyl)carbonate, di(chloronaphthyl)carbonate, phenyl tolyl carbonate, chlorophenyl chloronaphthyl carbonate, di(methyl salicyl)carbonate, and mixtures thereof. The haloformates suitable for use herein include bishaloformates of dihydric phenols, which include, but are not limited to, bischloroformates of hydroquinone, bisphenol-A, 6-hydroxy-1-(4'-hydroxyphenyl)-1,3,3-trimethylindane, 4,4'-(3,3,5-trimethylcyclohexylidene)diphenol; 1,1-bis(4-hydroxy-3-methylphenyl)cyclohexane, and the like; bischloroformate-terminated polycarbonate oligomers such as oligomers comprising hydroquinone, bisphenol-A, 6-hydroxy-1-(4'-hydroxyphenyl)-1,3,3-trimethylindane, 4,4'-(3,3,5-trimethylcyclohexylidene)diphenol, 1,1-bis(4-hydroxy-3-methylphenyl)cyclohexane, or the like; and bishaloformates of glycols including, but not limited to, bishaloformates of ethylene glycol, neopentyl glycol, and polyethylene glycol. Mixtures of haloformates may be employed. In a particular embodiment carbonyl chloride, also known as phosgene, is employed.

In one embodiment polycarbonates of the present invention comprise oxanilide structural units distributed within a polycarbonate chain. In a particular embodiment the components of a polycarbonate synthesis reaction comprise at least one dihydric phenol comprising at least one oxanilide moiety and at least one dihydric phenol not containing an oxanilide moiety, the latter being described for example in formulas (X), (XI), (XII), and (XIII). In various embodiments the components for preparation of polycarbonates comprising oxanilide structural units include one dihydric phenol as described above in combination with an oxanilide-comprising dihydric phenol, or mixtures of two or more different dihydric phenols in combination with an oxanilide-comprising dihydric phenol. In a particular embodiment a dihydric phenol of formula (X) is used alone in combination with an oxanilide-comprising dihydric phenol and is 2,2-bis(4-hydroxyphenyl)propane (bisphenol-A or "BPA"), in which D in formula (III) is bis(4-phenyl)isopropylidene. In other embodiments particular mixtures comprising two or more dihydric phenols used in combination with an oxanilide-comprising dihydric phenol are a mixture comprising bisphenol-A and 1,1-bis(4-hydroxy-3-methylphenyl)cyclohexane, and a mixture comprising bisphenol-A and 6,6'-dihydroxy-3,3,3',3'-tetramethyl-1,1'-spirobiindane.

Reactive conditions for preparing polycarbonates of the invention include, but are not limited to, solution processes, interfacial processes, melt processes, transesterification processes, solid-state processes, and redistribution processes, and combinations thereof. Solution processes may comprise a stoichiometric amount of base such as triethylamine or pyridine. If an interfacial process is used, the addition of various phase transfer catalysts is optional. Phase transfer catalysts which are suitable include, but are not limited, to tertiary amines, such as triethylamine, ammonium salts, such as tetrabutylammonium bromide; or hexaethylguanidinium chloride.

In one embodiment the polycarbonates as described are prepared by a melt or transesterification process. This process does not require the use of phosgene or a solvent, and minimizes the formation of low molecular weight contaminants, such as cyclic and linear low molecular weight oligomers in the final polymer. The monomers are typically mixed with a carbonate source, such as a diarylcarbonate, and a small amount of catalyst, such as an alkali metal hydroxide or ammonium

hydroxide, and heated under a vacuum according to a protocol in which the temperature is raised through a series of stages while the pressure in the headspace over the reaction mixture is lowered from ambient pressure to about 1 Torr. The time of the stages and the temperature are such that mechanical losses of material through foaming and the like are avoided. Phenol and excess diphenyl carbonate may be removed overhead to complete the polymerization process. The product high polymer may then be isolated as a melt which may be compounded with other additives, such as stabilizers and mold release agents prior to pelletization. Suitable carbonate sources, catalysts and reaction conditions may be found, for example, in U.S. Patent 5,880,248, and Kirk-Othmer Encyclopedia of Chemical Technology, Fourth Edition, Volume 19, pp. 585-600, herein incorporated by reference.

In various embodiments polycarbonates of the invention have a weight average molecular weight in a range of between about 5,000 and about 100,000, in other embodiments a weight average molecular weight in a range of between about 10,000 and about 65,000, and in still other embodiments a weight average molecular weight in a range of between about 18,000 and about 55,000 as measured by gel permeation chromatography versus polystyrene standards. In other embodiments polycarbonates of the invention have a weight average molecular weight in a range of between about 40,000 and about 55,000, as measured by gel permeation chromatography versus polystyrene standards.

The amount of polycarbonate structural units derived from oxanilide-comprising dihydric phenol will vary in accordance with the expected end-use application of the polycarbonate resins. In various embodiments, the amount of polycarbonate structural units derived from oxanilide-comprising dihydric phenol may be in a range of between about 0.1 mole percent and about 80 mole percent, in other embodiments in a range of between about 0.5 mole percent and about 50 mole percent, in other embodiments in a range of between about 1 mole percent and about 30 mole percent, in other embodiments in a range of between about 1 mole percent and about 20 mole percent, and in still other embodiments in a range of between about 1 mole percent and about 10 mole percent, based on the total amount of structural units derived from dihydric phenol (which includes those derived from both oxanilide-comprising

dihydric phenol and dihydric phenol not containing oxanilide moiety). These amounts of structural units derived from oxanilide-comprising dihydric phenol are applicable no matter whether a polycarbonate comprises structural units derived from a single dihydric phenol not containing an oxanilide moiety or a mixture comprising two or more dihydric phenols not containing an oxanilide moiety.

In any process for preparing a polycarbonate a molecular weight regulator (also known as a chain termination agent or a chain stopper) may be added, if so desired, to phenolic reactants, for example, prior to or during contacting the reactants with a carbonate precursor. Polycarbonates prepared in the presence of chain-termination agents comprise structural units derived from said chain-termination agents. Useful chain termination agents include, but are not limited to, monohydric phenols such as phenol, chroman-1, para-tertiary-butylphenol, isooctylphenol, isononylphenol, p-cumylphenol, and the like. In various embodiments structural units derived from chain termination agents are present at a level in a range of between about 0.1 mole percent and about 10 mole percent, in other embodiments in a range of between about 1 mole percent and about 10 mole percent, in other embodiments in a range of between about 4 mole percent and about 10 mole percent, and in still other embodiments in a range of between about 4 mole percent and about 7 mole percent based on the total amount of structural units derived from dihydric phenol. Techniques for the applying one or more chain termination agents are well known in the art and may be used in the any relevant process for controlling the molecular weight of a polycarbonate resin.

In one embodiment polycarbonates of the present invention comprise at least one oxanilide structural unit or oxamate structural unit attached to at least one terminal point on a polycarbonate chain. In a particular embodiment an oxanilide structural unit attached to at least one terminal point on a polycarbonate chain may be derived from an oxanilide-comprising dihydric phenol. In another particular embodiment an oxanilide structural unit or oxamate structural unit attached to at least one terminal point on a polycarbonate chain may be derived from an oxanilide-comprising monohydric phenol or oxamate-comprising monohydric phenol. In this latter embodiment the components of a polycarbonate synthesis reaction may comprise at

least one monohydric phenol comprising at least one oxanilide moiety included as a chain-termination agent or at least one monohydric phenol comprising at least one oxamate moiety included as a chain-termination agent. Mixtures of oxanilide-comprising monohydric phenol and oxamate-comprising monohydric phenol may also be employed as chain-termination agents.

Monohydric phenols comprising at least one oxanilide moiety or at least one oxamate moiety include those of formula (VI) and those of formula (IX), respectively. Said oxanilide-comprising monohydric phenol or oxamate-comprising monohydric phenol or a mixture thereof may comprise all or at least a portion of the amount of any chain termination agent added to a polycarbonate synthesis reaction, and subsequently present as structural units in a product polycarbonate. In one embodiment essentially all chain termination agent added to a polycarbonate synthesis reaction comprises an oxanilide moiety or an oxamate moiety or a mixture thereof. In various embodiments, the amount of polycarbonate structural units derived from oxanilide-comprising monohydric phenol or oxamate-comprising monohydric phenol (or a mixture thereof) may be in a range of from 0 mole percent to about 100 mole percent, in other embodiments in a range of from about 1 mole percent and about 100 mole percent, in other embodiments in a range of from about 1 mole percent and about 90 mole percent, in other embodiments in a range of from about 10 mole percent and about 80 mole percent, in other embodiments in a range of from about 20 mole percent and about 70 mole percent, and in still other embodiments in a range of from about 30 mole percent and about 60 mole percent, based on the total amount of structural units derived from monohydric phenol (which includes those derived from both oxanilide- and oxamate-comprising monohydric phenol, and any monohydric phenol not containing an oxanilide or an oxamate moiety).

All or at least a portion of polycarbonate chains may have at least one oxanilide or oxamate structural unit (or a mixture comprising both structural units) attached to at least one terminal point. In one embodiment essentially all of the polycarbonate chains have at least one oxanilide or oxamate structural unit attached to two terminal points on chains. In another embodiment a branching agent is included in a polycarbonate synthesis reaction and essentially all of the polycarbonate chains have

at least one oxanilide or oxamate structural unit attached at a terminal point. Those skilled in the art will recognize that variation in the number of chain ends with at least one oxanilide or oxamate structural unit attached and variation in the types of chain ends (for example, linear or branched) may occur without departing from the scope of the present invention.

In still another embodiment polycarbonates of the present invention comprise oxanilide structural units distributed within a polycarbonate chain and at least one oxanilide or oxamate structural unit attached to at least one terminal point on a polycarbonate chain. In a particular embodiment the components of a polycarbonate synthesis reaction comprise at least one dihydric phenol comprising at least one oxanilide moiety and at least one monohydric phenol comprising at least one oxanilide or oxamate moiety. Illustrative oxanilide-comprising dihydric phenols and oxanilide- or oxamate-comprising monohydric phenols include those described hereinabove. The amount of oxanilide-comprising dihydric phenol in relation to the total amount of dihydric phenol present and the amount of oxanilide- or oxamate-comprising monohydric phenol in relation to the total amount of monohydric phenol present are in the ranges described hereinabove.

Articles comprising a polycarbonate comprising oxanilide structural units (or oxamate structural units) are another embodiment of the present invention. In various embodiments articles may consist essentially of polycarbonates comprising oxanilide structural units (or oxamate structural units), for example in admixture with polycarbonate additives known in the art, such as conventional UV screeners. In other embodiments articles of the present invention are multilayer articles comprising two or more layers, typically in contiguous superposed contact with one another. In various embodiments multilayer articles comprise a substrate layer comprising at least one thermoplastic polymer, thermoset polymer, cellulosic material, glass, ceramic, or metal, and at least one coating layer thereon, said coating layer comprising an oxanilide-comprising polycarbonate. Optionally, the multilayer articles may further comprise an interlayer, for example an adhesive interlayer (or tie layer), between any substrate layer and any coating layer comprising an oxanilide-comprising polycarbonate. Multilayer articles of the invention include, but are not limited to,

those which comprise a substrate layer and a coating layer comprising an oxanilide-comprising polycarbonate; those which comprise a substrate layer with a coating layer comprising said polycarbonate on each side of said substrate layer; and those which comprise a substrate layer and at least one coating layer comprising an oxanilide-comprising polycarbonate with at least one interlayer between a substrate layer and a coating layer. Any interlayer may be transparent and/or may contain an additive, for example a colorant or decorative material such as metal flake. If desired, an overlayer may be included over the coating layer comprising an oxanilide-comprising polycarbonate, for example to provide abrasion or scratch resistance. In one embodiment the substrate layer, coating layer comprising an oxanilide-comprising polycarbonate, and any interlayers or overcoating layers are in contiguous superposed contact with one another. In any embodiment an oxanilide- or oxamate-comprising polycarbonate layer may comprise conventional additives known in the art for use with polycarbonate, including conventional UV screeners, heat stabilizers, flow promoters, lubricants, dyes, pigments, and the like.

Representative multilayer articles which can be made which comprise compositions of the invention include aircraft, automotive, truck, military vehicle (including automotive, aircraft, and water-borne vehicles), and motorcycle exterior and interior components, including panels, quarter panels, rocker panels, trim, fenders, doors, decklids, trunklids, hoods, bonnets, roofs, bumpers, fascia, grilles, mirror housings, pillar appliques, cladding, body side moldings, wheel covers, hubcaps, door handles, spoilers, window frames, headlamp bezels, headlamps, tail lamps, tail lamp housings, tail lamp bezels, license plate enclosures, roof racks, and running boards; enclosures, housings, panels, and parts for outdoor vehicles and devices; enclosures for electrical and telecommunication devices; outdoor furniture; boats and marine equipment, including trim, enclosures, and housings; outboard motor housings; depth finder housings, personal water-craft; jet-skis; pools; spas; hot-tubs; steps; step coverings; building and construction applications such as glazing, roofs, windows, floors, decorative window furnishings or treatments; treated glass covers for pictures, paintings, posters, and like display items; optical lenses; ophthalmic lenses; corrective ophthalmic lenses; implantable ophthalmic lenses; wall panels, and doors; protected


graphics; outdoor and indoor signs; enclosures, housings, panels, and parts for automatic teller machines (ATM); enclosures, housings, panels, and parts for lawn and garden tractors, lawn mowers, and tools, including lawn and garden tools; window and door trim; sports equipment and toys; enclosures, housings, panels, and parts for snowmobiles; recreational vehicle panels and components; playground equipment; articles made from plastic-wood combinations; golf course markers; utility pit covers; computer housings; desk-top computer housings; portable computer housings; lap-top computer housings; palm-held computer housings; monitor housings; printer housings; keyboards; FAX machine housings; copier housings; telephone housings; mobile phone housings; radio sender housings; radio receiver housings; light fixtures; lighting appliances; network interface device housings; transformer housings; air conditioner housings; cladding or seating for public transportation; cladding or seating for trains, subways, or buses; meter housings; antenna housings; cladding for satellite dishes; coated helmets and personal protective equipment; coated synthetic or natural textiles; coated photographic film and photographic prints; coated painted articles; coated dyed articles; coated fluorescent articles; coated foam articles; and like applications. The invention further contemplates additional fabrication operations on said articles, such as, but not limited to, molding, in-mold decoration, baking in a paint oven, lamination, and/or thermoforming.

Without further elaboration, it is believed that one skilled in the art can, using the description herein, utilize the present invention to its fullest extent. The following examples are included to provide additional guidance to those skilled in the art in practicing the claimed invention. While some of the examples are illustrative of various embodiments of the claimed invention, others are comparative. The examples provided are merely representative of the work that contributes to the teaching of the present application. Accordingly, these examples are not intended to limit the invention, as defined in the appended claims, in any manner.

Unless otherwise specified, solvents and reagents were dried by refluxing over calcium hydride. Glass transition temperatures (T_g) were determined by differential scanning calorimetry (DSC) in air at a heating rate of 20°C/minute. Molecular

weights were determined by gel permeation chromatography (GPC) vs. polystyrene standards.


EXAMPLE 1



(XII)

Synthesis of Compound (XII): To a cold (0°C) solution of freshly distilled o-phenetidine (2.61 milliliters [ml], 20 millimoles [mmol]) in dry dichloromethane (50 ml) was added dry triethylamine (4.2 ml, 30 mmol) followed by a dropwise addition of ethyl oxalyl chloride (2.25 ml, 20.4 mmol) over about 10 minutes. The reaction was allowed to warm to room temperature and stirred for one hour. Thin layer chromatographic analysis (TLC) using hexanes/ethyl acetate indicated complete conversion of starting material. The reaction mixture was washed twice with 1 N hydrochloric acid, twice with water and dried over anhydrous sodium sulfate. The solvent was removed under reduced pressure to give the oxamate, compound (XII), greater than 99% pure by high performance liquid chromatography (HPLC), as light yellow crystals with GC-MS: m/e 237.2 (M⁺).

EXAMPLE 2



(VI)

Synthesis of Compound (VI); Ar = 2,2-(4,4'-phenylene)propyl (also known as compound (VIII)) : A mixture of oxamate, compound (XII), (2.415 g, 10.18 mmol) and 2-(4-aminophenyl)-2-(4'-hydroxyphenyl)propane (2.545 g, 11.2 mmol) were

suspended in o-dichlorobenzene (10 ml), degassed, and heated to reflux for 20 hrs. TLC indicated complete conversion of the oxamate. The crude reaction mixture was concentrated under reduced pressure, taken up in dichloromethane, and filtered through a plug of silica gel. The product was recrystallized from hexanes/dichloromethane and again filtered through silica gel, yielding the desired oxanilide as white fine crystals.

EXAMPLE 3

Synthesis of Compound (VI); Ar = 4-phenylene : To a 25 ml flask were added oxamate, compound (XII), (4.65 g, 19.6 mmol), purified p-aminophenol (3g, 27.5 mmol), o-dichlorobenzene (12 ml) and N,N-dimethylacetamide (2 ml). The contents of the flask were degassed with a stream of nitrogen, then heated to 150°C for 10 hrs. TLC indicated complete conversion of the oxamate. The reaction mixture was concentrated under reduced pressure. Excess p-aminophenol was removed by triturating with ethyl acetate and the remaining brown powder was recrystallized from ethyl acetate/ methanol to give the crude product as a light brown powder.

EXAMPLE 4

Synthesis of bis(trifluoroethyl)oxalate: To a dry flask equipped with mechanical stirrer, pressure equalizing addition funnel and reflux condenser, was added dry diethylether (250 ml), trifluoroethanol (69.2 ml, 0.95 mol) and dry pyridine (114 ml, 1.41 mol). To the cold (0°C) mixture was added oxalyl chloride, dropwise (41 ml, 0.47 mol). The contents of the flask were then stirred at room temperature for 30 minutes, and the thick slurry was filtered, and washed with diethyl ether. The filtrate was washed twice with cold 1 N hydrochloric acid, then with water, dried over anhydrous sodium sulfate, and then fractionally distilled. Upon recovering about 20 ml of trifluoroethanol and an intermediate forerun, the main fraction boiling at 159-161°C at normal pressure was collected to provide bis(trifluoroethyl)oxalate as a colorless liquid, fuming in moist air, GC-MS m/e 254.2. GC purity 99.9+%.

EXAMPLE 5

Synthesis of oxanilide-comprising monohydric phenols : An aminophenol is combined with an excess of bis(trifluoroethyl)oxalate, optionally in a solvent such as tetrahydrofuran or ethyl acetate. The mixture is heated, for example, in an ethylene glycol bath at 71.5°C until analysis shows essentially complete disappearance of aminophenol starting material. Excess oxalate is distilled from the mixture and the monohydric phenol product isolated and purified by conventional means.

EXAMPLE 6

General procedure for the synthesis of symmetrical oxanilide-comprising dihydric phenols: To a 50 ml flask were added an aminophenol (50 mmol), bis(trifluoroethyl)oxalate (6.355g, 25 mmol) and either tetrahydrofuran or ethyl acetate (12 ml). The mixture was degassed using nitrogen and heated in an ethylene glycol bath at 71.5°C for about 5 –10 hours. In the case of 2-(4-aminophenyl)-2-(4'-hydroxyphenyl)propane the product was purified by recrystallization from ethyl acetate/isopropanol to provide white needles with the appropriate nuclear magnetic resonance (NMR) spectrum. HPLC analysis showed the product was about 99% pure.

COMPARATIVE EXAMPLE 6

A symmetrical oxanilide-comprising dihydric phenol was made from diethyl oxalate and 2-(4-aminophenyl)-2-(4'-hydroxyphenyl)propane using the procedure of U.S. Patent 5,847,196. A dark-colored product was obtained. TLC showed impurities in the product that were not completely removed by recrystallization.

EXAMPLE 7

General procedure for the synthesis of unsymmetrical oxanilide-comprising dihydric phenols: A first aminophenol is combined with an excess of bis(trifluoroethyl)oxalate, optionally in a solvent such as tetrahydrofuran or ethyl acetate. The mixture is heated, for example, in an ethylene glycol bath at 71.5°C until analysis shows essentially complete disappearance of aminophenol starting material. Excess oxalate is distilled from the mixture. The monohydric phenol product, optionally in a solvent such as

tetrahydrofuran or ethyl acetate, is combined with a second aminophenol and the mixture is heated, for example, in an ethylene glycol bath at 71.5°C until analysis shows essentially complete disappearance of aminophenol. The dihydric phenol product is isolated and purified by conventional means.

EXAMPLE 8

General procedure for the synthesis of phenyl chloroformate capped oxanilides: To a dry 5 ml flask was added the oxanilide-comprising monohydric or dihydric phenol (0.172 mmol), dichloromethane/THF 4/1 (vol/vol) (1.5 ml, dry) and pyridine (30 microliters, 2.1 equivalents [eq.], dry, for difunctional oxanilides or 16 microliters, 1.05 eq., dry, for monofunctional oxanilides). Phenyl chloroformate was then added (46 microliters, 2.1 eq. for difunctional oxanilides or 23 microliters, 1.05 eq. for monofunctional oxanilides) and the mixture was stirred at room temperature until colorless and disappearance of the starting material (TLC). The product was recovered by filtration through a plug of silica gel and recrystallization from ethyl acetate/hexanes.

Ultraviolet (UV) spectra for an oxanilide-comprising monohydric phenol (compound (VIII)) and an oxanilide-comprising dihydric phenol (compound (V)), both capped with phenyl chloroformate, are shown in Figure 1. The spectra indicate no tailing into the visible region of the spectrum, good coverage of the portion of the UV spectrum most responsible for polycarbonate degradation, and quite large extinction coefficients.

EXAMPLE 9

Polycarbonate (A) : An oxanilide-comprising monohydric phenol (compound (VIII)) was incorporated into a polycarbonate at 5 mole %. To a 250 ml phosgenation reactor was added BPA (3.424 g, 15 mmol), oxanilide (VIII) (314 milligrams [mg], 5 mole %, 9.2 wt%), dichloromethane (50 ml), water (40 ml) and triethylamine (45 microliters, 2 mole %). Phosgene was then added (1.8 g, 1.2 eq.) at a rate of 0.25 g/min and the polymer solution was worked up by separating the aqueous and organic layers, washing the organic phase twice with dilute hydrochloric acid and twice with

water, followed by precipitation into hot water to provide a colorless, transparent polymer with Mw 35,000, Mw/Mn 2.3, Tg 148°C.

EXAMPLE 10

Polycarbonate (B) : An oxanilide-comprising dihydric phenol (compound (V)) made by the method of the present invention was incorporated into a polycarbonate at 20 mole %. To a 250 ml phosgenation reactor was added BPA (2.740g, 12 mmol), oxanilide (V) (1.526g, 3 mmol, 35.8 wt%), dichloromethane (70 ml), water (40 ml), p-cumylphenol (110 mg, 3.5 mole %) and triethylamine (45 microliters, 2 mole %). Phosgene was then added (1.8 g, 1.2 eq.) at 0.25 g/min, and the polymer solution was worked up as usual, followed by precipitation into hot water to provide a colorless, transparent polymer with Mw 42,000, Mw/Mn 2.3, Tg 153°C.

COMPARATIVE EXAMPLE 10

Polycarbonate (D) : An oxanilide-comprising dihydric phenol (compound (V)) made by the method of Comparative Example 6 is incorporated into a polycarbonate at 20 mole % using the method for making Polycarbonate B. There is obtained a dark-colored polymer.

EXAMPLE 11

Polycarbonate (C) : An oxanilide-comprising dihydric phenol (compound (V)) made by the method of the present invention was incorporated into a polycarbonate at 50 mole %. To a 250 ml phosgenation reactor was added BPA (1.141g, 5 mmol), oxanilide (V) (2.543g, 5 mmol, 69 wt%), dichloromethane (70 ml), water (40 ml), p-cumylphenol (74 mg, 3.5 mole %) and triethylamine (45 microliters, 2 mole %). Phosgene was then added (1.2 g, 1.2 eq.) at 0.25 g/min, and the polymer solution was worked up as usual, followed by precipitation into hot water to provide a colorless, transparent polymer with Mw 42,000, Mw/Mn 2.3, Tg 155°C.

Multilayer articles comprising a coating layer of either polycarbonate (A) comprising oxanilide structural units as terminal groups or polycarbonates (B) or (C) comprising oxanilide structural units distributed within a polycarbonate chain were prepared

using a substrate comprising a bisphenol-A polycarbonate. In particular bisphenol-A polycarbonate substrate plaques containing 2 wt.% titanium dioxide were coated with a layer about 30 mils thick of oxanilide-comprising polycarbonate A, B, or C by compression molding. The articles were subjected to accelerated weathering in an Atlas Ci35a xenon arc weatherometer equipped with borosilicate inner and outer filters at an irradiance of 0.77 watts per meter squared (W/m^2) at 340 nanometers (nm). The temperatures were: black panel 70°C, dry bulb 45°C, wet bulb depression 10°C. The cycle was 160 minutes (min) light followed by 5 min dark and 15 min dark with water spray. Samples were evaluated for color on a MacBeth ColorEye 7000A colorimeter with results reported as ΔE^* ($\Delta E = (\Delta L^2 + \Delta a^2 + \Delta b^2)^{0.5}$). Color was measured in reflectance mode. Gloss (60°) was measured on a Byk Gardner Micro Trigloss gloss meter. Yellowing index (YI) was measured according to ASTM D1925.

Figure 2 shows the change in yellowing index (delta YI) upon exposure to ultraviolet radiation and Figure 3 shows the change in color (delta E) upon exposure to ultraviolet radiation for plaques of bisphenol-A polycarbonate compared to plaques comprising bisphenol-A polycarbonate with an overlayer of polycarbonate comprising bisphenol-A and oxanilide structural units (Polycarbonates A, B, and C). The results indicate that, after 2,000 hours of continuous exposure, all three sets of the plaques comprising oxanilide-comprising polycarbonates exhibit much lower yellowing and color shift than bisphenol-A polycarbonate control plaques. It is significant that plaques comprising polycarbonate A (comprising oxanilide structural units as terminal groups) shows good UV stabilization of polycarbonate substrate even though oxanilide moieties are present at only limited loading.


While the invention has been illustrated and described in typical embodiments, it is not intended to be limited to the details shown, since various modifications and substitutions can be made without departing in any way from the spirit of the present invention. As such, further modifications and equivalents of the invention herein disclosed may occur to persons skilled in the art using no more than routine experimentation, and all such modifications and equivalents are believed to be within

the spirit and scope of the invention as defined by the following claims. All U.S. Patents cited herein are incorporated herein by reference.

WHAT IS CLAIMED IS:

1.A polycarbonate comprising structural units derived from at least one dihydric phenol, a carbonate precursor, and at least one member selected from the group consisting of an oxanilide-comprising compound, an oxamate-comprising compound, and mixtures thereof.

2.The polycarbonate of claim 1 wherein a dihydric phenol has the structure HO-D-OH, wherein D is a divalent aromatic radical with the structure of formula (III) :




wherein A^1 is an aromatic group; E is at least one alkylene, alkylidene, or cycloaliphatic group; a sulfur-containing linkage; a phosphorus-containing linkage; an ether linkage; a carbonyl group; a tertiary nitrogen group; or a silicon-containing linkage; R^1 is hydrogen or a monovalent hydrocarbon group; Y^1 is selected from the group consisting of a monovalent hydrocarbon group, halogen, bromine, chlorine; nitro; and OR^2 , wherein R^2 is a monovalent hydrocarbon group; "m" represents any integer from and including zero through the number of positions on A^1 available for substitution; "p" represents an integer from and including zero through the number of positions on E available for substitution; "t" represents an integer equal to at least one; "s" is either zero or one; and "u" represents any integer including zero.


3.The polycarbonate of claim 1 wherein the dihydric phenol is at least one member selected from the group consisting of 2,2-bis(4-hydroxyphenyl)propane, 1,1-bis(4-hydroxy-3-methylphenyl)cyclohexane, 3-(4-hydroxyphenyl)-1,1,3-trimethylindan-5-ol, 1-(4-hydroxyphenyl)-1,3,3-trimethylindan-5-ol, and 6,6'-dihydroxy-3,3,3',3'-tetramethyl-1,1'-spirobiindane.

4.The polycarbonate of claim 1 wherein the oxanilide-comprising compound is an oxanilide-comprising dihydric phenol.

5. The polycarbonate of claim 4 wherein the oxanilide-comprising dihydric phenol has the structure of formula (II) :



wherein D and D¹ are each independently a divalent aromatic radical with the structure of formula (III) :



wherein A¹ is an aromatic group; E is at least one alkylene, alkylidene, or cycloaliphatic group; a sulfur-containing linkage; a phosphorus-containing linkage; an ether linkage; a carbonyl group; a tertiary nitrogen group; or a silicon-containing linkage; R¹ is hydrogen or a monovalent hydrocarbon group; Y¹ is selected from the group consisting of a monovalent hydrocarbon group, halogen, bromine, chlorine; nitro; and OR², wherein R² is a monovalent hydrocarbon group; “m” represents any integer from and including zero through the number of positions on A¹ available for substitution; “p” represents an integer from and including zero through the number of positions on E available for substitution; “t” represents an integer equal to at least one; “s” is either zero or one; and “u” represents any integer including zero.

6. The polycarbonate of claim 5 wherein D and D¹ are different.

7. The polycarbonate of claim 5 wherein D and D¹ are the same.

8. The polycarbonate of claim 7 wherein the oxanilide-comprising dihydric phenol is N,N'-bis[4-[1-(4-hydroxyphenyl)-1-methylethyl]phenyl]-ethanediamide.

9. The polycarbonate of claim 4 wherein the amount of structural units derived from oxanilide-comprising dihydric phenol is in a range of between about 0.1 mole percent

and about 80 mole percent, based on the total amount of structural units derived from dihydric phenol.


10. The polycarbonate of claim 4 wherein the amount of structural units derived from oxanilide-comprising dihydric phenol is in a range of between about 0.5 mole percent and about 50 mole percent, based on the total amount of structural units derived from dihydric phenol.

11. The polycarbonate of claim 4 wherein the amount of structural units derived from oxanilide-comprising dihydric phenol is in a range of between about 1 mole percent and about 30 mole percent, based on the total amount of structural units derived from dihydric phenol.


12. The polycarbonate of claim 4 wherein the amount of structural units derived from oxanilide-comprising dihydric phenol is in a range of between about 1 mole percent and about 20 mole percent, based on the total amount of structural units derived from dihydric phenol.

13. The polycarbonate of claim 1 wherein the oxanilide-comprising compound is an oxanilide-comprising monohydric phenol.

14. The polycarbonate of claim 13 wherein the oxanilide-comprising monohydric phenol has the structure of formula (VI) :



wherein D and D¹ are each independently a divalent aromatic radical with the structure of formula (III) :



wherein A^1 is an aromatic group; E is at least one alkylene, alkylidene, or cycloaliphatic group; a sulfur-containing linkage; a phosphorus-containing linkage; an ether linkage; a carbonyl group; a tertiary nitrogen group; or a silicon-containing linkage; R^1 is hydrogen or a monovalent hydrocarbon group; Y^1 is selected from the group consisting of a monovalent hydrocarbon group, halogen, bromine, chlorine; nitro; and OR^2 , wherein R^2 is a monovalent hydrocarbon group; "m" represents any integer from and including zero through the number of positions on A^1 available for substitution; "p" represents an integer from and including zero through the number of positions on E available for substitution; "t" represents an integer equal to at least one; "s" is either zero or one; "u" represents any integer including zero; and R^5 is selected from the group consisting of hydrogen, a monovalent hydrocarbon group; halogen, bromine, chlorine; nitro; and OR^2 , wherein R^2 is a monovalent hydrocarbon group.


15.The polycarbonate of claim 14 wherein the oxanilide-comprising monohydric phenol is N-[4-[1-(4-hydroxyphenyl)-1-methylphenyl]-N'-1-[2-ethoxyphenyl)]-ethanediamide.

16.The polycarbonate of claim 13 wherein structural units derived from oxanilide-comprising monohydric phenol are present at a level in a range of between about 0.1 mole percent and about 10 mole percent based on the total amount of structural units derived from dihydric phenol.


17.The polycarbonate of claim 16 wherein structural units derived from oxanilide-comprising monohydric phenol are in a range of between about 1 mole percent and about 100 mole percent, based on the total amount of structural units derived from chain-termination agent.

18.The polycarbonate of claim 17 wherein structural units derived from oxanilide-comprising monohydric phenol are present at a level of 100 mole percent, based on the total amount of structural units derived from chain-termination agent.

19.The polycarbonate of claim 1 wherein the oxamate-comprising compound is a monohydric phenol with the structure of formula (IX) :



wherein D is a divalent aromatic radical with the structure of formula (III) :



wherein A^1 is an aromatic group; E is at least one alkylene, alkylidene, or cycloaliphatic group; a sulfur-containing linkage; a phosphorus-containing linkage; an ether linkage; a carbonyl group; a tertiary nitrogen group; or a silicon-containing linkage; R^1 is hydrogen or a monovalent hydrocarbon group; Y^1 is selected from the group consisting of a monovalent hydrocarbon group, halogen, bromine, chlorine; nitro; and OR^2 , wherein R^2 is a monovalent hydrocarbon group; “m” represents any integer from and including zero through the number of positions on A^1 available for substitution; “p” represents an integer from and including zero through the number of positions on E available for substitution; “t” represents an integer equal to at least one; “s” is either zero or one; “u” represents any integer including zero; and R^6 is a monovalent hydrocarbon group, optionally substituted with an electron-withdrawing group.

20. The polycarbonate of claim 19 wherein the oxamate-comprising monohydric phenol is a compound of the formula (IX) in which D is a residue derived from 2-(4-aminophenyl)-2-(4'-hydroxyphenyl)propane and R^6 is trifluoroethyl.

21. The polycarbonate of claim 1 comprising structural units derived from both an oxanilide-comprising dihydric phenol and either an oxanilide-comprising monohydric phenol, or an oxamate-comprising monohydric phenol, or both.

22. The polycarbonate of claim 1 wherein the carbonate precursor is selected from the group consisting of phosgene, diaryl carbonate, and diphenyl carbonate.

23.A polycarbonate comprising structural units derived from bisphenol-A, N,N'-bis[4-[1-(4-hydroxyphenyl)-1-methylethyl]phenyl]-ethanediamide, and a carbonate precursor.

24. The polycarbonate of claim 23 comprising structural units derived from N,N'-bis[4-[1-(4-hydroxyphenyl)-1-methylethyl]phenyl]-ethanediamide in an amount in a range of between about 20 mole percent and about 50 mole percent, based on the total amount of structural units derived from dihydric phenol.

25.A polycarbonate comprising structural units derived from bisphenol-A, N-[4-[1-(4-hydroxyphenyl)-1-methylphenyl]-N'-1-[2-ethoxyphenyl]-ethanediamide, and a carbonate precursor.

26.The polycarbonate of claim 25 comprising structural units derived from N-[4-[1-(4-hydroxyphenyl)-1-methylphenyl]-N'-1-[2-ethoxyphenyl]-ethanediamide in an amount in a range of between about 1 mole percent and about 10 mole percent, based on the total amount of structural units derived from dihydric phenol.

27.An article comprising a polycarbonate of claim 1.

28.An article comprising a polycarbonate of claim 4.

29.An article comprising a polycarbonate of claim 8.

30.An article comprising a polycarbonate of claim 13.

31.An article comprising a polycarbonate of claim 15.

32.An article comprising a polycarbonate of claim 19.


33.An article comprising a polycarbonate of claim 21.

34.An article comprising a polycarbonate of claim 23.

35.An article comprising a polycarbonate of claim 25.

36.A method for making a polycarbonate comprising structural units derived from at least one dihydric phenol and at least one member selected from the group consisting of an oxanilide-comprising compound, an oxamate-comprising compound, and mixtures thereof, which comprises the step of contacting under reactive conditions at least one dihydric phenol, a carbonate precursor, and at least one member selected from the group consisting of an oxanilide-comprising compound, an oxamate-comprising compound, and mixtures thereof.

37.The method of claim 36 wherein a dihydric phenol has the structure HO-D-OH, wherein D is a divalent aromatic radical with the structure of formula (III):




wherein A^1 is an aromatic group; E is at least one alkylene, alkylidene, or cycloaliphatic group; a sulfur-containing linkage; a phosphorus-containing linkage; an ether linkage; a carbonyl group; a tertiary nitrogen group; or a silicon-containing linkage; R^1 is hydrogen or a monovalent hydrocarbon group; Y^1 is selected from the group consisting of a monovalent hydrocarbon group, halogen, bromine, chlorine; nitro; and OR^2 , wherein R^2 is a monovalent hydrocarbon group; "m" represents any integer from and including zero through the number of positions on A^1 available for substitution; "p" represents an integer from and including zero through the number of positions on E available for substitution; "t" represents an integer equal to at least one; "s" is either zero or one; and "u" represents any integer including zero.


38.The method of claim 37 wherein the dihydric phenol is at least one member selected from the group consisting of 2,2-bis(4-hydroxyphenyl)propane, 1,1-bis(4-hydroxy-3-methylphenyl)cyclohexane, 3-(4-hydroxyphenyl)-1,1,3-trimethylindan-5-ol, 1-(4-hydroxyphenyl)-1,3,3-trimethylindan-5-ol, and 6,6'-dihydroxy-3,3,3',3'-tetramethyl-1,1'-spirobiindane.

39. The method of claim 36 wherein the oxanilide-comprising compound is an oxanilide-comprising dihydric phenol.

40. The method of claim 39 wherein the oxanilide-comprising dihydric phenol has the structure of the formula (II) :



wherein D and D¹ are each independently a divalent aromatic radical with the structure of formula (III) :



wherein A¹ is an aromatic group; E is at least one alkylene, alkylidene, or cycloaliphatic group; a sulfur-containing linkage; a phosphorus-containing linkage; an ether linkage; a carbonyl group; a tertiary nitrogen group; or a silicon-containing linkage; R¹ is hydrogen or a monovalent hydrocarbon group; Y¹ is selected from the group consisting of a monovalent hydrocarbon group, halogen, bromine, chlorine; nitro; and OR², wherein R² is a monovalent hydrocarbon group; “m” represents any integer from and including zero through the number of positions on A¹ available for substitution; “p” represents an integer from and including zero through the number of positions on E available for substitution; “t” represents an integer equal to at least one; “s” is either zero or one; and “u” represents any integer including zero.

41. The method of claim 40 wherein D and D¹ are different.

42. The method of claim 40 wherein D and D¹ are the same.

43. The method of claim 42 wherein the oxanilide-comprising dihydric phenol is N,N'-bis[4-[1-(4-hydroxyphenyl)-1-methylethyl]phenyl]-ethanediamide.

44.The method of claim 39 wherein the amount of structural units derived from oxanilide-comprising dihydric phenol is in a range of between about 0.1 mole percent and about 80 mole percent, based on the total amount of structural units derived from dihydric phenol.


45.The method of claim 39 wherein the amount of structural units derived from oxanilide-comprising dihydric phenol is in a range of between about 0.5 mole percent and about 50 mole percent, based on the total amount of structural units derived from dihydric phenol.

46.The method of claim 39 wherein the amount of structural units derived from oxanilide-comprising dihydric phenol in a range of between about 1 mole percent and about 30 mole percent, based on the total amount of structural units derived from dihydric phenol.


47.The method of claim 39 wherein the amount of structural units derived from oxanilide-comprising dihydric phenol in a range of between about 1 mole percent and about 20 mole percent, based on the total amount of structural units derived from dihydric phenol.

48.The method of claim 36 wherein the oxanilide-comprising compound is an oxanilide-comprising monohydric phenol.

49.The method of claim 48 wherein the oxanilide-comprising monohydric phenol has the structure of formula (VI) :



wherein D and D¹ are each independently a divalent aromatic radical with the structure of formula (III) :



wherein A^1 is an aromatic group; E is at least one alkylene, alkylidene, or cycloaliphatic group; a sulfur-containing linkage; a phosphorus-containing linkage; an ether linkage; a carbonyl group; a tertiary nitrogen group; or a silicon-containing linkage; R^1 is hydrogen or a monovalent hydrocarbon group; Y^1 is selected from the group consisting of a monovalent hydrocarbon group, halogen, bromine, chlorine; nitro; and OR^2 , wherein R^2 is a monovalent hydrocarbon group; “m” represents any integer from and including zero through the number of positions on A^1 available for substitution; “p” represents an integer from and including zero through the number of positions on E available for substitution; “t” represents an integer equal to at least one; “s” is either zero or one; “u” represents any integer including zero; and R^5 is selected from the group consisting of hydrogen, a monovalent hydrocarbon group; halogen, bromine, chlorine; nitro; and OR^2 , wherein R^2 is a monovalent hydrocarbon group.


50.The method of claim 49 wherein the oxanilide-comprising monohydric phenol is N-[4-[1-(4-hydroxyphenyl)-1-methylphenyl]-N'-1-[2-ethoxyphenyl]-ethanediamide.

51.The method of claim 48 wherein structural units derived from oxanilide-comprising monohydric phenol are present at a level in a range of between about 0.1 mole percent and about 10 mole percent based on the total amount of structural units derived from dihydric phenol.


52.The method of claim 48 wherein the amount of structural units derived from oxanilide-comprising monohydric phenol is in a range of between about 1 mole percent and about 100 mole percent, based on the total amount of structural units derived from chain-termination agent.

53.The method of claim 48 wherein the amount of structural units derived from oxanilide-comprising monohydric phenol is 100 mole percent, based on the total amount of structural units derived from chain-termination agent.

54. The method of claim 36 wherein the oxamate-comprising compound is a monohydric phenol with the structure of formula (IX) :



wherein D is a divalent aromatic radical with the structure of formula (III) :



wherein A^1 is an aromatic group; E is at least one alkylene, alkylidene, or cycloaliphatic group; a sulfur-containing linkage; a phosphorus-containing linkage; an ether linkage; a carbonyl group; a tertiary nitrogen group; or a silicon-containing linkage; R^1 is hydrogen or a monovalent hydrocarbon group; Y^1 is selected from the group consisting of a monovalent hydrocarbon group, halogen, bromine, chlorine; nitro; and OR^2 , wherein R^2 is a monovalent hydrocarbon group; "m" represents any integer from and including zero through the number of positions on A^1 available for substitution; "p" represents an integer from and including zero through the number of positions on E available for substitution; "t" represents an integer equal to at least one; "s" is either zero or one; "u" represents any integer including zero; and R^6 is a monovalent hydrocarbon group, optionally substituted with an electron-withdrawing group.

55. The method of claim 54 wherein the oxamate-comprising monohydric phenol is a compound of the formula (IX) in which D is a residue derived from 2-(4-aminophenyl)-2-(4'-hydroxyphenyl)propane and R^6 is trifluoroethyl.

56. The method of claim 36 wherein the polycarbonate comprises structural units derived from both an oxanilide-comprising dihydric phenol and either an oxanilide-

comprising monohydric phenol, or an oxamate-comprising monohydric phenol, or both.

57. The method of claim 36 wherein the carbonate precursor is selected from the group consisting of phosgene, diaryl carbonate, and diphenyl carbonate.

58. The method of claim 36 wherein the step of contacting under reactive conditions is selected from the group consisting of a solution process, an interfacial process, a melt process, a transesterification process, a solid-state process, and a redistribution process, and combinations thereof.

59. A method for making a polycarbonate comprising oxanilide structural units which comprises the step of contacting under reactive conditions bisphenol-A, N,N'-bis[4-[1-(4-hydroxyphenyl)-1-methylethyl]phenyl]-ethanediamide, and a carbonate precursor.

60. The method of claim 59 wherein the polycarbonate comprises structural units derived from N,N'-bis[4-[1-(4-hydroxyphenyl)-1-methylethyl]phenyl]-ethanediamide in an amount in a range of between about 20 mole percent and about 50 mole percent, based on the total amount of structural units derived from dihydric phenol.

61. The method of claim 59 wherein the step of contacting under reactive conditions is selected from the group consisting of a solution process, an interfacial process, a melt process, a transesterification process, a solid-state process, or a redistribution process, or a combination thereof.


62. A method for making a polycarbonate comprising oxanilide structural units which comprises the step of contacting under reactive conditions bisphenol-A, N-[4-[1-(4-hydroxyphenyl)-1-methylphenyl]-N'-1-[2-ethoxyphenyl]-ethanediamide, and a carbonate precursor.

63. The method of claim 62 wherein the polycarbonate comprises structural units derived from N-[4-[1-(4-hydroxyphenyl)-1-methylphenyl]-N'-1-[2-ethoxyphenyl]-ethanediamide in an amount in a range of between about 1 mole percent and about 10


mole percent, based on the total amount of structural units derived from dihydric phenol.

64. The method of claim 62 wherein the step of contacting under reactive conditions is selected from the group consisting of a solution process, an interfacial process, a melt process, a transesterification process, a solid-state process, or a redistribution process, or a combination thereof.

65. An oxanilide-comprising monohydric phenol having the structure of formula (VI) :




wherein D and D¹ are each independently a divalent aromatic radical with the structure of formula (III) :




wherein A¹ is an aromatic group; E is at least one alkylene, alkylidene, or cycloaliphatic group; a sulfur-containing linkage; a phosphorus-containing linkage; an ether linkage; a carbonyl group; a tertiary nitrogen group; or a silicon-containing linkage; R¹ is hydrogen or a monovalent hydrocarbon group; Y¹ is selected from the group consisting of a monovalent hydrocarbon group, halogen, bromine, chlorine; nitro; and OR², wherein R² is a monovalent hydrocarbon group; "m" represents any integer from and including zero through the number of positions on A¹ available for substitution; "p" represents an integer from and including zero through the number of positions on E available for substitution; "t" represents an integer equal to at least one; "s" is either zero or one; "u" represents any integer including zero; and R⁵ is selected from the group consisting of hydrogen, a monovalent hydrocarbon group; halogen, bromine, chlorine; nitro; and OR², wherein R² is a monovalent hydrocarbon group.

66. The oxanilide-comprising monohydric phenol of claim 65 which is N-[4-[1-(4-hydroxyphenyl)-1-methylphenyl]-N'-1-[2-ethoxyphenyl]-ethanediamide.

67. An oxanilide-comprising monohydric phenol having the structure of formula (IX) :




wherein D is a divalent aromatic radical with the structure of formula (III) :



wherein A^1 is an aromatic group; E is at least one alkylene, alkylidene, or cycloaliphatic group; a sulfur-containing linkage; a phosphorus-containing linkage; an ether linkage; a carbonyl group; a tertiary nitrogen group; or a silicon-containing linkage; R^1 is hydrogen or a monovalent hydrocarbon group; Y^1 is selected from the group consisting of a monovalent hydrocarbon group, halogen, bromine, chlorine; nitro; and OR^2 , wherein R^2 is a monovalent hydrocarbon group; "m" represents any integer from and including zero through the number of positions on A^1 available for substitution; "p" represents an integer from and including zero through the number of positions on E available for substitution; "t" represents an integer equal to at least one; "s" is either zero or one; "u" represents any integer including zero; and R^6 is a monovalent hydrocarbon group substituted with an electron-withdrawing group.

68. The oxanilide-comprising monohydric phenol of claim 67 which is a compound of the formula (IX) in which D is a residue derived from 2-(4-aminophenyl)-2-(4'-hydroxyphenyl)propane and R^6 is trifluoroethyl.

69. An oxanilide-comprising monohydric phenol with the structure of the formula :




wherein R^3 is an alkylene, alkylidene, or cycloaliphatic group; R^4 and R^5 are each independently halogen, bromo, chloro, alkyl, aryl, aralkyl, alkaryl, cycloalkyl, or OR^2 , wherein R^2 is a monovalent hydrocarbon group; and "x" and "j" represent any integer from and including zero through the number of positions on the aromatic ring available for substitution.

70. The monohydric phenol of claim 69 which is N-[4-[1-(4-hydroxyphenyl)-1-methylphenyl]-N'-1-[2-ethoxyphenyl]-ethanediamide.


71. A method for making a symmetrical oxanilide-comprising dihydric phenol which comprises the step of contacting an aromatic amine bearing a hydroxy group with a diaryl oxalate or a dialkyl oxalate bearing alkyl groups each substituted with at least one electron-withdrawing group.

72. The method of claim 71 wherein the electron-withdrawing group is fluoro or chloro.

73. The method of claim 71 wherein the oxanilide-comprising dihydric phenol has the structure of the formula:



wherein D is a divalent aromatic radical with the structure of formula (III) :



wherein A^1 is an aromatic group; E is at least one alkylene, alkylidene, or cycloaliphatic group; a sulfur-containing linkage; a phosphorus-containing linkage; an ether linkage; a carbonyl group; a tertiary nitrogen group; or a silicon-containing linkage; R^1 is hydrogen or a monovalent hydrocarbon group; Y^1 is selected from the group consisting of a monovalent hydrocarbon group, halogen, bromine, chlorine; nitro; and OR^2 , wherein R^2 is a monovalent hydrocarbon group; "m" represents any integer from and including zero through the number of positions on A^1 available for substitution; "p" represents an integer from and including zero through the number of positions on E available for substitution; "t" represents an integer equal to at least one; "s" is either zero or one; and "u" represents any integer including zero.


74.The method of claim 71 wherein the temperature of contacting is in a range of between about 30°C and about 100°C.

75.A method for making a symmetrical oxanilide-comprising dihydric phenol which comprises the step of contacting an aromatic amine selected from the group consisting of 3-aminophenol, 4-aminophenol, and 2-(4-aminophenyl)-2-(4'-hydroxyphenyl)propane, with bis(trifluoroethyl)oxalate at a temperature in a range of between about 30°C and about 100°C.


76.A method for making an unsymmetrical oxanilide-comprising dihydric phenol which comprises the steps of contacting an aromatic amine bearing a hydroxy group with a diaryl oxalate or a dialkyl oxalate bearing alkyl groups each substituted with at least one electron-withdrawing group, followed by contacting the oxamate intermediate with a second aromatic amine bearing a hydroxy group and different from said first aromatic amine.

77.The method of claim 76 wherein the electron-withdrawing group is fluoro or chloro.

78.The method of claim 76 wherein the oxanilide-comprising dihydric phenol has the structure of the formula (II) :



wherein D and D¹ are each independently a divalent aromatic radical with the structure of formula (III) :



wherein A¹ is an aromatic group; E is at least one alkylene, alkylidene, or cycloaliphatic group; a sulfur-containing linkage; a phosphorus-containing linkage; an ether linkage; a carbonyl group; a tertiary nitrogen group; or a silicon-containing linkage; R¹ is hydrogen or a monovalent hydrocarbon group; Y¹ is selected from the group consisting of a monovalent hydrocarbon group, halogen, bromine, chlorine; nitro; and OR², wherein R² is a monovalent hydrocarbon group; "m" represents any integer from and including zero through the number of positions on A¹ available for substitution; "p" represents an integer from and including zero through the number of positions on E available for substitution; "t" represents an integer equal to at least one; "s" is either zero or one; and "u" represents any integer including zero.


79.The method of claim 76 wherein the temperature of contacting is in a range of between about 30°C and about 100°C.

80.A method for making an unsymmetrical oxanilide-comprising dihydric phenol which comprises the steps of contacting an aromatic amine bearing a hydroxy group with bis(trifluoroethyl)oxalate, followed by contacting the oxamate intermediate with a second aromatic amine bearing a hydroxy group and different from said first aromatic amine, wherein the aromatic amines are selected from the group consisting of 3-aminophenol, 4-aminophenol, and 2-(4-aminophenyl)-2-(4'-hydroxyphenyl)propane, and in each step the temperature of contacting is in a range of between about 30°C and about 100°C.


81.A method for making an oxanilide-comprising monohydric phenol which comprises the steps of contacting an aromatic amine with a diaryl oxalate or a dialkyl oxalate bearing alkyl groups each substituted with at least one electron-withdrawing group, followed by contacting the oxamate intermediate with a second aromatic amine different from said first aromatic amine, wherein only one aromatic amine bears a hydroxy group.

82.The method of claim 81 wherein the electron-withdrawing group is fluoro or chloro.

83.The method of claim 81 wherein an oxanilide-comprising monohydric phenol has the structure of formula (VI) :



wherein D and D¹ are each independently a divalent aromatic radical with the structure of formula (III) :



wherein A¹ is an aromatic group; E is at least one alkylene, alkylidene, or cycloaliphatic group; a sulfur-containing linkage; a phosphorus-containing linkage; an ether linkage; a carbonyl group; a tertiary nitrogen group; or a silicon-containing linkage; R¹ is hydrogen or a monovalent hydrocarbon group; Y¹ is selected from the group consisting of a monovalent hydrocarbon group, halogen, bromine, chlorine; nitro; and OR², wherein R² is a monovalent hydrocarbon group; “m” represents any integer from and including zero through the number of positions on A¹ available for substitution; “p” represents an integer from and including zero through the number of positions on E available for substitution; “t” represents an integer equal to at least one;

“s” is either zero or one; “u” represents any integer including zero; and R^5 is selected from the group consisting of hydrogen, a monovalent hydrocarbon group; halogen, bromine, chlorine; nitro; and OR^2 , wherein R^2 is a monovalent hydrocarbon group.


84. The method of claim 81 wherein the temperature of contacting is in a range of between about 30°C and about 100°C.

85. A method for making an oxanilide-comprising monohydric phenol which comprises the steps of contacting an aromatic amine with bis(trifluoroethyl)oxalate, followed by contacting the oxamate intermediate with a second aromatic amine different from said first aromatic amine, wherein only one aromatic amine bears a hydroxy group and wherein the aromatic amines are selected from the group consisting of aniline, phenetidine, 3-aminophenol, 4-aminophenol, and 2-(4-aminophenyl)-2-(4'-hydroxyphenyl)propane, and in each step the temperature of contacting is in a range of between about 30°C and about 100°C.


86. A method for making an oxamate-comprising monohydric phenol which comprises the step of contacting an aromatic amine bearing a hydroxy group with a diaryl oxalate or a dialkyl oxalate bearing alkyl groups each substituted with at least one electron-withdrawing group.

87. The method of claim 86 wherein the electron-withdrawing group is fluoro or chloro.

88. The method of claim 86 wherein an oxanilide-comprising monohydric phenol has the structure of formula (IX) :



wherein D is a divalent aromatic radical with the structure of formula (III) :



wherein A^1 is an aromatic group; E is at least one alkylene, alkylidene, or cycloaliphatic group; a sulfur-containing linkage; a phosphorus-containing linkage; an ether linkage; a carbonyl group; a tertiary nitrogen group; or a silicon-containing linkage; R^1 is hydrogen or a monovalent hydrocarbon group; Y^1 is selected from the group consisting of a monovalent hydrocarbon group, halogen, bromine, chlorine; nitro; and OR^2 , wherein R^2 is a monovalent hydrocarbon group; "m" represents any integer from and including zero through the number of positions on A^1 available for substitution; "p" represents an integer from and including zero through the number of positions on E available for substitution; "t" represents an integer equal to at least one; "s" is either zero or one; "u" represents any integer including zero; and R^6 is a monovalent hydrocarbon group substituted with an electron-withdrawing group.

89.The method of claim 88 wherein the electron-withdrawing group is fluoro or chloro.

90.The method of claim 86 wherein the temperature of contacting is in a range of between about 30°C and about 100°C.

91.A method for making an oxamate-comprising monohydric phenol which comprises the step of contacting an aromatic amine bearing a hydroxy group with bis(trifluoroethyl)oxalate, wherein the aromatic amines are selected from the group consisting of 3-aminophenol, 4-aminophenol, and 2-(4-aminophenyl)-2-(4'-hydroxyphenyl)propane, and in each step the temperature of contacting is in a range of between about 30°C and about 100°C.

92.A dialkyl oxalate bearing alkyl groups each substituted with at least one electron-withdrawing group, wherein the electron-withdrawing group is at least one member selected from the group consisting of chloro and fluoro.

93. The dialkyl oxalate of claim 92 which is bis(trifluoroethyl)oxalate.




Fig. 1




Fig. 2




Fig. 3

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/21433

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08G64/12 C07C233/56 C07C231/02 C07C69/36

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08G C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, EPO-Internal, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 698 732 A (LIKIBI PARFAIT JEAN MARIE) 16 December 1997 (1997-12-16) cited in the application column 1, line 25 - column 2, line 8 column 2, line 19 - line 44 examples column 6, line 5 - line 12 claims --- -/--	1-24, 27-34, 36-61, 67,68, 71-79, 81-84, 86-90

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

28 March 2003

Date of mailing of the international search report

11.04.2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Masson, P

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/21433

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 847 196 A (LIKIBI PARFAIT JEAN MARIE) 8 December 1998 (1998-12-08) column 1, line 25 -column 2, line 11 column 2, line 22 - line 46 column 5, line 36 - line 44 claims; examples ---	1-24, 27-34, 36-61, 67,68, 71-79, 81-84, 86-90
A	US 3 221 562 A (BORCHER CHARLES A ET AL) 7 December 1965 (1965-12-07)	1-70
X	the whole document ---	71-74
X	FR 2 671 552 A (PF MEDICAMENT) 17 July 1992 (1992-07-17)	67,68
A	page 1, line 1 - line 24 composé 7 claims ---	71-93
X	EP 0 116 931 A (BASF AG) 29 August 1984 (1984-08-29)	65,66
X	page 1, line 27 - line 36 page 3, line 16 -page 4, line 36; claims ---	76-84
X	US 4 003 875 A (LUTHI CHRISTIAN ET AL) 18 January 1977 (1977-01-18)	65,66
X	column 9, line 26 - line 56 examples compounds 26, 78,59,68,72,94,101,110,113,118,125,129,134, 138,164,168,174 ---	76-84
X	US 6 159 482 A (TULOUP REMY ET AL) 12 December 2000 (2000-12-12)	67,68
X	column 2, line 47 -column 3, line 26 column 4, line 65 -column 5, line 15; claims; example 1 ---	86-90
X	DE 42 33 973 A (SANDOZ AG) 15 April 1993 (1993-04-15)	65,66
X	page 2, line 8 - line 10 page 3, line 49 - line 62 claims ---	76-84
A	US 5 587 151 A (RICHARD HERVE ET AL) 24 December 1996 (1996-12-24)	1-70
A	the whole document ---	71-93
	-/--	

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/21433

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 580 550 A (CIBA GEIGY AG) 26 January 1994 (1994-01-26)	67,68
X	page 2, line 17 - line 52 page 3, line 54 - page 4, line 18 claims; examples 10,11,14,16,17,19-21,25,26,29-34,36 ----	86-90
X	DATABASE WPI Week 9217 Derwent Publications Ltd., London, GB; AN 1992-138028 XP002227791 & JP 04 080244 A (ASAHI DENKA KOGYO KK) abstract ----	65,66
A		71-93
X	US 3 904 674 A (ROWLEY GERALD L ET AL) 9 September 1975 (1975-09-09) column 1, line 11 - line 31 column 2, line 22 - line 34 claims; example 1 ----	92
A	US 4 113 880 A (WRIGHT JOHN B ET AL) 12 September 1978 (1978-09-12) the whole document ----	71-93
A	US 4 017 538 A (HALL CHARLES M ET AL) 12 April 1977 (1977-04-12) the whole document ----	71-93
A	DATABASE WPI Section Ch, Week 199135 Derwent Publications Ltd., London, GB; Class E14, AN 1991-256650 XP002236442 & JP 03 167154 A (SHINETSU CHEM IND CO LTD), 19 July 1991 (1991-07-19) abstract ----	71-93
X	US 6 236 398 B1 (HASHIMOTO TAKESHI ET AL) 22 May 2001 (2001-05-22) the whole document ----	86-90
X	US 3 993 679 A (WRIGHT JOHN B ET AL) 23 November 1976 (1976-11-23) the whole document -----	86-90

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US 02/21433

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

see additional sheet

1. ☒ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☒ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. Claims: 1-70

Polycarbonates containing special monomers (oxanilide and oxamate compounds), articles therefrom, methods of making the polycarbonates and special comonomers (oxanilide and oxamate compounds).

2. Claims: 71-93

Method for making oxanilide and oxamate compounds and products (oxalates) for making such compounds.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/21433

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5698732	A	16-12-1997	EP 0853080 A1 JP 10310564 A SG 60183 A1 US 5847196 A	15-07-1998 24-11-1998 22-02-1999 08-12-1998
US 5847196	A	08-12-1998	US 5698732 A EP 0853080 A1 JP 10310564 A SG 60183 A1	16-12-1997 15-07-1998 24-11-1998 22-02-1999
US 3221562	A	07-12-1965	NONE	
FR 2671552	A	17-07-1992	FR 2671552 A1 WO 9212972 A1	17-07-1992 06-08-1992
EP 0116931	A	29-08-1984	DE 3305638 A1 DE 3460408 D1 EP 0116931 A1	23-08-1984 11-09-1986 29-08-1984
US 4003875	A	18-01-1977	CH 480867 A CH 512933 A AT 271391 B BE 693605 A CH 503695 A DE 1618196 A1 DE 1618197 A1 ES 336503 A1 FR 1516276 A GB 1177094 A GB 1177095 A NL 6701776 A ,B NL 6701777 A ,B, SE 347959 B SE 346103 B US 3529982 A US 3661606 A AT 271390 B	15-11-1969 30-09-1971 27-05-1969 03-08-1967 28-02-1971 09-12-1971 09-12-1971 01-01-1968 08-03-1968 07-01-1970 07-01-1970 08-08-1967 08-08-1967 21-08-1972 26-06-1972 22-09-1970 09-05-1972 27-05-1969
US 6159482	A	12-12-2000	FR 2767689 A1 DE 69801878 D1 DE 69801878 T2 EP 0898956 A1 ES 2167852 T3 JP 3023088 B2 JP 11116425 A US 6326014 B1	05-03-1999 08-11-2001 28-03-2002 03-03-1999 16-05-2002 21-03-2000 27-04-1999 04-12-2001
DE 4233973	A	15-04-1993	DE 4233973 A1 FR 2682392 A1 GB 2260764 A IT 1263005 B JP 5214254 A	15-04-1993 16-04-1993 28-04-1993 23-07-1996 24-08-1993
US 5587151	A	24-12-1996	FR 2727114 A1 AT 162793 T AU 678912 B2 AU 3438195 A BR 9504906 A	24-05-1996 15-02-1998 12-06-1997 23-05-1996 02-09-1997

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/21433

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5587151	A		CA 2163072 A1	18-05-1996
			CN 1131671 A , B	25-09-1996
			DE 69501542 D1	05-03-1998
			DE 69501542 T2	14-05-1998
			EP 0712856 A1	22-05-1996
			ES 2117369 T3	01-08-1998
			HU 74043 A2	28-10-1996
			JP 2821404 B2	05-11-1998
			JP 8208669 A	13-08-1996
			KR 217969 B1	01-10-1999
			PL 311398 A1	27-05-1996
			RU 2126010 C1	10-02-1999
			ZA 9509068 A	17-05-1996
EP 0580550	A	26-01-1994	AT 159515 T	15-11-1997
			AU 4208193 A	27-01-1994
			CA 2100817 A1	22-01-1994
			DE 69314718 D1	27-11-1997
			DE 69314718 T2	26-02-1998
			DK 580550 T3	02-02-1998
			EP 0580550 A1	26-01-1994
			ES 2108855 T3	01-01-1998
			FI 933260 A	22-01-1994
			GR 3025517 T3	27-02-1998
			HU 64512 A2	28-01-1994
			JP 6172275 A	21-06-1994
			NO 932614 A	24-01-1994
			NZ 248181 A	27-11-1995
			US 5401772 A	28-03-1995
			US 5569674 A	29-10-1996
			US 5654468 A	05-08-1997
			ZA 9305196 A	07-07-1994
JP 4080244	A	13-03-1992	JP 2831817 B2	02-12-1998
US 3904674	A	09-09-1975	CA 977363 A1	04-11-1975
US 4113880	A	12-09-1978	BE 860918 A1	17-05-1978
			CA 1097680 A1	17-03-1981
			CH 640509 A5	13-01-1984
			DE 2746385 A1	18-05-1978
			FR 2371421 A1	16-06-1978
			GB 1569682 A	18-06-1980
			JP 53063342 A	06-06-1978
			JP 61011218 B	01-04-1986
			NL 7712001 A	19-05-1978
US 4017538	A	12-04-1977	GB 1508276 A	19-04-1978
JP 3167154	A	19-07-1991	JP 1998571 C	08-12-1995
			JP 7017575 B	01-03-1995
US 6236398	B1	22-05-2001	JP 10232757 A	02-09-1998
			GB 2322463 A , B	26-08-1998
US 3993679	A	23-11-1976	AU 6298073 A	29-05-1975
			CA 1030156 A1	25-04-1978
			CH 605662 A5	13-10-1978

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/21433

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3993679	A	DE 2362409 A1	27-06-1974
		ES 421536 A1	16-07-1976
		FR 2211230 A1	19-07-1974
		GB 1454778 A	03-11-1976
		GB 1454777 A	03-11-1976
		HK 10982 A	19-03-1982
		HU 168135 B	28-02-1976
		JP 1170994 C	17-10-1983
		JP 49108029 A	14-10-1974
		JP 57061028 B	22-12-1982
		MX 4294 E	17-03-1982
		NL 7316916 A , B,	24-06-1974
		SE 410965 B	19-11-1979
		US 3972911 A	03-08-1976
		US 4089973 A	16-05-1978
		US 4095028 A	13-06-1978
		US 4186127 A	29-01-1980
		US 4159278 A	26-06-1979
		BE 808898 A1	20-06-1974
		PL 91159 B1	28-02-1977
		US 4281151 A	28-07-1981
		ZA 7309037 A	26-03-1975