

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
25 July 2002 (25.07.2002)

PCT

(10) International Publication Number  
**WO 02/057383 A1**

(51) International Patent Classification<sup>7</sup>: **C09J 7/02**, 11/08, 7/00, C08K 7/02, A61L 15/58, C09J 133/08

(21) International Application Number: PCT/US01/18500

(22) International Filing Date: 8 June 2001 (08.06.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
09/764,478 17 January 2001 (17.01.2001) US

(71) Applicant: **3M INNOVATIVE PROPERTIES COMPANY** [US/US]; 3M Center, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(72) Inventors: **ZHIMING, Zhou**; Post Office Box 33427, Saint Paul, MN 55133-3427 (US). **EVERAERTS, Albert, I.**; Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(74) Agents: **BLANK, Colene, H.** et al.; Office of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AT (utility model), AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, CZ (utility model), DE, DE (utility model), DK, DK (utility model), DM, DZ, EC, EE, EE (utility model), ES, FI, FI (utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

**Published:**

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: PRESSURE SENSITIVE ADHESIVES WITH A FIBROUS REINFORCING MATERIAL

(57) Abstract: This invention is directed to a fiber reinforced adhesive composition comprising a pressure sensitive adhesive matrix and a fibrous reinforcing material within the pressure sensitive adhesive matrix. The adhesive composition has a yield strength and a tensile strength. The tensile strength is at least about 150 % of the yield strength. Generally, the adhesive composition exhibits these properties at least 50 % elongation when measured according to ASTM D 882-97 at a crosshead speed of 12 inches/minute (30 centimeters/minute).



WO 02/057383 A1

## **PRESSURE SENSITIVE ADHESIVES WITH A FIBROUS REINFORCING MATERIAL**

## Field of the Invention

The present invention relates to pressure sensitive adhesive compositions. In particular, the invention discloses fiber reinforced pressure sensitive adhesives and methods for their preparation and use.

## Background of the Invention

Pressure sensitive adhesives are generally characterized by their properties. Pressure sensitive adhesives are well known to one of ordinary skill in the art to possess properties including the following: (1) aggressive and permanent tack, (2) adherence to a substrate with no more than finger pressure, (3) sufficient ability to hold onto an adherend, and (4) sufficient cohesive strength to be removed cleanly from the adherend. Many pressure sensitive adhesives must satisfy these properties under an array of different stress rate conditions. Additives may be included in the pressure sensitive adhesive to optimize the characteristics of the pressure sensitive adhesive.

In particular systems, the additive improves the cohesive strength of the pressure sensitive adhesives, yet the tack is reduced. For example, a non-tacky additive may be mixed with a pressure sensitive adhesive, reducing the tack of the mixture (as compared to the tack of the pressure sensitive adhesive without the additive). In a specific example, thermoplastic polymers have been added to styrene block copolymer adhesives to reduce the tack of the resulting pressure sensitive adhesives. However, to avoid loss of tack when enhancing the pressure sensitive adhesive's cohesive strength, care must be taken in choosing an additive.

U.S. Patent Number 6,063,838 discloses a pressure sensitive adhesive comprising a blend of at least two components, wherein the first component is at least one pressure sensitive adhesive and the second component is at least one thermoplastic material, wherein the components form a blended composition having more than one domain and, wherein one domain is substantially continuous (generally, the pressure sensitive adhesive) and the other domain is substantially fibrillous to schistose (generally, the thermoplastic material). The blended pressure sensitive adhesives of the 6,063,838 patent

provide adhesives having one or more of the following properties including: (1) a peel adhesion greater than and shear strength similar to that of the pressure sensitive adhesive component if used alone, (2) a shear strength greater than and peel adhesion similar to that of the pressure sensitive adhesive component if used alone, (3) an anisotropic peel adhesion, (4) an anisotropic shear strength, (5) a tensile stress in the down-web direction that is at least two times greater than the tensile stress in the cross-web direction for all elongations up to the break elongation, and (6) a resistance to impact shear that is at least two times greater than that of the pressure sensitive adhesive component if used alone.

What is desired is an adhesive composition that has improved cohesive strength without losing the tackiness indicative of a pressure sensitive adhesive. In conjunction, it is desirable to create an adhesive composition that is removable from a substrate with ease without losing the tackiness indicative of a pressure sensitive adhesive. Additionally, a stretch removable adhesive composition is desirable.

#### Summary of the Invention

This invention is directed to a fiber reinforced adhesive composition comprising a pressure sensitive adhesive matrix and a fibrous reinforcing material within the pressure sensitive adhesive matrix. The fiber reinforced adhesive composition of the invention allows for an improved cohesive strength over the pressure sensitive adhesive alone, yet the tack of the pressure sensitive adhesive remains substantially unreduced.

The adhesive composition has a yield strength and a tensile strength. In one embodiment, the tensile strength is about 0.7 MPa or greater. In another embodiment, the tensile strength is at least about 150% of the yield strength when tested according to ASTM D 882-97 at a crosshead speed of 12 inches/minute (30 centimeters/minute). In one embodiment, the adhesive composition exhibits at least 50% elongation when measured according to ASTM D 882-97 at a crosshead speed of 12 inches/minute (30 centimeters/minute). In certain embodiments, the fibrous reinforcing material comprises substantially continuous fibers within the pressure sensitive adhesive matrix. Additionally, in preferred embodiments, the fiber reinforced adhesive composition will display stretch removable characteristics and easy removal from a substrate.

In addition, the invention is directed to a method for making a fiber reinforced adhesive. The method comprises forming a mixture comprising a pressure sensitive adhesive with a reinforcing material capable of forming fibers when subjected to an elongating shear force, and subjecting the mixture to the elongating shear force.

5 In this application, the following terms are defined as follows, unless otherwise stated:

“Stretch removable” means that a pressure sensitive adhesive, when pulled and elongated (preferably from a substrate surface at a rate of 30 centimeters/minute and at an angle of no greater than 45°), detaches from a substrate surface without significant damage  
10 to the substrate surface (e.g. tearing), and without leaving a significant residue, preferably that which is visible to the unaided human eye on the substrate.

“Substantially continuous” means that for an at least 0.5 centimeter length sample of the adhesive composition taken in the machine direction, at least 50% of the fibers present in the sample are continuous (i.e. unbroken).

15 “Tensile strength” is the maximum tensile strength at break when tested according to ASTM D 882-97 at a crosshead speed of 12 inches/minute (30 centimeters/minute).

#### Detailed Description of the Invention

The present invention is directed to a fiber reinforced adhesive composition  
20 comprising a pressure sensitive adhesive matrix and a reinforcing material within the pressure sensitive adhesive matrix. The fiber reinforced adhesive composition of the present invention has improved cohesive strength, as represented by a higher tensile strength of the fiber reinforced adhesive composition as compared to the pressure sensitive adhesive without the reinforcing material. Additionally, in a preferred  
25 embodiment, the adhesive composition is stretch removable. The adhesive composition of the invention has these properties while maintaining substantially unreduced tack properties in many embodiments.

In the present invention, the adhesive composition has a yield strength. In certain embodiments, the yield strength is no less than about 0.1 MPa when measured according  
30 to ASTM D 882-97 at a crosshead speed of 12 inches/minute (30 centimeters/minute). In

specific embodiments, the yield strength is no less than about 0.2 MPa when measured according to ASTM D 882-97 at a crosshead speed of 12 inches/minute (30 centimeters/minute).

Additionally, the adhesive composition has a tensile strength of at least about 150% of the yield strength when measured according to ASTM D 882-97 at a crosshead speed of 12 inches/minute (30 centimeters/minute). In certain embodiments, the tensile strength is about 0.7 MPa or greater when measured according to ASTM D 882-97 at a crosshead speed of 12 inches/minute (30 centimeters/minute). In specific embodiments, the tensile strength is about 0.8 MPa or greater when measured according to ASTM D 882-97 at a crosshead speed of 12 inches/minute (30 centimeters/minute). The adhesive composition may have a tensile strength of at least about two times greater than the tensile strength of the pressure sensitive adhesive alone when measured according to ASTM D 882-97 at a crosshead speed of 12 inches/minute (30 centimeters/minute).

For preferred embodiments, the elongation at break for the adhesive composition is at least about 50% when measured according to ASTM D 882-97 at a crosshead speed of 12 inches/minute (30 centimeters/minute), preferably more than about 200%, and may be higher than about 300%. In some embodiments the elongation at break is in excess of about 800%.

Additionally, in preferred embodiments, the amount of force required to remove the adhesive composition from a polypropylene substrate at an angle of between 15° and 35° is less than about 20 Newtons/decimeter. This low removal force permits facile removal of the adhesive composition from a substrate. In certain embodiments, the force necessary to remove the adhesive composition from a substrate at such an angle is as low as about 7 Newtons/decimeter.

#### Pressure Sensitive Adhesive

Any suitable pressure sensitive adhesive composition can be used for this invention. The pressure sensitive adhesive component can be any material that has pressure sensitive adhesive properties. Furthermore, the pressure sensitive adhesive component can be a single pressure sensitive adhesive or the pressure sensitive adhesive can be a combination of two or more pressure sensitive adhesives.

Pressure sensitive adhesives useful in the present invention include, for example, those based on natural rubbers, synthetic rubbers, styrene block copolymers, polyvinyl ethers, poly (meth)acrylates (including both acrylates and methacrylates), polyolefins, and silicones.

5           The pressure sensitive adhesive may be inherently tacky. If desired, tackifiers may be added to a base material to form the pressure sensitive adhesive. Useful tackifiers include, for example, rosin ester resins, aromatic hydrocarbon resins, aliphatic hydrocarbon resins, and terpene resins. Other materials can be added for special purposes, including, for example, oils, plasticizers, antioxidants, ultraviolet ("UV") stabilizers, 10 hydrogenated butyl rubber, pigments, and curing agents.

          In a preferred embodiment, the pressure sensitive adhesive is based on at least one poly(meth)acrylate (e.g. is a (meth)acrylic pressure sensitive adhesive). Poly(meth)acrylic pressure sensitive adhesives are derived from, for example, at least one alkyl (meth)acrylate ester monomer such as, for example, isooctyl acrylate, isononyl acrylate, 2- 15 methyl-butyl acrylate, 2-ethyl-hexyl acrylate and n-butyl acrylate; and at least one optional co-monomer component such as, for example, (meth)acrylic acid, vinyl acetate, N-vinyl pyrrolidone, (meth)acrylamide, a vinyl ester, a fumarate, a styrene macromer, or combinations thereof. Preferably, the poly(meth)acrylic pressure sensitive adhesive is derived from between about 0 and about 20 weight percent of acrylic acid and between 20 about 100 and about 80 weight percent of at least one of isooctyl acrylate, 2-ethyl-hexyl acrylate or n-butyl acrylate composition, preferably isooctyl acrylate. A preferred embodiment for the present invention is derived from between about 2 and about 10 weight percent acrylic acid and between about 90 and about 98 weight percent of at least one of isooctyl acrylate, 2-ethyl-hexyl acrylate or n-butyl acrylate composition. One 25 specific embodiment for the present invention is derived from about 2 weight percent to about 10 weight percent acrylic acid, about 90 weight percent to about 98 weight percent of isooctyl acrylate, and about 2 weight percent to about 6 weight percent styrene macromer.

### Reinforcing Material

Various reinforcing materials may be used to practice the present invention. In preferred embodiments, the reinforcing material is a polymer. In specific embodiments, the reinforcing material is elastomeric. Preferably, the reinforcing material is a semi-crystalline polymer. A semi-crystalline polymer is one having both amorphous and crystalline domains. Many specific embodiments incorporate semi-crystalline polymers, such as polycaprolactone (PCL), polybutene (PB), copolymers derived from ethylene and at least one other alpha-olefin monomer (e.g. poly(ethylene-co-1-alkene) and poly(ethylene-co-1-alkene-co-1-alkene)), ultra low density polyethylene (e.g. having a density below 0.915 grams/cubic centimeter, such as ATTANE 4202 commercially available from Dow Chemical Co.), linear low density polyethylene (e.g. having a density between 0.915 and 0.94 grams/cubic centimeter, such as LL-3003, ECD-125, 377D60, 369G09, 363C32, 361C33, 357C32, 350D65, 350D64, 350D60, LL-3013, and LL-3001 commercially available from ExxonMobil Corp.) or combinations thereof.

Preferred reinforcing materials have a measurable yield strength. In certain embodiments, the yield strength of the reinforcing material is less than about 20 MPa. The tensile strength of the reinforcing material is preferably at least about 150% of its yield strength. In specific embodiments, the tensile strength of the reinforcing material is higher than the tensile strength of the pressure sensitive adhesive. These values are measured using ASTM D 882-97 at a crosshead speed of 12 inches/minute (30 centimeters/minute).

The reinforcing material preferably has a melting point above the use temperature of the adhesive composition. Similarly, the reinforcing material preferably has a melting point above the storage temperature of the adhesive composition or any article manufactured with the adhesive composition. Both the use temperature and the storage temperature should not exceed the temperature that the pressure sensitive adhesive decomposes. In certain embodiments, the reinforcing material has a melting point of at least 70 °C. All temperatures are related as being measurable by differential scanning calorimetry ("DSC") at a scanning rate of 10 °C/minute.

It is particularly desirable for the reinforcing material to have a melt viscosity similar to the melt viscosity of the pressure sensitive adhesive at the processing temperature of the method of this invention. In specific embodiments, the ratio of the

reinforcing material melt viscosity to the pressure sensitive adhesive melt viscosity at the processing temperature is less than about 3, preferably less than about 1.5. In particularly preferred embodiments, the ratio is between about 0.5 and about 1.2 depending on specific extrusion parameters (e.g. shear rate, screw speed, temperature). Melt viscosity is measurable as understood by one skilled in the art using a capillary viscometer.

The reinforcing material is preferably immiscible (i.e. remains in a separate phase) in the pressure sensitive adhesive during mixing so that the reinforcing material can be substantially uniformly dispersed (i.e. distributed) in the pressure sensitive adhesive. In specific embodiments, during mixing, the reinforcing material is in the form of substantially spherical particles having an average diameter less than about 20 micrometers. In certain embodiments, the reinforcing material has an average diameter less than about 10 micrometers.

In preferred embodiments, the reinforcing material exists as substantially continuous fibers in the adhesive composition. Specifically, according to one aspect of the invention, the fibers are unbroken for at least about 0.5 centimeters in the machine direction of the pressure sensitive adhesive matrix, preferably at least about 2 centimeters. In more preferred embodiments, the substantially continuous fibers are continuous for at least about 5 centimeters and most preferably at least about 8 centimeters. According to another aspect of the invention, the substantially continuous fibers generally have a maximum diameter of about 0.05 to about 5 micrometers, preferably from about 0.1 to about 1 micrometers. According to another aspect of the invention, the aspect ratio (i.e. the ratio of the length to the diameter) of the substantially continuous fibers is greater than about 1000.

#### Mixing

The reinforcing material is mixed with the pressure sensitive adhesive before subjecting the mixture to an elongating shear force. Mixing of the reinforcing material and the pressure sensitive adhesive is done by any method that results in a dispersion, preferably a substantially uniform dispersion, of the reinforcing material in the pressure sensitive adhesive. For example, melt blending, solvent blending, or any suitable physical means are able to adequately mix the reinforcing material and the pressure sensitive adhesive.



Melt blending devices include those that provide dispersive mixing, distributive mixing, or a combination of dispersive and distributive mixing. Both batch and continuous methods of melt blending can be used. Examples of batch methods include those using a BRABENDER (e.g. a BRABENDER PREP CENTER, commercially available from C.W. Brabender Instruments, Inc.; South Hackensack, NJ) or BANBURY internal mixing and roll milling equipment (e.g. equipment available from Farrel Co.; Ansonia, CT). After batch mixing, the mixture created may be immediately quenched and stored below melting temperature of the mixture for later processing.

Examples of continuous methods include single screw extruding, twin screw extruding, disk extruding, reciprocating single screw extruding, and pin barrel single screw extruding. The continuous methods can include utilizing both distributive elements, such as cavity transfer mixers (e.g. CTM, commercially available from RAPRA Technology, Ltd.; Shrewsbury, England) and pin mixing elements, static mixing elements or dispersive mixing elements (commercially available from e.g., MADDOCK mixing elements or SAXTON mixing elements as described in "Mixing in Single-Screw Extruders," Mixing in Polymer Processing, edited by Chris Rauwendaal (Marcel Dekker Inc.: New York (1991), pp. 129, 176-177, and 185-186).

In certain embodiments, the reinforcing material comprises between about 2 and about 70 weight percent of the adhesive composition. In specific embodiments, the reinforcing material comprises between about 5 and about 60 weight percent of the adhesive composition. In preferred embodiments, the reinforcing material comprises between about 5 and about 50 weight percent of the adhesive composition. Typically, the pressure sensitive adhesive component comprises between about 30 and about 98 weight percent, preferably between about 40 and about 95 weight percent and more preferably between about 50 and about 95 weight percent of the total adhesive composition. Other additives may also be mixed into the pressure sensitive adhesive composition prior to application thereof, depending on the desired properties of the applied adhesive.

#### Method of Forming the Fiber Reinforced Pressure Sensitive Adhesive

The adhesive composition is subjected to an elongating shear force, creating fibers from the reinforcing material in a pressure sensitive adhesive matrix. Preferably, the adhesive composition is formed by continuous forming methods, including hot melt

coating, drawing or extruding, the adhesive composition from the elongating shear force device (e.g. a draw die, a film die, or a rotary rod die) and subsequently contacting the drawn adhesive composition to a moving web (e.g. plastic) or other suitable substrate. A related continuous forming method involves extruding the adhesive composition and a co-extruded backing material from a film die and cooling the layered product to form an adhesive tape. Other continuous forming methods involve directly contacting the adhesive composition to a rapidly moving web or other suitable preformed substrate. Using this method, the adhesive composition is applied to the moving preformed web using a die having flexible die lips, such as a rotary rod die.

After forming by any of these continuous methods, the fibers, thus formed, can be solidified by lowering the temperature of the adhesive composition to below the melting point of the reinforcing material. For example, the temperature may be lowered by quenching the adhesive composition using either direct methods (e.g., chill rolls or water baths) or indirect methods (e.g., air or gas impingement). The resulting fiber reinforced adhesive composition is then cooled to ambient temperature.

#### Application of the Fiber Reinforced Adhesive Composition

The fiber reinforced adhesive composition can be used for a variety of applications. For example, the fiber reinforced adhesive composition can be applied to sheeting products (e.g., decorative, reflective, and graphical), labelstock, and tape backings to form, for example, first aid dressings, medical drapes, or medical tapes. Additionally, the fiber reinforced adhesive composition of the present invention can be used in optical fibers and tapes. The substrate can be any suitable type of material depending on the desired application.

To form a tape, the fiber reinforced adhesive composition is coated onto at least a portion of a suitable backing. A release material (e.g., low adhesion backsize) can be applied to the opposite side of the backing, if desired. When double-coated tapes are formed, the fiber reinforced adhesive composition is coated, for example by co-extrusion or lamination, onto at least a portion of both sides of the backing. Additionally, the adhesive can be coated on at least one release liner to form a transfer tape.

Typically, the backing comprises a nonwoven, paper, polypropylene (e.g., biaxially oriented polypropylene (BOPP)), polyethylene, polyester (e.g., polyethylene

terephthalate), or a release liner (e.g., siliconized liner). In specific embodiments, the backing is stretchable so that an article comprising the adhesive composition and the backing would be stretch removable.

In specific embodiments, the adhesive compositions of the present invention are used in tapes that include gauze pads, for example, and are used as first aid dressings (i.e., wound or surgical dressings). They can also be used in a wide variety of other medical articles, such as medical tapes, athletic tapes, surgical drapes, or tapes or tabs used in adhering medical devices such as sensors, electrodes (as disclosed in U.S. Pat. No. 5,215,087 and U.S. Pat. No. 6,171,985, for example), ostomy appliances, or the like.

Preferably, webs made from natural or synthetic fibers or mixtures thereof can be used to form backings, particularly for medical articles. Woven or nonwoven materials can be employed for webs, with nonwoven materials being preferred for most applications. Melt-blown or spunbond techniques can be employed to make such nonwoven webs. Nonwoven webs can also be prepared, for example, on a RANDO WEBBER (Rando Corporation, Macedon, NY) air-laying machine or on a carding machine.

Typically, fibers forming a nonwoven tape backing are intimately entangled with each other in the form of a coherent breathable fibrous nonwoven tape backing. Suitable nonwoven tape backings can be formed as melt blown microfiber webs using the apparatus discussed, for example, in Wentz, Van A., "Superfine Thermoplastic Fibers," Industrial Engineering Chemistry, Vol. 48, pages 1342-1346; Wentz, Van A. et al., "Manufacture of Superfine Organic Fibers," Report No. 4364 of the Naval Research Laboratories, published May 25, 1954; and in U.S. Pat Nos. 3,849,241, 3,825,379, and others. These microfine fibers are termed melt blown fibers or blown microfibers (BMF) and are generally substantially continuous and form a coherent web between the exit die orifice and a collecting surface by entanglement of the microfibers, due in part to the turbulent airstream in which the fibers are entrained.

Other conventional melt spinning type processes, such as spunbond processes, where fibers are collected in a web form immediately upon formation, can also be used to form the nonwoven tape backing. Generally, the fibers are 100 microns or less in diameter when formed by melt spinning type processes, preferably 50 microns or less.

Multicomponent fibers, if formed by the melt blown process, can be produced as described in U.S. Pat. Nos. 5,176,952 (Joseph et al); 5,232,770 (Joseph); 5,238,733 (Joseph et al); 5,258,220 (Joseph); or 5,248,455 (Joseph et al). Multicomponent fibers can also be produced by a spunbond process as disclosed in U.S. Pat. Nos. 5,695,868 (McCormach); 5,336,552 (Strack et al); 5,545,464 (Stokes); 5,382,400; 5,512,358 (Shawyer et al); or 5,498,463 (McDowall et al).

Representative examples of materials suitable for the backing of the adhesive article of this invention include polyolefins, such as polyethylene, including high density polyethylene, low density polyethylene, linear low density polyethylene, and linear ultra low density polyethylene, polypropylene, and polybutylenes; vinyl copolymers, such as polyvinyl chlorides, both plasticized and unplasticized, and polyvinyl acetates; olefinic copolymers, such as ethylene/methacrylate copolymers, ethylene/vinyl acetate copolymers, acrylonitrile-butadiene-styrene copolymers, and ethylene/propylene copolymers; acrylic polymers and copolymers; polycaprolactones; and combinations of the foregoing. Mixtures or blends of any plastic or plastic and elastomeric materials such as polypropylene/polyethylene, polyurethane/polyolefin, polyurethane/polycarbonate, polyurethane/polyester, can also be used. Additionally, any nonstretchable material can be used for the tearable backings or for those with perforations, including paper and even metal. Preferred materials for the backing include polyurethane, polypropylene, ethylene vinyl acetate, or combinations thereof (e.g., blends, mixtures, etc.) in the form of melt blown fibers. Preferred materials for film backings include polycaprolactones and copolymers of ethylene/vinyl acetate and linear low density polyethylene.

In a preferred embodiment, the backing is formed from coherent multicomponent fibers having at least one pressure sensitive adhesive region or layer and at least one non-pressure sensitive adhesive region or layer as described in U.S. Pat. No. 6,107,219. In another preferred embodiment, the backing is a melt blown polypropylene web available from Kimberly Clark Corp.; Irving, TX.

If the backing is in the form of a laminate, additional components could be used, such as absorbent layers (e.g., gauze pads) for adhesive bandage products, or the like. If absorbent layers are used, they are typically thin, coherent, conformable, and able to flex and not interfere with the stretch removable characteristics of the articles, although they can be stretchable or not.

If a laminate, there may be one or more additional layers. Preferably, the outermost layer of such a laminate is a film that is substantially impervious to fluids, such as could arise from the external environment, yet permits passage of moisture vapor such that the adhesive article is breathable (typically, having a moisture vapor transmission rate (MVTR) of at least about 500 g/m<sup>2</sup>/day). Typically this breathable, liquid impervious film is the outermost (i.e., top) layer. Examples of such film materials include polyurethanes, polyolefins, metallocene catalyzed polyolefins, polyesters, polyamides, polyetheresters, and A-B-A block copolymers, such as KRATON copolymers available from Shell Chemical Ltd.; Houston, TX.

#### Examples

This invention is further illustrated by the following examples that are not intended to limit the scope of the invention. These examples are merely for illustrative purposes only and are not meant to be limiting on the scope of the appended claims. All parts, percentages, ratios, etc. in the examples and the rest of the specification are by weight unless indicated otherwise. All ultraviolet curing of adhesives described in the examples occurred with the adhesive exposed to the ultraviolet radiation source.

Table of Abbreviations

Abbreviation / Trade Designation	Description
AA	Acrylic acid
ATTANE 4202	Ultra Low Density Linear Poly(ethylene-co-octene) derived from 10% octene, commercially available from Dow Chemical Co.; Midland, MI.
CV-60	A controlled viscosity grade natural rubber, available from The Goodyear Tire and Rubber Co.; Akron, OH.
ELVAX 210	Ethylene-vinyl acetate copolymer commercially available from E.I. duPont deNemours and Co.; Wilmington, DE.
ELVAX 240	Ethylene-vinyl acetate copolymer commercially available from E.I. duPont deNemours and Co.; Wilmington, DE.
ELVAX 450	Ethylene-vinyl acetate copolymer commercially available from E.I. duPont deNemours and Co.; Wilmington, DE.
ELVAX 660	Ethylene-vinyl acetate copolymer commercially available from E.I. duPont deNemours and Co.; Wilmington, DE.
ENGAGE 8200	Ethylene-octene copolymer derived from 24% octene, having a DSC measured melting peak temperature of 60 °C, commercially available from DuPont Dow Elastomers LLC; Wilmington, DE.
ENGAGE 8490	Ethylene-octene copolymer derived from 14% octene, commercially available from DuPont Dow Elastomers LLC; Wilmington, DE.
ESCOREZ 2393	Aliphatic/aromatic mixed tackifier resin commercially available from ExxonMobil Corp.; Houston, TX.
HDPE	High Density Polyethylene, having a weight average molecular weight of 125,000 and a density of 0.95 grams/cubic centimeter, commercially available from Scientific Polymer Products, Inc.; Ontario, NY.
IOA	Isooctyl acrylate
KRATON D1107	Styrene-isoprene-styrene block copolymer commercially available from Shell Chemicals Ltd.; Houston, TX.
LDPE	Low density polyethylene, having a density of 0.918 grams/cubic centimeter, commercially available from Aldrich Chemical Co.; Milwaukee, WI.
MAA	Methacrylic acid
PB	Isotactic Polybutene, having a weight average molecular weight of 185,000, commercially available from Aldrich Chemical Co.; Milwaukee, WI.
PCL	Polycaprolactone, having a weight average molecular weight of 80,000, commercially available from Aldrich Chemical Co.; Milwaukee, WI.
PEBH	Metallocene catalyzed poly(ethylene-co-1-butene-co-1-hexene), with a melt index of 3.5, commercially available from Aldrich Chemical Co.; Milwaukee, WI.

PET	An aminated-polybutadiene primed polyester film of polyethylene terephthalate having a thickness of 38 micrometers.
PMMA	Polymethylmethacrylate, having a weight average molecular weight of 350,000 commercially available from Aldrich Chemical Co.; Milwaukee, WI.
PP substrate	Polypropylene substrate commercially available from Aeromat Plastics Inc.; Burnsville, MN.
PS	Polystyrene, having a weight average molecular weight of 280,000, commercially available from Aldrich Chemical Co.; Milwaukee, WI.
PSA-1	IOA/AA copolymer pressure sensitive adhesive, derived from an approximate ratio of IOA/AA monomers of 90/10. The pressure sensitive adhesive was prepared by mixing 21.6 grams of IOA, 2.4 grams of AA, 0.28 gram of carbon tetrabromide chain transfer agent, and 36 grams of ethyl acetate in a glass vessel. To this mixture, 0.072 gram of VAZO 64 was added. The vessel was made inert with nitrogen gas and sealed. The sealed bottle was tumbled in a 55°C water bath for 24 hours. The resultant polymer was coated onto a siliconized polyester release liner and oven dried for 15 minutes at 65°C to recover the dried polymer.
PSA-2	Pressure sensitive adhesive containing a mixture of 50 parts of KRATON D1107 and 50 parts of WINGTACK PLUS.
PSA-3	Kraton pressure sensitive adhesive HL-2552X, commercially available from H.B. Fuller Co.; St. Paul, MN.
PSA-4	IOA/MAA copolymer pressure sensitive adhesive derived from an approximate ratio of IOA/MAA monomers of 96/4. The pressure sensitive adhesive was prepared as described in U.S. Patent number 4,952,650, Example 5, and dried prior to use.
PSA-5	IOA/AA copolymer pressure sensitive adhesive, derived from an approximate ratio of IOA/AA monomers of 90/10. The pressure sensitive adhesive was polymerized as described in U.S. Patent number 5,804,610, Example 1, with the exception that the pouch was removed prior to feeding the pressure sensitive adhesive into the extruder.
PSA-6	IOA/AA copolymer pressure sensitive adhesive grafted with a polystyrene macromer, derived from an approximate ratio of IOA/AA/polystyrene components of 92/4/4. The pressure sensitive adhesive was prepared as described in U.S. Patent number 4,554,324, Example 74, except that the macromer was polystyrene and the inherent viscosity of the resulting PSA-6 was 0.65 dl/g (measured in ethylacetate at 27 °C.)
PSA-7	PSA-6 mixed with 23% ESCOREZ 2393 tackifier.
PSA-8	IOA/AA copolymer pressure sensitive adhesive, derived from an approximate ratio of IOA/AA monomers of 95.5/4.5 and polymerized as described in U.S. Patent number RE 24,906, Example 5, and dried prior to use.
PSA-9	Natural rubber pressure sensitive adhesive prepared from CV-60

	as described in U.S. Patent number 6,063,838, Examples 43-44.
REGALREZ 1126	Hydrogenated tackifier resin commercially available from Hercules, Inc.; Wilmington, DE.
WINGTACK PLUS	A C5 hydrocarbon tackifier resin commercially available from Goodyear Tire & Rubber Company; Akron, OH.

### Test Methods

#### Tensile Testing

Tensile testing was carried out according to ASTM test method D 882-97  
 5 “Standard Test Method for Tensile Properties of Thin Plastic Sheeting” using an INSTRON materials tester (commercially available from Instron; Canton, MA) at a crosshead speed of 30 centimeters/minute (12 inches/minute). Using this test, the values for “Yield Strength”, “Tensile Strength”, and “Percent Elongation at Break” were  
 10 obtained.

#### 180° Peel Adhesion

This peel adhesion test is similar to the test method described in ASTM D 3330-90, substituting a glass, high density polyethylene or polypropylene substrate for the stainless  
 15 steel substrate described in the test. The substrate used is noted in each particular example.

Adhesive-coated strips that had equilibrated at constant temperature (21°C) and humidity (50% relative humidity) for at least 24 hours, were adhered to a substrate panel. The substrate panel was either solvent-washed glass, polypropylene (PP), or high density polyethylene (HDPE) using a 2 kilogram roller passed once over the strip. The bonded  
 20 assembly was allowed to dwell at room temperature for one minute. The assembly was then tested for 180° peel adhesion in the machine direction using an IMASS slip/peel tester (Model 3M90, commercially available from Instrumentors Inc., Strongsville, OH) at a crosshead speed of 30 centimeters/minute (12 inches/minute).

#### Stretch Release Test Method

Adhesive-coated strips, which had equilibrated at constant temperature (21°C) and humidity (50% relative humidity) for at least 24 hours, were adhered to a polypropylene (PP) substrate panel using a 2 kilogram roller passed once over the strip. The bonded  
 25 assembly was allowed to dwell at room temperature for one minute. The assembly was



then tested for stretch release by pulling at an angle of between 15 and 35° either “by hand”, or “mechanically” using an IMASS slip/peel tester (Model 3M90, commercially available from Instrumentors Inc., Strongsville, OH) at a crosshead speed of 30 centimeters/minute (12 inches/minute). The data are reported for the by hand samples as “broke” if the sample broke before detachment (i.e. the sample did not stretch release), or “yes” if the sample exhibited stretch release properties. For the mechanically tested samples, the data is reported as “broke” if the sample broke (i.e. the sample did not stretch release), or, if the sample did exhibit stretch release properties, the maximum stretch release force in Newtons/decimeter is reported.

#### Probe Tack Test

Probe tack measurements were made following the test method described in ASTM D 2979-95 using a TA-XY2 texture tester (commercially available from Stable Microsystems, Surrey, U.K.).

#### Solvent Extraction Test

To determine the continuity of the fibrous reinforcing material of the adhesive composition, the pressure sensitive adhesive matrix was dissolved, leaving behind the fibrous reinforcing material. A strip of the adhesive composition film (approximately 7.5 centimeters long by 2.5 centimeters wide) was cut from the film in the machine direction. The strip was suspended on an open frame by looping the film over the edge of the open frame. The frame and adhesive strip were immersed in a solvent capable of dissolving the pressure sensitive adhesive but not the fibrous reinforcing material. After 24 hours the sample was checked to determine if the pressure sensitive adhesive had completely dissolved and if the fibrous reinforcing material remained on the frame. If fibers were not continuous for at least 5 centimeters, nothing remained on the frame. The samples were rated as “pass” if fibers remained on the frame and “fail” if no fibers remained on the frame.

#### Tensile Properties of Reinforcing Material

Films of possible fibrous reinforcing material were prepared by hot-press molding each reinforcing material to a thickness of 102 micrometers. The films were tested using

---

the Tensile Testing method described above. The results are shown in Table 1. Additionally, the materials are characterized as being elastomeric (rebounds upon deformation) or plastic (deforms permanently).

5

Table 1

Polymer	Yield Strength (MPa)	Tensile Strength (MPa)	Percent Elongation at Break (%)	Plastic or Elastomeric
PEBH	5.09	31.72	730	Elastomeric
PCL	7.45	16.41	620	Elastomeric
ATTANE 4202	8.27	27.58	>800	Elastomeric
HDPE	20.55	14.34	370	Plastic
PMMA	25.51	25.51	<10	Plastic

#### Comparative Example C1

A sample of PSA-1 was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The resulting film had a thickness of 127 micrometers. The tensile properties of the film were determined as described in the Tensile Testing method above. The results are shown in Table 2. A portion of the film was laminated to a PET backing to make a tape. The resulting tape was passed below a Fusion H-bulb lamp (commercially available from Fusion Total Ultraviolet Systems, Inc.; Gaithersburg, MD) at a crosshead speed of 15 meters/minute for a total ultraviolet dose of 300 millijoules/cm<sup>2</sup>. The tape was tested for 180° Peel Adhesion from glass. The results are shown in Table 3.

#### Comparative Example C2

A mixture of 90 parts PSA-1, 10 parts ENGAGE 8200 and 0.2 part benzophenone was prepared in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a

draw die. The resulting film had a thickness of 127 micrometers. The tensile properties of the film were determined as described in the Tensile Testing method above. The results are shown in Table 2. A portion of the film was laminated to a PET backing to make a tape. The resulting tape was passed below a Fusion H-bulb lamp (commercially available from Fusion Total Ultraviolet Systems, Inc.; Gaithersburg, MD) at a crosshead speed of 15 meters/minute for a total ultraviolet dose of 300 milliJoules/cm<sup>2</sup>. The tape was tested for 180° Peel Adhesion from glass. The results are shown in Table 3.

#### Comparative Example C3

A mixture of 90 parts PSA-1, 10 parts of LDPE and 0.2 part benzophenone were mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The resulting film had a thickness of 127 micrometers. The tensile properties of the film were determined as described in the Tensile Testing method above. The results are shown in Table 2. A portion of the film was laminated to a PET backing to make a tape. The resulting tape was passed below a Fusion H-bulb lamp (commercially available from Fusion Total Ultraviolet Systems, Inc.; Gaithersburg, MD) at a crosshead speed of 15 meters/minute for a total ultraviolet dose of 300 milliJoules/cm<sup>2</sup>. The tape was tested for 180° Peel Adhesion from glass. The results are shown in Table 3.

#### Example 1

A mixture of 90 parts PSA-1, 10 parts ENGAGE 8490 and 0.2 part benzophenone were mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The resulting film had a thickness of 127 micrometers. The tensile properties of the film were determined as described in the Tensile Testing method above. The results are shown in Table 2. A portion of the film was laminated to a PET backing to make a tape. The resulting tape was passed below a Fusion H-bulb lamp (commercially available

from Fusion Total Ultraviolet Systems, Inc.; Gaithersburg, MD) at a crosshead speed of 15 meters/minute for a UV dose of 300 milliJoules/cm<sup>2</sup>. The tape was tested for 180° Peel Adhesion from glass. The results are shown in Table 3.

## 5 Example 2

A mixture of 90 parts PSA-1, 10 parts of ATTANE 4202 and 0.2 part benzophenone were mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a  
 10 HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The resulting film had a thickness of 127 micrometers. The tensile properties of the film were determined as described in the Tensile Test Method above. The results are shown in Table 2. A portion of the film was laminated to a PET  
 15 backing to make a tape. The resulting tape was passed below a Fusion H-bulb lamp (commercially available from Fusion Total Ultraviolet Systems, Inc.; Gaithersburg, MD) at a crosshead speed of 15 meters/minute for a UV dose of 300 milliJoules/cm<sup>2</sup>. The tape was tested for 180° Peel Adhesion from glass. The results are shown in Table 3.

Table 2

Example	Yield Strength (MegaPascals)	Tensile Strength (MegaPascals)	Percent Elongation at Break (%)
C1	0.04	0.06	>800
C2	0.18	0.65	>800
C3	1.19	1.59	320
1	0.33	1.70	760
2	0.54	2.05	700

Table 3

Example	180° Peel Adhesion (N/dm)
C1	57.8
C2	52.1
C3	61.9
1	95.0
2	88.4

Comparative Example C4

5 A sample of PSA-1 was hot melt coated between two release liners at 150°C using  
 a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ)  
 equipped with a draw die. The resulting film had a thickness of 127 micrometers and was  
 laminated to a PET backing to make a tape. The resulting tape was passed below a Fusion  
 H-bulb lamp (commercially available from Fusion Total Ultraviolet Systems, Inc.;  
 Gaithersburg, MD) at a crosshead speed of 15 meters/minute for a UV dose of 300  
 10 millijoules/cm<sup>2</sup>. The tape was tested for 180° Peel Adhesion from glass in the machine  
 and the cross-web directions. The results are shown in Table 4.

Example 3

15 A mixture of 90 parts PSA-1 and 10 parts of ATTANE 4202 were mixed in a  
 BRABENDER mixer (commercially available from C.W. Brabender Instruments, South  
 Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot  
 melt coated between two release liners at 150°C using a HAAKE single screw extruder  
 (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The  
 resulting film had a thickness of 127 micrometers and was laminated to a PET backing to  
 20 make a tape. The resulting tape was passed below a Fusion H-bulb lamp (commercially  
 available from Fusion Total Ultraviolet Systems, Inc.; Gaithersburg, MD) at a crosshead  
 speed of 15 meters/minute for a UV dose of 300 millijoules/cm<sup>2</sup>. The tape was tested for  
 180° Peel Adhesion from glass in the machine and the cross-web directions. The results  
 are shown in Table 4.

Table 4

Example	180° Peel Adhesion in Machine Direction (N/dm)	180° Peel Adhesion in Cross-web Direction (N/dm)
C4	81.4	65.9
3	128.9	141.3

Comparative Example C5

5           A sample of PSA-1 was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The resulting film had a thickness of 51 micrometers and was laminated to a PET backing to make a tape. The resulting tape was passed below a Fusion H-bulb lamp (commercially available from Fusion Total Ultraviolet Systems, Inc.;  
10       Gaithersburg, MD) at a crosshead speed of 15 meters/minute for a UV dose of 300 millijoules/cm<sup>2</sup>. The tape was tested for 180° Peel Adhesion from glass in the machine and cross-web directions. The results are shown in Table 5.

Comparative Example C6

15           A mixture of 90 parts PSA-1 and 10 parts of LDPE were mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The  
20       resulting film had a thickness of 51 micrometers and was laminated to a PET backing to make a tape. The tape was tested for 180° Peel Adhesion from glass in the machine and cross-web directions. The results are shown in Table 5.

Example 4

25           A mixture of 90 parts PSA-1 and 10 parts of ATTANE 4202 were mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder

(commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The resulting film had a thickness of 51 micrometers and was laminated to a PET backing to make a tape. The resulting tape was passed below a Fusion H-bulb lamp (commercially available from Fusion Total Ultraviolet Systems, Inc.; Gaithersburg, MD) at a crosshead speed of 15 meters/minute for a UV dose of 300 milliJoules/cm<sup>2</sup>. The tape was tested for 180° Peel Adhesion from glass in the machine and cross-web directions. The results are shown in Table 5.

Table 5

Example	180° Peel Adhesion in Machine Direction (N/dm)	180° Peel Adhesion in Cross-web Direction (N/dm)
C5	54.9	51.4
C6	36.7	63.0
4	96.9	88.4

#### Comparative Example C7

A sample of PSA-2 was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The resulting film had a thickness of 127 micrometers and was laminated to a PET backing to make a tape. The tape was tested for 180° Peel Adhesion on various substrates. The results are shown in Table 6.

#### Example 5

A mixture of 90 parts PSA-2 and 10 parts of ATTANE 4202 were mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The resulting film had a thickness of 127 micrometers and was laminated to a PET backing to make a tape. The tape was tested for 180° Peel Adhesion on various substrates. The results are shown in Table 6.

Table 6

Example	180° Peel Adhesion from glass (N/dm)	180° Peel Adhesion for HDPE (N/dm)	180° Peel Adhesion from PP (N/dm)
C7	181	79	156
5	238	91	231

### 5 Comparative Example C8

A sample of PSA-3 was used as obtained and hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The resulting film had a thickness of 127 micrometers and was laminated to a PET backing to make a tape. The tape was tested for 180° Peel Adhesion on various substrates. The results are shown in Table 7.

### Example 6

A mixture of 90 parts PSA-3 and 10 parts of ATTANE 4202 were mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The resulting film had a thickness of 127 micrometers and was laminated to a PET backing to make a tape. The tape was tested for 180° Peel Adhesion on various substrates. The results are shown in Table 7.

Table 7

Example	180° Peel Adhesion from glass (N/dm)	180° Peel Adhesion from HDPE (N/dm)	180° Peel Adhesion from PP (N/dm)
C8	53	25	33
6	100	23	42



Comparative Example C9

A sample of PSA-4 was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The tensile properties of the film were determined as described in the Tensile Testing method above. The results are shown in Table 8.

Comparative Example C10

A mixture of 85 parts PSA-4 and 15 parts of PS were mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The tensile properties of the film were determined as described in the Tensile Testing method above. The results are shown in Table 8.

Comparative Example C11

A mixture of 85 parts PSA-4 and 15 parts HDPE were mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The tensile properties of the film were determined as described in the Tensile Testing method above. The results are shown in Table 8.

Example 7

A mixture of 85 parts PSA-4 and 15 parts of ATTANE 4202 were mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The tensile properties of the film were determined as described in the Tensile Testing method above. The results are shown in Table 8.

Example 8

A mixture of 85 parts PSA-4 and 15 parts PEBH were mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The tensile properties of the film were determined as described in the Tensile Testing method above. The results are shown in Table 8.

Table 8

Example	Yield Strength (MegaPascals)	Tensile Strength (MegaPascals)	Percent Elongation at Break (%)
C9	0.03	0.14	>800
C10	1.79	1.79	<50
C11	1.72	2.07	180
7	1.21	3.38	>800
8	0.47	2.83	630

Examples 9-13

The mixtures for Examples 9-13 were prepared using PSA-5 with the level of ATTANE 4202 shown in Table 9, were mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The tensile properties of the films were determined as described in the Tensile Testing method above. The results are shown in Table 9.

Table 9

Example	Level of ATTANE 4202 (weight %)	Yield Strength (MegaPascals)	Tensile Strength (MegaPascals)	Percent Elongation at Break (%)
9	5	0.21	0.90	610
10	10	0.52	1.79	670
11	15	0.95	3.59	610
12	30	2.21	7.31	650
13	40	3.45	13.51	580

Examples 14-16 and Comparative Examples C12-C14

5           The mixtures for Examples 14-16 and Comparative Examples C12-C14 were prepared using PSA-4 with 15 weight % of a polymer as shown in Table 10, and were mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die to give a thickness of 51 micrometers. The stretch release properties of the films were determined as described in the Stretch Release Test Method above. The results are shown in Table 10.

10

Table 10

Example	Polymer Added (15 weight %)	Stretch Release "by hand"
C12	PMMA	Broke
C13	PS	Broke
C14	HDPE	Broke
14	ATTANE 4202	Yes
15	PEBH	Yes
16	PB	Yes

Examples 17-22 and Comparative Example C15

5           The mixtures for Examples 17-22 and Comparative Example C15 were prepared using PSA-4 with the level of ATTANE 4202 shown in Table 11, and were mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder  
10           (commmercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die to give a thickness of 51 micrometers. The stretch release properties of the films were determined as described in the Stretch Release Test Method above. The results are shown in Table 11.

Table 11

Example	Level of ATTANE 4202 (weight %)	Stretch Release Force (N/dm)
C15	0	Broke
17	5	7.4
18	10	10.7
19	15	13.1
20	20	14.1
21	30	19.6
22	40	22.1

Examples 23-25 and Comparative Example C16

The mixtures for Examples 23-25 and Comparative Example C16 were prepared using PSA-6 with the level of ATTANE 4202 shown in Table 12 mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die to give a thickness of 51 micrometers. The stretch release properties of the films were determined as described in the Stretch Release Test Method above. The results are shown in Table 12.

Table 12

Example	Level of ATTANE 4202 (weight %)	Stretch Release Force (N/dm)
C16	0	Broke
23	5	9.0
24	10	10.3
25	20	14.3

Examples 26-27 and Comparative Example C17

The mixtures for Examples 26-27 and Comparative Example C17 were prepared using PSA-7 with the level of ATTANE 4202 shown in Table 13 mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die to give a thickness of 127 micrometers. The stretch release properties of the films were determined as described in the Stretch Release Test Method above. The results are shown in Table 13.

Table 13

Example	Level of ATTANE 4202 (weight %)	Stretch Release Force (N/dm)
C17	0	Broke
26	10	9.0
27	20	19.8

Examples 28-30 and Comparative Example C18

5           The mixtures for Examples 28-30 and Comparative Example C18 were prepared using PSA-6 with the level of ATTANE 4202 shown in Table 14 mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder

10           (commmercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die to give a thickness of 51 micrometers. The probe tack properties of the films were determined as described in the Probe Tack Test method above. The results are shown in Table 14.

Table 14

Example	Level of ATTANE 4202 (weight %)	Probe Tack for 51 micrometer thick sample (grams)
C18	0	261
28	5	262
29	10	229
30	20	279

Examples 31-32 and Comparative Example C19

The mixtures for Examples 31-32 and Comparative Example C19 were prepared using PSA-7 with the level of ATTANE 4202 shown in Table 15 mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die to give a thickness of 51 or 127 micrometers. The probe tack properties of the films were determined as described in the Probe Tack Test method above. The results are shown in Table 15.

Table 15

Example	Level of ATTANE 4202 (weight %)	Probe Tack for 127 micrometer thick sample (grams)	Probe Tack for 51 micrometer thick sample (grams)
C19	0	442	376
31	10	340	328
32	20	384	316

Examples 33-37 and Comparative Example C20

The mixtures for Examples 33-37 and Comparative Example C20 were prepared using PSA-4 with the level of ATTANE 4202 shown in Table 16 mixed in a BRABENDER mixer (commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixtures were hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die to give films having a thickness of 51 or 127 micrometers. The probe tack properties of the films were determined as described in the Probe Tack Test method above. The results are shown in Table 16.

Table 16

Example	Level of ATTANE 4202 (weight %)	Probe Tack for 127 micrometer thick sample (grams)	Probe Tack for 51 micrometer thick sample (grams)
C20	0	249	160
33	5	261	197
34	10	276	119
35	15	157	156
36	20	113	103
37	30	87	73

Comparative Examples C21-C22

Mixtures of PSA-8 and ELVAX 240 were prepared with the levels of ELVAX 240 shown in Table 17 and hot melt coated to form films as described in U.S. Patent Number 6,063,838 (Patnode, et al) Examples 1-17. The tensile properties of the films were determined as described in the Tensile Testing method above. The results are shown in Table 17.

Table 17

Example	Level of ELVAX 240 (weight %)	Yield Strength (MegaPascals)	Tensile Strength (MegaPascals)	Percent Elongation at Break (%)
C21	10	1.01	1.10	408
C22	15	1.43	1.52	460

Comparative Examples C23-C24

Mixtures of PSA-8 and ELVAX 210 were prepared with the levels of ELVAX 210 shown in Table 18 and hot melt coated to form films as described in U.S. Patent Number 6,063,838 (Patnode, et al) Examples 1-17. The tensile properties of the films were



determined as described in the Tensile Testing method above. The results are shown in Table 18.

Table 18

Example	Level of ELVAX 210 (weight %)	Yield Strength (MegaPascals)	Tensile Strength (MegaPascals)	Percent Elongation at Break (%)
C23	10	1.38	1.42	470
C24	15	1.45	1.52	460

#### Comparative Examples C25-C26

Mixtures of PSA-9 and ELVAX 240 were prepared with the levels of ELVAX 240 shown in Table 19 and hot melt coated to form films as described in U.S. Patent Number 6,063,838 (Patnode, et al) Examples 43-44. The tensile properties of the films were determined as described in the Tensile Testing method above. The results are shown in Table 19.

Table 19

Example	Level of ELVAX 240 (weight %)	Yield Strength (MegaPascals)	Tensile Strength (MegaPascals)	Percent Elongation at Break (%)
C25	10	0.33	0.37	270
C26	15	0.32	0.36	120

#### Comparative Examples C27-C28

Mixtures of PSA-9 and ELVAX 210 were prepared with the levels of ELVAX 210 shown in Table 20 and hot melt coated to form films as described in U.S. Patent Number 6,063,838 (Patnode, et al) Examples 43-44. The tensile properties of the films were determined as described in the Tensile Testing method above. The results are shown in Table 20.

Table 20

Example	Level of ELVAX 210 (weight %)	Yield Strength (MegaPascals)	Tensile Strength (MegaPascals)	Percent Elongation at Break (%)
C27	10	0.07	0.08	160
C28	15	0.14	0.16	220

Comparative Examples C29-C30

5            Mixtures of PSA-8 and ELVAX 450 were prepared with the levels of ELVAX 450 shown in Table 21 and hot melt coated to form films as described in U.S. Patent Number 6,063,838 (Patnode, et al) Examples 1-17. The tensile properties of the films were determined as described in the Tensile Testing method above. The results are shown in Table 21.

10

Table 21

Example	Level of ELVAX 450 (weight %)	Yield Strength (MegaPascals)	Tensile Strength (MegaPascals)	Percent Elongation at Break (%)
C29	10	1.65	1.72	260
C30	15	2.55	2.69	270

Comparative Examples C31-C32

15            Mixtures of PSA-8 and ELVAX 660 were prepared with the levels of ELVAX 660 shown in Table 22 and hot melt coated to form films as described in U.S. Patent Number 6,063,838 (Patnode, et al) Examples 1-17. The tensile properties of the films were determined as described in the Tensile Testing method above. The results are shown in Table 22.

Table 22

Example	Level of ELVAX 660 (weight %)	Yield Strength (MegaPascals)	Tensile Strength (MegaPascals)	Percent Elongation at Break (%)
C31	10	2.41	2.48	220
C32	15	2.14	2.21	240

Examples 38-41

5           The mixtures for Examples 38-41 were prepared using PSA-5 with the level of  
ATTANE 4202 shown in Table 23, and were mixed in a BRABENDER mixer  
(commercially available from C.W. Brabender Instruments, South Hackensack, NJ) at  
140°C to 150°C for 8 to 10 minutes. The resulting mixture was hot melt coated between  
two release liners at 150°C using a HAAKE single screw extruder (commercially available  
10       from Haake, Inc.; Paramus, NJ) equipped with a draw die. The solvent extraction  
properties of the film were determined as described in the Solvent Extraction Test method  
above. The results are shown in Table 23.

Table 23

Example	Level of ATTANE 4202 (weight %)	Solvent Extraction Test Result
38	10	Pass
39	15	Pass
40	30	Pass
41	40	Pass

Comparative Examples C33-C34

15           Mixtures of PSA-8, with ELVAX 210 were prepared with the levels of ELVAX  
210 shown in Table 24 and hot melt coated to form films as described in U.S. Patent  
Number 6,063,838 (Patnode, et al) Examples 1-17. The solvent extraction properties of

the films were determined as described in the Solvent Extraction Test method above. The results are shown in Table 24.

Table 24

Example	Level of ELVAX 210 (weight %)	Solvent Extraction Test Result
C33	10	Fail
C34	15	Fail

#### 5 Comparative Examples C35-C36

Mixtures of PSA-8 and ELVAX 240 were prepared with the levels of ELVAX 240 shown in Table 25 and hot melt coated to form films as described in U.S. Patent Number 6,063,838 (Patnode, et al) Examples 1-17. The solvent extraction properties of the films were determined as described in the Solvent Extraction Test method above. The results are shown in Table 25.

Table 25

Example	Level of ELVAX 240 (weight %)	Solvent Extraction Test Result
C35	10	Fail
C36	15	Fail

#### Comparative Examples C37-C38

Mixtures of PSA-9 and ELVAX 210 were prepared with the levels of ELVAX 210 shown in Table 26 and hot melt coated to form films as described in U.S. Patent Number 6,063,838 (Patnode, et al) Examples 43-44. The solvent extraction properties of the films were determined as described in the Solvent Extraction Test method above. The results are shown in Table 26.

Table 26

Example	Level of ELVAX 210 (weight %)	Solvent Extraction Test Result
C37	10	Fail
C38	15	Fail

Comparative Examples C39-C40

5            Mixtures of PSA-9 and ELVAX 240 were prepared with the levels of ELVAX 240 shown in Table 27 and hot melt coated to form films as described in U.S. Patent Number 6,063,838 (Patnode, et al) Examples 43-44. The solvent extraction properties of the films were determined as described in the Solvent Extraction Test method above. The results are shown in Table 27.

Table 27

Example	Level of ELVAX 240 (weight %)	Solvent Extraction Test Result
C39	10	Fail
C40	15	Fail

Comparative Examples C41-C42

10            Mixtures of PSA-8 and ELVAX 450 were prepared with the levels of ELVAX 450 shown in Table 28 and hot melt coated to form films as described in U.S. Patent Number 6,063,838 (Patnode, et al) Examples 1-17. The solvent extraction properties of the films were determined as described in the Solvent Extraction Test method above. The results are shown in Table 28.

Table 28

Example	Level of ELVAX 450 (weight %)	Solvent Extraction Test Result
C41	10	Fail
C42	15	Fail

Comparative Examples C43-C44

5            Mixtures of PSA-8 and ELVAX 660 were prepared with the levels of ELVAX 660 shown in Table 29 and hot melt coated to form films as described in U.S. Patent Number 6,063,838 (Patnode, et al) Examples 1-17. The solvent extraction properties of the films were determined as described in the Solvent Extraction Test method above. The results are shown in Table 29.

10

Table 29

Example	Level of ELVAX 660 (weight %)	Solvent Extraction Test Result
C43	10	Fail
C44	15	Fail

Example 42

15            A stretch removable First Aid Dressing (FAD) sample was made by laminating with thumb pressure at room temperature a strip (2.54-cm x 7.6-cm) of a perforated polymer film backing to a strip (2.54-cm x 7.6-cm) of the adhesive described in Example 20, with the fibers perpendicular to the long axis of the sample. The film backing comprised 60% ethylene/vinyl acetate copolymer, 35% linear low density polyethylene, 5% stabilizers and other additives (PGI Product No. 6012, Polymer Group, Inc.,  
20            Gainesville, GA); and the film had a basis weight of 1.15 oz/yd<sup>2</sup> (27 g/m<sup>2</sup>), was 5-mils (0.13-mm) thick, and had oval-shaped holes (approximately 0.2-mm width x 0.3-mm

length in the greatest dimensions) with the length dimension of the oval holes oriented parallel to the machine direction of the film. The film had about 530 holes/cm<sup>2</sup> arranged in a pattern of staggered lines.

The FAD sample was evaluated for ease of removal by adhering the sample with  
5 finger pressure to the forearm of a human subject, waiting 60 minutes, and then removing by pulling one end of the sample and stretching the sample at about a 35° angle to the plane of the forearm. Very little force was required to stretch the backing and to remove the sample painlessly from the skin and hair of the forearm.

#### 10 Example 43

A polyurethane backing (melt-blown nonwoven fibrous web comprised of three-layer polymeric fibers having a center layer of blended polyethylene and Kraton™ PSA, and outer layers of polyurethane; prepared as described for Backing Sample 16 in U.S. Pat. No. 6,107,219 (Joseph et al.)) was perforated with a metal die to provide parallel rows  
15 of holes separated by 3.8 cm. The holes were rectangular in shape (1.75-mm x 0.07-mm) and the space between holes within a row was 0.7 mm. The polyurethane backing had one side rougher than the other due to the collection technique used during the melt-blown process.

A stretch removable FAD sample was made by laminating with thumb pressure at  
20 room temperature a strip (2.54-cm x 7.6-cm) of the perforated polyurethane backing to a strip (2.54-cm x 7.6-cm) of the adhesive described in Example 20, with the fibers perpendicular to the long axis of the sample. The “rough” side of the backing was adjacent the adhesive layer. A 1.8-cm x 2.5-cm gauze pad was attached to the adhesive layer in the center of the sample and the holes had been pre-cut such that the rows began 6  
25 mm from each end of the sample.

The FAD sample was evaluated for ease of removal by adhering the sample with finger pressure to the forearm of a human subject, waiting 10 minutes, and then removing by lifting and stretching the gauze pad at about a 90° angle to the plane of the forearm. Very little force was required to stretch the backing and to remove the sample painlessly  
30 from the skin and hair of the forearm. During stretching and removal, the backing was observed to break and to delaminate from the adhesive layer.

Example 44

A paper backing (Hammermill Laserprint paper (0.11-mm thick), Product No. 00460-4, International Paper, Memphis, TN)) was perforated with a metal die to provide parallel rows of holes separated by 6.35 cm. The holes were rectangular in shape (1.75-mm x 0.07-mm) with the long sides of the holes oriented in the direction of the rows and the space between holes within a row was 0.7 mm.

A FAD sample was made by laminating with thumb pressure at room temperature a strip (2.54-cm x 7.6-cm) of the perforated paper backing to a strip (2.54-cm x 7.6-cm) of the adhesive described in Example 20, with the fibers perpendicular to the long axis of the sample. A 1.8-cm x 2.5-cm gauze pad was attached to the adhesive layer in the center of the sample and the holes had been pre-cut such that the rows began 6 mm from each end of the sample.

The FAD sample was evaluated for ease of removal by adhering the sample with finger pressure to the forearm of a human subject, waiting 10 minutes, and then removing by pulling one end of the sample and stretching the sample at about a 35° angle to the plane of the forearm. Very little force was required to stretch the backing and to remove the sample painlessly from the skin and hair of the forearm. During stretching and removal, the backing was observed to break and to delaminate from the adhesive layer.

Example 45

A stretch removable FAD sample was made by laminating with thumb pressure at room temperature a sheet (10.2-cm square) of a Rayon/Nylon nonwoven backing [thermal spunbond Rayon/Nylon nonwoven fabric, Fiber No. 149-245, basis weight = 25 g/m<sup>2</sup>, Veratec, Walpole, MA] to a sheet (10.2-cm square) of the adhesive described in Example 20, with the fibers perpendicular to the long axis of the sample. The sheets were oriented such that the adhesive layer, when subsequently stretched for removal, would be stretched in a direction parallel to the machine direction of the adhesive layer. Prior to lamination, the adhesive sheet was covered along one edge with a strip of paper that could serve as a handle for grasping the adhesive layer alone.

The resulting laminate was cut into a 2.54-cm x 7.6-cm FAD sample and adhered with thumb pressure onto a mirror-finished steel plate with the paper handle allowed to extend over the end of the plate. The paper handle of the sample was finger-grasped and



stretched in the plane of the adhesive-backing interface at a rate of about 150 cm/min. Upon stretching, the adhesive released from between the plate surface and the backing.

#### Example 46

5           A FAD sample was made by laminating with thumb pressure at room temperature a strip (2.54-cm x 7.6-cm) of a polypropylene backing [melt-blown nonwoven polypropylene (basis weight 20 g/m<sup>2</sup>), Kimberly-Clark, Irving, TX ] to a strip (2.54-cm x 7.6-cm) of the adhesive described in Example 20. A 1.3-cm piece of the adhesive/backing laminate was gathered in the middle of the strip in such a way that a fold was made  
10           perpendicular to the greatest length of the strip. A 1.8-cm x 2.5-cm gauze pad was attached to the adhesive layer in the center of the sample.

          The FAD sample was evaluated by adhering the sample with finger pressure to the forearm of a human subject, waiting 10 minutes, and then using the fold in the FAD as a handle, removing by lifting and stretching the gauze pad at about a 90° angle to the plane  
15           of the forearm. Very little force was required to stretch the backing and to remove the sample painlessly from the skin and hair of the forearm. During stretching and removal, the backing was observed to break and to delaminate from the adhesive layer.

#### Example 47

20           A FAD sample having a center fold and a gauze pad was made as described in Example 46, except that the polyurethane backing (as described in Example 43) was used in place of the polypropylene backing. The sample was evaluated as described in Example 46. During stretching and removal, the backing was observed to delaminate from the adhesive layer.

25

#### Example 48

          A FAD sample having a center fold and a gauze pad was made as described in Example 46, except that the adhesive described in Example 28 was used as the adhesive. The sample was evaluated and the same results obtained as described in Example 46.

30

Example 49

A blend of 80 parts of PSA-7 and 20 parts of ATTANE 4202 were mixed in a BRABENDER mixer (C.W. Brabender Instruments, South Hackensack, NJ) at 140°C to 150°C for 8 to 10 minutes. The resulting mixtures were hot melt coated between two release liners at 150°C using a HAAKE single screw extruder (commercially available from Haake, Inc.; Paramus, NJ) equipped with a draw die. The resulting PSA film had a thickness of 127 micrometers and was laminated to a PCL backing of thickness listed in Table 30 (prepared by solvent coating a 20% solids solution of PCL in toluene onto a release liner and drying at 70°C for 10 minutes) to make a tape. The stretch release properties of the tape was determined as described in the Stretch Release Test Method above except that samples were tested not only in the machine direction but also in the cross web direction and at 45° to the machine direction. The results of the laminated samples as well as the PSA film not laminated to a backing are shown in Table 30.

Table 30

Example	PCL backing thickness (micrometers)	Stretch release Force in the machine direction (N/dm)	Stretch release Force in the cross machine direction (N/dm)	Stretch release Force 45° to machine direction (N/dm)
49-1	0	18.2	9.6	13.8
49-2	13	37.2	30.6	36.8
49-3	25	39.6	21.9	25.6
49-4	38	36.8	26.7	32.6

Various modifications and alterations of the present invention will become apparent to those skilled in the art without departing from the spirit and scope of the invention.

What is Claimed is:

1. An adhesive composition comprising  
a pressure sensitive adhesive matrix; and  
a fibrous reinforcing material within the pressure sensitive adhesive matrix;  
5 wherein the adhesive composition has a yield strength and a tensile strength, and  
wherein the tensile strength is about 0.7 MPa or greater, and at least about 150% of the  
yield strength.

10 2. The adhesive composition of claim 1 wherein the fibrous reinforcing material  
comprises substantially continuous fibers.

3. The adhesive composition of claim 1 wherein the adhesive composition has an  
elongation at break of at least about 50%.

15 4. The adhesive composition of claim 1 wherein the adhesive composition has an  
elongation at break of at least about 300%.

5. The adhesive composition of claim 1 wherein the adhesive composition has a  
tensile strength of about 0.8 MPa or greater.

20 6. The adhesive composition of claim 1 wherein the adhesive composition has a yield  
strength of no less than about 0.1 MPa.

25 7. The adhesive composition of claim 1 wherein the adhesive composition has a yield  
strength of no less than about 0.2 MPa.

8. The adhesive composition of claim 1 wherein the pressure sensitive adhesive  
comprises about 60 to about 95 weight % of the adhesive composition and the reinforcing  
material comprises about 5 to about 40 weight % of the adhesive composition.

30

9. The adhesive composition of claim 1 wherein the pressure sensitive adhesive comprises about 70 to about 95 weight % of the adhesive composition and the reinforcing material comprises about 5 to about 30 weight % of the adhesive composition.

5 10. The adhesive composition of claim 1 wherein a ratio of the reinforcing material melt viscosity to the pressure sensitive adhesive melt viscosity is about 0.5 to about 1.2.

11. The adhesive composition of claim 1 wherein the fibrous reinforcing material comprises at least one fiber having a diameter of less than about 5 micrometers.

10

12. The adhesive composition of claim 1 wherein the fibrous reinforcing material comprises at least one fiber having an aspect ratio of greater than about 1000.

15

13. The adhesive composition of claim 1 wherein the pressure sensitive adhesive comprises a pressure sensitive adhesive based on at least one of a natural rubber, synthetic rubber, styrene block copolymer, polyvinyl ether, poly(meth)acrylate, polyolefin, silicone or combinations thereof.

20

14. The adhesive composition of claim 1 wherein the pressure sensitive adhesive comprises a polymer derived from at least one alkyl (meth)acrylate ester monomer selected from isooctyl acrylate, 2-ethyl-hexyl acrylate, and n-butyl acrylate; and at least one co-monomer selected from acrylic acid and acrylamide.

25

15. The adhesive composition of claim 1 wherein the reinforcing material comprises an elastomer having a yield strength no greater than about 20 MPa and a tensile strength of at least about 150% of the yield strength.

30

16. The adhesive composition of claim 1 wherein the reinforcing material comprises a semi crystalline polymer.

17. The adhesive composition of claim 1 wherein the reinforcing material has a melting point greater than about 70 °C.

18. A substrate at least partially coated with the adhesive composition of claim 1.

19. The substrate of claim 18 wherein the substrate comprises a release liner.

20. A tape comprising  
a backing having a first and second side; and  
the adhesive composition of claim 1 coated on at least a portion of the first  
side of the backing.

21. A tape comprising  
a backing having a first and second side; and  
the adhesive composition of claim 1 coated on at least a portion of the first side of  
the backing and, optionally, on at least a portion of the second side of the backing.

22. A stretch removable article comprising the adhesive composition of claim 1.

23. The adhesive composition of claim 1 wherein the adhesive composition is stretch  
removable from a substrate.

24. An adhesive composition comprising  
a pressure sensitive adhesive matrix; and  
a fibrous reinforcing material, having a melting temperature of no less than about  
70°C, within the pressure sensitive adhesive matrix;  
wherein the adhesive composition has a yield strength and a tensile strength, and  
the tensile strength is at least about 150% of the yield strength.

25. A method for making a fiber reinforced adhesive composition comprising  
(a) forming a mixture comprising a pressure sensitive adhesive with a  
reinforcing material capable of forming fibers when subjected to an elongating shear  
force; and

(b) subjecting the mixture to the elongating shear force to form the adhesive composition of claim 1.

26. The method of claim 25 further comprising quenching the adhesive composition.

27. A medical article comprising the adhesive composition of claim 1.

28. The medical article of claim 27 which is in the form of a wound dressing, surgical dressing, medical tape, athletic tape, or surgical tape.

29. The medical article of claim 27 which is in the form of a sensor, an electrode, or an ostomy appliance.

## INTERNATIONAL SEARCH REPORT

Int'l Application No

PCT/US 01/18500

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09J7/02 C09J11/08 C09J7/00 C08K7/02 A61L15/58  
C09J133/08

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09J C08K A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 97 23577 A (MINNESOTA MINING & MFG ;HYDE PATRICK D (US); WONG ROY (US); KRUEGE) 3 July 1997 (1997-07-03) claim 1 page 13, line 13 - line 21 page 17, line 30,31 -----	1,18, 20-22, 24,25,27
X	DE 12 49 428 B (MINNESOTA MINING AND MANUFACTURING COMPANY) 7 September 1967 (1967-09-07) column 1, line 1 - line 12 column 2, line 50 -column 3, line 10 example 1 -----	1,18,20, 24



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

## ° Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*Z\* document member of the same patent family

Date of the actual completion of the international search

21 December 2001

Date of mailing of the international search report

25/01/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Schlicke, B

## INTERNATIONAL SEARCH REPORT

Information on patent family members

Int: International Application No

PCT/US 01/18500

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9723577	A	03-07-1997	AU 705376 B2	20-05-1999
			AU 6898596 A	17-07-1997
			BR 9612254 A	13-07-1999
			CA 2241032 A1	03-07-1997
			EP 0868498 A1	07-10-1998
			JP 2000502385 T	29-02-2000
			NZ 316689 A	29-04-1999
			WO 9723577 A1	03-07-1997
			US 6063838 A	16-05-2000
			AU 4655896 A	04-09-1996
			BR 9607254 A	30-12-1997
			CA 2213243 A1	22-08-1996
			CN 1174564 A	25-02-1998
			EP 0809681 A1	03-12-1997
			JP 11501956 T	16-02-1999
			NO 973688 A	14-10-1997
			WO 9625469 A1	22-08-1996
<hr/>				
DE 1249428	B		NONE	
<hr/>				