

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization

International Bureau



(10) International Publication Number

WO 2017/105918 A1

(43) International Publication Date

22 June 2017 (22.06.2017)

AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(51) International Patent Classification:

*C09J 153/02* (2006.01) *C09D 133/08* (2006.01)  
*C09J 133/08* (2006.01) *C09D 133/10* (2006.01)  
*C09J 133/10* (2006.01) *C09D 133/14* (2006.01)  
*C09J 133/14* (2006.01) *C09D 5/00* (2006.01)  
*C09D 109/06* (2006.01)

(21) International Application Number:

PCT/US2016/065090

(22) International Filing Date:

6 December 2016 (06.12.2016)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

62/268,794 17 December 2015 (17.12.2015) US

(71) Applicant: 3M INNOVATIVE PROPERTIES COMPANY [US/US]; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(72) Inventors: MOREN, Dean M.; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US). AMOS, David T.; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(74) Agents: DAHL, Philip Y. et al.; 3M Center, Office of Intellectual Property Consel, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM,

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

#### Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))

#### Published:

- with international search report (Art. 21(3))



WO 2017/105918 A1

(54) Title: PRIMER COMPOSITION AND ARTICLES MADE THEREFROM

(57) Abstract: There are provided primer compositions comprising a primer component comprising: a rubber; an amine-functional (meth)acrylic resin; and a plasticizer. There are also provided articles made using these primer compositions.

## PRIMER COMPOSITION AND ARTICLES MADE THEREFROM

### FIELD

[0001] This disclosure relates to a primer composition comprising a primer component. The present 5 disclosure also relates to a primer composition having a primer component and a liquid carrier.

### BACKGROUND

[0002] Low surface energy substrates such as polyethylene, polypropylene, and other polyolefins are characterized as having critical surface tensions of wetting of about 35 dynes/cm or less. Such surfaces are generally unreceptive to inks, paints, and adhesives due to their poor wettability. There is a need to 10 improve adhesion to such surfaces, as well as to high energy surfaces.

[0003] Some tapes afford very high bond strengths to a wide variety of clean substrates. In some instances, primers may be applied before bonding to ensure maximum bond strength, which can be desirable for some applications. Use of some conventional primers may be complicated by various 15 factors, including government regulations and detrimental effects to substrates, such as for example, crazing and corrosion.


[0004] Commercially available primers, such as those known as universal primers, advertise adhesion to low surface energy, medium surface energy, and high surface energy substrates including polypropylene, thermoplastic polyolefin, ABS, Nylon, acrylic, polycarbonate, paints, stainless steel, and aluminum. These primers often comprise aromatic solvents (e.g. xylene, toluene, ethylbenzene, 20 chlorobenzene), halogen-based compounds (e.g. chlorinated polyolefin), and Bisphenol A-based compounds (e.g. epoxy resin).

[0005] There is a need for primer compositions comprising a primer component that provide strong adhesion to a wide range of low surface energy, medium surface energy, and high surface energy surfaces that are substantially free of aromatic solvents, halogen compounds, and Bisphenol A-based compounds. 25 There is also a need for these primer compositions to provide strong adhesion between double sided tapes, such as for example, double sided foam tapes, and a wide range of surfaces.

### SUMMARY


[0006] The present disclosure provides primer compositions comprising a non-volatile primer component that provide strong adhesion to a wide range of low surface energy, medium surface energy, 30 and high surface energy surfaces and that are substantially free of aromatic solvents, halogen compounds, and Bisphenol A-based compounds. The present disclosure also provides such primer compositions having strong adhesion between double sided tapes, such as for example, double sided foam tapes, and a wide range of surfaces.

[0007] In one aspect, the present disclosure provides a primer composition comprising a primer component comprising: a rubber; an amine-functional (meth)acrylic resin; and a plasticizer. In some embodiments, the amine-functional (meth)acrylic resin is a polymerization reaction product of an amine-functional (meth)acryloyl compound and a non-amine-vinyl monomer; wherein the amine-functional (meth)acryloyl compound is of Formula (I):



wherein R1 is hydrogen, alkyl, or aralkyl; R2 is alkyl or aralkyl; or R1 and R2 together with the nitrogen atom with which they are joined may form a 5, 6, or 7 member ring; R3 is alkylene or aralkylene; X is nitrogen or oxygen; R4 does not exist if X is oxygen and is hydrogen, alkyl, aryl, alkaryl, or aralkyl if X is nitrogen; and R5 is hydrogen or methyl;

wherein the amine-functional (meth)acryloyl compound is of Formula (II):



wherein R1 is hydrogen, alkyl, or aralkyl; each R3 is independently alkylene or aralkylene; X is nitrogen; and R5 is hydrogen or methyl; or combinations thereof.

[0008] In some embodiments, the amine-functional (meth)acrylic resin has a calculated glass transition temperature (Tg) greater than or equal to 12°C. In some embodiments, the amine-functional (meth)acrylic resin has a calculated Tg greater than or equal to 20°C. In some embodiments, the non-amine-vinyl monomer is selected from the group consisting of a (meth)acrylic acid, a (meth)acrylic acid ester, a (meth)acrylamide, a vinyl ester, a styrene, a (meth)acrylonitrile, and mixtures thereof. In some embodiments, the non-amine-vinyl monomer is a (meth)acrylic acid ester of a C1 to C18 alcohol.

[0009] In some embodiments, the rubber comprises a block copolymer of a styrene and an alkene. In some embodiments, the rubber comprises a styrene-ethylene/butylene-styrene block copolymer grafted with maleic anhydride.

[0010] In some embodiments, the plasticizer is of Formula III:

(R-X-)<sub>n</sub>Z        (III)

wherein: each R may be hydrogen, C1-C14 alkyl, aryl, alkaryl, or aralkyl; each optionally interrupted by oxygen, nitrogen, carbonyl, carboxyl, or carbamide; each X may be oxygen, nitrogen, carbonyl, carboxyl, or carbamide; Z may be a hydrogen, C1-C14 alkyl, aryl, alkaryl, aralkyl, C1-C14 alkylene, arylene, alkarylene, aralkylene; each optionally interrupted by oxygen, nitrogen, carbonyl, carboxyl, or carbamide; and n is an integer of 1 to 5. In some embodiments, n is an integer of 1 to 4.

5 [0011] In some embodiments, the plasticizer is selected from at least one of the following; a benzoic acid ester, a myristic acid ester, a citric acid ester, an acetic acid ester, a succinic acid ester, a glutaric acid ester, an adipic acid ester, a sebatic acid ester, and combinations thereof. In some embodiments, the plasticizer is selected from at least one of the following; a benzoic acid ester, a myristic acid ester, a citric acid ester, and combinations thereof. A citric acid ester may have one, two, three, or four R groups as referenced in Formula III.

10 [0012] In some embodiments, the primer component comprises: 35 wt.% to 70 wt.% of the rubber; 20 wt.% to 35 wt.% of the amine-functional (meth)acrylic resin; and 10 wt.% to 40 wt.% of the plasticizer, wherein the weight percentages are all based on the total weight of the primer component. In some 15 embodiments, the primer component comprises: 40 wt.% to 60 wt.% of the rubber; 20 wt.% to 35 wt.% of the amine-functional (meth)acrylic resin; and 15 wt.% to 35 wt.% of the plasticizer, wherein the weight percentages are all based on the total weight of the primer component.

20 [0013] In some embodiments, the primer composition further comprises a liquid carrier. In some embodiments, the liquid carrier is a solvent. In some embodiments, the primer composition comprises: 1 wt.% to 25 wt.% of the primer component; and 75 wt.% to 99 wt.% of the solvent, wherein the weight percentages are all based on the total weight of the primer composition. In some embodiments, the primer composition comprises: 2 wt.% to 7 wt.% of the primer component; and 93 wt.% to 98 wt.% of the solvent, wherein the weight percentages are all based on the total weight of the primer composition.

25 [0014] In some embodiments, the solvent is a solvent blend having a Hildebrand total solubility parameter in a range from about 15 MPa<sup>1/2</sup> to about 17.5 MPa<sup>1/2</sup>. In some embodiments, the plasticizer has a Predicted Enthalpy of Evaporation greater than about 50 kJ/mol. In some embodiments, the plasticizer has a Predicted Enthalpy of Evaporation greater than about 55 kJ/mol.

30 [0015] In another aspect, the present disclosure provides an article comprising: a substrate; and a layer of any of the aforementioned primer components disposed on at least one outer surface of the substrate. In some embodiments, the article further comprises a layer of adhesive disposed on the layer of the primer component opposite the substrate. In some embodiments, the article further comprises a backing layer disposed on the layer of adhesive opposite the layer of any of the aforementioned primer component.

[0016] The above summary of the present disclosure is not intended to describe each embodiment of the present invention. The details of one or more embodiments of the invention are also set forth in the

description below. Other features, objects, and advantages of the invention will be apparent from the description and from the claims.

#### DETAILED DESCRIPTION

5     **[0017]** Before any embodiments of the invention are explained in detail, it is to be understood that the invention is not limited in its application to the details of construction and the arrangement of components set forth in the following description. The invention is capable of other embodiments and of being practiced or of being carried out in various ways. Also, it is to be understood that the phraseology and terminology used herein is for the purpose of description and should not be regarded as limiting. The use 10 of "including," "comprising," or "having" and variations thereof herein is meant to encompass the items listed thereafter and equivalents thereof as well as additional items. Any numerical range recited herein includes all values from the lower value to the upper value. For example, if a concentration range is stated as 1% to 50%, it is intended that values such as 2% to 40%, 10% to 30%, or 1% to 3%, etc., are expressly enumerated. These are only examples of what is specifically intended, and all possible combinations of 15 numerical values between and including the lowest value and the highest value enumerated are to be considered to be expressly stated in this application.

20     **[0018]** Primer compositions of the present disclosure are conveniently applied in liquid form, for example from the melt; as aqueous emulsions, dispersions, or suspensions; or, preferably, as solvent solutions. Preferred solvent solutions are homogeneous and storage stable and minimally attack substrate during use. Solvent solutions may comprise a single solvent or a blend of solvents.


25     **[0019]** As used herein, a primer surface preparation, derived from the presently disclosed primer composition comprising non-volatile primer component, is considered to provide strong adhesion to double sided tapes, such as for example, double sided foam tapes, when there is a peel adhesion of at least 35 Newtons per centimeter (N/cm) (20 pounds per inch width (piw)) between two bonded substrates, preferably peel adhesion exceeding 52 N/cm (30 piw) between two bonded substrates, and more preferably peel adhesion exceeding 52 N/cm (30 piw) between two bonded substrates and resulting in cohesive failure in the tape.

30     **[0020]** The present disclosure provides a primer composition having a primer component comprising a rubber, an amine-functional (meth)acrylic resin, and a plasticizer. In some embodiments, the present disclosed primer composition comprises a rubber, an amine-functional (meth)acrylic resin, a plasticizer, and an aliphatic hydrocarbon.

**[0021]** Rubbers useful in the present disclosure include block copolymers of styrene and alkene, preferably hydrogenated styrene/alkene block copolymers, and more preferably hydrogenated styrene/alkene block copolymers further bearing pendant anhydride moieties. Most preferably, the rubber


is a styrene-ethylene/butylene-styrene block copolymer grafted with maleic anhydride, such as those available under the trade designation “KRATON FG1901” from Kraton Performance Polymers Inc., Houston, Texas.

**[0022]** Amine-functional acrylic resins useful in the present disclosure include those derivable by copolymerization of amine-functional (meth)acrylic acid esters and amides with non-amine-functional vinyl monomers. Amine-functional acrylic acid esters and amides are selected from those of Formula (I)



**[0023]** wherein R1 is hydrogen, alkyl, or aralkyl; R2 is alkyl or aralkyl; or R1 and R2 together with the nitrogen atom with which they are joined may form a 5, 6, or 7 member ring; R3 is alkylene or aralkylene; X is nitrogen or oxygen; R4 does not exist if X is oxygen and is hydrogen, alkyl, aryl, alkaryl, or aralkyl if X is nitrogen; and R5 is hydrogen or methyl;

**[0024]** and those of Formula (II)



**[0025]** wherein R1 is hydrogen, alkyl, or aralkyl; each R3 is independently alkylene or aralkylene; X is nitrogen; and R5 is hydrogen or methyl.

**[0026]** Preferred amine-functional (meth)acrylic acid esters and amides include 2-(N,N-dimethylaminoethyl) (meth)acrylate; 2-(N,N-diethylaminoethyl) (meth)acrylate; 2-(t-butylaminoethyl) (meth)acrylate; 2-(N,N-dimethylaminoethyl) (meth)acrylamide; 2-(N,N-diethylaminoethyl) (meth)acrylamide; 2-(t-butylaminoethyl) (meth)acrylamide; and N-(meth)acryloylpiperidine. 2-(N,N-dimethylaminoethyl) methacrylate and 2-(t-butylaminoethyl) methacrylate are particularly preferred.

**[0027]** In some embodiments, the amine-functional (meth)acrylic resin has a calculated Tg greater than or equal to 12°C. In some embodiments, the amine-functional (meth)acrylic resin has a calculated Tg greater than or equal to 20°C. The calculated Tg of an amine-functional (meth)acrylic resin can be conveniently estimated according to Formula V

$$Tg_{\text{amine-functional (meth)acrylic resin}} = 1/(\sum(W_i/(Tg_i+273))-273)$$

wherein  $Tg_{\text{amine-functional (meth)acrylic resin}}$  is the calculated Tg for the amine-functional (meth)acrylic resin and  $W_i$  and  $Tg_i$  are weight fraction and homopolymer Tg for individual amine-functional (meth)acrylic acid

esters and amides and non-amine-functional vinyl monomers present in the amine-functional (meth)acrylic resin. Each Tg has units in degrees Celsius. Values for homopolymer Tg for individual amine-functional (meth)acrylic acid esters and amides and non-amine-functional vinyl monomers are conveniently tabulated, for example, in *Polymer Handbook, 2nd edition*. John Wiley, 1975.

5 [0028] Non-amine-functional vinyl monomers include, for example, (meth)acrylic acid and their esters and amides, vinyl esters, styrene, and (meth)acrylonitrile. (meth)acrylic acid esters are preferred non-amine-functional vinyl monomers. More preferred (meth)acrylic acid esters are formally esters of (meth)acrylic acid with C1 to C18 alcohols.

10 [0029] Plasticizers useful in the present disclosure remain in the primer coating after evaporation of a liquid carrier, for example, a solvent, and minimize attack (e.g. dissolution, crazing, marring, discoloration) on a substrate used therewith. Preferred plasticizers have Predicted Enthalpies of Evaporation greater than about 50 kJ/mol and general structure of Formula III

15 [0030] (R-X-)<sub>n</sub>Z        wherein

[0031] each R may be hydrogen, C1-C14 alkyl, aryl, alkaryl, or aralkyl; each optionally interrupted by 15 oxygen, nitrogen, carbonyl, carboxyl, or carbamide;

[0032] each X may be oxygen, nitrogen, carbonyl, carboxyl, or carbamide;

[0033] each Z may be a hydrogen, C1-C14 alkyl, aryl, alkaryl, aralkyl, C1-C14 alkylene, arylene, alkarylene, aralkylene; each optionally interrupted by oxygen, nitrogen, carbonyl, carboxyl, or carbamide; and

20 [0034] n is an integer ranging from 1 to 5, or in some embodiments, n is an integer ranging from 1 to 4.

25 [0035] Preferred plasticizers include benzoic acid ester, myristic acid ester, citric acid ester, acetic acid ester, succinic acid ester, glutaric acid ester, adipic acid ester, and sebacic acid ester, and combinations thereof. More preferred plasticizers include benzoic acid ester, myristic acid ester, and citric acid ester.

30 [0036] Plasticizers useful in the present disclosure preferably resist evaporation and remain in the primer component for prolonged periods. While volatile plasticizers can be useful, for example, when a priming step immediately precedes a tape bonding step, preferred plasticizers remain in the primer component even when the tape bonding step is delayed. Useful plasticizers preferably retain efficacy for at least three minutes after application, more preferably for at least 60 minutes, most preferably for at least 24 hours. Resistance to evaporation can be conveniently quantified according to the predicted enthalpy of vaporization values provided by commercially available chemical computation software, such as that available under the name "Percepta Predictors—Software Modules to Predict Physicochemical,

ADME, and Toxicity Properties" from Structure Advanced Chemistry Development (publicly available by accessing the website called <http://www.chemspider.com> (last accessed on November 20, 2015).

Preferred plasticizers useful in the present disclosure have predicted enthalpies of vaporization greater than about 50 kJ/mol, and more preferably greater than about 55 kJ/mol. Predicted enthalpy of vaporization for plasticizers useful in the present disclosure are listed in the table below:

Compound	Predicted Enthalpy of Vaporization (kJ/mol)
tributyl acetylcitrate	89
tributyl citrate	74
dipropylene glycol dibenzoate	73
diethylene glycol dibenzoate	66
propylene glycol dicaprate/caprylate	65
dibutyl tartarate	65
triethyl citrate	62
diethyl tartarate	60
diethyl malate	60
isodecyl benzoate	59
dibutyl phthalate	58
triethyl acetylcitrate	57
isopropyl myristate	56
diethyl sebacate	55
ethyl toluenesulfonamide	55
ethylhexyl benzoate	55
dibutyl itaconate	55
dibutyl adipate	54
dimethyl sebacate	54
dibutyl fumarate	52
tributyl phosphate	51
phenoxypropanol	51
glycerol triacetate	50
butyl lactate	49
dimethyl adipate	47
diethyl succinate	46

**[0037]** In some embodiments, the present disclosure provides a primer composition having a primer component comprising a rubber, an amine-functional (meth)acrylic resin, a plasticizer, and a liquid carrier. In some embodiments, the present disclosed primer composition comprises a rubber, an amine-functional (meth)acrylic resin, a plasticizer, and an aliphatic hydrocarbon. Preferred liquid carrier useful in the present disclosure is solvent.

**[0038]** In some embodiments, the presently disclosed primer composition comprises: 1 wt.% to 25 wt.% of the primer component; and 75 wt.% to 99 wt.% of the solvent, where the weight percentages are all based on the total weight of the primer composition. In some embodiments, the presently disclosed primer composition comprises: 2 wt.% to 7 wt.% of the primer component; and 93 wt.% to 98 wt.% of the solvent, where the weight percentages are all based on the total weight of the primer composition.

[0039] Solvent solutions useful in the present disclosure are those having a Hildebrand total solubility parameter between about 15 MPa<sup>1/2</sup> and about 17.5 MPa<sup>1/2</sup>. Hildebrand total solubility parameters for single solvents are conveniently tabulated, for example, in *Handbook of Solubility Parameters and Other Cohesion Parameters, 2nd edition*. CRC Press, 1991. Hildebrand total solubility parameters for solvent blends can be estimated from the volume averaged Hildebrand total solubility parameters of the individual solvent components in the solvent blend according to Formula IV

$$SP_{blend} = \Sigma(W_i/SG_i \times SP_i) / \Sigma(W_i/SG_i)$$

[0040] wherein  $SP_{blend}$  is the Hildebrand total solubility parameter of the solvent blend and  $W_i$ ,  $SG_i$ , and  $SP_i$  are weight fraction, specific gravity, and Hildebrand total solubility parameter for each individual solvent in the blend. Representative Hildebrand total solubility parameter and specific gravity for select individual solvents and various solvent blends follow.

Individual Solvent	$SP_i$ (MPa <sup>1/2</sup> )	$SG_i$ (g/ml)
hexamethyldisiloxane (HMDS)	11.7	0.77
heptane	15.3	0.68
methylcyclohexane (MCH)	16.0	0.77
t-butyl acetate (tBAC)	16.2	0.87
methyl acetate (MAC)	19.4	0.94
acetone	19.7	0.79

Solvent Blend	Estimated $SP_{blend}$ (MPa <sup>1/2</sup> )
40/40/20 MCH/MAC/HMDS	16.3
30/40/30 MCH/MAC/HMDS	15.8
60/40 heptane/MAC	16.6
40/40/20 heptane/MAC/tBAC	16.9
46/15/39 heptane/MCH/MAC	16.7

[0041] Individual solvents preferably useful in the present disclosure include acetone, methyl acetate, t-butyl acetate, hexamethyldisiloxane, heptane, and methylcyclohexane.

[0042] More preferred solvent solutions for use in the present disclosure comprise less than 0.1 wt.% of any one aromatic hydrocarbon including, for example, benzene, toluene, xylene, ethylbenzene, and chlorobenzene. Even more preferred solvent solutions comprise less than 0.1 wt.% total aromatic hydrocarbon. Most preferably, the solvent solution comprises less than 0.01 wt.% total aromatic hydrocarbon.

[0043] More preferred solvent solutions comprise, for example 0-50 wt.% acetone, 0-50 wt.% methyl acetate, 0-40 wt.% hexamethyldisiloxane, and 0-40 wt.% t-butyl acetate. More preferred solvent solutions additionally comprise 25-90 wt.% aliphatic alkane, including straight chain, branched, and cyclic

hydrocarbons, especially those having five to twelve carbon atoms. Heptane and methylcyclohexane are especially preferred aliphatic alkanes. More preferred solvent solutions comprise 25-45 wt.% acetone or methyl acetate, 0-25 wt.% hexamethyldisiloxane, and 35-75 wt.% aliphatic alkane. Most preferred solvent solutions comprise methyl acetate and methylcyclohexane or methyl acetate and heptane.

5 [0044] Preferred primer compositions of the present disclosure comprise 92 to 99 wt.% volatile solvents and 1 to 8 wt.% non-volatile primer components, more preferably 94 to 97 wt.% volatile solvents and 3 to 6 wt.% non-volatile primer components.

10 [0045] In some embodiments, the presently disclosed primer composition comprises a primer component, where the primer component comprises: 35 wt.% to 70 wt.% of the rubber; 20 wt.% to 35 wt.% of the amine-functional (meth)acrylic resin; and 10 wt.% to 40 wt.% of the plasticizer, where the weight percentages are all based on the total weight of the primer component. In some embodiments, the presently disclosed primer composition comprises a primer component, where the primer component comprises: 40 wt.% to 60 wt.% of the rubber; 20 wt.% to 35 wt.% of the amine-functional (meth)acrylic resin; and 15 wt.% to 35 wt.% of the plasticizer, where the weight percentages are all based on the total weight of the primer component.

15 [0046] In some embodiments, the primer composition further comprises a colorant. In some embodiments, the colorant is fluorescent.

20 [0047] The present disclosure provides primer compositions comprising primer component that exhibit good adhesion to both low energy surfaces (e.g., polyolefins, such as polypropylene), as well as higher energy surfaces (i.e., having surface energies greater than 35 dynes/cm such as metal). The primer compositions are useful as primers (e.g., for use with adhesives, paints, and coatings).


25 [0048] In some embodiments, articles can be made comprising: a substrate; and a primer surface treatment of any of the previously disclosed embodiments of the primer component disposed on at least one surface of the substrate. These articles can also include a layer of adhesive disposed on the layer of the primer surface treatment opposite the substrate. In some embodiments, these articles can also include a backing layer disposed on the layer of adhesive opposite the layer of the primer surface treatment.

[0049] Following are non-limiting, exemplary embodiments and combinations of embodiments for the present disclosure:

30 [0050] Embodiment 1. A primer composition comprising a primer component comprising: a rubber; an amine-functional (meth)acrylic resin; and a plasticizer.


[0051] Embodiment 2. The primer composition of Embodiment 1, wherein the amine-functional (meth)acrylic resin is a polymerization reaction product of an amine-functional (meth)acryloyl compound

and a non-amine-vinyl monomer; wherein the amine-functional (meth)acryloyl compound is of Formula (I):



wherein R1 is hydrogen, alkyl, or aralkyl; R2 is alkyl or aralkyl; or R1 and R2 together with the nitrogen atom with which they are joined may form a 5, 6, or 7 member ring; R3 is alkylene or aralkylene; X is nitrogen or oxygen; R4 does not exist if X is oxygen and is hydrogen, alkyl, aryl, alkaryl, or aralkyl if X is nitrogen; and R5 is hydrogen or methyl;

wherein the amine-functional (meth)acryloyl compound is of Formula (II):



10 wherein R1 is hydrogen, alkyl, or aralkyl; each R3 is independently alkylene or aralkylene; X is nitrogen; and R5 is hydrogen or methyl; or combinations thereof.

**[0052]** Embodiment 3. The primer composition of Embodiment 1 or 2, wherein the amine-functional (meth)acrylic resin has a calculated Tg greater than or equal to 12°C.

**[0053]** Embodiment 4. The primer composition of Embodiment 2, wherein the non-amine-vinyl monomer is selected from the group consisting of a (meth)acrylic acid, a (meth)acrylic acid ester, a (meth)acrylamide, a vinyl ester, a styrene, a (meth)acrylonitrile, and mixtures thereof.

**[0054]** Embodiment 5. The primer composition of any of Embodiments 2, 3 or 4, wherein the non-amine-vinyl monomer is a (meth)acrylic acid ester of a C1 to C18 alcohol.

**[0055]** Embodiment 6. The primer composition of any of the preceding Embodiments, wherein the rubber comprises a block copolymer of a styrene and an alkene.

**[0056]** Embodiment 7. The primer composition of any of the preceding Embodiments, wherein the rubber comprises a styrene-ethylene/butylene-styrene block copolymer grafted with maleic anhydride.

**[0057]** Embodiment 8. The primer composition of any of the preceding Embodiments, wherein the plasticizer is of Formula III:

25  $(R-X-nZ)$  (III)

wherein: each R may be hydrogen, C1-C14 alkyl, aryl, alkaryl, or aralkyl; each optionally interrupted by oxygen, nitrogen, carbonyl, carboxyl, or carbamide; each X may be oxygen, nitrogen, carbonyl, carboxyl, or carbamide; Z may be a hydrogen, C1-C14 alkyl, aryl, alkaryl, aralkyl, C1-C14 alkylene, arylene, alkarylene, aralkylene; each optionally interrupted by oxygen, nitrogen, carbonyl, carboxyl, or carbamide; and n is an integer of 1 to 5.

5 [0058] Embodiment 9. The primer composition of Embodiment 8, wherein n is an integer of 1 to 4.

10 [0059] Embodiment 10. The primer composition of any of the preceding Embodiments, wherein the plasticizer is selected from at least one of the following a benzoic acid ester, a myristic acid ester, a citric acid ester, an acetic acid ester, a succinic acid ester, a glutaric acid ester, an adipic acid ester, a sebacic acid ester, and combinations thereof.

[0060] Embodiment 11. The primer composition of any Embodiments 1 to 9, wherein the plasticizer is selected from at least one of the following a benzoic acid ester, a myristic acid ester, a citric acid ester, and combinations thereof.

15 [0061] Embodiment 12. The primer composition of any of the preceding Embodiments, wherein the primer component comprises: 35 wt.% to 70 wt.% of the rubber; 20 wt.% to 35 wt.% of the amine-functional (meth)acrylic resin; and 10 wt.% to 40 wt.% of the plasticizer, wherein the weight percentages are all based on the total weight of the primer component.

20 [0062] Embodiment 13. The primer composition of any of Embodiments 1 to 11 wherein the primer component comprises: 40 wt.% to 60 wt.% of the rubber; 20 wt.% to 35 wt.% of the amine-functional (meth)acrylic resin; and 15 wt.% to 35 wt.% of the plasticizer, wherein the weight percentages are all based on the total weight of the primer component.

[0063] Embodiment 14. The primer composition of any of the preceding Embodiments further comprising a liquid carrier.

25 [0064] Embodiment 15. The primer composition of Embodiment 14 wherein the liquid carrier is a solvent.

[0065] Embodiment 16. The primer composition of Embodiment 15, wherein the primer composition comprises: 1 wt.% to 25 wt.% of the primer component; and 75 wt.% to 99 wt.% of the solvent, wherein the weight percentages are all based on the total weight of the primer composition.

30 [0066] Embodiment 17. The primer of Embodiment 15, wherein the primer composition comprises: 2 wt.% to 7 wt.% of the primer component; and 93 wt.% to 98 wt.% of the solvent, wherein the weight percentages are all based on the total weight of the primer composition.

**[0067]** Embodiment 18. The primer composition of any of Embodiments 15 to 17 wherein the solvent is a solvent blend having a Hildebrand total solubility parameter in a range from about 15 MPa<sup>1/2</sup> to about 17.5 MPa<sup>1/2</sup>.

5 **[0068]** Embodiment 19. The primer composition of any of the preceding Embodiments wherein the plasticizer has a Predicted Enthalpy of Evaporation greater than about 50 kJ/mol.

**[0069]** Embodiment 20. The primer composition of Embodiment 1 or 2, wherein the amine-functional (meth)acrylic resin has a calculated Tg greater than or equal to 20°C.

**[0070]** Embodiment 21. The primer composition of any of the preceding Embodiments wherein the plasticizer has a Predicted Enthalpy of Evaporation greater than about 55 kJ/mol.

10 **[0071]** Embodiment 22. An article comprising: a substrate; and a layer of any of the aforementioned primer components disposed on at least one outer surface of the substrate.

**[0072]** Embodiment 23. The article of Embodiment 22 further comprising a layer of adhesive disposed on the layer of any of the aforementioned primer components opposite the substrate.

15 **[0073]** Embodiment 24. The article of Embodiment 23 further comprising a backing layer disposed on the layer of adhesive opposite the layer of the primer component.

**[0074]** Various modifications and alterations of this invention will become apparent to those skilled in the art without departing from the scope and spirit of this invention.

### EXAMPLES

20

TABLE 1. Materials

Designation	Description	Source
MMA	methyl methacrylate	Dow Chemical, Midland, MI
IOA	iso-octyl acrylate	3M Co., St. Paul, MN
tBAEMA	2-(t-butylamino)ethyl methacrylate	BASF, Florham Park, NJ
MAC	Methyl acetate	Alfa-Aesar, Ward Hill, MA
VAZO	2,2'-azobis(2-methylbutyronitrile)	DuPont, Wilmington, DE
NVC	N-vinylcaprolactam	BASF, Florham Park, NJ
KRATON FG1901	a clear, linear triblock copolymer based on styrene and ethylene/butylene	Kraton Polymers, Houston, TX
TINOPAL OB	2,5-thiophenediylbis(5-tert-butyl-1,3-benzoxazole	BASF, Florham Park, NJ
ATBC	tributyl acetylcitrate	Lanxess, Orange, TX
A186	2-(3,4-epoxycyclohexyl)ethyltrimethoxysilane	Momentive, Columbus, OH

MCH	methylcyclohexane	Alfa-Aesar, Ward Hill, MA
HMDS	hexamethyldisiloxane	Alfa-Aesar, Ward Hill, MA
AA	Acrylic acid	Dow Chemical, Midland, MI

### Test Methods

#### Polymer Inherent Viscosity

The inherent viscosity was determined by conventional means using a Cannon-Fenske #50 viscometer in a 25°C water bath to measure the flow time of 10 milliliters polymer solution (0.60 grams per deciliter of ethyl acetate.)

#### Primer Component Adhesion Performance (“Peel Test”)

Substrates were cleaned with SURPASS facial tissues (Kimberly-Clark) wetted with aqueous isopropyl alcohol (50:50 vol/vol) then allowed to dry. The Primer Composition was poured onto a fresh SURPASS 10 facial tissue, applied to substrates in even coats, and allowed to dry for three minutes. 3M™ VHB™ TAPE 4611 tape strips (1 inch x 4 inches, ~2.5 cm x ~10 cm) were backed on one face with anodized aluminum foil and the other face was placed onto the primed surface, then pressed down twice under a 15 pound (6.8 kg) roller moving at 12 inches (~30 cm) per minute. 90° peel strengths were assessed after standing 15 overnight at room temperature, pulling the anodized aluminum foil backing perpendicular to the substrate at 12 inches (~30 cm) per minute. The average peel force was recorded along with failure mode. Failure mode “fs” indicates cohesive failure within the foam tape during testing, “cp” means the tape peeled cleanly from the surface and the tape did not fail cohesively during testing, and “mix” indicates a mixture of fs and cp failure modes were observed during testing. A list of adhesion performance test substrates immediately follows:

#### Adhesion Performance Test Substrates

Designation	Description	Source
stainless steel	Polished stainless steel	ChemInstruments, Fairfield, OH
acrylic	Acrylic Clear, Ext PE Mask, 0.118" thick	Plastics International, Eden Prairie, MN
polycarbonate	MAKROLON GP, clear, 0.118" thick	Plastics International
ABS	ABS Natural (Tan) S/S Ext, 0.125" thick	Plastics International
Nylon	Nylon Type 6/6 Natural, 0.125" thick	Plastics International
Rigid PVC	Type 1 Grade 1 Gray PVC, 0.125" thick	Plastics International
polyester FRP	GPO-3 Polyester/Glass red, 0.125" thick, glass fiber reinforced polyester	Plastics International
Epoxy FRP	FR4 Epoxy/Glass, 0.125" thick, glass fiber reinforced thermoset epoxy resin	Plastics International
phenolic	CE Phenolic/Canvas Natural, 0.125" thick, canvas reinforced phenolic	Plastics International

TPO	BASEL HIFAX ETA 3131 BLK thermoplastic polyolefin	Standard Plaque, Melvindale, MI
polypropylene	Polypropylene SR Natural, 0.125" thick	Plastics International
white truck paint	DC105W-2196 19G1393 POLAR WHITE, roll-coated, heat-cured, wax-containing coating (0.75mil thick) on 0.019" thick aluminum	Dura Coat Products, Huntsville, AL

Preparative Example 1 (PE-1): Preparation of Amine-Functional Acrylic Resin 1 (AFAR1)(55:30:15 MMA/IOA/tBAEMA, at 40 wt.% solids in MAC)

A reactor was charged with 132 grams MMA, 72 grams IOA, 36 grams of tBAEMA, 360 grams of MAC, and 1.92 grams of VAZO 67. The solution was deoxygenated with nitrogen, the reactor was sealed, and the solution was heated 46 hours at 65°C, then allowed to cool. The resulting solution was found to contain 40.3 wt.% solids and had inherent viscosity of 0.36.

Preparative Examples 2 to 9 (PE-2 to PE-9): Amine-Functional Acrylic Resins 2 to 9 (AFAR2-AFAR9)

The general procedure for preparation of PE-1 was repeated (with the same relative amounts of MAC and VAZO 67), but altering monomer weight ratios and/or incorporating alternative monomers, according to the amounts indicated in Table 2, with the resulting inherent viscosity and wt.% solid ("phr" is per hundred weight resin) values listed.

TABLE 2

Preparative Example	"AFAR" number	MMA, phr	BMA, phr	IOA, phr	tBAEMA, phr	DMAEMA, phr	Calculated Tg	Inherent viscosity	Wt.% solids
PE-1	AFAR1	55	0	30	15	0	26°C	0.36	40.3
PE-2	AFAR2	42	0	42	16	0	6°C	0.38	40.1
PE-3	AFAR3	35	53	0	12	0	49°C	0.42	34.2
PE-4	AFAR4	35	53	0	0	12	47°C	0.37	34.9
PE-5	AFAR5	42	42	0	16	0	55°C	0.33	40.6
PE-6	AFAR6	56	14	14	16	0	47°C	0.35	40.4
PE-7	AFAR7	28	28	28	16	0	12°C	0.37	40.1
PE-8	AFAR8	0	42	42	16	0	-16°C	0.38	39.9
PE-9	AFAR9	14	14	56	16	0	-21°C	0.39	39.8

15

Preparative Examples 10 (PE-10): Amide-Functional Acrylic Resin ("AMDA")

The general procedure for preparation of PE-1 was repeated, but replacing amino-functional monomer with amide-functional monomer, N-vinylcaprolactam (NVC), and using the monomer weight ratios, according to the amounts indicated in Table 3.

5

TABLE 3

Preparative Example	IOA, phr	NVC, phr	AA, phr	Inherent viscosity	Wt.% solids
PE-10 (AMDA)	78	21	1	0.58	37.5

Example 1 Primer Composition: (50:24:24:2 KRATON FG1901/ATBC/PE-1/A186 in solvent solution)

A 5-liter flask equipped with overhead stirring, thermocouple, condenser, and nitrogen inlet was charged with 100.0 grams KRATON FG1901, 3.0 grams TINOPAL OB, 48.0 grams ATBC, and 4.0 grams A186. Stirring was started, 567 grams of MCH was added, and the mixture was heated 3 hours at 60°C to ensure homogeneous solution. The solution was diluted with an additional 953 grams MCH, cooled to ambient temperature, then sequentially diluted with 1448 grams of methyl acetate, 120 grams of the AFAR of PE-1, and 760 grams HMDS. The final solution was found to have 4.7 wt.% solids.

15 Example 1 Primer Composition was applied to various substrates and performance of the dried coatings were assessed according to the Primer Component Adhesion Performance test method. Peel forces and failure modes were as recorded in Table 4.

TABLE 4

Substrate	Example 1 primer composition peel force test results	
	piw (N/cm)	failure mode
stainless steel	46 (80)	fs
acrylic	46 (80)	fs
polycarbonate	46 (80)	fs
ABS	46 (80)	fs
Nylon	47 (82)	mix
Rigid PVC	46 (80)	fs
Polyester FRP	43 (75)	mix
Epoxy FRP	46 (80)	fs
phenolic	46 (80)	fs
TPO	45 (78)	fs
polypropylene	27 (47)	mix

white truck paint	36 (63)	cp
-------------------	---------	----

piw: pounds force per inch width

N/cm: Newtons/cm

mode: fs = foam split

mix = mixed mode

cp = clean peel

5

### Examples 2-5

Example 1 was repeated, preserving the 50/24/24/2 KRATON FG1901/AFAR/ATBC/A186 ratio, but replacing AFAR1 with AFAR2, omitting TINOPAL OB, and varying concentration of total solids as shown 10 in Table 5. The peel force test results were as shown in Table 5.

TABLE 5

Substrate	Example 2		Example 3		Example 4		Example 5	
	3 wt.% solids		4 wt.% solids		5 wt.% solids		6 wt.% solids	
	piw (N/cm)	mode	piw (N/cm)	mode	piw (N/cm)	mode	piw (N/cm)	mode
Nylon	32 (56)	cp	32 (56)	cp	34 (59)	cp	34 (59)	cp
polypropylene	32 (56)	mix	36 (63)	mix	19 (33)	mix	28 (49)	mix
white truck paint	28 (49)	cp	32 (56)	cp	33 (57)	cp	31 (54)	cp

### Examples 6-7 and Comparative Example 1

15 Example 3 was repeated, except replacing AFAR2 with AMDA, AFAR3, AFAR4, or a mixture thereof, and adjusting the non-volatile ingredient ratio as shown in Table 6. The peel force test results were as shown in Table 6.

TABLE 6

Example	Non-volatiles, weight ratio	polypropylene		phenolic	
		piw (N/cm)	mode	piw (N/cm)	mode
Example 6	50/7/15/26/2 KRATON FG1901/AMDA/AFAR3/ATBC/A186	35 (61)	fs	35 (61)	fs
Example 7	50/7/15/26/2 KRATON FG1901/AMDA/AFAR4/ATBC/A186	35 (61)	fs	35 (61)	fs

Comparative 1	50/20/28/2 KRATON FG1901/AMDA/ATBC/A186	18 (31)	cp	19 (33)	cp
---------------	--	---------	----	---------	----

Examples 8-16 and Comparative Examples 2-3

Example 4 was repeated, except replacing ATBC with alternative plasticizer, or omitting plasticizer, with peel force test results as shown in Table 7.

5

TABLE 7

Example	Plasticizer	Nylon		polypropylene		white truck paint	
		piw (N/cm)	mode	piw (N/cm)	mode	piw (N/cm)	mode
Example 8	isopropyl myristate	38 (66)	mix	40 (70)	fs	32 (56)	cp
Example 9	dibutyl adipate	36 (63)	cp	43 (75)	fs	30 (52)	cp
Example 10	phenoxypropanol	32 (56)	cp	31 (54)	mix	38 (66)	cp
Example 11	isodecyl benzoate	32 (56)	cp	26 (45)	cp	37 (64)	mix
Example 12	dipropylene glycol dibenzoate	42 (73)	mix	21 (36)	cp	39 (68)	mix
Example 13	diethylene glycol dibenzoate / dipropylene glycol dibenzoate	32 (56)	cp	32 (56)	mix	38 (66)	mix
Example 14	2,2,4-trimethylpentyl dibenzoate	41 (71)	cp	19 (33)	cp	40 (70)	mix
Example 15	triethylene glycol diethylhexanoate	32 (56)	cp	21 (36)	cp	31 (54)	cp
Example 16	diethylhexyl terephthalate	32 (56)	cp	32 (56)	cp	29 (50)	cp
Comparative 2	none	42 (73)	mix	14 (24)	cp	26 (45)	cp
Comparative 3	2-octyldodecanol	31 (54)	cp	16 (28)	cp	30 (52)	cp

Examples 17-24 and Comparative Examples 4-9

Example 3 was repeated, all at 4 wt.% solids, but replacing AFAR2 with AFAR3 and varying KRATON FG1901/AFAR3/ATBC weight ratio, with peel force test results as shown in Table 8.

5

TABLE 8

Example	Non-volatiles, weight ratio KRATON FG1901/AFAR3/ATBC	Nylon		polypropylene		white truck paint	
		piw (N/cm)	mode	piw (N/cm)	mode	piw (N/cm)	mode
Example 17	48/32/20	36.8 (64)	mix	37.5 (65)	mix	39.5 (69)	mix
Example 18	40/24/36	33.3 (58)	mix	39 (68)	mix	28.7 (50)	cp
Example 19	64/24/12	29.4 (51)	cp	25.1 (44)	cp	24.9 (43)	cp
Example 20	64/10/26	25.6 (44)	cp	24.7 (43)	mix	22.1 (38)	cp
Example 21	48/24/28	31.6 (55)	cp	36 (63)	mix	26.3 (46)	cp
Example 22	40/32/28	29.5 (51)	cp	27.6 (48)	mix	28.1 (49)	cp
Example 23	48/16/36	29.2 (51)	cp	24 (42)	cp	23.7 (41)	cp
Example 24	5624/20	32.8 (57)	cp	29.1 (51)	mix	24.4 (42)	cp
Comparative 4	32/40/28	25.6 (44)	cp	10.8 (18)	cp	20.2 (35)	cp
Comparative 5	5517/28	35.8 (62)	mix	16.4 (28)	cp	28.7 (50)	cp
Comparative 6	40/48/12	24.8 (43)	cp	13.9 (24)	cp	18.4 (32)	cp
Comparative 7	55/40/5	28.1 (49)	cp	18.5 (32)	cp	16.9 (29)	cp
Comparative 8	32/24/44	33.1 (58)	cp	16.5 (28)	cp	16.7 (29)	cp

Comparative 9	48/10/42	28.2 (49)	cp	18.4 (32)	mix	25.3 (44)	cp
---------------	----------	--------------	----	--------------	-----	--------------	----

Example 25

Example 4 was repeated, except replacing the 40/40/20 MCH/MAC/HMDS solvent blend with the solvent blend indicated in Table 9.

5

TABLE 9

Example	Solvent Blend Weight Ratio			Nylon		polypropylene		white truck paint	
	MCH	MAC	HMDS	piw (N/cm)	mode	piw (N/cm)	mode	piw (N/cm)	mode
Example 25	30	40	30	32 (56)	cp	28 (49)	cp	30 (52)	cp

Examples 26-27

Example 1 was repeated, except replacing the 40/40/20 MCH/MAC/HMDS solvent blend with the solvent blend indicated in Table 10.

TABLE 10

Example	Solvent Blend Weight Ratio				polycarbonate		TPO		polypropylene	
	MCH	MAC	heptane	tBAC	piw (N/cm)	mode	piw (N/cm)	mode	piw (N/cm)	mode
Example 26	0	40	60	0	41 (71)	fs	41 (71)	fs	42 (73)	fs
Example 27	0	40	40	20	41 (71)	fs	42 (73)	fs	18 (31)	cp

Examples 28-30 and Comparative Example 10-11

Example 3 was repeated, except replacing AFAR2 as shown in Table 11.

TABLE 11

Example	AFAR	AFAR Calculated Tg	Nylon		polypropylene		white truck paint	
			piw (N/cm)	mode	piw (N/cm)	mode	piw (N/cm)	mode
Example 28	AFAR5	55°C	38 (66)	fs	30 (52)	mix	31 (54)	cp

Example 29	AFAR6	47°C	36 (63)	fs	40 (70)	mix	30 (52)	cp
Example 30	AFAR7	12°C	31 (54)	cp	29 (50)	mix	24 (42)	cp
Comparative 10	AFAR8	-16°C	23 (40)	cp	20 (35)	mix	17 (29)	cp
Comparative 11	AFAR9	-21°C	23 (40)	cp	7 (12)	cp	15 (26)	cp

Examples 31-32 and Comparative Example 12

Example 3 was repeated, except varying ATBC as shown in Table 12.

5

TABLE 12

Example	Non-volatiles, weight ratio KRATON FG1901/AFAR2/ATBC/A186	Nylon		polypropylene		white truck paint	
		piw (N/cm)	mode	piw (N/cm)	mode	piw (N/cm)	mode
Example 31	50/24/24/2	37 (64)	cp	38 (66)	fs	27 (47)	cp
Example 32	58/28/12/2	40 (70)	mix	25 (43)	cp	29 (50)	cp
Comparative 12	66/32/ 0 /2	39 (68)	mix	16 (28)	mix	22 (38)	cp


## Claims:

1. A primer composition comprising a primer component comprising:

- a rubber;
- an amine-functional (meth)acrylic resin; and
- 5 a plasticizer.


2. The primer composition of claim 1, wherein the amine-functional (meth)acrylic resin is a polymerization reaction product of an amine-functional (meth)acryloyl compound and a non-amine-vinyl monomer;

10 wherein the amine-functional (meth)acryloyl compound is of Formula (I) :



wherein R1 is hydrogen, alkyl, or aralkyl; R2 is alkyl or aralkyl; or R1 and R2 together with the nitrogen atom with which they are joined may form a 5, 6, or 7 member ring; R3 is alkylene or aralkylene; X is nitrogen or oxygen; R4 does not exist if X is oxygen and is hydrogen, alkyl, aryl, alkaryl, or aralkyl if X is nitrogen; and R5 is hydrogen or methyl;

15 wherein the amine-functional (meth)acryloyl compound is of Formula (II):




20 wherein R1 is hydrogen, alkyl, or aralkyl; each R3 is independently alkylene or aralkylene; X is nitrogen; and R5 is hydrogen or methyl; or combinations thereof.

25 3. The primer composition of claim 1 or 2, wherein the amine-functional (meth)acrylic resin has a calculated Tg greater than or equal to 12°C.

4. The primer composition of claim 2, wherein the non-amine-vinyl monomer is selected from the group consisting of a (meth)acrylic acid, a (meth)acrylic acid ester, a (meth)acrylamide, a vinyl ester, a styrene, a (meth)acrylonitrile, and mixtures thereof.

5. The primer composition of claims 2 or 4, wherein the non-amine-vinyl monomer is a (meth)acrylic acid ester of a C1 to C18 alcohol.
6. The primer composition of any of the preceding claims, wherein the rubber comprises a block copolymer of a styrene and an alkene.
- 5
7. The primer composition of any of the preceding claims, wherein the rubber comprises a styrene-ethylene/butylene-styrene block copolymer grafted with maleic anhydride.
- 10 8. The primer composition of any of the preceding claims, wherein the plasticizer is of Formula III:



wherein:

- each R may be hydrogen, C1-C14 alkyl, aryl, alkaryl, or aralkyl;
- 15 each optionally interrupted by oxygen, nitrogen, carbonyl, carboxyl, or carbamide;
- each X may be oxygen, nitrogen, carbonyl, carboxyl, or carbamide;
- Z may be a hydrogen, C1-C14 alkyl, aryl, alkaryl, aralkyl, C1-C14 alkylene, arylene, alkarylene, aralkylene; each optionally interrupted by oxygen, nitrogen, carbonyl, carboxyl, or carbamide; and
- 20 n is an integer of 1 to 5.

9. The primer composition of claim 8, wherein n is an integer of 1 to 4.
10. The primer composition of any of the preceding claims, wherein the plasticizer is selected from at least one of the following a benzoic acid ester, a myristic acid ester, a citric acid ester, an acetic acid ester, a succinic acid ester, a gluratic acid ester, an adipic acid ester, a sebacic acid ester, and combinations thereof.
- 25
11. The primer composition of any claims 1 to 9, wherein the plasticizer is selected from at least one of the following a benzoic acid ester, a myristic acid ester, a citric acid ester, and combinations thereof.
- 30
12. The primer composition of any of the preceding claims, wherein the primer component comprises:
  - 35 wt.% to 70 wt.% of the rubber;
  - 20 wt.% to 35 wt.% of the amine-functional (meth)acrylic resin; and
  - 35
  - 10 wt.% to 40 wt.% of the plasticizer,
- wherein the weight percentages are all based on the total weight of the primer component.

13. The primer composition of any of claims 1 to 11 wherein the primer component comprises:

40 wt.% to 60 wt.% of the rubber;

20 wt.% to 35 wt.% of the amine-functional (meth)acrylic resin; and

15 wt.% to 35 wt.% of the plasticizer,

5 wherein the weight percentages are all based on the total weight of the primer component.

14. The primer composition of any of the preceding claims further comprising a liquid carrier.

15. The primer composition of claim 14 wherein the liquid carrier is one or more solvent.

10

16. The primer composition of claim 15, wherein the primer composition comprises:

1 wt.% to 25 wt.% of the primer component; and

75 wt.% to 99 wt.% of the solvent,

wherein the weight percentages are all based on the total weight of the primer composition.

15

17. The primer of claim 15, wherein the primer composition comprises:

2 wt.% to 7 wt.% of the primer component; and

93 wt.% to 98 wt.% of the solvent,

wherein the weight percentages are all based on the total weight of the primer composition.

20

# INTERNATIONAL SEARCH REPORT

International application No  
PCT/US2016/065090

<b>A. CLASSIFICATION OF SUBJECT MATTER</b>				
INV.	C09J153/02	C09J133/08	C09J133/10	C09J133/14
	C09D133/08	C09D133/10	C09D133/14	C09D5/00

**ADD.**

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

C09J C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data, CHEM ABS Data

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 360 152 A2 (HENKEL KGAA [DE]) 28 March 1990 (1990-03-28) page 8 - page 10; claims 1-19 ----- A EP 0 341 578 A2 (HENKEL KGAA [DE]) 15 November 1989 (1989-11-15) page 6; claims 1-6 page 4, line 83 - line 93; example 24 ----- A GB 1 053 791 A (IMPERIAL CHEMISTRY LIMITED) 4 January 1967 (1967-01-04) page 6 - page 7; claims 1-13 -----	1-17 1-17 1-17



Further documents are listed in the continuation of Box C.



See patent family annex.

\* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier application or patent but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

Date of mailing of the international search report

1 March 2017

10/03/2017

Name and mailing address of the ISA/  
European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040,  
Fax: (+31-70) 340-3016

Authorized officer

Jung, Andreas

**INTERNATIONAL SEARCH REPORT**

Information on patent family members

International application No

PCT/US2016/065090

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
EP 0360152	A2 28-03-1990	DE	3832262 A1	29-03-1990
		DK	463489 A	23-03-1990
		EP	0360152 A2	28-03-1990
		FI	894475 A	23-03-1990
		NO	893755 A	23-03-1990
		PT	91760 A	30-03-1990
<hr/>				
EP 0341578	A2 15-11-1989	BR	8902192 A	02-01-1990
		DE	3816103 A1	23-11-1989
		EP	0341578 A2	15-11-1989
		JP	H0218500 A	22-01-1990
		TR	24626 A	24-12-1991
		US	4946471 A	07-08-1990
<hr/>				
GB 1053791	A 04-01-1967	NONE		
<hr/>				