



(86) Date de dépôt PCT/PCT Filing Date: 2016/09/16
(87) Date publication PCT/PCT Publication Date: 2017/03/23
(45) Date de délivrance/Issue Date: 2023/06/27
(85) Entrée phase nationale/National Entry: 2018/02/12
(86) N° demande PCT/PCT Application No.: IB 2016/055532
(87) N° publication PCT/PCT Publication No.: 2017/046755
(30) Priorité/Priority: 2015/09/17 (SE1551194-2)

(51) Cl.Int./Int.Cl. D21H 11/18(2006.01),
B29D 7/01(2006.01), B65D 65/46(2006.01),
C08J 5/18(2006.01), D21H 21/20(2006.01)

(72) Inventeurs/Inventors:
HEISKANEN, ISTO, FI;
BACKFOLK, KAJ, FI;
SAUKKONEN, ESA, FI;
RUOHONIEMI, NINA, FI;
LYYTIKAINEN, KATJA, FI

(73) Propriétaire/Owner:
STORA ENSO OYJ, FI

(74) Agent: SMART & BIGGAR LP

(54) Titre : PROCEDE DE PRODUCTION DE FILM AYANT DE BONNES PROPRIETES DE BARRIERE

(54) Title: A METHOD FOR PRODUCING A FILM HAVING GOOD BARRIER PROPERTIES

(57) Abrégé/Abstract:

The present invention relates to a method for manufacturing a film having an oxygen transmission rate in the range of from 1 cc/m²/24h to 500 cc/m²/24h according to ASTM D-3985, at a relative humidity of more than 50 % at 25°C, or higher than 75% at 25°C, or higher than 85% at 25°C, wherein the method comprises the steps of: providing a first suspension comprising a microfibrillated cellulose, wherein the dry content of the suspension is in the range of from 0.1 to 10% by weight, adding a wet strength additive to said first suspension, at an amount of from 0.1 to 10 weight-% based on the amount of microfibrillated cellulose (dry/dry), thereby forming a mixture of the microfibrillated cellulose and the wet strength additive, applying said mixture to a substrate to form a fibrous web and drying said web to form said film. The present invention also relates to a film produced according to the method.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(10) International Publication Number

WO 2017/046755 A1

(43) International Publication Date
23 March 2017 (23.03.2017)

(51) International Patent Classification:

D21H 11/18 (2006.01) *C08J 5/18* (2006.01)
B29D 7/01 (2006.01) *D21H 21/20* (2006.01)
B65D 65/46 (2006.01)

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(21) International Application Number:

PCT/IB2016/055532

(22) International Filing Date:

16 September 2016 (16.09.2016)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

1551194-2 17 September 2015 (17.09.2015) SE

(71) Applicant: STORA ENSO OYJ [FI/FI]; P.O 309, 00101 Helsinki (FI).

(72) Inventors: HEISKANEN, Isto; Kanava-aukio 10 as 13-14, 55100 Imatra (FI). BACKFOLK, Kaj; Valto Käkelän Katu 5 As 3, 53130 Lappeenranta (FI). SAUKKONEN, Esa; Poronkatu 17 B2, 53850 Lappeenranta (FI). RUOHONIEMI, Nina; Ahovuokonkuja 2, 55100 Imatra (FI). LYYTIKÄINEN, Katja; Ratavallinkaari 2, 55700 Imatra (FI).

(74) Agent: LINNÉ, Nina; Stora Enso AB, Group IP, P.O Box 9090, 65009 Karlstad (SE).

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))



WO 2017/046755 A1

(54) Title: A METHOD FOR PRODUCING A FILM HAVING GOOD BARRIER PROPERTIES

(57) Abstract: The present invention relates to a method for manufacturing a film having an oxygen transmission rate in the range of from 1 cc/m²/24h to 500 cc/m²/24h according to ASTM D-3985, at a relative humidity of more than 50 % at 25°C, or higher than 75% at 25°C, or higher than 85% at 25°C, wherein the method comprises the steps of: providing a first suspension comprising a microfibrillated cellulose, wherein the dry content of the suspension is in the range of from 0.1 to 10% by weight, adding a wet strength additive to said first suspension, at an amount of from 0.1 to 10 weight-% based on the amount of microfibrillated cellulose (dry/dry), thereby forming a mixture of the microfibrillated cellulose and the wet strength additive, applying said mixture to a substrate to form a fibrous web and drying said web to form said film. The present invention also relates to a film produced according to the method.

**A METHOD FOR PRODUCING A FILM HAVING GOOD BARRIER
PROPERTIES**

Technical field

The present document relates to a barrier film having a good and stable oxygen transmission rate (OTR) at high relative humidity's (RH). More particularly, the present
5 disclosure relates to a method of manufacturing such a film.

Background

Today, films comprising microfibrillated cellulose (MFC), have proven to give excellent barrier properties (see e.g. Aulin et al., Oxygen and oil barrier properties of
10 microfibrillated cellulose films and coatings, *Cellulose* (2010) 17:559-574, Lavoine et al., Microfibrillated cellulose – Its barrier properties and applications in cellulosic materials: A review, *Carbohydrate polymers* 90 (2012) 735-764, Kumar et al., Comparison of nano- and microfibrillated cellulose films, *Cellulose* (2014) 21:3443-3456), whereas the gas barrier properties are very dependent on the moisture or the relative humidity in the
15 surrounding environment. Therefore, it is quite common that MFC films have to be coated with a polymer film to prevent moisture or water vapor to swell and disrupt the MFC film.

The lack of gas barrier properties such as oxygen or air, at high relative humidity has been investigated and described although most of these solutions are expensive
20 and difficult to implement in industrial environment. One route is to modify the MFC or nanocellulose such as disclosed in EP2554589A1 where MFC dispersion was modified with silane coupling agent. The EP2551104A1 teaches the use of MFC and polyvinyl alcohol (PVOH) and/or polyuronic acid with improved barrier properties at higher relative humidity (RH). Another solution is to coat the film with a film that has high water
25 fastness and/or low water vapor transmission rate. The JP2000303386A discloses e.g. latex coated on MFC film, while US2012094047A teaches the use of wood hydrolysates mixed with polysaccharides such as MFC that can be coated with a polyolefin layer. In addition to this chemical modification, the possibility of cross-linking fibrils or fibrils and copolymers has been investigated. This improves water fastness of the films but also
30 water vapor transmission rates. EP2371892A1, EP2371893A1, claims cross-linking MFC with metal ions, glyoxal, glutaraldehyde and/or citric acid, respectively.

However, many of the above solutions require either a post-treatment step or high dosages in order to be effective. Many of the disclosed solutions also limit the production of a MFC film and particularly re-pulping of the same.

There is thus a need to find a simpler solution of producing such films, preferably 5 something that could be used on a paper or paperboard machine, or modified versions thereof, where a subsequent coating or impregnation step can be avoided, since the number of coating stations usually is limited on a paper machine.

Summary

10 It is an object of the present disclosure, to provide an improved film comprising microfibrillated cellulose, which has improved barrier properties even at higher relative humidity in the surroundings.

According to a first aspect, there is provided a method for manufacturing a film having an oxygen transmission rate in the range of from 1 cc/m²/24h to 15 500 cc/m²/24h, at a relative humidity of more than 50 % at 25°C, or higher than 75% at 25°C, or higher than 85% at 25°C, wherein the method comprises the steps of: providing a first suspension comprising a microfibrillated cellulose, wherein the dry content of the suspension is in the range of from 0.1 to 10% by weight, adding a wet strength additive to said first suspension, at an amount of from 0.1 to 10 weight-% based on the amount 20 microfibrillated cellulose (dry/dry), thereby forming a mixture of the microfibrillated cellulose and the wet strength additive and applying said mixture to a substrate to form a fibrous web and drying said web to form said film.

It has surprisingly been found that it is possible to add wet strength additive in a relative low amount when making barrier films to achieve a stable oxygen transmission 25 rate of the film even at high relative humidity values. Conventionally a wet strength additive is used in a paper just to increase the wet strength. This method provides for the manufacture of a film having a good oxygen transmission rate (OTR) at a high relative humidity level. Most important, the additive will not affect the ability of the

microfibrillated cellulose film to create low OTR values, i.e. being a good barrier film.

According to one embodiment the substrate to which the mixture is applied may be a porous wire on which the mixture forms a web. It is thus

5 possible to apply the method in the wet end of a paper machine.

Through this method a freestanding film can be manufactured by applying a suspension comprising MFC and wet strength additive in the wet end of a paper making machine. In this way a film having excellent barrier properties may be formed. The film may subsequently be applied as a barrier

10 layer on a paper or paper board.

According to one embodiment the substrate to which the mixture is applied may also be a paper or paper board in a paper making process, thus forming a film coating on said paper or paper board.

By this method it is possible to directly apply the mixture to a paper or

15 paperboard to achieve the barrier film on a paper or paper board in an easy manner.

According to one alternative embodiment the method may further comprise the step of applying said mixture to the substrate in a surface sizing step in a paper or paperboard making process.

20 The method may, according to one embodiment, further comprise a step of curing the formed film. The curing, i.e. drying, may be performed by heat, air, radiation or contact drying etc.

According to one embodiment the method may comprise the step of co-mixing and fibrillating said microfibrillated cellulose in the presence of said

25 wet strength resin. This may provide for even better barrier properties of the film.

According to one embodiment of the first aspect the microfibrillated cellulose may have a Schopper Riegler value (SR°) of more than 90 SR°, or more than 93 SR°, or more than 95 SR°.

30 The wet strength additive may be a wet strength resin, and may comprise any one of polyaminopolyamide-epichlorohydrin (PAE), melamine resins, urea formaldehyde resins, polyethylenepolyamino ammonia epichlorohydrin (PAE or PPE), polyethyleneimine, chitosan, maleic anhydride-acylated chitosan (MAAC), dialdehyde starch (DAS), or combinations and

35 mixtures thereof.

Preferably the wet strength additive or resin is such that it provides a long term wet strength.

According to one embodiment of the first aspect the first suspension may further comprise any one of a starch, carboxymethyl cellulose, a filler, retention chemicals, flocculation additives, deflocculating additives, dry strength additives, softeners, or mixtures thereof.

5 According to a second aspect there is provided a film obtained by the method as described herein which film comprises microfibrillated cellulose and a wet strength agent, wherein the film has an oxygen transmission rate in the range of from 1 cc/m²/24h to 500 cc/m²/24h measured according to the standard ASTM D-3985, at a relative humidity of more than 50 % at 25°C, and wherein the film comprises a mixture
10 of a microfibrillated cellulose and a wet strength resin.

According to one embodiment of the second aspect the film may have a basis weight of less than 50 g/m², or less than 35 g/m², or less than 25 g/m².

The film may be any one of a free-standing film and a film coating on a paper or paper board.

15 According to another aspect, there is provided a method for manufacturing a film having an oxygen transmission rate in the range of from 1 cc/m²/24h to 500 cc/m²/24h according to ASTM D-3985, at a relative humidity of more than 50 % at 25°C, or higher than 75% at 25°C, or higher than 85% at 25°C, wherein the method comprises:
20 providing a first suspension comprising a microfibrillated cellulose in an amount of 60 to 99.9 weight-% based on total dry solid content, wherein the dry content of the suspension is in the range of from 0.1 to 10% by weight, adding a wet strength additive to the first suspension, at an amount of from 0.1 to 10 weight-% based on the amount of microfibrillated cellulose (dry/dry), thereby forming a mixture of the microfibrillated cellulose and the wet strength additive, co-mixing and fibrillating the mixture of the
25 microfibrillated cellulose and the wet strength additive, applying the mixture to a substrate to form a fibrous web, and drying the web to form the film.

Description of Embodiments

According to the inventive method a first suspension comprising a microfibrillated
30 cellulose is provided and mixed with a wet strength additive to form mixture comprising the microfibrillated cellulose and the wet strength additive.

The mixture may then be applied onto a substrate to form a fibrous web.

The support may be a porous wire of a paper making machine, i.e. any kind of paper making machine known to a person skilled in the art used for making paper,
35 paperboard, tissue or any similar products.

According to one alternative embodiment the mixture of the microfibrillated cellulose and the wet strength additive may be applied as a coating to a paper or paper

board in a paper making process. The mixture thereby forms a film coating on said paper or paper board, having the desired barrier properties.

According to another embodiment the mixture may be applied to the substrate in a surface sizing step in a paper or paperboard making process. The mixture may be
5 applied as a conventional surface sizing liquid or as a foam. By surface sizing is meant conventional contact coating methods used in paper and paperboard industry. Those are e.g. film press, surface sizing

(pound or flooded nip size press), gate roll, Gate roll Inverted coater, Twin HSM applicator, Liquid application system, blade/roll metering with the Bill blade, TwoStream, Blade/Blade metering with the mirrorBlade, VACPLY, or application and metering with a nozzle unit onto paper web (Chapt. 14,

- 5 5 Coating and surface sizing technologies, Linnonmaa, J., and Trefz, M., in Pigment coating and surface sizing of paper, Papermaking Science and Technology, Book 11, 2nd Ed., 2009). In addition, reverse gravure or gravure methods, sizing based on indirect metering onto roll using e.g. spray, spinning or foam deposition may also be included in this definition. Other variations
- 10 10 and modifications or combinations of the coating methods, obvious for a person skilled in the art, are also included herein.

According to one embodiment this web can then subsequently be dried to form a film.

- 15 15 According to one embodiment the film, comprising the microfibrillated cellulose and a wet strength additive, has an oxygen transmission rate in the range of from 1 cc/m²/24h to 500 cc/m²/24h measured according to the standard ASTM D-3985, at a relative humidity of more than 50 % at 25°C.
- 20 20 According to one alterative embodiment the film, comprising the microfibrillated cellulose and a wet strength additive, has an oxygen transmission rate in the range of from 1 cc/m²/24h to 500 cc/m²/24h measured according to ASTM D-3985, at a relative humidity of more than 75 % at 25°C. According to yet an alternative embodiment the film, comprising the microfibrillated cellulose and a wet strength additive, has an oxygen transmission rate in the range of from 1 cc/m²/24h to 500 cc/m²/24h
- 25 25 measured according to ASTM D-3985, at a relative humidity of more than 85 % at 25°C.

The amount of microfibrillated cellulose in the first suspension and in the produced film may, according to one embodiment be in the range of from 60 to 99.9 weight-% based on total dry solid content. According to an

- 30 30 alternative embodiment the amount of MFC may be in the range of 70 to 95 weight- % based on total dry solid content, or in the range of from 75 to 90 weight-% based on total dry solid content.

According to one embodiment the film may have a basis weight of less than 50 g/m², or less than 35 g/m², or less than 25 g/m².

- 35 35 According to one embodiment the film formed may be calendered. The final density, film properties and moisture content may thus be adjusted in the

calender. Known techniques such as hard-nip, soft-nip, soft-hard nip, cylinder or belt, in various forms and combinations can be used.

According to one embodiment the film may be cured, i.e. dried. The curing may be performed by any conventional technique known to the skilled

5 person, such as by heat, air, radiation or contact drying etc.

According to one embodiment the MFC may have a Schopper Riegler value (SR°) of more than 90. According to another embodiment the MFC may have a Schopper Riegler value (SR°) of more than 93. According to yet another embodiment the MFC may have a Schopper Riegler value (SR°) of

10 more than 95. The Schopper-Riegler value can be obtained through the standard method defined in EN ISO 5267-1. This high SR value is determined for a repulped wet web, with or without additional chemicals, thus the fibers have not consolidated into a film or started e.g. hornification.

The dry solid content of this kind of web, before disintegrated and 15 measuring SR, is less than 50 % (w/w). To determine the Schopper Riegler value it is preferable to take a sample just after the wire section where the wet web consistency is relatively low.

The skilled person understands that paper making chemicals, such as retention agents or dewatering agents, have an impact on the SR value.

20 The SR value specified herein, is to be understood as an indication but not a limitation, to reflect the characteristics of the MFC material itself. However, the sampling point of MFC might also influence the measured SR value. For example, the furnish could be either a fractionated or unfractionated suspension and these might have different SR values.

25 Therefore, the specified SR values given herein, are thus either a mixture of coarse and fine fractions, or a single fraction comprising an MFC grade providing the desired SR value.

Microfibrillated cellulose (MFC) shall in the context of the patent application mean a nano scale cellulose particle fiber or fibril with at least one 30 dimension less than 100 nm. MFC comprises partly or totally fibrillated cellulose or lignocellulose fibers. The liberated fibrils have a diameter less than 100 nm, whereas the actual fibril diameter or particle size distribution and/or aspect ratio (length/width) depends on the source and the manufacturing methods. The smallest fibril is called elementary fibril and has 35 a diameter of approximately 2-4 nm (see e.g. Chinga-Carrasco, G., *Cellulose fibres, nanofibrils and microfibrils: The morphological sequence of MFC components from a plant physiology and fibre technology point of view*,

Nanoscale research letters 2011, 6:417), while it is common that the aggregated form of the elementary fibrils, also defined as microfibril (*Fengel, D., Ultrastructural behavior of cell wall polysaccharides, Tappi J., March 1970, Vol 53, No. 3.*), is the main product that is obtained when making MFC e.g. by

- 5 using an extended refining process or pressure-drop disintegration process. Depending on the source and the manufacturing process, the length of the fibrils can vary from around 1 to more than 10 micrometers. A coarse MFC grade might contain a substantial fraction of fibrillated fibers, i.e. protruding fibrils from the tracheid (cellulose fiber), and with a certain amount
- 10 of fibrils liberated from the tracheid (cellulose fiber).

There are different acronyms for MFC such as cellulose microfibrils, fibrillated cellulose, nanofibrillated cellulose, fibril aggregates, nanoscale cellulose fibrils, cellulose nanofibers, cellulose nanofibrils, cellulose microfibers, cellulose fibrils, microfibrillar cellulose, microfibril aggregates and

- 15 cellulose microfibril aggregates. MFC can also be characterized by various physical or physical-chemical properties such as large surface area or its ability to form a gel-like material at low solids (1-5 wt%) when dispersed in water. The cellulose fiber is preferably fibrillated to such an extent that the final specific surface area of the formed MFC is from about 1 to about 200
- 20 m²/g, or more preferably 50-200 m²/g when determined for a freeze-dried material with the BET method.

Various methods exist to make MFC, such as single or multiple pass refining, pre-hydrolysis followed by refining or high shear disintegration or liberation of fibrils. One or several pre-treatment step is usually required in

- 25 order to make MFC manufacturing both energy efficient and sustainable. The cellulose fibers of the pulp to be supplied may thus be pre-treated enzymatically or chemically, for example to hydrolyse or swell fiber or reduce the quantity of hemicellulose or lignin. The cellulose fibers may be chemically modified before fibrillation, wherein the cellulose molecules contain functional
- 30 groups other (or more) than found in the original cellulose. Such groups include, among others, carboxymethyl (CMC), aldehyde and/or carboxyl groups (cellulose obtained by N-oxyl mediated oxydation, for example "TEMPO"), or quaternary ammonium (cationic cellulose). After being modified or oxidized in one of the above-described methods, it is easier to disintegrate
- 35 the fibers into MFC or nanofibrillar size or NFC.

The nanofibrillar cellulose may contain some hemicelluloses; the amount is dependent on the plant source. Mechanical disintegration of the

pre-treated fibers, e.g. hydrolysed, pre-swelled, or oxidized cellulose raw material is carried out with suitable equipment such as a refiner, grinder, homogenizer, colloider, friction grinder, ultrasound sonicator, fluidizer such as microfluidizer, macrofluidizer or fluidizer-type homogenizer. Depending on the

- 5 MFC manufacturing method, the product might also contain fines, or nanocrystalline cellulose or e.g. other chemicals present in wood fibers or in papermaking process. The product might also contain various amounts of micron size fiber particles that have not been efficiently fibrillated.
- 10 MFC is produced from wood cellulose fibers, both from hardwood or softwood fibers. It can also be made from microbial sources, agricultural fibers such as wheat straw pulp, bamboo, bagasse, or other non-wood fiber sources. It is preferably made from pulp including pulp from virgin fiber, e.g. mechanical, chemical and/or thermomechanical pulps. It can also be made from broke or recycled paper.
- 15 The above described definition of MFC includes, but is not limited to, the new proposed TAPPI standard W13021 on cellulose nanofibril (CNF) defining a cellulose nanofiber material containing multiple elementary fibrils with both crystalline and amorphous regions, having a high aspect ratio with width of 5-30nm and aspect ratio usually greater than 50.

- 20 In one embodiment of the present invention, the microfibrillated cellulose is fibrillated in the presence of the wet strength additive. This means that the wet strength additive is either added before the fibrillation process or during the fibrillation process.

- 25 According to one embodiment the dry content of the first suspension comprising the microfibrillated cellulose may be in the range of from 0.1 to 10 % by weight.

- 30 The wet strength additive may be added to said first suspension, at an amount of from 0.1 to 10 weight-% based on the amount MFC (dry/dry). Too high amount of wet strength agent will increase the OTR value of the produced film.

According to one embodiment the said wet strength additive is a wet strength additive or a wet strength resin which provides for a long term wet strength in the web or film.

- 35 The wet strength resin may be any one of polyaminopolyamide-epichlorohydrin (PAE), melamine resins, urea formaldehyde resins, polyethylenepolyamino ammonia epichlorohydrin (PAE or PPE),

polyethyleneimine, chitosan, maleic anhydride-acylated chitosan (MAAC), dialdehyde starch (DAS), or combinations and mixtures thereof.

The first suspension may further comprise other additives to provide different characteristics to the film. Those additives, may be any one of a

5 starch, carboxymethyl cellulose, a filler, retention chemicals, flocculation additives, deflocculating additives, dry strength additives, softeners, or mixtures thereof, but may also be other types of additives suitable for the particular application of the film.

According to one embodiment the additives are selected such that the
10 film is biodegradable after a certain time.

Example

The Oxygen Transmission Rate (cc/m²/24h) for 20 gsm films prepared
15 from coarse MFC and fine MFC (3 x fluidized) with various amounts of added PAE wet strength resin was measured according to ASTM D-3985.

Table1: Tests with relatively coarse MFC -C (low viscosity, homogenized fibers)

	20	OTR value (50% RH)	OTR value (85 % RH)
MFC-C		190	455
MFC-C + 5 kg/t PAE		5.5	288
MFC-C + 15 kg/t PAE		250	480
25 MFC-C+ 50 kg/t PAE		6988	6919

Table 2: Tests with fine MFC-F (high viscosity, pre-treated fibers 3 x fluidized)

	30	OTR value (85 % RH)
MFC-F		1657
MFC-F + 5 kg/t PAE		431
MFC-F + 15 kg/t PAE		1144
MFC-F + 50 kg/t PAE		4046

10

Thus, it is clear from these tests that the addition of low amounts of wet strength agents clearly decreases the OTR value for the MFC film, thus it creates a good oxygen barrier.

5 In view of the above detailed description of the present invention, other modifications and variations will become apparent to those skilled in the art. However, it should be apparent that such other modifications and variations may be effected without departing from the spirit and scope of the invention.

10

CLAIMS:

1. A method for manufacturing a film having an oxygen transmission rate in the range of from 1 cc/m²/24h to 500 cc/m²/24h according to ASTM D-3985, at a relative humidity of more than 50 % at 25°C, or higher than 75% at 25°C, or higher than 85% at 25°C, wherein the method comprises:
 - 5 providing a first suspension comprising a microfibrillated cellulose in an amount of 60 to 99.9 weight-% based on total dry solid content, wherein the dry content of the suspension is in the range of from 0.1 to 10% by weight,
 - 10 adding a wet strength additive to said first suspension, at an amount of from 0.1 to 10 weight-% based on the amount of microfibrillated cellulose (dry/dry), thereby forming a mixture of the microfibrillated cellulose and the wet strength additive, co-mixing and fibrillating said mixture of said microfibrillated cellulose and said wet strength additive,
 - 15 applying said mixture to a substrate to form a fibrous web, and drying said web to form said film.
2. The method according to claim 1, wherein said support is a porous wire in a paper making machine to which the mixture is applied to form the fibrous web.
- 20 3. The method according to claim 1, wherein the support is a paper or paperboard to which the mixture is applied to form a film coating on said paper or paper board.
- 25 4. The method according to any one of claims 1 to 3, wherein the method further comprises applying said mixture to the substrate in a surface sizing step in a paper or paperboard making process.
- 30 5. The method according to any one of claims 1 to 4, wherein the method further comprises a step of curing the formed film.
6. The method according to any one of claims 1 to 5, wherein the microfibrillated cellulose has a Schopper Riegler value (SR°) of more than 90 SR°, or more than 93 SR°, or more than 95 SR°.

7. The method according to any one of claims 1 to 6, wherein said wet strength additive is a wet strength resin, comprising polyaminopolyamide-epichlorohydrin (PAE), melamine resins, a urea formaldehyde resin, polyethylenepolyamino ammonia epichlorohydrin (PAE or PPE), polyethyleneimine, chitosan, maleic anhydride-acylated
- 5 chitosan (MAAC), dialdehyde starch (DAS), or any combination or mixture thereof.

8. The method according to any one of claims 1 to 7, wherein said first suspension further comprises a starch, carboxymethyl cellulose, a filler, a retention chemical, a flocculation additive, a deflocculating additive, a dry strength additive, a
- 10 softener, or any mixture thereof.