



US 20170084454A1

(19) **United States**

(12) **Patent Application Publication**

**Bedell et al.**

(10) **Pub. No.: US 2017/0084454 A1**

(43) **Pub. Date: Mar. 23, 2017**

(54) **UNIFORM HEIGHT TALL FINS WITH VARYING SILICON GERMANIUM CONCENTRATIONS**

*H01L 29/66* (2006.01)  
*H01L 29/161* (2006.01)  
*H01L 29/06* (2006.01)

(71) Applicant: **International Business Machines Corporation**, Armonk, NY (US)

(52) **U.S. Cl.**  
CPC .. *H01L 21/02532* (2013.01); *H01L 21/02658* (2013.01); *H01L 21/02664* (2013.01); *H01L 29/161* (2013.01); *H01L 29/0649* (2013.01); *H01L 29/66795* (2013.01); *H01L 29/785* (2013.01)

(72) Inventors: **Stephen W. Bedell**, Wappingers Falls, NY (US); **Bruce B. Doris**, Slingerlands, NY (US); **Keith E. Fogel**, Hopewell Junction, NY (US); **Alexander Reznicek**, Troy, NY (US)


(21) Appl. No.: **14/856,930**

(22) Filed: **Sep. 17, 2015**

**Publication Classification**

(51) **Int. Cl.**  
*H01L 21/02* (2006.01)  
*H01L 29/78* (2006.01)

(57) **ABSTRACT**  
A method of making a semiconductor device includes forming a first fin in a first semiconducting material layer disposed over a substrate, the first semiconducting material layer comprising an element in a first concentration; and forming a second fin in a second semiconducting material layer disposed over the substrate and adjacent to the first semiconducting material layer, the second semiconducting material layer comprising the element in a second concentration; wherein the first concentration is different than the second concentration.






FIG. 1




FIG. 2




FIG. 3




FIG. 4A




FIG. 4B




FIG. 5




FIG. 6






FIG. 7

## UNIFORM HEIGHT TALL FINS WITH VARYING SILICON GERMANIUM CONCENTRATIONS

### BACKGROUND

**[0001]** The present invention relates to metal-oxide-semiconductor field-effect transistors (MOSFET), and more specifically, to fin-type field-effect transistors (FinFET).

**[0002]** The MOSFET is a transistor used for amplifying or switching electronic signals. The MOSFET has a source, a drain, and a metal oxide gate electrode. The metal gate is electrically insulated from the main semiconductor n-channel or p-channel by a thin layer of insulating material, for example, silicon dioxide or glass, which makes the input resistance of the MOSFET relatively high. The gate voltage controls whether the path from drain to source is an open circuit (“off”) or a resistive path (“on”).

**[0003]** The FinFET is a type of MOSFET. The FinFET is a double-gate silicon-on-insulator (SOI) device that mitigates the effects of short channels and reduces drain-induced barrier lowering. The “fin” refers to the narrow channel between source and drain regions. A thin insulating oxide layer on either side of the fin separates the fin from the gate.

### SUMMARY

**[0004]** According to an embodiment, a method of making a semiconductor device includes forming a first fin in a first semiconducting material layer disposed over a substrate, the first semiconducting material layer including an element in a first concentration; and forming a second fin in a second semiconducting material layer disposed over the substrate and adjacent to the first semiconducting material layer, the second semiconducting material layer including the element in a second concentration; wherein the first concentration is different than the second concentration.

**[0005]** According to another embodiment, a method of making a semiconductor device includes etching trenches in a semiconducting material disposed over a substrate to form a first active area and a second active area in the semiconducting material, the first active area being adjacent to the second active area; recessing the semiconducting material of the first active area and the second active area to different depths; growing a first epitaxial layer over the semiconducting material of the first active area and a second epitaxial layer over the semiconducting material of the second active area, the first epitaxial layer and the second epitaxial layer comprising a common element; performing a thermal mixing process to merge the first epitaxial layer with the semiconducting material of the first active area, distribute the common element of the first epitaxial layer within the semiconducting material of the first active area, and form a first merged active area comprising the first epitaxial layer and the semiconducting material of the first active area; and to merge the second epitaxial layer with the semiconducting material of the second active area, distribute the common element of the second epitaxial layer within the semiconducting material of the second active area, and form a second merged active area comprising the second epitaxial layer and the semiconducting material of the second active area, the first merged active area and the second merged active area comprising the common element in different

concentrations; forming a first fin in the first merged active area; and forming a second fin in the second merged active area.

**[0006]** Yet, according to another embodiment, a semiconductor device includes a first fin disposed over a substrate, the first fin including a semiconductor material including an element in a first concentration; and a second fin disposed over the substrate and adjacent to the first fin, the second fin including a semiconductor material including the element in a second concentration; wherein the first concentration is different than the second concentration.

### BRIEF DESCRIPTION OF THE DRAWINGS

**[0007]** The subject matter which is regarded as the invention is particularly pointed out and distinctly claimed in the claims at the conclusion of the specification. The forgoing and other features, and advantages of the invention are apparent from the following detailed description taken in conjunction with the accompanying drawings in which:

**[0008]** FIGS. 1-7 illustrate an exemplary method of making semiconductor devices according to various embodiments, in which:

**[0009]** FIG. 1 is a cross-sectional side view of a buried oxide (BOX) layer and silicon-on-insulator (SOI) disposed over a substrate;

**[0010]** FIG. 2 is a cross-sectional side view after forming shallow trench isolation (STI) regions within the SOI to form two SOI regions that form active areas;

**[0011]** FIG. 3 is a cross-sectional side view after recessing the two SOI regions to different depths;

**[0012]** FIG. 4A is a cross-sectional side view after growing epitaxial layers over the two SOI regions;

**[0013]** FIG. 4B is a cross-sectional side view after planarizing the epitaxial layers;

**[0014]** FIG. 5 is a cross-sectional side view after disposing a hard mask layer over the epitaxial layers;

**[0015]** FIG. 6 is a cross-sectional side view after thermal mixing to substantially uniformly distribute the epitaxial elements in the active regions; and

**[0016]** FIG. 7 is a cross-sectional side view after forming fins.

### DETAILED DESCRIPTION

**[0017]** As semiconductor device dimensions get smaller, taller fins may be used to improve device current densities. Fins including silicon germanium (SiGe) are also used to improve performance. Some applications, such as system-on-chip (SoC) applications, use fins with different SiGe concentrations.

**[0018]** Multiple threshold ( $V_t$ ) technology, which utilizes transistors with multiple threshold voltages to optimize delay or power, is one technology used in SoC systems. Fully depleted devices, such as FinFET devices, may use work function tuning to achieve different threshold voltages. However, channel doping may not be effective to accomplish the work function tuning, and the current integration scheme used to enable multiple threshold voltages is complex.

**[0019]** Accordingly, various embodiments described herein provide a structure and process to provide multiple  $V_t$  devices having fins of substantially uniform height. The structure and methods described provide at least two transistors with tall, substantially uniform fins with varying

SiGe concentrations. Embodiments of the inventive structure and methods provide multiple transistors, on the same chip, with fins having different threshold voltages. Like reference numerals refer to like elements across different embodiments.

**[0020]** The following definitions and abbreviations are to be used for the interpretation of the claims and the specification. As used herein, the terms “comprises,” “comprising,” “includes,” “including,” “has,” “having,” “contains” or “containing,” or any other variation thereof, are intended to cover a non-exclusive inclusion. For example, a composition, a mixture, process, method, article, or apparatus that comprises a list of elements is not necessarily limited to only those elements but can include other elements not expressly listed or inherent to such composition, mixture, process, method, article, or apparatus.

**[0021]** As used herein, the articles “a” and “an” preceding an element or component are intended to be nonrestrictive regarding the number of instances (i.e. occurrences) of the element or component. Therefore, “a” or “an” should be read to include one or at least one, and the singular word form of the element or component also includes the plural unless the number is obviously meant to be singular.

**[0022]** As used herein, the terms “invention” or “present invention” are non-limiting terms and not intended to refer to any single aspect of the particular invention but encompass all possible aspects as described in the specification and the claims.

**[0023]** As used herein, the term “about” modifying the quantity of an ingredient, component, or reactant of the invention employed refers to variation in the numerical quantity that can occur, for example, through typical measuring and liquid handling procedures used for making concentrates or solutions. Furthermore, variation can occur from inadvertent error in measuring procedures, differences in the manufacture, source, or purity of the ingredients employed to make the compositions or carry out the methods, and the like. In one aspect, the term “about” means within 10% of the reported numerical value. In another aspect, the term “about” means within 5% of the reported numerical value. Yet, in another aspect, the term “about” means within 10, 9, 8, 7, 6, 5, 4, 3, 2, or 1% of the reported numerical value.

**[0024]** Turning now to the Figures, FIGS. 1-7 illustrate an exemplary method of making semiconductor devices according to various embodiments. FIG. 1 is a cross-sectional side view of a buried oxide (BOX) layer **102** and silicon-on-insulator (SOI) **103** disposed over a substrate **101**. The substrate **101**, BOX layer **102**, and SOI **103** form a SOI wafer.

**[0025]** Non-limiting examples of suitable substrate **101** materials include Si (silicon), strained Si, SiC (silicon carbide), Ge (germanium), SiGe (silicon germanium), SiGeC (silicon-germanium-carbon), Si alloys, Ge alloys, GaAs (gallium arsenide), InAs (indium arsenide), InP (indium phosphide), or any combination thereof.

**[0026]** The thickness of the substrate **101** generally varies and is not intended to be limited. In one aspect, the thickness of the substrate **101** is in a range from about 50 micrometers to about 2000 micrometers.

**[0027]** The buried oxide (BOX) layer **102** is disposed over the substrate **101**. The BOX layer **102** is an oxide, for example silicon dioxide, or a nitride, for example, silicon nitride. The thickness of BOX layer **102** generally varies and

is not intended to be limited. In one aspect, the thickness of the BOX layer **102** is in a range from about 10 nm to about 1000 nm.

**[0028]** The SOI **103** is a semiconducting material that includes silicon or silicon germanium. The thickness of the SOI **103** generally varies and is not intended to be limited. In one aspect, the thickness of the SOI **103** is in a range from about 10 nm to about 1000 nm. In another aspect, the thickness of the SOI **103** is in a range from about 30 nm to about 100 nm.

**[0029]** Depending on the type of device, the SOI **103** may include more than one type of material, for example, semiconducting materials. In an exemplary embodiment, the SOI **103** includes silicon for forming an NFET and silicon germanium for forming a PFET. In other exemplary embodiments, the SOI **103** includes one type of material, for example, silicon for forming NFETS or silicon germanium for forming PFETs.

**[0030]** FIG. 2 is a cross-sectional side view after forming shallow trench isolation (STI) regions **201** within the SOI **103** to form two discrete SOI regions, first SOI region **210** and second SOI region **211**. First SOI region **210** forms the active area of a first transistor (first active area). Second SOI region **211** forms the active area of a second transistor (second active area). The first and second transistors may be the same type (e.g., PFET transistors). In other embodiments, the first and second SOI regions **210**, **211** include different semiconducting materials to form different transistors (e.g., an NFET and a PFET). The STI regions **201** will later function as a planarization stop, as shown in FIG. 4B described below.

**[0031]** The STI regions **201** are isolation regions formed by etching trenches in the SOI **103** and then filling the trenches with, for example, silicon dioxide. Other suitable oxide materials may be deposited to form the STI regions **201**. Non-limiting examples of suitable oxide materials for the STI regions **201** include silicon dioxide, tetraethylorthosilicate (TEOS) oxide, high aspect ratio plasma (HARP) oxide, silicon oxide, high temperature oxide (HTO), high density plasma (HDP) oxide, oxides formed by an atomic layer deposition (ALD) process, or any combination thereof.

**[0032]** FIG. 3 is a cross-sectional side view after recessing the first and second SOI regions **210**, **211**. The first and second SOI regions **210**, **211** are recessed by different amounts (different depths) by removing different amounts of the SOI **103**.

**[0033]** The first SOI region **210** is recessed to form a SOI **103** having a thickness **301** (first thickness) in a range from about 4 to about 100 nm. In some embodiments, the first SOI region **210** is recessed to form a SOI **103** having a thickness **301** in a range from about 6 to about 20 nm.

**[0034]** The second SOI region **211** is recessed to form a SOI **103** having a thickness **302** (second thickness) in a range from about 10 to about 100 nm. In some embodiments, the second SOI region **211** is recessed to form a SOI **103** having a thickness **302** in a range from about 8 to about 30 nm.

**[0035]** The first and second SOI regions **210**, **211** are recessed to different depths in active regions of different transistors by disposing a mask (not shown) over the either side (first or second SOI region **210**, **211**) and etching the respective exposed SOI **103** that is uncovered by the mask. For example, a mask may be disposed over the first SOI region **210**, followed by etching of the second SOI region

**211.** In another example, a mask is disposed over the second SOI region **211**, followed by etching the first SOI region **210**. The mask is removed, and the un-etched SOI **103** (first or second SOI region **210**) is covered by another mask (not shown). The respective uncovered SOI **103** is then etched, and the second mask is removed.

**[0036]** The mask may be any suitable resist. Suitable resists include photoresists, electron-beam resists, ion-beam resists, X-ray resists, and etchant resists. The resist may be a polymeric spin on material or a polymeric material. The mask may be removed by, for example, an ashing process.

**[0037]** The etching process employed to recess the SOI **103** may be any suitable reactive ion etching (RIE) process. Non-limiting examples of suitable etching processes include silicon etching methods selective to oxides.

**[0038]** FIG. 4A is a cross-sectional side view after depositing an epitaxial layer **401** over the recessed SOI **103** of the first and second SOI regions **210**, **211** to form first epitaxial layer **410** and second epitaxial layer **411**. First SOI region **210** and second SOI region **410** form a first active region **420** of a first transistor. Second SOI region **211** and second epitaxial layer **411** form a second active region **421** of a second transistor.

**[0039]** The first and second epitaxial layers **410**, **411** make up at least 40 atomic % (at. %) of the first and second active regions **420**, **421**, respectively. In some embodiments, the first and second epitaxial layers **410**, **411** make up from about 40 to about 70 at. % of the first and second active regions **420**, **421**, respectively. In other embodiments, the first and second epitaxial layers **410**, **411** make up from about 40 to about 90 at. % of the first and second active regions **420**, **421**, respectively.

**[0040]** An epitaxial growth process is used to form the epitaxial layers **401** specifically over the SOI **103**. The epitaxial growth process is performed to grow a crystalline layer of silicon germanium onto the crystalline SOI **103** beneath. The underlying silicon of the SOI **103** acts as a seed crystal. Epitaxial layers **401** may be grown from gaseous or liquid precursors. A non-limiting example of a suitable material (element) for the epitaxial layers **401** includes silicon germanium. The silicon germanium may have a germanium content of about 40 to about 70 atomic % (at. %).

**[0041]** The epitaxial layers **401** may be grown using a suitable growth process, for example, chemical vapor deposition (CVD) (liquid phase (LP) or reduced pressure chemical vapor deposition (RPCVD), vapor-phase epitaxy (VPE), molecular-beam epitaxy (MBE), liquid-phase epitaxy (LPE), metal organic chemical vapor deposition (MOCVD), or other suitable processes.

**[0042]** The thickness of the first and second epitaxial regions **410**, **411** is substantially the same because they will be formed concomitantly through the patterned mask. Because the thickness of the SOI **103** in the first and second SOI regions **210**, **211** is different, first and second epitaxial regions **410**, **411** will protrude over the STI regions **201** by different amounts.

**[0043]** FIG. 4B is a cross-sectional side view after planarizing the epitaxial layers **401**. The planarizing process may include, for example, a chemical mechanical planarization (CMP) process.

**[0044]** FIG. 5 is a cross-sectional side view after disposing an optional insulating layer **501** (hard mask layer) over the epitaxial layers **401**. The insulating layer **501** prevents

oxidation of the epitaxial layers **401** during the thermal mixing process (see FIG. 6) by forming a capping layer. The insulating layer **501** also maintains the shape of the surface of the epitaxial layers **401** by preventing surface rearrangement during thermal mixing annealing. The insulating layer should be thick enough to prevent oxygen from penetrating through to the epitaxial layers **401**.

**[0045]** The insulating layer **501** includes a suitable insulating or hard mask material. Non-limiting examples of suitable materials for the insulating layer **501** include silicon nitride, silicon oxide, silicon dioxide, aluminum oxide, or a combination thereof. The insulating layer **501** may be formed using a suitable deposition process, including, but not limited to CVD, PVD, plasma enhanced CVD, atomic layer deposition (ALD), evaporation, chemical solution deposition, or like processes.

**[0046]** The thickness of the insulating layer **501** may generally vary and is not intended to be limited. In some embodiments, the thickness of the insulating layer **501** is in a range from about 20 to about 200 nm. In other embodiments, the thickness of the insulating layer **501** is in a range from about 50 to about 100 nm.

**[0047]** FIG. 6 is a cross-sectional side view after thermal mixing to substantially uniformly distribute elements from the epitaxial layers **401** within first and second active regions **420**, **421**. Thermal mixing combines the composition of the first SOI region **210** with the first epitaxial layer **410** and the composition of the second SOI region **211** with the second epitaxial layer **411** to form merged active areas (first and second merged active areas). Because the first epitaxial layer **410** and the second epitaxial layer **411** have different thicknesses and make up different proportions of the total active regions (first and second active regions **420**, **421**), the resulting final active regions (first active region **601** and second active region **602**) include different elemental concentrations. First active region **601** includes more or less of at least one element (e.g., germanium). The first active region **601** and the second active region **602** include a common element. The common element is present in different concentrations in the first and second active regions **601**, **602**.

**[0048]** Thermal mixing is a thermal diffusion process that is performed at a temperature sufficient enough to cause diffusion of germanium out of the epitaxial layers **401** and into the SOI **103**. In one embodiment, the thermal mixing is performed at a temperature from about 700° C. to about 1300° C. In another embodiment, the thermal mixing is performed at a temperature from about 1000° C. to about 1200° C.

**[0049]** In other embodiments, the thermal mixing is performed in the presence of an inert ambient gas. Non-limiting examples of inert gases include helium (He), argon (Ar), nitrogen (N<sub>2</sub>), xenon (Xe), krypton (Kr), or neon (Ne), or any combination thereof.

**[0050]** The thermal mixing process of the present application may be carried out for a variable period of time. In one example, the thermal mixing process is carried out for a time period from 2 minutes to about 5 hours, depending on thermal mixing temperature. In another embodiment, the thermal mixing process may be carried out for a time period from 5 minutes to about 30 minutes. The thermal mixing process of the present application may be carried out at a single targeted temperature, or various ramp and soak cycles using various ramp rates and soak times can be employed.

[0051] The first active region **601** and second active region **602** include different amounts of at least one element. In one exemplary embodiment, first and second SOI regions **210**, **211** include silicon, and first and second epitaxial layers **410**, **411** include silicon germanium. The first and second active regions **601** include different amounts of germanium. In some embodiments, first active region **601** includes a higher amount of germanium than second active region **602**. In other embodiments, first active region **601** includes germanium in an amount in a range from about 20 at. % to about 60 at. % and silicon in an amount in a range from about 40 at. % to about 80 at. %. Second active region **602** includes germanium in an amount in a range from about 10 atomic percent to about 20 atomic percent and silicon in an amount in a range from about 80 at. % to about 90 at. %.

[0052] FIG. 7 is a cross-sectional side view after forming fins in the first and second active regions **601**, **602**. First fins **701** are formed in the first active region **601**. Second fins **702** are formed in the second active region **602**. The first and second fins **601**, **602** have different elemental concentrations for forming two different transistors.

[0053] In an exemplary embodiment, first and second fins **601**, **602** include different concentrations of silicon germanium. First and second fins **601**, **602** have different threshold voltages.

[0054] When the insulating layer **501** is used, the insulating layer **501** is removed before patterning first and second fins **701**, **702**. The insulating layer is removing by employing an etching process, for example, a wet etching process. Non-limiting examples of suitable methods for etching the insulating layer **501** include processes including aqueous hydrofluoric acid (HF) when the insulating layer **501** is silicon dioxide and hot phosphoric acid when the insulating layer **501** is silicon nitride.

[0055] The STI regions **201** are recessed during fin formation, described below. Etching processes, for example, wet etching processes with aqueous HF, may also be used to recess the STI regions **201**.

[0056] The first and second fins **601**, **602** may be formed in the first and second active regions **601**, **602** by a lithographic patterning and etching process. The first and second fins **601**, **602** have different threshold voltages due to the different elemental concentrations (e.g., different silicon germanium concentrations). In one non-limiting example, a hard mask material (not shown) may be disposed over the first and second active regions **601**, **602**. The first and second fins **601**, **602** are formed by etching material from the first and second active regions **601**, **602** using a suitable etching process such as reactive ion etching (RIE).

[0057] To form fins (first and second fins **601**, **602**) with substantially uniform height, a sidewall image transfer (SIT) process is employed. The height of the first and second fins **601**, **602** generally varies, as it depends on the type of device, and is not intended to be limited. In one aspect, the height of the first and second fins **601**, **602** is in a range from about 20 nm to about 150 nm. In another aspect, the height of the first and second fins **601**, **602** is in a range from about 30 nm to about 80 nm. In some embodiments, the height of the first and second fins **601**, **602** is substantially the same.

[0058] As described above, various embodiments described herein provide a structure and process to provide multiple  $V_t$  devices having fins of uniform height. The structure and methods described provide at least two transistors with tall, substantially uniform fins with varying

elemental (e.g., SiGe) concentrations. Embodiments of the inventive structure and methods provide multiple transistors, on the same chip, with fins having different threshold voltages.

[0059] The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting of the invention. As used herein, the singular forms “a”, “an” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise. It will be further understood that the terms “comprises” and/or “comprising,” when used in this specification, specify the presence of stated features, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, integers, steps, operations, element components, and/or groups thereof.

[0060] The corresponding structures, materials, acts, and equivalents of all means or step plus function elements in the claims below are intended to include any structure, material, or act for performing the function in combination with other claimed elements as specifically claimed. The description of the present invention has been presented for purposes of illustration and description, but is not intended to be exhaustive or limited to the invention in the form disclosed. Many modifications and variations will be apparent to those of ordinary skill in the art without departing from the scope and spirit of the invention. The embodiment was chosen and described in order to best explain the principles of the invention and the practical application, and to enable others of ordinary skill in the art to understand the invention for various embodiments with various modifications as are suited to the particular use contemplated.

[0061] The diagrams depicted herein are just one example. There may be many variations to this diagram or the steps (or operations) described therein without departing from the spirit of the invention. For instance, the steps may be performed in a differing order or steps may be added, deleted or modified. All of these variations are considered a part of the claimed invention.

[0062] The descriptions of the various embodiments of the present invention have been presented for purposes of illustration, but are not intended to be exhaustive or limited to the embodiments disclosed. Many modifications and variations will be apparent to those of ordinary skill in the art without departing from the scope and spirit of the described embodiments. The terminology used herein was chosen to best explain the principles of the embodiments, the practical application or technical improvement over technologies found in the marketplace, or to enable others of ordinary skill in the art to understand the embodiments disclosed herein.

1.-14. (canceled)

15. A semiconductor device, comprising:

- a first fin of a first transistor disposed over a substrate, the first fin comprising a semiconductor material comprising germanium in a first amount;
- a second fin of a second transistor disposed over the substrate and adjacent to the first fin, the second fin comprising a semiconductor material comprising germanium in a second amount; and
- a shallow trench isolation region arranged between the first fin and the second fin;

wherein the first amount is about 20 atomic % (at. %) to about 60 at. %, the second amount is about 10 at. % to

about 20 at. %, the first fin and the second fin have substantially the same height, and the first transistor and the second transistor have different threshold voltages and different amounts of germanium; wherein the first fin comprises a first substantially uniform concentration of germanium; and wherein the second fin comprises a second substantially uniform concentration of germanium.

**16.** The semiconductor device of claim **15**, wherein the first fin comprises silicon germanium and the second fin comprises silicon germanium.

**17.** The semiconductor device of claim **15**, wherein the substrate comprises silicon, silicon carbide, germanium, silicon germanium, silicon germanium carbon, gallium arsenide, indium arsenide, indium phosphide, or any combination thereof.

**18.-19.** (canceled)

**20.** The semiconductor device of claim **15**, further comprising a buried oxide layer disposed between the substrate and the first and second fins.

**21.** (canceled)

**22.** A semiconductor device, comprising:

a first active area of a first transistor disposed over a substrate, the first active area comprising a first silicon layer and a first silicon germanium layer arranged on the first silicon layer; and

a second active area of a second transistor disposed over the substrate and adjacent to the first fin, the second active area comprising a second silicon layer and a second silicon germanium layer arranged on the second silicon germanium layer;

wherein the first silicon layer is recessed with respect to the second silicon layer and has a thickness that is different than the second silicon layer, and the first silicon germanium layer and the second silicon germanium layer have thicknesses that are the same.

\* \* \* \* \*