

[54] **ORGANO-TITANATE GELLATION OF EPOXY RESIN COATED ARTICLES**

[52] U.S. Cl. **427/116; 427/333; 427/340; 427/341; 427/386; 427/430.1; 427/435**

[76] Inventors: **Leonard B. Simmonds**, 125 Kelvington Dr., Monroeville, Pa. 15146; **James D. B. Smith**, 104 Briaridge Dr., Turtle Creek, Pa. 15145; **Richard L. Oblich**, 108 Timber La., Trafford, Pa. 15085

[57] **ABSTRACT**
An article, such as a mica wrapped coil, a dynamo-electric machine component containing mica wrapped coils, or a metal substrate, is insulated by: (A) applying wet epoxy resin to the article, (B) contacting the wet epoxy resin with a titanate solution, for a time effective to form a resin impervious, gelled epoxy skin on the surface of the epoxy resin, where the titanate solution consists essentially of organo-titanate and an organic, non-polar solvent, where the weight ratio of organo-titanate:organic non-polar solvent is from 1:2.5 to 1:99, and (C) curing the epoxy resin.

[21] Appl. No.: **331,429**

[22] Filed: **Dec. 16, 1981**

Related U.S. Application Data

[63] Continuation of Ser. No. 967,808, Dec. 8, 1978, abandoned.

**10 Claims, 1 Sheet Drawing,
24 Pages Specification**

[51] Int. Cl.³ **B05D 5/12**

The file of this unexamined application may be inspected and copies thereof may be purchased (849 O.G. 1221, Apr. 9, 1968).



