

83130/87

APPLICATION ACCEPTED AND AMENDMENTS

ALLOWED 3-4-90

FORM 1

598084

SPRUSON & FERGUSON

COMMONWEALTH OF AUSTRALIA

PATENTS ACT 1952

APPLICATION FOR A STANDARD PATENT

LODGED AT SUB-OFFICE

30 DEC 1987

Sydney

Shell Internationale Research Maatschappij B.V., a Netherlands Company, of Carel van Bylandtlaan 30, 2596 HR, The Hague, THE NETHERLANDS, hereby apply for the grant of a standard patent for an invention entitled:

Modified Unsaturated Polyesters and Process for the Preparation Therefor

which is described in the accompanying complete specification.

Details of basic application(s):-

Basic Applic. No: Country:

948,374

UNITED STATES OF AMERICA

Application Date:

31 December 1986

The address for service is:-

Spruson & Ferguson
Patent Attorneys
Level 33 St Martins Tower
31 Market Street
Sydney New South Wales Australia

DATED this TWENTY NINTH day of DECEMBER 1987

Shell Internationale Research Maatschappij B.V.


By:

H. J. Anderson

Registered Patent Attorney

TO: THE COMMISSIONER OF PATENTS
OUR REF: 45543
S&F CODE: 61750

5845/2



SPRUSON & FERGUSON

COMMONWEALTH OF AUSTRALIA
PATENTS ACT 1952

DECLARATION IN SUPPORT OF A
CONVENTION APPLICATION FOR A PATENT

In support of the Convention Application made for a patent for an invention entitled:

Modified unsaturated polyesters and process for the preparation therefor

I, Onno Aalbers, of Carel van Bylandtlaan 30, 2596 HR The Hague, the Netherlands, do solemnly and sincerely declare as follows:-

1. I am authorised by SHELL INTERNATIONALE RESEARCH MAATSCHAPPIJ B.V., the applicant for the patent to make this declaration on its behalf.
2. The basic application(s) as defined by Section 141 of the Act was/were made in the U.S.A.
on 31st December, 1986
by ANTONIUS AUGUSTINUS BROEKHUIS
3. Antonius Augustinus BROEKHUIS, a Netherlands national of Badhuisweg 3, 1031 CM Amsterdam, the Netherlands

~~(respectively)~~, is/~~are~~ the actual inventor(s) of the invention and the facts upon which the applicant is entitled to make the application are as follows:

The Applicant is the assignee of the actual inventor(s).

4. The basic application(s) referred to in paragraph 2 of this Declaration was/were the first application(s) made in a Convention country in respect of the invention the subject of the application.

DECLARED at The Hague this 29th day of November 1987

.....
Onno Aalbers

TO: THE COMMISSIONER OF PATENTS
AUSTRALIA

(12) PATENT ABRIDGMENT (11) Document No. AU-B-83130/87
(19) AUSTRALIAN PATENT OFFICE (10) Acceptance No. 598084

(54) Title
MODIFIED UNSATURATED POLYESTERS AND PROCESS FOR THE PREPARATION THEREFOR

International Patent Classification(s)
(51)⁴ C08F 299/04 C08F 283/01

(21) Application No. : 83130/87 (22) Application Date : 30.12.87

(30) Priority Data

(31) Number (32) Date (33) Country
948374 31.12.86 US UNITED STATES OF AMERICA

(43) Publication Date : 07.07.88

(44) Publication Date of Accepted Application : 14.06.90

(71) Applicant(s)
SHELL INTERNATIONALE RESEARCH MAATSCHAPPIJ B.V.

(72) Inventor(s)
ANTONIUS AUGUSTINUS BROEKHUIS

(74) Attorney or Agent
SPRUSON & FERGUSON

(57) Claim

1. A modified unsaturated polyester which unsaturated polyester is modified by having at least one elastomeric polymer segment chemically bonded thereto, said chemical bond comprising a cyclic member containing 6 carbon atoms.

4. A polyester as claimed in claim 1 or 2 wherein said elastomeric polymer segment is a copolymer of an alkenyl-substituted aromatic hydrocarbon and a conjugated diolefin having in the range of from 4 to 12 carbon atoms per molecule.

10. A thermosetting unsaturated polyester resin composition comprising a modified unsaturated polyester as claimed in any one of the preceding claims and a vinyl monomer selected from a styrene monomer or a derivative thereof, a β -hydrocarbyl substituted derivative of acrylic acid in which the alkyl group has 1 to 8 carbon atoms, an acrylate or substituted acrylate, or a monomer containing a $\text{CH}=\text{C}$ group.



PATENTS ACT 1952-1973

Form 10

COMPLETE SPECIFICATION

(ORIGINAL)

FOR OFFICE USE

Class:

Int. Cl:

Application Number:
Lodged:

Complete Specification—Lodged:
Accepted:
Published:

Priority:

Related Art:

TO BE COMPLETED BY APPLICANT

Name of Applicant: *Shell Internationale Research Maatschappij B.V.*

Address of Applicant: *Carel van Bylandtlaan 30,
2596 HR, The Hague,
The Netherlands*

Actual Inventor: *Antonius Augustinus Broekhuis*

Address for Service: *Spruson & Ferguson, Patent Attorneys
Level 33 St. Martins Tower
31 Market Street
Sydney New South Wales Australia*

Complete Specification for the invention entitled:
*Modified unsaturated polyesters and process for the
preparation thereof.*

The following statement is a full description of this invention, including the best method of performing it known to me:—

*Note: The description is to be typed in double spacing, plain type face, in an area not exceeding 250 mm in depth and 160 mm in width, on tough white paper of good quality and it is to be inserted inside this form.

MODIFIED UNSATURATED POLYESTERS AND PROCESS
FOR THE PREPARATION THEREFOR

The invention relates to a modified unsaturated polyester, to a thermosetting unsaturated polyester resin composition containing the same and to a process for the preparation of said modified unsaturated polyester.

The use of unsaturated polyesters in thermosetting resin compositions is, of course, well known in the prior art. Generally, these compositions comprise an unsaturated polyester, a vinyl monomer, a curing agent and a filler. The thermal setting resin composition may also comprise other additives, such as reinforcing agents, anti-shrinking agents and thickeners. In this regard, it should be noted that anti-shrinking agents are commonly used to improve surface characteristics whereas thickeners are used to increase the viscosity of the uncured composition prior to moulding.

In general, unsaturated polyester resin compositions exhibit excellent rigidity, heat resistance and electrical characteristics when used in thermosetting applications. In some applications, however, such as the bulk moulding and sheet moulding applications, improved impact resistance and improved surface characteristics (less shrinkage) are required or at least desired. As indicated in the background section of U.S. patent specification 4,329,438 several methods have, heretofore, been proposed for improving the impact resistance and the surface characteristics of such unsaturated polyester resin compositions.

These methods include the addition of either a diolefin rubber or a styrene-diolefin block copolymer to the resin compositions. Moreover, it is known to use carboxylated derivatives of styrene-butadiene block copolymers as additives in polyester resin compositions for this same purpose. As indicated in the background section of said U.S. patent specification 4,329,438, however, these methods have not been completely successful due, primarily, to the incompatibility of the rubber polymer in the composition and the resulting destructive phase separation and bleeding of the rubber to the surface. Another difficulty with the proposed prior art solutions to the problem, particularly in those cases where a block copolymer is used, is solubility of the block copolymer in the vinyl monomer which functions both as a crosslinking agent and as a solvent in the composition.

U.S. patent specification 4,329,438 teaches yet another method for solving the destructive phase separation problem wherein a carboxylated derivative of a styrene-butadiene block copolymer is used. Specifically, the styrene-butadiene block copolymer is modified by grafting an unsaturated dicarboxylic acid and/or an unsaturated dicarboxylic acid derivative onto the block copolymer. According to the disclosure, significant improvement is realized but destructive phase separation and the associated rubber bleeding is apparently not completely eliminated since the block copolymer and the unsaturated polyester remain as a physical admixture in the thermosetting resin composition.

U.S. patent specification 3,892,819 teaches still another method of solving a compatibility problem in a vinyl ester composition wherein a carboxylated derivative of a polydiene rubber is used.

Particularly, this patent specification teaches that when a polydiene rubber is first treated so as to contain terminal carboxyl groups, the carboxyl groups may then be reacted with epoxy groups contained in the backbone of a polyvinyl ester. The polydiene rubber is, then, chemically bonded to the polyvinyl ester and, therefore, not subject to destructive phase separation so long as the chemical bond remains intact. The ester bond actually used in the thus modified polyvinyl ester is, of course, relatively weak and may be broken under certain conditions. Should this occur prior to curing of the resin composition destructive phase separation and the associated rubber bleeding would again surface. There is, then, a need for a still better way for incorporating a rubber or a thermoplastic elastomeric polymer into a thermosetting polyester resin composition.

It has now been discovered that the foregoing and other disadvantages of the prior art polyester resin compositions can be overcome or at least significantly reduced with the modified unsaturated polyester of this invention and an improved thermosetting unsaturated polyester resin composition provided therewith. It is, therefore, an object of the present invention to provide a modified polyester, methods of preparing the same and a thermosetting polyester resin composition containing the same. It is another object of this invention to provide such a modified polyester which when formulated into a thermosetting polyester resin composition will not be subject to destructive phase separation. It is a still further object of the present invention to provide such a modified polyester which, when formulated into a thermosetting polyester resin composition and cured, will yield a moulded product having improved impact resistance. It is yet

another object of this invention to provide such a modified unsaturated polyester which, when formulated into a thermal setting unsaturated polyester resin composition and cured, will yield a moulded product exhibiting less shrinkage, and hence, better surface characteristics. The foregoing and other objects and advantages will become apparent from the description set forth hereinafter.

Accordingly, the invention provides a modified unsaturated polyester which unsaturated polyester is modified by having at least one elastomeric polymer segment chemically bonded thereto, said chemical bond comprising a cyclic member containing 6 carbon atoms.

The unsaturated polyester of this invention is modified by chemically incorporating a treated elastomeric homopolymer or copolymer into the backbone of said polyester through a relatively stable chemical bond, which elastomeric homopolymer or copolymer is frequently referred to herein as an elastomeric polymer. The elastomeric homopolymer or copolymer may be chemically bonded to the unsaturated polyester by reacting the polyester with an elastomeric homopolymer or copolymer, which copolymer may be either random or block, comprising a conjugated diolefin linkage or by grafting the polyester onto such an elastomeric homopolymer or copolymer. The chemical bonding is accomplished by reacting the conjugated diolefin group of the elastomeric homopolymer or copolymer with an ethylenic unsaturation contained in a preformed polyester or with an ethylenic unsaturation of a monomer useful in preparing such a polyester via a Diels Alder condensation or cyclization. The Diels Alder addition reaction will be accomplished at typical Diels Alder reaction conditions. The modified unsaturated polyester thus produced will exhibit good

impact resistance and may be used in a thermosetting composition. The thermosetting resin composition may also comprise a vinyl monomer, a curing agent and other additives as desired or required.

5 As indicated hereinbefore, the present invention relates to a modified polyester, to methods for preparing said modified polyester and to an improved unsaturated polyester resin composition, which improved
10 unsaturated polyester resin composition exhibits good impact strength when cured and, therefore, may be used with advantage in various moulding applications and particularly sheet moulding and bulk moulding applica-
15 tions. The improved unsaturated polyester is, in effect, a conventional unsaturated polyester modified by chemically incorporating an elastomeric homopolymer or copolymer containing a conjugated diolefin linkage. The chemical incorporation is through a Diels Alder
20 addition reaction between the conjugated diolefin linkage of the elastomeric homopolymer or copolymer with a vinyl unsaturation in the unsaturated polyester or in a monomer subsequently used to prepare such a polyester. The modified unsaturated polyester of this invention may be prepared in at least two ways. Firstly, both an unsaturated polyester and an
25 elastomeric homopolymer or copolymer may be separately produced, the elastomeric homopolymer or copolymer then chemically treated so as to incorporate a conjugated diolefin structure and the thus treated elastomeric homopolymer or copolymer then reacted with the
30 unsaturated polyester at Diels Alder reaction conditions. Alternatively, the elastomeric homopolymer or copolymer may be first produced, chemically treated so as to incorporate a conjugated diolefin linkage, reacted with a suitable monomeric dienophile and then
35 incorporated into the unsaturated polyester by grafting

the polyester onto the elastomeric homopolymer or copolymer at the site of said dienophile.

The unsaturated polyesters which may be modified in the present invention include: those polyesters prepared through the condensation of an unsaturated dicarboxylic acid, an unsaturated dicarboxylic anhydride or a mixture thereof with a dihydric alcohol or mixture thereof and those prepared by condensing an unsaturated monocarboxylic acid with a polyepoxide. Since the modification consists of a 4+2 Diels-Alder cycloaddition reaction, however, it is essential to the present invention that the unsaturated polyester contain at least one dienophile group; i.e., a polar group or a substituted polar group, preferably a carboxyl group, adjacent to a carbon-carbon double bond in the unsaturated polyester structure. Most preferably, the unsaturated polyester will contain at least one group having a carboxyl group adjacent to each of the carbon atoms in a carbon carbon double bond.

Suitable unsaturated polyesters prepared from an unsaturated dicarboxylic acid and/or an anhydride thereof and a polyhydric alcohol include unsaturated polyesters obtained by replacing up to 90 %mol of the unsaturated dicarboxylic acid or anhydride thereof with a saturated dicarboxylic acid or an anhydride thereof. Suitable dicarboxylic acids or anhydrides include, for example, maleic, fumaric, itaconic, citraconic, chloromaleic, mesaconic and glutaconic. Suitable saturated dicarboxylic acids or anhydrides which may be substituted for a part of the unsaturated dicarboxylic acid or anhydride include, but are not necessarily limited to, for example phthalic, succinic, adipic, azelaic, isophthalic, terephthalic and tetrafluorophthalic. Suitable dihydric alcohols

include, but are not necessarily limited to, linear glycols such as ethylene glycol, propylene glycol, dipropylene glycol, diethylene glycol, 1,3-butanediol, neopentyl glycol, 1,4-cyclohexane dimethanol mixtures of these glycols and cyclohexane dimethanol with hydroxy-alkyl ethers of bisphenol A. Suitable unsaturated polyesters include those described in U.S. patent specifications Nos. 3,925,299, 3,925,300, and 3,489,707, the disclosure of which patent specifications are herein incorporated by reference. In general, these polyesters are produced by condensing the dicarboxylic acid or anhydride or mixture thereof with a dihydric alcohol or mixture thereof at a temperature within the range of from about 30°C to about 205°C. The condensation reaction is usually terminated when an acid number less than about 100 is reached most frequently by use of an indicator such as, for example, tolhydroquinone, hydroquinone, a methyl ester of hydroquinone and m-dinitrobenzene.

Suitable polyvinyl esters include those described in U.S. patent specifications Nos. 3,179,623; 3,256,266; 3,301,743; 3,317,465; 3,367,962 and 3,377,406, the disclosure of which patent specifications are all incorporated herein by reference. In general, unsaturated monocarboxylic acids useful in such polyvinyl esters include, for example, acrylic acid, methacrylic acid, halogenated acrylic or methacrylic acids, cinnamic acid and various half esters of dicarboxylic acids such as the half esters of hydroxyalkyl acrylate or methacrylate wherein the hydroxyalkyl group preferably has from 2 to 6 carbon atoms. Polyepoxides which may be used in polyvinyl esters include, but are not necessarily limited to, for example, glycidyl polyethers of both polyhydric alcohols and polyhydric phenols, flame



retardant epoxy resins based on tetrabromo bisphenol A, epoxy novolacs, epoxidized fatty acids or drying oil acids, epoxidized diolefins, epoxidized diunsaturated acid esters and epoxidized unsaturated polyesters containing more than one oxirane group per molecule. The polyepoxides may be monomeric or polymeric.

In general, any elastomeric polymer known in the prior art may be chemically treated to incorporate a conjugated diolefin linkage and then used to modify a polyester in accordance with this invention. Useful elastomeric polymers, then, include those prepared in bulk, suspension, solution or emulsion. As is well known, polymerization of monomers to produce an elastomer may be accomplished using free-radical, cationic and anionic initiators or polymerization catalyst. As indicated more fully hereinafter, however, it is important to the present invention that the elastomeric polymer comprise at least one active group containing an alkali metal atom when it is treated to incorporate the conjugated diolefin linkage. As a result elastomeric polymers prepared with free-radical or cationic initiators as well as those produced with an anionic initiator and then treated to deactivate the active site must be metallated to incorporate at least one such active site prior to treatment to incorporate the conjugated diolefin linkage. Metallization may, of course, be accomplished using techniques well known in the prior art such as the method taught in U.S. patent specification No. 4,145,298, the disclosure of which patent specification is herein incorporated by reference. Polyolefin elastomers containing ethylenic unsaturation could, of course, be easily metallated using these techniques. Notwithstanding that any elastomeric polymer may be used in the present invention, elastomers prepared with

an anionic initiator and then treated to incorporate a conjugated diolefin linkage before deactivation of the active site are preferred and the invention will be described in greater detail by reference to such polymers. Any metallated polymer containing an alkali-metal atom may, however, be substituted for such active, living polymers.

In general the elastomeric homopolymers and copolymers most useful in this invention will be prepared by contacting the monomer or monomers with an organo alkali metal compound in a suitable solvent at a temperature within the range from about -150°C to about 300°C . Particularly effective polymerization initiators are organo lithium compounds having the general formula RLi_n wherein R is an aliphatic, cycloaliphatic or aromatic hydrocarbon radical having from 1 to 20 carbon atoms and n is an integer of 1 to 4. In general, the elastomeric polymers useful in the present invention will have a molecular weight within the range from about 2,000 to about 200,000 and when the elastomeric polymer is a copolymer of one or more diolefins and one or more other monomers, the elastomeric polymer will comprise from 20 to 99 wt% monomeric diolefin units. At this point, it should again be noted, that it is essential to the present invention that the elastomeric homopolymer or copolymer be a living polymer; i.e., contain at least one active group, such as an alkali metal atom bonded to a carbon atom, which can be treated so as to incorporate a conjugated diolefin group by the process of this invention.

Elastomeric homopolymers and copolymers useful in the present invention include those terminally reactive homopolymers and copolymers described in U.S. patent specifications Nos. 3,135,716; 3,150,209; 3,496,154;




3,498,960; 4,145,298 and 4,238,202, the disclosure of which patent specifications are herein incorporated by reference, particularly those homopolymers and copolymers having only one terminal lithium atom and described in U.S. patent specifications Nos. 3,150,209; 3,496,154; 3,498,960; 4,145,298 and 4,238,202. In general, the elastomers taught by these patent specifications may be polymers of one or more conjugated dienes containing from 4 to about 12 carbon atoms such as, for example, 1,3-butadiene, isoprene, piperylene, 2- and 3-methylpentadiene, phenylbutadiene, 3,4-dimethyl-1,3-hexadiene and 4,5-diethyl-1,3-octadiene, preferably those containing 4 to 8 carbon atoms. Moreover, one or more of the hydrogen atoms in these conjugated diolefins may be substituted with halogen atoms. The elastomeric polymers may also be copolymers of one or more of the aforementioned conjugated diolefins and one or more other monomers. Other monomers which may be used include aryl substituted olefins such as, for example, styrene, various alkylstyrenes, paramethoxystyrene, vinyl naphthalene and vinyltoluene, heterocyclic nitrogen-containing monomers, such as pyridine and quinoline derivatives containing at least one vinyl or aliphatic vinyl group such as, for example, 2-vinylpyridine, 3-vinylpyridine and 4-vinylpyridine.


In addition to the foregoing polymers, other block copolymers useful in the present invention may be prepared in accordance with the methods described in U.S. patent specifications Nos. 3,231,635; 3,265,765 and 3,322,856. In practicing these methods, however, care should be exercised to produce block copolymers having the general formula $B_x-(A-B)_y$ or $A_x-(B-A)_y$ wherein x is a number equal to 0 or 1 and y is a whole number from 1 to about 15. A and B are as defined in

the aforementioned patent numbers 3 231 635; 3 265 765 and 3 322 856, A being a polymer block of an alkenyl-substituted aromatic hydrocarbon and B a polymer block of a conjugated diene.

In one process embodiment of the present invention and as indicated
5 hereinbefore, the elastomeric homopolymer or copolymer useful in the present invention may be first treated so as to comprise a conjugated diolefin group, as taught in copending Australian Patent Application No. 83129/87 which copending application was filed 12th December 1987, the disclosure of which copending application is herein incorporated by
10 reference, and then reacted with a preformed unsaturated polyester. Treatment of the elastomeric homopolymer or copolymer to incorporate a conjugated diolefin structure may be accomplished by reacting a so called living elastomeric homopolymer or copolymer first with a 2,3-ethylenically unsaturated aldehyde or ketone having, respectively, one of the following
15 general formulae:
1.



20 wherein R_1 represents a hydrogen atom or an aliphatic, cycloaliphatic, aryl or alkyl-substituted aryl hydrocarbon group having 1 to 10 carbon atoms; or
2.



25 wherein R_1 is as defined hereinbefore and R_2 represents an aliphatic, cycloaliphatic, aryl or alkyl-substituted aryl hydrocarbon group having 1 to 10 carbon atoms;

30 and thereafter converting the resulting alkali metal salt to the corresponding alcohol and then dehydrating the alcohol. As is known in the prior art, the latter two steps may be accomplished, in effect,



simultaneously when an acid is used in excess of the stoichiometric amount to convert the alkali metal salt to the corresponding alcohol at an elevated temperature.

5 In general, reaction of the 2,3-ethylenically unsaturated aldehyde or ketone with the living elastomeric homopolymer or copolymer will be accomplished in a suitable solvent at a temperature within the range from about 10°C to about 150°C.
10 Nominal holding times at reaction conditions will, generally, range from about 1 to about 120 minutes. Suitable solvents include any of the solvents known in the prior art to be effective for use during preparation of the elastomeric homopolymer or
15 copolymer. These include hydrocarbons such as paraffins, cycloparaffins, aromatics and alkyl-substituted aromatics containing from about 4 to about 10 carbon atoms per molecule. Suitable solvents include, for example, benzene, toluene, cyclohexane,
20 methyl cyclohexane, n-butane, n-hexane and n-heptane. Since the reaction between the living elastomeric homopolymer or copolymer and the 2,3-ethylenically unsaturated aldehyde or ketone proceeds stoichiometrically, it will, generally, be sufficient
25 to use 1 mol of 2,3-ethylenically unsaturated aldehyde or ketone per mol of alkali metal active sites in the living elastomeric polymer to be treated although lesser amounts as well as excess amounts of either the aldehyde or ketone may be used.

30 The alkali metal salt produced by reacting the living elastomeric homopolymer or copolymer with a 2,3-ethylenically unsaturated aldehyde or ketone is next converted to the corresponding alcohol. Any of the methods known in the prior art to be effective for
35 such conversion may be used in the present invention.



One such method is to simply react the alkali metal salt with an acid. In general, this reaction will be accomplished in a suitable solvent such as those solvents heretofore mentioned as useful for the aldehyde or ketone reaction with the elastomeric polymer. In general, any acid, organic or inorganic, may be used. Suitable acids, then include, but are not limited to, the series of aliphatic carboxylic acids starting with formic acid the series of aromatic carboxylic acids starting with benzoic acid and the various mineral acids such as, for example, hydrochloric acid, nitric acid and sulphuric acid. After the corresponding alcohol has been produced, the same will then be dehydrated, while still in solution, to yield the desired conjugated diolefin structure. Generally, this may be accomplished simply by heating the alcohol. More expediently, however, this may be accomplished by effecting the acid treatment at an elevated temperature. In a preferred embodiment of the present invention, then, the acid treatment will be accomplished at a temperature within the range of from about 40°C to about 205°C. Generally, nominal holding times at a temperature within the foregoing range within the range of from about 1 to about 120 minutes will be sufficient to permit both conversion of the lithium salt to the corresponding alcohol and dehydration of the alcohol. Again, conversion of the alkali metal salt to the alcohol will occur on a stoichiometric basis, however, an excess of acid will catalyze the dehydration reaction. Generally, then, a slightly greater than stoichiometric amount of acid will be used to effect the conversion. The elastomeric homopolymer or copolymer containing the conjugated diolefin structure may be recovered as a crumb from solution using conventional technology well known in



the prior art or the same may be used directly in the next step in the preparation of a modified unsaturated polyester.

5 In this one process embodiment the elastomeric homopolymer or copolymer containing the conjugated diolefin structure is next reacted with a preformed unsaturated polyester. In general, the reaction between the preformed polymers will be accomplished in a suitable solvent such as those solvents heretofore
10 described as useful in the previous steps. As indicated hereinbefore, the reaction will constitute a 4 + 2 Diels Alder addition involving the conjugated diolefin group incorporated into the elastomeric polymer and an ethylenically unsaturated linkage having
15 a polar group on at least one adjacent carbon atom in the unsaturated polyester. In general, and when the modified unsaturated polyester is to be used in a moulding composition, it will not be necessary to incorporate more than an average of about one
20 elastomeric segment into the unsaturated polyester. Moreover, when the unsaturated polyester has been preformed using vinyl substituted monocarboxylic acids, care should be exercised to ensure that no more than about one vinyl group is reacted with an elastomeric
25 segment containing a conjugated diolefin group. Notwithstanding this, it is contemplated in the present invention to incorporate more than one treated elastomeric segment per polyester segment, particularly when relatively high molecular weight unsaturated
30 polyesters containing unsaturated dicarboxylic acid monomer units are used.

In general, reaction between the conjugated diolefin group of the treated elastomeric polymer and an ethylenically unsaturated linkage in an unsaturated
35 polyester will be accomplished at a temperature within

the range from about 10°C to about 205°C. In this regard, and as is well known in the prior art, higher temperatures within this range will be required to effect reaction between the conjugated diolefin group and the ethylenic unsaturation when the ethylenic unsaturation has only one adjacent active polar group. Moreover, higher temperatures within this range will be required if the ethylenic unsaturation is hindered. The lower temperatures within this range are, of course, effective when the ethylenic unsaturation has two adjacent active groups and said ethylenic unsaturation is otherwise unhindered. In general, the pH will be maintained at a value within the range of from about 1 to about 7 during the Diels Alder addition reaction. Nominal holding times within the range from about 1 to about 240 minutes will be sufficient to permit the reaction to proceed to completion. Again, the 4 + 2 Diels Alder addition will proceed on a stoichiometric basis.

In general, and in moulding compositions comprising such modified polyester, the modified polyester will comprise from about 10 to about 100 %mol of the total polyester used in the composition. As a result, at least two methods may be used to produce the desired blend of modified unsaturated polyester and the unmodified unsaturated polyester. For example, when the unsaturated polyester resin composition is to comprise less than 100 %mol of modified unsaturated polyester a sufficient amount of treated elastomeric polymer may be added to an unsaturated polyester to convert the desired percentage thereof, less than 100 %mol, to a modified unsaturated polyester.

Alternatively, the unsaturated polyester may be modified on a stoichiometric basis and the thus modified unsaturated polyester then combined with the



desired amount of unmodified unsaturated polyester. This latter method does, of course, permit the use of an unsaturated polyester different from the one that was modified.

5 In a second process embodiment of the present invention, the elastomeric homopolymer or copolymer which has been treated so as to contain a conjugated diolefin group will first be reacted with a monomeric dienophile and then, in effect, used as a monomer in
10 the preparation of an unsaturated polyester. In this regard, it should be noted that the treated elastomeric polymer may be reacted with any one of the dicarboxylic acids heretofore mentioned as well as any one of the vinyl monocarboxylic acids identified above. The
15 elastomeric polymer which will now contain at least one terminal carboxyl group may then be substituted for a portion of the unsaturated dicarboxylic acid monomer or a portion of the vinyl substituted monocarboxylic acid monomer in any one of the aforementioned processes for
20 producing an unsaturated polyester. The conditions used to react the treated elastomeric polymer with the monomeric dienophile will, of course, be identical to those used in reacting the treated elastomeric polymer with a preformed unsaturated polyester. The conditions
25 used in the preparation of the unsaturated polyester, when using the treated elastomeric polymer containing at least one carboxyl group as a monomer, will also be identical to the conditions used in the afore-identified processes for preparing such
30 polyesters.

 Again, when a thermosetting polyester resin composition containing polyester which is less than 100% modified polyester is prepared, two methods may be used to prepare a mixture of modified polyester and
35 unmodified polyester suitable for use in a

thermosetting resin composition. In one such method, the amount of monomer comprising an elastomeric polymer segment actually substituted for acid in the condensation reaction may be controlled so as to yield a
5 polyester resin mixture comprising the desired amount of modified polyester and the desired amount of unmodified polyester. In a second such method, a sufficient amount of treated elastomeric polymer will be substituted for unsaturated dicarboxylic acid
10 monomer or vinyl substituted monocarboxylic acid monomer to produce a polyester containing the desired number of appendant elastomeric homopolymer or copolymer segments per polyester segment and the thus produced modified polyester then added to a sufficient
15 amount of unmodified polyester to yield the desired composition for use in a thermosetting polyester resin. In either of these methods, the polyester is, in effect, reacted with or grafted onto one or more of the treated elastomeric polymers at the site of the
20 monomeric dienophile.

As indicated hereinbefore, the modified unsaturated polyesters of this invention are particularly useful in thermosetting polyester resin compositions. The modified unsaturated polyesters of
25 this invention contain at least one elastomeric segment which imparts impact resistance to the moulded product. Since the elastomeric segment is chemically bonded in the modified unsaturated polyester the improved impact resistance is achieved without destructive phase
30 separation or rubber bleeding to the surface during formation of the moulded article.

In general, the modified polyester of this invention will comprise from about 1 to about 95 wt% of the thermosetting polyester composition. The
35 composition may also comprise from about 0 to about 95

wt% of an unmodified unsaturated polyester, which
unmodified unsaturated polyester may be the same or
different than the one which was modified. The
thermosetting unsaturated polyester resin composition
5 will also comprise a vinyl monomer which acts both as a
solvent and as a crosslinking agent. In general, the
vinyl monomer will comprise from about 5 to about 50
wt% of the thermosetting composition. The
thermosetting composition will, generally, also
10 comprise a curing agent. In general, the curing agent
will comprise from about 0.001 to about 1 wt% of the
thermosetting composition. The thermosetting
composition may also comprise a filler, a reinforcing
agent and a thickener. When a filler is used, the same
15 will, generally, comprise from about 5 to about 70 wt%
of the thermosetting composition. When a reinforcing
agent is used, the same will, generally, comprise from
about 5 wt% to about 90 wt% of the composition. When a
thickener is used, the same will, generally, comprise
20 from about 0.1 to about 5 wt% of the thermosetting
composition.

In general, any of the vinyl monomers known to be
useful in the prior art for crosslinking mouldable
compositions may be used in the thermosetting resin
25 composition of the present invention. Suitable vinyl
monomers include the styrene monomers and substituted
derivatives thereof such as, for example, styrene,
 α -methylstyrene, aminostyrene, methylethylaminostyrene,
methoxystyrene, chlorostyrene, dichlorostyrene,
30 dimethylstyrene, trimethylstyrene, t-butylstyrene,
sodium styrenesulfonate, p-benzylstyrene,
p-phenoxy styrene and similar aryl-substituted styrenes.
Suitable monomers also include
 β -hydrocarbyl-substituted derivatives of acrylic acid
35 in which the alkyl group has 1 to 8 carbon atoms such



as, for example, ethylacrylic acid, propylacrylic acid, butylacrylic acid, amylacrylic acid, hexylacrylic acid, heptylacrylic acid, octylacrylic acid, phenylacrylic acid and vinylacrylic acid. Suitable vinyl monomers
5 also include various acrylates and substituted acrylates such as, for example methylacrylate, methyl methacrylate, ethyl acrylate, butyl methacrylate and butyl acrylate. In addition to the foregoing vinyl
10 compounds, any $\text{CH}=\text{C}<$ group containing monomers may be utilized if desired.

In general, any of the curing agents known in the prior art to be effective for use in thermosetting unsaturated polyester resins may be used in the composition of the present invention. Generally,
15 curing agents are conventional free radical polymerization initiators, particularly organic peroxides and hydroperoxides. Suitable curing agents then, include, for example, benzoyl peroxide, dicumyl peroxide, methyl ethyl ketone peroxide, lauryl
20 peroxide, cyclohexanone peroxide, t-butyl perbenzoate, t-butyl hydroperoxide and t-butyl benzene hydroperoxide, cumene hydroperoxide and t-butyl peroctoate. In addition, various azo compounds such as azobisisobutyronitrile may be used. A particularly
25 preferred curing agent is t-butyl perbenzoate.

In general, any of the fillers known in the prior art to be useful in thermosetting polyester resins may be used in the thermosetting resin composition of the present invention. Suitable fillers include, for
30 example, calcium carbonate, calcium silicate, silica, calcined clay, chalk, talc, limestone, anhydrous calcium sulphate, barium sulphate, asbestos, powdered glass, quartz, aluminium hydrate, aluminium oxide and antimony oxide. Similarly, any of the reinforcing
35 agents known to be useful in thermosetting polyester

resins may be used in the thermosetting composition of this invention. Suitable reinforcing agents, then, include, for example, fibres of glass, metal silicates, asbestos, cellulose, carbon, graphite, polyesters, polyacryls, polyamides and polyolefins. Chopped glass fibres are particularly effective for use as reinforcing agents. In general, any of the thickening agents known in the prior art to be effective for use in thermosetting polyester resin compositions may be used in the composition of the present invention. Suitable thickeners include oxides and/or hydroxides of metals of Group II of the Periodic Table and are selected from oxides and hydroxides of magnesium, calcium, strontium, barium and zinc. The hydroxides of magnesium and/or calcium are particularly effective thickening agents.

In addition to the previous named components, the thermosetting unsaturated polyester resin composition may also comprise, for example, pigments, colorants, lubricants, stabilizers and silane coupling agents. In this regard, it should be noted that conventional colorants and pigments such as, for example, TiO_2 , carbon black and phthalocyanide pigment and mixtures thereof, are employed as desired in amounts sufficient to give the desired colour to the final moulded product. It should also be noted that lubricants such as, for example, aluminium, barium, calcium, magnesium or zinc stearate may be used to impart mould release properties to the composition.

The ingredients of the thermosetting resin composition of this invention may be combined by a mixing technique which involves moderate to high shear agitation. This can be accomplished by means of twin rotor mixers designed to give moderate shear to the paste-like ingredients. It is essential to provide

some shear and because of the viscosity of the materials being mixed, proper mixing cannot be obtained simply by stirring or by using a conventional impeller mixer. On the other hand, high intensity mixing which would generate excessive heat (above 35°C) and activate the catalyst must be avoided. Sheet moulding compounding line mixing equipment can also be used. This mixing under sufficient shear to achieve good dispersion of the ingredients without heat buildup sufficient to activate the catalyst insures a good blend and is necessitated by the fact that the resin composition may contain normally solid material. Shear which gives a heat buildup of, preferably, 2-30°C is particularly satisfactory. Low shear is preferred for BMC to avoid glass degradation.

The modified unsaturated polyester and the unmodified unsaturated polyester may be blended before incorporation into the moulding composition or each may be added separately during the mixing. Preferably, however, the polyesters will be blended before incorporation in the moulding composition.

The thermosetting polyester resin composition of this invention may be cured at conditions known to be effective for this purpose in the prior art. Generally, temperatures within the range of from about 100°C to about 200°C and a time of about 1 to about 15 minutes is sufficient.

In a preferred embodiment of the present invention, a preformed polyester comprising unsaturated dicarboxylic acid or anhydride and dihydric alcohol monomeric units will be modified by reaction with a block copolymer comprising a single alkenyl-substituted aromatic hydrocarbon block and a single diolefin block and having a conjugated diolefin linkage on or in the diolefin block. In a most preferred embodiment, the



preformed polyester will comprise from 5 to 50 %mol of maleic acid or maleic anhydride monomer units and 50 %mol of propylene glycol monomer units. The preferred polyester may also comprise from about 0 to 45 %mol of saturated dicarboxylic acid or anhydride monomeric units. The block copolymer will be prepared with an organo lithium compound using the method described in U.S. patent specification 3,231,635 and may be represented by the general formula A-B, wherein A and B are, respectively, polymer blocks of an alkenyl substituted aromatic hydrocarbon and a conjugated diolefin. In the preferred embodiment, the alkenyl-substituted aromatic hydrocarbon block will have a weight average molecular weight within the range of from 2,000 to 30,000 and the conjugated diene block will have a weight average molecular weight within the range from 2,000 to 90,000. In a most preferred embodiment, the alkenyl-substituted aromatic hydrocarbon will be styrene and the conjugated diolefin will be either butadiene or isoprene.

In the preferred embodiment, the block copolymer will be treated so as to incorporate a conjugated diolefin group by first contacting the living polymer obtained from the polymerization process with acrolein to produce the lithium salt and then with sulphuric acid at an elevated temperature to, in effect, simultaneously form the corresponding alcohol and dehydrate the same. The thus treated block copolymer is next reacted with a preformed polyester. In the preferred embodiment, the treated block copolymer will be mixed with a molar excess of the preformed polyester and the reaction carried substantially to completion such that the resulting modified polyester will contain an average of roughly one block copolymer (elastomeric) segment per polyester segment. In the preferred

embodiment, the treatment of the block copolymer will be accomplished in the same solvent as was used during the preparation of the block polymer. The reaction between the conjugated diene group and an ethylenically unsaturated group in the polyester will be accomplished at a temperature within the range from about 25 to about 125°C. As indicated hereinbefore, the reaction is a 4 + 2 Diels Alder addition and results, in effect, in the grafting of the block copolymer to the polyester through a cyclic structure comprising 6 carbon atoms. The preferred modified unsaturated polyesters of this invention are particularly effective, when used in thermosetting unsaturated polyester resin compositions, in imparting improved surface characteristics (less shrinkage) and improved impact resistance to the moulded products. Moreover, these improved properties are realized without the risk of destructive phase separation which has heretofore been experienced when elastomeric polymers were incorporated into a thermosetting unsaturated polyester composition.

In a preferred thermosetting unsaturated polyester resin composition, a modified unsaturated polyester within the scope of the present invention will, in effect, be substituted for from about 50 to about 100 wt% of the conventional unsaturated polyester normally used in such compositions. A preferred thermosetting unsaturated polyester resin composition will, then, comprise from 40 to 80% by weight of a modified unsaturated polyester within the scope of the present invention and from about 0 to 40% by weight of an unmodified or conventional unsaturated polyester. As used herein, the recitation "unmodified unsaturated polyester" is intended to mean any unsaturated polyester known in the prior art which is not chemically combined with an elastomeric homopolymer or

copolymer through a 6-member ring. The recitation "conventional unsaturated polyesters" is intended to mean any of those commercially available unsaturated polyesters which are commonly used in thermosetting polyester resin compositions. It will, of course, be appreciated that incorporation of the modified unsaturated polyester into the composition effectively incorporates from about 1 to about 50 wt% of an elastomeric polymer into said composition.

In addition to the modified and unmodified unsaturated polyesters, a preferred thermosetting unsaturated polyester resin will also comprise from 5 to 50% by weight of an ethylenically unsaturated monomer capable of functioning as both a solvent and as a crosslinking agent. In a most preferred composition, the vinyl monomer will be styrene. A preferred thermosetting composition will also comprise from 0.1 to 0.5% by weight of a curing agent.

The following Examples further illustrate the invention.

Example 1

Preparation of styrene-butadiene block copolymer

The block copolymer was prepared under anhydrous and anaerobic conditions in a closed, glass reaction vessel. Initially, styrene (13.1 g) dissolved in cyclohexane (170 g) was charged to the reaction vessel along with n-butoxy- t-butoxy-ethane (100 μ l) and a 0.25N solution of s-butyllithium (3 ml). The reaction vessel was heated to 50°C and when the polymerization of styrene was substantially complete polymerization grade butadiene monomer (24.1 g) was added to the vessel. Polymerization of the diene monomer was allowed to proceed substantially to completion and the resulting styrene-butadiene living block copolymer was quenched by the addition of an excess of methyl



alcohol. The nonfunctionalized styrene-butadiene block copolymer was then recovered as crumb by coagulation with an excess of methyl alcohol. Analysis of the recovered product indicated that the block copolymer
5 contained a single block of styrene having a weight average molecular weight of 13,400 and a single butadiene block having a weight average molecular weight of 29,400.

10 Preparation of three styrene-butadiene block copolymers containing a single acrolein end group

For convenience, these polymer samples have been identified as A, B and C. Each sample was prepared by repeating the polymerization steps summarized in this Example hereinbefore but before deactivating the
15 lithium atom with methyl alcohol the living diblock copolymer was titrated with acrolein until the pale yellow colour of the living anionic polymer had disappeared. The end-capped block copolymer was then contacted with an aliquot of ammonium chloride in
20 methyl alcohol to deactivate the lithium atom. Each of the three samples were recovered by coagulating with an excess of methyl alcohol. After recovery, each sample was analyzed to determine the weight average molecular weight of each block and the amount of coupled products
25 in each sample. These results are shown in the following table:

Acrolein Capped Block Copolymers	A	B	C
Molecular Weight of Styrene Block ($\times 10^{-3}$)	14.4	13.3	13.3
Molecular Weight of Butadiene Block ($\times 10^{-3}$)	29.1	29.1	29.5
Coupled Product (% by weight)	4	5	5

Preparation of styrene-butadiene block copolymer
containing a cyclic anhydride moiety

The acrolein capped polymers identified as A and B in this Example hereinbefore were combined and dissolved in cyclohexane (600 ml). The solution was then divided into two equal sized aliquots and each aliquot treated with an excess of maleic anhydride to produce an elastomer having a cyclic anhydride moiety chemically bonded thereto through a 6-carbon atom cyclic structure containing one carbon-carbon double bond and to dehydrate the alcohol which was produced in this Example hereinbefore. The treatment was accomplished by adding maleic anhydride (0.25g) to each aliquot and then heating both to reflux and holding each at this temperature for four hours. The resulting reaction products were then recovered as a crumb by coagulating in excess methyl alcohol. The elastomer thus produced could be substituted for a portion of the unsaturated dicarboxylic acid or anhydride monomer in any of the polyester resin operations hereinbefore discussed.

Example 2 - Preparation of modified unsaturated polyester

The acrolein capped polymer identified as C in Example 1 was dissolved in xylene (215ml) and combined with 10g of a maleate/propylene glycol unsaturated polyester resins (known under the trade name Koppers 3702-5 unsaturated polyester resin). Three drops of concentrated H_2SO_4 were then added to this solution and the solution heated to reflux temperature and held at this temperature for four hours. The H_2SO_4 , inter alia, acted as a catalyst for the Diels Alder reaction. As a result of this treatment, the alcohol produced in Example 1 was dehydrated and the conjugated diolefin group produced then reacted with the maleate/propylene

glycol unsaturated polyester resin. The product was contacted with an excess of methyl alcohol, a good solvent for the polyester resin. As a result of the contacting with methyl alcohol, the reaction product of the end-capped elastomer and the polyester and any unreacted end-capped elastomer were precipitated while any unreacted polyester remained in solution. After separation, the coagulated product was subjected to infra-red (IR) analysis to confirm the presence of grafted polyester therein. This was confirmed by a peak occurring at 1640 cm^{-1} . Signals in the IR spectrum at 690 cm^{-1} and 920 cm^{-1} also indicated that the coagulated product contained styrene-butadiene block copolymer. The relative intensities of the IR signals indicated that the modified polyester contained significant amounts of both of the polymeric reactants.

Example 3 and Comparative Experiment X

A portion of the styrene-butadiene block copolymer produced in Example 1 and a portion of the acrolein modified block copolymer produced in Example 1 and identified as C were dissolved in styrene monomer at a concentration of 30% by weight of polymer in said solution. A 50g aliquot of each solution was then treated with three drops of sulphuric acid and blended with an equal weight of solution (about 70% by weight of unsaturated polyester) containing Koppers 3702-5 unsaturated polyester, the same polyester which was modified in Example 2, in styrene. The blending was accomplished at 500 revolutions per minute (rpm) for three minutes using a 2.54 cm jiffy blade positioned in a 0.23 kg jar. Each of the blends were then set aside and observed to determine whether gross phase separation would occur. The observations are summarized in the following table:

	Blend	Phase Separation
Comparative Exp. X	with styrene-butadiene block copolymer of example 1	complete after 2 days
Example 3	with acrolein modified block copolymer of example 1	no separation after 7 days

Example 4 and Comparative Experiment Y

Blends were prepared with the polymers described in example 1 under "Preparation of styrene-butadiene block copolymer" and Example 2 and Koppers 3702-5 Polyester. These resin blends were then used in the preparation of Sheet Moulding Compound pastes. Each of the pastes were prepared according to the following recipe:

100g	Block Copolymer in Styrene Monomer (30wt% polymer)
100g	Koppers 3702-5 Unsaturated Polyester Resin (70wt% in styrene)
300g	Calcium Carbonate
6g	Zinc Stearate
0.5g	Black pigment
2.6g	t-Butyl perbenzoate
0.5g	PEP-100 Cure Promoter
7.8g	Marinco H Thickening Agent

Each paste was blended in an 800ml plastic beaker using a 2.54cm Jiffy Mixer blade at 500rpm. The fully blended pastes were then transferred to 0.46kg jars, sealed and set aside to age. After 18 days, the paste were inspected to access the homogeneity of the blend. The paste samples were evaluated for (1) the lack of exudate formation, (2) the absence of chalkiness and (3) smoothness. Each criteria was rated on a scale from 1 (worst) to 5 (best) so that a superior paste

would get a combined score of 15, and the worst possible score would be 3. The results of each of the paste are summarized in the following table:

Paste	Numerical Rating
Comparative Exp. Y with polymer of example 1	3
Example 4 with polymer of example 2	9

The claims defining the invention are as follows:

1. A modified unsaturated polyester which unsaturated polyester is modified by having at least one elastomeric polymer segment chemically bonded thereto, said chemical bond comprising a cyclic member containing 6 carbon atoms.
2. A polyester as claimed in claim 1 wherein said unsaturated polyester comprises unsaturated dicarboxylic acid or unsaturated dicarboxylic anhydride monomer units.
3. A polyester as claimed in claim 1 or 2 wherein said elastomeric polymer segment is a homopolymer of a conjugated diolefin having in the range of from 4 to 12 carbon atoms per molecule.
4. A polyester as claimed in claim 1 or 2 wherein said elastomeric polymer segment is a copolymer of an alkenyl-substituted aromatic hydrocarbon and a conjugated diolefin having in the range of from 4 to 12 carbon atoms per molecule.
5. A polyester as claimed in claim 4 wherein said copolymer is a block copolymer having the general formula $B_x-(A-B)_y$ or $A_x-(B-A)_y$, wherein x is a number equal to 0 or 1, y is a whole number from 1 to 15, A is a polymer block of an alkenyl-substituted aromatic hydrocarbon and B is a polymer block of a conjugated diene.
6. A polyester as claimed in claim 5 wherein said block copolymer comprises a single block comprising an alkenyl-substituted aromatic hydrocarbon and a single block comprising a conjugated diolefin.
7. A polyester as claimed in any one of the preceding claims wherein said elastomeric polymer segment contained a conjugated diolefin linkage prior to chemically bonding the same to said unsaturated polyester.
8. A polyester as claimed in claim 7 wherein one carbon atom in said conjugated diolefin linkage was contained in a diolefin monomeric unit of said elastomeric polymer segment.
9. A polyester as claimed in claim 7 wherein one of the carbon atoms in the conjugated diene linkage was contained in the alkenyl portion of an alkenyl-substituted aromatic hydrocarbon monomer unit of said elastomeric polymer segment.
10. A thermosetting unsaturated polyester resin composition comprising a modified unsaturated polyester as claimed in any one of the preceding claims and a vinyl monomer selected from a styrene monomer or a



derivative thereof, a β -hydrocarbyl substituted derivative of acrylic acid in which the alkyl group has 1 to 8 carbon atoms, an acrylate or substituted acrylate, or a monomer containing a $\text{CH}=\text{C}$ group.

11. A thermosetting unsaturated polyester resin composition as claimed in claim 10 which also contains an unmodified unsaturated polyester.

12. A thermosetting unsaturated polyester resin composition as claimed in claim 10 or 11 wherein said unmodified unsaturated polyester comprises unsaturated dicarboxylic acid or anhydride monomer units.

13. A thermosetting unsaturated polyester resin composition as claimed in claim 10 or 11 wherein said unmodified unsaturated polyester comprises vinyl substituted monocarboxylic acid monomer units.

14. A curable composition containing a curing agent and a modified unsaturated polyester as claimed in any one of claims 1 to 9.

15. An article containing a composition obtained by curing a curable composition as claimed in claim 14.

16. A process for the preparation of a modified unsaturated polyester as claimed in any one of claims 1 to 9, which process comprises:-

- a) treating a preformed elastomeric polymer so as to incorporate a conjugated diolefin group;
- b) reacting said conjugated diolefin group with an ethylenically unsaturated group in an unsaturated polyester so as to chemically combine said elastomeric



polymer and said unsaturated polyester through a cyclic hydrocarbon structure comprising 6 carbon atoms; and

c) recovering a modified polyester.

5 17. A process as claimed in claim 16 wherein said elastomeric polymer contains a lithium atom bonded to a terminal carbon atom and said diolefin group is produced by first reacting the lithium alkyl with a 2,3-ethylenically unsaturated aldehyde or ketone and thereafter neutralizing the resulting salt with an acid
10 to produce an alcohol which is then dehydrated.

18. A process as claimed in claim 17 wherein said lithium alkyl is reacted with a 2,3-ethylenically unsaturated aldehyde.

15 19. A process as claimed in claim 18 wherein said aldehyde is acrolein.

20. A process for grafting an unsaturated polyester onto an elastomeric polymer comprising the steps of:

a) treating a preformed elastomeric polymer so as to incorporate a conjugated diolefin group;
20 b) reacting said elastomeric polymer containing said conjugated diolefin with an unsaturated dicarboxylic acid or a vinyl substituted monocarboxylic acid via a 2 + 4 Diels-Alder addition; and
c) using the reaction product from step b) as a
25 monomer in a polyester polymerization process.

21. A process as claimed in claim 20 wherein said elastomeric polymer is reacted with an unsaturated dicarboxylic acid and the reaction product then substituted for a portion of unsaturated dicarboxylic
30 acid used in a process to produce a polyester by condensing an unsaturated dicarboxylic acid with a polyhydric alcohol.

22. A process as claimed in claim 20 wherein said elastomeric polymer is reacted with a vinyl-substituted
35 monocarboxylic acid and the reaction product then

substituted for a portion of vinyl-substituted monocarboxylic acid monomer in a process wherein a polyester is produced by condensing a vinyl-substituted monocarboxylic acid with a polyepoxide.

23. A process for the preparation of a modified unsaturated polyester, substantially as hereinbefore described with reference to Example 1 or Example 2.

24. The product of the process of any one of claims 16 to 23.

25. A modified unsaturated polyester, substantially as hereinbefore described with reference to Example 1 or Example 2.

26. A thermosetting unsaturated polyester resin composition, substantially as hereinbefore described with reference to Example 3 or Example 4.

DATED this TWENTY-SIXTH day of MARCH 1990
Shell International Research Maatschappij B.V.

Patent Attorneys for the Applicant
SPRUSON & FERGUSON

