




US 20100270601A1

(19) **United States**(12) **Patent Application Publication**
Udayakumar et al.(10) **Pub. No.: US 2010/0270601 A1**(43) **Pub. Date: Oct. 28, 2010**(54) **SEMICONDUCTOR DEVICE HAVING
REDUCED SINGLE BIT FAILS AND A
METHOD OF MANUFACTURE THEREOF****Publication Classification**(51) **Int. Cl.**
H01L 27/108 (2006.01)(52) **U.S. Cl.** **257/295; 257/E27.084**(75) **Inventors:** **Kezhakkedath R. Udayakumar,**
Dallas, TX (US); **Ted S. Moise,**
Dallas, TX (US); **Qi-Du Jiang,**
Plano, TX (US)**Correspondence Address:**
TEXAS INSTRUMENTS INCORPORATED
P O BOX 655474, M/S 3999
DALLAS, TX 75265(73) **Assignee:** **TEXAS INSTRUMENTS**
INCORPORATED, Dallas, TX
(US)(21) **Appl. No.:** **12/828,978**(22) **Filed:** **Jul. 1, 2010****Related U.S. Application Data**(62) Division of application No. 11/845,834, filed on Aug.
28, 2007, now Pat. No. 7,772,014.(57) **ABSTRACT**

One aspect of the invention provides a method of manufacturing a FeRAM semiconductor device having reduce single bit fails. This aspect includes forming an electrical contact within a dielectric layer located over a semiconductor substrate and forming a first barrier layer over the dielectric layer and the electrical contact. The first barrier layer is formed by depositing multiple barrier layers and densifying each of the barrier layers after its deposition. This forms a stack of multiple barrier layers of a same elemental composition. The method further includes forming a second barrier layer over the first barrier layer and forming a lower capacitor electrode, a ferroelectric dielectric layer over the lower capacitor, and forming an upper capacitor electrode over the ferroelectric dielectric layer. A device made by this method is also provided herein.






FIG. 1




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 2D




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10

SEMICONDUCTOR DEVICE HAVING REDUCED SINGLE BIT FAILS AND A METHOD OF MANUFACTURE THEREOF

CROSS REFERENCE TO RELATED APPLICATIONS

[0001] This is a division of U.S. application Ser. No. 11/845,834, filed on Aug. 28, 2007, the entire disclosure of which is hereby incorporated by reference.

TECHNICAL FIELD

[0002] The disclosure is directed, in general, to a method of manufacturing a semiconductor device and more specifically to a semiconductor device having reduced single bit fails and a method of manufacture thereof.

BACKGROUND

[0003] Demand for electronic devices that include non-volatile memory, such as ferroelectric random access memory (FeRAM), has greatly increased. FeRAMs utilize a ferroelectric material, such as strontium bismuth tantalate (SBT) or lead zirconate titanate (PZT), as a capacitor dielectric situated between a lower electrode and an upper electrode. Both read and write operations can be performed on a FeRAM. FeRAMs also often include a titanium nitride (TiN) barrier layer that serves to inhibit diffusion of atoms from the SBT or PZT ferroelectric layers to the underlying contact or interconnect structure.

[0004] FeRAMs, however, can suffer from bit failure. A bit typically consists of a FeRAM capacitor electrically connected, typically by a contact plug, to a transistor. These “bits” are connected to a bit line. During testing, the charge on the FeRAM capacitor is transferred to the bit line. The transferred charge induces a voltage on the bit line, which is then detected by a comparator. If the voltage falls within the range assigned to a “1”, then the comparator outputs a logical “1”. Conversely, if the voltage falls within the range assigned to a “0”, then the comparator outputs a logical “0”. If the bit line voltage of a defective bit deviates and falls outside of the assigned range, the comparator may output an incorrect value. When this condition exists, a bit failure occurs. Such bit failures are undesirable because they can affect the overall yield and reliability of the device.

SUMMARY

[0005] In one embodiment of the invention there is provided a method of manufacturing a semiconductor device. This embodiment comprises forming transistors over a semiconductor substrate, forming a pre-metal dielectric layer over the transistors, forming electrical contacts in the pre-metal dielectric layer that electrically contact the transistors, and forming ferroelectric random access memory (FeRAM) capacitors over the dielectric layer. The formation of the FeRAM capacitors includes forming a first barrier layer over the electrical contact and the pre-metal dielectric layer by conducting deposition and densification of the titanium nitride layer, which forms a stack of multiple titanium nitride layers. A second barrier layer is formed over the first barrier layer, and the second barrier layer has an elemental composition different from the first barrier layer. A lower capacitor electrode is formed over the second barrier layer, and a ferroelectric dielectric layer comprising lead, zirconium and titanium is formed over lower capacitor. This embodiment

further includes forming an upper capacitor electrode over the ferroelectric dielectric layer, forming interlevel dielectric layers over the FeRAM capacitors, and forming interconnects over and within the interlevel dielectric layers to interconnect the transistors and capacitors.

[0006] Another embodiment provides a method of manufacturing ferroelectric random access memory (FeRAM) capacitors. This embodiment includes forming an electrical contact within a dielectric layer located over a semiconductor substrate and forming a first barrier layer, comprising a stack of multiple barrier layers, over the dielectric layer and the electrical contact by depositing each of the barrier layers and densifying each of the barrier layers after its deposition. The same deposition process is used to form each of the layers. The method further includes forming a second barrier layer over the first barrier layer, forming a lower capacitor electrode over the second barrier layer, forming a ferroelectric dielectric layer over the lower capacitor, and forming an upper capacitor electrode over the ferroelectric dielectric layer.

[0007] In another embodiment, there is provided a semiconductor device. The device comprises transistors located over a semiconductor substrate, a pre-metal dielectric layer located over the transistors, electrical contacts located in the pre-metal dielectric layer that electrically contact the transistors and a ferroelectric random access memory (FeRAM) capacitors located over the pre-metal dielectric layer. The FeRAM capacitors include a first barrier layer located over the electrical contacts and the pre-metal dielectric layer, wherein the first barrier layer is a stack of multiple barrier layers having a same elemental composition and have interfaces located therebetween. The device further includes a second barrier layer located over the first barrier layer that has an elemental composition different from the first barrier layer. A lower capacitor electrode is located over the second barrier layer, a ferroelectric dielectric layer is located over the lower capacitor, and an upper capacitor electrode is located over the ferroelectric dielectric layer. Interlevel dielectric layers are located over the FeRAM capacitors, and interconnects are located over and within the interlevel dielectric layers that interconnect the transistors and capacitors.

BRIEF DESCRIPTION OF DRAWINGS

[0008] The disclosure is described with reference to example embodiments and to accompanying drawings, wherein:

[0009] FIG. 1 illustrates a semiconductor device that can be made using the principles of the invention;

[0010] FIGS. 2A-2D and 4-9 illustrate various fabrication steps used to construct the semiconductor device of FIG. 1;

[0011] FIG. 3 compares graphs of Numbers of Bits versus Data Bit “1” line voltage of wafers having conventional FeRAM devices formed thereon with wafers having FeRAM devices formed thereon using the principles of embodiments of the invention;

[0012] FIG. 10 illustrates an integrated circuit (IC) incorporating the semiconductor device of FIG. 1.

DETAILED DESCRIPTION

[0013] FIG. 1 illustrates one embodiment of a ferroelectric random access memory (FeRAM) device 100 constructed according to certain embodiments of the invention. In the embodiment illustrated in FIG. 1, the FeRAM 100 includes a

substrate **110**. A well region **115** is located within the substrate **110**, and a transistor **120** is located over the substrate **110**.

[0014] The transistor **120** may be conventionally formed over the substrate **110** and may include a gate oxide **123** that is located over the substrate **110**, as well as a gate electrode **125** located over the gate oxide **123**. Sidewall spacers flank both sides of the gate electrode **125** and gate oxide **123**. The transistor **120** may further include conventional source/drain regions **128** located within the substrate **110**. The source/drain regions **128** may each include a lightly doped extension implant as well as a higher doped source/drain implant.

[0015] In the illustrated embodiment, a pre-metal dielectric layer **130** is located over the transistor **120**. The pre-metal dielectric layer **130** may be any insulative material known for use in a semiconductor device. As used herein, the pre-metal dielectric layer **130** is the dielectric layer on which metal interconnects lines may be or are formed. Any dielectric layers deposited subsequent to the pre-metal dielectric layer **130** are considered to be interlevel dielectric layers for purposes herein. Located within the pre-metal dielectric layer **130** is an interconnect **140**, such as a contact plug. The interconnect **140** may include an optional barrier layer **143** and a conductive plug **148**. The conductive plug **148** may comprise tungsten and the barrier layer **143** may comprise a Ti/TiN stack. Other materials, however, could be used. The interconnect **140** optimally contacts the drain region of the source/drain regions **128**. The interconnect **140** may be of different types, including a damascene for dual damascene configuration.

[0016] A ferroelectric capacitor **150**, such as a FeRAM capacitor, is located over transistor **120** and contacts the interconnect **140**. The ferroelectric capacitor **150** in the embodiment of FIG. 1 includes a first barrier layer **155** that is a stack of multiple layers located over interconnect **140** and the pre-metal dielectric layer **130**. In one embodiment, the stack may include two to six or more layers, and in a more specific embodiment, it includes four layers. This embodiment also includes a second barrier layer **157** that has a different elemental composition different from the multi-layered barrier layer **155**; that is, all of the atomic elements in the first and second layers **155**, **157** are not the same. For example, each of the layers in the first barrier layer **155** may have an elemental composition that contains titanium and nitrogen, while the second barrier **157** may have an elemental composition that contains titanium, aluminum, and nitrogen. These elements are given as examples, and it should be understood that other elemental combinations used for barrier purposes in semiconductor devices may also be used. Moreover, other embodiments include instances where the elemental composition of both the first and second barrier layers **155**, **157** is the same, excluding any impurities or trace elements. The stack of the first barrier layer **155** provides benefits over conventional ferroelectric capacitors, as discussed in more detail below.

[0017] The ferroelectric capacitor **150** further includes a lower electrode **160**, which may include more than one layer, located over the second barrier layer **157**. Conventional processes may be used to form the electrode layer **160**, and it may comprise a number of different materials while staying within the scope of the invention. For example, the electrode **160** may comprise iridium or noble metals.

[0018] A ferroelectric dielectric layer **165** is located over the lower electrode and in one embodiment, may comprise a perovskite material, such as lead zirconate titanate (PZT),

strontium bismuth tantalate (SBT) or other similar materials. Located over the ferroelectric dielectric layer **165** is an upper electrode **170**, which may have the same composition as the lower electrode **160**, or it may include an oxide of the metal that comprises the electrode. For instance, the lower electrode **160** may be iridium, while the upper electrode **170** may include both iridium and iridium oxide.

[0019] A protective layer **175** that is located over the electrode **170** may also be included in the structure. It should be noted that other layers may also be included in the ferroelectric capacitor **150**, as design may require and is not limited to the illustrated embodiment.

[0020] The multi-layered barrier layer **155** provides benefits over conventional devices. For example, it has been found that the multi-layered barrier layer **155** reduces blistering that occurs as a result of the barrier layer being deposited over the interconnect **140**. In conventional processes, a single barrier layer is typically used and formed over the pre-metal dielectric layer and the interconnect or contact plug. In such instances, the upper portion of the contact plug may have a dip in its center, which can cause blistering of the barrier layer. It has been found that forming the barrier layer **155** in separate, multiple layers by cycling deposition and densification processes, reduces blistering of the barrier layer **155**. Furthermore, and as equally beneficial, it has been unexpectedly found that forming the barrier layer **155** in this way also reduces bit fails within the device. This is beneficial because reduced bit fails increase both yield and reliability of the device.

[0021] FIGS. 2A-2D and 4-9 illustrate views of selected manufacturing steps instructing how one might, in one embodiment, manufacture a FeRAM **100** depicted in FIG. 1. The FeRAM **200** of FIG. 2A includes a substrate **210**. The substrate **210** may be a doped region of a semiconductor wafer or a layer located over the wafer (e.g., epitaxial layer). A transistor **220**, which may be conventionally designed and fabricated, is located over the substrate **210**. As used here, the word "over" includes those instances where any portion of the transistor **220** is supported by or formed in the substrate **210**. The transistor **220** includes a gate dielectric **223**, a gate electrode **225** (e.g., polycrystalline silicon doped either p-type or n-type with a silicide formed on upper or a metal such as titanium, tungsten, TiN, tantalum, TaN), and side wall insulators. Source/drain regions **228** are preferably implanted using conventional dopants and processing conditions. Lightly doped drain extensions as well as pocket implants may also be utilized. In addition, the source/drain regions **228** may be silicided (preferably with titanium, cobalt, nickel, tungsten or other conventional silicide material).

[0022] A pre-metal dielectric layer **230**, which may be conventionally formed, is located over the entire substrate **210** and over the transistor **220**, which includes those instances where the layer **230** is located directly on the substrate **210** and the transistor. The pre-metal dielectric layer **230** may be comprised of a number of dielectric materials, such as silicon oxide, carbides, nitrides, or low-K polymer materials, all of which are well known, and one or more layers.

[0023] Located within the dielectric layer **230** is an interconnect **240**, such as a contact plug, that contacts and makes electrical contact with the transistor **220** and is thus associated therewith. To form the interconnect **240** the dielectric layer **230** is patterned and etched to form an opening for contact to the substrate **210**. An optional barrier layer **243** may be formed to line the opening. The opening is then filled

with one or more conductive materials, such as a conductive plug **248** (e.g., tungsten, molybdenum, titanium, titanium nitride, tantalum nitride, metal silicide, such as Ti, Ni or Co, copper or doped polysilicon). Often during the conductive plug's formation, a dip can form in the upper surface of the plug. The presence of this dip can cause blistering of subsequently deposited FeRAM capacitor barrier layers, which lie over both the dielectric layer **230** and the conductive plug **248**. Thus, it is beneficial to provide a barrier layer that does not blister and one that provides reduced bit fails.

[0024] FIG. 2A further illustrates the deposition of a first barrier layer **250**, one of which forms the barrier stack **155** of FIG. 1. The layer **250** may be deposited using an enhanced chemical vapor deposition process, such as a Metal Organic Chemical Vapor Deposition (MOCVD) process. In one embodiment, MOCVD may be used to deposit the layer **250**, an example of which may be a titanium nitride layer. One embodiment includes cycling layer deposition and densification steps. A general example of the process proceeds as follows. After the semiconductor wafer is transferred to the CVD chamber, it sits on the heater that is held at about 450° C. The temperature is allowed to stabilize at a deposition temperature ranging from about 340° C. to about 540° C. Other diluent gases, e.g., helium and nitrogen, are introduced into the CVD chamber at flow rates ranging from about 200 sccm to about 400 sccm, and the chamber pressure is stabilized to a pressure ranging from about 0.8 Torr to about 2 Torr. A metal organic precursor, such as tetrakis(dimethylamido) titanium (TDMAT), is introduced with helium as a carrier gas into the chamber to begin film deposition at a flow rate ranging from about 190 sccm to about 250 sccm. Other materials, such as tantalum silicon nitride, silicon nitride, titanium silicon nitride, tantalum nitride, hafnium nitride, zirconium nitride, or chromium nitride, may be used in place of the TDMAT. The deposition ends when the precursor gas flowing to the chamber is stopped or substantially stopped such that deposition is no longer occurring. In certain embodiments, the as-deposited layer **250** is amorphous and where TDMAT is used, the layer **250** may be an amorphous TiNxCyHz layer. The deposition time will depend on the targeted thickness.

[0025] Following the deposition, the wafer remains in the chamber for the densification process. Nitrogen and hydrogen gases are introduced at rates ranging from about 200 sccm to about 600 sccm for nitrogen and about 0 sccm to about 500 sccm for hydrogen and the chamber pressure is stabilized. The plasma is introduced to the chamber by using a radio-frequency power ranging from about 500 watts to about 880 watts to begin densification of the layer **250**.

[0026] It should be noted that the thickness of each of the layers of the barrier layer **155** (FIG. 1) may vary, and the layers thickness prior to densification is referred to herein as a pre-densification thickness, and the thickness of these layers after densification is referred to herein as a post-densification thickness. For example, in one embodiment, the layer **250** is deposited to a pre-deposition thickness of about 75 angstroms. During the densification process, the layer's **250** thickness may decrease by as much as 50% to about 40 angstroms due to the fact that the plasma densification reduces impurity components, e.g., carbon and oxygen, and the layer **250** is transformed into polycrystalline form. In the fabrication test samples, a post-densification thickness of 40 angstroms achieved after a 35 second densification plasma process showed good improvement in the reduction of impurity content and reduction in blistering and an unexpected

reduction in fail bit rates. It is believed that this thickness allows the plasma used in subsequent densification steps to penetrate through the newly deposited film into any previously deposited films of the stack and achieved the observed beneficial improvements.

[0027] Following the densification of layer **250**, another deposition cycle is conducted to form a second barrier layer **251** over the first barrier layer **250**, as shown in FIG. 2B. As with the first barrier layer **250**, the second barrier layer **251** is deposited using deposition and densification cycles. The deposition and densification cycles may be the same as those used to form layer **250** or they be different as to time, process conditions, or materials used. Moreover, the same above-discussed deposition and densification processes used to form layer **250** may also be used to form barrier layer **251**. Even in those embodiments where the deposition and densification processes are the same for each layer, the atomic percentages of the impurities in layer **251** that result from the deposition may vary from layer **250**. This can occur when impurities from layer **251** diffuse into layer **250** during the deposition and densification of layer **251**, thereby changing the impurity concentration, which can also form an impurity gradient within layer **251**. This provides a compositional modulation that may also be another reason for the reduction in bit failures.

[0028] Following the densification of layer **251**, another deposition cycle is conducted to form a third barrier layer **252** over the second barrier layer **251**, as shown in FIG. 2C. As with the first and second barrier layers **250**, **251**, the third barrier layer **252** is deposited using deposition and densification. Moreover, the same above-discussed deposition and densification processes used to form layers **250** and **251** may also be used to form barrier layer **252**, or they may be different. Also, even if the same deposition and densification processes are used, the atomic percentages of the impurities in layer **252** that result from the deposition and densification may vary from layer **251** for the same reasons noted above, thereby changing the impurity concentration, which can also form an impurity gradient within layer **252**. This provides a compositional modulation in layer **252** that may also be a reason for the reduction in bit failures.

[0029] Following the densification of layer **252**, another deposition cycle is conducted to form a fourth barrier layer **253** over the third barrier layer **252**, as shown in FIG. 2D. As with the first, second, and third barrier layers **250**, **251**, **252**, the fourth barrier layer **253** is deposited using a deposition process followed by a densification step. Moreover, the same above-discussed deposition and densification processes used to form layers **250**, **251**, and **252** may also be used to form barrier layer **253**, or they may be different. Also, even if the same deposition and densification processes are used, the atomic percentages of the impurities in layer **253** that result from the deposition and densification may vary from layer **250**, **251**, and **252** for the same reasons noted above, thereby changing the impurity concentration, which can also form an impurity gradient within layer **253**. This provides a compositional modulation in layer **253** that may also be a reason for the reduction in bit failures. In this embodiment, barrier layers **250**, **251**, **252**, and **253** collectively form a first barrier layer **254** for a FeRAM capacitor.

[0030] Test results show that the densification process of the thinner films provides a larger reduction in impurities than offered by conventional processes. For example, when a conventional single 100 angstrom thick barrier layer was formed,

the average carbon and oxygen atomic percent (i.e., percentage of the number of atoms) content within the layer was about 7.4% and 12.8% respectively. Moreover, this film had a higher resistivity of about 501 micro ohms centimeter. In contrast, the multi-layered barrier layer provided by embodiments covered by the invention showed improvements in both impurity content and resistivity. For example, in one embodiment that included two barrier layers, the stack had an average atomic percent of carbon of less than about 4.5% and an average atomic percent of oxygen of less than about 2.4% where each of the two layers had a post-densification thickness of about 40 angstroms. The resistivity of this stack was about 269 micro ohms centimeter. In another embodiment that included four deposited layers, the stack had an average atomic percent of carbon of less than about 3.3% and an average atomic percent of oxygen of less than about 1.0%, where each of the four layers had a post-densification thickness of about 40 angstroms. The resistivity of this stack was about 183 micro ohms centimeter. The reduced impurity content within the stacked barrier layer is believed to be another reason for the reduced bit failure within the device.

[0031] The embodiment discussed above shows four different layers comprising the first barrier layer **254**. However, it should be understood that the first barrier layer **254** may be comprised of any number of multiple layers. For example, the first barrier layer **254** may be comprised of two to six individual layers, or more in other embodiments.

[0032] Another benefit of the invention is that the deposition and densification cycles form interfaces between the various layers of the first barrier layer **254**, represented as the solid lines located between each of the layers **250** through **253**. It is believed that these interfaces provide an enhanced barrier to limit the diffusion of elements (e.g., lead, zirconium, oxygen) out of the ferroelectric capacitor layer **610**. It also provides an enhanced barrier to limit diffusion of metal elements from the contacts into the ferroelectric capacitor, both of which can degrade the ferroelectric properties.

[0033] A layer, as used herein, is a portion of a material that is terminated by an interface. An interface is a region having a discontinuity of characteristics of the material, such as, e.g., density, conductivity, permittivity, or permeability. An interface may be with respect to a different material or phase, or to a nominally identical material. In some cases the discontinuity may result from physical relaxation of the material in close proximity to the interface to reduce the free energy of a surface after formation of the layer. Relaxation may include, e.g., changes of distances between atoms, or rearrangement of atomic bonds to reduce dangling bonds at the surface. A buried interface may be present between multiple layers of a nominally identical material where formation of an underlying layer ends and formation of an overlying layer begins after a period of time during which relaxation of the surface of the underlying layer occurs. The buried interface may be detected by, e.g. transmission electron microscopy, and may present itself as, e.g., dislocations in a crystalline material, or a line of differing electron transmission contrast.

[0034] As discussed above, the first barrier layer **254**, as provided herein, shows an unexpected improvement over using a single layer as the barrier layer. In experiments that were conducted comparing a single **100** angstrom barrier layer to the multi-layer barrier layer comprising two or more layers, the bit fails rates were unexpectedly improved. This improvement is shown in FIG. 3.

[0035] FIG. 3 compares three different wafers having FeRAM capacitors thereon fabricated using a single **100** angstrom barrier layer. These wafers are represented by the graphs designated **305**, **310**, and **315** and were compared to four different wafers having FeRAM capacitors thereon fabricated using the principles of the invention. The wafers containing the FeRAM capacitors fabricated in accordance with the embodiments discussed herein are represented by the graphs designated **320**, **325**, **330**, and **335**. In the samples, bit failures occurred when the voltage on the "1" bit line fell below about 50 mV. Each of the FeRAM capacitors and associated transistor, which is the transistor to which the capacitor is electrically connected, formed a bit that was connected to a bit line. Each of the wafers contained a total population of these bits that had a wherein a bit with the lowest data "1" value had a polarization that is within 40% of the data "1" peak polarization. As seen in FIG. 3, the wafers **320**, **325**, **330**, and **335** showed a reduction in the number of bit failures when compared to wafers **305**, **310**, and **315**. In fact, there were virtually no bit failures. When the devices were made in accordance with the principles of the invention as represented by the embodiments discussed herein, an unexpected improvement occurred in the number of bit failures as compared to conventionally formed devices.

[0036] A second, optional barrier layer **410** may be conventionally formed over the first, stacked barrier layer **254**, as shown in FIG. 4. In one embodiment that includes the second barrier layer **410**, the second barrier layer has an elemental composition that is different from the layers of the first barrier layer **254**; that is the second barrier layer **410** contains elemental atoms that are not in the first barrier layer **254**, excluding depositional impurities. For example, the second barrier layer **410** may be comprised of titanium aluminum nitride, titanium aluminum, hafnium aluminum nitride, tantalum aluminum nitride or chromium aluminum nitride, while the first barrier layer **254** may comprise titanium nitride, tantalum nitride, hafnium nitride or chromium nitride. In another embodiment, however, the second barrier layer **410** may have the same elemental composition, excluding impurities, as the first barrier layer **254**. In addition, in certain embodiments, the second barrier layer **410** may also be formed in the same manner as the first barrier layer **254**. The thickness of this layer may be about 500 angstroms or more (e.g., 1000 angstroms or greater).

[0037] FIG. 5 illustrates the device **200** of FIG. 4 after the formation of a lower electrode **510** over the optional second barrier layer **410**. The lower electrode **510**, in one embodiment, may be a single layer or may comprise more than one layer. Conventional process may be used to form the lower electrode **510** and may have a thickness ranging from about 200 angstroms to about 1000 angstroms. In one embodiment, the lower electrode layer **510** is stable in oxygen and may comprise a noble metal such as Ir, Ru, or Pd.

[0038] FIG. 6 illustrates the device of FIG. 5 after the formation of a ferroelectric dielectric layer **610** over the lower electrode **510**. The ferroelectric dielectric layer **610** may have a thickness of about 750 angstroms, though the thickness may vary, depending on design. The dielectric layer **610** may comprise a wide range of ferroelectric materials. For example, the dielectric layer **610** may comprise materials, such as lead zirconate titanate (PZT); doped PZT with donors (Nb, La, Ta), acceptors (Mn, Co, Fe, Ni, Al), and/or both; PZT doped and alloyed with SrTiO₃, BaTiO₃ or CaTiO₃. Alternatively, the dielectric layer **610** may comprise strontium bis-

muth tantalate (SBT) and other layered perovskites such as strontium bismuth niobate tantalate (SBNT); or bismuth titanate; BaTiO_3 ; PbTiO_3 ; or Bi_2TiO_3 .

[0039] In one specific embodiment, the dielectric layer **610** comprises PZT because it has the highest polarization and the lowest processing temperature of the aforementioned materials. In addition, the preferred Zr/Ti composition is around 25/75, respectively, in order to obtain good ferroelectric switching properties (large switched polarization and relatively square-looking hysteresis loops). Alternatively, Zr/Ti compositions of approximately 65/35 may be used to maximize uniformity in capacitor properties. The donor dopant may improve the reliability of the PZT by helping to control the point defect concentrations.

[0040] Conventional deposition processes, such as MOCVD may be used to deposit the ferroelectric dielectric layer **610**, and it may be deposited in either a single crystalline/poly-crystalline state or it can be deposited in an amorphous phase at low temperatures and then crystallized using a post-deposition anneal. This is commonly done for Bi ferroelectric films. The post deposition crystallization anneal can be performed immediately after deposition or after later process steps such as electrode deposition or post capacitor etch anneal. The MOCVD PZT approach results in a poly-crystalline film completely formed using temperatures of about 500 EC or less.

[0041] FIG. 7 illustrates the device **200** of FIG. 6 after forming an upper electrode **710** over the ferroelectric dielectric layer **610**. Conventional processes and materials may be used to form the upper electrode **710**. The upper electrode **710** may be a single layer or may also include an oxide layer. When present, the oxide layer may comprise an oxide of the metal used to form the upper electrode **710**. For example, the upper electrode **710** may comprise a noble metal, such as iridium, while the oxide layer may be iridium oxide.

[0042] FIG. 8 illustrates the device **200** of FIG. 7 after the formation of a protective layer **810**. The protective layer **810** may comprise a material which is thick enough to retain its integrity during a subsequent etch process. The protective layer **810** may have a thickness ranging from about 500 angstroms to about 5000 angstroms and may comprise TiAlN, TiN, Ti, TiO_2 , Al, AlO_x , AlN, TiAl, TiAlO_x , Ta, TaO_x , TaN, Cr, CrN, CrO_x , Zr, ZrO_x , ZrN, Hf, HfN, HfO_x , silicon oxide, low-k dielectric, or any stack or combination thereof. An example of the protective layer **810** is a deposited SiO_2 on a TiAlN or TiN layer. The protective layer **810** thickness is controlled by the etch process and the relative etch rates of the various materials, the thicknesses of the etched layers, the amount of overetch required, and the desired remaining protective layer **810** thickness after etching all of the layers.

[0043] The protective layer **810** may or may not be removed after the etching of the capacitor stack. If the protective layer **810** is not removed, then it is preferable to form it of a conductive material. However, a non-conductive or semiconductive material may be used, but the interconnection to the upper electrode **710** may be formed through this layer to make direct connection to the second electrode **710**.

[0044] FIG. 9 illustrates the FeRAM device **200** of FIG. 8 after defining the first barrier layer **254**, the second optional barrier layer **410**, the lower electrode **510**, the ferroelectric dielectric layer **610**, the upper electrode **710** and the protective layer **810** to form a ferroelectric capacitor **910**. Conventional processes may be used to define the ferroelectric capacitor **910**. Using such conventional processes may form

steep sidewalls as shown in FIG. 9. Thus, a sidewall diffusion barrier, not shown, may be formed on the completed ferroelectric capacitor **910** prior to the formation of another interlevel dielectric thereover. The sidewall diffusion barrier allows for the misalignment of the interconnect without shorting the capacitor, it protects the capacitor from the diffusion of most substances into the capacitor and protects the rest of the structures from the out-diffusion of substances from the capacitor. The sidewall diffusion barrier often comprises two layers, but the sidewall diffusion barrier may be comprised of more or fewer layers and stay within the scope of the present invention. The first layer may comprise AlO_x , Ta_2O_5 , AlN, TiO_2 , ZrO_2 , HfO_2 , or any stack or combination thereof; and the second layer may comprise silicon nitride, AlN, or any stack or combination thereof.

[0045] FIG. 10 illustrates an IC **1000** incorporating the ferroelectric capacitor **910** and associated transistor **220** as discussed above. The IC **1000** may also include devices, such as transistors **1005** used to form CMOS devices, BiCMOS devices, Bipolar devices, as well as capacitors or other types of devices. The IC **1000** may further include passive devices, such as inductors or resistors, or it may also include optical devices or optoelectronic devices. Those skilled in the art are familiar with these various types of devices and their manufacture. In the embodiment illustrated in FIG. 10, the IC **1000** includes the ferroelectric capacitor **910** having a pre-metal dielectric layer **1020** located thereunder and interlevel dielectric layers **1022** located thereover. Additionally, interconnect structures **1030**, such as damascene or dual damascene interconnects, are located within the dielectric layers **1022** to interconnect various devices. Specifically, interconnect structure **1025** connects the ferroelectric capacitor **910** to source/drain regions of its associated transistor **220**.

[0046] Those skilled in the art to which the disclosure relates will appreciate that other and further additions, deletions, substitutions, and modifications may be made to the described example embodiments, without departing from the disclosure.

What is claimed is:

1. A semiconductor device, comprising:

- transistors located over a semiconductor substrate;
- a pre-metal dielectric layer located over the transistors;
- electrical contacts located in the pre-metal dielectric layer that electrically contact the transistors;
- ferroelectric random access memory (FeRAM) capacitors located over the pre-metal dielectric layer, including:
 - a first barrier layer located over the electrical contacts and the pre-metal dielectric layer, wherein the first barrier layer is a stack of multiple barrier layers having a same elemental composition and interfaces located therebetween;
 - a second barrier layer located over the first barrier layer, the second barrier layer having an elemental composition different from the first barrier layer;
 - a lower capacitor electrode located over the stack;
 - a ferroelectric dielectric layer located over the lower capacitor; and
 - an upper capacitor electrode located over the ferroelectric dielectric layer;
- interlevel dielectric layers located over the FERAM capacitors; and
- interconnects located over and within the interlevel dielectric layers that interconnect the transistors and capacitors.

2. The semiconductor device of claim 1, wherein the stack is a titanium nitride stack of barrier layers and has an atomic percent of carbon of less than about 4.5% and an atomic percent of oxygen of less than about 2.4% and includes two or more layers.

3. The semiconductor device of claim 1, wherein the stack has an atomic percent of carbon of less than about 3.3% and an atomic percent of oxygen of less than about 1.0% and includes 4 or more barrier layers, each having a thickness of about 40 angstroms.

4. The semiconductor device of claim 3, wherein the stack has a resistivity of about 183 microhm-centimeter.

5. The semiconductor device of claim 1, wherein each of the FeRAM capacitors and associated transistor forms a bit and a total population of the bits has a polarization in micro coulombs/cm² associated therewith and wherein a bit with the lowest data "1" value has a polarization that is within 40% of the data "1" peak polarization.

* * * * *