

(21) Application No: 1610017.4
(22) Date of Filing: 08.12.2014
Date Lodged: 08.06.2016

(62) Divided from Application No
1421741.8 under section 15(9) of the Patents Act 1977

(71) Applicant(s):
Johnson Matthey Public Limited Company
(Incorporated in the United Kingdom)
5th Floor, 25 Farringdon Street, LONDON, EC4A 4AB,
United Kingdom

(72) Inventor(s):
Haiying Chen
Dongxia Liu
Raj Rao Rajaram

(74) Agent and/or Address for Service:
Johnson Matthey PLC
Group Intellectual Property Department, Gate 20,
Orchard Road, Royston, Hertfordshire, SG8 5HE,
United Kingdom

(51) INT CL:
B01J 29/00 (2006.01) B01D 53/94 (2006.01)
B01J 29/22 (2006.01) B01J 29/44 (2006.01)
B01J 29/54 (2006.01) B01J 29/62 (2006.01)
B01J 29/74 (2006.01) B01J 35/04 (2006.01)

(56) Documents Cited:
WO 2012/170421 A1 WO 2012/166868 A1
WO 2011/112949 A1 WO 2008/132452 A2
US 20120189518 A1 US 20100267548 A1
US 20080159936 A1
Microporous and Mesoporous Materials, 2007,
Vol.104 (1-3), Altwasser S. et. al., pages 281-288, note
particularly page 287, disclosing ruthenium particles
in 8-membered ring zeolites with various framework
types, viz., LTA, KFI, MER and RHO, which are
suitable for use as NOx adsorber.

(58) Field of Search:
INT CL B01D, B01J
Other: EPODOC, WPI.

(54) Title of the Invention: **Passive NOx adsorber**
Abstract Title: **Use of a NOx adsorber**

(57) Use of a NOx adsorber comprising a noble metal, such as platinum, palladium, rhodium, gold, silver, iridium, ruthenium, osmium, and a small pore molecular sieve having a maximum ring size of eight tetrahedral atoms, such as aluminosilicate sieves, aluminophosphate molecular sieves and metal-substituted aluminophosphate molecular sieves, to adsorb NOx at or below 200°C and release the adsorbed NOx at temperatures above 200°C. Also disclosed, is an exhaust system for internal combustion engines comprising the NOx adsorber and a method of reducing NOx in an exhaust gas using the NOx adsorber.

PASSIVE NO_x ADSORBER

FIELD OF THE INVENTION

The invention relates to a passive NO_x adsorber and its use in an exhaust
5 system for internal combustion engines.

BACKGROUND OF THE INVENTION

Internal combustion engines produce exhaust gases containing a variety
of pollutants, including nitrogen oxides ("NO_x"), carbon monoxide, and
10 uncombusted hydrocarbons, which are the subject of governmental legislation.
Emission control systems are widely utilized to reduce the amount of these
pollutants emitted to atmosphere, and typically achieve very high efficiencies once
they reach their operating temperature (typically, 200°C and higher). However,
these systems are relatively inefficient below their operating temperature (the "cold
15 start" period).

For instance, current urea based selective catalytic reduction (SCR)
applications implemented for meeting Euro 6b emissions require that the
temperature at the urea dosing position be above about 180°C before urea can be
dosed and used to convert NO_x. NO_x conversion below 180°C is difficult to
20 address using the current systems, and future European and US legislation will
stress the low temperature NO_x storage and conversion. Currently this is achieved
by heating strategies but this has a detrimental effect of CO₂ emissions.

As even more stringent national and regional legislation lowers the amount
of pollutants that can be emitted from diesel or gasoline engines, reducing
25 emissions during the cold start period is becoming a major challenge. Thus,
methods for reducing the level of NO_x emitted during cold start condition continue
to be explored.

For instance, PCT Intl. Appl. WO 2008/047170 discloses a system wherein
NO_x from a lean exhaust gas is adsorbed at temperatures below 200°C and is
30 subsequently thermally desorbed above 200°C. The NO_x adsorbent is taught to

consist of palladium and a cerium oxide or a mixed oxide or composite oxide containing cerium and at least one other transition metal.

U.S. Appl. Pub. No. 2011/0005200 teaches a catalyst system that simultaneously removes ammonia and enhances net NO_x conversion by placing an ammonia-selective catalytic reduction (“NH₃-SCR”) catalyst formulation downstream of a lean NO_x trap. The NH₃-SCR catalyst is taught to adsorb the ammonia that is generated during the rich pulses in the lean NO_x trap. The stored ammonia then reacts with the NO_x emitted from the upstream lean NO_x trap, which increases NO_x conversion rate while depleting the stored ammonia.

PCT Intl. Appl. WO 2004/076829 discloses an exhaust-gas purification system which includes a NO_x storage catalyst arranged upstream of an SCR catalyst. The NO_x storage catalyst includes at least one alkali, alkaline earth, or rare earth metal which is coated or activated with at least one platinum group metal (Pt, Pd, Rh, or Ir). A particularly preferred NO_x storage catalyst is taught to include cerium oxide coated with platinum and additionally platinum as an oxidizing catalyst on a support based on aluminum oxide. EP 1027919 discloses a NO_x adsorbent material that comprises a porous support material, such as alumina, zeolite, zirconia, titania, and/or lanthana, and at least 0.1 wt% precious metal (Pt, Pd, and/or Rh). Platinum carried on alumina is exemplified. U.S. Appl. Pub. No. 2012/0308439 A1 teaches a cold start catalyst that comprises (1) a zeolite catalyst comprising a base metal, a noble metal, and a zeolite, and (2) a supported platinum group metal catalyst comprising one or more platinum group metals and one or more inorganic oxide carriers.

As with any automotive system and process, it is desirable to attain still further improvements in exhaust gas treatment systems, particularly under cold start conditions. We have discovered a new passive NO_x adsorber that provides enhanced cleaning of the exhaust gases from internal combustion engines. The new passive NO_x adsorber also exhibits improved sulfur tolerance.

SUMMARY OF THE INVENTION

The invention is a passive NO_x adsorber that is effective to adsorb NO_x at or below a low temperature and release the adsorbed NO_x at temperatures above the low temperature. The passive NO_x adsorber comprises a noble metal and a small pore molecular sieve. The small pore molecular sieve has a maximum ring size of eight tetrahedral atoms. The invention also includes an exhaust system comprising the passive NO_x adsorber, and a method for treating exhaust gas from an internal combustion engine utilizing the passive NO_x adsorber.

5
10

DETAILED DESCRIPTION OF THE INVENTION

The passive NO_x adsorber of the invention is effective to adsorb NO_x at or below a low temperature and release the adsorbed NO_x at temperatures above the low temperature. Preferably, the low temperature is about 200°C. The passive NO_x adsorber comprises a noble metal and a small pore molecular sieve. The noble metal is preferably palladium, platinum, rhodium, gold, silver, iridium, ruthenium, osmium, or mixtures thereof; more preferably, palladium, platinum, rhodium, or mixtures thereof. Palladium is particularly preferred.

The small pore molecular sieve has a maximum ring size of eight tetrahedral atoms. The small pore molecular sieve may be any natural or a synthetic molecular sieve, including zeolites, and is preferably composed of aluminum, silicon, and/or phosphorus. The molecular sieves typically have a three-dimensional arrangement of SiO₄, AlO₄, and/or PO₄ that are joined by the sharing of oxygen atoms, but may also be two-dimensional structures as well.

The molecular sieve frameworks are typically anionic, which are counterbalanced by charge compensating cations, typically alkali and alkaline earth elements (e.g., Na, K, Mg, Ca, Sr, and Ba), ammonium ions, and also protons. Other metals (e.g., Fe, Ti, and Ga) may be incorporated into the framework of the small pore molecular sieve to produce a metal-incorporated molecular sieve.

Preferably, the small pore molecular sieve is selected from an aluminosilicate molecular sieve, a metal-substituted aluminosilicate molecular

20
25
30

sieve, an aluminophosphate molecular sieve, or a metal-substituted aluminophosphate molecular sieve. More preferably, the small pore molecular sieve is a molecular sieve having the Framework Type of ACO, AEI, AEN, AFN, AFT, AFX, ANA, APC, APD, ATT, CDO, CHA, DDR, DFT, EAB, EDI, EPI, ERI, 5 GIS, GOO, IHW, ITE, ITW, LEV, KFI, MER, MON, NSI, OWE, PAU, PHI, RHO, RTH, SAT, SAV, SIV, THO, TSC, UEI, UFI, VNI, YUG, and ZON, as well as mixtures or intergrowths of any two or more. Particularly preferred intergrowths of the small pore molecular sieves include KFI-SIV, ITE-RTH, AEW-UEI, AEI-CHA, and AEI-SAV. Most preferably, the small pore molecular sieve is AEI or 10 CHA, or an AEI-CHA intergrowth.

The passive NO_x adsorber may be prepared by any known means. For instance, the noble metal may be added to the small pore molecular sieve to form the passive NO_x adsorber by any known means, the manner of addition is not considered to be particularly critical. For example, a noble metal compound 15 (such as palladium nitrate) may be supported on the molecular sieve by impregnation, adsorption, ion-exchange, incipient wetness, precipitation, or the like. Other metals may also be added to the passive NO_x adsorber.

Preferably, some of the noble metal (more than 1 percent of the total noble metal added) in the passive NO_x adsorber is located inside the pores of the 20 small pore molecular sieve. More preferably, more than 5 percent of the total amount of noble metal is located inside the pores of the small pore molecular sieve; and even more preferably may be greater than 10 percent or greater than 25% or greater than 50 percent of the total amount of noble metal that is located inside the pores of the small pore molecular sieve.

25 Preferably, the passive NO_x adsorber further comprises a flow-through substrate or filter substrate. In one embodiment, the passive NO_x adsorber is coated onto the flow-through or filter substrate, and preferably deposited on the flow-through or filter substrate using a washcoat procedure to produce a passive NO_x adsorber system.

30 The flow-through or filter substrate is a substrate that is capable of containing catalyst components. The substrate is preferably a ceramic substrate

or a metallic substrate. The ceramic substrate may be made of any suitable refractory material, e.g., alumina, silica, titania, ceria, zirconia, magnesia, zeolites, silicon nitride, silicon carbide, zirconium silicates, magnesium silicates, aluminosilicates, metallo aluminosilicates (such as cordierite and spudomene), or
5 a mixture or mixed oxide of any two or more thereof. Cordierite, a magnesium aluminosilicate, and silicon carbide are particularly preferred.

The metallic substrates may be made of any suitable metal, and in particular heat-resistant metals and metal alloys such as titanium and stainless steel as well as ferritic alloys containing iron, nickel, chromium, and/or aluminum
10 in addition to other trace metals.

The flow-through substrate is preferably a flow-through monolith having a honeycomb structure with many small, parallel thin-walled channels running axially through the substrate and extending throughout from an inlet or an outlet of the substrate. The channel cross-section of the substrate may be any shape,
15 but is preferably square, sinusoidal, triangular, rectangular, hexagonal, trapezoidal, circular, or oval.

The filter substrate is preferably a wall-flow monolith filter. The channels of a wall-flow filter are alternately blocked, which allow the exhaust gas stream to enter a channel from the inlet, then flow through the channel walls, and exit the
20 filter from a different channel leading to the outlet. Particulates in the exhaust gas stream are thus trapped in the filter.

The passive NO_x adsorber may be added to the flow-through or filter substrate by any known means. A representative process for preparing the passive NO_x adsorber using a washcoat procedure is set forth below. It will be
25 understood that the process below can be varied according to different embodiments of the invention.

The pre-formed passive NO_x adsorber may be added to the flow-through or filter substrate by a washcoating step. Alternatively, the passive NO_x adsorber may be formed on the flow-through or filter substrate by first washcoating
30 unmodified small pore molecular sieve onto the substrate to produce a molecular sieve-coated substrate. Noble metal may then be added to the molecular sieve-

coated substrate, which may be accomplished by an impregnation procedure, or the like.

The washcoating procedure is preferably performed by first slurring finely divided particles of the passive NO_x adsorber (or unmodified small pore molecular sieve) in an appropriate solvent, preferably water, to form the slurry. Additional components, such as transition metal oxides, binders, stabilizers, or promoters may also be incorporated in the slurry as a mixture of water soluble or water-dispersible compounds. The slurry preferably contains between 10 to 70 weight percent solids, more preferably between 20 to 50 weight percent. Prior to forming the slurry, the passive NO_x adsorber (or unmodified small pore molecular sieve) particles are preferably subject to a size reduction treatment (e.g., milling) such that the average particle size of the solid particles is less than 20 microns in diameter.

The flow-through or filter substrate may then be dipped one or more times into the slurry or the slurry may be coated on the substrate such that there will be deposited on the substrate the desired loading of catalytic materials. If noble metal is not incorporated into the molecular sieve prior to washcoating the flow-through or filter substrate, the molecular sieve-coated substrate is typically dried and calcined and then, the noble metal may be added to the molecular sieve-coated substrate by any known means, including impregnation, adsorption, or ion-exchange, for example, with a noble metal compound (such as palladium nitrate). Preferably, the entire length of the flow-through or filter substrate is coated with the slurry so that a washcoat of the passive NO_x adsorber covers the entire surface of the substrate.

After the flow-through or filter substrate has been coated with the passive NO_x adsorber, and impregnated with noble metal if necessary, the coated substrate is preferably dried and then calcined by heating at an elevated temperature to form the passive NO_x adsorber-coated substrate. Preferably, the calcination occurs at 400 to 600°C for approximately 1 to 8 hours.

In an alternative embodiment, the flow-through or filter substrate is comprised of the passive NO_x adsorber. In this case, the passive NO_x adsorber

is extruded to form the flow-through or filter substrate. The passive NO_x adsorber extruded substrate is preferably a honeycomb flow-through monolith.

Extruded molecular sieve substrates and honeycomb bodies, and processes for making them, are known in the art. See, for example, U.S. Pat. Nos. 5,492,883, 5,565,394, and 5,633,217 and U.S. Pat. No. Re. 34,804. Typically, the molecular sieve material is mixed with a permanent binder such as silicone resin and a temporary binder such as methylcellulose, and the mixture is extruded to form a green honeycomb body, which is then calcined and sintered to form the final small pore molecular sieve flow-through monolith. The molecular sieve may contain the noble metal prior to extruding such that a passive NO_x adsorber monolith is produced by the extrusion procedure. Alternatively, the noble metal may be added to a pre-formed molecular sieve monolith in order to produce the passive NO_x adsorber monolith.

The invention also includes an exhaust system for internal combustion engines comprising the passive NO_x adsorber. The exhaust system preferably comprises one or more additional after-treatment devices capable of removing pollutants from internal combustion engine exhaust gases at normal operating temperatures. Preferably, the exhaust system comprises the passive NO_x adsorber and one or more other catalyst components selected from: (1) a selective catalytic reduction (SCR) catalyst, (2) a particulate filter, (3) a SCR filter, (4) a NO_x adsorber catalyst, (5) a three-way catalyst, (6) an oxidation catalyst, or any combination thereof. The passive NO_x adsorber is preferably a separate component from any of the above after-treatment devices. Alternatively, the passive NO_x adsorber can be incorporated as a component into any of the above after-treatment devices.

These after-treatment devices are well known in the art. Selective catalytic reduction (SCR) catalysts are catalysts that reduce NO_x to N₂ by reaction with nitrogen compounds (such as ammonia or urea) or hydrocarbons (lean NO_x reduction). A typical SCR catalyst is comprised of a vanadia-titania catalyst, a vanadia-tungsta-titania catalyst, or a metal/zeolite catalyst such as

iron/beta zeolite, copper/beta zeolite, copper/SSZ-13, copper/SAPO-34, Fe/ZSM-5, or copper/ZSM-5.

Particulate filters are devices that reduce particulates from the exhaust of internal combustion engines. Particulate filters include catalyzed particulate filters and bare (non-catalyzed) particulate filters. Catalyzed particulate filters (for diesel and gasoline applications) include metal and metal oxide components (such as Pt, Pd, Fe, Mn, Cu, and ceria) to oxidize hydrocarbons and carbon monoxide in addition to destroying soot trapped by the filter.

Selective catalytic reduction filters (SCRF) are single-substrate devices that combine the functionality of an SCR and a particulate filter. They are used to reduce NO_x and particulate emissions from internal combustion engines. In addition to the SCR catalyst coating, the particulate filter may also include other metal and metal oxide components (such as Pt, Pd, Fe, Mn, Cu, and ceria) to oxidize hydrocarbons and carbon monoxide in addition to destroying soot trapped by the filter.

NO_x adsorber catalysts (NACs) are designed to adsorb NO_x under lean exhaust conditions, release the adsorbed NO_x under rich conditions, and reduce the released NO_x to form N_2 . NACs typically include a NO_x -storage component (e.g., Ba, Ca, Sr, Mg, K, Na, Li, Cs, La, Y, Pr, and Nd), an oxidation component (preferably Pt) and a reduction component (preferably Rh). These components are contained on one or more supports.

Three-way catalysts (TWCs) are typically used in gasoline engines under stoichiometric conditions in order to convert NO_x to N_2 , carbon monoxide to CO_2 , and hydrocarbons to CO_2 and H_2O on a single device.

Oxidation catalysts, and in particular diesel oxidation catalysts (DOCs), are well-known in the art. Oxidation catalysts are designed to oxidize CO to CO_2 and gas phase hydrocarbons (HC) and an organic fraction of diesel particulates (soluble organic fraction) to CO_2 and H_2O . Typical oxidation catalysts include platinum and optionally also palladium on a high surface area inorganic oxide support, such as alumina, silica-alumina and a zeolite.

The exhaust system can be configured so that the passive NO_x adsorber is located close to the engine and the additional after-treatment device(s) are located downstream of the passive NO_x adsorber. Thus, under normal operating conditions, engine exhaust gas first flows through the passive NO_x adsorber prior to contacting the after-treatment device(s). Alternatively, the exhaust system may contain valves or other gas-directing means such that during the low temperature period (below a temperature ranging from about 150 to 220°C, preferably 200°C, about as measured at the after-treatment device(s)), the exhaust gas is directed to contact the after-treatment device(s) before flowing to the passive NO_x adsorber. Once the after-treatment device(s) reaches the operating temperature (about 150 to 220°C, preferably 200°C, as measured at the after-treatment device(s)), the exhaust gas flow is then redirected to contact the passive NO_x adsorber prior to contacting the after-treatment device(s). This ensures that the temperature of the passive NO_x adsorber remains low for a longer period of time, and thus improves efficiency of the passive NO_x adsorber, while simultaneously allowing the after-treatment device(s) to more quickly reach operating temperature. U.S. Pat. No. 5,656,244, the teachings of which are incorporated herein by reference, for example, teaches means for controlling the flow of the exhaust gas during cold-start and normal operating conditions.

The invention also includes a method for treating exhaust gas from an internal combustion engine. The method comprises adsorbing NO_x onto the passive NO_x adsorber at temperatures at or below a low temperature, thermally desorbing NO_x from the passive NO_x adsorber at a temperature above the low temperature, and catalytically removing the desorbed NO_x on a catalyst component downstream of the passive NO_x adsorber. Preferably, the low temperature is about 200°C.

The catalyst component downstream of the passive NO_x adsorber is a SCR catalyst, a particulate filter, a SCR filter, a NO_x adsorber catalyst, a three-way catalyst, an oxidation catalyst, or combinations thereof.

30

The following examples merely illustrate the invention. Those skilled in the art will recognize many variations that are within the spirit of the invention and scope of the claims.

5 EXAMPLE 1: PREPARATION OF PASSIVE NO_x ADSORBERS (PNAs)

Palladium is added to a small pore chabazite (CHA) zeolite with a silica –to-alumina ratio (SAR) of 26, a medium pore ZSM-5 (MFI) zeolite with a SAR=23 and a large pore beta (BEA) zeolite with an SAR=26 to produce PNA 1A (Pd/CHA), Comparative PNA 1B (Pd/MFI) and Comparative PNA 1C (Pd/BEA)
10 according to the following general procedure: The powder catalyst is prepared by wet impregnation of the zeolite using palladium nitrate as the precursor. After drying at 100°C, the samples are calcined at 500°C. The samples are then hydrothermally aged at 750°C in an air atmosphere containing 10% H₂O. The Pd loading for all the three samples is 1 wt.%.

15 Comparative PNA 1D (Pd/CeO₂) is prepared following the procedures reported in WO 2008/047170. The Pd loading is 1 wt.%. The sample is hydrothermally aged at 750°C in an air atmosphere containing 10% H₂O.

 EXAMPLE 2: NO_x STORAGE CAPACITY TESTING PROCEDURES

20 The PNA (0.4 g) is held at an adsorption temperature about 80°C for 2 minutes in an NO-containing gas mixture flowing at 2 liters per minute at a MHSV of 300 L * hr⁻¹ * g⁻¹. This adsorption stage is followed by Temperature Programmed Desorption (TPD) at a ramping rate of 10°C/minute in the presence of the NO-containing gas until the bed temperature reaches about 400°C in order
25 to purge the catalyst of all stored NO_x for further testing. The test is then repeated starting from an adsorption temperature of 170°C, instead of 80°C.

 The NO-containing gas mixture during both the adsorption and desorption comprises 12 vol.% O₂, 200 ppm NO, 5 vol.% CO₂, 200 ppm CO, 50 ppm C₁₀H₂₂, and 5 vol.% H₂O.

The NO_x storage is calculated as the amount of NO₂ stored per liter of catalyst with reference to a monolith containing a catalyst loading of about 3 g/in³. The results at the different temperatures are shown in Table 1.

5 The results at Table 1 show that the PNA of the invention (PNA 1A) demonstrates comparable NO_x storage capacity both at 80 and 170°C as compared to Comparative PNA 1D. Although Comparative PNAs 1B and 1C exhibit higher NO_x storage capacity at 80°C, their NO_x storage capacity at 170°C is lower. For applications require high NO_x storage capacity at temperatures above
10 about 170°C, PNA 1A and Comparative PNA 1D show advantages over Comparative PNAs 1B and 1C.

EXAMPLE 3: NO_x STORAGE CAPACITY AFTER SULFUR EXPOSURE TESTING PROCEDURES

15 PNA 1A and Comparative PNA 1D were subjected to a high level of sulfation by contacting them with a SO₂ containing gas (100 ppm SO₂, 10% O₂, 5% CO₂ and H₂O, balance N₂) at 300°C to add about 64 mg S per gram of catalyst. The NO_x storage capacity of the catalysts before and after sulfation is measured at 100°C following the procedures of Example 2. The results are listed
20 in Table 2.

The results shown in Table 2 indicate that the PNA of the invention (PNA 1A) retains a significant amount of the NO_x storage capacity even after high a level of sulfur exposure. In contrast, Comparative PNA 1D loses almost all of its NO_x adsorption ability under the same sulfation conditions. The PNA of the
25 invention exhibits much improved sulfur tolerance.

EXAMPLE 4: PREPARATION OF SMALL PORE MOLECULAR SIEVE SUPPORTED PASSIVE NO_x ADSORBERS (PNAs)

30 Palladium is added to a series of small pore molecular sieves following the procedure of Example 1. The Pd loading is kept at 1 wt.% for all the samples. The samples are hydrothermally aged at 750°C in an air atmosphere containing 10%

H₂O. The aged samples are then tested for their NO_x storage capacities following the procedure of Example 2.

These PNAs and their NO_x storage capacity at 80 and 170°C are listed in Table 3.

5 The results in Table 3 show that a wide range of small pore molecular sieve supported PNAs have high NO_x storage capacity.

EXAMPLE 5: PREPARATION OF SMALL PORE MOLECULAR SIEVE
SUPPORTED PASSIVE NO_x ADSORBERS (PNAS) WITH DIFFERENT
10 PALLADIUM LOADINGS

Palladium is added to a small pore molecular sieve CHA following the procedure of Example 1. The Pd loading is increased to 2 wt.% for the sample. The sample is hydrothermally aged at 750°C in an air atmosphere containing 10% H₂O. The aged sample is tested for its NO_x storage capacities following the
15 procedure of Example 2. The NO_x storage capacities at 80 and 170°C on the sample are listed in Table 4.

The results in Table 4 show that increasing Pd loading increases the NO_x storage capacity.

20

TABLE 1: NO_x storage capacity (g NO₂/L)

Catalyst	NO _x storage capacity (80°C)	NO _x storage capacity (170°C)
1A	0.28	0.45
1B *	0.35	0.28
1C *	0.68	0.07
1D *	0.29	0.38

* Comparative Example

25

TABLE 2: NO_x storage capacity (g NO₂/L)

Catalyst	NO _x storage capacity at 100°C	
	Before Sulfation	After Sulfation
1A	0.41	0.28
1D *	0.31	0.01

* Comparative Example

5

TABLE 3: NO_x storage capacity (g NO₂/L)

Catalyst	Small pore molecular sieve	NO _x storage capacity (80°C)	NO _x storage capacity (170°C)
PNA 1A	CHA (SAR=26)	0.28	0.45
PNA 4A	CHA (SAR=12)	0.42	0.60
PNA 4B	CHA (SAR=13)	0.34	0.51
PNA 4C	CHA (SAR=17)	0.20	0.42
PNA 4D	CHA (SAR=22)	0.28	0.42
PNA 4E	AEI (SAR=20)	0.33	0.57
PNA 4F	ERI (SAR=12)	0.08	0.2
PNA 4G	CHA (SAPO-34)	0.29	0.41
PNA 4H	AEI-CHA Intergrowth (SAPO)	0.22	0.23

10

TABLE 4: NO_x storage capacity (g NO₂/L)

Catalyst	Molecular sieve	Pd loading (wt. %)	NO _x storage capacity (80°C)	NO _x storage capacity (170°C)
PNA 1A	CHA (SAR=26)	1	0.28	0.45
PNA 5A	CHA (SAR=26)	2	0.43	0.66

Some further aspects of the invention are described below.

A passive NO_x adsorber effective to adsorb NO_x at or below a low temperature and release the adsorbed NO_x at temperatures above the low temperature, said passive NO_x adsorber comprising a noble metal and a small
5 pore molecular sieve having a maximum ring size of eight tetrahedral atoms.

The passive NO_x adsorber as hereinbefore described wherein the noble metal is selected from the group consisting of platinum, palladium, rhodium, gold, silver, iridium, ruthenium, osmium, and mixtures thereof.

The passive NO_x adsorber as hereinbefore described wherein the noble
10 metal is palladium.

The passive NO_x adsorber as hereinbefore described wherein the small pore molecular sieve is selected from the group consisting of aluminosilicate molecular sieves, metal-substituted aluminosilicate molecular sieves, aluminophosphate molecular sieves and metal-substituted aluminophosphate
15 molecular sieves.

The passive NO_x adsorber as hereinbefore described wherein the small pore molecular sieve is selected from the group of Framework Type consisting of: ACO, AEI, AEN, AFN, AFT, AFX, ANA, APC, APD, ATT, CDO, CHA, DDR, DFT, EAB, EDI, EPI, ERI, GIS, GOO, IHW, ITE, ITW, LEV, KFI, MER, MON,
20 NSI, OWE, PAU, PHI, RHO, RTH, SAT, SAV, SIV, THO, TSC, UEI, UFI, VNI, YUG, ZON, and mixtures or intergrowths thereof.

The passive NO_x adsorber as hereinbefore described wherein the small pore molecular sieve is selected from the group Framework Type consisting of AEI and CHA.

The passive NO_x adsorber as hereinbefore described wherein the intergrowths of the small pore molecular sieves include KFI-SIV, ITE-RTH, AEW-UEI, AEI-CHA, and AEI-SAV.

The passive NO_x adsorber as hereinbefore described wherein the passive NO_x adsorber is coated onto a flow-through or filter substrate.

The passive NO_x adsorber as hereinbefore described wherein the flow-through substrate is a honeycomb monolith.
30

The passive NO_x adsorber as hereinbefore described wherein the passive NO_x adsorber is extruded to form a flow-through or filter substrate.

5 The passive NO_x adsorber as hereinbefore described wherein greater than 5 percent of the total amount of noble metal is located inside pores of the small pore molecular sieve.

The passive NO_x adsorber as hereinbefore described wherein the low temperature is 200°C.

10 An exhaust system for internal combustion engines comprising the passive NO_x adsorber as hereinbefore described and a catalyst component selected from the group consisting a selective catalytic reduction (SCR) catalyst, a particulate filter, a SCR filter, a NO_x adsorber catalyst, a three-way catalyst, an oxidation catalyst, and combinations thereof.

15 A method for reducing NO_x in an exhaust gas, said method comprising adsorbing NO_x onto the passive NO_x adsorber as hereinbefore described at or below a low temperature, thermally desorbing NO_x from the passive NO_x adsorber at a temperature above the low temperature, and catalytically removing the desorbed NO_x on a catalyst component downstream of the passive NO_x adsorber.

20 The method as hereinbefore described wherein the catalyst component is selected from the group consisting a selective catalytic reduction (SCR) catalyst, a particulate filter, a SCR filter, a NO_x adsorber catalyst, a three-way catalyst, an oxidation catalyst, and combinations thereof.

The method as hereinbefore described wherein the low temperature is 200°C.

25

We claim:

1. Use of a passive NO_x adsorber comprising a noble metal and a small pore molecular sieve having a maximum ring size of eight tetrahedral atoms to adsorb NO_x at or below a low temperature and release the adsorbed NO_x at temperatures above the low temperature.
5
2. The use of claim 1, wherein the low temperature is 200°C.
3. The use of claim 1 or claim 2 wherein the noble metal is selected from the group consisting of platinum, palladium, rhodium, gold, silver, iridium, ruthenium, osmium, and mixtures thereof.
- 10 4. The use of any of claims 1 to 3 wherein the noble metal is palladium.
5. The use of any of claims 1 to 4 wherein the small pore molecular sieve is selected from the group consisting of aluminosilicate molecular sieves, metal-substituted aluminosilicate molecular sieves, aluminophosphate molecular sieves and metal-substituted aluminophosphate molecular sieves.
15
6. The use of any of claims 1 to 5 wherein the small pore molecular sieve is selected from the group of Framework Type consisting of: ACO, AEI, AEN, AFN, AFT, AFX, ANA, APC, APD, ATT, CDO, CHA, DDR, DFT, EAB, EDI, EPI, ERI, GIS, GOO, IHW, ITE, ITW, LEV, KFI, MER, MON, NSI, OWE, PAU, PHI, RHO, RTH, SAT, SAV, SIV, THO, TSC, UEI, UFI, VNI, YUG, ZON, and mixtures or intergrowths thereof.
20
7. The use of claim 6 wherein the small pore molecular sieve is selected from the group Framework Type consisting of AEI and CHA.
8. The use of claim 6 wherein the intergrowths of the small pore molecular sieves include KFI-SIV, ITE-RTH, AEW-UEI, AEI-CHA, and AEI-SAV.
25
9. The use of any of claims 1 to 8 wherein the passive NO_x adsorber is coated onto a flow-through or filter substrate.
10. The use of claim 9 wherein the flow-through substrate is a honeycomb monolith.
- 30 11. The use of any of claims 1 to 8 wherein the passive NO_x adsorber is extruded to form a flow-through or filter substrate.

12. The use of any of claims 1 to 11 wherein greater than 5 percent of the total amount of noble metal is located inside pores of the small pore molecular sieve.



Application No: GB1610017.4

Examiner: Dr Albert Mthupha

Claims searched: 1-12

Date of search: 26 September 2016

Patents Act 1977: Search Report under Section 17

Documents considered to be relevant:

Category	Relevant to claims	Identity of document and passage or figure of particular relevance
A	-	US2012/0189518 A1 (JOHNSON MATTHEY), see whole document, note para. [0025], [0042]-[0043], [0046]-[0047], [0049], Table 1, claims 1, 5, 8, 10, 12, 16, disclosing treating exhaust gas comprising NO _x with molecular sieves having pores of 8-member rings and deposited therein Ru, Rh, Pd, Ag, Pt.
A	-	US2008/0159936 A1 (CHEVRON), see whole document, note claims 1, 8, 11, disclosing treatment of cold start engine exhaust, with molecular sieve of pores no larger than 8 membered rings, and deposited therein Pt, Pd, Rh, Ru.
A	-	WO2008/132452 A2 (JOHNSON MATTHEY), see whole document, note claims 1, 9, 11, 12, 38, 39, disclosing zeolite catalyst for treating NO _x -containing exhaust gas, wherein the zeolite catalyst contains at least Ru, Rh, Pd, Ag, In, Pt, & is a small pore zeolite containing maximum ring size of eight tetrahedral atoms.
A	-	Microporous and Mesoporous Materials, 2007, Vol.104 (1-3), Altwasser S. et. al., pages 281-288, note particularly page 287, disclosing ruthenium particles in 8-membered ring zeolites with various framework types, viz., LTA, KFI, MER and RHO, which are suitable for use as NO _x adsorber.
A	-	WO2012/166868 A1 (JOHNSON MATTHEY), see abstract, page 3 line 14-page 6 line 16, page 9 lines 5-9, lines 23-30, page 11 lines 1-8, page 15 lines 4-18, disclosing noble metal (Pd) & zeolite, thus implicitly small pore zeolite with ring of 8 tetrahedral atoms, suitable for use as passive NO _x adsorber.
A	-	WO2012/170421 A1 (JOHNSON MATTHEY), see Abstract and the claims, disclosing precious metal zeolite, suitable for use as a passive NO _x adsorber.
A	-	WO2011/112949 A1 (JOHNSON MATTHEY), see abstract, example 1, page 2 lines 2-28, page 3 line 26-page 4 line 2, page 5 lines 14-20, page 14 lines 14-21, page 17 lines 6-17, discloses the features of claim 1, whereby a catalyst comprising a small pore zeolite and copper (which is considered a



A	-	<p>“noble metal”) or Pd etc.</p> <p>US2010/0267548 A1 (ANDERSEN P. et al.), see abstract, para. [0002], [0011], [0012], [0018], [0019], [0025], [0028], [0063], discloses the features of claim 1, whereby the catalyst comprises a small pore zeolite and copper (considered a “noble metal”), & also some other noble metals are mentioned in para. [0063].</p>
---	---	---

Categories:

X	Document indicating lack of novelty or inventive step	A	Document indicating technological background and/or state of the art.
Y	Document indicating lack of inventive step if combined with one or more other documents of same category.	P	Document published on or after the declared priority date but before the filing date of this invention.
&	Member of the same patent family	E	Patent document published on or after, but with priority date earlier than, the filing date of this application.

Field of Search:

Search of GB, EP, WO & US patent documents classified in the following areas of the UKC^X :

Worldwide search of patent documents classified in the following areas of the IPC

B01D; B01J

The following online and other databases have been used in the preparation of this search report

EPODOC, WPI.

International Classification:

Subclass	Subgroup	Valid From
B01J	0029/00	01/01/2006
B01D	0053/94	01/01/2006
B01J	0029/22	01/01/2006
B01J	0029/44	01/01/2006
B01J	0029/54	01/01/2006
B01J	0029/62	01/01/2006
B01J	0029/74	01/01/2006
B01J	0035/04	01/01/2006