



(22) Date de dépôt/Filing Date: 2011/09/09

(41) Mise à la disp. pub./Open to Public Insp.: 2012/03/15

(62) Demande originale/Original Application: 2 810 672

(30) Priorité/Priority: 2010/09/09 (US61/381,286)

(51) Cl.Int./Int.Cl. *A61L 27/14* (2006.01),
A61B 17/04 (2006.01), *A61L 17/00* (2006.01),
C08J 5/18 (2006.01)


(71) Demandeur/Applicant:
W. L. GORE & ASSOCIATES, INC., US

(72) Inventeur/Inventor:
TOWLER, JEFFREY, US

(74) Agent: GOWLING WLG (CANADA) LLP

(54) Titre : PROCEDE D'AUGMENTATION DE LA RESISTANCE AU DECHIREMENT D'UN FILM

(54) Title: METHOD OF INCREASING FILM TEAR STRENGTH



(57) Abrégé/Abstract:

A method of increasing the tensile strength of polymer films is provided. The creation of the load distribution elements (50) in polymer films (10) necessary to achieve this result is described. Application of the present invention to increase suture retention in a surgical polymer film is also provided.

Abstract

A method of increasing the tensile strength of polymer films is provided. The creation of the load distribution elements (50) in polymer films (10) necessary to achieve this result is described. Application of the present invention to increase suture retention in a surgical polymer film is also provided.

TITLE OF THE INVENTION

Method of Increasing Film Tear Strength

5

10

BACKGROUND OF THE INVENTION

Thin films are routinely used to cover or repair valuable articles. In many applications, these thin films need to be secured in place via an attachment means. Unfortunately, the increased stresses that occur at the interface between the thin film itself and the attachment means often results in premature failure under load. There are many instances where a failure occurs at the interface between the attachment means and the thin film, such as when the surgical polymer film mesh affixed to body tissue during a hernia repair, or a when panels of a filter bag are sewn together, or when a synthetic graft is used in a medical procedure.

U.S. Patent 5,527,341 describes a method of using additional flat membrane layers to reinforce the hole region during tendon augmentation or repair. U.S. Patent 5,797,932 discusses a membrane hernia repair using a "platform-elevated part" approximately equivalent to the thickness of the base membrane. This double membrane thickness is intended to reduce tearing by the suture when after the membrane is stitched in place during the surgery.

U.S. Patent 6,544,167 discusses securing a sheet material such as Dacron (Hemoshield), or polytetrafluoroethylene (Gortex) to body tissue by providing a reinforcing "ring which will typically have a toroidal configuration with a circumferential cross section that is circular, and is typically formed of a plastic material or curled autogenous tissue such as fascia or pericardium, or any other biocompatible material."

US 2002/0026092 A1 discusses a reinforcing "ring can be attached to the material by adhesive or by stitches passing over the ring and through the material. Alternatively, the ring can be sandwiched between two pieces of the sheet material. In this case, a second piece of the sheet material can be positioned on the side of the ring opposite to the

sheet material. Appropriate sutures extending around the ring and through the materials and will sandwich the ring and maintain it in the preferred position.

European Patent Application EP0352972A discusses the need for
5 a thin wall expanded polytetrafluoroethylene (PTFE) "vascular graft which resists tearing by the sutures attaching it to perigraft material. [That inventive] composition comprises an expanded biocompatible fluoroplastic resin and biocompatible, high temperature-resistant fibers which are chemically compatible with the PTFE resin, wherein the fibers
10 are distributed throughout the resin in a random orientation."

The present invention provides a method of increasing tear strength of polymer films as described herein.

SUMMARY OF THE INVENTION

15 An aspect of the present invention relates to a method of increasing the tear strength of polymer films. This method also can be used to increase the force necessary to pull or otherwise remove an attachment means from a polymer film to which it is affixed. This method
20 of increasing tear strength in a polymer film is demonstrated by the inclusion of at least one load distribution element in the polymer film at a location near the foci of the applied load or attachment means. Load distribution elements such as but not limited to slits, perforations, and other apertures are included herein. Said load distribution element,
25 serving as a stress redistribution means, increases the load required for tear propagation through or within the film. In medical articles, such as but not limited to soft tissue patches, the present invention can be used to increase suture retention and similar load bearing characteristics. Thus, this method of increasing the load carrying capability of polymer
30 films is provided herein.

BRIEF DESCRIPTION OF THE FIGURES

35 In the figures in which like reference designations indicate like elements.

Figure 1 is a schematic of a polymer film having a longitudinally oriented load distribution element, an attachment means, and a load source.

Figure 2 is a schematic of a polymer film having a transversely oriented load distribution element, an attachment means, and a load source.

5 Figure 3 is a schematic of a polymer film having a "hat" shaped load distribution element and a point load source.

Figure 4 is a schematic of a polymer film having an aperture load distribution element and a point load source.

Figure 5 is a top view of a circular polymer film having multiple load distribution elements and a load source

10 Figure 6 is a top view of a circular polymer film having multiple load distribution elements of multiple sizes.

Figure 7 is a schematic depicting how the radius of contact was determined in the Mesh Tension test method.

15 Figure 8 is a graph of polymer film mesh orientation angle and suture pull-out force as a function of elliptical aperture aspect ratio.

Figure 9 is a graph of tensile test displacement versus suture pull-out as a function of slit width.

Figure 10 is a graph of tensile test displacement versus suture pull-out as a function of "hat" shaped slit width.

20 Figure 11 is a graph of tear propagation results in the machine, longitudinal direction for a mesh having multiple load distribution means.

Figure 12 is a graph of tear propagation results in the transverse direction for a mesh having multiple load distribution means.

25 DETAILED DESCRIPTION OF THE INVENTION

The present invention provides a method of increasing tear strength in polymer films. In some embodiments, this method is suitable for polymer films to which a load is applied via an attachment point or an attachment means. The method involves the inclusion of at least one load distribution element in the polymer film at or near the foci of the applied load. This method is useful in a variety of applications including but not limited to surgical articles such as surgical polymer film meshes wherein there often is a need to increase suture retention. Thin, strong, polymer film-based, surgical polymer film meshes used to demonstrate the present invention may be useful for minimally invasive laparoscopic technique to correct vaginal prolapse, stress urinary incontinence, or similar pelvic floor disorder.

35

Polymer films suitable for the present invention include, but not limited to, those produced by either casting or extrusion and in-plane (e.g. X-Y direction) expansion. Figure 1 depicts a flat sheet of polymer film (10) to which a tether (30) is attached via attachment means (20).

5 When a load (40) is applied to the tether (30), the force is transferred by the tether (30) to the polymer film (10) via attachment means (20). A skilled artisan will appreciate that a range of attachment means (20) may be employed with the present invention including but not limited to adhesives, mechanical interlocking, welding, bonding, sewing, or taping.

10 One aspect of the present invention is the inclusion of at least one load distribution element (50) which effectively increases the load required for system failure. The load distribution means (50) in this embodiment is a longitudinally oriented slit having a length greater than the width of the attachment means (20). The point of system failure is defined as the load

15 required to cause the polymer film (10) to be substantially separated from the applied load (40). One skilled in the art will appreciate that this separation may come about by detachment of the attachment means (20), failure the polymer film (10), failure of the tether (30) or any combination of thereof.

20 Polymer films to which the present invention applies are generally planar and have undergone in-plane expansion. These polymer films are substantially flat, thin, and flexible. They may be produced from any thermoplastic polymer or paste-extrudable polymer or castable polymer. Some typical thin films to which the present discovery applies include,

25 but are not limited to, those made from polyolefin, polyurethane, silicone, Teflon®, or polytetrafluoroethylene (PTFE), and blends, copolymers, or composites thereof.

Polymer films suitable for the present invention are typically thin, having a thickness less than about 0.10 inch. In some embodiments, the

30 polymer film thickness is less than about 0.050 inch. In other embodiments, the polymer film thickness is less than about 0.010 inch. And in yet other embodiments, the polymer film thickness is less than 0.002 inch thick. These polymer films are flexible and can be rolled or crumpled or folded.

35 A skilled artisan will appreciate that such thin polymer films are often produced from thicker films wherein the thickness is reduced by wet or dry calendaring, expansion, or both. Longitudinal, in-plane expansion (i.e. X-direction) is a common way to build strength while

decreasing thickness. Subsequent inclusion of load distribution elements can further increase the longitudinal load bearing capacity of the film. The load bearing capacity of the film as described herein is defined as the tensile load required to cause specimen failure.

- 5 Transverse expansion (i.e. Y-direction) may be used to build transverse strength. The inclusion of load distribution elements can further increase the transverse load bearing capacity of the film.

Some polymer films of the present discovery may comprise expanded PTFE (ePTFE) which may be produced via processes known
10 to one skilled in the art and based on U.S. Patent 3953566. The specific properties of the ePTFE films used herein may be tailored by the choice of PTFE resin and process conditions. In medical applications, the pore size of the resulting ePTFE film can be tailored to restrict tissue ingrowth. For many human medical applications, the ePTFE pore size should be
15 less than the size of the cells to which it will be exposed. Typically, this requires the resulting ePTFE film to have an average pore size of 13 μm or less.

Figure 2 depicts a bi-axially expanded polymer film (10) to which a
20 tether (30) is attached via attachment means (20). When a longitudinally oriented load (40) is applied to the tether (30), the force is transferred from the tether (30) to the polymer film (10) via attachment means (20). The transversely oriented load distribution element (50) effectively increases the load bearing capacity of the system prior to failure. The load distribution element (50) in Figure 2 is a slit having a width greater
25 than the width of the attachment means (20). The point of system failure is defined as the load required to cause the polymer film (10) to be substantially separated from the applied load (40). As before, one skilled in the area will appreciate that this separation may come about by detachment of the attachment means (20), failure the polymer film (10),
30 failure of the tether (30) or any combination of thereof.

Figure 3 depicts a bi-axially expanded polymer film (10) to which a
tether (30) is attached directly at location (22). When a transversely
oriented load (40) is applied to the tether (30), the force is transferred
from the tether (30) to the polymer film (10) at location (22). The non-
35 orthogonal load distribution element (50) effectively increases the longitudinal load bearing capacity of the system prior to failure. The load distribution element (50) in Figure 3 is a non-orthogonal slit having a longitudinal dimension greater than the width of the attachment at

location (22) of the tether (30) to the polymer film (10). System failure is defined as the load required to cause the polymer film (10) to be substantially separated from the applied load (40). As before, one skilled in the art will appreciate that this separation may come about by failure
5 the polymer film (10), failure of the tether (30), or a combination of thereof.

Figure 4 depicts a bi-axially expanded polymer film (10) to which a tether (30) is attached directly at location (22). When a transversely oriented load (40) is applied to the tether (30), the force is transferred
10 from the tether (30) to the polymer film (10) at location (22). An aperture load distribution element (50) effectively increases the longitudinal load bearing capacity of the system prior to failure. The load distribution element (50) in Figure 4 is an aperture having a longitudinal dimension greater than the width of the attachment at location (22) of the tether (30)
15 to the polymer film (10). System failure is defined as the load required to cause the polymer film (10) to be substantially separated from the applied load (40). As before, one skilled in the art will appreciate that this separation may come about by failure the polymer film (10), failure of the tether (30), or a combination of thereof.

Figure 5 depicts a perforated radially expanded polymer film (10) to which a tethers (30) are attached directly at location (22). When a transversely oriented load (40) is applied to the tether (30), the force is transferred from the tether (30) to the polymer film (10) at location (22). The tether may be a string or line or rope or suture or cable or any other
25 similar tensile element. The attachment means at location (22) may be passing the tether (30) through the polymer film (10) or affixing it to the polymer film surface. The array of circumferentially oriented load distribution elements (50) effectively increase the load bearing capacity of the system prior to failure. Load distribution elements (50) in Figure 5
30 are slits. Other load distribution element types may also be used in this embodiment such as, but not limited to, cross-hatched slits, circles, ellipses, curved slits, and the like. System failure is defined as the load required to cause the polymer film (10) to be substantially separated from the applied load (40). As before, one skilled in the art will
35 appreciate that this separation may come about by failure the polymer film (10), failure of the tether (30), or a combination of thereof.

Figure 6 depicts a perforated radially expanded polymer film (10) in which different types of load distribution elements (50) are present.

Some of the load distribution elements (50) in Figure 6 are an array of circumferentially oriented slits. In addition, Figure 6 depicts an additional set of load distribution elements (50) such as a uniform pattern of smaller perforations (55). Any combination of shapes and/or patterns of load distribution elements may be used in the present invention provided that the load distribution elements can deform under an applied tensile load and yield an increase in load to failure compared to the polymer film having no load distribution elements.

When the present invention is applied to a surgical patch or surgical polymer film mesh made from a microporous fluoropolymer or microporous biocompatible polymer, a second material may be imbibed into microstructure to impart additional functionality. In this instance, the article would comprise both macroscopic load distribution elements and microporous elements. Materials such as but not limited to a hydrogel may be imbibed into the microporous elements to enhance cell ingrowth. Optionally, a second material may be coated onto the external surface of the microporous material or applied to the internal surfaces of the microstructure of the microporous material. Coating materials such as, but not limited to, antibiotic or antiseptic materials may be useful to resist infection. The coating material, rheology, and process parameters can be adjusted to control the amount of material that is deposited on the available internal and/or external polymer film mesh surfaces. A broad range of complementary materials may be carried by or included in the present invention to meet the needs of numerous end applications.

Repairing damaged or weakened body tissues requires a relatively strong polymer film mesh having multiple load distribution elements. For example with a ventral hernia repair, the present invention can provide a 15cm by 19cm elliptical polymer film mesh having a Mesh Tension greater than 32 N/cm and yet be thin enough to be rolled up for delivery through a 5mm trocar port. In the case of this 32 N/cm polymer film mesh, the thickness was about 0.01 cm. When an adhesion barrier is desired, a thinner polymer film mesh may be employed having a Mesh Tension greater than 16 N/cm. In which case, an even larger polymer film mesh will fit within the same 5mm delivery trocar port. Alternatively a similar size polymer film mesh (elliptical shape measuring 15cm x 19cm) could be packaged into a trocar having a diameter less than 5mm. A 4mm OD trocar may be used. Or a 3mm OD trocar may be used.

The packaged polymer film mesh comprising at least one load distribution element may be sterilized while in a containment housing, or prior to insertion into the containment housing, or after relocation to the surgical device. Any suitable sterilization means may be used, including
5 but not limited to γ-radiation, steam, ethylene oxide (EtO), and peroxide.

In some surgical procedures, a different size or diameter delivery device may be warranted. The design parameters, including the number, size, shape, and location of load distribution element(s), may be changed accordingly. If the sole purpose is as an adhesion barrier, then
10 a strength less than 16 N/cm may be useful in which case fewer load distribution elements may be necessary for a given polymer film thickness or a thinner film thickness could be used with equal or more load distribution elements. Alternatively, to meet small package size and high load requirements, the number, shape, and pattern of load
15 distribution elements can be varied along with base polymer film properties.

TEST METHODS

Mesh Tension

20 Mesh Tensions for the examples described below were measured in accordance with ASTM D3787 based on the measured force and the radius of contact (r_{contact}) with the ball.

25
$$\text{Mesh Tension} = \text{Force} / 2 * \pi * r_{\text{contact}}$$

The radius of contact (r_{contact}) was determined using contact paper as follows:

A nip impression kit (10002002 Nip Impression Kit from Metso Paper, P.O. Box 155, Ivy Industrial Park, Clarks Summit, PA 18411) is
30 used to measure the length of ball contact with the polymer film mesh. This kit contains a roll of carbon paper and a roll of plain white paper, which can be dispensed so that any given length of both will be obtained with the carbon side flush against the white paper. The two papers are
35 inserted between the ball and the polymer film mesh. As the load or pressure is applied between the ball and the polymer film mesh the carbon paper will leave an ink mark impression in the shape of the knit on the white paper. The impression length on the white paper is measured with a steel ruler with 0.5 mm increments.

The length of ball contact and the radius of the ball are used to determine the angle of contact as shown in Figure 6.

$$2 \gamma = \text{length of ball contact} / r_{\text{ball}}$$

$$\square = (\text{length of ball contact} / r_{\text{ball}}) / 2$$

$$r_{\text{contact}} = r_{\text{ball}} * \sin (\square)$$

where, $2 \square = \text{angle of contact}$

$r_{\text{ball}} = \text{radius of the ball}$

$r_{\text{contact}} = \text{radius of contact}$

Suture Retention

Suture retention is a mechanical property reflecting the articles mechanical resistance under tension at a suture site placed in the article. To represent the load applied by a suture at a suture site, a small pin fixture was used in which a pin (typically 0.020", or multiple pins) was pressed through a 1 inch wide strip of the test article. The coupon/attached-pin-fixture combination is attached in a tensile test apparatus such as an Instron Tensile Tester. The crosshead speed was set to 200 mm/min. For purposes of this measure, the maximum force exhibited was as the 'suture retention' strength. However, other parameters shown in the stress-strain graphs in Figures 6 and 7 may also be used to define the reinforcement phenomenon described herein.

The following nonlimiting examples are provided to further illustrate the present invention.

EXAMPLES

Tape 1

Fine powder of PTFE polymer as described and taught in US Patent Number 6,541,589, comprising perfluorobutylethylene modifier, was blended with Isopar K (Exxon Mobil Corp., Fairfax, VA) in the proportion of 0.200 g/g of fine powder. The lubricated powder was compressed in a cylinder to form a pellet and placed into an oven set at 70°C for approximately 8 hours. The compressed and heated pellet was ram extruded to produce an extrudate tape approximately 15.2 cm wide by 0.75 mm thick. The tape was then calendered between compression rolls, distended, and dried to yield a tape having matrix tensile strengths of 6 kpsi (machine direction) x 6 kpsi (transverse direction). The side of

the resultant asymmetric polymer film mesh surface corresponding to Tape 1 is herein considered the tight-structure side.

Tape 2

5 Fine powder of PTFE polymer (DuPont, Wilmington, DE) was blended with Isopar K (Exxon Mobil Corp., Fairfax, VA) in the proportion of 0.243 g/g of fine powder. The lubricated powder was compressed in a cylinder to form a pellet. The compressed pellet was ram extruded at room temperature to produce an extrudate tape approximately 15.2 cm
10 wide by 0.75 mm thick. The tape was then calendered between compression rolls, set to a temperature of 38°C, to a thickness of 0.28 mm. The tape was then longitudinally distended 8% and dried. The process produced a calendered tape having matrix tensile strengths of 3.2 kpsi (machine direction) x 1.4kpsi (transverse direction). The side of
15 the resultant asymmetric polymer film mesh surface corresponding to Tape 2 is herein considered the open-structure side.

EXAMPLE 1 – Thin Two-Sided Polymer Film Patch

20 Six layers of Tape 1 were stacked on top of one another, each layer being 90 degrees offset from the previous. The stack was compressed and laminated together under high vacuum (< 29"Hg) at 309°C and 100 k-lbs force for 4 minutes to full density on OEM press Model VAC-Q-LAM-1/75/14X13/2/4.0"/ E370C/N/N/N-C-480V (OEM
25 Press Systems Inc., 311 S. Highland Ave., Fullerton, CA 92832). The compressed stack was allowed to cool and then cut into an 8.5 inch diameter circle.

The circular sample was gripped around the periphery and radially expanded at 300°C and an axial expansion rate of 3.0 inch/second to an
30 area expansion of about 11.25:1. The radially expanded sample was then relaxed to achieve a 1.5:1 area reduction. The sample was removed and cut into a 9"x9" coupon. This process was repeated four times to create four radially expanded PTFE disks.

A polymer film mesh was created by combining four radially
35 expanded PTFE disks from above with one layer of Tape 2 into a single stacked coupon. The stacked coupon was compressed and laminated together under high vacuum (< 29"Hg) at 309°C and ~100 k-lbs force for 4 minutes to approximately full density on OEM press Model VAC-Q-

LAM-1/75/14X13/2/4.0"/E370C/N/N/N-C-480V (OEM Press Systems Inc., 311 S. Highland Ave., Fullerton, CA 92832). The compressed densified stack was allowed to cool and cut to an 8.5 inch circle. The circular sample was gripped around the periphery and expanded at
5 300°C and a rate of 0.2 inch/second axial displacement to an expansion ratio of about 11.25:1. The expanded polymer film mesh was then allowed to relax to an area reduction of about 1.5:1. The polymer film mesh was then restrained in a convection oven (ESPEC Model SSPH-201, 4141 Central Parkway, Hudsonville, MI 49426) at 350°C for 10
10 minutes, and then allowed to cool.

A cross-sectional SEM of this microporous expanded asymmetric PTFE polymer film mesh article is shown in Figure 5.

EXAMPLE 2 – Thin Two-Sided Polymer Film Patch pre-sutured with
15 suture management.

A sample of the polymer film mesh from Example 1 was cut into 15 cm x 19 cm oval device using CO2 Plotter/Laser (Universal Laser Systems Model PLS6.60-50 16000 M 81st Street, Scottsdale, AZ 85260). Then GORE-TEX CV-2 sutures (W. L. Gore and Associates,
20 Inc., 301 Airport Road, Elkton, MD 21921) were looped through at four cardinal locations: 12, 3, 6, and 9 o'clock positions. Each suture was passed about 0.5cm inward from the edge. Each suture was looped through the device such that the free ends were on the abdominal side of the device. The entry and exit point of each suture loop was about 0.5
25 cm apart. Next a thin, strong piece of a fluorinated ethylene propylene (FEP)/expanded PTFE (ePTFE) composite film was cut into an approximately 1cm x 0.5cm rectangle. The expanded PTFE film was prepared in conformance with U.S. Patent 5476589A. The FEP layer was approximately 1 mil thick. This cut rectangle was placed on the open
30 side of the sutured polymer film mesh so that each exposed suture was covered. These FEP/ePTFE rectangles were then welded to the polymer film mesh thereby securing the sutures in place. The welding was accomplished using a soldering gun with a blunt tip and set to 800°F and hand pressure (Weller WSD161, APEX Tool Group LLC., 14600
35 York Road Suite A, Sparks, MD 21152).

Suture Management designed to avoid suture entanglement was accomplished by bundling attached pairs of oriented sutures using coils produced from a "string" of bioabsorbable polymer produced in

conformance with U.S. Patent Number 6,165,217. The bioabsorbable film mass was 7 mg/cm². This film was "cigarette rolled" to produce the "string". This "string" was then looped around sutures securing the parallel adjacent sutures. Heat (260°F, 10 seconds) was applied via heat gun (Steinel Model HL2010E, 9051 Lyndale Avenue, Bloomington, MN 55420) to retract and thermally set the bioabsorbable polymer.

EXAMPLE 3 – Thin Two-Sided Polymer Film Patch pre-sutured packed in tube for delivery through 5mm trocar port

The sutured polymer film mesh article from Example 2 was folded in half across the ellipse minor axis. The folded polymer film mesh was placed between two small mandrels (or a split mandrel) (New England Precision Grinding, 0.013"x70" PTFE coated 304SS mandrels, 35 Jeffrey Avenue, Holliston, MA 01746-2027) that were chucked on a horizontal rotary drill press and the drill press rotated to roll up sutured polymer film mesh device into a tight package around the mandrels. The rolled assembly was removed from the chucks, and the mandrels removed from within the rolled, sutured polymer film mesh. The rolled, sutured polymer film mesh was inserted into a ~5.2mm ID tube (nylon tubing of 0.005" wall from Grilamid). The tube and rolled suture device was inserted into a 5mm trocar port of ID ~5.5mm (Covidien 15 Hampshire Street, Mansfield, MA 02048). Deployment of the sutured polymer film mesh was demonstrated when the rolled sutured polymer film mesh was easily pushed out of the trocar and unrolled onto the table top where is laid relatively flat.

EXAMPLE 4 – Load Distribution – 5:1 Elliptical Aperture

The suture retention effect of creating elliptical apertures was determined using an ePTFE polymer film mesh article created in conformance with U.S. Patent 7306729. The base ePTFE material had matrix tensile strengths of 48kpsi and 46kpsi in the machine and transverse directions, respectively. The material was mounted in a CO₂ plotter/laser (Universal Laser Systems Model PLS6.60-50 16000 M-81st Street, Scottsdale, AZ 85260). The beam was focused on the plane of the material. In the orientation of the test directions (machine direction, transverse direction, and 45 degree nominally), an ellipse having r_{major} 0.05" and r_{minor} 0.010" (i.e. 5:1 ratio) was laser cut from the material oriented so the ellipse was substantially parallel to the perimeter of the

polymer film mesh article. The suture retention measurements were performed by sequentially locating the test pin in a lased aperture in each of the machine, transverse, and 45 degree directions. The results are shown in Figure 7.

5

EXAMPLE 5 – Load Distribution – 2:1 Elliptical Aperture

The suture retention effect of creating elliptical apertures was determined using an ePTFE polymer film mesh article created in conformance with U.S. Patent 7306729. The base ePTFE material had matrix tensile strengths of 48kpsi and 46kpsi in the machine and transverse directions, respectively. The material was mounted in a CO2 plotter/laser (Universal Laser Systems Model PLS6.60-50 16000 M 81st Street, Scottsdale, AZ 85260). The beam was focused on the plane of the material. In the orientation of the test directions (machine direction, transverse direction, and 45 degree nominally), an ellipse having r_{major} 0.05" and r_{minor} 0.025" (i.e. 5:1 ratio) was laser cut from the material oriented so the ellipse was substantially parallel to the perimeter of the polymer film mesh article. The suture retention measurements were performed by sequentially locating the test pin in a lased aperture in each of the machine, transverse, and 45 degree directions. The results are shown in Figure 7.

EXAMPLE 6 – Load Distribution – 1:1 Elliptical Aperture

The suture retention effect of creating elliptical apertures was determined using an ePTFE polymer film mesh article created in conformance with U.S. Patent 7306729. The base ePTFE material had matrix tensile strengths of 48kpsi and 46kpsi in the machine and transverse directions, respectively. The material was mounted in a CO2 plotter/laser (Universal Laser Systems Model PLS6.60-50 16000 M 81st Street, Scottsdale, AZ 85260). The beam was focused on the plane of the material. In the orientation of the test directions (machine direction, transverse direction, and 45 degree nominally), an ellipse having r_{major} 0.05" and r_{minor} 0.050" (i.e. 5:1 ratio) was laser cut from the material oriented so the ellipse was substantially parallel to the perimeter of the polymer film mesh article. The suture retention measurements were performed by sequentially locating the test pin in a lased aperture in each of the machine, transverse, and 45 degree directions. The results are shown in Figure 7.

EXAMPLE 7 – Load Distribution– Control, No Elliptical Aperture

The suture retention effect of creating elliptical apertures was determined using an ePTFE polymer film mesh article created in conformance with U.S. Patent 7306729. The base ePTFE material had matrix tensile strengths of 48kpsi and 46kpsi in the machine and transverse directions, respectively. This control sample was tested by pressing the test pin through the polymer film mesh article in locations corresponding to each of the machine, transverse, and 45 degree directions. The results are shown in Figure 7.

EXAMPLE 8 – Load Distribution – Slit Element

The effect on suture retention of creating a small slit near the suture location determined using an ePTFE polymer film mesh article created in conformance with U.S. Patent 7306729. The base ePTFE material had matrix tensile strengths of 48kpsi and 46kpsi in the machine and transverse directions, respectively. A small slit cut was cut with a razor blade approximately 0.5 cm in from and parallel to the edge of the polymer film mesh article. The test pin was then pressed through the polymer film mesh article at a location between the slit and the edge of the article. The tensile properties were measured. Figure 8 shows the suture pull-out tensile results as a function of slit length compared to a control sample having no slit.

EXAMPLE 9 – Load Distribution – “Hat” Element

The effect on suture retention of creating a small “hat” shaped slit near the suture location determined using an ePTFE polymer film mesh article created in conformance with U.S. Patent 7306729. The base ePTFE material had matrix tensile strengths of 48kpsi and 46kpsi in the machine and transverse directions, respectively. A small “hat” shaped slit cut was cut with a razor blade approximately 0.5 cm in from and parallel to the edge of the polymer film mesh article. The test pin was then pressed through the polymer film mesh article at a location between the “hat” shaped slit and the edge of the article. The tensile properties were measured. Figure 8 shows the suture pull-out tensile results as a function of the “hat” shaped slit length compared to a control sample having no slit.

EXAMPLE 10 – Multiple Longitudinal Load Distribution Elements

Tear Resistance in the machine direction of a material comprising multiple load distribution elements was evaluated as follows: An ePTFE article was created based on U.S. Patent 7306729 resulting in material of average mass of 193 g/m², an average density of 2.1 g/cc, and an MTS (MD) 36 kpsi & (TD) 55 kpsi. The material was mounted in a CO₂ plotter/laser (Universal Laser Systems Model PLS6.60-50 16000 M 81st Street, Scottsdale, AZ 85260). The beam was focused on the plane of the material. A matrix of ellipses of r_{major} 0.02" and r_{minor} 0.004" were
5 lased into the continuous material. The ellipses were oriented with the minor-axis parallel to the machine direction of the material. The ellipses were longitudinally spaced apart 0.07" (nominal center-on-center), and 0.08" transversely (nominal edge-to-edge). The resulting material had a hole pattern as depicted by the uniform pattern of smaller perforations
10 (55) in Figure 6.

A 1 inch by 2 inch sample test coupon was cut and removed from both the as received material as well as material with the lased matrix of load distribution elements described in above in this Example. The tear propagation characteristics of each sample were tested substantially in accordance with ASTM D1938 Trouser Tear Method. The sample test
20 coupon long axis was oriented parallel to the machine direction of the material. A sharp tear was initiated by manually slitting the coupon along the long axis using a sharp razor blade. Each tab was mounted in the lower and upper grips in a tensile tester, and tested at 200 mm/min crosshead speed and the resultant force trace was recorded. The Force
25 versus Displacement data for both the control and lased samples are depicted in Figure 11. The maximum force held by the lased samples is significantly higher than that for the control sample. This proves that with respect to maximum force or load bearing capacity, cutting a multitude of
30 holes in this thin film specimen increased machine direction tensile properties by approximately two times.

EXAMPLE 11 – Multiple Transverse Load Distribution Elements

Tear Resistance in the transverse direction of a material comprising multiple load distribution elements was evaluated as follows:
35 An ePTFE article was created based on U.S. Patent 7306729 resulting in material of average mass of 193 g/m², an average density of 2.1 g/cc, and an MTS (MD) 36 kpsi & (TD) 55 kpsi. The material was mounted in

a CO2 plotter/laser (Universal Laser Systems Model PLS6.60-50 16000 M 81st Street, Scottsdale, AZ 85260). The beam was focused on the plane of the material. A matrix of ellipses of r_{major} 0.02" and r_{minor} 0.004" were lasered into the continuous material. The ellipses were oriented with the minor-axis parallel to the transverse direction of the material. The ellipses were longitudinally spaced apart 0.07" (nominal center-on-center), and 0.08" transversely (nominal edge-to-edge). The resulting material had a hole pattern as depicted by the uniform pattern of smaller perforations (55) in Figure 6.

10 A 1 inch by 2 inch sample test coupon was cut and removed from both the as received material as well as material with the lasered matrix of load distribution elements described above in this Example. The tear propagation characteristics of each sample were tested substantially in accordance with ASTM D1938 Trouser Tear Method. The sample test coupon long axis was oriented parallel to the transverse direction of the material. A sharp tear was initiated by manually slitting the coupon along the long axis using a sharp razor blade. Each tab was mounted in the lower and upper grips in a tensile tester, and tested at 200 mm/min crosshead speed and the resultant force trace was recorded. The Force versus Displacement data for both the control and lasered samples are depicted in Figure 12. The maximum force held by the lasered samples is significantly higher than that for the control sample. This proves that with respect to maximum force or load bearing capacity, cutting a multitude of holes in this thin film specimen increased transverse direction tensile properties by approximately two times.

What is claimed is:

1. A method for increasing the tensile strength of a polymer film comprising the steps of:
providing a polymer film that has undergone in-plane expansion;
creating a load distribution element in said polymer film; and
applying a tensile load to the polymer film on or near to the load distribution element,
wherein the maximum tensile load is increased relative to an equivalent system without
the load distribution element, and
wherein the load distribution element deforms under applied tensile load and yields an
increase in load failure compared to a polymer film having no load distribution element.
2. The method of claim 1 wherein the load distribution element comprises a slit.
3. The method of claim 1 wherein the load distribution element comprises an aperture.
4. The method of claim 1 wherein the polymer film has a thickness less than 0.10 inch.
5. The method of claim 1 wherein the polymer film has a thickness less than 0.050 inch.
6. The method of claim 1 wherein the polymer film has a thickness less than 0.010 inch.
7. The method of claim 1 wherein the polymer film has a thickness less than 0.002 inch.
8. The method of claim 1 wherein the tensile load is applied to the polymer film via a tether.
9. The method of claim 8 wherein the tether is attached to the polymer film via an
attachment means.
10. The method of claim 9 wherein the attachment means comprises an adhesive or a
mechanical interlock or sewn connection.

11. The method according to claim 1 wherein the polymer film is a surgical film, said method further comprising the step of attaching a tether to the surgical polymer film on or adjacent to the load distribution elements using an attachment means, wherein the attachment means comprises an adhesive, a mechanical interlock, or sewn connection, and wherein the step of applying the tensile load is performed via the tether.
12. The method of claim 11 wherein the attachment means comprises a suture.
13. The method of claim 11 wherein the attachment means comprises a staple.
14. The method of claim 11 wherein the attachment means comprises an adhesive.

Figure 1




Figure 2




Figure 3




Figure 4




Figure 5




Figure 6




Figure 7





Figure 8



All R_{major} dimensions are 0.05 inch

Figure 9




Figure 10




Figure 11




Figure 12

