



- (51) International Patent Classification:
A61K 9/32 (2006.01)
- (21) International Application Number:
PCT/US2014/064680
- (22) International Filing Date:
7 November 2014 (07.11.2014)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
61/902,020 8 November 2013 (08.11.2013) US
- (71) Applicant: MICROVENTION, INC. [US/US]; 1311
Valencia Avenue, Tustin, CA 92780 (US).
- (72) Inventors: PLOTKIN, Steve; 1311 Valencia Avenue,
Tustin, CA 92780 (US). CRUISE, Gregory, M.; 6 Via
Taliana, Rancho Santa Margarita, CA 92688 (US). KEE-
LEY, Edward, Michael; 9581 Onset Circle, Huntington
Beach, CA 92646 (US). YU, Renee; 1311 Valencia Aven-
ue, Tustin, CA 92780 (US). HARRIS, Clayton; 1311
Valencia Avenue, Tustin, CA 92780 (US).
- (74) Agents: CULLMAN, Louis, C. et al.; K&L Gates LLP, 1
Park Plaza, Twelfth Floor, Irvine, CA 92604 (US).

- (81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,
BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,
HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR,
KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG,
MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM,
PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC,
SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN,
TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ,
TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU,
TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE,
DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU,
LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK,
SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, KM, ML, MR, NE, SN, TD, TG).

Published:
— with international search report (Art. 21(3))

(54) Title: POLYMER PARTICLES




FIG. 1

(57) Abstract: Polymer particle embolics and methods of making same are described. The particle embolics can be used as embolization agents.

WO 2015/070094 A1

Polymer Particles

Cross Reference to Related Applications

[001] This application claims the benefit of U.S. provisional patent application number 61/902,020, filed November 8, 2013, the entire disclosure of which is incorporated herein by reference.

Field

[002] Polymer particles for the occlusion of vascular sites and cavities within the body, such as the embolization of vascularized tumors or arteriovenous malformations are described.

Summary

[003] Described herein generally are particles including a polyether and optionally one or more monomers. These polymers can be used for/in embolization. The polymer particles are compressible for ease of delivery. Further, in some embodiments, the polymer particles are stable in/at physiological conditions. In some embodiments, the particles can be loaded or coated with a drug(s) or active agent(s).

[004] Polymer particles as described can comprise: at least one polyether including at least two functional groups and optionally at least one monomer. Particles as described herein can have various sizes depending on a particular use, but generally can have diameters less than about 1,200 μm .

[005] Further, in other embodiments, polymer particles are described comprising: at least one derivatized poly(ethylene glycol) macromer, poly(propylene glycol) macromer, poly(tetramethylene oxide) macromer, or a combination thereof at a concentration of between about 15% w/w and about 50% w/w; and at least one monomer that is not n-isopropyl acrylamide.

[006] The polymer particles can have an average diameter between about 40 μm and about 1,200 μm .

[007] The polymer particles can further include at least one monomer. The at least one monomer can include a functional group. The functional group can be an acrylate, acrylamide, methacrylate, or methacrylamide. Further, the at least one monomer can be glycerol

monomethacrylate, amino ethyl methacrylate, 3-sulfopropyl acrylate, amino propyl methacrylate, or a combination thereof.

[008] In one embodiment, the at least one monomer is glycerol monomethacrylate at a concentration of about 68% w/w. In another embodiment, the at least one monomer is 3-sulfopropyl acrylate at a concentration of about 59% w/w. In still another embodiment, the at least one monomer is amino propyl methacrylate at a concentration of about 1% w/w. In yet another embodiment, the at least one monomer is amino ethyl methacrylate at a concentration of about 3% w/w.

[009] In some embodiments, the at least one derivatized poly(ethylene glycol) macromer can be poly(ethylene glycol) diacrylamide, poly(ethylene glycol) diacrylate, poly(ethylene glycol) dimethacrylate, poly(ethylene glycol) dimethacrylamide, or a combination thereof.

[0010] Methods of making polymer particles as described herein are also disclosed. These methods can comprise: reacting an aqueous based prepolymer solution including at least one derivatized polyether macromer and an initiator in an oil to form polymer particles; wherein said polymer particle has a diameter less than about 1,200 μm .

[0011] In some embodiments of the methods, the oil is a mineral oil. In other embodiments of the methods, the initiator is ammonium persulfate, tetramethylethylene diamine, or a combination thereof.

[0012] In embodiments of the methods and particles described herein, the compositions and particles do not include n-isopropyl acrylamide.

Brief Description of the Drawings

[0013] Figure 1 illustrates a plot of average drug loading of particles charged with doxorubicin or irinotecan.

[0014] Figure 2 illustrates a plot of average drug elution from particles at 22 hours after *in situ*.

[0015] Figure 3 illustrates a plot of particle compressibility at 30% deformation.

[0016] Figure 4 illustrates another plot of particle compressibility at 30% deformation.

[0017] Figure 5 illustrates a plot of particle time in suspension.

[0018] Figure 6 illustrates a plot of drug loaded particle time in suspension.

Detailed Description

[0019] Described herein generally are particles made of polymer material including a reaction product of at least one polyether macromer, optionally at least one monomer, optionally at least one multifunctional crosslinker, and optionally at least one initiator. The particles can be referred to herein as being microparticles, microspheres, microbeads, spheres, microembolis, embolics, and the like. The particles can have diameters less than about 1,200 μm . The particles can also be compressible, biostable, and/or durable for ease of delivery.

[0020] The particles can be formed from a prepolymer solution or mixture comprising: (i) one or more polyether macromers that contain at least two functional groups amenable to polymerization, (ii) optionally one or more monomers, and (iii) optionally one or more multifunctional crosslinkers. In some embodiments, a polymerization initiator may be utilized.

[0021] In one embodiment, the macromer includes a plurality of functional groups suitable or amenable to polymerization. In some embodiments, the macromer can be linear. In other embodiments, the macromer can have one or more branches. In still other embodiments, the macromer can be an ethylenically unsaturated macromer. Macromers can include polyethers. Polyether macromers can include linear or branched poly(ethylene glycol), poly(propylene glycol), poly(tetramethylene oxide), derivatives thereof, or combinations thereof.

[0022] Macromers described herein can have molecular weights of about 200 grams/mole, 400 grams/mole, 600 grams/mole, 800 grams/mole, 1,000 grams/mole, 2,000 grams/mole, 3,000 grams/mole, 4,000 grams/mole, 5,000 grams/mole, 10,000 grams/mole, 15,000 grams/mole, 20,000 grams/mole, 25,000 grams/mole, 30,000 grams/mole, 35,000 grams/mole, between about 200 grams/mole and about 35,000 grams/mole, between about 200 grams/mole and about 30,000 grams/mole, between about 1,000 grams/mole and about 15,000 grams/mole, at least about 200 grams/mole, at most about 30,000 g/mole, or at most about 35,000 grams/mole. In one embodiment, macromers can have a molecular weight of about 10,000 g/mole.

[0023] Derivatives of these polyethers can be prepared to render them amenable to polymerization. While any type of chemistry can be utilized, for example nucleophile/N-hydroxysuccinimide esters, nucleophile/halide, vinyl sulfone/acrylate or maleimide/acrylate; a preferred chemistry is free radical polymerization. As such, polyethers with a plurality of ethylenically unsaturated groups, such as acrylate, acrylamide, methacrylate, methacrylamide, and vinyl, can be used. In one embodiment, a polyether macromer can be poly(ethylene glycol) diacrylamide with a molecular weight of about 10,000 g/mole.

[0024] In another embodiment the macromer is poly(ethylene glycol) diacrylamide, poly(ethylene glycol) diacrylate, poly(ethylene glycol) dimethacrylate, poly(ethylene glycol) dimethacrylamide, derivatives thereof, or combinations thereof.

[0025] Macromers can be included at a concentration in the solution of about 0% w/w, about 1% w/w, about 2% w/w, about 3% w/w, about 4% w/w, about 5% w/w, about 6% w/w, about 7% w/w, about 8% w/w, about 9% w/w, about 10% w/w, about 11% w/w, about 12% w/w, about 13% w/w, about 14% w/w, about 15% w/w, about 16% w/w, about 17% w/w, about 18% w/w, about 19% w/w, about 20% w/w, about 35% w/w, about 30% w/w, about 35% w/w, about 40% w/w, about 45% w/w, about 50% w/w, about 60% w/w, about 70% w/w, between about 5% w/w and about 10% w/w, between about 5% w/w and about 20% w/w, between about 5% w/w and about 25% w/w, between about 5% w/w and about 15% w/w, between about 6% w/w and about 8% w/w, or between about 14% w/w and about 16% w/w. In some embodiments, a macromer need not be used.

[0026] In one embodiment, the macromer can be included at a concentration of about 7% w/w in the solution.

[0027] In one embodiment, the macromer can be included at a concentration of about 15% w/w in the solution.

[0028] In some embodiments, if one of the monomer(s) and/or macromers(s) is a solid, a solvent can be used to form a solution from which the particles for use as embolics can be prepared. If liquid monomers and macromers are utilized, a solvent may not be required. In some embodiments, even when using liquid monomers and/or macromers, a solvent may still be used. Solvents may include any liquid that can dissolve or substantially dissolve a polyether macromer, monomers, multifunctional crosslinkers, and/or initiators. Any aqueous or organic solvent may be used that dissolves the desired monomer(s), macromer(s), multifunctional crosslinker(s) and/or polymerization initiators. In one embodiment, the solvent can be water. Additionally, solutes, e.g. sodium chloride, may be added to the solvent to increase the rate of polymerization. Solvent concentration can be varied to alter the compressibility of the embolic particle, allowing for delivery through a catheter of smaller inner diameter than the diameter of the particle.

[0029] Solvent concentrations can be about 25% w/w, about 35% w/w, about 45% w/w, about 55% w/w, about 65% w/w, about 75% w/w, about 85% w/w, about 95% w/w, between about 40% w/w and about 80% w/w, between about 30% w/w and about 90% w/w, or between about

50% w/w and about 70% w/w of the solution. In one embodiment, the solvent concentration can be about 50% w/w, about 51% w/w, about 52% w/w, about 53% w/w, about 54% w/w, about 55% w/w, about 56% w/w, about 57% w/w, about 58% w/w, about 59% w/w, or about 60% w/w. In another embodiment, the solvent concentration can be about 65% w/w, about 66% w/w, about 67% w/w, about 68% w/w, about 69% w/w, about 70% w/w, about 71% w/w, about 72% w/w, about 73% w/w, about 74% w/w, or about 75% w/w.

[0030] In one embodiment, the solvent concentration can be about 57% w/w.

[0031] In one embodiment, the solvent concentration can be about 70% w/w.

[0032] In one embodiment, the solvent concentration can be about 75% w/w.

[0033] In general, monomers can contain moieties such as acrylate, acrylamide, methacrylate, methacrylamide or other moieties amenable to polymerization. In one embodiment, the polymer particles are comprised of one or more macromers combined with one or more monomers.

[0034] Optionally, one or more monomers can be added to the polyether macromer to impart desired chemical and/or mechanical properties to the polymer particle. If the binding of positively charged drugs or other materials is desired, monomers with negatively charged moieties, e.g. carboxylic acids, can be polymerized into the particles. Acidic unsaturated monomers can include, but are not limited to, acrylic acid, methacrylic acid, 3-sulfopropyl acrylate, 3-sulfopropyl methacrylate, derivatives thereof, combinations thereof, and salts thereof. If the binding of negatively charged drugs is desired, monomers with positively charged moieties, e.g. amines, can be polymerized into the particles. Basic monomers can include amino ethyl methacrylate, 2-amino ethyl methacrylate, amino propyl methacrylamide, derivatives thereof, combinations thereof, and salts thereof.

[0035] Monomers including positive or negative moieties can be present in solution at concentrations of about 0.5% w/w, about 1% w/w, about 2% w/w, about 3% w/w, about 4% w/w, about 5% w/w, about 6% w/w, about 7% w/w, about 8% w/w, about 9% w/w, about 10% w/w, about 15% w/w, about 20% w/w, about 21% w/w, about 22% w/w, about 23% w/w, about 24% w/w, about 25% w/w, about 26% w/w, about 27% w/w, about 28% w/w, about 29% w/w, about 30% w/w, about 40% w/w, about 50% w/w, about 55% w/w, about 60% w/w, about 65% w/w, about 70% w/w, about 80% w/w, between about 1% w/w and about 10% w/w, between about 1% w/w and about 5% w/w, between about 15% w/w and about 35% w/w, or between about 20% w/w and about 30% w/w.

[0036] In one embodiment, a monomer(s) including charged moieties can be included at a concentration of about 14% w/w in the solution.

[0037] In one embodiment, a monomer(s) including charged moieties can be included at a concentration of about 24% w/w in the solution.

[0038] In one embodiment, 2-amino ethyl methacrylate can be included at a concentration of about 0.7% w/w in the solution.

[0039] In one embodiment, amino propyl methacrylamide can be included at a concentration of about 0.5% w/w in the solution.

[0040] In one embodiment, the monomer is not n-isopropyl acrylamide. In other embodiments, the polymer particles described herein do not include n-isopropyl acrylamide.

[0041] If desired, uncharged, reactive moieties can be introduced into the particles. For example, hydroxyl groups can be introduced into the particles with the addition of 2-hydroxyethyl acrylate, 2-hydroxyethyl methacrylate, glycerol monomethacrylate, glycerol monoacrylate, sorbitol monomethacrylate, sorbitol monoacrylate, a carbohydrate similar to sorbitol and amenable to polymerization, derivatives thereof, or combinations thereof. Alternatively, uncharged, relatively un-reactive moieties can be introduced into the particles. For example, acrylamide, methacrylamide, methyl methacrylate, derivatives thereof, or combinations thereof can be added to the polyether macromer. In some embodiments, the monomer(s) can be selected to vary the number of hydroxyl groups in the polymeric particles to enable the particles to remain suspended in radiopaque contrast solution used in the preparation of the particle for clinical use.

[0042] Such uncharged moieties if included can be present in the final particle (not including solvents, initiators, and salts) at about 0% w/w, about 10% w/w, about 20% w/w, about 30% w/w, about 40% w/w, about 50% w/w, about 60% w/w, about 61% w/w, about 62% w/w, about 63% w/w, about 64% w/w, about 65% w/w, about 66% w/w, about 67% w/w, about 68% w/w, about 69% w/w, about 70% w/w, about 71% w/w, about 72% w/w, about 73% w/w, about 74% w/w, about 75% w/w, about 80% w/w, about 90% w/w, between about 50% w/w and about 90% w/w, between about 60% w/w and about 70% w/w, between about 65% w/w and about 70% w/w, or between about 67% w/w and about 69% w/w.

[0043] In one embodiment, an uncharged moiety can be present at about 68% w/w of the final particle.

[0044] In one embodiment, the uncharged moiety can be glycerol monomethacrylate.

[0045] Adding multifunctional crosslinkers containing more than one moiety amenable to polymerization can create a more cohesive hydrogel polymer by adding crosslinking to the molecular structure. In some embodiments the polymer particles are comprised of a macromer combined with one or more multifunctional crosslinkers such as, but not limited to, glycerol dimethacrylate, glycerol diacrylate, sorbitol dimethacrylate, sorbitol acrylate, a derivatized carbohydrate similar to sorbitol, derivatives thereof, or combinations thereof. In a preferred embodiment the multifunctional crosslinker is N,N'-methylenebisacrylamide.

[0046] If used, a crosslinker can be present in the solution used to form the particles at a concentration of about 0.1% w/w, about 0.25% w/w, about 0.5% w/w, about 0.75% w/w, about 1.0% w/w, about 1.25% w/w, about 1.5% w/w, about 1.75% w/w, about 2% w/w, about 3% w/w, about 4% w/w, about 5% w/w, about 6% w/w, about 7% w/w, about 10% w/w, about 20% w/w, about 25% w/w, about 30% w/w, between about 0% w/w and about 10% w/w, between about 0% w/w and about 2% w/w, between about 0.5% w/w and about 1.5% w/w, between about 0.25% w/w and about 1.75% w/w, or between about 0.1% w/w and about 2% w/w.

[0047] In one embodiment, a crosslinker is not used.

[0048] In one embodiment, a crosslinker can be present at about 1% w/w.

[0049] In one embodiment, the crosslinker can be N,N'-methylenebisacrylamide.

[0050] Any amounts of macromer(s), monomer(s), and multifunctional crosslinker(s) can be used in the solution used to form the particles that allows for a desired particle. Total concentration of reactive compounds or solids in the solution can be about 5% w/w, about 10% w/w, about 11% w/w, about 12% w/w, about 13% w/w, about 14% w/w, about 15% w/w, about 16% w/w, about 17% w/w, about 18% w/w, about 19% w/w, about 20% w/w, about 21% w/w, about 22% w/w, about 23% w/w, about 24% w/w, about 25% w/w, about 30% w/w, about 31% w/w, about 32% w/w, about 33% w/w, about 34% w/w, about 35% w/w, about 36% w/w, about 37% w/w, about 38% w/w, about 39% w/w, 40% w/w, about 50% w/w, about 60% w/w, about 70% w/w, between about 10% and 60%, between about 15% w/w and about 50% w/w, or between about 20% w/w and about 40% w/w.

[0051] In one embodiment, the total concentration of reactive compounds in the solution can be about 20% w/w.

[0052] In one embodiment, the total concentration of reactive compounds in the solution can be about 41% w/w.

[0053] In one embodiment, polymer particles can be prepared from monomers having a single functional group and/or macromers having two or more functional groups suitable for polymerization. Functional groups can include those suitable to free radical polymerization, such as acrylate, acrylamide, methacrylate, and methacrylamide. Other polymerization schemes can include, but are not limited to nucleophile/N-hydroxysuccinimide esters, nucleophile/halide, vinyl sulfone/acrylate or maleimide/acrylate. Selection of the monomers is governed by the desired chemical and mechanical properties of the resulting particle.

[0054] Concentrations of macromers in the final desiccated particle products can be at a concentration of about 10% w/w, about 20% w/w, about 21% w/w, about 22% w/w, about 23% w/w, about 24% w/w, about 25% w/w, about 26% w/w, about 27% w/w, about 28% w/w, about 29% w/w, about 30% w/w, about 35% w/w, about 36% w/w, about 37% w/w, about 38% w/w, about 39% w/w, about 40% w/w, about 41% w/w, about 42% w/w, about 43% w/w, about 44% w/w, about 45% w/w, about 50% w/w, about 60% w/w, about 70% w/w, about 80% w/w, between about 15% w/w and about 60% w/w, between about 20% w/w and about 50% w/w, between about 25% w/w and about 45% w/w, between about 25% w/w and about 40% w/w, between about 35% w/w and about 45% w/w, between about 37% w/w and about 43% w/w, between about 39% w/w and about 41% w/w, between about 25% w/w and about 35% w/w, between about 26% w/w and about 30% w/w, or between about 27% w/w and about 29% w/w.

[0055] In one embodiment, the concentration of macromer(s) in the final desiccated particle products can be about 40% w/w.

[0056] In one embodiment, the concentration of macromer(s) in the final desiccated particle products can be about 27% w/w.

[0057] In one embodiment, poly(ethylene glycol) diacrylamide is present in the final desiccated particle products at about 40% w/w.

[0058] In one embodiment, poly(ethylene glycol) diacrylamide is present in the final desiccated particle products at about 27% w/w.

[0059] Concentrations of crosslinkers in the final desiccated particle products can be about 0.1% w/w, about 0.25% w/w, about 0.5% w/w, about 0.75% w/w, about 1% w/w, about 1.25% w/w, about 1.5% w/w, about 1.75% w/w, about 2% w/w, about 3% w/w, about 4% w/w, about

5% w/w, about 6% w/w, about 7% w/w, about 8% w/w, about 9% w/w, about 10% w/w, about 15% w/w, about 20% w/w, about 25% w/w, about 30% w/w, between about 0% w/w and about 5% w/w, between about 0% w/w and about 2% w/w, between about 0.5% w/w and about 1.5% w/w, between about 0.25% w/w and about 1.75% w/w, or between about 0.1% w/w and about 2% w/w.

[0060] In one embodiment, a crosslinker can be present in the final desiccated particle products at about 1% w/w.

[0061] In one embodiment, no crosslinker can be present in the final desiccated particle products.

[0062] In one embodiment, the crosslinker can be N,N'-methylenebisacrylamide.

[0063] Concentrations of one or more monomers in the final desiccated products can be about 10% w/w, about 15% w/w, about 20% w/w, about 25% w/w, about 30% w/w, about 40% w/w, about 50% w/w, about 55% w/w, about 60% w/w, about 61% w/w, about 62% w/w, about 63% w/w, about 64% w/w, about 65% w/w, about 66% w/w, about 67% w/w, about 68% w/w, about 69% w/w, about 70% w/w, about 71% w/w, about 72% w/w, about 73% w/w, about 74% w/w, about 75% w/w, about 80% w/w, between about 50% w/w and 80% w/w, between about 60% w/w and 70% w/w, between about 50% w/w and 80% w/w, between about 50% w/w and 75% w/w, between about 55% w/w and about 65% w/w, between about 57% w/w and 63% w/w, between about 59% w/w and 61% w/w, between about 63% w/w and 73% w/w, between about 65% w/w and 71% w/w, or between about 67% w/w and 69% w/w.

[0064] In one embodiment, the concentration of one or more monomers in the final desiccated products can be about 72% w/w.

[0065] In one embodiment, the concentration of one or more monomers in the final desiccated products can be about 60% w/w.

[0066] In one embodiment, the one or more monomers can be glycerol monomethacrylate and 2-amino ethyl methacrylate.

[0067] In one embodiment, glycerol monomethacrylate can be present at a concentration of about 68% w/w of the final desiccated products and 2-amino ethyl methacrylate can be present at a concentration of about 3% w/w of the final desiccated products.

[0068] In one embodiment, the one or more monomers can be 3-sulfopropyl acrylate and amino propyl methacrylamide.

[0069] In one embodiment, 3-sulfopropyl acrylate can be present at a concentration of about 59% w/w of the final desiccated products and amino propyl methacrylate can be present at a concentration of about 1% w/w of the final desiccated products

[0070] A skilled artisan understands how to calculate final concentrations based on amount in solvent already discussed.

[0071] The polymerization of the macromer and optional one or more monomers using free radical polymerization may require one or more initiators to start the reaction. The polymerization solution can be polymerized by reduction-oxidation, radiation, heat, or any other method known in the art. Radiation polymerization of the prepolymer solution can be achieved with ultraviolet light or visible light with suitable initiators or ionizing radiation (e.g. electron beam or gamma ray) without initiators. Polymerization can be achieved by application of heat, either by conventionally heating the solution using a heat source such as a heating well, or by application of infrared light to the prepolymer solution. In one embodiment, the polymerization method utilizes azobisisobutyronitrile (AIBN) or another water soluble AIBN derivative (2,2'-azobis(2-methylpropionamide) dihydrochloride). Other initiators useful according to the present description include N,N,N',N'-tetramethylethylenediamine, ammonium persulfate, benzoyl peroxides, and combinations thereof, including azobisisobutyronitriles.

[0072] In another embodiment, the initiator can be a combination of N,N,N',N'-tetramethylethylenediamine and ammonium persulfate at a concentration of about 0.25% w/w and about 2% w/w, respectively. In another embodiment, an initiator includes a combination of about 1.5% ammonium persulfate and about 0.3% N,N,N',N'-tetramethylethylenediamine. In still another embodiment, an initiator includes a combination of about 1.8% ammonium persulfate and about 0.2% N,N,N',N'-tetramethylethylenediamine.

[0073] The polymerization solution can be prepared by dissolving the reactants such as combinations of monomer(s), macromers(s), multifunctional crosslinkers(s), and optionally initiator(s) in a solvent. The particle embolics can be prepared by emulsion polymerization. A non-solvent for the monomer solution, typically mineral oil when the monomer solvent is water, is sonicated to remove any entrapped oxygen. The mineral oil is added to the reaction vessel. An overhead stirrer is placed in the reaction vessel. The reaction vessel is then sealed, degassed under vacuum, and sparged with an inert gas such as argon. The initiator component N,N,N',N'-tetramethylethylenediamine is added to the reaction vessel and stirring commenced. Ammonium persulfate is added to the polymerization solution and both are then added to the

reaction vessel, where the stirring suspends droplets of the polymerization solution in the mineral oil. A surfactant can be added before, after, or during the addition of the polymerization solution to stabilize the suspension. The rate of stirring can affect particle size, with faster stirring producing smaller particles. Stirring rates can be about 100 rpm, about 200 rpm, about 300 rpm, about 400 rpm, about 500 rpm, about 600 rpm, about 700 rpm, about 800 rpm, about 900 rpm, about 1,000 rpm, about 1,100 rpm, about 1,200 rpm, about 1,300 rpm, between about 200 rpm and about 1,200 rpm, between about 400 rpm and about 1,000 rpm, at least about 100 rpm, at least about 200 rpm, at most about 250 rpm, at most about 500 rpm, at most about 1,000 rpm, at most about 1,300 rpm, or at most about 1,200 rpm to produce particles with desired diameters.

[0074] Desired hydrated polymer particle diameters can be about 10 μm , about 20 μm , about 30 μm , about 40 μm , about 50 μm , about 100 μm , about 200 μm , about 300 μm , about 400 μm , about 500 μm , about 600 μm , about 700 μm , about 800 μm , about 900 μm , about 1,000 μm , about 1,100 μm , about 1,200 μm , about 1,300 μm , about 1,400 μm , about 1,500 μm , about 1,600 μm , about 1,700 μm , about 1,800 μm , about 1,900 μm , about 2,000 μm , between about 50 μm and about 1,500 μm , between about 100 μm and about 1,000 μm , at least about 50 μm , at least about 80 μm , less than about 600 μm , less than about 1,000 μm , less than about 1,200 μm , or less than about 1,500 μm . In one embodiment, the diameter is less than about 1,200 μm .

[0075] Polymerization can be allowed to proceed as long as necessary to produce particles with desired diameters. Polymerization can be allowed to proceed for about 1 hr, 2 hr, 2.5 hr, 3 hr, 4 hr, 5 hr, 6 hr, 7 hr, 8 hr, 9 hr, 10 hr, 11 hr, 12 hr, 18 hr, 24 hr, 48 hr, 72 hr, 96 hr, between about 1 hr and about 12 hr, between about 1 hr and about 6 hr, between about 4 hr and about 12 hr, between about 6 hr and about 24 hr, between about 12 hr and about 72 hr, or at least about 6 hours.

[0076] Polymerization can be run at a temperature to produce particles with desired diameters. Polymerization can be run at a temperature of about 10°C, about 15°C, about 20°C, about 25°C, about 30°C, about 35°C, about 40°C, about 45°C, about 50°C, about 60°C, about 70°C, about 80°C, about 90°C, about 100°C, between about 10°C and about 100°C, between about 10°C and about 30°C, at least about 20°C, at most about 100°C, or at about room temperature. In one embodiment, polymerization occurs at room temperature.

[0077] After the polymerization is complete, the polymer particles can be washed to remove any solute, mineral oil, un-reacted monomer(s), and/or unbound oligomers. Any solvent may be utilized and can include, but are not limited to hexane, acetone, alcohols, water and a surfactant, water, organic solvents, saline, and combinations thereof. In one embodiment, the washing solution is water. In another embodiment, the washing solution is a combination of hexane followed by water. In another embodiment, the washing solution is saline. In further embodiments, the washing solution is water and a surfactant.

[0078] The particles described herein can optionally be loaded or coated with a drug(s) and/or active agent(s) including, but not limited to anti-proliferative compounds, cytostatic compounds, toxic compounds, anti-inflammatory compounds, chemotherapeutic agents, analgesics, antibiotics, protease inhibitors, statins, nucleic acids, polypeptides, growth factors and delivery vectors including recombinant micro-organisms, liposomes, and the like. In one embodiment, particles can be loaded with doxorubicin. In another embodiment, the particles can be loaded with irinotecan. In still other embodiments, the particles can be loaded with irinotecan and doxorubicin.

[0079] Drugs and/or active agents can be eluted from the particles once implanted. Elution can occur over about 1 hour, about 2 hours, about 5 hours, about 10 hours, about 12 hours, about 18 hours, about 24 hours, about 2 days, about 3 days, about 4 days, about 5 days, about 7 days, about 2 weeks, about 1 month, about 2 months, about 6 months, about 9 months, about 1 year, or about 2 years. For example, about 1 mg, about 2 mg, about 3 mg, about 4 mg, about 5 mg, about 10 mg, about 20 mg, about 30 mg, about 40 mg, or about 50 mg of drug or active agent can be eluted from the particles in a 22 hour or 24 hour period.

[0080] Optionally, the washed polymer particles can be dyed prior to, during, or after polymerization to permit visualization before injection into a microcatheter. Any of the dyes from the family of reactive dyes which bond covalently to the particle embolics can be used. Dyes can include, but are not limited to, reactive blue 21, reactive orange 78, reactive yellow 15, reactive blue No. 19, reactive blue No.4, C.I. reactive red 11, C.I. reactive yellow 86, C.I. reactive blue 163, C.I. reactive red 180, C.I. reactive black 5, C.I. reactive orange 78, C.I. reactive yellow 15, C.I. reactive blue No. 19, C.I. reactive blue 21, any of the color additives. Some color additives are approved for use by the FDA part 73, subpart D. In other embodiments, a dye that can irreversibly bond to the polymer matrix of the particle embolic is utilized.

[0081] A dye bath can be made by dissolving sodium carbonate and the desired dye in water. Particle embolics are added to the dye bath and stirred. After the dyeing process, any unbound dye is removed through washing. After dyeing and washing, the particles can be packaged into vials or syringes, and sterilized.

[0082] The particles described herein can be sterilized without substantially degrading the polymer. After sterilization, at least about 50%, about 60%, about 70%, about 80%, about 90%, about 95% about 99% or about 100% of the polymer can remain intact. In one embodiment, the sterilization method can be autoclaving and can be utilized before administration.

[0083] The final polymer particle preparation can be delivered to the site to be embolized via a catheter, microcatheter, needle, or similar delivery device. A radiopaque contrast agent can be thoroughly mixed with the particle preparation in a syringe and injected through a catheter until blood flow is determined to be occluded from the site by interventional imaging techniques.

[0084] The particles can remain substantially stable once injected. For example, the polymer particles can remain greater than about 60%, about 70% about 80%, about 90%, about 95%, about 99% or about 100% intact after about 5 days, about 2 weeks, about 1 month, about 2 months, about 6 months, about 9 months, about a year, about 2 years, about 5 years, about 10 years, or about 20 years.

[0085] The polymer particles described herein can be compressible yet durable enough not to break apart or fragment. Substantially no change in circularity or diameter of particles may occur during delivery through a microcatheter. In other words, after delivery through a microcatheter, the polymer particles described herein remain greater than about 60%, about 70% about 80%, about 90%, about 95%, about 99% or about 100% intact.

[0086] In one embodiment, particles before delivery through a microcatheter can have an average diameter of 0.221 ± 0.054 mm and a post-delivery diameter of 0.226 ± 0.049 mm. These particles can also exhibit a pre-delivery average formcircle of 0.98 ± 0.04 and a post-delivery formcircle of 0.98 ± 0.02 .

[0087] In another embodiment, particles before delivery through a microcatheter can have an average diameter of 395 ± 25 μm and a post-delivery diameter of 401 ± 30 μm . These particles can also exhibit a pre-delivery average formcircle of 0.98 ± 0.01 and a post-delivery formcircle of 0.98 ± 0.04 .

[0088] Further, the particles can be cohesive enough to stick to tissue and/or remain in place through friction with the tissue. In other embodiments, the particles can act as a plug in a vessel held in place by the flow and pressure of blood.

[0089] In one example embodiment, a polymer particle can include a reaction product of a polyether, glycerol monomethacrylate, bisacrylamide, and aminoethyl methacrylate. In another example embodiment, a desiccated polymer particle can include a polyether at about 28% w/w, glycerol monomethacrylate at about 68% w/w, bisacrylamide at about 1% w/w, and aminoethyl methacrylate at about 3% w/w.

[0090] On another example embodiment, a desiccated polymer particle can include a reaction product of a polyether, aminopropyl methacrylamide, and sulfopropyl acrylate. In another embodiment, a polymer particle can include a polyether at about 40%, aminopropyl methacrylamide at about 1%, and sulfopropyl acrylate at about 59%.

Example 1

Preparation of a polyether macromer

[0091] Polyethylene glycol 10,000 (450 g) was dried by azeotropic distillation with 2,400 mL of toluene. Then, 200 mL of dichloromethane, 15.6 mL of triethylamine, and 10.4 mL of mesyl chloride were added and the solution was stirred for 4 hr. The solution was filtered, the product precipitated in diethyl ether, and collected by filtration. The resulting product was vacuum dried, added to 3,600 mL of 25% of ammonium hydroxide, and stirred closed for 4 days then open for 3 days. The water was removed and the product dried by azeotropic distillation with toluene. To the resulting poly(ethylene glycol) diamine in toluene, 15.6 mL of triethylamine and 10.9 mL of acryloyl chloride were added and the reaction was stirred for 4 hr. The resulting solution was filtered, precipitated in ether and the solvent removed, yielding PEG 10,000 diacrylamide.

Example 2

Particle embolic prepared with a polyether macromer and a plurality of monomers

[0092] The prepolymer formulation is prepared by dissolving 0.25 g 2-aminoethyl methacrylate, 2.125 g poly(ethylene glycol) diacrylamide from Example 1, 5.1 g glycerol monomethacrylate, 0.07 g N,N'-methylenebisacrylamide, and 1.2 g sodium chloride in 20 mL of de-ionized water. The solution was filtered into a clean 120 mL amber jar. An initiator solution was made by dissolving 1.0 g ammonium persulfate in 2.0 g of de-ionized water. Then, 1.0 mL of the

ammonium persulfate solution was added to the filtered prepolymer solution, and the solution was vacuum degassed for 2 min, and the vacuum was replaced with argon. 500 mL of mineral oil were sonicated for 1 hr, and then added to a sealed reaction vessel with an overhead stirring element. The vessel was vacuum degassed for 1 hr, and then the vacuum replaced with argon. Then, 1 mL of N,N,N',N'-tetramethylethylenediamine was added to the reaction vessel and overhead stirring started at 200 rpm. The prepolymer formulation was added to the reaction vessel. After 1 min, 0.1 mL of SPAN® 80 (sorbitan monooleate, Croda International Plc, East Yorkshire, purchased from Sigma-Aldrich Company LLC, St. Louis, MO) was added and the preparation was allowed to polymerize for at least 2 hr. The oil was decanted off and the particles were poured into a separatory funnel with 1,000 mL of de-ionized water. The bottom water/sphere layer was collected. The particles were washed with several 300 mL portions of hexane. After the final wash, all hexane was decanted off and the particles were washed several times with fresh 300 mL portions of de-ionized water and stored in a capped bottle with de-ionized water.

Example 3

Particle embolic prepared with a polyether macromer

[0093] A prepolymer formulation was prepared by dissolving 15.8 g poly(ethylene glycol) diacrylamide and 6.0 g of sodium chloride in 30.0 g of de-ionized water. Then, 10 g of this solution was filtered. An initiator solution was made by dissolving 1.0 g ammonium persulfate in 2.0 grams of de-ionized water. The ammonium persulfate solution (1 mL) was added to the filtered prepolymer solution, the solution was vacuum degassed for 2 min, and the vacuum was replaced with argon. Then, 500 mL of mineral oil was sonicated for 2 hr, and then added to a sealed reaction vessel with 0.5 mL of SPAN® 80 and an overhead stirring element. The vessel was vacuum degassed for 1 hr, and then the vacuum replaced with argon. Then, 1 mL of N,N,N',N'-tetramethylethylenediamine was added to the reaction vessel and overhead stirring started at 450 rpm. The 10 g of prepolymer formulation was added to the reaction vessel via syringe and allowed to polymerize for at least 8 hr.

Example 4

Particle embolic prepared with a polyether macromer and monomer

[0094] A prepolymer formulation was prepared by dissolving 9.2 g poly(ethylene glycol) diacrylamide from Example 1, 13.8 g 3-sulfopropyl acrylate potassium salt, and 0.248 g n-(3-aminopropyl)methacrylamide hydrochloride in 34.4 g of deionized water. Then, the solution was

filtered. An initiator solution was made by dissolving 1.0 g ammonium persulfate in 2.0 g of deionized water. Ammonium persulfate solution (0.85 mL) was added to the filtered prepolymer solution, the solution was then vacuum degassed for 2 min, and added to a sealed reaction vessel with 0.14 mL of SPAN® 80 and an overhead stirring element. The vessel was vacuum degassed for 1 hr, and then the vacuum was replaced with argon. N,N,N'N'-tetramethylethylenediamine (2 mL) was added to the reaction vessel and overhead stirring started at 400 rpm. The prepolymer formulation was added to the reaction vessel via syringe and allowed to polymerize for at least 8 hr.

Example 5

Purification of particle embolics

[0095] The mineral oil was decanted from the reaction vessel, and the polymer particles were washed three times with fresh portions of hexane to remove the mineral oil. The particles were then transferred to a separatory funnel with water, and separated from residual mineral oil and hexane. Next, the particles are washed with de-ionized water to remove any residual reactants. The particles can be packaged in 0.9% saline solution for the final preparation or dyed.

Example 6

Dying of particle embolics

[0096] To dye the particles, 50 g of sodium carbonate and 0.1 g reactive black 5 dye (Sigma-Aldrich Co. LLC, St. Louis, MO) were dissolved in 1,000 mL of de-ionized water. Then, 500 mL of drained particles were added and allowed to stir for 1 hr. The dyed particle preparation was washed with de-ionized water until all residual dye was removed. The particles can then be packaged in 0.9% saline solution for the final preparation.

Example 7

Drug loading particle embolics

[0097] Particles prepared in Example 4 were sieved to 100-300 μm and loaded with the drug doxorubicin. Four 1 mL particle aliquots were loaded with 37.5 mg of doxorubicin in solution. The solution was analyzed by an Agilent 1100 HPLC system before and after adding particles to determine amount of drug sequestered by the particles from the solution.

[0098] Loading particles with doxorubicin: 37.5 mg of doxorubicin was dissolved in 2 mL of de-ionized water. A drop of the drug solution was saved for LC analysis. The saline storage fluid

was removed from a 1 mL vial of particles and the drug solution added to the vial of particles. After 18 hours, a sample of the solution was analyzed, and the drug loading was determined by comparing peak area of drug present in solution before and after adding particles.

[0099] Particles prepared in Example 4 were similarly loaded with the drug irinotecan. Four 1 mL aliquots of particles sized 100–300 μm were loaded with 50.0 mg of irinotecan dissolved in citrate buffer solution. The solution was analyzed before and after adding particles.

[00100] Loading particles with irinotecan: 50.0 mg of irinotecan was dissolved in 5 mL of pH 4 citrate buffer solution. A drop of the solution was saved for LC analysis. The saline storage solution was removed from a 1 mL vial of particles and the irinotecan solution was added. After 18 hr a sample of the solution was analyzed and the drug loaded determined by comparing the peak area of drug present in solution before and after adding particles (Figure 1).

Example 8

Drug elution of particle embolic

[00101] Particles prepared in example 4 were aliquoted into six 1 mL samples and loaded with drug per Example 7. Excess drug solution was removed from the sample of particles after an 18 hr incubation period. The samples were placed into the dissolution chambers of a Sotax CE7 Smart USP 4 dissolution apparatus. The elution media of saline solution was run at 37.5°C for 22 hours with samples taken at various time points. The samples were analyzed by an Agilent 1100 HPLC system and milligrams of drug eluted calculated. Results are illustrated in Figure 2.

Example 9

Compressive modulus of particle embolic

[00102] Particles created as described herein are often delivered through a catheter with a smaller inner lumen than the average outer diameter of the particles. The compressive modulus required to compress a sample of particles to 30% of their a nominal diameter was tested on a Instron 5543 materials testing machine equipped with a 5 N load cell. To test a sample, an approximately 1 cm circular monolayer of spherical particles stored in saline, nominally sized 800 μm diameter, was placed on a flat lower platen. Excess saline was carefully blotted away with a lab wipe. A flat probe compressed the beads to 30% of the beads' average diameter and the Young's modulus was recorded. The test was repeated 3-5 times for each sample.

[00103] Two samples of spherical particles nominally sized 800 μm diameter from Example 2 and Example 3 were tested as described previously and the results are illustrated in Figure 3.

[00104] Two 1 mL aliquots of spherical particles nominally sized 800 μm from Example 4 were loaded with irinotecan and doxorubicin per Example 7. The compressibility was measured before and after loading with drug and the results are illustrated in Figure 4.

Example 10

Determination of suspension properties of particles in radiopaque contrast

[00105] Particle embolics can be prepared for delivery in radiopaque contrast solution. A homogeneous mixture of particles suspended in contrast solution can permit a uniform injection of beads through a catheter. To test suspension characteristics of embolic particles, a 10 mL syringe with 1 mL of particles and 2 mL of buffered saline were attached to a 3-way stopcock. Another syringe containing 3 mL of OMNIPAQUE® 300 (iohexol formulated as 300 mg of iodine per mL, GE Healthcare, Norway) contrast was attached to the stopcock. The contrast was injected into the particle syringe and a timer was started. The syringe containing contrast, saline, and particles was removed from the stopcock and capped with a syringe tip cap. The contents were mixed by inverting the syringe repeatedly. At a time point, the mixing was stopped and a second timer started. The time taken for particles to remain only in 2/3 of the syringe was recorded. Mixing by inverting was continued between measurements.

[00106] Particles from Example 2 and Example 3, nominally sized 800 μm diameter were tested using the method described above and results are illustrated in Figure 5.

[00107] Particles from Example 4, nominally sized 400 μm and drug loaded with doxorubicin were tested for suspension characteristics. To do so, 1 mL of the drug loaded particles and the solution they were drug loaded in were placed in a 10 mL syringe. Excess drug solution was expressed from the syringe and the syringe was attached to a 3-way stopcock. A second 10 mL syringe containing OMNIPAQUE® 300 contrast was attached to the 3-way stopcock. Enough contrast solution was added to the syringe containing the particles to make a total volume of 6 mL and the timer was started. The syringe containing contrast and particles was removed from the stopcock and capped with a syringe tip cap. The contents were mixed by inverting the syringe repeatedly. At a time point, the mixing was stopped and a second

timer started. The time taken for particles to remain only in 2/3 of the syringe was recorded. Mixing by inverting was continued between measurements.

[00108] Particles from Example 4, nominally sized 400 μm and drug loaded with irinotecan were tested for suspension characteristics. To do so, 1 mL of the drug loaded particles and drug loading solution were placed in a 10 mL syringe. Excess drug solution was expressed from the syringe and the syringe was attached to a 3-way stopcock. A second 10 mL syringe containing de-ionized water was attached to the 3-way stopcock and water was injected into the syringe containing the drug loaded particles to bring the total volume to 3 mL. The syringe containing water was removed and a syringe containing OMNIPAQUE® 300 contrast was attached to the 3-way stopcock. Enough contrast solution was added to the syringe containing the particles to make a total volume of 6 mL and the timer was started. The syringe containing contrast and particles was removed from the stopcock and capped with a syringe tip cap. The contents were mixed by inverting the syringe repeatedly. At various time points, the mixing was stopped and a second timer started. The time taken for particles to remain only in 2/3 of the syringe was recorded. Mixing by inverting was continued between measurements.

[00109] Results for particles loaded with doxorubicin and irinotecan are illustrated in Figure 6.

Example 11

Determination of durability of particle embolics after catheter delivery

[00110] To simulate use, a 1 mL sample of particles prepared in Example 3 was injected through a Headway 21 catheter (0.021", 533 μm inner lumen). One milliliter of particles with 2 mL of saline in a syringe were attached to a 3-way stopcock. The catheter and a syringe containing 3 mL of OMNIPAQUE® 300 contrast solution were also attached to the 3-way stopcock. The stopcock was opened between the syringes to mix the beads, saline, and contrast. This particle preparation was then contained in one syringe, the other syringe removed, and a 1 mL injection syringe attached to the stopcock in line with the catheter. The particles were delivered through the catheter into a dish. An image was acquired using a Zeiss Axio Imager A1 microscope and analyzed using Zeiss Axiovision image analysis software. The circularity (closeness to a circle) was scored and statistical analysis using a Student's *t*-test indicated no difference in the spherical particles before and after delivery, with no damaged spheres observed.

Pre-Delivery Table

Sphere #	Formcircle	Diameter (μm)
1	0.93	481
2	0.97	372
3	0.97	411
4	0.97	390
5	0.97	373
6	0.97	407
7	0.97	405
8	0.97	388
9	0.98	412
10	0.98	393
11	0.98	414
12	0.98	388
13	0.98	386
14	0.98	360
15	0.98	433
16	0.98	380
17	0.98	414
18	0.98	404
19	0.98	361
20	0.98	385
21	0.98	376
22	0.98	387
23	0.98	373
24	0.98	376
25	0.98	396
26	0.98	443
27	0.98	380
28	0.98	380
29	0.99	412
30	0.99	381

Post-Delivery Table

Sphere #	Formcircle	Diameter (μm)	Sphere #	Formcircle	Diameter (μm)
1	0.7	564	41	0.99	417
2	0.83	432	42	0.99	411
3	0.85	458	43	0.99	398
4	0.91	455	44	0.99	439
5	0.92	411	45	0.99	419
6	0.93	375	46	0.99	386
7	0.94	475	47	0.99	418
8	0.95	463	48	0.99	368
9	0.96	414	49	0.99	420
10	0.97	391	50	0.99	375
11	0.97	388	51	0.99	391
12	0.97	391	52	0.99	392
13	0.97	397	53	0.99	418
14	0.97	376	54	0.99	384
15	0.98	395	55	0.99	369
16	0.98	378	56	0.99	396
17	0.98	400	57	0.99	408
18	0.98	359	58	1	399
19	0.98	380	59	1	387
20	0.98	381	60	1	395
21	0.98	416	61	1	391
22	0.98	412	62	1	388
23	0.98	410	63	1	391
24	0.98	418	64	1	370
25	0.98	382	65	1	409
26	0.98	404	66	1	364
27	0.98	409	67	1	392
28	0.98	411	68	1	364
29	0.98	387	69	1	415
30	0.98	376	70	1	371
31	0.98	416	71	1	423
32	0.98	426	72	1	380
33	0.99	392	73	1	406
34	0.99	424	74	1	428

Sphere #	Formcircle	Diameter (µm)	Sphere #	Formcircle	Diameter (µm)
35	0.99	388	75	1	364
36	0.99	390	76	1	367
37	0.99	390	77	1	371
38	0.99	391	78	1	381
39	0.99	385	79	1	384
40	0.99	386	80	1	389
			81	1	408

Summary Table

Average Diameter Pre-delivery, µm	395 ± 25
Average Diameter Post-delivery, µm	401 ± 30
Average Formcircle Pre-delivery	0.98 ± 0.01
Average Formcircle Post-delivery	0.98 ± 0.04

Example 12

Determination of durability of drug loaded particle embolics after delivery

[00111] To simulate use of a drug loaded particle embolic, 1 mL sample of particles prepared in Example 4 was injected through a Headway 17 catheter (0.017", 432 µm inner lumen). Then, a syringe charged with 1 mL of particles loaded with doxorubicin per example 7 with 2 mL of de-ionized water was attached to a 3-way stopcock. The catheter and a syringe containing 3 mL of OMNIPAQUE® 300 radiopaque contrast solution were also attached to the 3-way stopcock. The stopcock was opened between the syringes to mix the beads, saline, and contrast. This particle preparation was then contained in one syringe, the other syringe removed, and a 1 mL injection syringe attached to the stopcock in line with the catheter. The particles were delivered through the catheter into a dish. An image was acquired using a Zeiss Axio Imager A1 microscope and analyzed using Zeiss Axiovision image analysis software. The circularity (closeness to circle) was scored and statistical analysis using a Student's *t*-test indicated no difference in the spherical particles before and after delivery, with no damaged spheres observed.

Pre-Delivery Table

Sphere #	Formcircle	Diameter (mm)
----------	------------	---------------

Sphere #	Formcircle	Diameter (mm)
1	0.73	0.173
2	0.95	0.148
3	0.95	0.266
4	0.96	0.265
5	0.96	0.203
6	0.96	0.159
7	0.97	0.221
8	0.97	0.263
9	0.97	0.176
10	0.98	0.305
11	0.98	0.2
12	0.98	0.172
13	0.98	0.193
14	0.98	0.237
15	0.98	0.226
16	0.98	0.202
17	0.98	0.277
18	0.98	0.203
19	0.98	0.288
20	0.99	0.167
21	0.99	0.213
22	0.99	0.176
23	0.99	0.203
24	0.99	0.301
25	0.99	0.27
26	0.99	0.199
27	0.99	0.247
28	0.99	0.208
29	0.99	0.212
30	0.99	0.391
31	0.99	0.201
32	0.99	0.177
33	0.99	0.175
34	0.99	0.158
35	1	0.243
36	1	0.198

Sphere #	Formcircle	Diameter (mm)
37	1	0.299
38	1	0.147
39	1	0.19
40	1	0.189
41	1	0.324

Post-Delivery Table

Sphere #	Formcircle	Diameter (mm)	Sphere #	Formcircle	Diameter (mm)
1	0.89	0.252	34	0.98	0.173
2	0.93	0.211	35	0.98	0.224
3	0.94	0.176	36	0.98	0.13
4	0.94	0.26	37	0.98	0.266
5	0.95	0.208	38	0.98	0.34
6	0.95	0.298	39	0.98	0.221
7	0.95	0.23	40	0.98	0.134
8	0.96	0.233	41	0.99	0.212
9	0.96	0.186	42	0.99	0.291
10	0.97	0.274	43	0.99	0.298
11	0.97	0.142	44	0.99	0.206
12	0.97	0.302	45	0.99	0.315
13	0.97	0.211	46	0.99	0.242
14	0.97	0.247	47	0.99	0.198
15	0.97	0.271	48	0.99	0.3
16	0.97	0.236	49	0.99	0.26
17	0.97	0.173	50	0.99	0.187
18	0.97	0.267	51	0.99	0.132
19	0.98	0.266	52	0.99	0.199
20	0.98	0.233	53	0.99	0.168
21	0.98	0.214	54	0.99	0.274
22	0.98	0.174	55	0.99	0.186
23	0.98	0.244	56	0.99	0.279
24	0.98	0.212	57	0.99	0.22
25	0.98	0.273	58	0.99	0.232
26	0.98	0.288	59	0.99	0.247

Sphere #	Formcircle	Diameter (mm)	Sphere #	Formcircle	Diameter (mm)
27	0.98	0.275	60	0.99	0.162
28	0.98	0.258	61	0.99	0.178
29	0.98	0.27	62	0.99	0.209
30	0.98	0.191	63	1	0.147
31	0.98	0.191	64	1	0.156
32	0.98	0.214	65	1	0.185
33	0.98	0.26	66	1	0.204

Summary Table

Average Diameter Pre-delivery, mm	0.221 ± 0.054
Average Diameter Post-delivery, mm	0.226 ± 0.049
Average Formcircle Pre-delivery	0.98 ± 0.04
Average Formcircle Post-delivery	0.98 ± 0.02

Example 13

Polymer Microsphere Comprised of a Macromer and Plurality of Monomers, Diluted Prepolymer Solution

[00112] The prepolymer formulation was prepared by dissolving 0.35 g 2-aminoethyl methacrylate, 2.98 g poly(ethylene glycol) diacrylamide from Example 1, 7.16 g glycerol monomethacrylate, 0.098 g N,N'-methylenebisacrylamide, and 3.0 g sodium chloride in 40 mL of de-ionized water. The solution was filtered into a clean 120 mL amber jar. An initiator solution was made by dissolving 1.0 g ammonium persulfate in 2.0 g of de-ionized water. 1.0 mL of the ammonium persulfate solution was added to the filtered prepolymer solution, and the solution was vacuum degassed for 2 min, and the vacuum was replaced with argon. Then, 500 mL of mineral oil were sonicated for 1 hr, and then added to a sealed reaction vessel with an overhead stirring element. The vessel was vacuum degassed for 1 hr, and then the vacuum replaced with argon. Then, 1 mL of N,N,N',N'-tetramethylethylenediamine was added to the reaction vessel and overhead stirring started at 200 rpm. The prepolymer formulation was added to the reaction vessel. After 1 min, 0.1 mL of SPAN® 80 was added and the preparation was allowed to polymerize for at least 2 hr. The oil was decanted off and the particles were poured into a

separatory funnel with 1,000 mL of de-ionized water. The bottom water/sphere layer was collected. The particles were washed with several 300 mL portions of hexane. After the final wash, all hexane was decanted off and the particles were washed several times with fresh 300 mL portions of de-ionized water and stored in a capped bottle with de-ionized water.

Example 14

Particle embolic prepared with a polyether macromer and monomer

[00113] A prepolymer formulation was prepared by dissolving 10.0 g poly(ethylene glycol) diacrylamide from Example 1, and 15.0 g 3-sulfopropyl acrylate potassium salt, in 35.0 g of de-ionized water. Then, 55 g of this solution was filtered. An initiator solution was made by dissolving 1.0 g ammonium persulfate in 2.0 g of deionized water. Ammonium persulfate solution (1 mL) was added to the filtered prepolymer solution, the solution was then vacuum degassed for 2 min, and the vacuum was replaced with argon. Then, 1000 mL of mineral oil was sonicated for 2 hr, and then added to a sealed reaction vessel with 0.5 mL of SPAN® 80 and an overhead stirring element. The vessel was vacuum degassed for 1 hr, and then the vacuum was replaced with argon. N,N,N',N'-tetramethylethylenediamine (1 mL) was added to the reaction vessel and overhead stirring started at 450 rpm. The prepolymer formulation (55 g) was added to the reaction vessel via syringe, then 0.35 mL of SPAN® 80. The beads were allowed to polymerize for at least 8 hr.

[00114] The preceding disclosures are illustrative embodiments. It should be appreciated by those of skill in the art that the devices, techniques and methods disclosed herein elucidate representative embodiments that function well in the practice of the present disclosure. However, those of skill in the art should, in light of the present disclosure, appreciate that many changes can be made in the specific embodiments that are disclosed and still obtain a like or similar result without departing from the spirit and scope of the invention.

[00115] Unless otherwise indicated, all numbers expressing quantities of ingredients, properties such as molecular weight, reaction conditions, and so forth used in the specification and claims are to be understood as being modified in all instances by the term "about." Accordingly, unless indicated to the contrary, the numerical parameters set forth in the following specification and attached claims are approximations that may vary depending upon the desired properties sought to be obtained by the present invention. At the very least, and not as an attempt to limit the application of the doctrine of equivalents to the scope of the claims, each numerical parameter should at least be construed in light of the number of reported significant

digits and by applying ordinary rounding techniques. Notwithstanding that the numerical ranges and parameters setting forth the broad scope of the invention are approximations, the numerical values set forth in the specific examples are reported as precisely as possible. Any numerical value, however, inherently contains certain errors necessarily resulting from the standard deviation found in their respective testing measurements.

[00116] The terms "a" and "an" and "the" and similar referents used in the context of describing the invention (especially in the context of the following claims) are to be construed to cover both the singular and the plural, unless otherwise indicated herein or clearly contradicted by context. Recitation of ranges of values herein is merely intended to serve as a shorthand method of referring individually to each separate value falling within the range. Unless otherwise indicated herein, each individual value is incorporated into the specification as if it were individually recited herein. All methods described herein can be performed in any suitable order unless otherwise indicated herein or otherwise clearly contradicted by context. The use of any and all examples, or exemplary language (e.g. "such as") provided herein is intended merely to better illuminate the invention and does not pose a limitation on the scope of the invention otherwise claimed. No language in the specification should be construed as indicating any non-claimed element essential to the practice of the invention.

[00117] The use of the term "or" in the claims is used to mean "and/or" unless explicitly indicated to refer to alternatives only or the alternatives are mutually exclusive, although the disclosure supports a definition that refers to only alternatives and "and/or."

[00118] Groupings of alternative elements or embodiments of the invention disclosed herein are not to be construed as limitations. Each group member may be referred to and claimed individually or in any combination with other members of the group or other elements found herein. It is anticipated that one or more members of a group may be included in, or deleted from, a group for reasons of convenience and/or patentability. When any such inclusion or deletion occurs, the specification is herein deemed to contain the group as modified thus fulfilling the written description of all Markush groups used in the appended claims.

[00119] Preferred embodiments of this invention are described herein, including the best mode known to the inventors for carrying out the invention. Of course, variations on those preferred embodiments will become apparent to those of ordinary skill in the art upon reading the foregoing description. The inventor expects those of ordinary skill in the art to employ such variations as appropriate, and the inventors intend for the invention to be practiced otherwise

than specifically described herein. Accordingly, this invention includes all modifications and equivalents of the subject matter recited in the claims appended hereto as permitted by applicable law. Moreover, any combination of the above-described elements in all possible variations thereof is encompassed by the invention unless otherwise indicated herein or otherwise clearly contradicted by context.

[00120] Specific embodiments disclosed herein may be further limited in the claims using consisting of or consisting essentially of language. When used in the claims, whether as filed or added per amendment, the transition term “consisting of” excludes any element, step, or ingredient not specified in the claims. The transition term “consisting essentially of” limits the scope of a claim to the specified materials or steps and those that do not materially affect the basic and novel characteristic(s). Embodiments of the invention so claimed are inherently or expressly described and enabled herein.

[00121] Further, it is to be understood that the embodiments of the invention disclosed herein are illustrative of the principles of the present invention. Other modifications that may be employed are within the scope of the invention. Thus, by way of example, but not of limitation, alternative configurations of the present invention may be utilized in accordance with the teachings herein. Accordingly, the present invention is not limited to that precisely as shown and described.

We claim:

1. A polymer particle comprising:
at least one derivatized poly(ethylene glycol) macromer, poly(propylene glycol) macromer, poly(tetramethylene oxide) macromer, or a combination thereof at a concentration of between about 15% w/w and about 50% w/w; and
at least one monomer that is not n-isopropyl acrylamide.
2. The polymer particle of claim 1, wherein the polymer particle has a diameter between about 40 μm and about 1,200 μm .
3. The polymer particle of claim 1, further comprising at least one monomer.
4. The polymer particle of claim 3, wherein the at least one monomer includes a functional group, wherein the functional group is acrylate, acrylamide, methacrylate, or methacrylamide.
5. The polymer particle of claim 3, wherein the at least one monomer is glycerol monomethacrylate, amino ethyl methacrylate, 3-sulfopropyl acrylate, amino propyl methacrylamide, or a combination thereof.
6. The polymer particle of claim 5, wherein the at least one monomer is glycerol monomethacrylate at a concentration of about 68% w/w.
7. The polymer particle of claim 5, wherein the at least one monomer is 3-sulfopropyl acrylate at a concentration of about 59% w/w.
8. The polymer particle of claim 5, wherein the at least one monomer is amino propyl methacrylamide at a concentration of about 1% w/w.

9. The polymer particle of claim 5, wherein the at least one monomer is amino ethyl methacrylate at a concentration of about 3% w/w.
10. The polymer particle of claim 1, wherein the at least one derivatized poly(ethylene glycol) macromer is poly(ethylene glycol) diacrylamide, poly(ethylene glycol) diacrylate, poly(ethylene glycol) dimethacrylate, poly(ethylene glycol) dimethacrylamide, or a combination thereof.
11. The polymer particle of claim 6, wherein the at least one derivatized poly(ethylene glycol) macromer is poly(ethylene glycol) diacrylamide 10,000.
12. A method of making a polymer particle comprising:
reacting an aqueous based prepolymer solution including at least one derivatized polyether macromer and an initiator in an oil to form polymer particles;
wherein said polymer particle has a diameter less than about 1,200 μm .
13. The method of claim 12, wherein the oil is a mineral oil.
14. The method of claim 12, wherein the initiator is ammonium persulfate, tetramethylethylene diamine, or a combination thereof.
15. The method of claim 12, wherein the polymer particle has a diameter between about 40 μm and about 1,200 μm .
16. The method of claim 12, wherein the at least one derivatized polyether macromer is a derivative of poly(ethylene glycol), poly(propylene glycol), poly(tetramethylene oxide), or a combination thereof.

17. The method of claim 16, wherein the at least one derivatized polyether macromer is poly(ethylene glycol) diacrylamide, poly(ethylene glycol) diacrylate, poly(ethylene glycol) dimethacrylate, poly(ethylene glycol) dimethacrylamide, or a combination thereof.
18. The method of claim 16, wherein the at least one derivatized polyether macromer is poly(ethylene glycol) diacrylamide 10,000.
19. The method of claim 12, further comprising at least one monomer.
20. The method of claim 19, wherein the at least one monomer is glycerol monomethacrylate, amino ethyl methacrylate, 3-sulfopropyl acrylate, amino propyl methacrylamide, or a combination thereof.
21. The method of claim 19, wherein the monomer is not n-isopropyl acrylamide.

1/3




FIG. 1




FIG. 2

2/3




FIG. 3




FIG. 4




FIG. 5




FIG. 6

A. CLASSIFICATION OF SUBJECT MATTER**A61K 9/32(2006.01)i**

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

A61K 9/32; A61K 31/337; A61K 31/135; A61K 9/14; A61K 51/12; A61F 2/02; A61K 47/32; A61F 2/01; C08L 33/26

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Korean utility models and applications for utility models

Japanese utility models and applications for utility models

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKOMPASS(KIPO internal) & Keywords: polymer particle, embolization, poly(ethylene glycol) diacrylamide, glycerol monomethacrylate, radiopaque contrast

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2012-0129798 A1 (AKALA, E. et al.) 24 May 2012 See abstract; and claims 9-19 and 27-30.	1,3,4
A		2,5-21
A	US 2006-0069168 A1 (TABATA, N. et al.) 30 March 2006 See abstract; and claims 1-20.	1-21
A	US 2012-0289995 A1 (CONSTANT, M. et al.) 15 November 2012 See abstract; and claims 1-21.	1-21
A	US 2009-0117033 A1 (O' GARA, J. E.) 07 May 2009 See abstract; and claims 1-25.	1-21
A	US 2009-0164013 A1 (CRUISE, G. M. et al.) 25 June 2009 See abstract; and claims 1-26.	1-21

 Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

27 February 2015 (27.02.2015)

Date of mailing of the international search report

27 February 2015 (27.02.2015)

Name and mailing address of the ISA/KR

International Application Division
Korean Intellectual Property Office
189 Cheongsu-ro, Seo-gu, Daejeon Metropolitan City, 302-701,
Republic of Korea

Facsimile No. ++82 42 472 3473

Authorized officer

LEE, Jeong A

Telephone No. +82-42-481-8740



INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2014/064680

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2012-0129798 A1	24/05/2012	CA 2818873 A1	31/05/2012
		EP 2643372 A2	02/10/2013
		EP 2643372 A4	18/06/2014
		US 2014-274929 A1	18/09/2014
		US 8772355 B2	08/07/2014
		WO 2012-071452 A2	31/05/2012
		WO 2012-071452 A3	27/09/2012
		US 2006-0069168 A1	30/03/2006
CA 2503949 C	23/10/2012		
EP 1559440 A1	03/08/2005		
EP 1559440 A4	10/11/2010		
JP 04686970 B2	25/05/2011		
JP 2004-167229 A	17/06/2004		
WO 2004-039425 A1	13/05/2004		
US 2012-0289995 A1	15/11/2012		
		WO 2012-145431 A3	17/01/2013
US 2009-0117033 A1	07/05/2009	US 2012-288441 A1	15/11/2012
		US 8246998 B2	21/08/2012
US 2009-0164013 A1	25/06/2009	AU 2008-345590 A1	09/07/2009
		AU 2008-345590 B2	30/10/2014
		CA 2709379 A1	09/07/2009
		CN 101903051 A	01/12/2010
		CN 101903051 B	31/07/2013
		EP 2231215 A2	29/09/2010
		EP 2266639 A1	29/12/2010
		JP 2011-507637 A	10/03/2011
		KR 10-2010-0105663 A	29/09/2010
		US 2013-253087 A1	26/09/2013
		US 8470035 B2	25/06/2013
		WO 2009-086208 A2	09/07/2009
		WO 2009-086208 A3	01/04/2010