

(19)



(11)

EP 3 135 746 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
01.03.2017 Bulletin 2017/09

(51) Int Cl.:
C09K 11/77 (2006.01) **H01L 33/50** (2010.01)
C09K 11/08 (2006.01)

(21) Application number: **16184714.0**

(22) Date of filing: **18.08.2016**

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR
Designated Extension States:
BA ME
Designated Validation States:
MA MD

(72) Inventors:
• **NISHIMATA, Kazuya**
Anan-shi, Tokushima 774-8601 (JP)
• **WATANABE, Hiroyuki**
Anan-shi, Tokushima 774-8601 (JP)
• **HOSOKAWA, Shoji**
Anan-shi, Tokushima 774-8601 (JP)

(30) Priority: **28.08.2015 JP 2015169327**
19.07.2016 JP 2016141227

(74) Representative: **Vossius & Partner**
Patentanwälte Rechtsanwälte mbB
Siebertstrasse 3
81675 München (DE)


(71) Applicant: **NICHIA CORPORATION**
Anan-shi
Tokushima 774-8601 (JP)

(54) **NITRIDE FLUORESCENT MATERIAL, METHOD FOR PRODUCING THE SAME, AND LIGHT EMITTING DEVICE**

(57) A method for producing a nitride fluorescent material having high emission luminance can be provided. The method includes heat-treating a raw material mixture

containing silicon nitride, silicon, an aluminium compound, a calcium compound, and a europium compound.

Fig. 1



EP 3 135 746 A1

Description

[0001] The present disclosure relates to a nitride fluorescent material, a method for producing the nitride fluorescent material, and a light emitting device.

[0002] Light emitting devices have been developed that emit white light by incorporating in combination a blue light emitting LED (Light Emitting Diode) as a light emitting element, a fluorescent material emitting green light when excited by the blue light, and a fluorescent material emitting red light when excited by the blue light. For instance, Japanese patent application JP 2008-303331 A describes a light emitting device that emits white light by incorporating in combination a β sialon fluorescent material having a β -type Si_3N_4 crystalline structure, and emitting green light; a nitride fluorescent material having a composition of $\text{CaAlSiN}_3\text{:Eu}$ and emitting red light (hereinafter also referred to as "CASN fluorescent material"); and a blue LED.

[0003] A red light emitting fluorescent material (hereinafter also referred to as "SCASN fluorescent material") having a composition of $(\text{Ca,Sr})\text{AlSiN}_3\text{:Eu}$ obtained by partially replacing Ca with Sr in a CASN fluorescent material is known. A SCASN fluorescent material is said to have a peak emission wavelength shorter than the peak emission wavelength of a CASN fluorescent material. A CASN fluorescent material can be obtained by, for instance, calcinating a mixture comprising silicon nitride, aluminium nitride, calcium nitride, and europium nitride. A SCASN fluorescent material can also be obtained in the same manner as a CASN fluorescent material (see, for instance, JP 2006-8721 A).

[0004] Because of demand for improved luminance of a light emitting device, nitride fluorescent materials, such as CASN fluorescent materials, having higher light emitting luminance are called for. One embodiment according to the present disclosure is to provide a method for producing a nitride fluorescent material having high light emitting luminance.

[0005] In view of the problem, the inventors have found, as a result of intensive study, that a nitride fluorescent material produced from materials of specific components achieves improved light emitting luminance, and accomplished the present invention. The present invention includes the following embodiments.

[0006] A first embodiment is a method for producing a nitride fluorescent material including heat-treating a raw material mixture containing silicon nitride, silicon, an aluminium compound, a calcium compound, and a europium compound.

[0007] According to one embodiment of the present disclosure, a method for producing a nitride fluorescent material with improved light emitting luminance can be provided.

[0008] A method for producing a nitride fluorescent material of the present invention will be described below with reference to embodiments. The embodiments shown below, however, exemplify the technical concept of the present invention, and the present invention is not limited to the following method for producing a nitride fluorescent material. The relationship between the color names and the chromaticity coordinates, the relationship between the wavelength ranges of light and the color names of monochromatic light, and others are in accordance with Japanese Industrial Standard (JIS) Z8110. As used herein, the term "step" means not only an independent step but also a step which cannot be clearly distinguished from the other steps but can achieve the anticipated effect of that step. Further, for the amount of each component contained in a composition, when a plurality of substances corresponding to the component exist, the amount of the component means the total amount of the substances present in the composition unless otherwise specified.

[0009] The embodiment is described in detail in conjunction with drawings, in which;

Fig. 1 is a schematic sectional view showing an example of a light emitting device,

Fig. 2 is an example of a light emission spectrum of relative energy versus wavelength for a nitride fluorescent material according to the present embodiment,


Fig. 3 is a scanning electron microscope (SEM) image of a nitride fluorescent material according to Comparative Example 1,

Fig. 4 is an SEM image of a nitride fluorescent material according to Example 1, and

Fig. 5 is an example of light emission spectrum of relative energy versus wavelength for a nitride fluorescent material according to the present embodiment.

[Method for producing a nitride fluorescent material]

[0010] The method for producing a nitride fluorescent material includes heat-treating a raw material mixture containing silicon nitride, elemental silicon, an aluminium compound, a calcium compound, and a europium compound. The nitride fluorescent material has a composition represented by, for instance, formula (I).



[0011] In the formula (I), s, t, u, v, and w respectively satisfy $0.0 \leq s < 1$, $0 < t \leq 1$, $s + t \leq 1$, $0.9 \leq u \leq 1.1$, $0.9 \leq v \leq 1.1$, and $2.5 \leq w \leq 3.5$.

[0012] The raw material mixture contains elemental silicon as well as silicon nitride as a silicon source. Although the details are unknown, when heat treated, elemental silicon is believed to react while undergoing nitridization. Because of this, sintering due to heat treatment at a high temperature is believed less likely to occur. Thus, a nitride fluorescent material of a large particle diameter can be obtained. The resultant nitride fluorescent material has high emitting efficiency and improved emitting luminance.

[0013] The raw material mixture contains silicon nitride, elemental silicon, at least one aluminium compound, and at least one europium compound.

[0014] The silicon nitride is a silicon compound containing a nitrogen atom and silicon atom, and may contain an oxygen atom. When the silicon nitride contains an oxygen atom, the oxygen atom may be contained in the form of a silicon oxide or in the form of an oxynitride of silicon.

[0015] The content of the oxygen atom in the silicon nitride is, for instance, less than 2 % by weight, and preferably 1.5 % by weight or less. The content of the oxygen atom is also, for instance, 0.3 % by weight or more, and preferably 0.4 % by weight or more. When the amount of oxygen is equal to or greater than a predetermined value, the reactivity is increased, and the particle growth is promoted. When the amount of oxygen is equal to or less than a predetermined amount, excessive sintering of the fluorescent material particles is suppressed, improving the shapes of the fluorescent material particles to be produced.

[0016] The purity of the silicon nitride is, for instance, 95 % by weight or more, and preferably 99 % by weight or more. When the purity of the silicon nitride is equal to or greater than a predetermined value, the influence of impurities is minimized, leading to further improved light emitting luminance of the nitride fluorescent material to be produced.

[0017] The average particle diameter of the silicon nitride is, for instance, from 0.1 μm to 15 μm , and preferably from 0.1 μm to 5 μm . When the average particle diameter of the silicon nitride is equal to or less than a predetermined value, the reactivity during production of the nitride fluorescent material is improved. When the average particle diameter of the silicon nitride is equal to or greater than a predetermined value, excessive reaction during production of the nitride fluorescent material is suppressed, which suppresses sintering of the fluorescent material particles to be produced.

[0018] The silicon nitride may be appropriately selected from commercially available products, or may be produced by nitriding silicon. The silicon nitride can be obtained, for instance, by grinding silicon to be used as a raw material in an inert gas atmosphere such as rare gas and nitrogen gas, and heat-treating the resultant powder in a nitrogen atmosphere so that the powder is nitrided. The elemental silicon to be used as the raw material preferably has high purity, and the purity is, for instance, 3 N (99.9 % by weight) or more. The average particle diameter of the ground silicon is, for instance, from 0.1 μm to 15 μm . The heat-treating temperature is, for instance, from 800°C to 2000°C, and the time for heat-treating is, for instance, from 1 hour to 20 hours.

[0019] The resultant silicon nitride may undergo, for instance, grinding treatment in a nitrogen atmosphere.

[0020] The silicon as a component of the raw material mixture is elemental silicon. The purity of the silicon is, for instance, 95 % by weight or more, and preferably 99.9 % by weight or more. When the purity of the silicon is equal to or greater than a predetermined value, the influence of impurities is minimized, leading to further improved luminance of the fluorescent material to be produced.

[0021] The average particle diameter of the silicon is, for instance, from 0.1 μm to 100 μm , and preferably from 0.1 μm to 80 μm . When the average particle diameter of the silicon nitride is equal to or less than a predetermined value, complete nitriding into the inside of the particles is achieved. When the average particle diameter of the silicon is equal to or greater than a predetermined value, excessive reaction during production of the nitride fluorescent material is suppressed, and thus sintering of the fluorescent material particles is suppressed.

[0022] A portion of silicon nitride and elemental silicon in the raw material mixture may be replaced with another silicon compound, such as silicon oxide. That is, the raw material mixture may contain a silicon compound such as silicon oxide in addition to silicon nitride and elemental silicon. Examples of the silicon compound include silicon oxide, silicon oxynitride, and silicate.

[0023] A portion of silicon nitride and elemental silicon in the raw material mixture may be replaced with a metal compound, a simple metal, or an alloy of elements from Group IV of the periodic table, such as germanium, tin, titanium, zirconium, and hafnium. Examples of the metal compound include oxide, hydroxide, nitride, oxynitride, fluoride, and chloride.

[0024] The weight percentage of the silicon relative to the total amount of the silicon nitride and silicon in the raw material mixture is, for instance, from 10 % by weight to 85 % by weight, preferably from 20 % by weight to 80 % by weight, and more preferably from 30 % by weight to 80 % by weight. When the weight percentage of the silicon is equal to or greater than a predetermined value, sintering of the particles during particle growth of the nitride fluorescent material is suppressed. Furthermore, since silicon nitride has an effect of accelerating nitriding reaction of silicon, incorporating a predetermined weight percentage or less of silicon (to have a greater weight percentage of the silicon nitride) leads to sufficient nitriding of silicon.

[0025] Examples of the aluminium compound include an aluminium-containing oxide, hydroxide, nitride, oxynitride, fluoride, and chloride. In place of at least a portion of the aluminium compound, for instance, simple aluminium metal or

an aluminium alloy may be used. Specific examples of the aluminium compound include aluminium nitride (AlN), aluminium oxide (Al₂O₃), and aluminium hydroxide (Al(OH)₃), and it is preferable to use at least one selected from the group consisting of these, and it is more preferable to use aluminium nitride. Since aluminium nitride is composed only of the elements to be contained in the target fluorescent material composition, introduction of impurities can be prevented more effectively. Compared to, for instance, an aluminium compound containing oxygen or hydrogen, aluminium nitride can reduce the influence of these elements, and needs no nitriding reaction unlike simple metals. These aluminium compounds may be used individually, or two or more of them may be used in combination.

[0026] The average particle diameter of the aluminium compound to be used as a raw material is, for instance, from 0.1 μm to 15 μm, and is preferably from 0.1 μm to 10 μm. When the average particle diameter of the aluminium compound is equal to or less than a predetermined value, the reactivity during production of the nitride fluorescent material is improved. When the average particle diameter of the aluminium compound is equal to or greater than a predetermined value, sintering of the fluorescent material particles during production of the nitride fluorescent material is suppressed.

[0027] The purity of the aluminium compound is, for instance, 95 % by weight or more, and is preferably 99 % by weight or more. When the purity of the aluminium compound is equal to or greater than a predetermined value, the influence of impurities is minimized, leading to further improved light emitting luminance of the fluorescent material.

[0028] The aluminium compound may be appropriately selected from commercially available products, or a desired aluminium compound may be produced. For instance, the aluminium nitride may be produced by, for example, the direct nitriding method of aluminium.

[0029] At least a portion of the aluminium compound in the raw material mixture may be replaced with a metal compound, a simple metal, or an alloy of elements from Group III of the periodic table, such as gallium, indium, vanadium, chrome, and cobalt. Examples of the metal compound include oxide, hydroxide, nitride, oxynitride, fluoride, and chloride.

[0030] Examples of the calcium compound may include calcium-containing hydrogen oxide, oxide, hydroxide, nitride, oxynitride, fluoride, and chloride. In place of at least a portion of the calcium compound, for instance, a simple calcium metal or an alloy of calcium may be used. Specific examples of the calcium compound include inorganic compounds such as calcium hydride (CaH₂), calcium nitride (Ca₃N₂), calcium oxide (CaO), calcium hydroxide (Ca(OH)₂), and salts of organic compounds such as an imide compound and an amide compound. It is preferable to use at least one selected from the group consisting of these, and calcium nitride is more preferable. Since calcium nitride is composed only of the elements to be contained in the composition of the target fluorescent material, introduction of impurities can be prevented more effectively. Compared to, for instance, a calcium compound containing oxygen or hydrogen, calcium nitride can reduce the influence of these elements, and needs no nitriding reaction unlike simple metals. These calcium compounds may be used individually, or two or more of them may be used in combination.

[0031] The average particle diameter of the calcium compound to be used as a raw material may be, for instance, from 0.1 μm to 100 μm, or from 0.1 μm to 80 μm. When the average particle diameter of the calcium compound is equal to or less than a predetermined value, the reactivity during production of the nitride fluorescent material may be improved. When the average particle diameter of the calcium compound is equal to or greater than a predetermined value, sintering of the nitride fluorescent material particles during production of the nitride fluorescent material may be suppressed.

[0032] The purity of the calcium compound is, for instance, 95 % by weight or more, and preferably 99 % by weight or more. When the purity is equal to or greater than a predetermined value, the influence of impurities is minimized, leading to further improved light emitting luminance of the fluorescent material.

[0033] The calcium compound may be appropriately selected from commercially available products, or a desired calcium compound may be produced. For instance, calcium nitride may be obtained by grinding calcium to be used as a raw material in an inert gas atmosphere, and heat-treating the resultant powder in a nitrogen atmosphere so that the powder is nitrided. The calcium to be used as a raw material is preferably highly pure, and the purity is, for instance, 2 N (99 % by weight) or more. The average particle diameter of ground calcium is, for instance, from 0.1 μm to 15 μm. The heat-treating temperature is, for instance, from 600°C to 900°C, and the time for heat-treating is, for instance, from 1 hour to 20 hours.

[0034] The resultant calcium nitride may undergo, for instance, grinding treatment in an inert gas atmosphere.

[0035] At least a portion of calcium compound in the raw material mixture may be replaced with a metal compound, a simple metal, an alloy, or the like of alkaline earth metals such as magnesium and barium; alkali metals such as lithium, sodium, and potassium; and elements from Group III of the periodic table, such as boron and aluminium. Examples of the metal compound include hydride, oxide, hydroxide, nitride, oxynitride, fluoride, and chloride.

[0036] Examples of the europium compounds include europium-containing oxide, hydroxide, nitride, oxynitride, fluoride, and chloride. In place of at least a portion of the europium compound, for instance, a simple europium metal or an alloy of europium may be used. Specific examples of the europium compound include europium oxide (Eu₂O₃), europium nitride (EuN), and europium fluoride (EuF₃). At least one selected from the group consisting of these is preferable, and europium oxide is more preferable. Since europium nitride (EuN) is composed only of the elements to be contained in the target composition of the fluorescent material, introduction of impurities can be more effectively prevented. Furthermore, since europium oxide (Eu₂O₃) and europium fluoride (EuF₃) also serve as a flux, these are preferably used. These

europium compounds may be used individually, or two or more of them may be used in combination.

[0037] The average particle diameter of the europium compound to be used as a raw material is, for instance, from 0.01 μm to 20 μm , and preferably from 0.05 μm to 10 μm . When the average particle diameter of the europium compound is equal to or greater than a predetermined value, agglomeration of the fluorescent material particles during production is suppressed. When the average particle diameter of the europium compound is equal to or less than a predetermined value, more uniformly activated fluorescent material particles can be obtained.

[0038] The purity of the europium compound is, for instance, 95 % by weight or more, and preferably 99.5 % by weight or more. When the purity of the europium compound is equal to or greater than a predetermined value, the influence of impurities is minimized, leading to further improved light emitting luminance of the fluorescent material.

[0039] The europium compound may be appropriately selected from commercially available products, or a desired europium compound may be produced. For instance, the europium nitride may be produced by grinding europium to be used as a raw material in an inert gas atmosphere, and heat-treating the resultant powder in a nitrogen atmosphere so that the powder is nitrided. The average particle diameter of the ground europium is, for instance, from 0.1 μm to 10 μm . The heat-treating temperature is, for instance, from 600°C to 1200°C, and the time for heat-treating is, for instance, from 1 hour to 20 hours.

[0040] The resultant europium nitride may undergo, for instance, grinding treatment in an inert gas atmosphere.

[0041] At least a portion of the europium compound in the raw material mixture may be replaced with a metal compound, a simple metal, or an alloy of rare-earth elements, such as scandium (Sc), yttrium (Y), lanthanum (La), cerium (Ce), praseodymium (Pr), neodymium (Nd), samarium (Sm), gadolinium (Gd), terbium (Tb), dysprosium (Dy), holmium (Ho), erbium (Er), thulium (Tm), ytterbium (Yb), and lutetium (Lu). Examples of the metal compound include oxide, hydroxide, nitride, oxynitride, fluoride, and chloride.


[0042] A portion of the calcium compound in the raw material mixture may be replaced with a strontium compound, metal strontium, or an alloy of strontium as necessary. Examples of the strontium compound include strontium-containing hydride, oxide, hydroxide, nitride, oxynitride, fluoride, and chloride.

[0043] The strontium compound may be appropriately selected from commercially available products, or a desired strontium compound may be produced. For instance, strontium nitride may be produced in the same manner as calcium nitride. Unlike calcium nitride, strontium nitride is likely to take any amount of nitrogen, and is represented by SrN_x . In the formula, x is, for instance, from 0.5 to 1.

[0044] In a raw material mixture containing a strontium atom, the ratio of the number of strontium atom in the total amount of calcium atom and strontium atom in the raw material mixture is, for instance, from 0.1 % by mol to 99.9 % by mol, and preferably from 0.1 % by mol to 98 % by mol. When the content of the strontium atom is in this range, a desired value of peak light emission wavelength of the nitride fluorescent material is achieved.

[0045] The mixing ratio of silicon nitride, silicon, an aluminium compound, a calcium compound, and a europium compound in the raw material mixture is not particularly limited as long as the nitride fluorescent material having a composition represented by formula (I) is obtained, and may be appropriately selected according to a desired composition. For instance, the molar ratio of silicon atom to aluminium atom in the raw material mixture is u:v, and is preferably from 0.9:1.1 to 1.1:0.9. The molar ratio of calcium atom (optionally strontium atom is contained) to aluminium atom is (s+t):u, and is preferably 0.9:1 to 1.11:1. The molar ratio of the europium atom in the total molar amount of calcium atom (optionally strontium atom is contained) and europium atom is, for instance, 1:0.05 to 1:0.001, and is preferably 1:0.03 to 1:0.003.

[0046] For instance, mixing calcium nitride, europium oxide, aluminium nitride, silicon nitride, and silicon to prepare a raw material mixture having a composition ratio of Ca:Eu:Al:Si = 0.993:0.007:1:1, and heat-treating the raw material mixture by a method described later can produce a nitride fluorescent material represented by:



[0047] The composition of the nitride fluorescent material, however, is a representative composition estimated by the mixing ratio of the raw material mixture. Since europium oxide is used and each raw material contains about 1 % by weight of oxygen, the actual fluorescent material to be obtained may contain a certain amount of oxygen. To show a representative composition, the chemical formula given above does not contain such oxygen. The resulting composition may slightly differ from the initial composition because a portion of the raw materials may degrade and scatter out while undergoing heat treatment. By changing the mixing ratio of each raw material, however, the composition of the target nitride fluorescent material may be changed. Although an explanation is made here using a composition containing no strontium, needless to say, the same can be said about a composition containing strontium.

[0048] The raw material mixture may further contain a separately prepared composition (nitride fluorescent material) represented by formula (I) as necessary. When a raw material mixture contains a nitride fluorescent material, the content may be, for instance, from 1 % by weight to 50 % by weight in the total amount of the raw material mixture.

[0049] The raw material mixture may contain a flux such as a halide as necessary. In a raw material containing a flux,

the reaction between raw materials is further accelerated, and the solid phase reaction proceeds more uniformly, so that a fluorescent material having a large particle diameter and superior light emitting properties can be obtained. This is, for instance, believed to be due to the fact that the temperature of heat treatment in the preparation step is equal to or greater than the temperature for generating a liquid phase such as halide, which is a flux. Examples of the halide include chlorides and fluorides of rare earth metals, alkali earth metals, and alkali metals. The flux may be added as a compound that helps the element ratio of the cations to achieve the target composition, or may be further added as an additive after various materials are added to make up the target composition. When the raw material mixture contains a flux, an amount of a flux is, for instance, 20 % by weight or less, or 10 % by weight or less. The content is also, for instance, 0.1 % by weight or more. A flux in such an amount can accelerate reaction without lowering the emitting luminance of the fluorescent material.

[0050] The raw material mixture may be obtained by weighing desired material compounds in a desired compounding ratio, and then mixing the material compounds by a mixing method using a ball mill, or a mixing method using a mixing machine, such as a Henschel mixer or a V-blender, or using a mortar and a pestle. The mixing may be dry mixing or wet mixing by adding, for instance, a solvent.

[0051] The temperature of the heat treatment of the raw material mixture is, for instance, 1200°C or more, preferably 1500°C or more, and more preferably 1900°C or more. The heat-treating temperature is also, for instance, 2200°C or less, preferably 2100°C or less, and more preferably 2050°C or less. Heat treatment at a temperature of 1200°C or more allows easier incorporation of Eu into the crystal, and efficient formation of a desired nitride fluorescent material. Heat treatment at a temperature of 2200°C or less is likely to suppress degradation of the resulting nitride fluorescent material.

[0052] The atmosphere in the heat treatment of the raw material mixture is, for instance, a nitrogen gas-containing atmosphere, and is preferably substantially a nitrogen gas atmosphere. A nitrogen gas-containing atmosphere may allow nitriding of silicon contained in the raw material. A nitrogen gas-containing atmosphere also suppresses degradation of nitride, which is a raw material, and the fluorescent material. When the atmosphere in the heat treatment of the raw material mixture contains a nitrogen gas, the atmosphere may contain another gas, such as hydrogen, rare gas such as argon, carbon dioxide, carbon monoxide, oxygen, or ammonia, in addition to nitrogen gas. The content of the nitrogen gas in the heat treating atmosphere of the raw material mixture is, for instance, 90 % by volume or more, and preferably 95 % by volume or more. When the content of gases containing elements other than nitrogen is equal to or less than a predetermined value, the possibility for these gaseous components to form impurities and lower the light emitting luminance of fluorescent material is further reduced.

[0053] The pressure in the heat treatment of the raw material mixture is, for instance, from ordinary pressure to 200 MPa. To suppress degradation of the nitride fluorescent material to be generated, the pressure is preferably high, and is preferably from 0.1 MPa to 200 MPa, and more preferably from 0.6 MPa to 1.2 MPa for less restrictions on industrial equipment.

[0054] Heat treatment of the raw material mixture may be performed at a single temperature, or by multiple stages including two or more heat-treating temperatures. Heat treatment by multiple stages, for instance, includes performing a first-stage heat treatment at 800°C to 1400°C, elevating the temperature slowly, and then performing a second-stage heat treatment at 1500°C to 2100°C.

[0055] In the heat treatment of the raw material mixture, the heat treatment is performed, for instance, by elevating the temperature from room temperature to a predetermined temperature. The time for elevating the temperature is, for instance, from 1 hour to 48 hours, preferably from 2 hours to 24 hours, and more preferably from 3 hours to 20 hours. When the time for elevating the temperature is 1 hour or more, the fluorescent material particles are likely to fully grow, and Eu is likely to be easily incorporated into the crystals of the fluorescent material particles.

[0056] In the heat treatment of the raw material mixture, a retention time at a predetermined temperature may be provided. The retention time is, for instance, from 0.5 hour to 48 hours, preferably from 1 hour to 30 hours, and more preferably from 2 hours to 20 hours. With a retention time of a predetermined value or more, more uniform particle growth is further accelerated. With a retention time of a predetermined value or less, degradation of the fluorescent material may be further suppressed.

[0057] The time for lowering the temperature from a predetermined temperature to room temperature in the heat treatment of the raw material mixture is, for instance, from 0.1 hour to 20 hours, preferably from 1 hour to 15 hours, and more preferably from 3 hours to 12 hours. A retention time may be provided at an appropriately selected temperature while the temperature is lowered from a predetermined temperature to room temperature. This retention time may be, for instance, adjusted to further enhance the light-emitting luminance of the nitride fluorescent material. The retention time at a predetermined temperature while the temperature is lowered is, for instance, from 0.1 hour to 20 hours, and preferably from 1 hour to 10 hours. The temperature during the retention time is, for instance, from 1000°C to less than 1800°C, and preferably from 1200°C to 1700°C.

[0058] The raw material mixture may be heat-treated, for instance, in a gas pressurized electric furnace. Heat treatment of the raw material mixture may be performed, for instance, by charging the raw material mixture into a crucible or boat made of a carbon material, such as black lead, or of a boron nitride (BN) material. Besides carbon materials or boron

nitride materials, alumina (Al_2O_3) or Mo materials, for example, may be used. A crucible or boat made of boron nitride is particularly preferable.

[0059] After the heat treatment of the raw material mixture, a sizing step including operations in combination of crushing, grinding, and classifying a nitride fluorescent material resulting from the heat treatment, may be performed. A powder of a desired particle diameter can be obtained by the sizing step. Specifically, after roughly grinding a nitride fluorescent material, the roughly ground particles may be ground using a common grinder, such as a ball mill, a jet mill, and a vibration mill to have a predetermined particle diameter. Excessive grinding, however, may cause defects on the surface of the fluorescent material particles, resulting in luminance decrease. When particles having different particle diameters are present after grinding, the particle diameters may be made uniform by classifying the particles.

[Nitride fluorescent material]

[0060] The present disclosure encompasses a nitride fluorescent material produced by the above-described production method. The nitride fluorescent material preferably contains an alkali earth metal, aluminium, silicon, and europium, and more preferably, the nitride fluorescent material has a composition represented by formula (I). As a result of the raw material mixture containing silicon and silicon nitride in combination, sintering of the nitride fluorescent material in the heat treatment during the production is suppressed, achieving a larger particle diameter and thus higher luminance.

[0061] The nitride fluorescent material is, for instance, a red-light emitting fluorescent material that absorbs light in the range of from 200 nm to 600 nm, and emits light having a peak emission wavelength in the range of from 605 nm to 670 nm. The excitation wavelength of the nitride fluorescent material preferably falls within the range of from 420 nm to 470 nm. The half bandwidth in the light emission spectrum of the nitride fluorescent material is, for instance, from 70 nm to 95 nm.

[0062] The specific surface area of the nitride fluorescent material is, for instance, less than $0.3 \text{ m}^2/\text{g}$, preferably $0.27 \text{ m}^2/\text{g}$ or less, more preferably $0.2 \text{ m}^2/\text{g}$ or less, still more preferably $0.16 \text{ m}^2/\text{g}$ or less, yet more preferably $0.15 \text{ m}^2/\text{g}$ or less, and particularly preferably $0.13 \text{ m}^2/\text{g}$ or less. The specific surface area is also, for instance, $0.05 \text{ m}^2/\text{g}$ or more, and preferably $0.1 \text{ m}^2/\text{g}$ or more. When the specific surface area is less than $0.3 \text{ m}^2/\text{g}$, the nitride fluorescent material is likely to have further improved light absorption and conversion efficiency, achieving higher luminance.

[0063] The specific surface area of the nitride fluorescent material is measured by the Brunauer-Emmett-Teller (BET) method. Specifically, the specific surface area is calculated by the dynamic constant-pressure method using Gemini 2370 manufactured by Shimadzu Corporation.

[0064] The average particle diameter of the nitride fluorescent material is, for instance, $15 \mu\text{m}$ or more, preferably $18 \mu\text{m}$ or more, and more preferably $20 \mu\text{m}$ or more. The average particle diameter is, for instance, $30 \mu\text{m}$ or less, and preferably $25 \mu\text{m}$ or less. When the average particle diameter is $15 \mu\text{m}$ or more, light absorption and conversion efficiency are likely to be further improved, achieving still higher luminance. When the average particle diameter is $30 \mu\text{m}$ or less, it is likely that the nitride fluorescent material is handled more easily, and the productivity of a light emitting device containing the nitride fluorescent material is likely to be further improved.

[0065] The average particle diameter of the nitride fluorescent material is, for instance, in the range of from $15 \mu\text{m}$ to $30 \mu\text{m}$. Preferably, the fluorescent material contains particles of this mean particle diameter at high frequency. The particle sizes are also preferably distributed in a narrow range. A light emitting device including a nitride fluorescent material with less variation in particle diameter and particle size distribution has less color unevenness, and thus has favorable color tone.

[0066] The average particle diameter of the nitride fluorescent material is Fisher Sub Sieve Sizer's No. (F.S.S.S.N.) obtained by the air permeability method using Fisher Sub Sieve Sizer. Specifically, this is a value obtained by measuring each sample of 1 cm^3 under the conditions of an atmospheric temperature of 25°C and a humidity of 70 %RH, packing each sample into a dedicated tubular container, to which dry air at a given pressure is introduced, and a specific surface area is read from the difference in pressure and converted to an average particle diameter.

[0067] To improve emitting luminance, the nitride fluorescent material preferably has a specific surface area of less than $0.3 \text{ m}^2/\text{g}$ by the BET method and an average particle diameter of $18 \mu\text{m}$ or more, and more preferably, a specific surface area of $0.2 \text{ m}^2/\text{g}$ or less and an average particle diameter of $20 \mu\text{m}$ or more, and still more preferably, a specific surface area of $0.16 \text{ m}^2/\text{g}$ or less and an average particle diameter of $20 \mu\text{m}$ or more. The nitride fluorescent material also preferably has a specific surface area of $0.1 \text{ m}^2/\text{g}$ or more, and an average particle diameter of $30 \mu\text{m}$ or less, and more preferably, $25 \mu\text{m}$ or less.

[0068] To improve emitting luminance, the nitride fluorescent material is a nitride containing an alkali earth metal, aluminium, silicon, and europium, and preferably has a specific surface area by the BET method of $0.1 \text{ m}^2/\text{g}$ to $0.16 \text{ m}^2/\text{g}$ and an average particle diameter of from $20 \mu\text{m}$ to $30 \mu\text{m}$. More preferably, the nitride fluorescent material has a composition represented by formula (I) and a specific surface area by the BET method of from $0.1 \text{ m}^2/\text{g}$ to $0.16 \text{ m}^2/\text{g}$ and an average particle diameter of from $20 \mu\text{m}$ to $30 \mu\text{m}$. To improve emitting luminance, the nitride fluorescent material is a nitride containing an alkali earth metal, aluminium, silicon, and europium, and preferably has a specific surface area

by the BET method of from 0.1 m²/g to 0.15 m²/g and an average particle diameter of from 20 μm to 30 μm. More preferably, the nitride fluorescent material has a composition of formula (I) wherein s = 0, a specific surface area by the BET method of from 0.1 m²/g to 0.15 m²/g, and an average particle diameter of from 20 μm to 30 μm.

[0069] The nitride fluorescent material preferably has a high crystalline structure in at least a portion thereof. For instance, since a glass body (amorphous) is of an irregular and less crystalline structure, the reaction conditions in the production process of a fluorescent material must be controlled to be strictly uniform. Otherwise, the ratio of components in the resultant fluorescent material varies, which is likely to cause chromaticity unevenness, for example. In contrast, the nitride fluorescent material according to the present embodiment is a powder or a granule having high crystallinity in at least a portion thereof, and thus may be easily produced and processed. In addition, the nitride fluorescent material can be uniformly dispersed in an organic medium, so that light emitting plastics and polymeric thin film materials, for example, can be readily produced. Specifically, the nitride fluorescent material is a crystalline structure in, for instance, 50 % by weight or more, and more preferably 80 % by weight or more. This indicates the proportion of a crystalline phase having light emission properties, and the presence of a crystalline phase of 50% by weight or more ensures emission of light enough for practical use. Thus the emitting luminance and ease of processability increase with the proportion of the crystalline phase.

[Light emitting device]

[0070] The present disclosure encompasses a light emitting device incorporating the nitride fluorescent material. The light emitting device at least includes a light emitting element having a peak emission wavelength in the range of, for instance, from 380 nm to 470 nm; and a fluorescent member containing at least a first fluorescent material including the nitride fluorescent material. The fluorescent member may further contain a second fluorescent material that emits green to yellow light. The light emitted by the light emitting device is a mix of light from the light emitting element and fluorescence from the fluorescent member. For instance, the light preferably has chromaticity coordinates defined by CIE 1931 of x = 0.220 to 0.340 and y = 0.160 to 0.340, and more preferably x = 0.220 to 0.330 and y = 0.170 to 0.330.

[0071] An example of a light emitting device 100 according to an embodiment of the present disclosure will be described with reference to the drawings. Fig. 1 is a schematic sectional view of an example of a light emitting device 100 according to the present disclosure. A light emitting device 100 is an example of a surface mounting type light emitting device.

[0072] The light emitting device 100 includes a nitride gallium compound semiconductor-light emitting element 10 that emits visible light at short wavelengths (e.g., in the range of from 380 nm to 485 nm) and has a peak emission wavelength of, for instance, from 440 nm to 460 nm, and a molded body 40 on which the light emitting element 10 is disposed. The molded body 40 includes a first lead 20, a second lead 30, and a resin portion 42, which are formed in an integral manner. Alternatively, a molded body 40 may be formed by a known method using a ceramic as a material in place of the resin portion 42. The molded body 40 has a recess defined by a bottom surface and side surfaces, and the light emitting element 10 is disposed on the bottom surface of the recess. The light emitting element 10 has a pair of electrodes, positive and negative, and the positive and negative electrodes are electrically connected to the first lead 20 and the second lead 30, respectively, with a wire 60. The light emitting element 10 is covered with a fluorescence member 50. The fluorescence member 50 contains, for example, a red light fluorescent material (a first fluorescent material 71) and a green light fluorescent material (a second fluorescent material 72) as a fluoride fluorescent material 70 that converts the wavelength of light emitted from the light emitting element 10, and a resin.

[0073] The fluorescence member 50 serves not only as a member containing a fluorescent material 70 for converting the wavelength, but also as a member for protecting the light emitting element 10 and the fluorescent material 70 from the outside environment. In Fig. 1, the particles of the fluorescent material 70 are unevenly dispersed in the fluorescence member 50. Arranging the particles of the fluorescent material 70 closer to the light emitting element 10 in this manner allows efficient conversion of the wavelength of light from the light emitting element 10, thereby providing a light emitting device with superior emitting efficiency. It should be noted that the arrangement of the particles of the fluorescent material 70 and the light emitting element 10 in the fluorescence member 50 is not limited to one in which they are in close proximity to each other, and the particles of the fluorescent material 70 may be arranged spaced apart from the light emitting element 10 within the fluorescence member 50 to avoid the influence of heat on the fluorescent material 70. The particles of the fluorescent material 70 may also be approximately evenly dispersed in the entire fluorescence member 50 so as to obtain light with further reduced color unevenness.

(Light emitting element)

[0074] The peak emission wavelength of the light emitting element lies in the range of, for instance, from 380 nm to 470 nm, and preferably from 440 nm to 460 nm. Using a light emitting element having a peak emission wavelength in this range as an excitation light source yields a light emitting device that emits light resulting from a mix of the light from the light emitting element and fluorescence from the fluorescent materials. In addition, because this allows effective use

of light radiated from the light emitting element to the outside, the loss of light emitted from the light emitting device can be minimized, resulting in a highly efficient light emitting device.

[0075] The half bandwidth of the light emission spectrum of the light emitting element may be, for instance, 30 nm or less.

[0076] The light emitting element preferably is a semiconductor light emitting element. Using a semiconductor light emitting element as the excitation light source yields a highly efficient light emitting device that has high output linearity to the input and is resistant and stable to mechanical impact.

[0077] For example, as a semiconductor light emitting element, a nitride semiconductor ($\text{In}_X\text{Al}_Y\text{Ga}_{1-X-Y}\text{N}$, wherein $0 \leq X$, $0 \leq Y$, and $X + Y \leq 1$) that emits blue or green light, for example, may be used as the semiconductor light emitting element.

(Fluorescent member)

[0078] The light emitting device includes a fluorescent member that converts a wavelength by absorbing a portion of light emitted from a light emitting element. The fluorescent member contains at least one first fluorescent material that emits red light, and may contain at least one second fluorescent material that emits green to yellow light. Examples of the first fluorescent material include the above-described nitride fluorescent material. For a second fluorescent material, a fluorescent material may be appropriately selected from green light fluorescent materials that emit fluorescence having a peak emission wavelength in the range of from 500 nm to 580 nm. By appropriately selecting the peak emission wavelength, light emission spectrum, and so forth of a second fluorescent material, the properties such as correlated color temperature and color rendering properties of the light emitting device may fall within the desired ranges. The fluorescent member may contain resin in addition to fluorescent materials. A light emitting device may include a fluorescent member that contains a fluorescent material and a resin, and covers a light emitting element.

[0079] The details of the nitride fluorescent material contained in the first fluorescent material are as follows. The content of a first fluorescent material in a light emitting device may be, for instance, from 0.1 part by weight to 50 parts by weight, and is preferably from 1 parts by weight to 30 parts by weight relative to 100 parts by weight of the resin contained in the fluorescent member.

[0080] The second fluorescent material emits fluorescence having peak emission wavelength in the range of, for instance, from 500 nm to 580 nm, and preferably from 520 nm to 550 nm. The second fluorescent material preferably is one selected from the group consisting of a β sialon fluorescent material having a composition represented by formula (IIa); a silicate fluorescent material having a composition represented by formula (IIb); a halosilicate fluorescent material having a composition represented by formula (IIc); a thiogallate fluorescent material having a composition represented by formula (IId); a rare earth aluminate fluorescent material having a composition represented by formula (IIe); an alkaline earth aluminate fluorescent material represented by formula (IIf); and an alkaline earth phosphate fluorescent material represented by formula (IIg). In particular, containing, as a second fluorescent material, at least one fluorescent material having a composition represented by formula (IIc), (IIe), (IIf) or (IIg) together with a first fluorescent material in a fluorescent member is preferable, because this combination improves color rendering properties of the light emitting device.



wherein w satisfies $0 < w \leq 4.2$.

(Ba,Sr,Ca,Mg) $_2\text{SiO}_4:\text{Eu}$ (IIb)

(Ca,Sr,Ba) $_8\text{MgSi}_4\text{O}_{16}(\text{F,Cl,Br})_2:\text{Eu}$ (IIc)

(Ba,Sr,Ca) $\text{Ga}_2\text{S}_4:\text{Eu}$ (IId)

(Y,Lu,Gd) $_3(\text{Al,Ga})_5\text{O}_{12}:\text{Ce}$ (IIe)

(Sr,Ca,Ba) $_4\text{Al}_4\text{O}_{25}:\text{Eu}$ (IIf)

(Ca,Sr,Ba) $_5(\text{PO}_4)_3(\text{Cl,Br}):\text{Eu}$ (IIg)

Preferably, w in the composition formula (IIa) satisfies $0.01 < w < 2$.

[0081] To improve emitting luminance, the average particle diameter of the second fluorescent material contained in a light emitting device is preferably from 2 μm to 35 μm , and more preferably from 5 μm to 30 μm .

[0082] The average particle diameter of a second fluorescent material is measured in the same manner as the average particle diameter of a first fluorescent material.

[0083] The content of a second fluorescent material in a light emitting device may be, for instance, from 1 part by weight to 70 parts by weight, and preferably from 2 parts by weight to 50 parts by weight relative to 100 parts by weight of the resin contained in the fluorescent member.

[0084] The ratio of a first fluorescent material to a second fluorescent material (first fluorescent material/second fluorescent material) in a light emitting device is, for instance, from 0.01 to 10 and preferably from 0.1 to 1 in terms of weight.

Other fluorescent materials

[0085] The light emitting device may contain another fluorescent material as necessary in addition to a first fluorescent material and a second fluorescent material. Examples of the other fluorescent material include $\text{Ca}_3\text{Sc}_2\text{Si}_3\text{O}_{12}:\text{Ce}$, $\text{CaSc}_2\text{O}_4:\text{Ce}$, $(\text{La},\text{Y})_3\text{Si}_6\text{N}_{11}:\text{Ce}$, $(\text{Ca},\text{Sr},\text{Ba})_3\text{Si}_6\text{O}_9\text{N}_4:\text{Eu}$, $(\text{Ca},\text{Sr},\text{Ba})_3\text{Si}_6\text{O}_{12}\text{N}_2:\text{Eu}$, $(\text{Ba},\text{Sr},\text{Ca})\text{Si}_2\text{O}_2\text{N}_2:\text{Eu}$, $(\text{Ca},\text{Sr},\text{Ba})_2\text{Si}_5\text{N}_8:\text{Eu}$, and $\text{K}_2(\text{Si},\text{Ti},\text{Ge})\text{F}_6:\text{Mn}$. When the light emitting device contains other fluorescent materials, the content thereof is, for instance, 10 % by weight or less, or 1 % by weight or less relative to the total amount of a first fluorescent material and a second fluorescent material.

[0086] The resin in the fluorescent member may include a thermoplastic resin or a thermosetting resin. Specific examples of the thermosetting resin include an epoxy resins and a silicone resin. The fluorescent member may contain another component as necessary in addition to a fluorescent material and a resin. Examples of the other component include a filler such as silica, barium titanate, titanium oxide, and aluminium oxide; a light stabilizer; and a colorant. When the fluorescence member contains another component, for instance, a filler, the amount contained may be from 0.01 part by weight to 20 parts by weight relative to 100 parts by weight of the resin.

EXAMPLES

[0087] Hereinafter, the Examples of the present disclosure will be specifically described, but the present disclosure is by no means limited to these Examples.

(Example 1)

[0088] Calcium nitride (Ca_3N_2), silicon nitride (Si_3N_4), elemental silicon (Si), aluminium nitride (AlN), and europium oxide (Eu_2O_3), which constitute a raw material compound, were weighed so as to have a molar ratio of Ca:Si:Al:Eu = 0.993:1.1:0.9:0.007, and mixed. Here, silicon nitride and elemental silicon were mixed so that the silicon nitride constitutes 41.6 % by weight and elemental silicon constitutes 58.4 % by weight. The resultant mixed raw material was charged into a crucible made of boron nitride, and heat-treated in a nitrogen atmosphere under the pressure of 0.92 MPa (gauge pressure) at 2000°C for 2 hours to obtain a nitride fluorescent material.

(Example 2)

[0089] A nitride fluorescent material was obtained in the same manner as Example 1 except that the mixing ratio of silicon nitride to elemental silicon was changed so that silicon nitride constitutes 37.5 % by weight and elemental silicon constitutes 62.5 % by weight.

(Example 3)

[0090] A nitride fluorescent material was obtained in the same manner as Example 1 except that the mixing ratio of silicon nitride to elemental silicon was changed so that silicon nitride constitutes 20.5 % by weight and elemental silicon constitutes 79.5 % by weight.

(Example 4)

[0091] A nitride fluorescent material was obtained in the same manner as Example 1 except that the mixing ratio of silicon nitride to elemental silicon was changed so that silicon nitride constitutes 70.6 % by weight and elemental silicon constitutes 29.4 % by weight.

(Example 5)

[0092] A nitride fluorescent material was obtained in the same manner as Example 1 except that the mixing ratio of silicon nitride to elemental silicon was changed so that silicon nitride constitutes 84.4 % by weight and elemental silicon constitutes 15.6 % by weight.

(Comparative Example 1)

[0093] A nitride fluorescent material was obtained in the same manner as Example 1 except that silicon nitride alone was used without using elemental silicon.

(Comparative Example 2)

[0094] A nitride fluorescent material was obtained in the same manner as Example 1 except that elemental silicon alone was used without using silicon nitride.

[0095] The resultant nitride fluorescent materials were evaluated for the following points.

Average particle diameter:

[0096] Samples of 1 cm³ were weighed using a Fisher Sub Sieve Sizer (F.S.S.S.) under the conditions of a temperature of 25°C and a humidity of 70 %RH. Each sample was packed into a dedicated tubular container, into which dried air of a given pressure is flown. For each sample, the specific surface area is determined from the difference in pressure, and the average particle diameter was calculated.

Specific surface area

[0097] For each nitride fluorescent material, the specific surface area was calculated by the dynamic constant-pressure method using Gemini 2370 manufactured by Shimadzu Corporation in accordance with the instruction manual.

Light emitting properties

[0098] The light emission spectrum of each nitride fluorescent material when excited at 460 nm was measured using F-4500 manufactured by Hitachi High-Technologies Corporation. The energy value: ENG (%) and peak emission wavelength: λ_p (nm) of the resultant light emission spectrum were calculated.

[0099] Table 1 shows the average particle diameter, specific surface area, λ_p , ENG (%) of each nitride fluorescent material. Each ENG (%) is a relative value when the energy value of the nitride fluorescent material of Comparative Example 1 is taken as 100%. Fig. 2 shows light emission spectra.

[Table 1]

	Weight percentages of Si material (%)		Average particle diameter (μm)	Specific surface area (m^2/g)	Light emitting properties	
	Si	Si_3N_4			λ_p (nm)	ENG (%)
Example 1	58.4	41.6	23.0	0.11	646	118.9
Example 2	37.5	62.5	23.0	0.13	651	115.4
Example 3	20.5	79.5	19.5	0.16	649	104.0
Example 4	70.6	29.4	20.5	0.11	649	114.9
Example 5	84.4	15.6	23.0	0.27	653	102.3
Comparative Example 1	0	100	17.0	0.23	652	100.0
Comparative Example 2	100	0	27.5	0.30	653	98.1

[0100] Comparative Example 1 is a fluorescent material using no elemental silicon and calcinated at 2000°C, and the ENG value of Comparative Example 1 serves as the reference. In Examples 1 to 5 where silicon nitride and elemental silicon were used in combination, specific surface areas were each less than 0.3 m²/g, the average particle diameters were each 18 μm or more, and ENGs were high, so that light emitting properties were superior.

[0101] Figs. 3 and 4 show scanning electron microscope (SEM) images of the nitride fluorescent materials of Comparative Example 1 and Example 1. In Comparative Example 1 shown in Fig. 3, large particles and fine particles are mixed. This is believed to be due to the fact that particles are sintered together when calcinated at a high temperature, and these particles are ground together during grinding process for dispersion to yield finer microparticles. In Example 1 as shown in Fig. 4, no such microparticles are present, because less grinding of particles occurred when the calcinated products were ground due to less sintering. The particles of the nitride fluorescent material of Example 1 suffer little damage during grinding process, so that the surfaces of particles are smooth as shown in Fig. 4, achieving high ENG

because of no mixture of microparticles with lower emitting luminance. A light emitting device containing a nitride fluorescent material of the present Examples are also believed to contain little microparticles that causes Rayleigh scattering, so that scattering of light emitted from the light emitting element towards the inside of the light emitting device (light emitting element) is minimized, accelerating scattering of light towards the outside of the light emitting device, i.e., the surface for taking out light (e.g., Mie scattering), achieving a light emitting device having high emitting efficiency.

[0102] This is believed to be attributable to the fact that, for instance, by using silicon nitride and elemental silicon in combination as raw materials, the amount of oxygen is reduced and thus sintering is suppressed compared to the case where silicon nitride alone is used, and change in volume that occurs when silicon turns into silicon nitride is also utilized to promote particle growth and reduce susceptibility to sintering.

[0103] In contrast, in Comparative Example 2 where no silicon nitride is used, the particle diameter and specific surface area are larger and ENG is lower. Since the formation of the fluorescent material and the nitriding of silicon are performed simultaneously, silicon is believed to be nitrided insufficiently, resulting in poor properties. Using silicon nitride and elemental silicon in combination accelerates nitriding of silicon, which is believed to produce this difference.

(Example 6)

[0104] A nitride fluorescent material was obtained in the same manner as Example 1 except that strontium nitride was used as a strontium compound, that the composition of the raw material mixture was changed so as to have a molar ratio of Sr:Ca:Si:Al:Eu = 0.099:0.891:1.1:0.9:0.01, and that the ratio of silicon nitride to elemental silicon was 37.5 % by weight to 62.5 % by weight.

(Comparative Example 3)

[0105] A nitride fluorescent material was obtained in the same manner as Example 6 except that silicon nitride alone without elemental silicon was used.

[0106] The resultant nitride fluorescent materials were evaluated in the same manner as described above. Table 2 shows the average particle diameter, specific surface area, λ_p , and ENG (%) of each nitride fluorescent material. ENG (%) is a relative value when the energy value of the nitride fluorescent material of Comparative Example 1 is taken as 100%. Fig. 5 shows resultant light emission spectra.

[Table 2]

	Weight percentages of Si material (%)		Average particle diameter (μm)	Specific surface area (m^2/g)	Light emitting properties	
	Si	Si_3N_4			λ_p (nm)	ENG (%)
Example 6	37.5	62.5	22.0	0.16	657	111.3
Comparative Example 3	0.0	100.0	19.5	0.31	663	99.5

[0107] As shown in Table 2 and Fig. 5, Example 6 has a peak emission wavelength of 657 nm, and Comparative Example 3 has a peak emission wavelength of 663 nm, both of which are longer than that of Example 1. This is believed to reflect changes in the amount of Eu. Like Examples 1 to 5, Example 6 also has a specific surface area of as small as 0.2 m^2/g or less, as a result of elemental silicon being added to the raw materials, and has higher light emitting properties than Comparative Example 3, demonstrating good results.


[0108] A light emitting device including a nitride fluorescent material obtained by a method for producing according to the present embodiment may be suitably used as, for example, a light source for lighting. In particular, the light emitting device may be suitably used for a light source for lighting, LED displays, backlight light sources, traffic signals, illuminated switches, and various indicators. Since a nitride fluorescent material having a high emitting luminance, for example, is obtained, the industrial applicability is significantly high.

[0109] It is to be understood that although the present invention has been described with regard to preferred embodiments thereof, various other embodiments and variants may occur to those skilled in the art, which are within the scope and spirit of the invention, and such other embodiments and variants are intended to be covered by the following claims.

[0110] All publications, patent applications, and technical standards mentioned in this specification are herein incorporated by reference to the same extent as if each individual publication, patent application, or technical standard was specifically and individually indicated to be incorporated by reference.


Claims

1. A method for producing a nitride fluorescent material, the method comprising heat-treating a raw material mixture comprising silicon nitride, silicon, an aluminium compound, a calcium compound, and a europium compound.
2. The method according to claim 1, wherein the aluminium compound comprises aluminium nitride.
3. The method according to claim 1 or 2, wherein the calcium compound comprises calcium nitride.
4. The method according to any one of claims 1 to 3, wherein the europium compound comprises europium oxide.
5. The method according to any one of claims 1 to 4, wherein the raw material mixture is heat-treated at 1200°C or more.
6. The method according to any one of claims 1 to 5, wherein content of silicon is from 10 % by weight to 85 % by weight relative to the total amount of silicon nitride and silicon in the raw material mixture.
7. The method according to any one of claims 1 to 6, wherein content of oxygen atom contained in the silicon nitride is from 0.3 % by weight to less than 2 % by weight.
8. The method according to any one of claims 1 to 7, wherein the nitride fluorescent material has a specific surface area by BET method of from 0.05 cm²/g to less than 0.3 cm²/g.
9. The method according to any one of claims 1 to 8, wherein the nitride fluorescent material has an average particle diameter of from 15 μm to 30 μm.
10. The method according to any one of claims 1 to 9, wherein the nitride fluorescent material has a specific surface area by BET method of from 0.1 cm²/g to 0.16 cm²/g, and the nitride fluorescent material has an average particle diameter of from 20 μm to 30 μm.
11. The method according to any one of claims 1 to 10, wherein the nitride fluorescent material has a composition represented by formula (I):



wherein s, t, u, v, and w respectively satisfy $0 \leq s < 1$, $0 < t \leq 1$, $s + t \leq 1$, $0.9 \leq u \leq 1.1$, $0.9 \leq v \leq 1.1$, and $2.5 \leq w \leq 3.5$.

12. A nitride fluorescent material comprising an alkali earth metal, aluminium, silicon, and europium, and having a specific surface area by the BET method of from 0.1 cm²/g to 0.16 cm²/g and an average particle diameter of from 20 μm to 30 μm.
13. The nitride fluorescent material according to claim 12, wherein the nitride fluorescent material has a composition represented by formula (I):



wherein s, t, u, v, and w respectively satisfy $0 \leq s < 1$, $0 < t \leq 1$, $s + t \leq 1$, $0.9 \leq u \leq 1.1$, $0.9 \leq v \leq 1.1$, and $2.5 \leq w \leq 3.5$.

14. A light emitting device comprising:

a fluorescent member comprising a first fluorescent material; and
a light emitting element having a peak emission wavelength in a range of from 380 nm to 470 nm,
wherein the first fluorescent material comprises the nitride fluorescent material according to claims 12 or 13.

15. A light emitting device according to claim 14, wherein the fluorescent member further comprises a second fluorescent material having a peak emission wavelength in a range of from 500 nm to 580 nm.

Fig. 1




Fig. 2




Fig. 3




Fig. 4





Fig 5





EUROPEAN SEARCH REPORT

Application Number
EP 16 18 4714

5

10

15

20

25

30

35

40

45

50

55

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X	WO 2007/052200 A1 (PHILIPS INTELLECTUAL PROPERTY [DE]; KONINKL PHILIPS ELECTRONICS NV [NL] 10 May 2007 (2007-05-10)	12-15	INV. C09K11/77 H01L33/50 C09K11/08
A	* page 12; example 1 *	1-11	

A	2+ ET AL: "Synthesis and Luminescence Properties of (Sr,Ca)AlSiN ₃ :Eu Phosphors under Atmospheric-Pressure", ECS Journal of Solid State Science and Technology, 1 January 2014 (2014-01-01), pages 234-237, XP055314821, DOI: 10.1149/2.0061412jss] Retrieved from the Internet: URL:http://jss.ecsdl.org/content/3/12/R234.full.pdf#page=1&view=FiTH [retrieved on 2016-10-28]	1-15	
	* see "Experimental" *		

A	US 2006/033083 A1 (SAKANE KENJI [JP] ET AL) 16 February 2006 (2006-02-16)	1-15	TECHNICAL FIELDS SEARCHED (IPC)
	* examples 1-8 *		

A	EP 2 610 217 A1 (UBE INDUSTRIES [JP]) 3 July 2013 (2013-07-03)	1-15	C09K H01L
	* examples 1-10 *		

The present search report has been drawn up for all claims			
Place of search		Date of completion of the search	Examiner
The Hague		8 November 2016	Poole, Robert
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03 82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 16 18 4714

5 This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

08-11-2016

10

Patent document
cited in search report

Publication
date

Patent family
member(s)

Publication
date

15

WO 2007052200 A1 10-05-2007 CN 101305072 A 12-11-2008
EP 1948757 A1 30-07-2008
JP 5356822 B2 04-12-2013
JP 2009515333 A 09-04-2009
US 2008290785 A1 27-11-2008
WO 2007052200 A1 10-05-2007

20

US 2006033083 A1 16-02-2006 EP 1788063 A1 23-05-2007
JP 4422653 B2 24-02-2010
JP 2006063323 A 09-03-2006
KR 20070041760 A 19-04-2007
KR 20100023054 A 03-03-2010
KR 20110025238 A 09-03-2011
TW 1391470 B 01-04-2013

25

US 2006033083 A1 16-02-2006
US 2009085010 A1 02-04-2009
US 2010301272 A1 02-12-2010
WO 2006011542 A1 02-02-2006

30

EP 2610217 A1 03-07-2013 CN 103201213 A 10-07-2013
EP 2610217 A1 03-07-2013
JP 5910498 B2 11-05-2016
KR 20130098322 A 04-09-2013
US 2013140490 A1 06-06-2013
WO 2012017949 A1 09-02-2012

35

40

45

50

55

ORM P0459

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 2008303331 A [0002]
- JP 2006008721 A [0003]