



US008993421B2

(12) **United States Patent**  
**Tanaka et al.**

(10) **Patent No.:** **US 8,993,421 B2**  
(45) **Date of Patent:** **Mar. 31, 2015**

(54) **LASER IRRADIATION METHOD, LASER IRRADIATION APPARATUS, AND METHOD OF MANUFACTURING A SEMICONDUCTOR DEVICE**

(71) Applicant: **Semiconductor Energy Laboratory Co., Ltd.**, Atsugi-shi, Kanagawa-ken (JP)

(72) Inventors: **Koichiro Tanaka**, Atsugi (JP); **Tomoaki Morioka**, Atsugi (JP)

(73) Assignee: **Semiconductor Energy Laboratory Co., Ltd.**, Atsugi-shi, Kanagawa-ken (JP)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/021,439**

(22) Filed: **Sep. 9, 2013**

(65) **Prior Publication Data**

US 2014/0011343 A1 Jan. 9, 2014

**Related U.S. Application Data**

(60) Continuation of application No. 10/866,802, filed on Jun. 15, 2004, now Pat. No. 8,530,788, which is a division of application No. 10/279,054, filed on Oct. 24, 2002, now Pat. No. 6,750,423.

(30) **Foreign Application Priority Data**

Oct. 25, 2001 (JP) ..... 2001-327196  
Oct. 25, 2001 (JP) ..... 2001-327208

(51) **Int. Cl.**  
**H01L 21/02** (2006.01)  
**B23K 26/06** (2014.01)  
**B23K 26/067** (2006.01)

(Continued)

(52) **U.S. Cl.**  
CPC ..... **H01L 21/02592** (2013.01); **B23K 26/0604** (2013.01); **B23K 26/0608** (2013.01); **B23K 26/067** (2013.01); **B23K 26/0732** (2013.01); **B23K 26/0736** (2013.01); **B23K 26/0738** (2013.01); **H01L 27/1285** (2013.01)

USPC ..... **438/487**

(58) **Field of Classification Search**

CPC ..... H01L 27/1214; H01L 21/02532; H01L 21/02678; H01L 21/268; H01L 27/1296  
USPC ..... 438/487  
See application file for complete search history.

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

4,726,849 A 2/1988 Murata et al.  
4,908,493 A 3/1990 Susemihl

(Continued)

**FOREIGN PATENT DOCUMENTS**

JP 08-195357 7/1996  
JP 08-309574 11/1996


*Primary Examiner* — Tony Tran

(74) *Attorney, Agent, or Firm* — Eric J. Robinson; Robinson Intellectual Property Law Office, P.C.

(57) **ABSTRACT**

In the present invention, each laser light emitted from a plurality of lasers is divided, and laser light including at least one laser light that is emitted from a different laser and that has different energy distribution is synthesized with another such laser light, or laser light including at least one laser light that has different energy distribution is synthesized with another such laser light through a convex lens that is set at an angle to the direction each laser light travels, to form laser light having excellent uniformity in energy distribution.

**11 Claims, 25 Drawing Sheets**



(51)	<b>Int. Cl.</b>		6,043,453	A	3/2000	Arai
	<b>B23K 26/073</b>		6,055,346	A	4/2000	Godard et al.
	<b>H01L 27/12</b>		6,239,913	B1	5/2001	Tanaka
			6,313,434	B1	11/2001	Patterson et al.
(56)	<b>References Cited</b>		6,393,042	B1	5/2002	Tanaka
			6,396,616	B1	5/2002	Fitzer et al.
			6,567,219	B1	5/2003	Tanaka
			6,573,162	B2	6/2003	Tanaka et al.
			6,580,055	B2	6/2003	Iso
			6,621,636	B2	9/2003	Tanaka et al.
			6,750,423	B2	6/2004	Tanaka et al.
			6,852,947	B2	2/2005	Tanaka
			6,955,956	B2	10/2005	Tanaka et al.
			2003/0035219	A1	2/2003	Tanaka
			2003/0042430	A1	3/2003	Tanaka et al.
			2003/0089691	A1	5/2003	Tanaka
			2005/0111339	A1	5/2005	Tanaka
U.S. PATENT DOCUMENTS						
	4,978,970	A	12/1990	Okazaki		
	5,145,808	A	9/1992	Sameshima et al.		
	5,208,187	A	5/1993	Tsubouchi et al.		
	5,212,710	A	5/1993	Kaneda et al.		
	5,463,202	A	10/1995	Kurosawa et al.		
	5,815,494	A	9/1998	Yamazaki et al.		
	5,854,803	A	12/1998	Yamazaki et al.		
	5,869,803	A	2/1999	Noguchi et al.		
	5,959,779	A	9/1999	Yamazaki et al.		




Fig. 1

Fig. 2A




Fig. 2B





Fig2C






Fig. 3

Fig. 4A




Fig. 4B




Fig. 4C




Fig. 4D




Fig. 4E

synthesis

- 1. First laser light
- 2. Second laser light
- 3. Third laser light
- 4. Fourth laser light






Fig. 5




Fig. 6






Fig. 7





Fig. 8






Fig. 10

PRIOR ART

Fig. 11A





Fig. 11B



PRIOR ART

Fig. 12A




Fig. 12B







Fig. 12C




File 13A




1  
 2  
 3  
 4  
 5  
 6  
 7  
 8  
 9  
 10  
 11  
 12  
 13  
 14  
 15  
 16  
 17  
 18  
 19  
 20  
 21  
 22  
 23  
 24  
 25  
 26  
 27  
 28  
 29  
 30  
 31  
 32  
 33  
 34  
 35  
 36  
 37  
 38  
 39  
 40  
 41  
 42  
 43  
 44  
 45  
 46  
 47  
 48  
 49  
 50  
 51  
 52  
 53  
 54  
 55  
 56  
 57  
 58  
 59  
 60  
 61  
 62  
 63  
 64  
 65  
 66  
 67  
 68  
 69  
 70  
 71  
 72  
 73  
 74  
 75  
 76  
 77  
 78  
 79  
 80  
 81  
 82  
 83  
 84  
 85  
 86  
 87  
 88  
 89  
 90  
 91  
 92  
 93  
 94  
 95  
 96  
 97  
 98  
 99  
 100  
 101  
 102  
 103  
 104  
 105  
 106  
 107  
 108  
 109  
 110  
 111  
 112  
 113  
 114  
 115  
 116  
 117  
 118  
 119  
 120  
 121  
 122  
 123  
 124  
 125  
 126  
 127  
 128  
 129  
 130  
 131  
 132  
 133  
 134  
 135  
 136  
 137  
 138  
 139  
 140  
 141  
 142  
 143  
 144  
 145  
 146  
 147  
 148  
 149  
 150  
 151  
 152  
 153  
 154  
 155  
 156  
 157  
 158  
 159  
 160  
 161  
 162  
 163  
 164  
 165  
 166  
 167  
 168  
 169  
 170  
 171  
 172  
 173  
 174  
 175  
 176  
 177  
 178  
 179  
 180  
 181  
 182  
 183  
 184  
 185  
 186  
 187  
 188  
 189  
 190  
 191  
 192  
 193  
 194  
 195  
 196  
 197  
 198  
 199  
 200  
 201  
 202  
 203  
 204  
 205  
 206  
 207  
 208  
 209  
 210  
 211  
 212  
 213  
 214  
 215  
 216  
 217  
 218  
 219  
 220  
 221  
 222  
 223  
 224  
 225  
 226  
 227  
 228  
 229  
 230  
 231  
 232  
 233  
 234  
 235  
 236  
 237  
 238  
 239  
 240  
 241  
 242  
 243  
 244  
 245  
 246  
 247  
 248  
 249  
 250  
 251  
 252  
 253  
 254  
 255  
 256  
 257  
 258  
 259  
 260  
 261  
 262  
 263  
 264  
 265  
 266  
 267  
 268  
 269  
 270  
 271  
 272  
 273  
 274  
 275  
 276  
 277  
 278  
 279  
 280  
 281  
 282  
 283  
 284  
 285  
 286  
 287  
 288  
 289  
 290  
 291  
 292  
 293  
 294  
 295  
 296  
 297  
 298  
 299  
 300  
 301  
 302  
 303  
 304  
 305  
 306  
 307  
 308  
 309  
 310  
 311  
 312  
 313  
 314  
 315  
 316  
 317  
 318  
 319  
 320  
 321  
 322  
 323  
 324  
 325  
 326  
 327  
 328  
 329  
 330  
 331  
 332  
 333  
 334  
 335  
 336  
 337  
 338  
 339  
 340  
 341  
 342  
 343  
 344  
 345  
 346  
 347  
 348  
 349  
 350  
 351  
 352  
 353  
 354  
 355  
 356  
 357  
 358  
 359  
 360  
 361  
 362  
 363  
 364  
 365  
 366  
 367  
 368  
 369  
 370  
 371  
 372  
 373  
 374  
 375  
 376  
 377  
 378  
 379  
 380  
 381  
 382  
 383  
 384  
 385  
 386  
 387  
 388  
 389  
 390  
 391  
 392  
 393  
 394  
 395  
 396  
 397  
 398  
 399  
 400  
 401  
 402  
 403  
 404  
 405  
 406  
 407  
 408  
 409  
 410  
 411  
 412  
 413  
 414  
 415  
 416  
 417  
 418  
 419  
 420  
 421  
 422  
 423  
 424  
 425  
 426  
 427  
 428  
 429  
 430  
 431  
 432  
 433  
 434  
 435  
 436  
 437  
 438  
 439  
 440  
 441  
 442  
 443  
 444  
 445  
 446  
 447  
 448  
 449  
 450  
 451  
 452  
 453  
 454  
 455  
 456  
 457  
 458  
 459  
 460  
 461  
 462  
 463  
 464  
 465  
 466  
 467  
 468  
 469  
 470  
 471  
 472  
 473  
 474  
 475  
 476  
 477  
 478  
 479  
 480  
 481  
 482  
 483  
 484  
 485  
 486  
 487  
 488  
 489  
 490  
 491  
 492  
 493  
 494  
 495  
 496  
 497  
 498  
 499  
 500  
 501  
 502  
 503  
 504  
 505  
 506  
 507  
 508  
 509  
 510  
 511  
 512  
 513  
 514  
 515  
 516  
 517  
 518  
 519  
 520  
 521  
 522  
 523  
 524  
 525



Fi. 13C





1415






Fig. 15





Fig. 16



7  
1  
5  
b  
b  
b




Fig. 18A




Fig. 18B




Fig. 18C




Fig. 18D




Fig. 18 E




Fig. 18.F




Fig. 19A




Fig. 19B




Fig. 19C




Fig. 19D




Fig. 20A




Fig. 20B




Fig. 20C





Fig. 21








Fig. 23




Fig. 24




Fig. 25

1

# LASER IRRADIATION METHOD, LASER IRRADIATION APPARATUS, AND METHOD OF MANUFACTURING A SEMICONDUCTOR DEVICE

## FIELD OF THE INVENTION

The present invention relates to a laser beam irradiation method and a laser irradiation apparatus for using the method (apparatus including a laser and an optical system for guiding laser beam emitted from the laser to an object to be irradiated). In addition, the present invention relates to a method of manufacturing a semiconductor device, which includes a laser beam irradiation step. Note that a semiconductor device described here includes an electro-optical device such as a liquid crystal display device or a light-emitting device and an electronic device that includes the electro-optical device as a part.

## DESCRIPTION OF THE RELATED ART

In recent years, a wide study has been made on a technique in which laser annealing is performed for a semiconductor film formed on an insulating substrate made of glass or the like, to crystallize the film, to improve its crystallinity so that a crystalline semiconductor film is obtained, or to activate an impurity element. Note that a crystalline semiconductor film in this specification indicates a semiconductor film in which a crystallized region is present, and also includes a semiconductor film that is crystallized as a whole.

A method of forming pulse laser beam from an excimer laser or the like by an optical system such that it becomes a square shape or a linear shape on an irradiation surface, and scanning the laser beam (or relatively shifting an irradiation position of the laser beam with respect to the irradiation surface) to conduct annealing is superior in mass productivity and is excellent in technology. The "linear shape" described here means not a "line" in the strict sense but a rectangle (or a prolate ellipsoid shape) having a high aspect ratio. For example, it indicates a shape having an aspect ratio of 10 or more (preferably, 100 to 10000). Note that the linear shape is used to obtain an energy density required for sufficiently annealing an object to be irradiated. Thus, if sufficient annealing is conducted for the object to be irradiated, it may be either a rectangular shape or a planar. Presently, excimer lasers with 15 J/pulse come onto the market and there is a possibility to perform a laser anneal by a planar beam. Further, the spot of the laser light is made laser light's energy distribution on an irradiation surface of the laser light when there is not a special definition.

FIG. 10 shows an example of a configuration of an optical system for forming laser beam in a linear shape on an irradiation surface. This configuration is extremely general. All optical systems described above are based on the configuration shown in FIG. 10. According to the configuration, a cross sectional shape of laser beam is converted into a linear shape, and simultaneously an energy density distribution of laser beam on the irradiation surface is homogenized. In general, an optical system for homogenizing the energy density distribution of laser beam is called a beam homogenizer.

The spot of the laser beam emitted from a laser 71 is divided by a cylindrical lens array 73. The direction is called a first direction in this specification. It is assumed that, when a mirror is inserted in a course of an optical system, the above-mentioned first direction is changed in accordance with a direction of light bent by the above-mentioned mirror. In this configuration, the cylindrical lens array is divided into

2

seven parts. Then, the laser beams are superposed on an irradiation surface 79 by a cylindrical lens 74, thereby homogenizing an energy density distribution of the linear laser beam in the longitudinal direction, and the length of the longitudinal direction is determined.

Next, the configuration shown in the side view of FIG. 10 will be described. The spot of the laser beam emitted from a laser 71 is divided by cylindrical lens arrays 72a and 72b. The direction is called a second direction in this specification. It is assumed that, when a mirror is inserted in a course of an optical system, the second direction is changed in accordance with a direction of light bent by the mirror. In this configuration, the cylindrical lens arrays 72a and 72b each are divided into four parts. The divided laser beams are temporarily synthesized by a cylindrical lens 74. After that, the laser beams are reflected by a mirror 77 and then condensed by a doublet cylindrical lens 78 so that they become again single laser beam on the irradiation surface 79. The doublet cylindrical lens 78 is a lens composed of two cylindrical lenses. Thus, an energy density distribution of the linear laser beam in a width direction is homogenized, thereby homogenizing an energy density distribution of the linear laser beam in the longitudinal direction, and the length of the width direction is determined.

For example, an excimer laser in which a size in a laser window is 10 mm×30 mm (which each are a half-width in beam profile) is used as the laser 71 and laser beam is produced by the optical system having the configuration shown in FIG. 10. Then, linear laser beam which has a uniform energy density distribution and a size of 125 mm×0.4 mm can be obtained on the irradiation surface 79.

At this time, when, for example, quartz is used for all base materials of the optical system, high transmittance is obtained. Note that coating is preferably conducted for the optical system such that transmittance of 99% or more is obtained at a frequency of the used excimer laser.

Then, the linear laser beam formed by the above configuration is irradiated with an overlap state while being gradually shifted in a width direction thereof. Thus, when laser annealing is performed for the entire surface of an amorphous semiconductor film, the amorphous semiconductor film can be crystallized, crystallinity can be improved to obtain a crystalline semiconductor film, or an impurity element can be activated.

At an edge of linear, rectangular, or sheet-like laser light formed on an irradiation surface or in the vicinity thereof by an optical system, the energy density is attenuated gradually due to aberration of a lens or the like (FIG. 11A). In this specification, a region at a laser light edge where the energy density is gradually attenuated is called an attenuation region.

As the substrate area is increased and the laser power is raised, it is now possible to form a longer linear beam or rectangular beam and a larger sheet-like beam. Annealing with such laser light is more efficient. However, the energy density of laser light emitted from a laser is smaller at its edge than around the center. Therefore, if laser light is expanded by an optical system more than prior art, attenuation in the attenuation region is intensified.

In the attenuation region, the energy density is lower than a region having a high uniformity in energy density and the low energy density is attenuated gradually. For that reason, an irradiation object cannot be annealed uniformly by laser light that has the attenuation region (FIG. 11B). Even when the laser light scans an irradiation object for annealing in a manner that makes the attenuation regions overlap each other, it still is impossible to anneal the irradiation object uniformly because annealing conditions of the attenuation region are

entirely different from annealing conditions of the highly uniform region. Accordingly, a region annealed by the attenuation region of laser light and a region annealed by the highly uniform region of the laser light cannot be treated equally.

For example, when a semiconductor film is an irradiation object, a region of the semiconductor film that is annealed by the attenuation region and a region of the semiconductor film that is annealed by the highly uniform region have different crystallinity. Therefore, if this semiconductor film varied in crystallinity from one region to another is used to manufacture TFTs, the electric characteristic of a TFT formed from the region that is annealed by the attenuation region is inferior to other TFTs and causes fluctuation among the TFTs on the same substrate.

As shown in FIG. 10, a complicate optical system is needed to form a linear beam. Optical adjustment for an optical system as such is very difficult to perform and, in addition, the apparatus has to be large in size because of large footprint.

If laser light used has high reflectance against an irradiation object and the laser light enters the irradiation object perpendicular to the object, the light goes back the light path it used upon entering the irradiation object (return light). Return light affects laser apparatus by changing the laser output and frequency and by breaking a rod.

#### SUMMARY OF THE INVENTION

The present invention has been made in view of the above, and an object of the present invention is therefore to provide laser irradiation apparatus which uses a simpler optical system than prior art to form a rectangular beam with the attenuation region at a laser light edge reduced for efficient annealing. Another object of the present invention is to provide a laser irradiation method using this laser irradiation apparatus as well as a method of manufacturing a semiconductor device which includes the laser irradiation method in its process.

The present invention is characterized in that laser beams emitted from a plurality of lasers are each divided and that laser beams emitted from different lasers and having different energy distributions are synthesized to form laser light having excellent uniformity in energy distribution. Here, energy distributions which are not identical but become the same distribution by rotation are deemed as different energy distributions. Also, the present invention is characterized in that laser beams emitted from a plurality of lasers are each divided, and that a laser beam including at least one laser beam that is emitted from a different laser and is in a different positional relation is synthesized with another such laser beam to form laser light having excellent uniformity in energy distribution.

Also, the present invention is characterized in that laser beams emitted from a plurality of lasers are each divided, and that laser beams emitted from different lasers and having different energy distributions enter a convex lens at an angle, exit the convex lens, and are synthesized on an irradiation surface or in the vicinity thereof to form rectangular laser light having excellent uniformity in energy distribution.

Even when laser beams emitted from different lasers are overlapped, they do not interfere each other. Accordingly the present invention is effective especially for laser light irradiation that uses highly interferential lasers such as a YVO<sub>4</sub> laser having a coherent length of several tens to several hundreds m and a YAG laser having a coherent length of 1 cm or more.

By making laser light enter a convex lens at an angle, astigmatism or other aberration is caused to shape laser light into a linear shape on an irradiation surface or in the vicinity thereof.

When a divided laser beam is overlapped with another divided laser beam, it is preferred to overlap laser beams having different energy distributions from one another. This is because overlapping a large number of laser beams that have different energy distributions produces uniform laser light.

A structure of the present invention disclosed in this specification is laser irradiation apparatus characterized by comprising: a plurality of lasers; means for dividing each of plural first laser beams emitted from the plural lasers into plural second laser beams; and means for choosing one laser beam out of the second laser beams for each of the plural first laser beams and synthesizing the chosen second laser beams in the same region on an irradiation surface or in the vicinity thereof.

In the above structure, the laser irradiation apparatus is characterized in that the lasers are continuous wave or pulse oscillation solid-state lasers or gas lasers or metal lasers. Examples of the solid-state lasers include a continuous wave or pulse oscillation YAG laser, YVO<sub>4</sub> laser, YLF laser, YAlO<sub>3</sub> laser, Y<sub>2</sub>O<sub>3</sub> laser, glass laser, ruby laser, alexandrite laser, and Ti:sapphire laser. Examples of the gas lasers include a continuous wave or pulse oscillation excimer laser, Ar laser, Kr laser, and CO<sub>2</sub> laser. Examples of the metal lasers include a continuous wave or pulse oscillation helium cadmium laser, copper steam laser, and gold steam laser.

In the above structure, the laser light is desirably converted into harmonic by a non-linear optical element. For example, a YAG laser is known to output laser light having a wavelength of 1065 nm as the fundamental wave. This laser light is absorbed by a silicon film at a very low absorption coefficient and it is technically very difficult to crystallize an amorphous silicon film, one of semiconductor films, with this laser light. However, this laser light can be converted into a shorter wavelength by a non-linear optical element. Examples of harmonic thereof include the second harmonic (532 nm), the third harmonic (355 nm), the fourth harmonic (266 nm), and the fifth harmonic (213 nm). These harmonics are absorbed in an amorphous silicon film at a high absorption coefficient and therefore can be used in crystallization of an amorphous silicon film.

In the above structure, the laser irradiation apparatus is characterized in that the dividing means is one or more kinds selected from a slit, a mirror, a prism, a cylindrical lens, and a cylindrical lens array.

In the above structure, the laser irradiation apparatus is characterized in that the synthesizing means is one or more kinds selected from a mirror and a cylindrical lens.

A structure of the present invention disclosed in this specification is a method of laser irradiation, characterized by comprising: dividing each of plural first laser beams that are emitted from a plurality of lasers into plural second laser beams; choosing one laser beam out of the second laser beams for each of the plural first laser beams and synthesizing the laser beams in the same region on an irradiation surface or in the vicinity thereof.

In the above structure, the laser irradiation apparatus is characterized in that the lasers are continuous wave or pulse oscillation solid-state lasers or gas lasers or metal lasers. Examples of the solid-state lasers include a continuous wave or pulse oscillation YAG laser, YVO<sub>4</sub> laser, YLF laser, YAlO<sub>3</sub> laser, Y<sub>2</sub>O<sub>3</sub> laser, glass laser, ruby laser, alexandrite laser, and Ti:sapphire laser. Examples of the gas lasers include a continuous wave or pulse oscillation excimer laser, Ar laser, Kr laser, and CO<sub>2</sub> laser. Examples of the metal lasers include a continuous wave or pulse oscillation helium cadmium laser, copper steam laser, and gold steam laser.

5

In the above structure, the laser light is desirably converted into harmonic by a non-linear optical element.

A structure of the present invention disclosed in this specification is a method of manufacturing a semiconductor device, characterized by comprising: dividing each of plural first laser beams that are emitted from a plurality of lasers into plural second laser beams; choosing one laser beam out of the second laser beams for each of the plural first laser beams to obtain third laser beams and synthesizing the third laser beams in the same region on an irradiation surface or in the vicinity thereof to form a fourth laser beam; and irradiating a semiconductor film with the fourth laser beam while moving the laser beam relative to the semiconductor film.

In the above structure, the laser irradiation apparatus is characterized in that the lasers are continuous wave or pulse oscillation solid-state lasers or gas lasers or metal lasers. Examples of the solid-state lasers include a continuous wave or pulse oscillation YAG laser, YVO<sub>4</sub> laser, YLF laser, YAlO<sub>3</sub> laser, Y<sub>2</sub>O<sub>3</sub> laser, glass laser, ruby laser, alexandrite laser, and Ti:sapphire laser. Examples of the gas lasers include a continuous wave or pulse oscillation excimer laser, Ar laser, Kr laser, and CO<sub>2</sub> laser. Examples of the metal lasers include a continuous wave or pulse oscillation helium cadmium laser, copper steam laser, and gold steam laser.

In the above structure, the laser light is desirably converted into harmonic by a non-linear optical element.

In the above structure, the semiconductor film is desirably a film containing silicon. A glass substrate, a quartz substrate, a silicon substrate, a plastic substrate, a metal substrate, a stainless steel substrate, a flexible substrate, etc. can be used as a substrate on which the semiconductor film is formed. Examples of the glass substrate include a barium borosilicate glass substrate and an aluminoborosilicate glass substrate. A flexible substrate means a substrate in the form of a PET, PES, PEN, or acrylic film or other similar film. When a flexible substrate is used to manufacture a semiconductor device, the device can have a reduced weight. It is desirable to form on the front side, or on the front side and back side, of a flexible substrate a single layer or multi-layer of aluminum films (AlON, AlN, AlO, or the like), carbon films (DLC (diamond-like carbon) or the like), or SiN films as a barrier layer because the barrier layer improves the durability and other properties.

The present invention synthesizes laser beams emitted from different lasers on an irradiation surface or in the vicinity thereof and therefore interference does not take place. Most desirably, laser beams having different energy distributions from one another are synthesized on an irradiation surface or in the vicinity thereof. However, since the optimum synthesizing method varies from one laser light mode to another, the synthesizing method used can be chosen to suit individual cases. For example, laser light in the TEM<sub>00</sub> mode is highly symmetrical and therefore laser light having a relatively high uniformity can be obtained by dividing laser light into two and synthesizing the left half and right half thereof. Needless to say, more highly uniform laser light is obtained when the number of division is larger. Laser light in other modes can also provide highly uniform laser light using the same method.

The present invention can irradiate a semiconductor film formed on a substrate with a rectangular beam having highly uniform energy distribution. Accordingly, a semiconductor film of uniform physical property can be obtained. This makes it possible to reduce fluctuation in electric characteristic of TFTs manufactured from this semiconductor film.

6

This also improves the operation characteristic and reliability of a semiconductor device manufactured from these TFTs.

## BRIEF DESCRIPTION OF THE DRAWINGS

In the accompanying drawings:

FIG. 1 is a diagram showing an example of an optical system of the present invention;

FIGS. 2A to 2C are diagrams showing an example of laser light being divided by the optical system of FIG. 1;

FIG. 3 is a diagram showing an example of an optical system of the present invention;

FIGS. 4A to 4E are diagrams showing an example of laser light being divided by the optical system of FIG. 3;

FIG. 5 is a diagram showing an example of a rectangular beam shape formed on an irradiation surface by the optical system of FIG. 3;

FIG. 6 is a diagram showing an example of an optical system of the present invention;

FIG. 7 is a diagram showing an example of an optical system of the present invention;

FIG. 8 is a diagram showing an example of an optical system of the present invention;

FIG. 9 is a diagram showing an example of an optical system of the present invention;

FIG. 10 is a diagram showing an example of a conventional optical system;

FIGS. 11A and 11B are a diagram showing an example of energy density distribution of laser light formed by a conventional optical system and a diagram showing an example of annealing a large-area substrate with the laser light shown in FIG. 11A, respectively;

FIGS. 12A to 12C are sectional views showing a process of manufacturing a pixel TFT and TFTs of a driving circuit;

FIGS. 13A to 13C are sectional views showing a process of manufacturing a pixel TFT and TFTs of a driving circuit;

FIG. 14 is a sectional view showing a process of manufacturing a pixel TFT and is of a driving circuit;

FIG. 15 is a top view showing the structure of a pixel TFT;

FIG. 16 is a sectional view of an active matrix liquid crystal display device;

FIG. 17 is a sectional structural view of a driving circuit and pixel portion of a light emitting device;

FIGS. 18A to 18F are diagrams showing examples of a semiconductor device;

FIGS. 19A to 19D are diagrams showing examples of a semiconductor device;

FIGS. 20A to 20C are diagrams showing examples of a semiconductor device;

FIG. 21 is a diagram showing an example of an optical system of the present invention;

FIGS. 22A to 22D are diagrams showing an example of laser light being divided by the optical system of FIG. 21;

FIG. 23 is a diagram for obtaining an incident angle  $\theta$  of laser light entering an irradiation object;

FIG. 24 is a diagram showing an example of an optical system of the present invention; and

FIG. 25 is a diagram showing an example of a laser light shape formed on an irradiation surface by the present invention.

## DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

### Embodiment Mode 1

This embodiment mode describes with reference to FIG. 1 and FIGS. 2A to 2C an example of optical system for dividing

laser beams that are emitted from a plurality of lasers and overlapping laser beams that have different energy distributions from one another.

A laser **101a** and a laser **101b** each emit laser light. The lasers **101a** and **101b** used here are continuous wave or pulse oscillation solid-state lasers, gas lasers, or metal lasers. Examples of the solid-state lasers include a continuous wave or pulse oscillation YAG laser, YVO<sub>4</sub> laser, YLF laser, YAlO<sub>3</sub> laser, Y<sub>2</sub>O<sub>3</sub> laser, glass laser, ruby laser, alexandrite laser, and Ti:sapphire laser. Examples of the gas lasers include a continuous wave or pulse oscillation excimer laser, Ar laser, Kr laser, and CO<sub>2</sub> laser. Examples of the metal lasers include a continuous wave or pulse oscillation helium cadmium laser, copper steam laser, and gold steam laser. The laser light emitted from the lasers **101a** and **101b** may be converted into harmonic by a non-linear optical element.

Denoted by **102a** and **102b** are isolators. If laser light used has high reflectance against an irradiation object and the laser light enters the irradiation object perpendicular to the object, the light goes back the light path it used upon entering the irradiation object (return light). Return light affects laser apparatus by changing the laser output and frequency and by breaking a rod. Components of the optical system in this embodiment mode are arranged symmetrically and therefore reflected light of the two lasers on the irradiation surface may mutually affect the other laser in a way similar to return light. This is why installing the isolators **102a** and **102b** is desirable.

Each of the laser light emitted is expanded by beam expanders **103a** and **104a**, or **103b** and **104b**. Beam expanders are effective especially when laser light emitted from a laser has a small shape, and may be omitted depending on the size of laser light. The laser light may be expanded not only in one direction but also in two directions. The cylindrical lenses **103a**, **104a**, **103b**, and **104b** are desirably made of synthetic silica glass because it gives them high transmittance. Coating on the surfaces of the cylindrical lenses **103a** and **104a**, or **103b** and **104b** is desirably capable of providing 99% or higher transmittance for the wavelength of laser light used.

The laser light that exits the beam expanders **103a** and **104a** or **103b** and **104b** is divided in two directions by a mirror **105a** or **105b**. The mirror **105a** or **105b** dividing the laser light is described referring to FIGS. 2A and 2B. FIGS. 2A and 2B show laser light shapes in section perpendicular to the direction the laser light travels. Laser light emitted from the laser **101a** is divided into first laser light and second laser light by the mirror **105a** as shown in FIG. 2A. The second laser light enters an irradiation object **108** whereas the first laser light is absorbed by a damper **107a**. On the other hand, laser light emitted from the laser **101b** is divided into third laser light and fourth laser light by the mirror **105b** as shown in FIG. 2B. The third laser light enters the irradiation object **108** whereas the fourth laser light is absorbed in a damper **107b**.

The two laser beams entering the irradiation object **108** do not interfere each other even when synthesized because they are emitted from different lasers. Since the second laser light of laser light emitted from the laser **101a** enters the irradiation object and the third laser light of laser light emitted from the laser **101b** enters the irradiation object, laser beams having different energy distributions are synthesized on the irradiation surface or in the vicinity thereof. As a result, rectangular laser light having excellent uniformity in energy distribution is formed. (FIG. 2C)

The irradiation object **108** is irradiated with the thus formed laser light while moving the laser light relative to the irradiation object **108** in the direction indicated by **110** or **111**,

for example. This way a desired region of the irradiation object **108**, or the entire region thereof can be irradiated.

If this laser irradiation apparatus is used to anneal a semiconductor film, the semiconductor film can be crystallized, the crystallinity is improved to obtain a crystalline semiconductor film, and an impurity element can be activated.

In this embodiment mode, laser light is divided by a mirror but the present invention is not limited thereto. A slit, a prism, a cylindrical lens, or a cylindrical lens array may be employed instead.

Although this embodiment mode uses two lasers and each laser light is divided in two, the present invention is not limited thereto. Preferably ten or so lasers are used. When using a small number of lasers, it is desirable to set the number of lasers to an even number and divide each laser light in an even number. Not all of lasers used may be identical.

In this embodiment mode, laser light is divided into equal widths by a plane perpendicular to the direction the laser light travels as shown in FIGS. 2A to 2C. However, the present invention is not limited thereto.

In this embodiment mode, laser beams having different energy distributions from one another are synthesized on an irradiation surface or in the vicinity thereof. However, since the optimum synthesizing method varies from one laser light mode to another, the synthesizing method used can be chosen to suit individual cases. For example, laser light in the TEM<sub>00</sub> mode is highly symmetrical and therefore laser light having a relatively high uniformity can be obtained by dividing laser light into two and synthesizing the left half and right half thereof. Needless to say, more highly uniform laser light is obtained when the number of division is larger. Laser light in other modes can also provide highly uniform laser light using the same method.

If the coating on the surface of synthesized silica glass is changed to suite the wavelength of laser light used, the present invention can be applied to various lasers.

Although a rectangular beam is formed in this embodiment mode so that laser light has a rectangular shape on an irradiation surface, the laser light shape formed is not limited thereto. The laser light shape emitted from a laser is varied from one type of laser to another type and, even when shaped by an optical system, the resultant shape tends to be influenced by the initial shape. For example, the laser light shape emitted from a XeCl excimer laser may be a 10 mm×30 mm (both are half-width in beam profile) rectangle, and laser light emitted from a solid-state laser has a circular shape if the rod shape is cylindrical and a rectangular shape if the rod shape is slab-like. The present invention can be applied to laser light of any shape without a problem as long as the laser light has an energy density sufficient for annealing of an irradiation object.

## Embodiment Mode 2

This embodiment mode describes with reference to FIGS. 21 to 23 an example of optical system for dividing laser beams that are emitted from three of lasers and overlapping laser beams that have different energy distributions from one another.

Lasers **101a** to **101c** each emit laser light. The lasers **101a** to **101c** used here are continuous wave or pulse oscillation solid-state lasers, gas lasers, or metal lasers. Examples of the solid-state lasers include a continuous wave or pulse oscillation YAG laser, YVO<sub>4</sub> laser, YLF laser, YAlO<sub>3</sub> laser, Y<sub>2</sub>O<sub>3</sub> laser, glass laser, ruby laser, alexandrite laser, and Ti:sapphire laser. Examples of the gas lasers include a continuous wave or pulse oscillation excimer laser, Ar laser, Kr laser, and CO<sub>2</sub>

laser. Examples of the metal lasers include a continuous wave or pulse oscillation helium cadmium laser, copper steam laser, and gold steam laser. The laser light emitted from the lasers **101a** to **101c** may be converted into harmonic by a non-linear optical element.

Though not shown, laser beams emitted from the lasers **101a** to **101c** separately may be expanded by beam expanders. Beam expanders are effective especially when laser light emitted from a laser has a small shape.

Laser beams emitted from the lasers **101a** to **101c** are divided by optical systems **102a** to **102c**, respectively, in two directions. Each of the optical systems **102a** to **102c** is a combination of a mirror and a cylindrical lens. The optical systems **102a** to **102c** dividing the laser light are shown in FIGS. **22A** to **22D**. Laser light emitted from the laser **101a** is divided into three by the optical system **102a** and only the left hand laser light of the three (first laser light in FIG. **22A**) travels straight whereas the other two are reflected by the mirror and reach a damper **110a**. Laser light emitted from the laser **101b** is divided into three by the optical system **102b** and only the center laser light of the three (second laser light in FIG. **22B**) travels straight whereas the other two are reflected by the mirror and reach a damper **110b**. Laser light emitted from the laser **101c** is divided into three by the optical system **102c** and only the right hand laser light of the three (third laser light in FIG. **22C**) travels straight whereas the other two are reflected by the mirror and reach a damper **110c**. In this way the optical systems **102a** to **102c** determine which laser light travels straight and which laser light is reflected.

Alternatively, each laser light may enter a cylindrical lens array to be divided and then only a desired one out of divided laser beams may be taken out using a slit that has a reflective surface.

The laser beams traveling straight through the optical systems **102a** to **102c** respectively pass through mirrors **103a** to **103c** and enter convex lenses **104a** to **104c** at angles. This causes aberration such as astigmatism to shift the focal point and make it possible to form a rectangular beam **106** on an irradiation surface or in the vicinity thereof. As shown in FIGS. **22A** to **22D**, laser beams that have passed through the optical systems **102a** and **102c** are longitudinally shorter than a laser beam that has passed the optical system **102b**. Therefore laser beams that have passed through the optical systems **102a** and **102c** are more slanted than a laser beam that has passed the optical system **102b** when the beams enter the lenses. This makes them longer in the longitudinal direction so that the three laser beams have the same length in the longitudinal direction. Alternatively, the shorter two laser beams may be expanded by a cylindrical lens or the like.

Coating on the surfaces of the convex lenses **104a** to **104c** is desirably capable of providing 99% or higher transmittance for the wavelength of laser light used. Furthermore, it is desirable to use as the convex lenses aspherical lenses in which spherical aberration is corrected. With the use of aspherical lenses, light collection is improved as well as the aspect ratio and energy density distribution.

The laser beams that have passed through the convex lenses **104a** to **104c** are synthesized on an irradiation surface or in the vicinity thereof to form a rectangular beam **106** (FIG. **22D**). The thus formed rectangular beam does not interfere since laser beams used to form the beam **106** are emitted from different lasers. In addition, the rectangular beam has excellent uniformity in energy distribution because plural laser beams having different energy distributions are synthesized on an irradiation surface or in the vicinity thereof.

An irradiation object **105** is irradiated with the thus formed rectangular beam while moving the beam relative to the irra-

diation object **105** in the direction indicated by **108** or **109**, for example. This way a desired region of the irradiation object **105**, or the entire region thereof can be irradiated.

However, depending on the wavelength of laser light, light reflected by the surface of the irradiation object **105** may interfere with light reflected by the back side of a substrate on which the irradiation object **105** is formed. FIG. **23** shows an example in which a semiconductor film **11** is formed as the irradiation object **105** on a substrate **10**. If light reflected by the semiconductor film **11** and light reflected by the back side of the substrate **10** do not overlap each other, interference of the reflected light does not take place.

In this case, when an incident face is defined as a plane which is perpendicular to the irradiation surface and which includes a shorter side or longer side of the rectangle shape of the long beam, an incident angle  $\theta$  of the laser light desirably satisfies  $\theta \geq \arctan(W/2d)$ , wherein the length of the shorter side or longer side included in the incident face is given as  $W$  and the thickness of a substrate transmissive of the laser light is given as  $d$ . The symbol  $W$  in the expression satisfies  $W = (w_1 + w_2)/2$  when  $w_1$  represents a beam length **15** upon entering the irradiation object and  $w_2$  represents the length of the beam reflected by the back side of the substrate **10**. If the laser light track is not on the incident face, the track is projected onto the incident face and the incident angle thereof is set as  $\theta$ . When laser light enters the incident face at this incident angle  $\theta$ , light reflected by the front side of the substrate and light reflected by the back side of the substrate do not interfere each other and uniform laser light irradiation can be obtained. If the incident angle  $\theta$  with respect to the irradiation object is set to Brewster angle, the reflectance is reduced to the lowest level and therefore laser light can be used efficiently. The above discussion is on the premise that the refractive index of the substrate is 1. In practice, the refractive index of most substrates is around 1.5 and, if the calculation is based on this value, the angle obtained is larger than the one calculated in the above discussion. However, the energy of a linear beam is attenuated at both edges in the longitudinal direction to lessen the influence of interference at the edges and therefore a satisfactory level of interference attenuation effect is obtained at the calculated value of the above discussion. Desirably, the incident angle of every laser light that enters the irradiation surface satisfies the above expression,  $\theta \geq \arctan(W/2d)$ .

A reflection preventive film may be formed on the surface of an irradiation object.

If this laser irradiation apparatus is used to anneal a semiconductor film, the semiconductor film can be crystallized, the crystallinity is improved to obtain a crystalline semiconductor film, and an impurity element can be activated.

Although this embodiment mode uses three lasers and each laser light is divided in three, the present invention is not limited thereto.

In this embodiment mode, laser light is divided into equal widths by a plane perpendicular to the direction the laser light travels as shown in FIG. **22**. However, the present invention is not limited thereto.

The laser light shape emitted from a laser is varied from one type of laser to another type and, even when shaped by an optical system, the resultant shape tends to be influenced by the initial shape. For example, the laser light shape emitted from a XeCl excimer laser is rectangular, and laser light emitted from a solid-state laser has a circular shape if the rod shape is cylindrical and a rectangular shape if the rod shape is slab-like. The present invention can be applied to laser light of any shape.



## 11

More detailed description will be given on the present invention structured as above using the following embodiments.

## Embodiment 1

This embodiment describes with reference to FIG. 3 and FIGS. 4A to 4E an example of optical system for dividing laser beams that are emitted from four lasers and overlapping laser beams that have different energy distributions from one another.

Lasers 131a to 131d each emit laser light. The lasers 131a to 131d used here are continuous wave or pulse oscillation solid-state lasers, gas lasers, or metal lasers. Examples of the solid-state lasers include a continuous wave or pulse oscillation YAG laser, YVO<sub>4</sub> laser, YLF laser, YAlO<sub>3</sub> laser, Y<sub>2</sub>O<sub>3</sub> laser, glass laser, ruby laser, alexandrite laser, and Ti:sapphire laser. Examples of the gas lasers include a continuous wave or pulse oscillation excimer laser, Ar laser, Kr laser, and CO<sub>2</sub> laser. Examples of the metal lasers include a continuous wave or pulse oscillation helium cadmium laser, copper steam laser, and gold steam laser. The laser light emitted from the lasers 131a to 131d may be converted into harmonic by a non-linear optical element.

In this embodiment, a continuous wave YVO<sub>4</sub> laser is used and its laser light is converted into the second harmonic by a non-linear optical element. The beam diameter of the laser light is 2.25 mm and the beam spread angle is set to 0.35 mrad.

Though not shown in the drawing, it is desirable to install isolators. This is because components of the optical system in this embodiment are arranged symmetrically and therefore reflected light of lasers on an irradiation surface may mutually affect other lasers in a way similar to return light.

Beam expanders (not shown) may be provided to expand laser light in the longitudinal direction and lateral direction. Beam expanders are effective especially when laser light emitted from a laser has a small shape.

Laser beams emitted from the lasers 131a to 131d are divided by slits 132a to 132d having reflective surfaces, respectively, so that each laser light is divided in two directions. Positioning of a slit with respect to laser light is varied among the slits 132a to 132d, and which one of divided laser beams travels straight varies from one slit to another. The laser beams being divided by the slits are described referring to FIGS. 4A to 4D. FIGS. 4A to 4D each show a laser light shape in section perpendicular to the direction the laser light travels. FIG. 4A shows laser light emitted from the laser 131a. The laser light is divided by the slit 132a into four, and a first laser beam travels straight whereas second to fourth laser beams are reflected and absorbed in a damper 137. FIG. 4B shows laser light emitted from the laser 131b. The laser light is divided by the slit 132b into four, and a second laser beam travels straight whereas first, third, and fourth laser beams are reflected and absorbed in the damper 137. FIG. 4C shows laser light emitted from the laser 131c. The laser light is divided by the slit 132c into four, and a third laser beam travels straight whereas first, second, and fourth laser beams are reflected and absorbed in the damper 137. FIG. 4D shows laser light emitted from the laser 131d. The laser light is divided by the slit 132d into four, and a fourth laser beam travels straight whereas first to third laser beams are reflected and absorbed in the damper 137. As described, each of the slits 132a to 132d lets one laser beam out of divided laser beams to travel straight whereas the rest of the divided laser beams are reflected, and a laser beam allowed to travel straight by one slit has different energy distribution than a laser beam allowed to travel straight by another slit.

## 12

The travel directions of the laser beams that have passed through the slits 132a to 132d are changed by prisms 133a to 133d, respectively. The prisms 133a to 133d are provided to synthesize all of the four laser beams at the same irradiation position.

If laser light that reaches the irradiation surface is one at an edge of the initial laser light, it is desirable to expand the length of this laser light in the longitudinal direction by a cylindrical lens 134a or 134d. As shown in FIGS. 4A to 4D, the length of laser light is shorter at its edges than around the center. Therefore, if the lengths of laser light edges are adjusted to have the same length as the center of the laser light prior to synthesization on the irradiation surface or in the vicinity thereof, a rectangular beam of high uniformity can be obtained upon the synthesization. In this embodiment, cylindrical lenses each having a focal length of 50 mm are placed such that the curvature is parallel to the longitudinal direction.

The laser beams are synthesized as shown in FIG. 4E on the irradiation surface by the optical system structured as above. The shape of laser light formed on the irradiation surface is simulated and the result thereof is shown in FIG. 5. FIG. 5 shows that a rectangular beam 7.1 mm in width and 22.2 mm in length is obtained. Since the laser beams used to form this rectangular beam are emitted from different lasers, interference does not take place. In addition, the rectangular beam has excellent uniformity in energy distribution because plural laser beams having different energy distributions are synthesized on the irradiation surface.

An irradiation object 108 is irradiated with the thus faulted rectangular beam while moving the beam relative to the irradiation object 108 in the direction indicated by 110 or 111, for example. This way a desired region of the irradiation object 108, or the entire region thereof can be irradiated.

Although this embodiment uses four lasers and each laser light is divided into four, the present invention is not limited thereto.

If this laser irradiation apparatus is used to anneal a semiconductor film, the semiconductor film can be crystallized, the crystallinity is improved to obtain a crystalline semiconductor film, and an impurity element can be activated.

## Embodiment 2

This embodiment describes with reference to FIG. 6 an example of optical system for dividing laser beams that are emitted from three lasers and overlapping laser beams that have different energy distributions from one another.

Lasers 121a to 121c each emit laser light. The lasers 121a to 121c used here are continuous wave or pulse oscillation solid-state lasers, gas lasers, or metal lasers. Examples of the solid-state lasers include a continuous wave or pulse oscillation YAG laser, YVO<sub>4</sub> laser, YLF laser, YAlO<sub>3</sub> laser, Y<sub>2</sub>O<sub>3</sub> laser, glass laser, ruby laser, alexandrite laser, and Ti:sapphire laser. Examples of the gas lasers include a continuous wave or pulse oscillation excimer laser, Ar laser, Kr laser, and CO<sub>2</sub> laser. Examples of the metal lasers include a continuous wave or pulse oscillation helium cadmium laser, copper steam laser, and gold steam laser. The laser light emitted from the lasers 121a to 121c may be converted into harmonic by a non-linear optical element.

In this embodiment, a pulse oscillation YAG laser is used and its laser light is converted into the second harmonic by a non-linear optical element.

The laser beams emitted are separately expanded by beam expanders 122a to 122c and then by beam expanders 123a to 123c. Beam expanders are effective especially when laser light emitted from a laser has a small shape, and may be

## 13

omitted depending on the size of laser light. The cylindrical lenses **122a** to **122c** and **123a** to **123c** are desirably made of synthetic silica glass because it gives them high transmittance. Coating on the surfaces of the cylindrical lenses **122a** to **122c** and **123a** to **123c** is desirably capable of providing 99% or higher transmittance for the wavelength of laser light used.

The laser beams that exit the beam expanders **122a** to **122c** and **123a** to **123c** are respectively divided in two directions by optical systems **124a** to **124c**. Each of the optical systems **124a** to **124c** is a combination of a mirror and a cylindrical lens. Laser light emitted from the laser **121a** is divided into three by the optical system **124a**, and only the left laser light of the three travels straight whereas the other two are reflected by the mirror and reach a damper **126**. Laser light emitted from the laser **121b** is divided into three by the optical system **124b** and only the center laser light of the three travels straight whereas the other two are reflected by the mirror and reach the damper **126**. Laser light emitted from the laser **121c** is divided into three by the optical system **124c** and only the right laser light of the three travels straight whereas the other two are reflected by the mirror and reach the damper **126**. In this way the optical systems **124a** to **124c** determine which laser light travels straight and which laser light is reflected.

Alternatively, each laser light may enter a cylindrical lens array to be divided and then only a desired one out of divided laser light may be taken out using a slit that has a reflective surface.

If laser light that reaches the irradiation surface is one at an edge of the initial laser light, it is desirable to expand the length of this laser light in the longitudinal direction by a cylindrical lens or the like (not shown) because edges of laser light are shorter in length than the center of the laser light.

The laser beams that have passed through the optical systems **124a** to **124c** are synthesized by a cylindrical lens **125** on the irradiation surface or in the vicinity thereof to form a rectangular beam. The thus formed rectangular beam does not interfere since laser beams used to form the rectangular beam are emitted from different lasers. In addition, the rectangular beam has excellent uniformity in energy distribution because plural laser beams having different energy distributions are synthesized on the irradiation surface or the vicinity thereof.

An irradiation object **108** is irradiated with the thus formed rectangular beam while moving the beam relative to the irradiation object **108** in the direction indicated by **110** or **111**, for example. This way a desired region of the irradiation object **108**, or the entire region thereof can be irradiated.

If this laser irradiation apparatus is used to anneal a semiconductor film, the semiconductor film can be crystallized, the crystallinity is improved to obtain a crystalline semiconductor film, and an impurity element can be activated.

Although this embodiment uses three lasers and the laser light is divided into three, the present invention is not limited thereto.

This embodiment may be combined freely with Embodiment 1.

## Embodiment 3

In this Embodiment, an optical system example of forming simultaneously a plurality of laser beams will be described by using the FIG. 7 that laser beams which are oscillated from two lasers are divided and laser beams whose energy densities are different from each other are overlapped.

## 14

Laser beams are respectively irradiated from laser **141a** and laser **141b**. Here, a solid state laser, a gas laser, or a metal laser of a continuous oscillation or a pulse oscillation are used as lasers **141a** and **141b**.

It should be noted that as the above-mentioned solid state laser, YAG laser, YVO<sub>4</sub> laser, YLF laser, YAlO<sub>3</sub> laser, Y<sub>2</sub>O<sub>3</sub> laser, glass laser, ruby laser, alexandrite laser, Ti:sapphire laser or the like of continuous oscillation or pulse oscillation are listed, as the above-mentioned gas laser, excimer laser, Ar laser, Kr laser, CO<sub>2</sub> laser or the like of continuous oscillation or pulse oscillation are listed, and as the above-mentioned metal laser, helium-cadmium laser, copper vapor laser, gold vapor laser and the like are listed. Further, laser beams irradiated from laser **141a** and laser **141b** may be converted into the higher harmonic wave by a non-linear optical element.

In this embodiment, lasers **141a** and **141b** are converted into the third higher harmonic wave by a continuous oscillation YAG lasers

Irradiated laser beams are expanded by beam expanders **142a** and **143a** or **142b** and **143b**. It should be noted that a beam expander is particularly effective in case, shapes of laser beams irradiated from lasers are small so that a beam expander is not used necessarily according to the size and the like of laser beams. It is desirable to obtain a high transmittance if a cylindrical lenses **142a**, **143a**, **142b**, **143b** are made of synthetic quartz glass. It is also desirable that coatings given to surfaces of lenses **142a**, **143a**, **142b** and **143b** can be obtained more than 99% transmittance against the wave length of the laser beam which is used.

Laser beam irradiated from beam expanders **142** and **143** are divided into two directions by the optical systems **144a** and **144b** combined mirrors and cylindrical lenses. Right laser beam of division into two which oscillated from the laser **141a** by the optical system **144a** goes straight and left laser beam reflects with the mirror. Left laser beam of division into two which oscillated from the laser **141b** by the optical system **144b** goes straight and right laser beam reflects with the mirror. In this way, laser beam are determined to go straight or to reflect by optical systems **144a** and **144b**.

Laser beams which go straight by optical systems **144a** and **144b** are synthesized at the irradiation side or near it by the cylindrical lens **147a** and forms rectangular shape beams. Rectangular shape beams which formed in this way are not interfered because they are oscillated by different lasers. Rectangular shape beams with excellent uniformity of energy densities are formed because a plurality of laser beams with different energy densities are formed at the irradiation side or near it.

While, laser beams which reflect by optical systems **144a** and **144b** are synthesized at the irradiation side or near it by the cylindrical lenses **146a**, **146b** and **147b** and form rectangular shape beams. Rectangular shape beams which formed in this way are not interfered because they are oscillated by different lasers. Rectangular shape beams with excellent uniformity of energy densities are formed because a plurality of laser beams with different energy densities are formed at the irradiation side or near it.

Then, while a plurality of rectangular shape beams formed in this way irradiate, they can irradiate the desired region or whole area on the irradiated body **108** by being relatively moved with respect to the irradiated body **108**, for example, in the direction indicated with the reference numerals **110** and **111**. Moreover, the through-put can be improved because a plurality of rectangular shape beams are formed.

The semiconductor film can be crystallized, a crystalline semiconductor film can be obtained with improving the crys-

## 15

talline and the activation of the impurity element can be performed if a semiconductor film is annealed by using such a laser irradiation apparatus

It should be noted that in this embodiment, although an example in which two lasers are used and the division number of laser beams is two, it is not limited and the number of rectangular shape beams which are formed are not limited two.

This embodiment can be combined with Embodiments 1 or 2 freely.

## Embodiment 4

This embodiment describes with reference to FIG. 8 an example of optical system for dividing laser beams that are emitted from four lasers and overlapping laser beams that have different energy distributions from one another.

Lasers **151a** to **151d** each emit laser light. The lasers **151a** to **151d** used here are continuous wave or pulse oscillation solid-state lasers, gas lasers, or metal lasers. Examples of the solid-state lasers include a continuous wave or pulse oscillation YAG laser, YVO<sub>4</sub> laser, YLF laser, YAlO<sub>3</sub> laser, Y<sub>2</sub>O<sub>3</sub> laser, glass laser, ruby laser, alexandrite laser, and Ti:sapphire laser. Examples of the gas lasers include a continuous wave or pulse oscillation excimer laser, Ar laser, Kr laser, and CO<sub>2</sub> laser. Examples of the metal lasers include a continuous wave or pulse oscillation helium cadmium laser, copper steam laser, and gold steam laser. The laser light emitted from the lasers **151a** to **151d** may be converted into harmonic by a non-linear optical element.

In this embodiment, a pulse oscillation YAG laser is used and its laser light is converted into the second harmonic by a non-linear optical element. The second harmonic of a YAG laser can be transmitted through a glass substrate or a quartz substrate and therefore is preferable when a substrate is irradiated from both sides as in this embodiment.

The laser beams emitted are separately expanded by beam expanders **152a** to **152d** and then by beam expanders **153a** to **153d**. Beam expanders are effective especially when laser light emitted from a laser has a small shape, and may be omitted depending on the size of laser light. The cylindrical lenses **152a** to **152d** and **153a** to **153d** are desirably made of synthetic silica glass because it gives them high transmittance. Coating on the surfaces of the cylindrical lenses **152a** to **152d** and **153a** to **153d** is desirably capable of providing 99% or higher transmittance for the wavelength of laser light used.

The laser beams that exit the beam expanders **152a** to **152d** and **153a** to **153d** are respectively divided in two directions by optical systems **154a** to **154d**. Each of the optical systems **154a** to **154d** is a combination of a mirror and a cylindrical lens. Laser light emitted from the laser **151a** is divided into four by the optical system **154a**, and only the most left laser light of the four travels straight whereas the other two are reflected by the mirror and reach a damper **156a**. Laser light emitted from the laser **151b** is divided into four by the optical system **154b** and only the second left laser light of the four travels straight whereas the other regions are reflected by the mirror and reach the damper **156a**. Laser light emitted from the laser **151c** is divided into four by the optical system **154c** and only the second right laser light of the four travels straight whereas the other three are reflected by the mirror and reach the damper **156c**. Laser light emitted from the laser **151d** is divided into four by the optical system **154d** and only the most right laser light of the four travels straight whereas the other three are reflected by the mirror and reach the damper **156c**. In

## 16

this way the optical systems **154a** to **154d** determine which laser light travels straight and which laser light is reflected.

Alternatively, each laser light may enter a cylindrical lens array to be divided and then only a desired one out of divided laser beams may be taken out using a slit that has a reflective surface.

Though not shown, laser light at an edge of the divided regions is desirably expanded by a cylindrical lens array or the like since laser light at an edge is shorter in the longitudinal direction than laser light near the center.

The laser beams that have passed through the optical systems **154a** to **154d** are synthesized by cylindrical lenses **155a** and **155c** on the irradiation surface or in the vicinity thereof to form a rectangular beam. The thus formed rectangular beam does not interfere since laser beams used to form the rectangular beam are emitted from different lasers. In addition, the rectangular beam has excellent uniformity in energy distribution because plural laser beams having different energy distributions are synthesized on the irradiation surface or the vicinity thereof.

An irradiation object **108** is irradiated with the thus formed rectangular beam while moving the beam relative to the irradiation object **108** in the direction indicated by **110** or **111**, for example. This way a desired region of the irradiation object **108**, or the entire region thereof can be irradiated.

When plural laser beams irradiate one side of the substrate and are synthesized at the same irradiation position, the laser beams have different light path lengths and spread angles of the laser beams may expand the synthesized beam unnecessarily, thereby lowering uniformity in energy distribution. The structure of this embodiment is free from this problem because the plural laser beams each have the same light path length to reach the irradiation surface.

If this laser irradiation apparatus is used to anneal a semiconductor film, the semiconductor film can be crystallized, the crystallinity is improved to obtain a crystalline semiconductor film, and an impurity element can be activated.

Although this embodiment uses four lasers and each laser light is divided into four, the present invention is not limited thereto.

This embodiment may be combined freely with Embodiments 1 to 3.

## Embodiment 5

This embodiment gives a description with reference to FIG. 9 an example of optical system for dividing laser beams that are emitted from four lasers, overlapping and synthesizing laser beams that have different energy distributions, and irradiating a substrate from both sides.

In FIG. 9, an optical system is composed of lasers **101a** and **101b**, isolators **102a** and **102b**, beam expanders **103a** and **104a** or **103b** and **104b**, mirrors **105a** and **105b**, mirrors **106a** and **106b**, an irradiation object **108**, and a stage **109**. The optical system is similar to the structure shown in Embodiment Mode 1 (FIG. 1).

In this embodiment, a YLF laser is used and its laser light is converted into the second harmonic. The second harmonic of a YLF laser can be transmitted through a glass substrate or a quartz substrate and therefore is preferable when a substrate is irradiated from both sides as in this embodiment. Even when the laser has a wavelength that does not allow a substrate to transmit it, the substrate can be partially annealed and it can be used in this embodiment.

Another optical system has the structure of FIG. 1 and is composed of lasers **101c** and **101d**, isolators **102c** and **102d**, beam expanders **103c** and **104c** or **103d** and **104d**, mirrors

17

**105c** and **105d**, and mirrors **106c** and **106d**. This optical system and the above optical system are arranged such that they are symmetrical with respect to the irradiation object **108**.

With this structure, the substrate can be irradiated with rectangular beams from both sides. The irradiation object **108** is irradiated with the thus formed rectangular beams while moving the beams relative to the irradiation object **108** in the direction indicated by **110** or **111**, for example. This way a desired region of the irradiation object **108**, or the entire region thereof can be irradiated.

By irradiating the substrate from both sides, the energy density can be enhanced. When plural laser beams irradiate one side of the substrate and are synthesized at the same irradiation position, the laser beams each have different light path lengths and spread angles of the laser beams may expand the synthesized beam unnecessarily, thereby lowering uniformity in energy distribution. The structure of this embodiment is free from this problem because the plural laser beams each have the same light path length to reach the irradiation surface.

If this laser irradiation apparatus is used to anneal a semiconductor film, the semiconductor film can be crystallized, the crystallinity is improved to obtain a crystalline semiconductor film, and an impurity element can be activated.

Although this embodiment uses four lasers and each laser light is divided into two, the present invention is not limited thereto.

This embodiment may be combined freely with Embodiments 1 to 4.

#### Embodiment 6

This embodiment describes with reference to FIGS. **4A** to **4E**, **24**, and **25** an example of optical system for dividing laser beams that are emitted from four lasers and overlapping laser beams that have different energy distributions from one another.

Lasers **131a** to **131d** each emit laser light. The lasers **131a** to **131d** used here are continuous wave or pulse oscillation solid-state lasers, gas lasers, or metal lasers. Examples of the solid-state lasers include a continuous wave or pulse oscillation YAG laser, YVO<sub>4</sub> laser, YLF laser, YAlO<sub>3</sub> laser, Y<sub>2</sub>O<sub>3</sub> laser, glass laser, ruby laser, alexandrite laser, and Ti:sapphire laser. Examples of the gas lasers include a continuous wave or pulse oscillation excimer laser, Ar laser, Kr laser, and CO<sub>2</sub> laser. Examples of the metal lasers include a continuous wave or pulse oscillation helium cadmium laser, copper steam laser, and gold steam laser. The laser light emitted from the lasers **131a** to **131d** may be converted into harmonic by a non-linear optical element.

In this embodiment, a continuous wave YVO<sub>4</sub> laser is used and its laser light is converted into the second harmonic by a non-linear optical element. The beam diameter of the laser light is 2.25 mm and the beam spread angle is set to 0.35 mrad.

Though not shown in the drawing, it is desirable to install isolators. This is because components of the optical system in this embodiment are arranged symmetrically and therefore reflected light of lasers on an irradiation surface may mutually affect other lasers in a way similar to return light.

Beam expanders (not shown) may be provided to expand laser light in the longitudinal direction and lateral direction. Beam expanders are effective especially when laser light emitted from a laser has a small shape.

Laser beams emitted from the lasers **131a** to **131d** are divided by slits **132a** to **132d** having reflective surfaces, respectively, so that each laser light is divided in two direc-

18

tions. Positioning of a slit with respect to laser light is varied among the slits **132a** to **132d**, and which one of divided laser beams travels straight varies from one slit to another. The laser beams being divided by the slits are described referring to FIGS. **4A** to **4D**. FIGS. **4A** to **4D** each show a laser light shape in section perpendicular to the direction the laser light travels. FIG. **4A** shows laser light emitted from the laser **131a**. The laser light is divided by the slit **132a** into four, and a first laser beam travels straight whereas second to fourth laser beams are reflected and absorbed in a damper **135a**. FIG. **4B** shows laser light emitted from the laser **131b**. The laser light is divided by the slit **132b** into four, and a second laser beam travels straight whereas first, third, and fourth laser beams are reflected and absorbed in the damper **135a**. FIG. **4C** shows laser light emitted from the laser **131c**. The laser light is divided by the slit **132c** into four, and a third laser beam travels straight whereas first, second, and fourth laser beams are reflected and absorbed in the damper **135c**. FIG. **4D** shows laser light emitted from the laser **131d**. The laser light is divided by the slit **132d** into four, and a fourth laser beam travels straight whereas first to third laser beams are reflected and absorbed in the damper **135c**. As described, each of the slits **132a** to **132d** lets one laser beam out of divided laser beams to travel straight whereas the rest of the divided laser beams are reflected, and a laser beam allowed to travel straight by one slit has different energy distribution than a laser beam allowed to travel straight by another slit.

Laser beams that have passed through the slits **132a** to **132d** enter convex lenses **134a** to **134d**, respectively, at angles. This causes aberration such as astigmatism to shift the focal point and make it possible to form a rectangular beam **106** on an irradiation surface or in the vicinity thereof. In this embodiment, the radius of curvature of the convex lenses **134a** and **134d** is set to 7 mm and the radius of curvature of the convex lenses **134b** and **134c** is set to 9 mm. As shown in FIGS. **4A** to **4D**, the length of laser light is shorter at edges than around the center. Therefore, by giving different radii of curvature, laser light at an edge of initial laser light is expanded in length in the longitudinal direction more than laser light at the center of the initial laser light is expanded. This way a rectangular beam of high uniformity can be obtained upon synthesization on the irradiation surface or in the vicinity thereof. Alternatively, a cylindrical lens or the like may be used to expand laser light in the longitudinal direction if the laser light that reaches the irradiation surface is one at an edge of the initial laser light.

The shape of laser light formed on the irradiation surface by the optical system structured as above is shown in FIG. **4E**. The shape of laser light formed on the irradiation surface is simulated and the result thereof is shown in FIG. **25**. FIG. **25** shows that a rectangular beam 190  $\mu$ m in width and 950  $\mu$ m in length is obtained. Since the laser beams used to form this rectangular beam are emitted from different lasers, interference does not take place. In addition, the rectangular beam has excellent uniformity in energy distribution because plural laser beams having different energy distributions are synthesized on the irradiation surface.

An irradiation object **105** is irradiated with the thus formed rectangular beam while moving the beam relative to the irradiation object **105** in the direction indicated by **108** or **109**, for example. This way a desired region of the irradiation object **105**, or the entire region thereof can be irradiated.

Although this embodiment uses four lasers and each laser light is divided into four, the present invention is not limited thereto.

If this laser irradiation apparatus is used to anneal a semiconductor film, the semiconductor film can be crystallized,

the crystallinity is improved to obtain a crystalline semiconductor film, and an impurity element can be activated.

#### Embodiment 7

A method of manufacturing an active matrix substrate is explained in this embodiment using FIGS. 12 to 15. A substrate on which a CMOS circuit, a driver circuit, and a pixel portion having a TFT pixel and a holding capacity are formed together is called active matrix substrate for convenience.

First, a substrate **400** made from glass such as barium borosilicate glass or aluminum borosilicate glass is used in this embodiment. Note that substrates such as quartz substrates, silicon substrates, metallic substrates, and stainless steel substrates having an insulating film formed on the substrate surface may also be used as the substrate **400**. Further, a plastic substrate having heat resisting properties capable of enduring the processing temperatures used in this embodiment may also be used. Because this invention can form a plurality of rectangular shape beams with a uniform energy distribution, it is possible that annealing the large area substrate is conducted effectively by using a plurality of rectangular shape beams.

Next, a base film **401** made from an insulating film such as a silicon oxide film, a silicon nitride film, or a silicon oxynitride film is then formed on the substrate **400** by the known method. A two layer structure is used as the base film **401** in this embodiment, but a single layer of the above-mentioned insulating film may also be used, and a structure in which more than two layers are laminated may also be used.

Next, semiconductor layers are formed on the base film. First of all, semiconductor film is formed with a thickness of 25 to 200 nm (preferably 30 to 150 nm) by a known method (such as the sputtering method, the LPCVD method, and the plasma CVD method). Then, the semiconductor film is crystallized by a laser crystallization method. As the laser crystallization method, the laser beam irradiates to the semiconductor film by applying one of Embodiments 1 to 6 or by freely combining any one of Embodiments 1 to 6. It is desirable that a solid-state laser of continuous oscillation or pulse oscillation, a gas laser, or metallic laser is used. Note that, as the above-mentioned solid-state laser, there may be given a YAG laser of a continuous oscillation or pulse oscillation, a YVO<sub>4</sub> laser, a YLF laser, a YAlO<sub>3</sub> laser, Y<sub>2</sub>O<sub>3</sub> laser, a glass laser, a ruby laser, an alexandrite laser, a Ti:sapphire laser, and the like. As the above-mentioned gas laser, there may be given an excimer laser of continuous oscillation or pulse oscillation, Ar laser, Kr laser, CO<sub>2</sub> laser, or the like. And as the above-mentioned metallic laser, there may be given a helium cadmium laser, a copper vapor laser, or a gold vapor laser. Of course, not only the laser crystallization method but also any other known crystallization method (RTA, the thermal crystallization method using a furnace annealing, the thermal crystallization method using metallic elements which promote crystallization) may also be combined. The above-mentioned semiconductor film may be an amorphous semiconductor film, a microcrystalline semiconductor film, a crystalline semiconductor film and the like. Alternatively, the semiconductor film may be a compound semiconductor film having an amorphous structure such as an amorphous silicon germanium film.

In this embodiment, plasma CVD method is used to form an amorphous silicon film with a thickness of 50 nm, and then the thermal crystallization method using metallic elements, which promote crystallization, and laser crystallization method are used for the amorphous silicon film. Nickel is used as a metal element, and is introduced onto the amor-

phous silicon film by a solution coating method. Then heat treatment is conducted at 550° C. for five hour, whereby obtaining a first crystalline silicon film. Subsequently, the laser beam shot from a continuous oscillation YVO<sub>4</sub> laser with output 10 W is converted into the second higher harmonic wave by a nonlinear optical element and then a rectangular shape beam is formed and irradiated by one of the optical system shown in Embodiments 1 thorough 6 or by the optical system combined these embodiments, whereby obtaining a second crystalline silicon film. Irradiating the laser beam to the first crystalline silicon film, and changing the first crystalline silicon film to the second crystalline silicon film improve the crystallinity of the second crystalline silicon film. At this moment, about 0.01 to 100 MW/cm<sup>2</sup> (preferably 0.1 to 10 MW/cm<sup>2</sup>) is necessary for the energy density. The stage is relatively moved to the laser beam at a speed of about 0.5 to 2000 cm/s, and it irradiates, and then the crystalline silicon film is formed. When the excimer laser of pulse oscillation is used, it is desirable that 300 Hz of frequency and 100 to 1000 mJ/cm<sup>2</sup> (typically, 200 to 800 mJ/cm<sup>2</sup>) of laser energy density are used. At this moment, laser beam may be overlapped by 50 to 98%.

Of course, although a TFT can be formed by using the first crystalline silicon film, it is desirable that the second crystalline silicon film is used to form the TFT since the second crystalline silicon film has an improved crystallinity and electric characteristics of TFT are improved. For instance, although, when TFT is formed by using the first crystalline silicon film, a mobility is almost 300 cm<sup>2</sup>/Vs, when TFT is formed by using the second crystalline silicon film, the mobility is extremely improved with about 500 to 600 cm<sup>2</sup>/Vs.

The semiconductor layers **402** to **406** are formed by performing patterning processing on thus obtained semiconductor film by using the photolithography method.

Doping of a very small amount of an impurity element (boron or phosphorous) may be performed after forming the semiconductor layers **402** to **406** in order to control a TFT threshold value.

A gate insulating film **407** is formed next, covering the semiconductor layers **402** to **406**. The gate insulating film **407** is formed by an insulating film containing silicon with a thickness of 40 to 150 nm using plasma CVD or sputtering. In this embodiment, a silicon oxynitride film having a film thickness of 110 nm is formed by plasma CVD method. The gate insulating film is of course not limited to a silicon oxynitride film, and other insulating films containing silicon may be used in a single layer or in a lamination structure.

Further, if a silicon oxide film is used, it can be formed by plasma CVD method with a mixture of TEOS (Tetraethyl Orthosilicate) and O<sub>2</sub>, at a reaction pressure of 40 Pa, with the substrate temperature set from 300 to 400° C., and by discharging at a high frequency (13.56 MHz) electric power density of 0.5 to 0.8 W/cm<sup>2</sup>. Good characteristics as a gate insulating film can be obtained by subsequently performing thermal annealing, at between 400 and 500° C., of the silicon oxide film thus manufactured.

A first conductive film **408** having a film thickness of 20 to 100 nm, and a second conductive film **409** having a film thickness of 100 to 400 nm are then formed and laminated on the gate insulating film **407**. The first conductive film **408**, made from a TaN film having a film thickness of 30 nm, and the second conductive film **409**, made from a W film having a film thickness of 370 nm, are formed and laminated in this embodiment. The TaN film is formed by sputtering, and sputtering of a Ta target is performed in a nitrogen atmosphere. Further, the W film is formed by sputtering using a W target. In addition, the W film can also be formed by thermal CVD

method using tungsten hexafluoride ( $WF_6$ ). Whichever is used, it is necessary to be able to make the film become low resistance in order to use it as a gate electrode, and it is desirable that the resistivity of the W film be made less than  $20 \mu\Omega\text{cm}$ .

Note that although the first conductive film **408** is TaN and the second conductive film **409** is W in this embodiment, there are no particular limitations placed on the conductive films. The first conductive film **408** and the second conductive film **409** may also be formed from an element selected from the group consisting of Ta, W, Ti, Mo, Al, Cu, Cr, and Nd, or from an alloy material having one of these elements as its main constituent, or from a chemical compound of these elements. Further, a semiconductor film, typically a polycrystalline crystalline silicon film, into which an impurity element such as phosphorous is doped may also be used, as may an AgPdCu alloy.

Masks **410** to **415** are formed next from resist using a photolithography method, and a first etching process is performed in order to form electrodes and wirings. The first etching processing is performed in accordance with first and second etching conditions (FIG. **12B**). An ICP (Inductively Coupled Plasma) etching method is used as a first etching condition in this embodiment. A gas mixture of  $CF_4$ ,  $Cl_2$ , and  $O_2$  is used as an etching gas, the gas flow rates are set to 25:25:10 (sccm), respectively, a plasma is generated by supplying a 500 W RF (13.56 MHz) electric power to a coil shape electrode at a pressure of 1 Pa; and etching is performed. A 150 W RF (13.56 MHz) electric power is also applied to the substrate side (sample stage), thereby applying a substantially negative self-bias voltage. The W film is etched under the first etching conditions, and the edge portion of the first conductive layer is made into a tapered shape.

The etching conditions are changed to a second etching condition without removing the masks **410** to **415** made of resist. A gas mixture of  $CF_4$  and  $Cl_2$  is used as an etching gas, the gas flow rates are set to 30:30 (sccm), respectively, a plasma is generated by applying a 500 W RF (13.56 MHz) electric power to a coil shape electrode at a pressure of 1 Pa, and etching is performed for approximately 30 seconds. A 20 W RF (13.56 MHz) electric power is also supplied to the substrate side (sample stage), thereby applying a substantially negative self-bias voltage. The W film and the TaN film are both etched by on the same order by the second etching conditions using the gas mixture of  $CF_4$  and  $Cl_2$ . Note that the etching time may be increased on the order of 10 to 20% in order to perform etching such that no residue remains on the gate insulating film.

Edge portions of the first conductive layer and the second conductive layer are made into a tapered shape in accordance with the effect of a bias voltage, applied to the substrate side, by making the shapes of the resist masks suitable with the above-mentioned first etching condition. The angle of the tapered portions is from 15 to 45°. First shape conductive layers **417** to **422** (first conductive layers **417a** to **422a**, and second conductive layers **417b** to **422b**) are thus formed from the first conductive layers and the second conductive layers by the first etching process. Reference numeral **416** denotes a gate insulating film, and regions not covered by the first shape conductive layers **417** to **422** become thinner by approximately 20 to 50 nm through etching.

A second etching process is then performed without removing the masks made of resist (FIG. **12C**). Here, W film is selectively etched by using  $CF_4$ ,  $Cl_2$ , and  $O_2$  for the etching gas. At this time, the second conductive layers **428b** to **433b** are formed by the second etching process. On the other hand,

the first conductive layers **417a** to **422a** are hardly etched and the second shape conductive layers **428** to **433** are formed.

A first doping process is then performed without removing the masks made of resist and the semiconductor layer is added to the impurity element which imparts n-type at a low concentration. The doping process may be performed by ion doping method or ion injection method. Ion doping is performed with process conditions in which the dosage is set from  $1 \times 10^{13}$  to  $5 \times 10^{14}/\text{cm}^2$ , and the acceleration voltage is set between 40 to 80 keV. Doping is performed in this embodiment with the dosage set to  $1.5 \times 10^{13}/\text{cm}^2$ , and the acceleration voltage set to 60 keV. An element belonging to the group 15, typically phosphorous (P) or arsenic (As) is used as an impurity element which imparts n-type. Phosphorous (P) is used here. In this case the conductive layers **428** to **433** act as masks with respect to the impurity element which imparts n-type conductivity, and the impurity regions **423** to **427** are formed in a self-aligning manner. The impurity element which imparts n-type is added to the impurity regions **423** to **427** at a concentration in a range of  $1 \times 10^{18}$  to  $1 \times 10^{20}/\text{cm}^3$ .

Next, after removing the masks made of resist, new masks **434a** to **434c** made of resist are formed, and the second doping process is performed in higher acceleration voltage than the first doping process. Ion doping is performed with process conditions in which the dosage is set from  $1 \times 10^{13}$  to  $1 \times 10^{15}/\text{cm}^2$ , and the acceleration voltage is set between 60 to 120 keV. The doping process is performed by using the second conductive layers **428b** to **432b** as masks and the semiconductor layer under the tapered portion of the first conductive layer is added to the impurity element. Continuously the acceleration voltage is lowered than the second doping process, the third doping process is done, and the state of FIG. **13A** is obtained. Ion doping method is performed with process conditions in which the dosage is set from  $1 \times 10^{15}$  to  $1 \times 10^{17}/\text{cm}^2$ , and the acceleration voltage is set between 50 to 100 keV. Low concentration impurity regions **436**, **442** and **448** overlapping with the first conductive layer are added to the impurity element, which imparts n-type within the range of the density of  $1 \times 10^{18}$  to  $5 \times 10^{19}/\text{cm}^2$  by the second doping process and the third doping process and high concentration impurity regions **435**, **441**, **444** and **447** are added to the impurity element, which imparts n-type within the range of the density of  $1 \times 10^{19}$  to  $5 \times 10^{21}/\text{cm}^2$ .

Of course, the second doping process and the third doping process can be one-time doping processes by making it to a suitable acceleration voltage and it is also possible to form the low concentration impurity region and high concentration impurity region.

Next, after removing the masks made of resist, new masks **450a** to **450c** made from resist are formed and the fourth doping process is performed. Impurity regions **453**, **454**, **459** and **460**, to which an impurity element which imparting a conductivity type opposite to that of the above one conductivity type is added, are formed in accordance with the fourth doping process in the semiconductor films which become active layers of the p-channel type TFTs. The first conductive layers **429a** to **432a** are used as masks with respect to the impurity element, and an impurity element which imparts p-type conductivity is added to form the impurity regions in a self-aligning manner. The impurity regions **453**, **454**, **459** and **460** are formed by ion doping method using diborane ( $B_2H_6$ ) in this embodiment (FIG. **13B**). The semiconductor layers for forming the n-channel type TFT are covered with the masks **450a** to **450c** made of resist when the fourth doping process is performed. Phosphorous is added at different concentrations into the impurity regions **453**, **454**, **459** and **460** by the first to

23

third doping processes. However, by performing doping such that the concentration of the impurity element which imparts p-type conductivity becomes from  $1 \times 10^{19}$  to  $5 \times 10^{21}$  atoms/cm<sup>3</sup> in the respective regions, no problems develop in making the regions function as source regions and drain regions of the p-channel type TFT.

The impurity regions are thus formed in the respective semiconductor layers by the steps up through this point.

A first interlayer insulating film **461** is formed next after removing the masks **450a** to **450c** made of mist. This first interlayer insulating film **461** is formed from an insulating film containing silicon, having a thickness of 100 to 200 nm, by using plasma CVD method or sputtering method. A silicon oxynitride film having a thickness of 150 nm is formed by plasma CVD method in this embodiment. The first interlayer insulating film **461** is of course not limited to a silicon oxynitride film, and other insulating films containing silicon may also be used, as a single layer or a lamination structure.

Subsequently, a recovery of the crystallinity of the semiconductor layer and an activation of the impurity elements added to the respective semiconductor layers are performed by irradiating the laser beam, as shown in FIG. 13C. As the laser activation, the laser beam irradiates to the semiconductor film by applying one of Embodiments 1 to 6 or by freely combining with these embodiments. It is desirable that a solid-state laser of a continuous oscillation or a pulse oscillation, a gas laser, or metallic laser is used. Note that, as the above-mentioned solid-state laser, there may be given a YAG laser of a continuous oscillation or a pulse oscillation, a YVO<sub>4</sub> laser, a YLF laser, a YAlO<sub>3</sub> laser, a Y<sub>2</sub>O<sub>3</sub> laser, a glass laser, a ruby laser, an alexandrite laser, a Ti:sapphire laser, and the like. As the above-mentioned gas laser, there may be given an excimer laser of continuous oscillation or pulse oscillation, Ar laser, Kr laser, CO<sub>2</sub> laser, or the like. And as the above-mentioned metallic laser, there may be given a helium cadmium laser, a copper vapor laser, or a gold vapor laser. At this moment, if a continuous oscillation laser is used, about 0.01 to 100 MW/cm<sup>2</sup> (preferably 0.01 to 10 MW/cm<sup>2</sup>) is necessary for the energy density of laser beam. The substrate is relatively moved to the laser beam at a speed of about 0.5 to 2000 cm/s. And, if a pulse oscillation laser is used, it is desirable that 300 Hz of frequency and 50 to 1000 mJ/cm<sup>2</sup> (typically, 50 to 500 mJ/cm<sup>2</sup>) of laser energy density are used. At this moment, laser beam may be overlapped by 50 to 98%. Besides laser annealing method, thermal annealing method or rapid thermal annealing method (RTA method) and the like can be applied.

Further, the activation may also be performed before the formation of a first interlayer insulating film. However, if the wiring material used is weak with respect to heat, then it is desirable to perform the activation processing after forming an interlayer insulating film (an insulating film having silicon as its main constituent, for example a silicon nitride film) in order to protect the wirings and the like, as in this embodiment.

Then, a heat treatment can also be performed (at 300 to 550° C. for 1 to 12 hours) and it is possible to conduct a hydrogenation. This process is one of terminating dangling bonds in the semiconductor layers by hydrogen contained within the first interlayer insulating film **461**. The semiconductor layers can be hydrogenated whether or not the first interlayer insulating film exists. Plasma hydrogenation (using hydrogen excited by a plasma), and a heat treatment for 1 to 12 hours at a temperature of 300 to 450° C. in an atmosphere containing hydrogen of from 3 to 100% may also be performed as other means of hydrogenation.

24

Subsequently, a second interlayer insulating film **462** made from an inorganic insulating film material or from an organic insulating material is formed on the first interlayer insulating film **461**. An acrylic resin film having a film thickness of 1.6 μm is formed in this embodiment, and the material used may have a viscosity from 10 to 1000 cp, preferably between 40 to 200 cp. A material in which unevenness is formed on its surface is used.

In order to prevent mirror reflection, the surface of a pixel electrode is made uneven by fanning a second interlayer insulating film which forms an uneven surface (not shown) in this embodiment. Further, the pixel electrode surface can be made to be uneven and have light scattering characteristics, and therefore a convex portion may also be formed in a region below the pixel electrode. The formation of the convex portion can be performed by the same photomask as that for forming the TFTs, and therefore it can be formed without increasing the number of process steps. Note that the convex portion may also be formed appropriately on the substrate of the pixel portion region except the wirings and TFTs. In this way, unevenness is formed in the surface of the pixel electrode along the unevenness formed in the surface of the insulating film which covers the convex portion.

A film having a level surface may also be used as the second interlayer insulating film **462**. In this case, it is desirable that the surface be made uneven by an added process such as a known sandblasting process or etching process to prevent mirror reflection, and thereby increasing whiteness by scattering reflected light.

Wirings **463** to **467** for electrically connecting respective impurity regions are then faulted in a driver circuit **506**. Note that a lamination film of a Ti film having a thickness of 50 nm and an alloy film (an alloy of Al and Ti) having a thickness of 500 nm is patterned in order to form the wirings. Of course, it is not limited to the two-layer structure, the single-layer structure or the lamination structure more than three layers may also be acceptable. Further, Al and Ti are not limited to the wiring material. For example, Al and Cu are formed on TaN film, and the lamination film forming the Ti film is formed by the patterning and form wiring (FIG. 14).

Further, a pixel electrode **470**, a gate wiring **469**, and a connection electrode **468** are formed in a pixel portion **507**. An electrical connection is formed with the pixel TFT and the source wiring (lamination of **433a** and **433b**) by the connection electrode **468**. Further, the gate wiring **469** forms an electrical connection with the gate electrode of the pixel TFT. The pixel electrode **470** forms an electrical connection with the drain region **444** of the pixel TFT, and in addition, forms an electrical connection with the semiconductor layer **459** which functions as one electrode forming a storage capacitor. It is desirable to use a material having superior reflectivity, such as a film having Al or Ag as its main constituent, or a lamination film of such films, as the pixel electrode **470**.

A CMOS circuit composed of a n-channel TFT **501** and a p-channel TFT **502**, a driver circuit **506** having a n-channel TFT **503**, and the pixel portion **507** having a pixel TFT **504** and a storage capacitor **505** can thus be formed on the same substrate. The active matrix substrate is thus completed.

The n-channel TFT **501** of the driver circuit **506** has: a channel forming region **437**; the low concentration impurity region **436** (GOLD region) which overlaps with the first conductive layer **428a** that structures a portion of the gate electrode; and the high concentration impurity region **452** which functions as a source region or a drain region. The p-channel TFT **502**, which forms the CMOS circuit with the n-channel TFT **501** and the electrode **466** by an electrical connection has: a channel forming region **455**; the low concentration



## 25

impurity region **454**; and the impurity region **453** in which the impurity elements imparting n-type and p-type are introduced. Further, the n-channel TFT **503** has: a channel forming region **443**; the low concentration impurity region **442** (GOLD region) which overlaps with the first conductive layer **430a** that structures a portion of the gate electrode; and the high concentration impurity region **456** which functions as a source region or a drain region.

The pixel TFT **504** of the pixel portion has: a channel forming region **446**; the low concentration impurity region **445** (LDD region) formed on the outside of the gate electrode; and the high concentration impurity region **458** which functions as a source region or a drain region. Further, an impurity element which imparts n-type and an impurity element which imparts p-type are added to the semiconductor layer which functions as one electrode of the storage capacitor **505**. The storage capacitor **505** comprises an electrode (lamination of **432a** and **432b**) and the semiconductor layer, with the insulating film **416** functioning as a dielectric.

Edge portions of the pixel electrodes are disposed so as to overlap with source wirings such that gaps between the pixel electrodes shield the light, without using a black matrix, with the pixel structure of this embodiment.

An upper surface diagram of the pixel portion of the active matrix substrate manufactured in this embodiment is shown in FIG. **15**. Note that the same reference symbols are used for portions corresponding to those in FIGS. **12** to **15**. A chain line A-A' in FIG. **14** corresponds to a cross sectional diagram cut along a chain line A-A' within FIG. **15**. Further, a chain line B-B' in FIG. **14** corresponds to a cross sectional diagram cut along a chain line B-B' within FIG. **15**.

## Embodiment 8

In this embodiment, a manufacturing process of a reflection type liquid crystal display device from the active matrix substrate manufactured in accordance with Embodiment 7 will be described hereinbelow. FIG. **16** is used for an explanation thereof.

First, in accordance with Embodiment 5, an active matrix substrate in a state shown in FIG. **14** is obtained, and thereafter, an alignment film **567** is formed on the active matrix substrate of FIG. **14**, at least on the pixel electrode **470**, and is subjected to a rubbing process. Note that, in this embodiment, before the formation of the alignment film **567**, a spacer **572** for maintaining a gap between the substrates is formed at a desired position by patterning an organic film such as an acrylic resin film. Further, spherical spacers may be scattered on the entire surface of the substrate in place of the columnar like spacer.

Next, an opposing substrate **569** is prepared. The colored layers **570**, **571** and a leveling film **573** are formed on the opposing substrate **569**. The red-colored layer **570** and the blue-colored layer **572** are partially overlapped with each other, thereby forming a light shielding portion. Note that, the red-colored layer and a green-colored layer are partially overlapped with each other, thereby forming a light shielding portion.

In this embodiment, the substrate shown in Embodiment 5 is used. Accordingly, in FIG. **15** showing a top view of the pixel portion in accordance with Embodiment 5, light shielding must be performed at least gaps between the gate wiring **469** and the pixel electrodes **470**, a gap between the gate wiring **469** and the connection electrode **468**, and a gap between the connection electrode **468** and the pixel electrode **470**. In this embodiment, the opposing substrate and the active matrix substrate are stuck so that the light shielding

## 26

portions from laminated layer of colored layer each other overlap with the positions which need to be shielded from light.

Like this, without forming a black matrix, the gaps between the respective pixels are shielded from light by the light shielding portion. As a result, the reduction of the manufacturing steps can be attained.

Next, the opposing electrode **576** from transparent conductive film is formed on the leveling film **573**, at least on the pixel portion. The alignment film **574** on the entire surface of the opposing substrate and the rubbing process is performed.

Then, an active matrix substrate on which a pixel portion and a driver circuit are formed is stuck with the opposing substrate by a sealing agent **568**. In the sealing agent **568**, a filler is mixed, and the two substrates are stuck with each other while keeping a uniform gap by the effect of this filler and the columnar spacer. Thereafter, a liquid crystal material **575** is injected between both the substrates to encapsulate the substrates completely by an encapsulant (not illustrated). A known liquid crystal material may be used as the liquid crystal material **575**. Thus, the reflection type liquid crystal display device shown in FIG. **16** is completed. Then, if necessary, the active matrix substrate or the opposing substrate may be parted into desired shapes. Further, a polarizing plate is adhered to only the opposing substrate (not illustrated). Then, an FPC is adhered using a known technique.

Thus formed liquid crystal display device have a TFT which is formed by using the semiconductor film conducted homogeneous annealing. Therefore, enough operating characteristics and reliability of the above-mentioned liquid crystal display device can be obtained. Such liquid crystal display device can be used as a display portion of various electronic device.

This embodiment can be combined with Embodiments 1 and 7 freely.

## Embodiment 9

In this embodiment, the example of manufacturing the light-emitting device by using manufacturing method of TFT when forming the active matrix substrate shown in Embodiment 7 is described. In this specification, the light-emitting device is a generic name which is a display panel enclosing the light-emitting element between the substrate and the cover material and the display module mounted mounting an TFT on the display panel. The light-emitting element has a light-emitting layer containing an organic compound material which can obtain the electro luminescence generated by adding the electric field, the anode layer and the cathode layer. Further, in the luminescence in an organic compound, the luminescence (fluorescence light) when returning from the state of singlet exciton to the basic state and the luminescence (phosphorus light) when returning from the state of triplet exciton to the basic state. Either or both luminescence are contained.

Further, in this embodiment, the organic light-emitting layer is defined all layers formed between the anode and the cathode. The organic light-emitting layer is specifically including the light-emitting layer, the hole injection layer, the electron injection layer, the hole transport layer, the electron transport layer and the like. Basically, the light-emitting element have a structure which is constructed by the anode layer, the light-emitting layer and the cathode layer sequentially. Additionally, the light-emitting layer may have following two structures. The first structure is constructed sequentially by the anode layer, the hole injection layer, the light-emitting layer and the cathode layer. The second structure is sequen-



tially constructed by the anode layer, the hole injection layer, the light-emitting layer, the electron injection layer, the cathode layer and the like.

FIG. 17 is a cross-sectional view of the light-emitting device of the present invention. In FIG. 17, a switching TFT 603 provided on a substrate 700 is formed using the n-channel type TFT 503 of FIG. 17. Thus, this structure may be referred to the description of the n-channel type TFT 503.

Note that, in this embodiment, a double gate structure in which two channel forming regions are formed is used. However, a single gate structure in which one channel forming region is formed, or a triple gate structure in which three channel forming regions are formed may be used.

A driver circuit provided on the substrate 700 is formed using the CMOS circuit of FIG. 14. Thus, this structure may be referred to the descriptions of the n-channel type TFT 501 and the p-channel type TFT 502. Note that, in this embodiment, the single gate structure is used. However, the double gate structure or the triple gate structure may also be used.

Also, wirings 701 and 703 function as a source wiring of the CMOS circuit, a wiring 702 functions as a drain wiring thereof. A wiring 704 functions as a wiring for electrically connecting a source wiring 708 with a source region of the switching TFT. A wiring 705 functions as a wiring for electrically connecting a drain wiring 709 with a drain region of the switching TFT.

Note that, a current-controlled TFT 604 is formed using the p-channel type TFT 502 of FIG. 14. Thus, this structure may be referred to the descriptions of the p-channel type TFT 502. Note that, in this embodiment, the single gate structure is used. However, the double gate structure or the triple gate structure may be used.

Also, a wiring 706 is a source wiring (corresponding to a current supply line) of the current-controlled TFT 604 and a wiring 707 is a drain wiring of the current-controlled TFT 604. Reference numeral 707 denotes an electrode which is electrically connected with a pixel electrode 711 by overlapping with the pixel electrode 711 of the current-controlled TFT 604.

Note that, reference numeral 711 denotes the pixel electrode (anode of a light-emitting element) made from a transparent conductive film. As the transparent conductive film, a compound of indium oxide and tin oxide, a compound of indium oxide and zinc oxide, zinc oxide, tin oxide, or indium oxide can be used. Also, the above-mentioned transparent conductive film to which gallium is added may be used. The pixel electrode 711 is formed on a level interlayer insulating film 710 before the formation of the above wirings. In this embodiment, it is very important to level a step in the TFT using the leveling film 710 made of resin. Since a light-emitting layer formed later is extremely thin, there is the case where insufficient light-emitting occurs due to the step. Thus, in order to form the light-emitting layer as level as possible, it is desired that the step is leveled before the formation of the pixel electrode 711.

After the wirings 701 to 707 are formed, a bank 712 is formed as shown in FIG. 17. The bank 712 may be formed by patterning an insulating film with a thickness of 100 to 400 nm containing silicon or an organic resin film.

Note that, since the bank 712 is an insulating film, it is necessary to pay attention to a dielectric breakdown of an element in the film formation. In this embodiment, a carbon particle or a metal particle is added to the insulating film which is a material of the bank 712 to reduce a resistivity. Thus, an electrostatic occurrence is suppressed. Here, an additional amount of the carbon particle or the metal particle

may be controlled such that the resistivity is  $1 \times 10^6$  to  $1 \times 10^{12}$   $\Omega\text{m}$  (preferably,  $1 \times 10^8$  to  $1 \times 10^{10}$   $\Omega\text{m}$ ).

A light emitting layer 713 is formed on the pixel electrode 710. Note that, only one pixel is shown in FIG. 17. However, in this embodiment, the light-emitting layers are formed corresponding to respective colors of R (red), G (green), and B (blue). Also, in this embodiment, a low molecular organic light-emitting material is formed by an evaporation method. Concretely, copper phthalocyanine (CuPc) film with a thickness of 20 nm is provided as a hole injection layer, and a tris-8-quinolinolate aluminum complex ( $\text{Alq}_3$ ) film with a thickness of 70 nm is provided thereon as a light-emitting layer. Thus, a lamination structure of those films is formed. A light-emitting color can be controlled by adding a fluoro-chrome such as quinacridon, perylene, or DCM1 to  $\text{Alq}_3$ .

Note that, the above example is one example of the organic light-emitting material which can be used as the light-emitting layer, and it is unnecessary to be limited to this example. The light-emitting layer (layer for causing light to emit and a carrier to move for the emitting of light) may be formed by freely combining the light-emitting layer and a charge transport layer or a charge injection layer. For example, in this embodiment, although the example that the low molecular organic light-emitting material is used as the light-emitting layer is shown, intermediate molecular-weight organic light emitting material or a polymer organic light-emitting material may be also used. Furthermore, an organic light-emitting material, having no sublimation property but having molecules in the number of 20 or less or chained molecules having a length of 10  $\mu\text{m}$  or less, is provided as an intermediate molecular organic light emitting material. For an example of using the high molecular weight organic light emitting material, a polythiophene (PEDOT) film with a thickness of 20 nm is formed by the spin coating method as a hole injection layer and the lamination structure installing paraphenylenvinylene (PPV) of about 100 nm on it as a light emitting layer may be good. The luminescence wave length can be selected from red to blue by using the  $\pi$ -conjugated type polymer of PPV. Meanwhile, it is possible to use an inorganic material such as silicon carbide for an electron transporting layer or charge injecting layer. These organic light emitting materials or inorganic materials can be a known material.

Next, a cathode 714 made from a conductive film is provided on the light-emitting layer 713. In the case of this embodiment, an alloy film of aluminum and lithium is used as the conductive film. Of course, a known MgAg film (alloy film of magnesium and silver) may be used. As a cathode material, the conductive film made of an element which belongs to group 1 or group 2 of the periodic table, or the conductive film to which those elements are added may be used.

When this cathode 714 is formed, a light-emitting element 715 is completed. Note that, the light-emitting element 715 completed here represents a diode formed by the pixel electrode (anode) 711, the light-emitting layer 713, and the cathode 714.

It is effective to provide a passivation film 716 so as to completely cover the light-emitting element 715. As the passivation film 716, a single layer of an insulating film containing a carbon film, a silicon nitride film, or silicon oxynitride film, or a lamination layer of a combination with the insulating film is used.

Here, it is preferred that a film with a good coverage is used as the passivation film, and it is effective to use the carbon film, in particular a DLC (diamond like carbon) film. Since the DLC film can be formed in a range of a room temperature to 100° C., it can be easily formed over the light-emitting

layer **713** with a low heat-resistance. Also, since the DLC film has a high blocking effect against oxygen, the oxidation of the light-emitting layer **713** can be suppressed. Thus, the oxidation of the light-emitting layer **713** during the following sealing process can be prevented.

Further, a sealing member **717** is provided on the passivation film **716**, and then a cover member **718** is adhered to the sealing member **717**. Ultraviolet light cured resin may be used as the sealing member **717**, and it is effective to provide a material having a hygroscopic effect or a material having an oxidation inhibition effect inside. Also, in this embodiment, a member in which a carbon film (preferably, a diamond carbon like film) is formed on both surfaces of, a glass substrate, a quartz substrate, or a plastic substrate (including a plastic film) is used as the cover member **718**. Aluminum film (AlON, AlN, AlO and the like), SiN and the like can be used instead of a carbon film.

Thus, a light-emitting device of the structure as shown in FIG. **17** is completed. Note that, after the formation of the bank **712**, it is effective to successively perform the processes until the formation of the passivation film **716** using a film formation apparatus of a multi chamber system (or an inline system) without exposing to air. Further, processes until the adhesion of the cover member **718** can be successively performed without exposing to air.

Thus, n-channel TFT **601**, p-channel TFT **602**, a switching TFT (n-channel TFT) **603**, and a current control TFT (p-channel TFT) **604** are formed on the substrate **700**.

Further, as described using FIG. **17**, when the impurity regions overlapped with the gate electrode through the insulating film are provided, the n-channel TFT having a high resistant against the deterioration due to a hot carrier effect can be formed. Thus, the light-emitting device with high reliability can be realized.

In this embodiment, only the structures of the pixel portion and the driver circuit are shown. However, according to the manufacturing process of this embodiment, logic circuits such as a signal separation circuit, a D/A converter, an operational amplifier, a  $\gamma$ -correction circuit and the like can be further formed on the same insulating material. A memory and a microprocessor can be also formed.

Thus formed light-emitting device have a TFT which is formed by using the semiconductor film conducted homogeneous annealing. Therefore, enough operating characteristics and reliability of the above-mentioned light-emitting device can be obtained. Such light-emitting device can be used as a display portion of various electronic devices.

This embodiment can be performed by freely combining with Embodiments 1 to 7.

#### Embodiment 10

Various semiconductor devices (active matrix type liquid crystal display device, active matrix type light-emitting device or active matrix type EC display device) can be formed by applying the present invention. Specifically, the present invention can be embodied in electrooptics equipment of any type in which such an electrooptical device is incorporated in a display portion.

Such electronic equipment is a video camera, a digital camera, a projector, a head-mounted display (goggle type display), a car navigation system, a car stereo, a personal computer, or a mobile information terminal (such as a mobile computer, a mobile telephone, an electronic book and the like). FIGS. **18A-18F**, **19A-19D**, and **20A-20C** show one of its examples.

FIG. **18A** shows a personal computer which includes a body **3001**, an image input portion **3002**, a display portion **3003**, a keyboard **3004** and the like. A personal computer completes by applying the semiconductor device that applies this invention to display portion **3003**.

FIG. **18B** shows a video camera which includes a body **3101**, a display portion **3102**, a sound input portion **3103**, operating switches **3104**, a battery **3105**, an image receiving portion **3106** and the like. A video camera completes by applying the semiconductor device that applies this invention to display portion **3102**.

FIG. **18C** shows a mobile computer which includes a body **3201**, a camera portion **3202**, an image receiving portion **3203**, an operating switch **3204**, a display portion **3205** and the like. A mobile computer completes by applying the semiconductor device that applies this invention to display portion **3205**.

FIG. **18D** shows a goggle type display which includes a body **3301**, a display portion **3302**, arm portions **3303** and the like. A goggle type display completes by applying the semiconductor device that applies this invention to display portion **3302**.

FIG. **18E** shows a player using a recording medium on which a program is recorded (hereinafter referred to as the recording medium), and the player includes a body **3401**, a display portion **3402**, speaker portions **3403**, a recording medium **3404**, operating switches **3405** and the like. This player uses a DVD (Digital Versatile Disc), a CD and the like as the recording medium, and enables a user to enjoy music, movies, games and the Internet. A recording medium completes by applying the semiconductor device that applies this invention to display portion **3402**.

FIG. **18F** shows a digital camera which includes a body **3501**, a display portion **3502**, an eyepiece portion **3503**, operating switches **3504**, an image receiving portion (not shown) and the like. A digital camera completes by applying the semiconductor device that applies this invention to display portion **3502**.

FIG. **19A** shows a front type projector which includes a projection device **3601**, a screen **3602** and the like. A front type projector completes by applying the semiconductor device that applies this invention to a liquid crystal display device **3808** composing a part of a projection device **3601** as well as other driver circuit.

FIG. **19B** shows a rear type projector which includes a body **3701**, a projection device **3702**, a mirror **3703**, a screen **3704** and the like. A rear type projector completes by applying the semiconductor device that applies this invention to a liquid crystal display device **3808** composing a part of a projection device **3702** as well as other driver circuit.

FIG. **19C** shows one example of the structure of each of the projection devices **3601** and **3702** which are respectively shown in FIGS. **19A** and **19B**. Each of the projection devices **3601** and **3702** is made of a light source optical system **3801**, mirrors **3802** and **3804-3806**, a dichroic mirror **3803**, a prism **3807**, a liquid crystal display device **3808**, a phase difference plate **3809** and a projection optical system **3810**. The projection optical system **3810** is made of an optical system including a projection lens. Embodiment 10 is an example of a three-plate type, but it is not limited to this example and may also be of a single-plate type. In addition, those who embody the invention may appropriately dispose an optical system such as an optical lens, a film having a polarization function, a film for adjusting phase difference or an IR film in the path indicated by arrows in FIG. **19C**.

FIG. **19D** is a view showing one example of the structure of the light source optical system **3801** shown in FIG. **19C**. In

31

Embodiment 10, the light source optical system **3801** is made of a reflector **3811**, a light source **3812**, lens arrays **3813** and **3814**, a polarizing conversion element **3815** and a condenser lens **3816**. Incidentally, the light source optical system shown in FIG. 19D is one example, and the invention is not particularly limited to the shown construction. For example, those who embody the invention may appropriately dispose an optical system such as an optical lens, a film having a polarization function, a film for adjusting phase difference or an IR film.

The projector shown in FIGS. 19A to 19D is of the type using a transparent type of electrooptical device, but there is not shown an example in which the invention is applied to a reflection type of electrooptical device and a light-emitting device.

FIG. 20A shows a cell phone which includes a body **3901**, a sound output portion **3902**, a sound input portion **3903**, a display portion **3904**, operating switches **3905**, an antenna **3906** and the like. A cell phone completes by applying the semiconductor device that applies this invention to display portion **3904**.

FIG. 20B shows a mobile book (electronic book) which includes body **4001**, display portions **4002** and **4003**, a storage medium **4004**, operating switches **4005**, an antenna **4006** and the like. A mobile book completes by applying the semiconductor device that applies this invention to display portion **4002** and **4003**.

FIG. 20C shows a display which includes a body **4101**, a support base **4102**, a display portion **4103** and the like. A display completes by applying the semiconductor device that applies this invention to display portion **4103**. The invention is particularly advantageous to a large-screen display, and is advantageous to a display having a diagonal size of 10 inches or more (particularly, 30 inches or more).

As is apparent from the foregoing description, the range of applications of the invention is extremely wide, and the invention can be applied to any category of electronic apparatus. Electronic apparatus according to the invention can be realized by using a construction made of a combination of arbitrary ones of Embodiments 1 to 8 and 9.

Employing the structures of the present invention provides the following basic usefulness:

a) Laser light very excellent in uniformity of energy distribution can be formed on an irradiation surface or in the vicinity thereof and accordingly an irradiation object can be annealed uniformly.

b) Laser beams emitted from different lasers are synthesized and therefore interference does not take place, and this is effective especially when highly interferential lasers are used.

c) The throughput can be improved, which is effective particularly when a substrate has a large area.

d) With those advantages given in the above, the present invention can improve the operation characteristic and reliability of semiconductor devices, typically, active matrix liquid crystal display devices, and can lower manufacture cost of semiconductor devices.

What is claimed is:

1. A method of manufacturing a semiconductor device comprising the steps of:

forming an amorphous semiconductor film over a substrate;

emitting a first laser beam from a first laser; dividing the first laser beam into at least two divided first laser beams;

emitting a second laser beam from a second laser; dividing the second laser beam into at least two divided second laser beams;

32

synthesizing one of the at least two divided first laser beams and one of the at least two divided second laser beams to form a synthesized laser beam; and

irradiating the amorphous semiconductor film with the synthesized laser beam to crystallize the amorphous semiconductor film;

patterning the crystallized semiconductor film to form a semiconductor layer including a channel formation region of a thin film transistor.

2. The method according to claim 1, wherein the amorphous semiconductor film comprises silicon.

3. The method according to claim 1, wherein each of the first laser beam and the second laser beam is selected from the group consisting of a continuous wave or pulse oscillation YAG laser, YVO<sub>4</sub> laser, YLF laser, YAlO<sub>3</sub> laser, Y<sub>2</sub>O<sub>3</sub> laser, glass laser, ruby laser, alexandrite laser, and Ti:sapphire laser.

4. The method according to claim 1, wherein each of the first laser beam and the second laser beam is selected from the group consisting of an Ar laser, Kr laser, and CO<sub>2</sub> laser.

5. The method according to claim 1, further comprising the steps of:

forming a gate insulating film over the semiconductor layer; and

forming a gate electrode over the semiconductor layer with the gate insulating film therebetween.

6. A method of manufacturing a semiconductor device comprising the steps of:

forming a semiconductor film over a substrate;

emitting a first laser beam from a first laser;

dividing the first laser beam into at least two divided first laser beams;

emitting a second laser beam from a second laser;

dividing the second laser beam into at least two divided second laser beams;

synthesizing one of the two divided first laser beams and one of the two divided second laser beams to form a synthesized laser beam; and

irradiating the semiconductor film with the synthesized laser beam to increase crystallinity of the semiconductor film;

patterning the semiconductor film after irradiation of the synthesized laser beam to form a semiconductor layer including a channel formation region of a thin film transistor.

7. The method according to claim 6, wherein the semiconductor film comprises silicon.

8. The method according to claim 6, wherein each of the first laser beam and the second laser beam is selected from the group consisting of a continuous wave or pulse oscillation YAG laser, YVO<sub>4</sub> laser, YLF laser, YAlO<sub>3</sub> laser, Y<sub>2</sub>O<sub>3</sub> laser, glass laser, ruby laser, alexandrite laser, and Ti:sapphire laser.

9. The method according to claim 6, wherein each of the first laser beam and the second laser beam is selected from the group consisting of an Ar laser, Kr laser, and CO<sub>2</sub> laser.

10. The method according to claim 6, further comprising the steps of:

forming a gate insulating film over the semiconductor layer; and

forming a gate electrode over the semiconductor layer with the gate insulating film therebetween.

11. The method according to claim 6, further comprising the step of heating the semiconductor film to crystallize the semiconductor film prior to irradiation of the synthesized laser beam.