

United States Defensive Publication [19] (H) [11]**T964,011****Blanken**

[43]


Nov. 1, 1976

- [54] **ADHESIVE COMPOSITIONS HAVING A CARBON BLACK COMPONENT**
- [76] Inventor: **Thomas C. Blanken**, 3 Badhuisweg, Amsterdam, Netherlands
- [21] Appl. No.: **772,810**
- [22] Filed: **Feb. 28, 1977**
- [30] **Foreign Application Priority Data**
Mar. 30, 1976 United Kingdom 12744/76
- [51] Int. Cl.² **C08L 95/00; C08L 53/02; B32B 11/04; B32B 27/00**
- [52] U.S. Cl. **428/489; 260/28.5 AS; 260/28.5 AV; 260/28.5 B; 428/408; 428/521; 428/522; 428/523**

[57] **ABSTRACT**

Article provided with a pressure-sensitive adhesive layer composition, which composition is characterized by improved flow resistance at high temperatures (e.g. at 90° C), and which comprises 50-97 parts by weight of a bituminous component dispersed in an extender oil, 3

to 50 parts by weight of at least one thermoplastic polymer, which is preferably a block polymer having the general structure:



where A is a monoalkenyl arene block, B is a conjugated diene block, and n is an integer from 1-15, and 5 to 50% by weight (based on the combined weight of the bituminous component and the thermoplastic polymer) of a carbon black having an oil absorptivity of above 80 milliliters per 100 grams. Such articles usually possess good low temperature flexibility, tack and adhesive strength.

9 Claims, No Sheets Drawing,**10 Pages Specification**

The file of this unexamined application may be inspected and copies thereof may be purchased (849 O.G. 1221, Apr. 9, 1968).