



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2758645 C 2014/01/21

(11)(21) **2 758 645**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(22) Date de dépôt/Filing Date: 2011/11/17

(41) Mise à la disp. pub./Open to Public Insp.: 2012/05/24

(45) Date de délivrance/Issue Date: 2014/01/21

(30) Priorité/Priority: 2010/11/24 (US12/954,332)

(51) Cl.Int./Int.Cl. *G03G 9/08* (2006.01),
C08J 3/16 (2006.01), *C09D 11/10* (2006.01)

(72) Inventeurs/Inventors:
KMIECIK-LAWRYNOWICZ, GRAZYNA E., US;
SWEENEY, MAURA A., US;
ASARESE, DANIEL W., US;
CORLETO, ROBERT A., US;
KUMAR, SAMIR, US;
MORALES-TIRADO, JUAN A., US;
ZONA, MICHAEL F., US

(73) Propriétaire/Owner:
XEROX CORPORATION, US

(74) Agent: SIM & MCBURNEY

(54) Titre : COMPOSITIONS DE TONER ET REVELATEURS CONTENANT CES TONERS

(54) Title: TONER COMPOSITIONS AND DEVELOPERS CONTAINING SUCH TONERS

(57) **Abrégé/Abstract:**

A toner composition with a novel surface additive package for developing images. The additive package includes sol-gel silica, a PDMS silica, an organic spacer such as PMMA and two HMDS silicas. The toner composition exhibits improved control of voltage, higher print density, lower toner amount remaining on the roll, lower toner usage, and reduced drum contamination. The toner composition also exhibits improved dry rheological properties and improved fix properties. These improved properties make this toner composition useful for higher speed printing while using less toner.

ABSTRACT

A toner composition with a novel surface additive package for developing images. The additive package includes sol-gel silica, a PDMS silica, an organic spacer such as PMMA and two HMDS silicas. The toner composition exhibits improved control of voltage, higher print density, lower toner amount remaining on the roll, lower toner usage, and reduced drum contamination. The toner composition also exhibits improved dry rheological properties and improved fix properties. These improved properties make this toner composition useful for higher speed printing while using less toner.

TONER COMPOSITIONS AND DEVELOPERS CONTAINING SUCH TONERS

TECHNICAL FIELD

[0001] This disclosure is generally directed to toner compositions, and methods for producing such toners, for use in forming and developing images of good quality. More specifically, this disclosure is directed to toner compositions containing a novel toner particle formulation and a novel surface additive package, and methods for producing such compositions. Such compositions are useful, for example, as toners in single component development (SCD) systems.

BACKGROUND

[0002] Emulsion aggregation (EA) toners are used in forming print and/or xerographic images. Emulsion aggregation techniques typically involve the formation of an emulsion latex of resin particles that have a small size of from, for example, about 5 to about 500 nanometers in diameter, by heating the resin, optionally with solvent if needed, in water, or by making a latex in water using an emulsion polymerization. A colorant dispersion, for example of a pigment dispersed in water, optionally with additional resin, is separately formed. The colorant dispersion is added to the emulsion latex mixture, and an aggregating agent or complexing agent is then added and/or aggregation is otherwise initiated to form aggregated toner particles. The aggregated toner particles are heated to enable coalescence/fusing, thereby achieving aggregated, fused toner particles. United States patent documents describing emulsion aggregation toners include, for example, U.S. Patent Nos. 5,278,020; 5,290,654; 5,308,734; 5,344,738; 5,346,797; 5,348,832; 5,364,729; 5,366,841; 5,370,963; 5,403,693; 5,405,728; 5,418,108; 5,496,676; 5,501,935; 5,527,658; 5,585,215; 5,650,255; 5,650,256; 5,723,253; 5,744,520; 5,747,215; 5,763,133; 5,766,818; 5,804,349; 5,827,633; 5,840,462; 5,853,943; 5,853,944; 5,863,698; 5,869,215; 5,902,710; 5,910,387; 5,916,725; 5,919,595; 5,925,488; 5,977,210; 6,576,389; 6,617,092; 6,627,373; 6,638,677; 6,656,657; 6,656,658; 6,664,017; 6,673,505; 6,730,450; 6,743,559; 6,756,176; 6,780,500; 6,830,860; and 7,029,817; and U.S Patent Application Publication No. 2008/0107989.

[0003] The appropriate components and process aspects of each of the foregoing patents and publications may also be selected for the present compositions and processes in embodiments thereof.

[0004] Current formulations of toner show a need for improved fusing performance. Poor fusing creates problems in paper adhesion and print performance.

[0005] Current formulations of toner show a need for improved flow. Poor flow creates problems in gravity-fed cartridges, causing toner to hang up due to poor flow properties and leads to deletions on paper.

[0006] There remains a need for an improved toner composition and process that overcomes or alleviates the above-described and other problems. There further remains a need for a toner composition suitable for high speed printing, particularly high speed monochrome printing that can provide excellent flow, charging, lower toner usage, and reduced drum contamination.

SUMMARY

[0007] This disclosure addresses some or all of the above problems, and others, by providing new toner compositions including a novel additive package. This disclosure thus relates to toners, developers containing toners, and devices for generating developed images with, for example, high print quality.

[0008] Herein is disclosed a toner composition comprising toner particles that comprise a resin, an optional wax, and an optional colorant; and a surface additive at least partially coating toner particle surfaces. The surface additive comprises a mixture of: a hexamethyldisilazane (HMDS) surface treated silica, a sol-gel silica that is not surface treated, and an optional polydimethylsiloxane (PDMS) surface treated silica.

[0009] Also disclosed is a method of making a toner composition by forming a slurry by mixing together an emulsion containing a resin, optionally a wax, optionally a colorant, optionally a surfactant, optionally a coagulant, and one or more additional optional additives; heating the slurry to form aggregated particles in the slurry; freezing aggregation of the particles by adjusting the pH; heating the aggregated particles in the slurry to coalesce the particles into toner particles; recovering the toner particles; and coating the toner particles with a surface additive comprising a mixture of: a hexamethyldisilazane (HMDS) surface treated silica, a sol-gel silica that is not surface treated, and an optional polydimethylsiloxane (PDMS) surface treated silica.

[0009a] In another aspect, there is provided a toner composition comprising:

toner particles comprising:

a resin;

an optional wax; and

an optional colorant; and

a surface additive at least partially coating toner particle surfaces, the surface additive comprising a mixture of:

2a

a first hexamethyldisilazane (HMDS) surface treated silica,
a second HMDS surface treated silica,
a sol-gel silica that is not surface treated, and
a polydimethylsiloxane (PDMS) surface treated silica,

wherein the first HMDS surface treated silica has a different average particle diameter than the second HMDS surface treated silica.

[0009b] In another aspect, there is provided a method of making a toner composition, the method comprising:

forming a slurry by mixing together:

an emulsion containing a resin;
optionally a wax;
optionally a colorant;
optionally a surfactant;
optionally a coagulant; and
one or more additional optional additives;

heating the slurry to form aggregated particles in the slurry;

freezing aggregation of the particles by adjusting the pH;

heating the aggregated particles in the slurry to coalesce the particles into toner particles;

washing and drying the toner particles; and

coating the toner particles with a surface additive comprising a mixture of:

a first hexamethyldisilazane (HMDS) surface treated silica,
a second HMDS surface treated silica,
a sol-gel silica that is not surface treated, and
a polydimethylsiloxane (PDMS) surface treated silica

wherein the first HMDS surface treated silica has a different average particle diameter than the second HMDS surface treated silica.

EMBODIMENTS

[0010] In this specification and the claims that follow, singular forms such as "a," "an," and "the" include plural forms unless the content clearly dictates otherwise. All ranges disclosed herein include, unless specifically indicated, all endpoints and intermediate values. In addition, reference may be made to a number of terms that shall be defined as follows:

2b

[0011] The term "functional group" refers, for example, to a group of atoms arranged in a way that determines the chemical properties of the group and the molecule to which it is

26. The method of claim 24, wherein the organic spacer has a volume average diameter of from about 300 to about 600 nm.

27. The composition of claim 1, further comprising an organic spacer, wherein the toner composition exhibits:

a flow of from about 25 to about 55%;

a compressibility of from about 8 to about 11% (at 10 kPa); and

an image density of from about 1.2 to about 1.8.

28. The composition of claim 27, wherein the organic spacer is polymethylmethacrylate (PMMA).

29. The composition of claim 1, wherein the surface additive further comprises an organic spacer having a volume average diameter of from about 300 to about 600 nm.