



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2675487 C 2012/05/08

(11)(21) **2 675 487**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**


(86) Date de dépôt PCT/PCT Filing Date: 2008/09/29
(87) Date publication PCT/PCT Publication Date: 2009/09/17
(45) Date de délivrance/Issue Date: 2012/05/08
(85) Entrée phase nationale/National Entry: 2009/08/21
(86) N° demande PCT/PCT Application No.: US 2008/078104
(87) N° publication PCT/PCT Publication No.: 2009/117022
(30) Priorité/Priority: 2008/03/17 (US12/049,668)

(51) Cl.Int./Int.Cl. *C08L 31/04* (2006.01),
C08J 11/18 (2006.01), *C08K 5/00* (2006.01)
(72) Inventeur/Inventor:
GROSSMAN, RICHARD F., US
(73) Propriétaire/Owner:
BIOTECH PRODUCTS, LLC, US
(74) Agent: MACRAE & CO.

(54) Titre : COMPOSITIONS DE POLYMERES D'ACETATE DE VINYLE COMPOSTABLES, COMPOSITES ET
BIODEGRADATION DANS UNE DECHARGE
(54) Title: COMPOSTABLE VINYL ACETATE POLYMER COMPOSITIONS, COMPOSITES AND LANDFILL
BIODEGRADATION

(57) **Abrégé/Abstract:**

Compositions of vinyl acetate polymers such as polyvinyl acetate (PVAc) are rendered compostable by a monomeric adduct of an organotitanate or zirconate as a prodegradant. PVAc sheets and composites are compostable in landfills.



-24-

**COMPOSTABLE VINYL ACETATE POLYMER COMPOSITIONS,
COMPOSITES AND LANDFILL BIODEGRADATION**

ABSTRACT OF THE DISCLOSURE

Compositions of vinyl acetate polymers such as polyvinyl acetate (PVAc) are rendered compostable by a monomeric adduct of an organotitanate or zirconate as a prodegradant. PVAc sheets and composites are compostable in landfills.

-1-

**COMPOSTABLE VINYL ACETATE POLYMER COMPOSITIONS,
COMPOSITES AND LANDFILL BIODEGRADATION**

FIELD OF THE INVENTION

[0002] This invention relates to compostable or biodegradable vinyl acetate polymer compositions, for example, polyvinyl acetate (PVAc) and composite sheets of such polymers. Articles of vinyl acetate polymers anaerobically biodegrade in landfills in a relatively short time.

BACKGROUND OF THE INVENTION

[0003] For many years it has been desired to make plastic materials from polymers such as polyvinyl chloride (PVC) and polyvinyl acetate (PVAc), which are either biodegradable by microorganisms or environmentally degradable such as in a landfill. In spite of considerable efforts, landfills are becoming inundated with plastic materials, and articles made therefrom, that will not degrade perhaps for centuries. This is especially true for vinyl halide polymer materials such as PVC that are considered non-biodegradable, that is, they persist in landfills under anaerobic conditions indefinitely without noticeable decomposition. This factor limits the

-2-

acceptance of PVC in many products where its useful balance of properties and low cost would be attractive. An example is that of printable film and sheet. If a sample of flexible (plasticized) PVC is tested per ASTM D 5526, Standard Test Method for Determining Anaerobic Biodegradation of Plastic Materials Under Accelerated Landfill Conditions, there is no appreciable weight loss or change in appearance after 100 days at 97°F in contact with simulated household waste. In contrast, cellulosic polymers and other biodegradable plastics, such as polylactic acid and polycaprolactone, are completely consumed.

[0004] There has been a particular need for a compostable polymer composition for use in many end products such as polyvinyl chloride or polyvinyl acetate films, banners, billboards, signs, laminates, ink jet media, diapers, hygienic pads and the like. These products must satisfy properties for practical purposes such as tear strength, tensile and impact strengths to function in many useful articles. However, the same properties that make them useful lead to their lack of biodegradability. PVC, PVAc and other vinyl polymers have achieved widespread usage. However, the explosive growth of such thermoplastics has aggravated the problem of disposing of them, and has caused their accumulation in landfills. Very little of these polymeric waste products degrade in most landfills because of anaerobic conditions. The problem has become aggravated because of the shortage of landfills and municipalities are seeking to restrict the use of plastics because of their inability to degrade in landfills.

SUMMARY OF THE INVENTION

[0005] This invention is directed to a compostable vinyl acetate polymer composition. In particular, polyvinyl acetate (PVAc) compositions have been rendered compostable by formulation with an organotitanate or zirconate compound, which compound facilitates biodegradation of the PVAc compositions (said organotitanate or zirconate compound hereinafter referred to as a "prodegradant"). Moreover, this invention is directed to a method of anaerobic biodegradation of vinyl acetate polymer articles in a landfill.

[0006] As reported in U.S. Patent No. 7,390,841, polyvinyl chloride compositions have been formulated with plasticizer and stabilizer along with the prodegradant composition. Polymeric sheets containing this composition and composites with woven or nonwoven sheets have been made compostable. Such compositions consist of (a) PVC; (b) a plasticizer selected from

the group of completely aliphatic carboxylic acid esters; (c) a heat stabilizer selected from the group of sulfur-free dialkyl and monoalkyltin carboxylates; and (d) a reactive organotitanate or organozirconate. As reported in Patent Appln. No. CA 2,575,674, further unobvious and unexpected improvements have been made. In particular, compositions of vinyl halide resins such as PVC, even without plasticizer, are compostable when the prodegradant system is employed. In addition, it has also been found that the reactive organotitanate or organozirconate can be broadened to include other monomeric adducts in addition to the amide adduct disclosed in U.S. Patent No. 7,390,841. For instance, an ester adduct of the organotitanate or organozirconate and an organotin compound, in relative amounts, has been found to render the vinyl halide polymer composition compostable, even in the absence of a plasticizer.

[0007] This application is directed to compostable vinyl acetate polymer compositions comprising a vinyl acetate polymer and a monomeric adduct of an organotitanate, or organozirconate, as a prodegradant in relative amounts to render the vinyl acetate polymer composition compostable. As employed herein, the term "adduct" is intended to mean a complex association of the monomeric molecule and the organotitanate or organozirconate molecule. It was previously reported that amide salts of the neoalkoxy modified monoalkoxy titanate or zirconate achieved the objectives of the invention. The amide salts were defined particularly by methacrylamide as the monomeric adduct of the reactive titanate or zirconate. It has also been found that the ester adducts of the specific organotitanates or zirconates can also function in the prodegradant of this invention. The monomeric ester of the organotitanate or organozirconate adduct is exemplified by dimethylaminoethyl methacrylate. It has also been found that the dimethylaminopropyl acrylamide is found to be as effective as the methacrylamide.

[0008] The compositions and composites of this invention, as well as useful articles made therefrom, are compostable. "Compostable" means that the composition or sheet undergoes chemical, physical, thermal and/or biological degradation such that it may be incorporated into and is physically indistinguishable from finished compost (humus) and which ultimately mineralizes (biodegrades) to CO₂, water and biomass in the environment like other known compostable matter such as paper and yard waste. The compostable films and composites are either

-4-

biodegradable or environmentally degradable. "Biodegradable" means that the composition or composite is susceptible to being assimilated by microorganisms when buried in the ground or otherwise contacted with the organisms under conditions conducive to their growth. "Environmentally degradable" means that the film or layer is capable of being degraded by heat or surrounding environmental elements without microorganisms to a form that ultimately may be biodegradable when it mineralizes, for example, biodegrades to carbon dioxide, water and biomass.

For purposes of this invention, "compostable" is intended to include "biodegradable" or "environmentally degradable".

[0009] Composting conditions that enable the chemical, physical, thermal and/or biological degradation of the composition or composite may vary. The compositions or composites of this invention are especially adapted to be compostable in municipal solid waste composting facilities or landfills. For example, following ASTM D 5526-94 (reapproved 2002), Standard Test Method for Determining Anaerobic Biodegradation of Plastic Materials Under Accelerated Landfill Conditions, samples of PVC were degraded, incorporated into and physically indistinguishable in the test landfill.

[0010] Compostable vinyl acetate polymer compositions and composites of this invention, their method of manufacture and compostability will be understood with reference to the following detailed description.

DETAILED DESCRIPTION OF THE INVENTION

A. Vinyl Acetate Polymer

[0011] The vinyl acetate polymer employed is most commonly a homopolymer of vinyl acetate, i.e., polyvinyl acetate. Copolymers of vinyl acetate are also suitably employed. It is to be understood, however, that this invention is not limited to polyvinyl acetate or its copolymers. Other vinyl acetate based polymers which are employed and which illustrate the principles of this invention include partially hydrolyzed polyvinyl acetate, e.g. polyvinyl alcohol, ethylene-vinyl acetate, vinyl chloride-vinyl acetate copolymer or other copolymer types. Vinyl acetate based polymer, as understood herein, and as appreciated in the art, is a common term and is adopted to define those polymers usually derived by polymerization or copolymerization of vinyl acetate monomer with or without other comonomers such

-5-

as ethylene, propylene, vinyl chloride, vinyl ethers, vinylidene chloride, methacrylate, acrylates, styrene, etc. A simple case is the conversion of vinyl acetate to polyvinyl acetate wherein the ether oxygen of the ester group is bonded to the carbon atoms of the carbon chain of the polymer.


B. Prodegradant Organotitanate or Organozirconate Monomeric Adducts

[0012] The prodegradant of this invention is a monomeric adduct of an organozirconate or organotitanate. The monomeric adducts are exemplified by the monomeric groups of dimethylaminopropyl acrylamide, methacrylamide, dimethylaminoethyl methacrylate, and other similar reactive monomeric groups as detailed herein. In a broader sense, the adducts more preferably comprise dialkylamino-short alkylchain-reactive monomers. The prodegradant may be defined more particularly as follows.

[0013] The chemical description and chemical structure of organotitanates or zirconates has been well developed. For instance, Kenrich LICA 38JTM is a reactive titanate under the chemical name titanium IV neoalkanolato, tri(dioctyl) pyrophosphate-O (adduct) N-substituted methacrylamide. Furthermore, with zirconium substituted for titanium, Kenrich produces NZ 38TM under the chemical description zirconium IV neoalkanolato, tri(dioctyl) pyrophosphate-O (adduct) N-substituted methacrylamide. These compounds are generally referred to as amide salts of neoalkoxy modified monoalkoxy titanate or zirconate. While the invention has been exemplified with these amide adducts of these specific organotitanates or organozirconates, it is to be understood that other similar compounds can achieve the objectives of this invention.


[0014] The K38J pyrophosphato titanium adduct is the reaction product of K38 + dimethylaminopropyl methacrylamide (DMPDMA), according to the following structure where R' = methyl, R'' = propyl, R = butyl, n ~ 3.

-6-



[0015] K38 = the above structure without DMPDMA. These two ingredients react rapidly at room temperature when mixed in stoichiometric proportions (close to 3:1). P-OH becomes P-O⁻ and R₂N, R₃N⁺. A bright red color develops, which is the thermochromic, indicating coordination of likely C=O to titanium, which displays such colors when penta-coordinate instead of tetra-coordinate. (For example, acetone•TiCl₄ is orange-red, and the precursors, colorless.) Neither K38 nor DMPDMA cause depolymerization of vinyl acetate polymers when used alone. However, if added separately to the PVAc compound, the combination *in situ* is as effective as K38J. Thus, use of the term "adduct" is intended to cover the use of preformed complex or the separate addition of the components to enable their association or complexing *in situ* to provide the prodegradant effects of this invention.

[0016] A substituted methacrylamide can also be employed as an adduct of the organotitanate or zirconate. For instance, Kenrich Ken-ReactTM KR-238J is another reactive titanate where the monomeric adduct is a substituted methacrylamide. The KR-238J is a dimethylaminopropyl acrylamide which has been found to be as effective as the methacrylamide adduct of Kenrich-38J, described above. A chemical description of KR-238J is di(dioctyl)pyrophosphato ethylene titanate (adduct) N-substituted methacrylamide. Furthermore, dimethylaminoethyl methacrylate, a monomeric ester adduct, is equally effective in combination with the pyrophosphato form of the titanium or zirconium coupling agent. The K238J adduct has the chemical structure as follows:



-7-

[0017] K238 = the above structure without DMPDMA. Thus, as used herein "K38 and "K238" are intended to mean the organopyrophosphato titanate portion of the adduct which is complexed with the monomeric amide, ester, or other like monomers. Specific compounds are exemplified by titanium IV neoalkanolato tri(dioctyl) pyrophosphato-O (adduct) N-substituted methacryloamide and zirconium IV neoalkanolato tri(dioctyl) pyrophosphato-O (adduct) N-substituted methacrylamide, titanium IV bis(dioctyl) pyrophosphato-O (adduct) N,N-dimethylamino-alkyl propenamide, and zirconium IV bis(dioctyl) pyrophosphato-O (adduct) N,N-dimethylamino-alkyl propenamide.

[0018] The above monomeric adducts result from salt formation via the titanate/zirconate acidic $-P=O(OH)$ group. The monomer contains a basic functional group that will react to form a salt (but not go on to other reactions such as oxidation). A tertiary amine group is favorable. This could be a dialkyl amine group, methyl pyridine functionality or a range of basic nitrogen heterocyclic groups. The rest of the reactive monomer must contain an activated carbon-carbon double bond. The $C=C$ bond, to be activated, should be conjugated with $C=O$, as in an ester, ketone, aldehyde or amide, with $-CN$, with oxygen as in a vinyl ether, or with oxygen, nitrogen or sulfur in an allylic linkage, or with an aromatic ring as in styrene or vinyl ferrocene.


[0019] In a more generalized form, the adducts can be defined as:

organotitanate or zirconate $-P=O(OH)$ salt-forming group- $R-C=C$ -activating group,
where R is a hydrocarbon radical or substituted hydrocarbon radical and the activating group is conjugated with the $C=C$.


-8-

[0020] Other monomers of the adducts of this invention are exemplified by the following:


ethyl dimethylaminoethylmethacrylate




methyl dimethylaminopropyl acrylate



2-morpholine-N-ethyl acrylamide




2-piperidinyl-N-ethyl acrylonitrile




-9-

2-dimethylaminoethyl acrolein



dimethylaminoethyl vinyl ether




dimethylaminoethyl vinyl thioether

4-dimethylaminomethyl styrene




allyl 3-dimethylamino propionate




methallyl 3-dimethylamino propionate


-10-




thioallyl 3-dimethylamino propionate



dimethylaminomethyl acrylate (reverse ester), also corresponding reverse amides



dimethylaminomethyl amide



[0021] These organotitanates or zirconates are further described in considerable detail in the following US Patents: 4,069,192; 4,080,353; 4,087,402; 4,094,853

-11-

4,096,110; 4,098,758; 4,122,062; 4,152,311; 4,192,792; 4,101,810; 4,261,913; 4,277,415; 4,338,220; 4,417,009.

C. Organotin Compounds

[0022] When copolymers of vinyl acetate and vinyl chloride are used, mono- and diorganotin compounds are employed as well known stabilizers for PVC in the copolymer. In other words, the prodegradant acts systematically with the organotin as reported in Patent Appln. No. CA 2,575,674, above identified.

The generalized organotin stabilizer formula is R_2SnX_2 or R_2SnX_3 . The R-group used in the above general formula of tin stabilizers can be lower alkyl such as butyl. More recently, because of availability and relatively low cost, fatty acid carboxylates have been employed. Cost-effective methods have been developed to produce tin intermediates, which were then reacted with carboxylic acids or with ligands containing mercaptan groups to yield stabilizers for vinyl acetate resins. Accordingly, among the class of organotin compounds suitable for use in accordance with this invention are organotin carboxylates or organotin sulfur-containing compounds are U.S. Patents 2,641,588; 2,648,650, 2,726,227; 2,726,254; 2,801,258; 2,870,119; 2,891,922; 2,914,506 and 2,954,363; the organotin mercaptoacid esters as described in U.S. Patent 2,641,596; organotin esters of mercapto alcohols of U.S. Patents 2,870,119; 2,870,182; 2,872,468 and 2,883,363; and organo thiostannoic acids such as butyl thiostannoic acid as disclosed in U.S. Patents 3,021,302; 3,413,264; 3,424,712 and 3,424,717.

Organotin carboxylates, such as dibutyltin dilaurate or dibutyltin maleate, are preferred. Other organotins can be used.

D. Prodegradant Synergistic Composition

[0023] It has been discovered that the prodegradant of organotitanate or organozirconate adduct, i.e., the organopyrophosphato monomeric adduct, displays an unpredicted synergism in the compostability of vinyl acetate polymers. The remarkable compostability property exists over ranges of ratios of the essential components. The exact mechanism for the unexpected results and the compostability of vinyl acetate polymers with the prodegradant is not completely

-12-

understood. Certainly there are theories which could be proposed, but regardless of theories, the beneficial results evident in the numerous examples of this invention which follow, in further view of this detailed description, speak for themselves. Applicant relies upon these empirical demonstrations of the principles of this invention to advance its merit.

[0024] With the prodegradant of this invention, it has been found that the total composition of prodegradant is useful over a range of about 1 to about 10 parts (phr) by weight based upon 100 parts by weight of the vinyl acetate polymer. The most useful range of total parts by weight of the organotin or zirconate in the total composition is on the order of about 5 to about 7 phr. Where copolymers of PVC/VAC are used as reported above, in the case of organotin compound, the most useful parts are on the order of about 2 to about 3 phr. Each of the components of the system can range from 1 to 10 phr. The ratios of the components is not considered to be critically limiting among the broader aspects of the invention.

E. Plasticizer

[0025] It has been found that the plasticized and unplasticized PVAc compositions are compostable with the prodegradant system of this invention, as reported in Example 13 of Patent Appln. No. CA 2,575,674. However, when necessary or as desired, the vinyl acetate composition can be plasticized with aliphatic or aromatic esters, typically, di-octyl adipate (DOA), di-isononylester of cyclohexane dicarboxylic acid or di-isodecyl phthalate (DIDP). In its presently best mode, the aliphatic ester is used.

[0026] The principles of this invention and its operating parameters will be further understood with reference to the following detailed examples which serve to illustrate the types of specific prodegradants and their amounts as used in typical vinyl acetate polymer resin formulations and the compostabilities displayed by the prodegradant of this invention. These examples are considered to be exemplary of this invention and should not be considered as limiting, especially in view of applicant's broad disclosure of the principles of this invention.

[0027] The compostability of the PVAc compositions of the examples was determined by following ASTM D 5526-94 (reapproved 2002), Standard Test Method for Determining Anaerobic Biodegradation of Plastic Materials Under Accelerated Landfill Conditions. Using the standard test, a mixture was prepared comprising

60% by weight of sterilized dehydrated manure (to simulate processed household waste), at different percentages of distilled water (35% or 60%), and 10% fermenting inoculum from an active composter. Film samples of the compostable PVAc polymers were run in the Examples which follow. All experiments were run at 97°F in a dark incubator.

Example 1

[0028] 1.5 grams of PovalTM (Kuraray) LM-20, a partially hydrolyzed polyvinyl acetate, having a number average molecular weight (Mn) of about 20,000 were dissolved in 50 grams of ethanol. The solution was coated on release liner to form a two-mil film when dry. Two grams of the dried film were placed in 50 grams of landfill composition per ASTM D 5526 containing 35% water; two grams were also placed in 50 grams of landfill composition having 60% water content. After ninety days at 35% moisture, the film was intact with a weight gain of about 6%. After ninety days at 60% moisture, the film appeared softened, and had gained about 10% in weight. There was no evidence of microbial growth. The cast film was clear and accepted pencil and ballpoint. It adhered strongly to 3M #142 pressure-sensitive tape.

Example 2

[0029] Example 1 was repeated, except each sample contained 0.05 gram of Kenrich LICA 38J, identified above, added while the polymer was in ethanol solution, and five samples were run of each variation of moisture levels. After 30 days' landfill exposure, at both moisture levels of 35% or 60% water, the polymer of all samples with the microlandfills, vanished into the landfill.

Example 3

Example 2 was repeated with a 1:1 blend of ethylene vinyl acetate (ELVAXTM 40 EVA) and a partially hydrolyzed polyvinyl acetate (Polval LM-20 PVAc). Both moisture level samples vanished in 30 days. The cast film was clear and accepted pencil and ballpoint ink without difficulty. 3M #142 transparent tape had strong adhesion to the film. A sample exposed to UV-A light at 40°C for 30 days showed no visible discoloration. The sample burned readily when ignited with a match, and did not self-extinguish.

Example 4

[0030] Example 1 was repeated with UCAR VYHHTM (Dow) PVC/VAC, which is a copolymer of polyvinyl chloride and vinyl acetate at 14% vinyl acetate, with a number average molecular weight (Mn) of about 10,000. Two films were cast from methylisobutylketone with two parts per hundred of dibutyltin dilaurate (DBTDL) heat stabilizer added. This Example demonstrates that when the vinyl copolymer of vinyl acetate with vinyl chloride is employed, stabilizer is added. The samples were translucent, accepted pencil and ballpoint ink, and had strong adhesion to 3M #142 tape. The samples showed no measurable weight loss after 90 days' exposure, either at a 35% or 60% moisture level, nor evidence of surface mold growth.

Example 5

[0031] Example 4 was run with the addition of 2 phr of LICA 38J at 35% water, weight loss after 30 and 60 days was 65% and 96%, respectively. At 60% water, weight loss after 30, 60, and 90 days was 12%, 20%, and 27%, respectively. This Example demonstrated, at various moisture levels, landfill compostability of the composition. This Example 5 may be compared to Example 13 in Patent Appln. No. CA 2,575,674, for the purpose of demonstrating unplasticized PVC/VAC polymer compositions. The VYHH PVC copolymer with 14% vinyl acetate was employed in that Example 13. As reported in that Example 13, the VYHH PVC/VAC copolymer with vinyl acetate does not itself decompose into the landfill, nor does this occur with 2-5 phr of K-38, which is the titanate component of the adduct. However, samples containing the prodegradant system of 5, 1, and 0.5 phr K38J adduct and 2 phr DBTL organotin depolymerization or compostability was observed upon performing the ASTM D 5526 conditions. Accordingly, when using the prodegradant system of K38J and organotin, after 60 days at 35°C in the dark, no visual traces of the PVC/VAC copolymer were observed. These Examples 5 (in this application) and Example 13 of the Patent Appln. No. CA 2,575,674, demonstrate that unplasticized halogenated copolymers with vinyl acetate will effectively decompose with the prodegradant of this invention.

Example 6

-15-

[0032] Example 5 was run using the 1:1 of UCAR VYHH PVC/VAC and Poval LM-20 PVAc, identified as above. At both moisture levels of 65% and 96%, the polymer had vanished into the landfill in 30 days. The 2 ml cast film was transparent, readily accepted pencil and ballpoint marking, and adhered strongly to 3MTM #142 tape. The sample exposed to UV-A radiation at 40°C for 30 days (Q-panel) showed no discoloration. The sample, when ignited with a match, self-extinguished.

Example 7

[0033] Example 5 was run using a blend of UCAR VYHH PVC/VAC and ELVAX-40, previously identified, at both 35 and 60 percent moisture levels, weight loss after 30 days was 45-50%, and 100% after sixty days. Accordingly, these Examples further illustrate the compostability of vinyl acetate copolymers according to the principles of this invention.

[0034] Having described this invention in its various embodiments and parameters, other variations will become apparent to a person of ordinary skill in the art without deviating from the scope of the described embodiments and the invention.

CLAIMS:

1. A compostable vinyl acetate polymer composition comprising
a vinyl acetate polymer and
a monomeric adduct of an organotitanate or organozirconate as a prodegradant
in relative amounts to render the vinyl acetate polymer composition compostable, and
wherein said adduct is defined by the formula
organotitanate or zirconate -P=O(OH) salt-forming group-R-C=C-activating group,
where R is a hydrocarbon radical or substituted hydrocarbon radical and the activating
group is conjugated with the C=C.
2. The composition of claim 1 wherein the monomeric adduct is an amide adduct or
an ester adduct.
3. The composition of claim 1 wherein the prodegradant is contained in an amount
of from about 1 to about 10 phr of polymer.
4. The composition of claim 1 wherein said adduct is an organopyrophosphato
adduct of a monomer selected from the group consisting of methacrylamide, substituted
methacrylamide, methacrylate and substituted methacrylate.
5. The composition of claim 1 wherein said organotitanate or organozirconate is an
amide or ester adduct of neoalkoxy modified monoalkoxy titanate or zirconate.
6. The composition of claim 1 wherein the monomeric adduct is selected from the
group consisting of titanium IV neoalkanolato tri(dioctyl) pyrophosphato-O (adduct)
N-substituted methacrylamide, titanium IV bis(dioctyl) pyrophosphato-O (adduct)
N,N-dimethylamino-alkyl propenamide, zirconium IV neoalkanolato tri(dioctyl)
pyrophosphate-O (adduct) N-substituted methacrylamide and zirconium IV bis(dioctyl)
pyrophosphato-O (adduct) N,N-dimethylamino-alkyl propenamide.
7. The composition of claim 1 wherein the vinyl acetate polymer is selected from the
group consisting of polyvinyl acetate, partially hydrolyzed polyvinyl acetate, poly(vinyl
acetate-vinyl chloride) and poly(ethylene-vinyl acetate).

-17-

8. The composition of claim 1 wherein the monomeric adduct is an adduct of a monomer selected from the group consisting of
- ethyl dimethylaminoethylmethacrylate,
 - methyl dimethylaminopropyl acrylate,
 - 2-morpholine-N-ethyl acrylamide,
 - 2-piperidiny-N-ethyl acrylonitrile,
 - 2-dimethylaminoethyl acrolein,
 - dimethylaminoethyl vinyl ether,
 - dimethylaminoethyl vinyl thioether,
 - 4-dimethylaminomethyl styrene,
 - allyl 3-dimethylamino propionate,
 - methallyl 3-dimethylamino propionate,
 - thioallyl 3-dimethylamino propionate,
 - dimethylaminomethyl acrylate, and
 - dimethylaminomethyl amide.
9. A compostable polyvinyl acetate (PVAc) polymer composition comprising polyvinyl acetate or a copolymer thereof and
- a monomeric adduct as a prodegradant selected from the group consisting of titanium IV neoalkanolato tri(dioctyl) pyrophosphato-O (adduct) N-substituted methacrylamide, zirconium IV neoalkanolato tri(dioctyl) pyrophosphato-O (adduct) N-substituted methacrylamide, titanium IV bis(dioctyl) pyrophosphato-O (adduct) N,N-dimethylamino-alkyl propenamide, and zirconium IV bis(dioctyl) pyrophosphato-O (adduct) N,N-dimethylamino-alkyl propenamide, said prodegradant in relative amounts to render the PVAc polymer composition compostable.
10. A compostable vinyl acetate polymer article comprising
- an article containing a vinyl acetate polymer and
 - a monomeric adduct of an organotitanate or organozirconate as a prodegradant in relative amounts to render the vinyl acetate polymer article compostable, and wherein said adduct is defined by the formula
- organotitanate or zirconate -P=O(OH) salt-forming group-R-C=C-activating group,
- where R is a hydrocarbon radical or substituted hydrocarbon radical and the activating group is conjugated with the C=C.

-18-

11. The compostable article of claim 10 wherein the monomeric adduct is selected from the group consisting of titanium IV neoalkanolato tri(dioctyl) pyrophosphato-O (adduct) N-substituted methacrylamide, titanium IV bis(dioctyl) pyrophosphato-O (adduct) N,N-dimethylamino-alkyl propenamide, zirconium IV neoalkanolato tri(dioctyl) pyrophosphate-O (adduct) N-substituted methacrylamide, and zirconium IV bis(dioctyl) pyrophosphato-O (adduct) N,N-dimethylamino-alkyl propenamide.
12. The compostable article of claim 10 wherein the vinyl acetate polymer is polyvinyl acetate or a copolymer thereof.
13. A composite comprising the article of claim 10 and a compostable woven or nonwoven fabric.
14. The compostable article of claim 10 wherein the monomeric adduct is a prodegradant of a monomer selected from the group consisting of
 - ethyl dimethylaminoethylmethacrylate,
 - methyl dimethylaminopropyl acrylate,
 - 2-morpholine-N-ethyl acrylamide,
 - 2-piperidiny-N-ethyl acrylonitrile,
 - 2-dimethylaminoethyl acrolein,
 - dimethylaminoethyl vinyl ether,
 - dimethylaminoethyl vinyl thioether,
 - 4-dimethylaminomethyl styrene,
 - allyl 3-dimethylamino propionate,
 - methallyl 3-dimethylamino propionate,
 - thioallyl 3-dimethylamino propionate,
 - dimethylaminomethyl acrylate, and
 - dimethylaminomethyl amide.

-19-

15. A compostable polyvinyl acetate (PVAc) article comprising
an article containing a polyvinyl acetate or a copolymer thereof and
a monomeric adduct as a prodegradant selected from the group consisting of
titanium IV neoalkanolato tri(dioctyl) pyrophosphato-O (adduct) N-substituted
methacrylamide, zirconium IV neoalkanolato tri(dioctyl) pyrophosphato-O (adduct) N-
substituted methacrylamide, titanium IV bis(dioctyl) pyrophosphato-O (adduct) N,N-
dimethylamino-alkyl propenamide, and zirconium IV bis(dioctyl) pyrophosphato-O
(adduct) N,N-dimethylamino-alkyl propenamide, said prodegradant in relative amounts
to render the polyvinyl acetate or copolymer compostable.
16. A composite article comprising a sheet of the compostable polyvinyl acetate article
of claim 15 and a compostable woven or nonwoven fabric.
17. The composite article of claim 16 wherein said woven or nonwoven fabric is a
compostable fabric of a polymer selected from the group consisting of polyvinyl alcohol,
polyacrylamide, polyacrylate, polymethacrylate and polyester.
18. A method of anaerobic biodegradation of a vinyl acetate polymer article in a landfill
comprising
introducing a vinyl acetate polymer article or a physically reduced form thereof into
a landfill for anaerobic degradation, said article having a composition of
a vinyl acetate polymer and
a monomeric adduct of an organotitanate or organozirconate as a prodegradant
in relative amounts to render the vinyl acetate polymer article compostable, and wherein
said adduct is defined by the formula
organotitanate or zirconate -P=O(OH) salt-forming group-R-C=C-activating group,
where R is a hydrocarbon radical or substituted hydrocarbon radical and the activating
group is conjugated with the C=C and
anaerobically biodegrading said article in the landfill.
19. The method of claim 18 wherein said adduct is an organopyrophosphato adduct
of a monomer selected from the group consisting of methacrylamide, substituted
methacrylamide, methacrylate and substituted methacrylate.

-20-

20. The method of claim 18 wherein said vinyl acetate (PVAc) polymer article comprises

polyvinyl acetate or a copolymer thereof and

a monomeric adduct as a prodegradant selected from the group consisting of titanium IV neoalkanolato tri(dioctyl) pyrophosphato-O (adduct) N-substituted methacrylamide, zirconium IV neoalkanolato tri(dioctyl) pyrophosphato-O (adduct) N-substituted methacrylamide, titanium IV bis(dioctyl) pyrophosphato-O (adduct) N,N-dimethylamino-alkyl propenamide, and zirconium IV bis(dioctyl) pyrophosphato-O (adduct) N,N-dimethylamino-alkyl propenamide, said prodegradant in relative amounts to render the vinyl acetate polymer article compostable.

21. The method of claim 18 wherein the monomeric adduct is an adduct of a monomer selected from the group consisting of

ethyl dimethylaminoethylmethacrylate,
methyl dimethylaminopropyl acrylate,
2-morpholine-N-ethyl acrylamide,
2-piperidiny-N-ethyl acrylonitrile,
2-dimethylaminoethyl acrolein,
dimethylaminoethyl vinyl ether,
dimethylaminoethyl vinyl thioether,
4-dimethylaminomethyl styrene,
allyl 3-dimethylamino propionate,
methallyl 3-dimethylamino propionate,
thioallyl 3-dimethylamino propionate,
dimethylaminomethyl acrylate, and
dimethylaminomethyl amide.