


(12) PATENT ABRIDGMENT (11) Document No. AU-B-44691/89
(19) AUSTRALIAN PATENT OFFICE (10) Acceptance No. 622237

- (54) Title
AZO DYE SOLUTIONS
- International Patent Classification(s)
(51)⁵ **C09B 069/04 C09B 067/26**
- (21) Application No. : **44691/89** (22) Application Date : **14.11.89**
- (30) Priority Data
- (31) Number (32) Date (33) Country
4223/88 15.11.88 CH SWITZERLAND
- (43) Publication Date : **24.05.90**
- (44) Publication Date of Accepted Application : **02.04.92**
- (71) Applicant(s)
CIBA-GEIGY AG
- (72) Inventor(s)
HANS MORAWIETZ
- (74) Attorney or Agent
SPRUSON & FERGUSON , GPO Box 3898, SYDNEY NSW 2001
- (56) Prior Art Documents
US 2692263
US 3862116
US 1333023
- (57) Claim

1. A concentrated aqueous dye solution containing

a) 7 to 30 % by weight of a dye of the formula



where K is a coupling component of the acetoacetanilide, pyridone, pyrazolone or pyrimidine series,

b) 1 to 5 moles of 3-diethylamino-1-propylamine, 2-diethylaminoethanol or 2-(2-aminoethoxy)ethanol per mole of dye of the formula (1) and


c) further, optional additives.

3. A concentrated aqueous dye solution according to either of claims 1 and 2, containing a dye of the formula (1) where

K is a coupling component of the formula


(11) AU-B-44691/89
(10) 622237

-2-



where Y^1 and Y^2 are each independently of the other =O, =NH or =N-C₁-C₄alkyl,
 Y^3 is =O, =S, =NR or =N-CN, where R is hydrogen or C₁-C₄alkyl and
 R^1 and R^2 are each independently of the other hydrogen, substituted or unsubstituted alkyl
or substituted or unsubstituted phenyl.

15. A process for preparing a concentrated aqueous dye solution,
which comprises stirring a dye of the formula



where K is a coupling component of the acetoacetanilide, pyridone, pyrazolone
or pyrimidine series, with a mixture of water, 3-diethylamino-1-propylamine, 2-
diethylaminoethanol or 2-(2-aminoethoxy)ethanol in the presence or absence of
an organic solubilizer until a homogeneous solution has formed.

622237

S & F Ref: 110779

FORM 10

COMMONWEALTH OF AUSTRALIA

PATENTS ACT 1952

COMPLETE SPECIFICATION

(ORIGINAL)

FOR OFFICE USE:

Class Int Class

Complete Specification Lodged:
Accepted:
Published:

Priority:

Related Art:

Name and Address
of Applicant:

Ciba-Geigy AG
Klybeckstrasse 141
4002 Basle
SWITZERLAND

Address for Service: Spruson & Ferguson, Patent Attorneys
Level 33 St Martins Tower, 31 Market Street
Sydney, New South Wales, 2000, Australia

Complete Specification for the invention entitled:

Azo
~~Concentrated~~ Dye Solutions

The following statement is a full description of this invention, including the best method of performing it known to me/us



5845/3

1-17300/=

Azo
Concentrated dye solutions

Abstract

Concentrated dye solutions of dyes of the formula (1) shown in claim 1 are described.


The dye solutions are notable for a long shelf life and are suitable in particular for dyeing paper.



Azo dye solutions

According to a first embodiment of this invention there is provided a concentrated aqueous dye solution containing

- a) 7 to 30% by weight of a dye of the formula




5

where K is a coupling component of the acetoacetanilide, pyridone, pyrazolone or pyrimidine series,

- b) 1 to 5 moles of 3-diethylamino-1-propylamine, 2-diethylaminoethanol or 2-(2-aminoethoxy)ethanol per mole of dye of the formula (1) and

- 10 c) further, optional additives.

According to a second embodiment of this invention there is provided a process for preparing a concentrated aqueous dye solution, which comprises stirring a dye of the formula



- 15 where K is a coupling component of the acetoacetanilide, pyridone, pyrazolone or pyrimidine series, with a mixture of water, 3-diethylamino-1-propylamine, 2-diethylaminoethanol or 2-(2-aminoethoxy)ethanol in the presence or absence of an organic solubilizer until a homogeneous solution has formed.

- 20 According to a third embodiment of this invention there is provided a method for dyeing textile material made of cellulose, comprising applying to said textile material a dye solution according to the first embodiment.




- 1B -

Preferably, the dye solutions according to the invention contain 10 to 25% by weight of a dye of the formula (I).

In the above formula (1) K is a coupling component of the acetoacetanilide, pyridone, pyrazolone or pyrimidine series. The possibilities 5 listed cover in particular the coupling components customary for azo dyes, in particular dyes for paper.

Preferably, K is a coupling component of the formula





(2)

where Y¹ and Y² are each independently of the other =O, =NH or =N-C₁-C₄alkyl, Y³ is =O, =S, =NR or =N-CN, where R is hydrogen or C₁-C₄alkyl and R¹ and R² are each independently of the other hydrogen, substituted or unsubstituted alkyl or substituted or unsubstituted phenyl.

The above formula (2), although showing only one of the possible tautomeric forms of coupling component, shall be taken to encompass all the tautomeric forms as well.

Substituted or unsubstituted alkyl R¹ or R² is for example methyl, ethyl, n-propyl, isopropyl, n-butyl, sec-butyl, tert-butyl, straight-chain or branched pentyl or hexyl, or cyclohexyl, which may each be monosubstituted or polysubstituted, for example by -OH, C₁-C₄alkoxy or C₁-C₄hydroxyalkoxy.

Examples of suitable substituted alkyl are: methoxymethyl, ethoxymethyl, ethoxyethyl, ethoxypropyl, n-propoxymethyl, isopropoxymethyl, butoxymethyl, butoxyethyl, butoxypropyl, ethoxypropyl, methoxybutyl, ethoxypentyl and 2-hydroxyethoxypentyl.

Substituted or unsubstituted phenyl R¹ or R² can be for example phenyl itself or phenyl which is monosubstituted or polysubstituted by identical or different radicals.

Examples of such radicals are: C₁-C₄alkyl, (which in this application means generally methyl, ethyl, n-propyl, isopropyl, n-butyl, sec-butyl or tert-butyl), C₁-C₄alkoxy (which in this application means generally methoxy, ethoxy, n-propoxy, isopropoxy, n-butoxy, sec-butoxy or tert-butoxy), halogen such as fluorine, chlorine or bromine, and nitro.

Preferably, phenyl R¹ and/or R² is unsubstituted phenyl or C₁-C₄alkyl-, chlorine- or methoxy-monosubstituted, -disubstituted or -trisubstituted phenyl, in particular unsubstituted phenyl.

R¹ and R² are each preferably hydrogen or C₁-C₄alkyl, particularly preferably hydrogen or

methyl.

Y^1 and/or Y^2 are each preferably a functional group =O or =NH, and are preferably identical to each other. Y^1 and Y^2 are particularly preferably identical, each being =NH.

Y^3 is preferably =O, =S, =NH or =N-CN, in particular =NH.

In a particularly preferred embodiment, the dye solutions according to the invention contain azo dyes of the formula (1) where R^1 and R^2 are each independently of the other hydrogen or C_1 - C_4 alkyl, Y^1 and Y^2 are each independently of the other =O or =NH, and Y^3 is =O, =S, =NH or =N-CN.

The dyes of the formula (1) are known or are obtained in a known manner.

The aqueous dye solutions according to the invention contain at least one mole of an amine selected from the group consisting of 3-diethylamino-1-propylamine, 2-diethylaminoethanol and 2-(2-aminoethoxy)ethanol per mole of dye of the formula (1).

Preferably, the dye solutions contain 1 to 4 moles of amine per mole of dye. Of the amines mentioned, 3-diethylamino-1-propylamine is particularly preferred.

In addition, the dye solutions according to the invention may contain water-soluble organic solubilizers. Possibilities are for example: urea, formamide, ϵ -caprolactam, dimethylformamide, 1,2-diaminopropane, polyhydric alcohols, e.g. ethylene glycol, propylene glycol or glycerol, and alkanolamines, e.g. ethanolamine, diethanolamine, triethanolamine, 2-dimethylaminoethanol, 2-methylaminoethanol, N,N-bis(2-hydroxyethyl)-1,3-diaminopropane or N-(2-hydroxyethyl)ethylenediamine.

The amount of organic solubilizer depends inter alia on the amount of the three abovementioned amines, 3-diethylamino-1-propylamine, 2-diethylaminoethanol or 2-(2-aminoethoxy)ethanol, in the dye solution. If about 2 to 4 moles of the amines mentioned are present per mole of dye, generally no organic solubilizer or only about 5 to 10 % by weight thereof, based on the total weight of the dye solution, is required. On the other hand, it is frequently advantageous for economic reasons to adjust the amines mentioned to about 1 to 2.5 moles per mole of dye and to use in addition about 10 to 25 % by weight of organic solubilizer.

Preferred aqueous dye solutions according to the invention contain

- a) 10 to 30 % by weight of a dye of the formula (1),
- b) 1 to 4 moles of 3-diethylamino-1-propylamine, 2-diethylaminoethanol or 2-(2-aminoethoxy)ethanol per mole of dye of the formula (1), and
- c) 0 to 25 % by weight of an organic solubilizer.

Of these, particular preference is given to those which contain

- a) 10 to 30 % by weight of a dye of the formula (1),
- b) 1 to 2.5 moles of 3-diethylamino-1-propylamine, 2-diethylaminoethanol or 2-(2-aminoethoxy)ethanol per mole of dye of the formula (1) and
- c) 10 to 25 % by weight of an organic solubilizer.


The concentrated aqueous dye solutions according to the invention are in general prepared by stirring the free dye acids with a mixture of water, 3-diethylamino-1-propylamine, 2-diethylaminoethanol or 2-(2-aminoethoxy)ethanol in the presence or absence of an organic solubilizer until a homogeneous solution has formed. If necessary, the mixture can be heated, for example to 40-80°C, and possibly filtered.

The concentrated aqueous dye solutions obtained are notable in particular for a long shelf life.

The concentrated dye solutions according to the invention are used as they are or after dilution with water, particularly for dyeing and printing paper, including paperboard and cardboard, the dyeing of these materials being effected for example in the mass, by coating or by dipping. Moreover, such a liquid formulation may also be used for the continuous or batchwise dyeing of textile materials, in particular cellulose.

The Examples which follow illustrate the invention. Parts are by weight.

Example 1: 920 parts of an aqueous presscake containing 260 parts of the dye of the formula



in the form of the free dye acid are admixed with 296 parts of 3-diethylamino-1-propylamine, and the mixture is adjusted with water to a total weight of 2080 parts. The suspension obtained is heated with stirring to 50°C and is stirred at that temperature until all the dye has dissolved. The dye solution is then clarified.

The result obtained is a commercial liquid dye which even after storage at 3-5°C for one month does not show any residue whatsoever.

Example 2: 920 parts of the same aqueous presscake as in Example 1 are admixed with 296 parts of 3-diethylamino-1-propylamine and 291 parts of urea, and the mixture is adjusted with water to a total weight of 2080 parts and otherwise further processed into a commercial liquid formulation as described in Example 1.

The commercial formulation does not show any solid residues whatsoever even after storage at 3-5°C for one month.

Example 3: 920 parts of the same aqueous presscake as in Example 1 are admixed with 148 parts of 3-diethylamino-1-propylamine, 60 parts of diethanolamine, 43 parts of 2-methylaminoethanol and 291 parts of urea, and the mixture is adjusted with water to a total weight of 2080 parts and otherwise further processed into a commercial liquid formulation as described in Example 1.

This commercial formulation does not show any solid residues whatsoever even after storage at 3-5°C for one month.

Example 4: 920 parts of the same aqueous presscake as in Example 1 are admixed with 148 parts of 3-diethylamino-1-propylamine, 60 parts of diethanolamine and 43 parts of 2-methylaminoethanol, and the mixture is adjusted with water to a total weight of 2080 parts and otherwise further processed into a commercial liquid formulation as described in Example 1.

This commercial formulation does not show any solid residues whatsoever even after storage at 3-5°C for one month.

Examples 5-9: Example 3 is repeated, except that the dye used therein is replaced by equivalent amounts of the dyes obtained by diazotization of dehydrothiotoluidine-7-sulfonic acid and coupling to the coupling components listed in the table below.

This method produces concentrated solutions of the dyes, which are notable for a long shelf life.

Example	Coupling component
5	Barbituric acid
6	Cyanoimino ^{2-Cyanoamino-4,6-dihydroxypyrimidine} barbituric acid
7	3-Methyl-5-pyrazolone
8	1,3-Dimethylbarbituric acid
9	4-Amino-2,6-dihydroxypyrimidine

Example 10: Example 1 is repeated, except that the 296 parts of 3-diethylamino-1-propylamine are replaced by the same amount of 2-diethylaminoethanol. A commercial stable liquid dye is obtained.

Example 11: Example 1 is repeated, except that the 296 parts of 3-diethylamino-1-propylamine are replaced by the same amount of 2-(2-aminoethoxy)ethanol. A stable commercial liquid dye is obtained.


Example 12: In a hollander, 70 parts of chemically bleached sulfite cellulose from softwood and 30 parts of chemically bleached sulfite cellulose from birchwood are beaten in 2000 parts of water. 0.3 part of the commercial dye formulation described in Example 3 is added. After 20 minutes of mixing, the stock is used for papermaking. The absorbent paper obtained in this manner has a yellow colour. The waste water is virtually colourless.



~~WHAT IS CLAIMED IS:~~

1. A concentrated aqueous dye solution containing

a) 7 to 30 % by weight of a dye of the formula



where K is a coupling component of the acetoacetanilide, pyridone, pyrazolone or pyrimidine series,

b) 1 to 5 moles of 3-diethylamino-1-propylamine, 2-diethylaminoethanol or 2-(2-aminoethoxy)ethanol per mole of dye of the formula (1) and

c) further, optional additives.

2. A concentrated aqueous dye solution according to claim 1, containing 10 to 25 % by weight of a dye of the formula (1).

3. A concentrated aqueous dye solution according to either of claims 1 and 2, containing a dye of the formula (1) where

K is a coupling component of the formula



where Y^1 and Y^2 are each independently of the other =O, =NH or =N-C₁-C₄alkyl,

Y^3 is =O, =S, =NR or =N-CN, where R is hydrogen or C₁-C₄alkyl and

R^1 and R^2 are each independently of the other hydrogen, substituted or unsubstituted alkyl

or substituted or unsubstituted phenyl.

4. A concentrated aqueous dye solution according to any one of claims 1 to 3, wherein R^1 and R^2 are each independently of the other hydrogen or C_1 - C_4 alkyl.

5 5. A concentrated aqueous dye solution according to any one of claims 1 to 4, wherein Y^1 and Y^2 are each independently of the other =O or =NH.

6. A concentrated aqueous dye solution according to any one of claims 1 to 5, wherein Y^3 is =O, =S, =NH or =N-CN.

10 7. A concentrated aqueous dye solution according to claim 6, wherein Y^3 is =NH.

8. A concentrated aqueous dye solution according to any one of claims 1 to 6, wherein R^1 and R^2 are each independently of the other hydrogen or C_1 - C_4 alkyl, Y^1 and Y^2 are each independently of the other =O or =NH and
15 Y^3 is =O, =S, =NH or =N-CN.

9. A concentrated aqueous dye solution according to any one of claims 1 to 8, containing 1 to 4 moles of 3-diethylamino-1-propylamine, 2-diethylaminoethanol or 2-(2-aminoethoxy)ethanol per mole of dye.

10. A concentrated aqueous dye solution according to any one of
20 claims 1 to 9, containing 3-diethylamino-1-propylamine.

11. A concentrated aqueous dye solution according to any one of claims 1 to 10, containing in addition an organic solubilizer.

12. A concentrated aqueous dye solution according to any one of claims 1 to 11, containing urea, ϵ -caprolactam, a polyhydric alcohol or an
25 alkanolamine as organic solubilizer.

13. A concentrated aqueous dye solution according to any one of claims 1 to 12, containing


- a) 10 to 30% by weight of a dye of the formula (1),
- b) 1 to 4 moles of 3-diethylamino-1-propylamine, 2-diethylaminoethanol or
30 2-(2-aminoethoxy)ethanol per mole of dye of the formula (1), and
- c) 0 to 25% by weight of an organic solubilizer.

14. A concentrated dye solution according to claim 13, containing

- a) 10 to 30% by weight of a dye of the formula (1),
- b) 1 to 2.5 moles of 3-diethylamino-1-propylamine, 2-diethylaminoethanol
35 or 2-(2-aminoethoxy)ethanol per mole of dye of the formula (1) and
- c) 10 to 25% by weight of an organic solubilizer.

15. A process for preparing a concentrated aqueous dye solution, which comprises stirring a dye of the formula





where K is a coupling component of the acetoacetanilide, pyridone, pyrazolone or pyrimidine series, with a mixture of water, 3-diethylamino-1-propylamine, 2-diethylaminoethanol or 2-(2-aminoethoxy)ethanol in the presence or absence of
5 an organic solubilizer until a homogeneous solution has formed.

16. A method for dyeing textile material made of cellulose, comprising applying to said textile material a dye solution according to any one of claims 1 to 13.

17. The method for dyeing textile material according to claim 16
10 wherein said textile material is paper.

18. A concentrated aqueous dye solution substantially as herein described with reference to any one of the Examples.

19. A process for preparing a concentrated aqueous dye solution which process is substantially as herein described with reference to any one of
15 the Examples.

20. A method for dyeing textile material made of cellulose, comprising applying to said textile material a dye solution according to claim 18.

DATED this NINTH day of JANUARY 1992

Ciba-Geigy AG

Patent Attorneys for the Applicant

SPRUSON & FERGUSON

20

