



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2224013 C 2007/09/25

(11)(21) **2 224 013**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(86) Date de dépôt PCT/PCT Filing Date: 1996/05/21

(87) Date publication PCT/PCT Publication Date: 1996/12/19

(45) Date de délivrance/Issue Date: 2007/09/25

(85) Entrée phase nationale/National Entry: 1997/12/08

(86) N° demande PCT/PCT Application No.: US 1996/007287

(87) N° publication PCT/PCT Publication No.: 1996/040306

(30) Priorité/Priority: 1995/06/07 (US08/485,767)

(51) Cl.Int./Int.Cl. *A61L 31/00* (2006.01),
A61B 19/04 (2006.01), *A61L 29/04* (2006.01),
A61L 31/04 (2006.01)

(72) Inventeurs/Inventors:
MEROVITZ, GERALD, US;
TUCK, RANDY, US;
BURNS, JIM, US;
CULP, RUSS, US

(73) Propriétaire/Owner:
ALLEGIANCE CORPORATION, US

(74) Agent: OGILVY RENAULT LLP/S.E.N.C.R.L.,S.R.L.

(54) Titre : GANTS DE CHIRURGIE REALISES A PARTIR DE COPOLYMERES DE NEOPRENE

(54) Title: SURGEON'S GLOVES FROM NEOPRENE COPOLYMERS

(57) Abrégé/Abstract:

Certain neoprene copolymers make it possible to manufacture surgeon's gloves Swanz-Ganz balloons having improved properties.



PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61L 31/00, 29/00	A1	(11) International Publication Number: WO 96/40306 (43) International Publication Date: 19 December 1996 (19.12.96)
(21) International Application Number: PCT/US96/07287 (22) International Filing Date: 21 May 1996 (21.05.96) (30) Priority Data: 08/485,767 7 June 1995 (07.06.95) US (71) Applicant: BAXTER INTERNATIONAL, INC. [US/US]; One Baxter Parkway, Deerfield, IL 60015 (US). (72) Inventors: MEROVITZ, Gerald; 3350 Young Charles Drive, Florence, SC 29501 (US). TUCK, Randy; 115 E. Mechanic Street #3, Eaton, OH 45320 (US). BURNS, Jim; 41 Franklin Drive, Plainsboro, NJ 08536 (US). CULP, Russ; 3617 Oak Ridge Lane, Dothan, AL 36303 (US). (74) Agent: STENZEL, Robert, A.; 1500 Waukegan Road, McGaw Park, IL 60085 (US).		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: SURGEON'S GLOVES FROM NEOPRENE COPOLYMERS (57) Abstract Certain neoprene copolymers make it possible to manufacture surgeon's gloves Swanz-Ganz balloons having improved properties.		

SURGEON'S GLOVES FROM NEOPRENE COPOLYMERS

FIELD OF THE INVENTION

The invention relates to improved surgeon's gloves and compositions used in their manufacture.

BACKGROUND OF THE INVENTION

In some cases, natural rubber medical gloves may produce allergic responses in individuals predisposed to developing an allergic reaction to latex. Some of the medical literature has suggested that allergen response is especially high in rubber glove use in areas of medicine due to continuous exposure by healthcare providers. Resistance to changing from natural latex has always been associated with the uncomfortable, or different feel, of all other synthetic offerings; including neoprene, silicones and other type materials.

Neoprene surgical gloves now on the market generally are unpopular since they feel tight and inflexible on the hands of the user. Surgical users of these products prefer the soft and flexible tactility of a natural rubber glove. The neoprene compound, and process developed by this invention produces a synthetic glove that has a modulus lower than the prior art. The invention produces a neoprene glove of equal or better softness in feel to the common surgeon's glove constructed of natural latex.

ADVANTAGES OF THE INVENTION

The neoprene gloves of the invention are made of synthetic elastomers, yet they possess the look and feel of natural latex gloves. They are basically non-allergenic and are free of proteins. They may be made using existing glove manufacturing techniques and processes. The gloves of the invention are resistant to solvents and ozone. The gloves may be treated with conventional lubricant powders. Alternatively, the gloves may be powder-free while yet maintaining good mold release and donning properties. To achieve

this effect, conventional halogenation procesis may be employed. There physical properties are not materially reduced after being subjected to radiation sterilization.

THE INVENTION

5 The invention comprises soft surgeon's glove or industrial medical gloves which have been constructed from a copolymer latex of neoprene and 2,3-dichloro-1,3- butadiene which copolymer contains between 25-55% and preferably, 35-45% of chlorine. In a most preferred embodiment, the copolymer contains 40% chlorine. The soft surgeon's glove may be further
10 characterized as having a low modulus, a slow crystallization rate, a high wet gel strength and a medium gel content.

The invention also comprises compositions useful in producing the soft surgeon's gloves of the types described above. A general formula used in the preparation of the gloves is set forth below in Table 1.

TABLE 1

<u>INGREDIENTS</u>	<u>PARTS PER HUNDRED OF RUBBER</u>
Neoprene Copolymer Latex	100.00
Plasticizer I Stabilizer	0.25 to 1 0.00
Emulsifier I Stabilizer	0.25 to 10.00
Antiozonant I Plasticizer	0.25 to 10.00
pH Stabilizer Sequesterate	0.10 to 1.50
pH Stabilizer	0.10 to 1.50
Vulcanization Activator	0.25 to 20.00
Crosslinker	0.10 to 3.00
Vulcanization Accelerator	0.25 to 4.00
Antioxidant	0.10 to 3.00
White Pigment*	0.05 to 3.00
Yellow Pigment*	0.05 to 3.00
(Rubber Reoderant)	0.001 to 1.0
Wetting Agent I Emulsifier	0.001 to 1.0
Defoamer	0.001 to 2.0
Rubber Softener	0.0 to 50.0
*Optional Ingredients	

DETAILED DESCRIPTION OF THE INVENTION

The Neoprene Copolymer Latex

As indicated, this copolymer of 2-chloro-1,3-butadiene and 2,3-dichloro, 3-butadiene contains between 30-50%, preferably 35-45% of chlorine and most preferably 40%. The modulus (of elasticity) MPa [psi] of these polymers should not be greater than 0.6 at 100%, preferably the modulus is about 0.4 at 100%. For a more detailed explanation of these values see Table II of the DuPont bulletin, A SELECTION GUIDE FOR NEOPRENE LATEXES, by C. H. Gilbert, 1985 (NL-020.1(R1)). These latexes may have a solids content ranging between 35-60 % by weight. Preferably it is 50%. As indicated, the Copolymers useful in the practice of the invention have a slow crystallization rate, a medium gel content and a high wet gel strength. They are preferably anionic latexes. More information about these polymers is available by referring to the C. H. Gilbert Bulletin and the DuPont Bulletin, NEOPRENE LATEXES-THEIR PREPARATION AND CHARACTERISTICS, by L. L. Harrell Jr., 1981 (ADH 200. 1).

The preferred commercial latex used in the practice of the invention is made available by DuPont under the code number 750. This anionic copolymer latex has a chlorine content of 40% and possesses all of the preferred properties described above. Specific details describing this latex are to be found in the C. H. Gilbert Bulletin.

Glove Thickness

The term, "surgeon's glove," as used herein and in the claims includes related products such as examining gloves, fingers and Swanz-Ganz balloons on catheters for medical uses. It is an important feature of the invention that the gloves are thin gloves having an average thickness in any part of the glove

less than 0.5". Preferably the thickness will not exceed .009". A typical glove produced in accordance with the invention has a cuff thickness of .006" and a finger thickness of .0075".

Processes for Making the Surgeon's Gloves

5 The gloves of the invention are preferably made using known dipping technologies. These processes are in most instances the well known processes e.g. straight dipping and coagulant dipping which latter process is most often comprises the Anode process or the Teague process. While either of these coagulation processes may be used in the practice of
10 this invention the Anode process is most preferred. Descriptions of these processes are described in the publication, NATURAL RUBBER DIPPING TECHNOLOGIES, by R. D. Culp and B. L. Pugh, symposium on Latex as a Barrier Material April 6 and 7 1989, University of Maryland. Another paper describing neoprene latex dipping is: NEOPRENE LATEX AND ITS
15 APPLICATIONS WITH EMPHASIS ON THE MANUFACTURE OF DIPPED GOODS, by O. H. Gilbert and H. E. Berkheimer. ACS spring Meeting, Rubber Division, Montreal, Quebec, May 27, 1987.

 Yet another reference describing the dipping of neoprene latexes is the publication, NEOPRENE LATEXES AND THEIR APPLICATIONS,
20 F. L. McMillan, ACS, Rubber Division, Toronto, Ontario, Canada, May 21-24, 1991. This Paper provides a good description of the various ingredients used in the formulation of neoprene latexes and their functions. This paper further provides a description of the Anode dipping process in the following language: "In the Anode process a form is dipped into a coagulant,
25 withdrawn, and rotated to allow uniform deposit of coagulant. After allowing it to dry partially, during which time the coagulant film becomes more viscous, the form is slowly and steadily dipped into the latex compound and held there for

- sufficient time to allow the film to build up to the desired thickness. It is then withdrawn at a steady rate - slowly enough to minimize flow of the outer layer of wet compound on the form." "As in straight dipping, rotation of the form after withdrawal helps to smooth out the film. The compound
- 5 dip is often followed by another coagulant dip to set the wet film. Since the rate of buildup is very rapid at first but then decreases rapidly with dwell time and since the entire process can be repeated many times, it is often less expensive and faster to use multiple dips when producing heavy films."

EXAMPLES

- 10 Using an anode dipping process of the type described and a formula of the type shown in Table 1, surgeon's gloves were made and tested against commercial neoprene gloves. The results of these tests are set forth in Tables 2 and 3.

TABLE 2
SURGICAL GLOVES ORIGINAL

	500% MOD	ELONG	TENSILE	CUFF GAUGE	PALM GAUGE	FINGER GAUGE	WEIGHT	COLOR
COMMERCIAL GLOVE	417 psi	830%	3365 psi	0085	0077	0078	5 grams	GOLD
GLOVE* OF INVENTION	255 psi	1100	2595 psi	0060	0085	0072	13 grams	YELLOW

ASTM STANDARDS

TYPE I (NATURAL)

TYPE II (SYNTHETIC)

500% MODULUS

800 PSI MAX

1020 PSI MAX

ELONGATION

750 % MIN

650% MIN

TENSILE

3500 PSI MIN

2470 PSI MIN

* NOTE: GLOVES OF THE INVENTION WERE NOT STERILIZED

TABLE 3
SURGICAL GLOVES
AFTER ACCELERATED
AGING 158°F - 7 DAYS

	500% MOD	ELONG	TENSILE	CUFF GAUGE	PALM GAUGE	FINGER GAUGE	WEIGHT	COLOR
COMMERCIAL GLOVE	597 psi	787%	2890 psi	0085	0077	0078	15 grams	GOLD
GLOVE* OF INVENTION	255 psi	933%	3834 psi	0060	0085	0072	13 grams	YELLOW

ASTM STANDARDS	TYPE 1 (NATURAL)	TYPE 11 (SYNTHETIC)
500% MODULUS	NONE	NONE
ELONGATION	560 % MIN	490% MIN
TENSILE	2610 PSI MIN	1740 PSI MIN

* NOTE: GLOVES OF THE INVENTION WERE NOT STERILIZED

To illustrate the fact that radiation sterilization does not materially diminish the physical properties of the gloves of the invention. Table 4 is set forth below.

TABLE 4
PHYSICAL PROPERTIES
BEFORE STERILIZATION

TEST NO.	TEST AVERAGE OF NO. OF TESTS	PSI TINSLE	PSI MODULUS (STRESS)	% ELONGATION	7-DAY PSI TINSLE	% ELONGATION
1.	3	3,000	200	1,100	4,000	1,000
2.	3	3,125	200	1,100+	-	-
AFTER CONVENTIONAL STERILIZATION BY RADIATION						
3.	5	3,500	225	1,080	3,600	880
4.	5	2,600	200	1,100	2,825	850
5.	5	2,550	250	1,090	2,900	820
6.	5	2,700	200	1,090	2,925	850
7.	5	3,500	200	1,090	3,900	850
8.	5	3,650	200	1,090	3,600	900

Using a similar formula, Swanz-Ganz balloons were prepared. These balloons successfully passed standard pressure tests.

The foregoing descriptions of specific embodiments of the present invention have been presented for purposes of illustration and description.

- 5 They are not intended to be exhaustive or to limit the invention to the precise forms disclosed, and obviously many modifications and variations are possible in light of the above teaching. The embodiments were chosen and described in order to best explain the principles of the invention and its practical application, to thereby enable others skilled in the art to best utilize the
- 10 invention and various embodiments with various modifications as are suited to the particular use contemplated. It is intended that the scope of the invention be defined by the Claims appended hereto and their equivalents.

CLAIMS:

1. A composition for use in producing surgeon's gloves comprising:
 - 100 parts copolymer latex of neoprene and 2,3-dichloro-1,3-butadiene latex wherein the copolymer comprises from about 25% to about 55% chlorine by weight;
 - from 0.25 to 10.00 parts plasticizer / stabilizer;
 - from 0.25 to 10.00 parts emulsifier / stabilizer;
 - from 0.25 to 10.00 parts antiozonant / plasticizer;
 - from 0.10 to 1.50 parts pH stabilizer sequestrant;
 - from 0.10 to 1.50 parts pH stabilizer;
 - from 0.25 to 20.00 parts vulcanization activator;
 - from 0.10 to 3.00 parts crosslinker;
 - from 0.25 to 4.00 parts vulcanization accelerator;
 - from 0.10 to 3.00 parts antioxidant;
 - from 0.001 to 1.00 parts rubber reodourant;
 - from 0.001 to 1.00 parts wetting agent / emulsifier;
 - from 0.001 to 2.00 parts defoamer; and
 - from 0.00 to 50.0 parts rubber softener.
2. The composition of claim 1 wherein the copolymer comprises from about 35% to about 45% chlorine by weight.
3. The composition of claim 1 wherein the copolymer comprises 40% chlorine by weight.
4. A surgeon's glove comprising:

100 parts copolymer latex of neoprene and 2,3-dichloro-1,3-butadiene latex wherein the copolymer comprises from about 25% to about 55% chlorine by weight;

from 0.25 to 10.00 parts plasticizer / stabilizer;

from 0.25 to 10.00 parts emulsifier / stabilizer;

from 0.25 to 10.00 parts antiozonant / plasticizer;

from 0.10 to 1.50 parts pH stabilizer sequestrant;

from 0.10 to 1.50 parts pH stabilizer;

from 0.25 to 20.00 parts vulcanization activator;

from 0.10 to 3.00 parts crosslinker;

from 0.25 to 4.00 parts vulcanization accelerator;

from 0.10 to 3.00 parts antioxidant;

from 0.001 to 1.00 parts rubber reodourant;

from 0.001 to 1.00 parts wetting agent / emulsifier;

from 0.001 to 2.00 parts defoamer; and

from 0.00 to 50.0 parts rubber softener.

5. The surgeon's glove of claim 4 wherein the copolymer comprises from about 35% to about 45% chlorine by weight.
6. The surgeon's glove of claim 4 wherein the copolymer comprises 40% chlorine by weight.