

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization

International Bureau



(10) International Publication Number

WO 2014/164196 A1

(43) International Publication Date
9 October 2014 (09.10.2014)

(51) International Patent Classification:

C22C 21/00 (2006.01) C22F 1/04 (2006.01)
C22C 21/08 (2006.01) C22F 1/047 (2006.01)
C22C 21/10 (2006.01) C22F 1/053 (2006.01)

(21) International Application Number:

PCT/US2014/021169

(22) International Filing Date:

6 March 2014 (06.03.2014)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

13/791,989 9 March 2013 (09.03.2013) US

(71) Applicant: ALCOA INC. [US/US]; 201 Isabella Street, Alcoa Corporate Center, Pittsburgh, Pennsylvania 15212-5858 (US).

(72) Inventor: LIN, Jen; 1001 Alton Court, Export, Pennsylvania 15632 (US).

(74) Agent: BRIGGS, Heath J.; Greenberg Traurig, LLP, c/o Alcoa Inc., 100 Technical Drive, Alcoa Center, PA 15069 (US).


(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: HEAT TREATABLE ALUMINUM ALLOYS HAVING MAGNESIUM AND ZINC AND METHODS FOR PRODUCING THE SAME



(57) Abstract: New heat treatable aluminum alloys having magnesium and zinc are disclosed. The new aluminum alloys generally contain 3.0 - 6.0 wt. % Mg, 2.5 - 5.0 wt. % Zn, where (wt. % Mg) / (wt. % Zn) is from 0.60 to 2.40.

HEAT TREATABLE ALUMINUM ALLOYS HAVING MAGNESIUM AND ZINC AND METHODS FOR PRODUCING THE SAME

BACKGROUND

[001] Aluminum alloys are useful in a variety of applications. However, improving one property of an aluminum alloy without degrading another property is elusive. For example, it is difficult to increase the strength of an alloy without decreasing the toughness of an alloy. Other properties of interest for aluminum alloys include corrosion resistance and fatigue crack growth resistance, to name two.

SUMMARY OF THE DISCLOSURE

[002] Broadly, the present patent application relates to improved heat treatable aluminum alloys having magnesium and zinc ("magnesium-zinc aluminum alloys"), and methods of producing the same. For purposes of the present application, magnesium-zinc aluminum alloys are aluminum alloys having 3.0 - 6.0 wt. % magnesium and 2.5 - 5.0 wt. % zinc, where at least one of the magnesium and the zinc is the predominate alloying element of the aluminum alloy other than aluminum, and wherein (wt. % Mg) / (wt. % Zn) is from 0.6 to 2.40. The new magnesium-zinc aluminum alloys may include copper, silicon, iron, secondary elements and/or other elements, as defined below.

[003] The new magnesium-zinc aluminum alloys generally include 3.0 - 6.0 wt. % magnesium (Mg). In one embodiment, a magnesium-zinc aluminum alloy includes at least 3.25 wt. % Mg. In another embodiment, a magnesium-zinc aluminum alloy includes at least 3.50 wt. % Mg. In yet another embodiment, a magnesium-zinc aluminum alloy includes at least 3.75 wt. % Mg. In one embodiment, a magnesium-zinc aluminum alloy includes not greater than 5.5 wt. % Mg. In another embodiment, a magnesium-zinc aluminum alloy includes not greater than 5.0 wt. % Mg. In yet another embodiment, a magnesium-zinc aluminum alloy includes not greater than 4.5 wt. % Mg.

[004] In one embodiment, a magnesium-zinc aluminum alloy includes at least 2.75 wt. % Zn. In another embodiment, a magnesium-zinc aluminum alloy includes at least 3.0 wt. % Zn. In another embodiment, a magnesium-zinc aluminum alloy includes at least 3.25 wt. % Zn. In one embodiment, a magnesium-zinc aluminum alloy includes not greater than 4.5 wt. % Zn. In one embodiment, a magnesium-zinc aluminum alloy includes not greater than 4.0 wt. % Zn.

[005] In one embodiment, the (wt. % Mg) / (wt. % Zn) (i.e. the Mg/Zn ratio) is at least 0.75. In another embodiment, the (wt. % Mg) / (wt. % Zn) is at least 0.90. In yet another embodiment, the (wt. % Mg) / (wt. % Zn) is at least 1.0. In another embodiment, the (wt. % Mg) / (wt. % Zn) is at least 1.02. In one embodiment, the (wt. % Mg) / (wt. % Zn) (i.e. the Mg/Zn ratio) is not greater than 2.00. In another embodiment, the (wt. % Mg) / (wt. % Zn) is not greater than 1.75. In another embodiment, the (wt. % Mg) / (wt. % Zn) is not greater than 1.50.

[006] The new magnesium-zinc aluminum alloys may include copper and/or silicon. In one embodiment, a magnesium-zinc aluminum alloy includes copper. In another embodiment, a magnesium-zinc aluminum alloy includes silicon. In yet another embodiment, a magnesium-zinc aluminum alloy includes both copper and silicon.

[007] When copper is used, the magnesium-zinc aluminum alloys generally include at least 0.05 wt. % Cu. In one embodiment, a magnesium-zinc aluminum alloy includes at least 0.10 wt. % Cu. The magnesium-zinc aluminum alloys generally include not greater than 1.0 wt. % Cu, such as not greater than 0.5 wt. % Cu. In other embodiments, copper is included in the alloy as an impurity, and in these embodiments is present at levels of less than 0.05 wt. % Cu.

[008] When silicon is used, the magnesium-zinc aluminum alloys generally include at least 0.10 wt. % Si. In one embodiment, a magnesium-zinc aluminum alloy includes at least 0.15 wt. % Si. The magnesium-zinc aluminum alloys generally include not greater than 0.50 wt. % Si. In one embodiment, a magnesium-zinc aluminum alloy includes not greater than 0.35 wt. % Si. In another embodiment, a magnesium-zinc aluminum alloy includes not greater than 0.25 wt. % Si. In other embodiments, silicon is included in the alloy as an impurity, and in these embodiments is present at levels of less than 0.10 wt. % Si.

[009] The new magnesium-zinc aluminum alloys may include at least one secondary element selected from the group consisting of Zr, Sc, Cr, Mn, Hf, V, Ti, and rare earth elements. Such elements may be used, for instance, to facilitate the appropriate grain structure in a resultant magnesium-zinc aluminum alloy product. The secondary elements may optionally be present as follows: up to 0.20 wt. % Zr, up to 0.30 wt. % Sc, up to 1.0 wt. % of Mn, up to 0.50 wt. % of Cr, up to 0.25 wt. % each of any of Hf, V, and rare earth elements, and up to 0.15 wt. % Ti. Zirconium (Zr) and/or scandium (Sc) are preferred for grain structure control. When zirconium is used, it is generally included in the new

magnesium-zinc aluminum alloys at 0.05 to 0.20 wt. % Zr. In one embodiment, a new magnesium-zinc aluminum alloy includes 0.07 to 0.16 wt. % Zr. Scandium may be used in addition to, or as a substitute for zirconium, and, when present, is generally included in the new magnesium-zinc aluminum alloys at 0.05 to 0.30 wt. % Sc. In one embodiment, a new magnesium-zinc aluminum alloy includes 0.07 to 0.25 wt. % Sc. Chromium (Cr) may also be used in addition to, or as a substitute for zirconium, and/or scandium, and when present is generally included in the new magnesium-zinc aluminum alloys at 0.05 to 0.50 wt. % Cr. In one embodiment, a new magnesium-zinc aluminum alloy includes 0.05 to 0.35 wt. % Cr. In another embodiment, a new magnesium-zinc aluminum alloy includes 0.05 to 0.25 wt. % Cr. In other embodiments, any of zirconium, scandium, and/or chromium may be included in the alloy as an impurity, and in these embodiments such elements would be included in the alloy at less than 0.05 wt. %.

[0010] Hf, V and rare earth elements may be included an in an amount of up to 0.25 wt. % each (i.e., up to 0.25 wt. % each of any of Hf and V and up to 0.25 wt. % each of any rare earth element may be included). In one embodiment, a new magnesium-zinc aluminum alloy includes not greater than 0.05 wt. % each of Hf, V, and rare earth elements (not greater than 0.05 wt. % each of any of Hf and V and not greater than 0.05 wt. % each of any rare earth element may be included).

[0011] Titanium is preferred for grain refining, and, when present is generally included in the new magnesium-zinc aluminum alloys at 0.005 to 0.10 wt. % Ti. In one embodiment, a new magnesium-zinc aluminum alloy includes 0.01 to 0.05 wt. % Ti. In another embodiment, a new magnesium-zinc aluminum alloy includes 0.01 to 0.03 wt. % Ti.

[0012] Manganese (Mn) may be used in the new magnesium-zinc aluminum alloys and in an amount of up to 1.0 wt. %. In one embodiment, a new magnesium-zinc aluminum alloy includes not greater than 0.75 wt. % Mn. In another embodiment, a new magnesium-zinc aluminum alloy includes not greater than 0.60 wt. % Mn. In yet another embodiment, a new magnesium-zinc aluminum alloy includes not greater than 0.50 wt. % Mn. In another embodiment, a new magnesium-zinc aluminum alloy includes not greater than 0.40 wt. % Mn. In one embodiment, a new magnesium-zinc aluminum alloy includes at least 0.05 wt. % Mn. In another embodiment, a new magnesium-zinc aluminum alloy includes at least 0.10 wt. % Mn. In yet another embodiment, a new magnesium-zinc aluminum alloy includes at least 0.15 wt. % Mn. In another embodiment, a new magnesium-zinc aluminum alloy

includes at least 0.20 wt. % Mn. In one embodiment, a new magnesium-zinc aluminum alloy is substantially free of manganese and includes less than 0.05 wt. % Mn.

[0013] Iron (Fe) may be present in the new magnesium-zinc aluminum alloys, and generally as an impurity. The iron content of the new magnesium-zinc aluminum alloys should generally not exceed about 0.35 wt. % Fe. In one embodiments, a new magnesium-zinc aluminum alloy includes not greater than about 0.25 wt. % Fe. In other embodiments, a new magnesium-zinc aluminum alloy may include not greater than about 0.15 wt. % Fe, or not greater than about 0.10 wt. % Fe, or not greater than about 0.08 wt. % Fe, or less.

[0014] Aside from the above-listed elements, the balance (remainder) of the new magnesium-zinc aluminum alloys is generally aluminum and other elements, where the new magnesium-zinc aluminum alloys include not greater than 0.15 wt. % each of these other elements, and with the total of these other elements does not exceed 0.35 wt. %. As used herein, "other elements" includes any elements of the periodic table other than the above-identified elements, i.e., any elements other than Al, Mg, Zn, Cu, Si, Fe, Zr, Sc, Cr, Mn, Ti, Hf, V, and rare earth elements. In one embodiment, a new magnesium-zinc aluminum alloy includes not greater than 0.10 wt. % each of other elements, and with the total of these other elements not exceeding 0.25 wt. %. In another embodiment, a new magnesium-zinc aluminum alloy includes not greater than 0.05 wt. % each of other elements, and with the total of these other elements not exceeding 0.15 wt. %. In yet another embodiment, a new magnesium-zinc aluminum alloy includes not greater than 0.03 wt. % each of other elements, and with the total of these other elements not exceeding 0.10 wt. %.

[0015] The total amount of elements contained in the aluminum (i.e., all of the above described elements, or the "alloying elements") should be chosen so that the aluminum alloy can be appropriately solution heat treated and quenched (e.g., to promote hardening while restricting the amount of constituent particles). In one embodiment, a magnesium-zinc aluminum alloy includes an amount of alloying elements that leaves the magnesium-zinc aluminum alloy free of, or substantially free of, soluble constituent particles after solution heat treating and quenching. In one embodiment, a magnesium-zinc aluminum alloy includes an amount of alloying elements that leaves the aluminum alloy with low amounts of (e.g., restricted / minimized) insoluble constituent particles after solution heat treating and quenching. In other embodiments, a magnesium-zinc aluminum alloy may benefit from controlled amounts of insoluble constituent particles.

[0016] Except where stated otherwise, the expression "up to" when referring to the amount of an element means that that elemental composition is optional and includes a zero amount of that particular compositional component. Unless stated otherwise, all compositional percentages are in weight percent (wt. %).

[0017] The new magnesium-zinc aluminum alloys may be processed into a variety of wrought forms, such as in rolled form (sheet, plate), as an extrusion, or as a forging, and in a variety of tempers. In this regard, the new magnesium-zinc aluminum alloys may be cast (e.g., direct chill cast or continuously cast), and then worked (hot and/or cold worked) into the appropriate product form (sheet, plate, extrusion, or forging). After working, the new magnesium-zinc aluminum alloys may be processed into one of a T temper and a W temper, as defined by the Aluminum Association. In one embodiment, a new magnesium-zinc aluminum alloy is processed to a "T temper" (thermally treated). In this regard, the new magnesium-zinc aluminum alloys may be processed to any of a T1, T2, T3, T4, T5, T6, T7, T8 or T9 temper, as defined by the Aluminum Association. In one embodiment, a new magnesium-zinc aluminum alloy is processed to one of a T4, T6 or T7 temper, where the new magnesium-zinc aluminum alloy is solution heat treated, and then quenched, and then either naturally aged (T4) or artificially aged (T6 or T7). In one embodiment, a new magnesium-zinc aluminum alloys is processed to one of a T3 or T8 temper, where the new magnesium-zinc aluminum alloy is solution heat treated, and then quenched, and then cold worked, and then either naturally aged (T3) or artificially aged (T8). In another embodiment, a new magnesium-zinc aluminum alloy is processed to an "W temper" (solution heat treated), as defined by the Aluminum Association. In yet another embodiment, no solution heat treatment is applied after working the aluminum alloy into the appropriate product form, and thus the new magnesium-zinc aluminum alloys may be processed to an "F temper" (as fabricated), as defined by the Aluminum Association.

[0018] The new magnesium-zinc aluminum alloys may be used in a variety of applications, such as in an automotive application or an aerospace application.

[0019] In one embodiment, the new magnesium-zinc aluminum alloys are used in an aerospace application, such as wing skins (upper and lower) or stringers / stiffeners, fuselage skin or stringers, ribs, frames, spars, seat tracks, bulkheads, circumferential frames, empennage (such as horizontal and vertical stabilizers), floor beams, seat tracks, doors, and control surface components (e.g., rudders, ailerons) among others.

[0020] In another embodiment, the new magnesium-zinc aluminum alloys are used in an automotive application, such as closure panels (e.g., hoods, fenders, doors, roofs, and trunk lids, among others), wheels, and critical strength applications, such as in body-in-white (e.g., pillars, reinforcements) applications, among others.

BRIEF DESCRIPTION OF THE DRAWINGS

[0021] FIGS. 1-3 are graphs illustrating results of Example 1.

[0022] FIG. 4 contains micrographs of alloys of Example 1 showing their corrosion resistance.

DETAILED DESCRIPTION

Example 1

[0023] Six book mold ingots were cast (2.25" (H) x 3.75" (W) x 14" (L)) having the compositions shown in Table 1, below.

Table 1 - Composition of Ex. 1 Alloys (in wt. %)

Alloy	Mg	Zn	Mg/Zn	Cu	Mn	Note
1	3.88	2.13	1.82	0.48	0.31	Non-invention
2	3.31	3.2	1.03	0.48	0.32	Invention
3	4.34	3.25	1.34	0	0.53	Invention
4	3.87	2.17	1.78	0.25	0.32	Non-invention
5	3.89	2.19	1.78	0.25	0.64	Non-invention
6	3.72	3.56	1.04	0	0.32	Invention

The alloys all contained not greater than about 0.12 wt. % Fe, not greater than about 0.11 wt. % Si, from about 0.01 to about 0.02 wt. % Ti, and from about 0.10 to 0.11 wt. % Zr. The remainder of the aluminum alloy was aluminum and other elements, where the aluminum alloy included not greater than 0.03 wt. % each of other elements, and with the total of these other elements not exceeding 0.10 wt. %.

[0024] The ingots were processed to a T6-style temper. Specifically, the ingots were homogenized, hot rolled to 0.5" gauge, solution heat treated and cold water quenched, and then stretched about 1-2% for flatness. The products were then naturally aged at least 96 hours at room temperature and then artificially aged at various temperatures for various times (shown below). After aging, mechanical properties were measured, the results of which are provided in Tables 2-4, below. Strength and elongation properties were measured in

accordance with ASTM E8 and B557. Charpy impact energy tests were performed according to ASTM E23-07a.

Table 2 - Properties (L) of Ex. 1 alloys - Aged at 325°F

Alloy	Aging Time (hours)	TYS (ksi)	UTS (ksi)	Elong. (%)
2	0	31.6	50.2	32.0
	2	36.4	51.6	22.0
	4	44.6	58.7	21.0
	8	48.3	61.7	21.0
	12	53.0	65.5	18.0
3	0	29.4	52.8	32.0
	2	41.5	57.0	21.0
	4	44.5	58.1	19.0
	8	48.2	61.4	19.0
	12	52.7	65.8	15.0
4	0	23.7	47.4	36.0
	2	23.9	46.5	34.0
	4	23.2	44.8	33.0
	8	24.4	44.8	30.0
	12	26.4	46.7	29.0
6	0	33.2	51.9	29.0
	2	49.1	59.8	19.0
	4	51.4	61.5	18.0
	8	53.5	63.7	17.0
	12	56.0	66.9	16.0

Table 3 - Properties (L) of Ex. 1 alloys - Aged at 350°F

Alloy	Aging Time (hours)	TYS (ksi)	UTS (ksi)	Elong. (%)	Charpy Impact Energy (ft-lbf)
1	0	24.6	40.1	36.0	--
	2	25.6	47.1	30.0	--
	4	27.7	48.8	31.0	--
	8	28.6	48.5	28.0	--
	12	28.6	46.6	24.0	--
2	0	31.6	50.2	32.0	--
	2	45.8	59.3	19.0	--
	4	50.4	63.6	19.0	157
	8	46.4	60.4	18.0	--
	12	46.6	60.9	18.0	--
3	0	29.4	52.8	32.0	--

Alloy	Aging Time (hours)	TYS (ksi)	UTS (ksi)	Elong. (%)	Charpy Impact Energy (ft-lbf)
3	2	41.4	56.4	18.0	--
	4	44.9	60.3	17.0	156
	8	43.6	58.8	17.0	--
	12	46.5	61.8	16.0	--
4	0	23.7	47.4	36.0	--
	2	24.2	45.5	28.0	--
	4	26.4	46.5	28.5	--
	8	30.0	50.5	21.0	--
	12	27.5	45.5	27.0	--
5	0	23.7	47.0	36.0	--
	2	24.7	47.2	26.0	--
	4	26.2	46.5	24.0	--
	8	28.6	48.8	24.0	--
	12	26.1	43.8	22.0	--
6	0	33.2	51.9	29.0	--
	2	51.7	62.5	18.0	--
	4	50.4	62.3	17.0	154
	8	51.6	64.2	16.0	--
	12	48.6	62.0	16.0	--

Table 4 - Properties (L) of Ex. 1 alloys - Aged at 375°F

Alloy	Aging Time (hours)	TYS (ksi)	UTS (ksi)	Elong. (%)
1	0	24.6	40.1	36.0
	1	26.0	47.4	35.0
	2	26.3	45.7	32.0
	4	28.1	47.0	27.0
	8	29.2	47.7	26.0
2	0	31.6	50.2	32.0
	1	42.0	57.0	20.0
	2	50.0	63.9	19.0
	4	40.6	56.2	18.0
	8	43.0	57.8	18.0
3	0	29.4	52.8	32.0
	1	43.9	58.7	17.0
	2	45.2	60.6	17.0
	4	41.4	57.5	18.0
	8	41.7	57.9	19.0
4	0	23.7	47.4	36.0
	1	27.6	46.9	26.0

Alloy	Aging Time (hours)	TYS (ksi)	UTS (ksi)	Elong. (%)
	2	30.3	51.1	22.0
	4	28.8	48.0	22.0
	8	27.5	46.2	27.0
5	0	24.7	47.0	36.0
	1	25.9	48.2	30.0
	2	28.3	49.5	26.0
	4	27.4	46.4	20.0
	8	28.6	47.9	21.0
6	0	33.2	51.9	29.0
	1	46.0	58.0	18.0
	2	44.6	58.4	18.0
	4	46.4	60.6	17.0
	8	45.5	60.6	17.0

[0025] As shown above, and in FIGS. 1-3, the invention alloys having at least 3.0 wt. % Zn achieve higher strengths than the non-invention alloys having 2.19 wt. % Zn or less. The invention alloy also realize high charpy impact resistance, all realizing about 154-157 ft-lbf. By comparison, conventional alloy 6061 realized a charpy impact resistance of about 85 ft-lbf under similar processing conditions.

[0026] The invention alloys also realized good intergranular corrosion resistance. Alloys 3, 4 and 6 were tested for intergranular corrosion in accordance with ASTM G110. Conventional alloy 6061 was also tested for comparison purposes. As shown in FIG. 4 and in Table 5, below, the invention alloys realized improved intergranular corrosion resistance as compared to conventional alloy 6061.

Table 5 - Corrosion Properties of Alloys - Peak Strength Condition
(385°F for 2 hours)

Alloy	G110 - Depth of Attack - 24 hours (in.)			
	T/10 (ave.)	T10 (max.)	Surface (ave.)	Surface (max.)
1	0.00886	0.00948	0.00499	0.00847
2	0.00811	0.01060	0.00685	0.00929
3	0.00062	0.00091	0.00200	0.00287
4	0.00063	0.00084	0.00291	0.00494
5	0.00064	0.00071	0.00522	0.00935
6	0.00078	0.00100	0.00729	0.02348
6061	0.01044	0.01385	0.00822	0.01141

Example 2

[0027] Alloy 6 of Example 1 was also processed with high cold work after solution heat treatment. Specifically, Alloy 6 was hot rolled to an intermediate gauge of 1.0 inch, solution heat treated, cold water quenched, and then cold rolled 50% (i.e., reduced in thickness by 50%) to a final gauge of 0.5 inch, thereby inducing 50% cold work. Alloy 6 was then artificially aged at 350°F for 0.5 hour and 2 hours. Before and after aging, mechanical properties were measured, the results of which are provided in Table 6, below. Strength and elongation properties were measured in accordance with ASTM E8 and B557.

Table 6 - Properties (L) of Ex. 2, Alloy 6 - Aged at 350°F

Aging Time (hours)	TYS (ksi)	UTS (ksi)	Elong. (%)
0	58.5	68.6	13.0
0.5	58.9	67.2	16.0
2	56.0	64.7	16.0

[0028] As shown above, the 0.5 inch plate realizes high strength and with good elongation, achieving about a peak tensile yield strength of about 59 ksi, with an elongation of about 16% and with only 30 minutes of aging. By comparison, conventional alloy 5083 at similar thickness generally realizes a tensile yield strength (LT) of about 36 ksi at similar elongation and similar corrosion resistance.

[0029] While various embodiments of the present disclosure have been described in detail, it is apparent that modifications and adaptations of those embodiments will occur to those skilled in the art. However, it is to be expressly understood that such modifications and adaptations are within the spirit and scope of the present disclosure.

CLAIMS

What is claimed is:

1. An aluminum alloy consisting of:

3.0 - 6.0 wt. % Mg;

2.5 - 5.0 wt. % Zn;

wherein (wt. % Mg) / (wt. % Zn) is from 0.6 to 2.40;

up to 1.0 wt. % Cu;

up to 0.5 wt. % Si;

optionally at least one secondary element selected from the group consisting of Zr, Sc, Cr, Mn, Hf, V, Ti, and rare earth elements, and in the following amounts:

up to 0.20 wt. % Zr;

up to 0.30 wt. % Sc;

up to 0.50 wt. % Cr;

up to 1.0 wt. % Mn;

up to 0.25 wt. % each of any of Hf, V, and rare earth elements;

up to 0.15 wt. % Ti;

up to 0.35 wt. Fe; and

the balance being aluminum and other elements, wherein the aluminum alloy includes not greater than 0.15 wt. % each of these other elements, and wherein the total of these other elements does not exceed 0.35 wt. %.

2. The aluminum alloy of claim 1, wherein the aluminum alloy includes at least 3.25 wt. % Mg.

3. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes at least 3.50 wt. % Mg.

4. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes at least 3.75 wt. % Mg.

5. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 5.5 wt. % Mg.

6. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 5.0 wt. % Mg.

7. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 4.5 wt. % Mg.

8. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes at least 2.75 wt. % Zn.
9. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes at least 3.0 wt. % Zn.
10. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes at least 3.25 wt. % Zn.
11. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 4.5 wt. % Zn.
12. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 4.0 wt. % Zn.
13. The aluminum alloy of any of the preceding claims, wherein (wt. % Mg) / (wt. % Zn) is at least 0.75.
14. The aluminum alloy of any of the preceding claims, wherein (wt. % Mg) / (wt. % Zn) is at least 0.90.
15. The aluminum alloy of any of the preceding claims, wherein (wt. % Mg) / (wt. % Zn) is at least 1.00.
16. The aluminum alloy of any of the preceding claims, wherein (wt. % Mg) / (wt. % Zn) is at least 1.02.
17. The aluminum alloy of any of the preceding claims, wherein (wt. % Mg) / (wt. % Zn) is not greater than 2.00.
18. The aluminum alloy of any of the preceding claims, wherein (wt. % Mg) / (wt. % Zn) is not greater than 1.75.
19. The aluminum alloy of any of the preceding claims, wherein (wt. % Mg) / (wt. % Zn) is not greater than 1.50.
20. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 0.5 wt. % Cu.
21. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes less than 0.05 wt. % Cu.
22. The aluminum alloy of any of claims 1-20, wherein the aluminum alloy includes at least 0.05 wt. % Cu.
23. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 0.35 wt. % Si.

24. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 0.25 wt. % Si.
25. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes at least 0.10 wt. % Si.
26. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes at least 0.125 wt. % Si.
27. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes at least 0.15 wt. % Si.
28. The aluminum alloy of any of claims 1-24, wherein the aluminum alloy includes less than 0.10 wt. % Si.
29. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes 0.05 - 0.20 wt. % Zr.
30. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes 0.07 - 0.16 wt. % Zr.
31. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes 0.05 - 0.30 wt. % Sc.
32. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes 0.07 - 0.25 wt. % Sc.
33. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes 0.05 - 0.35 wt. % Cr.
34. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes 0.05 - 0.25 wt. % Cr.
35. The aluminum alloy of any of claims 1-32, wherein the aluminum alloy includes less than 0.05 wt. % Cr.
36. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 0.05 wt. % each of any of Hf, V, and rare earth elements.
37. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes 0.005 - 0.10 wt. % Ti.
38. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes 0.01 - 0.05 wt. % Ti.
39. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes 0.01 - 0.03 wt. % Ti.

40. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 0.75 wt. % Mn.
41. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 0.60 wt. % Mn.
42. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 0.50 wt. % Mn.
43. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 0.40 wt. % Mn.
44. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes at least 0.05 wt. % Mn.
45. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes at least 0.10 wt. % Mn.
46. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes at least 0.15 wt. % Mn.
47. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes at least 0.20 wt. % Mn.
48. The aluminum alloy of any of claims 1-43, wherein the aluminum alloy includes less than 0.05 wt. % Mn.
49. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 0.25 wt. % Fe.
50. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 0.15 wt. % Fe.
51. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 0.10 wt. % Fe.
52. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 0.08 wt. % Fe.
53. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 0.10 wt. % each of these other elements, and wherein the total of these other elements does not exceed 0.25 wt. %.
54. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 0.05 wt. % each of these other elements, and wherein the total of these other elements does not exceed 0.15 wt. %.

55. The aluminum alloy of any of the preceding claims, wherein the aluminum alloy includes not greater than 0.03 wt. % each of these other elements, and wherein the total of these other elements does not exceed 0.10 wt. %.

56. A method comprising:

(a) casting the aluminum alloy of any of claims 1-55 into an aluminum alloy body;

(b) processing the aluminum alloy body into one of a W temper and a T temper, wherein the processing step (b) comprises solution heat treating and then quenching the aluminum alloy body.

57. The method of claim 56, wherein the processing comprises artificial aging the aluminum alloy body to one of a T6, T7 or a T8 temper, wherein the aluminum alloy body in the T6 or T7 temper realizes a higher strength than the aluminum alloy body in a T4 temper, or wherein the aluminum alloy body in the T8 temper realizes a higher strength than the aluminum alloy body in a T3 temper.

FIG. 1




FIG. 2





FIG. 3






FIG. 4 - ASTM G110 24 hrs test on T/10

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US2014/021169

A. CLASSIFICATION OF SUBJECT MATTER

C22C 21/00(2006.01)i, C22C 21/08(2006.01)i, C22C 21/10(2006.01)i, C22F 1/04(2006.01)i, C22F 1/047(2006.01)i, C22F 1/053(2006.01)i

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C22C 21/00; C22C 21/12; C22F 1/047; C22C 21/06; C22C 21/10; C22B 9/05; C22C 21/08; C22F 1/053

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
Korean utility models and applications for utility models
Japanese utility models and applications for utility models

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
eKOMPASS(KIPO internal) & keywords: aluminum alloy, magnesium, zinc, and heat treatable

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5759302 A (NAKAI et al.) 2 June 1998 See column 3, lines 14-23; and claim 6.	1-3
A	US 2007-0017604 A1 (YAN et al.) 25 January 2007 See paragraphs [0013], [0017]; and claim 1.	1-3
A	JP 2009-256782 A (KOBE STEEL LTD.) 5 November 2009 See paragraphs [0020], [0037]; and claim 2.	1-3
A	JP 2006-152403 A (KOBE STEEL LTD.) 15 June 2006 See paragraphs [0024], [0049]; and claim 1.	1-3
A	US 2006-0016523 A1 (DIF et al.) 26 January 2006 See paragraphs [0103]-[0108]; and claims 1,5.	1-3

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier application or patent but published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search 18 June 2014 (18.06.2014)	Date of mailing of the international search report 25 June 2014 (25.06.2014)
Name and mailing address of the ISA/KR International Application Division Korean Intellectual Property Office 189 Cheongsa-ro, Seo-gu, Daejeon Metropolitan City, 302-701, Republic of Korea Facsimile No. +82-42-472-7140	Authorized officer SONG, Ho Keun Telephone No. +82-42-481-5580

INTERNATIONAL SEARCH REPORTInternational application No.
PCT/US2014/021169**Box No. II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)**

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. Claims Nos.: because they relate to subject matter not required to be searched by this Authority, namely:
2. Claims Nos.: 57 because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
Claim 57 is unclear because it refers to multiple dependent claim 56 which does not comply with PCT Rule 6.4(a).
3. Claims Nos.: 4-56 because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box No. III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. As all searchable claims could be searched without effort justifying an additional fees, this Authority did not invite payment of any additional fees.
3. As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- The additional search fees were accompanied by the applicant's protest and, where applicable, the payment of a protest fee.
- The additional search fees were accompanied by the applicant's protest but the applicable protest fee was not paid within the time limit specified in the invitation.
- No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2014/021169

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5759302 A	02/06/1998	JP 08-283892 A JP 3053352 B2	29/10/1996 19/06/2000
US 2007-0017604 A1	25/01/2007	AT 483035 T CA 2609257 A1 CA 2609257 C DE 602006017204 D1 EP 1885898 A2 EP 1885898 A4 EP 1885898 B1 JP 2008-542534 A US 8157932 B2 WO 2006-127812 A2 WO 2006-127812 A3	15/10/2010 30/11/2006 06/08/2013 11/11/2010 13/02/2008 08/10/2008 29/09/2010 27/11/2008 17/04/2012 30/11/2006 22/11/2007
JP 2009-256782 A	05/11/2009	CN 101959625 A EP 2263811 A1 EP 2263811 A4 JP 4410835 B2 KR 10-1251235 B1 KR 10-2010-0116698 A TW 201006578 A TW I355301 B TW I355301 I WO 2009-119724 A1	26/01/2011 22/12/2010 04/05/2011 03/02/2010 08/04/2013 01/11/2010 16/02/2010 01/01/2012 01/01/2012 01/10/2009
JP 2006-152403 A	15/06/2006	JP 4477998 B2	09/06/2010
US 2006-0016523 A1	26/01/2006	AT 413477 T AU 2003-292348 A1 CA 2504931 A1 CA 2504931 C DE 60324581 D1 EP 1558778 A1 EP 1558778 B1 ES 2314255 T3 FR 2846669 A1 FR 2846669 B1 JP 2006-505695 A RU 2005117168 A RU 2326182 C2 US 7780802 B2 WO 2004-044256 A1	15/11/2008 03/06/2004 27/05/2004 04/10/2011 18/12/2008 03/08/2005 05/11/2008 16/03/2009 07/05/2004 22/07/2005 16/02/2006 20/01/2006 10/06/2008 24/08/2010 27/05/2004