

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization

International Bureau



WIPO | PCT



(10) International Publication Number

WO 2013/131649 A1

(43) International Publication Date

12 September 2013 (12.09.2013)

(51) International Patent Classification:

C08K 3/34 (2006.01) B65D 81/38 (2006.01)  
C08L 67/04 (2006.01)

(21) International Application Number:

PCT/EP2013/000665

(22) International Filing Date:

7 March 2013 (07.03.2013)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

EP 12001550.8 7 March 2012 (07.03.2012) EP

(71) Applicants: HUHTAMÄKI OYJ [FI/FI]; Miestentie 9, FIN-02150 Espoo (FI). PURAC BIOCHEM B.V. [NL/NL]; Arkelsedijk 46, NL-4206 AC Gorinchem (NL).

(72) Inventors: HOEKSTRA, Aad; Coehoornsingel 82, NL-7201 AE Zutphen (NL). SCHENNINK, Gerald G. J.; Keppelseweg 32A, NL-7031 EB Wehl (NL). DE VOS, Sicco; De Spade 12, NL-6846 JL Arnhem (NL).

(74) Agents: KUTZENBERGER, Helga et al.; Patentanwälte Kutzenberger & Wolff, Theodor-Heuss-Ring 23, 50668 Cologne (DE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))



WO 2013/131649 A1

(54) Title: AN ESSENTIALLY BIOBASED, THERMOFORMABLE COMPOSITION AND CONTAINERS FORMED THEREOF

(57) Abstract: The present invention relates to an essentially biobased and optionally biodegradable, thermoformable composition containing a) as thermoformable resin at least one poly-L-lactide with less than 1 mol% of D-lactoyl units (PLLA) or at least one poly-L-lactide with from 1 mol% to 5 mol% of D-lactoyl units (PLA) and b) a nucleating combination consisting of  $\alpha$ ) 1 to 10 % by weight, based on the total amount of the thermoformable resin a), of at least one poly-D-lactide with less than 1 mol% of L-lactoyl-units (PDLA) as component a 1 ) or of 0.5 to 5% by weight, based on the total amount of the thermoformable resin a), of PLLA/PDLA or PLA/PDLA stereocomplex crystallites, preferably with a molar ratio of 1:1, as component a 2),  $\beta$ ) 0.1 to 25% by weight, based on the total amount of the thermoformable resin a), of an inorganic nucleating agent, preferably talc, and  $\gamma$ ) 0.1 to 30 % by weight, based on the total amount of the thermoformable resin a), of at least an inorganic filler with lamellar structure, preferably a lamellar clay mineral, and to thermoformed, essentially biobased and optionally biodegradable containers formed of the inventive compositions.

**An essentially biobased, thermoformable composition  
and containers formed thereof**

The present invention relates to a preferably essentially biobased and optionally biodegradable, thermoformable composition containing

- a) as thermoformable, biodegradable resin at least one poly-L-lactide with less than 1 mol% of D-lactoyl units (PLLA) or at least one poly-L-lactide with from 1 mol% to 5 mol% of D-lactoyl units (PLA) and
- b) a nucleating combination consisting of
  - α) 1 to 10 % by weight, based on the total amount of the thermoformable resin a), of at least one poly-D-lactide with less than 1 mol% of L-lactoyl-units (PDLA) as component α 1) or of 0.5 to 5% by weight, based on the total amount of the thermoformable resin a), of PLLA/PDLA or PLA/PDLA stereocomplex crystallites, preferably with a molar ratio of 1:1, as component α 2),
  - β) 0.1 to 25% by weight, based on the total amount of the thermoformable resin a), of an inorganic nucleating agent, preferably talc, and
  - γ) 0.1 to 30 % by weight, based on the total amount of the thermoformable resin a), of at least an inorganic filler with lamellar structure, preferably a lamellar clay mineral,

and to thermoformed, essentially biobased and optionally biodegradable containers formed of the inventive compositions.

Food containers like cups, which have to withstand temperatures around the boiling point of water, because they are used for hot drinks like tea, coffee or soup, are usually not manufactured of polylactides, although it is known that polylactides are biodegradable polymers which are decomposed by the action of microbes and enzymes into lactide acid, carbon dioxide and water.

One of the main reasons that polylactides are not suitable for the manufacturing of such cups is the low glass transition temperature of these polymers, which causes softening of the material already about 50°C, which is more than 40°C below the application temperature of these polymers.

Another important disadvantage of polylactides are the crystallization properties of these polymers. Although homopolymers, PDLA respectively PLLA, are crystalline, the crystallization rate of these polymers is relatively slow and the polymers exhibit a behavior particularly similar to that of a non-crystalline resin.

In view of this relatively long time for crystallization, compositions containing PLA, even homopolymers, do not crystallize sufficiently during the usual short cycle times for the production of thermoformed articles, e.g. by thermoforming with moulding. Therefore, the use of these biodegradable polymers is rather disadvantageous.

Consequently, a considerable portion of food containers, especially cups for hot beverages and predominantly cups for a single use, are still manufactured of plastic resins produced from fossil sources, and not of plastic resin produced from renewable raw material, although the thermoformable PLA, PLLA and PDLA, are

produced from renewable raw materials and therefore are biobased as well as biodegradable.

In order to be able to provide containers for hot beverages, especially cups for single use, manufactured of biobased and biodegradable polymers like PLLA or PLA, the above identified disadvantages of these polymers have to be overcome. Especially the need for the production of such containers, especially cups, in short cycle times has to be satisfied by increasing the rate of crystallization and the resistance against deformation at elevated temperatures, especially if such containers, especially cups, are used for hot beverages like hot coffee or tea.

Therefore, an object of the present invention was to provide thermoformable compositions containing as biobased polymers poly-L-lactide with less than 1 mol% of D-lactoyl-units (PLLA) or poly-L-lactide with from 1 mol% to 5 mol% of D-lactoyl-units (PLA), which guarantee a rate of crystallization allowing to usual short cycle times in the production of thermoformed food containers, especially cups, and the provision of such containers having excellent mechanical properties up to temperatures of 100 °C.

This object is solved by providing a preferably essentially biobased and optionally biodegradable, thermoformable composition containing

- a) as thermoformable, biodegradable resin at least one poly-L-lactide with less than 1 mol% of D-lactoyl units (PLLA) or at least one poly-L-lactide with from 1 mol% to 5 mol% of D-lactoyl units (PLA) and
- b) a nucleating combination consisting of

- a) 1 to 10 % by weight, based on the total amount of the thermoformable resin a), of at least one poly-D-lactide with less than 1 mol% of L-lactoyl-units (PDLA) as component  $\alpha$  1) or of 0.5 to 5% by weight, based on the total amount of the thermoformable resin a), of PLLA/PDLA or PLA/PDLA stereocomplex crystallites, preferably with a molar ratio of 1:1, as component  $\alpha$  2),
- β) 0.1 to 25% by weight, based on the total amount of the thermoformable resin a), of an inorganic nucleating agent, preferably talc, and
- γ) 0.1 to 30 % by weight, based on the total amount of the thermoformable resin a), of at least an inorganic filler with lamellar structure, preferably a lamellar clay mineral.

A further object of the present invention is a thermoformed, essentially biobased and optionally biodegradable container formed of an inventive thermoformable composition containing

- a) as thermoformable, biodegradable resin at least one PLLA or PLA and
- b) a nucleating combination consisting of
  - a) 1 to 10 % by weight, based on the total amount of the thermoformable resin a), of at least one poly-D-lactide with less than 1 mol% of L-lactoyl-units (PDLA) as component  $\alpha$  1) or of 0.5 to 5% by weight, based on the total amount of the thermoformable resin a), of PLLA/PDLA or PLA/PDLA stereocomplex crystallites, preferably with a molar ratio of 1:1, as component  $\alpha$  2),

- β) 0.1 to 25% by weight, based on the total amount of the thermoformable resin a), of an inorganic nucleating agent, preferably talc, and
- γ) 0.1 to 30 % by weight, based on the total amount of the thermoformable resin a), of at least an inorganic filler with lamellar structure, preferably a lamellar clay mineral.

According to the present invention the term "PLLA" means a poly-L-lactide with less than 1 mol% of D-lactoyl-units.

According to the present invention the term "PLA" means a poly-L-lactide with from 1 mol% to 5 mol% of D-lactoyl units.

According to the present invention the term "PDLA" means a poly-D-lactide with less than 1 mol% of L-lactoyl units.

The term "biodegradable" means according to the present invention that such a biodegradable polymer, copolymer or plastic resin complies with European standard EN 13432 on the compostability. This means that at least 90% of the organic carbon in the material (polymer, copolymer, plastic resin) has been converted in a test period of maximum 180 days to CO<sub>2</sub>, water, energy and biomass.

The term "essentially biodegradable" means according to the present invention that at least 70% by weight of such an article (container, cups) complies with European standard EN 13432 on the compostability.

The term "biobased" means according to the present invention that an article (container, cups) is manufactured of compounds produced from renewable raw materials completely.

The term "essentially biobased" means according to the present invention that an article (cup, container) is manufactured of at least 60% by weight of the components produced from renewable materials.

The inventive thermoformable composition of which the inventive essentially biobased, thermoformed container is formed, comprises, besides the nucleating composition b), as thermoformable, biobased resin a) at least one PLLA or PLA, which PLA is preferably a copolymer consisting of L-lactoyl units and from 1 to 2,5 mol% D-lactoyl units.

Such biobased and biodegradable PLLA respectively PLA or PDLA can be produced by ring-opening polymerization of the dimers of corresponding lactic acid, which is well known in the art.

Preferably, these biobased and biodegradable polymers, PLLA or PLA, have a weight-average molecular weight of at least 30.000, more preferably at least 60.000, most preferably at least 90.000 g/mol. The weight-average molecular weight of the biodegradable polymers PLLA is preferably at most 300.000 g/mol. With the weight-average molecular weight of less than the lower limit the mechanical properties such as stiffness and elastic modulus of inventive containers formed of inventive compositions become insufficient and by contrast by exceeding the upper limit the molding processability of the inventive thermoformable composition becomes insufficient.

The inventive, thermoformable compositions used for the production of the inventive thermoformed, essentially biobased and optionally biodegradable containers comprise a nucleating composition b) consisting of three components α), β) and γ) which guarantees not only a sufficient high rate of crystallization combined with a thereof independent, broad window for thermoforming and consequently a sufficient high thermoforming speed with short cycle times, but also a sufficiently high resistance against deformation up to a temperature of 100 °C by maintaining sufficient stiffness for the use of the inventive containers, preferably of cups, which are produced by thermoforming the inventive thermoformable composition containing the nucleating combination b).

As component α 1) the biobased and biodegradable polymer PDLA, that is incorporated in the inventive thermoformable composition in an amount of 1 to 10%, preferably 1 to 6% by weight, based on the total amount of the thermoformable resin a), is a poly-D-lactide, which is a copolymer consisting of D-lactoyl units and less than 1 mol% of L-lactoyl units as already defined. The weight-average molecular weight of the PDLA is preferably in the range disclosed already before for the thermoformable resin PLLA. However, preferably, the weight-average molecular weight of the PDLA used is different to the weight-average molecular weight of PLLA used.

As component α 2), instead of the component α 1), stereocomplex crystallites of PLLA/PDLA or of PLA/PDLA with a molar ratio of 1:1 in an amount of 0.5 to 5% by weight, preferably 1 to 3% by weight, based on the total weight of the thermoformable resin a), can be incorporated into the inventive thermoformable

compositions. These stereocomplex crystallites can be produced separately before adding into the inventive thermoformable composition by melting a mixture of preferably equal amounts of PLLA and PDLA respectively PLA and PDLA above 180°C up to 230°C, preferably up to 190 °C, and then cooling the melted mixture under crystallization or by heating the thermoformable composition containing the nucleating composition b) comprising as component a) the component a 1) above the melting point of PLLA, PLA respectively PDLA and cooling the mixture under crystallization.

As further component β) of the nucleating combination b) a known inorganic nucleating agent, preferably in particulated form, especially with an aspect ratio of 1 to 150 (median particle size preferably from 0,5 to 15 µm as determined by Sedigraph technique according to ISO 13317-3), preferably in form of compacted particles, in an amount of 0,1 to 25%, preferably 1 to 20% by weight, based on the total amount of the thermoformable resin a), is present. Such agent is preferably talc used preferably in an amount of 1 to 20%, based on the total amount of the thermoformable resin a). This talc has preferably an aspect ratio of 2 to 150 (median particle size can vary from 0,5 to 15 µm determined by the before mentioned Sedigraph technique). The inorganic nucleating agent, preferably talc, is preferably provided as masterbatch in PDLA, PLLA or PLA.

This component β) of the nucleating composition has to be present if as the biobased, biodegradable, thermoformable resin a) is PLA, and is preferably present if PLLA is used, in order to achieve the necessary high crystallization velocity.

The nucleating combination b) contains also at least one inorganic filler with lamellar structure, preferably a lamellar clay, more preferably lamellar aluminum silicate, in an amount of 0.1 to 30% by weight, preferably 10 to 25% by weight, based on the total amount of the thermoformable resin a) as component γ). Preferably as lamellar aluminum silicate kaolin in a multiparticulated form, preferably in form of flakes, is incorporated into the thermoformable resin a) preferably as masterbatch in PDLA, PLLA or PLA. The component γ) is always a different compound to any inorganic nucleating compound used as component β).

The component γ), especially kaolin, surprisingly does not influence the crystallization rate, however improves the demolding velocity and the mechanical properties like stiffness at high temperatures.

A preferred embodiment of the present invention is a thermoformable, essentially biobased and optionally biodegradable composition containing

- a) as thermoformable, biodegradable resin at least one PLLA and
- b) a nucleating combination consisting of
  - α) 1 to 10 % by weight, preferably 1 to 6% by weight, based on the total amount of the thermoformable resin a), of at least one PDLA as component α 1) or 0.5 to 5% by weight, preferably 0,5 to 3% by weight, based on the total amount of the thermoformable resin a), of PLLA/PDLA or PLA/PDLA stereocomplex crystallites in a molar ratio of 1:1 as component α 2),
  - β) 0.1 to 25% by weight, preferably 1 to 20% by weight, based on the total amount of the thermoformable resin a) of an inorganic nucleating agent, preferably talc, and

γ) 0.1 to 30 % by weight, preferably 5 to 25% by weight, based on the total amount of the thermoformable resin a), of at least an inorganic filler with lamellar structure, preferably a lamellar clay mineral, more preferably kaolin.

A further preferred embodiment of the present invention is a thermoformed, essentially biobased and optionally biodegradable container formed of an inventive thermoformable composition containing

- a) as thermoformable, biodegradable resin at least one PLLA or PLA and
- b) a nucleating combination consisting of
  - α) 1 to 10 % by weight, preferably 1 to 6% by weight, based on the total amount of the thermoformable resin a), of at least one PDLA as component α 1) or 0.5 to 5% by weight, preferably 0,5 to 3% by weight, based on the total amount of the thermoformable resin a), of PLLA/PDLA or PLA/PDLA stereocomplex crystallites in a molar ratio of 1:1, as component α 2),
  - β) 0,1 to 25% by weight, preferably 1 to 20% by weight, based on the total amount of the thermoformable resin a), of an inorganic nucleating agent, preferably talc and
  - γ) 0.1 to 30 % by weight, preferably 5 to 25% by weight, based on the total amount of the thermoformable resin a), of at least an inorganic filler with lamellar structure, preferably a lamellar clay mineral, more preferably kaolin.

The inventive, thermoformable composition can, if desired, contain additional additives, as long as the properties of the composition are not impaired to a

significant extent or not at all. Accordingly, the inventive, thermoformable composition may content UV stabilizers, heat stabilizers, anti-oxidants, flame retardants, impact modifiers, plasticizers, rheology modifiers, antistatic agents, mold release agents, lubricants or degassing agents.

The inventive, thermoformable composition containing the thermoformable resin a) and the nucleating combination b) is used for manufacturing containers, especially food containers like cups.

It is known in the art that polylactides – like all polyesters - are very sensitive to moisture. Therefore, these polymers have to be stored in packages having a barrier against moisture and, if necessary, handled under very dry conditions. Accordingly, all the components that are mixed with the polylactide resin have to be dried in order to avoid any degradation of the polylactide during the melting process of the thermoformable mixture, for example in an extruder.

In detail, for providing the inventive thermoformable compositions and for manufacturing an inventive container thereof, the thermoformable resin a) and the nucleating combination b) have to be mixed and melted under dry conditions before the molten material can be shaped into a sheet or film which solidifies. In this plasticising steps, the melting temperature should be at least 170°C, preferably 180 to 200°C, which means above the melting temperature of PDLA, PLA respectively PLLA, but below the melting temperature of stereocomplex crystallites. Therefore the upper limit of the melting temperature should not be exceeded, since stereocomplex crystallites melt about  $\geq 230^\circ\text{C}$  and the polylactide can be impaired at higher temperatures.

As mentioned before, these stereocomplex crystallites can be formed separately by mixing equivalent amounts of PLLA and PDLA or PLA and PDLA, heating this mixture up to 190 °C, above the melting temperature of these polylactide polymers, and cooling the mixture under crystallization.

It is also possible to produce the stereocomplex crystallites already distributed in the inventive composition by heating the composition containing as thermoplastic resin a) either PLLA or PLA and of the nucleating combination b) only the component  $\alpha$  1) and optionally the components  $\beta$  and  $\gamma$ ) up to a temperature of 190 °C, cooling the composition for crystallization, admixing the components  $\beta$  and  $\gamma$ ), if necessary.

It is known that the use of the stereocomplex crystallites speeds up the crystallization rate of the thermoformable resin a) and results in shorter cycle times in the production of shaped containers.

The reasonable mould time at the thermoforming temperature of about 95°C of the sheet should be preferably  $\geq$  1 to 5 sec., preferably < 5 sec., at mould temperatures respectively tool temperatures of about 100°C. With a mould time for the thermoformed container of less than the lower limit the crystallization of the thermoformed sheet or film containing the PLLA or PLA and the nucleating composition tends to be insufficient and by contrast by exceeding the upper limit the cycle times are not sufficient short.

In detail, the inventive thermoformed, essentially biobased and optionally biodegradable containers, especially food containers like cups or lids used as

closures, preferably for the complementary lids for the inventive containers, preferably for the cups, are produced in the following way preferably:

The inventive thermoformable composition containing the thermoformable resin a), PLLA or PLA, and the nucleating combination b), stored under dry conditions and mixed in an extruder, is extrusion molded through a flat dye into a sheet or optionally multilayered film according to cast extrusion preferably at a temperature of 180 °C at maximum. Such sheet or film is either stored intermediately and then thermoformed or in line thermoformed into containers, preferably cups, preferably by deep drawing, according to known methods like vacuum deep drawing or pressure deep drawing, optionally by means of a plug.

As far as such a multilayered film is used to manufacture inventive food containers, especially cups, the multilayered film, preferably a two-layered film, is prepared by cast extruding the inventive thermoformable composition containing a thermoformable resin a) and the nucleating composition b) as one layer and preferably as second layer a layer of a thermoformable resin consisting of PLLA or PLA, which becomes after the thermoforming into the containers, preferably into cups, the inside surface of the inventive containers, preferable of the cups, respectively the inner surface of lids being thermoformed of said film. After thermoforming by means of deep drawing, the containers or lids are separated, preferably cut out from the remaining sheet or film to obtain the single products, namely containers, like cups, or lids.

According to the thermoforming process by preferably cast extrusion, the extruded sheet respectively film is cooled to preferably at least 100°C, more preferably to a

temperature in a range of about 65°C to about 50°C, preferably by quenching, before it is thermoformed by deep drawing into the inventive containers, preferably cups, which are separated from the remaining sheet by cutting, preferably continuously.

The inventive thermoformed, essentially biodegradable containers, preferably the cups or lids, preferably thermoformed complementary lids, are not only essentially biobased and optionally biodegradable, but also have an excellent resistance against deformation up to a temperature of at least 93 °C and therefore can be used for providing hot liquid beverages without losing their shape.

In order to improve the handling of the inventive container, especially the inventive cup when filled with hot or cold liquids, especially beverages, at least part of the outside surface of the sidewall, preferably at least the area for gripping the container, especially the cup, are thermoformed circumferentially as corrugated surface with wavepeaks, extending in straight lines vertically to the bottom area of the container, preferably of the cup, for easier gripping and to improve hoop strength. Preferably, the height of each of these wavepeaks declines continuously from the gripping area to the bottom area of the container, especially the cup.

It is also possible to provide the inventive container, especially the inventive cup, with a handling help by arranging an external sleeve with such corrugated surface circumferentially around at least such part of the sidewall of an inventive container, especially inventive cup as described before. The corrugated surface of such sleeve functions as the outside surface of the container, respectively cup, after combining the sleeve with the container. Such sleeve can be thermoformed of an inventive composition as described before, of PLLA or PLA only or of cardboard.

Quite unexpected, the inventive thermoformed containers produced from the inventive compositions can be produced with a considerable, e.g. up to 20% improved yield especially at a temperature of about 100°C of the tool since the inventive thermoformable composition containing a thermoformable resin a) and the nucleating composition b) provides not only an increased rate of crystallization, but also provides an at least about 20% to 30% broader window for thermoforming in comparison to a thermoformable resin a) without any nucleating combination, which broader window for thermoforming allow improved short cycle times.

## Examples

### a) Container production

Each of the thermoformable compositions set forth in the following tables 1 and 2 were mixed and molded in an extruder at a temperature of about 190°C from the feed-in to the flat dye through which each molded composition was extruded as a sheet and cooled to about 50°C by means of calanders to a sheet with a thickness of 900 µm. Each sheet was converted into cups by means of a horizontally working deep drawing machine. Thereby, the sheet was thermoformed at a temperature of about 95°C into cups by means of a deep drawing equipment having a tool temperature of 100°C.

The thermoformed cups were cut out of the remaining sheet by conventional equipment continuously.

### b) Physical properties of the containers produced

Of each thermoformable composition set forth in the tables 1 and 2 the E-modulus was determined.

Accordingly the E-modulus was measured according to ISO 294-1. Therefore, flexural bars (4\*10\*80 mm) of each composition were produced by injection moulding with help of a DEMAG Ergotech NC IV 25-80 compact machine. Processing parameters were as usual. Samples were conditioned at least 1 week at 20°C, 50%RH prior to annealing the samples for 4 hours at 110 °C (between iron plates). Thereafter, the samples were inserted in a 93 °C test chamber to acclimatize for least 1 hour prior to testing. The E-modulus (3 pnt. bending) was determined using a Zwick Allround line 10kN mechanical testing machine according to ISO 178 with the specifications:

- Temperature: 93 °C
- E-Modulus speed: 1 mm/min
- Test speed for strength: 10 mm/min

The corresponding results are also set forth in the tables 1 and 2.

### c) Polymers used

A PLLA with less than 1% D-lactoyl-units has a  $M_n$  of  $152 \cdot 10^3$  g/mol (relative to PS standards measured by GPC [gel permeation chromatography] in chloroform) and a MFI of 4.5 +/- 0.3 [g/10 min] (190 °C/2.16kg) according to ASTM-D 1238 was used.

A PDLA was less than 1% of L-lactoyl-units and a  $M_n$  of  $120 \cdot 10^3$  g/mol (relative to PS standards measured by GPC in chloroform) and a MFI of 7.5 +/- 0.2 [g/10 min] (190°C/2.16kg) according to ASTM-D 1238 was used.

The PLA used is defined in table 2.

Table 1

Number	PLA type	D-lactoyl unit content	Nucleating Combination	E-modulus 1 mm/min [MPa] at 93°C	E-modulus 10 mm/min [MPa] at 93°C	Minimal moulding time needed (sec)
	polystyrene	-	-	330	908	
220710-V	PLLA	< 0.1 %	5 % PDLA	-	474	537
280311-IV	PLLA	<0.1%	5 % PDLA	20 % chalk	465	618
050711-V	PLLA	<0.1%	2,5% PDLA	-	450	525
050711-VI	PLLA	<0.1%	2.5 % PDLA 20% Kaolin	-		10
050711-VII	PLLA	<0.1%	2.5 % PDLA 20 % Kaolin	0.25 % talc	850	5
050711-VIII	PLLA	<0.1%	2.5 % PDLA 20 % Kaolin	0.5 % talc	850	2
					850	1

Masterbatch (MB) used: 72% PLLA + 3% PDLA + 25% talc

Table 2

Number	PLA type	D-lactoyl unit content	Nucleating Combination	E-modulus 1 mm/min [MPa] at 93°C	E-modulus 10 mm/min [MPa] at 93°C	Minimal moulding time needed (sec)
260308-X	PLA	1,4%	5 % PDLA	-	286	326
220611-IV	PLA	1,4%	3 % PDLA 20 % Kaolin	-	687	30
220611-VII	PLA	1,4%	3 % PDLA 20 % Kaolin	2 % talc (= 8 % MB)	710	20
050711-III	PLA	1,4%	3% PDLA 20% Kaolin	6% talc (=24% MB)	710	1

**Claims:**

1. A thermoformable composition containing
  - a) as thermoformable, biodegradable resin at least one poly-L-lactide with less than 1 mol% of D-lactoyl units (PLLA) or at least one poly-L-lactide with from 1 mol% to 5 mol% of D-lactoyl units (PLA) and
  - b) a nucleating combination consisting of
    - a) 1 to 10 % by weight, based on the total amount of the thermoformable resin a), of at least one poly-D-lactide with less than 1 mol% of L-lactoyl-units (PDLA) as component α 1) or of 0.5 to 5% by weight, based on the total amount of the thermoformable resin a), of PLLA/PDLA or PLA/PDLA stereocomplex crystallites, preferably with a molar ratio of 1:1, as component α 2),
    - β) 0.1 to 25% by weight, based on the total amount of the thermoformable resin a), of an inorganic nucleating agent, preferably talc, and
    - γ) 0.1 to 30 % by weight, based on the total amount of the thermoformable resin a), of at least an inorganic filler with lamellar structure, preferably a lamellar clay mineral.
2. A thermoformable composition as claimed in claim 1 wherein the thermoformable resin PLA is a copolymer of L-lactide units with up to 2,5 mol% D-lactoyl-units.

3. A thermoformable composition as claimed in claim 1 or 2 wherein the nucleating combination b) consists of 1 to 6% by weight of PDLA as component α 1) or of 0.5 to 3% by weight of stereocomplex crystallites PLLA/PDLA or of PLA/PDLA in a molar ratio of 1:1 as component α 2), of 1 to 20% by weight of talc as component β) and of 10 to 25% by weight of at least one lamellar clay mineral as component γ), each based on the total amount of the thermoforming resin a).
4. A thermoformable composition as claimed in anyone of the preceding claims wherein the talc has an aspect ratio of 2 to 150.
5. A thermoformable composition as claimed in claim 1 or 2, wherein the nucleating combination b) consists of 0.5 to 3% by weight of stereocomplex crystallites of PLLA/PDLA or PLA/PDLA in a molar ratio of 1:1 as component α 2), of 1 to 20% by weight of talc as component β) and of 10 to 25% by weight of at least one lamellar clay mineral as component γ), each based on the total amount of the thermoformable resin a).
6. A thermoformable composition as claimed in anyone of the preceding claims, wherein the lamellar clay mineral is a lamellar aluminum mineral, preferably kaolin.
7. A thermoformed, essentially biobased and optionally biodegradable container formed of a thermoformable composition as claimed in anyone of claims 1 to 6.

8. A thermoformed container as claimed in claim 7, wherein the container has a resistance against deformation up to a temperature of 100 °C.
9. A thermoformed container as claimed in claim 7 or 8, obtained by heating the composition containing as thermoplastic resin a) either PLLA or PLA and of the nucleating combination b) only the component  $\alpha$  1) and optionally the components  $\beta$  and  $\gamma$  up to a temperature of 190 °C, cooling the composition for crystallization, admixing the components  $\beta$  and  $\gamma$ , if necessary, and optionally reheating it up to a temperature of 190 °C at maximum for thermoforming.
10. A thermoformed container, preferably a cup, as claimed in anyone of the claims 7 to 9 obtained by molding, preferably by cast extrusion, the thermoformable composition as claimed in anyone of the claims 1 to 6 at a temperature of 180 °C at maximum into a sheet or optionally into a multilayered film, and by thermoforming said sheet or film by means of vacuum deep drawing or pressure deep drawing into containers, preferably into food containers, most preferably into cups, and optionally into complementary lids as closures of the containers.
11. A thermoformed container as claimed in anyone of the claims 7 to 10 wherein the container is an essentially biobased and optionally biodegradable container, preferably an essentially biobased and optionally biodegradable cup.

12. A thermoformed container according to anyone of claims 7 to 11 wherein the plastic container is a cup, preferably for hot beverages like coffee, tea or soups, preferably with a shape of its outside surface or means on its outside surface for easier gripping and improved hoop strength, optionally in combination with a complementary lid as closure.

13. A thermoformed, essentially biobased and optionally biodegradable lid formed of a thermoformable composition as claimed in anyone of claims 1 to 6.

14. Use of a thermoformed lid as claimed in claim 13 as closure for a thermoformed container, preferably a cup, as claimed in anyone of claims 7 to 12.

# INTERNATIONAL SEARCH REPORT

International application No  
PCT/EP2013/000665

**A. CLASSIFICATION OF SUBJECT MATTER**  
INV. C08K3/34 C08L67/04 B65D81/38  
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
C08L C08K B65D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>DATABASE WPI Week 200576 Thomson Scientific, London, GB; AN 2005-737816 XP002680613, -&amp; JP 2005 281331 A (TOYOTA CHUO KENKYUSHO KK) 13 October 2005 (2005-10-13) abstract paragraph [0019] paragraph [0030] - paragraph [0036] paragraph [0056] - paragraph [0057] examples 1-5; table 1</p> <p>-----</p> <p>US 2009/186178 A1 (ITO TAKUROU [JP] ET AL) 23 July 2009 (2009-07-23) paragraph [0045] - paragraph [0046] paragraph [0071] examples 1,2,4,9,10; table 1</p> <p>-----</p> <p>-/-</p>	1-14
X		1-14

Further documents are listed in the continuation of Box C.

See patent family annex.

\* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier application or patent but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
28 May 2013	07/06/2013
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer  Russell, Graham

## INTERNATIONAL SEARCH REPORT

International application No  
PCT/EP2013/000665

## C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2007/032631 A1 (OUCHI MAKOTO [JP] ET AL) 8 February 2007 (2007-02-08) paragraph [0053] - paragraph [0054] examples 1-7; table 1 comparative examples 7 & 8 paragraph [0105] -----	1-14
A	US 2009/035585 A1 (WAKAKI HIROYUKI [JP] ET AL) 5 February 2009 (2009-02-05) paragraph [0076] - paragraph [0077] paragraph [0113] - paragraph [0117] comparative examples 22 & 23; ; table 7 -----	1-14

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/EP2013/000665
---

Patent document cited in search report	Publication date	Patent family member(s)			Publication date
JP 2005281331	A 13-10-2005	JP 4470550 B2			02-06-2010
		JP 2005281331 A			13-10-2005
-----					
US 2009186178	A1 23-07-2009	EP 2025703 A1			18-02-2009
		JP 5157094 B2			06-03-2013
		JP 2008007736 A			17-01-2008
		US 2009186178 A1			23-07-2009
		WO 2007138842 A1			06-12-2007
-----					
US 2007032631	A1 08-02-2007	CN 1860178 A			08-11-2006
		EP 1681316 A1			19-07-2006
		JP 4358603 B2			04-11-2009
		JP 2005139270 A			02-06-2005
		US 2007032631 A1			08-02-2007
		WO 2005044918 A1			19-05-2005
-----					
US 2009035585	A1 05-02-2009	CN 101180362 A			14-05-2008
		EP 1867679 A1			19-12-2007
		KR 20070110535 A			19-11-2007
		US 2009035585 A1			05-02-2009
		WO 2006095923 A1			14-09-2006
-----					