

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
28 September 2006 (28.09.2006)

PCT

(10) International Publication Number
WO 2006/101955 A2

(51) International Patent Classification:
C08L 83/04 (2006.01) C08K 5/5415 (2006.01)

(74) Agents: BAUM, Allen, R. et al.; Hutchison Law Group
PLLC, P.O. Box 31686, Raleigh, NC 27612 (US).

(21) International Application Number:
PCT/US2006/009461

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV,
LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI,
NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG,
SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US,
UZ, VC, VN, YU, ZA, ZM, ZW.

(22) International Filing Date: 15 March 2006 (15.03.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
11/084,326 18 March 2005 (18.03.2005) US

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT,
RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA,
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (for all designated States except US): CLO-
SURE MEDICAL CORPORATION [US/US]; 5250
Greens Dairy Road, Raleigh, NC 27616 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): JONN, Jerry, Y.
[US/US]; 2308 Wakefield Plantation Drive, Raleigh, NC
27614 (US). MC CRUM, Brian [US/US]; 4128 Breadfruit
Court, Raleigh, NC 27616 (US). SU, Wendy [US/US];
4701 Malone Court, Raleigh, NC 27616 (US). WARREN,
Teresa [US/US]; 4513 Fawn Glen Drive, Raleigh, NC
27616 (US). BADEJO, Ibraheem, T. [US/US]; 4905
Summit Arbor Drive, Apt. 205, Raleigh, NC 27616 (US).

Published:

— without international search report and to be republished
upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: LIQUID COATING COMPOSITIONS

(57) Abstract: Liquid coating compositions are provided that comprise siloxane containing polymer, volatile polydimethylsiloxane, and aliphatic hydrocarbon. The liquid coating compositions preferably comprise from 18-55 weight % of volatile polydimethylsiloxane, from 5-55 weight % of aliphatic hydrocarbon, from 1-40 weight % of siloxane containing polymer, and from 0-15 weight % of adjuvant.

WO 2006/101955 A2

LIQUID COATING COMPOSITIONS

FIELD

[0001] The invention generally relates to liquid coating compositions that
5 comprise siloxane containing polymer, volatile polydimethylsiloxane, and aliphatic hydrocarbon.

BACKGROUND

[0002] Various liquid coating compositions are known. For example, U.S.
10 Patent Nos. 4,987,893 and 5,103,812 both relate to combinations of alkyl siloxy siloxane-containing polymers admixed with liquid polydimethylsiloxanes. The combinations are described as excellent non-stinging, non-irritating liquid coating material for forming films which act as conformable bandages adhering to and protecting nails, skin and mucous membrane wounds from abrasion, contamination,
15 and desiccation, while stopping pain from exposed nerve ends and allowing body fluid evaporation.

[0003] U.S. Patent No. 6,383,502 relates to compositions comprising 1-40% siloxane containing polymer; 60-99% of an alkane-based siloxy polymer reaction solvent, and 0-15% of adjuvants. The compositions are described as being useful for
20 application to the skin or as components in cosmetic or topical medicament compositions.

SUMMARY

[0004] In one aspect, a liquid coating composition is provided that comprises (a)
25 1-40 weight % of siloxane containing polymer; (b) 18-55 weight % of volatile polydimethylsiloxane; (c) 5-55 weight % of aliphatic hydrocarbon; and (d) 0-15 weight % of adjuvant.

[0005] In another aspect, a liquid coating composition is provided that
30 comprises (a) 1-40 weight % of siloxane containing polymer; (b) 20-55 weight % of volatile polydimethylsiloxane; (c) 15-55 weight % of aliphatic hydrocarbon; and (d) 0-15 weight % of adjuvant.

[0006] In yet another aspect, a liquid coating composition is provided that

comprises (a) 1-40 weight % of siloxane containing polymer; (b) 25-50 weight % of volatile polydimethylsiloxane; (c) 20-50 weight % of aliphatic hydrocarbon; and (d) 0-15 weight % of adjuvant.

[0007] In a further aspect, a liquid coating composition is provided that
5 comprises (a) 1-40 weight % of siloxane containing polymer; (b) 25-45 weight % of volatile polydimethylsiloxane; (c) 20-45 weight % of aliphatic hydrocarbon; and (d) 0-15 weight % of adjuvant.

[0008] In yet a further aspect, a liquid coating composition is provided that
10 comprises (a) 1-40 weight % of siloxane containing polymer; (b) 30-40 weight % of volatile polydimethylsiloxane; (c) 30-40 weight % of aliphatic hydrocarbon; and (d) 0-15 weight % of adjuvant.

[0009] In yet another aspect, a liquid coating composition is provided that
15 comprises (a) 1-40 weight % of siloxane containing polymer; (b) 30-40 weight % of hexamethyldisiloxane; (c) 30-40 weight % of isooctane; and (d) 0-15 weight % of adjuvant. The composition includes an adjuvant comprising a plasticizer.

DETAILED DESCRIPTION

[0010] The invention relates to liquid coating compositions that comprise
20 siloxane containing polymer, volatile polydimethylsiloxane, and aliphatic hydrocarbon. As explained herein, the liquid coating compositions are useful for protecting or treating skin, nails, and mucous membranes of a user as the liquid coating compositions, when applied to skin, nails, and/or mucous membranes of a user, dry to form a coating or film. The liquid coating compositions are preferably in the form of solutions.

25 [0011] The liquid coating compositions preferably comprise from 18-55 weight (wt.) % of volatile polydimethylsiloxane, from 5-55 wt. % of aliphatic hydrocarbon, from 1-40 wt. % of siloxane containing polymer, and from 0-15 wt. % of adjuvant. In some embodiments, the liquid coating compositions comprise from 20-55 wt. % of volatile polydimethylsiloxane, from 15-55 wt. % of aliphatic hydrocarbon, from
30 1-40 wt. % of siloxane containing polymer, and from 0-15 wt. % of adjuvant. In other embodiments, the liquid coating compositions comprise from 25-50 wt. % of volatile polydimethylsiloxane, from 20-50 wt. % of aliphatic hydrocarbon, from 1-

40 wt. % of siloxane containing polymer, and from 0-15 wt. % of adjuvant. In further embodiments, the liquid coating compositions comprise from 25-45 wt. % of volatile polydimethylsiloxane, from 20-45 wt. % of aliphatic hydrocarbon, from 1-40 wt. % of siloxane containing polymer, and from 0-15 wt. % of adjuvant. In yet
5 further embodiments, the liquid coating compositions comprise from 30-40 wt. % of volatile polydimethylsiloxane, from 30-40 wt. % of aliphatic hydrocarbon, from 1-40 wt. % of siloxane containing polymer, and from 0-15 wt. % of adjuvant. In any of these embodiments, the siloxane containing polymer may be present in the composition from 5-40 wt. %, 10-30 wt. %, or 15-25 wt. %, and the adjuvant may be
10 present in the composition from 0.01-10 wt. %, 0.1-8 wt. %, or 1-6 wt. %. In the various embodiments, the volatile polydimethylsiloxane, aliphatic hydrocarbon, siloxane containing polymer, and optional adjuvant are chosen to form 100 wt. % of the liquid coating compositions.

[0012] The volatile polydimethylsiloxane of the liquid coating compositions
15 may be any polydimethylsiloxane including, but not limited to, hexamethyl disiloxane (HMDS), octamethyl cyclotetrasiloxane, decamethyl cyclopentasiloxane, octamethyl trisiloxane, and mixtures of polydimethylsiloxanes. The preferred polydimethylsiloxane used in the compositions is HMDS.

[0013] The aliphatic hydrocarbon of the liquid coating compositions may be any
20 aliphatic hydrocarbon, including an alkane, a mixture of alkanes, an alkene, a mixture of alkenes, an alkyne, a mixture of alkynes, or a mixture thereof. The aliphatic hydrocarbon is preferably an alkane such as pentane, isooctane, or a mixture of alkanes. The aliphatic hydrocarbon is more preferably isooctane.

[0014] The siloxane containing polymer of the liquid coating compositions may
25 be a siloxane containing polymer as described in U.S. Patent Nos. 6,383,502, 5,103,812, and 4,987,893, which are hereby incorporated in their entirety by reference herein. As described in the patents, the siloxane containing polymers may comprise vinyl containing alkylsiloxysilanes alone or as co-, ter- or multi-
30 component polymers which can include other polymerizable monomers that do not make the polymers hydrophilic. Typical vinylalkylsiloxysilanes that may be utilized are:

3-methacryloyloxypropyltris(trimethylsiloxy)silane (TRIS);

3-methacryloyloxypropylpentamethyldisiloxane;
3-methacryloyloxypropylbis(trimethylsiloxy)methylsilane;
3-acryloyloxypropylmethylbis(trimethylsiloxy)silane;
3-acryloyloxypropyltris(trimethylsiloxy)silane; and others.

5 [0015] Typical addition polymerizable monomers which may be reacted with the vinylalkylsiloxysilanes to form multi component siloxane containing polymers are: acrylates including, but not limited to, methyl methacrylate, methyl acrylate, tetrahydrofurfuryl methacrylate, cyclohexyl acrylate, tetrahydrofurfuryl acrylate, n-lauryl acrylate, n-lauryl methacrylate, 2-phenoxyethyl acrylate, 2-phenoxyethyl
10 methacrylate, isodecyl acrylate, isodecyl methacrylate, isooctyl acrylate, isooctyl methacrylate, isobornyl acrylate, isobornyl methacrylate, benzyl methacrylate, 2-butoxyethyl acrylate, n-butyl acrylate, n-butyl methacrylate, ethyl acrylate, ethyl methacrylate, dimethyl itaconate, di-n butyl itaconate, 2-ethylhexyl acrylate, 2-ethylhexyl methacrylate, furfuryl methacrylate, n-hexyl acrylate, n-hexyl
15 methacrylate, isobutyl acrylate, isobutyl methacrylate, isopropyl methacrylate, n-octadecyl acrylate, n-octadecyl methacrylate, 2-phenylethyl methacrylate, and n-tridecyl methacrylate; and other polymerizable monomers including, but not limited to, alpha methyl styrene, styrene, p-t-butyl styrene, 4-methoxystyrene, vinyl benzoate, vinyl naphthalene. In addition, fluorinated siloxanes, fluorinated
20 itaconates, fluorinated methacrylates or acrylates, such as hexafluoroisopropyl methacrylate, may be used. Any hydrophobic polymerizable monomer may be used as long as the resulting copolymer has desired O₂ and H₂O vapor permeability. These additional polymerizable comonomers may be present in the siloxane containing polymer in amounts up to 0.85 mole fraction.

25 [0016] The siloxane containing polymers are preferably in proportions between about 15-100 mole % vinylalkylsiloxysilane, which component maintains the desired compatibility of the polymer in the volatile polydimethylsiloxane and aliphatic hydrocarbon, provides high moisture and oxygen permeability, and provides biocompatibility. A range of 20 to 40 mole % of the vinylalkylsiloxysilane
30 in the polymer is preferred. Other addition polymerizable monomers may be copolymerized with the vinylalkylsiloxysilanes between about 0-85% mole of the polymer composition to adjust permeability, adhesion, toughness, elasticity,

temperature stability, and impact resistance, among other film qualities.

[0017] The siloxane containing polymers are preferably at least partially soluble in the volatile polydimethylsiloxane and aliphatic hydrocarbon solvent system of the liquid coating compositions, and are more preferably completely soluble in the
5 volatile polydimethylsiloxane and aliphatic hydrocarbon solvent system of the liquid coating compositions.

[0018] The siloxane containing polymers may be linear, branched, or slightly cross-linked and can be homo, co-, ter- or multi polymers. They may be random copolymers or segmental in nature.

10 [0019] Typical vinylalkylsiloxysilane monomers that may be used in forming the siloxane containing polymer include those having the following formulas:



Where $\text{R}^1 = \text{H}, \text{CH}_3, \text{ or } \text{CH}_2\text{COOR}'$,

Where $\text{R}^2 = \text{alkyl (C}_1\text{-C}_4\text{) or } \text{CH}_2\text{CH}(\text{OH})\text{CH}_2$,

15 Where $\text{R}^3, \text{R}^4, \text{R}^5 = \text{OSi}(\text{Y})_3$, or alkyl (C₁-C₆),

Wherein, at least one of $\text{R}^3, \text{R}^4, \text{R}^5 = \text{OSi}(\text{Y})_3$

Where $\text{Y} = \text{alkyl (C}_1\text{-C}_6\text{), OSi}(\text{Z})_3 \text{ or } \text{R}_2\text{OOC}(\text{R}^1)\text{C}=\text{CH}_2$,

Where $\text{Z} = \text{alkyl (C}_1\text{-C}_6\text{) or aryl}$, and

Where $\text{R}' = \text{R}^2\text{SiR}^3\text{R}^4\text{R}^5$.

20 [0020] The siloxane containing polymers may have molecular weights from 50,000 to several million. The preferred molecular weight range is 50,000 to 500,000 weight average molecular weight. Lower molecular weight siloxane containing polymers have notably higher solubility in the solvents and solvent systems and hence, while they can be film formers, they generally are slow to dry
25 and remain tacky. The molecular weight of the siloxane containing polymers may be controlled by varying initiator, initiator concentration, reaction temperature, reaction solvent, and/or reaction method.

[0021] Preferably, the siloxane containing polymers are acrylate or methacrylate terpolymers having an "A" monomer component that is a silane derivative, a "B"
30 monomer component that when provided as a homopolymer would prepare a "hard" polymer, and a "C" monomer component that, when provided as a homopolymer would prepare a "soft" polymer. This mix of monomers provides the ability to

adjust mole fraction ratios to optimize oxygen permeability, ductility, moisture vapor transmissibility of the film and cost of materials. Highly durable coatings are particularly desired to enable the coating to remain on the skin for an extended time and to provide superior protection.

5 [0022] For the "A" monomer, examples of the silane derivatives are as described above. "B" monomers are "hard" where the corresponding homopolymer typically has a glass transition temperature (T_g) of more than about -5°C . Examples of such monomers are acrylate or methacrylate monomers, preferably C_1 - C_4 alkyl methacrylates. Most preferably, the hard monomer is methyl methacrylate. Other
10 examples of monomers that may be used for the hard monomer component are monomers having the requisite T_g values including methacrylates having a structure other than delineated above, such as benzyl methacrylate and isobornyl methacrylate methacrylamide such as N-t-butylmethacrylamide; acrylates such as isobornyl acrylate; acrylamides such as N-butylacrylamide and N-t-butylacrylamide; diesters
15 of unsaturated dicarboxylic acids such as diethyl itaconate and diethyl fumarate; vinyl nitrites such acrylonitrile and methacrylonitrile; vinyl esters such as vinyl acetate and vinyl propionate; and monomers containing an aromatic ring such as styrene; α -methyl styrene and vinyl toluene.

[0023] "C" monomers may be selected from monomers that form soft
20 homopolymers. "Soft" monomers are monomers where the corresponding homopolymer typically has a T_g of less than about 10°C ., provided that the hard monomer has a higher T_g than the soft monomer in each polymer. Such monomers may be C_4 - C_{12} alkyl acrylates and C_6 - C_{12} alkyl methacrylates, wherein the alkyl groups are straight, branched, or cyclic. Most preferably, the soft monomer is
25 selected from C_7 - C_{10} straight chain alkyl acrylates. Other examples of monomers that may be used for the soft monomer component are monomers having the requisite T_g values including dienes, such as butadiene and isoprene; acrylamides, such as N-octylacrylamide; vinyl ethers such as butoxyethylene, propyloxyethylene and octyl oxyethylene; vinyl halides, such as 1,1-dichloroethylene; and vinyl esters
30 such as vinyl caprate and vinyl laurate.

[0024] Most preferably, the siloxane-containing polymer comprises about 50 to 60 weight percent A monomer, 25-45 weight percent B monomer, and about 3 to 20

weight percent of C monomer. A specifically preferred embodiment is where the siloxane-containing polymer comprises about 50 to 60 weight percent of 3-methacryloxypropyl tris(trimethylsiloxy)silane, about 25 to 45 weight percent methyl methacrylate, and about 3 to 20 weight percent of a monomer selected from
5 C₇-C₁₀ straight chain or branched alkyl acrylates.

[0025] One variation in selection of monomers to be used in siloxane containing polymer is using more than one monomer within each category A, B, or C. For example, the polymer may comprise 57% 3-methacryloxypropyl tris(trimethylsiloxy)silane, 39% methyl methacrylate, 2% isooctyl acrylate and 2%
10 decyl acrylate. The last two monomers each satisfy the definition of the C monomer, and together provide the desired quantity of this component.

[0026] Any free radical initiator may be used in forming the siloxane containing polymers including azobisisobutyronitrile; 2,2'-azobis(2,4 dimethylpentane nitrile); 2,2'-azobis-(2-methylbutane nitrile); potassium persulfate; ammonium persulfate;
15 benzoyl peroxide; 2,5-dimethyl 2,5-bis(2-ethylhexanoylperoxy)hexane; and the like. The polymerization may be carried out by solution, emulsion, or suspension techniques. The polymers may be formed in solvents such as volatile polydimethylsiloxane, aliphatic hydrocarbons (e.g., alkanes), other solvents, or combinations thereof.

[0027] The adjuvant of the liquid coating composition may be one or more plasticizers, polar solvents (e.g., isopropyl alcohol), medicaments or other active agents, adhesion promoters, rheology additives, colorants, masking agents, other adjuvants, and mixtures thereof. In some embodiments, an adjuvant that does not include polar solvents is present in the liquid coating compositions.
20

[0028] Medicaments and other active agents that may be used as an adjuvant include, but are not limited to, antiseptic agents (e.g., benzalkonium chloride), anti-microbial agents, anti-fungal agents, anti-itch agents, anti-bacterial agents, antivirals, antitumor agents, blood pressure regulators, heart regulators, other active agents, and combinations thereof. Other types of active agents that may be desirable to
25 incorporate include plant growth regulators, DEET, citronella oil, plant insecticides, UV and IR absorbers, etc. When a medicament or other active agent (e.g., an antiseptic agent such as benzalkonium chloride) is included in the liquid coating
30

compositions, the medicament or other active agent is typically present in the compositions at 0.01-5.00 wt. %, although higher or lower amounts of medicaments and active agents may be used in the compositions.

5 [0029] The liquid coating compositions preferably contain a plasticizer as an adjuvant to provide flexibility to the film deposited on the skin. Plasticizers used as the adjuvant may include acetyl tributyl citrate, acetyl triethyl citrate, tributyl citrate, triethyl citrate, acetyl tripropyl citrate, tripropyl citrate, dibutyl sebacate, acetyl dibutyl sebacate, dipropyl sebacate, acetyl dipropyl sebacate, diethyl sebacate, acetyl diethyl sebacate, other plasticizers, and mixtures thereof. Other plasticizers may be
10 used, including homologues and derivatives of these esters. When the liquid coating compositions include a plasticizer, the plasticizer is typically present in the composition at 1-3 wt. %, preferably at 1.60-2.25 wt. %, although higher or lower amounts of plasticizer may be used in the compositions.

15 [0030] Other typical plasticizer/adhesion promoters are dibutylphthalate, sucrose acetate isobutyrate, sucrose benzoate, mineral oil, decamethyl cyclopentasiloxane, octamethyl cyclotetrasiloxane, butyl glycolate, and others. Typical rheology additives that may be utilized are fumed silica, such as Cab-o-sil® fumed silica, bentonite and other clay derivatives, and saturated fatty acids, such as hydrated ricinoleic acid.

20 [0031] Coloring or masking agents that may be used as an adjuvant include dyes and pigments.

[0032] In one embodiment, the liquid coating compositions include an adjuvant comprising a plasticizer, a medicament or other active agent (e.g., an antiseptic agent such as benzalkonium chloride), and optionally a polar solvent. The optional
25 polar solvent may be useful for dissolving the medicament or other active agent for formulation in the liquid coating composition. The polar solvents, when present, are preferably present in the composition at 1-3 wt. %, more preferably 1.2-3.0 wt. %, although more or less of the polar solvents may be used.

[0033] In a preferred embodiment, the adjuvant of the liquid coating
30 compositions comprises a plasticizer that is present in the composition at 1-3 wt. %, more preferably at 1.60-2.25 wt. %; an antiseptic such as benzalkonium chloride that is present in the composition at 0.10-0.15 wt. %; and a polar solvent such as

isopropanol that is present in the composition at 1-3 wt. %, more preferably 1.2-3.0 wt %. In such embodiments, the antiseptic may be dissolved in the polar solvent for formulation in the liquid coating compositions.

5 [0034] The liquid coating compositions, when applied to skin, nails, and/or mucous membranes of a user, dry to form a coating or film. The coatings or films may be useful for protecting or treating skin, nails, and mucous membranes (e.g., skin cuts, abrasions, incisions and blisters; dry cracked skin; abraded gums and other oral surfaces; hemorrhoids and abraded body areas; inflamed digestive tract; other mucosal membrane incisions and wounds). The films formed from the liquid
10 coating composition may act as conformable bandages adhering to and protecting nails, skin and mucous membrane wounds from abrasion, contamination, and desiccation, as the liquid coating compositions may provide for a fast drying, flexible, waterproof, breathable, non-stinging liquid adhesive coating or bandage.

[0035] When medicaments or other active agents are included in the liquid
15 coating compositions, the coatings formed by the compositions may be used to administer the medicaments or other active agents to the targeted site.

[0036] The liquid coating compositions preferably act at room temperature (20° C.) when applied to skin, nails, and/or mucous membranes of a user to form films, preferably in minutes or less. The films are preferably conformable and comfortable
20 and may be elastic and flexible. The films preferably do not irritate the skin and mucous membrane when sprayed or deposited in any way during application and in use after drying. The bandages are preferably substantially painless and easily removable substantially without pain. The dried bandages formed from the liquid coating compositions are also preferably substantially non-water sensitive and
25 waterproof and preferably have high water vapor and oxygen gas transmission therethrough. The bandages preferably form when applied over surfaces wet with water, blood or body fluids, in short times at standard room temperature and reasonable variants thereof. The liquid composition and/or dried polymer film may have various medicaments or other agents incorporated therein for maintaining
30 sterility and/or for release to the underlying area of the body of a user.

[0037] The liquid coating compositions may be applied to the skin, nails, mucous membranes, etc. in liquid form by utilization of an applicator, such as a

brush, rod, finger, sponge, cloth, dropper, etc; in spray or mist form; or any other usable technique for applying a liquid to a surface. Preferably, the liquid coating compositions are non-stinging.

5 [0038] Medicaments and other active agents may be incorporated into the liquid or solid, dried film bandages for ready or continual release as the bandages formed from the liquid coating compositions may provide an inert, longlasting, highly permeable film that may contain medicaments or other active agents to be applied to the skin, mucous membranes and other body areas on which it is desired to release the active agent over an extended period of time.

10 [0039] The liquid coating compositions may be used for applications other than medical body care. For instance, the coating could be used as a water repellent, yet H₂O vapor permeable, film applied to sanitary napkins, diapers, or panties. With the incorporation of fungicides, the coating could be used to cover grout in tiled surfaces. The liquid coating compositions may further be useful as a sunscreen with
15 the incorporation of UV absorbers. Still other uses include forming films for use in eliminating chapped lips, treating skin and internal body surfaces, and providing protection to skin and other surfaces which may be medicated prior to application.

[0040] As discussed above, the siloxane containing polymer may be manufactured in one or more of the solvents used in the final formulation of the
20 liquid coating compositions, in other solvents, and/or in combinations thereof. The liquid coating composition may be formulated by using the siloxane containing polymer in the mixture in which it was manufactured or by isolating the polymer from the mixture in which it was manufactured and then formulating the liquid coating composition. The liquid coating compositions may be formulated, e.g., by
25 mixing the siloxane containing polymer (with or without the solvent in which it was manufactured), the volatile polydimethylsiloxane, the aliphatic hydrocarbon, and the optional adjuvant. In embodiments where the siloxane containing polymer is manufactured in volatile polydimethylsiloxane and/or aliphatic hydrocarbon, it may not be necessary to add more of such solvent(s) when formulating the liquid coating
30 composition.

EXAMPLES

[0041] The invention will be further explained by the following illustrative examples that are intended to be non-limiting.

Example 1—Synthesis of Polymer

- 5 [0042] A 1L resin flask with overhead stirrer, N₂ outlet, condenser and thermocouple under a nitrogen atmosphere was charged with 455 mL of isooctane, 111.3 g (0.263 mol) of methacryloxypropyl tris(trimethylsiloxy)silane (TRIS), 81.9 g (0.818 mol) of methyl methacrylate, 16.8 g (0.091 mol) of isooctyl acrylate and 0.315g of VAZO®-67 free radical initiator (obtained from DuPont). The reaction
- 10 mixture was heated to 75°C and held at that temperature for 24 hours. During the hold at 75°C, two additional amounts of 0.153 g of VAZO®-67 free radical initiator dissolved in 8 g of isooctane were added to the reaction mixture at 12 hours and at 18 hours, respectively. After the 24 hours at 75°C, the reaction mixture was heated to 100°C and maintained at 100°C for 6 hours, for a total reaction time of 30 hours.
- 15 The reaction mixture was then cooled to room temperature. The reaction produced a solution with a siloxane containing polymer.

Example 2—Formulation of siloxane containing polymer as liquid coating composition

- 20 [0043] 8.7 g of hexamethyldisiloxane (HMDS) was added to a flask containing 23.7 g (63.3% solid) of siloxane containing polymer prepared in Example 1. 64.4 g of diluent (HMDS:isooctane 50:50 wt/wt) was added to the flask and the mixture was stirred at room temperature. 1.6 g of dibutyl sebacate was added and the mixture was stirred until it dissolved. The resulting liquid adhesive coating
- 25 composition contained 15% siloxane containing polymer solid.

Example 3—Formulation of siloxane containing polymer as liquid coating composition with bioactive agent

- [0044] 8.7 g of hexamethyldisiloxane (HMDS) was added to a flask containing
- 30 23.7 g (63.3% solid) of siloxane containing polymer prepared in Example 1. 64.4 g of diluent (HMDS:isooctane 50:50 wt/wt) was added to the flask and the mixture was stirred at room temperature. 0.106g of benzalkonium chloride dissolved in 1.5

g of isopropanol and 1.6 g of dibutyl sebacate were added to the flask and the mixture was stirred until complete dissolution and clarity. The resulting liquid adhesive coating composition contained 15% siloxane containing polymer solid and 0.1% antiseptic agent.

- 5 [0045] While the invention has been described in detail and with reference to specific embodiments thereof, it will be apparent to one skilled in the art that various changes and modifications can be made without departing from the spirit and scope of the invention.

WHAT IS CLAIMED IS:

1. A liquid coating composition comprising:
 - (a) 1-40 weight % of siloxane containing polymer;
 - 5 (b) 18-55 weight % of volatile polydimethylsiloxane;
 - (c) 5-55 weight % of aliphatic hydrocarbon; and
 - (d) 0-15 weight % of adjuvant.

2. The composition of claim 1, wherein the volatile polydimethylsiloxane is
10 selected from the group consisting of hexamethyldisiloxane, octamethyl
cyclotetrasiloxane, decamethyl cyclopentasiloxane, octamethyl trisiloxane, and
mixtures thereof.

3. The composition of claim 2, wherein the volatile polydimethylsiloxane is
15 hexamethyldisiloxane.

4. The composition of claim 1, wherein the aliphatic hydrocarbon is selected
from the group consisting of alkane, alkene, alkyne, and mixtures thereof.

- 20 5. The composition of claim 4, wherein the aliphatic hydrocarbon is an
alkane selected from the group consisting of pentane, isooctane, and mixtures
thereof.

6. The composition of claim 5, wherein the alkane is isooctane.
25

7. The composition of claim 1, wherein the adjuvant is selected from the
group consisting of plasticizers, antiseptics, polar solvents, anti-microbial agents,
anti-fungal agents, anti-itch agents, anti-bacterial agents, antivirals, antitumor
agents, adhesion promoters, rheology additives, colorants, masking agents, and
30 mixtures thereof.

8. The composition of claim 1, wherein the siloxane containing polymer comprises an A monomer component that is a silane derivative, a B monomer component that forms a hard polymer when polymerized as a homopolymer, and a C monomer component that forms a soft polymer when polymerized as a
5 homopolymer.

9. The composition of claim 8, wherein the siloxane containing polymer comprises about 50 to 60 weight % of the A monomer, about 25 to 45 weight % of the B monomer, and about 3 to 20 weight % of the C monomer.
10

10. The composition of claim 9, wherein the A monomer is 3-methacryloyloxypropyl tris(trimethylsiloxy)silane, the B monomer is methyl methacrylate, and the C monomer is isooctyl acrylate.

11. The composition of claim 1, wherein the composition comprises 20-55 weight % of volatile polydimethylsiloxane and 15-55 weight % of aliphatic hydrocarbon.
15

12. A liquid coating composition comprising:
20 (a) 1-40 weight % of siloxane containing polymer;
(b) 25-50 weight % of volatile polydimethylsiloxane;
(c) 20-50 weight % of aliphatic hydrocarbon; and
(d) 0-15 weight % of adjuvant.

13. The composition of claim 12, wherein the volatile polydimethylsiloxane is hexamethyldisiloxane.
25

14. The composition of claim 12, wherein the aliphatic hydrocarbon is isooctane.
30

15. The composition of claim 12, wherein the siloxane containing polymer comprises about 50 to 60 weight % of 3-methacryloyloxypropyl

tris(trimethylsiloxy)silane, about 25 to 45 weight % of methyl methacrylate, and about 3 to 20 weight % of isooctyl acrylate.

16. The composition of claim 12, wherein the adjuvant is selected from the
5 group consisting of plasticizers, antiseptics, polar solvents, anti-microbial agents, anti-fungal agents, anti-itch agents, anti-bacterial agents, antivirals, antitumor agents, adhesion promoters, rheology additives, colorants, masking agents, and mixtures thereof.

10 17. The composition of claim 12, wherein the volatile polydimethylsiloxane is hexamethyldisiloxane and the aliphatic hydrocarbon is isooctane.

18. The composition of claim 17, wherein the siloxane containing polymer
15 comprises about 50 to 60 weight % of 3-methacryloyloxypropyl tris(trimethylsiloxy)silane, about 25 to 45 weight % of methyl methacrylate, and about 3 to 20 weight % of the isooctyl acrylate.

19. The composition of claim 12, wherein the composition comprises 25-45
20 weight % of volatile polydimethylsiloxane and 20-45 weight % of aliphatic hydrocarbon.

20. The composition of claim 19, wherein:
the volatile polydimethylsiloxane is hexamethyldisiloxane;
the aliphatic hydrocarbon is isooctane; and
25 the siloxane containing polymer comprises about 50 to 60 weight % of 3-methacryloyloxypropyl tris(trimethylsiloxy)silane, about 25 to 45 weight % of methyl methacrylate, and about 3 to 20 weight % of isooctyl acrylate.

21. A liquid coating composition comprising:
30 (a) 1-40 weight % of siloxane containing polymer;
(b) 30-40 weight % of volatile polydimethylsiloxane;
(c) 30-40 weight % of aliphatic hydrocarbon; and

(d) 0-15 weight % of adjuvant.

22. The composition of claim 21, wherein the volatile polydimethylsiloxane is hexamethyldisiloxane.

5

23. The composition of claim 21, wherein the aliphatic hydrocarbon is isooctane.

24. The composition of claim 21, wherein the siloxane containing polymer
10 comprises about 50 to 60 weight % of 3-methacryloyloxypropyl
tris(trimethylsiloxy)silane, about 25 to 45 weight % of methyl methacrylate, and
about 3 to 20 weight % of isooctyl acrylate.

25. The composition of claim 21, wherein the adjuvant is selected from the
15 group consisting of plasticizers, antiseptics, polar solvents, anti-microbial agents,
anti-fungal agents, anti-itch agents, anti-bacterial agents, antivirals, antitumor
agents, adhesion promoters, rheology additives, colorants, masking agents, and
mixtures thereof.

20 26. The composition of claim 21, wherein:
the volatile polydimethylsiloxane is hexamethyldisiloxane;
the aliphatic hydrocarbon is isooctane; and
the siloxane containing polymer comprises about 50 to 60 weight % of 3-
methacryloyloxypropyl tris(trimethylsiloxy)silane, about 25 to 45 weight % of
25 methyl methacrylate, and about 3 to 20 weight % of isooctyl acrylate.

27. A liquid coating composition comprising:

(a) 1-40 weight % of siloxane containing polymer;

(b) 30-40 weight % of hexamethyldisiloxane;

30 (c) 30-40 weight % of isooctane; and

(d) 0-15 weight % of adjuvant,

wherein the composition includes an adjuvant comprising a plasticizer.

28. The composition of claim 27, wherein the adjuvant of the composition further comprises an antiseptic and a polar solvent.

5 29. The composition of claim 27, wherein the plasticizer is present in the composition at 1-3 weight %.

30. The composition of claim 28, wherein the antiseptic is benzalkonium chloride and the polar solvent is isopropanol.

10

31. The composition of claim 28, wherein the antiseptic is present in the composition at 0.10-0.15 weight %.

32. The composition of claim 31, wherein the polar solvent is present in the
15 composition at 1-3 weight %.

33. The composition of claim 27, wherein:
the adjuvant of the composition further comprises an antiseptic and a polar
solvent,

20

the plasticizer is present in the composition at 1-3 weight %,
the antiseptic is present in the composition at 0.10-0.15 weight %, and
the polar solvent is present in the composition at 1-3 weight %.

34. The composition of claim 33, wherein the composition is in the form of
25 a solution.

35. The composition of claim 27, wherein the siloxane containing polymer
comprises about 50 to 60 weight % of 3-methacryloyloxypropyl
tris(trimethylsiloxy)silane, about 25 to 45 weight % of methyl methacrylate, and
30 about 3 to 20 weight % of isooctyl acrylate.