

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
2 November 2006 (02.11.2006)

PCT

(10) International Publication Number
WO 2006/116765 A2(51) International Patent Classification:
A61N 1/05 (2006.01)(21) International Application Number:
PCT/US2006/016655

(22) International Filing Date: 28 April 2006 (28.04.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/676,008 28 April 2005 (28.04.2005) US
11/207,644 19 August 2005 (19.08.2005) US(71) Applicant (for all designated States except US): **SECOND SIGHT MEDICAL PRODUCTS, INC.** [US/US]; 12744 San Fernando Road, Building 3, Sylmar, California 91342 (US).

(72) Inventors; and


(75) Inventors/Applicants (for US only): **GREENBERG, Robert Jay** [US/US]; 2431 Wild Oak Drive, Los Angeles, California 90068 (US). **TALBOT, Neil** [US/US]; 2254 Mira Vista, Apt. 6, Montrose, California 91020 (US). **NEYSMITH, Jordan** [CA/US]; 350 S. Oakland Ave. #107, Pasadena, California 91101 (US). **LITTLE, James S.** [US/US]; 21674 Agajania Lane, Saugus, California 91101 (US). **MECH, Brian, V.** [US/US]; 25061Riverwalk Lane, Stevenson Ranch, California 91381 (US). **HUMAYAN, Mark** [US/US]; 2757 Sleepy Hollow Place, Glendale, California 91206 (US). **GUVEN, Dilek** [TR/TR]; KIZILIRMAK MOH, 36 Cad, 2/29, Yuzuncu Yil, 06520 Ankara (TR). **RIPLEY, Ann Marie de Merlier** [US/US]; 3921 Melbourne Avenue, Los Angeles, California 90027 (US).(74) Agents: **DUNBAR, Scott B** et al.; SECOND SIGHT MEDICAL PRODUCTS, INC., 12744 San Fernando Road, Building 3, Sylmar, California 91342 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),

[Continued on next page]

(54) Title: FLEXIBLE CIRCUIT ELECTRODE ARRAY



(57) Abstract: Polymer materials are useful as electrode array bodies for neural stimulation. They are particularly useful for retinal stimulation to create artificial vision, cochlear stimulation to create artificial hearing, or cortical stimulation many purposes. The pressure applied against the retina, or other neural tissue, by an electrode array is critical. Too little pressure causes increased electrical resistance, along with electric field dispersion. Too much pressure may block blood flow. Common flexible circuit fabrication techniques generally require that a flexible circuit electrode array be made flat. Since neural tissue is almost never flat, a flat array will necessarily apply uneven pressure. Further, the edges of a flexible circuit polymer array may be sharp and cut the delicate neural tissue. By applying the right amount of heat to a completed array, a curve can be induced. With a thermoplastic polymer it may be further advantageous to repeatedly heat the flexible circuit in multiple molds, each with a decreasing radius. Further, it is advantageous to add material along the edges. It is further advantageous to provide a fold or twist in the flexible circuit array. Additional material may be added inside and outside the fold to promote a good seal with tissue.



European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- *as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))*
- *as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))*

— *of inventorship (Rule 4.17(iv))*

Published:

- *without international search report and to be republished upon receipt of that report*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Flexible Circuit Electrode Array

Cross-Reference to Related Applications

This application is a Continuation-In-Part of U.S. Application No. 11/207,644, filed August 19, 2005 which claims the benefit of U.S. Provisional
5 Application No. 60/676,008, "Thin Film Electrode Array", filed April 28, 2005, the disclosures of both are incorporated herein by reference.

Government Rights Notice

This invention was made with government support under grant No. R24EY12893-01, awarded by the National Institutes of Health. The government
10 has certain rights in the invention.

Field of the Invention

The present invention is generally directed to neural stimulation and more specifically to an improved electrode array for neural stimulation.

Background of the Invention

15 In 1755 LeRoy passed the discharge of a Leyden jar through the orbit of a man who was blind from cataract and the patient saw "flames passing rapidly downwards." Ever since, there has been a fascination with electrically elicited visual perception. The general concept of electrical stimulation of retinal cells to
20 produce these flashes of light or phosphenes has been known for quite some time. Based on these general principles, some early attempts at devising prostheses for aiding the visually impaired have included attaching electrodes to the head or eyelids of patients. While some of these early attempts met with some limited success, these early prosthetic devices were large, bulky and could
25 not produce adequate simulated vision to truly aid the visually impaired.

In the early 1930's, Foerster investigated the effect of electrically stimulating the exposed occipital pole of one cerebral hemisphere. He found that, when a point at the extreme occipital pole was stimulated, the patient

perceived a small spot of light directly in front and motionless (a phosphene). Subsequently, Brindley and Lewin (1968) thoroughly studied electrical stimulation of the human occipital (visual) cortex. By varying the stimulation parameters, these investigators described in detail the location of the phosphenes produced relative to the specific region of the occipital cortex stimulated. These experiments demonstrated: (1) the consistent shape and position of phosphenes; (2) that increased stimulation pulse duration made phosphenes brighter; and (3) that there was no detectable interaction between neighboring electrodes which were as close as 2.4 mm apart.

As intraocular surgical techniques have advanced, it has become possible to apply stimulation on small groups and even on individual retinal cells to generate focused phosphenes through devices implanted within the eye itself. This has sparked renewed interest in developing methods and apparatus to aid the visually impaired. Specifically, great effort has been expended in the area of intraocular retinal prosthesis devices in an effort to restore vision in cases where blindness is caused by photoreceptor degenerative retinal diseases; such as retinitis pigmentosa and age related macular degeneration which affect millions of people worldwide.

Neural tissue can be artificially stimulated and activated by prosthetic devices that pass pulses of electrical current through electrodes on such a device. The passage of current causes changes in electrical potentials across visual neuronal membranes, which can initiate visual neuron action potentials, which are the means of information transfer in the nervous system.

Based on this mechanism, it is possible to input information into the nervous system by coding the sensory information as a sequence of electrical pulses which are relayed to the nervous system via the prosthetic device. In this way, it is possible to provide artificial sensations including vision.

One typical application of neural tissue stimulation is in the rehabilitation of the blind. Some forms of blindness involve selective loss of the light sensitive

transducers of the retina. Other retinal neurons remain viable, however, and may be activated in the manner described above by placement of a prosthetic electrode device on the inner (toward the vitreous) retinal surface (epiretinal). This placement must be mechanically stable, minimize the distance between the device electrodes and the visual neurons, control the electronic field distribution and avoid undue compression of the visual neurons.

In 1986, Bullara (US Pat. No. 4,573,481) patented an electrode assembly for surgical implantation on a nerve. The matrix was silicone with embedded iridium electrodes. The assembly fit around a nerve to stimulate it.

Dawson and Radtke stimulated cat's retina by direct electrical stimulation of the retinal ganglion cell layer. These experimenters placed nine and then fourteen electrodes upon the inner retinal layer (i.e., primarily the ganglion cell layer) of two cats. Their experiments suggested that electrical stimulation of the retina with 30 to 100 μ A current resulted in visual cortical responses. These experiments were carried out with needle-shaped electrodes that penetrated the surface of the retina (see also US Pat. No. 4,628,933 to Michelson).

The Michelson '933 apparatus includes an array of photosensitive devices on its surface that are connected to a plurality of electrodes positioned on the opposite surface of the device to stimulate the retina. These electrodes are disposed to form an array similar to a "bed of nails" having conductors which impinge directly on the retina to stimulate the retinal cells. US Patent 4,837,049 to Byers describes spike electrodes for neural stimulation. Each spike electrode pierces neural tissue for better electrical contact. US Patent 5,215,088 to Norman describes an array of spike electrodes for cortical stimulation. Each spike pierces cortical tissue for better electrical contact.

The art of implanting an intraocular prosthetic device to electrically stimulate the retina was advanced with the introduction of retinal tacks in retinal surgery. De Juan, et al. at Duke University Eye Center inserted retinal tacks into retinas in an effort to reattach retinas that had detached from the underlying

choroid, which is the source of blood supply for the outer retina and thus the photoreceptors. See, e.g., E. de Juan, et al., 99 Am. J. Ophthalmol. 272 (1985). These retinal tacks have proved to be biocompatible and remain embedded in the retina, and choroid/sclera, effectively pinning the retina against the choroid and the posterior aspects of the globe. Retinal tacks are one way to attach a retinal electrode array to the retina. US Patent 5,109,844 to de Juan describes a flat electrode array placed against the retina for visual stimulation. US Patent 5,935,155 to Humayun describes a retinal prosthesis for use with the flat retinal array described in de Juan.

Summary of the Invention

Polymer materials are useful as electrode array bodies for neural stimulation. They are particularly useful for retinal stimulation to create artificial vision, cochlear stimulation to create artificial hearing, or cortical stimulation for many purposes. Regardless of which polymer is used, the basic construction method is the same. A layer of polymer is laid down, commonly by some form of chemical vapor deposition, spinning, meniscus coating or casting. A layer of metal, preferably platinum, is applied to the polymer and patterned to create electrodes and leads for those electrodes. Patterning is commonly done by photolithographic methods. A second layer of polymer is applied over the metal layer and patterned to leave openings for the electrodes, or openings are created later by means such as laser ablation. Hence the array and its supply cable are formed of a single body. Alternatively, multiple alternating layers of metal and polymer may be applied to obtain more metal traces within a given width.

The pressure applied against the retina, or other neural tissue, by an electrode array is critical. Too little pressure causes increased electrical resistance between the array and retina, along with electric field dispersion. Too much pressure may block blood flow causing retinal ischemia and hemorrhage. Pressure on the neural retina may also block axonal flow or cause neuronal

atrophy leading to optic atrophy. Common flexible circuit fabrication techniques such as photolithography generally require that a flexible circuit electrode array be made flat. Since the retina is spherical, a flat array will necessarily apply more pressure near its edges, than at its center. Further, the edges of a flexible circuit polymer array may be quite sharp and cut the delicate retinal tissue. With most polymers, it is possible to curve them when heated in a mold. By applying the right amount of heat to a completed array, a curve can be induced that matches the curve of the retina. With a thermoplastic polymer such as liquid crystal polymer, it may be further advantageous to repeatedly heat the flexible circuit in multiple molds, each with a decreasing radius. Further, it is advantageous to add material along the edges of a flexible circuit array. Particularly, it is advantageous to add material that is more compliant than the polymer used for the flexible circuit array.

It is further advantageous to provide a fold or twist in the flexible circuit array at the point where it passes through the sclera. Additional material may be added inside and outside the fold to promote a good seal with the scleral tissue.

The novel features of the invention are set forth with particularity in the appended claims. The invention will be best understood from the following description when read in conjunction with the accompanying drawings.

Brief Description of the Drawings

FIG. 1 is a perspective view of the implanted portion of the preferred retinal prosthesis.

FIG. 2 is a side view of the implanted portion of the preferred retinal prosthesis showing the fan tail in more detail.

FIG. 3A – 3 E depict molds for forming the flexible circuit array in a curve.

FIG. 4 depicts an alternate view of the invention with ribs to help maintain curvature and prevent retinal damage.

FIG. 5 depicts an alternate view of the invention with ribs to help maintain curvature and prevent retinal damage fold of the flexible circuit cable and a fold A between the circuit electrode array and the flexible circuit cable.

FIG. 6 depicts a cross-sectional view of the prosthesis shown insight of the eye with an angle in the fold of the flexible circuit cable and a fold between the circuit electrode array and the flexible circuit cable.

FIG. 7 depicts the implanted portion including a twist in the array to reduce the width of a sclerotomy and a sleeve to promote sealing of the sclerotomy.

FIG. 8 depicts the flexible circuit array before it is folded and attached to the implanted portion.

FIG. 9 depicts the flexible circuit array folded.

FIG. 10 depicts a flexible circuit array with a protective skirt.

FIG. 11 depicts a flexible circuit array with a protective skirt bonded to the back side of the flexible circuit array.

FIG. 12 depicts a flexible circuit array with a protective skirt bonded to the front side of the flexible circuit array.

FIG. 13 depicts a flexible circuit array with a protective skirt bonded to the back side of the flexible circuit array and molded around the edges of the flexible circuit array.

FIG. 14 depicts a flexible circuit array with a protective skirt bonded to the back side of the flexible circuit array and molded around the edges of the flexible circuit array and flush with the front side of the array.

FIG. 15 is an enlarged view of a single electrode within the flexible circuit electrode array.

FIG. 16 depicts the flexible circuit array before it is folded and attached to the implanted portion containing an additional fold between the flexible electrode array and the flexible cable.

FIG. 17 depicts the flexible circuit array of FIG. 16 folded containing an additional fold between the flexible electrode array and the flexible cable.

FIG. 18 depicts a flexible circuit array of FIG. 17 with a protective skirt and containing an additional fold between the flexible electrode array and the flexible
5 cable.

FIG. 19 depicts a top view of a flexible circuit array and flexible circuit cable showing an additional horizontal angel between the flexible electrode array and the flexible cable.

FIG. 20 depicts another variation without the horizontal angel between the
10 flexible electrode array and the flexible cable but with an orientation of the electrodes in the flexible electrode array as shown for the variation in FIG. 19.

FIG. 21 depicts a top view of a flexible circuit array and flexible circuit cable wherein the array contains a slit along the length axis.

FIG. 22 depicts a top view of a flexible circuit array and flexible circuit
15 cable wherein the array contains a slit along the length axis with a two attachment points.

FIG. 23 depicts a flexible circuit array with a protective skirt bonded to the back side of the flexible circuit array with a progressively decreasing radius.

FIG. 24 depicts a flexible circuit array with a protective skirt bonded to the
20 front side of the flexible circuit array with a progressively decreasing radius.

FIG. 25 depicts a flexible circuit array with a protective skirt bonded to the back side of the flexible circuit array and molded around the edges of the flexible circuit array with a progressively decreasing radius.

FIG. 26 depicts a flexible circuit array with a protective skirt bonded to the
25 back side of the flexible circuit array and molded around the edges of the flexible circuit array and flush with the front side of the array with a progressively decreasing radius.

FIG. 27 depicts a side view of the flexible circuit array with a skirt containing a grooved and rippled pad instead a suture tab.

FIG. 28 depicts a side view of the enlarged portion of the skirt shown in FIG. 27 containing a grooved and rippled pad and a mattress suture.

FIG. 29 depicts a flexible circuit array with a protective skirt bonded to the front side of the flexible circuit array with individual electrode windows.

5 FIG. 30 depicts a flexible circuit array with a protective skirt bonded to the back side of the flexible circuit array and molded around the edges of the flexible circuit array with individual electrode windows.

FIGS. 31-36 show several surfaces to be applied on top of the cable.

10 FIG. 37 depicts the top view of the flexible circuit array being enveloped within an insulating material.

FIG. 38 depicts a cross-sectional view of the flexible circuit array being enveloped within an insulating material.

15 FIG. 39 depicts a cross-sectional view of the flexible circuit array being enveloped within an insulating material with open electrodes and the material between the electrodes.

FIG. 40 depicts a cross-sectional view of the flexible circuit array being enveloped within an insulating material with open electrodes.

20 FIG. 41 depicts a cross-sectional view of the flexible circuit array being enveloped within an insulating material with electrodes on the surface of the material.

FIG. 42 depicts a cross-sectional view of the flexible circuit array being enveloped within an insulating material with electrodes on the surface of the material insight the eye with an angle in the fold of the flexible circuit cable and a fold between the circuit electrode array and the flexible circuit cable.

25 FIG. 43 depicts a side view of the enlarged portion of the flexible circuit array being enveloped within an insulating material with electrodes on the surface of the material insight the eye.

FIG.44 shows of front view of a cochlear electrode array according to the present invention.

FIG. 45 shows a side view of a cochlear electrode array according to the present invention.

FIG. 46 shows a cochlear electrode array according to the present invention as implanted in the cochlea.

5

Detailed Description of the Preferred Embodiments

The following description is of the best mode presently contemplated for carrying out the invention. This description is not to be taken in a limiting sense, but is made merely for the purpose of describing the general principles of the invention. The scope of the invention should be determined with reference to the claims.

Fig. 1 shows a perspective view of the implanted portion of the preferred retinal prosthesis. A flexible circuit 1 includes a flexible circuit electrode array 10 which is mounted by a retinal tack (not shown) or similar means to the epiretinal surface. The flexible circuit electrode array 10 is electrically coupled by a flexible circuit cable 12, which pierces the sclera and is electrically coupled to an electronics package 14, external to the sclera.

The electronics package 14 is electrically coupled to a secondary inductive coil 16. Preferably the secondary inductive coil 16 is made from wound wire. Alternatively, the secondary inductive coil 16 may be made from a flexible circuit polymer sandwich with wire traces deposited between layers of flexible circuit polymer. The electronics package 14 and secondary inductive coil 16 are held together by a molded body 18. The molded body 18 may also include suture tabs 20. The molded body 18 narrows to form a strap 22 which surrounds the sclera and holds the molded body 18, secondary inductive coil 16, and electronics package 14 in place. The molded body 18, suture tabs 20 and strap 22 are preferably an integrated unit made of silicone elastomer. Silicone elastomer can be formed in a pre-curved shape to match the curvature of a typical sclera. However, silicone remains flexible enough to accommodate

implantation and to adapt to variations in the curvature of an individual sclera. The secondary inductive coil 16 and molded body 18 are preferably oval shaped. A strap 22 can better support an oval shaped coil.

It should be noted that the entire implant is attached to and supported by the sclera. An eye moves constantly. The eye moves to scan a scene and also has a jitter motion to improve acuity. Even though such motion is useless in the blind, it often continues long after a person has lost their sight. By placing the device under the rectus muscles with the electronics package in an area of fatty tissue between the rectus muscles, eye motion does not cause any flexing which might fatigue, and eventually damage, the device.

Fig. 2 shows a side view of the implanted portion of the retinal prosthesis, in particular, emphasizing the fan tail 24. When implanting the retinal prosthesis, it is necessary to pass the strap 22 under the eye muscles to surround the sclera. The secondary inductive coil 16 and molded body 18 must also follow the strap 22 under the lateral rectus muscle on the side of the sclera. The implanted portion of the retinal prosthesis is very delicate. It is easy to tear the molded body 18 or break wires in the secondary inductive coil 16. In order to allow the molded body 18 to slide smoothly under the lateral rectus muscle, the molded body 18 is shaped in the form of a fan tail 24 on the end opposite the electronics package 14.

The flexible circuit 1 is made by the following process. First, a layer of polymer (such as polyimide, fluoro-polymers, silicone or other polymers) is applied to a support substrate (not part of the array) such as glass. Layers may be applied by spinning, meniscus coating, casting, sputtering or other physical or chemical vapor deposition, or similar process. Subsequently, a metal layer is applied to the polymer. The metal is patterned by photolithographic process. Preferably, a photo-resist is applied and patterned by photolithography followed by a wet etch of the unprotected metal. Alternatively, the metal can be patterned by lift-off technique, laser ablation or direct write techniques.

It is advantageous to make this metal thicker at the electrode and bond pad to improve electrical continuity. This can be accomplished through any of the above methods or electroplating. Then, the top layer of polymer is applied over the metal. Openings in the top layer for electrical contact to the electronics package 14 and the electrodes may be accomplished by laser ablation or reactive ion etching (RIE) or photolithograph and wet etch. Making the electrode openings in the top layer smaller than the electrodes promotes adhesion by avoiding delaminating around the electrode edges.

The pressure applied against the retina by the flexible circuit electrode array is critical. Too little pressure causes increased electrical resistance between the array and retina. It should be noted that while the present invention is described in terms of application to the retina, the techniques described are equally applicable to many forms of neural stimulation. Application to the retina requires a convex spherical curve. Application to the cochlea requires a constant curve in one dimension and a spiral curve in the other. Application to the cerebral cortex requires a concave spherical curve. Cortical stimulation is useful for artificial vision or hearing, touch and motor control for limb prostheses, deep brain stimulation for Parkinson's disease and multiple sclerosis, and many other applications.

Common flexible circuit fabrication techniques such as photolithography generally require that a flexible circuit electrode array be made flat. Since the retina is spherical, a flat array will necessarily apply more pressure near its edges, than at its center. With most polymers, it is possible to curve them when heated in a mold. By applying the right amount of heat to a completed array, a curve can be induced that matches the curve of the retina. To minimize warping, it is often advantageous to repeatedly heat the flexible circuit in multiple molds, each with a decreasing radius. Fig. 3 illustrates a series of molds according to the preferred embodiment. Since the flexible circuit will maintain a constant length, the curvature must be slowly increased along that length. As the

curvature 30 decreases in successive molds (Figs. 3A – 3E) the straight line length between ends 32 and 34, must decrease to keep the length along the curvature 30 constant, where mold 3E approximates the curvature of the retina or other desired neural tissue. The molds provide a further opening 36 for the
5 flexible circuit cable 12 of the array to exit the mold without excessive curvature.

It should be noted that suitable polymers include thermoplastic materials and thermoset materials. While a thermoplastic material will provide some stretch when heated a thermoset material will not. The successive molds are, therefore, advantageous only with a thermoplastic material. A thermoset
10 material works as well in a single mold as it will with successive smaller molds. It should be noted that, particularly with a thermoset material, excessive curvature in three dimensions will cause the polymer material to wrinkle at the edges. This can cause damage to both the array and the retina. Hence, the amount of curvature is a compromise between the desired curvature, array surface area,
15 and the properties of the material.

Referring to Fig. 4, the edges of the polymer layers are often sharp. There is a risk that the sharp edges of a flexible circuit will cut into delicate retinal tissue. It is advantageous to add a soft material, such as silicone, to the edges of a flexible circuit electrode array to round the edges and protect the retina.
20 Silicone around the entire edge may make the flexible circuit less flexible. So, it is advantageous to provide silicone bumpers or ribs to hold the edge of the flexible circuit electrode array away from the retinal tissue. Curvature 40 fits against the retina. The leading edge 44 is most likely to cause damage and is therefore fit with molded silicone bumper. Also, edge 46, where the array lifts off
25 the retina can cause damage and should be fit with a bumper. Any space along the side edges of curvature 40 may cause damage and may be fit with bumpers as well. It is also possible for the flexible circuit cable 12 of the electrode array to contact the retina. It is, therefore, advantageous to add periodic bumpers along the flexible circuit cable 12.

It is also advantageous to create a reverse curve or service loop in the flexible circuit cable 12 of the flexible circuit electrode array to gently lift the flexible circuit cable 12 off the retina and curve it away from the retina, before it pierces the sclera at a sclerotomy. It is not necessary to heat curve the service
5 loop as described above, the flexible circuit electrode array can simply be bent or creased upon implantation. This service loop reduces the likelihood of any stress exerted extraocularly from being transmitted to the electrode region and retina. It also provides for accommodation of a range of eye sizes.

With existing technology, it is necessary to place the implanted control
10 electronics outside of the sclera, while a retinal flexible circuit electrode array must be inside the sclera in order to contact the retina. The sclera is cut through at the pars plana, forming a sclerotomy, and the flexible circuit passed through the sclerotomy. A flexible circuit is thin but wide. The more electrode wires, the wider the flexible circuit must be. It may be difficult to seal a sclerotomy over a
15 flexible circuit wide enough to support enough wires for a high resolution array. A narrow sclerotomy is preferable.

Fig. 5 depicts a further embodiment of the part of the prosthesis shown in Fig. 4 with a fold A between the circuit electrode array 10 and the flexible circuit cable 12. The angle in the fold A also called ankle has an angle of 1° - 180° ,
20 preferably 80° - 120° . The fold A is advantageous since it reduces tension and enables an effective attachment of the flexible electrode circuit array 10 to the retina.

Fig. 6 depicts a side view of the prosthesis insight of the eye with an angle K of the flexible circuit cable 12 and a fold A between the circuit electrode array
25 10 and the flexible circuit cable 12. The angle K is about 45° - 180° and preferably 80° - 100° . The fold K also called knee is advantageous because it decreases pressure which would be applied by the flexible circuit cable 10.

Fig. 7 shows the implanted portion of the retinal prosthesis including the additional feature of a gentle twist or fold 48 in the flexible circuit cable 12, where

the flexible circuit cable 12 passes through the sclera (sclerotomy). The twist may be a simple sharp twist, or fold 48; or it may be a longer twist, forming a tube. While the tube is rounder, it reduces the flexibility of the flexible circuit. A simple fold 48 reduces the width of the flexible circuit with only minimal impact on flexibility.

Further, silicone or other pliable substance may be used to fill the center of the tube or fold 48 formed by the twisted flexible circuit cable 12. Further it is advantageous to provide a sleeve or coating 50 that promotes healing of the sclerotomy. Polymers such as polyimide, which may be used to form the flexible circuit cable 12 and flexible circuit electrode array 10, are generally very smooth and do not promote a good bond between the flexible circuit cable 12 and scleral tissue. A sleeve or coating of polyester, collagen, silicone, Gore-tex or similar material would bond with scleral tissue and promote healing. In particular, a porous material will allow scleral tissue to grow into the pores promoting a good bond.

Alternatively, the flexible circuit electrode array 10 may be inserted through the sclera, behind the retina and placed between the retina and choroid to stimulate the retina subretinally. In this case, it is advantageous to provide a widened portion, or stop, of the flexible circuit cable 12 to limit how far the flexible circuit electrode array is inserted and to limit the transmission of stress through the sclera. The stop may be widening of the flexible circuit 1 or it may be added material such as a bumper or sleeve.

Human vision provides a field of view that is wider than it is high. This is partially due to fact that we have two eyes, but even a single eye provides a field of view that is approximately 90° high and 140° to 160° degrees wide. It is therefore, advantageous to provide a flexible circuit electrode array 10 that is wider than it is tall. This is equally applicable to a cortical visual array. In which case, the wider dimension is not horizontal on the visual cortex, but corresponds to horizontal in the visual scene.

Fig. 8 shows the flexible circuit electrode array prior to folding and attaching the array to the electronics package 14. At one end of the flexible circuit cable 12 is an interconnection pad 52 for connection to the electronics package 14. At the other end of the flexible circuit cable 12 is the flexible circuit electrode array 10. Further, an attachment point 54 is provided near the flexible circuit electrode array 10. A retina tack (not shown) is placed through the attachment point 54 to hold the flexible circuit electrode array 10 to the retina. A stress relief 55 is provided surrounding the attachment point 54. The stress relief 55 may be made of a softer polymer than the flexible circuit, or it may include cutouts or thinning of the polymer to reduce the stress transmitted from the retina tack to the flexible circuit electrode array 10. The flexible circuit cable 12 is formed in a dog leg pattern so that when it is folded at fold 48 it effectively forms a straight flexible circuit cable 12 with a narrower portion at the fold 48 for passing through the sclerotomy.

Fig. 9 shows the flexible circuit electrode array after the flexible circuit cable 12 is folded at the fold 48 to form a narrowed section. The flexible circuit cable 12 may include a twist or tube shape as well. With a retinal prosthesis as shown in Fig. 1, the bond pad 52 for connection to the electronics package 14 and the flexible circuit electrode array 10 are on opposite side of the flexible circuit. This requires patterning, in some manner, both the base polymer layer and the top polymer layer. By folding the flexible circuit cable 12 of the flexible circuit electrode array 10, the openings for the bond pad 52 and the electrodes are on the top polymer layer and only the top polymer layer needs to be patterned.

Also, since the narrowed portion of the flexible circuit cable 12 pierces the sclera, shoulders formed by opposite ends of the narrowed portion help prevent the flexible circuit cable 12 from moving through the sclera. It may be further advantageous to add ribs or bumps of silicone or similar material to the

shoulders to further prevent the flexible circuit cable 12 from moving through the sclera.

Further it is advantageous to provide a suture tab 56 in the flexible circuit body near the electronics package to prevent any movement in the electronics package from being transmitted to the flexible circuit electrode array 10. Alternatively, a segment of the flexible circuit cable 12 can be reinforced to permit it to be secured directly with a suture.

An alternative to the bumpers described in Fig. 4, is a skirt of silicone or other pliable material as shown in Figs. 10, 11, 12, and 13. A skirt 60 covers the flexible circuit electrode array 10, and extends beyond its edges. It is further advantageous to include wings 62 adjacent to the attachment point 54 to spread any stress of attachment over a larger area of the retina. There are several ways of forming and bonding the skirt 60. The skirt 60 may be directly bonded through surface activation or indirectly bonded using an adhesive.

Alternatively, a flexible circuit electrode array 10 may be layered using different polymers for each layer. Using too soft of a polymer may allow too much stretch and break the metal traces. Too hard of a polymer may cause damage to delicate neural tissue. Hence a relatively hard polymer, such a polyimide may be used for the bottom layer and a relatively softer polymer such a silicone may be used for the top layer including an integral skirt to protect delicate neural tissue.

The simplest solution is to bond the skirt 60 to the back side (away from the retina) of the flexible circuit electrode array 10 as shown in Fig. 11. While this is the simplest mechanical solution, sharp edges of the flexible circuit electrode array 10 may contact the delicate retina tissue. Bonding the skirt to the front side (toward the retina) of the flexible circuit electrode array 10, as shown in Fig. 12, will protect the retina from sharp edges of the flexible circuit electrode array 10. However, a window 62 must be cut in the skirt 60 around the electrodes. Further, it is more difficult to reliably bond the skirt 60 to the flexible

circuit electrode array 10 with such a small contact area. This method also creates a space between the electrodes and the retina which will reduce efficiency and broaden the electrical field distribution of each electrode. Broadening the electric field distribution will limit the possible resolution of the flexible circuit electrode array 10.

Fig. 13 shows another structure where the skirt 60 is bonded to the back side of the flexible circuit electrode array 10, but curves around any sharp edges of the flexible circuit electrode array 10 to protect the retina. This gives a strong bond and protects the flexible circuit electrode array 10 edges. Because it is bonded to the back side and molded around the edges, rather than bonded to the front side, of the flexible circuit electrode array 10, the portion extending beyond the front side of the flexible circuit electrode array 10 can be much smaller. This limits any additional spacing between the electrodes and the retinal tissue.

Fig. 14 shows a flexible circuit electrode array 10 similar to Fig. 13, with the skirt 60, flush with the front side of the flexible circuit electrode array 10 rather than extending beyond the front side. While this is more difficult to manufacture, it does not lift the electrodes off the retinal surface as with the array in Fig. 10. It should be noted that Figs. 11, 13, and 14 show skirt 60 material along the back of the flexible circuit electrode array 10 that is not necessary other than for bonding purposes. If there is sufficient bond with the flexible circuit electrode array 10, it may advantageous to thin or remove portions of the skirt 60 material for weight reduction.

Referring to Fig. 15, the flexible circuit electrode array 10 is manufactured in layers. A base layer of polymer 70 is laid down, commonly by some form of chemical vapor deposition, spinning, meniscus coating or casting. A layer of metal 72 (preferably platinum) is applied to the polymer base layer 70 and patterned to create electrodes 74 and traces for those electrodes. Patterning is commonly done by photolithographic methods. The electrodes 74 may be built

up by electroplating or similar method to increase the surface area of the electrode 74 and to allow for some reduction in the electrodes 74 over time.

Similar plating may also be applied to the bond pads 52 (fig. 8-10). A top polymer layer 76 is applied over the metal layer 72 and patterned to leave openings for the electrodes 74, or openings are created later by means such as laser ablation. It is advantageous to allow an overlap of the top polymer layer 76 over the electrodes 74 to promote better adhesion between the layers, and to avoid increased electrode reduction along their edges. The overlapping top layer promotes adhesion by forming a clamp to hold the metal electrode between the two polymer layers. Alternatively, multiple alternating layers of metal and polymer may be applied to obtain more metal traces within a given width.

FIG. 16 depicts the flexible circuit array 12 before it is folded and attached to the implanted portion containing an additional fold A between the flexible electrode array 12 and the flexible cable 10. The angle in the fold A also called ankle has an angle of 1° - 180° , preferably 80° - 120° . The ankle is advantageous in the process of inserting the prostheses in the eye and attaching it to the retina.

FIG. 17 depicts the flexible circuit array 12 FIG. 16 folded containing an additional fold A between the flexible electrode array 12 and the flexible cable 10. The flexible circuit array as shown in FIGS. 8 and 16 differ by the fold A from each other.

FIG. 18 depicts a flexible circuit array of FIG. 17 with a protective skirt 60 and containing an additional fold A between the flexible electrode array and the flexible cable. The flexible circuit array as shown in FIGS. 10 and 18 differ by the fold A from each other.

FIG. 19 depicts a top view of a flexible circuit array and flexible circuit cable showing the additional horizontal angle H between the flexible electrode array 12 and the flexible cable 10. The angle H is from about 1° to about 90° and preferably from about 30° to about 60° .

FIG. 20 depicts another variation without the horizontal angle H between the flexible electrode array 12 and the flexible cable 10 but with an orientation of the electrodes in the flexible electrode array 12 as shown in FIG. 19 for a flexible electrode array 12. The grid of electrodes 13 has the angle H with the flexible
5 cable which can be the same as the angle H in the flexible electrode array 12 of FIG. 19.

Both variation shown in FIGS. 19 and 20 have the advantage that the electrodes are oriented horizontally if they are inserted into the eye. Further, both variations as shown in FIGS. 19 and 20 can also additionally contain a fold
10 K.

FIG. 21 depicts a top view of a flexible circuit array and flexible circuit cable as shown in FIGS. 10 and 18 wherein the array contains a slit along the length axis.

FIG. 22 depicts a skirt of silicone or other pliable material as shown in Fig. 10 to 14. A skirt 60 covers the flexible circuit electrode array 10, and extends
15 beyond its edges. In this embodiment of the present invention the flexible circuit electrode array contains a slit 80 along the length axis. Further, according to this embodiment the skirt of silicone or other pliable material contains preferably at least two attachment points 81 and stress reliefs 82 are provided surrounding
20 the attachment points 81. The attachment points 81 are located preferably on the skirt 60 outside the flexible circuit electrode 10 and are positioned apart as far as possible from each other. The two tacks 81 are far enough apart not to cause tenting, therefore fibrosis between the two tacks which cause a traction detachment of the retina. Furthermore, the polyimide is completely between the
25 two tacks, which also reduce the possibility of tenting. Also, this orientation of tacks keeps the tacks away from the axons, which arise from the ganglion cells which are tried to be activated. They are away from the retina. The wings act like external tabs or strain relieves. The multiple tacks prevent rotation of the array.

The stress relief 82 may be made of a softer polymer than the flexible circuit, or it may include cutouts or thinning of the polymer to reduce the stress transmitted from the retina tack to the flexible circuit electrode array 10.

FIG. 23 depicts a flexible circuit array 10 with a protective skirt 60 bonded to the back side of the flexible circuit array 10 with a progressively decreasing radius.

FIG. 24 depicts a flexible circuit array 10 with a protective skirt 60 bonded to the front side of the flexible circuit array 10 with a progressively decreasing radius.

FIG. 25 depicts a flexible circuit array 10 with a protective skirt 60 bonded to the back side of the flexible circuit array 10 and molded around the edges of the flexible circuit array with a progressively decreasing radius.

FIG. 26 depicts a flexible circuit array 10 with a protective skirt 60 bonded to the back side of the flexible circuit array 10 and molded around the edges of the flexible circuit array and flush with the front side of the array with a progressively decreasing radius.

FIG. 27 depicts a side view of the array with a skirt 60 containing a grooved and rippled pad 56a instead a suture tab 56. This pad 56a has the advantage of capturing a mattress suture 57. A mattress suture 57 has the advantage of holding the grove or rippled pad 56a in two places as shown in FIG. 28. Each suture 57 is fixed on the tissue on two places 59. A mattress suture 57 on a grooved or rippled mattress 56a therefore provides a better stability.

FIG. 29 depicts a flexible circuit array 10 with a protective skirt 60 bonded to the front side of the flexible circuit array 10 with individual electrode windows and with material, preferably silicon between the electrodes 13.

FIG. 30 depicts a flexible circuit array with a protective skirt bonded to the back side of the flexible circuit array and molded around the edges of the flexible

circuit array with individual electrode windows and with material, preferably silicon between the electrodes 13.

FIGS 31-36 show several surfaces to be applied on top of the cable. The surfaces are thin films containing a soft polymer, preferably silicone. FIG. 31 shows a flange 15: A flange 15 can be a solid film of material containing silicone added to the surface of the polymer containing polyimide. FIGS. 32-34 show a ladder 15a: A ladder 15a is a flange with material removed from central portions in some shape 19. FIG. 35 shows a skeleton structure 15b. A skeleton 15b is a flange with material removed from perimeter portions in some shape 21. FIG. 36 shows a structure 15c with beads 23 and bumpers 25. A bead 23 is material added to perimeter portions of the polymer cable in some shape without material being added on the central area. A bumper 25 can be an extended or continuous version of the beaded approach. Both approaches are helpful in preventing any possible injury of the tissue by the polymer.

FIG. 37 depicts the top view of the flexible circuit array 10 being enveloped within an insulating material 11. The electrode array 10 comprises oval-shaped electrode array body 10, a plurality of electrodes 13 made of a conductive material, such as platinum or one of its alloys, but that can be made of any conductive biocompatible material such as iridium, iridium oxide or titanium nitride. The electrode array 10 is enveloped within an insulating material 11 that is preferably silicone. "Oval-shaped" electrode array body means that the body may approximate either a square or a rectangle shape, but where the corners are rounded. This shape of an electrode array is described in the U.S. Patent Application No. 20020111658, entitled "Implantable retinal electrode array configuration for minimal retinal damage and method of reducing retinal stress" and No. 20020188282, entitled "Implantable drug delivery device" to Rober J. Greenberg et al., the disclosures of both are incorporated herein by reference.

The material body 11 is made of a soft material that is compatible with the electrode array body 10. In a preferred embodiment the body 11 made of

silicone having hardness of about 50 or less on the Shore A scale as measured with a durometer. In an alternate embodiment the hardness is about 25 or less on the Shore A scale as measured with a durometer.

FIG. 38 depicts a cross-sectional view of the flexible circuit array 10 being
5 enveloped within an insulating material 11. It shows how the edges of the material body 11 are lift off due to the contracted radius. The electrode array 10 preferably also contains a fold A between the cable 12 and the electrode array 10. The angle of the fold A secures a relief of the implanted material.

FIG. 39 depicts a cross-sectional view of the flexible circuit array 10 being
10 enveloped within an insulating material 11 with open electrodes 13 and the material 11 between the electrodes 13. This embodiment also has relief between the body 10 and the retinal R.

FIG. 40 depicts a cross-sectional view of the flexible circuit array 10 being
enveloped within an insulating material 11 with open electrodes 13. This is
15 another embodiment wherein the electrodes 13 are not separated by the material 11 but the material 11 is extended so that the electrodes 13 are prevented of direct contact with the retina R.

FIG. 41 depicts a cross-sectional view of the flexible circuit array 10 being
enveloped within an insulating material 11 with electrodes 13 on the surface of
20 the material 11. This is a further embodiment with the electrode 13 on the surface of the material 11, preferably silicone. The embodiments shown in FIGS. 39, 40, and 41 show a preferred body 11 containing silicone with the edges being lift off from the retina due to contracted radius of the silicon body 11.

FIG. 42 depicts a cross-sectional view of the flexible circuit array 10 being
25 enveloped within an insulating material 11 with electrodes 13 on the surface of the material 11 insight the eye with an angle K in the fold of the flexible circuit cable 12 and a fold A between the circuit electrode array 10 and the flexible circuit cable 12. The material 11 and electrode array body 10 are in intimate contact with retina R. The surface of electrode array body 10 in contact with

retina R is a curved surface with a contracted radius compared to the spherical curvature of retina R to minimize stress concentrations therein. Further, the decreasing radius of spherical curvature of material 11 near its edge forms edge relief that causes the edges of the body 11 to lift off the surface of retina R eliminating stress concentrations. The edges of body 11 are strongly lifted off due to the contracted radius of the body 11. The edge of body 11 has a rounded edge eliminating stress and cutting of retina R.

FIG. 43 shows a part of the FIG. 42 enlarged showing the electrode array 10 and the electrodes 13 enveloped by the polymer material, preferably silicone 11 being attached to the retina R.

The electrode array 10 embedded in or enveloped by the polymer material, preferably silicone 11 can be preferably produced through the following steps. The soft polymer material which contains silicone is molded into the designed shape and partially hardened. The electrode array 10 which preferably contains polyimide is introduced and positioned in the partially hardened soft polymer containing silicone. Finally, the soft polymer 11 containing silicone is fully hardened in the designed shape enveloping the electrode array 10. The polymer body 11 has a shape with a contracted radius compared with the retina R so that the edges of the body 11 lift off from the retina R.

Figs. 44 – 46 show application of the present invention to a cochlear prosthesis. Figure 44 shows of front view of cochlear electrode array 110. The cochlear electrode array 110 tapers toward the top to fit in an ever smaller cochlea and because less width is required toward the top for metal traces. The electrodes 174 are arranged linearly along the length of the array 110. Further a skirt 160 of more compliant polymer, such as silicone surrounds the array 110. Figure 45 is a side view of the cochlear electrode array 110. The cochlear electrode array 110 includes a bottom polymer layer 170, metal traces 172 and a top polymer layer 176. Openings in the top polymer layer 176 define electrodes 174.

The cochlear electrode array 110 is made flat as shown in figures 44 and 13B. It is then thermoformed, as described above, into a spiral shape to approximate the shape of the cochlea, as shown in Figure 46. The cochlear electrode array 110 is implanted with the bottom layer 170 formed toward the outside of the curvature, and the top polymer layer 176 toward the inside of the curvature. This is opposite of the thermoforming process used for a retinal array. A cortical array would be thermoformed to curve inward like a cochlear array.

Accordingly, what has been shown is an improved method making a neural electrode array and improved method of stimulating neural tissue. While the invention has been described by means of specific embodiments and applications thereof, it is understood that numerous modifications and variations could be made thereto by those skilled in the art without departing from the spirit and scope of the invention. It is therefore to be understood that within the scope of the claims, the invention may be practiced otherwise than as specifically described herein.

Claims:

1. A flexible circuit electrode array comprising:
a polymer base layer;
metal traces deposited on said polymer base layer, including electrodes
5 suitable to stimulate neural tissue; and
a polymer top layer deposited on said polymer base layer and said metal
traces.
2. The flexible circuit electrode array according to claim 1, wherein said
10 polymer base layer, said metal traces and said polymer top layer are curved
to approximately the curvature of an eye.
3. The flexible circuit electrode array according to claim 1, wherein said
polymer base layer, said metal traces and said polymer top layer are
15 thermoformed in a three dimensional shape.
4. The flexible circuit electrode array according to claim 1, further comprising
at least one bumper bonded to a peripheral edge of said flexible circuit
electrode array.
20
5. The flexible circuit electrode array according to claim 1, further comprising a
narrowed portion in a flexible circuit cable portion of said flexible circuit
electrode array.
- 25 6. The flexible circuit electrode array according to claim 1, wherein said
polymer top layer is a more compliant polymer than said polymer base
layer.

7. The flexible circuit electrode array according to claim 1, further comprising a stress relief membrane suitable for attachment of said flexible circuit electrode array, wherein said stress relief membrane is a more compliant material than said polymer base layer.
- 5 8. The flexible circuit electrode array according to claim 1, further comprising a narrowed portion in a flexible circuit cable portion of said flexible circuit electrode array.
- 10 9. The flexible circuit electrode array according to claim 8, wherein said narrowed portion is suitable to pierce a sclera.
10. The flexible circuit electrode array according to claim 1, further comprising diagonal fold in a flexible circuit cable portion of said flexible circuit electrode array.
- 15 11. The flexible circuit electrode array according to claim 10, where said diagonal fold is across a dogleg in said flexible circuit electrode array.
- 20 12. The flexible circuit electrode array according to claim 10, further comprising bond pads coupled to said metal traces on an end of said flexible circuit electrode array opposite to said electrodes and openings in said polymer top layer for said electrodes and said bond pads.
- 25 13. The flexible circuit electrode array according to claim 10, wherein said fold forms a narrowed portion.
14. The flexible circuit electrode array according to claim 1, further comprising a widened portion of a flexible circuit cable portion of said flexible circuit

electrode array suitable to resist movement of said flexible circuit electrode array.

- 5 15. The flexible circuit electrode array according to claim 14 wherein said flexible circuit electrode array is suitable to be implanted in an eye and said widened portion is suitable to resist movement of said flexible circuit electrode array through a sclera.
- 10 16. The flexible circuit electrode array according to claim 1, further comprising a bumper bonded to a peripheral edge of said flexible circuit electrode array.
- 15 17. The flexible circuit electrode array according to claim 16, further comprising at least one bumper bonded to a flexible circuit cable portion of said flexible circuit electrode array.
18. The flexible circuit electrode array according to claim 17, where said bumper is a continuous skirt covering at least of portion of said flexible circuit electrode array.
- 20 19. The flexible circuit electrode array according to claim 17, where said bumper is a continuous skirt covering at least of portion of a cable portion of said flexible circuit electrode array.
- 25 20. The flexible circuit electrode array according to claim 16, further comprising a sleeve at least partially covering a flexible circuit cable portion of said flexible circuit electrode array.
21. The flexible circuit electrode array according to claim 20, wherein said sleeve and said bumper are a continuous body.

22. The flexible circuit electrode array according to claim 1, wherein said polymer base layer, said metal traces and said polymer top layer for a continuous electrode array and flexible circuit cable where said flexible circuit cable forms a partial loop to resist transmission of forces through said flexible circuit cable.
23. The flexible circuit electrode array according to claim 1, wherein said polymer top layer defines openings smaller than said electrodes to overlap said electrodes.
24. The flexible circuit electrode array according to claim 1, wherein a polymer top layer is deposited on said polymer base layer and said metal traces; and wherein said polymer base layer, said metal traces and said polymer top layer are thermoformed in a three dimensional shape.
25. The flexible circuit electrode array according to claim 1, wherein the flexible circuit cable portion has a bend with an angle of about 45° to about 180°.
26. The flexible circuit electrode array according to claim 25, wherein the flexible circuit cable portion has a bend with an angle of about 60° to about 120°.
27. The flexible circuit electrode array according to claim 24, wherein the flexible circuit cable portion has a fold with the attached flexible circuit electrode array with an angle of about 1° to about 180°.
28. The flexible circuit electrode array according to claim 27, wherein the flexible circuit cable portion has a fold with the attached flexible circuit electrode array with an angle of about 20° to about 90°.

29. The flexible circuit electrode array according to claim 1, wherein the flexible circuit cable portion has a horizontal angle with the attached flexible circuit electrode array with an angle of about 1° to about 90°.
- 5 30. The flexible circuit electrode array according to claim 29, wherein the flexible circuit cable portion has a horizontal angle with the attached flexible circuit electrode array with an angle of about 10° to about 45°.
- 10 31. The flexible circuit electrode array according to claim 1, wherein the flexible circuit cable portion has a horizontal angle with the line of electrodes in the attached flexible circuit electrode array with an angle of about 1° to about 90°.
- 15 32. The flexible circuit electrode array according to claim 31, wherein the flexible circuit cable portion has a horizontal angle with the line of electrodes in the attached flexible circuit electrode array with an angle of about 10° to about 45°.
- 20 33. The flexible circuit electrode array according to claim 1, wherein the flexible circuit cable portion comprises at least one grooved or rippled pad for capturing a mattress suture.
- 25 34. The flexible circuit electrode array according to claim 1, further comprising a slit along the length axis of said flexible circuit electrode array.
35. The flexible circuit electrode array according to claim 1, further comprising a slit along the length axis of said flexible circuit electrode array and a central attachment point.

36. The flexible circuit electrode array according to claim 1, further comprising a slit along the length axis of said flexible circuit electrode array and two attachment points located outside of the flexible circuit electrode array and positioned apart as far as possible from each other.
- 5 37. The flexible circuit electrode array according to claim 1, wherein the flexible circuit electrode array has a contracted radius compared to the radius of the hosting eye.
- 10 38. The flexible circuit electrode array according to claim 1, wherein the flexible circuit electrode array contains soft insulating material on the surface between the electrodes.
- 15 39. The flexible circuit electrode array according to claim 38, wherein the material contains silicone.
40. The flexible circuit electrode array according to claim 1, wherein a film containing a soft polymer is applied on the flexible circuit cable portion.
- 20 41. The flexible circuit electrode array according to claim 40, wherein a film containing a soft polymer contains silicone.
- 25 42. The flexible circuit electrode array according to claim 41, wherein a film containing a soft polymer comprises a structure like a ladder, flange skeleton.
43. The flexible circuit electrode array according to claim 40, wherein a film containing a soft polymer contains beads and/or bumpers.

44. A flexible circuit electrode array comprising:
a polymer base layer;
metal traces deposited on said polymer base layer, including electrodes
suitable to stimulate neural tissue; and
5 said polymer base layer and said metal traces are embedded in a body
having a generally oval shape in the plane of the retina, said oval shaped
body being curved such that it substantially conforms to the spherical
curvature of the retina of the recipient's eye.
- 10 45. The flexible circuit electrode array according to claim 44 comprising at least
one mounting aperture in said body for attaching the electrode array to the
retina with a tack.
- 15 46. The flexible circuit electrode array according to claim 44 wherein, said oval
shaped body has a radius of spherical curvature, which is smaller than the
radius of the curvature of the eye.
- 20 47. The flexible circuit electrode array according to claim 44 wherein, said oval
shaped body is made of a soft polymer containing silicone having a
hardness of about 50 or less on the Shore A scale as measured with a
durometer.
- 25 48. The flexible circuit electrode array according to claim 44, wherein said
flexible circuit cable portion has an angle of about 45° to about 180°.
49. The flexible circuit electrode array according to claim 48, wherein said
flexible circuit cable portion has a bend with an angle of about 60° to about
120°.

50. The flexible circuit electrode array according to claim 44, wherein said flexible circuit cable portion has a bend with an angle of about 45° to about 180°.
- 5 51. The flexible circuit electrode array according to claim 50, wherein said flexible circuit cable portion has a bend with an angle of about 60° to about 120°.
- 10 52. The flexible circuit electrode array according to claim 44, wherein said flexible circuit cable portion has a fold within the attached flexible circuit electrode array with an angle of about 1° to about 180°.
- 15 53. The flexible circuit electrode array according to claim 52, wherein said flexible circuit cable portion has a fold within the attached flexible circuit electrode array with an angle of about 20° to about 90°.
- 20 54. The flexible circuit electrode array according to claim 44, wherein said flexible circuit cable portion has a horizontal angle within the attached flexible circuit electrode array of about 1° to about 90°.
- 25 55. The flexible circuit electrode array according to claim 54, wherein said flexible circuit cable portion has a horizontal angle within the attached flexible circuit electrode array of about 10° to about 45°.
56. The flexible circuit electrode array according to claim 44, wherein said flexible circuit cable portion comprises at least one grooved or rippled pad for capturing a mattress suture.

57. The flexible circuit electrode array according to claim 44, wherein said flexible circuit electrode array is positioned on the surface of the body having a generally oval shape.
- 5 58. The flexible circuit electrode array according to claim 57, wherein soft insulating material is positioned on the surface between said electrodes.
59. The flexible circuit electrode array according to claim 44, wherein a film containing a soft polymer is applied on said flexible circuit cable portion.
- 10 60. The flexible circuit electrode array according to claim 59, wherein said film containing a soft polymer contains silicone.
61. The flexible circuit electrode array according to claim 59, wherein said film containing a soft polymer comprises a ladder like structure.
- 15 62. The flexible circuit electrode array according to claim 59, wherein a film containing a soft polymer contains beads and/or bumpers.
- 20 63. A method of making a flexible circuit electrode array comprising:
depositing a polymer base layer;
depositing metal on said polymer base layer;
patterning said metal to form metal traces;
depositing a polymer top layer on said polymer base layer and said metal
25 traces; and
heating said flexible circuit electrode array in a mold to form a three dimensional shape in said flexible circuit electrode array.

64. The method according to claim 63, further comprising the steps of heating said flexible circuit electrode array in successively smaller molds.
- 5 65. The method according to claim 63, wherein said step of depositing said polymer base layer and said polymer top layer is depositing polyimide.
66. The method according to claim 63, wherein said step of depositing said polymer base layer and said polymer top layer is depositing silicone.
- 10 67. The method according to claim 63, wherein said step of depositing said polymer base layer and said polymer top layer is depositing fluoro-polymer.
68. The method according to claim 63, further comprising forming a twist in a flexible circuit cable portion of said flexible circuit electrode array.

1/20




Fig. 1

2/20









Fig. 2

3/20

*Fig. 3A**Fig. 3B**Fig. 3C**Fig. 3D**Fig. 3E*

4/20




Fig. 4

5/20




Fig. 5

6/20




Fig. 6

7/20




Fig. 7

8/20




Fig. 8




Fig. 9




Fig. 10

9/20




Fig. 11




Fig. 12




Fig. 13




Fig. 14




Fig. 15

10/20




Fig. 16




Fig. 17




Fig. 18




Fig. 19




Fig. 20

12/20




Fig. 21








Fig. 22

13/20



14/20




Fig. 27






Fig. 28

15/20



16/20




Fig. 31




Fig. 32




Fig. 33




Fig. 34




Fig. 35




Fig. 36




Fig. 37




Fig. 38




Fig. 39




Fig. 40




Fig. 41

19/20




Fig. 42




Fig. 43




Fig. 44




Fig. 45




Fig. 46