

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
29 March 2007 (29.03.2007)

PCT

(10) International Publication Number  
**WO 2007/034933 A1**

(51) International Patent Classification:  
*C08L 51/06* (2006.01)    *C08K 5/00* (2006.01)  
*C08F 265/06* (2006.01)    *F16F 15/02* (2006.01)  
*C08K 3/00* (2006.01)

(74) Agents: YASUTOMI, Yasuo et al.; MT-2 BLDG., 5-36,  
Miyahara 3-chome, Yodogawa-ku, Osaka-shi, Osaka,  
5320003 (JP).

(21) International Application Number:  
PCT/JP2006/318897

(81) Designated States (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AL, AM,  
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,  
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,  
GB, GD, GE, GH, GM, HN, HR, HU, ID, IL, IN, IS, JP,  
KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT,  
LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MY, MZ,  
NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU,  
SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR,  
TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(22) International Filing Date:  
19 September 2006 (19.09.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
2005-272602    20 September 2005 (20.09.2005)    JP

(84) Designated States (unless otherwise indicated, for every  
kind of regional protection available): ARIPO (BW, GH,  
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,  
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,  
FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT,  
RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA,  
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicants (for all designated States except US): NI-  
HON TOKUSHU TORYO CO., LTD. [JP/JP]; 16-7,  
Oji 5-chome, Kita-ku, Tokyo, 1148584 (JP). NIP-  
PON SHOKUBAI CO., LTD. [JP/JP]; 1-1, Koraibashi  
4-chome, Chuo-ku, Osaka-shi, Osaka, 5410043 (JP).

(72) Inventors; and

(75) Inventors/Applicants (for US only): YASUI, Yoshihiko  
[JP/JP]; c/o NIHON TOKUSHU TORYO CO., LTD.,  
16-15, Toshima 8-chome, Kita-ku, Tokyo, 1140003 (JP).  
SUZUKI, Hiroshi [JP/JP]; c/o NIHON TOKUSHU  
TORYO CO., LTD., 16-15, Toshima 8-chome, Kita-ku,  
Tokyo, 1140003 (JP). NAGAISHI, Dai [JP/JP]; 4-52,  
Nakanoshimacho, Suita-shi, Osaka, 5640035 (JP).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: VIBRATION DAMPING COMPOSITION

(57) Abstract: To provide a vibration damping composition : excellent in vibration damping property and thermal drying property in a wide temperature range; and sufficiently suppressing sagging of a vibration damping coating film on the vertical surface; and therefore useful for vibration damping materials of various structures. A vibration damping composition comprising an emulsion for vibration damping materials, a foaming agent, and an inorganic pigment, wherein the emulsion for vibration damping materials comprises a particle having a core part formed from an acrylic copolymer (A) and a shell part formed from an acrylic copolymer (B), and at least one of the acrylic copolymers (A) and (B) is prepared by copolymerizing a monomer component comprising methacrylic acid.



WO 2007/034933 A1

## DESCRIPTION

## VIBRATION DAMPING COMPOSITION

5

## TECHNICAL FIELD

The present invention relates to a vibration damping composition. More preferably, the present invention relates to a vibration damping composition useful as a raw material of vibration damping materials used to prevent vibration and noise of various structures, thereby to insure sustained quietude.

10

## BACKGROUND ART

Vibration damping materials are used to prevent vibration and noise of various structures to insure sustained quietude and have been widely used beneath cabin floors of road vehicles and also applied to rolling stock, ships, aircraft, electric machines, buildings, and construction machines, among other uses. Molded products such as plate products and sheet products produced by using materials having vibration absorbing performance and sound absorbing performance have been conventionally used as raw materials used for such vibration damping materials. However, it is difficult for such molded products to be used at vibration or noise-generation positions having complicated shapes. Therefore, various methods for improving the workability and thereby sufficiently exhibiting the vibration damping property have been investigated. That is, an inorganic powder-containing asphalt sheet has been installed under automotive cabin flooring, for instance, but since the sheet must be secured in position by thermal fusion, improvements in workability and the like are needed and studies are underway on various compositions for vibration damping materials and polymers for the formation of vibration damping materials, for example.

15

20

25

30

Coating type vibration damping materials (coating materials) have been developed as an alternative material for

35

such molded products. For example, the following vibration damping coating materials have been variously proposed: vibration damping coating materials are sprayed onto positions to be subjected to damping treatment with a spray or applied thereto by any methods, and thus-formed coating film can provide vibration absorbing effect. Specifically, not only aqueous vibration damping coating materials in which synthetic resin powders are blended with vehicles such as asphalt, rubber, and synthetic resin and thereby the hardness of the obtained coating film is improved, but also as materials suitably used for interior parts of cars, vibration coating materials in which activated carbon as a filler is dispersed into a resin emulsion, have been developed. However, even these conventional products do not provide sufficiently satisfactory vibration damping performances. Techniques for further sufficiently exhibiting the vibration damping performances have been desired.

With respect to conventional coating type vibration damping materials, disclosed is an aqueous vibration damping composition prepared by adding a compatibilizing agent to a mixture of aqueous dispersions of two or more kinds of polymers having different glass transition temperatures at a specific ratio (for example, referring to Japanese Kokai Publication No. 2001-152028 (page 2)). In this composition, the mixture of aqueous dispersions of incompatible polymers is used, and the compatibilizing agent is added to cover the incompatibility, and thereby the temperature peak of the vibration damping property can be broad. However, in such a composition, the compatibilizing agent may remain in the vibration damping coating film. Therefore, such a composition has room for improvement in order to sufficiently exhibit the vibration damping performances.

With respect to an emulsion for vibration damping materials containing particles having a core part formed from an acrylic copolymer and a shell part formed from an acrylic copolymer, disclosed is a technique for adjusting glass transition

temperatures of these acrylic copolymers (for example, referring to Japanese Kokai Publication No. 2005-105133 (page 2)). Such an emulsion for vibration damping materials shows excellent vibration damping property in a wide temperature range.

5 Therefore, such a technique is industrially very useful. However, such a technique has room for improvement in order that such an emulsion exhibits more excellent vibration damping performances and thereby is more preferably used as vibration damping materials of various structures.

10

#### SUMMARY OF THE INVENTION

The present invention has been made in view of the above-mentioned state of the art. The present invention has an object to provide a vibration damping composition: excellent  
15 in vibration damping property in a wide temperature range and thermal drying property; and sufficiently suppressing sagging of a vibration damping coating film on the vertical surface; and therefore useful for vibration damping materials of various structures.

20

The present inventors have made various investigations about vibration damping compositions. The inventors noted that if a vibration damping composition contains an emulsion for vibration damping materials containing a particle having a core part formed from an acrylic copolymer and a shell part formed  
25 from an acrylic copolymer, such a vibration damping composition can exhibit excellent vibration damping property in a wide temperature range, as compared with compositions prepared by using an acrylic copolymer singly or using two or more species of acrylic copolymers in combination. The inventors found that  
30 if at least one of such acrylic copolymers constituting the core part and the shell part is prepared using methacrylic acid, the methacrylic acid is uniformly polymerized into a copolymer by emulsion polymerization and interaction between the molecular chains improves, and thereby cohesion in the copolymer increases,  
35 leading to significant improvement in vibration damping property.

The inventors also found that if such an emulsion for vibration damping materials further contains a foaming agent and an inorganic pigment, the vibration damping coating film has a uniform foaming structure and becomes a thick film, and thereby sufficient thermal drying property or high vibration damping property is exhibited, and also found that the composition is excellent in film-forming property after applied at low temperatures. Thereby, the above-mentioned problems have been admirably solved, and therefore the present invention has been completed.

The vibration damping composition of the present invention can be particularly preferably used for aqueous coating type vibration damping materials.

That is, the present invention is a vibration damping composition comprising an emulsion for vibration damping materials, a foaming agent, and an inorganic pigment, wherein the emulsion for vibration damping materials comprises a particle having a core part formed from an acrylic copolymer (A) and a shell part formed from an acrylic copolymer (B), and at least one of the acrylic copolymers (A) and (B) is prepared by copolymerizing a monomer component comprising methacrylic acid.

#### DETAILED DESCRIPTION OF THE INVENTION

The present invention is described in more detail below.

The vibration damping composition of the present invention contains an emulsion for vibration damping materials, a foaming agent, and an inorganic pigment. In each of these components, one or two or more species may be used. The vibration damping composition may further contain another component unless functional effects of the present invention are sacrificed.

In such a vibration damping composition, the emulsion for vibration damping materials contains particles having a core part and a shell part (hereinafter, also referred to as "core-shell type particle"). Such particles generally exist in the form in which they are dispersed in a medium. That is,

it is preferable that the emulsion for vibration damping materials has a medium and core-shell type particles dispersed in the medium. The medium is preferably an aqueous medium. Examples of such an aqueous medium include water and mixed solvents of water and a solvent capable of mixing with water. Among them, water is preferred in view of influence on environment or safety, which may be caused by use of a coating material prepared by using the vibration damping composition of the present invention.

In the above-mentioned emulsion for vibration damping materials, the proportion of the core-shell type particles is 70% by weight or less, relative to 100% by weight of the total amount of the emulsion for vibration damping materials. If the proportion is more than 70% by weight, the viscosity of the emulsion for vibration damping materials becomes too high, and thereby, the emulsion may not maintain sufficient dispersion stability and then aggregate. The proportion is more preferably 60% by weight or less.

The above-mentioned core-shell type particle is a particle having a core part formed from an acrylic copolymer (A) and a shell part formed from an acrylic copolymer (B). Such a particle has a structure in which the acrylic copolymer (A) forming the core part and the acrylic copolymer (B) forming the shell part are combined. Representative examples of such a combined structure include a structure in which the acrylic copolymers (A) and (B) are completely compatible with each other (homogeneous structure), and a structure inhomogeneously formed, in which the acrylic copolymers (A) and (B) are not completely compatible with each other (core-shell combined structure and microdomain structure). It is preferable that the core-shell type particle has the latter core-shell combined structure in order that the properties of both the acrylic copolymers are sufficiently exhibited and a stable emulsion is prepared.

The above-mentioned core-shell combined structure has a form in which the surface of the core part is covered with the

shell part. It is preferable that the surface of the core part is perfectly covered with the shell part, in this case. However, the surface of the core part may not be perfectly covered. For example, the core-shell combined structure may have a form in which the surface of the core part is covered in a mesh-like state or a form in which the core part is not covered in some places.

The average particle diameter of the above-mentioned core-shell type particle is not especially limited and preferably 10 nm to 1  $\mu\text{m}$ . If the average particle diameter is less than 10 nm, the viscosity of the emulsion for vibration damping materials may become too high or the emulsion for vibration damping materials may not maintain sufficient dispersion stability and then aggregate. If the average particle diameter is more than 1  $\mu\text{m}$ , such an emulsion is no longer an emulsion. The average particle diameter is more preferably 20 to 500 nm.

The average particle diameter can be measured by the following procedures, for example. The emulsion is diluted with distilled water and then sufficiently stirred and mixed. Then, about 10 mL of the mixture is charged into a glass cell and subjected to measurement using a dynamic light scattering photometer NICOMP 380 (product of Particle Sizing Systems Inc.).

In the above-mentioned core-shell type particle, two species of acrylic copolymers, that is, the acrylic copolymer (A) and the acrylic copolymer (B) different from the acrylic copolymer (A) are used. These copolymers are different in any of various properties such as glass transition temperature, SP value (solubility coefficient), kind of monomer to be used, and proportion of the monomer. Among them, it is preferable that the copolymer (A) and (B) are different in at least one of the glass transition temperature and the SP value, as mentioned below.

It is preferable that the above-mentioned acrylic copolymer (A) constituting the core part has a glass transition temperature ( $T_gA$ ) higher than a glass transition temperature

(TgB) of the above-mentioned acrylic copolymer (B). Such difference in glass transition temperature (Tg) makes it possible for the vibration damping composition to exhibit higher vibration damping property in a wide temperature range. The difference between TgA and TgB is more preferably 15°C or more. Thereby, the vibration damping property can be efficiently exhibited particularly in a practical range of 20 to 60°C. If the difference is less than 15°C, the vibration damping property may be insufficiently exhibited at either 20°C or 60°C. The difference is still more preferably 20°C or more, and particularly preferably 25°C or more. The vibration damping property within the practical range may be insufficient if the difference is too large. Therefore, the difference between TgA and TgB is preferably 100°C or less, and more preferably 90°C or less, and still more preferably 80°C or less.

The glass transition temperature (TgA) of the above-mentioned acrylic copolymer (A) is preferably 0°C or more, specifically. Thereby, a vibration damping coating film formed by using a coating material containing the vibration damping composition of the present invention has more excellent drying property, and therefore expansion or cracks on the surface of the coating film can be more sufficiently suppressed. That is, a vibration damping material having dramatically excellent vibration damping property is formed. The glass transition temperature (TgA) of the acrylic copolymer (A) is more preferably 5°C or more.

As mentioned above, the preferable embodiments of the present invention include an embodiment in which the glass transition temperature (TgA) of the above-mentioned acrylic copolymer (A) is 0°C or more and higher than the glass transition temperature (TgB) of the above-mentioned acrylic copolymer (B), and the difference between TgA and TgB is 15°C or more.

The Tg of the acrylic copolymers may be determined based on already acquired knowledge, and also may be controlled by the kind or proportion of the monomer component. However, the

Tg can be calculated through the following calculation formula, theoretically.

[Equation 1]

$$\frac{1}{Tg'} = \left[ \frac{W_1'}{T_1} + \frac{W_2'}{T_2} + \dots + \frac{W_n'}{T_n} \right]$$

5 in the formula, Tg' representing Tg of the acrylic copolymer (absolute temperature);

W<sub>1</sub>' , W<sub>2</sub>' , and ... W<sub>n</sub>' each representing a mass fraction of each monomer to all the monomer component; and

10 T<sub>1</sub> , T<sub>2</sub> , and ... T<sub>n</sub> each representing a glass transition temperature (absolute temperature) of a homopolymer prepared by each monomer component.

It is also preferable that the above-mentioned acrylic copolymer (A) constituting the core part has a SP value smaller than that of the above-mentioned acrylic copolymer (B). Such  
15 difference in SP value makes it possible for the vibration damping composition to exhibit higher vibration damping property in a wide temperature range. The difference in SP value between the above-mentioned acrylic copolymers (A) and (B) is more preferably 0.2 or more, and still more preferably 0.35 or more. Further,  
20 the difference is preferably 2.0 or less.

The SP values (δ) of the acrylic copolymers can be measured based on the following Small formula, for example.

[Equation 2]

$$\delta = \left[ \frac{(\sum \Delta e_1)(x)}{(\sum \Delta V_m)(x)} \right]^{0.5}$$

25 in the formula,

δ representing a SP value of the acrylic copolymer;

Δ<sub>e1</sub> representing a calculated value (kcal/mol) of evaporation energy of each monomer component constituting the acrylic copolymer;

30 ΣΔ<sub>e1</sub> representing a total value of the calculated values of all the monomer components constituting the acrylic

copolymers;

$\Delta V_m$  being a calculated value (ml/mol) of molecular volume of each monomer component constituting the acrylic copolymer;

$\Sigma \Delta V_m$  being a total value of the calculated values of all the monomer components constituting the acrylic copolymer; and

$x$  being a molar distribution of each monomer component constituting the acrylic copolymer.

In the above-mentioned core-shell type particle, the ratio by weight of the acrylic copolymer (A) to the acrylic copolymer (B) ((A)/(B)) is preferably 10 to 70/30 to 90, for example. If the ratio of the acrylic copolymer (A) constituting the core part is smaller than the above-mentioned range, generation of blister (expansion of the coating film) after drying by heating may be insufficiently suppressed. In contrast, if the ratio of the acrylic copolymer (A) is larger than the above-mentioned range, generation of crack after heating by drying may be insufficiently suppressed. The ratio by weight is more preferably 30 to 60/40 to 70.

Then, the monomer components used for preparing the above-mentioned acrylic copolymers (A) and (B) are further explained. The same kind of monomers may be used as long as the acrylic copolymers (A) and (B) are different in the above-mentioned respects.

It is preferable that at least one of the above-mentioned acrylic copolymers (A) and (B) comprises methacrylic acid as a monomer component. Thereby, methacrylic acid is uniformly polymerized into a copolymer by emulsion polymerization interaction between the molecular chains, and thereby cohesion in the copolymer increases, leading to significant improvement in vibration damping property. It is more preferable that both of the above-mentioned acrylic copolymers (A) and (B) comprise methacrylic acid as a monomer component.

In the acrylic copolymer prepared by using a monomer component containing methacrylic acid, the proportion of methacrylic acid is preferably 0.1% by weight or more, relative

to 100% by weight of the total amount of the monomer component used for preparing the acrylic copolymer, for example. If the proportion of methacrylic acid is less than 0.1% by weight, the vibration damping property may be insufficiently exhibited.

5 The proportion is more preferably 0.3% by weight or more and still more preferably 0.5% by weight or more. Also, the proportion is preferably 20% by weight or less.

The above-mentioned monomer component may further contain another monomer other than methacrylic acid. Examples of  
10 another monomer include (meth)acrylic acid (salt) monomers such as acrylic acid, crotonic acid, citraconic acid, itaconic acid, maleic acid, maleic anhydride, fumaric acid, methyl acrylate, methylmethacrylate, ethyl acrylate, ethylmethacrylate, propyl acrylate, propyl methacrylate, isopropyl acrylate, isopropyl  
15 methacrylate, butyl acrylate, butyl methacrylate, isobutyl acrylate, isobutyl methacrylate, tert-butyl acrylate, tert-butyl methacrylate, pentyl acrylate, pentyl methacrylate, isoamyl acrylate, isoamyl methacrylate, hexyl acrylate, hexyl methacrylate, cyclohexyl acrylate, cyclohexyl methacrylate,  
20 octyl acrylate, octyl methacrylate, isooctyl acrylate, isooctyl methacrylate, nonyl acrylate, nonyl methacrylate, isononyl acrylate, isononyl methacrylate, decyl acrylate, decyl methacrylate, dodecyl acrylate, dodecyl methacrylate, tridecyl acrylate, tridecyl methacrylate, hexadecyl acrylate, hexadecyl  
25 methacrylate, octadecyl acrylate, octadecyl methacrylate, 2-ethylhexyl acrylate, 2-ethylhexyl methacrylate, vinyl formate, vinyl acetate, vinyl propionate, 2-hydroxyethyl acrylate, hydroxyethyl methacrylate, 2-hydroxypropyl acrylate, 2-hydroxypropyl methacrylate, diallyl phthalate, triallyl  
30 cyanurate, ethylene glycol diacrylate, ethylene glycol dimethacrylate, 1,4-butanediol diacrylate, 1,4-butanediol dimethacrylate, 1,6-hexanediol diacrylate, 1,6-hexanediol dimethacrylate, diethylene glycol diacrylate, diethylene glycol dimethacrylate, allyl acrylate, allyl methacrylate, and  
35 salts thereof or esterified products thereof. One or two or

more species of them may be used.

The above-mentioned salts are preferably metal salts, ammonium salts, organic amine salts, and the like. Examples of a metal atom forming the metal salts include monovalent metal atoms such as alkali metal atoms such as lithium, sodium, and potassium; divalent metal atoms such as alkaline earth metal atoms such as calcium and magnesium; and trivalent metal atoms such as aluminum and iron. Preferred examples of the organic amine salts include alkanolamines such as ethanolamine, diethanolamine, and triethanolamine, and triethylamines.

In the above-mentioned acrylic copolymer (A), the proportion of the above-mentioned (meth)acrylic acid (salt) monomer is preferably 10 to 100% by weight relative to 100% by weight of the total monomer component used in the acrylic copolymer (A), for example. The proportion is more preferably 30 to 80% by weight. In the above-mentioned acrylic copolymer (B), the proportion of the above-mentioned (meth)acrylic acid (salt) monomer is preferably 10 to 100% by weight relative to 100% by weight of the total monomer component used in the acrylic copolymer (B). The proportion is more preferably 50 to 100% by weight.

The proportion of the methacrylic acid is not included in "proportion of the (meth)acrylic acid (salt) monomer". The value represented by "% by weight" is an average value of the total particle contained in the emulsion for vibration damping materials.

The above-mentioned monomer component may further contain another monomer copolymerizable with methacrylic acid or the above-mentioned (meth)acrylic acid (salt) monomer. Examples of another monomer include styrene, divinylbenzene,  $\alpha$ -methyl styrene, vinyltoluene, ethyl vinylbenzene, acrylonitrile, acrylamide, methacrylamide, diacetone acrylamide, N-methylolacrylamide, and N-methylolmethacrylamide.

The proportion of the above-mentioned another monomer is preferably 50% by weight or less, and more preferably 30% by

weight or less, relative to 100% by weight of the total monomer component, for example.

The pH of the above-mentioned emulsion for vibration damping materials is not especially limited, and preferably 2 to 10, and more preferably 3 to 9, for example. The pH of the emulsion can be adjusted by adding ammonia water, water-soluble amines, alkali hydroxide aqueous solutions or the like, into the emulsion.

The viscosity of the above-mentioned emulsion for vibration damping materials is not especially limited. The viscosity is preferably 10 to 10000 mPa·s, and more preferably 50 to 5000 mPa·s. The viscosity can be measured under 25°C and 20 rpm conditions with a B type rotational viscometer.

The above-mentioned emulsion for vibration damping materials is preferably produced by multistage polymerization using a usual emulsion polymerization method. The preferable embodiments of the present invention include an embodiment in which the above-mentioned emulsion for vibration damping materials is produced by multistage polymerization.

The present invention is also a production method of the above-mentioned emulsion for vibration damping materials, wherein the emulsion for vibration damping materials is produced by performing an emulsion polymerization step using monomer components having different glass transition temperatures in multiple stages.

In the above-mentioned production method of the emulsion for vibration damping materials, it is preferable that the emulsion for vibration damping materials is produced by performing an emulsion polymerization step using a monomer component constituting the core part formed from the acrylic copolymer (A) prior to a polymerization step using a monomer component constituting the shell part formed from the acrylic copolymer (B). For example, preferred is the production method of the above-mentioned emulsion for vibration damping materials, wherein an emulsion polymerization step using monomer components

having different glass transition temperatures is performed in multiple stages, and an emulsion polymerization step in the first stage is a step of performing polymerization using the monomer component constituting the acrylic copolymer (A) and an emulsion polymerization step in the last stage is a step of performing polymerization using the monomer component constituting the acrylic copolymer (B).

The vibration damping composition can be preferably produced also by the above-mentioned production method. The preferable embodiments of the present invention also include the vibration damping composition, wherein the emulsion for vibration damping materials is produced by performing an emulsion polymerization step using monomer components having different glass transition temperatures in multiple stages. Further, the preferable embodiments of the present invention include the vibration damping composition, wherein the emulsion for vibration damping materials is produced by performing an emulsion polymerization step using a monomer component constituting the core part formed from the acrylic copolymer (A) prior to an emulsion polymerization step using a monomer component constituting the shell part formed from the acrylic copolymer (B).

As the above-mentioned production method, specifically, preferred is a method including the steps of (1) forming the core part formed from the acrylic copolymer (A) by emulsion polymerization of the monomer component in the aqueous medium, in the presence of a surfactant and/or a protective colloid, and (2) forming the shell part formed from the acrylic copolymer (B) by further emulsion polymerization of the monomer component into the emulsion containing the core part. Emulsions for vibration damping materials containing particles containing the core-shell combined structure can be preferably produced by such a production method. It is particularly preferable in the above-mentioned production method to adjust the compatibility of the acrylic copolymer (A) constituting the core part with

the acrylic copolymer (B) constituting the shell part, the hydrophobic level (SP value) of these acrylic copolymers, the weight average molecular weight of these acrylic polymers, and the like. Thereby, ideal emulsions for vibration damping materials containing particles having core-shell structures can be produced.

According to the above-mentioned production method in the preferable embodiment, for example, the core part formed from the acrylic copolymer (A) is formed in the emulsion

polymerization step using the monomer component constituting the core part formed from the acrylic copolymer (A), and the shell part formed from the acrylic copolymer (B) is formed so as to be exposed to the core part in the emulsion polymerization step using the monomer component constituting the shell part formed from the acrylic copolymer (B). Thereby, the emulsion for vibration damping materials can be more efficiently obtained.

If the emulsion polymerization step is performed in three or more stages, the following embodiment is preferable. The emulsion polymerization step using the monomer component constituting the core part formed from the acrylic copolymer (A) is performed as the first stage, and the emulsion polymerization step using the monomer component constituting the shell part formed from the acrylic copolymer (B) is performed as the last stage. And other steps, that is, the emulsion polymerization step between the first stage and the last stage is not especially limited as long as the emulsion polymerization step is performed in the above-mentioned order.

Herein, the above-mentioned "monomer components having different glass transition temperatures" means monomer components satisfying the condition that homopolymers prepared using such monomer components have different glass transition temperatures (absolute temperatures).

The aqueous medium and the monomer component in the above-mentioned production method are as mentioned above.

The surfactant in the above-mentioned production method

maybe a surfactant generally used in the emulsion polymerization, and is not especially limited. Examples of such a surfactant include anionic surfactants, nonionic surfactants, cationic surfactants, amphoteric surfactants, polymer surfactants, and reactive surfactants. One or two or more species of them is/are preferably used.

The above-mentioned anionic surfactant is not especially limited. Examples of the anionic surfactant include alkyl sulfate salts such as sodium dodecyl sulfate, potassium dodecyl sulfate, and ammonium alkyl sulfate; sodium dodecyl polyglycol ether sulfate; sodium sulforicinate; alkyl sulfonates such as sulfonated paraffin salt; alkyl sulfonates such as sodium dodecylbenzene sulfonate, and alkali metal sulfates of alkali phenol hydroxyethylene; higher alkyl naphthalene sulfonates; naphthalene sulfonic acid formalin condensate; fatty acid salts such as sodium laurate, triethanol amine oleate, and triethanol amine abietate; sulfuric esters of polyoxyalkyl ether; sulfuric esters of polyoxyethylene carboxylic acid ester; sulfuric esters of polyoxyethylene phenyl ether; sulfonic acid salts of succinic acid dialkyl esters; and polyoxyethylene alkylaryl sulfates. One or two or more species of them may be used.

The above-mentioned nonionic surfactant is not especially limited. Examples of the nonionic surfactant include polyoxyethylene alkyl ethers; polyoxyethylene alkylaryl ethers; sorbitan aliphatic esters; polyoxyethylene sorbitan aliphatic esters; aliphatic monoglycerides such as monolaurate of glycerol; polyoxyethylene-oxypropylene copolymer; condensates of ethylene oxide and aliphatic amines, aliphatic amides, or aliphatic acids. One or two or more species of them may be used.

The above-mentioned cationic surfactant is not especially limited. Examples of the cationic surfactant include dialkyl dimethyl ammonium salts, ester type dialkyl ammonium salts, amide type dialkyl ammonium salts, and dialkylimidazolium salts. One or two or more species of them may be used.

The above-mentioned amphoteric surfactant is not especially limited. Examples of the amphoteric surfactant include alkyl dimethylamino acetic acid betaine, alkyl dimethyl amine oxide, alkyl carboxy methyl hydroxyethyl imidazolinium betaine, alkyl amide propyl betaine, and alkyl hydroxy sulfobetaine. One or two or more species of them may be used.

The above-mentioned polymer surfactant is not especially limited. Examples of the polymer surfactant include polyvinyl alcohols and modified products thereof; (meth)acrylic acid water-soluble polymers; hydroxyethyl (meth)acrylic acid water-soluble polymers; hydroxypropyl (meth)acrylic acid water-soluble polymers; and polyvinyl pyrrolidone. One or two or more species of them may be used.

Among the above-mentioned surfactants, non-nonylphenyl type surfactants are preferably used in view of environment.

The use amount of the above-mentioned surfactant may be appropriately determined depending on the kind of the surfactant to be used or the kind of the monomer component to be used. For example, the use amount of the surfactant is preferably 0.3 to 10 parts by weight, and more preferably 0.5 to 5 parts by weight, relative to 100 parts by weight of the total amount of the monomer component used for preparing the acrylic copolymer.

Examples of the above-mentioned protective colloid include polyvinyl alcohols such as partially saponificated polyvinyl alcohols, completely saponificated polyvinyl alcohols, and modified polyvinyl alcohols; cellulose derivatives such as hydroxyethyl cellulose, hydroxypropylcellulose, and carboxymethylcellulose salt; natural polysaccharides such as Guar gum. One or two or more species of them may be used. Such a protective colloid may be used singly or in combination with the surfactant.

The use amount of the above-mentioned protective colloid may be appropriately determined depending on the use conditions and the like. For example, the use amount of the protective colloid is preferably 5 parts by weight or less, and more

preferably 3 parts by weight or less, relative to 100 parts by weight of the total amount of the monomer component used for preparing the acrylic copolymer.

A polymerization initiator is preferably used in order to initiate the emulsion polymerization in the above-mentioned production method. The polymerization initiator is not especially limited as long as it is a substance which is decomposed by heating and generates radical molecules. Water-soluble initiators are preferably used. Examples of such an initiator include persulfates such as potassium persulfate, ammonium persulfate, and sodium persulfate; water-soluble azo compounds such as 2,2'-azobis(2-amidinopropane) dihydrochloride, and 4,4'-azobis(4-cyanopentanoic acid); thermal decomposition initiators such as hydrogen peroxide; redox polymerization initiators such as hydrogen peroxide and ascorbic acid, t-butyl hydroperoxide and rongalite, potassium persulfate and metal salt, and ammonium persulfate and sodium hydrogensulfite. One or two or more species of them may be used.

The use amount of the above-mentioned polymerization initiator is not especially limited and may be appropriately determined depending on the kind of the polymerization initiator and the like. For example, the use amount of the polymerization initiator is preferably 0.1 to 2 parts by weight and more preferably 0.2 to 1 part by weight, relative to 100 parts by weight of the total amount of the monomer component used for preparing the acrylic copolymer.

A reducing agent may be used in combination with the above-mentioned polymerization initiator, if necessary, in order to accelerate the emulsion polymerization. Examples of the reducing agent include reducing organic compounds such as ascorbic acid, tartaric acid, citric acid, and grape sugar; and reducing inorganic compounds such as sodium thiosulfate, sodium sulfite, sodium bisulfite, and sodium metabisulfite. One or two or more species of them may be used.

The use amount of the above-mentioned reducing agent is

not especially limited and preferably 0.05 to 1 part by weight, relative to 100 parts by weight of the total amount of the monomer component used for preparing the acrylic copolymer, for example.

It is also preferable in the above-mentioned production method to use a chain transfer agent if necessary at the time of the emulsion polymerization in order to adjust the average molecular weight of the above-mentioned acrylic copolymer (A) or (B). The chain transfer agent may be a generally used chain transfer agent and is not especially limited. Examples of the chain transfer agent include alkyl mercaptans such as hexyl mercaptan, octyl mercaptan, n-dodecyl mercaptan, t-dodecyl mercaptan, n-hexadecyl mercaptan, and n-tetradecyl mercaptan; halogenated hydrocarbons such as carbon tetrachloride, carbon tetrabromide, and ethylene bromide; mercaptocarboxylic acid alkyl esters such as 2-ethylhexyl mercaptoacetate, 2-ethylhexyl mercaptopropionate, and tridecyl mercaptopropionate; mercaptocarboxylic acid alkoxyalkyl esters such as methoxybutyl mercaptoacetate and methoxybutyl mercaptopropionate; carboxylic acid mercaptoalkyl esters such as 2-mercaptoethyl octanoate;  $\alpha$ -methylstyrene dimer, terpinolene,  $\alpha$ -terpinene,  $\gamma$ -terpinene, dipentene, anisole, and allyl alcohol. One or two or more species of them may be used. Among them, it is preferable to use an alkyl mercaptans such as hexyl mercaptan, octyl mercaptan, n-dodecyl mercaptan, t-dodecyl mercaptan, n-hexadecyl mercaptan, and n-tetradecyl mercaptan.

The use amount of the above-mentioned chain transfer agent is not especially limited and preferably 2 parts by weight or less, and more preferably 1.0 part by weight or less, relative to 100 parts by weight of the total amount of the monomer component used for preparing the acrylic copolymer, for example.

Regarding the emulsion polymerization conditions in the above-mentioned production method, the polymerization temperature is not especially limited and preferably 0 to 100°C and more preferably 40 to 95°C, for example. The polymerization time is not especially limited, and preferably 1 to 15 hours,

for example.

The addition mode of the monomer component, the polymerization initiator or the like is not especially limited. Any of en bloc addition, continuous addition, multistage addition and the like may be employed. These addition modes may be used  
5 in a suitable combination.

In the above-mentioned production method, the core part and the shell part are formed under the same operation, basically. The additives or the reaction conditions may be different, if  
10 necessary. For example, the surfactant and/or the protective colloid may not be added in the emulsion polymerization in the above-mentioned step (2).

The vibration damping composition of the present invention may generate blisters when drying of the coating film surface proceeds and residual moisture inside the coating film evaporates  
15 in the heat-drying step. In order to prevent this, a foaming agent foaming at the time of drying by heating is contained in the vibration damping composition and thereby residual moisture inside the coating film evaporates simultaneously with the foam  
20 formation. Thereby, such blisters are prevented. The thickness of the coating film increases because the vibration damping composition contains the foaming agent. Therefore, the vibration damping performances are also improved. Thus, the preferable embodiments of the present invention include the  
25 vibration damping composition comprising a foaming agent foaming during drying by heating.

The kind of the foaming agent is not especially limited in the above-mentioned vibration damping composition. Examples of the foaming agent include organic foaming agents such as  
30 diazoamino benzole, azoisobutyl nitrile, benzole sulfohydrazide, azodicarbonamide, P-P'-oxybenzole sulfohydrazide, benzyl monohydrazole; and thermal expansion microcapsules. Thermal expansion microcapsules are preferably used because they are excellent in stability in aqueous coating  
35 materials.

In the vibration damping composition of the present invention, the content of the foaming agent is not especially limited, and preferably 0.2 to 3.0 parts by weight relative to 100 parts by weight of the vibration damping composition.

5           The kind of the inorganic pigment is not especially limited in the vibration damping composition of the present invention. Used maybe inorganic pigments such as calcium carbonate, kaolin, silica, talc, clay, barium sulfate, alumina, iron oxide, titanium oxide, glass powders, magnesium carbonate, aluminum hydroxide,  
10 bentonite, fly ash, and kieselguhr; flaky inorganic pigments such as glass flakes, pearlite, and mica; and filamentous inorganic pigments such as metal oxide whiskers, glass fibers. Particularly, flaky inorganic pigments have an effect of decreasing vibration energy by forming a layer structure inside  
15 the coating film. Therefore, mica having a high aspect ratio is preferably used. The use of such flaky inorganic pigments makes it possible to more sufficiently improve the vibration damping property. Thus, the preferable embodiments of the present invention include an embodiment in which the inorganic  
20 pigment comprises a flaky inorganic pigment. In this case, as the inorganic pigment, ordinarily used inorganic pigments such as calcium carbonate, kaolin, silica, and talc may be used in combination with such a flaky inorganic pigment.

The mix amount of the above-mentioned inorganic pigment  
25 is preferably 50 to 700 parts by weight, relative to 100 parts by weight of the emulsion for vibration damping materials, for example. That is, it is preferable that the vibration damping composition comprises 50 to 700 parts by weight of the inorganic pigment relative to 100 parts by weight of the emulsion for  
30 vibration damping materials. The vibration damping composition may insufficiently exhibit the thermal drying property or the vibration damping property if the inorganic pigment is less than 50 parts by weight. If the inorganic pigment is more than 700 parts by weight, cracks may be generated after drying by heating  
35 because of reduction in toughness of the coating film, or the

coating film may be easily peeled from a substrate because of reduction in adhesion to the substrate. More preferably, the above-mentioned vibration damping composition contains 100 to 550 parts by weight of the inorganic pigment. Among them, it is preferable that 30 to 150 parts by weight of the flaky inorganic pigment is used, relative to 100 parts by weight of the emulsion for vibration damping materials. More preferably, 40 to 120 parts by weight of the flaky inorganic pigment is used.

The vibration damping composition of the present invention may contain other components other than the emulsion for vibration damping materials, the foaming agent, and the inorganic pigment, unless the functional effects of the present invention are sacrificed.

Examples of the above-mentioned other components include solvent; plasticizer; stabilizer; thickener; wetting agent; antiseptic; foaming inhibitor; organic pigment; glass bead; glass balloon; plastic bead; plastic balloon; antifreezing agent; dispersant; antifoaming agent; antioxidant; mildewproofing agent; ultraviolet absorber; and antistatic agent. One or two or more species of them may be used. Among them, the vibration damping composition preferably contains a filler. The above-mentioned other components can be mixed with the above-mentioned emulsion for vibration damping materials and the like using, for example, a butterfly mixer, a planetary mixer, a spiral mixer, kneader, and a Dissolver.

The above-mentioned other components may be those generally used and are not especially limited. The following compounds and the like may be used, for example.

Examples of the above-mentioned solvent include ethylene glycol, butyl cellosolve, butyl carbitol, and butyl carbitol acetate. The mix amount of the solvent may be appropriately determined such that the solids concentration of the emulsion for vibration damping materials in the vibration damping composition is within the above-mentioned range.

Polyvinyl alcohols, cellulose derivatives, and

polycarboxylic acid resins may be mentioned as the above-mentioned thickener, for example. The mix amount of the thickener is preferably, 0.01 to 4 parts by weight of solids, and more preferably 0.05 to 1.5 parts by weight, and still more preferably 0.1 to 1 part by weight, relative to 100 parts by weight of solids of the emulsion for vibration damping materials.

Hansa yellow, benzine yellow, copper phthalocyanine blue, quinacridone red may be mentioned as the above-mentioned organic pigment, for example.

Inorganic dispersants such as sodium hexametaphosphate and sodium tripolyphosphate and organic dispersants such as polycarboxylic acid dispersants may be mentioned as the above-mentioned dispersant, for example.

Ethylene glycol and propylene glycol may be mentioned as the above-mentioned antifreezing agent.

Silicone antifoaming agents may be mentioned as the above-mentioned antifoaming agent, for example.

Polyvalent metal compounds may be used as the above-mentioned other components. In this case, the polyvalent metal compound improves the stability, dispersibility, thermal drying property of the vibration damping composition or the vibration damping property of the vibration damping material formed by the vibration damping composition. The polyvalent metal compounds are not especially limited. Examples of the polyvalent metal compounds include zinc oxide, zinc chloride, and zinc sulfate. One or two or more species of them may be used.

The form of the above-mentioned polyvalent metal compound is not especially limited, and may be in the form of a fine particle, an aqueous dispersion, an emulsified dispersion, or the like. Among them, the polyvalent metal compound is preferably used in the form of an aqueous dispersion or an emulsified dispersion, and more preferably in the form of an emulsified dispersion because the dispersibility in the vibration damping composition is improved. The use amount of the polyvalent metal compound

is preferably 0.05 to 5.0 parts by weight, and more preferably 0.05 to 3.5 parts by weight, relative to 100 parts by weight of solids in the vibration damping composition.

The production method of the vibration damping composition of the present invention is not especially limited as long as the composition contains the above-mentioned emulsion for vibration damping materials, foaming agent, inorganic material and, if necessary, other components. The vibration damping composition can be produced by mixing each of the components by a usual method.

The above-mentioned vibration damping composition is coated on a substrate and dried to give a coating film serving as a vibration damping material. The substrate is not especially limited. As the method of coating the substrate with the vibration damping composition, brush, roller, spatula, air spray gun, airless spray gun, mortar gun, texture gun, and the like, may be used for coating.

The coating amount of the above-mentioned vibration damping composition may be appropriately determined depending on the intended application, expected performance, and the like. The vibration damping composition is preferably coated such that the coating film at the time of (after) drying has a face weight of 1.0 to 7.0 kg/m<sup>2</sup>, and more preferably 2.0 to 6.0 kg/m<sup>2</sup>. Use of the emulsion for vibration damping materials of the present invention makes it possible to obtain a coating film which hardly generates expansion or cracks at the time of drying and hardly causes sagging on the vertical surface. Thus, the preferable embodiments of the present invention include a coating method of the vibration damping composition, wherein the vibration damping composition is coated so as to have a face weight of 2.0 to 6.0 kg/m<sup>2</sup> after drying, and dried. The preferable embodiments of the present invention also include a vibration damping material obtainable by the coating method of the vibration damping composition. Further, the preferable embodiments of the present invention include a use method of

the vibration damping composition, wherein the vibration damping composition is used as an aqueous vibration damping material.

Regarding the conditions to be used in the case where the above-mentioned vibration damping composition is coated on the substrate and dried to form a coating film, either drying by heating or drying at atmospheric temperature may be adopted. However, from efficiency points of view, drying by heating is preferred and preferably employed because the vibration damping composition of the present invention has excellent thermal drying property. The temperature of the drying by heating is preferably 80 to 210°C, and more preferably 90 to 180°C, and still more preferably 120 to 170°C.

The application of the vibration damping composition of the present invention is not especially limited. The vibration damping composition can exhibit excellent thermal drying property, vibration damping property and the like, and therefore can be preferably used in such applications as rolling stock, ships, aircraft, electric machines, buildings and construction machines, in addition to as automotive cabin floor base.

The vibration damping composition of the present invention has the above-mentioned configuration. The vibration damping composition is particularly useful as a raw material used in vibration damping materials of various structures because it is excellent in vibration damping property and the thermal drying property in a wide temperature range and it can sufficiently suppress sagging on the vertical surface of the vibration damping coating film.

#### BEST MODE FOR CARRYING OUT THE INVENTION

The present invention is described in more detail with reference to Examples below, but the present invention is not limited to only these Examples. The terms, "part(s)" and "%" represent "part(s) by weight" and "% by weight", respectively, unless otherwise specified.

The SP value, the glass transition temperature (T<sub>g</sub>), and

the viscosity in the following Synthetic Examples and the like were determined by the above-mentioned procedures, respectively.

5 The white turbidity of the film was determined by the following procedures;

The obtained emulsion was charged into a mold in 50.00 mm (length) x 100.00 mm (width) x 2.00 mm (height) and left for 10 minutes at a room temperature. Then, the emulsion was baked at 140°C to form a resin film. Thus-obtained resin film was  
10 visually observed for transparency.

#### "Emulsion for vibration damping materials"

##### Synthetic Example 1

A polymerization container equipped with a stirrer, a  
15 reflux condenser, a thermometer, a nitrogen gas inlet pipe and a dropping funnel was filled with deionized water (76 parts). Then, under stirring in a nitrogen gas stream, the contents of the container were heated to an internal temperature of 70°C. The dropping funnel was filled with a monomer emulsion 1 composed  
20 of methyl methacrylate (22.8 parts), styrene (40.0 parts), 2-ethylhexylacrylate (22.5 parts), butyl acrylate (12.2 parts), acrylic acid (2.0 parts), methacrylic acid (0.5 parts), previously adjusted 20% aqueous solution of polyoxyethylene alkyl ether sulfate ester salt (product of DAI-ICHI KOGYO SEIYAKU  
25 CO., LTD., "Hitenol NF-08") (15 parts), and deionized water (10 parts).

The monomer emulsion 1 was added dropwise into the polymerization container adjusted to 70°C, and thereby the reaction was allowed to proceed. The temperature was raised  
30 to 80°C, and the monomer emulsion 1 was uniformly added dropwise into the container over 2 hours while keeping the internal temperature at 80°C. At the same time, 5% aqueous solution of potassium persulfate (7 parts) and 2% aqueous solution of sodium hydrogensulfite (17.5 parts) were uniformly added dropwise into  
35 the container over 2 hours. Through such dropwise addition,

an emulsion forming a core part was formed. After completion of the dropwise addition, the reaction was continued for 1 hour at 75°C. Thereby, each of the monomer components was completely consumed.

5            Thus-obtained emulsion forming the core part was measured for SP value, and the glass transition temperature (TgA) was determined based on the formulation of the monomers constituting the core part. Table 1 shows these results.

10            Then, in another dropping funnel, prepared was a monomer emulsion 2 composed of methyl methacrylate (25.3 parts), styrene (10.0 parts), 2-ethylhexyl acrylate (25.8 parts), butyl acrylate (36.4 parts), acrylic acid (2.0 parts), methacrylic acid (0.5 parts), previously adjusted 20% aqueous solution of polyoxyethylene alkyl ether sulfate ester salt (product of  
15            DAI-ICH KOGYO SEIYAKU CO., LTD., "Hitenol NF-08") (15 parts), and deionized water (10 parts). The prepared monomer emulsion 2 was added dropwise into the emulsion forming the core part and thereby the reaction was allowed to proceed. The monomer emulsion 2 was added dropwise over 2 hours while keeping the  
20            internal temperature at 80°C. At the same time, 5% aqueous solution of potassium persulfate (7 parts) and 2% aqueous solution of sodium hydrogensulfite (17.5 parts) were uniformly added dropwise into the mixture over 2 hours. Through such  
25            dropwise addition, a shell part was formed to obtain a core-shell type particle. After completion of the dropwise addition, the reaction was continued for 1 hour at 75°C. Thereby, each of the monomers was completely consumed. Then, the reaction solution was cooled at 25°C, and a proper amount of 25% ammonia water was added into the reaction solution. Thereby, an emulsion  
30            for vibration damping materials was obtained.

            The obtained emulsion for vibration damping materials was determined for solids concentration, pH and viscosity. And the white turbidity of the film was evaluated by visual observation. The SP value of the shell part was determined, and the glass  
35            transition temperature (TgB) was measured based on the

formulation of the monomers constituting the shell part. Table 1 shows these results.

Synthetic Examples 2 to 5, Comparative Synthetic Examples 1 and 2

Emulsions for vibration damping materials were obtained in the same manner as in Synthetic Example 1, except that the formulations of the monomer components used for forming the core part and the shell part were changed as shown in Table 1 or 2.

These emulsions for vibration damping materials were evaluated for various physical properties and the like, as performed in Synthetic Example 1. Table 1 shows the results.

Comparative Synthetic Example 3

An emulsion for vibration damping materials was obtained in the same manner as in Synthetic Example 1, except that the formulation of the monomer components used for forming the core part was changed as shown in Table 1 and the shell part was not formed.

This emulsion for vibration damping materials was evaluated for various physical properties and the like, as performed in Synthetic Example 1. Table 1 shows results.

25

30

35

[Table 1]

5  
10  
15  
20  
25  
30  
35

	Synthetic Example					Comparative Synthetic Example		
	1	2	3	4	5	1	2	3
MMA	22.8	20.9	23.3	22.6	—	23.3	—	14.6
St	40.0	40.0	40.0	36.0	63.0	40.0	65.4	39.5
2EHA	22.5	22.5	22.5	22.5	33.0	22.5	32.6	43.9
BA	12.2	12.6	12.2	12.9	—	12.2	—	—
AA	2.0	0.0	2.0	0.0	0.0	2.0	2.0	2.0
MAA	0.5	4.0	0.0	7.0	4.0	0.0	0.0	—
SP value	9.21	9.22	9.20	9.35	8.90	9.20	8.86	9.10
MMA	25.3	23.4	25.8	20.2	29.1	25.8	31.5	—
St	10.0	10.0	10.0	10.0	—	10.0	—	—
2EHA	25.8	25.8	25.8	25.8	—	25.8	—	—
BA	36.4	36.8	36.8	37.0	66.9	36.4	66.5	—
AA	2.0	0.0	0.0	0.0	0.0	2.0	2.0	—
MAA	0.5	4.0	4.0	7.0	4.0	0.0	0.0	—
SP value	9.59	9.60	9.60	9.67	9.91	9.58	9.89	—
T <sub>E</sub> A/T <sub>g</sub> B(°C)	20/-20	20/-20	20/-20	20/-20	20/-20	20/-20	20/-20	0
Ratio of WA/WB	50/50	50/50	50/50	50/50	50/50	50/50	50/50	100
ΔSP(B-A)	0.38	0.38	0.40	0.32	1.01	0.38	1.03	—
Solids (% by weight)	55.0	55.0	55.0	55.0	55.0	55.0	54.9	55.0
pH	7.7	7.7	7.7	7.7	7.7	7.7	7.6	7.5
Viscosity (mPa·s)	200	350	610	800	650	280	610	450
White turbidity of film	Fluorescence	Fluorescence	Fluorescence	Fluorescence	White turbidity	Fluorescence	White turbidity	Transparency

Descriptions in Table 1 are as follows.

MMA: methyl methacrylate

St: styrene

2EHA: 2-ethylhexyl acrylate

5 BA: butyl acrylate

EA: ethyl acrylate

AA: acrylic acid

TgA/TgB (°C): glass transition temperature (°C) of the core part (A)/glass transition temperature (°C) of the shell part (B)

10 Ratio of WA/WB: ratio by weight (%/%) of the core part (A) to the shell part (B)

$\Delta$ SP (B-A): value calculated by subtracting the SP value of the core part (A) from the SP value of the shell part (B)

15 As  $\Delta$ SP (B-A) becomes small, the compatibility becomes relatively more excellent. On the other hand, the compatibility becomes relatively more poor as  $\Delta$ SP (B-A) becomes larger.

"Vibration damping composition"

Examples 1 to 5, Comparative Examples 1 to 2

20 Vibration damping compositions of Examples 1 to 5 and Comparative Examples 1 to 3 were obtained by preparing coating materials using the emulsions for vibration damping materials obtained in the above-mentioned Synthetic Examples and Comparative Synthetic Examples at formulations shown in Table

25 2.

Each of the obtained vibration damping composition was coated on a reed-shaped sheet steel in 30 x 300 x 1.6 mm with a spatula such that the weight after drying was 4 kg per m<sup>2</sup>. Then, the coated composition was dried for 45 minutes at 140°C.

30 Thereby, testpieces for vibration damping measurement were prepared.

Each of these testpieces for vibration damping measurement was measured for loss factor values at 20°C, 40°C, and 60°C atmosphere. Table 3 shows the results. The loss factor value

35 was calculated from half band width of each resonance point at

1 to 1000 Hz of mechanical impedance, based on midpoint excitation method. Then, the loss factor value at 200 Hz was determined by interpolation method. The larger the loss factor value is, the higher the effect of decreasing vibration damping energy is.

[Table 2]

		Formulation (part by weight)	Remarks
Raw material	Emulsion for vibration damping materials	45.0	Emulsion
	Polycarboxylic acid ammonium salt	0.5	Dispersant
	Mineral oil based antifoaming agent	0.2	Antifoaming agent
	Propylene glycol	1.0	Antifreezing agent
	Calcium carbonate	31.3	Inorganic pigment
	Mica	20.0	Inorganic pigment
	Thermal expansion microcapsule	0.5	Foaming agent
	Polyacrylic acid ester	1.5	Thickener
Total		100.0	

10 [Table 3]

		Example					Comparative Example		
		1	2	3	4	5	1	2	3
Emulsion for vibration damping materials		Synthetic Example 1	Synthetic Example 2	Synthetic Example 3	Synthetic Example 4	Synthetic Example 5	Comparative Synthetic Example 1	Comparative Synthetic Example 2	Comparative Synthetic Example 3
Vibration damping property (loss factor)	20°C	0.084	0.095	0.107	0.079	0.102	0.084	0.090	0.045
	40°C	0.125	0.145	0.141	0.141	0.126	0.102	0.095	0.146
	60°C	0.082	0.087	0.077	0.104	0.097	0.074	0.077	0.019

High loss factor values were obtained in a wide temperature range in Examples 1 to 5 using the emulsions for vibration damping materials with a core-shell type structure prepared by copolymerizing methacrylic acid.

In contrast, the loss factor values at 20°C and 60°C were low and the temperature range where the vibration damping effect

is exhibited is narrow in Comparative Example 3 using the emulsion for vibration damping materials not having a shell part (with a homogeneous particle structure).

- 5 The loss factor value was low and the vibration damping effect was low in each temperature range in Comparative Examples 1 and 2 using the emulsion for vibration damping materials not containing methacrylic acid.

#### Example 6

- 10 The vibration damping composition obtained in Example 2 was coated on a reed-shaped sheet steel in 30 x 300 x 1.6 mm with a spatula such that the weight after drying was 1 kg per m<sup>2</sup> (the face weight after drying was 1.0 kg/m<sup>2</sup>). Then, the coated composition was dried for 45 minutes at 140°C. Thereby, a
- 15 testpiece for vibration damping measurement was prepared. Using this testpiece, the loss factor values at 20°C, 40°C, and 60°C atmosphere were measured. Table 4 shows the results.

#### Examples 7 to 10

- 20 The vibration damping compositions obtained in Example 2 were used and the loss factor values at 20°C, 40°C, and 60°C atmosphere were measured in the same manner as in Example 6, except that each of the compositions was coated such that the face weight after drying showed a value described in Table 4.
- 25 Table 4 shows the results.

[Table 4]

	Face weight (kg/m <sup>2</sup> )	Vibration damping property		
		20°C	40°C	60°C
Example 6	1.0	0.008	0.020	0.004
Example 7	2.0	0.020	0.060	0.030
Example 8	4.0	0.095	0.145	0.087
Example 9	6.0	0.195	0.252	0.209
Example 10	7.5	0.166	0.142	0.079

In Example 6 in which the face weight after drying was 1.0 kg/m<sup>2</sup>, the vibration damping property was the lowest. However, in Examples 7 to 9 in which the face weight after drying was 2.0 to 6.0 kg/m<sup>2</sup>, the effect of the vibration damping property was observed. And the vibration damping property was the best in Example 9. In Example 10 in which the face weight after drying was 7.5 kg/m<sup>2</sup>, the properties of the vibration damping composition were not sufficiently exhibited because the drying property was insufficient.

10

Examples 11 to 15

Vibration compositions were obtained as performed in Example 2 and the loss factor values at 20°C, 40°C, and 60°C atmosphere were measured in the same manner as in Example 2, except that the amounts of the calcium carbonate and mica were changed to amounts described in Table 5, respectively. Table 5 shows the results.

15

[Table 5]

		Example 11	Example 12	Example 13	Example 14	Example 15
Inorganic pigment	Calcium carbonate (part by weight)	31.3	31.3	0.0	20.0	0.0
	Mica (part by weight)	20	0.0	20	10	51.3
Vibration damping property	20°C	0.095	0.045	0.12	0.102	0.295
	40°C	0.145	0.076	0.152	0.121	0.543
	60°C	0.087	0.035	0.045	0.061	0.351

20

## CLAIMS

1. A vibration damping composition comprising an emulsion for vibration damping materials, a foaming agent, and an inorganic pigment,  
5 wherein the emulsion for vibration damping materials comprises a particle having a core part formed from an acrylic copolymer (A) and a shell part formed from an acrylic copolymer (B), and  
10 at least one of the acrylic copolymers (A) and (B) is prepared by copolymerizing a monomer component comprising methacrylic acid.
2. The vibration damping composition according to Claim 1,  
15 wherein the emulsion for vibration damping materials is produced by performing an emulsion polymerization step using monomer components having different glass transition temperatures in multiple stages.
- 20 3. The vibration damping composition according to Claim 1 or 2,  
wherein the emulsion for vibration damping materials is produced by performing an emulsion polymerization step using  
25 a monomer component constituting the core part formed from the acrylic copolymer (A) prior to an emulsion polymerization step using a monomer component constituting the shell part formed from the acrylic copolymer (B).
- 30 4. The vibration damping composition according to any of Claims 1 to 3,  
wherein the vibration damping composition comprising a foaming agent foaming during drying by heating.
- 35 5. The vibration damping composition according to any

of Claims 1 to 4,

wherein the vibration damping composition comprises 50 to 700 parts by weight of inorganic pigment relative to 100 parts by weight of the emulsion for vibration damping materials.

5

6. The vibration damping composition according to any of Claims 1 to 5,

wherein the inorganic pigment comprises a flaky inorganic pigment.

10

7. A use method of the vibration damping composition of any of Claims 1 to 6,

wherein the vibration damping composition is used as an aqueous vibration damping material.

15

8. A coating method of the vibration damping composition of any of Claims 1 to 6,

wherein the vibration damping composition is coated so as to have a face weight of 1.0 to 7.0 kg/m<sup>2</sup> after drying, and dried.

20

9. A vibration damping material obtainable by the coating method of the vibration damping composition of Claim 8.

25

## INTERNATIONALSEARCHREPORT

International application No.

PCT/JP2006/318897

A. CLASSIFICATION OF SUBJECT MATTER		
Int.Cl. C08L51/06(2006.01)i, C08F265/06(2006.01)i, C08K3/00(2006.01)i, C08K5/00(2006.01)i, F16F15/02(2006.01)i		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols)		
Int.Cl. C08L51/06, C08F265/06, C08K3/00, C08K5/00, F16F15/02		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Published examined utility model applications of Japan 1922-1996 Published unexamined utility model applications of Japan 1971-2006 Registered utility model specifications of Japan 1996-2006 Published registered utility model applications of Japan 1994-2006		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	J P 2 0 0 5 - 1 0 5 1 3 3 A (NIPPON SHOKUBAI Co., LTD.) 2005. 04. 21, CLAIM, 【0019】 - 【0022】, 【0057】 - 【0058】 &EP 1520865 A2 &US 2005/101697 A1	1-9
A	J P 2 0 0 1 - 1 5 2 0 2 8 A (CEMEDINE Co., LTD) 2001. 06. 05, CLAIMS, 【0021】 - 【0025】 (NO FAMILIES)	1-9
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier application or patent but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family		
Date of the actual completion of the international search		Date of mailing of the international search report
04.12.2006		12.12.2006
Name and mailing address of the ISA/JP		Authorized officer
<b>Japan Patent Office</b>		4J 8620
3-4-3, Kasumigaseki, Chiyoda-ku, Tokyo 100-8915, Japan		SHIGEKAZU HASHIMOTO
		Telephone No. +81-3-3581-1101 Ext. 3457