



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : D06P 5/08, D06M 16/00, C11D 3/386, 3/39, C12S 11/00</p>	<p>A1</p>	<p>(11) International Publication Number: WO 99/34054</p> <p>(43) International Publication Date: 8 July 1999 (08.07.99)</p>
<p>(21) International Application Number: PCT/DK98/00560</p> <p>(22) International Filing Date: 17 December 1998 (17.12.98)</p> <p>(30) Priority Data: 1526/97 23 December 1997 (23.12.97) DK</p> <p>(71) Applicants: NOVO NORDISK A/S [DK/DK]; Novo Allé, DK-2880 Bagsværd (DK). BAYER, AG [DE/DE]; D-51368 Leverkusen (DE).</p> <p>(72) Inventors: DAMHUS, Ture; Livjærggade 43, st. tv., DK-2100 Copenhagen Ø (DK). VOGT, Uwe; Glaire-Waldoff-Strasse 36, D-40789 Monheim (DE).</p> <p>(74) Common Representative: NOVO NORDISK A/S; Corporate Patents, Novo Allé, DK-2880 Bagsværd (DK).</p>	<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i></p>	
<p>(54) Title: PROCESS FOR REMOVAL OF EXCESS DYE FROM PRINTED OR DYED FABRIC OR YARN</p>		
<p>(57) Abstract</p> <p>The present invention provides a process for removal of excess dye from newly manufactured printed or dyed fabric or yarn, comprising treatment with a rinse liquor comprising at least one enzyme selected from the group consisting of enzymes exhibiting peroxidase activity or laccase activity, an oxidation agent, and at least one mediator selected from the group consisting of aliphatic, cyclo-aliphatic, heterocyclic or aromatic compounds containing the moiety > N-OH, in particular 1-hydroxybenzotriazole.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

PROCESS FOR REMOVAL OF EXCESS DYE FROM PRINTED OR DYED FABRIC OR YARN

The present invention relates to a novel method of removing
5 excess dye from newly printed or dyed fabric or yarn as well as
a system and a composition for use in the method.

BACKGROUND OF THE INVENTION

10 Printing and dyeing of textiles is carried out by applying
dyes to the textile by any appropriate method for binding the
dyestuff to the fibres in the textiles. Excess soluble dyestuff
not bound to the fibres must be removed after dyeing to ensure
fastness of the dyed textiles and to prevent unwanted dye trans-
15 fer during laundering of the textiles by the consumer.

Generally, a large amount of water is required for complete
removal of excess dye. In a conventional process the printed or
dyed textile is first rinsed with cold water, then washed at
high temperature with the addition of a suitable additive to de-
20 crease back-staining, like poly(vinylpyrrolidone) (PVP). The
process is repeated until a satisfactory amount of dyestuff (and
thickeners) has been removed. PVP can be added to reduce back-
staining during rinsing, but this compound does not bleach the
dye and is relatively expensive. Furthermore, the waste liquor
25 from a conventional process tends to be strongly coloured and
may represent a disposal problem, which is not reduced by the
use of PVP.

WO 92/18687 discloses a method of bleaching excess dye from
printed or dyed fabric by treating with a liquor containing an
30 enzyme exhibiting peroxidase activity or oxidase activity, an O₂
or H₂O₂ source as applicable, and optionally an additional oxidiz-
able substrate, such as a metal ion, a halide ion or an organic
compound, such as a phenol.

However, the concentrations of such additional substrates
35 necessary for enzymatically bleaching the excess dye in the
rinse liquor may present a risk of bleaching the dyed textiles
themselves.

Accordingly, it is an object of the present invention to provide a method for removing or bleaching excess dye without bleaching the dyed textile. This is achieved by a process for removal of excess dye from newly manufactured printed or dyed fabric or yarn comprising treatment with a rinse liquor comprising

- at least one enzyme selected from the group consisting of enzymes exhibiting peroxidase activity or laccase activity,

- an oxidation agent, and

- at least one mediator selected from the group consisting of aliphatic, cyclo-aliphatic, heterocyclic or aromatic compounds containing the moiety >N-OH, and

- optionally additives.

In the present invention the term "mediator" means an additional oxidizable substance improving the bleaching performance.

By suitable combination of mediator and enzyme it is possible to avoid bleaching of the dyed textile while bleaching dyes in solution, thereby reducing the amount of unbleached dye deposited on the fibres and thus increasing the wet fastness of the dyed or printed textile.

By this process it is furthermore possible to reduce the number of rinsing steps and the temperature of the rinsing water in the rinsing steps compared to the conventional processes, thereby saving energy and costs.

Another object of the present invention is a system for removal of excess dye from newly manufactured printed or dyed fabric or yarn, which is a multi-component system comprising at least one enzyme selected from the group consisting of enzymes exhibiting peroxidase activity or laccase activity, an oxidation agent, and at least one mediator selected from the group consisting of aliphatic, cyclo-aliphatic, heterocyclic or aromatic compounds containing the moiety >N-OH, and optionally additives, such as rinsing additives.

The components of the system may be combined as a solution, a slurry or granulates depending on the specific enzymes and mediators selected.

A further object of the present invention is the use of the components specified above for the preparation of a multi-

component system for removal of excess dye or print from newly manufactured fabric or yarn.

DETAILED DESCRIPTION OF THE INVENTION

5

Fabric or yarn

The process of the invention is applicable to all types of textile materials, both natural fibres and synthetic fibres as well as blends thereof. Typical examples are cellulosic fibres (cotton and flax), modified cellulose fibres (e.g. acetate and triacetate), protein fibres (e.g. wool and silk), polyamide fibres (e.g. nylon 6 and 6,6), polyester fibres (e.g. poly(ethylene terephthalate)) and acrylic fibres.

The process of the invention may be applied to dyed yarn, to knitted, woven or non-woven fabric, or to garments made from dyed and/or printed fabric, especially garments made from differently coloured material.

Printing method

The process of the invention is suited for excess dye bleaching after any kind of textile printing. Examples of commonly used techniques are printing on a Rotation film, a Rouleaux, a Flash film, or a Transfer film device. After printing the dye is fixed on the textile by e.g. steaming or treatment with hot air.

Dyeing method

The process of the invention is suited for excess dye bleaching after any kind of dyeing. The dyeing of textiles is for example carried out by passing the fabric through a concentrated solution of dye, followed by storage of the wet fabric in a vapour tight enclosure to permit time for diffusion and reaction of the dye with the fabric substrate prior to rinsing off un-reacted dye. Alternatively, the dye may be fixed by subsequent steaming of the textile prior to rinsing.

The process applies to any kind of dyes, such as reactive dyes.

Enzyme

Enzymes exhibiting peroxidase activity or laccase activity are those which by using hydrogen peroxide or molecular oxygen, respectively are capable of oxidising a variety of compounds, such as phenols and aromatic amines.

According to the invention the concentration of enzyme is 0.005 to 5 mg enzyme protein per l of rinse liquor, preferably, 0.02 to 2 mg enzyme protein per l of rinse liquor, more preferably 0.05 to 1 mg enzyme protein per l of rinse liquor. According to the liquor ratio, this may be translated to dosages of enzyme per kg of fabric, e.g. at a liquor ratio of 10:1, the most preferred enzyme dosage is from 0.5 to 10 mg enzyme per kg of textile fabric.

15 Peroxidase activity exhibiting enzymes

An enzyme exhibiting peroxidase activity may be any peroxidase comprised by the enzyme classification (EC 1.11.1.7), or a haloperoxidase, such as a chloride peroxidase (EC 1.11.1.10) or any fragment or synthetic or semisynthetic derivatives thereof exhibiting enzymatic activity (e.g. porphyrin ring systems or microperoxidases, cf. e.g. US 4,077,768, EP 537 381, WO 91/05858 and WO 92/16634). Such enzymes are known from microbial, plant and animal origins.

Preferably, the peroxidase employed in the method of the invention is producible by plants (e.g. horseradish or soybean peroxidase), in particular soybean peroxidase, or by microorganisms, such as fungi (including filamentous fungi and yeasts) or bacteria.

Some preferred fungi include strains belonging to the subdivision *Deuteromycotina*, class *Hyphomycetes*, e.g., *Fusarium*, *Humicola*, *Trichoderma*, *Myrothecium*, *Verticillum*, *Arthromyces*, *Caldariomyces*, *Ulocladium*, *Embellisia*, *Cladosporium* or *Dreschlera*, in particular *Fusarium oxysporum* (DSM 2672), *Humicola insolens*, *Trichoderma reesii*, *Myrothecium verrucana* (IFO 6113), *Verticillum alboatrum*, *Verticillum dahlie*, *Arthromyces ramosus* (FERM P-7754), *Caldariomyces fumago*, *Ulocladium chartarum*, *Embellisia alli* or *Dreschlera halodes*.

Other preferred fungi include strains belonging to the subdivision *Basidiomycotina*, class *Basidiomycetes*, e.g. *Coprinus*, *Phanerochaete*, *Coriolus* or *Trametes*, in particular *Coprinus cinereus* f. *microsporus* (IFO 8371), *Coprinus macrorhizus*, *Phanero-*
5 *chaete chrysosporium* (e.g. NA-12) or *Trametes* (some classes previously called *Polyporus* have been renamed to *Trametes*), e.g., *T. versicolor* (e.g. PR4 28-A).

Further preferred fungi include strains belonging to the subdivision *Zygomycotina*, class *Mycoraceae*, e.g. *Rhizopus* or *Mu-*
10 *cor*, in particular *Mucor hiemalis*.

Some preferred bacteria include strains of the order *Actinomycetales*, e.g., *Streptomyces spheroides* (ATTC 23965), *Streptomyces thermoviolaceus* (IFO 12382) or *Streptoverticillum verticillium* ssp. *verticillium*.

15 Other preferred bacteria include *Bacillus pumilus* (ATCC 12905), *Bacillus stearothermophilus*, *Rhodobacter sphaeroides*, *Rhodomonas palustri*, *Streptococcus lactis*, *Pseudomonas purrocinia* (ATCC 15958) or *Pseudomonas fluorescens* (NRRL B-11).

Further preferred bacteria include strains belonging to
20 *Myxococcus*, e.g., *M. virescens*.

The peroxidase may furthermore be one which is producible by a method comprising cultivating a host cell transformed with a recombinant DNA vector which carries a DNA sequence encoding said peroxidase as well as DNA sequences encoding functions per-
25 mitting the expression of the DNA sequence encoding the peroxidase, in a culture medium under conditions permitting the expression of the peroxidase, and recovering the peroxidase from the culture.

Particularly, a recombinantly produced peroxidase is a per-
30 oxidase derived from a *Coprinus* sp., in particular *C. macrorhizus* or *C. cinereus* according to WO 92/16634, or a variant thereof.

In the context of this invention, peroxidase acting compounds comprise peroxidase active fragments derived from cyto-
35 chromes, hemoglobin or peroxidase enzymes, and synthetic or

semisynthetic derivatives thereof, e.g. iron complexes of porphyrin or phthalocyanine and derivatives thereof.

Laccase and laccase related enzymes

5 In the context of this invention, the term "enzymes exhibiting laccase activity" means laccases and laccase related enzymes, such as any laccase comprised by the enzyme classification (EC 1.10.3.2), any catechol oxidase comprised by the enzyme classification (EC 1.10.3.1), any bilirubin oxidase comprised by
10 the enzyme classification (EC 1.3.3.5) or any monophenol monooxygenase comprised by the enzyme classification (EC 1.14.99.1).

The laccases are known from microbial and plant origin. The microbial laccases may be derived from bacteria or fungi (including filamentous fungi and yeasts) and suitable examples
15 include a laccase derivable from a strain of *Aspergillus*, *Neurospora*, e.g., *N. crassa*, *Podospora*, *Botrytis*, *Collybia*, *Fomes*, *Lentinus*, *Pleurotus*, *Trametes*, e.g., *T. villosa* and *T. versicolor*, *Rhizoctonia*, e.g., *R. solani*, *Coprinus*, e.g. *C. plicatilis* and *C. cinereus*, *Psatyrella*, *Myceliophthora*, e.g. *M. thermophila*, *Schytalidium*, *Polyporus*, e.g., *P. pinsitus*, *Phlebia*,
20 e.g., *P. radiata* (WO 92/01046), or *Coriolus*, e.g., *C. hirsutus* (JP 2-238885), in particular a laccase derivable from a strain of *Fomes*, *Trametes*, *Rhizoctonia*, *Coprinus*, *Myceliophthora*, *Schytalidium*, or *Polyporus*.

25 The laccase or the laccase related enzyme may furthermore be one which is producible by a method comprising cultivating a host cell transformed with a recombinant DNA vector which carries a DNA sequence encoding said laccase as well as DNA sequences encoding functions permitting the expression of the DNA
30 sequence encoding the laccase, in a culture medium under conditions permitting the expression of the laccase, and recovering the laccase from the culture.

Oxidation agent

35 If the oxidizing enzyme requires a source of hydrogen peroxide, the source may be hydrogen peroxide or a hydrogen peroxide precursor for in situ production of hydrogen peroxide, e.g.,


a percarbonate or a perborate, a persulfate, such as a tri-oxo(peroxo)sulfate or a μ -peroxo-bis(trioxosulfate), a hydrogen peroxide-urea addition compound, a peroxy-carboxylic acid or a salt thereof or a hydrogen peroxide generating enzyme system, e.g., an oxidase and a substrate for the oxidase, e.g. an amino acid oxidase and a suitable amino acid.

Hydrogen peroxide may be added at the beginning of or during the process, e.g., in a concentration corresponding to 0.01-50 mM H_2O_2 , preferably 0.1 to 5 mM.

If the oxidizing enzyme requires molecular oxygen, molecular oxygen from the atmosphere will usually be present in sufficient quantity. Otherwise pure O_2 may be led to the rinse liquor, or an O_2 generating enzymatic system, e.g. a system based on hydrogen peroxide and a catalase, may be added.

Mediator

According to the invention at least one mediator selected from the group consisting of aliphatic, cyclo-aliphatic, heterocyclic or aromatic compounds containing the moiety $>N-OH$ is added to the rinse liquor. In a preferred embodiment of the invention the mediator is a compound of the general formula I:




wherein R^1 , R^2 , R^3 , R^4 are individually selected from the group consisting of hydrogen, halogen, hydroxy, formyl, carboxy and salts and esters thereof, amino, nitro, C_1 - C_{12} alkyl, C_1 - C_6 alkoxy, carbonyl(C_1 - C_{12} alkyl), aryl, in particular phenyl, sulfo, amino-sulfonyl, carbamoyl, phosphono, phosphonoxy, and salts and esters thereof, wherein the R^1 , R^2 , R^3 , R^4 may be substituted with R^5 , wherein R^5 represents hydrogen, halogen, hydroxy, formyl, carboxy and salts and esters thereof, amino, nitro, C_1 - C_{12} alkyl, C_1 - C_6 alkoxy, carbonyl(C_1 - C_{12} alkyl), aryl, in particular phenyl, sulfo, aminosulfonyl, carbamoyl, phosphono, phosphonoxy, and salts and esters thereof,

[X] represents a group from $(-N=N-)$, $(-N=CR^6-)_m$, $(-CR^6=N-)_m$, $(-CR^7=CR^8-)_m$,

and m is 1 or 2.

- 5 In a more preferred embodiment of the invention the mediator is a compound of the general formula II:



wherein R^1 , R^2 , R^3 , R^4 are individually selected from the group
 10 consisting of hydrogen, halogen, hydroxy, formyl, carboxy and salts and esters thereof, amino, nitro, C_1 - C_{12} alkyl, C_1 - C_6 alkoxy, carbonyl(C_1 - C_{12} alkyl), aryl, in particular phenyl, sulfo, amino-sulfonyl, carbamoyl, phosphono, phosphonooxy, and salts and es-
 15 R^5 , wherein R^5 represents hydrogen, halogen, hydroxy, formyl, carboxy and salts and esters thereof, amino, nitro, C_1 - C_{12} alkyl, C_1 - C_6 alkoxy, carbonyl(C_1 - C_{12} alkyl), aryl, in particular phenyl, sulfo, aminosulfonyl, carbamoyl, phosphono, phosphonooxy, and salts and esters thereof.

20 The mediator may also be a salt or an ester of formula I or II.

Further preferred mediators are oxoderivatives and N-hydroxy derivatives of heterocyclic compounds and oximes of oxo- and formyl-derivatives of heterocyclic compounds, said heterocyclic
 25 cyclic compounds including five-membered nitrogen-containing heterocycles, in particular pyrrol, pyrazole and imidazole and their hydrogenated counterparts (e.g. pyrrolidine) as well as triazoles, such as 1,2,4-triazole; six-membered nitrogen-containing heterocycles, in particular mono-, di- and triaz-
 30 inanes (such as piperidine and piperazine), morpholine and their unsaturated counterparts (e.g. pyridine and pyrimidine); and condensed heterocycles containing the above heterocycles as sub-

structures, e.g. indole, benzothiazole, quinoline and benzazepine.

Examples of preferred mediators from these classes of compounds are pyridine aldoximes; N-hydroxypyrrolidinediones such as N-hydroxysuccinimide and N-hydroxyphthalimide; 3,4-dihydro-3-hydroxybenzo[1,2,3]triazine-4-one; formaldoxime trimer (N,N',N''-trihydroxy-1,3,5-triazinane); and violuric acid (1,3-diazinane-2,4,5,6-tetrone-5-oxime).

Still further mediators which may be applied in the invention include oximes of oxo- and formyl-derivatives of aromatic compounds, such as benzoquinone dioxime and salicylaldehyde oxime (2-hydroxybenzaldehyde oxime), and N-hydroxyamides and N-hydroxyanilides, such as N-hydroxyacetanilide.

Preferred mediators are selected from the group consisting of 1-hydroxybenzotriazole; 1-hydroxybenzotriazole hydrate; 1-hydroxybenzotriazole sodium salt; 1-hydroxybenzotriazole potassium salt; 1-hydroxybenzotriazole lithium salt; 1-hydroxybenzotriazole ammonium salt; 1-hydroxybenzotriazole calcium salt; 1-hydroxybenzotriazole magnesium salt; and 1-hydroxybenzotriazole-6-sulphonic acid.

A particularly preferred mediator is 1-hydroxybenzotriazole.

All the specifications of N-hydroxy compounds above are understood to include tautomeric forms such as N-oxides whenever relevant.

Usually, the concentration of mediator in the rinse liquor is from 0.1 μM to 50 mM, preferably 1 μM to 1 mM, more preferably 10 μM to 0.5 mM.

30 Additives

The rinse liquor may comprise further additives, such as surfactants and/or water conditioning agents.

Multi-component system

35 In order to carry out the process described above a multi-component system is added to the rinse liquor in at least one of the rinsing steps.

The components of the multi-component system may individually be in one of several product forms, such as a slurry, a solution or a granulate.

In one embodiment of the invention two components are mixed
5 in the represented form, such as a co-granulate, a solution or a slurry comprising enzyme and mediator.

In cases of co-granulates, the co-granulate may comprise at least one enzyme and at least one mediator. Another example of a co-granulate is a granulate comprising at least two different
10 enzymes and optionally at least one mediator.

In a further embodiment the system is a mixture of granulates wherein the component(s) in one granulate is(are) enzyme(s) and the component(s) in another granulate is(are) mediator(s).

15 According to the present invention a preferred multi-component system comprises at least one enzyme selected from the group consisting of enzymes exhibiting peroxidase activity or laccase activity, optionally an oxidation agent, and at least one mediator selected from the group consisting of aliphatic,
20 cyclo-aliphatic, heterocyclic or aromatic compounds containing the moiety >N-OH as described above, and optionally additives, such as rinsing additives.

The enzymes exhibiting peroxidase activity or laccase activity are preferably as described above.

25 The system may comprise an oxidation agent, but in cases where the enzyme is an enzyme exhibiting laccase activity, molecular oxygen from the atmosphere is normally sufficient, and the system used will not comprise an oxidation agent. However, when the enzymes used require addition of an oxidation agent
30 those are as described above. In all cases wherein a H₂O₂ source is the oxidation agent the enzyme and oxidation agent may not be mixed before use.

The mediator is as described above, in a preferred embodiment the mediator is selected from the group consisting of oxid-
35 erivatives and N-hydroxy derivatives of heterocyclic compounds and oximes of oxo- and formyl-derivatives of heterocyclic compounds, said heterocyclic compounds including five-membered nitrogen-containing heterocycles, in particular pyrrol, pyrazole and imidazole and their hydrogenated counterparts (e.g. pyr-

rolidine) as well as triazoles, such as 1,2,4-triazole; six-membered nitrogen-containing heterocycles, in particular mono-, di- and triazinanes (such as piperidine and piperazine), morpholine and their unsaturated counterparts (e.g. pyridine and pyrimidine); and condensed heterocycles containing the above heterocycles as substructures, e.g. indole, benzothiazole, quinoline and benzoazepine.

Examples of preferred mediators from these classes of compounds are pyridine aldoximes; N-hydroxypyrrolidinediones such as N-hydroxysuccinimide and N-hydroxyphthalimide; 3,4-dihydro-3-hydroxybenzo[1,2,3]triazine-4-one; formaldoxime trimer (N,N',N''-trihydroxy-1,3,5-triazinane); and violuric acid (1,3-diazinane-2,4,5,6-tetrone-5-oxime).

Still further mediators which may be applied in the invention include oximes of oxo- and formyl-derivatives of aromatic compounds, such as benzoquinone dioxime and salicylaldoxime (2-hydroxybenzaldehyde oxime), and N-hydroxyamides and N-hydroxyanilides, such as N-hydroxyacetanilide.

A particularly preferred mediator is 1-hydroxybenzotriazole.

All the specifications of N-hydroxy compounds above are understood to include tautomeric forms such as N-oxides whenever relevant.

A further aspect of the present invention is the use of components comprising

- at least one enzyme selected from the group consisting of enzymes exhibiting peroxidase activity or laccase activity,

- optionally an oxidation agent, and

- at least one mediator selected from the group consisting of aliphatic, cyclo-aliphatic, heterocyclic or aromatic compounds containing the moiety >N-OH, and

35

- optionally additives

for the preparation of a multi-component system for removal of excess dye or print from newly manufactured fabric or yarn.

Process conditions

The removal of excess dye, according to the invention, may comprise rinsing with rinse liquor in 2 to 6 rinsing steps, more preferred in 2 to 5 rinsing steps, even more preferred in 2 to 4 rinsing steps, in particular in 3 to 4 rinsing steps. The amount of rinsing steps is dependent on the concentration of the mediator and of the concentration of the peroxidase.

The multi-component system as defined according to this invention may be used in any of the rinsing steps performed, however it is preferably added in one of the last rinsing steps, in particular in the third or fourth rinsing step.

The process may be run in batch mode or continuous mode. The process may be applied on a winch, a beck, a jet dyer, an open-width washing machine, a J or U box, a steamer, or any other equipment available suitable for a rinsing process.

The process conditions must be chosen according to the characteristics of the enzyme in question. The temperature at the rinsing step comprising a multi-component system as defined above is preferably ranging from 40°C to 80°C, such as from 50°C to 70°C, and pH is typically in the range of 5.5-9.5, such as 6.5-9.

Fatness

Fatness (wet, crock, light, etc.) may be measured by various methods as known in the art. Wet fastness may be measured as described below. Colourfastness to crocking, which is designed to determine the amount of colour transferred from the surface of coloured materials to other surfaces by rubbing, may be measured according to AATCC Test Method 8-1996. Colourfastness to light, in which samples of the material to be tested and the agreed upon comparison standard(s) are exposed simultaneously to a light source under specified conditions, may be measured according to AATCC Test Method 16-1993.

35

Wet fastness

The multi-component system as defined above is added to the rinsing liquor to prevent re-deposition of solubilised excess dye by bleaching it in solution.

5 The wet fastness or water fastness reflects the degree to which this has successfully been achieved.

In the present invention the wet fastness is measured by the standard method (DIN 54 006). Briefly, the method comprises soaking a dyed fabric and pressing it together with swatches of white fabric. After separate drying of the fabrics, the swatches
10 are evaluated for staining.

The degree of wet fastness is indicated on a scale, the higher number the better wet fastness. 1 means very low wet fastness, whereas 5 means very high wet fastness.

15 Colour measurement (Example 5)

A Gretag-Mecbath Colour Eye 3100 was used according to the manufacturer's instructions to evaluate the chromaticity using the change in the colour space coordinates $L^*a^*b^*$ (CIELAB-system), where as usual:

20 L^* gives the change in white/black on a scale from 0 to 100, and a decrease in L^* means an increase in black colour (decrease in white colour) and an increase in L^* means an increase in white colour (decrease in black colour).

25 a^* gives the change in red/green, and a decrease in a^* means an increase in green colour (decrease in red colour), and an increase in a^* means an increase in red colour (decrease in green colour).

30 b^* gives the change in blue/yellow, and a decrease in b^* means an increase in blue colour (decrease in yellow colour), and an increase in b^* means an increase in yellow colour (decrease in blue colour) (Vide WO 96/12846 NOVO).

The Gretag-Macbeth Colour Eye 3100 was operated in the $L^*a^*b^*$ colour space. The light source was D65 standard light. The software used for evaluation was Optiview Quality Control
35 1.7c. The observation angle was 10° . The instrument was calibrated using a Macbeth calibration plate (white). Each result was an average of 10 measurements. Fabric rinsed without enzyme and mediator was measured and the coordinates $L^*a^*b^*$ were calculated and entered as a reference. The coordinates of the samples

were then for each of L^* , a^* , b^* calculated as the difference (Δ) of the average of the measurements on each swatch from the reference value.

The present invention is further illustrated in the following examples which are not in any way intended to limit the scope of the invention as claimed.

Example 1

10 Reactive dyeing of cotton fabric followed by an enzymatic rinsing process

Knitted, bleached 100 % cotton was dyed in a Mathis jet-dyer (laboratory scale jet dyeing machine) under the following conditions:

Water:	softened water, 10 l/kg of fabric	
Temperature:	50°C	
Dyestuff:	4 % LEVAFIX Scarlet E-2GA (Reactive Red 123)	
20 Na ₂ SO ₄ :	50 g/l	
Na ₂ CO ₃ :	4 g/l	
NaOH (32 %):	2 ml/l	
LEVEGAL RL:	1.0 g/l	(levelling agent)
ERKANTOL NR:	1.0 g/l	(wetting agent)
25 PERSOFTAL L:	1.0 g/l	(crease-preventing agent)
RESPUMIT S:	1.0 g/l	(antifoaming agent)

LEVAFIX Scarlett E-2GA is a product of DyStar.

30 LEVEGAL RL, ERKANTOL NR, PERSOFTAL L and RESPUMIT S are products of BAYER.

The dyeing process started at 50°C by addition of dyestuff, Na₂SO₄, LEVEGAL RL, ERKANTOL NR, PERSOFTAL L and RESPUMIT S. 35 Na₂CO₃ was added 30 minutes after start and NaOH 60 minutes after start. During the whole process the temperature was held at 50°C.

60 minutes after addition of NaOH the dyeing process was stopped by draining off the dyeing liquor, whereafter the rinsing process was started.

- 5 The rinsing process was carried out as follows:

First rinsing step:

Addition of fresh softened water; 10 l/kg fabric.

Rinsing 10 minutes at 40°C.

- 10 Draining the rinsing liquor.

Second rinsing step:

Addition of fresh softened water; 10 l/kg fabric.

Addition of 10 ml/l of acetic acid (6 % solution in water)

Rinsing 20 minutes at 95°C.

- 15 Draining the rinsing liquor.

Third rinsing step:

Addition of fresh softened water; 10 l/kg fabric.

Addition of 5.0 ml/l of potassium phosphate buffer (1.0 M, pH=7.0)

- 20 Rinsing 40 minutes at 60°C.

Addition of 0.8 mg/l Peroxidase SP502, 55 mg/l (0.4 mM) HOBt and 39 mg/l (0.4 mM) H₂O₂ (35 % solution in water)

Rinsing 10 minutes at 60°C.

Draining the rinsing liquor.

25

SP502 was a liquid preparation of recombinant *Coprinus cinereus* peroxidase supplied by Novo Nordisk A/S (produced as described in WO 92/16634). HOBt was 1-hydroxybenzotriazole ex Sigma.

- 30 The fabric was squeezed and dried. The wet fastness was determined according to DIN 54 006. The degree of fastness was found to be 3 (adjacent fabric cotton).

Example 2 (for comparison)

35

Conventional 3 step rinsing process

The dyeing process was carried out as described in Example 1. The rinsing steps were carried out as follows.

First rinsing step:

5 Addition of fresh softened water; 10 l/kg fabric.

Rinsing 10 minutes at 40°C.

Draining the rinsing liquor.

Second rinsing step:

Addition of fresh softened water; 10 l/kg fabric.

10 Rinsing 20 minutes at 95°C.

Draining the rinsing liquor.

Third rinsing step:

Addition of fresh softened water; 10 l/kg fabric.

Rinsing 10 minutes at 80°C.

15 Draining the rinsing liquor.

The fabric was squeezed and dried. The wet fastness was determined according to DIN 54 006. The degree of fastness was found to be 2 (adjacent fabric cotton).

20 **Example 3 (for comparison)**

Conventional 4 step rinsing process

The dyeing process was carried out as described in Example 1.

25 The rinsing steps were carried out as follows.

First rinsing step:

Addition of fresh softened water; 10 l/kg fabric.

Rinsing 10 minutes at 40°C.

Draining the rinsing liquor.

30 *Second rinsing step:*

Addition of fresh softened water; 10 l/kg fabric.

Rinsing 10 minutes at 70°C.

Draining the rinsing liquor.

Third rinsing step:

35 Addition of fresh softened water; 10 l/kg fabric.

Rinsing 20 minutes at 95°C.

Draining the rinsing liquor.

Fourth rinsing step:

Addition of fresh softened water; 10 l/kg fabric.

Rinsing 10 minutes at 40°C.

5 Draining the rinsing liquor.

The fabric was squeezed and dried. The wet fastness was determined according to DIN 54 006. The degree of fastness was found to be 2-3 (adjacent fabric cotton).

10 **Example 4 (for comparison)**

Conventional 6 step rinsing process

The dyeing process was carried out as described in Example 1.

15 The rinsing steps were carried out as follows.

First rinsing step:

Addition of fresh softened water; 10 l/kg fabric.

Rinsing 10 minutes at 40°C.

Draining the rinsing liquor.

20 *Second rinsing step:*

Addition of fresh softened water; 10 l/kg fabric.

Rinsing 10 minutes at 70°C.

Draining the rinsing liquor.

Third rinsing step:

25 Addition of fresh softened water; 10 l/kg fabric.

Rinsing 10 minutes at 70°C.

Draining the rinsing liquor.

Fourth rinsing step:

Addition of fresh softened water; 10 l/kg fabric.

30 Rinsing 20 minutes at 95°C.

Draining the rinsing liquor.

Fifth rinsing step:

Addition of fresh softened water; 10 l/kg fabric.

Rinsing 10 minutes at 70°C.

35 Draining the rinsing liquor.

Sixth rinsing step:

Addition of fresh softened water; 10 l/kg fabric.

Rinsing 10 minutes at 40°C.

Draining the rinsing liquor.

- 5 The fabric was squeezed and dried. The wet fastness was determined according to DIN 54006. The degree of fastness was found to be 3 (adjacent fabric cotton).

10 Conclusion: The wet fastness 3 (corresponding to the conventional 6 step rinsing process) was also obtained by the process according to the invention (see Example 1), whereby a substantial amount of rinsing steps can be avoided (saving water and energy and process time).

15 **Example 5**

Reactive dyeing of cotton fabric followed by enzymatic rinsing processes using two different mediators

- 20 Knitted, bleached 100 % cotton was dyed in a Mathis jet-dyer (laboratory scale jet dyeing machine) at the following conditions:

Water: softened water, 10 l/kg of fabric

- 25 Dyestuff: 1 % Remazol Yellow RR
1 % Remazol Red RR
1 % Remazol Blue RR

Na₂SO₄: 70 g/l

Na₂CO₃: 5 g/l

- 30 NaOH (32 % in water): 3 ml/l

LEVEGAL RL: 1.0 g/l (levelling agent)

ERKANTOL NR: 1.0 g/l (wetting agent)

PERSOFTAL L: 1.0 g/l (crease-preventing agent)

35

Remazol Yellow RR, Remazol Red RR, and Remazol Blue RR are products of DyStar.

LEVEGAL RL, ERKANTOL NR, and PERSOFTAL L are products of BAYER.

The dyeing process started at 30°C by addition of Na₂CO₃, NaOH (1 ml/l), Na₂SO₄, LEVEGAL RL, ERKANTOL NR, PERSOFTAL L. The dye-
5 stuffs were added 15 minutes after start. 30 minutes after start
the temperature was increased up to 50°C within 20 minutes. 30
minutes after reaching 50°C the remaining NaOH (2 ml/l) was
added. 45 minutes after the addition of NaOH (2 ml/l) the dyeing
process was finished by draining off the dyeing liquor, whereaf-
10 ter the rinsing process was started.

The following rinsing process was carried out for each mediator
(1-hydroxybenzotriazole (according to the invention); and methyl
syringate (comparison)):

15

First rinsing step:

Addition of fresh softened water; 10 l/kg fabric.

Rinsing 10 minutes at 40°C.

Draining the rinsing liquor.

20

Second rinsing step:

Addition of fresh softened water; 10 l/kg fabric.

Addition of 10 ml/l of acetic acid (6 % solution in water)

Rinsing 20 minutes at 95°C.

Draining the rinsing liquor.

25

Third rinsing step:

Addition of fresh softened water; 10 l/kg fabric.

Addition of 5.0 ml/l of potassium phosphate buffer (1.0 M,
pH=7.0)

Rinsing 40 minutes at 60°C.

30

Addition of 0.8 mg/l Peroxidase SP502, 0.4 mM mediator and
39 mg/l (0.4 mM) H₂O₂ (35 % solution in water)

Rinsing 10 minutes at 60°C.

Draining the rinsing liquor.

35

SP502 was a liquid preparation of recombinant *Coprinus cinereus*
peroxidase supplied by Novo Nordisk A/S.

The fabric was squeezed and dried. A colour measurement was performed using a colour measuring instrument (Gretag-Macbeth Colour Eye 3100) as described above.

5

Results:

Mediator: 1-hydroxybenzotriazole

$\Delta L^* = 0.756$

$\Delta a^* = 0.045$

10

$\Delta b^* = 0.022$

Mediator: Methyl syringate

$\Delta L^* = 3.142$

$\Delta a^* = 0.134$

15

$\Delta b^* = 0.834$

Conclusion: It can be seen that methyl syringate has a significant and undesired influence on the chromaticity of the fabric. The positive Δb^* of 0.834 indicates a very strong and not acceptable increase in yellow colour whereas a Δb^* of 0.022 which is found for 1-hydroxybenzotriazole is negligible and not visible. It is seen that also ΔL^* and Δa^* are significantly smaller in the treatment according to the invention than in the comparison treatment.

25

Example 6

Enzymatic bleaching of soluble dyes

30 The dyes tested were Reactive Black 5 (Remazol Black B), Reactive Red 198 (Remazol Red RB), Reactive Blue 220 (Remazol Brilliant Blue BB), Reactive Blue 21 (Remazol Turquoise Blue G), and Reactive Orange 107 (Remazol Golden Yellow RNL), all ex Dystar. All dyes were dissolved in a 0.5 mM sodium phosphate buffer (pH 35 7.0) to an initial absorbance of approximately 0.4 at the wavelength λ_{max} of maximum absorbance within the visible range. The solutions were then placed in a thermostated quartz cell in a HP

8453 diode array spectrophotometer, the three components of the enzymatic oxidation system were added (CiP to 0.2 mg/l, HOBT to 100 μ M, hydrogen peroxide to 200 μ M), and the absorbance ABS(λ max) at λ max monitored over time. The degree of bleaching at 5 min, i.e. the decrease in ABS(λ max) over 5 min divided by ABS(λ max) at t = 0, is shown below, measured at three temperatures.

Degree of bleaching at 5 min(%) :

10

Reactive Black 5 (λ max=596 nm):

79 (60°C); 82 (70°C); 72 (80°C);

Reactive Red 198 (λ max=517 nm):

15

97 (60°C); 100 (70°C); 88 (80°C);

Reactive Blue 220 (λ max=608 nm):

100 (60°C); 98 (70°C); 30 (80°C);

20

Reactive Blue 21 (λ max=663 nm):

100 (60°C); 88 (70°C); 61 (80°C);

Reactive Orange 107 (λ max=408 nm):

90 (60°C); 67 (70°C); 36 (80°C).

25

This example demonstrates that one of the preferred mediators according to the invention, HOBT (1-hydroxybenzotriazole), combined with *Coprinus cinereus* peroxidase (CiP) and hydrogen peroxide, provides high degrees of bleaching of soluble dyes in short time with a range of reactive dyes.

30

Claims:

1. A process for removal of excess dye from newly manufactured printed or dyed fabric or yarn, comprising treatment with a
5 rinse liquor comprising
- at least one enzyme selected from the group consisting of enzymes exhibiting peroxidase activity or laccase activity,
 - 10 - an oxidation agent, and
 - at least one mediator selected from the group consisting of aliphatic, cyclo-aliphatic, heterocyclic or aromatic compounds containing the moiety >N-OH, and
 - 15 - optionally additives.
2. A process according to claim 1, wherein the enzyme is a laccase (EC 1.10.3.2), a catechol oxidase (EC 1.10.3.1), a bilirubin oxidase (EC 1.3.3.5), a peroxidase (EC 1.11.1.7), or a haloperoxidase, such as a chloride peroxidase (EC 1.11.1.10) or any fragment derived therefrom exhibiting enzymatic activity or synthetic or semisynthetic derivatives thereof.
- 25 3. A process according to claim 2, wherein the peroxidase is derived from a strain of *Coprinus* or from soybean.
4. A process according to claim 2, wherein the laccase is derived from a strain of *Fomes*, *Trametes*, *Rhizoctonia*, *Coprinus*,
30 *Myceliophthora*, *Schytalidium*, or *Polyporus*.
5. A process according to any of the preceding claims, wherein the amount of enzyme is 0.005 to 5 mg enzyme protein per l of rinse liquor, preferably, 0.02 to 2 mg enzyme protein per l of
35 rinse liquor, more preferably 0.05 to 1 mg enzyme protein per l of rinse liquor.

6. A process according to any of the preceding claims, wherein the oxidation agent is a H₂O₂ source.


7. A process according to claim 6, wherein the H₂O₂ source is hydrogen peroxide, a perborate, a percarbonate, a persulfate, a peroxy-carboxylic acid or a salt thereof, or an enzymatic system capable of generating hydrogen peroxide.

8. A process according to claim 7, wherein the concentration of H₂O₂ is from 0.01 to 50 mM, preferably 0.1 to 5 mM.

9. A process according to any of the claims 1-5, wherein the oxidation agent is a O₂ source.

10. A process according to claim 9, wherein the O₂ source is air, pure O₂, or an O₂ generating enzymatic system.

11. A process according to any of the preceding claims, wherein the mediator is a compound of the general formula I:




wherein R¹, R², R³, R⁴ are individually selected from the group consisting of hydrogen, halogen, hydroxy, formyl, carboxy and salts and esters thereof, amino, nitro, C₁-C₁₂ alkyl, C₁-C₆ alkoxy, carbonyl(C₁-C₁₂ alkyl), aryl, in particular phenyl, sulfo, aminosulfonyl, carbamoyl, phosphono, phosphonoxy, and salts and esters thereof, wherein the R¹, R², R³, R⁴ may be substituted with R⁵, wherein R⁵ represents hydrogen, halogen, hydroxy, formyl, carboxy and salts and esters thereof, amino, nitro, C₁-C₁₂ alkyl, C₁-C₆ alkoxy, carbonyl(C₁-C₁₂ alkyl), aryl, in particular phenyl, sulfo, aminosulfonyl, carbamoyl, phosphono, phosphonoxy, and salts and esters thereof,

[X] represents a group from $(-N=N-)$, $(-N=CR^6-)_m$, $(-CR^6=N-)_m$, $(-CR^7=CR^8-)_m$,

and m is 1 or 2.

5

12. A process according to claim 11, wherein the mediator is a compound of the general formula II:



10

wherein R^1 , R^2 , R^3 , R^4 are as defined in claim 11 or a salt or an ester thereof.

15

13. A process according to claim 12, wherein the mediator is 1-hydroxybenzotriazole.

20

14. A process according to any of the preceding claims, wherein the concentration of mediator in the rinse liquor is from 0.1 μ M to 50 mM, preferably 1 μ M to 1 mM, more preferably 10 μ M to 0.5 mM.

15. A process according to any of the preceding claims, wherein the additives are surfactants and/or water conditioning agents.

25

16. A process according to any of the preceding claims, wherein the dye or print is a reactive dye.

30

17. A system for removal of excess dye from newly manufactured printed or dyed fabric or yarn, which is a multi-component system comprising

- at least one enzyme selected from the group consisting of enzymes exhibiting peroxidase activity or laccase activity,

- optionally an oxidation agent, and

- at least one mediator selected from the group consisting of aliphatic, cyclo-aliphatic, heterocyclic or aromatic compounds
5 containing the moiety >N-OH, and

- optionally additives.

10 18. A system according to claim 17, wherein the enzyme is a laccase (EC 1.10.3.2), a catechol oxidase (EC 1.10.3.1), a bilirubin oxidase (EC 1.3.3.5), a peroxidase (EC 1.11.1.7), or a haloperoxidase, such as a chloride peroxidase (EC 1.11.1.10) or any fragment derived therefrom exhibiting enzymatic activity or synthetic or semisynthetic derivatives.

15

19. A system according to claim 18, wherein the peroxidase is derived from a strain of *Coprinus* or from soybean.

20

20. A system according to claim 18, wherein the laccase is derived from a strain of *Fomes*, *Trametes*, *Rhizoctonia*, *Coprinus*, *Myceliophthora*, *Schytalidium*, or *Polyporus*.

25

21. A system according to any of the claims 17-20, wherein the oxidation agent is a H₂O₂ source.

30

22. A system according to claim 21, wherein the H₂O₂ source is hydrogen peroxide, a perborate, a percarbonate, a persulfate, a peroxy-carboxylic acid or a salt thereof, or an enzymatic system capable of generating hydrogen peroxide.


23. A system according to claim 22, wherein the concentration of H₂O₂ is from 0.01 to 50 mM, preferably 0.1 to 5 mM.

35

24. A system according to any of the claims 17-20, wherein the oxidation agent is a O₂ source.

25. A system according to claim 24, wherein the O₂ source is air, pure O₂, or an O₂ generating enzymatic system.

26. A system according to any of the claims 17-25, wherein the mediator is a compound of the general formula I:



5


wherein R^1 , R^2 , R^3 , R^4 are individually selected from the group consisting of hydrogen, halogen, hydroxy, formyl, carboxy and salts and esters thereof, amino, nitro, C_1 - C_{12} alkyl, C_1 - C_6 alkoxy, carbonyl(C_1 - C_{12} alkyl), aryl, in particular phenyl, sulfo, amino-sulfonyl, carbamoyl, phosphono, phosphonoxy, and salts and esters thereof, wherein the R^1 , R^2 , R^3 , R^4 may be substituted with R^5 , wherein R^5 represents hydrogen, halogen, hydroxy, formyl, carboxy and salts and esters thereof, amino, nitro, C_1 - C_{12} alkyl, C_1 - C_6 alkoxy, carbonyl(C_1 - C_{12} alkyl), aryl, in particular phenyl, sulfo, aminosulfonyl, carbamoyl, phosphono, phosphonoxy, and salts and esters thereof,

[X] represents a group from $(-N=N-)$, $(-N=CR^6-)_m$, $(-CR^6=N-)_m$, $(-CR^7=CR^8-)_m$,

20

and m is 1 or 2.

27. A system according to claim 26, wherein the mediator is a compound of the general formula II:



25

wherein R^1 , R^2 , R^3 , R^4 are as defined in claim 26 or a salt or ester thereof.

28. A system according to claim 27, wherein the mediator is 1-hydroxybenzotriazole.

29. A system according to any of the claims 17-28, wherein one
5 component is a solution comprising the enzyme(s) and the mediator(s).

30. A system according to any of the claims 17-28, wherein one
10 component is a slurry comprising the enzyme(s) and the mediator(s).

31. A system according to any of the claims 17-28, wherein one
component is a granulate comprising the enzyme(s) and the mediator(s).

15

32. A system according to claim 17-28, wherein one component is a granulate comprising the enzyme(s) and another component is a granulate comprising the mediator(s).

20 33. Use of components comprising

- at least one enzyme selected from the group consisting of enzymes exhibiting peroxidase activity or laccase activity,

25 - optionally an oxidation agent, and

- at least one mediator selected from the group consisting of aliphatic, cyclo-aliphatic, heterocyclic or aromatic compounds containing the moiety >N-OH, and

30

- optionally additives

for the preparation of a multi-component system for removal of excess dye or print from newly manufactured fabric or yarn.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/DK 98/00560

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: D06P 5/08, D06M 16/00, C11D 3/386, C11D 3/39, C12S 11/00
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: D06M, D06P, C11D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPODOC, WPI, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 9218687 A1 (NOVO NORDISK A/S), 29 October 1992 (29.10.92), See especially page 6, line 4 - line 17 and claim 6 --	1-33
Y	WO 9429425 A2 (CALL, HANS-PETER), 22 December 1994 (22.12.94) -- -----	1-33

 Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

6 April 1999

Date of mailing of the international search report

12 -04- 1999

Name and mailing address of the ISA/

Swedish Patent Office

Box 5055, S-102 42 STOCKHOLM

Facsimile No. +46 8 666 02 86

Authorized officer

Patrick Andersson

Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

Information on patent family members

02/03/99

International application No.

PCT/DK 98/00560

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9218687 A1	29/10/92	AT 155539 T	15/08/97
		DE 69220936 D,T	15/01/98
		DK 580707 T	19/01/98
		EP 0580707 A,B	02/02/94
		SE 0580707 T3	
		ES 2104912 T	16/10/97
		GR 3024911 T	30/01/98
		JP 6506731 T	28/07/94
		US 5356437 A	18/10/94

WO 9429425 A2	22/12/94	AT 169699 T	15/08/98
		AU 680666 B	07/08/97
		AU 7124094 A	03/01/95
		AU 7739794 A	03/01/95
		BR 9406854 A	26/03/96
		CA 2165426 A	17/12/94
		CA 2182182 A	22/12/94
		CN 1127523 A	24/07/96
		CN 1129468 A	21/08/96
		CZ 9503325 A	15/05/96
		DE 59406698 D	00/00/00
		EP 0705327 A	10/04/96
		EP 0739433 A,B	30/10/96
		SE 0739433 T3	
		ES 2122299 T	16/12/98
		FI 956023 A	25/01/96
		FI 961157 A	13/03/96
		HU 74975 A	28/03/97
		HU 9503600 D	00/00/00
		JP 9500153 T	07/01/97
		NO 955111 A	07/02/96
		NO 961205 A	25/03/96
		NZ 268359 A	26/01/98
NZ 273923 A	24/06/97		
SK 157995 A	09/07/97		
WO 9429510 A	22/12/94		
