

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization

International Bureau



WIPO | PCT



(10) International Publication Number

WO 2013/133906 A2

(43) International Publication Date

12 September 2013 (12.09.2013)

(51) International Patent Classification:

H01M 10/39 (2006.01) *H01M 10/44* (2006.01)
H01M 10/0562 (2010.01) *H01M 4/136* (2010.01)

(21) International Application Number:

PCT/US2013/020819

(22) International Filing Date:

9 January 2013 (09.01.2013)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/585,098 10 January 2012 (10.01.2012) US
61/590,494 25 January 2012 (25.01.2012) US

(71) Applicant: THE REGENTS OF THE UNIVERSITY OF COLORADO, A BODY CORPORATE [US/US]; 1800 Grant Street, 8th Floor, Denver, Colorado 80203 (US).

(72) Inventors: YERSAK, Thomas A.; Apt. 13, 2127 Glenwood Drive, Boulder, Colorado 80304 (US). LEE, Se-Hee; 787 Nighthawk Circle, Louisville, Colorado 80027 (US). STOLDT, Conrad; 1810 Willow Way, Golden, Colorado 80401 (US).

(74) Agent: TRENNER, Mark D.; 1153 Bergen Parkway, #M115, Evergreen, Colorado 80439 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM,

AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to the identity of the inventor (Rule 4.17(i))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))

Published:

- without international search report and to be republished upon receipt of that report (Rule 48.2(g))



WO 2013/133906 A2

(54) Title: LITHIUM ALL-SOLID-STATE BATTERY

(57) Abstract: An all-solid-state lithium battery, thermo-electromechanical activation of Li₂S in sulfide based solid state electrolyte with transition metal sulfides, and electromechanical evolution of a bulk-type all-solid-state iron sulfur cathode, are disclosed. An example all-solid-state lithium battery includes a cathode having a transition metal sulfide mixed with elemental sulfur to increase electrical conductivity. In one example method of in-situ electromechanical synthesis of Pyrite (FeS₂) from Sulfide (FeS) and elemental sulfur (S) precursors for operation of a solid-state lithium battery, FeS + S composite electrodes are cycled at moderately elevated temperatures.

LITHIUM ALL-SOLID-STATE BATTERY

GOVERNMENT RIGHTS

[0001] This invention was made with government support under grant number FA8650-08-1-7839 awarded by the Air Force Research Laboratory. The government has certain rights in the invention.

PRIORITY CLAIM

[0002] This application claims the benefit of U.S. Provisional Application No. 61/585,098 filed January 10, 2012 and titled "Lithium all-solid-state battery," and U.S. Provisional Application No. 61/590,494 filed January 25, 2012 and titled "Thermo-electrochemical activation of solid state electrolyte," both of Yersak, et al., and each incorporated by reference as though fully set forth herein.

BACKGROUND

[0003] Use of traditional rechargeable lithium-ion batteries in consumer products is a concern due to safety issues. Such safety issues include, but are not limited to, solvent leakage and flammability of commercial grade liquid electrolytes. Traditional solid-state batteries (composed of glass ceramic rather than liquid electrolytes) do not pose such safety risks and offer high reliability for end-users. However, traditional solid-state batteries suffer from poor rate capability, low ionic conductivity, interfacial instability, and low loading of active materials.

[0004] Molten salt solid-state batteries require high operating temperatures (e.g., 400°C and higher), so research was abandoned in search of room temperature lithium-ion and lithium-polymer technologies. Iron disulfide has been successfully commercialized in high energy density primary cells. Unfortunately, sulfide conversion chemistries are irreversible at ambient to moderately elevated temperatures, making these unusable for rechargeable batteries.

BRIEF DESCRIPTION OF THE DRAWINGS

[0005] **Figure 1** is a high-level depiction of an example lithium or lithium-ion all-solid-state battery structure.

[0006] **Figure 2** shows for an example battery: (a) a field emission scanning electron microscope (FESEM) micrograph of synthetic FeS_2 that confirms cubic structure with 2-3 μm cubes, and (b) X-ray diffraction of synthetic pyrite.

[0007] **Figure 3** shows as an example of FeS_2 cycled at ambient temperature (about 30°C) and moderately elevated temperature (60°C) in a liquid coin cell and in an all-solid-state configuration for: (a) solid-state at 30°C, (b) solid-state at 60°C, (c) liquid coin cell at 30°C, (d) a liquid coin cell at 60°C, (e) capacity retention comparison of cells cycled at 30°C, and (f) capacity retention comparison of cells cycled at 60°C.

[0008] **Figure 4** shows an example DFT simulation, where (a) is a so-called "ball-and-stick" representation of Li_xFeS_2 along a charging cycle, and (b) illustrates the average Fe-Fe distance ($d_{\text{Fe-Fe}}$) at each state in comparison with the Fe bulk value.

[0009] **Figure 5** shows a) Coulometric titration results for a solid-state cell, b) shows dQ/dV of a solid-state cell, and c) shows deconvolution of the dQ/dV peaks.

[0010] **Figure 6** shows electrode material from the solid-state cell cycled at 60°C recovered after the twentieth charge for transmission electron microscopy (TEM), where (a) is a bright field TEM image, and (b) is a high resolution (HR-) TEM image.

[0011] **Figures 7-9** are plots showing actual data obtained for Example 2.

[0012] **Figure 10** is a plot illustrating that activation of Li_2S exhibits ionic and electronic conductivity, as well as added thermal energy.

[0013] **Figure 11** is a plot showing cells cycled at C/5 and C/5 charge and discharge rates.

[0014] **Figures 12(a)-(d)** are plots of an example rate study.

[0015] **Figures 13(a)-(b)** are plots showing cycling data for a lithium metal cell.

[0016] **Figure 14** is an x-ray diffraction (XRD) spectra.

[0017] **Figure 15** shows (a) x-ray diffraction (XRD) spectra and (b) a TEM image.

[0018] **Figure 16** shows (a) cyclic stability of a FeS + S/Li battery, and (b)-(e) are voltage profiles of the same battery.

[0019] **Figure 17** shows (a) dQ/dV profiles for bulk-type all-solid-state Li metal batteries, and (b)-(e) dQ/dV profiles of an example battery.

[0020] **Figure 18** shows (a) XRD of FeS before and after milling, (b) an FESEM micrograph of FeS, and (c) an FESEM micrograph of $Fe_{1-x}S$ after mechanical milling.

[0021] **Figure 19** shows (a) voltage profiles for two initially overcharged FeS/LiIn batteries, and (b) XRD measurements normalized with the (100) reflection of the beta-Be sample window.

[0022] **Figure 20** shows voltage profiles of a FeS/LiIn battery.

[0023] **Figure 21** shows (a) specific discharge capacity of a battery as a function of applied current, and (b) voltage profiles of the same battery as a function of applied current.

DETAILED DESCRIPTION

[0024] Many advanced battery technologies are vying to be the successor of today's conventional Li-ion batteries. A strong argument can be made that bulk-type all-solid-state lithium batteries (ASSLB) hold a competitive edge in this technological race because they are inherently safe, have excellent shelf life, perform stably at high temperatures, and enable the reversibility of high capacity conversion battery materials like FeS_2 . However, the energy density of high power ASSLBs must be improved. The success of the ASSLB architecture can be realized with energy dense all-solid-state composite cathodes.

[0025] Examples of an ambient temperature, reversible solid-state cathode are disclosed. An example implementation is in a lithium (Li) metal configuration. The battery may be constructed using a sulfide glass-ceramic solid electrolyte, and is implemented in an all-solid-state cell architecture. In an example, the battery may be characterized as $M_xS_y + zS$ where M = Fe, Co, Mo, y = 0, 1, 2, 3 and z = 0, $\frac{1}{2}$, 1, and so forth. This nomenclature is intended to include at least

the following systems: FeS_2 , FeS , $\text{FeS} + \text{S}$, and may also include other suitable substitutes as will be understood by those having ordinary skill in the art after becoming familiar with the teachings herein. It is noted that the electrochemical synthesis of metal nano-particles maintains the electrochemical activity of Li_2S . Accordingly, the battery addresses issues previously associated with rapid capacity fade at ambient temperature. The electrochemically driven synthesis of orthorhombic- FeS_2 (marcasite) can be at least partially achieved at ambient temperatures.

[0026] The design of an ambient temperature transition metal plus sulfide batteries is based at least in part on management of electro-active species formed upon full charge (2.5V versus Li^+/Li) and full discharge (1.0V versus Li^+/Li). Two example species are elemental iron (Fe^0) and polysulfides (S_n^{2-}). To reduce or altogether prevent diffusion and agglomeration of Fe^0 nanoparticles in conventional cells, a variety of polymer electrolytes have been employed with limited success.

[0027] A similar approach may be applied to the confinement of intermediate polysulfides in conventional Li-S batteries. Example methods for addressing intermediate polysulfide dissolution and Li_2S irreversibility include polysulfide adsorption on high surface area CMK-3 nano-porous carbon electrodes, polymer electrolytes, and polyacrylonitrile-sulfur composites.

[0028] Another approach is to limit the upper and/or lower voltage bounds of the FeS_2 cells, for example, to about 2.2V and 1.3V respectively. The formation of Fe^0 and S_n^{2-} is inhibited by avoiding full discharge and charge. However, limiting the cell voltage range diminishes achievable energy density and subjects the cells to the risk of over-charge or over-discharge.

[0029] The basic nature of an all-solid-state cell architecture allows for the confinement of electro-active species. For example, FeS_2 and Li_2FeS_2 can both be utilized reversibly as an all-solid-state anode. An all-solid-state architecture reduces or altogether prevents Fe^0 dissolution and agglomeration. Sulfide-based, glass-ceramic solid electrolytes and other materials that are stable at elevated temperatures demonstrate higher conductivities at ambient temperatures. Accordingly, lithium metal anodes can be safely used with solid

electrolytes because cell failure does not precipitate thermal runaway. A lithium metal electrode has a theoretical capacity of about 3876 mAh g⁻¹, is non-polarizable and has a low operating voltage that increases achievable cell energy density. An all-solid-state architecture not only enables the safe use of a lithium metal anode, but also enables the reversible full utilization the cathode material.

[0030] Further examples herein disclose in-situ electrochemical formation of high capacity conversion battery materials like FeS₂ and reversible utilization of a glass or other stable electrolyte for higher overall electrode energy density. In an example, the best performing composite electrode compositions are composed of no more than about 25% S or Li₂S by weight. Sulfur's high theoretical specific capacity of about 1672 mAh g⁻¹ offsets poor active material mass loading so that high overall electrode energy densities can be achieved for ASSLBs. To increase the overall energy density of a composite electrode without changing the composition, the techniques described herein reversibly electrochemically utilize the glass-ceramic electrolyte. For example, by incorporating μ m-Cu powder, acetylene black, and 80Li₂S:20P₂S₅ glass-ceramic electrolyte into a composite electrode, the the Li₂S component of glass-ceramic electrolyte electrochemical can be utilized. For more effective electrolyte activation and better electrode reversibility, the active metal can be provided by in-situ electrochemical reduction.

[0031] The examples described herein may be further optimized by utilizing a mechanochemically prepared active material nano-composite of high capacity conversion battery materials like FeS and S. This material provides an alternative to the expensive solvothermally synthesized cubic-FeS₂ (pyrite) based cathode. The precursors (e.g., FeS and S) are comparatively inexpensive and can be obtained in much higher purities than natural pyrite. The mechanical milling process also provides material much more readily than the solvothermal method.

[0032] During testing, the rapidly increasing specific capacity of the nano-composite electrode (e.g., FeS + S) quickly exceeded its theoretical capacity by about 94% in testing. The excess capacity is a result of a dramatic utilization of

the glass electrolyte in the composite electrode without a degradation of cell performance. At its maximum, an example electrode exhibited an energy density of about 1040 Wh kg⁻¹ which is the highest energy density achieved for a bulk-type all-solid-state electrode. With extended cycling, the electrochemistry of the composite electrode (e.g., FeS + S) evolves a redox chemistry based primarily on that of only sulfur. The results show that electrochemically structured interfaces between conversion active materials and the glass electrolyte can be utilized to increase energy density of ASSLBs, while maintaining good rate performance.

[0033] It is noted that examples are described herein with respect to specific materials and process parameters for purposes of illustration only, and are not intended to be limiting. Other examples will be understood by those having ordinary skill in the art after becoming familiar with the teachings herein, and are also intended to be included within the scope of the claims.

[0034] Before continuing, it is noted that as used herein, the terms "includes" and "including" mean, but is not limited to, "includes" or "including" and "includes at least" or "including at least." The term "based on" means "based on" and "based at least in part on."

Lithium All-Solid-State Battery

[0035] Figure 1 shows a high-level depiction of a lithium all-solid-state battery structure 100. The battery structure 100 is shown including a cathode 101, solid state electrolyte 102, and an anode 103. The arrows are illustrative of charge and recharge cycles. The anode may include a lithium metal, graphite, silicon, and/or other active materials that transfer electrons during charge/discharge cycles. In an example, the lithium reservoir may be a stabilized Li metal powder.

[0036] The cathode 101 is shown in more detail in the exploded view 101', wherein the white circles labeled 110 represent a transition metal sulfide (e.g., FeS₂ or an mixture of FeS plus S). The gray circles labeled 111 represent solid

state electrolyte (SSE) particles. The SSE particles promote ionic conductive pathways in and out of the cathode 101. The black circles labeled 112 represent a conducting additive, such as acetylene black.

[0037] In an example, the transition metal sulfide (e.g., FeS plus S) may be mechanically mixed (e.g., using ball milling or other mechanical processes), and are not chemically combined. The chemistry of the cathode approximates FeS₂ on the first cycle. After 10 or more charge cycles, the cathode exhibits a behavior that is similar to that of the first cycle.

[0038] Although the lithium all-solid-state battery structure 100 may be implemented using any suitable transition metal sulfide plus sulfide combination, the following discusses a specific battery structure based upon synthetic iron disulfide.


[0039] Synthetically prepared FeS₂ is characterized with field emission scanning electron microscopy (FESEM) and x-ray analysis. **Figure 2** shows (a) a FESEM micrograph of synthetic FeS₂ that confirms cubic structure with wide 2-3 μ m cubes, and (b) X-ray diffraction of synthetic pyrite. The FESEM micrograph shown in Figure 2(a) reveals cubic FeS₂ particles with 3 μ m wide faces. The X-ray analysis of synthetically prepared FeS₂ shown in Figure 2(b) shows diffraction peaks that match well with indexed peaks.

[0040] Synthetic FeS₂ was tested in both an all-solid-state and liquid cell configuration. To achieve full utilization of FeS₂, the cells are cycled to full discharge (1.0V) and full charge (3.0V). The results of cycling at ambient and moderate temperatures are shown in Figure 3. For purposes of illustration, **Figure 3** shows FeS₂ cycled at ambient temperature (about 30°C) and moderately elevated temperature (about 60°C) in a liquid coin cell and in an all-solid-state configuration for: (a) solid-state at 30°C, (b) solid-state at 60°C, (c) liquid coin cell at 30°C, (d) a liquid coin cell at 60°C, (e) capacity retention comparison of cells cycled at 30°C, and (f) capacity retention comparison of cells cycled at 60°C. All cells except for the 30°C solid-state cell were cycled at a current of 144 μ A which corresponds to a rate of C/10 for charge and discharge. The 30°C solid-state cell was cycled at rate of C/10 for the first cycle and C/20 (72 μ A) for all subsequent cycles.

[0041] Both solid-state cells are observed to have good capacity retention and a high degree of FeS₂ utilization. The gradual increase in capacity with cycling is observed to be a result of better FeS₂ utilization. This conclusion is supported by differential capacity (dQ/dV) analysis. By the twentieth cycle, the cell tested at 30°C exhibits a discharge capacity of nearly 750 mAh g⁻¹ while the cell tested at 60°C exhibits a theoretical discharge capacity of about 894 mAh g⁻¹. It is likely that the temperature dependence of solid electrolyte's conductivity contributes to the full FeS₂ utilization at 60°C, but not at 30°C. At 60°C the conductivity of the 77.5Li₂S-22.5P₂S₅ solid electrolyte increases to 4.4x10⁻³ Ω⁻¹ cm⁻¹ from 9.17x10⁻⁴ Ω⁻¹ cm⁻¹ at 30°C. In addition, a higher operating temperature increases the Li⁺ diffusivity in pyrite particles. More efficient Li⁺ insertion into cubic-FeS₂ is also likely to result in better FeS₂ utilization.

[0042] In liquid cells, the discharge capacity rapidly fades upon cycling. By the twentieth cycle, the liquid cell tested at 30°C exhibits a discharge capacity of only 190 mAh g⁻¹ while the cell tested at 60°C exhibits no discharge capacity. Decomposition processes are accelerated at 60°C leading to such a fast rate of capacity fade that negligible capacity is observed after the second cycle. On the other hand, we have just shown that cycling a solid-state FeS₂ cell at 60°C only improves its performance. At 60°C, it is possible to achieve a reversible, four electron utilization of FeS₂. It is noted that many traction battery packs are designed to operate at temperatures near about 60°C. The superior performance of all-solid-state batteries described herein at higher temperatures may reduce the need for extensive thermal management systems.

[0043] Mössbauer spectroscopy and near-edge X-ray absorption spectroscopy (XANES) show that the products of FeS₂ reduction are elemental iron (Fe⁰) and Li₂S. The initial discharge of FeS₂ proceeds in two steps:



[0044] Each reaction can occur at one voltage or two, depending at least in part on the kinetics of the system.

[0045] Discharge profiles were observed having one plateau when the cell is cycled at 30°C, as can be seen in Figures 3(a) and (c), and two plateaus at 60°C, as can be seen in Figures 3(b) and (d). At lower temperatures the reactions are limited by the low diffusivity of Li⁺ into the micron sized FeS₂ particles. At 30°C, reactions corresponding to equations (1) and (2) shown above proceed simultaneously at 1.5V versus Li⁺/Li. At moderately elevated temperatures, equations (1) and (2) can proceed at 1.7 and 1.5V respectively due to the higher diffusivity of Li⁺ into the micron sized FeS₂ particles. The shoulder at 1.3V in the ambient temperature liquid cell, as can be seen in Figure 3(c), may be attributed to an irreversible side reaction of FeS₂ intermediaries with the organic electrolyte. It is noted that the initial discharge profile of the FeS₂ cells is much different than subsequent discharge profiles. The variation in discharge profiles may be due to the improved reaction kinetics of charge products compared to that of cubic- μ FeS₂. Better kinetics may be due to changes in FeS₂ particle morphology and the electrochemical formation of a different phase of stoichiometric of FeS₂ like orthorhombic-FeS₂ (marcasite).




[0046] Superior performance observed in the solid state is believed to be due to the confinement of electro-active species. The confinement of Fe⁰ by solid electrolyte partially explains the better performance. Fe⁰ takes the form of super-paramagnetic atoms or small aggregates of atoms of about 3.6nm in diameter. Nano-particles of Fe⁰ have a high reactivity which is related to the nano-particle's large surface area. Should Fe⁰ particles agglomerate into larger particles with smaller overall surface area, then these particles will have a lower reactivity. Without meaning to be limited by the theory, it may be the high reactivity of the Fe⁰ nano-particles that maintains the electro-activity of Li₂S. Of course, other theories are also possible.

[0047] But Fe⁰ is susceptible to continuous agglomeration upon cycling. Agglomeration of Fe⁰ results in the isolation of Li₂S species and the observed capacity fade when cells are discharged to low voltages. An all-solid-state architecture can reduce or altogether prevent the agglomeration of Fe⁰ nano-particles. The atomic proximity of Fe⁰ nanoparticles with Li₂S maintains the


electro-activity of Li_2S without the excessive amount of conductive additive needed in $\text{S}/\text{Li}_2\text{S}$ based batteries.

[0048] An all-solid-state architecture is also successful at confining polysulfides S_{n-2}^{2-} formed when the electro-active species present at full charge are reduced. At ambient to moderate temperatures, FeS_2 is not regenerated by the four electron oxidation of Fe^0 and Li_2S . But the same is not true for molten salt FeS_2 cells, which operate reversibly at temperatures in excess of 400°C.

[0049] Generally, subsequent charge and discharge cycles may proceed according to the following reactions:



However equation (5) may be better represented by equation (6) based on the results to be outlined below:



[0050] The direct reduction of sulfur by Li^+ upon subsequent discharge therefore introduces intermediate polysulfides (S_{n-2}^{2-}) into the system. In a liquid cell, polysulfides dissolve into the electrolyte and participate in a parasitic "shuttle" mechanism which causes rapid capacity fade and self-discharge. The "shuttle" mechanism is the primary degradation process occurring in sulfur-based cells. Polysulfides cannot dissolve into the solid electrolyte. Therefore, the confinement of polysulfides in an all-solid-state cell inhibits the "shuttle" mechanism.

[0051] Charge products at about 30-60°C are likely a multi-phase mixture of nano-particles of orthorhombic- FeS_2 , non-stoichiometric FeS_y phases like pyrrhotite and elemental sulfur. In any case, the electrochemically active products resulting from sequential charge cycles simulate the FeS_2 chemistry as

well as provide electrical conductivity within the electrode thus reducing the amount of conductive additive required. This conclusion is supported by the results of a DFT simulation shown in **Figures 4-6**.

[0052] **Figure 4** shows an example DFT simulation of lithiated Li_xFeS_2 indicating material amorphization and Fe agglomeration for $x = 4$, where (a) is a so-called "ball-and-stick" representation of Li_xFeS_2 along a charging cycle from $x=4$ to $x=0$, and (b) shows the average Fe-Fe distance ($d_{\text{Fe-Fe}}$) at each state in comparison with the Fe bulk value.

[0053] **Figure 5** shows: a) Coulometric titration results for a solid-state cell titrated at 60°C compared with the first, second, and tenth discharge profiles for a solid-state cell cycled at 60°C, b) shows dQ/dV of a solid-state cell cycled at 30°C, and c) shows deconvolution of the dQ/dV peaks at 2.1 and 2.2V with fitted peaks and residual.

[0054] **Figure 6** shows electrode material from the solid-state cell cycled at 60°C recovered after the twentieth charge for transmission electron microscope (TEM) analysis, where: (a) is a bright field TEM image of the twentieth cycle sample with darker areas corresponding to nano-crystalline orthorhombic- FeS_2 and lighter areas corresponding to an amorphous region composed of FeS_y and elemental sulfur, and (b) is a high resolution (HR-) TEM of the twentieth cycle sample. FFT analysis matches with orthorhombic- FeS_2 along the [-110] zone axis.

[0055] Contrary to previous assumptions, subsequent discharges largely follow the same initial reaction path. Instead, the difference between the initial and subsequent discharge profiles is likely to changes in particle morphology and the formation of the more open orthorhombic- FeS_2 (marcasite). Thus, equation (6) more accurately describes the chemistry of subsequent cycles.

[0056] A study used coulometric titration to indicate that cubic- FeS_2 is not produced electrochemically. However, the time needed for the FeS_2 electrode to reach equilibrium is much longer than the 24 hours allowed in that study. When an FeS_2 cell is allowed up to about 144 hours to establish equilibrium during initial discharge, the open circuit voltage (OCV) of the cell approaches the voltage of a subsequent discharge at the appropriate reaction coordinate (x) as

shown in Figure 5(a). This result indicates that the difference between the initial discharge profile and subsequent discharge profiles can be explained by kinetics. The difference is not a result of a different reaction pathway. The diffusion of Li^+ into the inner core of 2-3 μm pyrite cubes severely limits the reaction rate of FeS_2 reduction. If electrochemically produced FeS_2 particles are nano-crystalline, then the greatly increased interfacial surface area facilitates a fast reaction rate despite poor Li^+ diffusivity. The diffusivity of Li^+ may also be improved by regenerating a phase other than cubic- FeS_2 . For example, orthorhombic- FeS_2 has a more open structure than cubic- FeS_2 . The formation of orthorhombic- FeS_2 instead of cubic- FeS_2 may result in faster Li^+ diffusion, thus further increasing the reduction reaction kinetics.

[0057] High resolution transmission electron microscopy (HR-TEM) can be used to support this understanding through direct observation of orthorhombic- FeS_2 nano-particles upon charge. In an example, electrode material was recovered from the solid-state cell cycled at about 60°C upon completion of the twentieth charge as can be seen in Figure 3(b). This cell exhibits full utilization of FeS_2 so it is unlikely that a significant mass of electrochemically inactive synthetic cubic- FeS_2 remains in the cell by the twentieth charge.

[0058] Figure 6(a) shows a bright field (BF) TEM image of the 20th cycled charged FeS_2 solid-state electrode. This image depicts nano-crystalline domains (darker) of 100-200nm in diameter encased by an amorphous material (lighter). Fast Fourier transform (FFT) analyses of HR-TEM images matches well with orthorhombic- FeS_2 along the [-110] zone axis as can be seen in Figure 6(b).

[0059] High resolution TEM imaging indicates a large amount of amorphous material encasing the crystalline FeS_2 domains. To explore this issue further, the differential capacity of the all-solid-state cell cycled at 30°C was examined, as can be seen in Figures 5(b) and (c). The peaks shown in Figure 5(b) correspond to the oxidation of Li_2S , and the reduction of S in an all-solid-state sulfur cell. The purple peaks correspond to reaction plateaus observed in the solid-state FeS_2 cells cycled at 30°C.

[0060] When the solid-state FeS_2 cell is charged, no peaks are observed corresponding to the oxidation of Li_2S . However, upon discharge a peak is observed at 2.2V, which corresponds to the direct reduction of sulfur to Li_2S . This result indicates that discharge and charge of a FeS_2 all-solid-state cell at higher voltages at least somewhat follows equation (5), above. It indicates that sulfur is electrochemically produced by the disproportionation of Li_2FeS_2 . For this reason, the amorphous region is likely a mixture of elemental sulfur and non-stoichiometric FeS_y .

[0061] To quantify the amount of elemental sulfur produced upon charging, all elemental sulfur is said to be directly reduced to Li_2S at 2.2V. The solid-state cell cycled at about 30°C exhibited a discharge capacity of about 737 mAh g^{-1} upon the ninth discharge. If the peaks at 2.1 and 2.2 V correspond to the reaction of charge products with two electrons, then integrating the dQ/dV curve between about 1.6 and 2.5 V yields a capacity 368 mAh g^{-1} for this cell. When these two peaks are de-convoluted and fitted with a Voigt profile, the calculated total area gives a capacity of about 342.2 mAh g^{-1} , as can be seen in Figure 5(c). This value matches well with the expected capacity of about 368 mAh g^{-1} .

[0062] The peak at about 2.2 V has an area of about 57.14 mAh g^{-1} , while the peak at about 2.1V has an area of about 285.79 mAh g^{-1} . If $(2-y)\text{S}$ is directly reduced to Li_2S , then the remaining capacity may be attributed to FeS_y . The value of y can be determined to be about 0.085. If subsequent discharges follow equation (5), then the chemical formula of FeS_y is about $\text{FeS}_{1.92}$. If FeS_y primarily takes the form of Fe_7S_8 (pyrrhotite), then the chemistry of subsequent cycles likely follows equation (6).

[0063] The charge products are likely a multiple phase mixture of nano-crystalline orthorhombic- FeS_2 , sulfur deficient phases of FeS_y and elemental sulfur. Accordingly, the charge products are believed to be nano-crystalline orthorhombic- FeS_2 encased in amorphous sulfur deficient FeS_y and sulfur (see Figure 6(a)).

[0064] Coulometric titration indicates that the initial discharge is kinetically limited, and subsequent discharges follow a similar reaction path (see Figure 5(a)). Nano-crystalline orthorhombic- FeS_2 enables faster reaction rates.

[0065] Sulfur reduction was observed at about 2.2V upon charge, but not Li₂S oxidation upon charge, as can be seen in Figure 5(b). FeS_y phases and elemental sulfur may explain the amorphous domains observed in the high resolution TEM images. The presence of sulfur deficient FeS_y phases and the observation of orthorhombic-FeS₂ is consistent. Orthorhombic-FeS₂ exhibits very weak temperature independent paramagnetism. For this reason, it is likely that ⁵⁷Fe Mössbauer spectroscopy used in previous studies was not capable of distinguishing orthorhombic-FeS₂ from other strong temperature dependent paramagnetic phases like FeS_y and cubic-FeS₂. By way of example, Fe₇S₈ is ferrimagnetic while FeS is paramagnetic. It is noted that ferrimagnetism is a much stronger effect.

[0066] The results of the DFT analysis shown in Figure 4 indicate the formation of highly reactive atomic particles of Fe⁰. The fully-discharged, amorphous-like Li₄FeS₂ model (Figure 4(a)) shows nanoscale separation of a Fe⁰ nanocluster from Li₂S. The average Fe-Fe interatomic distance (d_{Fe-Fe}) at full discharge, x = 4, is much shorter than that of Fe in the bulk (Figure 4(b)). A shorter d_{Fe-Fe} indicates that Fe⁰ should be very catalytically active. Results also indicate the presence of elemental sulfur as a charge product. At x = 0, our atomic model depicts some degree of FeS₂ crystallization with a rather open structure (Figure 4a). The x = 0 model also depicts the presence of a S₂ dimer. It is the presence of elemental sulfur that inhibits the full crystallization of FeS₂ in our simulation. It is likely that the observed FeS_{2-y} nano-clusters could crystalize into orthorhombic-FeS₂ rather than cubic-FeS₂ because of the former's lower density.

[0067] Before continuing, it should be noted that the description of example ambient temperature, reversible metallic lithium iron sulfide (FeS₂) solid-state batteries given above and further described below with reference to specific Examples is provided for purposes of illustration, and is not intended to be limiting. Other devices and/or device configurations using these and/or other materials may be utilized as will be readily apparent to one having ordinary skill in the art after becoming familiar with the teachings herein.

Example 1

[0068] In this example, the batteries discussed above were made for laboratory scale analysis using commercially available polyvinylpyrrolidone (PVP, $M_{w,avg} \approx 10,000$) and $FeCl_2 \cdot 4H_2O$ (>99%) obtained from Sigma Aldrich, ethylene glycol (99%) obtained from Mallinckrodt Baker Inc., and sulfur obtained from Fischer Scientific. HPLC grade water, analytical grade NaOH, and absolute ethanol were used without further purification. The FeS_2 synthetic methodology used solvothermal reaction conditions. Dielectric heating for the reaction was provided with a microwave reactor. Microwave heating was selected because of its high reproducibility and the ability for automation, making this methodology amenable to high throughput syntheses.

[0069] For the reaction 17 mL of ethylene glycol was added to 600 mg of PVP in a 35 mL microwave flask with a magnetic stirbar. Then 127 mg $FeCl_2 \cdot 4H_2O$ (0.64 mmol) was introduced. 8 mL of 1 M NaOH was then added, resulting in a dark green color. Finally, 180 mg of sulfur was added. This solution was stirred for 20 minutes while changing color from green to black. Some sulfur remained undissolved during this process. The reaction flask was then capped (70% full) and introduced to the microwave.

[0070] The microwave used for this example was a Discover SP (CEM Inc.). The sample was irradiated with 75 W of power until reaching 190°C, as measured by an infrared detector. The heating took about 7 minutes, and was held at this temperature for 12 hours. Approximately 690 kPa of autogenous pressure was generated. After the reaction was finished, the product was cooled by compressed air.

[0071] The resulting silver colored precipitate was separated by centrifugation and washed three times by sonication in ethanol. The precipitate was then stored in ethanol and vacuum dried overnight at 50°C for battery utilization. Synthetic FeS_2 was characterized by Cu-K α x-ray diffraction (XRD) measurement, FESEM microscopy (JEOL JSM-7401F), and Raman spectroscopy (Jasco NRS-3100).

[0072] Cell fabrication and cell testing for this example was carried out under an inert argon gas environment. The all-solid-state cells used in this study were

based upon the 77.5Li₂S-22.5P₂S₅ binary solid-state electrolyte. The composite positive electrode had a 10:20:2 weight ratio mixture of synthetically prepared FeS₂, 77.5Li₂S-22.5P₂S₅, and carbon black (Timcal Super C65), respectively. The composite positive electrode was mixed using an agate mortar and pestle. Stabilized lithium metal powder (SLMP) was used as the negative electrode (FMC Lithium Corp.). The construction of solid-state cells utilized a titanium-polyaryletheretherketone (PEEK) test cell die. 200mg of solid electrolyte powder was pressed at 1 metric ton in the PEEK cell die. 5mg of composite positive electrode and the stabilized lithium metal powder were then attached to opposite sides of the solid electrolyte layer by pressing at 5 metric tons.

[0073] Liquid cells were fabricated by spreading an electrode slurry with a 6:2:2 weight ratio of synthetic FeS₂, polyvinylfluorine (PVDF) binder (Alfa Aesar) and acetylene black (Alfa-Aesar, 50% compressed) respectively. PVDF binder was first dissolved into N-methyl-2-Pyrrolidone (NMP) (Alfa-Aesar) solvent. FeS₂ and acetylene black were then stirred into the PVDF binder. A 50 μ m thick layer of slurry was spread on onto aluminum foil (ESPI Metals, 0.001" thick) and dried at 60°C in a single wall gravity convection oven (Blue M) for 5 hours. To ensure good electronic contact, the electrode sheet was then calendared with a Durston rolling mill to 75% of the total thickness. 9/16" diameter electrodes were punched and heat treated at 200°C in an Argon environment overnight. FeS₂ electrodes were then assembled into coin cells with a lithium foil negative electrode (Alfa-Aesar, 0.25mm thick) and 1M LiPF₄ electrolyte.




[0074] Cells were cycled galvanostatically using an Arbin BT2100 battery tester at room temperature (30°C) and elevated temperature (60°C). Declared C-rates were based upon FeS₂'s theoretical capacity of 894 mAh g⁻¹. Reaction equilibrium was studied by use of the galvanostatic intermittent titration technique (GITT).

Example 2

[0075] Figures 7-9 are plots showing actual data obtained for Example 2. Specifically, Figure 7 shows charge/discharge profiles for FeS₂ in a solid state lithium battery, made from microwave synthesis. Figure 8 shows

charge/discharge profiles for *in-situ* formation of FeS₂ upon cycling of FeS+S combined by planetary ball milling (cycled at C/10). The top plot in Figure 9 shows the performance of FeS, with significantly lowered capacity and a lack of voltage plateaus correlating to Eq. 7 and 8 below. Upon discharge at room temperature, a slightly lower voltage is observed due to internal resistance in the cell, and similarly for charging with a slightly higher voltage. A significant decrease in reversibility is also observed, with first cycle coulombic efficiency of both room temperature and elevated temperature FeS cells below 75%. The bottom plot in Figure 8 shows a first cycle of FeS at (a) room temperature and (b) elevated temperature.

[0076] In this example, solid state batteries utilizing highly conducting sulfide based solid electrolytes were used for reversible cycling of FeS₂ electrodes in both room temperature (25°C) and elevated temperature environments (60°C) as shown in Figure 7. Furthermore, it was shown that there is no capacity loss for increasing rates up to C/8 for elevated temperature testing. The first cycle shows the reaction formation of Li₂S and Fe down to 1.0V. Reversible cycling is allowed by the highly reactive iron allowing successful de-Lithiation of Li₂S, and subsequent formation of various Li-Fe-S compounds according to the following equations which are visible in the charging profile.



[0077] After the first cycle, well defined voltage plateaus exist, showing the successful formation of FeS₂ (from discharging) upon charging, and subsequent formation of specific reversible Li-Fe-S phases upon discharge.

[0078] FeS₂ was formed *in-situ* during the first cycle (and also occurs over the course of many cycles), utilizing stoichiometric combinations of other materials. FeS and S were mixed either by mortar and pestle grinding, or by ball

milling to produce an active material that is simply the addition of both, without formation of FeS_2 .

[0079] Upon the first discharge, plateaus corresponding to FeS and S were present, and resulted in a similar capacity of FeS_2 made by microwave synthesis. By comparison (Figure 8), it can be seen that there is a difference between discharge profiles for FeS_2 and $\text{FeS}+\text{S}$ electrodes. However, these both resulted in the same highly reactive iron species that allows the reversible cycling of Li_2S . Voltage plateaus corresponding to the similar peaks of FeS_2 occurred for $\text{FeS}+\text{S}$ electrodes (Figure 8) during charging. Subsequent discharging (2nd cycle) shows that these exhibited high reversibility and reaction plateaus for FeS_2 , resulting from the FeS/S electrodes. Based on this understanding, it is further noted that another potential system includes electrochemical formation of FeS_2 from elemental iron and sulfur being ball milled or mixed by hand.

Thermoelectrochemical activation of solid state electrolyte

[0080] Thermoelectrochemical activation of solid state electrolyte is also disclosed herein. To increase cell energy density, it may be desirable to thermally activate the solid state electrolyte (e.g., Li_2S) in sulfide-based solid electrolytes, including but not limited to $x\text{Li}_2\text{S}-(100 - x)\text{P}_2\text{S}_5$. Initially charging a cell at an elevated temperature increases the energy density of the cell in one example by over 50%.

[0081] For purposes of illustration, two different composite electrodes were studied: an $80\text{Li}_2\text{S}-20\text{P}_2\text{S}_5$:acetylene black composite with a 20:1 weight ratio respectively and a $\text{TiS}_2:80\text{Li}_2\text{S}-20\text{P}_2\text{S}_5$:acetylene black composite with 10:20:1 weight ratio respectively. The cells in this example have an In metal negative electrode. However, the claims are not limited to these electrodes, as suitable substitutes may be used as will be understood by those having ordinary skill in the art after becoming familiar with the teachings herein.

[0082] Figure 10 is a plot illustrating that the activation of Li_2S is based at least in part on both the ionic and electronic conductivity of TiS_2 , as well as added thermal energy (e.g., about 60°C). The specific charge capacities shown in Figure 10 are based on the total mass of TiS_2 solid electrolyte and acetylene black. Even at elevated temperature the composite with only solid electrolyte shows no capacity. Likewise, the composite with TiS_2 also shows no capacity when charged at room temperature.

[0083] However, the composite electrode with TiS_2 exhibited a charge capacity of 13 mAh g⁻¹ when charged at an elevated temperature of about 60°C. This corresponds to a specific charge capacity of about 40 mAh g⁻¹ based upon the TiS_2 mass. As these cells have a lithium-ion configuration, and TiS_2 is already in the charged state, the only source of lithium in these cells was Li_2S . Under an applied current at elevated temperature, it is believed that otherwise inert Li_2S is activated by the highly ionic and electronic conductive character of TiS_2 . Other transition metal sulfides have similar material properties as TiS_2 , and may be useful in a similar Li_2S activation process.

[0084] Figure 11 shows results of thermo-electrochemical activation of Li_2S using nano-LiT₂S₂. Figure 11 is a plot showing cells with a 10:20:1 wt% nano-LiT₂S₂:80Li₂S-20P₂S₅:acetylene black composite electrode cycled at C/5 and C/5 charge and discharge rates. The bottom data series (squares) shows the cell cycled at 30°C (without thermal-electrochemical activation), and the top data series (triangles) shows the cell initially charged at 60°C before being removed to room temperature. The nano-LiT₂S₂ was synthesized using mechano-chemical milling process involving Li_3N decomposition. The composite electrodes are a 10:20:1 weight ratio mixture of nano-LiT₂S₂:80Li₂S-20P₂S₅:acetylene black.

[0085] The cells in this example have an In metal negative electrode and are cycled at a rate of C/5 for both charge and discharge. However, the initial charge and discharge cycles are both conducted at a rate of C/10. Specific charge capacities presented are based upon the mass of LiT₂S₂ initially present in the composite electrode.

[0086] The first cell cycled at room temperature exhibits a very stable capacity of about 230 mAh g⁻¹ after about forty cycles. The second cell undergoes an initial elevated temperature activation charge at about 60°C. It is then moved to room temperature (about 30°C) for the first discharge and all cycles thereafter. This cell exhibits a 345 mAh g⁻¹ discharge capacity after about the fortieth cycle. This represents about a 119 mAh g⁻¹ (or about a 53%) increase in capacity over the theoretical capacity of LiTiS₂ of 226mAh g⁻¹.

[0087] The increase in capacity observed with nano-LiTis₂ is much larger than the 40mAh g⁻¹ excess capacity achieved with the TiS₂-80Li₂S:P₂S₅-acetylene black composite. The greater surface area of the nano-LiTis₂ particles is thought to more easily facilitate the activation of Li₂S in the solid electrolyte. Supporting the previous finding, the rate performance of nano-LiTis₂ composite electrodes is shown in Figure 12.

[0088] **Figures 12(a)-(d)** are plots of an illustrative rate study of a 10:20:1 wt% LiTiS₂: 80Li₂S-20P₂S₅:acetylene black composite electrode, where (a) and (b) are at 30°C, and (c) and (d) are at 60°C. The plots in Figures 12(a)-(d) confirm the repeatability of results shown in Figure 11. The cell cycled at an elevated temperature exhibits discharge capacities in excess of 160mAhg⁻¹ greater than the theoretical capacity of 226 mAhg⁻¹ for LiTiS₂.

[0089] The cells in this example have a Li metal negative electrode to facilitate fast ion transfer. It is noted that the cell cycled at elevated temperature has a specific discharge capacity of nearly 390 mAh g⁻¹ at a rate of C/2 while the cell cycled room temperature only exhibits a capacity of 210 mAh g⁻¹ at C/2. Repeatedly charging at elevated temperature activates Li₂S in the solid electrolyte, providing excess capacity.

[0090] **Figures 13(a)-(b)** are plots showing cycling data for a lithium metal cell. The plots show cycling data for a lithium metal cell with a 10:20:1 wt% FeS₈₇ + S:77.5Li₂S-22.5P₂S₅:acetylene black composite cathode cycled at 60°C. At an elevated temperature, the cell gains capacity during the first 10 cycles. The increase in capacity is attributed to the S/Li₂S redox reaction. The activation of excess sulfur is responsible for the evolution of a voltage plateau at about 2.2V. It can be seen that the cell has a specific discharge capacity of

about 807 mAh g⁻¹ on the first discharge, but a specific discharge capacity of 1341 mAh g⁻¹ by the ninth cycle. This represents an activation of about 534 mAh g⁻¹. The activated capacity can be attributed to the evolution of the S/Li₂S reduction plateau at about 2.2V.

[0091] As stated above, the particular solid electrolyte system in this example is xLi₂S-(100-x)P₂S₅. However, this technique is applicable to any Li₂S containing sulfide based electrolyte system is not limited to Li₂S-GeS₂-P₂S₅ or Li₂S-SiS₂. These solid electrolytes are known as glass ceramics. During electrolyte synthesis (e.g., by melt-quenching or mechano-chemical milling) Li₂S is incorporated into glass formers not limited to GeS₂, P₂S₅, and SiS₂. Super- ionically conducting crystalline phases can also be precipitated in a glassy matrix upon subsequent heat treatment. It is also possible, that these crystalline phases may decompose and result in some excess capacity.

[0092] Figure 14 are x-ray diffraction (XRD) spectra of an example 80Li₂S-20P₂S₅ solid electrolyte, example 10:20:1 wt% LiTiS₂:80Li₂S-20P₂S₅:acetylene black composite electrodes, and indexed spectra for Li_{1.0}TiS₂ and Li₂S. The XRD spectra of the solid electrolyte in this illustration shows Li₂S peaking at about 27 and about 31.2 degrees, indicating that there are some Li₂S domains still present in the solid electrolyte. It is believed that the additional capacity is a result of reacting excess Li₂S in the solid electrolyte. It is expected that the 77.5Li₂S-22.5P₂S₅ solid electrolyte has less excess Li₂S to participate in activation reactions.

[0093] There is evidence of Cu_yS formation and Li₂S decomposition upon charging at about 25°C. The cells in this example tend to exhibit initial specific charge capacities of up to about 150 mAh g⁻¹. Composites without Cu tend to exhibit no capacity, indicating that Cu is a reacting species in the solid electrolyte.

[0094] The process described herein is analogous, but is also somewhat different. That is, Cu reacts to form Cu_yS, while TiS₂ remains chemically/structurally stable. TiS₂ is an intercalation electrode material, while Cu_yS is a conversion battery material. TiS₂ succeeds in electrochemically activating excess Li₂S because it is both highly ionically and electronically

conductive. The process described herein is based on an initial charging at elevated temperature, as no excess capacity is observed at room temperature.

[0095] The iron sulfide (FeS₂, FeS_x, or FeS_x + S) systems disclosed herein are more like the Cu_xS electrodes. During lithiation (reduction), FeS₂ is not chemically/structurally stable like TiS₂. Instead, FeS₂ reacts with 4Li⁺ in a conversion reaction to form the completely reduced products of Fe⁰ and 2Li₂S. Fe⁰ acts as a catalyst for the oxidation of Li₂S. The products of oxidation include various electronically conducting phases of FeS_x. These phases then help to electrochemically activate excess Li₂S present in the solid electrolyte.

Electrochemical evolution of a bulk-type all-solid-state iron sulfur cathode

[0096] The lithium all-solid-state battery described above, which may be thermally activated as described above, may also be made using a high capacity conversion battery materials (e.g., FeS₂) equivalent. Examples are described in the following discussing as in-situ electrochemical formation of a FeS₂ phase and reversible utilization of a glass electrolyte for higher overall electrode energy density. However, the lithium all-solid state battery is not limited to such an implementation.

[0097] The results described below show that electrochemically structured interfaces between conversion active materials and the glass electrolyte can be utilized to increase energy density of ASSLBs, while maintaining good rate performance.

[0098] For purposes of illustration, synthesis of the iron sulfide based all-solid-state composite electrodes can be by a three step planetary ball milling procedure (Across International, PQ-N2). An example 77.5Li₂S-22.5P₂S₅ (molar ratio) glass electrolyte can be prepared by milling about 0.832g Li₂S (Aldrich, 99.999%, reagent grade) and about 1.168g P₂S₅ (Aldrich, 99%) in a 500mL stainless steel vial (Across International) with two stainless steel balls (having about a 16mm diameter) and twenty stainless steel balls (having about a 10mm diameter) at about 400 rpm for about 20 hours.

[0099] The 1:1 molar ratio FeS:S active material composite (denoted as FeS + S) can be prepared by milling about 0.733g FeS (Aldrich, technical grade) and about 0.267g Sulfur (Aldrich, 99.98%) in a 100mL agate jar (Across International) with five agate balls (having about a 10mm diameter) and fifty agate balls (having about a 6mm diameter) at about 400 rpm for about 20 hours.

[00100] The composite electrode can be synthesized by milling a ratio of prepared FeS + S, 77.5Li₂S-22.5P₂S₅, and carbon black conductive additive (Timcal, C65) in a 100mL agate jar with five agate balls (having about a 10mm diameter) and fifty agate balls (having about a 6mm diameter) at about 400 rpm for about 18 minutes.

[00101] In an example, cell fabrication and cell testing was carried out under an inert Argon gas environment, although other environments may also be utilized. The working electrode is about 5mg of the mechanically prepared FeS + S based composite electrode. In this example, about 5mg of stabilized lithium metal powder (SLMP) was used as the counter electrode (FMC Lithium Corp., Lectro Max Powder 100). The shell of the solid state battery was a titanium-polyaryletheretherketone (PEEK) test cell die. To fabricate each cell, the glass electrolyte powder was first compressed at about 5 metric tons inside the PEEK cell die to form the separator pellet. In this example, about 5mg of composite positive electrode and the SLMP were then attached to opposite sides of the glass electrolyte pellet with about 5 metric tons force.

[00102] A variety of different batteries were fabricated to aid in the characterization of the FeS + S/Li battery's electrochemistry. Still other examples are contemplated, and the examples discussed herein are merely illustrative. In an example, the FeS in these batteries was prepared by mechanically milling about 2g of FeS in a 100mL agate jar (Across International) with five agate balls (having about a 10mm diameter) and fifty agate balls (having about a 6mm diameter) at about 400 rpm for about 20 hours. The cells used to electrochemically prepare the cycled XRD samples had a 165 mg FeS composite cathode and an InLi alloy anode. These cells operate at a lower potential because the InLi alloy has a potential of about 0.62V vs. Li⁺/Li.

[00103] In these examples, all cells were cycled under constant current constant voltage (CCCV) conditions using an Arbin BT2000 battery tester at about 60°C. Because the overall capacity of the FeS electrode is a moving target, rate performance is described by current and not by C-rate. Unless otherwise noted, specific capacities are given with respect to the total mass of the composite electrode. Materials are characterized by field emission scanning electron microscopy (FESEM, JEOL JSM-7401F) and Cu-K α X-ray (XRD) measurement.

[00104] Figure 15 shows (a) XRD of FeS + S composite active material and FeS precursor with indexed reflections for Fe₇S₈ and FeS. The FeS precursor material is likely a multiphase mixture of FeS and an iron deficient Fe_{1-x}S phase. After mechanochemical milling, only reflections for FeS and S are observed which indicates that no solid state reactions occurred to form FeS₂; and (b) is an FESEM micrograph of the FeS + S composite active material.

[00105] XRD measurement presented in Figure 15(a) shows that the FeS precursor is composed partly of FeS (Trollite). However, the precursor also exhibits ferrimagnetism, which indicates that the sample is likely a multiphase mixture of FeS and an iron deficient phase like Fe₇S₈ (Pyrrhotite). An unidentified peak at 44.64° suggests that other phases may be present as well.

[00106] After mechanical milling with S, the reflections for FeS are observed to decrease in intensity and broaden. This is consistent with a decrease in average particle size by mechanical grinding action. Further, no new reflections are observed which suggests that the nano-composite is an intimate mixture of elemental FeS and S. The peak at 37.1° can be attributed to the strong (317) reflection of the S precursor (JCPDS #832285). Figure 15(b) confirms that the FeS + S nano-composite is comprised of sub-micron sized particles.

[00107] The electrochemical behavior of a FeS + S composite electrode over time is complex. Figure 16 shows (a) cyclic stability of a FeS + S/Li battery. Assuming that the active material composition of FeS + S has a theoretical specific capacity of 900 mAh g⁻¹, the electrode's specific capacity should not exceed 281 mAh g⁻¹. Excess capacity is evidence for the electrochemical utilization of the 77.5Li₂S-22.5P₂S₅ glass electrolyte component; and (b)-(e) are

voltage profiles for cycles 1, 2, 10, 20, 30, 40, 60, and 150 of the same battery. The variability of voltage profiles with respect to cycle number suggests an evolving electrochemistry.

[00108] Figure 16(a) shows the cyclic stability of a 5mg electrode cycled at 60°C with a current of 144 μ A. The electrode exhibits an initial discharge of 320 mAh g^{-1} , or 1020 mAh g^{-1} based only on the mass fraction of the FeS + S nanocomposite active material. The theoretical capacity of FeS + S should only be approximately 900 mAh g^{-1} , however, the other iron deficient phases present in the FeS precursor affect the actual theoretical value. After the initial discharge, the electrode rapidly gains capacity until a maximum capacity of 550 mAh g^{-1} and maximum energy density of 1040 Wh kg^{-1} are achieved by the 16th cycle. This maximum is followed by an extended phase of capacity fade until the electrode's capacity stabilizes at 330 mAh g^{-1} by the sixty-eighth cycle. The initial discharge and the one-hundred-fiftieth cycle both exhibit a specific capacity of very nearly 320 mAh g^{-1} , yet the energy densities of these cycles are 470 and 600 Wh kg^{-1} , respectively. The discrepancy in energy densities despite similar specific capacities is a reflection of voltage profile evolution to higher potentials. Figures 2(b-e) present the voltage profiles of the first and second, tenth and twentieth, thirtieth and fortieth, and sixtieth and one-hundred-fiftieth cycles, respectively.

[00109] Voltage profile evolution can be correlated to the rise, fade and stabilization of the electrode's capacity. To understand the behavior of the FeS + S electrode, dQ/dV analysis was employed to qualitatively identify parallel redox chemistries. Figure 17 shows (a) dQ/dV profiles for bulk-type all-solid-state Li metal batteries with FeS, syn-FeS₂, and S composite cathodes; and (b)-(e) dQ/dV profiles for cycles 1, 2, 10, 20, 30, 40, 60 and 150 of an example FeS + S/Li battery. It is observed that the evolution of three parallel redox chemistries accounts for the changing capacity of the battery. Twinning of reduction peaks in voltage ranges between 2.13 – 2.19 and 1.56 – 1.51 V provides evidence for the in-situ electrochemical formation of a FeS₂ phase.

[00110] Figure 17a shows the characteristic behavior of FeS, FeS₂, and S in an ASSLB. The FeS₂ chemistry is characterized by dominant reduction peaks at

2.20, 2.14 and 1.49 V, while S is characterized by a reduction peak at 2.2V and FeS by a peak at 1.55V. The dQ/dV profiles in Figure 17b for the first and second cycles show evidence for the reduction of only FeS and S. As the cell's capacity increases, so too does the complexity of the voltage profiles. By the tenth and twentieth cycle, the dQ/dV profiles in Figure 17c show evidence for the reduction of FeS, S and FeS₂. The reduction of FeS₂ is apparent due to the twinning of reduction peaks in voltage ranges of 2.14 – 2.19 V and 1.51 – 1.56 V. This is the first time evidence for the in-situ electrochemical formation of FeS₂ has been presented.

[00111] Next, capacity fade is correlated to the decline of peaks associated with $\text{Fe}^0 \leftrightarrow \text{Fe}^{2+}$ reduction and oxidation. The dQ/dV profiles in Figure 17d for the thirtieth and fortieth cycles during the capacity fade phase show that Fe redox peaks disappear while the S redox peaks remain relatively stable. By the sixtieth cycle the dQ/dV profiles in Figure 17e for the electrode achieve a degree of stability. Extended cycling capacity loss is associated with continued fade of the Fe redox peaks and the fade of S redox peaks.

[00112] The electrochemical utilization of the 77.5Li₂S:22.5P₂S₅ glass electrolyte can be understood with reference to ex-situ XRD measurement of FeS based electrodes. In this example, FeS was used instead of FeS + S to simplify the analysis. A glass electrolyte was used because the absence of ceramic electrolyte diffraction patterns also simplifies the analysis. To mimic the nano-size morphology of the FeS + S active material, the FeS used in this experiment was mechanically milled.

[00113] Figure 18 shows (a) XRD of FeS before and after milling indicates that no phase changes occur during milling; (b) an FESEM micrograph of FeS as received from the vendor, and (c) an FESEM micrograph of Fe_{1-x}S after mechanical milling. The XRD and FESEM analysis confirm that the mechanical milling provides the needed size reduction. Utilization of nano-FeS helps obtain good contact with the glass electrolyte.

[00114] Figure 19(a) shows voltage profiles for two initially overcharged FeS/LiIn batteries. Composite electrodes were collected for XRD after full overcharge (solid) and full discharge (dashed). As seen in Figure 19(a), the FeS

composite electrode was recovered after an initial overcharge (solid) and after full discharge (dashed) (Figure 4a).

[00115] In Figure 19(b), all XRD measurements are normalized with the (100) reflection of the beta-Be sample window (dotted). Li₂S reflections are indicated by the dashed lines while Fe_{1-x}S reflections are indicated by the solid lines. The XRD sample cycled to an initial full discharge exhibits a low capacity because the electrode composite was mixed manually and not mechanically. Because FeS is already in the fully charged state, these cells should have exhibited zero charge capacity. Instead, both cells achieve an overcharge capacity of about 100 mAh g⁻¹.

[00116] It can be seen from the XRD of cycled FeS composite electrodes in Figure 19(b), that this capacity is associated with the utilization of excess Li₂S in the glass electrolyte component of the composite electrode. The diffraction pattern for the glass electrolyte 1950 includes reflections for Li₂S (dashed). As expected, the diffraction pattern for an uncycled composite electrode 1951 includes reflections for Li₂S and FeS (solid). After an initial overcharge 1952, the reflections for Li₂S disappear. When an electrode is discharged after an initial overcharge 1953, reflections for FeS disappear and weak reflections for Li₂S are once again detected. The reduced intensity of the Li₂S reflections in this sample is believed to be due to the small size of electrochemically precipitated Li₂S particles.

[00117] To determine how reasonable it is to attribute the excess capacity to the utilization of excess Li₂S in the glass electrolyte, the percentage of Li₂S oxidized in the cell presented in Figures 16 and 17 can be estimated by assuming that all of the FeS + S was electrochemically utilized and by acknowledging that the highest achieved capacity is 2.8 mAh. A fraction of this capacity can be attributed to utilization of the glass electrolyte at the electrode/glass electrolyte separator interface, as indicated by Figure 21.

[00118] Figure 20 shows the first through seventeenth voltage profiles of a FeS/LiIn battery where the cathode is composed entirely of 5mg of nano-FeS. Normally, FeS should reversibly exhibit only a single plateau. However, with cycling, this battery develops a higher voltage plateau at approximately 1.4 V

versus. InLi. The evolution of the second plateau can be attributed to the electrochemical utilization of Li_2S in the glass electrolyte at the electrode/glass electrolyte separator interface. By the seventeenth cycle, up to 300 μAh of capacity can be attributed to the utilization of glass electrolyte separator. This interface utilization effect may lead to an overestimation of specific capacity and contribute to the observed excess capacity.

[00119] Utilization of the glass electrolyte separator may lead to an overestimation of specific capacity and contribute to the observed excess capacity especially when the electrode is very small like it is in this case. The $\text{FeS} + \text{S}$ component can account for 1.45 mAh of the maximum capacity. Without accounting for utilization of the glass electrolyte separator, the remaining capacity indicates that 1.16 mg, or 86%, of Li_2S in the glass electrolyte is electrochemically utilized.

[00120] Such a large percentage of the Li_2S component is likely not oxidized without decreasing the ionic transport of the composite electrode. Yet, a rate test at 60°C was conducted on another $\text{FeS} + \text{S}$ electrode after a five cycle activation and good performance was observed.

[00121] **Figure 21** shows (a) specific discharge capacity of a battery as a function of applied current, and (b) voltage profiles of the same battery as a function of applied current. The electrode maintains a specific capacity of 200 mAh g^{-1} with an applied current of about 2.40 mA. To maintain good ionic transport, it is likely that the P_2S_5 component of the glass electrolyte may be electrochemically utilized as well. Utilization of P_2S_5 also explains why capacity increases during discharge cycles, and not only during the charge cycles when excess Li_2S is initially oxidized to S.

[00122] It is noted that while the initial specific discharge capacity of the cell presented in Figures 16 and 17 is similar to that presented in Figure 20, the degree and rate of capacity activation of each cell is much different. By the fifth cycle the first cell exhibits a specific capacity of about 488 mAh g^{-1} , while the cell used in the rate test only exhibits a specific capacity of about 400 mAh g^{-1} . The maximum capacity of the rate cell is also about 15% lower than that achieved by the first cell.


[00123] The electrodes for these two samples were prepared separately which attests to the sensitivity of electrolyte activation to the quality of the glass electrolyte. Electrolyte sensitivity is emphasized by the results of another study that did not observe electrolyte utilization. Like this study, nano-FeS was used as an active material and Li₂S was a precursor for their electrolyte. However, the electrolyte was a different composition, thio-LISICON Li_{3.25}Ge_{0.25}P_{0.75}S₄, and was prepared by melt quenching instead of mechanochemical milling. Previous work also did not show evidence for electrochemical activation of the glass electrolyte. In this study, three 5 micron cubes of synthetic FeS₂ were used as the active material. Such a large particle size results in poor contact between the glass electrolyte and the active material which may inhibit electrolyte utilization. Cubic-FeS₂ is also a semiconductor with a much lower electronic conductivity than that of the ferrimagnetic Fe_{1-x}S precursor used in this study.

[00124] It is noted that the decision to mechanically combine μ m-Cu powder with S or Li₂S can be further improved. For example, the conversion materials, FeF₂ and CuF₂ suggest that a nano-structured network of reduced metallic nanoparticles may be employed for good reversibility. A mechanical mixture with micron active metal particles is therefore not ideal for good reversibility or for good electrolyte utilization. Instead, electrochemically reduced nano-active metal particles may be used due to the better atomic proximity to other reduced species, as well as to the electrolyte particles, to further enhance reversibility and effective electrolyte utilization.

[00125] The examples shown and described herein are provided for purposes of illustration and are not intended to be limiting. Still other examples are also contemplated.

CLAIMS

1. An all-solid-state lithium battery, comprising:
 - a cathode having a transition metal sulfide mixed with elemental sulfur, wherein:
 - upon full discharge, the cathode undergoes conversion reactions to form a transition metal + lithium sulfide; and
 - upon full charge, the cathode undergoes conversion reactions to form the transition metal sulfide + lithium + electrons.
2. The battery of claim 1, wherein the transition metal sulfide is selected from monosulfides, disulfides, and trisulfides.
3. The battery of claim 1, wherein transition metal sulfide is mechanically combined.
4. The battery of claim 1, wherein the cathode comprises solid state electrode (SSE) particles, and a conducting additive.
5. The battery of claim 1, further comprising a solid state electrode (SSE) layer between the cathode and an anode.
6. The battery of claim 1, further comprising an anode including lithium metal, graphite, or silicon-based active materials.
7. The battery of claim 1, wherein the cathode is selected from FeS_2 or FeS_2 equivalent.
8. A method of in-situ electrochemical synthesis of pyrite (FeS_2) from iron sulfide (FeS) and elemental sulfur (S) precursors, comprising:
 - cycling $\text{FeS} + \text{S}$ composite electrodes at moderately elevated temperature;
 - wherein charge products are described by the following equation:




9. The method of claim 8, further comprising producing voltage plateaus indicative of FeS_2 in battery cells constructed with $\text{FeS} + \text{S}$ or as an FeS_2 equivalent.


10. The method of claim 9, wherein the voltage plateaus become more defined upon further cycling.

11. The method of claim 8, wherein the moderately elevated temperature is about 60°C.

12. The method of claim 8, wherein initial discharge of FeS_2 proceeds in two steps:



13. The method of claim 12, wherein subsequent charge and discharge cycles proceed according to the following reactions:



14. A solid-state lithium battery, comprising:
a solid state electrolyte; and
an activating agent, wherein the activating agent activates excess Li_2S in the solid state electrolyte to realize an improved charge capacity.

15. The battery of claim 14, wherein solid state electrolyte is sulfide-based.

16. The battery of claim 14, wherein activating agent is a transition metal sulfide such as FeS, TiS₂, FeS₂ and/or FeS₂ equivalent.
17. The battery of claim 14, wherein the activating agent has a highly ionic and/or electrically conductive character.
18. The battery of claim 17, wherein the highly ionic and electrically conductive character of the activating agent activates the solid state electrolyte.
19. The battery of claim 18, wherein the activating agent activates otherwise inert excess Li₂S in the solid state electrolyte.
20. The battery of claim 14, wherein the improved charge capacity is realized after a single charge event at an elevated temperature.
21. The battery of claim 20, wherein the elevated temperature is about 60°C.
22. The battery of claim 20, wherein the improved charge capacity is greater than about 50%.
23. The battery of claim 14, wherein the sulfide based solid electrolyte is xLi₂S-(100-x)P₂S₅.
24. The battery of claim 14, further comprising a composite electrode.
25. The battery of claim 24, wherein the composite electrode is 80Li₂S-20P₂S₅:acetylene black.
26. The battery of claim 24, wherein the composite electrode is TiS₂:80Li₂S-20P₂S₅ acetylene black.

27. The battery of claim 24, further comprising an In metal negative electrode.
28. A method of activation of a solid-state lithium battery, comprising thermo-electrochemical activating excess Li₂S in a solid state electrolyte to realize an improved charge capacity.
29. The method of claim 28, wherein the improved charge capacity is realized after a single charge event at an elevated temperature.
30. The method of claim 29, wherein the elevated temperature is about 60°C.
31. The method of claim 29, wherein the improved charge capacity is greater than about 50%.
32. The method of claim 29, further comprising an FeS₂ equivalent cathode.




Fig. 2a




Fig. 2b










Fig. 3a**Fig. 3b****Fig. 3c****Fig. 3d****Fig. 3e****Fig. 3f**








Fig. 5a**Fig. 5b****Fig. 5c**






Fig. 7a**Fig. 7b**



Fig. 8a**Fig. 8b**



Fig. 9a**Fig. 9b**


Fig. 10


Fig. 11





Fig. 12a**Fig. 12c****Fig. 12b****Fig. 12d**



Fig. 13a**Fig. 13b**


Fig. 14




Fig. 15a**Fig. 15b**

Fig. 16a**Fig. 16a**

Cycle Index





Fig. 16c**Fig. 16b****Fig. 16d**






Fig. 17a)**Fig. 17b****Fig. 17d****Fig. 17c****Fig. 17e**

Fig. 18a




Fig. 18b




Fig. 18c






Fig. 19a**Fig. 19b**



Fig. 20

Fig. 21a**Fig. 21b**