



US 20030162099A1

(19) **United States**

(12) **Patent Application Publication**

Bowden et al.

(10) **Pub. No.: US 2003/0162099 A1**

(43) **Pub. Date: Aug. 28, 2003**

(54) **NON-AQUEOUS ELECTROCHEMICAL CELL**

Publication Classification

(76) Inventors: **William L. Bowden**, Nashua, NH (US);
Nikolai N. Issaev, Woodbridge, CT
(US); **Michael Pozin**, Brookfield, CT
(US)

(51) **Int. Cl.⁷ H01M 10/40**

(52) **U.S. Cl. 429/333; 429/331**

Correspondence Address:
FISH & RICHARDSON PC
225 FRANKLIN ST
BOSTON, MA 02110 (US)

(21) Appl. No.: **10/085,303**

(22) Filed: **Feb. 28, 2002**

(57) **ABSTRACT**

A lithium electrochemical cell includes an electrolyte having a mixture of solvents including propylene carbonate (PC) and dimethoxyethane (DME), and a salt mixture. The salt mixture includes lithium trifluoromethanesulfonate (LiTFS), and lithium trifluoromethanesulfonimide (LiTFSI), and the cell contains less than 1500 ppm by weight of sodium. The mixture of solvents can further include ethylene carbonate (EC).





FIG. 1



NON-AQUEOUS ELECTROCHEMICAL CELL

TECHNICAL FIELD

[0001] The invention relates to non-aqueous electrochemical cells.

BACKGROUND

[0002] Batteries are commonly used electrical energy sources. A battery contains a negative electrode, typically called the anode, and a positive electrode, typically called the cathode. The anode contains an active material that can be oxidized; the cathode contains or consumes an active material that can be reduced. The anode active material is capable of reducing the cathode active material.

[0003] When a battery is used as an electrical energy source in a device, electrical contact is made to the anode and the cathode, allowing electrons to flow through the device and permitting the respective oxidation and reduction reactions to occur to provide electrical power. An electrolyte in contact with the anode and the cathode contains ions that flow through the separator between the electrodes to maintain charge balance throughout the battery during discharge.

[0004] It is desirable for batteries to have good capacity, after they are produced and/or after they have been stored for extended periods of time.

SUMMARY

[0005] The invention relates to non-aqueous electrochemical cells.

[0006] In one aspect, the invention features a lithium electrochemical cell including an electrolyte having a mixture of solvents including propylene carbonate and dimethoxyethane, and a salt mixture including lithium trifluoromethanesulfonate and lithium trifluoromethanesulfonimide. The cell contains less than 1500 ppm by weight of sodium.

[0007] Embodiments of the invention may include one or more of the following features. The cell contains less than 1200 ppm, e.g., less than 1000 ppm, less than 800 ppm, or less than 600 ppm, by weight of sodium. The cell includes a mixture of solvents having 40-80%, e.g., 50-75%, by weight of dimethoxyethane, and 20-60%, e.g., 25-50%, by weight of propylene carbonate; and the salt mixture has a concentration between 0.4 M and 1.2 M in the mixture of solvents.

[0008] In another aspect, the invention features a lithium electrochemical cell including an electrolyte having a mixture of solvents including ethylene carbonate, propylene carbonate, and dimethoxyethane, and a salt mixture having lithium trifluoromethanesulfonate and lithium trifluoromethanesulfonimide. The cell contains less than 1500 ppm, e.g., less than 1200 ppm, less than 1000 ppm, less than 800 ppm, or less than 600 ppm by weight of sodium.

[0009] Embodiments of the invention may include one or more of the following features. The cell includes a mixture of solvents having less than 30%, e.g. 10-20%, by weight of ethylene carbonate, 40-85%, e.g., 50-70%, by weight of dimethoxyethane; and the salt mixture has a concentration between 0.4 M and 1.2 M in the mixture of solvents. The cell includes a mixture of solvents including 5-15% by weight of

ethylene carbonate, 70-80% by weight of dimethoxyethane, and 10-20% by weight of propylene carbonate. The cell contains less than 500 ppm by weight of sodium.

[0010] In another aspect, the invention features an electrolyte for a lithium electrochemical cell consisting essentially of a mixture of solvents including propylene carbonate and dimethoxyethane, and a salt mixture having lithium trifluoromethanesulfonate and lithium trifluoromethanesulfonimide. The electrolyte can be used in a cell, e.g., one that contains less than 1500 ppm, e.g., less than 1000 ppm, or less than 500 ppm, by weight of sodium.

[0011] The electrolyte mixture can include a mixture of solvents including 40-80%, e.g., 50-75%, by weight of dimethoxyethane, and 20-60%, e.g., 25-50%, by weight of propylene carbonate; and the salt mixture can have a concentration between 0.4 M and 1.2 M in the mixture of solvents.

[0012] In another aspect, the invention features an electrolyte for a lithium electrochemical cell consisting essentially of a mixture of solvents including ethylene carbonate, propylene carbonate, and dimethoxyethane, and a salt mixture having lithium trifluoromethanesulfonate and lithium trifluoromethanesulfonimide. The electrolyte can be used in a cell, e.g., one that contains less than 1500 ppm, e.g., less than 1000 ppm, or less than 500 ppm by weight of sodium.

[0013] The electrolyte may include a mixture of solvents including less than 30%, e.g., 10-20%, by weight of ethylene carbonate, and 40-85%, e.g., 50-70%, by weight of dimethoxyethane; and the salt mixture may have a concentration between 0.4 M and 1.2 M in the mixture of solvents.

[0014] The electrolyte may include a mixture of solvents including 5-15% by weight of ethylene carbonate, 70-80% by weight of dimethoxyethane, and 10-20% by weight of propylene carbonate.

[0015] Embodiments may have one or more of the following advantages. The cells can have good capacity, after production and/or after storage for extended periods of time.

[0016] Other features and advantages of the invention will be apparent from the description of the preferred embodiments thereof and from the claims.

DESCRIPTION OF DRAWINGS

[0017] **FIG. 1** is a sectional view of a nonaqueous electrochemical cell.

DETAILED DESCRIPTION

[0018] Referring to **FIG. 1**, an electrochemical cell **10** includes an anode **12** in electrical contact with a negative current collector **14**, a cathode **16** in electrical contact with a positive current collector **18**, a separator **20**, and an electrolyte. Anode **12**, cathode **16**, separator **20**, and the electrolyte are contained within a case **22**. The electrolytic solution includes a mixture of solvents and a salt that is at least partially dissolved in the mixture of solvents.

[0019] The electrolyte can be in liquid, solid or gel (polymer) form. The electrolyte can contain an organic solvent such as propylene carbonate (PC), ethylene carbonate (EC), dimethoxyethane (DME), dioxolane (DO), tetrahydrofuran (THF), acetonitrile (CH₃CN), gamma-butyrolactone, diethyl

carbonate (DEC), dimethyl carbonate (DMC), ethyl methyl carbonate (EMC) dimethylsulfoxide (DMSO), methyl acetate (MA), methyl formate (MF), sulfolane or combinations thereof. The electrolyte can alternatively contain an inorganic solvent such as SO_2 or SOCl_2 . The solvents can be selected to provide a mixture having a combination of physical and chemical properties. For example, the electrolyte can include a first solvent, such as PC or EC, that is polar, sluggishly reactive, and/or high boiling; and a second solvent, such as DME, THF, or DMC, that is relatively less polar, volatile, relatively non-viscous, and/or unreactive.

[0020] The electrolyte can also contain a lithium salt such as lithium trifluoromethanesulfonate (LiTFS) or lithium trifluoromethanesulfonimide (LiTFSI), or a combination thereof. Additional lithium salts that can be included are listed in U.S. Pat. No. 5,595,841, which is hereby incorporated by reference in its entirety.

[0021] In some embodiments, cell **10** includes an electrolyte formed of a mixture of solvents having DME and PC, and a salt mixture of LiTFS and LiTFSI. Cell **10** can further have a low sodium concentration. The concentration of DME in the mixture of solvents can range from about 30% to about 85%. The concentration of DME in the mixture of solvents can be equal to or greater than 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 75%, or 80%; and/or equal to or less than 85%, 80%, 75%, 70%, 65%, 60%, 55%, 50%, 45%, 40%, or 35%. The concentration of PC in the mixture of solvents can be equal to 100% minus the concentration of DME. For example, if the concentration of DME in the mixture of solvents is 75%, then the concentration of PC in the mixture of solvents is 25%. If the concentration of DME in the mixture of solvents is 50%-75%, then the concentration of PC in the mixture of solvents is 25%-50%.

[0022] For the LiTFS and LiTFSI salt mixture, the total concentration of salt in the mixture of solvents can range from about 0.4 M to about 1.2 M. The total concentration of LiTFS and LiTFSI in the mixture of solvents can be equal to or greater than 0.40 M, 0.45 M, 0.50 M, 0.55 M, 0.60 M, 0.65 M, 0.70 M, 0.75 M, 0.80 M, 0.85 M, 0.90 M, 0.95 M, 1.00 M, 1.05 M, 1.10 M, or 1.15 M; and/or equal to or less than 1.2 M, 1.15 M, 1.10 M, 1.05 M, 1.00 M, 0.95 M, 0.90 M, 0.85 M, 0.80 M, 0.75 M, 0.70 M, 0.65 M, 0.60 M, 0.55 M, 0.50 M, or 0.45 M. Of the total concentration of salt, the concentration of LiTFS in the mixture of solvents can be equal to or greater than 5%, 10%, 15%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 75%, 80%, 85%, 90%, or 95%; and/or equal to or less than 95%, 90%, 85%, 80%, 75%, 70%, 65%, 60%, 55%, 50%, 45%, 40%, 35%, 30%, 25%, 20%, 15%, 10%, or 5%. The concentration of LiTFSI in the mixture of solvents can be equal to 100% minus the concentration of LiTFS in the mixture of solvents. For example, if the total concentration of salt in the mixture of solvents is 0.5 M, and the LiTFS concentration in the mixture of solvents is 90% (i.e., 0.45 M), then the LiTFSI concentration in the electrolyte mixture is 10% (i.e., 0.05 M). In embodiments, other types of salts can be added to the electrolyte.

[0023] The sodium concentration described herein applies to contents inside cell **10** plus any sodium on the inner side of case **20** and/or cap **24**. For example, the sodium content may apply to the electrolyte and a "jelly roll" inside cell **10**.

The jelly roll is formed of anode **12**, cathode **16**, current collectors **14** and **18**, separator **20**, and any protective tapes used in cell **10**.

[0024] The sodium concentration in cell **10** can be between about 100 ppm to 1500 ppm by weight. The sodium concentration can be equal to or greater than 100, 200, 300, 400, 500, 600, 700, 800, 900, 1000, 1100, 1200, 1300, or 1400 ppm by weight; and/or equal to or less than 1500, 1400, 1300, 1200, 1100, 1000, 900, 800, 700, 600, 500, 400, 300, 200, or 100 ppm by weight. Generally, the concentration of sodium in cell **10** can be controlled, e.g., minimized or reduced, by controlling the manufacturing of the cell. For example, in embodiments in which electrolytic manganese dioxide (EMD) is used in cathode **16**, the EMD can be washed and/or neutralized after electrodeposition with an agent that does not contain sodium or have reduced amounts of sodium, such as LiOH. Case **20** can be cleaned with a solution that does not contain sodium or carefully washed. Generally, other components of cell **10**, such as anode **12** and separator **20**, can be similarly specified not to contain sodium or to contain reduced amounts of sodium.

[0025] Other materials can be added to the electrolyte mixture. For example, in certain embodiments, cell **10** includes an electrolyte formed of a mixture of solvents including EC, DME and PC, and a salt mixture of LiTFS and LiTFSI. The concentration of EC in the mixture of solvents can be between about 5% and 30%. The concentration of EC in the mixture of solvents can be equal to or greater than 5%, 10%, 15%, 20%, or 25%; and/or equal to or less than 30%, 25%, 20%, 15%, or 10%. The concentration of DME in the mixture of solvents can range from about 30% to about 85%. The concentration of DME in the mixture of solvents can be equal to or greater than 30%, 35%, 40%, 45%, 50%, 55%, 60%, 65%, 70%, 75%, or 80%; and/or equal to or less than 85%, 80%, 75%, 70%, 65%, 60%, 55%, 50%, 45%, 40%, or 35%. The concentration of PC in the mixture of solvents can be equal to 100% minus the concentration of EC and DME. For example, if the concentration of EC in the mixture of solvents is 15%, and the concentration of DME in the mixture of solvents is 60%, then the concentration of PC in the mixture of solvents is 25%. Examples of an EC:DME:PC solvent mixture are 14:62:24 and 10:75:15 by weight.

[0026] The LiTFS and LiTFSI concentrations in the electrolyte, e.g., 0.4-1.2 M, can be generally similar to those described herein. In embodiments, other types of salts can be added to the electrolyte.

[0027] The sodium concentration in cell **10**, e.g., 100-1500 ppm by weight, can be generally similar to those described herein. Without wishing to be bound by theory, it is believed that as the concentration of EC increases, the concentration of sodium can be increased without substantially affecting cell **10** adversely. Accordingly, in embodiments, the sodium concentration in cell **10** having EC can be between about 100 ppm to 3,000 ppm by weight. The sodium concentration can be equal to or greater than 100, 200, 300, 400, 500, 600, 700, 800, 900, 1000, 1100, 1200, 1300, 1400, 1600, 1800, 1900, 2100, 2300, 2500, 2700, or 2900 ppm by weight; and/or equal to or less than 2900, 2700, 2500, 2300, 2100, 1900, 1800, 1600, 1500, 1400, 1300, 1200, 1100, 1000, 900, 800, 700, 600, 500, 400, 300, 200, or 100 ppm by weight.

[0028] Cathode **16** includes an active cathode material, which is generally coated on the cathode current collector.

The current collector is generally titanium, stainless steel, nickel, aluminum, or an aluminum alloy, e.g., aluminum foil. The active material can be, e.g., a metal oxide, halide, or chalcogenide; alternatively, the active material can be sulfur, an organosulfur polymer, or a conducting polymer. Specific examples include MnO_2 , V_2O_5 , CoF_3 , MoS_2 , FeS_2 , SOCl_2 , MoO_3 , S, $(\text{C}_6\text{H}_5\text{N})_n$, $(\text{S}_3\text{N}_2)_n$, where n is at least 2. The active material can also be a carbon monofluoride. An example is a compound having the formula CF_x , where x is 0.5 to 1.0. The active material can be mixed with a conductive material such as carbon and a binder such as polytetrafluoroethylene (PTFE). An example of a cathode is one that includes aluminum foil coated with MnO_2 . The cathode can be prepared as described in U.S. Pat. No. 4,279,972.

[0029] Anode **12** can consist of an active anode material, usually in the form of an alkali metal, e.g., Li, K, or an alkaline earth metal, e.g., Ca, Mg. The anode can also consist of alloys of alkali metals and alkaline earth metals or alloys of alkali metals and Al. The anode can be used with or without a substrate. The anode also can consist of an active anode material and a binder. In this case an active anode material can include carbon, graphite, an acetylenic mesophase carbon, coke, a metal oxide and/or a lithiated metal oxide. The binder can be, for example, PTFE. The active anode material and binder can be mixed to form a paste that can be applied to the substrate of anode **12**.

[0030] In some embodiments, the sodium content in a lithium anode is less than about 500 ppm by weight, e.g., less than 400 ppm, less than 300 ppm, less than 200, or less than 100 ppm. The sodium content can be controlled by carefully controlling anode processing (e.g., lithium extrusion), cell processing, cell aging, cell predischARGE, cell storage, and/or cell discharge.

[0031] Separator **20** can be formed of any of the standard separator materials used in nonaqueous electrochemical cells. For example, separator **20** can be formed of polypropylene (e.g., nonwoven polypropylene or microporous polypropylene), polyethylene, layers of polypropylene and polyethylene, and/or a polysulfone.

[0032] To assemble the cell, separator **20** can be cut into pieces of a similar size as anode **12** and cathode **16** and placed therebetween as shown in FIG. 1. Anode **12**, cathode **16**, and separator **20** are then placed within case **22**, which can be made of a metal such as nickel, nickel plated steel, stainless steel, or aluminum, or a plastic such as polyvinyl chloride, polypropylene, polysulfone, ABS or a polyamide. Case **22** is then filled with the electrolytic solution and sealed. One end of case **22** is closed with a cap **24** and an annular insulating gasket **26** that can provide a gas-tight and fluid-tight seal. Positive current collector **18**, which can be made of aluminum, connects cathode **16** to cap **24**. Cap **24** may also be made of aluminum. A safety valve **28** is disposed in the inner side of cap **24** and is configured to decrease the pressure within battery **10** when the pressure exceeds some predetermined value. Additional methods for assembling the cell are described in U.S. Pat. Nos. 4,279,972; 4,401,735; and 4,526,846.

[0033] Other configurations of battery **10** can also be used, including, e.g., the coin cell configuration. The batteries can be of different voltages, e.g., 1.5V, 3.0V, or 4.0V.

[0034] Other embodiments are within the claims.

What is claimed is:

1. A lithium electrochemical cell, comprising:
 - an electrolyte comprising:
 - a mixture of solvents comprising:
 - propylene carbonate;
 - dimethoxyethane; and
 - a salt mixture comprising:
 - lithium trifluoromethanesulfonate; and
 - lithium trifluoromethanesulfonimide,
 - wherein the cell contains less than 1500 ppm by weight of sodium.
 - 2. The cell of claim 1, wherein the cell contains less than 1200 ppm by weight of sodium.
 - 3. The cell of claim 1, wherein the cell contains less than 1000 ppm by weight of sodium.
 - 4. The cell of claim 1, wherein the cell contains less than 800 ppm by weight of sodium.
 - 5. The cell of claim 1, wherein the cell contains less than 600 ppm by weight of sodium.
 - 6. The cell of claim 1, wherein the mixture of solvents comprises:
 - 40-80% by weight of dimethoxyethane; and
 - 20-60% by weight of propylene carbonate; and
 - the salt mixture has a concentration between 0.4 M and 1.2 M in the mixture of solvents.
 - 7. The cell of claim 6, wherein the mixture of solvents comprises:
 - 50-75% by weight of dimethoxyethane; and
 - 25-50% by weight of propylene carbonate.
 - 8. A lithium electrochemical cell, comprising:
 - an electrolyte comprising:
 - a mixture of solvents comprising:
 - ethylene carbonate;
 - propylene carbonate; and
 - dimethoxyethane; and
 - a salt mixture comprising:
 - lithium trifluoromethanesulfonate; and
 - lithium trifluoromethanesulfonimide,
 - wherein the cell contains less than 1500 ppm by weight of sodium.
 - 9. The cell of claim 8, wherein the cell contains less than 1200 ppm by weight of sodium.
 - 10. The cell of claim 8, wherein the cell contains less than 1000 ppm by weight of sodium.
 - 11. The cell of claim 8, wherein the cell contains less than 800 ppm by weight of sodium.
 - 12. The cell of claim 8, wherein the cell contains less than 600 ppm by weight of sodium.
 - 13. The cell of claim 8, wherein the mixture of solvents comprises:
 - less than 30% by weight of ethylene carbonate;
 - 40-85% by weight of dimethoxyethane; and

the salt mixture has a concentration between 0.4 M and 1.2 M in the mixture of solvents.

14. The cell of claim 13, wherein the mixture of solvents comprises:

10-20% by weight of ethylene carbonate;

50-70% by weight of dimethoxyethane.

15. The cell of claim 14, comprising less than 500 ppm by weight of sodium.

16. The cell of claim 13, wherein the mixture of solvents comprises: 5-15% by weight of ethylene carbonate; 70-80% by weight of dimethoxyethane; and 10-20% by weight of propylene carbonate.

17. The cell of claim 16, comprising less than 500 ppm by weight of sodium.

* * * * *