



(86) Date de dépôt PCT/PCT Filing Date: 2012/10/31
(87) Date publication PCT/PCT Publication Date: 2013/05/10
(45) Date de délivrance/Issue Date: 2017/04/25
(85) Entrée phase nationale/National Entry: 2014/04/07
(86) N° demande PCT/PCT Application No.: JP 2012/006975
(87) N° publication PCT/PCT Publication No.: 2013/065298
(30) Priorité/Priority: 2011/11/01 (JP2011-240051)

(51) Cl.Int./Int.Cl. *C22C 38/06* (2006.01),
C21D 8/02 (2006.01), *C21D 9/46* (2006.01),
C22C 38/58 (2006.01)
(72) Inventeurs/Inventors:
KAMI, CHIKARA, JP;
YAMAZAKI, KAZUHIKO, JP
(73) Propriétaire/Owner:
JFE STEEL CORPORATION, JP
(74) Agent: MOFFAT & CO.

(54) Titre : FEUILLE D'ACIER LAMINEE A CHAUD A HAUTE RESISTANCE AYANT D'EXCELLENTES
CARACTERISTIQUES DE FLEXION ET UNE EXCELLENTE TENACITE A BASSE TEMPERATURE ET SON
PROCEDE DE FABRICATION

(54) Title: HIGH-STRENGTH HOT ROLLED STEEL SHEET WITH EXCELLENT BENDABILITY AND LOW-
TEMPERATURE TOUGHNESS, AND METHOD FOR MANUFACTURING THE SAME

(57) **Abrégé/Abstract:**

Provided is a high-strength hot-rolled steel sheet that is suitable for structural members of large construction/industrial machinery. A steel material having a composition that comprises 0.08 to 0.25% of C, 0.01 to 1.0% of Si, and 0.8 to 2.1% of Mn and in which the contents of P, S, and Al are adjusted to appropriate ranges is: heated to a temperature of 1100 to 1250°C; subjected to rough rolling; subjected to finish rolling such that the value found by dividing the cumulative rolling-reduction rate in the partially recrystallized γ region and the non-recrystallized γ region by the cumulative rolling-reduction rate in the recrystallized γ region is from 0 to 0.2; immediately cooled after completion of said finish rolling and cooled to a cooling stop temperature, which is lower than or equal to 150°C above the Ms point, within 30 seconds from the start of cooling at a cooling rate that is higher than or equal to the martensite-generating critical cooling rate in terms of average cooling rate within the temperature range of 750°C to 500°C; kept for 5 to 60 seconds within the temperature range of $\pm 100^\circ\text{C}$ of said cooling stop temperature; and wound up into a coil shape at a winding temperature within the range of $\pm 100^\circ\text{C}$ of said cooling stop temperature. Thus, it is possible to obtain a hot-rolled steel sheet that: comprises a tempered martensite phase or a low-temperature transformation bainite phase as the main phase; has a structure in which the average grain size of prior γ grains in a cross section parallel to the rolling direction is 20 μm or less and the average grain size of prior γ grains in a cross section orthogonal to the rolling direction is 15 μm or less; and has high toughness and high strength with a yield strength YS of 960 MPa or higher and also has excellent bending characteristics.



ABSTRACT

The invention provides high-strength hot rolled steel sheets suited for large-sized construction and industrial machinery structural members. A steel with a chemical composition including C: 0.08 to 0.25%, Si: 0.01 to 1.0%, Mn: 0.8 to 2.1% and appropriately controlled amounts of P, S and Al is heated to a temperature of 1100 to 1250°C, rough rolled, and finish rolled in such a manner that the cumulative reduction ratio in the partially recrystallized γ region and the non-recrystallized γ region divided by the cumulative reduction ratio in the recrystallized γ region becomes 0 to 0.2. Immediately after the completion of the finish rolling, cooling is initiated and the steel sheet is cooled to a cooling termination temperature that is not more than M_s transformation temperature + 150°C within 30 seconds from the initiation of the cooling, the average cooling rate in the temperature range of 750°C to 500°C being not less than the critical cooling rate for the occurrence of martensite formation. The steel sheet is then held at a temperature in the range of the cooling termination temperature $\pm 100^\circ\text{C}$ for 5 to 60 seconds, and is coiled into a coil at a coiling temperature in the range of the cooling termination temperature $\pm 100^\circ\text{C}$. In this manner, hot rolled steel sheets may be obtained which have high strength with a yield strength YS of 960 MPa or above and high toughness as

well as excellent bendability and which have a microstructure in which the main phase is a tempered martensite phase or a lower temperature-transformed bainite phase, the average grain diameter of prior γ grains is not more than 20 μm in a cross section parallel to the rolling direction and the average grain diameter of prior γ grains is not more than 15 μm in a cross section perpendicular to the rolling direction.

- 1 -

DESCRIPTION

Title of Invention:

HIGH-STRENGTH HOT ROLLED STEEL SHEET WITH EXCELLENT
BENDABILITY AND LOW-TEMPERATURE TOUGHNESS, AND METHOD FOR
MANUFACTURING THE SAME

Technical Field

[0001]

The present invention relates to high-strength hot rolled steel sheets suited for structural members of construction machines and industrial machines (hereinafter, also referred to as construction and industrial machinery structural members). In particular, the invention pertains to improvements in bendability and low-temperature toughness. As used herein, the term "steel sheets" is defined to include steel sheets and steel strips. Further, the term "high-strength hot rolled steel sheets" is defined to refer to high-strength hot rolled steel sheets having a yield strength YS of 960 to 1200 MPa grade.

Background Art

[0002]

In recent years, larger construction machines such as cranes and trucks have come to be used in the construction of high-rise buildings. Industrial machines tend to be upsized too. Such trends require that the self weight of these machines be reduced. Thus, there has been a demand

- 2 -

for thin steel sheets with a high strength of not less than 960 MPa in terms of yield strength YS for use as structural members of these large-sized construction and industrial machineries.

[0003]

In response to such demands, for example, Patent Literature 1 proposes a method for manufacturing high-strength hot rolled steel sheets with good workability and weldability which involves a steel slab including, in mass%, C: 0.05 to 0.15%, Si: not more than 1.50%, Mn: 0.70 to 2.50%, Ni: 0.25 to 1.5%, Ti: 0.12 to 0.30% and B: 0.0005 to 0.0015% as well as appropriate amounts of P, S, Al and N, the method including heating the steel slab to 1250°C or above, hot rolling the slab at a temperature of from the Ar₃ transformation temperature to 950°C with a total finish reduction ratio of not less than 80%, cooling the steel sheet at a cooling rate of 30 to 80°C/s in the range of 800 to 500°C, and coiling the steel sheet at 500°C or below. Patent Literature 1 describes that the technique allows for reliable manufacturing of high-strength hot rolled steel sheets with excellent bending workability and weldability that have a yield point of not less than 890 MPa and a tensile strength of not less than 950 MPa.

[0004]

Further, Patent Literature 2 proposes a method for

- 3 -

manufacturing high-strength hot rolled steel sheets which involves a steel slab including, in mass%, C: 0.05 to 0.20%, Si: not more than 0.60%, Mn: 0.10 to 2.50%, sol Al: 0.004 to 0.10%, Ti: 0.04 to 0.30% and B: 0.0005 to 0.0015%, the method including heating the steel slab at a heating rate of not less than 150°C/h in the temperature range of at least from 1100°C to a heating temperature that is not less than the TiC solution treatment temperature and not more than 1400°C while the holding time at the heating temperature is 5 to 30 minutes, and thereafter hot rolling the slab. The technique described in Patent Literature 2 utilizes a trace amount of titanium as a precipitation hardening element and a trace amount of solute boron as an austenite (γ) stabilizing element, thereby lowering the temperature at which transformation occurs during cooling, and reducing the grain size of ferrite microstructure formed after transformation. The patent literature teaches that the above configuration results in hot rolled steel sheets having high strength of about 1020 MPa in terms of tensile strength as well as high toughness of about -70°C in terms of fracture appearance transition temperature $vTrs$.

[0005]

Patent Literature 3 proposes a method for manufacturing high-strength hot rolled steel sheets with excellent bending workability and weldability which involves a steel slab

- 4 -

including, in mass%, C: 0.05 to 0.15%, Si: not more than 1.50%, Mn: 0.70 to 2.50%, Ni: 0.25 to 1.5%, Ti: 0.12 to 0.30% and B: 0.0005 to 0.0015% as well as appropriate amounts of P, S, Al and N, the method including heating the steel slab to 1250°C or above, hot rolling the slab at a temperature of from the Ar3 transformation temperature to 950°C with a total finish reduction ratio of not less than 80%, cooling the steel sheet at a cooling rate of 20°C/s to less than 30°C/s in the range of 800 to 200°C, coiling the steel sheet at 200°C or below, and subjecting the steel sheet to a thermo-mechanical treatment in which the steel sheet is subjected to a working strain of 0.2 to 5.0% and held at a temperature in the range of 100 to 400°C for an appropriate time. Patent Literature 3 describes that high-strength hot rolled steel sheets having a yield point of not less than 890 MPa and a tensile strength of not less than 950 MPa may be easily manufactured according to the disclosed technique.

[0006]

Further, Patent Literature 4 describes a method for manufacturing ultrahigh-strength hot rolled steel sheets with excellent workability. This method involves a steel slab having a chemical composition which includes C: 0.05 to 0.20%, Si: 0.05 to 0.50%, Mn: 1.0 to 3.5%, P: not more than 0.05%, S: not more than 0.01%, Nb: 0.005 to 0.30%, Ti: 0.001

- 5 -

to 0.100%, Cr: 0.01 to 1.0% and Al: not more than 0.1% and in which the contents of Si, P, Cr, Ti, Nb and Mn satisfy a specific relationship, the method including heating the steel slab to 1100 to 1300°C immediately after casting or after cooling, then hot rolling the slab at a finish rolling end temperature of 950 to 800°C, cooling the steel sheet at a cooling rate of not less than 30°C/s by initiating the cooling within 0.5 seconds from the completion of the rolling, and coiling the steel sheet at 500 to 300°C. According to the disclosure, the above configuration results in ultrahigh-strength hot rolled steel sheets with excellent workability which have a metallic microstructure containing bainite as the main phase with a volume fraction of 60 to less than 90% and at least one of pearlite, ferrite, retained austenite and martensite as the second phase, the bainite phase having an average grain diameter of less than 4 μm . In spite of the fact that the tensile strength is 980 MPa or above, the steel sheets are described to exhibit excellent stretch flangeability and excellent strength-ductility balance as well as have a low yield ratio.

[0007]

Further, Patent Literature 5 describes a method for manufacturing high-strength hot rolled steel sheets which involves a steel slab having a chemical composition containing C: 0.10 to 0.25%, Si: not more than 1.5%, Mn: 1.0

- 6 -

to 3.0%, P: not more than 0.10%, S: not more than 0.005%, Al: 0.01 to 0.5%, N: not more than 0.010% and V: 0.10 to 1.0% and satisfying $(10\text{Mn} + \text{V})/\text{C} \geq 50$. The method includes heating the steel slab to 1000°C or above, rough rolling the slab into a sheet bar, finish rolling the sheet bar at a finishing delivery temperature of not less than 800°C, cooling the steel sheet within 3 seconds after the completion of the finish rolling at an average cooling rate of not less than 20°C/s in the temperature range of 400 to 600°C to a temperature T_a °C satisfying $11000 - 3000[\%V] \leq 24 \times T_a \leq 15000 - 1000[\%V]$, and coiling the steel sheet.

According to the disclosure, the above configuration results in high-strength hot rolled steel sheets which have a microstructure in which the volume fraction of a tempered martensite phase is not less than 80%, the number of 20 nm or finer vanadium-containing carbide grains precipitated per μm^3 is not less than 1000 and the average grain diameter of the 20 nm or finer vanadium-containing carbide grains is not more than 10 nm, as well as which exhibit a tensile strength of not less than 980 MPa and excellent strength-ductility balance.

Citation List

Patent Literature

[0008]

PTL 1: Japanese Unexamined Patent Application

- 7 -

Publication No. 5-230529

PTL 2: Japanese Unexamined Patent Application

Publication No. 5-345917

PTL 3: Japanese Unexamined Patent Application

Publication No. 7-138638

PTL 4: Japanese Unexamined Patent Application

Publication No. 2000-282175

PTL 5: Japanese Unexamined Patent Application

Publication No. 2006-183141

Summary of Invention

Technical Problem

[0009]

However, the techniques described in Patent Literatures 1 to 5 have difficulties in stably attaining the desired shapes as well as in realizing stable and facilitated manufacturing of hot rolled steel sheets which have a yield strength YS of not less than 960 MPa, namely, 960 MPa to 1100 MPa grade high strength, and exhibit high toughness such that the absorption energy vE_{-40} according to a Charpy impact test at a test temperature of -40°C is not less than 40 J.

[0010]

To solve the aforementioned problems in the art, the present invention has an object of providing high-strength hot rolled steel sheets with high toughness and excellent

- 8 -

bendability that are suited for large-sized construction and industrial machinery structural members as well as methods for manufacturing such steel sheets. As used herein, the term "high-strength" indicates that the yield strength YS is not less than 960 MPa, the term "high toughness" indicates that vE_{-40} is not less than 30 J, and preferably not less than 40 J, and the term "excellent bendability" indicates that the bending radius is not more than $(3.0 \times \text{sheet thickness})$ and that 180° bending is possible. Further, the hot rolled steel sheets addressed in the present invention are defined to be hot rolled steel sheets with a sheet thickness of 3 mm to 12 mm.

Solution to Problem

[0011]

To achieve the above object, the present inventors extensively studied various factors that would affect the toughness and the ductility of high-strength hot rolled steel sheets having a yield strength YS of not less than 960 MPa. As a result, the present inventors have found that in spite of such high strength of 960 MPa or above in terms of yield strength YS, excellent toughness and excellent bendability may be ensured by configuring the microstructure such that the main phase is bainite or tempered martensite, the average grain diameter of prior austenite (γ) grains is not more than 20 μm as measured with respect to a cross

- 9 -

section parallel to the rolling direction, and the average grain diameter of prior γ grains is not more than 15 μm as measured with respect to a cross section perpendicular to the rolling direction.

[0012]

Further, the present inventors have found that higher bendability may be advantageously maintained by configuring the microstructure such that the ratio of the average length of the prior γ grains in the rolling direction relative to the average length in a direction perpendicular to the rolling direction, namely, (average length of prior γ grains in rolling direction)/(average length of prior γ grains in direction perpendicular to rolling direction) is not more than 10, or by configuring the microstructure such that the X-ray plane intensity $\{223\} \langle 252 \rangle$ (the ratio of the X-ray diffraction intensity of the $\{223\} \langle 252 \rangle$ orientation relative to a random sample) is not more than 5.0.

[0013]

In order to obtain the above microstructure, it has been found critical that a steel having a prescribed chemical composition be hot rolled into a steel sheet through a series of sequential steps including a heating step of heating the steel, a hot rolling step of subjecting the heated steel to hot rolling including rough rolling and finish rolling, a cooling step and a coiling step,

- 10 -

specifically, through a series of steps including a heating step in which the steel is heated to a temperature of 1100 to 1250°C, a hot rolling step in which the steel is rough rolled into a sheet bar, which is then subjected to finish rolling in such a manner that the cumulative reduction ratio in the partially recrystallized austenite region and the non-recrystallized austenite region divided by the cumulative reduction ratio in the recrystallized austenite region becomes 0 to 0.2, a cooling step in which cooling is initiated immediately after the completion of the finish rolling and the steel sheet is cooled to a cooling termination temperature that is not more than the Ms transformation temperature plus 150°C within 30 seconds from the initiation of the cooling, the average cooling rate in the temperature range of 750°C to 500°C being not less than the critical cooling rate for the occurrence of martensite formation, and further in which the steel sheet is held at a temperature in the range of the cooling termination temperature $\pm 100^\circ\text{C}$ for 5 to 60 seconds, and a coiling step in which the steel sheet is coiled into a coil at a coiling temperature in the range of the cooling termination temperature $\pm 100^\circ\text{C}$.

[0014]

The present invention has been completed based on the above findings and further studies. The summary of the

- 11 -

Invention is as follows.

[0015]

(1) A hot rolled steel sheet comprising a chemical composition including, in mass%, C: 0.08 to 0.25%, Si: 0.01 to 1.0%, Mn: 0.8 to 2.1%, P: not more than 0.025%, S: not more than 0.005% and Al: 0.005 to 0.10%, the balance comprising Fe and inevitable impurities, and a microstructure having a bainite phase and/or a tempered martensite phase as a main phase, the average grain diameter of prior austenite grains being not more than 20 μm as measured with respect to a cross section parallel to the rolling direction and not more than 15 μm as measured with respect to a cross section perpendicular to the rolling direction.

[0016]

(2) The hot rolled steel sheet according to (1), wherein the prior austenite grains have a ratio of the average length in the rolling direction relative to the average length in a direction perpendicular to the rolling direction, (average length in rolling direction)/(average length in direction perpendicular to rolling direction), of not more than 10.

[0017]

(3) The hot rolled steel sheet according to (1) or (2), wherein the microstructure has an X-ray plane intensity

- 12 -

{223} <252> of not more than 5.0.

[0018]

(4) The hot rolled steel sheet according to any one of (1) to (3), wherein the chemical composition further includes, in mass%, B: 0.0001 to 0.0050%.

[0019]

(5) The hot rolled steel sheet according to any one of (1) to (4), wherein the chemical composition further includes, in mass%, at least one selected from the group consisting of Nb: 0.001 to 0.05%, Ti: 0.001 to 0.05%, Mo: 0.001 to 1.0%, Cr: 0.01 to 1.0%, V: 0.001 to 0.10%, Cu: 0.01 to 0.50% and Ni: 0.01 to 0.50%.

[0020]

(6) The hot rolled steel sheet according to any one of (1) to (5), wherein the chemical composition further includes, in mass%, Ca: 0.0005 to 0.005%.

[0021]

(7) A method for manufacturing hot rolled steel sheets, comprising subjecting a steel to a series of sequential steps including a heating step of heating the steel, a hot rolling step of subjecting the heated steel to hot rolling including rough rolling and finish rolling, a cooling step and a coiling step, thereby producing a hot rolled steel sheet, wherein the steel has a chemical composition including, in mass%, C: 0.08 to 0.25%, Si: 0.01 to 1.0%, Mn:

- 13 -

0.8 to 2.1%, P: not more than 0.025%, S: not more than 0.005% and Al: 0.005 to 0.10%, the balance comprising Fe and inevitable impurities, and wherein the heating step is a step in which the steel is heated to a temperature of 1100 to 1250°C, the rough rolling in the hot rolling step is rolling of the steel heated in the heating step into a sheet bar, and the finish rolling in the hot rolling step is rolling of the sheet bar in such a manner that the cumulative reduction ratio in the partially recrystallized austenite region and the non-recrystallized austenite region divided by the cumulative reduction ratio in the recrystallized austenite region becomes 0 to 0.2, the cooling step includes a cooling treatment in which cooling is initiated immediately after the completion of the finish rolling and the steel sheet is cooled to a cooling termination temperature that is not more than (M_s transformation temperature + 150°C) within 30 seconds from the initiation of the cooling, the average cooling rate in the temperature range of 750°C to 500°C being not less than the critical cooling rate for the occurrence of martensite formation, and a holding treatment in which after the cooling treatment is terminated, the steel sheet is held at a temperature in the range of the cooling termination temperature $\pm$ 100°C for 5 to 60 seconds, and the coiling step is a step in which the steel sheet is coiled into a coil at

- 14 -

a coiling temperature in the range of (cooling termination temperature $\pm 100^{\circ}\text{C}$).

[0022]

(8) The method for manufacturing hot rolled steel sheets according to (7), wherein the chemical composition further includes, in mass%, B: 0.0001 to 0.0050%.

[0023]

(9) The method for manufacturing hot rolled steel sheets according to (7) or (8), wherein the chemical composition further includes, in mass%, at least one selected from the group consisting of Nb: 0.001 to 0.05%, Ti: 0.001 to 0.05%, Mo: 0.001 to 1.0%, Cr: 0.01 to 1.0%, V: 0.001 to 0.10%, Cu: 0.01 to 0.50% and Ni: 0.01 to 0.50%.

[0024]

(10) The method for manufacturing hot rolled steel sheets according to any one of (7) to (9), wherein the chemical composition further includes, in mass%, Ca: 0.0005 to 0.005%.

Advantageous Effects of Invention

[0025]

According to the present invention, stable production is possible of hot rolled steel sheets having high strength with a yield strength YS of not less than 960 MPa and high

- 15 -

toughness with an absorption energy of not less than 30 J according to a Charpy impact test at -40°C , as well as having excellent bendability, thus achieving marked industrial effects. Further, the hot rolled steel sheets manufactured in the invention have a sheet thickness of about 3 mm to 12 mm, the size being suited for structural members of large-sized construction machines and industrial machines. Thus, the invention also makes a great contribution to the reduction of body weight of construction machines and industrial machines.

Description of Embodiments

[0026]

First, the reasons why the chemical composition of the inventive hot rolled steel sheets is limited will be described. The unit mass% will be simply referred to as % unless otherwise mentioned.

[0027]

C: 0.08 to 0.25%

Carbon is an element that increases the strength of steel. In order to ensure the desired high strength, the present invention involves 0.08% or more carbon. On the other hand, excessive addition exceeding 0.25% results in a decrease in weldability as well as in a decrease in the toughness of base material. Thus, the C content is limited to the range of 0.08 to 0.25%. Preferably, the C content is

- 16 -

0.10 to 0.20%.

[0028]

Si: 0.01 to 1.0%

Silicon increases the strength of steel by effecting solid solution hardening and by improving hardenability. These effects are obtained by adding 0.01% or more silicon. If silicon is added in an amount exceeding 1.0%, carbon is concentrated in the γ phase and the γ phase stabilization is promoted to lower strength, and further Si-containing oxides are formed at welds to deteriorate the quality of the welds. Thus, the Si content in the invention is limited to the range of 0.01 to 1.0%. To suppress the formation of γ phase, the Si content is preferably not more than 0.8%.

[0029]

Mn: 0.8 to 2.1%

Manganese increases the strength of steel sheets by improving hardenability. Further, manganese fixes sulfur by forming MnS and thereby prevents the grain boundary segregation of sulfur, thus suppressing the occurrence of cracks in slab (steel). To obtain these effects, a Mn content of 0.8% or more is required. On the other hand, a Mn content exceeding 2.1% promotes solidification segregation during slab casting and results in Mn-enriched portions in the steel sheets to increase the occurrence of separation. The elimination of such Mn-enriched portions

- 17 -

entails heating at a temperature above 1300°C, and performing such a heat treatment on an industrial scale is not realistic. Thus, the Mn content is limited to the range of 0.8 to 2.1%. The Mn content is preferably 0.9 to 2.0%. From the viewpoint of the prevention of delayed fracture, the Mn content is more preferably not more than 1.3%.

[0030]

P: not more than 0.025%

Phosphorus is an inevitable impurity in steel and has an effect of increasing the strength of steel. However, weldability is lowered if this element is present in a content exceeding 0.025%. Thus, the P content is limited to not more than 0.025%. The P content is preferably not more than 0.015%.

[0031]

S: not more than 0.005%

Similarly to phosphorus, sulfur is an inevitable impurity in steel. If present in a high content exceeding 0.005%, this element causes the occurrence of slab cracks and lowers ductility by forming coarse MnS in hot rolled steel sheets. Thus, the S content is limited to not more than 0.005%. The S content is preferably not more than 0.004%.

[0032]

Al: 0.005 to 0.10%

- 18 -

Aluminum functions as a deoxidizer. To obtain this effect, the Al content is desirably not less than 0.005%. On the other hand, any Al content exceeding 0.10% results in a marked deterioration in cleanliness at welds. Thus, the Al content is limited to 0.005 to 0.10%. The Al content is preferably not more than 0.05%.

[0033]

The aforementioned components are basic components. In addition to the basic components, the chemical composition may optionally further include any of selective elements which are B: 0.0001 to 0.0050%, and/or one, or two or more of Nb: 0.001 to 0.05%, Ti: 0.001 to 0.05%, Mo: 0.001 to 1.0%, Cr: 0.01 to 1.0%, V: 0.001 to 0.10%, Cu: 0.01 to 0.50% and Ni: 0.01 to 0.50%, and/or Ca: 0.0005 to 0.005%.

[0034]

B: 0.0001 to 0.0050%

Boron is an element that is segregated in γ grain boundaries and markedly improves hardenability when added in a low content. Thus, this element may be added as required to ensure the desired high strength. In order to obtain the above effects, the B content is desirably not less than 0.0001%. On the other hand, the effects are saturated after 0.0050% and thus any further addition cannot be expected to give appropriate effects and will cause economic disadvantages. Thus, the content of boron, when added, is

- 19 -

preferably limited to the range of 0.0001 to 0.0050%, and more preferably 0.0005 to 0.0030%.

[0035]

One, or two or more of Nb: 0.001 to 0.05%, Ti: 0.001 to 0.05%, Mo: 0.001 to 1.0%, Cr: 0.01 to 1.0%, V: 0.001 to 0.10%, Cu: 0.01 to 0.50% and Ni: 0.01 to 0.50%

Niobium, titanium, molybdenum, chromium, vanadium, copper and nickel all have an effect of increasing strength. One, or two or more of these elements may be selectively added as required.

[0036]

Nb: 0.001 to 0.05%

Niobium is finely precipitated as carbonitride and increases the strength of hot rolled steel sheets in a low content without causing any deterioration in weldability. Further, this element suppresses the coarsening and recrystallization of austenite grains, allowing the steel sheets to be finish rolled by hot rolling in the austenite non-recrystallization temperature region. In order to obtain these effects, the Nb content is desirably not less than 0.001%. On the other hand, any high content exceeding 0.05% results in an increase in rolling load during hot finish rolling and may make the practice of hot rolling difficult. Thus, the content of niobium, when added, is preferably limited to the range of 0.001 to 0.05%, and more

- 20 -

preferably 0.005 to 0.04%.

[0037]

Ti: 0.001 to 0.05%

Titanium increases the strength of steel sheets by being finely precipitated as carbide, and also prevents the occurrence of cracks in slab (steel) by fixing nitrogen in the form of nitride. These effects are markedly obtained when the Ti content is 0.001% or above. If the Ti content exceeds 0.05%, however, the yield point is excessively increased by precipitation hardening and toughness is lowered; further, heating at a high temperature of above 1250°C is entailed for the melting of titanium carbonitride to invite the coarsening of prior γ grains, thus making it difficult to adjust the aspect ratio of prior γ grains to the desired range. Thus, the content of titanium, when added, is preferably limited to the range of 0.001 to 0.05%, and more preferably 0.005 to 0.035%.

[0038]

Mo: 0.001 to 1.0%

Molybdenum increases the strength of steel sheets by improving hardenability as well as by forming carbonitride. In order to obtain these effects, the Mo content is desirably not less than 0.001%. If molybdenum is present in a high content exceeding 1.0%, however, weldability is lowered. Thus, the content of molybdenum, when added, is

- 21 -

preferably limited to the range of 0.001 to 1.0%, and more preferably 0.05 to 0.8%.

[0039]

Cr: 0.01 to 1.0%

Chromium increases the strength of steel sheets by improving hardenability. In order to obtain this effect, the Cr content is desirably not less than 0.01%. If chromium is present in a high content exceeding 1.0%, however, weldability is lowered. Thus, the content of chromium, when added, is preferably limited to the range of 0.01 to 1.0%, and more preferably 0.1 to 0.8%.

[0040]

V: 0.001 to 0.10%

Vanadium contributes to increasing the strength of steel sheets by being dissolved in steel to effect solid solution hardening. Further, this element contributes to strength increasing by being precipitated as carbide, nitride or carbonitride, namely, by precipitation hardening. In order to obtain these effects, the V content is desirably not less than 0.001%. If vanadium is present in excess of 0.05%, however, toughness is lowered. Thus, the content of vanadium, when added, is preferably limited to the range of 0.001 to 0.05%.

[0041]

Cu: 0.01 to 0.50%

- 22 -

Copper contributes to strength increasing by being dissolved in steel, and also improves corrosion resistance. In order to obtain these effects, the Cu content is desirably not less than 0.01%. However, any Cu content exceeding 0.50% results in deteriorations in surface properties of steel sheets. Thus, the content of copper, when added, is preferably limited to the range of 0.01 to 0.50%.

[0042]

Ni: 0.01 to 0.50%

Nickel contributes to strength increasing by being dissolved in steel, and also improves toughness. In order to obtain these effects, the Ni content is desirably not less than 0.01%. However, adding nickel to a high content exceeding 0.50% results in an increase in material costs. Thus, the content of nickel, when added, is preferably limited to the range of 0.01 to 0.50%.

[0043]

Ca: 0.0005 to 0.005%

Calcium may be added as required. Calcium fixes sulfur as CaS and controls the configurations of sulfide inclusions to spherical forms. Further, this element reduces a lattice strain of the matrix around the inclusions, and lowers the hydrogen trapping ability. In order to obtain these effects, the Ca content is desirably not less than 0.0005%. If the

- 23 -

Ca content exceeds 0.005%, however, the amount of CaO is so increased that corrosion resistance and toughness are lowered. Thus, the content of calcium, when added, is preferably limited to the range of 0.0005 to 0.005%, and more preferably 0.0005 to 0.0030%.

[0044]

The balance after the deduction of the aforementioned components is Fe and inevitable impurities. A few of such inevitable impurities and their acceptable contents are N: not more than 0.005%, O: not more than 0.005%, Mg: not more than 0.003% and Sn: not more than 0.005%.

[0045]

Nitrogen is inevitably found in steel, but an excessively high content thereof increases the frequency of cracks during the casting of steel (slab). Thus, the N content is desirably limited to not more than 0.005%, and more preferably not more than 0.004%.

[0046]

Oxygen is present in steel in the forms of various oxides, serving as a factor that deteriorates properties such as hot workability, corrosion resistance and toughness. In the invention, it is therefore desirable that oxygen be reduced as much as possible. However, oxygen is acceptable up to 0.005%. Reducing the oxygen content to an extreme extent adds refining costs. Thus, the oxygen content is

- 24 -

desirably reduced to 0.005% or below.

[0047]

Similarly to calcium, magnesium forms oxide and sulfide to suppress the formation of coarse MnS. However, the presence of this element in excess of 0.003% increases the occurrence of clusters of magnesium oxide and magnesium sulfide, resulting in a decrease in toughness. Thus, it is desirable that the Mg content be reduced to 0.003% or below.

[0048]

Tin comes from steelmaking raw materials such as scraps. Tin is an element that is easily segregated in grain boundaries or the like. If this element is present in a large amount exceeding 0.005%, the grain boundary strength is lowered and the toughness is decreased. Thus, it is desirable that the Sn content be reduced to 0.005% or below.

[0049]

Next, there will be described the reasons why the microstructure of the inventive hot rolled steel sheets is limited.

[0050]

The hot rolled steel sheet of the invention has the aforementioned chemical composition, and has a main phase composed of a bainite phase, a tempered martensite phase, or a mixture of a bainite phase and a tempered martensite phase. As used herein, the term "bainite" indicates bainite

- 25 -

transformed at lower temperature. Further, the term "main phase" as used herein indicates that the phase has a volume fraction of not less than 90%, and preferably not less than 95%. This configuration of the main phase ensures that the desired high strength may be obtained. The second phase other than the main phase is a ferrite phase or a pearlite phase. Strength is decreased with increasing fraction of the second phase in the microstructure, and consequently the desired high strength cannot be ensured. Thus, the volume fraction of the second phase is preferably not more than 10%. It is needless to mention that the microstructure may be sometimes a mixture containing a bainite phase or a tempered martensite phase that does not constitute the main phase, in addition to the second phase.

[0051]

In the inventive hot rolled steel sheet, the microstructure has a bainite phase or a tempered martensite phase as the main phase or contains a mixture of these phases, and the average grain diameter of prior γ grains is not more than 20 μm as measured with respect to a cross section parallel to the rolling direction and the average grain diameter of prior γ grains is not more than 15 μm as measured with respect to a cross section perpendicular to the rolling direction. The microstructure having such a configuration ensures that the absorption energy vE_{-40}

- 26 -

according to a Charpy impact test at a test temperature of - 40°C will be not less than 30 J and that the hot rolled steel sheet will achieve high toughness and excellent bendability. The above toughness properties can be no longer ensured if the prior γ grains become coarse and their average grain diameter exceeds 20 μm in the L-direction cross section and exceeds 15 μm in the C-direction cross section. The average grain diameter of the prior γ grains is preferably not more than 18 μm in the L-direction cross section and not more than 13 μm in the C-direction cross section.

[0052]

In the inventive hot rolled steel sheet, the microstructure is preferably such that the ratio of the average length of the prior γ grains in the rolling direction relative to the average length of the prior γ grains in a direction perpendicular to the rolling direction, namely, (average length of prior γ grains in rolling direction)/(average length of prior γ grains in direction perpendicular to rolling direction) is not more than 10. With this configuration, bendability is further enhanced. Bendability is lowered if anisotropy is so increased that (average length of prior γ grains in rolling direction)/(average length of prior γ grains in direction perpendicular to rolling direction) exceeds 10. Preferably,

- 27 -

the ratio is not more than 7.

[0053]

The average lengths of the prior γ grains are defined to be determined by image processing a microstructure picture showing the exposed prior γ grains to obtain the respective lengths of the prior γ grains in the rolling direction and in the direction perpendicular to the rolling direction, and arithmetically averaging the respective lengths.

[0054]

Further, the inventive hot rolled steel sheet is preferably such that the X-ray plane intensity $\{223\} \langle 252 \rangle$ (the ratio of the X-ray diffraction intensity of the $\{223\} \langle 252 \rangle$ orientation relative to a random sample) is not more than 5.0. If the plane intensity of $\{223\} \langle 252 \rangle$ is increased to a ratio exceeding 5.0, the anisotropy of strength is so increased that bendability is lowered. Thus, it is preferable that the plane intensity of $\{223\} \langle 252 \rangle$ of the steel sheet be not more than 5.0, and more preferably not more than 4.5. The X-ray plane intensity of $\{223\} \langle 252 \rangle$ of the steel sheet is defined to be measured by X-ray orientation distribution function (ODF) analysis at 1/4 sheet thickness from the surface.

[0055]

As used herein, " $\{223\} \langle 252 \rangle$ " represents X-ray orientation distribution function analytical data according

- 28 -

to the Bunge definition, and means $\{223\} \langle 252 \rangle$ expressed by $(\phi_1, \Phi, \phi_2) = (30.5, 43.3, 45.0)$ in a cross section where $\phi_2 = 45$ degrees. The orientations equivalent to $\{223\} \langle 252 \rangle$ include $\{322\} \langle 225 \rangle$, and $\{232\} \langle 522 \rangle$. The description of $\{223\} \langle 252 \rangle$ may take such equivalent orientations into consideration. That is, $\{223\} \langle 252 \rangle$ in the invention is defined to include equivalent orientations.

[0056]

Next, a preferred method for manufacturing the inventive hot rolled steel sheets will be described.

[0057]

A steel having the aforementioned chemical composition is hot rolled into a hot rolled sheet (a steel sheet) through a series of sequential steps including a heating step of heating the steel, a hot rolling step of subjecting the heated steel to hot rolling including rough rolling and finish rolling, a cooling step and a coiling step.

[0058]

The steel may be manufactured by any methods without limitation. It is however preferable that a molten steel having the aforementioned chemical composition be smelted by a common smelting method such as a converter furnace method and cast into a steel material such as slab by a common casting method such as a continuous casting method.

[0059]

- 29 -

First, the steel is subjected to a heating step.

In the heating step, the steel is heated to a temperature of 1100 to 1250°C. If the heating temperature is less than 1100°C, the deformation resistance is high and the rolling load is increased to cause an excessive load to the rolling mill. On the other hand, heating to a high temperature exceeding 1250°C results in the coarsening of crystal grains to decrease low-temperature toughness as well as results in an increase in the amount of scales to lower the yield. Thus, the temperature to which the steel is heated is preferably 1100 to 1250°C, and more preferably not more than 1240°C.

[0060]

Next, a hot rolling step is performed in which the heated steel is rough rolled into a sheet bar and the sheet bar is finish rolled into a hot rolled sheet.

[0061]

The rough rolling conditions are not particularly limited as long as the steel may be rolled into a sheet bar with desired size and shape. The sheet bar thickness affects the amount of temperature decrease in the finish rolling mill. Thus, it is preferable that the sheet bar thickness be selected in consideration of the amount of temperature drop in the finish rolling mill as well as the difference between the finish rolling start temperature and

- 30 -

the finish rolling end temperature. Since the present invention addresses hot rolled steel sheets having a sheet thickness of about 3 mm to 12 mm, the sheet bar thickness is preferably controlled to 30 to 45 mm.

[0062]

The rough rolling is followed by finish rolling, in which the sheet bar is rolled in such a manner that the cumulative reduction ratio in the partially recrystallized austenite region and the non-recrystallized austenite region divided by the cumulative reduction ratio in the recrystallized austenite region (hereinafter, this quotient value is also referred to as the cumulative reduction-ratio ratio) becomes not more than 0.2 (including 0).

[0063]

If the cumulative reduction-ratio ratio exceeds 0.2, the prior γ grains are elongated in the rolling direction and it becomes impossible to ensure a microstructure in which the average grain diameter of prior γ grains is not more than 20 μm in a cross section parallel to the rolling direction and the average grain diameter of prior γ grains is not more than 15 μm in a cross section perpendicular to the rolling direction. Further, such rolling causes the (average length of prior γ grains in rolling direction)/(average length of prior austenite grains in direction perpendicular to rolling direction) ratio to

- 31 -

exceed 10, and the X-ray plane intensity $\{223\} \langle 252 \rangle$ at $1/4$ sheet thickness from the surface to exceed 5, resulting in decreases in bendability and toughness. Thus, it is preferable that the ratio of the cumulative reduction ratio in the partial recrystallization and non-recrystallization regions during finish rolling be limited to 0.2 or below. The ratio is more preferably not more than 0.15.

[0064]

In order to achieve the above reduction ratio during finish rolling, it is preferable, in view of the chemical composition of the steel used in the invention, that the finish rolling entry (start) temperature be in the range of 900 to 1050°C, the finish rolling delivery (end) temperature be in the range of 800 to 950°C, and the difference ΔT between the finish rolling entry (start) temperature and delivery (end) temperature be not more than 200°C. Any difference ΔT larger than 200°C indicates that the finish rolling end temperature is so low that the desired prior γ grain diameters cannot be ensured. The temperatures in finish rolling are surface temperatures.

[0065]

The finish rolling in the hot rolling step is usually tandem rolling in which the time intervals between passes are short. Thus, it tends to be that the non-recrystallized γ region including the partially recrystallized γ region is

- 32 -

shifted toward a higher temperature side and, in the case of producing thin sheets, the amount of temperature drop in the finish rolling mill is increased. In order to satisfy the aforementioned finish rolling conditions in a well balanced manner, it is therefore preferable that an appropriate sheet bar thickness be selected and the sheet thickness schedule (reduction schedule) control during finish rolling be optimized as well as that the amount of temperature decrease in the finish rolling mill be adjusted utilizing devices such as scale breakers and strip coolants.

[0066]

After the completion of the finish rolling, the steel sheet is immediately subjected to a cooling step in a cooling device disposed on the hot run table. After the completion of the finish rolling, cooling is initiated immediately, preferably within 5 seconds after the steel sheet is discharged from the finish rolling stand. If the retention time before the start of cooling is prolonged, the critical time for the occurrence of martensite formation may lapse and also the growth of γ grains proceeds with the result that the block sizes of tempered martensite phase and bainite phase become nonuniform.

[0067]

In the cooling step, the steel sheet is subjected to a cooling treatment in which the sheet is cooled to a cooling

- 33 -

termination temperature that is not more than (M_s transformation temperature + 150°C) with respect to a sheet thickness-wise center portion within 30 seconds from the initiation of the cooling, at a cooling rate not less than the critical cooling rate for the occurrence of martensite formation. The cooling rate is an average cooling rate in the temperature range of 750 to 500°C . The M_s temperature is a value calculated according to the following equation. Of the elements shown in the equation, those which are absent in the steel are regarded as zero in the calculation.

$$M_s (^{\circ}\text{C}) = 486 - 470C - 8\text{Si} - 33\text{Mn} - 24\text{Cr} - 17\text{Ni} - 15\text{Mo}$$

(Here, C, Si, Mn, Cr, Ni and Mo: contents of respective elements (mass%))

The cooling treatment is desirably initiated before the temperature of a sheet thickness-wise center portion falls below 750°C . If the temperature of a sheet thickness-wise center portion is left to fall below 750°C , ferrite (polygonal ferrite) or pearlite that is transformed at high temperature is formed during that period and consequently the desired microstructure cannot be obtained.

[0068]

Any cooling rate that is less than the critical cooling rate for the occurrence of martensite formation cannot ensure the desired microstructure having a tempered martensite phase or a bainite phase (a lower temperature-

- 34 -

transformed bainite phase) as the main phase or containing a mixture of these phases. The upper limit of the cooling rate is determined depending on the performance of the cooling device used. It is however preferable that a cooling rate be selected which does not involve deteriorations in the shape of steel sheets such as warpage. A more preferred cooling rate is not less than 25°C/s. In view of the chemical composition of the steel used in the invention, the critical cooling rate for the occurrence of martensite formation is generally about 22°C/s.

[0069]

If the cooling termination temperature is higher than (M_s temperature + 150°C), it becomes impossible to ensure the desired microstructure having a bainite phase (a lower temperature-transformed bainite phase) or a tempered martensite phase as the main phase or containing a mixture of these phases. The cooling termination temperature is preferably (M_s temperature - 200°C) to (M_s temperature + 100°C). If the cooling time from the initiation of cooling until the cooling termination temperature is reached is extended to more than 30 seconds, the fraction of second phases (ferrite, pearlite) other than the martensite phase and the bainite phase (the lower temperature-transformed bainite phase) is increased in the microstructure. Because the martensite transformation and the bainite transformation

- 35 -

occurring at low temperatures are not allowed to proceed to a sufficient extent, the desired microstructure cannot be ensured at times.

[0070]

In the cooling step, a holding treatment is carried out in which after the cooling treatment is terminated, the steel sheet is held at a temperature in the range of (cooling termination temperature $\pm 100^{\circ}\text{C}$) for 5 to 60 seconds. Through this holding treatment, the martensite phase and the bainite phase (the lower temperature-transformed bainite phase) formed are tempered and fine cementite is precipitated in the lath. As a result, strength (yield strength) is increased and toughness is improved. Further, the practice of the holding treatment prevents the occurrence of coarse cementite serving as hydrogen trapping sites, and makes it possible to prevent the occurrence of delayed fracture. If the holding temperature is less than (cooling termination temperature - 100°C), the desired tempering effects cannot be expected at times. On the other hand, holding at a temperature exceeding (cooling termination temperature + 100°C) results in excessive tempering effects and causes cementite to be coarsened, thus possibly failing to ensure the desired toughness and delayed fracture resistance.

[0071]

- 36 -

If the holding time in the holding treatment is less than 5 seconds, the holding treatment cannot be expected to provide sufficient effects, namely, the desired tempering effects. On the other hand, the treatment for more than 60 seconds decreases the tempering effects obtained in the coiling step as well as decreases productivity.

[0072]

Specifically, the holding treatment may involve methods such as induction heating. Alternatively, the holding treatment in the temperature range of (cooling termination temperature $\pm 100^{\circ}\text{C}$) may be performed by utilizing the heat generated by the martensite transformation on the hot run table while adjusting the amount or pressure of water in the water-cooling bank with reference to surface thermometers disposed at a plurality of locations on the hot run table.

[0073]

After the completion of the cooling step, the steel sheet is subjected to a coiling step in which the steel sheet is coiled into a coil at a coiling temperature in the range of (cooling termination temperature $\pm 100^{\circ}\text{C}$).

In the coiling step, the hot rolled steel sheet is coiled into a coil and undergoes prescribed tempering. If the coiling temperature is outside the range of (cooling termination temperature $\pm 100^{\circ}\text{C}$), the desired tempering effects in the coiling step cannot be ensured.

- 37 -

[0074]

Hereinbelow, the present invention will be described in further detail based on EXAMPLES.

EXAMPLES

[0075]

Slabs (steels) (thickness: 230 mm) having chemical compositions in Table 1 were subjected to a heating step and a hot rolling step described in Table 2. After the completion of hot rolling, the steel sheets were sequentially subjected to a cooling step involving a cooling treatment under conditions described in Table 2 and a holding treatment described in Table 2, and to a coiling step in which the steel sheet was coiled at a coiling temperature described in Table 2. Thus, hot rolled steel sheets (steel strips) with sheet thicknesses described in Table 2 were manufactured.

[0076]

Test pieces were sampled from the hot rolled steel sheets, and microstructure observation, tensile test and impact test were carried out. The testing methods were as follows.

[0077]

(1) Microstructure observation

Microstructure observation test pieces were sampled from the hot rolled steel sheet. A cross section parallel

- 38 -

to the rolling direction (an L-direction cross section) and a cross section perpendicular to the rolling direction (a C-direction cross section) were polished and etched to expose prior γ grain boundaries, and the microstructure was observed with an optical microscope (magnification: x500). The observation took place at $1/4t$ sheet thickness. At least two fields of view were observed and imaged with respect to each observation site. With use of an image analyzer, the grain diameters were measured of the respective prior austenite grains in the cross section parallel to the rolling direction and in the cross section perpendicular to the rolling direction, the results being arithmetically averaged, thereby calculating the average grain diameter D_L of prior austenite grains in the cross section parallel to the rolling direction and the average grain diameter D_C of prior austenite grains in the cross section perpendicular to the rolling direction.

[0078]

Further, the prior austenite grains were analyzed to measure the lengths in the rolling direction and the lengths in a direction perpendicular to the rolling direction. After the respective results were arithmetically averaged, the ratio R ($=$ (average length of prior austenite grains in rolling direction)/(average length in direction perpendicular to rolling direction)) was calculated.

- 39 -

[0079]

Furthermore, a C-direction cross section of the microstructure observation test piece was polished and was etched with Nital. With use of a scanning electron microscope (magnification: x2000), the microstructure was observed and imaged with respect to three or more sites in a region at 1/4 sheet thickness from the surface in the sheet thickness direction. The types of structures and the fractions (volume fractions) of phases in the microstructure were determined with use of an image analyzer.

[0080]

Separately, the hot rolled steel sheet was ground by 1/4 sheet thickness from the surface in the ND direction to give an X-ray measurement test piece. The obtained X-ray measurement test piece was chemically polished, and the working strain was removed. Thereafter, the test piece was subjected to X-ray orientation distribution function (ODF) analysis. The obtained orientation distribution function analysis results were represented according to the Bunge definition, and the X-ray intensity of the orientation $\{223\} \langle 252 \rangle$ expressed by $(\phi_1, \Phi, \phi_2) = (30.5, 43.3, 45.0)$ in a cross section where $\phi_2 = 45$ degrees was determined.

[0081]

(2) Tensile test

Sheet-shaped test pieces (parallel widths: 25 mm, bench

- 40 -

mark intervals: 50 mm) were sampled from a prescribed position (longitudinal coil end, 1/4 in width direction) of the hot rolled steel sheet such that the longitudinal direction of the test piece would be a direction (C-direction) perpendicular to the rolling direction. A tensile test was performed at room temperature in accordance with JIS Z 2241 to determine the yield strength YS, the tensile strength TS and the total elongation El.

[0082]

(3) Impact test

V-notched test pieces were sampled from a sheet thickness-wise center portion at a prescribed position (longitudinal coil end, 1/4 in width direction) of the hot rolled steel sheet such that the longitudinal direction would be a direction (C-direction) perpendicular to the rolling direction. A Charpy impact test was performed in accordance with JIS Z 2242 to determine the absorption energy vE_{-40} (J) at a test temperature of -40°C . Three test pieces were tested, and the obtained absorption energy values were arithmetically averaged, thereby obtaining the absorption energy vE_{-40} (J) of the steel sheet. For those steel sheets with a sheet thickness of less than 10 mm, data measured with respect to subsize test pieces are described.

[0083]

(4) Bending test

- 41 -

Bending test pieces (rectangular test pieces in which the longer sides were 300 mm and perpendicular to the rolling direction, and the shorter sides were at least five times the sheet thickness) were sampled from a prescribed position of the hot rolled steel sheet. The test pieces were subjected to a 180° bending test, and the minimum bending radius was determined by measuring the minimum inner bending radius (mm) which did not cause any cracks. The minimum bending radius/sheet thickness ratio was then calculated. Those steel sheets with a minimum bending radius/sheet thickness ratio of not more than 3.0 were evaluated to be "excellent in bendability".

[0084]

The results are described in Table 3.

[0085]

[Table 1]

Steel No.	Chemical composition (mass%)											Ms* (°C)	Remarks
	C	Si	Mn	P	S	Al	N	B	Nb, Ti, Mo, Cr, V, Cu, Ni	Ca			
A	0.15	0.01	1.45	0.011	0.001	0.047	0.0035	-	-	-	-	367	Appl. Ex.
B	0.07	0.01	1.50	0.012	0.002	0.032	0.0035	-	-	-	-	403	Comp. Ex.
C	0.15	0.01	2.20	0.011	0.001	0.047	0.0035	-	-	-	-	342	Comp. Ex.
D	0.18	0.01	1.41	0.021	0.001	0.038	0.0035	-	Ti: 0.009	-	-	354	Appl. Ex.
E	0.15	0.01	1.20	0.011	0.001	0.035	0.0025	0.0010	Nb: 0.020, Ti: 0.008, Cr: 0.40, Mo: 0.20	-	-	363	Appl. Ex.
F	0.15	0.40	1.20	0.018	0.001	0.035	0.0040	0.0010	Nb: 0.020, Ti: 0.008, Cr: 0.50, Mo: 0.40	-	-	355	Appl. Ex.
G	0.15	0.20	1.20	0.011	0.001	0.035	0.0030	0.0010	Nb: 0.020, Ti: 0.008, Cr: 0.50, Mo: 0.40, V: 0.04	-	-	356	Appl. Ex.
H	0.17	0.01	1.20	0.011	0.001	0.035	0.0029	0.0010	Nb: 0.020, Ti: 0.008, Cr: 0.50, Mo: 0.40, V: 0.04	-	-	347	Appl. Ex.
I	0.16	0.01	1.43	0.016	0.001	0.047	0.0032	0.0012	-	-	-	363	Appl. Ex.
J	0.16	0.01	1.20	0.011	0.001	0.042	0.0028	0.0012	Mo: 0.18	-	-	363	Appl. Ex.
K	0.16	0.01	1.20	0.018	0.001	0.040	0.0028	0.0012	Cr: 0.39	-	-	361	Appl. Ex.
L	0.16	0.01	1.20	0.011	0.001	0.047	0.0028	0.0012	Nb: 0.021	-	-	371	Appl. Ex.
M	0.17	0.01	1.35	0.009	0.002	0.034	0.0028	0.0009	Ti: 0.015, Ni: 0.35	-	-	355	Appl. Ex.
N	0.13	0.01	1.89	0.015	0.002	0.032	0.0031	0.0011	Cu: 0.15	-	-	362	Appl. Ex.
O	0.14	0.01	1.78	0.014	0.001	0.028	0.0027	0.0009	-	0.0015	361	Appl. Ex.	

*) Ms (°C) = 486 - 470C - 8Si - 33Mn - 24Cr - 17Ni - 15Mo

[0086]

[Table 2]

Steel sheet No.	Steel No.	Hot rolling step										Cooling step						Coiling step		Remarks
		Heating temperature (°C)	Rough rolling		Finish rolling				Time to initiation of cooling (s)	Cooling treatment				Holding treatment		Coiling temperature (°C)				
			End temperature (°C)	Sheet bar thickness (mm)	Start temperature (°C)	End temperature (°C)	Reduction ratio in recrystallization region (%)	Reduction ratio in non-recrystallization region* (%)		Cumulative reduction-ratio ratio**	Finished sheet thickness (mm)	Average cooling rate*** (°C/s)	Critical cooling rate**** (°C/s)	Cooling termination temperature (°C)	Time to termination of cooling (s)		Holding temperature (°C)	Holding time (s)		
1	A	1208	1032	36.4	973	890	82.7	3.2	0.04	6.0	2.9	100	50	364	5	325	25	Inv. Ex.		
2	A	1210	1032	38.6	979	878	81.9	14.3	0.17	6.0	2.9	30	50	340	18	329	12	Comp. Ex.		
3	A	1202	1036	36.9	983	892	81.0	14.3	0.18	6.0	2.9	50	50	312	12	312	0	Comp. Ex.		
4	B	1208	1032	36.4	973	890	81.7	0.2	0.0	6.1	2.9	100	100	364	5	325	25	Comp. Ex.		
5	C	1207	1035	36.4	981	909	83.2	0.0	0.0	6.1	2.9	60	19	364	9	325	21	Comp. Ex.		
6	D	1230	1049	36.8	996	899	76.2	13.0	0.17	8.0	3.8	60	38	323	10	283	15	Inv. Ex.		
7	D	1290	1140	38.8	1049	899	76.2	13.0	0.17	8.0	3.8	60	38	280	10	275	15	Comp. Ex.		
8	D	1090	982	38.8	895	795	35.8	67.9	1.90	8.0	3.8	60	38	280	9	275	16	Comp. Ex.		
9	E	1203	1036	36.4	978	905	83.5	0.0	0.0	8.0	2.9	30	24	260	22	240	12	Inv. Ex.		
10	E	1210	1054	48.7	998	882	71.2	13.8	0.19	11.9	5.7	60	24	350	9	290	24	Inv. Ex.		
11	E	1210	1054	48.7	998	882	67.4	25.2	0.37	11.9	5.7	60	24	350	9	290	24	Comp. Ex.		
12	F	1203	1036	36.4	978	895	81.7	9.0	0.11	6.1	2.9	25	21	300	24	290	6	Inv. Ex.		
13	F	1209	1035	30.0	970	823	42.7	65.1	1.52	6.1	2.9	30	21	300	17	290	13	Comp. Ex.		
14	F	1205	1039	36.4	982	899	81.7	9.0	0.11	6.1	15.0	30	21	310	40	320	0	Comp. Ex.		
15	G	1150	1006	42.6	936	892	77.9	14.9	0.19	8.0	3.8	60	19	298	10	290	20	Inv. Ex.		
16	G	1250	1095	42.6	989	873	78.9	11.1	0.14	8.0	3.8	30	19	420	15	450	15	Inv. Ex.		
17	G	1250	1095	42.6	1012	873	79.0	10.1	0.13	8.0	3.8	20	19	418	23	319	7	Inv. Ex.		
18	H	1190	1010	42.6	1015	899	79.1	10.2	0.13	8.0	3.8	30	14	497	13	397	25	Inv. Ex.		
19	H	1175	985	44.5	1003	875	75.2	9.1	0.12	10.0	4.8	20	14	600	14	550	25	Comp. Ex.		
20	H	1207	999	46.5	1003	893	78.1	4.0	0.05	12.0	5.8	15	14	25	58	25	4	Comp. Ex.		
21	I	1180	1000	28.0	987	875	82.1	10.0	0.12	4.5	2.2	30	20	272	20	360	17	Inv. Ex.		
22	J	1220	983	46.8	973	903	72.2	7.7	0.11	12.0	5.8	63	20	450	7	440	26	Inv. Ex.		
23	K	1211	1012	39.8	979	891	72.4	11.8	0.16	9.7	4.7	68	19	467	6	527	19	Inv. Ex.		
24	L	1232	1069	39.8	979	893	78.6	11.8	0.15	7.5	3.6	75	30	510	5	522	20	Inv. Ex.		
25	M	1152	989	39.8	982	893	77.9	14.8	0.19	7.5	3.6	86	16	495	5	525	20	Inv. Ex.		
26	N	1198	1030	37.8	983	883	76.7	9.1	0.12	8.0	3.8	60	26	320	9	381	16	Inv. Ex.		
27	O	1203	1035	38.8	983	882	76.7	9.1	0.12	8.0	3.8	60	21	330	9	338	16	Inv. Ex.		

*) Cumulative reduction ratio in non-recrystallization region including partial recrystallization region

**) (Cumulative reduction ratio in non-recrystallization region)/(Cumulative reduction ratio in recrystallization region)

***) Average cooling rate between 750-500°C

****) Critical cooling rate for occurrence of martensite formation

[0087]

[Table 3]

Steel sheet No.	Steel No.	Microstructure						Mechanical characteristics					Remarks	
		Prior γ grains*			Main phase (vol%)		Second phase (vol%)	X-ray plane intensity***	Tensile characteristics			Toughness		Bendability
		DL	DC	R	Tempered M**	B**	Type** : %		YS (Mpa)	TS (MPa)	EI (%)			
1	A	9.4	6.9	2.6	90	10		1.9	1184	1338	14.8	48	2.1	Inv. Ex.
2	A	16.3	10.1	6.8		80	F:10, P:10	3.5	887	1003	19.8	64	2.2	Comp. Ex.
3	A	16.4	10.1	6.9	20	40	F:40	3.5	796	1103	18.0	58	2.2	Comp. Ex.
4	B	8.1	5.9	2.0	95	5		1.4	900	1017	19.6	63	1.7	Comp. Ex.
5	C	8.0	5.8	2.0	40	60		1.4	1310	1481	13.4	14	1.7	Comp. Ex.
6	D	16.1	10.0	6.7	90	10		3.5	1173	1326	15.8	48	2.2	Inv. Ex.
7	D	28.9	18.0	6.7	100			3.5	1169	1313	16.0	16	2.2	Comp. Ex.
8	D	38.4	17.7	19.1	100			6.8	1178	1335	15.7	48	>5.0	Comp. Ex.
9	E	8.0	5.8	2.6	100			1.4	1160	1311	15.1	49	1.7	Inv. Ex.
10	E	17.6	10.5	7.7	90	10		3.8	1295	1463	15.5	79	2.4	Inv. Ex.
11	E	32.3	13.4	18.9	90	10		6.1	1286	1459	15.6	79	>5.0	Comp. Ex.
12	F	12.6	8.7	4.4	95	5		2.7	1237	1320	15.1	48	1.9	Inv. Ex.
13	F	26.1	16.3	17.1	100			6.2	1241	1335	14.9	48	>5.0	Comp. Ex.
14	F	12.6	8.7	4.4		20	F:75, P:5	2.7	818	1122	17.7	57	1.9	Comp. Ex.
15	G	17.4	10.4	7.6	100			3.7	1363	1543	13.6	41	2.3	Inv. Ex.
16	G	14.3	9.4	5.5	10	90		3.1	1297	1468	14.3	44	2.0	Inv. Ex.
17	G	13.6	9.1	5.0	10	90		2.9	1108	1182	19.5	54	2.0	Inv. Ex.
18	H	13.6	9.1	5.0		100		2.9	1238	1400	16.5	46	2.0	Inv. Ex.
19	H	13.2	8.9	4.8		60	F:30, P:10	2.8	1316	1415	15.5	15	2.0	Comp. Ex.
20	H	10.0	7.3	2.9			M:100	2.0	876	1401	16.3	82	1.8	Comp. Ex.
21	I	13.2	8.9	4.8	100			2.9	1013	1145	16.3	56	2.0	Inv. Ex.
22	J	12.4	8.6	4.3		100		2.7	1101	1245	20.1	62	1.9	Inv. Ex.
23	K	15.6	9.9	6.3		100		3.4	1123	1269	18.9	60	2.1	Inv. Ex.
24	L	14.8	9.6	5.8		100		3.2	993	1121	20.3	68	2.1	Inv. Ex.
25	M	17.3	10.4	7.5		100		3.7	1169	1320	17.3	58	2.3	Inv. Ex.
26	N	13.1	4.7	2.8	90	10		2.8	1265	1430	16.2	54	2.0	Inv. Ex.
27	O	13.0	4.7	2.8	95	5		2.8	1258	1421	16.3	54	2.0	Inv. Ex.

*) DL: average grain diameter (μm) of prior γ grains in cross section parallel to rolling direction, DC: average grain diameter (μm) of prior γ grains in cross section perpendicular to rolling direction, R = (average length in rolling direction)/(average length in direction perpendicular to rolling direction)

**) M: martensite, B: bainite, F: ferrite, P: pearlite

***) {223} <252>

- 45 -

[0088]

All the hot rolled steel sheets in Inventive Examples achieved high strength of not less than 960 MPa in terms of yield strength YS and high toughness with vE₋₄₀ of not less than 30 J and also exhibited excellent bendability with a crack-free minimum bending radius of not more than (3.0 × sheet thickness). On the other hand, Comparative Examples outside the scope of the present invention resulted in hot rolled steel sheets which failed to satisfy at least one of the desired high strength, high toughness, and excellent bendability, i.e. the yield strength YS being less than 960 MPa, vE₋₄₀ being less than 30 J and the crack-free minimum bending radius exceeding (3.0 × sheet thickness).

- 46 -

CLAIMS

[Claim 1]

A hot rolled steel sheet comprising a chemical composition including, in mass%,

C: 0.08 to 0.25%, Si: 0.01 to 1.0%,

Mn: 0.8 to 2.1%, P: not more than 0.025%,

S: not more than 0.005% and Al: 0.005 to 0.10%,

the balance comprising Fe and inevitable impurities,

and a microstructure having a bainite phase and/or a tempered martensite phase as a main phase, the average grain diameter of prior austenite grains being not more than 20 μm as measured with respect to a cross section parallel to the rolling direction and not more than 15 μm as measured with respect to a cross section perpendicular to the rolling direction.

[Claim 2]

The hot rolled steel sheet according to claim 1,

wherein the prior austenite grains have a ratio of the average length in the rolling direction relative to the average length in a direction perpendicular to the rolling direction, (average length in rolling direction)/(average

- 47 -

length in direction perpendicular to rolling direction), of not more than 10.

[Claim 3]

The hot rolled steel sheet according to claim 1 or 2, wherein the microstructure has an X-ray plane intensity {223} <252> of not more than 5.0.

[Claim 4]

The hot rolled steel sheet according to any one of claims 1 to 3, wherein the chemical composition further includes, in mass%, B: 0.0001 to 0.0050%.

[Claim 5]

The hot rolled steel sheet according to any one of claims 1 to 4, wherein the chemical composition further includes, in mass%, at least one selected from the group consisting of Nb: 0.001 to 0.05%, Ti: 0.001 to 0.05%, Mo: 0.001 to 1.0%, Cr: 0.01 to 1.0%, V: 0.001 to 0.10%, Cu: 0.01 to 0.50% and Ni: 0.01 to 0.50%.

[Claim 6]

The hot rolled steel sheet according to any one of claims 1

- 48 -

to 5, wherein the chemical composition further includes, in mass%, Ca: 0.0005 to 0.005%.

[Claim 7]

A method for manufacturing hot rolled steel sheets, comprising subjecting a steel to a series of sequential steps including a heating step of heating the steel, a hot rolling step of subjecting the heated steel to hot rolling including rough rolling and finish rolling, a cooling step and a coiling step, thereby producing a hot rolled steel sheet, wherein the steel has a chemical composition including, in mass%,

C: 0.08 to 0.25%, Si: 0.01 to 1.0%,

Mn: 0.8 to 2.1%, P: not more than 0.025%,

S: not more than 0.005% and Al: 0.005 to 0.10%,

the balance comprising Fe and inevitable impurities, and wherein

the heating step is a step in which the steel is heated to a temperature of 1100 to 1250°C,

the rough rolling in the hot rolling step is rolling of the steel heated in the heating step into a sheet bar, and the finish rolling in the hot rolling step is rolling of the sheet bar in such a manner that the cumulative reduction

- 49 -

ratio in the partially recrystallized austenite region and the non-recrystallized austenite region divided by the cumulative reduction ratio in the recrystallized austenite region becomes 0 to 0.2,

the cooling step includes a cooling treatment in which cooling is initiated immediately after the completion of the finish rolling and the steel sheet is cooled to a cooling termination temperature that is not more than (M_s transformation temperature + 150°C) within 30 seconds from the initiation of the cooling, the average cooling rate in the temperature range of 750°C to 500°C being not less than the critical cooling rate for the occurrence of martensite formation, and a holding treatment in which after the cooling treatment is terminated, the steel sheet is held at a temperature in the range of the cooling termination temperature $\pm$ 100°C for 5 to 60 seconds, and

the coiling step is a step in which the steel sheet is coiled into a coil at a coiling temperature in the range of (cooling termination temperature $\pm$ 100°C).

[Claim 8]

The method for manufacturing hot rolled steel sheets according to claim 7, wherein the chemical composition

- 50 -

further includes, in mass%, B: 0.0001 to 0.0050%.

[Claim 9]

The method for manufacturing hot rolled steel sheets according to claim 7 or 8, wherein the chemical composition further includes, in mass%, at least one selected from the group consisting of Nb: 0.001 to 0.05%, Ti: 0.001 to 0.05%, Mo: 0.001 to 1.0%, Cr: 0.01 to 1.0%, V: 0.001 to 0.10%, Cu: 0.01 to 0.50% and Ni: 0.01 to 0.50%.

[Claim 10]

The method for manufacturing hot rolled steel sheets according to any one of claims 7 to 9, wherein the chemical composition further includes, in mass%, Ca: 0.0005 to 0.005%.