

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
20 August 2009 (20.08.2009)

PCT

(10) International Publication Number  
**WO 2009/101429 A1**

(51) International Patent Classification:  
*B01J 20/02* (2006.01) *C10G 25/00* (2006.01)  
*B01J 20/28* (2006.01)

(74) Agent: **RIDLAND, John**; Johnson Matthey Catalysts, Intellectual Property Dept., PO Box 1, Belasis Avenue, Billingham Cleveland TS23 1LB (GB).

(21) International Application Number:  
PCT/GB2009/050085

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(22) International Filing Date:  
29 January 2009 (29.01.2009)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
0802828.4 15 February 2008 (15.02.2008) GB

(71) Applicant (*for all designated States except US*): **JOHNSON MATTHEY PLC** [GB/GB]; 40-42 Hatton Garden, London EC1N 8EE (GB).

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **COUSINS, Matthew John** [GB/GB]; 234 Greenbank Road, Darlington, County Durham DL3 6ES (GB). **YOUNG, Christopher John** [GB/GB]; 15 Bluebell Way, Bishop Cuthbert, Hartlepool, Cleveland TS26 0WF (GB). **LOGAN, Robert** [GB/GB]; 8 Wilmire Road, Billingham, Cleveland TS22 5EN (GB).

Published:

— with international search report (Art. 21(3))



WO 2009/101429 A1

(54) Title: ABSORBENTS

(57) Abstract: An absorbent composition suitable for removing mercury, arsenic or antimony from fluid streams is described, comprising 5-50% by weight of a particulate sulphidedcopper compound, 30-90% by weight of a particulate support material, and the remainder one or more binders, wherein the metal sulphide content of the absorbent, other than copper sulphide, is below 5% by weight.

### Absorbents

This invention relates to absorbents and in particular to metal sulphide absorbents suitable for capturing mercury and/or arsenic and antimony from fluid streams.

5

Mercury is found in small quantities in fluid streams such as hydrocarbon or other gas and liquid streams. Arsenic and antimony may also be found in small quantities in hydrocarbon streams. Mercury, in addition to its toxicity, can cause failure of aluminium heat exchangers and other processing equipment. Therefore there is a need to efficiently remove these metals from fluid streams, preferably as early as possible in the process flowsheet.

10

Copper sulphide mercury removal materials are known. US 4094777 discloses the use of a pre-sulphided absorbent comprising copper sulphide for the absorption of mercury from a natural gas stream containing mercury. The pre-sulphided absorbent is prepared by forming a precursor comprising basic copper carbonate and a refractory cement binder, and then contacting the precursor with a gaseous stream containing a sulphur compound, e.g. hydrogen sulphide, so as to sulphide the copper compound. The pre-sulphided absorbent is then used to remove mercury from a natural gas stream.

15

EP 0480603 describes a process for the removal of mercury from a stream wherein an absorbent comprising copper sulphide is prepared in situ, preferably by a mercury-containing stream also containing a sulphur compound thereby concomitantly preparing the mercury absorbent and absorbing the mercury, such that the formation of ineffective and undesired metal compounds e.g. metal sulphates, formed by oxidation of metal sulphides, is avoided.

20

The Examples utilize copper and zinc sulphide materials. However, not all gas streams containing mercury also contain sulphur compounds.

25

We have found that the presence of metal sulphates, such as zinc sulphate, formed by the oxidation of metal sulphides other than copper sulphide, can cause agglomeration of the absorbent as a result of dissolution and re-deposition of metal sulphate by water present in the fluid stream. Re-deposition in use can cause a reduction in mercury capacity through loss in reactive copper sulphide surface area. Agglomeration can cause an unacceptable increase in pressure drop, and can make discharge of the absorbent from the absorption vessel difficult and lengthy. This may cause a particular problem where purification is required as part of an off-shore hydrocarbon extraction process or where purification is required in wet gas streams such as regeneration gases from dehydration units or wet carbon dioxide streams.

30

35

Accordingly, the invention provides an absorbent composition suitable for removing mercury, arsenic or antimony from a fluid stream comprising 5-50% by weight of a particulate sulphided

copper compound, 30-90% by weight of a particulate support material, and the remainder one or more binders, wherein the metal sulphide content of the absorbent, other than copper sulphide, is  $\leq 5\%$  by weight.

- 5 The invention further provides a method for making the absorbent comprising the steps of:
- i) forming a composition comprising a particulate copper compound capable of forming copper sulphide, a particulate support material, and one or more binders,
  - ii) shaping the composition to form an absorbent precursor,
  - iii) drying the absorbent precursor material, and
  - 10 iv) sulphiding the precursor to form the absorbent.

The invention further provides a mercury, arsenic or antimony removal process comprising contacting a mercury-, arsenic- or antimony-containing process fluid with the absorbent.

- 15 The absorbent comprises 5-50% by weight of a particulate sulphided copper compound. The sulphided copper compound therefore comprises copper sulphide. Preferably  $>90\%$  wt of the copper is sulphided, preferably  $>95\%$  wt.. Absorbents used in the present invention preferably comprise copper in an amount 10-45% wt (expressed as the oxide, CuO), preferably, more preferably 15-30% wt Cu (as oxide) in the sulphided composition.

20

- The copper compound suitable for use in the absorbent is one that may be readily sulphided such as copper oxide, hydroxide and/or basic carbonate. One or more sulphidable copper compounds may be used. A particularly suitable copper compound is basic copper carbonate (i.e. a copper hydroxycarbonate). Preferably the copper compound used to form the absorbent is pre-dried. The copper compounds are particulate and desirably are in the form of powders, preferably with an average, i.e.  $D_{50}$ , particle size in the range 10-100 $\mu\text{m}$ .

25

- Unlike the aforesaid US4094777, the absorbents of the present invention comprise 30-90% by weight of a particulate support material. The support material offers a means to adapt the physical properties of the absorbent to the duty. Thus the surface area, porosity and crush strength of the absorbent may suitably be tailored to its use. Furthermore, the presence of support particles can increase the strength and durability of the absorbent composition by acting as a diluent. The absorbent composition is then better able to retain its physical integrity during the sulphiding process, which causes a volumetric change in the copper compound as the copper sulphide is formed. Support materials are desirably oxide materials such as aluminas, titanias, zirconias, silicas and aluminosilicates, or mixtures of two or more of these. Hydrated oxides may also be used, for example alumina trihydrate or boehmite. Particularly suitable supports are transition aluminas, such as gamma, theta and delta alumina, and hydrated aluminas. The support may be present in an amount 30-90% wt, preferably 50-80%
- 30
- 35

wt (based upon on the sulphided composition). The support materials are desirably in the form of powders with a particle size of <100µm, preferably 5-65µm.

In the present invention, the total metal sulphide content of the absorbent, other than other than  
5 copper sulphide, is below 5% by weight. This is so that the corresponding water-soluble metal sulphates are formed in sufficiently low levels not to cause the undesirable re-deposition and agglomeration problem. Preferably the total metal sulphide content, other than copper sulphide, is  $\leq 1\%$  wt, more preferably  $\leq 0.5\%$  wt, especially  $\leq 0.1\%$  wt. The contaminant metal sulphide may be one or more of zinc sulphide, iron sulphide, nickel sulphide, chromium  
10 sulphide and manganese sulphide. They may be introduced by contamination of the copper compound, support material or binders. Accordingly the low contaminant metal sulphide level required by the present invention may be achieved by the selection of high purity copper compound, support and binder material, and by the exclusion of contaminant metal compounds from the composition. Copper compounds, e.g. copper hydroxycarbonates, often contain small  
15 amounts of zinc. Hence, it is preferable that their zinc content is <0.5% by weight (expressed as the oxide, ZnO), more preferably < 0.2% by weight (as oxide).

It should be understood that the sulphided copper compound may be susceptible to the formation of copper sulphate, but we have found that this is less important than the formation  
20 and presence of the other metal sulphates, in particular zinc sulphate, which has a considerably higher solubility in water than copper sulphate under the typical conditions for mercury removal.

The absorbent composition comprises one or more binders, making up the remaining part of  
25 the absorbent. Preferably the total amount of the one or more binders is in the range 2-20% by weight (based on the sulphided composition). The preferred binders include cement materials, including calcium aluminate cements and related materials such as ciment fondu. The cement binders react when treated with water to form stable hydrates that bind the particulate copper compound and support particles together to form a strong composition.

30 The absorbent materials can undergo considerable physiochemical changes upon treatment with sulphur compounds to form the active copper sulphide phase known to be effective for mercury, arsenic or antimony removal. The physiochemical change, even where support materials are included, can result in reduced crush strength and an increased susceptibility to  
35 attrition, particularly with high metal sulphide containing materials. It is therefore desirable to increase the crush strength whilst maintaining attrition resistance. We have found that a combination of binders and support material in the absorbent overcomes this problem. Furthermore, by using the two binders we have found that the amount of support material may

be increased compared to prior art materials without sacrificing rate of mercury absorption, strength or attrition resistance.

Thus in a preferred embodiment, the absorbent composition comprises a first binder and a  
5 second binder, wherein the first binder is a cement binder and the second binder is a high aspect ratio binder having an aspect ratio >2.

The first binder is preferably a cement binder, in particular a calcium aluminate cement. By the  
term calcium aluminate cement we include such calcium aluminate compounds as calcium  
10 monoaluminate ( $\text{CaO} \cdot \text{Al}_2\text{O}_3$ ), tricalcium aluminate ( $3\text{CaO} \cdot \text{Al}_2\text{O}_3$ ), pentacalcium trialuminate  
( $5\text{CaO} \cdot 3\text{Al}_2\text{O}_3$ ), tricalcium penta aluminate ( $3\text{CaO} \cdot 5\text{Al}_2\text{O}_3$ ), dodeca calcium hepta aluminate  
( $12\text{CaO} \cdot 7\text{Al}_2\text{O}_3$ ) and high alumina cements which may contain alumina in admixture with,  
dissolved in, or combined with such calcium aluminate compounds. For example, a well-known  
commercial cement has a composition corresponding to about 18% wt calcium oxide, 79% wt  
15 alumina and 3% wt water and other oxides. Another suitable commercially available calcium  
aluminate cement has a composition corresponding to about 40% wt calcium oxide, about 37%  
wt alumina, about 6% wt silica and about 20% other oxides.

The second binder is preferably a high aspect ratio binder having an aspect ratio >2. By the  
20 term high aspect ratio we mean that the ratio between the maximum dimension and the  
minimum dimension of the particles is >2. The particles may thus be plate-like where the  
length and breadth are at least twice the thickness. Alternatively, and preferably, the particles  
are acicular, wherein the average length is at least twice, preferably at least 2.5 times, the  
breadth, e.g. having a "rod" configuration wherein the cross sectional dimensions, i.e. breadth  
25 and thickness are approximately equal, or a "lath" configuration, wherein the thickness is  
significantly less than the breadth. Suitable high aspect ratio binders include clays such as  
aluminosilicate clays, preferably an aluminium-magnesium silicate clay, commonly referred to  
as an Attapulgite clay. Without wishing to be bound by theory, we believe that the acicular  
nature of this binder comprising elongate particles with an aspect ratio >2 contributes to the  
30 improved physical properties obtained. We have found surprisingly that the combination of  
these two types of binder in combination with the sulphided copper compound and support are  
capable of providing absorbent materials of high crush strength and low attrition, and which are  
water tolerant, as well as providing a suitably high rate of mercury absorption.

35 The amount of the first binder may be in the range 1 to 10% by weight based on the un-  
sulphided absorbent precursor composition. The amount of the second binder may be in the  
range 1 to 10%, preferably 2 to 5% by weight on the un-sulphided absorbent precursor.  
Preferably, the relative amounts of the binders are 1:1 to 3:1 first to second binder.

A particularly preferred absorbent composition comprises one or more particulate sulphided copper compounds and a particulate alumina or hydrated alumina support material, bound together with the first and second binders, wherein the zinc content of the absorbent is  $\leq 0.1\%$  by weight (expressed as oxide).

5

The absorbent may usefully be prepared by forming a composition comprising a particulate copper compound capable of forming copper sulphide, a particulate support material, and one or more binders, shaping the composition to form an absorbent precursor, drying the absorbent precursor material, and sulphiding the absorbent precursor to form the absorbent. Hence the invention also includes an absorbent precursor comprising a copper compound capable of forming copper sulphide, a particulate support material, and one or more binders, wherein the sulphidable metal content of the absorbent precursor, other than copper, is below 5% by weight (as oxide).

10

15

The absorbent comprising the sulphided copper compound may be in any suitable physical form, e.g. as a granule, extrudate, or tablet so that the mercury-containing stream may be contacted with a bed of solid absorbent particles. The absorbent composition preferably has a particle size within the range 1-15 mm, more preferably 1-10 mm.

20

The absorbent precursor may be in the form of tablets or pellets formed by moulding a suitable powder composition, generally containing a material such as graphite or magnesium stearate as a moulding aid, in suitably sized moulds, e.g. as in conventional tableting or pelleting operation. Alternatively, the shaped units may be in the form of extrudes formed by forcing a suitable composition, containing the absorbent precursor material and often a little water and/or a moulding aid through a die followed by cutting the material emerging from the die into short lengths. For example extrudes may be made using a pellet mill of the type used for pelleting animal feedstuffs, wherein the mixture to be pelleted is charged to a rotating perforate cylinder through the perforations of which the mixture is forced by a bar or roller within the cylinder: the resulting extruded mixture is cut from the surface of the rotating cylinder by a doctor knife positioned to give extruded pellets of the desired length. Alternatively, and preferably, the absorbent or absorbent precursor may be in the form of agglomerates formed by mixing the absorbent precursor material with a little water, insufficient to form a slurry, and then causing the composition to agglomerate into roughly spherical, but generally irregular, granules. Granulated absorbents with a particle size range of 2 to 5mm are especially preferred.

25

30

35

If desired the absorbent or absorbent precursors may be heated or treated in another way to accelerate the setting of the cement binder.

The different shaping methods have an effect on the surface area, porosity and pore structure within the shaped articles and in turn this often has a significant effect on the absorption characteristics and on the bulk density.

- 5 The sulphiding agent used to sulphide the absorbent precursor may be one or more sulphur compounds such as hydrogen sulphide, carbonyl sulphide, mercaptans and polysulphides, or mixtures of these. Hydrogen sulphide is preferred. Using a hydrogen sulphide-containing gas mixture is considerably easier and faster than using alternatives such as solutions of sulphur or sulphur compounds such as polysulphides. The gas mixture may, if desired, contain other
- 10 sulphur compounds such as carbonyl sulphide or volatile mercaptans. Inert gases such as nitrogen, helium or argon may also be present. The sulphiding gas mixture is preferably free of reducing gases such as hydrogen and carbon monoxide, but these may be present where the sulphiding step is performed at temperatures below 150°C, particularly below 100°C. Hydrogen sulphide is preferably provided to the precursor in gas streams at concentrations of 0.1 to 5%
- 15 by volume. Sulphiding temperatures in the range 1-100°C, preferably 5-50°C may be used.

The sulphiding step may be performed on the dried absorbent precursor ex-situ in a sulphiding vessel through which a sulphiding agent is passed, or the sulphiding step may be performed in situ, in which case an absorbent precursor is installed and undergoes sulphidation in the vessel

20 in which it is used to absorb mercury compounds. In-situ sulphiding may be achieved using a sulphiding agent stream or where the stream containing mercury also contains sulphur compounds, the mercury-containing stream. Where such concomitant sulphiding and mercury absorption occurs, the amount of sulphur compound that is present depends on the type of sulphur compound and metal compound used. Usually, a concentration ratio, as defined by the

25 ratio of sulphur compound (expressed as hydrogen sulphide) concentration (v/v) to mercury concentration (v/v), of at least one, and preferably of at least 10 is used so that the precursor is sufficiently sulphided. Should the initial concentration of the sulphur compound in the feed stream be below the level necessary to establish the desired ratio of sulphur compound to mercury compound concentration then it is preferred that the concentration of the sulphur

30 compound is increased by any suitable method.

In contrast to the previous absorbents, e.g. as described in the aforesaid EP 0480603, the absorbent according to the present invention is preferably pre-sulphided. Pre-sulphiding avoids problems caused by the change in volume and strength of the sorbent that can accompany the

35 sulphiding step.

The mercury capacity of the absorbent is proportional to its sulphur content. However very high copper sulphide absorbents often do not have the necessary strength and durability. Furthermore copper is an expensive metal component. The present invention provides an

optimised combination of sulphur content and physical properties compared to current commercially available materials.

5 In order to provide process-efficient materials that allow for suitable absorption vessel sizes, it is preferred that the density of the absorbent, expressed as the sulphur density, is in the range 50 to 200 kg S/m<sup>3</sup>.

10 The present invention may be used to treat both liquid and gaseous fluids containing mercury, arsenic or antimony. In one embodiment, the fluid is a hydrocarbon stream. The hydrocarbon stream may be a refinery hydrocarbon stream such as naphtha (e.g. containing hydrocarbons having 5 or more carbon atoms and a final atmospheric pressure boiling point of up to 204°C), middle distillate or atmospheric gas oil (e.g. having an atmospheric pressure boiling point range of 177°C to 343°C), vacuum gas oil (e.g. atmospheric pressure boiling point range 343°C to 566°C), or residuum (atmospheric pressure boiling point above 566°C), or a hydrocarbon  
15 stream produced from such a feedstock by e.g. catalytic reforming. Refinery hydrocarbon streams also include carrier streams such as "cycle oil" as used in FCC processes and hydrocarbons used in solvent extraction. The hydrocarbon stream may also be a crude oil stream, particularly when the crude oil is relatively light, or a synthetic crude stream as produced from tar oil or coal extraction for example. Gaseous hydrocarbons may be treated  
20 using the process of the invention, e.g. natural gas or refined paraffins or olefins, for example. Off-shore crude oil and off-shore natural gas streams in particular may be treated with the absorbent of the present invention. Contaminated fuels such as petrol or diesel may also be treated. Alternatively, the hydrocarbon may be a condensate such as natural gas liquid (NGL) or liquefied petroleum gas (LPG), or gases such as a coal bed methane, landfill gas or biogas.

25 Non-hydrocarbon fluids which may be treated according to the invention include carbon dioxide, which may be used in enhanced oil recovery processes or in carbon capture and storage, solvents for decaffeination of coffee, flavour and fragrance extraction, solvent extraction of coal etc. Fluids, such as alcohols (including glycols) and ethers used in wash  
30 processes or drying processes (e.g. triethylene glycol, monoethylene glycol, Rectisol™, Purisol™ and methanol), may be treated by the inventive process. Mercury may also be removed from amine streams used in acid gas removal units. Natural oils and fats such as vegetable and fish oils may be treated by the process of the invention, optionally after further processing such as hydrogenation or transesterification e.g. to form biodiesel.

35 Other fluid streams that may be treated include the regeneration gases from dehydration units, such as molecular sieve off-gases, or gases from the regeneration of glycol driers.

Feed streams which are susceptible to being treated by the absorbents may also include those which inherently contain both mercury, arsenic or antimony and a sulphur compound e.g. certain natural gas streams, or a mercury-, arsenic- or antimony- containing stream to which a sulphur compound has been added to effect mercury, arsenic, or antimony absorption.

5

The present invention is of particular utility where the fluid contains water, preferably in low levels in the range 0.02 to 1% vol. Higher levels up to 5% vol may be tolerated for short periods. The absorbents of the present invention may be regenerated simply after prolonged exposure to water simply by purging with a dry gas, preferably a dry inert gas such as nitrogen.

10

Preferably the absorption of mercury is conducted at a temperature below 150 °C, preferably at or below 120 °C in that at such temperatures the overall capacity for mercury absorption is increased. Temperatures as low as 4 °C may be used to good effect in the present invention. A preferred temperature range is 10 to 60 °C.

15

The mercury may be in the form of elemental mercury, or organomercuric, or organomercurous compounds. The present invention is particularly effective in removing elemental mercury although other forms of mercury may be removed for short periods. Typically the concentration of mercury in a gaseous feed stream is from 0.01 to 1100 µg/Nm<sup>3</sup>, and more usually between 20 10 to 600µg/Nm<sup>3</sup>.

25

In use, the absorbent material may be placed in an absorption vessel and the fluid stream containing mercury is passed through it. Desirably, the absorbent is placed in the vessel as one or more fixed beds according to known methods. More than one bed may be employed and the beds may be the same or different in composition. The gas hourly space velocity through the absorbent may be in the range normally employed.

30

The invention is further described by reference to the following Examples and Figures in which: Figure 1 is a graph depicting the Hg absorption profiles of a wet and a dry pre-sulphided comparative Cu/Zn/alumina absorbent not according to the invention, Figure 2 is a is a graph depicting the Hg absorption profiles of two dry pre-sulphided Cu/alumina absorbents according to the invention in comparison with a commercially available pre-sulphided 9% wt Cu (as oxide) impregnated alumina absorbent not according to the invention, and

35

Figure 3 is a graph depicting the Hg absorption profiles of a wet pre-sulphided Cu/Alumina absorbent according to the invention in comparison with a wet commercially available pre-sulphided 9% wt Cu (as oxide) impregnated alumina absorbent,.

Unless otherwise stated, absorbent precursor particles were prepared using a granulation technique wherein the solid components were combined with a little water and mixed to form granules in a Hobart mixer. The precursors were sulphided using a dilute hydrogen sulphide stream using known methods. The precursor materials were taken to a fully sulphided state  
5 using 1% H<sub>2</sub>S in an inert carrier gas, (typically N<sub>2</sub>) at ambient temperature and pressure.

Example 1 (comparative)

In order to assess the problems caused when water is present, 25 ml of a 1-2mm-sized particulate granulated absorbent comprising sulphided copper and zinc compounds, alumina  
10 support and single cement binder was charged to a tubular lab-scale absorption vessel (i.d. 18 mm). The copper content of the sulphided absorbent was 45% wt (as oxide) and the zinc content was 22% wt (as oxide).

The lower 25 wt% by volume of the bed was made up from a pre-soaked absorbent. The  
15 material was immersed in demineralised water for 30 minutes at ambient temperature, then the water was decanted off and the particles touch-dried with absorbent paper. The remaining upper 75% by volume of the bed was dry material. N-hexane saturated with elemental mercury to ca. 1ppm (w/v) was passed upwards through the bed at ambient temperature (about 20°C) such that the fluid contacted the water-soaked material and then the dry material, at a Liquid  
20 Hourly Space Velocity (LHSV) of 7.0hr<sup>-1</sup> for 750 hours. Exit samples were taken from the reactor exit line and analysed on a PSA modified Hewlett Packard 6890 GC to monitor mercury levels. At the end of the test, the bed was discharged into 9 equivalent discrete sub-beds, which were analysed for total mercury content by ICP-Optical Emission Spectroscopy.

25 The bed profile of the absorbent charged with the inlet 25% wet in comparison with an entirely dry bed used in the same test is shown in Figure 1.

No elemental mercury was detected from the reactor exit stream during the 750 hours in which the test was carried out. As the test run progressed, a white solid was observed to form at the  
30 interface between the initially wet granules and the dry granules. Agglomeration was also observed at this interface.

In comparison with the wet material, the dry absorbent profile is sharp, with the majority of the mercury pickup confined to the first 6-10ml of the bed volume. However, with water present in  
35 the inlet 25% of the bed volume, the mercury pickup slides down the bed and results in a much lazier profile with the reaction zone being extended. This would result eventually in a faster breakthrough of mercury from the vessel. A second reaction front is also observed, where the mercury pickup of the bed increases at about 48% along the bed after a minimum. The minimum point at about 30% down the bed corresponds to the section of the bed that was

white in colour and had agglomerated. As one progresses further down the bed, the mercury pickup increases.

5 It may be concluded from this data that the area that was white in colour and had agglomerated had a reduced capability to remove mercury from the liquid hydrocarbon stream.

When water is present, the copper and zinc sulphides are converted to sulphates. Without wishing to be bound by any theory, It is thought that the reduced mercury absorption is due to a combination of zinc sulphate's high solubility in water and its subsequent coating of the copper sulphide-sulphate rich granules further down the bed, resulting in a decrease in the capability of the bed to remove mercury.

#### Example 2 (dry testing)

Absorbent precursor compositions were prepared in a granulator with the following  
15 compositions;  
20 or 30 parts by weight of a flash-dried copper hydroxycarbonate,  
80 or 70 parts by weight of alumina trihydrate,  
14 parts by weight of binders comprising 10 parts of a calcium aluminate cement having a CaO content of about 40% wt, plus 4 parts Attapulgate clay).

20 The granules were dried at 105°C in air for 16 hours after a period of 2 hours at ambient temperature (ca 20°C). The size range of granules obtained was 1-5 mm.

The granulated materials were sulphided in the laboratory to saturation in 1% H<sub>2</sub>S to generate  
25 the active absorbent.

The sulphided absorbents were run in the test as described in Example 1, although the beds in each case were run dry and not pre-soaked. The test was repeated on a commercially available pre-sulphided 9% wt Cu (as oxide) impregnated alumina absorbent. The results are  
30 depicted in Figure 2. The results show that both compositions according to the invention were effective in removing Hg from the fluid, with the higher Cu content material providing a sharper bed profile. The compositions according to the present invention also provide a sharper bed profile than the commercially available impregnated Cu on alumina material.

#### Example 3 (wet testing)

35 An absorbent precursor composition was prepared in a granulator with the following composition;

25 parts by weight of a flash-dried copper hydroxycarbonate,  
75 parts by weight of alumina trihydrate,

14 parts by weight of binders comprising 10 parts of a calcium aluminate cement having a CaO content of about 40% wt, plus 4 parts Attapulgite clay).

5 The granules were dried at 105°C in air for 16 hours after a period of 2 hours at ambient temperature (ca 20°C). The size range of granules obtained was 1-5 mm.

The granulated materials were sulphided in the laboratory to saturation in 1% H<sub>2</sub>S to generate the active absorbent.

10 The sulphided absorbent was run as tested in Example 1 with the first 25% vol of the bed pre-soaked in demineralised water. The test was repeated on a commercially available presulphided 9% wt Cu (as oxide) impregnated alumina absorbent, again with the first 25% of the bed pre-soaked. The results are depicted in Figure 3.

15 The absorbent according to the present invention showed no signs of agglomeration or colour change at the wet/dry interface. The comparative 9% wt Cu impregnated alumina material, although being copper-only, suffered from the presence of water, with mercury pickup continuing into about 72% of the thickness of the bed.

20 A series of tests was performed to establish the physical properties of the sulphided absorbents in Examples 1 and 3, and the 9%wt Cu commercially available material. In respect of the Cu/Zn composition of Example 1, the physical properties were determined on a 2-5 mm granulate for better comparison.

25 i) Tapped Bulk Densities (TBD)

60ml of absorbent granules (size cut 2-5mm) were weighed into a 100ml plastic measuring cylinder. The density was calculated by dividing the mass by the volume. The cylinder was manually tapped to achieve a constant volume. The density was calculated by dividing the mass by the tapped volume (TBD).

30

ii) Mean Crush Strength

An Engineering Systems CT-5 was used to measure the mean crush strength (MCS) of the absorbent granules. The instrument was fitted with a 5kg load cell and calibrated. The granules selected for testing were sized 3-4.mm, in order to reduce the effect of granule size on crush strength. Twenty granules of each absorbent were crushed and a statistical analysis  
35 performed.

## iii) Sulphur Analysis

Analysis for sulphur content was performed using a LECO SC632, by combustion and the subsequent infrared measurement of sulphur dioxide.

## 5 iv) Pore Structure Analysis

The samples were outgassed at 140°C for 1 hour with a nitrogen purge prior to BET surface area / isotherm measurements.

## v) X-Ray Fluorescence (XRF)

- 10 Semi-quantitative XRF analysis was performed using a Philips Magix-Pro/Bruker SRS3400. The results estimate the relative abundance of each element in the absorbent samples by comparison of their relative peak intensities.

The results are given in Table 1. The compositions for the materials of Examples 1 and 3 have  
15 been calculated from theoretical mass balances, whereas the composition of the impregnated material was determined by XRF analysis.

20

25

30

35

Table 1

Description	Example 1 Comparative Cu/Zn on alumina granulated with cement binder	Example 3 Cu on alumina granulated with mixed binders	Comparative 9% wt Cu impregnated alumina support
Precursor			
Cu (% wt as oxide)	54	21.75	-
Zn (% wt as oxide)	27	0.06	-
Al (% wt as oxide)	14	72	-
Ca (% wt as oxide)	3	4	-
Mg (% wt as oxide)	0.00	0.43	-
Na (% wt as oxide)	0.07	0.07	-
Sulphided			
Cu (% wt as oxide)	47	20	11.1
Zn (% wt as oxide)	23	0.05	0.00
Al (% wt as oxide)	12	64	83
Ca (% wt as oxide)	2	3	0.04
Mg (% wt as oxide)	0.00	0.40	0.00
Na (% wt as oxide)	0.05	0.06	0.19
Tests on sulphided absorbent			
TBD (g cm <sup>3</sup> )	0.76	1.06	0.65
MCS (kg)	1.13	2.39	1.33
Sulphur (%)	21	8	6.7
Sulphur Density kg/m <sup>3</sup>	160	85	43.6
BET Surface Area (m <sup>2</sup> g <sup>-1</sup> )	53.6	12.3	59.2
Pore Volume (cm <sup>3</sup> g <sup>-1</sup> )	0.27	0.05	0.41
Average Pore Diameter (Å)	203	174	276

An increase in crush strength is observed for the absorbent of the present invention. The sulphur density is also higher than for the impregnated material.

Claims.

1. An absorbent composition, suitable for removing mercury, arsenic or antimony from a fluid stream, comprising 5-50% by weight of a particulate sulphided copper compound, 30-90% by weight of a particulate support material, and the remainder one or more binders, wherein the metal sulphide content of the absorbent, other than copper sulphide, is  $\leq 5\%$  by weight.
2. An absorbent according to claim 1 wherein the sulphided copper compound is sulphided basic copper carbonate, sulphided copper hydroxide, sulphided copper oxide or mixtures of these.
3. An absorbent according to claim 1 or claim 2 wherein the support material is an alumina, hydrated alumina, titania, zirconia, silica or aluminosilicate, or a mixture of two or more of these.
4. An absorbent according to any one of claim 1 to 3 wherein the binder content of the absorbent is in the range 5-20% by weight.
5. An absorbent according to any one of claims 1 to 4 comprising a first binder and optionally a second binder, wherein the first binder is a cement binder and the second binder is a high aspect ratio binder having an aspect ratio  $>2$ .
6. An absorbent according to claim 5 wherein the first binder is a calcium aluminate cement binder.
7. An absorbent according to claim 5 or claim 6 wherein the second binder is an aluminosilicate clay.
8. An absorbent according to any one of claims 5 to 7 wherein the second binder is an Attapulgite clay.
9. An absorbent according to any one of claims 5 to 8 wherein the relative amounts of the first and second binder are in the range 1:1 to 3:1 (first to second binder).
10. An absorbent according to any one of claims 1 to 9 wherein the total metal sulphide content, other than copper sulphide, is  $\leq 1\%$  wt, more preferably  $\leq 0.5\%$  wt, especially  $\leq 0.1\%$  wt.

11. An absorbent according to any one of claims 1 to 10 wherein the density of the absorbent, expressed as the sulphur density, is in the range 50 to 200 kg S/m<sup>3</sup>.
12. A method for making the absorbent according to any one of claims 1 to 11 comprising the steps of:
  - i) forming a composition comprising a particulate copper compound capable of forming copper sulphide, a particulate support material, and one or more binders,
  - ii) shaping the composition to form an absorbent precursor,
  - iii) drying the absorbent precursor material, and
  - iv) sulphiding the precursor to form the absorbent.
13. A method according to claim 12 wherein the sulphiding step is performed by reacting a sulphur compound selected from hydrogen sulphide, carbonyl sulphide, mercaptans and polysulphides with the metal compound capable of forming a metal sulphide in the dried absorbent precursor.
14. A process for removing mercury, arsenic or antimony from a process fluid comprising contacting said fluid with an absorbent according to any of claims 1 to 11 or as prepared according to claim 12 or claim 13.
15. A mercury removal process according to claim 14 wherein the mercury containing fluid contains water in an amount in the range 0.02 to 5% vol.
16. A mercury removal process comprising according to claim 14 or claim 15 wherein the fluid is a hydrocarbon stream.
17. A mercury removal process according to claim 15 or claim 16 wherein the fluid is an off-shore hydrocarbon stream or a regeneration stream from a hydrocarbon dehydration unit.




Figure 1




Figure 2




Figure 3

**INTERNATIONAL SEARCH REPORT**

International application No  
PCT/GB2009/050085

**A. CLASSIFICATION OF SUBJECT MATTER**  
INV. B01J20/02 B01J20/28 C10G25/00

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
B01J C10G B01D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 484 233 A (INST FRANCAIS DU PETROLE [FR];) 6 May 1992 (1992-05-06) page 5, line 27 page 3, line 2 - line 3 page 3, line 17 - line 18 example 2 page 3, line 30 - line 31	1-4, 10, 14, 16
X	US 4 094 777 A (SUGIER ANDRE ET AL) 13 June 1978 (1978-06-13). cited in the application column 2, line 41 - line 43 column 4; examples A,C column 1, line 65 - line 66 column 2, line 47 - line 48 column 2, line 18 - line 21 column 4, line 4 column 4, line 24	1-5, 10, 12-14, 16
	-/--	

Further documents are listed in the continuation of Box C.

See patent family annex.

\* Special categories of cited documents :

\*A\* document defining the general state of the art which is not considered to be of particular relevance

\*E\* earlier document but published on or after the international filing date

\*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

\*O\* document referring to an oral disclosure, use, exhibition or other means

\*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*&\* document member of the same patent family

Date of the actual completion of the international search

26 May 2009

Date of mailing of the international search report

03/06/2009

Name and mailing address of the ISA/  
European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040,  
Fax: (+31-70) 340-3016

Authorized officer  
  
Hilgenga, Klaas

## INTERNATIONAL SEARCH REPORT

International application No  
PCT/GB2009/050085

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 487 370 A (INST FRANCAIS DU PETROLE [FR]) 27 May 1992 (1992-05-27) page 3, line 18 page 3, line 29 page 3, line 33 - line 34 page 3, line 51 page 3, line 46 page 3, line 41 - line 43	1-4, 10, 14, 16
X	EP 0 628 337 A (INST FRANCAIS DU PETROLE [FR]) 14 December 1994 (1994-12-14) page 3, line 21 - line 22 page 3, line 9 page 3, line 35 - line 36; claim 4	1-4, 10, 14, 16
A	US 2006/148642 A1 (RYU CHONG-KUL [KR] ET AL) 6 July 2006 (2006-07-06) page 3, paragraph 34 page 3, paragraph 37 - paragraph 38	1, 3, 5-7
A	US 4 909 926 A (YAN TSOUNG Y [US]) 20 March 1990 (1990-03-20) column 4; table 2 column 3, line 14 - line 19 column 4, line 60 column 3, line 31 - line 33 column 4; tables 1, 2	1-4, 10, 12-16

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/GB2009/050085

Patent document cited in search report	A	Publication date	Patent family member(s)	Publication date
EP 0484233	A	06-05-1992	AU 648120 B2	14-04-1994
			AU 8683891 A	28-01-1993
			CN 1063239 A	05-08-1992
			DE 69101899 D1	09-06-1994
			DE 69101899 T2	25-08-1994
			DZ 1536 A1	17-02-2002
			ES 2064063 T3	16-01-1995
			FI 915108 A	01-05-1992
			FR 2668388 A1	30-04-1992
			JP 3198345 B2	13-08-2001
			JP 5168912 A	02-07-1993
			NO 914221 A	04-05-1992
			US 4094777	A
ES 454417 A1	16-03-1978			
GB 1533059 A	22-11-1978			
IT 1065797 B	04-03-1985			
JP 52076284 A	27-06-1977			
NL 7613998 A	21-06-1977			
EP 0487370	A	27-05-1992	AU 641559 B2	23-09-1993
			AU 8685991 A	07-05-1992
			CN 1062300 A	01-07-1992
			DE 69112576 D1	05-10-1995
			DE 69112576 T2	08-02-1996
			ES 2079605 T3	16-01-1996
			FR 2668385 A1	30-04-1992
			JP 4265121 A	21-09-1992
EP 0628337	A	14-12-1994	NONE	
US 2006148642	A1	06-07-2006	US 2008119356 A1	22-05-2008
US 4909926	A	20-03-1990	AU 626015 B2	23-07-1992
			AU 4892690 A	09-08-1990
			CA 2008611 A1	01-08-1990
			EP 0381453 A1	08-08-1990
			JP 2261895 A	24-10-1990