

AUSTRALIA

NON CONVENTION

Patents Act

622282

APPLICATION FOR A STANDARD PATENT

Imperial Chemical Industries PLC  
Imperial Chemical House, Millbank, London SW1P 3JF, UNITED KINGDOM

hereby applies for the grant of a standard patent for an invention entitled:

**GREASE COMPOSITION**

which is described in the accompanying complete specification.

Address for Service:

PHILLIPS ORMONDE & FITZPATRICK  
Patent and Trade Mark Attorneys  
367 Collins Street  
Melbourne 3000 AUSTRALIA

DATED this FIFTEENTH day of FEBRUARY 1990

PHILLIPS ORMONDE & FITZPATRICK  
Attorneys for:  
Imperial Chemical Industries PLC

By:



Our Ref : 163963  
POF Code: 1453/1453

6010



AUSTRALIA

Patents Act

## DECLARATION IN SUPPORT OF AN APPLICATION FOR A PATENT

In support of the Application made by Imperial Chemical Industries PLC for a patent for an invention entitled:

GREASE COMPOSITION


I, John Lindley LENG ..... (Full Name)

of IMPERIAL CHEMICAL INDUSTRIES PLC, Imperial Chemical  
House, Millbank, London SW1P 3JF, England  
do solemnly and sincerely declare as follows:

1. I am authorized by Imperial Chemical Industries PLC, the applicant for the patent to make this declaration on its behalf.
2. BERNARD TURY of 8 Spring Vale, Prestwich, Manchester M25 8SE, England is/are the actual inventor/s of the invention and the facts upon which the Imperial Chemical Industries PLC is entitled to make the application are as follows:

The applicant is the assignee of the actual inventor/s.

Declared at Welwyn Garden City this ..... 28th day of February 1990  
Hertfordshire, England

.....  (Signature)  
(Typed Name)

JOHN LINDLEY LENG  
Authorised Officer

To: The Commissioner of Patents IMPERIAL CHEMICAL INDUSTRIES PLC

PHILLIPS ORMONDE & FITZPATRICK

Our Ref : 163963

POF Code: 1453/1453

(12) PATENT ABRIDGMENT (11) Document No. AU-B-49801/90  
(19) AUSTRALIAN PATENT OFFICE (10) Acceptance No. 622282

(54) Title  
**GREASE COMPOSITION**

International Patent Classification(s)

(51)<sup>4</sup> C10M 129/50 C10M 113/10 C10M 113/12 C10M 131/12

(21) Application No. : 49801/90 (22) Application Date : 15.02.90

(43) Publication Date : 22.08.91

(44) Publication Date of Accepted Application : 02.04.92

(71) Applicant(s)  
**IMPERIAL CHEMICAL INDUSTRIES PLC**

(72) Inventor(s)  
**BERNARD TURY**

(74) Attorney or Agent  
**PHILLIPS ORMONDE & FITZPATRICK , 367 Collins Street, MELBOURNE VIC 3000**

(56) Prior Art Documents  
AU 605276 14763/88 C09D C10M  
US 3711407  
US 2652364

(57) Claim

1. A composition which comprises

(a) a salt of a monovalent metal (M) of a carboxylic acid in which the carboxylic acid group is attached to a ring atom of a fused ring system; and

(b) a grease which is a non-soap thickened mineral or synthetic oil wherein the composition contains 0.1 to 30% by weight of the salt which is component (a) relative to the total volume of the composition.

3. A composition as claimed in either claim 1 or claim 2 wherein component (a) is a salt of an alkali metal and the fused ring system is a fused aromatic hydrocarbon ring system.

5. A composition as claimed in any one of claims 1 to 4 wherein component (a) is sodium 2-naphthoate or sodium 3-hydroxy-2-naphthoate.

10. A bearing containing as a lubricant a composition as claimed in any one of claims 1 to 9.

AUSTRALIA

Patents Act

622282

COMPLETE SPECIFICATION  
(ORIGINAL)

Class Int. Class

Application Number:  
Lodged:

Complete Specification Lodged:  
Accepted:  
Published:

Priority

Related Art:

---

Applicant(s):

Imperial Chemical Industries PLC  
Imperial Chemical House, Millbank, London SW1P 3JF, UNITED KINGDOM

Address for Service is:

PHILLIPS ORMONDE & FITZPATRICK  
Patent and Trade Mark Attorneys  
367 Collins Street  
Melbourne 3000 AUSTRALIA

Complete Specification for the invention entitled:

**GREASE COMPOSITION**

Our Ref : 163963  
POF Code: 1453/1453

The following statement is a full description of this invention, including the best method of performing it known to applicant(s):

GREASE COMPOSITION

The present invention relates to a grease composition, particularly a grease composition which gives reduced corrosion of metals in contact with the grease.

Many greases are oils which have been thickened by the addition to the oil of a gelling agent. The oils used for most greases are mineral oils, that is hydrocarbon oils, but other oils, such as synthetic oils, can be used to produce greases, for example synthetic hydrocarbon oils, diesters such as di(2-ethylhexyl) sebacate, perfluoroalkyl ethers and silicone oils. Many greases are obtained using soaps, generally lithium soaps, as the gelling agent. However, non-soap gelling agents can produce a grease having improved properties, for example such greases may be used at a higher continuous use temperature.

Non-soap gelling agents include clays, carbon black, silica and polyurea, all of which are preferably used as finely divided solid materials. Finely divided clay particles, for example clays of the bentonite or hectorite types, can be used as non-soap gelling agents to obtain grease from an oil such as a mineral oil. The clay particles are commonly used after being surface coated with an organic material such as a quaternary ammonium compound. In silicone oils, a silica filler may be used as a non-soap gelling agent, a typical silica for this purpose being fumed silica having an average particle size less than one micron.

In use many greases are in contact with metal bearing surfaces and the metal is frequently susceptible to corrosion. To reduce the corrosion of the metal, additives to provide corrosion protection may be added to the grease. However, greases containing non-soap gelling agents such as clays or silica can undergo de-structuring, by which is meant that the oil and gelling agent separate. Additives which are useful to provide corrosion protection can cause de-structuring of greases containing non-soap gelling agents. Sodium nitrite has been proposed as a corrosion inhibitor in non-soap thickened greases. However, many greases contain amine compounds as antioxidants and there is then a risk of carcinogenic nitrosoamines being formed and hence the use of sodium

nitrite is undesirable. Disodium sebacate is used in non-soap thickened greases to provide some corrosion protection without promoting de-structuring of the grease. However, this material is expensive and it is desirable to find alternative corrosion inhibitors which do not cause de-structuring of non-soap thickened greases.

We have now found certain metal salts of aromatic carboxylic acids provide useful inhibition of corrosion without causing de-structuring of a non-soap thickened grease.

According to the present invention there is provided a composition which comprises

- (a) a salt of a monovalent metal (M) of a carboxylic acid in which at least one carboxylic acid group is attached to a ring atom of a fused ring system; and
- (b) a grease which is a non-soap thickened mineral or synthetic oil.

Hereafter the salt of a monovalent metal (M) of a carboxylic acid in which the carboxylic acid group is attached to a ring atom of a fused ring system will be referred to simply as "the salt".

The fused ring system may be substituted or unsubstituted. Suitable substituents include halogen atoms, hydroxyl groups, hydrocarbyl groups, hydrocarbonoxy groups, hydrocarbonyl groups or hydrocarbonyloxy groups. Any substituent groups which are present in the fused ring system are additional to the carboxylic acid group or groups. The substituent groups may be such as to modify the solubility characteristics of the salt but preferably should not produce appreciable solubility in the oil on which the grease is based. Thus, the substituent may be an alkyl, alkenyl, alkoxy or acyl group preferably one which contains not more than 4 carbon atoms. Useful results have been obtained when the fused ring system contains at least one substituent group which is a hydroxyl group.

The fused ring system contains at least two rings fused together. One or more of the rings may contain a heteroatom, for example a nitrogen atom. Salts in accordance with the present invention are particularly those in which at least one ring of the fused ring system is a hydrocarbon ring. Convenient compounds are those in which the fused ring system is a hydrocarbon ring system,

for example a fused aromatic hydrocarbon ring system. If the fused ring system contains a hydroxyl group substituent, it is preferred that the hydroxyl group and the carboxylic acid group are attached to adjacent carbon atoms of the fused ring system, and especially of a fused hydrocarbon ring system. The fused ring system is typically a naphthalene ring system, for example as in 2-naphthoic acid, 3-hydroxy-2-naphthoic acid, 2-hydroxy-1-naphthoic acid and 1-hydroxy-2-naphthoic acid.

The metal (M) is monovalent and is typically an alkali metal, for example lithium, potassium and especially sodium. We have obtained useful results using sodium 2-naphthoate and sodium 3-hydroxy-2-naphthoate. The salt is preferably finely divided and in general is sufficiently fine to pass through a sieve having a mesh spacing of not more than 100 micrometres.

The composition of the present invention also includes a grease. The grease may be based on a mineral oil and with such a grease the non-soap thickening agent is preferably a finely divided clay and especially an organophilic clay. Alternatively the grease may be based on a synthetic oil which may be a silicone oil such as a polydiorganosiloxane, for example a polydimethylsiloxane or copolymer thereof. A suitable thickening agent for such a grease is finely divided silica, particularly fumed silica.

Non-soap thickened greases in which the thickening agent is a clay, carbon black, silica or a polyurea are commercially available and the salt which is component (a) can be incorporated into such a grease to provide useful corrosion protection with no detectable de-structuring of the grease.

The composition of the present invention which comprises components (a) and (b) may include other materials as additives to the grease, in addition to the salt. These other materials may include those which have been proposed as corrosion inhibitors. However, it should be appreciated that the other materials should not themselves cause de-structuring of the grease and should not interact with the salt to cause de-structuring of the grease. Whether or not de-structuring of the grease occurs can be determined readily, for example by visual observation or by a comparatively simple test.

The composition typically contains from 0.1 to 30% by weight of the salt relative to the total volume of the composition and preferably the salt is present in an amount of 0.1 to 5% w/v.

In addition to the metal salt, the composition of the present invention may include various other ingredients commonly incorporated into a grease such as oxidation inhibitors, and extreme pressure additives.

The composition of the present invention may be prepared using any of the techniques which are effective for incorporating solids into a liquid or plastic medium in which the solid is essentially insoluble. Satisfactory incorporation of the salt, preferably in finely divided form, into the grease may be achieved by mixing the salt and the preformed grease together, for example by stirring together for a few minutes, typically not more than 10 minutes. Alternatively the salt may be incorporated into the oil which is subsequently thickened to form the desired grease.

The grease composition of the present invention may be used in any application for which a grease is known, and in particular can be used in general automotive applications and also in bearings including high performance bearings. We have found that when subjected to an anti-rust test the compositions of the present invention show improved resistance to corrosion compared to a grease composition containing the same weight of the known corrosion inhibitor, disodium sebacate.

A bearing containing, as a lubricant, a grease composition in accordance with the present invention is a further feature of the present invention.

Various aspects of the present invention are set out in more detail hereafter in the following illustrative examples in which all parts and percentages are by weight unless otherwise stated.

#### Preparation of sodium salts

The sodium salts of 2-naphthoic acid and 3-hydroxy-2-naphthoic acid were prepared by neutralising the acid with an equivalent amount of aqueous sodium hydroxide solution to obtain a solution of the salt and evaporating the solution to dryness.

The salt obtained was crushed through a 300 mesh sieve (about 57 micrometres mesh spacing).

Examples 1 and 2

Samples of an organo clay grease were applied to bearings which were then subjected to the IP dynamic anti-rust test for lubricating greases (IP 220) using distilled water. The grease had been obtained by thickening lubricating oil with 9% w/w of an organophilic clay and contained no corrosion inhibitor. The test was carried out using samples of the grease to which 1% w/w of a corrosion inhibitor had been added and also a grease to which there was no addition of a corrosion inhibitor. The corrosion inhibitors were used as fine solids and were incorporated into the grease by stirring in by hand.

On completion of the test after seven days, the bearings were removed, cleaned and the outer ring track carefully examined for rust or etch spots and rated in accordance with the standards of the test. The results obtained are set out in Table One.

Table One

Example or Comp.Ex.	Additive Type (a)	Corrosion rating (b)
1	SB	0
2	SN	0
A	DSS	2
B	Nil	5

Notes to Table One

(a) SB is sodium 3-hydroxy-2-naphthoate.

SN is sodium 2-naphthoate.

DSS is disodium sebacate, a commercially available corrosion inhibitor.

Nil means that no corrosion inhibitor was added to the grease.

(b) The corrosion rating is assessed in accordance with IP 220 in which ratings are assigned, on a non-linear scale from zero (no visible corrosion) to five (an area of corrosion more than 10% of the surface).

Visual examination of the grease samples showed no obvious signs of de-structuring of the grease. Using a Bohlin rheometer in the oscillatory mode, the data obtained indicated that no appreciable de-structuring had occurred, the variation in the viscoelastic properties with shear being essentially the same in all the grease compositions tested, both with and without a corrosion inhibitor.

By way of contrast, when zinc 3-hydroxy-2-naphthoate was used, the EMCOR rating was 0 but de-structuring of the grease was apparent both from visual inspection and from tests using the Bohlin rheometer.

Example 3

The procedure of Examples 1 and 2 was repeated using a grease obtained by thickening a silicone oil with about 8% w/w of finely divided silica.

The results obtained are set out in Table Two.

Table Two

Example or Comp.Ex.	Additive Type (a)	Corrosion rating (b)
3	SB	0
C	Nil	5

Notes to Table Two

(a) and (b) are both as defined in Notes to Table One.

Examination of the grease, both by visual examination and by using the Bohlin rheometer indicated that no appreciable de-structuring had taken place.

Examples 4 and 5

To samples of an organo-clay lubricating grease (prepared as described in Examples 1 and 2) were added 1% w/w of a corrosion inhibitor using the procedure described in Examples 1 and 2.

Samples of grease containing a corrosion inhibitor, and also samples of a grease containing no corrosion inhibitor, were subjected to the cone penetration of lubricating grease using one-half scale cone equipment and the procedure of ASTM Test Method D1403. The cone penetrations were carried out on samples of grease which had been brought to 25°C and subjected to sixty double strokes in a grease worker in the manner described in ASTM Test Method D1403. Using the standard formula as set out in ASTM Test Method D1403, the measurements made were transformed to give the worked penetration of the cone for full scale cone equipment. The results obtained are set out in Table Three.

Table Three

Example or Comp.Ex.	Additive Type (a)	Worked Penetration (b)
4	SB	327
5	SN	327
D	DSS	331
E	NIL	320

Notes to Table Three

- (a) is as defined in Notes to Table One;
- (b) Worked penetration is the depth, in tenths of a millimetre, that the standard cone penetrates the worked grease using the conditions as set out in ASTM Test Method D1403 and the standard formula to transform the measurements.

THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:

1. A composition which comprises
  - (a) a salt of a monovalent metal (M) of a carboxylic acid in which the carboxylic acid group is attached to a ring atom of a fused ring system; and
  - (b) a grease which is a non-soap thickened mineral or synthetic oil wherein the composition contains 0.1 to 30% by weight of the salt which is component (a) relative to the total volume of the composition.
2. A composition as claimed in claim 1 wherein component (a) is a salt in which the fused ring system is further substituted with at least one group which is a halogen atom, a hydroxyl group, a hydrocarbyl group, a hydrocarbonoxy group, a hydrocarbonyl group or a hydrocarbonyloxy group.
3. A composition as claimed in either claim 1 or claim 2 wherein component (a) is a salt of an alkali metal and the fused ring system is a fused aromatic hydrocarbon ring system.
4. A composition as claimed in either claim 2 or claim 3 in which component (a) is a salt containing a hydroxyl group and the carboxylic acid and the hydroxyl group are attached to adjacent carbon atoms of the fused ring system.
5. A composition as claimed in any one of claims 1 to 4 wherein component (a) is sodium 2-naphthoate or sodium 3-hydroxy-2-naphthoate.
6. A composition as claimed in any one of claims 1 to 5 wherein the grease is a clay, carbon black, silica or polyurea thickened mineral or synthetic oil grease.
7. A composition as claimed in claim 5 wherein the grease is a mineral oil which has been thickened with an organophilic clay.
8. A composition as claimed in any one of claims 1 to 6 wherein the grease is a non-soap thickened synthetic oil grease obtained from a synthetic hydrocarbon oil, a diester, a perfluoralkyl ether or a silicone oil.



9. A composition as claimed in claim 8 wherein the grease is a silicone oil thickened with fumed silica.

10. A bearing containing as a lubricant a composition as claimed in any one of claims 1 to 9.

5 11. A composition as claimed in claim 1 substantially as hereinbefore described with reference to any one of the examples.

DATED: 28 January, 1992.

10 PHILLIPS ORMONDE & FITZPATRICK  
Attorneys for:  
IMPERIAL CHEMICAL INDUSTRIES PLC.

*David B Fitzpatrick*

15

20

25

30

35

40



RB