

(56)

References Cited

U.S. PATENT DOCUMENTS

2006/0097341 A1* 5/2006 Pellizzer H01L 45/1691
257/528
2010/0059730 A1 3/2010 Ito et al.
2018/0040669 A1* 2/2018 Wu H01L 23/528

OTHER PUBLICATIONS

Velea, et al. "Te-Based Chalcogenide Materials for Selector Applications." Scientific Reports | 7: 8103 | DOI:10.1038/s41598-017-08251-z. Published Aug. 14, 2017.

Raoux, et al. "Crystallization Properties of Ultrathin Phase Change Films." Journal of Applied Physics 103, 114310 (2008).

Chen, An. "Analysis of Partial Bias Schemes for the Writing of Crossbar Memory Arrays." IEEE Transactions on Electron Devices, vol. 62, No. 9, Sep. 2015.

Non-Final Office Action dated May 1, 2019 for U.S. Appl. No. 16/025,008.

Notice of Allowance dated Aug. 2, 2019 for U.S. Appl. No. 16/025,008.

* cited by examiner




Fig. 1A




Fig. 1B




Fig. 2A




Fig. 2B




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7




Fig. 8




Fig. 9




Fig. 10




Fig. 11




Fig. 12




Fig. 13





Fig. 14

**Fig. 15**

MULTI-LAYER STRUCTURE TO INCREASE CRYSTALLINE TEMPERATURE OF A SELECTOR DEVICE

REFERENCE TO RELATED APPLICATION

This Application is a Continuation of U.S. application Ser. No. 16/025,008, filed on Jul. 2, 2018, the contents of which are hereby incorporated by reference in their entirety.

BACKGROUND

Many modern day electronic devices contain electronic memory. Electronic memory may be volatile memory or non-volatile memory. Non-volatile memory is able to store data in the absence of power, whereas volatile memory is not. Some examples of next generation electronic memory include resistive random-access memory (RRAM), phase-change random-access memory (PCRAM), magnetoresistive random-access memory (MRAM), and conductive-bridging random-access memory (CBRAM). In some next generation electronic memory, selector devices are coupled to memory cells to mitigate the negative effects (e.g., sneak paths) associated with scaling down the feature size of next generation electronic memory.

BRIEF DESCRIPTION OF THE DRAWINGS

Aspects of the present disclosure are best understood from the following detailed description when read with the accompanying figures. It is noted that, in accordance with the standard practice in the industry, various features are not drawn to scale. In fact, the dimensions of the various features may be arbitrarily increased or reduced for clarity of discussion.

FIGS. 1A-1B illustrate various views of some embodiments of a memory device having a plurality of semiconductor devices each having a buffer structure disposed between a first amorphous switching structure and a second amorphous switching structure.

FIGS. 2A-2B illustrate various views of some alternative embodiments of the memory device of FIG. 1 in which the threshold selector has additional buffer structures and an additional amorphous switching structure.

FIG. 3 illustrates a cross-sectional view of some embodiments of an integrated chip (IC) comprising a memory device having a plurality of semiconductor devices each having a plurality of buffer structures and a plurality of amorphous switching structures.

FIGS. 4-14 illustrate a series of cross-sectional views of some embodiments for forming an integrated chip (IC) comprising a memory device having a plurality of semiconductor devices each having a plurality of buffer structures and a plurality of amorphous switching structures.

FIG. 15 illustrates a flowchart of some embodiments of a method for forming an integrated chip (IC) comprising a memory device having a plurality of semiconductor devices each having a plurality of buffer structures and a plurality of amorphous switching structures.

DETAILED DESCRIPTION

The present disclosure will now be described with reference to the drawings wherein like reference numerals are used to refer to like elements throughout, and wherein the illustrated structures are not necessarily drawn to scale. It will be appreciated that this detailed description and the

corresponding figures do not limit the scope of the present disclosure in any way, and that the detailed description and figures merely provide a few examples to illustrate some ways in which the inventive concepts can manifest themselves.

The present disclosure provides many different embodiments, or examples, for implementing different features of this disclosure. Specific examples of components and arrangements are described below to simplify the present disclosure. These are, of course, merely examples and are not intended to be limiting. For example, the formation of a first feature over or on a second feature in the description that follows may include embodiments in which the first and second features are formed in direct contact, and may also include embodiments in which additional features may be formed between the first and second features, such that the first and second features may not be in direct contact. In addition, the present disclosure may repeat reference numerals and/or letters in the various examples. This repetition is for the purpose of simplicity and clarity and does not in itself dictate a relationship between the various embodiments and/or configurations discussed.

Further, spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature’s relationship to another element(s) or feature(s) as illustrated in the figures. The spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. The apparatus may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein may likewise be interpreted accordingly.

Some next generation memory comprises a plurality of resistive switching cells. The resistive switching cells define a memory array and are arranged in a plurality of rows and a plurality of columns (e.g., in a cross-bar array). A plurality of first conductive lines are disposed beneath the memory array, and a plurality of second conductive lines are disposed over the memory array. The first conductive lines each extend along an individual column in the memory array and are each coupled to the resistive switching cells in the individual column. The second conductive lines each extend along an individual row in the memory array and are each coupled to the resistive switching elements in the individual row. To select an individual resistive switching cell (e.g., to read/write/erase the cell), a first bias is applied to a first conductive line coupled to the individual resistive switching cell, while a second bias is applied to a second conductive line coupled to the individual resistive switching cell. To improve the sensing margin (e.g., the difference in current between read state “1” and read state “0”), partial biasing schemes (e.g., $\frac{1}{2}$ bias and $\frac{1}{3}$ bias schemes) are utilized by applying a partial bias to unselected first conductive lines and unselected second conductive lines.

One challenge with next generation memory is the unintentional activation of unselected resistive switching cells. Due to sneak current and/or the partial biasing of unselected cells, an unselected cell may be exposed to a bias that is sufficient to activate the unselected cell. Accordingly, to prevent the unintentional selection of unselected devices, select devices may be coupled to resistive switching cells (e.g., to obtain a more nonlinear I-V characteristic of the resistive switching cell). In various instances, the select devices comprise an ovonic threshold switching (OTS) layer. The OTS layer is formed in an amorphous state and is configured to switch between a high resistance state and a

low resistance state depending on whether a bias applied across the select device exceeds a threshold bias.

One challenge with utilizing an OTS layer in a select device is integrating the formation of the OTS layer in typical back-end-of-line (BEOL) fabrication. During BEOL fabrication, an interconnect structure comprising the select devices may be formed over a semiconductor substrate. To form the interconnect structure, the semiconductor substrate is exposed to a relatively high BEOL fabrication temperature (e.g., about 300° C. or about 400° C.). However, the BEOL fabrication temperature may be greater than the crystallization temperature of the OTS layer (e.g., the temperature at which the OTS layer crystallizes). If the OTS layer crystallizes, the OTS layer may be formed having a low resistance state and the select device may not prevent unintentional activation of unselected cells.

Various embodiments of the present disclosure are directed toward a semiconductor device having a buffer structure disposed between a first amorphous switching structure and a second amorphous switching structure to increase the crystallization temperature of the first and second amorphous switching structures. In various embodiments, a first amorphous switching structure is arranged over a first electrode. A buffer structure is arranged over the first amorphous switching structure. A second amorphous switching structure is arranged over the buffer structure. A second electrode is arranged over the second amorphous switching structure. The first and second amorphous switching structures are configured to switch between low resistance states and high resistance states depending on whether a voltage from the first electrode to the second electrode exceeds a threshold voltage.

The buffer structure reduces the individual thicknesses of the first amorphous switching structure and the second amorphous switching structure. By reducing the individual thicknesses, respective crystallization temperatures of the first amorphous switching structure and the second amorphous switching structure are increased. Thus, the first amorphous switching structure and the second amorphous switching structure may have a crystallization temperature that is greater than the BEOL fabrication temperature. Accordingly, the first amorphous switching structure and the second amorphous switching structure may be integrated into an interconnect structure formed during BEOL fabrication.

FIGS. 1A-1B illustrate various views of some embodiments of a memory device **100** having a plurality of semiconductor devices each having a buffer structure disposed between a first amorphous switching structure and a second amorphous switching structure. FIG. 1A illustrates a perspective view of some embodiments of the memory device **100**. FIG. 1B illustrates a cross-sectional view of some embodiments of a region of the memory device **100** taken along line A-A' of FIG. 1A.

The memory device **100** comprises a plurality of first conductive lines **102**. The first conductive lines **102** each extend laterally in a first direction. In various embodiments, the first conductive lines **102** are arranged in parallel with one another. In some embodiments, the plurality of first conductive lines **102** may comprise, for example, copper, aluminum, tungsten, some other suitable conductor, or a combination of the foregoing.

A plurality of second conductive lines **104** are arranged over the plurality of first conductive lines **102**. The second conductive lines **104** each extend laterally in a second direction transverse the first direction. In various embodiments, the second conductive lines **104** are arranged in

parallel with one another. In some embodiments, the plurality of second conductive lines **104** may comprise, for example, copper, aluminum, tungsten, some other suitable conductor, or a combination of the foregoing.

A plurality of one selector-one memory cell (1S1MC) stacks **106** are disposed between the plurality of first conductive lines **102** and the plurality of second conductive lines **104**. In various embodiments, the 1S1MC stacks **106** are arranged in an array having a plurality of rows **108a-c** and a plurality of columns **110a-c**. In some embodiments, an individual first conductive line **102** and an individual second conductive line **104** are coupled to each individual 1S1MC stack **106**. In further embodiments, respective first conductive lines **102** are coupled to respective columns **110a-110c** of 1S1MC stacks **106**. In yet further embodiments, respective second conductive lines **104** are coupled to respective rows **108a-108c** of 1S1MC stacks **106**.

Each 1S1MC stack **106** comprises a memory cell **112** separated from a threshold selector **114** by an electrode **116**. In various embodiments, the electrode **116** is a common electrode directly contacting the memory cell **112** and the threshold selector **114**. In some embodiments, the electrode **116** may comprise, for example, doped polysilicon, copper, aluminum, tungsten, some other suitable conductor, or a combination of the foregoing.

The memory cell **112** is configured to store data and may be a non-volatile memory cell or a volatile memory cell. In some embodiments, the memory cell **112** may be a resistive switching memory cell (e.g., resistive random-access memory (RRAM) cell, phase-change random-access memory (PCRAM) cell, conductive-bridging random-access memory (CBRAM) cell, etc.) configured to store data based on a resistive state of a data storage structure. For example, the data storage structure may have a high resistance state associated with a first data state (e.g., binary "0") or a low resistance state associated with a second data state (e.g., binary "1"). In some embodiments, the data storage structure may comprise, for example, a chalcogenide, an oxide, a nitride, a high-k dielectric, or some other suitable dielectric. In further embodiments, the memory cell may be a magnetoresistive random-access memory (MRAM) cell. In such an embodiment, the data storage structure may comprise a magnetic tunnel junction (MTJ) configured to store data based on a magnetic orientation of the MTJ.

The threshold selector **114** comprises a first amorphous switching structure **120** separated from a second amorphous switching structure **122** by a first buffer structure **124**. The threshold selector **114** is configured to switch between a low resistance state and a high resistance state depending on whether a voltage applied across the threshold selector **114** is greater than a threshold voltage. For example, the threshold selector **114** may have a high resistance state if a voltage across the threshold selector **114** is less than the threshold voltage, and the threshold selector **114** may have a low resistance state if a voltage across the threshold selector **114** is greater than the threshold voltage.

In various embodiments, the first buffer structure **124** contacts both the first amorphous switching structure **120** and the second amorphous switching structure **122**. In some embodiments, the first buffer structure **124** may comprise an amorphous solid. In further embodiments, the first buffer structure **124** may comprise, for example, amorphous silicon (a-Si), amorphous germanium (a-Ge), amorphous silicon germanium (a-SiGe), an amorphous carbon nitride compound (a-CN_x), amorphous carbon (a-C), boron-doped carbon, a silicon oxide compound (SiO_x), or an aluminum oxide compound (AlO_x). In yet further embodiments, the

first buffer structure **124** may not comprise a chalcogenide (e.g., generally a chemical compound comprising a Group 16 element other than oxygen). In some embodiments, the first buffer structure **124** may have a thickness between about 0.5 nanometer (nm) and about 5 nm. In further embodiments, if the first buffer structure **124** comprises an insulator, the first buffer structure **124** may have a thickness less than about 1 nm, such that the first buffer structure **124** does not negatively affect the electrical properties (e.g., current) of the threshold selector **114**.

The first amorphous switching structure **120** and the second amorphous switching structure **122** are configured to switch between low resistance states and high resistance states depending on whether a voltage applied across the threshold selector **114** exceeds a threshold voltage. For example, the first amorphous switching structure **120** may have a high resistance state if a voltage across the first amorphous switching structure **120** is less than the threshold voltage, and the first amorphous switching structure **120** may have a low resistance state if a voltage across the first amorphous switching structure **120** is greater than the threshold voltage. In various embodiments, the first amorphous switching structure **120** may contact the first buffer structure **124** and the electrode **116**. In some embodiments, the second amorphous switching structure **122** may contact the first buffer structure **124** and an individual first conductive line **102**. In further embodiments, the first amorphous switching structure **120** and the second amorphous switching structure **122** comprise a chalcogenide (e.g., generally a chemical compound comprising a Group 16 element other than oxygen). In yet further embodiments, the first amorphous switching structure **120** and the second amorphous switching structure **122** may comprise, for example, tellurium (Te), selenium (Se), sulfur (S), polonium (Po), in combination with, for example, germanium (Ge), silicon (Si), gallium (Ga), indium (In), phosphorus (P), boron (B), carbon (C), nitrogen (N), oxygen (O), etc.

In some embodiments, the first amorphous switching structure **120** and the second amorphous switching structure **122** may have a thickness between about 2 nm and about 10 nm. The ability of the threshold selector **114** to prevent leakage current in its high resistance state and the threshold voltage of the threshold selector **114** are related to an overall thickness of the first amorphous switching structure **120** and the second amorphous switching structure **122** (e.g., a combined thickness of the first amorphous switching structure **120** and the second amorphous switching structure **122**). For example, if the overall thickness is less than a minimum thickness (e.g., about 10 nm), leakage current may be high. On the other hand, if the overall thickness exceeds a maximum thickness (e.g., about 30 nm), the threshold voltage may be too high (e.g., outside a range of operating voltages in a typical integrated chip (IC)).

Further, the crystallization temperature of the first amorphous switching structure **120** and the second amorphous switching structure **122** is related to their respective thicknesses. For example, as a thickness of the first amorphous switching structure **120** or the second amorphous switching structure **122** increases, their respective crystallization temperatures decrease. In some embodiments, the crystallization temperature of the first amorphous switching structure **120** and the second amorphous switching structure **122** is great than about 300° C. In further embodiments, the crystallization temperature of the first amorphous switching structure **120** and the second amorphous switching structure **122** is great than about 400° C.

As discussed above, a threshold selector typically has a single amorphous switching structure. For the threshold selector to prevent leakage current in its high resistance state, the amorphous switching structure generally has a thickness that causes the crystallization temperature of the amorphous switching structure to be less than a back-end-of-line (BEOL) fabrication temperature (e.g., about 300° C. or about 400° C.). Because the crystallization temperature is below the BEOL fabrication temperature, the amorphous switching structure may crystallize. If the amorphous switching structure crystallizes during BEOL fabrication, the amorphous switching structure may be formed having a low resistance state and the threshold selector may not prevent leakage current. Thus, the threshold selector may not prevent unintentional activation of unselected cells.

By inserting the first buffer structure **124** between the first amorphous switching structure **120** and the second amorphous switching structure **122**, the respective thicknesses of the first amorphous switching structure **120** and the second amorphous switching structure **122** may effectively be reduced. Therefore, the overall thickness of the first amorphous switching structure **120** and the second amorphous switching structure **122** may be increased (e.g., to prevent leakage current) without decreasing the crystallization temperatures of the first amorphous switching structure **120** and the second amorphous switching structure **122**. Thus, the first amorphous switching structure **120** and the second amorphous switching structure **122** may have a crystallization temperature greater than the BEOL fabrication temperature. Because the first amorphous switching structure **120** and the second amorphous switching structure **122** may have a crystallization temperature greater than the BEOL fabrication temperature, the first amorphous switching structure **120** or the second amorphous switching structure **122** may not crystallize during BEOL fabrication. Accordingly, the threshold selector **114** may be formed during BEOL fabrication while ensuring the threshold selector **114** have desirable electrical properties (e.g., prevent leakage current and/or have a functional threshold voltage).

FIGS. 2A-2B illustrate various views of some alternative embodiments of the memory device **100** of FIG. 1 in which the threshold selector **114** has additional buffer structures and an additional amorphous switching structure. FIG. 2A illustrates a perspective view of some embodiments of the memory device **100**. FIG. 2B illustrates a cross-sectional view of some embodiments of a region of the memory device **100** taken along line A-A' of FIG. 2A.

As shown in FIGS. 2A-2B, a second buffer structure **202** is disposed between the first amorphous switching structure **120** and the electrode **116**. In various embodiments, the second buffer structure **202** directly contacts both the first amorphous switching structure **120** and the electrode **116**. In some embodiments, the second buffer structure **202** comprises the same material as the first buffer structure **124**. In other embodiments, the second buffer structure **202** comprises a different material than the first buffer structure **124**. In further embodiments, the second buffer structure **202** may comprise an amorphous solid. In yet further embodiments, the second buffer structure **202** is configured to minimize nucleation sites for the first amorphous switching structure **120** due to the electrode **116** being a crystalline metal, which may act as a crystalline promoter for the first amorphous switching structure **120** during subsequent thermal process(es).

A third buffer structure **204** is disposed between the second amorphous switching structure **122** and a third amorphous switching structure **206**. In various embodi-

ments, the third buffer structure **204** directly contacts both the second amorphous switching structure **122** and the third amorphous switching structure **206**. In some embodiments, the third buffer structure **204** comprises the same material as the first buffer structure **124**. In other embodiments, the second buffer structure **202** comprises a different material than the first buffer structure **124**. In further embodiments, the third buffer structure **204** may comprise an amorphous solid.

In various embodiments, the third amorphous switching structure **206** is disposed between the third buffer structure **204** and a fourth buffer structure **208**. The third amorphous switching structure **206** is configured to switch between a low resistance state and a high resistance state depending on whether a voltage applied across the threshold selector **114** exceeds a threshold voltage. In various embodiments, the third amorphous switching structure **206** may directly contact the third buffer structure **204** and the fourth buffer structure **208**. In various embodiments, the third amorphous switching structure **206** may comprise the same material as the first amorphous switching structure **120** and/or the second amorphous switching structure **122**. In some embodiments, the third amorphous switching structure **206** may comprise a different material than the first amorphous switching structure **120** and/or the second amorphous switching structure **122**. In further embodiments, a crystallization temperature of the third amorphous switching structure **206** is great than about 300° C. In further embodiments, the crystallization temperature of the third amorphous switching structure **206** is great than about 400° C.

In various embodiments, the fourth buffer structure **208** is disposed between the third amorphous switching structure **206** and an individual first conductive line **102**. In various embodiments, the fourth buffer structure **208** directly contacts both the third amorphous switching structure **206** and the individual first conductive line **102**. In some embodiments, the fourth buffer structure **208** comprises the same material as the second buffer structure **202**. In other embodiments, the fourth buffer structure **208** comprises a different material than the second buffer structure **202**. In further embodiments, the fourth buffer structure **208** may comprise an amorphous solid. In yet further embodiments, the fourth buffer structure **208** is configured to minimize nucleation sites for the third amorphous switching structure **206** due to the individual first conductive line **102** being a crystalline metal, which may act as a crystalline promoter for the third amorphous switching structure **206** during subsequent thermal process(es).

In various embodiments, the second buffer structure **202**, the third buffer structure **204**, and the fourth buffer structure **208** may comprise, for example, amorphous silicon (a-Si), amorphous germanium (a-Ge), amorphous silicon germanium (a-SiGe), an amorphous carbon nitride compound (a-CN_x), amorphous carbon (a-C), boron-doped carbon, a silicon oxide compound (SiO_x), an aluminum oxide compound (AlO_x). In yet further embodiments, the second buffer structure **202**, the third buffer structure **204**, and the fourth buffer structure **208** may not comprise a chalcogenide (e.g., generally a chemical compound comprising a Group 16 element other than oxygen).

In some embodiments, the second buffer structure **202**, the third buffer structure **204**, and the fourth buffer structure **208** may have respective thicknesses between about 0.5 nanometer (nm) and about 5 nm. In various embodiments, the first buffer structure, **124**, the second buffer structure **202**, the third buffer structure **204**, and the fourth buffer structure **208** may have respective thicknesses that are

substantially the same. In further embodiments, the first buffer structure **124** and the third buffer structure **204** may have respective thicknesses that are substantially the same, while the second buffer structure **202** and the fourth buffer structure **208** have respective thicknesses that are substantially the same but different than the respective thicknesses of the first buffer structure **124** and the third buffer structure **204**. In yet further embodiments, if the second buffer structure **202**, the third buffer structure **204**, or the fourth buffer structure **208** comprise an insulator, their respective thicknesses may be less than about 1 nm, such that the electrical properties (e.g., current) of the threshold selector is not adversely affected.

In various embodiments, the third amorphous switching structure **206** comprises a chalcogenide (e.g., generally a chemical compound comprising a Group 16 element other than oxygen). In some embodiments, the third amorphous switching structure may comprise, for example, tellurium (Te), selenium (Se), sulfur (S), polonium (Po), in combination with, for example, germanium (Ge), silicon (Si), gallium (Ga), indium (In), phosphorus (P), boron (B), carbon (C), nitrogen (N), oxygen (O), etc. In further embodiments, the third amorphous switching structure **206** may have a thickness between about 2 nm and about 10 nm. In yet further embodiments, the first amorphous switching structure **120**, the second amorphous switching structure **122**, and the third amorphous switching structure **206** have respective thicknesses that are substantially the same.

FIG. 3 illustrates a cross-sectional view of some embodiments of an integrated chip (IC) **300** comprising a memory device **100** having a plurality of semiconductor devices each having a plurality of buffer structures and a plurality of amorphous switching structures.

The IC **300** comprises a metal-oxide-semiconductor field-effect transistor (MOSFET) **302** disposed on a semiconductor substrate **304**. The MOSFET **302** comprises a pair of source/drain regions **306** disposed in the semiconductor substrate **304** and laterally spaced. A gate dielectric **308** is disposed over the semiconductor substrate **304** between the individual source/drain regions **306**, and a gate electrode **310** is disposed over the gate dielectric **308**.

An interlayer dielectric (ILD) layer **312** is disposed over the MOSFET **302** and the semiconductor substrate **304**. The ILD layer **312** comprises one or more ILD materials. In some embodiments, the ILD layer **312** may comprise one or more of a low-k dielectric layer (e.g., a dielectric with a dielectric constant less than about 3.9), an ultra-low-k dielectric layer, or an oxide (e.g., silicon oxide). Conductive contacts **314** are arranged within the ILD layer **312**. The conductive contacts **314** extend through the ILD layer **312** to the gate electrode **310** and the pair of source/drain regions **306**. In various embodiments, the conductive contacts **314** may comprise, for example, copper, tungsten, or some other conductive material.

An interconnect structure **316** is disposed over the ILD layer **312**. The interconnect structure **316** comprises a plurality of inter-metal dielectric (IMD) layers **318**. A plurality of conductive wires **320** and a plurality of conductive vias **322** are disposed within the IMD layers **318**. The conductive wires **320** and conductive vias **322** are configured to provide electrical connections between various devices disposed throughout the IC **300**. In some embodiments, the IMD layer **318** may comprise a low-k dielectric layer, an ultra-low-k dielectric layer, or an oxide. In various embodiments, the conductive wires **320** and conductive vias **322** may comprise, for example, copper, aluminum, or some other conductive material.

In various embodiments, the memory device **100** is disposed within the interconnect structure **316**. In some embodiments, the memory device **100** is disposed within one of the IMD layers **318**. In further embodiments, the memory device **100** may be disposed within multiple IMD layers **318**. In such an embodiment, the memory device **100** may comprise multiple layers each comprising a plurality of one selector-one memory cell (1S1MC) stacks **106**.

In some embodiment, each of the first conductive lines **102** are electrically coupled to an individual MOSFET **302** (e.g., to a source/drain region **306** of each MOSFET **302**) via conductive wires **320** and conductive vias **322** that are disposed beneath the memory device **100**. In various embodiments, a conductive via **322** and a conductive wire **320** disposed over the memory device **100** are coupled to each of the second conductive lines **104**. In further embodiments, the conductive vias **322** and the conductive wires **320** that are coupled to the plurality of second conductive lines **104** may be electrically coupled to other individual MOSFETs **302** (not shown) (e.g., to a source/drain region **306** of the other MOSFET **302**).

FIGS. 4-14 illustrate a series of cross-sectional views of some embodiments for forming an integrated chip (IC) comprising a memory device having a plurality of semiconductor devices each having a plurality of buffer structures and a plurality of amorphous switching structures.

As illustrated by FIG. 4, a gate dielectric layer **402** and a conductive layer **404** are formed over a semiconductor substrate **304**, such that the gate dielectric layer **402** separates the conductive layer **404** from the semiconductor substrate **304**. In some embodiments, the gate dielectric layer **402** may be silicon dioxide, a high-k dielectric, or some other dielectric. In further embodiments, the conductive layer **404** may be doped polysilicon, metal, or some other conductor. In yet further embodiments, the semiconductor substrate **304** may comprise any type of semiconductor body (e.g., monocrystalline silicon/CMOS bulk, silicon-germanium (SiGe), silicon on insulator (SOI), etc.).

In some embodiments, a process for forming the gate dielectric layer **402** and the conductive layer **404** comprises depositing or growing the gate dielectric layer **402** on the semiconductor substrate **304**, and subsequently depositing or growing the conductive layer **404** on the gate dielectric layer **402**. In further embodiments, the gate dielectric layer **402** may be deposited or grown by thermal oxidation, chemical vapor deposition (CVD), physical vapor deposition (PVD), atomic layer deposition (ALD), sputtering, or some other deposition or growth process. In yet further embodiments, the conductive layer **404** may be deposited or grown by CVD, PVD, ALD, sputtering, electrochemical plating, electroless plating, or some other deposition or growth process.

As shown in FIG. 5, the conductive layer **404** and the gate dielectric layer **402** are patterned into a plurality of gate electrodes **310** and a plurality of gate dielectrics **308**. In some embodiments, a process for patterning the conductive layer **404** and the gate dielectric layer **402** comprises forming a masking layer (not shown) on the conductive layer **404**. In various embodiments, the masking layer may be formed by a spin on process and patterned using photolithography. In further embodiments, the process comprises performing an etch into the conductive layer **404** and the gate dielectric layer **402** with the patterned masking layer in place, and subsequently stripping the patterned masking layer.

As shown in FIG. 6, pairs of source/drain regions **306** are formed within the semiconductor substrate **304** on opposing

sides of the gate electrodes **310**. In various embodiments, the pairs of source/drain regions **306** comprise a different doping type than adjoining regions of the semiconductor substrate **304**. In some embodiments, the pairs of source/drain regions **306** may be formed by an ion implantation process and may utilize a masking layer (not shown) to selectively implant ions into the semiconductor substrate **304**. In further embodiments, forming the pairs of source/drain regions **306** may be a self-aligned process that utilizes the gate electrodes **310** as a masking layer.

As shown in FIG. 7, an interlayer dielectric (ILD) layer **312** is formed over the semiconductor substrate **304**. In some embodiments, the ILD layer **312** may be formed by CVD, PVD, ALD, or some other deposition or growth process. In further embodiments, a planarization process (e.g., a chemical-mechanical planarization (CMP)) may be performed on the ILD layer **312** to form a substantially planar upper surface.

Also shown in FIG. 7, conductive contacts **314** are formed extending through the ILD layer **312** to the source/drain regions **306** and the gate electrodes **310**. In some embodiments, a process for forming the conductive contacts **314** comprises performing an etch into the ILD layer **312** to form contact openings that correspond to the conductive contacts **314**. In some embodiments, the etch may be performed with a patterned masking layer formed over the ILD layer **312**. In further embodiments, the process comprises filling the contact openings with a conductive material. In yet further embodiments, the contact openings may be filled by depositing or growing a conductive layer covering the ILD layer **312** that fills the contact openings, and subsequently performing a planarization (e.g., CMP) on the ILD layer **312**. In various embodiments, the process may be part of a single damascene like process or a dual damascene like process.

As shown in FIG. 8, a lower group of IMD layers **318** are formed over the ILD layer **312**. In some embodiments, an individual IMD layer **318** may be formed by CVD, PVD, ALD, or some other deposition or growth process. In further embodiments, a planarization process (e.g., CMP) may be performed on the individual IMD layer **318** to form substantially planar upper surfaces. This process may be repeated multiple time to form each IMD layer **318** of the lower group of IMD layers **318**.

Also shown in FIG. 8, a plurality of conductive wires **320** and a plurality of conductive vias **322** are formed within the IMD layers **318**. In some embodiments, a process for forming the conductive wires **320** and the conductive vias **322** in an individual IMD layer **318** comprises performing an etch into the individual IMD layer **318** to form via openings and conductive wire openings that respectively correspond to the conductive vias **322** and the conductive wires **320**. In some embodiments, the etch may be performed with a patterned masking layer formed over the individual IMD layer **318**. In further embodiments, the process comprises filling the openings with a conductive material. In yet further embodiments, the openings may be filled by depositing or growing a conductive layer covering the individual IMD layer **318** that fills the openings, and subsequently performing a planarization (e.g., CMP) on the individual IMD layer **318**. This process may be repeated multiple time to form the plurality of conductive wires **320** and plurality of conductive vias **322** in each of the IMD layer **318** of the lower group of IMD layers **318**.

As shown in FIG. 9, a first conductive layer **902** is formed over the lower group of IMD layers **318**. A first buffer layer **904** is formed over the first conductive layer **902**. A first amorphous switching layer **906** is formed over the first

11

buffer layer **904**. A second buffer layer **908** is formed over the first amorphous switching layer **906**. A second amorphous switching layer **910** is formed over the second buffer layer **908**. A third buffer layer **912** is formed over the second amorphous switching layer **910**. A third amorphous switching layer **914** is formed over the third buffer layer **912**. A fourth buffer layer **916** is formed over the third amorphous switching layer **914**. A second conductive layer **918** is formed over the fourth buffer layer **916**. A data storage layer **920** is formed over the second conductive layer **918**.

In some embodiments, a process for forming the first conductive layer **902**, the first buffer layer **904**, the first amorphous switching layer **906**, the second buffer layer **908**, the second amorphous switching layer **910**, the third buffer layer **912**, the third amorphous switching layer **914**, the fourth buffer layer **916**, the second conductive layer **918**, and the data storage layer **920** comprises depositing or growing the respective layers over one another by, for example, CVD, PVD, ALD, sputtering, electrochemical plating, electroless plating, or some other deposition or growth process.

In various embodiments, the first conductive layer **902** and the second conductive layer **918** may comprise, for example, copper, aluminum, tungsten, some other suitable conductor, or a combination of the foregoing. In some embodiments, the data storage layer **920** may comprise, for example, a chalcogenide, an oxide, a nitride, a high-k dielectric, or some other suitable dielectric. In further embodiments, the first amorphous switching layer **906**, the second amorphous switching layer **910**, and the third amorphous switching layer **914** may comprise a chalcogenide. More specifically, the first amorphous switching layer **906**, the second amorphous switching layer **910**, and the third amorphous switching layer **914** may comprise, for example, tellurium (Te), selenium (Se), sulfur (S), polonium (Po), in combination with, for example, germanium (Ge), silicon (Si), gallium (Ga), indium (In), phosphorus (P), boron (B), carbon (C), nitrogen (N), oxygen (O), etc. In yet further embodiments, the first buffer layer **904**, the second buffer layer **908**, the third buffer layer **912**, and the fourth buffer layer **916** may not comprise a chalcogenide. More specifically, the first buffer layer **904**, the second buffer layer **908**, the third buffer layer **912**, and the fourth buffer layer **916** may comprise, for example, amorphous silicon (a-Si), amorphous germanium (a-Ge), amorphous silicon germanium (a-SiGe), an amorphous carbon nitride compound (a-CN_x), amorphous carbon (a-C), boron-doped carbon, a silicon oxide compound (SiO_x), an aluminum oxide compound (AlO_x).

As shown in FIG. 10, a plurality of patterned line structures **1002a-c** are respectively formed over a plurality of first conductive lines **102**. While not visible within the cross-sectional view of FIG. 10, the patterned line structures **1002a-c** are elongated/line shaped along axes extending into and out of the page. The first conductive lines **102** respectively separate the patterned line structures **1002a-1002c** from the lower group of IMD layers **318**. In various embodiments, the first conductive lines **102** and the patterned line structures **1002a-c** extend continuously in a first direction. In some embodiments, the first conductive lines **102** and the patterned line structures **1002a-c** respectively extend in substantially straight lines parallel to one another in the first direction.

In some embodiments, a process for forming the patterned line structures **1002a-c** and the first conductive lines **102** comprises forming a masking layer (not shown) on the data storage layer **920**. In further embodiments, the process comprises performing an etch into the data storage layer

12

920, the second conductive layer **918**, the fourth buffer layer **916**, the third amorphous switching layer **914**, the third buffer layer **912**, the second amorphous switching layer **910**, the second buffer layer **908**, the first amorphous switching layer **906**, the first buffer layer **904**, and the first conductive layer **902** with the patterned masking layer in place, and subsequently stripping the patterned masking layer. In further embodiments, a single etch is performed to form the patterned line structures **1002a-c** and the first conductive lines **102**. In other embodiments, multiples etches are performed to form the patterned line structures **1002a-c** and the first conductive lines **102**.

As shown in FIG. 11, an intermediate IMD layer **318** is formed over the patterned line structures **1002a-c** and the lower group of IMD layers **318**. In some embodiments, the intermediate IMD layer **318** may be formed by CVD, PVD, sputtering, or some other deposition or growth process. In further embodiments, planarization processes (e.g., CMP) may be performed on the intermediate IMD layer **318** to form substantially planar upper surfaces.

As shown in FIG. 12, a third conductive layer **1202** is formed over the patterned line structures **1002a-c** and the intermediate IMD layer **318**. In some embodiments, a process for forming the third conductive layer **1202** may comprise depositing the third conductive layer **1202** by, for example, CVD, PVD, ALD, sputtering, electrochemical plating, electroless plating, or some other deposition or growth process. In various embodiments, the third conductive layer may comprise, for example, copper, aluminum, tungsten, some other suitable conductor, or a combination of the foregoing.

As shown in FIG. 13, a plurality of second conductive lines **104** are formed over a plurality of one selector-one memory cell (1S1MC) stacks **106**. Note that only one of the second conductive lines **104** is visible within the cross-sectional view of FIG. 13. In various embodiments, the second conductive lines **104** respectively extend in a second direction transverse the first direction. In some embodiments, the 1S1MC stacks **106** are formed as discrete structures that are arranged in a plurality of rows and columns. In further embodiments, the 1S1MC stacks **106** respectively extend between the second conductive lines **104** and the first conductive lines **102** at a plurality of points in which the second conductive lines **104** and the first conductive lines **102** overlap one another in a vertical direction.

In some embodiments, a process for forming the 1S1MC stacks **106** and the second conductive lines **104** comprises forming a masking layer (not shown) on the third conductive layer **1202**. In further embodiments, the process comprises performing an etch into the third conductive layer **1202**, the patterned line structures **1002a-c**, and the intermediate IMD layer **318** with the patterned masking layer in place, and subsequently stripping the patterned masking layer. In further embodiments, a single etch is performed to form the 1S1MC stacks **106** and second conductive lines **104**. In other embodiments, multiple etches are performed to form the 1S1MC stacks **106** and the second conductive lines **104**.

As shown in FIG. 14, an upper IMD layer **318** is formed over the 1S1MC stacks **106** and the second conductive lines **104**. In some embodiments, the upper IMD layer **318** is part of an upper group of IMD layers **318** comprising a plurality of IMD layers **318**. In some embodiments, the upper IMD layer **318** may be formed by CVD, PVD, ALD, or some other deposition or growth process. In further embodiments, a planarization process (e.g., CMP) may be performed on the upper IMD layer **318** to form substantially planar upper surfaces. In further embodiments, formation of the upper

13

IMD layer **318** fills openings between the 1S1MC stacks **106** formed during formation of the second conductive lines **104** and 1S1MC stacks **106**, such that the 1S1MC stacks **106** are separated from one another by an IMD layer **318**.

Also shown in FIG. **14**, a plurality of conductive wires **320** and a plurality of conductive vias **322** are formed within the upper IMD layer **318**. In some embodiments, a process for forming the conductive wires **320** and the conductive vias **322** in the upper IMD layer **318** comprises performing an etch into the upper IMD layer **318** to form via openings and conductive wire openings that respectively correspond to the conductive vias **322** and the conductive wires **320**. In some embodiments, the etch may be performed with a patterned masking layer formed over the upper IMD layer **318**. In further embodiments, the process comprises filling the openings with a conductive material. In yet further embodiments, the openings may be filled by depositing or growing a conductive layer covering the upper IMD layer **318** that fills the openings, and subsequently performing a planarization (e.g., CMP) on the upper IMD layer **318**.

The upper IMD layer **318** is formed with a fabrication temperature that is less than the crystallization temperature of the amorphous switching structures (e.g., the crystallization temperature of the first amorphous switching structure **120**, the second amorphous switching structure **122**, and/or the third amorphous switching structure **206**). If the crystallization temperatures of the amorphous switching structures were less than the fabrication temperature, the amorphous switching structures may crystallize, and thus have a low resistance state. Because the buffer structures (e.g., the first buffer structure **124**, the second buffer structure **202**, the third buffer structure **204**, and/or the fourth buffer structure **208**) reduce the individual thicknesses of the amorphous switching structures, the crystallization temperatures of the amorphous switching structures may be greater than the fabrication temperature. By utilizing amorphous switching structures and buffer structures in the threshold selector **114**, a combined thickness of the amorphous switching structures is sufficient to minimize leakage current through the threshold selector **114** without reducing the crystallization temperatures of the amorphous switching structures below the fabrication temperature.

As illustrated in FIG. **15**, a flowchart **1500** of some embodiments of a method for forming an integrated chip (IC) comprising a memory device having a plurality of semiconductor devices each having a plurality of buffer structures and a plurality of amorphous switching structures is provided. While the flowchart **1500** of FIG. **15** is illustrated and described herein as a series of acts or events, it will be appreciated that the illustrated ordering of such acts or events is not to be interpreted in a limiting sense. For example, some acts may occur in different orders and/or concurrently with other acts or events apart from those illustrated and/or described herein. Further, not all illustrated acts may be required to implement one or more aspects or embodiments of the description herein, and one or more of the acts depicted herein may be carried out in one or more separate acts and/or phases.

At **1502**, an interlayer dielectric (ILD) layer is formed over a semiconductor device, where the semiconductor device is disposed on a semiconductor substrate. FIGS. **4-7** illustrate cross-sectional views of some embodiments corresponding to act **1502**.

At **1504**, a first inter-metal dielectric (IMD) layer is formed over the ILD layer. FIG. **8** illustrates a cross-sectional view of some embodiments corresponding to act **1504**.

14

At **1506**, a first conductive layer is formed over the first IMD layer, a first amorphous switching layer is formed over the first conductive layer, a buffer layer is formed over the first amorphous switching layer, and a second amorphous switching layer is formed over the buffer layer. FIG. **9** illustrates a cross-sectional view of some embodiments corresponding to act **1506**.

At **1508**, the second amorphous switching layer, the buffer layer, the first amorphous switching layer, and the first conductive layer are patterned to form a plurality of patterned line structures respectively over a plurality of first conductive lines. FIG. **10** illustrates a cross-sectional view of some embodiments corresponding to act **1508**.

At **1510**, a second IMD layer is formed over the plurality of patterned line structures and the plurality of first conductive lines. FIG. **11** illustrates a cross-sectional view of some embodiments corresponding to act **1510**.

At **1512**, a second conductive layer is formed over the second IMD layer. FIG. **12** illustrates a cross-sectional view of some embodiments corresponding to act **1512**.

At **1514**, the second conductive layer, the second IMD layer, and the patterned line structures are patterned to form a plurality of second conductive lines over a plurality of one selector-one memory cell (1S1MC) stacks, where the plurality of 1S1MC stacks extend between the plurality of first conductive lines and the plurality of second conductive lines. FIG. **13** illustrates a cross-sectional view of some embodiments corresponding to act **1514**.

At **1516**, a third IMD layer is formed over the plurality of second conductive lines and the plurality of 1S1MC stacks. FIG. **14** illustrates a cross-sectional view of some embodiments corresponding to act **1516**.

In some embodiments, the present application provides a semiconductor device. The semiconductor device includes a first amorphous switching layer disposed over a first electrode. A first buffer structure is disposed over the first amorphous switching structure. A second amorphous switching structure is disposed over the first buffer structure. A second electrode is disposed over the second amorphous switching structure, where the first and second amorphous switching structures are configured to switch between low resistance states and high resistance states depending on whether a voltage from the first electrode to the second electrode exceeds a threshold voltage.

In other embodiments, the present application provides an integrated chip (IC). The IC includes a semiconductor device disposed on a semiconductor substrate. An interlayer dielectric (ILD) layer is disposed over the semiconductor substrate and the semiconductor device, where a contact via extends through the ILD layer to the semiconductor device. A threshold selector and a memory cell are stacked over the ILD layer, where the threshold selector includes a first amorphous switching structure separated from a second amorphous switching structure by a buffer structure.

In yet other embodiments, the present application provides a method for forming a semiconductor device. The method includes forming an interlayer dielectric (ILD) layer over a semiconductor substrate. A first conductive layer is formed over the ILD layer. A first amorphous switching layer is formed over the first conductive layer. A buffer layer is formed over the first amorphous switching layer. A second amorphous switching layer is formed over the buffer layer. The first amorphous switching layer, the second amorphous switching layer, and the buffer layer are etched to form a plurality of threshold selectors, where the plurality of threshold selectors are disposed in an array and each threshold selector of the plurality of threshold selectors comprises a

15

first amorphous switching structure separated from a second amorphous switching structure by a buffer structure.

The foregoing outlines features of several embodiments so that those skilled in the art may better understand the aspects of the present disclosure. Those skilled in the art should appreciate that they may readily use the present disclosure as a basis for designing or modifying other processes and structures for carrying out the same purposes and/or achieving the same advantages of the embodiments introduced herein. Those skilled in the art should also realize that such equivalent constructions do not depart from the spirit and scope of the present disclosure, and that they may make various changes, substitutions, and alterations herein without departing from the spirit and scope of the present disclosure.

What is claimed is:

1. A selector device, comprising:
 - a plurality of amorphous switching structures disposed between a first electrode and a second electrode, wherein the amorphous switching structures are configured to switch between low resistance states and high resistance states based on a voltage between the first electrode and the second electrode; and
 - a plurality of buffer structures disposed between the first electrode and the second electrode, wherein the buffer structures and the amorphous switching structures are alternately stacked between the first electrode and the second electrode, wherein there are more of the buffer structures than the amorphous switching structures disposed between the first electrode and the second electrode, and wherein each of the buffer structures are a same amorphous solid material.
2. The selector device of claim 1, wherein the plurality of buffer structures comprises greater than or equal to three buffer structures.
3. The selector device of claim 1, wherein:
 - each of the plurality of buffer structures have a first width and a first length;
 - each of the plurality of amorphous switching structures have a second width and a second length;
 - the first width is substantially the same as the second width; and
 - the first length is substantially the same as the second length.
4. The selector device of claim 1, further comprising:
 - a conductive line disposed over both the first electrode and the second electrode; and
 - a memory cell disposed between the conductive line and the second electrode, wherein both the memory cell and the selector device contact the first electrode.
5. The selector device of claim 1, wherein each of the amorphous switching structures are spaced further away from the second electrode than a first buffer structure of the plurality of buffer structures.
6. The selector device of claim 1, wherein each of the amorphous switching structures are spaced further away from the first electrode than a second buffer structure of the plurality of buffer structures.
7. The selector device of claim 6, wherein each of the amorphous switching structures are spaced further away from the second electrode than a first buffer structure of the plurality of buffer structures.
8. The selector device of claim 1, wherein each of the plurality of amorphous switching structures comprises a chalcogenide.

16

9. The selector device of claim 8, wherein each of the plurality of amorphous switching structures have a first thickness between about 2 nanometers (nm) and about 10 nm.

10. The selector device of claim 9, wherein each of the plurality of buffer structures have a second thickness between about 0.5 nm and about 5 nm.

11. A semiconductor device, comprising:

a memory cell disposed over a semiconductor substrate; and

a threshold selector disposed over the semiconductor substrate and electrically coupled to the memory cell, wherein the threshold selector comprises:

a first amorphous switching structure disposed over a first electrode;

a second amorphous switching structure disposed over and spaced from the first amorphous switching structure; and

a first buffer structure disposed between the first amorphous switching structure and the first electrode, wherein the first buffer structure extends continuously from a surface of the first amorphous switching structure to a surface of the first electrode.

12. The semiconductor device of claim 11, wherein:

the first buffer structure has a first thickness;

the first amorphous switching structure has a second thickness;

the second amorphous switching structure has a third thickness; and

the first thickness is less than both the second thickness and the third thickness.

13. The semiconductor device of claim 11, further comprising:

a second buffer structure disposed between the first amorphous switching structure and the second amorphous switching structure.

14. The semiconductor device of claim 13, wherein:

the first buffer structure has a first sidewall;

the second buffer structure has a second sidewall;

the first amorphous switching structure has a third sidewall;

the second amorphous switching structure has a fourth sidewall; and

the first sidewall, the second sidewall, the third sidewall, and the fourth sidewall are substantially aligned with one another along a vertical axis.

15. The semiconductor device of claim 11, further comprising:

a dielectric layer disposed over the semiconductor substrate, wherein the first electrode is a first conductive line disposed in the dielectric layer.

16. The semiconductor device of claim 15, further comprising:

a second conductive line disposed over both the memory cell and the threshold selector, wherein:

the first conductive line extends in a first lateral direction;

the second conductive line extends in a second lateral direction perpendicular to the first lateral direction, such that a first portion of the second conductive line directly overlies a second portion of the first conductive line; and

the threshold selector and the memory cell collectively extend from the first portion of the first conductive line to the second portion of the second conductive line.

17

17. The semiconductor device of claim 16, further comprising:

a second electrode disposed between the memory cell and the threshold selector and disposed over the second amorphous switching structure.

18. An integrated chip, comprising:

a first conductive line disposed over a semiconductor substrate and extending in a first direction;

a second conductive line disposed over the first conductive line and extending in a second direction perpendicular to the first direction; and

a selector-memory cell stack disposed between the first conductive line and the second conductive line, wherein the selector-memory cell stack comprises:

a memory cell electrically coupled to the second conductive line;

an electrode disposed below and electrically coupled to the memory cell; and

a threshold selector disposed below the electrode, wherein the threshold selector is electrically coupled to both the electrode and the first conductive line, wherein the threshold selector comprises a plurality of amorphous switching structures and a plurality of buffer structures, wherein the buffer structures and

18

the amorphous switching structures are alternately stacked between the electrode and the first conductive line, wherein there are more of the buffer structures than the amorphous switching structures disposed between the electrode and the first conductive line, and wherein a first one of the buffer structures extends continuously from a surface of the electrode to a surface of a first one of the amorphous switching structures.

19. The integrated chip of claim 18, wherein: the plurality of buffer structures have first thicknesses, respectively;

the plurality of amorphous switching structures have second thicknesses, respectively; and

each of the first thicknesses is less than each of the second thicknesses.

20. The integrated chip of claim 18, wherein: a second one of the buffer structures extends continuously from a surface of the first conductive line to a surface of a second one of the amorphous switching structures; and

each of the buffer structures are a same amorphous solid material.

* * * * *