

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
20 November 2008 (20.11.2008)

PCT

(10) International Publication Number
WO 2008/139140 A1

(51) International Patent Classification:
C09K 8/467 (2006.01) **C04B 20/00** (2006.01)
C04B 14/06 (2006.01)

Lane, Duncan, OK 73533 (US). **CROMWELL, Roger, S.**
[US/US]; 128 East Nevada, Walters, OK 73572 (US).

(21) International Application Number:
PCT/GB2008/001524

(74) Agents: **CURTIS, Philip, Anthony** et al.; A A Thornton
& Co, 235 High Holborn, London WC1V 7LE (GB).

(22) International Filing Date: 1 May 2008 (01.05.2008)

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
11/747,002 10 May 2007 (10.05.2007) US

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): **HAL-LIBURTON ENERGY SERVICES, INC.** [US/US]; PO Box 1431, Duncan, OK 73533 (US).

(71) Applicant (*for MW only*): **CURTIS, Philip, Anthony** [GB/GB]; A A Thornton & Co, 235 High Holborn, London WC1V 7LE (GB).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **RODDY, Craig, W.** [US/US]; 2906 Timber Ridge Drive, Duncan, OK 73533 (US). **CHATTERJI, Jiten** [IN/US]; 2213 Scott

Published:

— with international search report

(54) Title: WELL TREATMENT COMPOSITIONS AND METHODS UTILIZING NANO-PARTICLES

(57) Abstract: Disclosed embodiments relate to well treatment fluids and methods that utilize nano-particles. Exemplary nano-particles are selected from the group consisting of particulate nano-silica, nano-alumina, nano-zinc oxide, nano-boron, nano-iron oxide, and combinations thereof. Embodiments also relate to methods of cementing that include the use of nano-particles. An exemplary method of cementing comprises introducing a cement composition into a subterranean formation, wherein the cement composition comprises cement, water and a particulate nano-silica. Embodiments also relate to use of nano-particles in drilling fluids, completion fluids, stimulation fluids, and well clean-up fluids.



WO 2008/139140 A1

WELL TREATMENT COMPOSITIONS AND METHODS UTILIZING NANO-PARTICLES

BACKGROUND

[0001] The present invention relates to well treatment compositions and methods utilizing nano-particles and, more particularly, to well cement compositions and methods utilizing particulate nano-silica.

[0002] In general, well treatments include a wide variety of methods that may be performed in oil, gas, geothermal and/or water wells, such as drilling, completion and workover methods. The drilling, completion and workover methods may include, but are not limited to, drilling, fracturing, acidizing, logging, cementing, gravel packing, perforating and conformance methods. Many of these well treatments are designed to enhance and/or facilitate the recovery of desirable fluids from a subterranean well.

[0003] In cementing methods, such as well construction and remedial cementing, well cement compositions are commonly utilized. For example, in subterranean well construction, a pipe string (e.g., casing and liners) may be run into a well bore and cemented in place using a cement composition. The process of cementing the pipe string in place is commonly referred to as "primary cementing." In a typical primary cementing method, a cement composition may be pumped into an annulus between the walls of the well bore and the exterior surface of the pipe string disposed therein. The cement composition sets in the annular space, thereby forming an annular sheath of hardened, substantially impermeable cement that supports and positions the pipe string in the well bore and bonds the exterior surface of the pipe string to the subterranean formation. Among other things, the annular sheath of set cement surrounding the pipe string functions to prevent the migration of fluids in the annulus, as well as protecting the pipe string from corrosion. Cement compositions also may be used in remedial cementing methods, such as squeeze cementing and the placement of cement plugs.

[0004] In operation, the annular sheath of cement formed between the well bore and the pipe string often suffers structural failure due to pipe movements which cause shear stresses to be exerted on the set cement. Such stress conditions are commonly the result of relatively high fluid pressures and/or temperatures inside the cemented pipe string during

testing, perforating, fluid injection or fluid production. For example, such stress may occur in wells subjected to steam recovery or production of hot formation fluids from high-temperature formations. The high-internal pipe pressure and/or temperature can result in the expansion of the pipe string, both radially and longitudinally, which places stresses on the cement sheath causing the cement bond between the exterior surfaces of the pipe or the well bore walls, or both, to fail and thus allow leakage of formation fluids and so forth. Accordingly, it may be desirable for the cement composition utilized for cementing pipe strings in the well bores to develop high strength after setting and to have sufficient resiliency (e.g., elasticity and ductility) to resist loss of the cement bond between the exterior surfaces of the pipe or the well bore walls, or both. Also, it may be desirable for the cement composition to be able to resist cracking and/or shattering that may result from other forces on the cement sheath. For example, it may be desirable for the cement sheath to include structural characteristics that protect its structural integrity from forces associated with formation shifting, overburden pressure, subsidence, tectonic creep, pipe movements, impacts and shocks subsequently generated by drilling and other well operations.

[0005] In addition to including components that improve mechanical properties of the cement, in a number of cementing methods, it may also be desirable to include one or more set accelerators in the well cement compositions to counteract certain constituents and/or environmental characteristics that excessively slow set times. For example, among other things, low temperatures and cement additives (e.g., fluid loss control additives and dispersants) can cause or contribute to an excessive set time for a cement composition. Accordingly, in certain situations, it may be desirable to reduce the set time by including a set accelerator in the cement composition. That is, the set accelerator may be included in a cement composition to counteract components of the cement composition or conditions surrounding the cement composition that are causing an excessive set time.

SUMMARY

[0006] The present invention relates to well treatment compositions and methods utilizing nano-particles and, more particularly, to well cement compositions and methods utilizing particulate nano-silica.

[0007] An exemplary embodiment of the present invention provides a method of cementing. The method comprises introducing a cement composition into a subterranean formation, wherein the cement composition comprises cement, water and at least one nano-particle selected from the group consisting of particulate nano-silica, nano-alumina, nano-zinc oxide, nano-boron, nano-iron oxide and combinations thereof.

[0008] Another exemplary embodiment of the present invention provides a method of cementing in a subterranean formation. The method comprises including encapsulated nano-particles in a cement composition. The method further comprises introducing the cement composition into the subterranean formation.

[0009] Another exemplary embodiment of the present invention provides a method of accelerating set time of a cement composition. The method comprises including particulate nano-silica in a cement composition. The method further comprises introducing the cement composition into a subterranean formation. The method further comprises allowing the cement composition to set in the subterranean formation.

[0010] Another exemplary embodiment of the present invention provides a well cement composition. The well cement composition comprises cement, water and at least one nano-particle selected from the group consisting of particulate nano-silica, nano-alumina, nano-zinc oxide, nano-boron, nano-iron oxide and combinations thereof.

[0011] Another exemplary embodiment of the present invention provides a method of treating a subterranean formation. The method includes introducing a treatment fluid into a subterranean formation, wherein the treatment fluid comprises at least one nano-particle selected from the group consisting of particulate nano-silica, nano-alumina, nano-zinc oxide, nano-boron, nano-iron oxide, and combinations thereof.

[0012] Another exemplary embodiment of the present invention provides a method of using nano-particles in a well treatment fluid. The method comprises including encapsulated nano-particles in the well treatment fluid.

[0013] Another exemplary embodiment of the present invention provides a well treatment fluid. An embodiment of the well treatment fluid comprises at least one nano-particle selected from the group consisting of particulate nano-silica, nano-alumina, nano-zinc oxide, nano-boron, nano-iron oxide, and combinations thereof. Another embodiment of the well treatment fluid comprises encapsulated nano-particles.

[0014] The features and advantages of the present invention will be apparent to those skilled in the art upon reading the following description of specific embodiments.

DESCRIPTION OF SPECIFIC EMBODIMENTS

[0015] The present invention relates to well treatment compositions and methods utilizing nano-particles and, more particularly, to well cement compositions and methods utilizing particulate nano-silica.

[0016] An exemplary embodiment of the cement compositions of the present invention comprises cement, water and particulate nano-silica. Those of ordinary skill in the art will appreciate that the exemplary cement compositions generally should have a density suitable for a particular application. By way of example, the cement composition may have a density in the range of from about 4 pounds per gallon ("ppg") to about 20 ppg. In exemplary embodiments, the cement compositions may have a density in the range of from about 8 ppg to about 17 ppg. Exemplary embodiments of the cement compositions may be foamed or unfoamed or may comprise other means to reduce their densities, such as hollow microspheres, low-density elastic beads, or other density-reducing additives known in the art. Those of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate density for a particular application.

[0017] Exemplary embodiments of the cement compositions of the present invention comprise a cement. Any of a variety of cements suitable for use in subterranean cementing operations may be used in accordance with exemplary embodiments of the present invention. Suitable examples include hydraulic cements that comprise calcium, aluminum, silicon, oxygen and/or sulfur, which set and harden by reaction with water. Such hydraulic cements, include, but are not limited to, Portland cements, pozzolana cements, gypsum cements, high-alumina-content cements, slag cements, silica cements and combinations thereof. In certain embodiments, the hydraulic cement may comprise a Portland cement. The Portland cements that may be suited for use in exemplary embodiments of the present invention are classified as Class A, C, H and G cements according to American Petroleum Institute, *API Specification for Materials and Testing for Well Cements*, API Specification 10, Fifth Ed., July 1, 1990.

[0018] The water used in exemplary embodiments of the cement compositions of the present invention may be freshwater or saltwater (e.g., water containing one or more salts dissolved therein, seawater, brines, saturated saltwater, etc.). In general, the water may be

present in an amount sufficient to form a pumpable slurry. In exemplary embodiments, the water may be present in the cement compositions in an amount in the range of from about 33% to about 200% by weight of the cement on a dry basis ("bwoc"). In exemplary embodiments, the water may be present in an amount in the range of from about 35% to about 70% bwoc.

[0019] In addition, exemplary embodiments of the cement compositions comprise nano-silica. The nano-silica may be described as particulate nano-silica. That is, the nano-silica may be particulate in nature and not, for example, a colloidal silica or a suspension of silica in solution. Indeed, in one embodiment, the particulate nano-silica may be added to the cement composition as a dry nano-silica powder. Generally, the particulate nano-silica may be defined as nano-silica having a particle size of less than or equal to about 100 nm. For example, the particulate nano-silica may have a particle size in the range of from about 1 nm to about 100 nm (about 1×10^{-9} m to about 100×10^{-9} m). In certain exemplary embodiments, the particulate nano-silica may have a particle size of less than or equal to about 50 nm. For example, the particulate nano-silica may have a particle size in the range of from about 5 nm to about 50 nm. In further exemplary embodiments, the particulate nano-silica may have a particle size of less than or equal to about 30 nm. For example, the particulate nano-silica may have a particle size in the range of from about 5 nm to about 30 nm. However, it should be noted that the particulate nano-silica may be utilized in combination with differently sized silica particles in accordance with present embodiments. For example, a number of silica particles with particle sizes greater than 100 nm may be included in a cement composition in accordance with present embodiments.

[0020] It is now recognized that the particulate nano-silica utilized with present embodiments, which may include silicon dioxide, may have an impact on certain physical characteristics of resulting cements. For example, relative to inclusion of colloidal silica or larger silica particles in a cement slurry, inclusion of particulate nano-silica in the cement slurry may provide improved mechanical properties, such as compressive strength, tensile strength, Young's modulus and Poisson's ratio. In addition, the particulate nano-silica also may be included in the cement composition as a set accelerator to accelerate the set time of the resultant cement composition. Accordingly, a cement composition in accordance with present embodiments may comprise a sufficient amount of particulate nano-silica to provide

the desired characteristics in a resulting cement. In exemplary embodiments, the particulate nano-silica may be present in the cement composition in an amount in the range of from about 1% to about 25% bwoc. In exemplary embodiments, the particulate nano-silica may be present in the cement composition in an amount in the range of from about 5% to about 15% bwoc.

[0021] Other additives suitable for use in subterranean cementing operations also may be added to exemplary embodiments of the cement compositions. Examples of such additives include, strength-retrogression additives, set accelerators, weighting agents, weight-reducing additives, heavyweight additives, lost-circulation materials, filtration-control additives, dispersants, defoaming agents, foaming agents, and combinations thereof. Specific examples of these, and other, additives include crystalline silica, amorphous silica, salts, fibers, hydratable clays, vitrified shale, microspheres, fly ash, lime, latex, thixotropic additives, combinations thereof and the like. A person having ordinary skill in the art, with the benefit of this disclosure, will readily be able to determine the type and amount of additive useful for a particular application and desired result.

[0022] As will be appreciated by those of ordinary skill in the art, exemplary embodiments of the cement compositions of the present invention may be used in a variety of subterranean applications, including primary and remedial cementing. Exemplary embodiments of the cement compositions may be introduced into a subterranean formation and allowed to set therein. Exemplary embodiments of the cement compositions may comprise cement, water and the particulate nano-silica. By way of example, in exemplary primary cementing embodiments, a cement composition may be introduced into a space between a subterranean formation and a pipe string located in the subterranean formation. The cement composition may be allowed to set to form a hardened mass in the space between the subterranean formation and the pipe string. In addition, in exemplary remedial cementing embodiments, a cement composition may be used, for example, in squeeze-cementing operations or in the placement of cement plugs. One or more hydrocarbons (e.g., oil, gas, etc.) may be produced from a well bore penetrating the subterranean formation.

[0023] While the preceding discussion is directed to the use of particulate nano-silica, those of ordinary skill in the art will also appreciate that it may be desirable to utilize other

types of nano-particles, in accordance with embodiments of the present invention. Examples of such nano-particles include nano-alumina, nano-zinc oxide, nano-boron, nano-iron oxide and combinations thereof. In certain exemplary embodiments, the nano-particles may be particulate in nature and not, for example, a colloidal nano-particle or a suspension of the nano-particle in solution. Furthermore, while the preceding discussion is directed to the use of particulate nano-silica in well cementing methods, those of ordinary skill in the art will appreciate that the present technique also encompasses the use of nano-particles in any of a variety of different subterranean treatments. For example, the nano-particles may be included in any of a number of well treatment fluids that may be used in subterranean treatments, including drilling fluids, completion fluids, stimulation fluids and well clean-up fluids. In accordance with another embodiment, the nano-particles may be included as proppant in a well treatment fluid. For example, a well treatment fluid containing the nano-particles may be introduced into a subterranean formation at or above a pressure sufficient to create or enhance or more fractures in the subterranean formation. Enhancing a fracture includes enlarging a pre-existing fracture in the formation. At least a portion of the nano-particles may be deposited in the one or more fractures such that the fractures are prevented from fully closing upon the release of pressure, forming conductive channels through which fluids may flow to (or from) the well bore.

[0024] In addition to the use of the nano-particles without encapsulation, embodiments of the present invention may include encapsulation of the nano-particles to facilitate transportation and incorporation of the nano-particles in well treatment fluids (e.g., cement compositions). Specifically, encapsulation of the nano-particles in accordance with present embodiments may include enclosing the nano-particles within an outer coating or container in particulate form. Exemplary methods of encapsulation are set forth in U.S. Patent Nos. 5,373,901; 6,444,316; 6,527,051; 6,554,071; 7,156,174; and 7,204,312, the relevant disclosures of which are incorporated herein by reference.

[0025] Various types of encapsulation may be employed such that the nano-particles (e.g., the particulate nano-silica) are contained but retains its particulate nature and, thus, retains its corresponding impact on physical properties of cement slurries. For example, the nano-particles may be encapsulated within a bag, capsule, layer, coating or the like. Further, the material utilized to encapsulate the nano-particles may be selected to facilitate

transportation and/or incorporation of the nano-particles into a well treatment fluid. For example, to facilitate handling of the nano-particles and/or to facilitate timed release of the nano-particles, the encapsulation material may be degradable. This may facilitate handling of the nano-particles by allowing inclusion of the encapsulated nano-particles in a well treatment fluid without requiring that the nano-particles first be removed from the encapsulating material. Further, the encapsulating material may be designed to degrade at a certain rate when in contact with certain materials (e.g., water) so that the nano-particles are released into the well treatment fluid at a desired time. Exemplary water-dissolvable materials that may be utilized to encapsulate the nano-particles are described in U.S. Patent Nos. 4,961,790 and 5,783,541, the relevant disclosures of which are incorporated herein by reference.

[0026] In accordance with exemplary embodiments, the cement compositions of the present invention may utilize a packing volume fraction suitable for a particular application as desired. As used herein, the term “packing volume fraction” refers to the volume of the particulate materials in a fluid divided by the total volume of the fluid. The size ranges of the preferred particulate materials are selected, as well as their respective proportions, in order to provide a maximized packing volume fraction so that the fluid is in a hindered settling state. It is known that, in such a state, the particulate materials behave “collectively” like a porous solid material. The hindered settling state is believed to correspond, in practice, to a much higher solid material concentration in the fluid than that present in the some traditional cement compositions.

[0027] The present embodiments may include a combination of at least three features to obtain a maximum packing volume fraction. One is the use of at least three particulate materials wherein the at least three particulate materials are in size ranges “disjointed” from one another. In some embodiments, each of the three particulate materials may include a different particle size selected from the following ranges: about 7 nm to about 50 nm, about 0.05 microns to about 0.5 microns, 0.5 microns to about 10 microns, about 10 microns to about 20 microns, about 20 microns to about 200 microns, about 200 microns to about 800 microns, and greater than about 1 millimeter. For example, a first particulate material may include particles sized from about 7 nm to about 50 nm, a second particulate material may include particles sized from about 0.05 microns to about 0.5 microns, and a third particulate

material may include particles sized from about 10 microns to about 20 microns. In accordance with present embodiments, the first particulate material includes at least one of nano-silica, nano-alumina, nano-zinc oxide, nano-boron, nano-iron oxide or combinations thereof. Another feature of present embodiments may include a choice of the proportions of the three particulate materials in relation to the mixing, such that the fluid, when mixed, is in a hindered settling state. Another feature may include the choice of the proportions of the three particulate materials between each other, and according to their respective size ranges, such that the maximum packing volume fraction is at least substantially achieved for the sum total of all particulate materials in the fluid system. Packing volume fraction is described in further detail in United States Patent Nos. 5,518,996 and 7,213,646, the relevant portions of which are incorporated herein by reference.

[0028] To facilitate a better understanding of the present technique, the following examples of some specific embodiments are given. In no way should the following examples be read to limit, or to define, the scope of the invention.

EXAMPLE 1

[0029] Five different cement slurries (i.e., Slurry A, Slurry B, Slurry C, Slurry D and Slurry E) were prepared. The slurries and resulting set cements were then tested to determine setting or thickening times and other physical properties of each of the five different slurries. As set forth below, the respective test results for the five different slurries demonstrate that inclusion of particulate nano-silica in the slurry reduces the set time and increases the strength of the resulting cement relative to cements resulting from inclusion of the other silica components that were tested.

[0030] Slurries A, B, C and D were prepared by dry blending dry components with cement prior to adding water to form the respective slurry. Slurry E was prepared by dry blending dry components with cement prior to adding water and then adding colloidal silica to form the respective slurry. Further, each of the five slurries included a different type of silica. Two of the five slurries included particulate nano-silica in accordance with present embodiments, and the other three included silica in different forms and sizes (e.g., colloidal silica and micro-silica). While the silica included in each of the five slurries was different, the other components utilized in each of the five slurries were similar. Specifically, in

addition to a specific type of silica, each of the five slurries included 100% bwoc of Class G cement, 0.5% bwoc of a retarder, and sufficient water to make the density of the slurry approximately 12.00 lbs/gal. The specific retarder utilized in the slurries was HR-5 cement retarder, which is a sulfomethylated lignosulfonate. It should be noted that HR-5 cement retarder is available from Halliburton Energy Services, Inc. and is described in U.S. Patent No. RE31,190.

[0031] As set forth above, each of the five slurries included a different type of silica and sufficient water to make the resulting slurry have a density of 12.00 ppg. Slurries A and B included particulate nano-silica in accordance with present embodiments and 15.36 gal/sk of water. Specifically, Slurry A included 15% bwoc of particulate nano-silica having a particle size of approximately 30 nm, and Slurry B included particulate nano-silica having a particle size of approximately 10 nm. Slurry C included 15% bwoc of SILICALITE cement additive and 15.68 gal/sk of water. SILICALITE (compacted) cement additive, which is available from Halliburton Energy Services, Inc., Duncan, Oklahoma, is an amorphous silica generally sized in a range from about 2.5 microns to about 50 microns. Slurry D included 15% bwoc of MICROSAND cement additive and 15.77 gal/sk of water. MICROSAND cement additive, which is available from Halliburton Energy Services, Inc., Duncan, Oklahoma, is a crystalline silica ground to a substantially uniform particle size distribution of approximately 5 to 10 microns. Slurry E included 5.12 gal/sk of GasCon 469™ lightweight cement additive and 10.09 gal/sk of water. GASCOND 469 lightweight cement additive is available from Halliburton Energy Services, Inc., Duncan, Oklahoma, and may be defined as a colloidal silicic acid suspension containing suspended silicic acid particles generally having a particle size of less than about 20 nm.

[0032] After the five slurries were prepared, tests were performed to determine various physical characteristics associated with inclusion of the different silica components in each of the associated cement compositions. One of these tests was performed to measure a thickening time associated with each of the five slurries. Specifically, the total thickening time (TTT) associated with each cement slurry was determined by performing a thickening-time test in accordance with API Recommended Practice 10, *API Specification for Materials and Testing for Well Cements*. The measurement of the TTT for each slurry was based on the

respective slurry reaching a consistency of 70 Bearden units (Bc) at 80 °F. The results of these measurements are set forth for each of the five slurries in Table 1 below.

[0033] Additional tests were performed on the cement slurries to determine force-resistance properties (e.g., compressive strength, shear-bond strength, and tensile strength) for each of the slurries. Each of the force-resistance property tests was performed on the respective cement slurries at a temperature of 80°F and after the slurries had set for 72 hours. The force-resistance property tests included nondestructive and destructive ultrasonic strength tests, a compressive-strength test, a shear-bond test, and a tensile-strength test. The nondestructive and destructive ultrasonic analyzer tests were conducted using a UCA ultrasonic cement analyzer to determine a $UCA_{72 \text{ hrs}}$ value and a UCA_{crush} value, respectively. The compressive-strength tests and UCA analyzer tests were performed in accordance with API Recommended Practice 10B. Further, shear-bond and Brazilian-tensile-strength tests were performed to determine shear strength and tensile strength values, respectively, for the different cement compositions. The shear-bond-strength tests were performed as described in SPE 764 entitled "A Study of Cement – Pipe Bonding" by L.G. Carter and G.W. Evans. The Brazilian-tensile-strength tests were performed in accordance with ASTM C496-96. The results of the tests performed on each of the five compositions are shown in Table 1 below.

TABLE 1

Slurry	Silica Type	TTT to 70 Bc (Hr:Min)	$UCA_{72 \text{ hrs}}$ (psi)	UCA_{crush} (psi)	Comp. Strength (psi)	Shear-Bond Strength (psi)	Brazilian Tensile Strength (psi)
Slurry A	30 nm particulate nano-silica	2:43	328	419	428	169	148.28
Slurry B	10 nm particulate nano-silica	5:00	500	481	402	51	14.72
Slurry C	Amorphous silica	14:32	266	206	211	98	95.5
Slurry D	Crystalline Silica	20:00+	260	285	252	37.2	102.16
Slurry E	Colloidal Silica	20:00+	225	219	374	42.4	84.71

EXAMPLE 2

[0034] Samples of Slurries A, C, D and E discussed above were also tested to determine various additional physical properties associated with the resulting set cements and to confirm relative differences demonstrated above. While different instruments and calibration settings were used in the additional testing of the slurries, the test data indicates that relative differences between the different slurries are similar to those differences illustrated in Example 1. Indeed, as indicated above in Example 1, the respective test results in Example 2 for the five different cements demonstrate that inclusion of particulate nano-silica in the cement composition increases the strength of the resulting cement relative to cements resulting from inclusion of the other silica components that were tested.

[0035] Three samples for each of the three conventional cement slurries (Slurry C, Slurry D, and Slurry E) and four samples of Slurry A were tested to determine compressive strength, Young's modulus, and Poisson's ratio. The compressive-strength tests were performed in accordance with API Specification 10. It should be noted that the compressive-strength measurements in Example 1 are different than those in Example 2 because different equipment and different calibrations were utilized. However, the relative differences between compressive strengths for each of the five slurries are similar. The Young's modulus and Poisson's ratio were statically determined by means of compression testing using a load frame. The Young's modulus or modulus of elasticity for each sample was obtained by taking a ratio of a simple tension stress applied to each sample to a resulting strain parallel to the tension in that sample. The Poisson's ratio for each sample was determined by calculating a ratio of transverse strain to a corresponding axial strain resulting from uniformly distributed axial stress below a proportional limit of each sample. The values determined for the three samples of each of the five different cement slurries are set forth below in Table 2.

TABLE 2

Slurry	Sample	Silica Type	Compressive Strength (psi)	Young's Modulus	Poisson's Ratio
Slurry A	Sample 1	30 nm particulate nano-silica	1257	2.26E+05	**
Slurry A	Sample 2	30 nm particulate nano-silica	1189	2.12E+05	0.109
Slurry A	Sample 3	30 nm particulate nano-silica	1249	2.04E+05	0.092
Slurry A	Sample 4	30 nm particulate nano-silica	1275	2.13E+05	0.110
Slurry C	Sample 1	Amorphous silica	466	2.53E+05	0.064
Slurry C	Sample 2	Amorphous silica	483	2.38E+05	0.064
Slurry C	Sample 3	Amorphous silica	506	2.40E+05	0.053
Slurry D	Sample 1	Crystalline Silica	350	1.42E+05	0.068
Slurry D	Sample 2	Crystalline Silica	397	1.50E+05	0.063
Slurry D	Sample 3	Crystalline Silica	378	1.46E+05	0.060
Slurry E	Sample 1	Colloidal Silica	514	1.03E+05	0.063
Slurry E	Sample 2	Colloidal Silica	598	1.15E+05	0.072
Slurry E	Sample 3	Colloidal Silica	627	1.23E+05	0.071

[0036] The particular embodiments disclosed above are illustrative only, as the present invention may be susceptible to various modifications and alternative forms. However, it should be understood that the invention is not intended to be limited to the particular embodiments disclosed. Rather, the present invention is to cover all modifications, equivalents and alternatives falling within the scope and spirit of the present invention as defined by the following appended claims. In addition, every range of values (of the form, "from about a to about b," or, equivalently, "from approximately a to b," or, equivalently,

“from approximately a-b”) disclosed in the present Description of Specific Embodiments is to be understood as referring to the power set (the set of all subsets) of the respective range of values, and set for the every range encompassed within the broader range of value.

What is claimed is:

1. A method of cementing comprising:
introducing a cement composition into a subterranean formation, wherein the cement composition comprises cement, water, and at least one nano-particle selected from the group consisting of particulate nano-silica, nano-alumina, nano-zinc oxide, nano-boron, nano-iron oxide, and combinations thereof.
2. The method of claim 1, wherein the introducing the cement composition into the subterranean formation comprises introducing the cement composition into a space between a pipe string and the subterranean formation and allowing the cement composition to set in the space.
3. The method of claim 2, comprising running the pipe string into a well bore penetrating the subterranean formation.
4. The method of claim 1, wherein the method comprises allowing the cement composition to set in the subterranean formation.
5. The method of claim 1, comprising producing one or more hydrocarbons from a well bore penetrating the subterranean formation.
6. The method of claim 1, wherein a solids volume total in the cement composition comprises a maximized packing volume fraction.
7. The method of claim 1, comprising maximizing a packing volume fraction in the cement composition using particulate material including the particulate nano-silica.
8. The method of claim 1, wherein the cement comprises a hydraulic cement selected from the group consisting of a Portland cement, a pozzolana cement, a gypsum cement, a high-alumina-content cement, a slag cement, a silica cement, and combinations thereof.

9. The method of claim 1, wherein the at least one nano-particle is the particulate nano-silica.
10. The method of claim 9, wherein the particulate nano-silica comprises silicon dioxide.
11. The method of claim 9, wherein the particulate nano-silica has a particle size of from about 5 nanometers to about 50 nanometers.
12. The method of claim 9, wherein the particulate nano-silica is present in the cement composition in a range of from about 1% to about 25% by weight of the cement.
13. The method of claim 1, wherein the cement composition comprises an additive selected from the group consisting of a crystalline silica, an amorphous silica, a salt, a fiber, a hydratable clay, a vitrified shale, a microsphere, a fly ash, a lime, a latex, a thixotropic additive, and combinations thereof.
14. The method of claim 1, comprising including the at least one nano-particle in the cement composition while the at least one particulate material is encapsulated in a degradable material.
15. A method of cementing in a subterranean formation, comprising:
including encapsulated nano-particles in a cement composition; and
introducing the cement composition into the subterranean formation.
16. The method of claim 15, wherein the encapsulated nano-particles comprises at least one nano-particle selected from the group consisting of particulate nano-silica, nano-alumina, nano-zinc oxide, nano-boron, nano-iron oxide, and combinations thereof.

17. The method of claim 15, wherein the encapsulated nano-particles are encapsulated particulate nano-silica.

18. A method of accelerating set time of a cement composition, comprising:
including particulate nano-silica in a cement composition;
introducing the cement composition into a subterranean formation; and
allowing the cement composition to set in the subterranean formation.

19. A well cement composition comprising cement, water, and at least one nano-particle selected from the group consisting of particulate nano-silica, nano-alumina, nano-zinc oxide, nano-boron, nano-iron oxide, and combinations thereof.

20. The well cement composition of claim 19, wherein the at least one nano-particle is the particulate nano-silica.

21. A method of treating a subterranean formation comprising:
introducing a treatment fluid into a subterranean formation, wherein the treatment fluid comprises at least one nano-particle selected from the group consisting of particulate nano-silica, nano-alumina, nano-zinc oxide, nano-boron, nano-iron oxide, and combinations thereof.

22. The method of claim 21, wherein the at least one nano-particle is the particulate nano-silica.

23. The method of claim 21, wherein the treatment fluid is introduced into the subterranean formation at or above a pressure sufficient to create or enhance one or more fractures in the subterranean formation, and wherein the at least one nano-particle is deposited into the one or more fractures.

24. The method of claim 21, wherein the treatment fluid is a drilling fluid, a completion fluid, a stimulation fluid, or a well clean-up fluid.

25. A method of using nano-particles in a well treatment fluid, comprising:
including encapsulated nano-particles in the well treatment fluid.
26. The method of claim 25, wherein the encapsulated nano-particles are encapsulated particulate nano-silica.
27. The method of claim 25, wherein the treatment fluid is a drilling fluid, a completion fluid, a stimulation fluid, or a well clean-up fluid.
28. A well treatment fluid comprising at least one nano-particle selected from the group consisting of particulate nano-silica, nano-alumina, nano-zinc oxide, nano-boron, nano-iron oxide, and combinations thereof.
29. The well treatment fluid of claim 28, wherein the at least one nano-particle is the particulate nano-silica.
30. The well treatment fluid of claim 28, wherein the at least one nano-particle is encapsulated.
31. The well treatment fluid of claim 28, wherein the treatment fluid is a drilling fluid, a completion fluid, a stimulation fluid, or a well clean-up fluid.
32. A well treatment fluid comprising encapsulated nano-particles.
33. The method of claim 32, wherein the encapsulated nano-particles are encapsulated particulate nano-silica.
34. The method of claim 32, wherein the treatment fluid is a drilling fluid, a completion fluid, a stimulation fluid, or a well clean-up fluid.

INTERNATIONAL SEARCH REPORT

International application No

PCT/GB2008/001524

A. CLASSIFICATION OF SUBJECT MATTER

INV. C09K8/467 C04B14/06 C04B20/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 97/49644 A (BJ SERVICES COMPANY USA [US]; NOWSCO WELL SERVICE LTD [CA]; GANGULI KA) 31 December 1997 (1997-12-31) page 1, line 1 - line 3 page 3, line 31 - line 33 page 7, line 34 - line 36 page 8, line 1 - line 3 page 4, line 9 - line 14	1,4, 6-10,12, 13, 18-22, 28,29
X	US 5 207 832 A (BAFFREAU DANIEL [FR] ET AL) 4 May 1993 (1993-05-04) column 2, line 64 - column 3, line 2 column 2, line 40 - line 48; example 1; compound B1 column 3, line 53 - line 59	1-13, 18-22, 28,29

-/--



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

1 August 2008

Date of mailing of the international search report

20/08/2008

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Redecker, Michael

INTERNATIONAL SEARCH REPORT

International application No

PCT/GB2008/001524

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2007/056732 A1 (RODDY CRAIG W [US] ET AL) 15 March 2007 (2007-03-15) claim 11	1,4-11, 13, 18-22, 28,29
X	D.M.ROY: "New Strong Cement Materials: Chemically Bonded Ceramics" SCIENCE, vol. 6, 1987, pages 651-658, XP002490242 page 655, column 1, line 14 - line 38; table 2	19,20, 28,29
X	R.L. DILLENBECK,D.T.MUELLER,B.R.ORR: "The effect of microsilica on the thermal stability of lightweight cement systems" SPE CIM-90, no. 021597, 1990, pages 116-1-116-5, XP002490243 pages 116-1, column 1, paragraph 1 pages 116-1, column 2; table 2 pages 116-2, column 2, paragraph 2	1,4-10, 12, 18-22, 28,29
X	L. MA. FLORES-VELEZ, O. DOMINGUEZ: "Characterization and properties of portland cement composites incorporating zinc-iron oxide nanoparticles" JOURNAL OF MATERIALS SCIENCE, vol. 37, 2002, pages 983-988, XP002490244 page 984, column 2; figure 7 page 984, column 2	19,28
X	US 5 518 996 A (MAROY PIERRE [FR] ET AL) 21 May 1996 (1996-05-21) cited in the application column 1, line 9 - line 12 column 5, line 7 - line 34; examples 2,4	21-24, 28,29,31
X	US 7 156 174 B2 (RODDY CRAIG W [US] ET AL) 2 January 2007 (2007-01-02) cited in the application claims 10,13	1,4,9, 10, 13-17, 19-22, 25-30, 32-34
A	US 4 321 243 A (CORNWELL CHARLES E ET AL) 23 March 1982 (1982-03-23) column 1, line 40 - line 56	1-34

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No
PCT/GB2008/001524

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9749644	A	31-12-1997	AU 3486197 A	14-01-1998
US 5207832	A	04-05-1993	BR 9007048 A	22-10-1991
			EP 0458852 A1	04-12-1991
			FR 2643068 A1	17-08-1990
			WO 9009357 A1	23-08-1990
			OA 9900 A	15-09-1994
US 2007056732	A1	15-03-2007	WO 2008007040 A1	17-01-2008
US 5518996	A	21-05-1996	NONE	
US 7156174	B2	02-01-2007	AR 047866 A1	01-03-2006
			CA 2553892 A1	11-08-2005
			EP 1709290 A1	11-10-2006
			WO 2005073503 A1	11-08-2005
			US 2005167105 A1	04-08-2005
US 4321243	A	23-03-1982	NONE	