

WO 03/015179 A2



For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

TRENCH MIS DEVICE WITH REDUCED GATE-TO-DRAIN CAPACITANCE

FIELD OF THE INVENTION

This invention relates to trench metal-insulator-semiconductor (MIS) devices and
5 in particular to trench MOSFETs that are suitable for high frequency operation.

BACKGROUND

Some metal-insulator-semiconductor (MIS) devices include a gate located in a trench that extends downward from the surface of a semiconductor substrate (e.g., silicon). The current flow in such devices is primarily vertical and, as a result, the cells can be more
10 densely packed. All else being equal, this increases the current carrying capability and reduces the on-resistance of the device. Devices included in the general category of MIS devices include metal-oxide-semiconductor field effect transistors (MOSFETs), insulated gate bipolar transistors (IGBTs), and MOS-gated thyristors.

Trench MOSFETs, for example, can be fabricated with a high transconductance
15 ($g_{m,max}$) and low specific on resistance (R_{on}), which are important for optimal linear signal amplification and switching. One of the most important issues for high frequency operation, however, is reduction of the MOSFET internal capacitances. The internal capacitances include the gate-to-drain capacitance (C_{gd}), which is also called the feedback capacitance (C_{rss}), the input capacitance (C_{iss}), and the output capacitance (C_{oss}).

20 **Fig. 1** is a cross-sectional view of a conventional n-type trench MOSFET 10. In MOSFET 10, an n-type epitaxial ("N-epi") layer 13, which is usually grown on an N^+ substrate (not shown), is the drain. N-epi layer 13 may be a lightly doped layer, that is, an N^- layer. A p-type body region 12 separates N-epi layer 13 from N^+ source regions 11. Current flows vertically through a channel (denoted by the dashed lines) along the sidewall
25 of a trench 19. The sidewall and bottom of trench 19 are lined with a thin gate insulator 15 (e.g., silicon dioxide). Trench 19 is filled with a conductive material, such as doped polysilicon, which forms a gate 14. Trench 19, including gate 14 therein, is covered with an insulative layer 16, which may be borophosphosilicate glass (BPSG). Electrical contact to source regions 11 and body region 12 is made with a conductor 17, which is typically a
30 metal or metal alloy. Gate 14 is contacted in the third dimension, outside of the plane of **Fig. 1**.

A significant disadvantage of MOSFET 10 is a large overlap region 18 formed between gate 14 and N-epi layer 13, which subjects a portion of thin gate insulator 15 to the drain operating voltage. The large overlap limits the drain voltage rating of MOSFET 10, presents long term reliability issues for thin gate insulator 15, and greatly increases the gate-to-drain capacitance, C_{gd} , of MOSFET 10. In a trench structure, C_{gd} is larger than in conventional lateral devices, limiting the switching speed of MOSFET 10 and thus its use in high frequency applications.

One possible method to address this disadvantage is described in the above-referenced Application No. 09/591,179 and is illustrated in **Fig. 2**. **Fig. 2** is a cross-sectional view of a trench MOSFET 20 with an undoped polysilicon plug 22 near the bottom of trench 19. MOSFET 20 is similar to MOSFET 10 of **Fig. 1**, except for polysilicon plug 22, which is isolated from the bottom of trench 19 by oxide layer 21 and from gate 14 by oxide layer 23. The sandwich of oxide layer 21, polysilicon plug 22, and oxide layer 23 serves to increase the distance between gate 14 and N-epi layer 13, thereby decreasing C_{gd} .

In some situations, however, it may be preferable to have a material even more insulative than undoped polysilicon in the bottom of trench 19 to minimize C_{gd} for high frequency applications. Accordingly, a trench MOSFET with decreased gate-to-drain capacitance, C_{gd} , and better high frequency performance is desirable.

SUMMARY

In accordance with the present invention, a metal-insulator-semiconductor (MIS) device includes a semiconductor substrate including a trench extending into the substrate from a surface of the substrate. A source region of a first conductivity type is adjacent to a sidewall of the trench and to the surface of the substrate. A body region of a second conductivity type opposite to the first conductivity type is adjacent to the source region and to the sidewall. A drain region of the first conductivity type is adjacent to the body region and to the sidewall. The trench is lined with a first insulative layer along a portion of the sidewall that abuts the body region. The trench is also lined with a second insulative layer along a bottom portion of the trench. The second insulative layer is coupled to the first insulative layer, and the second insulative layer is thicker than the first insulative layer. The stress in the substrate along the bottom portion of the trench does not change appreciably.

In an exemplary embodiment of a fabrication process for such an MIS device, a trench including a sidewall and a bottom is formed in a substrate. A thick insulative layer is deposited on the bottom of the trench. A thin insulative layer is formed on the sidewall, and is coupled to the thick insulative layer. A gate is formed above the portion of the thick
5 insulative layer and adjacent to the thin insulative layer in the trench.

The thick insulative layer separates the trench gate from the drain conductive region at the bottom of the trench resulting in a reduced gate-to-drain capacitance. This makes MIS devices in accordance with the present invention, such as trench MOSFETs, suitable for high frequency applications.

10 BRIEF DESCRIPTION OF THE DRAWINGS

This invention will be better understood by reference to the following description and drawings. In the drawings, like or similar features are typically labeled with the same reference numbers.

Fig. 1 is a cross-sectional view of a conventional trench MOSFET.

15 **Fig. 2** is a cross-sectional view of a trench MOSFET with a polysilicon plug at the bottom of the trench.

Fig. 3 is a cross-sectional view of one embodiment of a trench MOSFET in accordance with the present invention.

Figs. 4A-4K are cross-sectional views illustrating one embodiment of a process for
20 fabricating a trench MOSFET in accordance with the present invention.

Fig. 5 is a cross-sectional view of an alternative embodiment of a trench MOSFET in accordance with the present invention.

DETAILED DESCRIPTION OF THE INVENTION

Fig. 3 is a cross-sectional view of one embodiment of a trench MOSFET 30 in
25 accordance with the present invention. MOSFET 30 has some similarities to MOSFET 10 of **Fig. 1**. The elements of MOSFET 30 outside of trench 19 can be the same as those of MOSFET 10 of **Fig. 1**. In MOSFET 30, however, only the sidewall of trench 19 is lined with thin gate insulator 15 (e.g., silicon dioxide). Unlike MOSFET 10 of **Fig. 1**, a thick insulative layer 31 (e.g., silicon dioxide) lines the bottom of trench 19 of MOSFET 30 of
30 **Fig. 3**. Thick insulative layer 31 separates gate 14 from N-epi layer 13 (which may be an N⁺ layer). This circumvents the problems that occur when only thin gate insulator 15

separates gate 14 from N-epi layer 13 (the drain) as in **Fig. 1**. Thick insulative layer 31 also provides a more effective insulator than is achievable with polysilicon plug 22 as shown in **Fig. 2**. Thus, thick insulative layer 31 minimizes the gate-to-drain capacitance, C_{gd} , and yields a trench MOSFET 30 useful for high frequency applications.

5 **Figs. 4A-4K** are cross-sectional views illustrating one embodiment of a process for fabricating a trench MOSFET, such as MOSFET 30 of **Fig. 3**, in accordance with the present invention. As shown in **Fig. 4A**, the process begins with a lightly-doped N-epi layer 413 (typically about 8 μm thick) grown on a heavily doped N^+ substrate (not shown). A trench mask 450, which may be photoresist or an oxide, is deposited on N-epi layer 413
10 and patterned to form an opening 452 where a trench 419 is to be located. Trench 419 is etched through opening 452, typically using a dry plasma etch, for example, a reactive ion etch (RIE). Trench 419 may be about 0.5-1.2 μm wide and about 1-2 μm deep.

Mask 450 is removed, and a thick insulative layer 431 (e.g., about 0.1-0.3 μm) is deposited on N-epi layer 413, as shown in **Fig. 4B**. The deposition process is chosen,
15 according to conventional deposition techniques such as chemical vapor deposition (CVD), to yield conformal deposition of insulative layer 431 on the sidewall and bottom of trench 419, as well as on the top surface of N-epi layer 413. Thick insulative layer 431 may be, for example, a low temperature oxide (LTO), a phosphosilicate glass (PSG), a BPSG, or another insulative material. In some embodiments, a thin insulative layer (e.g.,
20 100-200 Å of silicon dioxide) could be thermally grown, for example, using a well known dry oxidation process at 950 °C for 10 minutes, prior to deposition of thick insulative layer 431.

As shown in **Fig. 4C**, a barrier layer 454 is then deposited by CVD. This deposition can be non-conformal, filling trench 419 and overflowing past the topmost
25 surface of thick insulative layer 431. Barrier layer 454 may be, for example, silicon nitride (Si_3N_4), and may be 2-4 μm thick. Barrier layer 454 is etched back, typically by performing a dry etch followed by a wet etch, using etchants that have high selectivity for barrier layer 454 over thick insulative layer 431. Barrier layer 454 is etched back into trench 419 until only about 0.1-0.2 μm remains in trench 419, as shown in **Fig. 4D**.

30 Thick insulative layer 431 is then etched, typically by a wet etch technique, using an etchant that has high selectivity for insulative layer 431 over barrier layer 454 and over N-epi layer 413. Insulative layer 431 is etched from the top of N-epi layer 413 and from the sidewall of trench 419 until insulative layer 431 remains only in the bottom of trench

431. The remainder of barrier layer 454 is removed, leaving the structure shown in **Fig. 4E**.

As shown in **Fig. 4F**, a thin gate insulator 415 (e.g., about 100-1000 Å thick) is then formed on the top surface of N-epi layer 413 and on the sidewall of trench 419. Thin gate insulator 415 may be, for example, a silicon dioxide layer that is thermally grown using a dry oxidation technique at 1050 °C for 20 minutes. In some embodiments, a sacrificial gate oxide (not shown) can be thermally grown and removed by a wet etch to clean the sidewall of trench 419 prior to growing thin gate insulator 415. The wet etch of such a sacrificial gate oxide is kept short to minimize etching of thick insulative layer 431.

As shown in **Fig. 4G**, a conductive material 456 is deposited by CVD, possibly by low pressure CVD (LPCVD), to fill trench 419 and overflow past the topmost surface of thin gate insulator 415. Conductive material 456 may be, for example, an in-situ doped polysilicon, or an undoped polysilicon layer that is subsequently implanted and annealed, or an alternative conductive material. Conductive material 456 is etched, typically using a reactive ion etch, until the top surface of material 456 is approximately level with the top of N-epi layer 413, thereby forming gate 414, as shown in **Fig. 4H**. In an n-type MOSFET, gate 414 may be, for example, a polysilicon layer with a doping concentration of 10^{20} cm^{-3} . In some embodiments, conductive material 456 may be etched past the top of trench 419, thereby recessing gate 414 to minimize the gate-to-source overlap capacitance.

Using known implantation and diffusion processes, p-type body regions 412 and N^+ source regions 411 are formed in N-epi layer 413 as shown in **Fig. 4I**. The PN junctions between p-type body regions 412 and the remainder of N-epi layer 413 are located at a depth above the interface between thick insulative layer 431 and thin gate insulator 415.

As shown in **Fig. 4J**, an insulative layer 416, which may be borophosphosilicate glass (BPSG), is deposited by CVD on the surfaces of N-epi layer 413 and gate 414. Insulative layer 416 is etched, typically using a dry etch, to expose portions of p-type body regions 412 and N^+ source regions 411, as shown in **Fig. 4K**. Electrical contact to body regions 412 and source regions 411 is made with a conductor 417, which is typically a deposited (e.g., by physical vapor deposition, plating, sputtering, or evaporation) metal or metal alloy. Electrical contact to gate 414 is made in the third dimension, outside of the

plane of **Fig. 4K**. Electrical contact to the drain (not shown) is made to the opposite surface of the N^+ substrate (not shown) on which N-epi layer 413 is grown.

This method thus allows incorporation of thick insulative layer 431 at the bottom of trench 419 to minimize C_{gd} with minimal undesirable effects or manufacturing concerns, which may be caused by thermally growing thick insulative layer 431. For example, stress effects from growing a thick oxide in the concave bottom of trench 419 are avoided by depositing the oxide rather than thermally growing it. Thinning of the insulative layers at the juncture of thick insulative layer 431 and thin gate insulator 415, possibly caused by formation of a “bird’s beak” during a thermal growth of thick insulative layer 431, are avoided by depositing thick insulative layer 431. In addition, shifts in the etched sidewall profile of trench 419 are also avoided by depositing thick insulative layer 431. Growing thick insulative layer 431 could cause such shifts, resulting in a “bulb” effect at the bottom of trench 419 that is not compensated by subsequent growth of thin gate insulator 415 on the sidewall of trench 419.

Fig. 5 is a cross-sectional view of an alternative embodiment of a trench MOSFET 50 in accordance with the present invention. MOSFET 50 has many similarities to MOSFET 30 of **Fig. 3**. In particular, only the sidewall of trench 19 is lined with thin gate insulator 15, while thick insulative layer 31 lines the bottom of trench 19. In MOSFET 30 of **Fig. 3**, thick insulative layer 31 may increase the on-resistance (R_{on}) of MOSFET 30 due to an increase in the spreading resistance in the accumulation layer at the bottom of trench 19. MOSFET 50 of **Fig. 5**, however, includes a high doping region 53 at the bottom of trench 19 to help spread current more effectively. High doping region 53 is formed in N-epi layer 13, which overlies an N^+ substrate 55. High doping region 53 may be created by implanting an n-type dopant, such as arsenic or phosphorous, before mask 450 is removed after the trench etch shown in **Fig. 4A**. Thus, thick insulative layer 31 minimizes gate-to-drain capacitance, C_{gd} , and high doped region 53 minimizes on-resistance, R_{on} , yielding a trench MOSFET 50 well-suited for high frequency applications.

The foregoing embodiments are intended to be illustrative and not limiting of the broad principles of this invention. Many additional embodiments will be apparent to persons skilled in the art. For example, the structures and methods of this invention can be used with any type of metal-insulator-semiconductor (MIS) device in which it is desirable to form an insulating layer between a trench gate and a region outside the trench. Also, various insulative or conductive materials can be used where appropriate, and the

invention is also applicable to p-type MOSFETs. The invention is limited only by the following claims.

CLAIMS

We claim:

1. A metal-insulator-semiconductor device, comprising:
a semiconductor substrate including a trench extending into said substrate
5 from a surface of said substrate;
a source region of a first conductivity type adjacent to a sidewall of said trench and to said surface;
a body region of a second conductivity type opposite to said first conductivity type adjacent to said source region and to said sidewall; and
10 a drain region of said first conductivity type adjacent to said body region and to said sidewall,
wherein a stress in said substrate along a bottom portion of said trench does not change appreciably and wherein said trench is lined with a first insulative layer along a portion of said sidewall that abuts said body region and wherein said trench
15 is lined with a second insulative layer along said bottom portion of said trench, said second insulative layer being coupled to said first insulative layer and said second insulative layer being thicker than said first insulative layer.
2. The MIS device of Claim 1, further comprising a gate region coupled to said first insulative layer and said second insulative layer within said trench.
- 20 3. The MIS device of Claim 2, wherein said gate region comprises polysilicon.
4. The MIS device of Claim 1, further including a high conductivity region of said first conductivity type formed in said drain region adjacent to at least said bottom portion of said trench.
- 25 5. The MIS device of Claim 1, wherein said first insulative layer comprises an oxide.
6. The MIS device of Claim 1, wherein said second insulative layer comprises an oxide.
7. The MIS device of Claim 1, wherein said second insulative layer comprises
30 a multi-layer insulative layer.

8. The MIS device of Claim 1, wherein said MIS device comprises a MOSFET.

9. A trench-gate MOSFET, comprising:

a semiconductor substrate including a trench extending into said substrate
5 from a surface of said substrate;

a source region of a first conductivity type adjacent to a sidewall of said trench and to said surface;

a body region of a second conductivity type opposite to said first conductivity type adjacent to said source region and to said sidewall;

10 a drain region of said first conductivity type adjacent to said body region and to said sidewall,

wherein a stress in said substrate along a bottom portion of said trench does not change appreciably and wherein said trench is lined with a first insulative layer along a portion of said sidewall that abuts said body region and wherein said trench
15 is lined with a second insulative layer along said bottom portion of said trench, said second insulative layer being coupled to said first insulative layer and said second insulative layer being thicker than said first insulative layer; and

a gate region coupled to said first insulative layer and said second insulative layer within said trench.

20 10. The trench-gate MOSFET of Claim 9, wherein said gate region comprises polysilicon.

11. The trench-gate MOSFET of Claim 9, further including a high conductivity region of said first conductivity type formed in said drain region adjacent to at least said bottom portion of said trench.

25 12. The trench-gate MOSFET of Claim 9, wherein said first insulative layer comprises an oxide.

13. The trench-gate MOSFET of Claim 9, wherein said second insulative layer comprises an oxide.

30 14. The trench-gate MOSFET of Claim 9, wherein said second insulative layer comprises a multi-layer insulative layer.

15. A trench-gate MOSFET, comprising:

a semiconductor substrate including a trench extending into said substrate from a surface of said substrate;

5 a source region of a first conductivity type adjacent to a sidewall of said trench and to said surface;

a body region of a second conductivity type opposite to said first conductivity type adjacent to said source region and to said sidewall;

a drain region of said first conductivity type adjacent to said body region and to said sidewall;

10 a first insulative layer lining said trench along a portion of said sidewall that abuts said body region;

a second insulative layer lining said trench along a bottom portion of said trench, said second insulative layer being thicker than said first insulative layer and said second insulative layer being coupled to said first insulative layer,

15 wherein a thickness of a transition insulative layer at the juncture of said first insulative layer and said second insulative layer is not less than a thickness of said first insulative layer; and

a gate region coupled to said first insulative layer and said second insulative layer within said trench.

20 16. The trench-gate MOSFET of Claim 15, further including a high conductivity region of said first conductivity type formed in said drain region adjacent to at least said bottom portion of said trench.

17. A trench-gate MOSFET, comprising:

25 a semiconductor substrate including a trench extending into said substrate from a surface of said substrate;

a source region of a first conductivity type adjacent to a sidewall of said trench and to said surface;

a body region of a second conductivity type opposite to said first conductivity type adjacent to said source region and to said sidewall;

a drain region of said first conductivity type adjacent to said body region and to said sidewall;

a first insulative layer lining said trench along a portion of said sidewall that abuts said body region;

5 a second insulative layer lining said trench along a bottom portion of said trench, said second insulative layer being thicker than said first insulative layer and said second insulative layer being coupled to said first insulative layer,

wherein a first diameter of said trench taken at a vertical midpoint of said second insulative layer is not greater than a second diameter of said trench taken
10 adjacent to said body region; and

a gate region coupled to said first insulative layer and said second insulative layer within said trench.

18. The trench-gate MOSFET of Claim 17, further including a high conductivity region of said first conductivity type formed in said drain region adjacent to
15 at least said bottom portion of said trench.

19. A method of fabricating an MIS device, comprising:

providing a semiconductor substrate;

forming a trench in said substrate, said trench including a sidewall and a
bottom;

20 depositing a thick insulative layer on said sidewall and said bottom;

depositing a mask layer in said trench;

etching said mask layer to expose a portion of said thick insulative layer on said sidewall while leaving a portion of said mask layer at said bottom of said
trench;

25 etching said thick insulative layer to form an exposed portion of said sidewall while leaving a portion of said thick insulative layer at said bottom of said trench;

forming a thin insulative layer on said exposed portion of said sidewall; and

forming a gate above said portion of said thick insulative layer and adjacent
30 said thin insulative layer in said trench.

20. The method of Claim 19, wherein said forming a thin insulative layer includes thermally oxidizing said sidewall.
21. The method of Claim 20, further comprising:
growing a thin sacrificial oxide layer on said sidewall prior to said forming
5 a thin insulative layer; and
removing said sacrificial oxide layer prior to said forming a thin insulative layer.
22. The method of Claim 19, wherein said forming a gate comprises:
depositing doped polysilicon in said trench; and
10 etching said doped polysilicon to a level about equal to said surface of said substrate.
23. The method of Claim 19, further comprising growing a thin insulative layer on said sidewall and said bottom prior to said depositing a thick insulative layer.
24. The method of Claim 19, further comprising:
15 forming a body region in said substrate adjacent said sidewall; and
forming a source region in said body region, said source region adjacent said sidewall and a top surface of said substrate.
25. The method of Claim 19, further comprising forming a high conductivity region in said substrate adjacent to at least said bottom of said trench.
- 20 26. A method of fabricating an MIS device, comprising:
providing a semiconductor substrate;
forming a trench in said substrate, said trench including a sidewall and a bottom;
depositing a thick insulative layer on said bottom;
25 forming a thin insulative layer on said sidewall, said thin insulative layer coupled to said thick insulative layer; and
forming a gate in said trench above said thick insulative layer and adjacent to said thin insulative layer.

27. The method of Claim 26, wherein said depositing a thick insulative layer comprises:

depositing said thick insulative layer on said sidewall and said bottom;

depositing a mask layer in said trench;

5 etching said mask layer to expose a portion of said thick insulative layer on said sidewall while leaving a portion of said mask layer at said bottom of said trench; and

etching said thick insulative layer to form an exposed portion of said sidewall while leaving a portion of said thick insulative layer at said bottom of said trench.

10

28. The method of Claim 26, further comprising:

forming a body region in said substrate adjacent said sidewall; and

forming a source region in said body region, said source region adjacent said sidewall and a top surface of said substrate.

15 29. The method of Claim 26, further comprising forming a high conductivity region in said substrate adjacent to at least said bottom of said trench.

1/8




FIG. 1 (PRIOR ART)




FIG. 2




FIG. 3
SUBSTITUTE SHEET (RULE 26)




FIG. 4A




FIG. 4B




FIG. 4C




FIG. 4D

5/8




FIG. 4E




FIG. 4F




FIG. 4G




FIG. 4H




FIG. 4I




FIG. 4J




FIG. 4K




FIG. 5