



- (51) **International Patent Classification:**
C08G 61/12 (2006.01)
- (21) **International Application Number:**
PCT/GB2013/050463
- (22) **International Filing Date:**
25 February 2013 (25.02.2013)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
1203159.7 23 February 2012 (23.02.2012) GB
- (71) **Applicant:** SMARTKEM LIMITED [GB/GB]; Hexagon Tower, Delaunays Road, Blackley, Manchester Greater Manchester M9 8ZS (GB).
- (72) **Inventor:** GRIFFITHS, Russell Jon; 31 Shillingford Road, Farnworth, Bolton Lancashire BL4 7DJ (GB).
- (74) **Agent:** CLARKE, Lionel Paul; The Broadgate Tower, 20 Primrose Street, London GB EC2A 2ES (GB).
- (81) **Designated States** (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM,

AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

- (84) **Designated States** (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- *without international search report and to be republished upon receipt of that report (Rule 48.2(g))*

(54) **Title:** ORGANIC SEMICONDUCTOR COMPOSITIONS




Figure 1

(57) **Abstract:** The present invention relates to organic copolymers and organic semiconducting compositions comprising these materials, including layers and devices comprising such organic semiconductor compositions. The invention is also concerned with methods of preparing such organic semiconductor compositions and layers and uses thereof. The invention has application in the field of printed electronics and is particularly useful as a semiconducting material for use in formulations for organic thin film transistor (OTFT) backplanes for displays, integrated circuits, organic light emitting diodes (OLEDs), photodetectors, organic photovoltaic (OPV) cells, sensors, memory elements and logic circuits.



ORGANIC SEMICONDUCTOR COMPOSITIONS

Field of the Invention

The present invention relates to organic copolymers and organic semiconducting compositions comprising these materials, including layers and devices comprising
5 such organic semiconductor compositions. The invention is also concerned with methods of preparing such organic semiconductor compositions and layers and uses thereof. The invention has application in the field of printed electronics and is particularly useful as a semiconducting material for use in formulations for organic field effect transistor (OFET) backplanes for displays, integrated circuits, organic
10 light emitting diodes (OLEDs), photodetectors, organic photovoltaic (OPV) cells, sensors, memory elements and logic circuits.

Background of the Invention

In recent years, there has been an increasing interest in organic semiconducting materials as an alternative to conventional silicon-based semiconductors. Organic
15 semiconducting materials have several advantages over those based on silicon, such as lower cost, easier manufacturing, solution processability at low temperatures as well as increased flexibility, mechanical robustness, good compatibility with a wide variety of flexible substrates and light weight. They thus offer the possibility of producing more convenient high performance electronic
20 devices.

Polyacene compounds and their analogues in particular have shown promise in this field of technology. WO 2005/055248 for example, discloses an organic semiconducting layer formulation comprising an organic binder which has a permittivity (ϵ) at 1000 Hz of 3.3 or less, and a polyacene compound. However the
25 method for preparing the OFETs described in WO 2005/055248 in practice is limited and is only useful for producing top gate OFETs having relatively long channel lengths (typically > 50 microns). A further disadvantage of WO 2005/055248 that is overcome by the present invention, is that it frequently uses undesirable chlorinated solvents. The highest performance semiconductor compositions disclosed in WO
30 2005/055248 having mobilities $\geq 1.0 \text{ cm}^2 \text{V}^{-1} \text{s}^{-1}$, incorporated 1,2-dichlorobenzene as the solvent (page 54, Table 5 and examples 14, 21 and 25). Moreover these solvents are not ones that would be industrially acceptable in a printing process and these are also damaging to the environment. Therefore it would be desirable to use more benign solvents for the manufacture of these semiconductor compositions.

Furthermore, it is generally thought that only polymer binders with a permittivity of less than 3.3 could be used since any polymers with a higher permittivity resulted in a very significant reduction in mobility values of the OFET device.

5 This reduction in mobility value can further be seen in WO 2007/078993 which discloses the use of 2,3,9,10-substituted pentacene compounds in combination with insulating polymers having a dielectric constant at 1000 Hz of greater than 3.3. These compounds are reported to exhibit mobility values of between 10^{-2} and 10^{-7} $\text{cm}^2\text{V}^{-1}\text{s}^{-1}$ which are too low to be industrially useful.

10 Therefore, the present invention seeks to provide organic semiconductor compositions, which overcome the above-mentioned problems, by providing solvent soluble, high mobility, high flexibility polycyclic aromatic hydrocarbon copolymers, especially benzodichalcogenophenobenzodichalogenophene 'BXXB' copolymers and BXXB analogue copolymers having a tunable permittivity value and which exhibit high mobility values.

15 **Summary of the Invention**


The copolymers and compositions of the invention are expected to produce soluble materials that, on deposition, afford flexible, non-brittle layers unlike layers made from solely small molecule compounds. The copolymers of this invention have significantly higher mobilities than typical semiconducting binders used in the field of
20 printable electronics, such as the polytriarylamine class of semiconducting binders that have mobilities in the order of $\sim 10^{-6}$ to 10^{-3} cm^2/Vs . The copolymers of the invention will be industrially useful in the fabrication of rollable and flexible electronic devices such as OTFT arrays for displays; large area printed sensors and printed logic. In particular, the semiconducting polymers of this invention will be useful in
25 formulations for organic thin film transistors (OTFTs) having short channel lengths (≤ 30 microns and even ≤ 5 to 10 microns) that may be used as the backplane driver for electrophoretic displays, high resolution LCD and AMOLED displays.

The copolymers are also soluble in benign, non-chlorinated solvents, such as those typically used in printing.


30 The present invention also provides highly flexible, non-brittle, semi-conducting films.

Polycyclic Aromatic Hydrocarbon Copolymers (A and B)

Polycyclic Aromatic Hydrocarbon Copolymers (hereinafter PAHCs) according to the first aspect of the present invention comprise a mixture of at least one benzodichalcogenophenobenzodichalogenophene (hereafter referred to as BXB) monomer unit having the Formula (A) and at least one triarylamine monomer unit having the Formula (B):



Formula (A)



Formula (B)

10 wherein

Y^1 and Y^2 are independently S or Se;

k is 0 or 1

l is 0 or 1

15 wherein each of R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , R^{11} and R^{12} , which may be the same or different, independently represents hydrogen; a branched or unbranched, substituted or unsubstituted C_1 - C_{40} alkyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkenyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkynyl group; an optionally substituted C_3 - C_{40} cycloalkyl group; an optionally substituted C_6 - C_{40} aryl group; an optionally substituted C_1 - C_{40} heterocyclic group; an optionally substituted C_1 - C_{40} heteroaryl group; an optionally substituted C_1 - C_{40} alkoxy group; an optionally substituted C_6 - C_{40} aryloxy group; an optionally substituted C_7 - C_{40} alkylaryloxy group; an optionally substituted C_2 - C_{40} alkoxycarbonyl group; an optionally substituted C_7 - C_{40} aryloxycarbonyl group; a cyano group (-CN); a carbamoyl group (-C(=O)NR¹⁵R¹⁶); a carbonyl group (-C(=O)-R¹⁷); a carboxyl group (-CO₂R¹⁸) a

20

25

- cyanate group (-OCN); an isocyano group (-NC); an isocyanate group (-NCO); a thiocyanate group (-SCN) or a thioisocyanate group (-NCS); an optionally substituted amino group; a hydroxy group; a nitro group; a CF₃ group; a halo group (Cl, Br, F, I); -SR¹⁹; -SO₃H; -SO₂R²⁰; -SF₅; an optionally substituted silyl group; a C₂-C₁₀ alkynyl group substituted with a SiH₂R²² group, a C₂-C₁₀ alkynyl substituted with a SiHR²²R²³ group, or a C₂-C₁₀ alkynyl substituted with a -Si(R²²)_x(R²³)_y(R²⁴)_z group;

- wherein each R²² group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted C₁-C₁₀ alkyl group, a branched or unbranched, substituted or unsubstituted C₂-C₁₀ alkynyl group, a substituted or unsubstituted C₂-C₂₀ cycloalkyl group, a substituted or unsubstituted C₂-C₁₀ alkenyl group, and a substituted or unsubstituted C₆-C₂₀ cycloalkylalkylene group;

- each R²³ group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted C₁-C₁₀ alkyl group, a branched or unbranched, substituted or unsubstituted C₂-C₁₀ alkynyl group, a substituted or unsubstituted C₂-C₁₀ alkenyl group, a substituted or unsubstituted C₂-C₂₀ cycloalkyl group, and a substituted or unsubstituted C₆-C₂₀ cycloalkylalkylene group;

- R²⁴ is independently selected from the group consisting of hydrogen, a branched or unbranched, substituted or unsubstituted C₂-C₁₀ alkynyl group, a substituted or unsubstituted C₂-C₂₀ cycloalkyl group, a substituted or unsubstituted C₆-C₂₀ cycloalkylalkylene group, a substituted C₅-C₂₀ aryl group, a substituted or unsubstituted C₆-C₂₀ arylalkylene group, an acetyl group, a substituted or unsubstituted C₃-C₂₀ heterocyclic ring comprising at least one of O, N, S and Se in the ring;

- wherein x= 1 or 2; y=1 or 2; z=0 or 1; and (x+y+z)=3;

wherein each of R¹⁵, R¹⁶, R¹⁸, R¹⁹ and R²⁰ independently represent H or optionally substituted C₁-C₄₀ carbyl or hydrocarbyl group optionally comprising one or more heteroatoms;

- wherein R¹⁷ represents a halogen atom, H or optionally substituted C₁-C₄₀ carbyl or C₁-C₄₀ hydrocarbyl group optionally comprising one or more heteroatoms;

wherein at least two of R¹, R³, R⁴, R⁶, R⁷, R⁹, R¹⁰, and R¹², are a bond, represented by —*, to another monomer unit having the Formula (A) or (B); and wherein Ar₁, Ar₂ and Ar₃, which may be the same or different, each represent, independently if in different repeat units, an optionally substituted C₆₋₄₀ aromatic group

(mononuclear or polynuclear), wherein preferably at least one of Ar_1 , Ar_2 and Ar_3 is substituted with at least one polar or polarising groups and for the monomer group (B), —* represents a bond to another monomer unit having the Formula (A) or (B).

5 Preferably, $k=l=0$ or 1.

Preferably k and $l=0$.

Preferably, $x=2$ and $y=1$.



Preferably when $z=0$, R^{22} and R^{23} together comprise a combination of (i) branched or unbranched, substituted or unsubstituted C_1 - C_8 alkyl group(s) and (ii) branched or unbranched, substituted or unsubstituted C_2 - C_8 alkenyl group(s).

Preferably, any of R^{22} , R^{23} and R^{24} may optionally be substituted with a halogen atom.



Particularly preferred PAHCs according to the present invention are shown in the following table 1:

15

Table 1

Preferred PAHCs	
Monomer A	Monomer B
	
Case 1 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^4 and R^{10} are C_1 to C_{14} alkyl groups, most preferably n-octyl groups. R^3 and R^9 are bonds to another unit of Monomer (A) or (B).	$R'^a, R'^b, R'^c, R'^d, R'^e = H$

Case 2 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^3 and R^9 are C_1 to C_{14} alkyl groups, most preferably n-octyl groups. R^4 and R^{10} are bonds to another unit of Monomer (A) or (B).	
Case 3 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^4 and R^{10} are CF_3 groups. R^3 and R^9 are bonds to another unit of Monomer (A) or (B).	
Case 4 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^3 and, R^9 are CF_3 groups. R^4 and R^{10} are bonds to another unit of Monomer (A) or (B).	
Case 1	$R^b, R^d, R^e = H$
Case 2	
Case 3	R^a and $R^c = C_1$ to C_4 alkyl
Case 4	
Case 1	$R^b, R^c, R^d, R^e = H$
Case 2	$R^a = C_1$ to C_6 alkoxy
Case 3	
Case 4	(i) $R^a =$ methoxy (ii) $R^a =$ ethoxy
Case 1	$R^a, R^b, R^d, R^e = H$
Case 2	$R^c = C_1$ to C_6 alkoxy
Case 3	
Case 4	(i) $R^c =$ methoxy (ii) $R^c =$ ethoxy
Case 1	$R^a, R^b, R^c, R^d = H$
Case 2	$R^e = C_1$ to C_6 alkoxy
Case 3	
Case 4	(i) $R^e =$ methoxy

	(ii) R^e = ethoxy
Case 1	$R^b, R^d, R^e = H$
Case 2	$R^a = R^c = C_1 \text{ to } C_6 \text{ alkoxy}$
Case 3	
Case 4	(i) $R^a = R^c = \text{methoxy}$ (ii) $R^a = R^c = \text{ethoxy}$
Case 1	$R^b, R^d = H$
Case 2	$R^a, R^c, R^e = C_1 \text{ to } C_6 \text{ alkoxy}$
Case 3	
Case 4	(i) $R^a, R^c, R^e = \text{methoxy}$ (ii) $R^a, R^c, R^e = \text{ethoxy}$
Case 1	$R^b, R^d = H$
Case 2	$R^b, R^c, R^d = C_1 \text{ to } C_6 \text{ alkoxy}$
Case 3	
Case 4	(i) $R^b, R^c, R^d = \text{methoxy}$ (ii) $R^b, R^c, R^d = \text{ethoxy}$
Case 1	$R^b, R^c, R^d, R^e = H$
Case 2	
Case 3	$R^a = \text{Cyano (CN)}$
Case 4	
Case 1	$R^b, R^c, R^d, R^e = H$
Case 2	
Case 3	$R^a = \text{Isopropylcyano group}$
Case 4	Monomer B: 
Case 1	$R^a, R^b, R^d, R^e = H$
Case 2	
Case 3	$R^c = \text{Isopropylcyano group}$
Case 4	Monomer B: 

The organic semiconductor compounds specified in the table are particularly preferred as they combine the beneficial properties of high charge transport mobility (of the binders) with a polarity that is more compatible with benign, non-chlorinated solvents that will be desirable for use in large area printing. In addition, as these compounds are more polar once deposited as the OSC layer, or alternatively as a component in the OSC layer, they are expected to be resistant to

being re-dissolved by the hydrophobic solvents used for the organic gate insulators (OGI) such as Cytop. Furthermore, it is expected that the polar binders are useful for both top gate and bottom gate OTFTs, particularly for bottom gate OTFTs.

5 The copolymers according to the present invention preferably have a number average molecular weight (M_n) of between 500 and 100,000, more preferably between 1600 and 20000, more preferably between 500 and 10000, even more preferably between 850 and 5000.

10 The copolymers according to the present invention preferably have between 1 and 100000 monomer units having the Formula (A) and between 1 and 100000 triarylamine monomer units having the Formula (B). More preferably, the copolymers have between 1 and 1000 monomer units having the Formula (A) and between 1 and 1000 triarylamine monomer units having the Formula (B). More preferably, the copolymers have between 1 and 100 monomer units having the Formula (A) and between 1 and 100 triarylamine monomer units having the Formula (B).
15 Yet even more preferably, the copolymers have between 1 and 10 monomer units having the Formula (A) and between 1 and 10 triarylamine monomer units having the Formula (B).


20 Preferably, the organic semiconductor compositions according to the present invention contain less than 10% by weight, more preferably less than 5% by weight, more preferably less than 1%, more preferably, substantially no organic binders which have a permittivity at 1000 Hz of less than 3.4.

Preferred PAHCs and compositions of the present invention contain at least 20 wt. %, more preferably at least 20-40 wt. % (of the total of all monomer units (A) and (B) in the copolymer or composition) of a heteroacene monomer unit having the Formula (A) and at least 20 wt. %, preferably at least 20-80 wt. %, more preferably at least 50 wt. %, and even more preferably at least 60-80 wt.% of a monomer unit having the Formula (B).
25

Preferred PAHCs and compositions of the present invention contain at least 40 wt. % (of the total of all monomer units (A) and (B) in the copolymer or composition) of a BXB monomer unit having the Formula (A) and at least 40 wt. %, preferably 60 wt. % of a monomer unit having the Formula (B). Preferred PAHCs contain monomer unit (B) as the major component.
30

The BXB copolymers may be produced according to the following general synthetic regime. For simplicity, a representative BXB monomer is shown (no


- further substitutions are shown, the skilled person understanding how this can be genericised to the structures shown above) being coupled to a representative triphenylamine monomer. The coupling reaction is preferably a Yamamoto type coupling (using Nickel chloride, zinc, 2,2'-bipyridyl, triphenylphosphine and dimethyl acetamide). However, Suzuki coupling is also possible, although in this case it is preferable to remove the boronic esters from the resulting semiconducting polymer.



General Synthesis Route to the PAHC

- wherein α and β are preferably integers of 1-100000; and R is preferably H or a polar or polarising group as defined below. The halogen end groups are preferentially reacted either by substitution or hydrogenation.

10




Alternative Synthesis Route to the PAHC

wherein α and β are preferably integers of 1-100000; and R is preferably H or a polar or polarising group as defined below. On completion of the coupling reaction, the halogen and boronic ester end groups are preferably substituted by other groups, for example by hydrogenation and/or hydrolysis respectively.

Following the polymerization step to form the copolymer of the present invention, the copolymer may be cross-linked. Cross-linking may be achieved by any known technique. Examples include the application of heat and/or moisture, ethylene oxide treatment, UV irradiation, gamma sterilisation, electron beam irradiation, and autoclaving.


Thus, according to another aspect of the present invention, there is provided a process for producing a Polycyclic Aromatic Hydrocarbon Copolymer (PAHC) comprising copolymerising a composition containing at least one BXB monomer unit selected from the structure A':

11



Structure A'

and at least one monomer unit selected from the structure B':



5

Structure B'


wherein each of R groups, and k and l have the same general and preferred meanings as described in relation to the PAHC definitions above; wherein Ar₁, Ar₂ and Ar₃, which may be the same or different, each represent an optionally substituted C₆₋₄₀ aromatic group (mononuclear or polynuclear), wherein preferably at least one of Ar₁, Ar₂ and Ar₃ is substituted with at least one polar or more polarising group;

wherein X' is a halogen atom or a cyclic borate group; and

wherein Z' is a halogen atom.

Alternatively, X' may be a cyclic borate group and then in this case, Z' may be a halogen.

Preferably, the cyclic borate group is



Preferably, the process is carried out in a solvent, preferably an organic solvent, preferably an aromatic organic solvent.

The compositions of the present invention can comprise additional curable monomers, for example, diluent monomers. Examples of suitable materials include

radically curable monomer compounds, such as acrylate and methacrylate monomer compounds. Examples of acrylate and methacrylate monomers include isobornyl acrylate, isobornyl methacrylate, lauryl acrylate, lauryl methacrylate, isodecylacrylate, isodecylmethacrylate, caprolactone acrylate, 2-phenoxyethyl
5 acrylate, isooctylacrylate, isooctylmethacrylate, butyl acrylate, alkoxylated lauryl acrylate, ethoxylated nonyl phenol acrylate, ethoxylated nonyl phenol methacrylate, ethoxylated hydroxyethyl methacrylate, methoxy polyethylene glycol monoacrylate, methoxy polyethylene glycol monomethacrylate, tetrahydrofurfuryl methacrylate, as well as mixtures or combinations thereof.

- 10 In addition, multifunctional acrylate and methacrylate monomers and oligomers can be included in the compositions as reactive diluents and as materials that can increase the crosslink density of the cured composition. Examples of suitable multifunctional acrylate and methacrylate monomers and oligomers include pentaerythritol tetraacrylate, pentaerythritol tetramethacrylate, 1,2-ethylene glycol
15 diacrylate, 1,2-ethylene glycol dimethacrylate, 1,6-hexanediol diacrylate, 1,6-hexanediol dimethacrylate, 1,12-dodecanol diacrylate, 1,12-dodecanol dimethacrylate, tris(2-hydroxy ethyl) isocyanurate triacrylate, propoxylated neopentyl glycol diacrylate, hexanediol diacrylate, tripropylene glycol diacrylate, dipropylene glycol diacrylate, ethoxylated bisphenol A diacrylate, ethoxylated bisphenol A
20 dimethacrylate, alkoxylated hexanediol diacrylate, alkoxylated cyclohexane dimethanol diacrylate, polyethylene glycol diacrylate, polyethylene glycol dimethacrylate, tris (2-hydroxy ethyl) isocyanurate triacrylate, amine modified polyether acrylates (available as PO 83 F®, LR 8869®, and/or LR 8889® (all available from BASF Corporation), trimethylolpropane triacrylate, glycerol
25 propoxylate triacrylate, dipentaerythritol pentaacrylate, dipentaerythritol hexaacrylate, ethoxylated pentaerythritol tetraacrylate (available from Sartomer Co. Inc. as SR 494®), as well as mixtures and combinations thereof. When a reactive diluent is added to the composition of the present invention, the reactive diluent is added in any desired or effective amount, in one embodiment at least about 1
30 percent by weight of the carrier, at least about 35 percent by weight of the carrier, no more than about 98 percent by weight of the carrier, no more than about 75 percent by weight of the carrier, although the amount of diluent can be outside of these ranges.

- Copolymers according to the present invention may have a permittivity at 1000 Hz of
35 greater than 1.5, preferably greater than 2, preferably greater than 3. Particularly preferably, copolymers according to the present invention are semiconducting

copolymers having a permittivity at 1000 Hz of between 1.5 and 8, more preferably between 3.4 and 8. In a preferred embodiment, the polyacene copolymers have a permittivity at 1000 Hz of between 3.4 and 7, more preferably between 3.4 and 6.5, yet more preferably between 3.4 and 4.5 and even more preferably between 3.4 and 4.0. Copolymers according to the present invention are preferably semiconducting copolymers and may have a permittivity at 1000 Hz of greater than 3.4, for example greater than 3.8, greater than 4.0, greater than 4.2 and the like.

Preferably, the organic semiconductor compositions according to the present invention contain less than 10% by weight, more preferably less than 5% by weight, more preferably less than 1% by weight, more preferably, substantially no copolymers which have a permittivity at 1000 Hz of less than 3.4. In a preferred embodiment, the permittivity is determined by the method disclosed in WO 2004/102690 or by using the method disclosed herein, preferably by using the method disclosed herein.

Preferably, the copolymers of the present invention are semiconducting copolymers having a permittivity at 1000 Hz of between 3.4 and 8. In a preferred embodiment, the copolymers have a permittivity at 1000 Hz of between 3.4 and 7, more preferably between 3.4 and 6.5, and even more preferably between 3.4 and 4.5. The permittivity of the copolymers can be measured using any standard method known to those skilled in the art. In a preferred embodiment, the permittivity is determined by the method disclosed in WO 2004/102690 or by using the method disclosed herein, preferably by using the method disclosed herein.

Monomer Units of Formula (A)

The following are some preferred characteristics of the BXB monomer units defined above as (A).

In a preferred embodiment, at least one (and more preferably 2) of groups R^1 , R^6 , R^7 , and R^{12} are tri- C_{1-20} hydrocarbylsilyl C_{1-4} alkynyl groups.

Preferably at least one pair of R^1/R^6 and/or R^7/R^{12} are trihydrocarbylsilyl ethynyl groups.

In a preferred embodiment, at least one pair of R^1/R^6 and/or R^7/R^{12} are (trihydrocarbylsilyl)ethynyl- groups, $-C\equiv C-SiR^{22}R^{23}R^{24}$, wherein R^{22} , R^{23} and R^{24} independently represent C_1-C_6 alkyl or C_2-C_6 alkenyl. In a more preferred embodiment, R^{22} , R^{23} and R^{24} are independently selected from the group consisting

of methyl, ethyl, propyl, isopropyl, n-butyl, isobutyl, t-butyl, 1-propenyl and 2-propenyl.

In a preferred embodiment, at least one pair of R^1/R^6 and/or R^7/R^{12} are trialkylsilyl ethynyl groups, $-C\equiv C-SiR^{22}R^{23}R^{24}$, wherein R^{22} , R^{23} and R^{24} independently represent
 5 C_1 - C_6 alkyl or C_2 - C_6 alkenyl. In a more preferred embodiment, R^{22} , R^{23} and R^{24} are independently selected from the group consisting of methyl, ethyl, propyl, isopropyl, n-butyl, isobutyl, t-butyl 1-propenyl and 2-propenyl.


In yet another preferred embodiment, when $k = l = 0$; R^1 , R^3 , R^4 , R^6 , R^7 , R^9 , R^{10} and R^{12} , independently represent H, C_1 - C_{14} alkyl or C_1 - C_6 alkoxy. More preferably, R^1 ,
 10 R^3 , R^4 , R^6 , R^7 , R^9 , R^{10} and R^{12} are the same and represent H, C_1 - C_{14} alkyl or C_1 - C_6 alkoxy. In an even more preferred embodiment, R^1 , R^3 , R^4 , R^6 , R^7 , R^9 , R^{10} and R^{12} are the same or different and are selected from the group consisting of hydrogen, methyl, ethyl, propyl, n-butyl, isobutyl, t-butyl, n-octyl, methoxy, ethoxy, propyloxy and butyloxy, provided that at least at least one of each pair of R^3/R^4 and R^9/R^{10} are
 15 a bond, represented by $—^*$, to another monomer unit having the Formula (B)

Preferably, R^{22} , R^{23} and R^{24} are independently selected from the group consisting hydrogen, a C_1 - C_{10} alkyl group (preferably C_1 - C_4 -alkyl and most preferably methyl, ethyl, n-propyl or isopropyl) which may optionally be substituted for example with a halogen atom.

20 R^{22} and R^{23} are preferably independently selected from the group consisting optionally substituted C_{1-10} alkyl group and optionally substituted C_{2-10} alkenyl, more preferably C_1 - C_6 alkyl or C_2 - C_6 alkenyl. A preferred alkyl group in this case is isopropyl.

Examples of the silyl group $-Si(R^{22})_x(R^{23})_y(R^{24})_z$ include, without limitation,
 25 trimethylsilyl, triethylsilyl, tripropylsilyl, dimethylethylsilyl, diethylmethylsilyl, dimethylpropylsilyl, dimethylisopropylsilyl, dipropylmethylsilyl, diisopropylmethylsilyl, dipropylethylsilyl, diisopropylethylsilyl, diethylisopropylsilyl, triisopropylsilyl, trimethoxysilyl, triethoxysilyl, triphenylsilyl, diphenylisopropylsilyl, diisopropylphenylsilyl, diphenylethylsilyl, diethylphenylsilyl, diphenylmethylsilyl,
 30 triphenoxysilyl, dimethylmethoxysilyl, dimethylphenoxysilyl, methylmethoxyphenyl, etc. For each example in the foregoing list, the alkyl, aryl or alkoxy group may optionally be substituted.

In a preferred embodiment of the first aspect of the invention, PAHCs according to the present invention comprise at least one BXB monomer unit having the Formula (A1):



5

Formula (A1)

wherein each of R^2 , R^5 , R^8 and R^{11} are hydrogen;

At least one pair of R^1/R^6 and/or R^8/R^{11} are H or trialkylsilyl ethynyl groups, $-C\equiv C-SiR^{22}R^{23}R^{24}$, wherein R^{22} , R^{23} and R^{24} independently represent C_1 - C_4 alkyl or C_2 - C_4 alkenyl;

- 10 R^3 , R^4 , R^9 and R^{10} are independently selected from the group consisting of hydrogen; a branched or unbranched, unsubstituted C_1 - C_{14} alkyl group; C_1 - C_6 alkoxy group and C_6 - C_{12} aryloxy group;


Provided that at least one of each pair of R^3/R^4 and R^9/R^{10} are a bond, represented by $—^*$, to another monomer unit having the Formula (A), (A1) or (B) and

- 15 wherein k and l are independently 0, or 1, preferably both k and l are 0.

- In monomer units of Formula (A1), wherein k and l are both 0; R^1/R^6 and/or R^8/R^{11} are (trialkylsilyl)ethynyl groups, $-C\equiv C-SiR^{22}R^{23}R^{24}$, wherein R^{22} , R^{23} and R^{24} are preferably selected from ethyl, *n*-propyl, isopropyl, 1-propenyl or 2-propenyl; R^1 , R^3 , R^4 , R^6 , R^7 , R^9 , R^{10} , R^{11} and R^{12} are independently selected from the group consisting of hydrogen, methyl, ethyl and methoxy, provided that at least one of each pair of R^3/R^4 and R^9/R^{10} are a bond, represented by $—^*$, to another monomer unit having the Formula (A), (A1) or (B).
- 20

- In a more preferred embodiment the BXB moiety in the PAHC copolymer is a substituted BXB, wherein each R^{22} group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted C_1 - C_8 alkyl group, a substituted or unsubstituted C_2 - C_{12} cycloalkyl group, and a substituted or unsubstituted C_6 - C_{12} cycloalkylalkylene group; each R^{23} group is independently
- 25

- selected from the group consisting of a substituted or unsubstituted C₂-C₈ alkenyl group, a substituted or unsubstituted C₂-C₁₂ cycloalkyl group, and a substituted or unsubstituted C₆-C₁₂ cycloalkylalkylene group; and R²⁴ is independently selected from the group consisting of hydrogen, a branched or unbranched, substituted or unsubstituted C₂-C₈ alkynyl group, a substituted or unsubstituted C₂-C₁₂ cycloalkyl group, a substituted or unsubstituted C₆-C₁₂ cycloalkylalkylene group, a substituted C₅-C₁₂ aryl group, a substituted or unsubstituted C₆-C₁₄ arylalkylene group, an acetyl group, a substituted or unsubstituted C₅-C₁₂ heterocyclic ring comprising at least one of O, N, S and Se in the ring.
- 10 Preferred PAHCs and compositions of the present invention contain at least 20 wt. % (of the total of all monomer units (A), (A1) and (B), in the copolymer or composition) of a BXB monomer unit having the Formula (A1) and at least 20 wt. %, preferably between 20-80 wt. % of a monomer unit having the Formula (B).
- Especially preferred BXB monomer units according to the present invention are
- 15 those of Formulae (A2)



Formula (A2)


Preferably Y¹=Y²=S

- R¹, R³, R⁴, R⁶, R⁷, R⁹, R¹⁰ and R¹² are the same or different and are independently selected from the group consisting of hydrogen, methyl, ethyl, propyl, n-butyl, isobutyl, t-butyl, n-octyl, methoxy, ethoxy, propyloxy and butyloxy, more preferably hydrogen, methyl, propyl and methoxy.
- In monomer units of Formula (A2), R¹, R³, R⁴, R⁶, R⁷, R⁹, R¹⁰ and R¹² are independently selected from the group consisting of H, C₁-C₁₄ alkyl and C₁-C₆ alkoxy, provided that at least one of each pair of R³/R⁴ and R⁹/R¹⁰ are a bond, represented by —*, to another monomer unit having the Formula (A), (A1), (A2) or (B). In a preferred embodiment, R³, R⁴, R⁹ and R¹⁰ are the same or different and are independently selected from the group consisting of hydrogen, methyl, ethyl,

propyl, n-butyl, isobutyl, t-butyl, n-octyl, methoxy, ethoxy, propyloxy and butyloxy, more preferably hydrogen, methyl, ethyl, propyl, n-octyl and methoxy, provided that at least one of each pair of R^3/R^4 and R^9/R^{10} are a bond, represented by ---^* , to another monomer unit having the Formula (A), (A1), (A2), or (B).

- 5 In monomer units of Formula (A2), R^{25} , R^{26} and R^{27} are independently selected from the group consisting of C_1 - C_6 alkyl and C_2 - C_6 alkenyl, preferably R^{25} , R^{26} and R^{27} are independently selected from the group consisting of methyl, ethyl, propyl, isopropyl, n-butyl, isobutyl, t-butyl, 1-propenyl and 2-propenyl, more preferably ethyl, n-propyl and isopropyl.
- 10 Preferred PAHCs and compositions of the present invention contain at least 20 wt. % (of the total of all monomer units in the copolymer or composition) of a BXB monomer unit having the Formula (A2) and at least 20 wt. %, preferably between 20-80 wt. % of a monomer unit having the Formula (B).

The "R" substituents (that is R^1 , R^2 , etc) denote the substituents at the positions of
 15 the heteroacene according to conventional nomenclature:



BXB monomers according to the present invention may be synthesised by any known method within the common general knowledge of a person skilled in the art. In a preferred embodiment, methods disclosed in EP 2098527, EP 2254171, in the
 20 journal Heterocycles, 2011, Volume 83, pages 1187 and in Zh. Org. Khim, 1980, Volume 16, pages 384, 425 and 430, can be employed for the synthesis of heteroacene compounds used in the present invention. High permittivity analogues of the PAHCs of the invention may be prepared according to WO2012/160383 and WO2012/164282.

25 **Monomer Units (B)**

The following are some preferred characteristics of the triarylamine monomer unit defined above as (B),

Preferably, in monomer unit (B), Ar_1 , Ar_2 and Ar_3 , which may be the same or different, each represent, independently if in different repeat units, an optionally

substituted C₆₋₂₀ aromatic group (mononuclear or polynuclear), wherein at least one of Ar₁, Ar₂ and Ar₃ is substituted with at least one polar or more polarising group, and n = 1 to 100, preferably 1 to 50, preferably 1 to 20, even more preferably 1 to 10 and more preferably 1 to 5, wherein n refers to the number of monomer units.

- 5 Preferably, at least one of Ar₁, Ar₂ and Ar₃ is substituted with 1, 2, 3, or 4, more preferably 1, 2 or 3, more preferably 1 or 2, preferably 1 polar or more polarising group(s).

In a preferred embodiment, the one or more polar or polarising group(s) is independently selected from the group consisting of nitro group, nitrile group, C₁₋₄₀ alkyl group substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; C₁₋₄₀ alkoxy group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; C₁₋₄₀ carboxylic acid group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; C₂₋₄₀ carboxylic acid ester optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; sulfonic acid optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; sulfonic acid ester optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; cyanate group, isocyanate group, thiocyanate group, thioisocyanate group; and an amino group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; and combinations thereof.

In a more preferred embodiment, the one or more polar or polarising group(s) is independently selected from the group consisting of nitro group, nitrile group, C₁₋₁₀ alkyl group substituted with a nitrile group, a cyanate group, or an isocyanate group; C₁₋₂₀ alkoxy group, C₁₋₂₀ carboxylic acid group, C₂₋₂₀ carboxylic acid ester; sulfonic acid ester; cyanate group, isocyanate group, thiocyanate group, thioisocyanate group, and an amino group; and combinations thereof.

More preferably the polar or polarizing group is selected from the group consisting of C₁₋₄ cyanoalkyl group, C₁₋₁₀ alkoxy group, nitrile group and combinations thereof.

More preferably the polar or polarizing group(s) is selected from the group consisting of cyanomethyl, cyanoethyl, cyanopropyl, cyanobutyl, methoxy, ethoxy,

propoxy, butoxy, nitrile, NH_2 and combinations thereof. Preferably at least one of Ar_1 , Ar_2 and Ar_3 is substituted with 1 or 2 polar or more polarising group, which may be the same or different.

5 Yet more preferably, polar or polarizing group(s) is selected from the group consisting of isopropyl cyano, cyclohexylcyano, methoxy, ethoxy, nitrile and combinations thereof. Preferably at least one of Ar_1 , Ar_2 and Ar_3 is substituted with 1 or 2 polar or more polarising group, which may be the same or different.

10 More preferably, polar or polarizing group(s) is selected from the group consisting of methoxy, ethoxy, propoxy, butoxy and combinations thereof, wherein at least one of Ar_1 , Ar_2 and Ar_3 is substituted with 1 or 2 polar or more polarising group, which may be the same or different.

More preferably, polar or polarizing group(s) is selected from the group consisting of methoxy and ethoxy, wherein at least one of Ar_1 , Ar_2 and Ar_3 is substituted with 1 or 2 of the same polar or more polarising group.

15 In the context of Ar_1 , Ar_2 and Ar_3 , a mononuclear aromatic group has only one aromatic ring, for example phenyl or phenylene. A polynuclear aromatic group has two or more aromatic rings which may be fused (for example naphthyl or naphthylene), individually covalently linked (for example biphenyl) and/or a combination of both fused and individually linked aromatic rings. Preferably each
20 Ar_1 , Ar_2 and Ar_3 is an aromatic group which is substantially conjugated over substantially the whole group.

Preferably, Ar_1 , Ar_2 and Ar_3 , are independently selected from the group consisting of C_{6-20} aryl, C_{7-20} aralkyl and C_{7-20} alkaryl, any of which may be substituted with 1, 2, or 3 groups independently selected from C_{1-4} alkoxy, C_{3-20} cycloalkylcyano, C_{1-4}
25 cyanoalkyl, CN and mixtures thereof, and $n = 1$ to 10, wherein n refers to the number of monomer units.

Preferably, Ar_1 , Ar_2 and Ar_3 , are independently selected from the group consisting of C_{6-10} aryl, C_{7-12} aralkyl and C_{7-12} alkaryl, any of which may be substituted with 1, 2, or 3 groups independently selected from C_{1-2} alkoxy, C_{1-3} cyanoalkyl, CN and mixtures
30 thereof, and $n = 1$ to 10.

Preferably, Ar_1 , Ar_2 and Ar_3 , are independently selected from the group consisting of C_{6-20} aryl, substituted with 1 or 2 groups independently selected from C_{1-4} alkoxy, C_{3-20} cycloalkylcyano, C_{1-4} cyanoalkyl, CN and mixtures thereof, and $n = 1$ to 10.

Preferably, Ar₁, Ar₂ and Ar₃, are independently selected from the group consisting of C₆₋₁₀ aryl, wherein Ar₃, is substituted with 1 or 2 C₁₋₄ alkoxy, and n = 1 to 10.

Preferably, Ar₁, Ar₂ and Ar₃, are independently selected from the group consisting of C₆₋₁₀ aryl, wherein Ar₃ is substituted with 1 C₁₋₄ alkoxy, and n = 1 to 10.

- 5 Preferably, Ar₁, Ar₂ and Ar₃, are independently selected from the group consisting of phenyl, benzyl, tolyl and naphthyl, any of which may be substituted with 1, 2 or 3 groups independently selected from methoxy, ethoxy, cyanomethyl, cyanoethyl, CN and mixtures thereof, and n = 1 to 10.

- 10 Preferably, Ar₁, Ar₂ and Ar₃, are all phenyl, wherein Ar₃ is substituted with 1 or 2 C₁₋₄ alkoxy, and n = 1 to 10.

Preferably, Ar₁, Ar₂ and Ar₃, are all phenyl which may be independently substituted with 1, 2 or 3 groups selected from methoxy, ethoxy, isopropylcyano, cyanomethyl, cyanoethyl, CN and mixtures thereof, and n = 1 to 10.

- 15 Preferably, Ar₁, Ar₂ and Ar₃, are all phenyl which may be independently substituted with 1 or 2 groups selected from methoxy, ethoxy, cyanomethyl, CN and mixtures thereof, and n = 1 to 10.

Preferably, Ar₁, Ar₂ and Ar₃, are all phenyl which may be independently substituted with 1 or 2 groups selected from methoxy, ethoxy and mixtures thereof, and n = 1 to 10.


- 20 Preferably, Ar₁, Ar₂ and Ar₃, are all phenyl which may be independently substituted with 2,4-dimethoxy, 2-cyano, 2-methoxy, 2-ethoxy, 4-methoxy, 4-ethoxy, 4-isopropylcyano and 4-cyclohexylcyano, and n = 1 to 10.

Preferably, Ar₁, Ar₂ and Ar₃, are all phenyl which may be independently substituted with 2,4-dimethoxy, 2-methoxy, 2-ethoxy, 4-methoxy and 4-ethoxy, and n = 1 to 10.


- 25 The copolymers of the present invention may be a random or block copolymer of different monomer units. In such a case, any monomer unit defined by Formula (A) or (B), may be combined with a different or same monomer unit of (A) or (B) provided that at least one monomer unit (A) is bonded to at least one monomer unit (B).

- 30 The ratio of the monomers in the polycyclic aromatic hydrocarbon copolymers can be altered to allow for adjustment of the permittivity relative to a homopolymer. Furthermore, preferably the monomer unit of (A) or (B) may be mixed with monomer units which do not meet the definition of (A) or (B), provided that the average

permittivity of the binder in the compositions is preferably between 3.4 and 8.0. In this regard, other suitable monomer units include fluorene monomers such as (C), cis and trans-indenofluorene monomers such as (D and D') and spirobifluorene monomers such as (E):




(C)



(D)

(D')

10



(E)

wherein each $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$, $R^{5'}$, $R^{6'}$ and $R^{7'}$, each of which may be the same or different, is selected from the same group as R^1 , R^2 , R^3 , R^4 , R^5 , R^6 and R^7 , already defined above.


15 $n' = 1$ to 3.

When the PAHC according to the present invention comprises one or more monomers (C), (D), (D') and/or (E), the PAHC is comprised of monomer (A) in an amount of at least 20 wt. %; monomer (B) in an amount of at least 60 wt. % and the


remainder is comprised of monomers (C), (D), (D') and/or (E), based on the total weight of all monomer units in the copolymer.

In an even more preferred embodiment of the present invention, the monomer unit (B) comprises at least one unit having the structures (F) to (J):


5




(F)




(G)



(H)



(I)



(J)


10

Polycyclic Aromatic Hydrocarbon Copolymers (A and K)


Polycyclic Aromatic Hydrocarbon Copolymers (hereinafter PAHCs) according to a second aspect of the present invention comprise a mixture of at least one benzodichalcogenophenobenzodichalogenophene (hereafter referred to as BXB_X) monomer unit having the Formula (A) and at least one fluorene monomer unit having the Formula (K):

15

23



Formula (A)



Formula (K)

5 wherein

Y¹ and Y² are independently S or Se;

k is 0 or 1

l is 0 or 1

- 10 wherein each of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, R¹¹ and R¹², which may be the same or different, independently represents hydrogen; a branched or unbranched, substituted or unsubstituted C₁-C₄₀ alkyl group; a branched or unbranched, substituted or unsubstituted C₂-C₄₀ alkenyl group; a branched or unbranched, substituted or unsubstituted C₂-C₄₀ alkynyl group; an optionally substituted C₃-C₄₀ cycloalkyl group; an optionally substituted C₆-C₄₀ aryl group; an
- 15 optionally substituted C₁-C₄₀ heterocyclic group; an optionally substituted C₁-C₄₀ heteroaryl group; an optionally substituted C₁-C₄₀ alkoxy group; an optionally substituted C₆-C₄₀ aryloxy group; an optionally substituted C₇-C₄₀ alkylaryloxy group; an optionally substituted C₂-C₄₀ alkoxycarbonyl group; an optionally substituted C₇-C₄₀ aryloxycarbonyl group; a cyano group (-CN); a carbamoyl group (-C(=O)NR¹⁵R¹⁶);
- 20 a carbonyl group (-C(=O)-R¹⁷); a carboxyl group (-CO₂R¹⁸); a cyanate group (-OCN); an isocyano group (-NC); an isocyanate group (-NCO); a thiocyanate group (-SCN) or a thioisocyanate group (-NCS); an optionally substituted amino group; a hydroxy group; a nitro group; a CF₃ group; a halo group

(Cl, Br, F, I); $-\text{SR}^{19}$; $-\text{SO}_3\text{H}$; $-\text{SO}_2\text{R}^{20}$; $-\text{SF}_5$; an optionally substituted silyl group; a $\text{C}_2\text{-C}_{10}$ alkynyl group substituted with a $\text{SiH}_2\text{R}^{22}$ group, a $\text{C}_2\text{-C}_{10}$ alkynyl substituted with a $\text{SiHR}^{22}\text{R}^{23}$ group, or a $\text{C}_2\text{-C}_{10}$ alkynyl substituted with a $-\text{Si}(\text{R}^{22})_x(\text{R}^{23})_y(\text{R}^{24})_z$ group;

5 wherein each R^{22} group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ alkyl group, a branched or unbranched, substituted or unsubstituted $\text{C}_2\text{-C}_{10}$ alkynyl group, a substituted or unsubstituted $\text{C}_2\text{-C}_{20}$ cycloalkyl group, a substituted or unsubstituted $\text{C}_2\text{-C}_{10}$ alkenyl group, and a substituted or unsubstituted $\text{C}_6\text{-C}_{20}$ cycloalkylalkylene group;

10 each R^{23} group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ alkyl group, a branched or unbranched, substituted or unsubstituted $\text{C}_2\text{-C}_{10}$ alkynyl group, a substituted or unsubstituted $\text{C}_2\text{-C}_{10}$ alkenyl group, a substituted or unsubstituted $\text{C}_2\text{-C}_{20}$ cycloalkyl group, and a substituted or unsubstituted $\text{C}_6\text{-C}_{20}$ cycloalkylalkylene group;

15 R^{24} is independently selected from the group consisting of hydrogen, a branched or unbranched, substituted or unsubstituted $\text{C}_2\text{-C}_{10}$ alkynyl group, a substituted or unsubstituted $\text{C}_2\text{-C}_{20}$ cycloalkyl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{20}$ cycloalkylalkylene group, a substituted $\text{C}_5\text{-C}_{20}$ aryl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{20}$ arylalkylene group, an acetyl group, a substituted or
20 unsubstituted $\text{C}_3\text{-C}_{20}$ heterocyclic ring comprising at least one of O, N, S and Se in the ring;

wherein $x = 1$ or 2 ; $y = 1$ or 2 ; $z = 0$ or 1 ; and $(x+y+z) = 3$;

25 wherein each of R^{15} , R^{16} , R^{18} , R^{19} and R^{20} independently represent H or optionally substituted $\text{C}_1\text{-C}_{40}$ carbyl or hydrocarbyl group optionally comprising one or more heteroatoms;

wherein R^{17} represents a halogen atom, H or optionally substituted $\text{C}_1\text{-C}_{40}$ carbyl or $\text{C}_1\text{-C}_{40}$ hydrocarbyl group optionally comprising one or more heteroatoms;

wherein at least two of R^1 , R^3 , R^4 , R^6 , R^7 , R^9 , R^{10} , and R^{12} , are a bond, represented by ---^* , to another monomer unit having the Formula (A) or (K);

30 wherein each $\text{R}^{1'}$, $\text{R}^{2'}$, $\text{R}^{3'}$ and $\text{R}^{4'}$, each of which may be the same or different, is selected from the same group as R^1 , R^2 , R^3 , R^4 ; and wherein preferably at least one of the groups $\text{R}^{1'}$, $\text{R}^{2'}$, $\text{R}^{3'}$, $\text{R}^{4'}$ is a polar group or polarising group and for the

monomer group (K), —* represents a bond to another monomer unit having the Formula (A) or (K); and

$n' = 1$ to 3.

Preferably, $k=l = 0$ or 1.

5 Preferably k and $l = 0$.

Preferably, $x=2$ and $y=1$.

Preferably when $z=0$, R^{22} and R^{23} together comprise a combination of (i) branched or unbranched, substituted or unsubstituted C_1 - C_8 alkyl group(s) and (ii) branched or unbranched, substituted or unsubstituted C_2 - C_8 alkenyl group(s).

10 Preferably, any of R^{22} , R^{23} and R^{24} may optionally be substituted with a halogen atom.

Particularly preferred PAHCs according to the present invention are shown in the following table 2:



Table 2

15

Preferred PAHCs		
Monomer A	Monomer B	Monomer C
Case 1 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^4 and R^{10} are C_1 to C_{14} alkyl groups, most preferably n-octyl groups. R^3 and R^9 are bonds to another unit of Monomer (A) or (B).	$R^{1'} = R^{2'} = C_1$ to C_{14} alkyl group, preferably n-octyl groups $R^{3'}, R^{4'} = H$ or C_1 to C_4 alkyl groups; or C_1 to C_4 alkoxy groups; or cyano groups; or isopropyl cyano groups.	$R'^a, R'^b, R'^c, R'^d, R'^e = H$

Case 2 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^3 and R^9 are C_1 to C_{14} alkyl groups, most preferably n-octyl groups. R^4 and R^{10} are bonds to another unit of Monomer (A) or (B).		
Case 3 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^4 and R^{10} are CF_3 groups. R^3 and R^9 are bonds to another unit of Monomer (A) or (B).		
Case 4 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^3 and R^9 are CF_3 groups. R^4 and R^{10} are bonds to another unit of Monomer (A) or (B).		
Case 1	$R^{1'} = R^{2'} = C_1$ to C_{14} alkyl group, preferably n-octyl groups	$R^b, R^d, R^e = H$
Case 2		R^a and $R^c = C_1$ to C_4 alkyl
Case 3		
Case 4		
Case 1	$R^{1'} = R^{2'} = C_1$ to C_{14} alkyl group, preferably n-octyl groups	$R^b, R^c, R^d, R^e = H$ $R^a = C_1$ to C_6 alkoxy
Case 2		
Case 3		
Case 4	$R^3, R^4 = H$ or C_1 to C_4 alkyl groups; or C_1 to C_4 alkoxy groups; or cyano groups; or isopropyl cyano groups.	(i) $R^a =$ methoxy (ii) $R^a =$ ethoxy

Case 1	$R^1 = R^2 = C_1 \text{ to } C_{14} \text{ alkyl group, preferably n-octyl groups}$ $R^3, R^4 = H \text{ or } C_1 \text{ to } C_4 \text{ alkyl groups; or } C_1 \text{ to } C_4 \text{ alkoxy groups; or cyano groups; or isopropyl cyano groups.}$	$R^a, R^b, R^d, R^e = H$ $R^c = C_1 \text{ to } C_6 \text{ alkoxy}$ (i) $R^c = \text{methoxy}$ (ii) $R^c = \text{ethoxy}$
Case 2		
Case 3		
Case 4		
Case 1	$R^1 = R^2 = C_1 \text{ to } C_{14} \text{ alkyl group, preferably n-octyl groups}$ $R^3, R^4 = H \text{ or } C_1 \text{ to } C_4 \text{ alkyl groups; or } C_1 \text{ to } C_4 \text{ alkoxy groups; or cyano groups; or isopropyl cyano groups.}$	$R^a, R^b, R^c, R^d = H$ $R^e = C_1 \text{ to } C_6 \text{ alkoxy}$ (i) $R^e = \text{methoxy}$ (ii) $R^e = \text{ethoxy}$
Case 2		
Case 3		
Case 4		
Case 1	$R^1 = R^2 = C_1 \text{ to } C_{14} \text{ alkyl group, preferably n-octyl groups}$ $R^3, R^4 = H \text{ or } C_1 \text{ to } C_4 \text{ alkyl groups; or } C_1 \text{ to } C_4 \text{ alkoxy groups; or cyano groups; or isopropyl cyano groups.}$	$R^b, R^d, R^e = H$ $R^a = R^c = C_1 \text{ to } C_6 \text{ alkoxy}$ (i) $R^a = R^c = \text{methoxy}$ (ii) $R^a = R^c = \text{ethoxy}$
Case 2		
Case 3		
Case 4		
Case 1	$R^1 = R^2 = C_1 \text{ to } C_{14} \text{ alkyl group, preferably n-octyl groups}$ $R^3, R^4 = H \text{ or } C_1 \text{ to } C_4 \text{ alkyl groups; or } C_1 \text{ to } C_4 \text{ alkoxy groups; or cyano groups; or isopropyl cyano groups.}$	$R^b, R^d = H$ $R^a, R^c, R^e = C_1 \text{ to } C_6 \text{ alkoxy}$ (i) $R^a, R^c, R^e = \text{methoxy}$ (ii) $R^a, R^c, R^e = \text{ethoxy}$
Case 2		
Case 3		
Case 4		
Case 1	$R^1 = R^2 = C_1 \text{ to } C_{14} \text{ alkyl group, preferably n-octyl groups}$ $R^3, R^4 = H \text{ or } C_1 \text{ to } C_4 \text{ alkyl groups; or } C_1 \text{ to } C_4 \text{ alkoxy groups; or cyano groups; or isopropyl cyano groups.}$	$R^b, R^d = H$ $R^b, R^c, R^d = C_1 \text{ to } C_6 \text{ alkoxy}$ (i) $R^b, R^c, R^d = \text{methoxy}$ (ii) $R^b, R^c, R^d = \text{ethoxy}$
Case 2		
Case 3		
Case 4		
Case 1	$R^1 = R^2 = C_1 \text{ to } C_{14} \text{ alkyl group, preferably n-octyl groups}$ $R^3, R^4 = H \text{ or } C_1 \text{ to } C_4 \text{ alkyl groups; or } C_1 \text{ to } C_4 \text{ alkoxy groups; or cyano groups; or isopropyl cyano groups.}$	$R^b, R^c, R^d, R^e = H$ $R^a = \text{Cyano (CN)}$
Case 2		
Case 3		
Case 4		

	alkoxy groups; or cyano groups; or isopropyl cyano groups.	
Case 1	R ^{1'} = R ^{2'} = C ₁ to C ₁₄ alkyl group, preferably n-octyl groups	R ^b , R ^c , R ^d , R ^e = H R ^a = Isopropylcyano group Monomer C: 
Case 2		
Case 3		
Case 4		
Case 1	R ^{1'} = R ^{2'} = C ₁ to C ₁₄ alkyl group, preferably n-octyl groups	R ^a , R ^b , R ^d , R ^e = H R ^c = Isopropylcyano group Monomer C: 
Case 2		
Case 3		
Case 4		

- The organic semiconductor compounds specified in the table are particularly preferred as they combine the beneficial properties of high charge transport mobility (of the binders) with a polarity that is more compatible with benign, non-chlorinated solvents that will be desirable for use in large area printing. In addition,
- 5 as these compounds are more polar once deposited as the OSC layer, or alternatively as a component in the OSC layer, they are expected to be resistant to being re-dissolved by the hydrophobic solvents used for the organic gate insulators (OGI) such as Cytop. Furthermore, it is expected that the polar binders are useful
- 10 for both top gate and bottom gate OTFTs, particularly for bottom gate OTFTs.

The copolymers according to the present invention preferably have a number average molecular weight (Mn) of between 500 and 100,000, more preferably between 1600 and 20000, more preferably between 500 and 10000, even more preferably between 850 and 5000.

- 15 The copolymers according to the present invention preferably have between 1 and 100000 monomer units having the Formula (A) and between 1 and 100000 fluorene monomer units having the Formula (K). More preferably, the copolymers have

between 1 and 1000 monomer units having the Formula (A) and between 1 and 1000 fluorene monomer units having the Formula (K). More preferably, the copolymers have between 1 and 100 monomer units having the Formula (A) and between 1 and 100 fluorene monomer units having the Formula (K). Yet even
5 more preferably, the copolymers have between 1 and 10 monomer units having the Formula (A) and between 1 and 10 fluorene monomer units having the Formula (K).


Preferably, the organic semiconductor compositions according to the present invention contain less than 10% by weight, more preferably less than 5% by weight, more preferably less than 1%, more preferably, substantially no organic binders
10 which have a permittivity at 1000 Hz of less than 3.4.

Preferred PAHCs and compositions of the present invention contain at least 20 wt. %, more preferably at least 20-40 wt. % (of the total of all monomer units (A) and (K) in the copolymer or composition) of a heteroacene monomer unit having the Formula (A) and at least 20 wt. %, preferably at least 20-80 wt. %, more preferably
15 at least 50 wt. %, and even more preferably at least 60-80 wt.% of a monomer unit having the Formula (K).

Preferred PAHCs and compositions of the present invention contain at least 40 wt. % (of the total of all monomer units (A) and (K) in the copolymer or composition) of a BXB monomer unit having the Formula (A) and at least 40 wt. %, preferably
20 60 wt. % of a monomer unit having the Formula (K). Preferred PAHCs contain monomer unit (K) as the major component.

The BXB copolymers may be produced according to the following general synthetic regime. For simplicity, a representative BXB monomer is shown (no further substitutions are shown, the skilled person understanding how this can be
25 genericised to the structures shown above) being coupled to a representative fluorene monomer. The coupling reaction is preferably a Yamamoto type coupling (using Nickel chloride, zinc, 2,2'-bipyridyl, triphenylphosphine and dimethyl acetamide). However, Suzuki coupling is also possible, although in this case it is preferable to remove the boronic esters from the resulting semiconducting polymer.


30



General Synthesis Route to the PAHC

- wherein α and β are preferably integers of 1-100000; and R^1 groups have the same definition as R^1 , R^2 groups defined below. The halogen end groups are
- 5 preferentially reacted either by substitution or hydrogenation.

31




Alternative Synthesis Route to the PAHC

- wherein α and β are preferably integers of 1-100000; and R' groups have the same definition as $\text{R}^{1'}$, $\text{R}^{2'}$ groups defined below. On completion of the coupling reaction,
- 5 the halogen and boronic ester end groups are preferably substituted by other groups, for example by hydrogenation and/or hydrolysis respectively.


- Following the polymerization step to form the copolymer of the present invention, the copolymer may be cross-linked. Cross-linking may be achieved by any known technique. Examples include the application of heat and/or moisture, ethylene oxide
- 10 treatment, UV irradiation, gamma sterilisation, electron beam irradiation, and autoclaving.

- Thus, according to another aspect of the present invention, there is provided a process for producing a Polycyclic Aromatic Hydrocarbon Copolymer (PAHC) comprising copolymerising a composition containing at least one BXB monomer
- 15 unit selected from the structure A' :



Structure A'

and at least one monomer unit selected from the structure K':



Structure K'

5

wherein each of R groups, and k and l have the same general and preferred meanings as described in relation to the PAHC definitions above; wherein each R^{1'}, R^{2'}, R^{3'} and R^{4'}, each of which may be the same or different, is selected from the same group as R¹, R², R³, R⁴; and wherein preferably at least one of the groups R^{1'}, R^{2'}, R^{3'}, R^{4'} is a polar group or polarising group and for the monomer group (K), —* represents a bond to another monomer unit having the Formula (A) or (K); and

10


n' = 1 to 3.

wherein X' is a halogen atom or a cyclic borate group; and

15 wherein Z' is a halogen atom.

Alternatively, X' may be a cyclic borate group and then in this case, Z' may be a halogen.

Preferably, the cyclic borate group is



Preferably, the process is carried out in a solvent, preferably an organic solvent, preferably an aromatic organic solvent.

The compositions of the present invention can comprise additional curable monomers, for example, diluent monomers. Examples of suitable materials include
5 radically curable monomer compounds, such as acrylate and methacrylate monomer compounds. Examples of acrylate and methacrylate monomers include isobornyl acrylate, isobornyl methacrylate, lauryl acrylate, lauryl methacrylate, isodecylacrylate, isodecylmethacrylate, caprolactone acrylate, 2-phenoxyethyl acrylate, isooctylacrylate, isooctylmethacrylate, butyl acrylate, alkoxyated lauryl
10 acrylate, ethoxylated nonyl phenol acrylate, ethoxylated nonyl phenol methacrylate, ethoxylated hydroxyethyl methacrylate, methoxy polyethylene glycol monoacrylate, methoxy polyethylene glycol monomethacrylate, tetrahydrofurfuryl methacrylate, as well as mixtures or combinations thereof.

In addition, multifunctional acrylate and methacrylate monomers and oligomers can
15 be included in the compositions as reactive diluents and as materials that can increase the crosslink density of the cured composition. Examples of suitable multifunctional acrylate and methacrylate monomers and oligomers include pentaerythritol tetraacrylate, pentaerythritol tetramethacrylate, 1,2-ethylene glycol diacrylate, 1,2-ethylene glycol dimethacrylate, 1,6-hexanediol diacrylate, 1,6-
20 hexanediol dimethacrylate, 1,12-dodecanol diacrylate, 1,12-dodecanol dimethacrylate, tris(2-hydroxy ethyl) isocyanurate triacrylate, propoxylated neopentyl glycol diacrylate, hexanediol diacrylate, tripropylene glycol diacrylate, dipropylene glycol diacrylate, ethoxylated bisphenol A diacrylate, ethoxylated bisphenol A dimethacrylate, alkoxyated hexanediol diacrylate, alkoxyated cyclohexane
25 dimethanol diacrylate, polyethylene glycol diacrylate, polyethylene glycol dimethacrylate, tris (2-hydroxy ethyl) isocyanurate triacrylate, amine modified polyether acrylates (available as PO 83 F®, LR 8869®, and/or LR 8889® (all available from BASF Corporation), trimethylolpropane triacrylate, glycerol propoxylate triacrylate, dipentaerythritol pentaacrylate, dipentaerythritol
30 hexaacrylate, ethoxylated pentaerythritol tetraacrylate (available from Sartomer Co. Inc. as SR 494®), as well as mixtures and combinations thereof. When a reactive diluent is added to the composition of the present invention, the reactive diluent is added in any desired or effective amount, in one embodiment at least about 1 percent by weight of the carrier, at least about 35 percent by weight of the carrier, no
35 more than about 98 percent by weight of the carrier, no more than about 75 percent

by weight of the carrier, although the amount of diluent can be outside of these ranges.

Copolymers according to the present invention may have a permittivity at 1000 Hz of greater than 1.5, preferably greater than 2, preferably greater than 3. Particularly
5 preferably, copolymers according to the present invention are semiconducting copolymers having a permittivity at 1000 Hz of between 1.5 and 8, more preferably between 3.4 and 8. In a preferred embodiment, the polyacene copolymers have a permittivity at 1000 Hz of between 3.4 and 7, more preferably between 3.4 and 6.5, yet more preferably between 3.4 and 4.5 and even more preferably between 3.4 and
10 4.0. Copolymers according to the present invention are preferably semiconducting copolymers and may have a permittivity at 1000 Hz of greater than 3.4, for example greater than 3.8, greater than 4.0, greater than 4.2 and the like.

Preferably, the organic semiconductor compositions according to the present invention contain less than 10% by weight, more preferably less than 5% by weight,
15 more preferably less than 1% by weight, more preferably, substantially no copolymers which have a permittivity at 1000 Hz of less than 3.4. In a preferred embodiment, the permittivity is determined by the method disclosed in WO 2004/102690 or by using the method disclosed herein, preferably by using the method disclosed herein.

20 Preferably, the copolymers of the present invention are semiconducting copolymers having a permittivity at 1000 Hz of between 3.4 and 8. In a preferred embodiment, the copolymers have a permittivity at 1000 Hz of between 3.4 and 7, more preferably between 3.4 and 6.5, and even more preferably between 3.4 and 4.5. The permittivity of the copolymers can be measured using any standard method
25 known to those skilled in the art. In a preferred embodiment, the permittivity is determined by the method disclosed in WO 2004/102690 or by using the method disclosed herein, preferably by using the method disclosed herein.

Monomer Units of Formula (A)

The preferred characteristics of the BXB monomer units (A) are as defined above,
30 except that any reference to monomer (B) should be considered to be a reference to monomer (K), in accordance with the second aspect of the present invention.

Monomer Units (K)

The following are some preferred characteristics of the fluorene monomer unit defined above as (K).

In monomer unit (K), preferably each R^1 , R^2 , R^3 , R^4 , each of which may be the same or different, is selected from hydrogen; a branched or unbranched, substituted or unsubstituted C_1 - C_{10} alkyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{10} alkenyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{10} alkynyl group; an optionally substituted C_3 - C_{10} cycloalkyl group; an optionally substituted C_6 - C_{10} aryl group; an optionally substituted C_1 - C_{10} heterocyclic group; an optionally substituted C_1 - C_{10} heteroaryl group; an optionally substituted C_1 - C_{10} alkoxy group; an optionally substituted C_6 - C_{10} aryloxy group; an optionally substituted C_7 - C_{10} alkylaryloxy group; an optionally substituted C_2 - C_{10} alkoxycarbonyl group; an optionally substituted C_7 - C_{20} aryloxycarbonyl group; a cyano group (-CN); a carbamoyl group (-C(=O)NR¹⁵R¹⁶); a carbonyl group (-C(=O)-R¹⁷); a carboxyl group (-CO₂R¹⁸); a cyanate group (-OCN); an isocyano group (-NC); an isocyanate group (-NCO); a thiocyanate group (-SCN) or a thioisocyanate group (-NCS); an optionally substituted amino group; a hydroxy group; a nitro group; a CF₃ group; a halo group (Cl, Br, F, I); -SR¹⁹; -SO₃H; -SO₂R²⁰; -SF₅; an optionally substituted silyl group; a C_2 - C_{10} alkynyl group substituted with a SiHR²² group, a C_2 - C_{10} alkynyl substituted with a SiHR²²R²³ group, or a C_2 - C_{10} alkynyl substituted with a -Si(R²²)_x(R²³)_y(R²⁴)_z group, wherein each of x, y and z, and R¹⁵, R¹⁶, R¹⁸, R¹⁹ and R²⁰, R²², R²³ and R²⁴ are as defined above.

In monomer unit (K), preferably each R^1 , R^2 , R^3 , R^4 , each of which may be the same or different, is H, methyl, methoxy, cyano, cyanomethyl, preferably H.

Preferably, in monomer unit (K), at least one of R^1 , R^2 , R^3 and R^4 is a polar group or more polarising group and $n = 1$ to 100, preferably 1 to 50, preferably 1 to 20, even more preferably 1 to 10 and more preferably 1 to 5, wherein n refers to the number of monomer units. Preferably, at least one of R^1 , R^2 , R^3 , R^4 , more preferably at least two of R^1 , R^2 , R^3 , R^4 are polar groups or polarising groups.

In a preferred embodiment, the one or more polar or polarising group(s) is independently selected from the group consisting of nitro group, nitrile group, C_{1-40} alkyl group substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; a C_{1-40} alkoxy group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; a C_{1-40} carboxylic acid group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; a C_{2-40} carboxylic acid ester optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group;

sulfonic acid optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; sulfonic acid ester optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; cyanate group, isocyanate group, thiocyanate group, thioisocyanate group; and an amino group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; and combinations thereof.

In a more preferred embodiment, the one or more polar or polarising group(s) is independently selected from the group consisting of nitro group, nitrile group, C₁₋₁₀ alkyl group substituted with a nitrile group, a cyanate group, or an isocyanate group; C₁₋₂₀ alkoxy group, C₁₋₂₀ carboxylic acid group, C₂₋₂₀ carboxylic acid ester; sulfonic acid ester; cyanate group, isocyanate group, thiocyanate group, thioisocyanate group, and an amino group; and combinations thereof.

More preferably the polar or polarizing group is selected from the group consisting of C₁₋₄ cyanoalkyl group, C₁₋₁₀ alkoxy group, nitrile group and combinations thereof.

More preferably the polar or polarizing group(s) is selected from the group consisting of cyanomethyl, cyanoethyl, cyanopropyl, cyanobutyl, methoxy, ethoxy, propoxy, butoxy, nitrile, NH₂ and combinations thereof. Preferably at least one of the R¹, R², R³, R⁴ groups is a polar group or more polarising group, which may be the same or different.

Yet more preferably, the polar or polarizing group(s) is selected from the group consisting of isopropyl cyano, cyclohexylcyano, methoxy, ethoxy, nitrile and combinations thereof. Preferably at least one of R¹, R², R³, R⁴ is a polar or more polarising group, which may be the same or different.

More preferably, the polar group or polarizing group(s) is selected from the group consisting of methoxy, ethoxy, propoxy, butoxy and combinations thereof, wherein at least one of R¹, R², R³ and R⁴ is 1 or 2 polar or more polarising group, which may be the same or different.

More preferably, polar or polarizing group(s) is selected from the group consisting of methoxy and ethoxy, wherein at least one of R¹, R², R³, R⁴ is 1 or 2 of the same polar or more polarising group.

Preferably, R¹, R², R³, R⁴, are independently selected from the groups consisting of C₁₋₂ alkoxy, C₁₋₃ cyanoalkyl, CN and mixtures thereof, and n = 1 to 10.

Preferably, $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$, are independently selected from the group consisting of C_{1-4} alkoxy, C_{3-20} cycloalkylcyano, C_{1-4} cyanoalkyl, CN and mixtures thereof, and $n = 1$ to 10.

5 Preferably, $R^{3'}$, is independently selected from the group consisting of 1 C_{1-4} alkoxy, and $n = 1$ to 10.

Preferably, $R^{3'}$ and $R^{4'}$, are independently selected from the group consisting of methoxy, ethoxy, cyanomethyl, cyanoethyl, CN and mixtures thereof, and $n = 1$ to 10.

10 Preferably, $R^{4'}$ is independently selected from the group consisting of 1 C_{1-4} alkoxy, and $n = 1$ to 10.


Preferably, $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$ are independently selected from methoxy, ethoxy, isopropylcyano, cyanomethyl, cyanoethyl, CN and mixtures thereof, and $n = 1$ to 10.

Preferably, $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$ are independently selected from methoxy, ethoxy, cyanomethyl, CN and mixtures thereof, and $n = 1$ to 10.

15 Preferably, $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$ are independently selected from methoxy, ethoxy and mixtures thereof, and $n = 1$ to 10.


20 The copolymers of the present invention may be a random or block copolymer of different monomer units. In such a case, any monomer unit defined by Formula (A) or (K), may be combined with a different or same monomer unit of (A) or (K) provided that at least one monomer unit (A) is bonded to at least one monomer unit (K).

25 The ratio of the monomers in the polycyclic aromatic hydrocarbon copolymers can be altered to allow for adjustment of the permittivity relative to a homopolymer. Furthermore, preferably the monomer unit of (A) or (K) may be mixed with monomer units which do not meet the definition of (A) or (K), provided that the average permittivity of the binder in the compositions is preferably between 3.4 and 8.0. In this regard, other suitable monomer units include arylamine monomers such as (L), cis and trans-indenofluorene monomers such as (M and M') respectively and spirobifluorene monomers such as (N):




38


(L)



(M)



(M')



(N)

- 10 wherein each $R^{1''}$, $R^{2''}$, $R^{3''}$, $R^{4''}$, $R^{5''}$, $R^{6''}$ and $R^{7''}$, each of which may be the same or different, is selected from the same group as R^1 to R^7 , already defined above;


- Ar_1 , Ar_2 and Ar_3 , which may be the same or different, each represent, independently an optionally substituted C_{6-40} aromatic group (mononuclear or polynuclear). Preferably at least one of Ar_1 , Ar_2 and Ar_3 is substituted with at least one polar or more polarising group, and $n = 1$ to 20 , preferably 1 to 10 and more preferably 1 to 5 . Preferably, at least one of Ar_1 , Ar_2 and Ar_3 is substituted with 1 , 2 , 3 , or 4 , more preferably 1 , 2 or 3 , more preferably 1 or 2 , preferably 1 polar or more polarising group(s); and
- 15

$n'' = 1$ to 3.


When the PAHC according to the present invention comprises one or more monomers (L), (M), (M') and/or (N), the PAHC is comprised of monomer (A) in an amount of at least 20 wt. %; monomer (K) in an amount of at least 60 wt. % and the remainder is comprised of monomers (L), (M), (M') and/or (N), based on the total weight of all monomer units in the copolymer.

Polycyclic Aromatic Hydrocarbon Copolymers (A and O)

Polycyclic Aromatic Hydrocarbon Copolymers (hereinafter PAHCs) according to the present invention comprise a mixture of at least one benzodichalcogenophenobenzodichalogenophene (hereafter referred to as BXB_X) monomer unit having the Formula (A) and at least one triarylamine monomer unit having the Formula (O):



Formula (A)



Formula (O/O') -represents cis and/or trans-indenofluorene isomers

wherein

Y^1 and Y^2 are independently S or Se;

k is 0 or 1

l is 0 or 1

- 5 wherein each of R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , R^{11} and R^{12} , which may be the same or different, independently represents hydrogen; a branched or unbranched, substituted or unsubstituted C_1 - C_{40} alkyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkenyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkynyl group; an optionally substituted C_3 - C_{40} cycloalkyl group; an optionally substituted C_6 - C_{40} aryl group; an optionally substituted C_1 - C_{40} heterocyclic group; an optionally substituted C_1 - C_{40} heteroaryl group; an optionally substituted C_1 - C_{40} alkoxy group; an optionally substituted C_6 - C_{40} aryloxy group; an optionally substituted C_7 - C_{40} alkylaryloxy group; an optionally substituted C_2 - C_{40} alkoxycarbonyl group; an optionally substituted C_7 - C_{40} aryloxycarbonyl group; a cyano group ($-CN$); a carbamoyl group ($-C(=O)NR^{15}R^{16}$); a carbonyl group ($-C(=O)-R^{17}$); a carboxyl group ($-CO_2R^{18}$); a cyanate group ($-OCN$); an isocyano group ($-NC$); an isocyanate group ($-NCO$); a thiocyanate group ($-SCN$) or a thioisocyanate group ($-NCS$); an optionally substituted amino group; a hydroxy group; a nitro group; a CF_3 group; a halo group (Cl, Br, F, I); $-SR^{19}$; $-SO_3H$; $-SO_2R^{20}$; $-SF_5$; an optionally substituted silyl group; a C_2 - C_{10} alkynyl group substituted with a SiH_2R^{22} group, a C_2 - C_{10} alkynyl substituted with a $SiHR^{22}R^{23}$ group, or a C_2 - C_{10} alkynyl substituted with a $-Si(R^{22})_x(R^{23})_y(R^{24})_z$ group;

- 25 wherein each R^{22} group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted C_1 - C_{10} alkyl group, a branched or unbranched, substituted or unsubstituted C_2 - C_{10} alkynyl group, a substituted or unsubstituted C_2 - C_{20} cycloalkyl group, a substituted or unsubstituted C_2 - C_{10} alkenyl group, and a substituted or unsubstituted C_6 - C_{20} cycloalkylalkylene group;

- 30 each R^{23} group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted C_1 - C_{10} alkyl group, a branched or unbranched, substituted or unsubstituted C_2 - C_{10} alkynyl group, a substituted or unsubstituted C_2 - C_{10} alkenyl group, a substituted or unsubstituted C_2 - C_{20} cycloalkyl group, and a substituted or unsubstituted C_6 - C_{20} cycloalkylalkylene group;

R²⁴ is independently selected from the group consisting of hydrogen, a branched or unbranched, substituted or unsubstituted C₂-C₁₀ alkynyl group, a substituted or unsubstituted C₂-C₂₀ cycloalkyl group, a substituted or unsubstituted C₆-C₂₀ cycloalkylalkylene group, a substituted C₅-C₂₀ aryl group, a substituted or
 5 unsubstituted C₆-C₂₀ arylalkylene group, an acetyl group, a substituted or unsubstituted C₃-C₂₀ heterocyclic ring comprising at least one of O,N,S and Se in the ring;

wherein x= 1 or 2; y=1 or 2; z=0 or 1; and (x+y+z)=3;

wherein each of R¹⁵, R¹⁶, R¹⁸, R¹⁹ and R²⁰ independently represent H or optionally
 10 substituted C₁-C₄₀ carbyl or hydrocarbyl group optionally comprising one or more heteroatoms;

wherein R¹⁷ represents a halogen atom, H or optionally substituted C₁-C₄₀ carbyl or C₁-C₄₀ hydrocarbyl group optionally comprising one or more heteroatoms;

wherein at least two of R¹, R³, R⁴, R⁶, R⁷, R⁹, R¹⁰, and R¹², are a bond, represented
 15 by —*, to another monomer unit having the Formula (A) or (O);

wherein monomer (O/O') is either the cis and/or trans-indenofluorene monomer and each R^{1'}, R^{2'}, R^{3'}, R^{4'}, R^{5'}, R^{6'}, R^{7'}, each of which may be the same or different, is selected from the same group as R¹, R², R³, R⁴, R⁶, R⁷ and wherein preferably at least one of the groups ,R^{1'}, R^{2'}, R^{3'}, R^{4'}, R^{5'}, R^{6'} and R^{7'} is a polar or polarising group
 20 and for the monomer group (O/O') —* represents a bond to another monomer unit having the Formula (A) or (O/O'); and

wherein n' = 1 to 3.

Preferably, k+l = 0 or 1.

Preferably k and l = 0




25 Preferably, x=2 and y=1.

Preferably when z=0, R²² and R²³ together comprise a combination of (i) branched or unbranched, substituted or unsubstituted C₁-C₈ alkyl group(s) and (ii) branched or unbranched, substituted or unsubstituted C₂-C₈ alkenyl group(s).



Preferably, any of R²², R²³ and R²⁴ may optionally be substituted with a halogen
 30 atom.

Particularly preferred PAHCs according to the present invention are shown in the following table 3:

Table 3

Preferred PAHCs		
Monomer A	Monomer B	Monomer C
		
Case 1 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^4 and R^{10} are C_1 to C_{14} alkyl groups, most preferably n-octyl groups. R^3 and R^9 are bonds to another unit of Monomer (A) or (B).	$R^{1'}, R^{2'}, R^{3'}$ and $R^{4'}$ are C_1 to C_{14} alkyl group, preferably n-octyl groups $R^{5'}, R^{6'}$ and $R^{7'}$ are H or C_1 to C_4 alkyl groups; or C_1 to C_4 alkoxy groups; or cyano groups; or isopropyl cyano groups.	$R'^a, R'^b, R'^c, R'^d, R'^e = H$
Case 2 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^3 and R^9 are C_1 to C_{14} alkyl groups, most preferably n-octyl groups. R^4 and R^{10} are bonds to another unit of Monomer (A) or (B).		
Case 3 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^4 and R^{10} are CF_3 groups. R^3 and R^9 are bonds to another unit of		

Monomer (A) or (B).		
Case 4 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^3 and, R^9 are CF_3 groups. R^4 and R^{10} are bonds to another unit of Monomer (A) or (B).		
Case 1	$R^{1'}, R^{2'}, R^{3'}$ and $R^{4'}$ are C_1 to C_{14} alkyl group, preferably n-octyl groups $R^{5'}, R^{6'}$ and $R^{7'}$ are H or C_1 to C_4 alkyl groups; or C_1 to C_4 alkoxy groups; or cyano groups; or isopropyl cyano groups.	$R^{b'}, R^{d'}, R^{e'} = H$ $R^{a'}$ and $R^{c'} = C_1$ to C_4 alkyl
Case 2		
Case 3		
Case 4		
Case 1	$R^{1'}, R^{2'}, R^{3'}$ and $R^{4'}$ are C_1 to C_{14} alkyl group, preferably n-octyl groups $R^{5'}, R^{6'}$ and $R^{7'}$ are H or C_1 to C_4 alkyl groups; or C_1 to C_4 alkoxy groups; or cyano groups; or isopropyl cyano groups.	$R^{b'}, R^{c'}, R^{d'}, R^{e'} = H$ $R^{a'} = C_1$ to C_6 alkoxy (i) $R^{a'} =$ methoxy (ii) $R^{a'} =$ ethoxy
Case 2		
Case 3		
Case 4		
Case 1	$R^{1'}, R^{2'}, R^{3'}$ and $R^{4'}$ are C_1 to C_{14} alkyl group, preferably n-octyl groups $R^{5'}, R^{6'}$ and $R^{7'}$ are H or C_1 to C_4 alkyl groups; or C_1 to C_4 alkoxy groups; or cyano groups; or isopropyl cyano groups.	$R^{a'}, R^{b'}, R^{d'}, R^{e'} = H$ $R^{c'} = C_1$ to C_6 alkoxy (i) $R^{c'} =$ methoxy (ii) $R^{c'} =$ ethoxy
Case 2		
Case 3		
Case 4		
Case 1	$R^{1'}, R^{2'}, R^{3'}$ and $R^{4'}$ are C_1 to C_{14} alkyl group, preferably n-octyl groups	$R^{a'}, R^{b'}, R^{c'}, R^{d'} = H$ $R^{e'} = C_1$ to C_6 alkoxy (i) $R^{e'} =$ methoxy (ii) $R^{e'} =$ ethoxy
Case 2		
Case 3		
Case 4		
Case 1	$R^{1'}, R^{2'}, R^{3'}$ and $R^{4'}$ are C_1 to C_{14} alkyl group, preferably n-octyl groups	$R^{b'}, R^{d'}, R^{e'} = H$ $R^{a'} = R^{c'} = C_1$ to C_6 alkoxy
Case 2		
Case 3		

Case 4	R^5 , R^6 and R^7 are H or C_1 to C_4 alkyl groups; or C_1 to C_4 alkoxy groups; or cyano groups; or isopropyl cyano groups.	(i) $R^a = R^c =$ methoxy (ii) $R^a = R^c =$ ethoxy
Case 1	$R^{1'}$, $R^{2'}$, $R^{3'}$ and $R^{4'}$ are C_1 to C_{14} alkyl group, preferably n-octyl groups $R^{1'}$, $R^{2'}$, $R^{3'}$ and $R^{4'}$ are C_1 to C_{14} alkyl group, preferably n-octyl groups	R^b , $R^d =$ H R^a , R^c , $R^e = C_1$ to C_6 alkoxy (i) R^a , R^c , $R^e =$ methoxy (ii) R^a , R^c , $R^e =$ ethoxy
Case 2		
Case 3		
Case 4		
Case 1	$R^{1'}$, $R^{2'}$, $R^{3'}$ and $R^{4'}$ are C_1 to C_{14} alkyl group, preferably n-octyl groups	R^a , $R^e =$ H R^b , R^c , $R^d = C_1$ to C_6 alkoxy (i) R^b , R^c , $R^d =$ methoxy (ii) R^b , R^c , $R^d =$ ethoxy
Case 2		
Case 3		
Case 4		
Case 1		R^b , R^c , R^d , $R^e =$ H $R^a =$ Cyano (CN)
Case 2		
Case 3		
Case 4		
Case 1	$R^{1'}$, $R^{2'}$, $R^{3'}$ and $R^{4'}$ are C_1 to C_{14} alkyl group, preferably n-octyl groups	R^b , R^c , R^d , $R^e =$ H $R^a =$ Isopropylcyano group Monomer C: 
Case 2		
Case 3		
Case 4		
Case 1	$R^{1'}$, $R^{2'}$, $R^{3'}$ and $R^{4'}$ are C_1 to C_{14} alkyl group, preferably n-octyl groups	R^a , R^b , R^d , $R^e =$ H $R^c =$ Isopropylcyano group Monomer C: 
Case 2		
Case 3		
Case 4		
Case 4	R^5 , R^6 and R^7 are H or C_1 to C_4 alkyl groups; or C_1 to C_4 alkoxy groups; or cyano groups; or isopropyl cyano groups.	

The organic semiconductor compounds specified in the table are particularly preferred as they combine the beneficial properties of high charge transport mobility (of the binders) with a polarity that is more compatible with benign, non-chlorinated solvents that will be desirable for use in large area printing. In addition,
5 as these compounds are more polar once deposited as the OSC layer, or alternatively as a component in the OSC layer, they are expected to be resistant to being re-dissolved by the hydrophobic solvents used for the organic gate insulators (OGI) such as Cytop. Furthermore, it is expected that the polar binders are useful for both top gate and bottom gate OTFTs, particularly for bottom gate OTFTs.

10 The copolymers according to the present invention preferably have a number average molecular weight (Mn) of between 500 and 100,000, more preferably between 1600 and 20000, more preferably between 500 and 10000, even more preferably between 850 and 5000.

The copolymers according to the present invention preferably have between 1 and
15 100000 monomer units having the Formula (A) and between 1 and 100000 cis/trans-indenofluorene monomer units having the Formula (O). More preferably, the copolymers have between 1 and 1000 monomer units having the Formula (A) and between 1 and 1000 cis/trans-indenofluorene monomer units having the Formula (O). More preferably, the copolymers have between 1 and 100 monomer
20 units having the Formula (A) and between 1 and 100 cis/trans-indenofluorene units having the Formula (O). Yet even more preferably, the copolymers have between 1 and 10 monomer units having the Formula (A) and between 1 and 10 cis/trans-indenofluorene monomer units having the Formula (O).


Preferably, the organic semiconductor compositions according to the present
25 invention contain less than 10% by weight, more preferably less than 5% by weight, more preferably less than 1%, more preferably, substantially no organic binders which have a permittivity at 1000 Hz of less than 3.4.

Preferred PAHCs and compositions of the present invention contain at least 20 wt. %, more preferably at least 20-40 wt. % (of the total of all monomer units (A)
30 and (O) in the copolymer or composition) of a heteroacene monomer unit having the Formula (A) and at least 20 wt. %, preferably at least 20-80 wt. %, more preferably at least 50 wt. %, and even more preferably at least 60-80 wt.% of a monomer unit having the Formula (O).

Preferred PAHCs and compositions of the present invention contain at least 40
35 wt. % (of the total of all monomer units (A) and (O) in the copolymer or composition)

of a BXB monomer unit having the Formula (A) and at least 40 wt. %, preferably 60 wt. % of a monomer unit having the Formula (O). Preferred PAHCs contain monomer unit (O) as the major component.

The BXB copolymers may be produced according to the following general synthetic regime. For simplicity, a representative BXB monomer is shown (no further substitutions are shown, the skilled person understanding how this can be genericised to the structures shown above) being coupled to a representative cis/trans-indenofluorene monomer. The coupling reaction is preferably a Yamamoto type coupling (using Nickel chloride, zinc, 2,2'-bipyridyl, triphenylphosphine and dimethyl acetamide). However, Suzuki coupling is also possible, although in this case it is preferable to remove the boronic esters from the resulting semiconducting polymer.




15

General Synthesis Route to the PAHC

wherein α and β are preferably integers of 1-100000; R' has the same definition as for R^1 , R^2 , R^3 and R^4 group defined below. The halogen end groups are preferentially reacted either by substitution or hydrogenation.

47




Alternative Synthesis Route to the PAHC

wherein α and β are preferably integers of 1-100000; R' has the same definition as for R^1 , R^2 , R^3 and R^4 group defined below. On completion of the coupling reaction, the halogen and boronic ester end groups are preferably substituted by other groups, for example by hydrogenation and/or hydrolysis respectively.

Following the polymerization step to form the copolymer of the present invention, the copolymer may be cross-linked. Cross-linking may be achieved by any known technique. Examples include the application of heat and/or moisture, ethylene oxide treatment, UV irradiation, gamma sterilisation, electron beam irradiation, and autoclaving.


Thus, according to another aspect of the present invention, there is provided a process for producing a Polycyclic Aromatic Hydrocarbon Copolymer (PAHC) comprising copolymerising a composition containing at least one BXB monomer unit selected from the structure A':

48




Structure A'

and at least one monomer unit selected from the structure O':



5




Structure (O/O')'

wherein each of R and R' groups, and k and l have the same general and preferred meanings as described in relation to the PAHC definitions above; wherein preferably
 10 at least one of and R^{1'}, R^{2'}, R^{3'}, R^{4'}, R^{5'}, R^{6'}, R^{7'} is a polar group or more polarising group; and

wherein X' is a halogen atom or a cyclic borate group; and

wherein Z' is a halogen atom.

Preferably, the cyclic borate group is



15

Preferably, the process is carried out in a solvent, preferably an organic solvent, preferably an aromatic organic solvent.

The compositions of the present invention can comprise additional curable monomers, for example, diluent monomers. Examples of suitable materials include
5 radically curable monomer compounds, such as acrylate and methacrylate monomer compounds. Examples of acrylate and methacrylate monomers include isobornyl acrylate, isobornyl methacrylate, lauryl acrylate, lauryl methacrylate, isodecylacrylate, isodecylmethacrylate, caprolactone acrylate, 2-phenoxyethyl acrylate, isooctylacrylate, isooctylmethacrylate, butyl acrylate, alkoxyated lauryl
10 acrylate, ethoxylated nonyl phenol acrylate, ethoxylated nonyl phenol methacrylate, ethoxylated hydroxyethyl methacrylate, methoxy polyethylene glycol monoacrylate, methoxy polyethylene glycol monomethacrylate, tetrahydrofurfuryl methacrylate, as well as mixtures or combinations thereof.

In addition, multifunctional acrylate and methacrylate monomers and oligomers can
15 be included in the compositions as reactive diluents and as materials that can increase the crosslink density of the cured composition. Examples of suitable multifunctional acrylate and methacrylate monomers and oligomers include pentaerythritol tetraacrylate, pentaerythritol tetramethacrylate, 1,2-ethylene glycol diacrylate, 1,2-ethylene glycol dimethacrylate, 1,6-hexanediol diacrylate, 1,6-
20 hexanediol dimethacrylate, 1,12-dodecanol diacrylate, 1,12-dodecanol dimethacrylate, tris(2-hydroxy ethyl) isocyanurate triacrylate, propoxylated neopentyl glycol diacrylate, hexanediol diacrylate, tripropylene glycol diacrylate, dipropylene glycol diacrylate, ethoxylated bisphenol A diacrylate, ethoxylated bisphenol A dimethacrylate, alkoxyated hexanediol diacrylate, alkoxyated cyclohexane
25 dimethanol diacrylate, polyethylene glycol diacrylate, polyethylene glycol dimethacrylate, tris (2-hydroxy ethyl) isocyanurate triacrylate, amine modified polyether acrylates (available as PO 83 F®, LR 8869®, and/or LR 8889® (all available from BASF Corporation), trimethylolpropane triacrylate, glycerol propoxylate triacrylate, dipentaerythritol pentaacrylate, dipentaerythritol
30 hexaacrylate, ethoxylated pentaerythritol tetraacrylate (available from Sartomer Co. Inc. as SR 494®), as well as mixtures and combinations thereof. When a reactive diluent is added to the composition of the present invention, the reactive diluent is added in any desired or effective amount, in one embodiment at least about 1 percent by weight of the carrier, at least about 35 percent by weight of the carrier, no
35 more than about 98 percent by weight of the carrier, no more than about 75 percent

by weight of the carrier, although the amount of diluent can be outside of these ranges.

Copolymers according to the present invention may have a permittivity at 1000 Hz of greater than 1.5, preferably greater than 2, preferably greater than 3. Particularly preferably, copolymers according to the present invention are semiconducting copolymers having a permittivity at 1000 Hz of between 1.5 and 8, more preferably between 3.4 and 8. In a preferred embodiment, the polyacene copolymers have a permittivity at 1000 Hz of between 3.4 and 7, more preferably between 3.4 and 6.5, yet more preferably between 3.4 and 4.5 and even more preferably between 3.4 and 4.0. Copolymers according to the present invention are preferably semiconducting copolymers and may have a permittivity at 1000 Hz of greater than 3.4, for example greater than 3.8, greater than 4.0, greater than 4.2 and the like.

Preferably, the organic semiconductor compositions according to the present invention contain less than 10% by weight, more preferably less than 5% by weight, more preferably less than 1% by weight, more preferably, substantially no copolymers which have a permittivity at 1000 Hz of less than 3.4. In a preferred embodiment, the permittivity is determined by the method disclosed in WO 2004/102690 or by using the method disclosed herein, preferably by using the method disclosed herein.

Preferably, the copolymers of the present invention are semiconducting copolymers having a permittivity at 1000 Hz of between 3.4 and 8. In a preferred embodiment, the copolymers have a permittivity at 1000 Hz of between 3.4 and 7, more preferably between 3.4 and 6.5, and even more preferably between 3.4 and 4.5. The permittivity of the copolymers can be measured using any standard method known to those skilled in the art. In a preferred embodiment, the permittivity is determined by the method disclosed in WO 2004/102690 or by using the method disclosed herein, preferably by using the method disclosed herein.

Monomer Units of Formula (A)

The preferred characteristics of the BXB monomer units (A) are as defined above, except that any reference to monomer (B) should be considered to be a reference to monomer (O), in accordance with the second aspect of the present invention.

Monomer Units (O)/(O')

The following are some preferred characteristics of the cis/trans-indenofluorene monomer unit defined above as (O)/(O').

In monomer unit (O)/(O'), preferably each R^1 , R^2 , R^3 , R^4 , R^5 , R^6 and R^7 , each of which may be the same or different, is selected from hydrogen; a branched or unbranched, substituted or unsubstituted C_1 - C_{10} alkyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{10} alkenyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{10} alkynyl group; an optionally substituted C_3 - C_{10} cycloalkyl group; an optionally substituted C_6 - C_{10} aryl group; an optionally substituted C_1 - C_{10} heterocyclic group; an optionally substituted C_1 - C_{10} heteroaryl group; an optionally substituted C_1 - C_{10} alkoxy group; an optionally substituted C_6 - C_{10} aryloxy group; an optionally substituted C_7 - C_{10} alkylaryloxy group; an optionally substituted C_2 - C_{10} alkoxycarbonyl group; an optionally substituted C_7 - C_{20} aryloxycarbonyl group; a cyano group (-CN); a carbamoyl group (-C(=O)NR¹⁵R¹⁶); a carbonyl group (-C(=O)-R¹⁷); a carboxyl group (-CO₂R¹⁸); a cyanate group (-OCN); an isocyano group (-NC); an isocyanate group (-NCO); a thiocyanate group (-SCN) or a thioisocyanate group (-NCS); an optionally substituted amino group; a hydroxy group; a nitro group; a CF₃ group; a halo group (Cl, Br, F, I); -SR¹⁹; -SO₃H; -SO₂R²⁰; -SF₅; an optionally substituted silyl group; a C_2 - C_{10} alkynyl group substituted with a SiH₂R²² group, a C_2 - C_{10} alkynyl substituted with a SiHR²²R²³ group, or a C_2 - C_{10} alkynyl substituted with a -Si(R²²)_x(R²³)_y(R²⁴)_z group, wherein each of x, y and z, and R¹⁵, R¹⁶, R¹⁸, R¹⁹ and R²⁰, R²², R²³ and R²⁴ are as defined above.

In monomer unit (O)/(O'), preferably each R^1 , R^2 , R^3 , R^4 , each of which may be the same or different, is H, methyl, methoxy, cyano, cyanomethyl, preferably H.

Preferably, in monomer unit (O)/(O'), at least one of R^1 , R^2 , R^3 , R^4 , R^5 , R^6 and R^7 is a polar or more polarising group and n = 1 to 100, preferably 1 to 50, preferably 1 to 20, even more preferably 1 to 10 and more preferably 1 to 5, wherein n refers to the number of monomer units. Preferably, at least one of R^1 , R^2 , R^3 , R^4 , R^5 , R^6 and R^7 , more preferably at least two of R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 are polar or polarising groups.

In a preferred embodiment, the one or more polar or polarising group(s) is independently selected from the group consisting of nitro group, nitrile group, C_{1-40} alkyl group substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; a C_{1-40} alkoxy group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; a C_{1-40} carboxylic acid group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; a C_{2-40}

carboxylic acid ester optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; sulfonic acid optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; sulfonic acid ester optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; cyanate group, isocyanate group, thiocyanate group, thioisocyanate group; and an amino group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; and combinations thereof.

In a more preferred embodiment, the one or more polar or polarising group(s) is independently selected from the group consisting of nitro group, nitrile group, C₁₋₁₀ alkyl group substituted with a nitrile group, a cyanate group, or an isocyanate group; C₁₋₂₀ alkoxy group, C₁₋₂₀ carboxylic acid group, C₂₋₂₀ carboxylic acid ester; sulfonic acid ester; cyanate group, isocyanate group, thiocyanate group, thioisocyanate group, and an amino group; and combinations thereof.

More preferably the polar or polarizing group is selected from the group consisting of C₁₋₄ cyanoalkyl group, C₁₋₁₀ alkoxy group, nitrile group and combinations thereof.

More preferably the polar or polarizing group(s) is selected from the group consisting of cyanomethyl, cyanoethyl, cyanopropyl, cyanobutyl, methoxy, ethoxy, propoxy, butoxy, nitrile, NH₂ and combinations thereof. Preferably at least one of the R^{1'}, R^{2'}, R^{3'}, R^{4'}, R^{5'}, R^{6'}, R^{7'} groups is a polar or more polarising group, which may be the same or different.

Yet more preferably, the polar or polarizing group(s) is selected from the group consisting of isopropyl cyano, cyclohexylcyano, methoxy, ethoxy, nitrile and combinations thereof. Preferably at least one of R^{1'}, R^{2'}, R^{3'}, R^{4'}, R^{5'}, R^{6'}, R^{7'} is a polar or more polarising group, which may be the same or different.

More preferably, the polar group or polarizing group(s) is selected from the group consisting of methoxy, ethoxy, propoxy, butoxy and combinations thereof, wherein at least one of R^{1'}, R^{2'}, R^{3'}, R^{4'}, R^{5'}, R^{6'}, R^{7'} is a polar or more polarising group, which may be the same or different.

More preferably, the polar or polarizing group(s) is selected from the group consisting of methoxy and ethoxy, wherein at least one of R^{1'}, R^{2'}, R^{3'}, R^{4'}, R^{5'}, R^{6'},

$R^{7'}$ is the same polar or more polarising group. Yet more preferably, at least one of $R^{5'}$, $R^{6'}$, $R^{7'}$ is the same polar or more polarising group.

Preferably, $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$, $R^{5'}$, $R^{6'}$, $R^{7'}$, are independently selected from the groups consisting of C_{1-2} alkoxy, C_{1-3} cyanoalkyl, CN and mixtures thereof, and $n = 1$ to 10.

- 5 Preferably, $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$, $R^{5'}$, $R^{6'}$, $R^{7'}$, are independently selected from the group consisting of C_{1-4} alkoxy, C_{3-20} cycloalkylcyano, C_{1-4} cyanoalkyl, CN and mixtures thereof, and $n = 1$ to 10.

Preferably, $R^{5'}$, $R^{6'}$ and $R^{7'}$, is independently selected from the group consisting of 1 C_{1-4} alkoxy, and $n = 1$ to 10.

- 10 Preferably, $R^{5'}$, $R^{6'}$ and $R^{7'}$, are independently selected from the group consisting of methoxy, ethoxy, cyanomethyl, cyanoethyl, CN and mixtures thereof, and $n = 1$ to 10.

In an even more preferred embodiment of the present invention, the monomer unit (O)/(O') comprises at least one substituent that is methoxy, or cyano,

- 15 Preferably, $R^{4'}$ is independently selected from the group consisting of 1 C_{1-4} alkoxy, and $n = 1$ to 10.

Preferably, $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$, $R^{5'}$, $R^{6'}$, $R^{7'}$ are independently selected from methoxy, ethoxy, isopropylcyano, cyanomethyl, cyanoethyl, CN and mixtures thereof, and $n = 1$ to 10.


- 20 Preferably, $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$, $R^{5'}$, $R^{6'}$, $R^{7'}$ are independently selected from methoxy, ethoxy, cyanomethyl, CN and mixtures thereof, and $n = 1$ to 10.

Preferably, $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$, $R^{5'}$, $R^{6'}$, $R^{7'}$ are independently selected from methoxy, ethoxy and mixtures thereof, and $n = 1$ to 10.

- 25 The copolymers of the present invention may be a random or block copolymer of different monomer units. In such a case, any monomer unit defined by Formula (A) or (O)/(O'), may be combined with a different or same monomer unit of (A) or (O)/(O') provided that at least one monomer unit (A) is bonded to at least one monomer unit (O)/(O').


- 30 The ratio of the monomers in the polycyclic aromatic hydrocarbon copolymers can be altered to allow for adjustment of the permittivity relative to a homopolymer. Furthermore, optionally the monomer unit of (A) or (O)/(O') may be mixed with monomer units which do not meet the definition of (A) or (O)/(O'), provided that the

average permittivity of the binder in the compositions is preferably between 3.4 and 8.0. In this regard, other suitable monomer units include arylamine monomers such as (P), fluorene monomers such as (Q) and spirobifluorene monomers such as (R):




5

(P)



(Q)



(R)

- 10 wherein each $\text{R}^{1''}$, $\text{R}^{2''}$, $\text{R}^{3''}$ and $\text{R}^{4''}$, each of which may be the same or different, is selected from the same group as R^1 , R^2 , R^3 and R^4 , already defined above;

Ar_1 , Ar_2 and Ar_3 , which may be the same or different, each represent, independently an optionally substituted C_{6-40} aromatic group (mononuclear or polynuclear). Preferably at least one of Ar_1 , Ar_2 and Ar_3 is substituted with at least one polar or more polarising group, and $n = 1$ to 20, preferably 1 to 10 and more preferably 1 to 5. Preferably, at least one of Ar_1 , Ar_2 and Ar_3 is substituted with 1, 2, 3, or 4, more preferably 1, 2 or 3, more preferably 1 or 2, preferably 1 polar or more polarising group(s); and

$n'' = 1$ to 3.

- 20 When the PAHC according to the present invention comprises one or more monomers (P), (Q) and/or (R), the PAHC is comprised of monomer (A) in an amount

of at least 20 wt. %; monomer (O) in an amount of at least 60 wt. % and the remainder is comprised of monomers (P), (Q) and/or (R), based on the total weight of all monomer units in the copolymer.

Organic Semiconductor Compositions

- 5 The present invention is also concerned with organic semiconductor compositions. In a first aspect of the present invention, the organic semiconductor composition comprises a PAHC comprising a mixture of at least one BXB monomer unit having the Formula (A) and at least one monomer unit having the Formula (B). In a second aspect of the present invention, the organic semiconductor composition comprises a
- 10 PAHC comprising a mixture of at least one BXB monomer unit having the Formula (A) and at least one monomer unit having the Formula (K). In a third aspect of the present invention, the organic semiconductor composition comprises a PAHC comprising a mixture of at least one BXB monomer unit having the Formula (A) and at least one monomer unit having the Formula (O).
- 15 An organic semiconductor composition according to the present invention comprises a copolymer composition, the composition having a permittivity at 1000 Hz of greater than 1.5, more preferably greater than 3.4, and yet more preferably between 1.5 and 6.5, even more preferably between 3 and 6.5, more preferably between 3.0 to 5.0 and still more preferably between 3.4 to 4.5.
- 20 The organic semiconductor composition according to the present invention can comprise a polycyclic aromatic hydrocarbon copolymer as herein disclosed. In a preferred embodiment, an organic semiconductor composition may comprise a copolymer as defined herein, further comprising a polycrystalline polyacene small molecule semiconductor as described in our application WO 2012/164282, wherein
- 25 the PAHC has a permittivity at 1000 Hz of between 3.4 and 8, preferably between 3.4 and 6.5, more preferably between 4 and 6.5, yet more preferably between 3.4 to 4.5. In a preferred embodiment, a copolymer as defined herein may be used in combination with a polyacene small molecule or a benzodichalcogenophenobenzodichalcogenophene 'BXB' small molecule, where
- 30 the 'dried state' composition contains between 10 to 50% of the polyacene small molecule and 10 to 90% of the PAHC.

The organic semiconductor composition according to the present invention can comprise a polycyclic aromatic hydrocarbon copolymer as herein disclosed. In a preferred embodiment, an organic semiconductor composition may comprise a

35 copolymer as defined herein, further comprising an organic binder, wherein the

organic binder has a permittivity at 1000 Hz of between 3.4 and 8, preferably between 3.4 and 6.5, more preferably between 4 and 6.5, yet more preferably between 3.4 to 4.5.

- 5 In a particularly preferred embodiment, a copolymer as defined herein may be used in combination with an organic binder, wherein the organic binder has a permittivity at 1000 Hz of between 3.4 and 8.0, preferably between 3.6 and 6.5, more preferably between 3.4 to 4.5.

In yet another preferred embodiment, a copolymer of the invention preferably has a permittivity at 1000 Hz of between 3.4 and 8.0, preferably between 3.4 and 4.5.

- 10 The concentration of the copolymer and solvent present in the composition will vary depending on the preferred solution coating method, for example ink jet printing compositions require low viscosity, low solids loading compositions, whilst screen printing processes require high viscosity, high solids loading compositions. Following deposition of the copolymer composition, the solvent is preferably
- 15 evaporated to afford the semiconductor layer having 1-99.9% by weight of the binder and 0.1 to 99% by weight of the copolymer (in the printed or dried state) based on a total weight of the composition; preferably the semiconductor layer having 25 to 75% by weight of the small molecule polyacene and 25 to 75% by weight of the copolymer.
- 20 In the composition prior to deposition, one or more of the above-described PAHCs is preferably present at a concentration of at least 0.1 wt%, preferably 0.5 wt% based on a total weight of the composition. The upper limit of the concentration of the PAHC in the composition is often near the solubility limit of that copolymer in the particular solvent at the temperature of the composition during its application to a
- 25 substrate such as in the fabrication of an electronic device. Typical compositions of the present invention comprise one of the PAHCs at a concentration ranging from about 0.1 wt%, preferably 0.5 wt% to about 20.0 wt% based on a total weight of the composition, more typically, from about 0.5 wt% to about 10.0 wt%, more typically 0.5 to 5.0, more typically 1 to 3 wt%.
- 30 In the printed or dried composition, one or more of the above-described PAHCs is preferably present at a concentration of at least 10 wt% based on a total weight of the composition, preferably between 10 and 90 wt%, more preferably between 20 and 80 wt%, more preferably between 30 and 70 wt%, more preferably between 40 and 60 wt%.

In a preferred embodiment, one or more solvents may be present in the organic semiconductor compositions.

Suitable solvents include, but are not limited to, tetrahydrofuran, aromatic hydrocarbons such as toluene, o-xylene, m-xylene, p-xylene, mesitylene, bromomesitylene, anisole, bromoanisole, bromobenzene, tetralin, o-xylene, 1,4-dioxane, methylethylketone, gamma-butyrolactone, cyclohexanone, morpholine, N-methylpyrrolidone, ethyl acetate, n-butyl acetate, dimethylformamide, dimethylacetamide, decalin or mixtures of two or more thereof. Preferably, no chlorinated solvents are used.

Solvent blends may also be utilised. Suitable solvent blends include, but are not limited to compositions of the above solvents in conjunction with solvents such as dimethylformamide, dimethylacetamide, dimethylsulfoxide, methyl ethyl ketone, dichloromethane, dichlorobenzene, furfuryl alcohol, dimethoxyethane and ethyl acetate, higher boiling point alkanes such as n-heptane and alcohols such as isopropyl alcohol. Such compositions (prior to deposition) preferably contain a suitable solvent in an amount of greater than 50 wt% based on a total weight of the composition, preferably between 60 and 95 wt% based on a total weight of the composition.

In yet another preferred embodiment, one or more additional composition components may be present in the organic semiconductor composition. Suitable additional composition components include, but are not limited to, a polymer additive, a rheological modifier, a surfactant, another semiconductor that is a matched hole transfer compound for the copolymer. In some exemplary embodiments, the compositions comprise a polymer additive selected from the group consisting of polystyrene, poly(alpha-methylstyrene), poly(pentafluorostyrene), poly(methyl methacrylate), poly(4-cyanomethyl styrene), poly(4-vinylphenol), or any other suitable polymer disclosed in U.S. Patent Application Publication No. 2004/0222412 A1 or U.S. Patent Application Publication No. 2007/0146426 A1. In some desired embodiments, the polymer additive comprises polystyrene, poly(alpha-methylstyrene), poly(pentafluorostyrene) or poly(methyl methacrylate). In some exemplary embodiments, the compositions comprise a surfactant selected from fluorinated surfactants or fluorosurfactants. When present, each additional composition component is independently present in an amount of greater than 0 to about 50 wt% based on a total weight of the composition. Preferably, each additional composition component is independently present in an amount ranging from about 0.0001 to about 10.0 wt% based on a total

weight of the composition. For example, when a polymer is present in the composition, the polymer additive is typically present in an amount of greater than 0 to about 5.0 wt%, preferably from about 0.5 to about 3.0 wt% based on a total weight of the composition. For example, when a surfactant is present in the composition, the surfactant is preferably present in an amount of greater than 0 to about 1.0 wt%, more typically, from about 0.001 to about 0.5 wt% based on a total weight of the composition.

The organic semiconductor composition according to the present invention preferably has a charge mobility value of at least $0.5 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$, preferably between 0.5 and $8.0 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$, more preferably between 0.5 and $6.0 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$, more preferably between 0.8 and $5.0 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$, more preferably between 1.0 and $5.0 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$, more preferably between 1.5 and $5.0 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$, more preferably between 2.0 and $5.0 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$. The charge mobility value of the semiconductor composition can be measured using any standard method known to those skilled in the art, such as techniques disclosed in *J. Appl. Phys.*, 1994, Volume 75, page 7954 and WO 2005/055248, preferably by those described in WO 2005/055248.

The organic semiconductor composition according to the present invention may be prepared by any known method within the common general knowledge of a person skilled in the art. In a preferred embodiment, the organic semiconductor composition is prepared by the method disclosed in WO 2005/055248 or by using the method disclosed herein, preferably by using the method disclosed herein.

Preferably, organic semiconductor compositions according to the present invention are semiconducting compositions having a permittivity at 1000 Hz greater than 1.5, more preferably greater than 3.4, and yet more preferably, between 3.4 and 8. In a preferred embodiment, the compositions have a permittivity at 1000 Hz of between 4.0 and 7, more preferably between 4.0 and 6.5, even more preferably between 4.0 and 6 and yet more preferably between 3.4 and 4.5.

Organic Semiconductor Layers

The present invention is also concerned with organic semiconductor layers. In a first aspect of the present invention, the organic semiconductor layer comprises a PAHC comprising a mixture of at least one BXB monomer unit having the Formula (A) and at least one monomer unit having the Formula (B). In a second aspect of the present invention, the organic semiconductor layer comprises a PAHC comprising a mixture of at least one BXB monomer unit having the Formula (A) and at least one monomer unit having the Formula (K). In a third aspect of the

present invention, the organic semiconductor layer comprises a PAHC comprising a mixture of at least one BXB monomer unit having the Formula (A) and at least one monomer unit having the Formula (O).

The organic semiconductor compositions according to the present invention may be deposited onto a variety of substrates, to form organic semiconductor layers.

The organic semiconductor layer according to the present invention may be prepared using a method comprising the steps of:

- (i) Mixing the organic semiconductor composition according to the present invention with a solvent to form a semiconductor layer formulation;
- 10 (ii) Depositing said formulation onto a substrate; and
- (iii) Optionally removing the solvent to form an organic semiconductor layer.

Useful substrate materials include, but are not limited to, polymeric films such as polyamides, polycarbonates, polyimides, polyketones, polyethylene terephthalate (PET) and polyethylene naphthalate (PEN), and inorganic substrates such as silica, alumina, silicon wafers and glass. The surface of a given substrate may be treated, e.g. by reaction of chemical functionality inherent to the surface with chemical reagents such as silanes or exposure of the surface to plasma, in order to alter the surface characteristics.

Prior to depositing the organic semiconductor composition onto the substrate, the composition may be combined with one or more solvents in order to facilitate the deposition step. Suitable solvents include any solvent which is able to dissolve both the copolymer, and which upon evaporation from the solution blend, give a coherent, defect-free layer. Suitable solvents for the copolymer can be determined by preparing a contour diagram for the material as described in ASTM Method D 3132 at the concentration at which the mixture will be employed. The material is added to a wide variety of solvents as described in the ASTM method.

Suitable solvents include, but are not limited to, tetrahydrofuran, aromatic hydrocarbons such as toluene, o-xylene, m-xylene, p-xylene, mesitylene, bromomesitylene, anisole, bromoanisole, bromobenzene, tetralin, o-xylene, 1,4-dioxane, methylethylketone, gamma-butyrolactone, cyclohexanone, morpholine, N-methylpyrrolidone, ethyl acetate, n-butyl acetate, dimethylformamide, dimethylacetamide, decalin or mixtures of two or more thereof. Preferably, no chlorinated solvents are used.

In accordance with the present invention it has further been found that the level of the solids content in the organic semiconducting layer formulation is also a factor in achieving improved mobility values for electronic devices such as OFETs. The solids content of the formulation is commonly expressed as follows:

5 Solids content (%) = $\frac{a+b}{a+b+c} \times 100$

wherein: a = mass of polyacene small molecule, b = mass of PAHC and c = mass of solvent.

The solids content of the formulation is preferably 0.1 to 10% by weight, more preferably 0.5 to 5% by weight.

- 10 Suitable conventional deposition methods include, but are not limited to, spin coating, spray coating, blade/slot-die coating, flexographic printing, gravure printing, roll-to-roll web-coating, and dip coating, as well as printing processes such as ink-jet printing, screen printing, and offset lithography. In one desired embodiment, the resulting composition is a printable composition, even more desirably, an ink jet
15 printable composition.

- Once the composition is deposited onto a substrate surface, the solvent may be removed to form an organic semiconductor layer. Any suitable method may be used to remove the solvent. For example, the solvent may be removed by evaporation or drying. Typically, at least about 80 percent of the solvent is removed to form the
20 semiconductor layer. For example, at least about 85 weight percent, at least about 90 weight percent, at least about 92 weight percent, at least about 95 weight percent, at least about 97 weight percent, at least about 98 weight percent, at least about 99 weight percent, or at least about 99.5 weight percent of the solvent is removed.

- 25 The solvent often can be evaporated at any suitable temperature. In some methods, the solvent mixture is evaporated at ambient temperature. In other methods, the solvent is evaporated at a temperature higher or lower than ambient temperature. For example, a platen supporting the substrate can be heated or cooled to a temperature higher or lower than ambient temperature. In still other
30 preferred methods, some or most of the solvent can be evaporated at ambient temperature, and any remaining solvent can be evaporated at a temperature higher than ambient temperature. In methods where the solvent evaporates at a

temperature higher than ambient temperature, the evaporation can be carried out under an inert atmosphere, such as a nitrogen atmosphere.

Alternatively, the solvent can be removed by application of reduced pressure (i.e., at a pressure that is less than atmospheric pressure) such as through the use of a vacuum. During application of reduced pressure, the solvent can be removed at any suitable temperature such as those described above.

The rate of removal of the solvent can affect the resulting semiconductor layer. For example, if the removal process is too rapid, poor packing of the semiconductor molecules can occur during crystallisation. Poor packing of the semiconductor molecules can be detrimental to the charge mobility of the semiconductor layer. The solvent can evaporate entirely on its own in an uncontrolled fashion (i.e., no time constraints), or the conditions can be controlled in order to control the rate of evaporation. In order to minimise poor packing, the solvent can be evaporated while slowing the evaporation rate by covering the deposited layer. Such conditions can lead to a semiconductor layer having a relatively high degree of crystallinity.

After removal of a desired amount of solvent to form the semiconductor layer, the semiconductor layer can be annealed by exposure to heat or solvent vapours, i.e., by thermal annealing or solvent annealing.

The organic semiconductor layer according to the present invention preferably has a charge mobility value of at least $0.5 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$, preferably between 0.5 and $8.0 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$, more preferably between 0.5 and $6.0 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$, more preferably between 0.8 and $5.0 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$, more preferably between 1 and $5.0 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$, more preferably between 1.5 and $5.0 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$, more preferably between 2.0 and $5.0 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$. The charge mobility value of the semiconductor layer can be measured using any standard method known to those skilled in the art, such as techniques disclosed in *J. Appl. Phys.*, 1994, Volume 75, page 7954 and WO 2005/055248, preferably by those described in WO 2005/055248.

Preferably, the organic semiconductor layer(s) of the present invention are semiconducting layers having a permittivity at 1000 Hz of between 3.4 and 8. In a preferred embodiment, the layer(s) have a permittivity at 1000 Hz of between 4.0 and 7, more preferably between 4.0 and 6.5, yet more preferably between 4.0 and 6 and even more preferably between 3.4 and 4.5

Electronic Devices

The invention additionally provides an electronic device comprising the organic semiconductor composition according to the present invention. In a first aspect of the present invention, the electronic device may comprise an organic semiconductor composition comprising a PAHC comprising a mixture of at least one BXB monomer unit having the Formula (A) and at least one monomer unit having the Formula (B). In a second aspect of the present invention, the electronic device may comprise an organic semiconductor composition comprising a PAHC comprising a mixture of at least one BXB monomer unit having the Formula (A) and at least one monomer unit having the Formula (K). In a third aspect of the present invention, the electronic device may comprise an organic semiconductor composition comprising a PAHC comprising a mixture of at least one BXB monomer unit having the Formula (A) and at least one monomer unit having the Formula (O).

The composition may be used, for example, in the form of a semiconducting layer or film. Additionally, the invention preferably provides an electronic device comprising the organic semiconductor layer according to the present invention.

The thickness of the layer or film may be between 0.02 and 20 microns, 0.2 and 20 microns, preferably between 0.05 and 10 microns, preferably between 0.5 and 10 microns, between 0.05 and 5 microns, even more preferably between 0.5 and 5 microns, yet more preferably between 0.5 and 2 microns, and more preferably between 0.02 and 1 microns.

The electronic device may include, without limitation, organic field effect transistors (OFETS), organic light emitting diodes (OLEDs), photodetectors, organic photovoltaic (OPV) cells, sensors, lasers, memory elements and logic circuits.

Exemplary electronic devices of the present invention may be fabricated by solution deposition of the above-described organic semiconductor composition onto a substrate.

Detailed Description of the Invention

General

For the heteroacene monomers used in the invention whilst one isomer is shown the invention applies to pure cis isomer, pure trans isomer and mixtures of cis and trans isomers.

The term "about" in relation to a numerical value x means, for example, $x \pm 10\%$.

The word “substantially” does not exclude “completely” e.g. a composition which is “substantially free” from Y may be completely free from Y. Where necessary, the word “substantially” may be omitted from the definition of the invention.

- 5 "Molecular weight" of a polymeric material (including monomeric or macromeric materials), as used herein, refers to the number-average molecular weight unless otherwise specifically noted or unless testing conditions indicate otherwise.

A "polymer" means a material formed by polymerising and/or crosslinking one or more monomers, macromers and/or oligomers and having two or more repeat units.

- 10 As used herein, the term “alkyl” group refers to a straight or branched saturated monovalent hydrocarbon radical, having the number of carbon atoms as indicated. By way of non limiting example, suitable alkyl groups include, methyl, ethyl, propyl, n-butyl, t-butyl, iso-butyl and dodecanyl.

As used herein, the term “alkoxy” group include without limitation, methoxy, ethoxy, 2-methoxyethoxy, t-butoxy, etc.

- 15 As used herein, the term “amino” group includes, without limitation, dimethylamino, methylamino, methylphenylamino, phenylamino, etc.

- 20 The term “carbyl” refers to any monovalent or multivalent organic radical moiety which comprises at least one carbon atom other without any non-carbon atoms ($\text{C}\equiv\text{C}$), or optionally combined with at least one non-carbon atoms such as N, O, S, P, Si, Se, As, Te or Ge (for example carbonyl etc.).

The term “hydrocarbon” group denotes a carbyl group that additionally contains one or more H atoms and optionally contains one or more hetero atoms.

A carbyl or hydrocarbyl group comprising 3 or more carbon atoms may be linear, branched and/or cyclic, including spiro and/or fused rings.

- 25 Preferred carbyl or hydrocarbyl groups include alkyl, alkoxy, alkylcarbonyl, alkylcarbonyloxy, alkoxycarbonyloxy, each of which is optionally substituted and has 1 to 40, preferably 1 to 18 carbon atoms, furthermore optionally substituted aryl, aryl derivative or aryloxy having 6 to 40, preferably 6 to 18 carbon atoms, furthermore alkylaryloxy, arylcarbonyl, aryloxycarbonyl, arylcarbonyloxy and aryloxycarbonyloxy,
30 each or which is optionally substituted and has 7 to 40, more preferable 7 to 25 carbon atoms.

The carbyl or hydrocarbyl group may be saturated or unsaturated acyclic group, or a saturated or unsaturated cyclic group. Unsaturated acyclic or cyclic groups are preferred, especially alkenyl and alkynyl groups (especially ethynyl).

In the polyacenes of the present invention, the optional substituents on the said C₁-C₄₀ carbyl or hydrocarbyl groups for R₁-R₁₄ etc. preferably are selected from: silyl, sulpho, sulphonyl, formyl, amino, imino, nitrilo, mercapto, cyano, nitro, halo, C₁₋₄ alkyl, C₆₋₁₂ aryl, C₁₋₄ alkoxy, hydroxy and/or all chemically possible combinations thereof. More preferable among these optional substituents are silyl and C₆₋₁₂ aryl and most preferable is silyl.

10 "Substituted alkyl group" refers to an alkyl group having one or more substituents thereon, wherein each of the one or more substituents comprises a monovalent moiety containing one or more atoms other than carbon and hydrogen either alone (e.g., a halogen such as F) or in combination with carbon (e.g., a cyano group) and/or hydrogen atoms (e.g., a hydroxyl group or a carboxylic acid group).

15 "Alkenyl group" refers to a monovalent group that is a radical of an alkene, which is a hydrocarbon with at least one carbon-carbon double bond. The alkenyl can be linear, branched, cyclic, or combinations thereof and typically contains 2 to 30 carbon atoms. In some embodiments, the alkenyl contains 2 to 20, 2 to 14, 2 to 10, 4 to 10, 4 to 8, 2 to 8, 2 to 6, or 2 to 4 carbon atoms. Exemplary alkenyl groups
20 include, but are not limited to, ethenyl, propenyl, and butenyl.

"Substituted alkenyl group" refers to an alkenyl group having (i) one or more C-C double bonds, and (ii) one or more substituents thereon, wherein each of the one or more substituents comprises a monovalent moiety containing one or more atoms other than carbon and hydrogen either alone (e.g., a halogen such as F) or in
25 combination with carbon (e.g., a cyano group) and/or hydrogen atoms (e.g., a hydroxyl group or a carboxylic acid group).

"Alkynyl group" refers to a monovalent group that is a radical of an alkyne, a hydrocarbon with at least one carbon-carbon triple bond. The alkynyl can be linear, branched, cyclic, or combinations thereof and typically contains 2 to 30 carbon
30 atoms. In some embodiments, the alkynyl contains 2 to 20, 2 to 14, 2 to 10, 4 to 10, 4 to 8, 2 to 8, 2 to 6, or 2 to 4 carbon atoms. Exemplary alkynyl groups include, but are not limited to, ethynyl, propynyl, and butynyl.

"Substituted alkynyl group" refers to an alkynyl group having (i) one or more C-C triple bonds, and (ii) one or more substituents thereon, wherein each of the one or

more substituents comprises a monovalent moiety containing one or more atoms other than carbon and hydrogen either alone (e.g., a halogen such as F) or in combination with carbon (e.g., a cyano group) and/or hydrogen atoms (e.g., a hydroxyl group or a carboxylic acid group or a silyl group).

- 5 "Cycloalkyl group" refers to a monovalent group that is a radical of a ring structure consisting of 3 or more carbon atoms in the ring structure (i.e., only carbon atoms in the ring structure and one of the carbon atoms of the ring structure is the radical).

"Substituted cycloalkyl group" refers to a cycloalkyl group having one or more substituents thereon, wherein each of the one or more substituents comprises a
10 monovalent moiety containing one or more atoms (e.g., a halogen such as F, an alkyl group, a cyano group, a hydroxyl group, or a carboxylic acid group).

"Cycloalkylalkylene group" refers to a monovalent group that is a ring structure consisting of 3 or more carbon atoms in the ring structure (i.e., only carbon atoms in the ring), wherein the ring structure is attached to an acyclic alkyl group (typically,
15 from 1 to 3 carbon atoms, more typically, 1 carbon atom) and one of the carbon atoms of the acyclic alkyl group is the radical. "Substituted cycloalkylalkylene group" refers to a cycloalkylalkylene group having one or more substituents thereon, wherein each of the one or more substituents comprises a monovalent moiety containing one or more atoms (e.g., a halogen such as F, an alkyl group, a cyano
20 group, a hydroxyl group, or a carboxylic acid group).

"Aryl group" refers to a monovalent group that is a radical of an aromatic carbocyclic compound. The aryl can have one aromatic ring or can include up to 5 carbocyclic ring structures that are connected to or fused to the aromatic ring. The other ring structures can be aromatic, non-aromatic, or combinations thereof. Examples of
25 preferred aryl groups include, but are not limited to, phenyl, 2-tolyl, 3-tolyl, 4-tolyl, biphenyl, 4-phenoxyphenyl, 4-fluorophenyl, 3-carbomethoxyphenyl, 4-carbomethoxyphenyl, terphenyl, anthryl, naphthyl, acenaphthyl, anthraquinonyl, phenanthryl, anthracenyl, pyrenyl, perylenyl, and fluorenyl.

"Substituted aryl group" refers to an aryl group having one or more substituents on
30 the ring structure, wherein each of the one or more substituents comprises a monovalent moiety containing one or more atoms (e.g., a halogen such as F, an alkyl group, a cyano group, a hydroxyl group, or a carboxylic acid group).

"Arylalkylene group" refers to a monovalent group that is an aromatic ring structure consisting of 6 to 10 carbon atoms in the ring structure (i.e., only carbon atoms in

the ring structure), wherein the aromatic ring structure is attached to an acyclic alkyl group having one or more carbon atoms (typically, from 1 to 3 carbon atoms, more typically, 1 carbon atom) and one of the carbons of the acyclic alkyl group is the radical.

- 5 "Substituted arylalkylene group" refers to an arylalkylene group having one or more substituents thereon, wherein each of the one or more substituents comprises a monovalent moiety containing one or more atoms (e.g., a halogen such as F, an alkyl group, a cyano group, a hydroxyl group, or a carboxylic acid group).

"Acetyl group" refers to a monovalent radical having the formula $-C(O)CH_3$.

- 10 "Heterocyclic ring" refers to a saturated, partially saturated, or unsaturated ring structure comprising at least one of O, N, S and Se in the ring structure.

"Substituted heterocyclic ring" refers to a heterocyclic ring having one or more substituents bonded to one or more members of the ring structure, wherein each of the one or more substituents comprises a monovalent moiety containing one or
15 more atoms (e.g., a halogen such as F, an alkyl group, a cyano group, a hydroxyl group, or a carboxylic acid group).

"Carbocyclic ring" refers to a saturated, partially saturated, or unsaturated ring structure comprising only carbon in the ring structure.

- "Substituted carbocyclic ring" refers to a carbocyclic ring having one or more
20 substituents bonded to one or more members of the ring structure, wherein each of the one or more substituents comprises a monovalent moiety containing one or more atoms (e.g., a halogen such as F, an alkyl group, a cyano group, a hydroxyl group, or a carboxylic acid group).

- "Ether group" refers to a $-R_a-O-R_b$ radical wherein R_a is a branched or unbranched
25 alkylene, arylene, alkylarylene or arylalkylene hydrocarbon and R_b is a branched or unbranched alkyl, aryl, alkylaryl or arylalkyl hydrocarbon.

- "Substituted ether group" refers to an ether group having one or more substituents thereon, wherein each of the one or more substituents comprises a monovalent moiety containing one or more atoms other than carbon and hydrogen either alone
30 (e.g., a halogen such as F) or in combination with carbon (e.g., a cyano group) and/or hydrogen atoms (e.g., a hydroxyl group or a carboxylic acid group).

Unless otherwise defined, a “substituent” or “optional substituent” is preferably selected from the group consisting of halo (I, Br, Cl, F), CN, NO₂, NH₂, -COOH and OH.

Brief Description of the Drawings

- 5 Figure 1 is a representation of top contact/bottom gate organic thin film transistor (OTFT)

Figure 2 is a representation of bottom contact/bottom gate (OTFT)

Figure 3 is a representation of top contact/top gate (OTFT)

Figure 4 is a representation of bottom contact/top gate (OTFT)

- 10 Labels- A: Substrate; B: Gate electrode; C: Dielectric layer; D: Semiconductor layer; E: Source electrode; F: Gate electrode

Examples of the Present Invention

The following examples of the present invention are merely exemplary and should not be viewed as limiting the scope of the invention.

- 15 Measurement of the Capacitance of the Polymer Binder

The polymer binder was diluted with tetralin in order to lower its viscosity and make it possible to obtain a film thickness of ~1 micron when spin coated for the spin speed range 1000-2000 rpm/s. The polymer binder solution was spin coated at 500rpm for 10 seconds, followed by 1500 rpm for 30 seconds, onto ITO coated and
20 cleaned 1 x 1 inch glass substrates.

To clean the ITO coated substrates they were submerged in a 3% solution of DECon 90 and put in an ultrasonic bath (water temperature >65 °C), washed with deionised water, submerged in deionised water and put in an ultrasonic bath (water temperature >65 °C), washed a further time with deionised water, submerged in
25 isopropyl alcohol and then put in an ultrasonic bath (water temperature >65 °C), and then spin dried.

After deposition of the polymer binder the substrate was annealed on a hotplate at 120 °C for 5 minutes.

The substrate was then covered with a capacitance shadow mask, and top
30 electrodes were deposited by evaporation of gold using a thermal deposition method. In order to determine the exact thickness of the polymer binder layer, the

thickness was measured using a Dektak 3030 profilometer (available from Veeco, Plainview NY) at three different positions and averaged; these values were subsequently used to calculate the dielectric constants of the polymer binders.

Capacitance measurements were then carried out using impedance analyser Agilent 43961A and a probe station. In order to improve the electrical contact between the ITO back electrode and the external probe electrode, a conductive silver paste was applied. The sample being measured was placed in a metal box on the metal plate to ensure minimum influence from the external environment.

Before each set of measurements was obtained, the analyser was calibrated using the 43961A Impedance Test Kit as a compensation routine was carried out to account for internal capacitance of the analyser and test fixture. The measurement calibration was carried out with open and shorted circuit; the dielectric constant was calculated using the following equation:

$$C = \epsilon \times \epsilon_0 \times (A/d).$$

Wherein C is the capacitance (Farads), A is the area (m^2), d is the coating thickness (m), ϵ is the dielectric constant (permittivity), and ϵ_0 is the permittivity of free space and is taken as 8.8854×10^{-12} F/m.

As a reference sample, a polystyrene sample (Mw~350,000) having a thickness of 1 μm was tested. The measured and calculated dielectric constant of the polystyrene reference was $\epsilon=2.55$ at 10,000 Hz, which is in good agreement with the reported value ($\epsilon \sim 2.5$), refer to J. R. Wunsch, Polystyrene-Synthesis, Production and Applications, *Rapra Review Reports*, 2000, Volume 10, No. 4, page 32.

OTFT fabrication method

A substrate (either glass or a polymer substrate such as PEN) is patterned with Au source drain electrodes either by a process of thermal evaporation through a shadow mask or by photolithography (an adhesion layer of either Cr or Ti is deposited on the substrate prior to deposition of Au). The Au electrodes can the optionally be cleaned using an O_2 plasma cleaning process. A solution of organic semiconductor in binder is then applied by spin coating (the sample is flooded with the solution and the substrate is then spun at 500 rpm for 5 seconds then 1500 rpm for 1 minute). The coated substrate is then dried in air on a hot stage. The dielectric material, for example 3 wt% PTFE-AF 1600 (Sigma-Aldrich cat # 469610) dissolved in FC-43) was then applied to the substrate by spin coating (sample flooded then spun at 500 rpm for 5 seconds then 1500 rpm for 30 seconds). The

substrate was then dried in air on a hot stage (100 °C for 1 minute). A gate electrode (Au) is then defined over the channel area by evaporation through a shadow mask.

The mobility of the OTFT for the binders is characterised by placing on a manual probe station connected to a Keithley SCS 4200 semiconductor analyzer. The source drain voltage (V_{DS}) is set at -2V (linear) or -40V (saturation) and the gate voltage (V_G) scanned from +20V to -60V. Drain current is measured and mobility calculated from the transconductance.

The mobility of the OTFT for the formulations is characterised by placing on a semi-auto probe station connected to a Keithley SCS 4200 semiconductor analyzer. The source drain voltage is set at -2V and the gate voltage scanned from +20V to -40V. Drain current is measured and mobility calculated from the transconductance.

In linear regime, when $|V_G| > |V_{DS}|$, the source-drain current varies linearly with V_G . Thus the field effect mobility (μ) can be calculated from the gradient (S) of I_{DS} vs. V_G given by equation 1 (where C_i is the capacitance per unit area, W is the channel width and L is the channel length):

$$S = \frac{\mu W C_i V_{DS}}{L} \quad \text{Equation 1}$$

In the saturation regime, the mobility is determined by finding the slope of $I_{DS}^{1/2}$ vs. V_G and solving for the mobility (Equation 2)

$$I_{DS} \approx \frac{W C_i \mu (V_{GS} - V_T)^2}{2L} \quad \text{Equation 2}$$



Examples of the Present Invention


The following examples are intended to explain the invention without restricting it. The methods, structures and properties described herein can also be applied to materials that are claimed in this invention but not explicitly described in the examples.

Particularly preferred PAHCs according to the present invention are shown in the following tables 1 to 3:

Table 1

Preferred PAHCs	
Monomer A	Monomer B

	
Case 1 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^4 and R^{10} are C_1 to C_{14} alkyl groups, most preferably n-octyl groups. R^3 and R^9 are bonds to another unit of Monomer (A) or (B).	$R'^a, R'^b, R'^c, R'^d, R'^e = H$
Case 2 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^3 and R^9 are C_1 to C_{14} alkyl groups, most preferably n-octyl groups. R^4 and R^{10} are bonds to another unit of Monomer (A) or (B).	
Case 3 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^4 and R^{10} are CF_3 groups. R^3 and R^9 are bonds to another unit of Monomer (A) or (B).	
Case 4 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^3 and R^9 are CF_3 groups.	

R ⁴ and R ¹⁰ are bonds to another unit of Monomer (A) or (B).	
Case 1	R ^b , R ^d , R ^e = H R ^a and R ^c = C ₁ to C ₄ alkyl
Case 2	
Case 3	
Case 4	
Case 1	R ^b , R ^c , R ^d , R ^e = H R ^a = C ₁ to C ₆ alkoxy (i) R ^a = methoxy (ii) R ^a = ethoxy
Case 2	
Case 3	
Case 4	
Case 1	R ^a , R ^b , R ^d , R ^e = H R ^c = C ₁ to C ₆ alkoxy (i) R ^c = methoxy (ii) R ^c = ethoxy
Case 2	
Case 3	
Case 4	
Case 1	R ^a , R ^b , R ^c , R ^d = H R ^e = C ₁ to C ₆ alkoxy (i) R ^e = methoxy (ii) R ^e = ethoxy
Case 2	
Case 3	
Case 4	
Case 1	R ^b , R ^d , R ^e = H R ^a = R ^c = C ₁ to C ₆ alkoxy (i) R ^a = R ^c = methoxy (ii) R ^a = R ^c = ethoxy
Case 2	
Case 3	
Case 4	
Case 1	R ^b , R ^d = H R ^a , R ^c , R ^e = C ₁ to C ₆ alkoxy (i) R ^a , R ^c , R ^e = methoxy (ii) R ^a , R ^c , R ^e = ethoxy
Case 2	
Case 3	
Case 4	
Case 1	R ^b , R ^d = H R ^b , R ^c , R ^d = C ₁ to C ₆ alkoxy (i) R ^b , R ^c , R ^d = methoxy (ii) R ^b , R ^c , R ^d = ethoxy
Case 2	
Case 3	
Case 4	
Case 1	R ^b , R ^c , R ^d , R ^e = H R ^a = Cyano (CN)
Case 2	
Case 3	
Case 4	
Case 1	R ^b , R ^c , R ^d , R ^e = H R ^a = Isopropylcyano group Monomer B: 
Case 2	
Case 3	
Case 4	





Case 1	$R^a, R^b, R^d, R^e = H$ $R^c = \text{Isopropylcyano group}$ Monomer B: 
Case 2	
Case 3	
Case 4	

Table 2

Preferred PAHCs		
Monomer A	Monomer B	Monomer C
		
Case 1 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^4 and R^{10} are C_1 to C_{14} alkyl groups, most preferably n-octyl groups. R^3 and R^9 are bonds to another unit of Monomer (A) or (B).	$R^1' = R^2' = C_1$ to C_{14} alkyl group, preferably n-octyl groups $R^3', R^4' = H$ or C_1 to C_4 alkyl groups; or C_1 to C_4 alkoxy groups; or cyano groups; or isopropyl cyano groups.	$R^a, R^b, R^c, R^d, R^e = H$
Case 2 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^3 and R^9 are C_1 to C_{14} alkyl groups,		

most preferably n-octyl groups.		
R ⁴ and R ¹⁰ are bonds to another unit of Monomer (A) or (B).		
Case 3		
Y ¹ = Y ² are S		
R ¹ , R ² , R ⁵ , R ⁶ , R ⁷ , R ⁸ , R ¹¹ , R ¹² are all H.		
R ⁴ and R ¹⁰ are CF ₃ groups.		
R ³ and R ⁹ are bonds to another unit of Monomer (A) or (B).		
Case 4		
Y ¹ = Y ² are S		
R ¹ , R ² , R ⁵ , R ⁶ , R ⁷ , R ⁸ , R ¹¹ , R ¹² are all H.		
R ³ and R ⁹ are CF ₃ groups.		
R ⁴ and R ¹⁰ are bonds to another unit of Monomer (A) or (B).		
Case 1	R ¹ = R ² = C ₁ to C ₁₄ alkyl group, preferably n-octyl groups	R ^b , R ^d , R ^e = H R ^a and R ^c = C ₁ to C ₄ alkyl
Case 2		
Case 3		
Case 4	R ³ , R ⁴ = H or C ₁ to C ₄ alkyl groups; or C ₁ to C ₄ alkoxy groups; or cyano groups; or isopropyl cyano groups.	
Case 1	R ¹ = R ² = C ₁ to C ₁₄ alkyl group, preferably n-octyl groups	R ^b , R ^c , R ^d , R ^e = H R ^a = C ₁ to C ₆ alkoxy
Case 2		
Case 3		
Case 4	R ³ , R ⁴ = H or C ₁ to C ₄ alkyl groups; or C ₁ to C ₄ alkoxy groups; or cyano groups; or isopropyl cyano groups.	(i) R ^a = methoxy (ii) R ^a = ethoxy
Case 1	R ¹ = R ² = C ₁ to C ₁₄ alkyl group, preferably n-octyl groups	R ^a , R ^b , R ^d , R ^e = H R ^c = C ₁ to C ₆ alkoxy
Case 2		
Case 3		
Case 4	R ³ , R ⁴ = H or C ₁ to C ₄ alkyl groups; or C ₁ to C ₄ alkoxy groups; or cyano groups; or isopropyl cyano groups.	(i) R ^c = methoxy (ii) R ^c = ethoxy

	groups.	
Case 1	$R^1 = R^2 = C_1$ to C_{14} alkyl group, preferably n-octyl groups	$R^a, R^b, R^c, R^d = H$ $R^e = C_1$ to C_6 alkoxy (i) $R^e =$ methoxy (ii) $R^e =$ ethoxy
Case 2		
Case 3		
Case 4		
Case 1	$R^1 = R^2 = C_1$ to C_{14} alkyl group, preferably n-octyl groups	$R^b, R^d, R^e = H$ $R^a = R^c = C_1$ to C_6 alkoxy (i) $R^a = R^c =$ methoxy (ii) $R^a = R^c =$ ethoxy
Case 2		
Case 3		
Case 4		
Case 1	$R^1 = R^2 = C_1$ to C_{14} alkyl group, preferably n-octyl groups	$R^b, R^d = H$ $R^a, R^c, R^e = C_1$ to C_6 alkoxy (i) $R^a, R^c, R^e =$ methoxy (ii) $R^a, R^c, R^e =$ ethoxy
Case 2		
Case 3		
Case 4		
Case 1	$R^1 = R^2 = C_1$ to C_{14} alkyl group, preferably n-octyl groups	$R^b, R^d = H$ $R^b, R^c, R^d = C_1$ to C_6 alkoxy (i) $R^b, R^c, R^d =$ methoxy (ii) $R^b, R^c, R^d =$ ethoxy
Case 2		
Case 3		
Case 4		
Case 1	$R^1 = R^2 = C_1$ to C_{14} alkyl group, preferably n-octyl groups	$R^b, R^c, R^d, R^e = H$ $R^a =$ Cyano (CN)
Case 2		
Case 3		
Case 4		
Case 1	$R^1 = R^2 = C_1$ to C_{14} alkyl group, preferably n-octyl groups	$R^b, R^c, R^d, R^e = H$ $R^a =$ Isopropylcyano group Monomer C:
Case 2		
Case 3		
Case 4		








	alkyl groups; or C ₁ to C ₄ alkoxy groups; or cyano groups; or isopropyl cyano groups.	
Case 1	R ^{1'} = R ^{2'} = C ₁ to C ₁₄ alkyl group, preferably n-octyl groups	R ^{1'a} , R ^{1'b} , R ^{1'd} , R ^{1'e} = H R ^{1'c} = Isopropylcyano group Monomer C: 
Case 2		
Case 3		
Case 4	R ^{3'} , R ^{4'} = H or C ₁ to C ₄ alkyl groups; or C ₁ to C ₄ alkoxy groups; or cyano groups; or isopropyl cyano groups.	

Table 3

Preferred PAHCs		
Monomer A 	Monomer B 	Monomer C 
Case 1 Y¹ = Y² are S R¹, R², R⁵, R⁶, R⁷, R⁸, R¹¹, R¹² are all H. R⁴ and R¹⁰ are C₁ to C₁₄ alkyl groups, most preferably n-octyl groups. R³ and, R⁹ are bonds to another unit of Monomer (A) or (B).	R^{1'}, R^{2'}, R^{3'} and R^{4'} are C₁ to C₁₄ alkyl group, preferably n-octyl groups R^{5'}, R^{6'} and R^{7'} are H or C₁ to C₄ alkyl groups; or C₁ to C₄ alkoxy groups; or cyano groups; or isopropyl cyano groups.	R^{1'a}, R^{1'b}, R^{1'c}, R^{1'd}, R^{1'e} = H
Case 2 Y¹ = Y² are S		

$R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^3 and R^9 are C_1 to C_{14} alkyl groups, most preferably n-octyl groups. R^4 and R^{10} are bonds to another unit of Monomer (A) or (B).		
Case 3 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^4 and R^{10} are CF_3 groups. R^3 and R^9 are bonds to another unit of Monomer (A) or (B).		
Case 4 $Y^1 = Y^2$ are S $R^1, R^2, R^5, R^6, R^7, R^8, R^{11}, R^{12}$ are all H. R^3 and R^9 are CF_3 groups. R^4 and R^{10} are bonds to another unit of Monomer (A) or (B).		
Case 1	$R^{1'}, R^{2'}, R^{3'}$ and $R^{4'}$ are C_1 to C_{14} alkyl group, preferably n-octyl groups $R^{5'}, R^{6'}$ and $R^{7'}$ are H or C_1 to C_4 alkyl groups; or C_1 to C_4 alkoxy groups; or cyano groups; or isopropyl cyano groups.	$R^{b'}, R^{d'}, R^{e'} = H$ $R^{a'}$ and $R^{c'} = C_1$ to C_4 alkyl
Case 2		
Case 3		
Case 4		
Case 1	$R^{1'}, R^{2'}, R^{3'}$ and $R^{4'}$ are C_1 to C_{14} alkyl group, preferably n-octyl groups $R^{5'}, R^{6'}$ and $R^{7'}$ are H or C_1 to C_4 alkyl groups; or C_1 to C_4 alkoxy groups; or cyano groups; or isopropyl cyano groups.	$R^{b'}, R^{c'}, R^{d'}, R^{e'} = H$ $R^{a'} = C_1$ to C_6 alkoxy (i) $R^{a'} =$ methoxy (ii) $R^{a'} =$ ethoxy
Case 2		
Case 3		
Case 4		


Case 1	R ^{1'} , R ^{2'} , R ^{3'} and R ^{4'} are C ₁ to C ₁₄ alkyl group, preferably n-octyl groups	R ^a , R ^b , R ^d , R ^e = H R ^c = C ₁ to C ₆ alkoxy (i) R ^c = methoxy (ii) R ^c = ethoxy
Case 2		
Case 3		
Case 4	R ^{5'} , R ^{6'} and R ^{7'} are H or C ₁ to C ₄ alkyl groups; or C ₁ to C ₄ alkoxy groups; or cyano groups; or isopropyl cyano groups.	
Case 1	R ^{1'} , R ^{2'} , R ^{3'} and R ^{4'} are C ₁ to C ₁₄ alkyl group, preferably n-octyl groups	R ^a , R ^b , R ^c , R ^d = H R ^e = C ₁ to C ₆ alkoxy (i) R ^e = methoxy (ii) R ^e = ethoxy
Case 2		
Case 3		
Case 4		
Case 1	R ^{1'} , R ^{2'} , R ^{3'} and R ^{4'} are C ₁ to C ₁₄ alkyl group, preferably n-octyl groups	R ^b , R ^d , R ^e = H R ^a = R ^c = C ₁ to C ₆ alkoxy (i) R ^a = R ^c = methoxy (ii) R ^a = R ^c = ethoxy
Case 2		
Case 3		
Case 4	R ^{5'} , R ^{6'} and R ^{7'} are H or C ₁ to C ₄ alkyl groups; or C ₁ to C ₄ alkoxy groups; or cyano groups; or isopropyl cyano groups.	
Case 1	R ^{1'} , R ^{2'} , R ^{3'} and R ^{4'} are C ₁ to C ₁₄ alkyl group, preferably n-octyl groups	R ^b , R ^d = H R ^a , R ^c , R ^e = C ₁ to C ₆ alkoxy (i) R ^a , R ^c , R ^e = methoxy (ii) R ^a , R ^c , R ^e = ethoxy
Case 2		
Case 3		
Case 4	R ^{1'} , R ^{2'} , R ^{3'} and R ^{4'} are C ₁ to C ₁₄ alkyl group, preferably n-octyl groups	
Case 1	R ^{1'} , R ^{2'} , R ^{3'} and R ^{4'} are C ₁ to C ₁₄ alkyl group, preferably n-octyl groups	R ^a , R ^e = H R ^b , R ^c , R ^d = C ₁ to C ₆ alkoxy (i) R ^b , R ^c , R ^d = methoxy (ii) R ^b , R ^c , R ^d = ethoxy
Case 2		
Case 3		
Case 4		
Case 1		R ^b , R ^c , R ^d , R ^e = H R ^a = Cyano (CN)
Case 2		
Case 3		
Case 4		
Case 1	R ^{1'} , R ^{2'} , R ^{3'} and R ^{4'} are C ₁ to C ₁₄ alkyl group, preferably n-octyl groups	R ^b , R ^c , R ^d , R ^e = H R ^a = Isopropylcyano group Monomer C:
Case 2		
Case 3		
Case 4		

		
Case 1	$R^{1'}$, $R^{2'}$, $R^{3'}$ and $R^{4'}$ are C_1 to C_{14} alkyl group, preferably n-octyl groups $R^{5'}$, $R^{6'}$ and $R^{7'}$ are H or C_1 to C_4 alkyl groups; or C_1 to C_4 alkoxy groups; or cyano groups; or isopropyl cyano groups.	R^{1a} , R^{1b} , R^{1d} , R^{1e} = H R^{1c} = Isopropylcyano group Monomer C: 
Case 2		
Case 3		
Case 4		


- The organic semiconductors compounds specified in the table are particularly preferred as they combine the beneficial properties of high charge transport mobility (of the binders) with a polarity that is more compatible with benign, non-chlorinated solvents that will be desirable for use in large area printing. In addition,
- 5 as these compounds are more polar once deposited as the OSC layer, or alternatively as a component in the OSC layer, they are expected to be resistant to being re-dissolved by the hydrophobic solvents used for the organic gate insulators (OGI) such as Cytop. Furthermore, it is expected that the polar binders are useful for both top gate and bottom gate OTFTs, particularly for bottom gate OTFTs.

CLAIMS

1. A Polycyclic Aromatic Hydrocarbon Copolymer (PAHC) comprising a mixture of at least one BXB monomer unit having the Formula (A) and at least one
- 5 monomer unit having the Formula (B):



Formula (A)



Formula (B)

10

wherein

Y^1 and Y^2 are independently S or Se;

k and l are independently 0 or 1

- 15 wherein each of R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , R^{11} and R^{12} , which may be the same or different, independently represents hydrogen; a branched or unbranched, substituted or unsubstituted C_1 - C_{40} alkyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkenyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkynyl group; an optionally substituted C_3 - C_{40} cycloalkyl group; an optionally substituted C_6 - C_{40} aryl group; an
- 20 optionally substituted C_1 - C_{40} heterocyclic group; an optionally substituted C_1 - C_{40} heteroaryl group; an optionally substituted C_1 - C_{40} alkoxy group; an optionally substituted C_6 - C_{40} aryloxy group; an optionally substituted C_7 - C_{40} alkylaryloxy group; an optionally substituted C_2 - C_{40} alkoxycarbonyl group; an optionally substituted C_7 - C_{40} aryloxycarbonyl group; a cyano group (-CN); a carbamoyl group (-

$C(=O)NR^{15}R^{16}$; a carbonyl group $(-C(=O)-R^{17})$; a carboxyl group $(-CO_2R^{18})$; a cyanate group $(-OCN)$; an isocyano group $(-NC)$; an isocyanate group $(-NCO)$; a thiocyanate group $(-SCN)$ or a thioisocyanate group $(-NCS)$; an optionally substituted amino group; a hydroxy group; a nitro group; a CF_3 group; a halo group (Cl, Br, F, I); $-SR^{19}$; $-SO_3H$; $-SO_2R^{20}$; $-SF_5$; an optionally substituted silyl group; a C_2-C_{10} alkynyl group substituted with a SiH_2R^{22} group, a C_2-C_{10} alkynyl substituted with a $SiHR^{22}R^{23}$ group, or a C_2-C_{10} alkynyl substituted with a $-Si(R^{22})_x(R^{23})_y(R^{24})_z$ group;

wherein each R^{22} group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted C_1-C_{10} alkyl group, a branched or unbranched, substituted or unsubstituted C_2-C_{10} alkynyl group, a substituted or unsubstituted C_2-C_{20} cycloalkyl group, a substituted or unsubstituted C_2-C_{10} alkenyl group, and a substituted or unsubstituted C_6-C_{20} cycloalkylalkylene group;

each R^{23} group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted C_1-C_{10} alkyl group, a branched or unbranched, substituted or unsubstituted C_2-C_{10} alkynyl group, a substituted or unsubstituted C_2-C_{10} alkenyl group, a substituted or unsubstituted C_2-C_{20} cycloalkyl group, and a substituted or unsubstituted C_6-C_{20} cycloalkylalkylene group;

R^{24} is independently selected from the group consisting of hydrogen, a branched or unbranched, substituted or unsubstituted C_2-C_{10} alkynyl group, a substituted or unsubstituted C_2-C_{20} cycloalkyl group, a substituted or unsubstituted C_6-C_{20} cycloalkylalkylene group, a substituted C_5-C_{20} aryl group, a substituted or unsubstituted C_6-C_{20} arylalkylene group, an acetyl group, a substituted or unsubstituted C_3-C_{20} heterocyclic ring comprising at least one of O, N, S and Se in the ring;

wherein $x = 1$ or 2 ; $y = 1$ or 2 ; $z = 0$ or 1 ; and $(x+y+z) = 3$;

wherein each of R^{15} , R^{16} , R^{18} , R^{19} and R^{20} independently represent H or optionally substituted C_1-C_{40} carbyl or hydrocarbyl group optionally comprising one or more heteroatoms;

wherein R^{17} represents a halogen atom, H or optionally substituted C_1-C_{40} carbyl or C_1-C_{40} hydrocarbyl group optionally comprising one or more heteroatoms;


wherein k and l are independently 0 or 1;

wherein at least two of R^1 , R^3 , R^4 , R^6 , R^7 , R^9 , R^{10} , and R^{12} , are a bond, represented by —*, to another monomer unit having the Formula (A) or (B); and


wherein Ar_1 , Ar_2 and Ar_3 , which may be the same or different, each represent, independently if in different repeat units, an optionally substituted C_{6-40} aromatic group (mononuclear or polynuclear), wherein preferably at least one of Ar_1 , Ar_2 and Ar_3 is substituted with at least one polar or polarising groups.

2. A PAHC according to claim 1, comprising at least 20 to 40% of monomer (A) and at least 60 to 80% of monomer (B), based on the total of all monomer units (A) and (B) in the copolymer.
- 10 3. A PAHC according to claims 1 or claim 2, wherein monomer unit (B) having the, Ar_1 , Ar_2 and Ar_3 , which may be the same or different, each representing, independently if in different repeat units, an optionally substituted C_{6-20} aromatic group (mononuclear or polynuclear), wherein at least one of Ar_1 , Ar_2 and Ar_3 is substituted with at least one or more polar or polarising group, and $n = 1$ to 20.
- 15 4. A PAHC according to claim 3, wherein Ar_1 , Ar_2 and Ar_3 are all phenyl which may be independently substituted with 1 or 2 groups selected from methoxy, cyanomethyl, CN and mixtures thereof, and $n = 1$ to 10.
5. A PAHC according to any preceding claim, further comprising one or more monomers (C), (D), (D') and/or (E):

20




(C)



(D)

(D')

82




(E)

wherein each $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$, $R^{5'}$, $R^{6'}$ and $R^{7'}$, each of which may be the same or different, is selected from the same group as R^1 , R^2 , R^3 , R^4 , R^5 , R^6 and R^7 , as defined in claim 1;

wherein $n' = 1$ to 3; and


wherein monomer (A) is present in an amount of at least 20 wt. %; monomer (B) is present in an amount of at least 60 wt. % and the remainder is comprised of monomers (C), (D), (D') and/or (E), based on the total weight of all monomer units in the copolymer.

6. A Polycyclic Aromatic Hydrocarbon Copolymer (PAHC) comprising a mixture of at least one BXB monomer unit having the Formula (A) and at least one monomer unit having the Formula (K):



Formula (A)

83



Formula (K)

wherein

Y^1 and Y^2 are independently S or Se;

5 k and l are independently 0 or 1

wherein each of R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , R^{11} and R^{12} , which may be the same or different, independently represents hydrogen; a branched or unbranched, substituted or unsubstituted C_1 - C_{40} alkyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkenyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkynyl group; an optionally substituted C_3 - C_{40} cycloalkyl group; an optionally substituted C_6 - C_{40} aryl group; an optionally substituted C_1 - C_{40} heterocyclic group; an optionally substituted C_1 - C_{40} heteroaryl group; an optionally substituted C_1 - C_{40} alkoxy group; an optionally substituted C_6 - C_{40} aryloxy group; an optionally substituted C_7 - C_{40} alkylaryloxy group; an optionally substituted C_2 - C_{40} alkoxycarbonyl group; an optionally substituted C_7 - C_{40} aryloxycarbonyl group; a cyano group (-CN); a carbamoyl group (-C(=O)NR¹⁵R¹⁶); a carbonyl group (-C(=O)-R¹⁷); a carboxyl group (-CO₂R¹⁸); a cyanate group (-OCN); an isocyano group (-NC); an isocyanate group (-NCO); a thiocyanate group (-SCN) or a thioisocyanate group (-NCS); an optionally substituted amino group; a hydroxy group; a nitro group; a CF₃ group; a halo group (Cl, Br, F, I); -SR¹⁹; -SO₃H; -SO₂R²⁰; -SF₅; an optionally substituted silyl group; a C_2 - C_{10} alkynyl group substituted with a SiH₂R²² group, a C_2 - C_{10} alkynyl substituted with a SiHR²²R²³ group, or a C_2 - C_{10} alkynyl substituted with a -Si(R²²)_x(R²³)_y(R²⁴)_z group;

wherein each R²² group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted C_1 - C_{10} alkyl group, a branched or unbranched, substituted or unsubstituted C_2 - C_{10} alkynyl group, a substituted or unsubstituted C_2 - C_{20} cycloalkyl group, a substituted or unsubstituted C_2 - C_{10} alkenyl group, and a substituted or unsubstituted C_6 - C_{20} cycloalkylalkylene group;

each R^{23} group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted C_1 - C_{10} alkyl group, a branched or unbranched, substituted or unsubstituted C_2 - C_{10} alkynyl group, a substituted or unsubstituted C_2 - C_{10} alkenyl group, a substituted or unsubstituted C_2 - C_{20} cycloalkyl group, and a substituted or unsubstituted C_6 - C_{20} cycloalkylalkylene group;

R^{24} is independently selected from the group consisting of hydrogen, a branched or unbranched, substituted or unsubstituted C_2 - C_{10} alkynyl group, a substituted or unsubstituted C_2 - C_{20} cycloalkyl group, a substituted or unsubstituted C_6 - C_{20} cycloalkylalkylene group, a substituted C_5 - C_{20} aryl group, a substituted or unsubstituted C_6 - C_{20} arylalkylene group, an acetyl group, a substituted or unsubstituted C_3 - C_{20} heterocyclic ring comprising at least one of O, N, S and Se in the ring;

wherein $x = 1$ or 2 ; $y = 1$ or 2 ; $z = 0$ or 1 ; and $(x+y+z) = 3$;

wherein each of R^{15} , R^{16} , R^{18} , R^{19} and R^{20} independently represent H or optionally substituted C_1 - C_{40} carbyl or hydrocarbyl group optionally comprising one or more heteroatoms;

wherein R^{17} represents a halogen atom, H or optionally substituted C_1 - C_{40} carbyl or C_1 - C_{40} hydrocarbyl group optionally comprising one or more heteroatoms;

wherein k and l are independently 0 or 1;

wherein at least two of R^1 , R^3 , R^4 , R^6 , R^7 , R^9 , R^{10} , and R^{12} , are a bond, represented by ---^* , to another monomer unit having the Formula (A) or (K); and

wherein each $R^{1'}$, $R^{2'}$, $R^{3'}$ and $R^{4'}$, each of which may be the same or different, is selected from the same group as R^1 , R^2 , R^3 , R^4 ; and wherein preferably at least one of the groups $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$ is a polar group or polarising group and for the monomer group (K), ---^* represents a bond to another monomer unit having the Formula (A) or (K); and

$n' = 1$ to 3 .


7. A PAHC according to claim 6, comprising at least 20 to 40% of monomer (A) and at least 60 to 80% of monomer (K), based on the total of all monomer units (A) and (K) in the copolymer.

8. A PAHC according to claim 6 or claim 7, wherein at least one of $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$ is a polar group or polarising group, and $n = 1$ to 20 .


9. A PAHC according to claim 8, wherein one or 2 of the groups $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$ are selected from methoxy, cyanomethyl, CN and mixtures thereof, and $n = 1$ to 10.

10. A PAHC according to any of claims 6 to 9, further comprising one or more monomers (L), (M), (M') and/or (N):

5




(L)




(M)

10



(M')



(N)


wherein each $R^{1''}$, $R^{2''}$, $R^{3''}$, $R^{4''}$, $R^{5''}$, $R^{6''}$ and $R^{7''}$, each of which may be the same or different, is selected from the same group as R^1 , R^2 , R^3 , R^4 , R^5 , R^6 and R^7 , as defined in claim 1;

5 wherein $n'' = 1$ to 3;


Ar_1 , Ar_2 and Ar_3 , which may be the same or different, each represent, independently an optionally substituted C_{6-40} aromatic group (mononuclear or polynuclear); and

wherein monomer (A) is present in an amount of at least 20 wt.%; monomer (K) is present in an amount of at least 60 wt. % and the remainder is comprised of
 10 monomers (L), (M), (M') and/or (N), based on the total weight of all monomer units in the copolymer.


11. A Polycyclic Aromatic Hydrocarbon Copolymer (PAHC) comprising a mixture of at least one BXB monomer unit having the Formula (A) and at least one monomer unit having the Formula (O/O'):



Formula (A)



87



Formula (O/O') -represents cis and/or trans-indenofluorene isomers

wherein

Y^1 and Y^2 are independently S or Se;

5 k and l are independently 0 or 1;

wherein each of R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , R^{11} and R^{12} , which may be the same or different, independently represents hydrogen; a branched or unbranched, substituted or unsubstituted C_1 - C_{40} alkyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkenyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkynyl group; an optionally substituted C_3 - C_{40} cycloalkyl group; an optionally substituted C_6 - C_{40} aryl group; an optionally substituted C_1 - C_{40} heterocyclic group; an optionally substituted C_1 - C_{40} heteroaryl group; an optionally substituted C_1 - C_{40} alkoxy group; an optionally substituted C_6 - C_{40} aryloxy group; an optionally substituted C_7 - C_{40} alkylaryloxy group; an optionally substituted C_2 - C_{40} alkoxycarbonyl group; an optionally substituted C_7 - C_{40} aryloxycarbonyl group; a cyano group (-CN); a carbamoyl group (-C(=O)NR¹⁵R¹⁶); a carbonyl group (-C(=O)-R¹⁷); a carboxyl group (-CO₂R¹⁸); a cyanate group (-OCN); an isocyano group (-NC); an isocyanate group (-NCO); a thiocyanate group (-SCN) or a thioisocyanate group (-NCS); an optionally substituted amino group; a hydroxy group; a nitro group; a CF₃ group; a halo group (Cl, Br, F, I); -SR¹⁹; -SO₃H; -SO₂R²⁰; -SF₅; an optionally substituted silyl group; a C_2 - C_{10} alkynyl group substituted with a SiH₂R²² group, a C_2 - C_{10} alkynyl substituted with a SiHR²²R²³ group, or a C_2 - C_{10} alkynyl substituted with a -Si(R²²)_x(R²³)_y(R²⁴)_z group;

wherein each R²² group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted C_1 - C_{10} alkyl group, a branched or unbranched, substituted or unsubstituted C_2 - C_{10} alkynyl group, a substituted or unsubstituted C_2 - C_{20} cycloalkyl group, a substituted or unsubstituted C_2 - C_{10} alkenyl group, and a substituted or unsubstituted C_6 - C_{20} cycloalkylalkylene group;

each R^{23} group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted C_1 - C_{10} alkyl group, a branched or unbranched, substituted or unsubstituted C_2 - C_{10} alkynyl group, a substituted or unsubstituted C_2 - C_{10} alkenyl group, a substituted or unsubstituted C_2 - C_{20} cycloalkyl group, and a substituted or unsubstituted C_6 - C_{20} cycloalkylalkylene group;

R^{24} is independently selected from the group consisting of hydrogen, a branched or unbranched, substituted or unsubstituted C_2 - C_{10} alkynyl group, a substituted or unsubstituted C_2 - C_{20} cycloalkyl group, a substituted or unsubstituted C_6 - C_{20} cycloalkylalkylene group, a substituted C_5 - C_{20} aryl group, a substituted or unsubstituted C_6 - C_{20} arylalkylene group, an acetyl group, a substituted or unsubstituted C_3 - C_{20} heterocyclic ring comprising at least one of O, N, S and Se in the ring;

wherein $x = 1$ or 2 ; $y = 1$ or 2 ; $z = 0$ or 1 ; and $(x+y+z) = 3$;

wherein each of R^{15} , R^{16} , R^{18} , R^{19} and R^{20} independently represent H or optionally substituted C_1 - C_{40} carbyl or hydrocarbyl group optionally comprising one or more heteroatoms;

wherein R^{17} represents a halogen atom, H or optionally substituted C_1 - C_{40} carbyl or C_1 - C_{40} hydrocarbyl group optionally comprising one or more heteroatoms;

wherein k and l are independently 0 or 1;

wherein at least two of R^1 , R^3 , R^4 , R^6 , R^7 , R^9 , R^{10} , and R^{12} , are a bond, represented by ---^* , to another monomer unit having the Formula (A) or (O);

wherein monomer (O/O') is either the cis and/or trans-indenofluorene monomer and each $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$, $R^{5'}$, $R^{6'}$, $R^{7'}$, each of which may be the same or different, is selected from the same group as R^1 , R^2 , R^3 , R^4 , R^6 , R^7 and wherein preferably at least one of the groups $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$, $R^{5'}$, $R^{6'}$ and $R^{7'}$ is a polar or polarising group and for the monomer group (O/O') ---^* represents a bond to another monomer unit having the Formula (A) or (O/O'); and


$n' = 1$ to 3 .

12. A PAHC according to claim 11, comprising at least 20 to 40% of monomer (A) and at least 60 to 80% of monomer (O), based on the total of all monomer units (A) and (O) in the copolymer.


13. A PAHC according to claim 11 or claim 12, wherein for the cis/trans-indenofluorene monomer (O/O'), $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$, $R^{5'}$, $R^{6'}$, and $R^{7'}$ which may be the same or different and at least one wherein preferably at least one of $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$, $R^{5'}$, $R^{6'}$, and $R^{7'}$ is substituted with at least one polar group or more polarising group ,
5 and $n = 1$ to 20.

14. A PAHC according to claim 13, wherein one or 2 of the groups $R^{1'}$, $R^{2'}$, $R^{3'}$, $R^{4'}$, $R^{5'}$, $R^{6'}$ and $R^{7'}$ are selected from methoxy, cyanomethyl, CN and mixtures thereof, and $n = 1$ to 10.


15. A PAHC according to any of claims 11 to 14, further comprising one or more
10 monomers (P), (Q) and/or (R):



(P)



(Q)



(R)

wherein each $R^{1''}$, $R^{2''}$, $R^{3''}$ and $R^{4''}$, each of which may be the same or different, is selected from the same group as R^1 , R^2 , R^3 and R^4 , already defined above;

Ar₁, Ar₂ and Ar₃, which may be the same or different, each represent, independently an optionally substituted C₆₋₄₀ aromatic group (mononuclear or polynuclear). Preferably at least one of Ar₁, Ar₂ and Ar₃ is substituted with at least one polar or more polarising group, and n = 1 to 20, preferably 1 to 10 and more preferably 1 to 5.

5 5. Preferably, at least one of Ar₁, Ar₂ and Ar₃ is substituted with 1, 2, 3, or 4, more preferably 1, 2 or 3, more preferably 1 or 2, preferably 1 polar or more polarising group(s);

n" = 1 to 3; and

wherein monomer (A) is present in an amount of at least 20 wt. %; monomer (O) is present in an amount of at least 60 wt. % and the remainder is comprised of monomers (P), (Q) and/or (R), based on the total weight of all monomer units in the copolymer.

10

16. A PAHC according to any preceding claim, wherein R³ = R¹⁰ = a C₁ to C₁₄ alkyl group or optionally substituted C₁ to C₁₄ alkyl group.

15 17. A PAHC according to any preceding claim, wherein k = l = 0 or 1.

18. A PAHC according to claim 17, wherein k = 0 and l = 0.

19. A PAHC according to any preceding claim, wherein the copolymers have a number average molecular weight (Mn) of between 500 and 100,000.

20. A PAHC according to any preceding claim, wherein the copolymers are semiconducting copolymers having a permittivity at 1000 Hz of greater than 1.5, preferably between 3.4 and 8.

20

21. A PAHC according to claim 20, wherein the copolymers are semiconducting copolymers having a permittivity at 1000 Hz of between 3.4 and 8.0.

22. A PAHC according to any preceding claim, wherein at least one (and more preferably 2) of groups R¹, R⁶, R⁷, and R¹² are (tri-C₁₋₂₀ hydrocarbylsilyl) C₁₋₄ alkynyl groups, preferably (trihydrocarbylsilyl)ethynyl- groups. Preferably at least one pair of R¹/R⁶ and/or R⁷/R¹² are trihydrocarbylsilyl ethynyl groups.


25

23. A PAHC according to any preceding claim, wherein R¹, R³, R⁶, R⁷, R⁹ and R¹² are hydrogen.


30 24. A PAHC according to any preceding claim, wherein -Si(R²²)_x(R²³)_y(R²⁴)_z is selected from the group consisting of trimethylsilyl, triethylsilyl, tripropylsilyl, dimethylethylsilyl, diethylmethylsilyl, dimethylpropylsilyl, dimethylisopropylsilyl,

dipropylmethylsilyl, diisopropylmethylsilyl, dipropylethylsilyl, diisopropylethylsilyl, diethylisopropylsilyl, triisopropylsilyl, trimethoxysilyl, triethoxysilyl, triphenylsilyl, diphenylisopropylsilyl, diisopropylphenylsilyl, diphenylethylsilyl, diethylphenylsilyl, diphenylmethylsilyl, triphenoxysilyl, dimethylmethoxysilyl, dimethylphenoxysilyl, and methylmethoxyphenyl.

25. A PAHC according to any preceding claim, having the Formula (A1) or (A2)



Formula (A1)



Formula (A2)


wherein R²⁵, R²⁶ and R²⁷ are independently selected from the group consisting of C₁-C₆ alkyl and C₂-C₆ alkenyl, preferably independently selected from the group consisting of methyl, ethyl, propyl, isopropyl, n-butyl, isobutyl, t-butyl, 1-propenyl and 2-propenyl, more preferably ethyl, n-propyl and isopropyl;

26. A PAHC according to any of claims 3, 8 or 13 wherein the one or more polar or polarising group(s) is independently selected from the group consisting of nitro group, nitrile group, C₁₋₄₀ alkyl group substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; C₁₋₄₀ alkoxy group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; C₁₋₄₀ carboxylic acid group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group;


- C₂₋₄₀ carboxylic acid ester optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; sulfonic acid optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; sulfonic acid ester optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; cyanate group, isocyanate group, thiocyanate group, thioisocyanate group; and an amino group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; and combinations thereof.
27. An organic semiconductor composition comprising a PAHC according to any of claims 1 to 26 and a polyacene small molecule, wherein the PAHC has a permittivity at 1000Hz of between 3.4 and 8.0.
28. An organic semiconductor composition comprising a PAHC according to any of claims 1 to 26 and a polyacene small molecule, wherein the PAHC has a permittivity at 1000Hz of between 3.4 and 4.5.
29. An organic semiconductor composition comprising a Polycyclic Aromatic Hydrocarbon Copolymer (PAHC) according to any of claims 1 to 26, wherein the composition has a permittivity at 1000 Hz of between 3 and 6.5.
30. An organic semiconductor composition according to claim 23, comprising an organic binder, wherein the organic binder has a permittivity at 1000 Hz of between 3.4 and 8, preferably between 4 and 6.5.
31. An organic semiconductor composition according to any of claims 27 to 30 having a charge mobility value of at least $0.5 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$, preferably between 2 and $5.0 \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$.
32. An organic semiconductor layer, comprising a PAHC or an organic semiconductor composition according to any preceding claim.
33. An electronic device comprising a PAHC, an organic semiconductor composition or a semiconductor layer according to any preceding claim.
34. An electronic device according to claim 33, selected from organic thin film transistors (OTFTs), organic light emitting diodes (OLEDs), photodetectors, organic photovoltaic (OPV) cells, sensors, lasers, memory elements and logic circuits.

35. An ink comprising a PAHC or an organic semiconductor composition according to any of claims 1-31.

36. A process for producing a Polycyclic Aromatic Hydrocarbon Copolymer (PAHC) comprising copolymerising a composition containing at least one BXB
5 monomer unit selected from the structures (A') and at least one arylamine monomer (B'):



Structure A'



Structure B'

wherein

Y^1 and Y^2 are independently S or Se;

k and l are independently 0 or 1

15 wherein each of R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , R^{11} and R^{12} , which may be the same or different, independently represents hydrogen; a branched or unbranched, substituted or unsubstituted C_1 - C_{40} alkyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkenyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkynyl group; an optionally
20 substituted C_3 - C_{40} cycloalkyl group; an optionally substituted C_6 - C_{40} aryl group; an optionally substituted C_1 - C_{40} heterocyclic group; an optionally substituted C_1 - C_{40} heteroaryl group; an optionally substituted C_1 - C_{40} alkoxy group; an optionally substituted C_6 - C_{40} aryloxy group; an optionally substituted C_7 - C_{40} alkylaryloxy group; an optionally substituted C_2 - C_{40} alkoxycarbonyl group; an optionally substituted C_7 -
25 C_{40} aryloxycarbonyl group; a cyano group (-CN); a carbamoyl group (-

C(=O)NR¹⁵R¹⁶); a carbonyl group (-C(=O)-R¹⁷); a carboxyl group (-CO₂R¹⁸) a cyanate group (-OCN); an isocyano group (-NC); an isocyanate group (-NCO); a thiocyanate group (-SCN) or a thioisocyanate group (-NCS); an optionally substituted amino group; a hydroxy group; a nitro group; a CF₃ group; a halo group (Cl, Br, F, I); -SR¹⁹; -SO₃H; -SO₂R²⁰; -SF₅; an optionally substituted silyl group; a C₂-C₁₀ alkynyl group substituted with a SiH₂R²² group, a C₂-C₁₀ alkynyl substituted with a SiHR²²R²³ group, or a C₂-C₁₀ alkynyl substituted with a -Si(R²²)_x(R²³)_y(R²⁴)_z group;

wherein each R²² group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted C₁-C₁₀ alkyl group, a branched or unbranched, substituted or unsubstituted C₂-C₁₀ alkynyl group, a substituted or unsubstituted C₂-C₂₀ cycloalkyl group, a substituted or unsubstituted C₂-C₁₀ alkenyl group, and a substituted or unsubstituted C₆-C₂₀ cycloalkylalkylene group;

each R²³ group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted C₁-C₁₀ alkyl group, a branched or unbranched, substituted or unsubstituted C₂-C₁₀ alkynyl group, a substituted or unsubstituted C₂-C₁₀ alkenyl group, a substituted or unsubstituted C₂-C₂₀ cycloalkyl group, and a substituted or unsubstituted C₆-C₂₀ cycloalkylalkylene group;

R²⁴ is independently selected from the group consisting of hydrogen, a branched or unbranched, substituted or unsubstituted C₂-C₁₀ alkynyl group, a substituted or unsubstituted C₂-C₂₀ cycloalkyl group, a substituted or unsubstituted C₆-C₂₀ cycloalkylalkylene group, a substituted C₅-C₂₀ aryl group, a substituted or unsubstituted C₆-C₂₀ arylalkylene group, an acetyl group, a substituted or unsubstituted C₃-C₂₀ heterocyclic ring comprising at least one of O, N, S and Se in the ring;

wherein x= 1 or 2; y=1 or 2; z=0 or 1; and (x+y+z)=3;

wherein each of R¹⁵, R¹⁶, R¹⁸, R¹⁹ and R²⁰ independently represent H or optionally substituted C₁-C₄₀ carbyl or hydrocarbyl group optionally comprising one or more heteroatoms;

wherein R¹⁷ represents a halogen atom, H or optionally substituted C₁-C₄₀ carbyl or C₁-C₄₀ hydrocarbyl group optionally comprising one or more heteroatoms;

wherein Ar₁, Ar₂ and Ar₃, which may be the same or different, each represent, independently if in different repeat units, an optionally substituted C₆₋₄₀ aromatic


group (mononuclear or polynuclear), wherein preferably at least one of Ar₁, Ar₂ and Ar₃ is substituted with at least one polar or more polarising group;

wherein X' is a halogen atom or a cyclic borate group; and


wherein Z' is a halogen atom.

- 5 37. A process for producing a Polycyclic Aromatic Hydrocarbon Copolymer (PAHC) according to claim 36, further comprising any of the features as defined in any of claims 2 to 5, or 16 to 26.

38. A process for producing a Polycyclic Aromatic Hydrocarbon Copolymer (PAHC) comprising copolymerising a composition containing at least one monomer
 10 unit selected from the structures (A') and at least one monomer selected from the structure (K'):



Structure A'



Structure K'

wherein

Y¹ and Y² are independently S or Se;

k and l are independently 0 or 1;

- wherein each of R¹, R², R³, R⁴, R⁵, R⁶, R⁷, R⁸, R⁹, R¹⁰, R¹¹ and R¹², which may be
 20 the same or different, independently represents hydrogen; a branched or unbranched, substituted or unsubstituted C₁-C₄₀ alkyl group; a branched or unbranched, substituted or unsubstituted C₂-C₄₀ alkenyl group; a branched or unbranched, substituted or unsubstituted C₂-C₄₀ alkynyl group; an optionally

substituted C₃-C₄₀ cycloalkyl group; an optionally substituted C₆-C₄₀ aryl group; an optionally substituted C₁-C₄₀ heterocyclic group; an optionally substituted C₁-C₄₀ heteroaryl group; an optionally substituted C₁-C₄₀ alkoxy group; an optionally substituted C₆-C₄₀ aryloxy group; an optionally substituted C₇-C₄₀ alkylaryloxy group;

5 an optionally substituted C₂-C₄₀ alkoxycarbonyl group; an optionally substituted C₇-C₄₀ aryloxycarbonyl group; a cyano group (-CN); a carbamoyl group (-C(=O)NR¹⁵R¹⁶); a carbonyl group (-C(=O)-R¹⁷); a carboxyl group (-CO₂R¹⁸); a cyanate group (-OCN); an isocyano group (-NC); an isocyanate group (-NCO); a thiocyanate group (-SCN) or a thioisocyanate group (-NCS); an optionally

10 substituted amino group; a hydroxy group; a nitro group; a CF₃ group; a halo group (Cl, Br, F, I); -SR¹⁹; -SO₃H; -SO₂R²⁰; -SF₅; an optionally substituted silyl group; a C₂-C₁₀ alkynyl group substituted with a SiH₂R²² group, a C₂-C₁₀ alkynyl substituted with a SiHR²²R²³ group, or a C₂-C₁₀ alkynyl substituted with a -Si(R²²)_x(R²³)_y(R²⁴)_z group;

wherein each R²² group is independently selected from the group consisting of a

15 branched or unbranched, substituted or unsubstituted C₁-C₁₀ alkyl group, a branched or unbranched, substituted or unsubstituted C₂-C₁₀ alkynyl group, a substituted or unsubstituted C₂-C₂₀ cycloalkyl group, a substituted or unsubstituted C₂-C₁₀ alkenyl group, and a substituted or unsubstituted C₆-C₂₀ cycloalkylalkylene group;

20 each R²³ group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted C₁-C₁₀ alkyl group, a branched or unbranched, substituted or unsubstituted C₂-C₁₀ alkynyl group, a substituted or unsubstituted C₂-C₁₀ alkenyl group, a substituted or unsubstituted C₂-C₂₀ cycloalkyl group, and a substituted or unsubstituted C₆-C₂₀ cycloalkylalkylene group;

25 R²⁴ is independently selected from the group consisting of hydrogen, a branched or unbranched, substituted or unsubstituted C₂-C₁₀ alkynyl group, a substituted or unsubstituted C₂-C₂₀ cycloalkyl group, a substituted or unsubstituted C₆-C₂₀ cycloalkylalkylene group, a substituted C₅-C₂₀ aryl group, a substituted or unsubstituted C₆-C₂₀ arylalkylene group, an acetyl group, a substituted or

30 unsubstituted C₃-C₂₀ heterocyclic ring comprising at least one of O, N, S and Se in the ring;

wherein x= 1 or 2; y=1 or 2; z=0 or 1; and (x+y+z)=3;

wherein each of R¹⁵, R¹⁶, R¹⁸, R¹⁹ and R²⁰ independently represent H or optionally substituted C₁-C₄₀ carbyl or hydrocarbyl group optionally comprising one or more

35 heteroatoms;

wherein R^{17} represents a halogen atom, H or optionally substituted C_1 - C_{40} carbyl or C_1 - C_{40} hydrocarbyl group optionally comprising one or more heteroatoms;

wherein R^1 , R^2 , R^3 , R^4 which may be the same or different, independently each represent, hydrogen; a branched or unbranched, substituted or unsubstituted C_1 - C_{40} alkyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkenyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkynyl group; an optionally substituted C_3 - C_{40} cycloalkyl group; an optionally substituted C_6 - C_{40} aryl group; an optionally substituted C_1 - C_{40} heterocyclic group; an optionally substituted C_1 - C_{40} heteroaryl group; an optionally substituted C_1 - C_{40} alkoxy group; an optionally substituted C_6 - C_{40} aryloxy group; an optionally substituted C_7 - C_{40} alkylaryloxy group; an optionally substituted C_2 - C_{40} alkoxycarbonyl group; an optionally substituted C_7 - C_{40} aryloxycarbonyl group; a cyano group (-CN); a carbamoyl group (-C(=O)NR¹⁵R¹⁶); a carbonyl group (-C(=O)-R¹⁷); a carboxyl group (-CO₂R¹⁸); a cyanate group (-OCN); an isocyano group (-NC); an isocyanate group (-NCO); a thiocyanate group (-SCN) or a thioisocyanate group (-NCS); an optionally substituted amino group; a hydroxy group; a nitro group; a CF₃ group; a halo group (Cl, Br, F, I); -SR¹⁹; -SO₃H; -SO₂R²⁰; -SF₅; an optionally substituted silyl group;

wherein preferably at least one of R^1 , R^2 , R^3 , R^4 is substituted with at least one polar or more polarising group which is independently selected from the group consisting of nitro group, nitrile group, C_{1-40} alkyl group substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; a C_{1-40} alkoxy group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; a C_{1-40} carboxylic acid group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; a C_{2-40} carboxylic acid ester optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; sulfonic acid optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; sulfonic acid ester optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; cyanate group, isocyanate group, thiocyanate group, thioisocyanate group; and an amino group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; and combinations thereof;

wherein at least one of R^1 , R^2 , R^3 , R^4 groups is a polar or polarising group, and $n = 1$ to 20 ;


wherein X' is a halogen atom or a cyclic borate group; and

wherein Z' is a halogen atom.



- 5 39. A process for producing a Polycyclic Aromatic Hydrocarbon Copolymer (PAHC) according to claim 28, further comprising any of the features as defined in claims 7 to 10 or 16 to 26.

40. A process for producing a Polycyclic Aromatic Hydrocarbon Copolymer (PAHC) comprising copolymerising a composition containing at least one BXB

- 10 monomer unit selected from the structures (A') and at least one monomer (O'):



Structure A'



Structure O/O'

wherein

Y^1 and Y^2 are independently S or Se;

k and l are independently 0 or 1

- wherein each of R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , R^9 , R^{10} , R^{11} and R^{12} , which may be the same or different, independently represents hydrogen; a branched or unbranched, substituted or unsubstituted C_1 - C_{40} alkyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkenyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkynyl group; an optionally substituted C_3 - C_{40} cycloalkyl group; an optionally substituted C_6 - C_{40} aryl group; an optionally substituted C_1 - C_{40} heterocyclic group; an optionally substituted C_1 - C_{40} heteroaryl group; an optionally substituted C_1 - C_{40} alkoxy group; an optionally substituted C_6 - C_{40} aryloxy group; an optionally substituted C_7 - C_{40} alkylaryloxy group; an optionally substituted C_2 - C_{40} alkoxycarbonyl group; an optionally substituted C_7 - C_{40} aryloxycarbonyl group; a cyano group ($-CN$); a carbamoyl group ($-C(=O)NR^{15}R^{16}$); a carbonyl group ($-C(=O)-R^{17}$); a carboxyl group ($-CO_2R^{18}$); a cyanate group ($-OCN$); an isocyano group ($-NC$); an isocyanate group ($-NCO$); a thiocyanate group ($-SCN$) or a thioisocyanate group ($-NCS$); an optionally substituted amino group; a hydroxy group; a nitro group; a CF_3 group; a halo group (Cl, Br, F, I); $-SR^{19}$; $-SO_3H$; $-SO_2R^{20}$; $-SF_5$; an optionally substituted silyl group; a C_2 - C_{10} alkynyl group substituted with a SiH_2R^{22} group, a C_2 - C_{10} alkynyl substituted with a $SiHR^{22}R^{23}$ group, or a C_2 - C_{10} alkynyl substituted with a $-Si(R^{22})_x(R^{23})_y(R^{24})_z$ group;
- wherein each R^{22} group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted C_1 - C_{10} alkyl group, a branched or unbranched, substituted or unsubstituted C_2 - C_{10} alkynyl group, a substituted or unsubstituted C_2 - C_{20} cycloalkyl group, a substituted or unsubstituted C_2 - C_{10} alkenyl group, and a substituted or unsubstituted C_6 - C_{20} cycloalkylalkylene group;
- each R^{23} group is independently selected from the group consisting of a branched or unbranched, substituted or unsubstituted C_1 - C_{10} alkyl group, a branched or unbranched, substituted or unsubstituted C_2 - C_{10} alkynyl group, a substituted or unsubstituted C_2 - C_{10} alkenyl group, a substituted or unsubstituted C_2 - C_{20} cycloalkyl group, and a substituted or unsubstituted C_6 - C_{20} cycloalkylalkylene group;
- R^{24} is independently selected from the group consisting of hydrogen, a branched or unbranched, substituted or unsubstituted C_2 - C_{10} alkynyl group, a substituted or unsubstituted C_2 - C_{20} cycloalkyl group, a substituted or unsubstituted C_6 - C_{20} cycloalkylalkylene group, a substituted C_5 - C_{20} aryl group, a substituted or unsubstituted C_6 - C_{20} arylalkylene group, an acetyl group, a substituted or unsubstituted C_3 - C_{20} heterocyclic ring comprising at least one of O, N, S and Se in the ring;

wherein $x = 1$ or 2 ; $y = 1$ or 2 ; $z = 0$ or 1 ; and $(x+y+z) = 3$;

wherein each of R^{15} , R^{16} , R^{18} , R^{19} and R^{20} independently represent H or optionally substituted C_1 - C_{40} carbyl or hydrocarbyl group optionally comprising one or more heteroatoms;

- 5 wherein R^{17} represents a halogen atom, H or optionally substituted C_1 - C_{40} carbyl or C_1 - C_{40} hydrocarbyl group optionally comprising one or more heteroatoms;

wherein k and l are independently 0 or 1;

- wherein R^1 , R^2 , R^3 , R^4 , R^5 , R^6 and R^7 which may be the same or different, independently each represent, hydrogen; a branched or unbranched, substituted or
 10 unsubstituted C_1 - C_{40} alkyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkenyl group; a branched or unbranched, substituted or unsubstituted C_2 - C_{40} alkynyl group; an optionally substituted C_3 - C_{40} cycloalkyl group; an optionally substituted C_6 - C_{40} aryl group; an optionally substituted C_1 - C_{40} heterocyclic group; an optionally substituted C_1 - C_{40} heteroaryl group; an optionally
 15 substituted C_1 - C_{40} alkoxy group; an optionally substituted C_6 - C_{40} aryloxy group; an optionally substituted C_7 - C_{40} alkylaryloxy group; an optionally substituted C_2 - C_{40} alkoxycarbonyl group; an optionally substituted C_7 - C_{40} aryloxycarbonyl group; a cyano group ($-CN$); a carbamoyl group ($-C(=O)NR^{15}R^{16}$); a carbonyl group ($-C(=O)-R^{17}$); a carboxyl group ($-CO_2R^{18}$); a cyanate group ($-OCN$); an isocyano group ($-NC$);
 20 an isocyanate group ($-NCO$); a thiocyanate group ($-SCN$) or a thioisocyanate group ($-NCS$); an optionally substituted amino group; a hydroxy group; a nitro group; a CF_3 group; a halo group (Cl, Br, F, I); $-SR^{19}$; $-SO_3H$; $-SO_2R^{20}$; $-SF_5$; an optionally substituted silyl group;

- wherein preferably at least one of R^1 , R^2 , R^3 , R^4 , R^5 , R^6 and R^7 is substituted with
 25 at least one polar or more polarising group which is independently selected from the group consisting of nitro group, nitrile group, C_{1-40} alkyl group substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; a C_{1-40} alkoxy group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a
 30 thioisocyanate group; a C_{1-40} carboxylic acid group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; a C_{2-40} carboxylic acid ester optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; sulfonic acid optionally substituted with a nitro
 35 group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or

- a thioisocyanate group; sulfonic acid ester optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; cyanate group, isocyanate group, thiocyanate group, thioisocyanate group; and an amino group optionally substituted with a nitro group, a nitrile group, a cyanate group, an isocyanate group, a thiocyanate group or a thioisocyanate group; and combinations thereof;

wherein X' is a halogen atom or a cyclic borate group; and

wherein Z' is a halogen atom.

41. A process for producing a Polycyclic Aromatic Hydrocarbon Copolymer (PAHC) according to claim 40, further comprising any of the features as defined in any of claims 12 to 26.

42. A Polycyclic Aromatic Hydrocarbon Copolymer (PAHC) obtainable according to a process of any of claims 36 to 41.




Figure 1




Figure 2




Figure 3




Figure 4