

**(12) PATENT
(19) AUSTRALIAN PATENT OFFICE**

**(11) Application No. AU 199922566 B2
(10) Patent No. 752078**

(54) Title
Ink, ink set, ink cartridge, recording unit, image recording process and image recording apparatus

(51)⁷ International Patent Classification(s)
B41J 002/175 C09D 011/10

(21) Application No: **199922566** (22) Application Date: **1999.03.31**

(30) Priority Data

(31) Number	(32) Date	(33) Country
10-088690	1998.04.01	JP
10-088691	1998.04.01	JP
11-083598	1999.03.26	JP

(43) Publication Date : **1999.10.14**

(43) Publication Journal Date : **1999.10.14**

(44) Accepted Journal Date : **2002.09.05**

(71) Applicant(s)
Canon Kabushiki Kaisha

(72) Inventor(s)
Yutaka Kurabayashi

(74) Agent/Attorney
SPRUSON and FERGUSON, GPO Box 3898, SYDNEY NSW 2001

(56) Related Art
US 5879439

ABSTRACT

INK, INK SET, INK CARTRIDGE, RECORDING UNIT, IMAGE RECORDING

5

PROCESS AND IMAGE RECORDING APPARATUS

There is disclosed an ink (21) comprising a pigment and a resin encapsulating a coloring material. The ink can provide an image high in optical density and excellent in
10 rub-off resistance, water fastness and resistance to line marker, and exhibits excellent ejection (22) stability from a recording head (13) when used in ink-jet recording.

100
200
300
400
500

600
700

800
900

1000
1100

AUSTRALIA

PATENTS ACT 1990

COMPLETE SPECIFICATION

FOR A STANDARD PATENT

ORIGINAL

Name and Address
of Applicant: Canon Kabushiki Kaisha
30-2, Shimomaruko 3-chome
Ohta-ku
Tokyo 146
JAPAN

Actual Inventor(s): Yutaka Kurabayashi

Address for Service: Spruson & Ferguson, Patent Attorneys
Level 33 St Martins Tower, 31 Market Street
Sydney, New South Wales, 2000, Australia

Invention Title: Ink, Ink Set, Ink Cartridge, Recording Unit, Image
Recording Process and Image Recording Apparatus

The following statement is a full description of this invention, including the
best method of performing it known to me/us:-

INK, INK SET, INK CARTRIDGE, RECORDING UNIT,
IMAGE RECORDING PROCESS AND
IMAGE RECORDING APPARATUS

5 BACKGROUND OF THE INVENTION

Field of the Invention

The present invention relates to an ink which is suitable for use in ink-jet recording, excellent in reliability, and capable of providing an image having a high optical density even on plain paper and also forming an image having excellent water fastness and resistance to line marker, and an ink set, ink cartridge, recording unit, image recording apparatus and image recording process using such an ink. The present invention also relates to an ink which is suitable for use in ink-jet recording, excellent in reliability, capable of providing an image having a high optical density even on plain paper, forming an image having excellent water fastness and resistance and further extremely effectively preventing bleeding at boundaries between different colors of a multi-color image on a recording medium when the multi-color image is formed together with other color inks by an ink-jet recording method, and an ink set, ink cartridge, recording unit, image recording apparatus and image recording process using such an ink.

Related Background Art

An ink-jet recording method is a system in which recording is conducted by ejecting an ink to apply the ink to a recording medium such as paper. According to 5 an ink-jet recording system disclosed in, for example, Japanese Patent Publication Nos. 61-59911, 61-59912 and 61-59914, in which an electrothermal converter is used as an ejection-energy supply means to apply thermal energy to an ink so as to generate bubbles, thereby 10 ejecting the ink, the formation of a high-density multi-orifice in a recording head can be realized with ease, and a high-resolution and high-quality image can be recorded at high speed. Therefore, such an ink-jet system is a main system for ink-jet recording methods 15 put to practical use at present.

By the way, for example, a water-soluble dye is used as a coloring material in an ink used in such an ink-jet recording method. However, images recorded with such an ink are required to more improve their 20 water fastness, and resistance to line marker on plain paper.

When a multi-color printing is conducted on plain paper, there is also a demand for further reduction in the so-called color bleed caused by mixing of inks of 25 different colors at boundaries between the inks in an image formed with such inks.

A great number of means for overcoming such

problems, particularly, improving the optical density and water fastness of recorded images have been proposed to date. As one of the solutions thereof, it is proposed to prepare an ink containing a pigment as a 5 coloring material and dispersed in water. For example, an ink using carbon black as a coloring material permits the provision of an image having a high optical density and excellent water fastness by ink-jet recording. However, such a recorded image still 10 leaves room for improvement in rub-off resistance and resistance to line marker on plain paper in particular.

As a technique for overcoming such problems as described above, it has been known to improve image fixing ability by adding a resin in the ink. For 15 example, Japanese Patent Application Laid-Open No. 3-172362 discloses a technique wherein a cationic emulsion, in which resin particles are dispersed as a fixing agent, is contained in an ink comprising a dye or pigment as a coloring material to improve the fixing 20 ability of the ink on a recording medium. Japanese Patent Application Laid-Open No. 8-239610 discloses a water-based pigment composition for ink-jet, comprising a pigment, a colored resin and a humectant as essential components. It is also disclosed that a print 25 excellent in both coloring ability and water fastness can be provided by such a composition.

SUMMARY OF THE INVENTION

According to the extensive study of the aforementioned prior art by the present inventor, since the upper limits of amounts of a pigment and a resin, which can be contained in an ink, are naturally defined when the ejection stability of the ink is taken into consideration, it is inevitable to choose the amount of the pigment, which affects the optical density of a recorded image, and the amount of the resin, which affects the image fixing ability of the ink, in terms of the balance between the trade-off characteristics, i.e., the optical density and the image fixing ability. Therefore, the present inventor has concluded that it cannot be yet said under the circumstances that the pigment inks proposed to date fully make the best use of merits obtained by using a pigment as a coloring material.

More specifically, Japanese Patent Application Laid-Open No. 8-239160 explains in the specification thereof that the colored resin is a dispersion of a resin colored by a dye. According to the preparation process of the colored resin described in the Example thereof, a dye is first added to an emulsion of a resin, and the mixture is heated to about 80°C and then cooled, thereby preparing the colored resin. However, in page 4, left column, lines 38 to 41 of this patent specification, it is described that "In order

for the dye to be sufficiently taken in the resin, the amount (of the dye) is preferably 10 parts or less, particularly 8 parts or less, per 100 parts of the resin". In each of the preparation processes described 5 in Preparation Examples 8 to 13 of the specification, a mixing proportion of the dye to the solid resin content in the emulsion polymer is described as about 1:10 to 1:12 (dye:resin). According to the investigation by the present inventor, it has however been concluded 10 that, when such a colored resin as described in Japanese Patent Application Laid-Open No. 8-239610 is used, such a proportion of the dye to the resin as described in the specification may not be said in some cases to be sufficient to compensate for a reduction in 15 an optical density, due to a reduction of amount of a coloring material which can be contained in an ink, accompanied by the addition of the resin to the pigment ink for the purpose of improving the fixing ability of the ink to recording media. Further, it is inferred 20 that when the colored resin is intended to added to such an extent that a sufficient optical density is achieved, the colored resin must be added in such an amount that departs from a range in which an ink-jet ink can be precisely ejected by an ink-jet recording 25 system. As described above, from the investigations as to the prior art, the present inventor has reached

a conclusion that the development of a new technique entirely different from the conventional techniques is required for further improvements in optical density and image fixing ability in pigment inks.

Therefore, the present inventor has carried out a further investigation. As a result, a technique which can solve the problems on inks containing a pigment while making the best use of the merits obtained by using the pigment as a coloring material has been found, thus leading to completion of the present invention. Similarly, as the result of the investigation by the present inventors, a technique which can solve the problems on inks containing a pigment while making the best use of the merits obtained by using the pigment as a coloring material, and extremely effectively prevent bleeding when applied to multi-color printing has also been found, thus leading to completion of the present invention.

In one embodiment of the present invention, there is thus provided an aqueous ink for ink-jet recording, comprising a self-dispersing pigment in which at least one hydrophilic group is bonded directly or through another atomic group to the surface of the pigment, and a resin encapsulating a coloring material, the self-dispersing pigment and the resin encapsulating a coloring material being dispersed in an aqueous medium.



Such an ink can provide a high-quality image high in optical density and excellent in rub-off resistance, water fastness and resistance to line marker by ink-jet recording, and is excellent in reliability (ejection durability, ejection stability, anti-clogging property, etc.) upon ink-jet recording.

5 In another embodiment of the present invention, there is provided an aqueous ink for an ink-jet printing process comprising:

10 a colorant comprised of a self-dispersing pigment in which at least one hydrophilic group is bonded directly or through another atomic group, and a resin encapsulating coloring material in a certain amount, the self-dispersing pigment and the resin encapsulating coloring material being dispersed in an aqueous medium,

wherein the ink provides an image whose optical density is substantially equivalent to that formed by an ink comprising the self-dispersing pigment as a sole colorant in the certain amount.

15 The above embodiments are adopted, thereby bringing about an effect that a high-quality image high in optical density and excellent in rub-off resistance, water fastness and resistance to line marker is provided by ink-jet recording.

33
34
35
36
37

38
39
40
41
42



BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a longitudinal cross-sectional view of a head of an ink-jet recording apparatus according to an embodiment.

Fig. 2 is a transverse cross-sectional view taken along line 2-2 in Fig. 1.

5

THE NEXT PAGE IS PAGE 14



Fig. 3 schematically illustrates a multi-head.

Fig. 4 is a schematic perspective view illustrating an ink-jet recording apparatus according to an embodiment.

5 Fig. 5 is a longitudinal cross-sectional view of an ink cartridge according to an embodiment.

Fig. 6 is a perspective view of a recording unit.

10 Fig. 7 is a schematic perspective view illustrating another exemplary construction of an ink-jet recording head.

Fig. 8 schematically illustrates a recording head in which 4 ink cartridges are installed.

Fig. 9 schematically illustrates the construction that 4 recording heads are arranged on a carriage.

15

DESCRIPTION OF THE PREFERRED EMBODIMENTS

The ink according to the first embodiment of the present invention comprises a pigment and a resin encapsulating a coloring material. The respective requirements for components will hereinafter be 20 described in the following order:

- (1) a resin encapsulating a coloring material;
- (2) a pigment;
- (3) an aqueous medium, other additives, etc.; and
- 25 (4) a recording apparatus, recording process, etc.

(1) Resin encapsulating a coloring material:

The resin encapsulating a coloring material will hereinafter be described.

As examples of the resin encapsulating a coloring material, may be mentioned a resin with a coloring material encapsulated in a microcapsule made of the resin, and a resin emulsion with a dye or pigment, which has been dispersed or dispersed in an oily solvent, dispersed in an aqueous medium. However, the microcapsulized resin encapsulating the coloring material is particularly preferred.

More specifically, in the case where a hydrophobic coloring material, for example, an oil color or a pigment, is used as the coloring material, it is considered that since the coloring material and the hydrophobic moiety of the resin are easy to interact with each other by the microcapsulization, the hydrophobic moiety of the resin becomes hard to be oriented toward a water system. As a result, it is expected that when an ink-jet ink comprising such a resin encapsulating the coloring material is ejected from an ink-jet printer, the resin is prevented from depositing to and accumulating on the nozzle-formed surface of an ink-jet head subjected to a water-repellent treatment, and so such a resin contributes to a further improvement in the ejection stability of the ink over a long period of time.

The resin with the coloring material

microcapsulized therein is a resin dispersion obtained by dissolving or dispersing the coloring material in an oily solvent, emulsifying and dispersing the solution or dispersion thus obtained in water and then 5 microcapsulizing the resultant emulsion by a proper method conventionally known.

As the coloring material, there may preferably be used a water-insoluble coloring material, for example, a pigment or oil-soluble dye. Namely, the water-insoluble coloring material is easy to prepare the resin with the coloring material microcapsulized therein. Specifically, carbon black or the like may be used as a pigment for black (Bk). As the carbon black, may preferably be used ones which are produced in accordance with the furnace process or channel process and have such properties that the primary particle diameter is from 15 to 40 nm, the specific surface area is from 50 to 300 m²/g as measured by the BET method, the oil absorption is from 40 to 150 ml/100 g as 10 determined by using DBP, the volatile matter is from 0.5 to 10 %, and the pH is from 2 to 9. Examples of 15 commercially-available carbon black having such properties include No. 2300, No. 900, MCF88, No. 33, No. 40, No. 45, No. 52, MA7, MA8 and No. 2200B (all, 20 products of Mitsubishi Chemical Industries Limited), RAVEN 1255 (product of Columbian Carbon Japan Limited), 25 REGAL 400R, REGAL 330R, REGAL 660R and MOGUL L (all,

products of CABOT Co.), and Color Black FW-1, Color Black FW18, Color Black S170, Color Black S150, Printex 35 and Printex U (all, products of Degussa AG).

As the oil-soluble dye, may preferably be used
5 the following dyes:

C.I. Solvent Yellow 1, 2, 3, 13, 19, 22, 29, 36,
37, 38, 39, 40, 43, 44, 45, 47, 62, 63, 71, 76, 81, 85
and 86;

10 C.I. Solvent Red 8, 27, 35, 36, 37, 38, 39, 40,
58, 60, 65, 69, 81, 86, 89, 91, 92, 97, 99, 100, 109,
118, 119 and 122;

C.I. Solvent Blue 14, 24, 26, 34, 37, 38, 39, 42,
43, 45, 48, 52, 53, 55, 59 and 67; and

15 C.I. Solvent Black 3, 5, 7, 8, 14, 17, 19, 20,
22, 24, 26, 27, 28, 29, 43 and 45.

Various kinds of conventionally known water-soluble dyes may also be used so far as the counter ions thereof (usually, sodium, potassium or ammonium ion) are replaced by an organic amine or the like.

20 It is preferred that a coloring material having the same color tone as the pigment, which will be described subsequently, be selected from among the various kinds of coloring materials described above in order to, for example, adjust or compensate for the 25 color tone of the pigment. The optical density of the resulting recorded image can be thereby further enhanced. For example, when carbon black is used as

the pigment as will be described subsequently, it is preferred that carbon black be also used as the coloring material. Two or more coloring materials may be used as the coloring material encapsulated in the 5 resin.

In this case, the respective coloring materials may be encapsulated in either different resins or a resin in common with the coloring materials.

A process for preparing the resin with the 10 coloring material encapsulated in a microcapsule in the resin as the resin encapsulating the coloring material will hereinafter be described.

The coloring material is first dissolved or dispersed in an oily solvent, and the oily solvent is 15 then emulsified and dispersed in water. Examples of a method for emulsifying and dispersing the oily solvent with the coloring material dissolved or dispersed therein in water, may be mentioned a dispersion method by ultrasonic wave and methods using various kinds of 20 dispersing machines or stirring machines. At this time, various kinds of emulsifiers and/or dispersants, and moreover emulsification or dispersion aids such as protective colloid may also be used as needed.

As these emulsifiers and dispersion aids, there 25 may be used polymeric substances such as PVA, PVP and gum arabic, and besides anionic surfactants, nonionic surfactants and the like. Examples of a method for

microcapsulizing the above emulsion include a method in which the coloring material and the resin are dissolved in a water-insoluble organic solvent (oily solvent), and the solution is subjected to phase inversion into a 5 water system, thereby conducting phase-inversion emulsification, an interfacial polymerization method in which a polymerization reaction is caused at an interface between an organic phase and an aqueous phase to conduct microcapsulization, the so-called *in-situ* 10 polymerization method in which a material capable of forming a wall to an organic phase alone is dissolved or co-existed, thereby forming microcapsules, and a coacervation method in which the pH, temperature, concentration and the like of an aqueous solution of a 15 polymer are changed, thereby phase-separating a concentrated phase of the polymer to form microcapsules. After the formation of microcapsules, a step of removing the oily solvent is added. The average particle diameter of the resin encapsulating 20 the coloring material obtained in the above-described manner is preferably within a range of from 0.01 to 2.0 μm , more preferably from 0.05 to 1 μm .

In this embodiment, examples of the resin include polymers of a monomer as a hydrophilic functional group 25 and a monomer as a hydrophobic functional group, and salts thereof. Examples of monomers having anionic hydrophilic group generally include sulfonic acid type

monomers and carboxylic acid type monomers. Examples of the sulfonic acid type monomers include styrenesulfonic acid and salts thereof, and vinylsulfonic acid and salts thereof. Examples of the 5 carboxylic acid type monomers include α, β -ethylenically unsaturated carboxylic acids, α, β -ethylenically unsaturated carboxylic acid derivatives, acrylic acid, acrylic acid derivatives, methacrylic acid, methacrylic acid derivatives, maleic acid, maleic acid derivatives, 10 itaconic acid, itaconic acid derivatives, fumaric acid and fumaric acid derivatives. Examples of the monomer as the hydrophobic component include styrene, styrene derivatives, vinyltoluene, vinyltoluene derivatives, vinylnaphthalene, vinylnaphthalene derivatives, 15 butadiene, butadiene derivatives, isoprene, isoprene derivatives, ethylene, ethylene derivatives, propylene, propylene derivatives, alkyl acrylates and alkyl methacrylates.

Examples of the salts of the polymers include 20 onium compounds with an alkali metal, ammonium ion, organic ammonium ion, phosphonium ion, sulfonium ion, oxonium ion, stibonium ion, stannonium ion or iodonium ion. To the above polymers and salts thereof, may be suitably added a polyoxyethylene group, hydroxyl group, 25 acrylamide, acrylamide derivative, dimethylaminoethyl methacrylate, ethoxyethyl methacrylate, butoxyethyl methacrylate, ethoxytriethylene methacrylate,

methoxypolyethylene glycol methacrylate,
vinylpyrrolidone, vinylpyridine, vinyl alcohol, alkyl
ether and the like.

(2) Pigment:

5 As the pigment, the conventionally known
pigments, for example, carbon black and organic
pigments, may be used without any problem. In the case
where a black ink is prepared, it is preferred to use a
self-dispersing carbon black to the surface of which at
10 least one hydrophilic group is bonded directly or
through another atomic group. More specifically, when
the self-dispersing carbon black is used, there need
not add a dispersant for dispersing a pigment in an
ink, or its amount added can be reduced to a great
15 extent. As the dispersant, there may be used a
conventionally known water-soluble polymer or the like.
However, such a polymer may deposit on the ink-ejection
opening face of an ink-jet recording head in some cases
to lower the ejection stability of the ink.

20 When such the self-dispersing carbon black as
described above is used as the pigment, however, the
content of such a polymer can be made zero or reduced
to a great extent. As a result, the ejection stability
of the resulting ink upon ink-jet recording can be
25 further improved.

The self-dispersing carbon black will hereinafter
be described in detail. The self-dispersing carbon

black preferably has an ionicity, and, for example, those anionically charged may be preferably used.

Examples of the carbon black anionically charged include those obtained by bonding, for example, any of 5 such hydrophilic groups:

-COO(M2), -SO₃(M2), -PO₃H(M2) and -PO₃(M2)₂, to the furface of carbon black.

In the above formulae, M2 is hydrogen, alkali metal, ammonium or organic ammonium. Of these, carbon black 10 anionically charged by bonding -COO(M2) or -SO₃(M2) to the surface thereof is particularly preferably used in this embodiment, since its dispersibility in the ink is good. Of those represented by "M2" in the above-described hydrophilic 15 groups, specific examples of the alkali metal include Li, Na, K, Rb and Cs, and specific examples of the organic ammonium include methylammonium, dimethylammonium, trimethyl-ammonium, ethylammonium, diethylammonium, triethyl-ammonium, methanol ammonium, 20 dimethanol ammonium and trimethanol ammonium. As an example of a method for preparing the anionically charged self-dispersing carbon black may be mentioned a method in which carbon black is subjected to an oxidation treatment with sodium hypochlorite.

25 According to this method, a -COONa group can be chemically bonded to the surface of carbon black.

(3) Aqueous medium, other additives, etc.:

The resin encapsulating the coloring material and the pigment are held in a dispersed state by an aqueous medium to constitute the ink. The aqueous medium preferably contain at least water as a 5 component. It is preferred that a proportion of water accounted for in the ink be, for example, 20 to 95 % by weight, particularly 40 to 95 % by weight, more particularly 60 to 95 % by weight based on the total weight of the ink.

10 At least one water-soluble organic solvent may be contained in the aqueous medium. Examples of water-soluble organic solvents preferably used include alkyl alcohols having 1 to 4 carbon atoms, such as methyl alcohol, ethyl alcohol, n-propyl alcohol, isopropyl 15 alcohol, n-butyl alcohol, sec-butyl alcohol and tert-butyl alcohol; ketones and ketone alcohols such as acetone and diacetone alcohol; amides such as dimethylformamide and dimethylacetamide; ethers such as tetrahydrofuran and dioxane; polyalkylene glycols such 20 as polyethylene glycol and polypropylene glycol; alkylene glycols the alkylene moiety of which has 2 to 6 carbon atoms, such as ethylene glycol, propylene glycol, butylene glycol, triethylene glycol, thiodiglycol, hexylene glycol and diethylene glycol; 25 1,2,6-hexanetriol; glycerol; alkyl ethers of polyhydric alcohols, such as ethylene glycol methyl ether, ethylene glycol ethyl ether, triethylene glycol

monomethyl and triethylene glycol monoethyl ether; N-methyl-2-pyrrolidone; 2-pyrrolidone; and 1,3-dimethyl-2-imidazolidinone. The total content of the water-soluble organic solvents in the ink is within a range of from 2 to 60 % by weight, preferably from 5 to 25 % by weight based on the total weight of the ink.

A preferred water-soluble organic solvent is glycerol, and its amount added is preferably 2 to 30 % by weight, more preferably 5 to 15 % by weight based on the total weight of the ink. A more preferred water-soluble organic solvent is a mixed solvent comprising glycerol and another polyhydric alcohol (for example, diethylene glycol, ethylene glycol or the like). The mixing ratio of glycerol to said another polyhydric alcohol is preferably within a range of from 10:5 to 10:50. Examples of the polyhydric alcohol another than glycerol include diethylene glycol, ethylene glycol, polyethylene glycol and propylene glycol. Further, these glycerol and mixed solvent of glycerol and another polyhydric alcohol may be used in combination with other water-soluble organic solvents.

The inks according to this embodiment are suitably used in ink-jet recording method in which an ink is ejected from a recording head by thermal energy or mechanical energy to apply it to a recording medium, thereby recording an image. When the inks according to this embodiment are made particularly suitable for use

in ink-jet recording, the inks are controlled so as to have, as their own physical properties as measured at 25°C, a surface tension of 15 to 60 dyn/cm, preferably 20 to 50 dyn/cm, a viscosity of 15 cP or lower, 5 particularly 10 cP or lower, more particularly 5 cP or lower and a pH within a range of preferably from 3 to 11, more preferably from 3.5 to 8. As specific ink compositions capable of achieving such properties, may be mentioned, for example, the compositions of various 10 inks used in Examples which will be described subsequently.

Incidentally, to the inks according to this embodiment, may be added various kinds of additives such as surfactants, pH adjusters and mildewproofing 15 agents in addition to the resin encapsulating the coloring material obtained in the above-described manner and the pigment.

No particular limitation is imposed on recording media used in a recording process using the inks 20 according to this embodiment, and examples thereof include various kinds of plain paper such as paper for copying and bond paper, coated paper specially prepared for ink-jet recording, glossy paper, and OHP films.

The ink according to the second embodiment of the 25 present invention comprises either a pigment having a cationic group, or a pigment and a pigment dispersant having a cationic group, and a resin encapsulating a

coloring material.

The respective requirement for components of this embodiment will hereinafter be described in the following order:

- 5 (4) a resin having a cationic group and encapsulating a coloring material;
- (5) a pigment dispersion in which a pigment or a pigment dispersant has a cationic group; and
- (6) an aqueous medium, other additives, etc.

10 (4) Resin having a cationic group and encapsulating a coloring material:

The resin encapsulating a coloring material will hereinafter be described.

15 Examples of the resin encapsulating a coloring material include a resin with a coloring material encapsulated in a microcapsule of the resin, and an aqueous dispersion of a resin having a cationic group, wherein the resin encapsulates a coloring material by emulsifying a dye or pigment dissolved or dispersed in 20 an oily solvent. Of these, the resin with the coloring material encapsulated in a microcapsule of the resin is particularly preferred.

25 The resin with the coloring material encapsulated in a microcapsule of the resin is a resin dispersion obtained by dissolving or dispersing the coloring material in an oily solvent, emulsifying and dispersing the solution or dispersion thus obtained in water and

then microcapsulizing the resultant emulsion by a proper method conventionally known.

As the coloring material, there may be used any of those described in the above requirement (1).

5 A process for preparing the resin with the coloring material encapsulated in the microcapsule of the resin as the resin encapsulating the coloring material will hereinafter be described.

10 The coloring material is first dissolved or dispersed in an oily solvent, and the oily solvent is then emulsified and dispersed in water. Examples of a method for emulsifying and dispersing the oily solvent with the coloring material dissolved or dispersed therein, may be mentioned a dispersion method by 15 ultrasonic wave and methods using various kinds of dispersing machines or stirring machines. At this time, various kinds of emulsifiers and/or dispersants, and moreover emulsification or dispersion aids such as protective colloid may also be used as needed. As 20 these emulsifiers and dispersion aids, there may be used polymeric substances such as PVA, PVP and gum arabic, and besides anionic surfactants, nonionic surfactants and the like. Examples of a method for 25 microcapsulizing the above emulsion include a method in which the coloring material and the resin are dissolved in a water-insoluble organic solvent (oily solvent), and the solution is subjected to phase inversion into a

water system, thereby conducting phase-inversion emulsification, an interfacial polymerization method in which a polymerization reaction is caused at an interface between an organic phase and an aqueous phase 5 to conduct microcapsulization, the so-called *in-situ* polymerization method in which a material capable of forming a wall to an organic phase alone is dissolved or co-existed, thereby forming microcapsules, and a coacervation method in which the pH, temperature, 10 concentration and the like of an aqueous solution of a polymer are changed, thereby phase-separating a concentrated phase of the polymer to form microcapsules. After the formation of microcapsules, a 15 step of removing the oily solvent is added. The average particle diameter of the resin encapsulating the coloring material obtained in the above-described manner is preferably within a range of from 0.01 to 2.0 μm , more preferably from 0.05 to 1 μm .

Examples of the cationic group in the resin which 20 encapsulates the coloring material include N,N-dimethyl-aminoethyl methacrylate
[$\text{CH}_2=\text{C}(\text{CH}_3)\cdot\text{COO}\cdot\text{C}_2\text{H}_4\text{N}(\text{CH}_3)_2$], N,N-dimethylaminoethyl acrylate [$\text{CH}_2=\text{CH}\cdot\text{COO}\cdot\text{C}_2\text{H}_4\text{N}(\text{CH}_3)_2$], N,N-dimethylaminopropyl methacrylate [$\text{CH}_2=\text{C}(\text{CH}_3)\cdot\text{COO}\cdot\text{C}_3\text{H}_6\text{N}(\text{CH}_3)_2$], N,N-dimethylaminopropyl acrylate [$\text{CH}_2=\text{CH}\cdot\text{COO}\cdot\text{C}_3\text{H}_6\text{N}(\text{CH}_3)_2$], N,N-dimethylacrylamide
[$\text{CH}_2=\text{CH}\cdot\text{CON}(\text{CH}_3)_2$], N,N-dimethylmethacrylamide

[$\text{CH}_2=\text{C}(\text{CH}_3)\cdot\text{CON}(\text{CH}_3)_2$], N,N- dimethylaminoethyl acrylamide [$\text{CH}_2=\text{CH}\cdot\text{CONHC}_2\text{H}_4\text{N}(\text{CH}_3)_2$], N,N- dimethylaminoethyl methacrylamide [$\text{CH}_2=\text{C}(\text{CH}_3)\cdot\text{CONH-C}_2\text{H}_4\text{N}(\text{CH}_3)_2$], N,N-dimethylaminopropyl acrylamide 5 [$\text{CH}_2=\text{CH}\cdot\text{CONHC}_3\text{H}_6\text{N}(\text{CH}_3)_2$] and N,N-dimethylaminopropyl methacrylamide [$\text{CH}_2=\text{C}(\text{CH}_3)\cdot\text{CONHC}_3\text{H}_6\text{N}(\text{CH}_3)_2$].

In the case of a tertiary amine, examples of a compound for forming a salt include hydrochloric acid, sulfuric acid and acetic acid. Examples of a compound 10 used in quaternization include methyl chloride, dimethylsulfuric acid, benzyl chloride and epichlorohydrin.

(5) Pigment:






As the pigment according to this embodiment, the 15 conventionally known carbon black and organic pigments may be used without any problem. However, particularly preferred is a self-dispersing carbon black to the surface of which at least one cationic hydrophilic group is bonded directly or through another atomic 20 group.

Specific examples thereof will hereinafter be described.

(Cationically charged carbon black)

Examples of cationically charged carbon black 25 include those obtained by bonding at least one selected from among the following quaternary ammonium groups to the surface of carbon black.


$-\text{SO}_2\text{N}^+\text{H}_3$, $-\text{SO}_2\text{N}^+\text{H}_2\text{COR}$, $-\text{N}^+\text{H}_3$, $-\text{N}^+\text{R}_3$,



In the above formulae, R is a straight or branched alkyl group having 1 to 12 carbon atoms, a substituted or unsubstituted phenyl group or a substituted or unsubstituted naphthyl group.

5 As an example of a method for producing the self-dispersing carbon black cationically charged by bonding such a hydrophilic group as described above, is described a method for bonding, for example, an N-ethylpyridyl group of the structure

10



to the surface of carbon black.

15 Namely, there is mentioned a method in which carbon black is treated with 3-amino-N-ethylpyridinium bromide. The self-dispersing carbon black cationically charged by introducing the hydrophilic group into the surface of carbon black in this manner keeps a stably dispersed state even when it is contained in a water-based ink without adding any dispersant or the like, since it has good dispersibility in water by virtue of repulsion of the ion thereof.

20 Such various hydrophilic groups as described above may be bonded directly to the surface of carbon black. Alternatively, another atomic group may be intervened between the surface of carbon black and the hydrophilic group to bond the hydrophilic group

indirectly to the surface of carbon black. Specific examples of said another atomic group include linear or branched alkylene groups having 1 to 12 carbon atoms, a substituted or unsubstituted phenylene group and a substituted or unsubstituted naphthylene group.

5 Examples of substituent groups on the phenylene and naphthylene groups include linear or branched alkyl groups having 1 to 6 carbon atoms. Specific examples of combinations of said another group and the 10 hydrophilic group include $-C_2H_4-COOM$, $-Ph-SO_3M$, $Ph-COOM$ and $-C_5H_{10}-NH_3^+$, wherein Ph is a phenyl group.

In this embodiment, two or more of the self-dispersing carbon black described above may be suitably 15 selected and used as a coloring material for the ink. The amount of the self-dispersing carbon black to be added in the ink is preferably within a range of from 0.1 to 15 % by weight, particularly from 1 to 10 % by weight, based on the total weight of the ink. When the 20 self-dispersing carbon black is added in this range, its satisfactory dispersion state can be kept in the ink.

In this embodiment, not only the self-dispersing carbon black having a cationic group but also a pigment 25 dispersion in which the conventionally known carbon black as described above is dispersed by a dispersant having a cationic group may be used. The term "a

pigment dispersant" herein used means "a dispersant for dispersing a pigment". Examples of the dispersant having a cationic group include those obtained by polymerization of vinyl monomers. Examples of a 5 cationic monomer constituting at least a part of the polymers obtained include salts of a tertiary amine monomer and quaternized compounds thereof. Examples of such compounds include N,N-dimethylaminoethyl methacrylate [$\text{CH}_2=\text{C}(\text{CH}_3)\cdot\text{COO}\cdot\text{C}_2\text{H}_4\text{N}(\text{CH}_3)_2$], N,N- 10 dimethylaminoethyl acrylate [$\text{CH}_2=\text{CH}\cdot\text{COO}\cdot\text{C}_2\text{H}_4\text{N}(\text{CH}_3)_2$], N,N-dimethylaminopropyl methacrylate [$\text{CH}_2=\text{C}(\text{CH}_3)\cdot\text{COO}\cdot\text{C}_3\text{H}_6\text{N}(\text{CH}_3)_2$], N,N-dimethyl-aminopropyl 15 acrylate [$\text{CH}_2=\text{CH}\cdot\text{COO}\cdot\text{C}_3\text{H}_6\text{N}(\text{CH}_3)_2$], N,N-dimethylacrylamide [$\text{CH}_2=\text{CH}\cdot\text{CON}(\text{CH}_3)_2$], N,N-dimethyl-methacrylamide 20 [$\text{CH}_2=\text{C}(\text{CH}_3)\cdot\text{CON}(\text{CH}_3)_2$], N,N-dimethyl-aminoethyl acrylamide [$\text{CH}_2=\text{CH}\cdot\text{CONHC}_2\text{H}_4\text{N}(\text{CH}_3)_2$], N,N-dimethylaminoethyl methacrylamide [$\text{CH}_2=\text{C}(\text{CH}_3)\cdot\text{CONH-}\text{C}_2\text{H}_4\text{N}(\text{CH}_3)_2$], N,N-dimethylaminopropyl acrylamide [$\text{CH}_2=\text{CH}\cdot\text{CONHC}_3\text{H}_6\text{N}(\text{CH}_3)_2$] and N,N-dimethylaminopropyl 25 methacrylamide [$\text{CH}_2=\text{C}(\text{CH}_3)\cdot\text{CONHC}_3\text{H}_6\text{N}(\text{CH}_3)_2$]. In the case of a tertiary amine, examples of a compound for forming a salt include hydrochloric acid, sulfuric acid and acetic acid. Examples of a compound used in quaternization include methyl chloride, dimethylsulfuric acid, benzyl chloride and epichlorohydrin. Of these, methyl chloride and dimethylsulfuric acid are preferred from the view point

of the preparation of the dispersant used in this embodiment. Such tertiary amine salts and quaternary ammonium compounds as described above act as cations in water, and they are stably soluble in an acidic region 5 under neutralized conditions. The content of these monomers in their corresponding copolymers is preferably within a range of from 20 to 60 % by weight.

Examples of other monomers used for constituting the above-described cationic polymer dispersants 10 include acrylic esters having a hydroxyl group, such as 2-hydroxyethyl methacrylate and acrylic esters having a long ethylene oxide chain at their side chains, hydrophobic monomers such as styrenic monomers, and water-soluble monomers soluble in water at about pH 7, 15 such as acrylamide and derivatives thereof, vinyl ether and derivatives thereof, vinylpyrrolidone and derivatives thereof, vinylpyridine and derivatives thereof, and vinyloxazoline and derivatives thereof. Examples of the hydrophobic monomers used include 20 styrene, styrene derivatives, vinylnaphthalene, vinylnaphthalene derivatives, alkyl esters of (meth)acrylic acid and acrylonitrile. In the polymer dispersant obtained by copolymerization, it is preferred that the water-soluble monomer be used in a 25 range of from 15 to 35 % by weight in order to stabilize the copolymer in an aqueous solution, while the hydrophobic monomer be used in a range of from 20

to 40 % by weight in order to enhance the dispersing effect of the copolymer on the pigment.

Upon use of the above-described cationic water-soluble polymer as a dispersant to disperse a pigment, 5 it is preferred from the viewpoint of physical properties that the pigment be a pigment adjusted so as to have an isoelectric point of at least 6, or such a pigment that the pH of a simple aqueous dispersion which characterizes the pigment is neutral or basic, 10 for example, from 7 to 10. It is understood that such a pigment is preferred from the viewpoint of dispersibility due to the fact that the ionic interaction between the pigment and the cationic water-soluble polymer becomes strong.

15 In order to obtain a fine particulate aqueous dispersion of a pigment using such a material as described above, for example, carbon black is premixed in a solution of the cationic dispersant and subsequently milled in a dispersing machine at a high 20 shear rate. After diluted, the mixture is centrifuged to remove coarse particles from the dilute mixture. Thereafter, materials necessary for achieving the desired ink formulation are added, and the resulting mixture is aged if circumstances require. Thereafter, 25 the thus-treated mixture is finally centrifuged to obtain a pigment dispersion having the desired average particle diameter, whereby an aqueous dispersion of

carbon black can be obtained. The pH of the ink thus prepared is preferably adjusted to a range of from 3 to 7.

(6) Aqueous medium, other additives, etc.:

As an aqueous medium for holding the resin having a cationic group and encapsulating the coloring material, as described in the requirement (4), and the cationic pigment or the pigment dispersion containing the pigment dispersant having a cationic group described in the requirement (5) in a dispersed state to constitute the ink, that described in the composing requirement (3) may be suitably used. It is preferred that a proportion of water accounted for in the ink be, for example, 20 to 95 % by weight, particularly 40 to 95 % by weight, more particularly 60 to 95 % by weight based on the total weight of the ink. As a water-soluble organic solvent, which may be added to the aqueous medium, that mentioned in the composing requirement (3) may also be used. A preferred water-soluble organic solvent is glycerol, and its amount added is preferably 2 to 30 % by weight, more preferably 5 to 15 % by weight based on the total weight of the ink. A more preferred water-soluble organic solvent is a mixed solvent comprising glycerol and another polyhydric alcohol such as diethylene glycol or ethylene glycol. The mixing ratio of glycerol to said another polyhydric alcohol is

preferably within a range of from 10:5 to 10:50.

Examples of the polyhydric alcohol another than glycerol include diethylene glycol, ethylene glycol, polyethylene glycol and propylene glycol. Further,

5 these glycerol and mixed solvent of glycerol and another polyhydric alcohol may be used in combination with other water-soluble organic solvents.

The inks according to this embodiment are suitably used in ink-jet recording method in which an 10 ink is ejected from a recording head by thermal energy or mechanical energy to apply it to a recording medium, thereby recording an image. When the inks according to this embodiment are made particularly suitable for use in ink-jet recording, the inks are controlled so as to 15 have, as their own physical properties as measured at 25°C, a surface tension of 15 to 60 dyn/cm, preferably 20 to 50 dyn/cm, a viscosity of 15 cP or lower, particularly 10 cP or lower, more particularly 5 cP or lower and a pH within a range of preferably from 3 to 20 11, more preferably from 3.5 to 8.

As specific ink compositions capable of achieving such properties, may be mentioned, for example, the compositions of various inks used in Examples which will be described subsequently.

25 To the inks according to this embodiment, may be further added various kinds of additives such as surfactants, pH adjusters and mildewproofing agents in

addition to the resin encapsulating the coloring material obtained in the above described manner and the pigment.

No particular limitation is imposed on recording 5 media used in a recording method using the inks according to this embodiment, and various kinds of plain paper such as paper for copying and bond paper, coated paper specially prepared for ink-jet recording, glossy paper, and OHP films are suitably used.

10 (7) Recording apparatus, recording process, etc.:

An image recording apparatus suitable for use in recording with the above-described inks according to the first or second embodiment on a recording medium, and an image recording process using it will 15 hereinafter be described. As an example of the image recording apparatus, may be mentioned an apparatus in which thermal energy corresponding to recording signals is applied to an ink within a recording head, and ink droplets are generated by the thermal energy. Such an 20 apparatus will hereinafter be described.

Figs. 1 and 2 are schematic sectional views illustrating an example of the construction of a head, which is a main component of such an image recording apparatus. Specifically, Fig. 1 is a schematic cross-sectional view of a head 13 taken along the flow path of ink, and Fig. 2 is a cross-sectional view taken 25 along line 2-2 in Fig. 1. The head 13 is formed by

bonding a glass, ceramic, silicon or plastic plate or
the like having a flow path (nozzle) 14 through which
an ink is passed, to a heating substrate 15. The
heating substrate 15 is composed of a protective film
5 16 made of silicon oxide, silicon nitride, silicon
carbide or the like, electrodes 17-1 and 17-2 formed of
aluminum, gold, aluminum-copper alloy or the like, a
heating resistor layer 18 formed of a high-melting
material such as, HfB_2 , TaN or TaAl , a heat accumulating
10 layer 19 formed of silicon oxide, aluminum oxide or the
like, and a substrate 20 made of silicon, aluminum,
aluminum nitride or the like having a good heat
radiating property.

Now, upon application of pulsed electric signals
15 to the electrodes 17-1 and 17-2 of the head 13, the
heating substrate 15 rapidly generates heat at the
region shown by "n" to form bubbles in an ink 21 which
is in contact with this region. A meniscus 23 of the
ink is projected by the pressure thus produced, and the
20 ink 21 is ejected from an ejection orifice 22 through
the nozzle 14 of the head 13 toward a recording medium
25. Fig. 3 illustrates an appearance of a multi-head
composed of an array of a number of heads as shown in
Fig. 1. The multi-head is formed by closely bonding a
25 glass plate 27 having a number of grooves 26 to a
heating head 28 similar to that described in Fig. 1.

Fig. 4 illustrates an example of an ink-jet

recording apparatus in which such a head as described above has been incorporated. In Fig. 4, reference numeral 61 designates a blade serving as a wiping member, one end of which is a stationary end held by a 5 blade-holding member to form a cantilever. The blade 61 is provided at a position adjacent to a region in which a recording head 65 operates, and in this embodiment, is held in such a form that it protrudes into the course through which the recording head 65 is 10 moved. Reference numeral 62 indicates a cap for the face of ejection openings of the recording head 65, which is provided at a home position adjacent to the blade 61, and is so constructed that it moves in a direction perpendicular to a direction in which the 15 recording head 65 is moved, and comes into contact with the face of the ejection openings to cap it. Reference numeral 63 denotes an ink absorbing member provided adjoining to the blade 61 and, similar to the blade 61, held in such a form that it protrudes into the 20 course through which the recording head 65 is moved. The above-described blade 61, cap 62 and ink absorbing member 63 constitute an ejection-recovery portion 64, where the blade 61 and ink absorbing member 63 remove water, dust and/or the like from the face of the ink- 25 ejecting openings. Reference numeral 65 designates the recording head having an ejection-energy-generating means and serving to eject the ink onto a recording

medium set in an opposing relation to the ejection opening face provided with the ejection openings to conduct recording. Reference numeral 66 indicates a carriage on which the recording head 65 is mounted so that the recording head 65 can be moved. The carriage 66 is slidably interlocked with a guide rod 67 and is connected (not illustrated) at its part to a belt 69 driven by a motor 68. Thus, the carriage 66 can be moved along the guide rod 67 and hence, the recording head 65 can be moved from a recording region to a region adjacent thereto. Reference numerals 51 and 52 denote a feeding part from which the recording medium is inserted, and feed rollers driven by a motor (not illustrated), respectively. With such a construction, the recording medium is fed to the position opposite to the ejection opening face of the recording head 65, and discharged from a discharge section provided with discharge rollers 53 with the progress of recording.

In the above construction, the cap 62 in the head recovery portion 64 is receded from the path of motion of the recording head 65 when the recording head 65 is returned to its home position, for example, after completion of recording, and the blade 61 remains protruded into the path of motion. As a result, the ejection opening face of the recording head 65 is wiped. When the cap 62 comes into contact with the ejection opening face of the recording head 65 to cap

it, the cap 62 is moved so as to protrude into the path of motion of the recording head 65.

When the recording head 65 is moved from its home position to the position at which recording is started, 5 the cap 62 and the blade 61 are at the same positions as the positions for the wiping as described above. As a result, the ejection opening face of the recording head 65 is also wiped at the time of this movement.

The above movement of the recording head 65 to its home position is made not only when the recording is completed or the recording head 65 is recovered for ejection, but also when the recording head 65 is moved between recording regions for the purpose of recording, during which it is moved to the home position adjacent to each recording region at given intervals, where the ejection opening face is wiped in accordance with this movement. 15

Fig. 5 illustrates an exemplary ink cartridge 45 in which an ink to be fed to a head through an ink-feeding member, for example, a tube is contained. 20 Here, reference numeral 40 designates an ink container portion containing the ink to be fed, as exemplified by a bag for the ink. One end thereof is provided with a stopper 42 made of rubber. A needle (not illustrated) 25 may be inserted into this stopper 42 so that the ink in the bag 40 for the ink can be fed to the head.

Reference numeral 44 indicates an absorbing member for

receiving a waste ink. It is preferred that the ink container portion 40 be formed of a polyolefin, in particular, polyethylene, at its surface with which the ink comes into contact.

5 [Recording unit]

The ink-jet recording apparatus used in the present invention are not limited to the apparatus as described above in which the head and the ink cartridge are separately provided. Therefore, a device in which 10 these members are integrally formed as shown in Fig. 6 can also be preferably used. In Fig. 6, reference numeral 70 designates a recording unit, in the interior of which an ink container portion containing an ink, for example, an ink absorbing member, is contained. 15 The recording unit 70 is so constructed that the ink in such an ink absorbing member is ejected in the form of ink droplets through a head 71 having a plurality of orifices. In the present invention, polyurethane is preferably used as a material for the ink absorbing 20 member. The ink container portion may be constructed without using the ink absorbing member by a bag for the ink in the interior of which a spring or the like is provided. Reference numeral 72 indicates an air passage for communicating the interior of the recording 25 unit 70 with the atmosphere.

This recording unit 70 is used in place of the recording head 65 shown in Fig. 4, and is detachably

installed on the carriage 66.

[Ink-jet recording apparatus and recording process
using piezoelectric element]

As a preferable example of an ink-jet recording
5 apparatus making good use of mechanical energy, may be
mentioned an On-Demand type ink-jet recording apparatus
comprising a nozzle-forming substrate having a
plurality of nozzles, pressure-generating devices
composed of a piezoelectric material and an electric
10 conductive material provided in an opposing relation to
the nozzles, and an ink filled around the pressure-
generating devices, wherein the pressure-generating
devices are changed by voltage applied to eject
droplets of the ink from the nozzles.

15 An example of the construction of a recording
head, which is a main component of such a recording
apparatus, is illustrated in Fig. 7.

The head is composed of an ink flow path 80
communicating with an ink chamber (not illustrated), an
20 orifice plate 81 through which ink droplets having a
desired volume are ejected, a vibration plate 82 for
directly applying a pressure to the ink, a
piezoelectric element 83 bonded to the vibration plate
82 undergoing a change according to an electric signal,
25 and a substrate 84 adapted to support and fix the
orifice plate 81, the vibration plate 82 and the like
thereon.

In Fig. 7, the ink flow path 80 is formed with a photosensitive resin or the like. The orifice plate 81 is made of a metal such as stainless steel or nickel, and an ejection opening 85 of which is formed by 5 electroforming, punching by press working, or the like. The vibration plate 82 is formed with a film of a metal such as stainless steel, nickel or titanium and a high-modulus resin film or the like. The piezoelectric element 83 is made of a dielectric material such as 10 barium titanate or PZT.

The recording head with the above construction is operated in such a manner that pulsed voltage is applied to the piezoelectric element 83 to generate a stress to cause strain, the vibration plate 82 bonded 15 to the piezoelectric element 83 is deformed by the energy of the stress, and the ink in the ink flow path 80 is thus perpendicularly pressurized to eject ink droplets (not illustrated) from the ejection opening 85 of the orifice plate 81, thereby conducting recording.

20 Such a recording head is used by incorporating it into an ink-jet recording apparatus similar to that illustrated in Fig. 4. Operation of details of the ink-jet recording apparatus may be conducted in the same manner as described above.

25 [Ink set]

The above-described inks according to the various embodiments of the present invention constitute black

inks and can each be provided as an ink set suitable for use in the formation of color images by combining it with at least one color ink selected from the group consisting of color inks comprising coloring materials 5 for yellow, magenta, cyan, red, blue and green, respectively. In particular, the black inks according to the second embodiment can extremely effectively reduce the occurrence of bleeding when used together with an ink comprising at least one of a water-soluble 10 dye having an anionic group and a compound containing at least an anionic group, since an ionic reaction takes place in a boundary region between both inks on a recording medium. Examples of the water-soluble dye having an anionic group include the conventionally 15 known direct dyes and acid dyes. Examples of the compound containing at least an anionic group include the conventionally known anionic surfactants and anionic group-containing high-molecular compounds. In these, pigment dispersants and the like are also 20 included.

(Color ink)

As coloring materials for the color inks usable for the above ink set, may be used publicly known dyes and pigments. As the dyes, for example, acid dyes and 25 direct dyes may be used. As, for example, anionic dyes, most of both dyes already known and newly synthesized may be used so far as they have proper

color tone and density. Some of them may also be used in combination. As Specific examples of the anionic dyes, may be mentioned the following dyes:

(Coloring material for yellow)

5 C.I. Direct Yellow 8, 11, 12, 27, 28, 33, 39, 44, 50,
58, 85, 86, 87, 88, 89, 98, 100 and 110;
C.I. Acid Yellow 1, 3, 7, 11, 17, 23, 25, 29, 36, 38,
40, 42, 44, 76, 98 and 99;
C.I. Reactive Yellow 2, 3, 17, 25, 37 and 42; and
10 C.I. Food Yellow 3.

(Coloring material for red)

C.I. Direct Red 2, 4, 9, 11, 20, 23, 24, 31, 39, 46,
62, 75, 79, 80, 83, 89, 95, 197, 201, 218, 220, 224,
225, 226, 227, 228 and 229;
15 C.I. Acid Red 6, 8, 9, 13, 14, 18, 26, 27, 32, 35, 42,
51, 52, 80, 83, 87, 89, 92, 106, 114, 115, 133, 134,
145, 158, 198, 249, 265 and 289;
C.I. Reactive Red 7, 12, 13, 15, 17, 20, 23, 24, 31,
42, 45, 46 and 59; and
20 C.I. Food Red 87, 92 and 94.

(Coloring material for blue)

C.I. Direct Blue 1, 15, 22, 25, 41, 76, 77, 80, 86, 90,
98, 106, 108, 120, 158, 163, 168, 199 and 226;
C.I. Acid Blue 1, 7, 9, 15, 22, 23, 25, 29, 40, 43, 59,
25 62, 74, 78, 80, 90, 100, 102, 104, 117, 127, 138, 158
and 161; and
C.I. Reactive Blue 4, 5, 7, 13, 14, 15, 18, 19, 21, 26,

27, 29, 32, 38, 40, 44 and 100.

(Coloring material for black)

C.I. Acid Black 2, 4, 8, 51, 52, 110, 115, 156; and

C.I. Food Black 1 and 2.

5 (Solvent)

Examples of solvents or dispersion media for inks respectively comprising such coloring materials for color inks as described above include water and mixed solvents of water and a water-soluble organic solvent.

10 Examples of the water-soluble organic solvent include the same solvents as those described in the first embodiment. When such color inks are applied to a recording medium by an ink-jet system (for example, bubble-jet system), it is preferred that the inks be
15 controlled so as to have the desired viscosity and surface tension in order for the inks to exhibit excellent ink-jet ejection properties as described above.

(Content of coloring material)

20 The content of the coloring material in each of the color inks may be suitably selected in such a manner that such an ink has excellent ink-jet ejection properties and the desired color tone and density when it is used in, for example, ink-jet recording. For
25 example, as a standard, it is preferably within a range of from 3 to 50 % by weight based on the total weight of the ink. The amount of water contained in the ink

is preferably within a range of from 50 to 95 % by weight based on the total weight of the ink.

[Recording apparatus and recording process using ink sets]

5 When each of the above-described ink sets is used to record color images, for example, a recording apparatus in which 4 recording heads, each of which has been illustrated in Fig. 3, are arranged on a carriage, may be used. An embodiment thereof is illustrated in
10 Fig. 9. Reference numerals 91, 92, 93 and 94 indicate recording units for ejecting yellow, magenta, cyan and black inks, respectively. The recording units are arranged on a carriage of the above-described recording apparatus and serve to eject the respective inks in
15 response to recording signals. Fig. 9 shows the case where the four recording heads have been used. However, the present invention is not limited thereto. For example, an embodiment, wherein ink cartridges 86 to 89 respectively containing the above four colors ink
20 are set in a recording head 90 in which ink flow paths are separately formed in such a manner that the color inks fed from the ink cartridges 86 to 89 can be separately ejected by one recording head as shown in Fig. 8, thereby conducting recording, is also included.
25 The present invention will hereinafter be described more specifically by the following Examples and Comparative Examples. However, the present

invention is not limited to the following examples so far as it does not exceed the subject matter thereof. Incidentally, all designations of "part" or "parts" and "%" as will be used in the following examples mean part 5 or parts by weight and % by weight unless expressly noted. In the following examples, the average particle diameter is a value measured by means of a dynamic light scattering particle diameter measurement equipment (ELS-800, trade name, manufactured by 10 Otsuka Denshi K.K.).

Examples 1 to 6:

Dispersions C-1 and C-2 were provided as carbon black dispersions.

(Preparation of Dispersion C-1)

15 Dispersion C-1 was prepared in the following manner.

A styrene-methacrylic acid-ethyl acrylate copolymer (acid value: 350; weight average molecular weight: 3,000; as a 20 % aqueous solution; neutralizing 20 agent: potassium hydroxide) was used as a dispersant. The following materials were charged in a batch-wise sand mill (manufactured by Aimex Company), and glass beads having a diameter of 1 mm were charged as a grinding medium to conduct a dispersion treatment for 3 25 hours while cooling with water.

Aqueous solution of dispersant	30 parts
(20 % aqueous solution)	

Carbon black (Mogul, trade name; 20 parts
product of Cabblack Co.)

Glycerol 10 parts

Water 30 parts.

5 The carbon black dispersion thus obtained had an
average particle diameter of 0.1 μm and a pH of 10.0.

(Preparation of Dispersion C-2)

Dispersion C-2 was obtained in the same manner as
the preparation of Dispersion C-1 except that self-
10 dispersing carbon black CAB-O-JET 200 (trade name,
product of CABOT Co.; solid content: 20 %; having a
sulfonic group as a functional group on its surface)
was used. The carbon black dispersion thus obtained
had an average particle diameter of 0.13 μm and a pH of
15 7.0. Preparation of Dispersions MC-1 and MC-2 of
resins encapsulating a coloring material:

Dispersions MC-1 and MC-2 were also provided as
dispersions of resins encapsulating a coloring
material.

20 (Preparation of Dispersion MC-1)

The following materials were mixed into a
solution.

C.I. Solvent Black 3 10 parts

25 Styrene-acrylic acid copolymer (acid
value: 200; molecular weight: 30,000)

40 parts

Methyl ethyl ketone 50 parts.

The resultant solution was phase inversion-emulsified in water using sodium hydroxide as a neutralizing agent, and methyl ethyl ketone was removed 5 to finally obtain an aqueous dispersion of microcapsules having an average particle diameter of 0.08 μm containing solids at a concentration of 20 %.

(Preparation of Dispersion MC-2)

An aqueous dispersion of microcapsules having an 10 average particle diameter of 0.13 μm containing solids at a concentration of 20 % was finally obtained in the same manner as the preparation of Dispersion MC-1 except that the resin used in Dispersion MC-1 was changed to a styrene-acrylic acid-methyl methacrylate 15 terpolymer (acid value: 250; molecular weight: 25,000).

After the respective dispersions provided in the above-described manner were mixed so as to give solid 20 contents in their corresponding proportions shown in Table 1, glycerol and isopropyl alcohol were mixed with each of the mixtures in such a manner that the concentrations of glycerol and isopropyl alcohol amount to 16 % and 4.0 %, respectively, thereby preparing respective inks finally containing carbon black and the resin encapsulating the coloring material at a 25 concentration of 8 % in terms of total solid content in each ink.

"C.B./MC" shown in Table 1 indicates final

concentrations of the respective solids (i.e. carbon black and the resin) in each ink prepared. More specifically, it indicates that, for example, Ink A according to Example 1 was prepared in such a manner 5 that the solid contents of carbon black and the resin encapsulating the coloring material amount to 1.5 % and 6.5 %, respectively. Incidentally, the amount of carbon black in Examples 1 to 3 in Table 1 means the total solid content of carbon black and the dispersant. 10 On the other hand, the amount of carbon black in Examples 4 to 6 means an amount of carbon black alone because no dispersant was used for the carbon black.

The six inks A, B, C, D, E and F thus prepared were separately charged into an ink tank for black of a 15 BJ Cartridge BC-21 installed in a color BJ printer BJC-420J (trade name; manufactured by Canon Inc.), and the cartridge was set in BJC-420 to conduct printing on recording paper Canon PB Paper (trade name, product of Canon Inc.; paper for common use in BJ- 20 electrophotography) in accordance with the 360 × 360 DPI, HQ mode for plain paper of BJC-420J.

Comparative Examples 1 to 3:

Inks G and H containing only their corresponding carbon black shown in Table 1, and Ink I containing 25 only its corresponding resin encapsulating a coloring material shown in Table 1 were used to conduct printing in exactly the same manner as in Examples 1 to 6.

Table 1

	Ink	C.B. dispersion	Resin encapsulating coloring material	C.B./MC
Ex. 1	A	C-1	MC-1	1.5/6.5
Ex. 2	B	C-1	MC-1	3.0/5.0
Ex. 3	C	C-1	MC-1	4.0/4.0
Ex. 4	D	C-2	MC-2	1.5/6.5
Ex. 5	E	C-2	MC-2	3.0/5.0
Ex. 6	F	C-2	MC-2	4.0/4.0
Comp. Ex. 1	G	C-1	Not used	8.0/0
Comp. Ex. 2	H	C-2	Not used	8.0/0
Comp. Ex. 3	I	Not used	MC-1	0/8.0

The thus-obtained prints were evaluated in the following manner:

Optical density of image:

After a solid printed sample was left to stand for 12 hours after its printing, its optical density was measured by means of a reflection densitometer, Macbeth RD-918 (trade name, manufactured by Macbeth Company). The evaluation result was ranked in accordance with the following standard:

A: Optical density was not lower than 1.35;

B: Optical density was from 1.2 to 1.34; and

C: Optical density was lower than 1.2.

Water fastness:

The same solid printed sample as that used in the evaluation of the optical density of image was used and left to stand for 12 hours after the printing. The 5 image sample was then dipped in tap water for 3 seconds and dried to measure its optical density by means of the reflection densitometer described above, whereby the percent retention of the optical density was found from the optical densities before and after the water 10 fastness test to use it as a measure of the water fastness. The evaluation result was ranked in accordance with the following standard:

A: Percent retention of optical density was not lower than 90 %;

15 B: Percent retention of optical density was not lower than 70 % but lower than 90 %;

C: Percent retention of optical density was lower than 70%.

Resistance to line marker:

20 Upon elapsed time of 1 hour after the printing of characters, the character portion of the resulting print sample was marked once under ordinary writing pressure with a yellow fluorescent pen, Spot Lighter Yellow, (trade name; product of Pilot Pen Co., Ltd.), 25 whereby the resistance to line marker was ranked in accordance with the following evaluation standard:

A: Neither bleeding nor stain on white portions

was observed in the print sample, and a pen point was also not stained;

B: No stain on white portions was observed in the print sample, but a pen point was somewhat 5 stained; and

C: Stain on white portion was observed in the print sample.

Rub-off resistance:

Upon elapsed time of 4 hours after the printing 10 of an image, silbon paper was placed on the paper printed, and an 1-kg weight having a bottom area of 5 cm square was then placed on the silbon paper. The silbon paper was then pull out to visually observe whether the unprinted portions (white portions) of the 15 printed paper and the silbon paper were stained by the rubbing between the printed portions of the printed paper and the silbon paper. The rub-off resistance was ranked in accordance with the following evaluation standard:

20 A: No stain was observed in both white portions and silbon paper;

B: Stain was observed in the silbon paper alone; and

C: Stain was observed in both white portions and 25 silbon paper.

Ejection stability:

An 1-dot vertical line was printed on recording

paper at the beginning of use of Cartridge BC-21. Text printing was conducted until the Cartridge BC-21 was consumed. The cartridge right before it was consumed was used to print an 1-dot vertical line on another recording paper. These recording paper samples were visually observed from a position 25 cm distant, thereby comparing the result of the printing by the cartridge at the beginning of use with the result of the printing by the cartridge right before it was consumed to rank the ejection stability in accordance with the following evaluation standard:

- A: No difference was observed between both samples;
- B: Deviation of dot impact was observed in a part of the vertical line printed by the cartridge right before it was consumed, but the line could be recognized as a straight line; and
- C: Deviation of dot impact was clearly observed in the vertical line printed by the cartridge right before it was consumed, and the vertical line could be recognized to deviate.

The evaluation results are shown in Table 2.

Table 2

	Optical density	Water fastness	Resistance to line marker	Rub-off resistance	Ejection stability
Ex. 1	B	A	A	A	B
Ex. 2	B	A	A	A	B
Ex. 3	A	A	B	A	B
Ex. 4	A	A	A	A	A
Ex. 5	A	A	A	A	A
Ex. 6	A	A	A	A	A
Comp.	A	A	C	C	B
Ex. 1					
Comp.	A	A	C	C	A
Ex. 2					
Comp.	C	A	A	A	A
Ex. 3					

It is understood from Table 2 that the inks according to the present invention are inks for ink-jet, which can provide an image sufficiently high in optical density on plain paper and excellent in water fastness, resistance to line marker and rub-off resistance and are sufficiently good in ejection stability. The inks of the sole system of carbon black and the ink of the sole system of the resin encapsulating the coloring material could not obtain

results satisfying all the optical density of image, water fastness, resistance to line marker, rub-off resistance and ejection stability at the same time.

Examples 7 to 12:

5 Dispersions C-3 and C-4 were provided as carbon black dispersions.

(Preparation of Dispersion C-3)

Dispersion C-3 was prepared in the following manner.

10 Cationic Polymer P-1 (weight average molecular weight: 11,000, pH of aqueous solution: 3.26) containing acrylamide and trimethylaminopropylacrylamide sulfate as monomers in a weight ratio of 70:30 was used as a dispersant to 15 prepare the following Carbon Black Dispersion C-3.

	Aqueous solution of Cationic Polymer	20 parts
	P-1 (solid content: 20 %)	
	Carbon black #2600 (product of	10 parts
	Mitsubishi Kagaku Co., Ltd.)	
20	Diethylene glycol	5 parts
	Isopropyl alcohol	5 parts
	Water	60 parts.


The above materials were charged in a batch-wise vertical sand mill (manufactured by Aimex Company), and 25 glass beads having a diameter of 1 mm were charged as a grinding medium to conduct a dispersion treatment for 3 hours while cooling with water. After the dispersion

treatment, the dispersion had a viscosity of 28 cP and a pH of 4.05. This dispersion was centrifuged to remove coarse particles, thereby obtaining Dispersion C-3 having an average particle diameter of 0.12 μm .

5 The dispersion had a solid content of 10 % in total.
(Preparation of Dispersion C-4)

Dispersion C-4 was prepared in the following manner.

After 10 g of carbon black having a surface area of 230 m^2/g and a DBP oil absorption of 70 ml/100 g, and 10 3.06 g of 3-amino-N-ethylpyridinium bromide were thoroughly mixed with 72 g of water, 1.62 g of nitric acid were added dropwise to the mixture, followed by stirring at 70°C. After several minutes, a solution 15 with 1.07 g of sodium nitrite dissolved in 5 g of water was further added to the mixture, and the resultant mixture was stirred for an additional 1 hour. The resultant slurry was filtered through filter paper (Toyo Filter Paper No. 2, trade name; product of 20 Advantes Co.), and the resultant pigment particles were fully washed with water and dried in an oven controlled to 110°C. Water was added to the dry pigment to prepare an aqueous dispersion of the pigment having a pigment concentration of 10 %. The above-described process was 25 followed to introduce a group of the chemical formula



in the surface of the carbon black.

Preparation of Dispersions MC-3 and MC-4 of resins encapsulating a coloring material:

Dispersions MC-3 and MC-4 were also provided as
5 dispersions of resins encapsulating a coloring
material.

(Preparation of Dispersion MC-3)

The following materials were mixed into a
solution.

10	C.I. Solvent Black 3	10 parts
	Styrene-N,N-dimethylaminoethyl	
	methacrylate copolymer (molecular	
	weight: 40,000)	40 parts
	Methyl ethyl ketone	50 parts.
15	The resultant solution was phase inversion-	
	emulsified using acetic acid as a neutralizing agent,	
	and methyl ethyl ketone was removed to finally obtain	
	an aqueous dispersion of microcapsules having an	
	average particle diameter of 0.08 μm containing solids	
20	at a concentration of 20 %.	

(Preparation of Dispersion MC-4)

An aqueous dispersion of microcapsules having an
average particle diameter of 0.13 μm containing solids
at a concentration of 20 % was finally obtained in the
25 same manner as the preparation of Dispersion MC-3
except that the resin used in Dispersion MC-3 was
changed to a styrene-N,N-dimethylaminopropyl

methacrylate copolymer (molecular weight: 35,000).

After the respective dispersions provided in the above-described manner were mixed so as to give solid contents in their corresponding proportions shown in Table 3, glycerol and isopropyl alcohol were mixed with each of the mixtures in such a manner that the concentrations of glycerol and isopropyl alcohol amount to 16 % and 4.0 %, respectively, thereby preparing respective inks finally containing carbon black and the resin encapsulating the coloring material at a concentration of 8 % in terms of total solid content in each ink. C.B./MC shown in Table 3 indicates final concentrations of the respective solids in each ink prepared. More specifically, it indicates that Ink A according to Example 7 was prepared in such a manner that the solid contents of carbon black and the resin encapsulating the coloring material amount to 1.5 % and 6.5 %, respectively. The same shall apply hereinafter. Incidentally, the amount of carbon black in Examples 7 to 9 in Table 3 means the total solid content of carbon black and the dispersant. On the other hand, the amount of carbon black in Examples 10 to 12 means an amount of carbon black alone because no dispersant was used for the carbon black.

The six Inks J, K, K, M, N and O thus prepared were separately charged into an ink tank for black of a BJ Cartridge BC-21 installed in a color BJ printer.

(BJC-420J, trade name; manufactured by Canon Inc.), and the cartridge was set in BJC-420 to conduct printing on recording paper, Canon PB Paper, (trade name, product of Canon Inc.; paper for common use in BJ-
5 electrophotography) in accordance with the 360 × 360 DPI, HQ mode for plain paper of BJC-420J. The thus-obtained prints were evaluated as to optical density of image, water fastness, resistance to line marker, rub-off resistance and ejection stability in exactly the
10 same manner as in Examples 1 to 6. The evaluation results are shown in Table 4.

Comparative Examples 4 to 6:

Inks P and Q containing only their corresponding carbon black shown in Table 3, and Ink R containing
15 only its corresponding resin encapsulating a coloring material shown in Table 3 were prepared in the same manner as in the inks according to Examples 7 to 12 and evaluated as to optical density of image, water fastness, resistance to line marker, rub-off resistance
20 and ejection stability in exactly the same manner as in Examples 7 to 12. The evaluation results are shown in Table 4.

Table 3

	Ink	C.B. dispersion	Resin encapsulating coloring material	C.B./MC
Ex. 7	J	C-3	MC-3	1.5/6.5
Ex. 8	K	C-3	MC-3	3.0/5.0
Ex. 9	L	C-3	MC-3	4.0/4.0
Ex. 10	M	C-4	MC-4	1.5/6.5
Ex. 11	N	C-4	MC-4	3.0/5.0
Ex. 12	O	C-4	MC-4	4.0/4.0
Comp. Ex. 4	P	C-3	Not used	8.0/0
Comp. Ex. 5	Q	C-4	Not used	8.0/0
Comp. Ex. 6	R	Not used	MC-3	0/8.0

Optical density, water-fastness, resistance to line marker, rub-off resistance and effection stability were evaluated in the same manner as in Examples 1 to 6. The results are shown in Table 4.

Table 4

	Optical density	Water fastness	Resistance to line marker	Rub-off resistance	Ejection stability
Ex. 7	B	A	A	A	B
Ex. 8	B	A	A	A	B
Ex. 9	A	A	B	A	B
Ex. 10	A	A	A	A	A
Ex. 11	A	A	A	A	A
Ex. 12	A	A	A	A	A
Comp.	A	A	C	C	B
Ex. 4					
Comp.	A	A	C	C	A
Ex. 5					
Comp.	C	A	A	A	A
Ex. 6					

It is understood from Table 4 that the use of the inks according to the above examples can provide images sufficiently high in optical density on plain paper and excellent in water fastness, resistance to line marker and rub-off resistance. As shown in Table 4, the inks of the sole system of carbon black and the ink of the sole system of the resin encapsulating the coloring material could not obtain results satisfying all the optical density of image, water fastness, resistance to

line marker, rub-off resistance and ejection stability at the same time.

Examples 13 to 18:

Inks J to O prepared in Examples 7 to 12, 5 respectively, were separately charged into an ink tank for black of a color BJ printer, BJC-610JW, (trade name; manufactured by Canon Inc.) to use them for evaluation in Examples 13 to 18. Color inks exclusively prepared for BJC-610JW were used as color 10 inks. Black characters were printed in a color solid-printed background on PB paper (product of Canon Inc.), thereby evaluating Inks J to O as to resistance to color bleed between a black image formed with each of such inks and a color image. More specifically, 15 resistance to color bleed between black and yellow, resistance to color bleed between black and cyan, and resistance to color bleed between black and magenta were separately evaluated.

As a control example, a black ink and color inks 20 exclusively prepared for BJC-610JW were used to evaluate them as to resistance to color bleed in the same manner as described above. As a result, in each of Examples 13 to 18, color bleeds were reduced compared with the control example, no exudation of the 25 black characters into the color background occurred, and the sharpness of the black characters was also recognized to be improved compared with the control

example.

At this time, the optical density, water fastness, resistance to line marker and rub-off resistance of the images formed with the black inks according to Examples 13 to 18 were evaluated (printing was conducted in accordance with Bk accent mode). As a result, the same results as in Examples 7 to 12 were obtained.

Examples 19 to 24:

10 Dispersions MC-5 was provided as a dispersion of
a resin encapsulating carbon black as a coloring
material.

(Preparation of Dispersion MC-5)

The following materials were mixed and dispersed.

15 Carbon black MCF-88 (trade name; 20 parts

product of Mitsubishi Kagaku Co., Ltd.)

Styrene-N,N-dimethylaminoethyl methacrylate copolymer (molecular weight: 45,000) 40 parts

20 Methyl ethyl ketone 40 parts.

The resultant mixture was phase inversion-emulsified using acetic acid as a neutralizing agent, and methyl ethyl ketone was removed to finally obtain an aqueous dispersion of a cationic resin encapsulating carbon black having an average particle diameter of 0.10 μm containing solids at a concentration of 20 %.

After the aqueous dispersion MC-5 of the carbon

black-containing resin provided in the above-described manner and the carbon black dispersion C-3 and C-4 prepared in Examples 7 to 12 were mixed so as to give solid contents in their corresponding proportions shown 5 in Table 5, glycerol, propylene glycol and isopropyl alcohol were mixed with each of the mixtures in such a manner that the concentrations of glycerol, propylene glycol and isopropyl alcohol amount to 7.0 %, 8.0 % and 4.0 %, respectively, thereby preparing respective inks 10 finally containing carbon black and the resin encapsulating the carbon black at a concentration of 8 % in terms of total solid content in each ink.

Table 5

	Ink	C.B. dispersion	Resin encapsulating coloring material	C.B./MC
	Ex. 19	S	C-3	MC-5
	Ex. 20	T	C-3	MC-5
	Ex. 21	U	C-3	MC-5
20	Ex. 22	V	C-4	MC-5
	Ex. 23	W	C-4	MC-5
	Ex. 24	X	C-4	MC-5

25 The inks thus obtained were evaluated as to optical density of image, water fastness, resistance to line marker, rub-off resistance and ejection stability

in the same manner as in Examples 7 to 12. However, the ranking of the optical density of image was conducted in accordance with the following standard:

AA: Optical density was not lower than 1.4;

5 A: Optical density was from 1.35 to 1.39;

B: Optical density was from 1.2 to 1.34; and

C: Optical density was lower than 1.2.

The evaluation results are shown in Table 6.

10

Table 6

	Optical density	Water fastness	Resistance to line marker	Rub-off resistance	Ejection stability
Ex. 19	B	A	A	A	B
Ex. 20	A	A	A	A	A
Ex. 21	A	A	A	A	A
Ex. 22	AA	A	A	A	A
Ex. 23	AA	A	A	A	A
Ex. 24	AA	A	A	A	A

Examples 25 to 30:

Color inks having their corresponding compositions shown below were prepared.

Yellow ink:

25 C.I. Direct Yellow 86 3.5 parts
Glycerol 10.0 parts

Acetylenol EH (trade name, product of
Kawaken Fine Chemicals Co., Ltd.;
acetylene glycol type surfactant) 1.0 parts
Water 85.5 parts.

5 Magenta ink:

C.I. Acid Red 285 3.5 parts
Glycerol 10.0 parts
Acetylenol EH (ditto) 1.0 part
Water 85.5 parts.

10 Cyan ink:

C.I. Acid Blue 199 3.5 parts
Glycerol 10.0 parts
Acetylenol EH (ditto) 1.0 part
Water 85.5 parts.

15 These inks were respectively charged into ink tanks for color ink of a color BJ printer BJC-610JW (trade name; manufactured by Canon Inc.). The black inks S to X prepared in Examples 19 to 24, respectively, were separately charged into an ink tank
20 for black ink of the color BJ printer, BJC-610JW, to use them for evaluation in Examples 25 to 30. Resistance to color bleed between each of the black inks S to X and the above-described color inks of yellow, magenta and cyan was evaluated in exactly the
25 same manner as in Example 13 to 18. The results thereof were the same as in Examples 13 to 18. No exudation into the color background occurred in the

black images formed with the black inks S to X, and the sharpness of the black characters was also improved compared with the control example. At this time, the optical density, water fastness, resistance to line 5 marker and rub-off resistance of the images formed with the black inks alone were evaluated (printing was conducted in accordance with Bk accent mode). As a result, exactly the same results as in Examples 19 to 24 were obtained.

10 According to the present invention, as described above, there can be provided inks which can provide images improved in resistance to line marker and rub-off resistance without impairing the merits of a pigment ink that it can provide images excellent in 15 optical density and water fastness, and moreover are also excellent in reliability (ejection durability, ejection stability, anti-clogging property, etc.) upon ink-jet recording.

20 It is also possible to form images having excellent resistance to line marker and rub-off resistance in addition to high optical density of image and excellent water fastness.

25 By the encapsulation in a resin, the hydrophobic group of the resin is basically arranged inside a capsule, while the hydrophilic group of the resin is arranged outside the capsule. Therefore, the resin is hard to adhere to the ejection opening face of a

recording head when the ejection opening face is subjected to a water-repellent treatment, and so the resin can be effectively prevented from depositing on the ejection opening face of the ink-jet head.

5 Therefore, the ejection stability of the ink can be still more improved.

According to the present invention, the problems of a pigment ink can also be offset without impairing the merits of the pigment ink. More specifically, 10 there can be stably provided images high in optical density and excellent in water fastness, resistance to line marker and rub-off resistance. When a resin capsule is used as the resin encapsulating a coloring material, the hydrophobic group of the resin is 15 basically arranged inside a capsule, while the hydrophilic group of the resin is arranged outside the capsule. Therefore, the resin is hard to adhere to the ejection opening face of a recording head when the ejection opening face is subjected to a water-repellent 20 treatment, and so the resin can be prevented from depositing on the ejection opening face of the ink-jet head. Therefore, the ejection stability of the ink can be still more improved.

When a multi-color image is formed with at least 25 two inks according to the present invention by ink-jet recording, bleeding on a recording medium can be

effectively lessened in addition to the above-described effects.

12
13
14
15
16
17
18
19
20
21
22
23
24
25
26

The claims defining the invention are as follows:

1. An aqueous ink for ink-jet recording, comprising a self-dispersing pigment in which at least one hydrophilic group is bonded directly or through another atomic group to the surface of the pigment, and a resin encapsulating a coloring material, the self-dispersing pigment and the resin encapsulating a coloring material being dispersed in an aqueous medium.
2. The ink according to claim 1, wherein the pigment is a carbon black.
3. The ink according to claim 2, wherein the carbon black is a self-dispersing carbon black to the surface of which at least one hydrophilic group is bonded directly or through another atomic group.
4. The ink according to claim 3, wherein the hydrophilic group is anionic.
5. The ink according to claim 4, wherein the resin encapsulating a coloring material has an anionic hydrophilic group at the surface thereof.
6. The ink according to claim 3, wherein the hydrophilic group is cationic.
7. The ink according to claim 6, wherein the resin encapsulating a coloring material has a cationic hydrophilic group at the surface thereof.
8. The ink according to claim 1, further comprising a pigment dispersant.
9. The ink according to claim 8, wherein the dispersant has an anionic hydrophilic group when the hydrophilic group bonded to the surface of the self-dispersing carbon black is anionic.
10. The ink according to claim 8, wherein the dispersant has a cationic hydrophilic group when the hydrophilic group bonded to the surface of the self-dispersing carbon black is cationic.



11. The ink according to claim 1, wherein the coloring material is a water-insoluble dye.

12. The ink according to claim 1, wherein the coloring material is a
5 pigment.

13. The ink according to claim 1, wherein the pigment and the coloring material have the same color.

10 14. The ink according to claim 1, wherein the coloring material is encapsulated in a microcapsule made of the resin.

15 15. An ink cartridge, comprising an ink container containing an ink according to any one of claims 1 to 14.

16. A recording unit, comprising:
an ink container containing an ink according to any one of claims 1 to 14,
a recording head, and
means for feeding the ink from the ink container to the recording head.

20 17. An ink set comprising a first ink and a second ink in combination, wherein the first ink is an ink according to any one of claims 1 to 14, and each of the first and second inks has a color selected from the group consisting of yellow, magenta cyan, black, red, green and blue.

25 18. An image recording process, comprising the step of applying an ink according to any one of claims 1 to 14 to a recording medium by an ink-jet process.

19. An image recording process, comprising the step of applying at least
30 two color inks to a recording medium using an ink-jet method to form a multi-color image, wherein one ink is an ink according to claim 6, 7 or 10, and the other ink comprises a compound having an anionic group.

20. An image recording apparatus, comprising:
an ink container containing an ink according to any one of claims 1 to 14; and



an ink jet head for ejecting the ink.

21. An image recording apparatus, comprising:
ink containers containing first and second inks respectively, and a recording head
5 for ejecting the respective inks, wherein the first ink is an ink according to claim 6, 7 or
10, and the second ink is an anionic ink.

22. An aqueous ink for an ink-jet printing process comprising:
a colorant comprised of a self-dispersing pigment in which at least one
10 hydrophilic group is bonded directly or through another atomic group, and a resin
encapsulating coloring material in a certain amount, the self-dispersing pigment and the
resin encapsulating coloring material being dispersed in an aqueous medium,
wherein the ink provides an image whose optical density is substantially
equivalent to that formed by an ink comprising the self-dispersing pigment as a sole
15 colorant in the certain amount.

23. An ink substantially as described herein with reference to any one of the
embodiments, as that embodiment is illustrated in the accompanying drawings.

20 DATED this third Day of July, 2002
Canon Kabushiki Kaisha
Patent Attorneys for the Applicant
SPRUSON & FERGUSON






FIG. 1**FIG. 2****FIG. 3**

FIG. 4




FIG. 5




FIG. 6




FIG. 7





FIG. 8**FIG. 9**