



(51) International Patent Classification:

C08F 4/6592 (2006.01) C08F 210/02 (2006.01)

C08F 4/642 (2006.01) C08F 10/06 (2006.01)

C08F 10/02 (2006.01) C08F 2/38 (2006.01)

C08F 10/04 (2006.01)

(21) International Application Number:

PCT/US2017/025400

(22) International Filing Date:

31 March 2017 (31.03.2017)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

15/145,320 03 May 2016 (03.05.2016) US

(71) Applicant: EXXONMOBIL CHEMICAL PATENTS, INC. [US/US]; 52 Bayway Drive, Bayway, TX 77520 (US).

(72) Inventors: CANICH, Jo Ann, M.; 15710 Mesa Verde Drive, Houston, TX 77059 (US). IZMER, Vyatcheslav, V.; Remezova Street 2, Apt. 248, Moscow, 117186 (RU). KONONOVICH, Dmitry, S.; Vorobyovy Gory 1 (MSU). Apt. V-1016, Moscow, 119234 (RU). VOSKOBOYNIKOV, Alexander, Z.; Akademika Korol'eva Street 5, Apt. 93, Moscow, 129515 (RU).

(74) Agent: BELL, Catherine L. et al.; ExxonMobil Chemical Company, Law Department, P.O. Box 2149, Baytown, TX 77522-2149 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

(54) Title: TETRAHYDRO-AS-INDACENYL CATALYST COMPOSITION, CATALYST SYSTEM, AND PROCESSES FOR USE THEREOF




FIG. 1

(57) Abstract: This invention relates to a compound represented by the formula: $T_y\text{LAMX}_{n-2}$ wherein: A is a substituted or unsubstituted tetrahydro-as-indacenyl group bonded to M; L is substituted or unsubstituted monocyclic or polycyclic arenyl ligand or monocyclic or polycyclic heteroarenyl ligand bonded to M; M is a group 3, 4, 5, or 6 transition metal (preferably group 4); T is a bridging group bonded to L and A; y is 0 or 1, indicating the absence or presence of T; X is a leaving group, typically a univalent anionic ligand, or two Xs are joined and bound to the metal atom to form a metallocycle ring, or two Xs are joined to form a chelating ligand, a diene ligand, or an alkylidene; n is the oxidation state of M and is 3, 4, 5, or 6.

Declarations under Rule 4.17:

- *as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))*
- *as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))*

Published:

- *with international search report (Art. 21(3))*

TITLE: Tetrahydro-*as*-indacenyl Catalyst Composition, Catalyst System, and Processes for Use Thereof

5

PRIORITY CLAIM

This application claims priority to and the benefit of USSN 15/145,320, filed May 3, 2016 and is incorporated by reference in its entirety.

10

FIELD OF THE INVENTION

This invention relates to novel transition metal compounds, catalyst systems comprising such and polymerization process using such. This invention also relates to novel substituted tetrahydro-*as*-indacene and a method to produce substituted or unsubstituted tetrahydro-*as*-indacene.

15

BACKGROUND OF THE INVENTION

Olefin polymerization catalysts are of great use in industry. Hence, there is interest in finding new catalyst systems that increase the commercial usefulness of the catalyst and allow the production of polymers having improved properties.

Catalysts for olefin polymerization are often based on transition metal compounds as
20 catalyst precursors, which are activated either with an alumoxane or with an activator containing a non-coordinating anion. A typical catalyst system includes a metallocene catalyst and an activator, and an optional support. Many metallocene catalyst systems can be used in homogeneous polymerizations (such as solution or supercritical) and supported catalyst systems are used in many polymerization processes, often in slurry or gas phase
25 polymerization processes.

WO 2004/013149 A1 discloses group 4 metal constrained geometry complexes of tricyclic 4-aryl substituted indenyl ligands, esp. 1,5,6,7-tetrahydro-4-aryl-*s*-indacen-1-yl ligands, where the tetrahydro-*s*-indacene is substituted in the 4 position with a C₆₋₁₂ aryl group, and is preferably not substituted in the 5, 6, or 7 position, and if substituted in the 5, 6,
30 or 7 position, is substituted by at most only one substituent at each position.

US 6,420,507 discloses substituted tetrahydro-*s*-indacenyl transition metal complexes (such as Examples H to N), where the tetrahydro-*s*-indacene is not substituted the 5, 6, or 7 position and is substituted in the 2 and/or 3 position.

EP 1 120 424 (and family member US 6,613,713) disclose tert-butylamino-2-(5,6,7-tetrahydro-s-indacenyl)dimethylsilyl) titanium dichloride indenyl ligands as polymerization catalyst where the tetrahydro-s-indacene is not substituted the 5, 6, or 7 position.

WO 2001/042315 discloses dimethylsilylene(t-butylamido)(2-methyl -tetrahydro-s-indacenyl)Ti(CH₂SiMe₃)₂ (see examples 27 and 28, and compounds IB5 and IB5' in claim 21) as polymerization catalysts where the tetrahydro-s-indacene is not substituted the 5, 6, or 7 position.

WO 98/27103 discloses dimethylsilylene(t-butylamido)(2-methyl-tetrahydro-s-indacenyl)TiCl₂ (see example 1) and others as polymerization catalysts where the tetrahydro-s-indacene is not substituted the 5, 6, or 7 position.

Tuor, et al. (Journal of the American Chemical Society 136 (36), 12794-12798 (2014)) disclose Mono- and trinuclear sumanenyl zirconocene complexes Cp(sumanenyl)ZrCl₂, Cp*(sumanenyl)ZrCl₂, and (C₂₁H₉)[(Cp*)ZrCl₂]₃.

Kociolek, et al. (Tetrahedron Letters (1999), 40(22), 4141-4144) discloses flash vapor pyrolysis tetrahydro-[as]-indacene ligand.

Other references of interest include: US 5,382,630; US 5,382,631; US 8,575,284; US 6,069,213; Kim, J. D. et al., J. Polym. Sci. Part A: Polym Chem., 38, 1427 (2000); Iedema, P.D. et al., Ind. Eng. Chem. Res., 43, 36 (2004); US 6,656,866; US 8,815,357; US 2014/0031504; US 5,135,526; US 7,385,015; WO 2007/080365; WO2012/006272; WO2014/0242314; WO 00/12565; WO 02/060957; WO 2004/046214; US 6,846,770; US 6,664,348; WO 05/075525; US 2002/007023; WO 2003/025027; US 2005/0288461; US 2014/0031504; US 8,088,867; US 5,516,848; US 4,701,432; US 5,077,255; US 7,141,632; US 6,207,606; US 8,598,061; Polymer Engineering and Science-2007, DOI 10.1002/pen, pages 131-139, published online in Wiley InterScience (www.interscience.wiley.com) 2007 Society of Plastics Engineers; US 2012/0130032; US 7,192,902; US 8,110,518; US 9,193,856; US 7,355,058; USSN 62/149,799, filed April 20, 2015 (and all cases claiming priority to or the benefit of USSN 62/149,799); USSN 62/103,372, filed January 14, 2015 (and all cases claiming priority to or the benefit of USSN 62/103,372); and PCT/US2015/067582, filed December 28, 2015.

There is still a need in the art for new and improved catalyst systems for the polymerization of olefins, in order to achieve increased activity or specific polymer properties, such as high melting point, high molecular weights, to increase conversion or

comonomer incorporation, or to alter comonomer distribution without deteriorating the resulting polymer's properties.

It is therefore also an object of the present invention to provide novel supported catalysts systems and processes for the polymerization of olefins using such catalyst systems.

- 5 The metallocene compounds and catalyst systems described herein address these needs by producing highly active catalysts containing a higher comonomer incorporation and molecular weight, that when formed into a molded part has improved properties (such as improved strength).

SUMMARY OF THE INVENTION

- 10 This invention relates to transition metal compounds represented by the formula:



wherein:

A is a substituted or unsubstituted tetrahydro-*as*-indacenyl group bonded to M;

- 15 L is substituted or unsubstituted monocyclic or polycyclic arenyl ligand or monocyclic or polycyclic heteroarenyl ligand bonded to M;

M is a group 3, 4, 5, or 6 transition metal (preferably group 4);

T is a bridging group bonded to L and A;

y is 0 or 1, indicating the absence or presence of T;

- 20 X is a leaving group, typically a univalent anionic ligand, or two Xs are joined and bound to the metal atom to form a metallocycle ring, or two Xs are joined to form a chelating ligand, a diene ligand, or an alkylidene;

n is the oxidation state of M and is 3, 4, 5, or 6.

This invention also relates to a catalyst system comprising the bridged transition metal compound described herein and an activator.

- 25 This invention also relates to a process to produce olefin polymer comprising: i) contacting olefin and optional C₂ to C₂₀ comonomer with a catalyst system comprising activator and bridged transition metal compound described herein, and ii) obtaining an olefin polymer.

- 30 This invention also relates to transition metal catalyst compositions comprising the reaction product of: (1) one or more bridged transition metal compounds described above; (2) one or more activators.

This invention further relates to polymer compositions produced by the methods described herein.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a graph of isotactic polypropylene (iPP) Mn vs. Tm for catalyst A (black) and comparatives C-1 (dark grey), C-2 (light grey) and C-7 (white) at 70 (squares) and 100°C (circles) polymerization temperature. A higher melting temperature correlates with increased isotacticity for the polymer produced from catalyst A vs. the comparatives.

Figure 2 is a graph of catalyst activity vs. iPP Tm for catalyst A (black) and comparatives C-1 (dark grey), C-2 (light grey) and C-7 (white) at 70 (squares) and 100°C (circles) polymerization temperature. Catalyst A provides significantly higher activity and iPP Tm for a given polymerization temperature.

Figure 3 is a graph of iPP Mn vs. Tm for catalyst C (black) and comparatives C-3 (grey) and C-4 (white) at 70 (squares) and 100°C (circles) polymerization temperature. Catalyst C provides both higher polymer Tm and Mn at a given polymerization temperature vs. the comparatives.

Figure 4 is a graph of iPP Mn vs. Tm for catalyst E (black) and comparatives C-5 (grey) and C-6 (white) at 70 (squares) and 100°C (circles) polymerization temperature. Catalyst E provides both higher polymer Tm and Mn at a given polymerization temperature vs. the comparatives.

Figure 5 is a graph of catalyst activity vs. iPP Tm for catalyst E (black) and comparatives C-5 (grey) and C-6 (white) at 70 (squares) and 100°C (circles) polymerization temperature. Catalyst E provides significantly higher activity and iPP Tm for a given polymerization temperature.

Figure 6 is a graph of iPP Mn vs. Tm for catalyst L (black) and comparatives C-9 (grey) and C-10 (white) at 70 (squares) and 100°C (circles) polymerization temperature. Catalyst L provides both higher polymer Tm and Mn at a given polymerization temperature vs. the comparatives.

Figure 7 is a graph of catalyst activity vs. iPP Tm for catalyst L (black) and comparatives C-9 (grey) and C-10 (white) at 70 (squares) and 100°C (circles) polymerization temperature. Catalyst L provides significantly higher activity and iPP Tm for a given polymerization temperature.

DETAILED DESCRIPTION OF THE INVENTION

For the purposes of this invention and the claims thereto, the new numbering scheme for the Periodic Table Groups is used as described in CHEMICAL AND ENGINEERING NEWS,

63(5), pg. 27 (1985), e.g., a “Group 4 metal” is an element from Group 4 of the Periodic Table, e.g., Hf, Ti, or Zr.

An “olefin,” alternatively referred to as “alkene,” is a linear, branched, or cyclic compound of carbon and hydrogen having at least one carbon-carbon double bond. For purposes of this specification and the claims appended thereto, when a polymer or copolymer is referred to as comprising an olefin, the olefin present in such polymer or copolymer is the polymerized form of the olefin. For example, when a copolymer is said to have an “ethylene” content of 35 wt% to 55 wt%, it is understood that the mer unit in the copolymer is derived from ethylene in the polymerization reaction and said derived units are present at 35 wt% to 55 wt%, based upon the weight of the copolymer. A “polymer” has two or more of the same or different mer units. A “homopolymer” is a polymer having mer units that are the same. A “copolymer” is a polymer having two or more mer units that are different from each other. A “terpolymer” is a polymer having three mer units that are different from each other. “Different” as used to refer to mer units indicates that the mer units differ from each other by at least one atom or are different isomerically. Accordingly, the definition of copolymer, as used herein, includes terpolymers and the like. An “ethylene polymer” or “ethylene copolymer” is a polymer or copolymer comprising at least 50 mole% ethylene derived units, a “propylene polymer” or “propylene copolymer” is a polymer or copolymer comprising at least 50 mole% propylene derived units, and so on.

For the purposes of this invention, ethylene shall be considered an α -olefin.

The terms “hydrocarbyl radical,” “hydrocarbyl,” and “hydrocarbyl group” are used interchangeably throughout this document. Likewise the terms “group,” “radical,” and “substituent” are also used interchangeably in this document. For purposes of this disclosure, “hydrocarbyl radical” is defined to be a radical, which contains hydrogen atoms and up to 50 carbon atoms and which may be linear, branched, or cyclic, and when cyclic, aromatic or non-aromatic.

Substituted hydrocarbyl radicals are radicals in which at least one hydrogen atom has been substituted with at least one functional group such as NR^x , OR^x , SeR^x , TeR^x , PR^x , AsR^x , SbR^x , SR^x , BR^x , and the like, or where at least one non-hydrocarbon atom or group has been inserted within the hydrocarbyl radical, such as -O-, -S-, -Se-, -Te-, -N(R^x)-, =N-, -P(R^x)-, =P-, -As(R^x)-, =As-, -Sb(R^x)-, =Sb-, -B(R^x)-, =B-, and the like, where R^x is independently a hydrocarbyl or halocarbyl radical, and two or more R^x may join together to form a substituted or unsubstituted saturated, partially unsaturated or aromatic cyclic or

polycyclic ring structure. Examples of a substituted hydrocarbyls would include $-\text{CH}_2\text{CH}_2-\text{O}-\text{CH}_3$ and $-\text{CH}_2-\text{NMe}_2$ where the radical is bonded via the carbon atom, but would not include groups where the radical is bonded through the heteroatom such as $-\text{OCH}_2\text{CH}_3$ or $-\text{NMe}_2$.

Silylcarbyl radicals are radicals in which one or more hydrocarbyl hydrogen atoms
 5 have been substituted with at least one SiR^*_3 containing group or where at least one $-\text{Si}(\text{R}^*)_2-$ has been inserted within the hydrocarbyl radical where R^* is independently a hydrocarbyl or halocarbyl radical, and two or more R^* may join together to form a substituted or unsubstituted saturated, partially unsaturated or aromatic cyclic or polycyclic ring structure.

Substituted silylcarbyl radicals are radicals in which at least one hydrogen atom has
 10 been substituted with at least one functional group such as NR^*_2 , OR^* , SeR^* , TeR^* , PR^*_2 , AsR^*_2 , SbR^*_2 , SR^* , BR^*_2 , GeR^*_3 , SnR^*_3 , PbR^*_3 and the like or where at least one non-hydrocarbon atom or group has been inserted within the silylcarbyl radical, such as $-\text{O}-$, $-\text{S}-$, $-\text{Se}-$, $-\text{Te}-$, $-\text{N}(\text{R}^*)-$, $=\text{N}-$, $-\text{P}(\text{R}^*)-$, $=\text{P}-$, $-\text{As}(\text{R}^*)-$, $=\text{As}-$, $-\text{Sb}(\text{R}^*)-$, $=\text{Sb}-$, $-\text{B}(\text{R}^*)-$, $=\text{B}-$, $-\text{Ge}(\text{R}^*)_2-$, $-\text{Sn}(\text{R}^*)_2-$, $-\text{Pb}(\text{R}^*)_2-$, and the like, where R^* is independently a hydrocarbyl or
 15 halocarbyl radical, and two or more R^* may join together to form a substituted or unsubstituted saturated, partially unsaturated or aromatic cyclic or polycyclic ring structure. Substituted silylcarbyl radicals are only bonded via a carbon or silicon atom.

Germylcarbyl radicals are radicals in which one or more hydrocarbyl hydrogen atoms have been substituted with at least one GeR^*_3 containing group or where at least one
 20 $-\text{Ge}(\text{R}^*)_2-$ has been inserted within the hydrocarbyl radical where R^* independently a hydrocarbyl or halocarbyl radical, and two or more R^* may join together to form a substituted or unsubstituted saturated, partially unsaturated or aromatic cyclic or polycyclic ring structure. Substituted germylcarbyl radicals are only bonded via a carbon or germanium atom.

Substituted germylcarbyl radicals are radicals in which at least one hydrogen atom has
 25 been substituted with at least one functional group such as NR^*_2 , OR^* , SeR^* , TeR^* , PR^*_2 , AsR^*_2 , SbR^*_2 , SR^* , BR^*_2 , SiR^*_3 , SnR^*_3 , PbR^*_3 and the like or where at least one non-hydrocarbon atom or group has been inserted within the germylcarbyl radical, such as $-\text{O}-$, $-\text{S}-$, $-\text{Se}-$, $-\text{Te}-$, $-\text{N}(\text{R}^*)-$, $=\text{N}-$, $-\text{P}(\text{R}^*)-$, $=\text{P}-$, $-\text{As}(\text{R}^*)-$, $=\text{As}-$, $-\text{Sb}(\text{R}^*)-$, $=\text{Sb}-$, $-\text{B}(\text{R}^*)-$, $=\text{B}-$, $-\text{Si}(\text{R}^*)_2-$, $-\text{Sn}(\text{R}^*)_2-$, $-\text{Pb}(\text{R}^*)_2-$, and the like, where R^* is independently a hydrocarbyl or
 30 halocarbyl radical, and two or more R^* may join together to form a substituted or unsubstituted saturated, partially unsaturated or aromatic cyclic or polycyclic ring structure.


Halocarbyl radicals are radicals in which one or more hydrocarbyl hydrogen atoms have been substituted with at least one halogen (e.g., F, Cl, Br, I) or halogen-containing group (e.g., CF₃).

Substituted halocarbyl radicals are radicals in which at least one halocarbyl hydrogen
5 or halogen atom has been substituted with at least one functional group such as NR^{*}₂, OR^{*},
SeR^{*}, TeR^{*}, PR^{*}₂, AsR^{*}₂, SbR^{*}₂, SR^{*}, BR^{*}₂, and the like, or where at least one non-carbon
atom or group has been inserted within the halocarbyl radical such as -O-, -S-, -Se-, -Te-,
-N(R^{*})-, =N-, -P(R^{*})-, =P-, -As(R^{*})-, =As-, -Sb(R^{*})-, =Sb-, -B(R^{*})-, =B-, and the like,
where R^{*} is independently a hydrocarbyl or halocarbyl radical provided that at least one
10 halogen atom remains on the original halocarbyl radical. Additionally, two or more R^{*} may
join together to form a substituted or unsubstituted saturated, partially unsaturated or aromatic
cyclic or polycyclic ring structure. Substituted halocarbyl radicals are only bonded via a
carbon atom.


A heteroatom is an atom other than carbon or hydrogen.

15 The term “aryl” or “aryl group” means a monocyclic or polycyclic aromatic ring and the
substituted variants thereof, including but not limited to, phenyl, naphthyl, 2-methyl-phenyl,
xylyl, 4-bromo-xylyl. Likewise “heteroaryl” means an aryl group where a ring carbon atom (or
two or three ring carbon atoms) has been replaced with a heteroatom, such as N, O, or S. The
term “substituted aryl” means: 1) an aryl group where a hydrogen has been replaced by a
20 substituted or unsubstituted hydrocarbyl group, a substituted or unsubstituted halocarbyl
group, a substituted or unsubstituted silylcarbyl group, or a substituted or unsubstituted
germylcarbyl group. The term “substituted heteroaryl” means: 1) a heteroaryl group where a
hydrogen has been replaced by a substituted or unsubstituted hydrocarbyl group, a substituted
or unsubstituted halocarbyl group, a substituted or unsubstituted silylcarbyl group, or a
25 substituted or unsubstituted germlycarbyl group.

The following numbering schemes are used herein for cyclopentadienyl, indenyl,
fluorenyl, and cyclopentanaphthyl (also termed benzindenyl). It should be noted that indenyl
can be considered a cyclopentadienyl fused with a benzene ring. Analogously, fluorenyl can
be considered a cyclopentadienyl with two phenyl rings fused onto the cyclopentadienyl ring.
30 Each structure below is drawn and named as an anion.



The following numbering schemes are used herein for indenyl, tetrahydro-*s*-indacenyl
 5 and tetrahydro-*as*-indacenyl ligands.



The term “arenyl” ligand is used herein to mean a substituted or unsubstituted unsaturated cyclic hydrocarbyl ligand that can consist of one ring, or two or more fused or catenated rings. Cyclopentadienyl ligands, indenyl ligands, and fluorenyl ligands are all
 10 examples of arenyl ligands. The term “heteroarenyl” ligand is used herein to mean a heteroatom substituted arenyl ligand wherein one or more heteroatom(s) is part of the ring structure. Common heteroatoms include B, N, O, Si, P, and S.

The term “monocyclic arenyl ligand” is used herein to mean a substituted or unsubstituted monoanionic C₅ to C₁₀₀ hydrocarbyl ligand that contains an aromatic five-

membered single hydrocarbyl ring (also referred to as a cyclopentadienyl ring).

The term “polycyclic arenyl ligand” is used herein to mean a substituted or unsubstituted monoanionic C₈ to C₁₀₃ hydrocarbyl ligand that contains an aromatic five-membered hydrocarbyl ring (also referred to as a cyclopentadienyl ring) that is fused to one or two partially unsaturated, or aromatic hydrocarbyl ring structures which may be fused to additional saturated, partially unsaturated, or aromatic hydrocarbyl rings.


Non-limiting examples of polycyclic arenyl ligands, are those listed in US 7,446,216 at column 12, line 61 to column 14, line 31.

Partially hydrogenated polycyclic arenyl ligands retain the numbering scheme of the parent polycyclic arenyl ligand, namely the numbering schemes defined for indenyl, fluorenyl, cyclopenta[*b*]naphthyl, and cyclopenta[*a*]naphthyl ligands.

A “bondable ring position” is a ring position that is capable of bearing a substituent or bridging substituent. For example, cyclopenta[*b*]thienyl has five bondable ring positions (at the carbon atoms) and one non-bondable ring position (the sulfur atom); cyclopenta[*b*]pyrrolyl has six bondable ring positions (at the carbon atoms and at the nitrogen atom).


In using the terms “substituted or unsubstituted cyclopentadienyl ligand,” “substituted or unsubstituted indenyl ligand,” “substituted or unsubstituted fluorenyl ligand,” “substituted or unsubstituted cyclopentanaphthyl ligand,” “substituted or unsubstituted tetrahydro-*as*-indacenyl ligand”, “substituted or unsubstituted monocyclic arenyl ligand,” or “substituted or unsubstituted polycyclic arenyl ligand,” the substitution to the aforementioned ligand is on a bondable ring position, and each occurrence is selected from hydrocarbyl, substituted hydrocarbyl, halocarbyl, substituted halocarbyl, silylcarbyl, germlylcarbyl, a halogen radical, or a polar group.

A “tetrahydro-*as*-indecenyl” ligand is defined to mean a substituted or unsubstituted unsaturated cyclic hydrocarbyl ligand that consists of at least one cyclopentadienyl ring fused to at least one six membered aromatic ring which is fused to at least one saturated five membered ring, typically represented by the formula:




where 1, 2, 3, 4, 5, 6, 7, and 8 indicate bondable ring positions.

Both isomers of substituted and unsubstituted tetrahydro-*as*-indacene compounds are typically named with the numbering scheme illustrated below:



1,2,3,6-tetrahydro-*as*-indacene



1,2,3,8-tetrahydro-*as*-indacene

As used herein, M_n is number average molecular weight, M_w is weight average molecular weight, and M_z is z average molecular weight, wt% is weight percent, and mol% is mole percent. Molecular weight distribution (MWD), also referred to as polydispersity, is defined to be M_w divided by M_n . Unless otherwise noted, all molecular weight units (e.g., M_w , M_n , M_z) are g/mol. The following abbreviations may be used herein: Me is methyl, Et is ethyl, Pr is propyl, cPr is cyclopropyl, nPr is n-propyl, iPr is isopropyl, Bu is butyl, nBu is normal butyl, iBu is isobutyl, sBu is sec-butyl, tBu is tert-butyl, Oct is octyl, Ph is phenyl, Bn is benzyl, Cp is cyclopentadienyl, Ind is indenyl, Flu is fluorenyl, and MAO is methylalumoxane.

For purposes of this invention and the claims thereto, a “catalyst system” is the combination of at least one catalyst compound, at least one activator, an optional co-activator, and an optional support material. For the purposes of this invention and the claims thereto, when catalyst systems are described as comprising neutral stable forms of the components, it is well understood by one of ordinary skill in the art, that the ionic form of the component is the form that reacts with the monomers to produce polymers.

In the description herein, the metallocene catalyst may be described as a catalyst precursor, a pre-catalyst compound, metallocene catalyst compound or a transition metal

compound, and these terms are used interchangeably.

A metallocene catalyst is defined as an organometallic transition metal compound with at least one π -bound arenyl moiety such as cyclopentadienyl (or substituted arenyl moiety such as 2-methylindenyl) bound to a transition metal.

5 For purposes of this invention and claims thereto in relation to metallocene catalyst compounds, the term “substituted” means that one or more hydrogen atoms have been replaced with a hydrocarbyl, heteroatom (such as a halide), or a heteroatom containing group, (such as silylcarbyl, germylcarbyl, halocarbyl, etc.). For example, methyl cyclopentadiene (Cp) is a Cp group substituted with a methyl group.

10 For purposes of this invention and claims thereto, “alkoxides” include those where the alkyl group is a C₁ to C₁₀ hydrocarbyl. The alkyl group may be straight chain, branched, or cyclic. The alkyl group may be saturated or unsaturated. In some embodiments, the alkyl group may comprise at least one aromatic group.

Embodiments

15 This invention relates to tetrahydro-*as*-indacenyl metallocene catalyst compounds, catalyst systems comprising such compounds and an optional support and polymerization processes using such.

This invention relates to transition metal compounds represented by the formula:



20 A is a substituted or unsubstituted tetrahydro-*as*-indacenyl group bonded to M;

L is substituted or unsubstituted monocyclic or polycyclic arenyl ligand or monocyclic or polycyclic heteroarenyl ligand bonded to M;

M is a group 3, 4, 5, or 6 transition metal, preferably group 4 transition metal, for example titanium, zirconium, or hafnium (preferably zirconium or hafnium);

25 T is a bridging group (such as dialkylsilylene or dialkylcarbylene); T is preferably (CR⁸R⁹)_x, SiR⁸R⁹ or GeR⁸R⁹ where x is 1 or 2, R⁸ and R⁹ are independently selected from substituted or unsubstituted hydrocarbyl, halocarbyl, silylcarbyl and germylcarbyl and R⁸ and R⁹ may optionally be bonded together to form a ring structure;

y is 0 or 1, indicating the absence or presence of T;

30 X is a leaving group, typically a univalent anionic ligand such as a halide, a hydride, an alkyl group, an alkenyl group or an arylalkyl group, or two Xs are joined and bound to the metal atom to form a metallocycle ring, or two Xs are joined to form a chelating ligand, a diene ligand, or an alkylidene; and

n is the oxidation state of M and is 3, 4, 5, or 6, preferably 4.

This invention relates to a catalyst system comprising an activator, and at least one metallocene catalyst compound, where the metallocene is a tetrahydro-*as*-indacenyl transition metal compound, preferably represented by the formula:



A is a substituted or unsubstituted tetrahydro-*as*-indacenyl group bonded to M;

L is substituted or unsubstituted monocyclic or polycyclic arenyl ligand or monocyclic or polycyclic heteroarenyl ligand bonded to M;

M is a group 3, 4, 5, or 6 transition metal, preferably group 4 transition metal, for example titanium, zirconium, or hafnium (preferably zirconium or hafnium);

T is a bridging group (such as dialkylsilylene or dialkylcarbylene) bonded to L and A; T is preferably $(CR^8R^9)_x$, SiR^8R^9 or GeR^8R^9 where x is 1 or 2, R^8 and R^9 are independently selected from substituted or unsubstituted hydrocarbyl, halocarbyl, silylcarbyl and germylcarbyl and R^8 and R^9 may optionally be bonded together to form a ring structure;


y is 0 or 1, indicating the absence or presence of T;

X is a leaving group, typically a univalent anionic ligand such as a halide, a hydride, an alkyl group, an alkenyl group or an arylalkyl group, or two Xs are joined and bound to the metal atom to form a metallocycle ring, or two Xs are joined to form a chelating ligand, a diene ligand, or an alkylidene; and

n is the oxidation state of M and is 3, 4, 5, or 6, preferably 4.

Catalyst Compounds and Ligands


This invention relates to transition metal compounds comprising a tetrahydro-*as*-indacenyl ligand wherein the ligand is derived from tetrahydro-*as*-indacene isomers represented by the formulas (4a and 4b):



wherein R^1 , R^2 , R^4 , R^5 , and each R^a , R^b , and R^c are as defined below for Formulas 1 and 2, and R^3 is hydrogen or hydrocarbyl, preferable hydrogen. Preferably, at least one R^a , R^b and

R^c is not hydrogen. This invention also relates to the tetrahydro-*as*-indacene compounds of Formulas 4a and 4b wherein R^1 , R^2 , R^4 , R^5 , and each R^a , R^b and R^c are as defined below for Formulas 1 and 2, and R^3 is hydrogen or hydrocarbyl, preferably hydrogen.

This invention further relates to tetrahydro-*as*-indacenyl transition metal compounds
5 represented by the formula 2 or 3:



wherein

M is a group 3, 4, 5, or 6 transition metal, preferably group 4 transition metal, for example titanium, zirconium, or hafnium (preferably zirconium or hafnium);

10 B is the oxidation state of M and is 3, 4, 5, or 6, preferably 4;

C is B-2;

T is a bridging group;

y is 1 or 0 indicating the presence of absence of T ;

X is a leaving group, typically a univalent anionic ligand such as a halide, a hydride, an alkyl
15 group, an alkenyl group or an arylalkyl group, or two X s are joined and bound to the metal atom to form a metallocycle ring, or two X s are joined to form a chelating ligand, a diene ligand, or an alkylidene;

L is a substituted or unsubstituted monocyclic or polycyclic arenyl ligand or monocyclic or polycyclic heteroarenyl ligand bonded (typically pi-bonded) to M ;

20 each R^1 , R^2 , R^4 , and R^5 is independently hydrogen, or a C_1 - C_{50} substituted or unsubstituted hydrocarbyl, halocarbyl or silylcarbyl; and

each R^a , R^b , and R^c is independently a C_1 - C_{50} substituted or unsubstituted hydrocarbyl (preferably a C_1 - C_{10} alkyl), or hydrogen.

In any embodiment of the invention, each R^a , R^b , R^c , R^1 , R^2 , R^4 and R^5 is independently hydrogen or a C_1 - C_{50} substituted or unsubstituted hydrocarbyl.

In any embodiment of the invention, each R^a , R^b , R^c , R^1 , R^2 , R^4 , and R^5 is independently hydrogen or a C_1 - C_{10} alkyl.

5 In any embodiment of the invention, each R^b and R^2 is independently a C_1 - C_{10} alkyl and each R^a , R^c , R^1 , R^4 , and R^5 is hydrogen.

In any embodiment of the invention, each R^b is independently a C_1 - C_{10} alkyl and each R^a , R^c , R^1 , R^2 , R^4 , and R^5 is hydrogen.

10 In any embodiment of the invention each R^2 is independently a C_1 - C_{10} alkyl and each R^a , R^b , R^c , R^1 , R^4 , and R^5 is hydrogen.

In any embodiment of the invention, each R^b and R^2 is independently methyl, ethyl, or an isomer of propyl, butyl, pentyl or hexyl, and each R^a , R^c , R^1 , R^4 , and R^5 is hydrogen.

In any embodiment of the invention, each R^2 is methyl, ethyl, or an isomer of propyl, butyl, pentyl or hexyl, and each R^a , R^b , R^c , R^1 , R^4 , and R^5 is hydrogen.

15 In any embodiment of the invention, each R^b and R^2 is independently methyl or ethyl and each R^a , R^c , R^1 , R^4 , and R^5 is hydrogen.

In any embodiment of the invention, each R^2 is methyl or ethyl and R^a , R^b , R^c , R^1 , R^4 , and R^5 are hydrogen.

20 In any embodiment of the invention, each R^2 is independently hydrogen, methyl, ethyl, propyl, butyl, pentyl or hexyl.

In any embodiment of the invention, each R^2 is independently hydrogen, methyl or ethyl.

In any embodiment of the invention, each R^2 is methyl or ethyl.

25 In any embodiment of the invention, each R^b is independently hydrogen, methyl, ethyl, propyl, butyl, pentyl or hexyl.

In any embodiment of the invention, each R^b is independently hydrogen, methyl or ethyl.

In any embodiment of the invention, each R^b is methyl or ethyl.

30 In any embodiment of the invention, each R^a and R^c is independently hydrogen, methyl or ethyl.

In any embodiment of the invention, each R^a and R^c is independently hydrogen.

In any embodiment of the invention, T is selected from $(CR^8R^9)_x$, $(SiR^{10}R^{11})_x$, $CR^8R^9SiR^{10}R^{11}$, $GeR^{10}R^{11}$, BR^{12} , NR^{12} , PR^{12} , O, or S where x is 1 or 2, R^8 and R^9 are

independently selected from hydrogen, substituted or unsubstituted hydrocarbyl, halocarbyl, silylcarbyl, R^{10} , R^{11} , and R^{12} are independently selected from substituted or unsubstituted hydrocarbyl, halocarbyl, silylcarbyl and any two or more adjacent R^8 , R^9 , R^{10} , or R^{11} may optionally be bonded together to form a ring structure.

5 In any embodiment of the invention, T is selected from $(CR^8R^9)_x$, $(SiR^{10}R^{11})_x$, or $GeR^{10}R^{11}$ where x is 1 or 2, R^8 , R^9 , R^{10} , and R^{11} are as defined above.

In any embodiment of the invention, T is selected from diphenylmethylenes, dimethylmethylenes, 1,2-ethylene, cyclotrimethylenesilylene, cyclo-tetramethylenesilylene, cyclopentamethylenesilylene, dimethylsilylene, diethylsilylene, methylethylsilylene, methylphenylsilylene, diphenylsilylene, dipropylsilylene and 1,2-tetramethyldisilylene.

In any embodiment of the invention, T is selected from cyclo-tetramethylenesilylene, dimethylsilylene, and 1,2-tetramethyldisilylene.

In any embodiment of the invention, each X is hydrocarbyl, halocarbyl, or substituted hydrocarbyl or halocarbyl.

15 In any embodiment of the invention, X is methyl, benzyl, or halo where halo includes fluoride, chloride, bromide and iodide.

In any embodiment of any formula described herein, y is 1 and T is a bridging group containing at least one Group 13, 14, 15, or 16 element, in particular boron or a Group 14, 15 or 16 element. Examples of suitable bridging groups include $P(=S)R^*$, $P(=Se)R^*$, $P(=O)R^*$, R^*_2C , R^*_2Si , R^*_2Ge , $R^*_2CCR^*_2$, $R^*_2CCR^*_2CR^*_2$, $R^*_2CCR^*_2CR^*_2CR^*_2$, $R^*C=CR^*$, $R^*C=CR^*CR^*_2$, $R^*_2CCR^*=CR^*CR^*_2$, $R^*C=CR^*CR^*=CR^*$, $R^*C=CR^*CR^*_2CR^*_2$, $R^*_2CSiR^*_2$, $R^*_2SiSiR^*_2$, $R^*_2SiOSiR^*_2$, $R^*_2CSiR^*_2CR^*_2$, $R^*_2SiCR^*_2SiR^*_2$, $R^*C=CR^*SiR^*_2$, $R^*_2CGeR^*_2$, $R^*_2GeGeR^*_2$, $R^*_2CGeR^*_2CR^*_2$, $R^*_2GeCR^*_2GeR^*_2$, $R^*_2SiGeR^*_2$, $R^*C=CR^*GeR^*_2$, R^*B , $R^*_2C-BR^*$, $R^*_2C-BR^*-CR^*_2$, $R^*_2C-O-CR^*_2$, $R^*_2CR^*_2C-O-CR^*_2CR^*_2$, $R^*_2C-O-CR^*_2CR^*_2$, $R^*_2C-O-CR^*=CR^*$, $R^*_2C-S-CR^*_2$, $R^*_2CR^*_2C-S-CR^*_2CR^*_2$, $R^*_2C-S-CR^*_2CR^*_2$, $R^*_2C-S-CR^*=CR^*$, $R^*_2C-Se-CR^*_2$, $R^*_2CR^*_2C-Se-CR^*_2CR^*_2$, $R^*_2C-Se-CR^*_2CR^*_2$, $R^*_2C-Se-CR^*=CR^*$, $R^*_2C-N=CR^*$, $R^*_2C-NR^*-CR^*_2$, $R^*_2C-NR^*-CR^*_2CR^*_2$, $R^*_2C-NR^*-CR^*=CR^*$, $R^*_2CR^*_2C-NR^*-CR^*_2CR^*_2$, $R^*_2C-P=CR^*$, $R^*_2C-PR^*-CR^*_2$, O, S, Se, Te, NR^* , PR^* , AsR^* , SbR^* , O-O, S-S, R^*N-NR^* , R^*P-PR^* , O-S, O- NR^* , O- PR^* , S- NR^* , S- PR^* , and R^*N-PR^* where R^* is hydrogen or a C_{1-20} containing hydrocarbyl, substituted hydrocarbyl, halocarbyl, substituted halocarbyl, silylcarbyl or germlylcarbyl substituent and optionally two or more adjacent R^* may join to form a substituted or unsubstituted, saturated, partially unsaturated or aromatic, cyclic or

polycyclic substituent. Preferred examples for the bridging group T include CH₂, CH₂CH₂, SiMe₂, SiPh₂, SiMePh, Si(CH₂)₃, Si(CH₂)₄, O, S, NPh, PPh, NMe, PMe, NEt, NPr, NBu, PEt, PPr, Me₂SiOSiMe₂, and PBu. In a preferred embodiment of the invention in any embodiment of any formula described herein, T is represented by the formula ER^d₂ or (ER^d₂)₂, where E is

5 C, Si, or Ge, and each R^d is, independently, hydrogen, halogen, C₁ to C₂₀ hydrocarbyl (such as methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, or dodecyl) or a C₁ to C₂₀ substituted hydrocarbyl, and two R^d can form a cyclic structure including aromatic, partially saturated, or saturated cyclic or fused ring system. Preferably, T is a bridging group comprising carbon or silica, such as dialkylsilyl, preferably T is selected from

10 CH₂, CH₂CH₂, C(CH₃)₂, SiMe₂, cyclotrimethylenesilylene (Si(CH₂)₃), cyclopentamethylenesilylene (Si(CH₂)₅) and cyclotetramethylenesilylene (Si(CH₂)₄).

Illustrative, but not limiting, examples of preferred metallocenes for use in this invention's mixed catalyst composition include:

dimethylsilylene(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)(indenyl)M(R)₂,

15 cyclotetramethylenesilylene(2,7,7-trimethyl-1,6,7,8-tetrahydro-*as*-indacen-3-yl)(indenyl)M(R)₂,

dimethylsilylene(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)(cyclopentadienyl)M(R)₂,

cyclotetramethylenesilylene(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)(cyclopentadienyl)M(R)₂, dimethylsilylene-bis(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-

20 indacen-3-yl)M(R)₂,

cyclotetramethylenesilylene-bis(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,

cyclotrimethylenesilylene-bis(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,

ethylene-bis-(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,

dimethylmethylenes-bis-(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,

25 tetramethyldisilanediy-bis(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,

dimethylsilylene-bis(7,7-dimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,

cyclotetramethylenesilylene-bis(7,7-dimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,

cyclotrimethylenesilylene-bis(7,7-dimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,

ethylene-bis-(7,7-dimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,

30 dimethylmethylenes-bis-(7,7-dimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,

tetramethyldisilanediy-bis(7,7-dimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,

dimethylsilylene-bis(2-methyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,

cyclotetramethylenesilylene-bis(2-methyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,

- cyclotrimethylenesilylene-bis(2-methyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
ethylene-bis-(2-methyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
dimethylmethylen-bis-(2-methyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
tetramethyldisilanediy-bis(2-methyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
5 dimethylsilylene-bis(2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
cyclotetramethylenesilylene-bis(2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
cyclotrimethylenesilylene-bis(2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
ethylene-bis-(2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
dimethylmethylen-bis-(2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
10 tetramethyldisilanediy-bis(2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
dimethylsilylene-bis(7,7-diethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
cyclotetramethylenesilylene-bis(7,7-diethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
cyclotrimethylenesilylene-bis(7,7-diethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
ethylene-bis-(7,7-diethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
15 dimethylmethylen-bis-(7,7-diethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
tetramethyldisilanediy-bis(7,7-diethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
dimethylsilylene-bis(2-ethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
cyclotetramethylenesilylene-bis(2-ethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
cyclotrimethylenesilylene-bis(2-ethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
20 ethylene-bis-(2-ethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
dimethylmethylen-bis-(2-ethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
tetramethyldisilanediy-bis(2-ethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
dimethylsilylene-bis(2-methyl-7,7-diethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
cyclotetramethylenesilylene-bis(2-methyl-7,7-diethyl-3,6,7,8-tetrahydro-*as*-indacen-3-
25 yl)M(R)₂,
cyclotrimethylenesilylene-bis(2-methyl-7,7-diethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)M(R)₂,
where M is selected from a group consisting of Ti, Zr, and Hf (preferably Zr and Hf) and R is
selected from halogen or C₁ to C₅ alkyl or benzyl, preferably R is a methyl group or a halogen
group (preferably C₁) and preferably M(R)₂ is ZrCl₂, ZrMe₂, HfCl₂ or HfMe₂.
- 30 In alternate embodiments, two or more different transition metal compounds may be
used herein. For purposes of this invention one transition metal compound is considered
different from another if they differ by at least one atom. For example, “Me₂Si(2,7,7-Me₃-
3,6,7,8-tetrahydro-*as*-indacen-3-yl)₂ ZrCl₂” is different from “Me₂Si(7,7-Me₂-3,6,7,8-

tetrahydro-*as*-indacen-3-yl)₂ZrCl₂” which is different from “Me₂Si(2,7,7-Me₃-3,6,7,8-tetrahydro-*as*-indacen-3-yl)₂ HfCl₂.”

In a preferred embodiment, one tetrahydro-*as*-indacenyl compound as described herein is used in the catalyst system.

5 Activators

The terms “cocatalyst” and “activator” are used herein interchangeably and are defined to be any compound which can activate any one of the catalyst compounds described above by converting the neutral catalyst compound to a catalytically active catalyst compound cation. Non-limiting activators, for example, include alumoxanes, aluminum alkyls, ionizing
10 activators, which may be neutral or ionic, and conventional-type cocatalysts. Preferred activators typically include alumoxane compounds, modified alumoxane compounds, and ionizing anion precursor compounds that abstract a reactive, σ -bound, metal ligand making the metal complex cationic and providing a charge-balancing noncoordinating or weakly coordinating anion.

15 Alumoxane Activators

Alumoxane activators are utilized as activators in the catalyst systems described herein. Alumoxanes are generally oligomeric compounds containing -Al(R¹)-O- sub-units, where R¹ is an alkyl group. Examples of alumoxanes include methylalumoxane (MAO), modified methylalumoxane (MMAO), ethylalumoxane and isobutylalumoxane.
20 Alkylalumoxanes and modified alkylalumoxanes are suitable as catalyst activators, particularly when the abstractable ligand is an alkyl, halide, alkoxide or amide. Mixtures of different alumoxanes and modified alumoxanes may also be used. It may be preferable to use a visually clear methylalumoxane. A cloudy or gelled alumoxane can be filtered to produce a clear solution or clear alumoxane can be decanted from the cloudy solution. A useful
25 alumoxane is a modified methyl alumoxane (MMAO) cocatalyst type 3A (commercially available from Akzo Chemicals, Inc. under the trade name Modified Methylalumoxane type 3A, covered under patent number US 5,041,584).

When the activator is an alumoxane (modified or unmodified), some embodiments select the maximum amount of activator typically at up to a 5000-fold molar excess Al/M
30 over the catalyst compound (per metal catalytic site). The minimum activator-to-catalyst-compound is a 1:1 molar ratio. Alternate preferred ranges include from 1:1 to 500:1, alternately from 1:1 to 200:1, alternately from 1:1 to 100:1, or alternately from 1:1 to 50:1.

Non Coordinating Anion Activators


Non-coordinating anion activators may also be used herein. The term “non-coordinating anion” (NCA) means an anion which either does not coordinate to a cation or which is only weakly coordinated to a cation thereby remaining sufficiently labile to be displaced by a neutral Lewis base. “Compatible” non-coordinating anions are those which are not degraded to neutrality when the initially formed complex decomposes. Further, the anion will not transfer an anionic substituent or fragment to the cation so as to cause it to form a neutral transition metal compound and a neutral by-product from the anion. Non-coordinating anions useful in accordance with this invention are those that are compatible, stabilize the transition metal cation in the sense of balancing its ionic charge at +1, and yet retain sufficient lability to permit displacement during polymerization.

It is within the scope of this invention to use an ionizing or stoichiometric activator, neutral or ionic, such as tri (n-butyl) ammonium tetrakis (pentafluorophenyl) borate, a tris perfluorophenyl boron metalloid precursor or a tris perfluoronaphthyl boron metalloid precursor, polyhalogenated heteroborane anions (WO 98/43983), boric acid (US 5,942,459), in combination with the alumoxane or modified alumoxane activators. It is also within the scope of this invention to use neutral or ionic activators in combination with the alumoxane or modified alumoxane activators.

The catalyst systems of this invention can include at least one non-coordinating anion (NCA) activator. Specifically, the catalyst systems may include an NCAs which either do not coordinate to a cation or which only weakly coordinate to a cation thereby remaining sufficiently labile to be displaced during polymerization.

The terms “cocatalyst” and “activator” are used herein interchangeably and are defined to be any compound which can activate any one of the catalyst compounds described above by converting the neutral catalyst compound to a catalytically active catalyst compound cation.

In a preferred embodiment, boron containing NCA activators represented by the formula below can be used:



where: Z is (L-H) or a reducible Lewis acid; L is a neutral Lewis base; H is hydrogen; (L-H) is a Bronsted acid; A^{d-} is a boron containing non-coordinating anion having the charge d-; d is 1, 2, or 3.

The cation component, Z_d^+ may include Bronsted acids such as protons or protonated

Lewis bases or reducible Lewis acids capable of protonating or abstracting a moiety, such as an alkyl or aryl, from the bulky ligand metallocene containing transition metal catalyst precursor, resulting in a cationic transition metal species.

The activating cation Z_d^+ may also be a moiety such as silver, tropylium, carboniums, ferroceniums and mixtures, preferably carboniums and ferroceniums. Most preferably Z_d^+ is triphenyl carbonium. Preferred reducible Lewis acids can be any triaryl carbonium (where the aryl can be substituted or unsubstituted, such as those represented by the formula: (Ar_3C^+) , where Ar is aryl or aryl substituted with a heteroatom, a C_1 to C_{40} hydrocarbyl, or a substituted C_1 to C_{40} hydrocarbyl), preferably the reducible Lewis acids in formula (14) above as "Z" include those represented by the formula: (Ph_3C^+) , where Ph is a substituted or unsubstituted phenyl, preferably substituted with C_1 to C_{40} hydrocarbyls or substituted a C_1 to C_{40} hydrocarbyls, preferably C_1 to C_{20} alkyls or aromatics or substituted C_1 to C_{20} alkyls or aromatics, preferably Z is a triphenylcarbonium.


When Z_d^+ is the activating cation $(L-H)_d^+$, it is preferably a Bronsted acid, capable of donating a proton to the transition metal catalytic precursor resulting in a transition metal cation, including ammoniums, oxoniums, phosphoniums, silyliums, and mixtures thereof, preferably ammoniums of methylamine, aniline, dimethylamine, diethylamine, N-methylaniline, diphenylamine, trimethylamine, triethylamine, N,N-dimethylaniline, methyldiphenylamine, pyridine, p-bromo N,N-dimethylaniline, p-nitro-N,N-dimethylaniline, phosphoniums from triethylphosphine, triphenylphosphine, and diphenylphosphine, oxoniums from ethers such as dimethyl ether diethyl ether, tetrahydrofuran and dioxane, sulfoniums from thioethers, such as diethyl thioethers, tetrahydrothiophene, and mixtures thereof.

The anion component A^{d-} includes those having the formula $[M^{k+}Q_n]^{d-}$ wherein k is 1, 2, or 3; n is 1, 2, 3, 4, 5, or 6 (preferably 1, 2, 3, or 4); $n - k = d$; M is an element selected from Group 13 of the Periodic Table of the Elements, preferably boron or aluminum, and Q is independently a hydride, bridged or unbridged dialkylamido, halide, alkoxide, aryloxy, hydrocarbyl, substituted hydrocarbyl, halocarbyl, substituted halocarbyl, and halosubstituted-hydrocarbyl radicals, said Q having up to 20 carbon atoms with the proviso that in not more than 1 occurrence is Q a halide. Preferably, each Q is a fluorinated hydrocarbyl group having 1 to 20 carbon atoms, more preferably each Q is a fluorinated aryl group, and most preferably each Q is a pentafluoryl aryl group. Examples of suitable A^{d-} also include diboron compounds as disclosed in US 5,447,895, which is fully incorporated herein by reference.

Illustrative, but, not limiting, examples of boron compounds which may be used as an activating cocatalyst are the compounds described as (and particularly those specifically listed as) activators in US 8,658,556, which is incorporated by reference herein.

Most preferably, the ionic stoichiometric activator Z_d^+ (A^{d-}) is one or more of N,N-dimethylanilinium
 5 dimethylanilinium tetra(perfluorophenyl)borate, N,N-dimethylanilinium tetrakis(perfluoronaphthyl)borate, N,N-dimethylanilinium tetrakis(perfluorobiphenyl)borate, N,N-dimethylanilinium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, triphenylcarbenium tetrakis(perfluoronaphthyl)borate, triphenylcarbenium tetrakis(perfluorobiphenyl)borate, triphenylcarbenium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, or triphenylcarbenium
 10 tetra(perfluorophenyl)borate.

Bulky activators are also useful herein as NCAs. "Bulky activator" as used herein refers to anionic activators represented by the formula:



15 where: each R_1 is, independently, a halide, preferably a fluoride; Ar is substituted or unsubstituted aryl group (preferably a substituted or unsubstituted phenyl), preferably substituted with C_1 to C_{40} hydrocarbyls, preferably C_1 to C_{20} alkyls or aromatics; each R_2 is, independently, a halide, a C_6 to C_{20} substituted aromatic hydrocarbyl group or a siloxy group of the formula $-O-Si-R_a$, where R_a is a C_1 to C_{20} hydrocarbyl or hydrocarbylsilyl group
 20 (preferably R_2 is a fluoride or a perfluorinated phenyl group); each R_3 is a halide, C_6 to C_{20} substituted aromatic hydrocarbyl group or a siloxy group of the formula $-O-Si-R_a$, where R_a is a C_1 to C_{20} hydrocarbyl or hydrocarbylsilyl group (preferably R_3 is a fluoride or a C_6 perfluorinated aromatic hydrocarbyl group); wherein R_2 and R_3 can form one or more saturated or unsaturated, substituted or unsubstituted rings (preferably R_2 and R_3 form a

perfluorinated phenyl ring); and L is a neutral Lewis base; (L-H)⁺ is a Bronsted acid; d is 1, 2, or 3; wherein the anion has a molecular weight of greater than 1020 g/mol; wherein at least three of the substituents on the B atom each have a molecular volume of greater than 250 cubic Å, alternately greater than 300 cubic Å, or alternately greater than 500 cubic Å.

- 5 Preferably (Ar₃C)_d⁺ is (Ph₃C)_d⁺, where Ph is a substituted or unsubstituted phenyl, preferably substituted with C₁ to C₄₀ hydrocarbyls or substituted C₁ to C₄₀ hydrocarbyls, preferably C₁ to C₂₀ alkyls or aromatics or substituted C₁ to C₂₀ alkyls or aromatics.

“Molecular volume” is used herein as an approximation of spatial steric bulk of an activator molecule in solution. Comparison of substituents with differing molecular volumes
10 allows the substituent with the smaller molecular volume to be considered “less bulky” in comparison to the substituent with the larger molecular volume. Conversely, a substituent with a larger molecular volume may be considered “more bulky” than a substituent with a smaller molecular volume.

Molecular volume may be calculated as reported in “A Simple ‘Back of the Envelope’
15 Method for Estimating the Densities and Molecular Volumes of Liquids and Solids,” Journal of Chemical Education, Vol. 71, No. 11, November 1994, pp. 962-964. Molecular volume (MV), in units of cubic Å, is calculated using the formula: MV = 8.3V_s, where V_s is the scaled volume. V_s is the sum of the relative volumes of the constituent atoms, and is calculated from the molecular formula of the substituent using the following table of relative
20 volumes. For fused rings, the V_s is decreased by 7.5% per fused ring.

Element	Relative Volume
H	1
1 st short period, Li to F	2
2 nd short period, Na to Cl	4
1 st long period, K to Br	5
2 nd long period, Rb to I	7.5
3 rd long period, Cs to Bi	9

For a list of particularly useful Bulky activators please see US 8,658,556, which is incorporated by reference herein.

In another embodiment, one or more of the NCA activators is chosen from the
25 activators described in US 6,211,105.

Preferred activators include N,N-dimethylanilinium tetrakis(perfluoronaphthyl)borate, N,N-dimethylanilinium tetrakis(perfluorobiphenyl)borate, N,N-dimethylanilinium tetrakis(perfluorophenyl)borate, N,N-dimethylanilinium tetrakis(3,5-

bis(trifluoromethyl)phenyl)borate, triphenylcarbenium tetrakis(perfluoronaphthyl)borate, triphenylcarbenium tetrakis(perfluorobiphenyl)borate, triphenylcarbenium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, triphenylcarbenium tetrakis(perfluorophenyl)borate, $[\text{Ph}_3\text{C}^+][\text{B}(\text{C}_6\text{F}_5)_4^-]$, $[\text{Me}_3\text{NH}^+][\text{B}(\text{C}_6\text{F}_5)_4^-]$; 1-(4-(tris(pentafluorophenyl)borate)-2,3,5,6-tetrafluorophenyl)pyrrolidinium; and tetrakis(pentafluorophenyl)borate, 4-(tris(pentafluorophenyl)borate)-2,3,5,6-tetrafluoropyridine.

In a preferred embodiment, the activator comprises a triaryl carbonium (such as triphenylcarbenium tetraphenylborate, triphenylcarbenium tetrakis(pentafluorophenyl)borate, triphenylcarbenium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, triphenylcarbenium tetrakis(perfluoronaphthyl)borate, triphenylcarbenium tetrakis(perfluorobiphenyl)borate, triphenylcarbenium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate).

In another embodiment, the activator comprises one or more of trialkylammonium tetrakis(pentafluorophenyl)borate, N,N-dialkylanilinium tetrakis(pentafluorophenyl)borate, N,N-dimethyl-(2,4,6-trimethylanilinium) tetrakis(pentafluorophenyl)borate, trialkylammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate, N,N-dialkylanilinium tetrakis-(2,3,4,6-tetrafluorophenyl)borate, trialkylammonium tetrakis(perfluoronaphthyl)borate, N,N-dialkylanilinium tetrakis(perfluoronaphthyl)borate, trialkylammonium tetrakis(perfluorobiphenyl)borate, N,N-dialkylanilinium tetrakis(perfluorobiphenyl)borate, trialkylammonium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, N,N-dialkylanilinium tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, N,N-dialkyl-(2,4,6-trimethylanilinium) tetrakis(3,5-bis(trifluoromethyl)phenyl)borate, di-(i-propyl)ammonium tetrakis(pentafluorophenyl)borate, (where alkyl is methyl, ethyl, propyl, n-butyl, sec-butyl, or t-butyl).

The typical NCA activator-to-catalyst ratio, e.g., all NCA activators-to-catalyst ratio is about a 1:1 molar ratio. Alternate preferred ranges include from 0.1:1 to 100:1, alternately from 0.5:1 to 200:1, alternately from 1:1 to 500:1 alternately from 1:1 to 1000:1. A particularly useful range is from 0.5:1 to 10:1, preferably 1:1 to 5:1.

Activators useful herein also include those described in US 7,247,687 at column 169, line 50 to column 174, line 43, particularly column 172, line 24 to column 173, line 53.

It is also within the scope of this invention that the catalyst compounds can be combined with combinations of alumoxanes and NCA's (see for example, US 5,153,157; US 5,453,410; EP 0 573 120; WO 94/07928; and WO 95/14044, which discuss the use of an alumoxane in combination with an ionizing activator).

Optional Scavengers or Co-Activators

In addition to the activator compounds, scavengers, chain transfer agents or co-activators may be used. Aluminum alkyl or organoaluminum compounds which may be utilized as scavengers or co-activators include, for example, trimethylaluminum, triethylaluminum, triisobutylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum, and diethyl zinc.

Useful chain transfer agents that may also be used herein are typically a compound represented by the formula AlR_3 , ZnR_2 (where each R is, independently, a C_1 - C_8 aliphatic radical, preferably methyl, ethyl, propyl, butyl, pentyl, hexyl, octyl or an isomer thereof) or a combination thereof, such as diethyl zinc, trimethylaluminum, triisobutylaluminum, trioctylaluminum, or a combination thereof.

Supports

In some embodiments, the complexes described herein may be supported (with or without an activator) by any method effective to support other coordination catalyst systems, effective meaning that the catalyst so prepared can be used for oligomerizing or polymerizing olefin in a heterogeneous process. The catalyst precursor, activator, co-activator if needed, suitable solvent, and support may be added in any order or simultaneously. Typically, the complex and activator may be combined in solvent to form a solution. Then the support is added, and the mixture is stirred for 1 minute to 10 hours. The total solution volume may be greater than the pore volume of the support, but some embodiments limit the total solution volume below that needed to form a gel or slurry (about 90% to 400%, preferably about 100-200% of the pore volume). After stirring, the residual solvent is removed under vacuum, typically at ambient temperature and over 10-16 hours. But greater or lesser times and temperatures are possible.

The complex may also be supported absent the activator; in that case, the activator (and co-activator if needed) is added to a polymerization process's liquid phase. Additionally, two or more different complexes may be placed on the same support. Likewise, two or more activators or an activator and co-activator may be placed on the same support.

Suitable solid particle supports are typically comprised of polymeric or refractory oxide materials, each being preferably porous. Preferably, any support material that has an average particle size greater than 10 μm is suitable for use in this invention. Various embodiments select a porous support material, such as for example, talc, inorganic oxides, inorganic chlorides, for example, magnesium chloride and resinous support materials such as

polystyrene polyolefin or polymeric compounds or any other organic support material and the like. Some embodiments select inorganic oxide materials as the support material including Group-2, -3, -4, -5, -13, or -14 metal or metalloid oxides. Some embodiments select the catalyst support materials to include silica, alumina, silica-alumina, and their mixtures. Other
5 inorganic oxides may serve either alone or in combination with the silica, alumina, or silica-alumina. These are magnesia, titania, zirconia, and the like. Lewis acidic materials such as montmorillonite and similar clays may also serve as a support. In this case, the support can optionally double as the activator component; however, an additional activator may also be used.

10 The support material may be pretreated by any number of methods. For example, inorganic oxides may be calcined, chemically treated with dehydroxylating agents such as aluminum alkyls and the like, or both.

As stated above, polymeric carriers will also be suitable in accordance with the invention, see for example the descriptions in WO 95/15815 and US 5,427,991. The methods
15 disclosed may be used with the catalyst complexes, activators or catalyst systems of this invention to adsorb or absorb them on the polymeric supports, particularly if made up of porous particles, or may be chemically bound through functional groups bound to or in the polymer chains.

Useful supports typically have a surface area of from 10-700 m²/g, a pore volume of
20 0.1-4.0 cc/g and an average particle size of 10-500 μm. Some embodiments select a surface area of 50-500 m²/g, a pore volume of 0.5-3.5 cc/g, or an average particle size of 20-200 μm. Other embodiments select a surface area of 100-400 m²/g, a pore volume of 0.8-3.0 cc/g, and an average particle size of 30-100 μm. Useful supports typically have a pore size of 10-1000 Angstroms, alternatively 50-500 Angstroms, or 75-350 Angstroms.

25 The catalyst complexes described herein are generally deposited on the support at a loading level of 10-100 micromoles of complex per gram of solid support; alternately 20-80 micromoles of complex per gram of solid support; or 40-60 micromoles of complex per gram of support. But greater or lesser values may be used provided that the total amount of solid complex does not exceed the support's pore volume.

30 In an alternate embodiment, catalyst complexes and catalyst systems described herein may be present on a fluorided support, e.g., a support, desirably particulate and porous, which has been treated with at least one inorganic fluorine containing compound. For example, the fluorided support composition can be a silicon dioxide support wherein a portion of the silica

hydroxyl groups has been replaced with fluorine or fluorine containing compounds. For example, a useful support herein, is a silica support treated with ammonium hexafluorosilicate and/or ammonium tetrafluoroborate fluorine compounds. Typically the fluorine concentration present on the support is in the range of from 0.1 to 25 wt%, alternately
5 0.19 to 19 wt%, alternately from 0.6 to 3.5 wt%, based upon the weight of the support.

In an embodiment of the invention, the catalyst system comprises fluorided silica, alkylalumoxane activator, and the bridged group 4 transition metal compound, where the fluorided support has not been calcined at a temperature of 400°C or more.

The catalyst compound may be present on a support at 1 to 100 µmol/g supported
10 catalyst, preferably 20-60 µmol/g supported catalyst.

This invention also relates to metallocene catalyst compositions comprising the reaction product of at least three components: (1) one or more bridged metallocenes having one tetrahydroindacenyl group; (2) one or more alkylalumoxane activators; and (3) one or more fluorided support compositions, where the fluorided support composition has not been
15 calcined at 400°C or more, preferably the fluorided support composition has been calcined at a temperature of 100°C to 395°C, alternately 125°C to 350°C, alternately 150°C to 300°C.

Typically, the fluorided supports described herein are prepared by combining a solution of polar solvent (such as water) and fluorinating agent (such as SiF₄ or (NH₄)₂SiF₆) with a slurry of support (such as a toluene slurry of silica), then drying until it is free flowing,
20 and optionally, calcining (typically at temperatures over 100°C for at least 1 hour). The supports are then combined with activator(s) and catalyst compound (separately or together).

For more information on fluorided supports and methods to prepare them, please see USSN 62/149,799, filed April 20, 2015 (and all cases claiming priority to or the benefit of USSN 62/149,799); USSN 62/103372, filed January 14, 2015 (and all cases claiming priority
25 to or the benefit of USSN 62/103372); and PCT/US2015/067582, filed December 28, 2015 which are incorporated by reference herein.

Polymerization Processes

In embodiments herein, the invention relates to polymerization processes where monomer (such as ethylene), and optionally comonomer (such as hexene), are contacted with
30 a catalyst system comprising the result of the combination of an activator, optional support (such as a fluorided support), and a tetrahydroindacene compound, as described above. The catalyst compound, optional support and activator may be combined in any order, and are combined typically prior to contacting with the monomer.

Monomers useful herein include substituted or unsubstituted C₂ to C₄₀ alpha olefins, preferably C₂ to C₂₀ alpha olefins, preferably C₂ to C₁₂ alpha olefins, preferably ethylene, propylene, butene, pentene, hexene, heptene, octene, nonene, decene, undecene, dodecene and isomers thereof. In a preferred embodiment of the invention, the monomers comprises
5 ethylene and optional comonomers comprising one or more C₃ to C₄₀ olefins, preferably C₄ to C₂₀ olefins, or preferably C₆ to C₁₂ olefins. The C₃ to C₄₀ olefin monomers may be linear, branched, or cyclic. The C₃ to C₄₀ cyclic olefins may be strained or unstrained, monocyclic or polycyclic, and may optionally include heteroatoms and/or one or more functional groups.

Exemplary C₃ to C₄₀ comonomers include propylene, butene, pentene, hexene,
10 heptene, octene, nonene, decene, undecene, dodecene, norbornene, norbornadiene, dicyclopentadiene, cyclopentene, cycloheptene, cyclooctene, cyclooctadiene, cyclododecene, 7-oxanorbornene, 7-oxanorbornadiene, substituted derivatives thereof, and isomers thereof, preferably hexene, heptene, octene, nonene, decene, dodecene, cyclooctene, 1,5-cyclooctadiene, 1-hydroxy-4-cyclooctene, 1-acetoxy-4-cyclooctene, 5-methylcyclopentene,
15 cyclopentene, dicyclopentadiene, norbornene, norbornadiene, 5-ethylidene-2-norbornene, and their respective homologs and derivatives.

In a preferred embodiment, one or more dienes are present in the polymer produced herein at up to 10 wt%, preferably at 0.00001 to 1.0 wt%, preferably 0.002 to 0.5 wt%, even more preferably 0.003 to 0.2 wt%, based upon the total weight of the composition. In some
20 embodiments 500 ppm or less of diene is added to the polymerization, preferably 400 ppm or less, preferably or 300 ppm or less. In other embodiments at least 50 ppm of diene is added to the polymerization, or 100 ppm or more, or 150 ppm or more.

Preferred diolefin monomers useful in this invention include any hydrocarbon structure, preferably C₄ to C₃₀, having at least two unsaturated bonds, wherein at least two of
25 the unsaturated bonds are readily incorporated into a polymer by either a stereospecific or a non-stereospecific catalyst(s). It is further preferred that the diolefin monomers be selected from alpha, omega-diene monomers (i.e., di-vinyl monomers). More preferably, the diolefin monomers are linear di-vinyl monomers, most preferably those containing from 4 to 30 carbon atoms. Examples of preferred dienes include butadiene, pentadiene, hexadiene,
30 heptadiene, octadiene, nonadiene, decadiene, undecadiene, dodecadiene, tridecadiene, tetradecadiene, pentadecadiene, hexadecadiene, heptadecadiene, octadecadiene, nonadecadiene, icosadiene, heneicosadiene, docosadiene, tricosadiene, tetracosadiene, pentacosadiene, hexacosadiene, heptacosadiene, octacosadiene, nonacosadiene,

triacontadiene, particularly preferred dienes include 1,6-heptadiene, 1,7-octadiene, 1,8-nonadiene, 1,9-decadiene, 1,10-undecadiene, 1,11-dodecadiene, 1,12-tridecadiene, 1,13-tetradecadiene, and low molecular weight polybutadienes (Mw less than 1000 g/mol). Preferred cyclic dienes include cyclopentadiene, vinylnorbornene, norbornadiene, 5-ethylidene-2-norbornene, 5-vinyl-2-norbornene, divinylbenzene, dicyclopentadiene or higher
5 ring containing diolefins with or without substituents at various ring positions.

In a particularly preferred embodiment, the process of the invention relates to the polymerization of ethylene and at least one comonomer having from 3 to 8 carbon atoms, preferably 4 to 8 carbon atoms. Particularly, the comonomers are propylene, butene-1, 4-methyl-pentene-1, 3-methyl-pentene-1, hexene-1 and octene-1, the most preferred being
10 hexene-1, butene-1 and octene-1.

Polymerization processes of this invention can be carried out in any manner known in the art. Any suspension, homogeneous, bulk, solution, slurry, or gas phase polymerization process known in the art can be used. Such processes can be run in a batch, semi-batch, or
15 continuous mode. Gas phase polymerization processes and slurry processes are preferred. (A homogeneous polymerization process is defined to be a process where at least 90 wt% of the product is soluble in the reaction media.) A bulk homogeneous process is particularly preferred. (A bulk process is defined to be a process where monomer concentration in all feeds to the reactor is 70 vol% or more.) Alternately, no solvent or diluent is present or added
20 in the reaction medium, (except for the small amounts used as the carrier for the catalyst system or other additives, or amounts typically found with the monomer; e.g., propane in propylene). In another embodiment, the process is a slurry process. As used herein the term "slurry polymerization process" means a polymerization process where a supported catalyst is employed and monomers are polymerized on the supported catalyst particles. At least 95
25 wt% of polymer products derived from the supported catalyst are in granular form as solid particles (not dissolved in the diluent).

Suitable diluents/solvents for polymerization include non-coordinating, inert liquids. Examples include straight and branched-chain hydrocarbons, such as isobutane, butane, pentane, isopentane, hexanes, isohexane, heptane, octane, dodecane, and mixtures thereof;
30 cyclic and alicyclic hydrocarbons, such as cyclohexane, cycloheptane, methylcyclohexane, methylcycloheptane, and mixtures thereof, such as can be found commercially (Isopar™); perhalogenated hydrocarbons, such as perfluorinated C₄₋₁₀ alkanes, chlorobenzene, and aromatic and alkylsubstituted aromatic compounds, such as benzene, toluene, mesitylene, and

xylylene. Suitable solvents also include liquid olefins which may act as monomers or comonomers including ethylene, propylene, 1-butene, 1-hexene, 1-pentene, 3-methyl-1-pentene, 4-methyl-1-pentene, 1-octene, 1-decene, and mixtures thereof. In a preferred embodiment, aliphatic hydrocarbon solvents are used as the solvent, such as isobutane, butane, pentane, isopentane, hexanes, isohexane, heptane, octane, dodecane, and mixtures thereof; cyclic and alicyclic hydrocarbons, such as cyclohexane, cycloheptane, methylcyclohexane, methylcycloheptane, and mixtures thereof. In another embodiment, the solvent is not aromatic, preferably aromatics are present in the solvent at less than 1 wt%, preferably less than 0.5 wt%, preferably less than 0 wt% based upon the weight of the solvents.

In a preferred embodiment, the feed concentration of the monomers and comonomers for the polymerization is 60 vol% solvent or less, preferably 40 vol% or less, or preferably 20 vol% or less, based on the total volume of the feedstream. Preferably, the polymerization is run in a bulk process.

Preferred polymerizations can be run at any temperature and/or pressure suitable to obtain the desired polymers. Typical temperatures and/or pressures include a temperature in the range of from about 0°C to about 300°C, preferably about 20°C to about 200°C, preferably about 35°C to about 150°C, preferably from about 40°C to about 120°C, preferably from about 45°C to about 80°C; and at a pressure in the range of from about 0.35 MPa to about 16 MPa, preferably from about 0.45 MPa to about 13 MPa, or preferably from about 0.5 MPa to about 12 MPa.

In a typical polymerization, the run time of the reaction is up to 300 minutes, preferably in the range of from about 5 to 250 minutes, or preferably from about 10 to 120 minutes.

In some embodiments, hydrogen is present in the polymerization reactor at a partial pressure of 0.001 to 50 psig (0.007 to 345 kPa), preferably from 0.01 to 25 psig (0.07 to 172 kPa), more preferably 0.1 to 10 psig (0.7 to 70 kPa).

In an alternate embodiment, the activity of the catalyst is at least 800 gpolymer/gsupported catalyst/hour, preferably 1000 or more gpolymer/gsupported catalyst/hour, preferably 100 or more gpolymer/gsupported catalyst/hour, preferably 1600 or more gpolymer/gsupported catalyst/hour.

In a preferred embodiment, little or no scavenger is used in the process to produce the ethylene polymer. Preferably, scavenger (such as tri alkyl aluminum) is present at zero mol%,

alternately the scavenger is present at a molar ratio of scavenger metal to transition metal of less than 100:1, preferably less than 50:1, preferably less than 15:1, preferably less than 10:1.

In a preferred embodiment, the polymerization: 1) is conducted at temperatures of 0°C to 300°C (preferably 25°C to 150°C, preferably 40°C to 120°C, preferably 45°C to 80°C); 2) is conducted at a pressure of atmospheric pressure to 16 MPa (preferably 0.35 to 14 MPa, preferably from 0.45 to 12 MPa, preferably from 0.5 to 6 MPa); 3) is conducted in an aliphatic hydrocarbon solvent (such as isobutane, butane, pentane, isopentane, hexanes, isohexane, heptane, octane, dodecane, and mixtures thereof; cyclic and alicyclic hydrocarbons, such as cyclohexane, cycloheptane, methylcyclohexane, methylcycloheptane, and mixtures thereof; preferably where aromatics are preferably present in the solvent at less than 1 wt%, preferably less than 0.5 wt%, preferably at 0 wt% based upon the weight of the solvents); 4) the polymerization preferably occurs in one reaction zone; and 5) optionally, hydrogen is present in the polymerization reactor at a partial pressure of 0.001 to 50 psig (0.007 to 345 kPa) (preferably from 0.01 to 25 psig (0.07 to 172 kPa), more preferably 0.1 to 10 psig (0.7 to 70 kPa)).

A “reaction zone” also referred to as a “polymerization zone” is a vessel where polymerization takes place, for example a batch reactor. When multiple reactors are used in either series or parallel configuration, each reactor is considered as a separate polymerization zone. For a multi-stage polymerization in both a batch reactor and a continuous reactor, each polymerization stage is considered as a separate polymerization zone. In a preferred embodiment, the polymerization occurs in one reaction zone.

Gas phase polymerization

Generally, in a fluidized gas bed process used for producing polymers, a gaseous stream containing one or more monomers is continuously cycled through a fluidized bed in the presence of a catalyst under reactive conditions. The gaseous stream is withdrawn from the fluidized bed and recycled back into the reactor. Simultaneously, polymer product is withdrawn from the reactor and fresh monomer is added to replace the polymerized monomer. (See for example US 4,543,399; US 4,588,790; US 5,028,670; US 5,317,036; US 5,352,749; US 5,405,922; US 5,436,304; US 5,453,471; US 5,462,999; US 5,616,661; and US 5,668,228, all of which are fully incorporated herein by reference.)

Slurry phase polymerization

A slurry polymerization process generally operates between 1 to about 50 atmosphere pressure range (15 psi to 735 psi, 103 kPa to 5068 kPa) or even greater and temperatures in

the range of 0°C to about 120°C. In a slurry polymerization, a suspension of solid, particulate polymer is formed in a liquid polymerization diluent medium to which monomer and comonomers along with catalyst are added. The suspension including diluent is intermittently or continuously removed from the reactor where the volatile components are separated from the polymer and recycled, optionally after a distillation, to the reactor. The liquid diluent employed in the polymerization medium is typically an alkane having from 3 to 7 carbon atoms, preferably a branched alkane. The medium employed should be liquid under the conditions of polymerization and relatively inert. When a propane medium is used the process must be operated above the reaction diluent critical temperature and pressure. Preferably, a hexane or an isobutane medium is employed.

In an embodiment, a preferred polymerization technique useful in the invention is referred to as a particle form polymerization, or a slurry process where the temperature is kept below the temperature at which the polymer goes into solution. Such technique is well known in the art, and described in for instance US 3,248,179 which is fully incorporated herein by reference. The preferred temperature in the particle form process is within the range of about 85°C to about 110°C. Two preferred polymerization methods for the slurry process are those employing a loop reactor and those utilizing a plurality of stirred reactors in series, parallel, or combinations thereof. Non-limiting examples of slurry processes include continuous loop or stirred tank processes. Also, other examples of slurry processes are described in US 4,613,484, which is herein fully incorporated by reference.

In another embodiment, the slurry process is carried out continuously in a loop reactor. The catalyst, as a slurry in isobutane or as a dry free flowing powder, is injected regularly to the reactor loop, which is itself filled with circulating slurry of growing polymer particles in a diluent of isobutane containing monomer and comonomer. Hydrogen, optionally, may be added as a molecular weight control. (In one embodiment 500 ppm or less of hydrogen is added, or 400 ppm or less or 300 ppm or less. In other embodiments at least 50 ppm of hydrogen is added, or 100 ppm or more, or 150 ppm or more.)

The reactor may be maintained at a pressure of 3620 kPa to 4309 kPa and at a temperature in the range of about 60°C to about 104°C depending on the desired polymer melting characteristics. Reaction heat is removed through the loop wall since much of the reactor is in the form of a double-jacketed pipe. The slurry is allowed to exit the reactor at regular intervals or continuously to a heated low pressure flash vessel, rotary dryer and a nitrogen purge column in sequence for removal of the isobutane diluent and all unreacted

monomer and comonomers. The resulting hydrocarbon free powder is then compounded for use in various applications.

Other additives may also be used in the polymerization, as desired, such as one or more scavengers, promoters, modifiers, chain transfer agents (such as diethyl zinc), reducing
5 agents, oxidizing agents, hydrogen, aluminum alkyls, or silanes.

Useful chain transfer agents are typically alkylalumoxanes, a compound represented by the formula AlR_3 , ZnR_2 (where each R is, independently, a C_1 - C_8 aliphatic radical, preferably methyl, ethyl, propyl, butyl, pentyl, hexyl octyl or an isomer thereof) or a combination thereof, such as diethyl zinc, methylalumoxane, trimethylaluminum,
10 triisobutylaluminum, trioctylaluminum, or a combination thereof.

Polyolefin Products

This invention also relates to compositions of matter produced by the methods described herein.

In a preferred embodiment, the process described herein produces ethylene
15 homopolymers or ethylene copolymers, such as ethylene-alphaolefin (preferably C_3 to C_{20}) copolymers (such as ethylene-butene copolymers, ethylene-hexene and/or ethylene-octene copolymers) having: a Mw/Mn of greater than 1 to 4 (preferably greater than 1 to 3).

Likewise, the process of this invention produces ethylene copolymers. In a preferred embodiment, the copolymers produced herein have from 0 to 25 mol% (alternately from 0.5
20 to 20 mol%, alternately from 1 to 15 mol%, preferably from 3 to 10 mol%) of one or more C_3 to C_{20} olefin comonomer (preferably C_3 to C_{12} alpha-olefin, preferably propylene, butene, hexene, octene, decene, dodecene, preferably propylene, butene, hexene, octene).

In a preferred embodiment, the monomer is ethylene and the comonomer is hexene, preferably from 1 to 15 mol% hexene, alternately 1 to 10 mol%.

25 Typically, the polymers produced herein have an Mw of 5,000 to 1,000,000 g/mol (preferably 25,000 to 750,000 g/mol, preferably 50,000 to 500,000 g/mol), and/or an Mw/Mn of greater than 1 to 40 (alternately 1.2 to 20, alternately 1.3 to 10, alternately 1.4 to 5, 1.5 to 4, alternately 1.5 to 3).

In a preferred embodiment, the polymer produced herein has a unimodal or
30 multimodal molecular weight distribution as determined by Gel Permeation Chromatography (GPC). By "unimodal" is meant that the GPC trace has one peak or inflection point. By "multimodal" is meant that the GPC trace has at least two peaks or inflection points. An

inflection point is that point where the second derivative of the curve changes in sign (e.g., from negative to positive or vice versa).

Unless otherwise indicated M_w , M_n and M_w/M_n are determined by using a High Temperature Gel Permeation Chromatography (Agilent PL-220), equipped with three in-line
 5 detectors, a differential refractive index detector (DRI), a light scattering (LS) detector, and a viscometer. Experimental details, including detector calibration, are described in: T. Sun, P. Brant, R. R. Chance, and W. W. Graessley, *Macromolecules*, Volume 34, Number 19, pp. 6812-6820, (2001) and references therein. Three Agilent PLgel 10 μ m Mixed-B LS columns are used. The nominal flow rate is 0.5 mL/min, and the nominal injection volume is 300 μ L.
 10 The various transfer lines, columns, viscometer and differential refractometer (the DRI detector) are contained in an oven maintained at 145°C. Solvent for the experiment is prepared by dissolving 6 grams of butylated hydroxytoluene as an antioxidant in 4 liters of Aldrich reagent grade 1,2,4-trichlorobenzene (TCB). The TCB mixture is then filtered through a 0.1 μ m Teflon filter. The TCB is then degassed with an online degasser before
 15 entering the GPC-3D. Polymer solutions are prepared by placing dry polymer in a glass container, adding the desired amount of TCB, then heating the mixture at 160°C with continuous shaking for about 2 hours. All quantities are measured gravimetrically. The TCB densities used to express the polymer concentration in mass/volume units are 1.463 g/ml at room temperature and 1.284 g/ml at 145°C. The injection concentration is from 0.5 to 2.0
 20 mg/ml, with lower concentrations being used for higher molecular weight samples. Prior to running each sample the DRI detector and the viscometer are purged. Flow rate in the apparatus is then increased to 0.5 ml/minute, and the DRI is allowed to stabilize for 8 hours before injecting the first sample. The LS laser is turned on at least 1 to 1.5 hours before running the samples. The concentration, c , at each point in the chromatogram is calculated
 25 from the baseline-subtracted DRI signal, I_{DRI} , using the following equation:

$$c = K_{DRI} I_{DRI} / (dn/dc)$$

where K_{DRI} is a constant determined by calibrating the DRI, and (dn/dc) is the refractive index increment for the system. The refractive index, $n = 1.500$ for TCB at 145°C and $\lambda = 690$ nm. Units on parameters throughout this description of the GPC-3D method are such
 30 that concentration is expressed in g/cm³, molecular weight is expressed in g/mole, and intrinsic viscosity is expressed in dL/g.

The LS detector is a Wyatt Technology High Temperature DAWN HELEOS. The molecular weight, M , at each point in the chromatogram is determined by analyzing the LS

output using the Zimm model for static light scattering (M.B. Huglin, LIGHT SCATTERING FROM POLYMER SOLUTIONS, Academic Press, 1971):

$$\frac{K_o c}{\Delta R(\theta)} = \frac{1}{MP(\theta)} + 2A_2 c$$

Here, $\Delta R(\theta)$ is the measured excess Rayleigh scattering intensity at scattering angle θ ,
 5 c is the polymer concentration determined from the DRI analysis, A_2 is the second virial coefficient. $P(\theta)$ is the form factor for a monodisperse random coil, and K_o is the optical constant for the system:

$$K_o = \frac{4\pi^2 n^2 (dn/dc)^2}{\lambda^4 N_A}$$

where N_A is Avogadro's number, and (dn/dc) is the refractive index increment for the system,
 10 which take the same value as the one obtained from DRI method. The refractive index, $n = 1.500$ for TCB at 145°C and $\lambda = 690 \text{ nm}$.

A high temperature Viscotek Corporation viscometer, which has four capillaries arranged in a Wheatstone bridge configuration with two pressure transducers, is used to determine specific viscosity. One transducer measures the total pressure drop across the
 15 detector, and the other, positioned between the two sides of the bridge, measures a differential pressure. The specific viscosity, η_s , for the solution flowing through the viscometer is calculated from their outputs. The intrinsic viscosity, $[\eta]$, at each point in the chromatogram is calculated from the following equation:

$$\eta_s = c[\eta] + 0.3(c[\eta])^2$$

20 where c is concentration and was determined from the DRI output. All molecular weights are weight average unless otherwise noted. All molecular weights are reported in g/mol unless otherwise noted.

In a preferred embodiment, the polymer produced herein has a composition distribution breadth index (CDBI) of 50% or more, preferably 60% or more, preferably 70%
 25 or more. CDBI is a measure of the composition distribution of monomer within the polymer chains and is measured by the procedure described in PCT publication WO 93/03093, published February 18, 1993, specifically columns 7 and 8 as well as in Wild et al, J. Poly. Sci., Poly. Phys. Ed., Vol. 20, p. 441 (1982) and US 5,008,204, including that fractions having a weight average molecular weight (M_w) below 15,000 are ignored when determining
 30 CDBI.

In another embodiment, the polymer produced herein has two peaks in the TREF measurement (see below). Two peaks in the TREF measurement as used in this specification and the appended claims means the presence of two distinct normalized ELS (evaporation mass light scattering) response peaks in a graph of normalized ELS response (vertical or y axis) versus elution temperature (horizontal or x axis with temperature increasing from left to right) using the TREF method below. A “peak” in this context means where the general slope of the graph changes from positive to negative with increasing temperature. Between the two peaks is a local minimum in which the general slope of the graph changes from negative to positive with increasing temperature. “General trend” of the graph is intended to exclude the multiple local minimums and maximums that can occur in intervals of 2°C or less. Preferably, the two distinct peaks are at least 3°C apart, more preferably at least 4°C apart, even more preferably at least 5°C apart. Additionally, both of the distinct peaks occur at a temperature on the graph above 20°C and below 120°C where the elution temperature is run to 0°C or lower. This limitation avoids confusion with the apparent peak on the graph at low temperature caused by material that remains soluble at the lowest elution temperature. Two peaks on such a graph indicates a bi-modal composition distribution (CD). Bimodal CD may also be determined by other methods known to those skilled in the art. One such alternate method for TREF measurement then can be used if the above method does not show two peaks is disclosed in B. Monrabal, “Crystallization Analysis Fractionation: A New Technique for the Analysis of Branching Distribution in Polyolefins,” *Journal of Applied Polymer Science*, Vol. 52, 491–499 (1994).

TREF Method

Temperature Rising Elution Fractionation (TREF) analysis is done using a CRYSTAF-TREF 200+ instrument from Polymer Char, S.A., Valencia, Spain. The principles of TREF analysis and a general description of the particular apparatus to be used are given in the article Monrabal, B.; del Hierro, P. *Anal. Bioanal. Chem.*, 2011, 399, 1557. Fig. 3 of the article is an appropriate schematic of the particular apparatus used; however, the connections to the 6-port valve shown in Fig. 3 differ from the apparatus to be used in that the tubing connected to the 11-o'clock port is connected to the 9-o'clock port and the tubing connected to the 9-o'clock port is connected to the 11-o'clock port. Pertinent details of the analysis method and features of the apparatus to be used are as follows.

1,2-Dichlorobenzene (ODCB) solvent stabilized with approximately 380 ppm of 2,6-bis(1,1-dimethylethyl)-4-methylphenol (butylated hydroxytoluene) is used for preparing the

sample solution and for elution. The sample to be analyzed (approximately 25 mg but as low as approximately 10 mg) is dissolved in ODCB (25 ml metered at ambient temperature) by stirring at 150°C for 60 min. A small volume (0.5 ml) of the solution is introduced into a column (15-cm long by 3/8" o.d.) packed with an inert support (of stainless steel balls) at 5 150°C, and the column temperature is stabilized at 140°C for 45 min. The sample volume is then allowed to crystallize in the column by reducing the temperature to 30°C at a cooling rate of 1°C/min. The column is kept at 30°C for 15 min before injecting the ODCB flow (1 ml/min) into the column for 10 min to elute and measure the polymer that did not crystallize (soluble fraction). The infrared detector used (Polymer Char IR4) generates an 10 absorbance signal that is proportional to the concentration of polymer in the eluting flow. A complete TREF curve is then generated by increasing the temperature of the column from 30 to 140°C at a rate of 2°C/min while maintaining the ODCB flow at 1 ml/min to elute and measure the dissolving polymer.

Blends

15 In another embodiment, the polymer produced herein is combined with one or more additional polymers prior to being formed into a film, molded part or other article. Other useful polymers include polyethylene, isotactic polypropylene, highly isotactic polypropylene, syndiotactic polypropylene, random copolymer of propylene and ethylene, and/or butene, and/or hexene, polybutene, ethylene vinyl acetate, LDPE, LLDPE, HDPE, ethylene vinyl 20 acetate, ethylene methyl acrylate, copolymers of acrylic acid, polymethylmethacrylate or any other polymers polymerizable by a high-pressure free radical process, polyvinylchloride, polybutene-1, isotactic polybutene, ABS resins, ethylene-propylene rubber (EPR), vulcanized EPR, EPDM, block copolymer, styrenic block copolymers, polyamides, polycarbonates, PET resins, cross linked polyethylene, copolymers of ethylene and vinyl alcohol (EVOH), 25 polymers of aromatic monomers such as polystyrene, poly-1 esters, polyacetal, polyvinylidene fluoride, polyethylene glycols, and/or polyisobutylene.

In a preferred embodiment, the polymer (preferably the polyethylene produced herein) is present in the above blends, at from 10 to 99 wt%, based upon the weight of the polymers in the blend, preferably 20 to 95 wt%, even more preferably at least 30 to 90 wt%, even more 30 preferably at least 40 to 90 wt%, even more preferably at least 50 to 90 wt%, even more preferably at least 60 to 90 wt%, even more preferably at least 70 to 90 wt%.

Additionally, additives may be included in the blend, in one or more components of the blend, and/or in a product formed from the blend, such as a film, as desired. Such

additives are well known in the art, and can include, for example: fillers; antioxidants (e.g., hindered phenolics such as IRGANOX™ 1010 or IRGANOX™ 1076 available from Ciba-Geigy); phosphites (e.g., IRGAFOS™ 168 available from Ciba-Geigy); anti-cling additives; tackifiers, such as polybutenes, terpene resins, aliphatic and aromatic hydrocarbon resins, alkali metal and glycerol stearates, and hydrogenated rosins; UV stabilizers; heat stabilizers; anti-blocking agents; release agents; anti-static agents; pigments; colorants; dyes; waxes; silica; fillers; talc; and the like.

Films

Specifically, any of the foregoing polymers, such as the foregoing ethylene copolymers or blends thereof, may be used in a variety of end-use applications. Such applications include, for example, mono- or multi-layer blown, extruded, and/or shrink films. These films may be formed by any number of well known extrusion or coextrusion techniques, such as a blown bubble film processing technique, wherein the composition can be extruded in a molten state through an annular die and then expanded to form a uni-axial or biaxial orientation melt prior to being cooled to form a tubular, blown film, which can then be axially slit and unfolded to form a flat film. Films may be subsequently unoriented, uniaxially oriented, or biaxially oriented to the same or different extents. One or more of the layers of the film may be oriented in the transverse and/or longitudinal directions to the same or different extents. The uniaxially orientation can be accomplished using typical cold drawing or hot drawing methods. Biaxial orientation can be accomplished using tenter frame equipment or a double bubble processes and may occur before or after the individual layers are brought together. For example, a polyethylene layer can be extrusion coated or laminated onto an oriented polypropylene layer or the polyethylene and polypropylene can be coextruded together into a film then oriented. Likewise, oriented polypropylene could be laminated to oriented polyethylene or oriented polyethylene could be coated onto polypropylene then optionally the combination could be oriented even further. Typically the films are oriented in the Machine Direction (MD) at a ratio of up to 15, preferably between 5 and 7, and in the Transverse Direction (TD) at a ratio of up to 15, preferably 7 to 9. However, in another embodiment, the film is oriented to the same extent in both the MD and TD directions.

The films may vary in thickness depending on the intended application; however, films of a thickness from 1 to 50 μm are usually suitable. Films intended for packaging are usually from 10 to 50 μm thick. The thickness of the sealing layer is typically 0.2 to 50 μm .


There may be a sealing layer on both the inner and outer surfaces of the film or the sealing layer may be present on only the inner or the outer surface.







- In another embodiment, one or more layers may be modified by corona treatment, electron beam irradiation, gamma irradiation, flame treatment, or microwave. In a preferred
- 5 embodiment, one or both of the surface layers is modified by corona treatment.



Experimental


Room temperature is 23°C unless otherwise noted.

The inventive pre-catalysts are illustrated below:












C




E




B




D




A




F




I




L




H



K



G




J

Starting Reagents: Diethyl malonate (Acros), diethyl methylmalonate (Acros), iodomethane (Acros), iodoethane (Acros), bromoethane (Merck), 1,2-bis(bromomethyl)benzene (Aldrich), methylmagnesium bromide solution in ether (Aldrich), n-butyllithium solution in hexanes (Chemetal), sodium borohydride (Aldrich), TsOH (Aldrich), $\text{ZrCl}_4(\text{THF})_2$ (Aldrich), $\text{HfCl}_4(\text{THF})_2$ (Aldrich), CuCN (Merck), sodium metal (Merck), Na_2CO_3 (Merck), K_2CO_3 (Merck), AlCl_3 (Merck), thionyl chloride (Merck), silica gel 60, 40-63 μm (Merck), potassium *tert*-butoxide (Acros), hydrazine hydrate (Acros), 12 M HCl (Merck), KOH (Merck), 96% ethanol (Merck), anhydrous ethanol (Merck), methanol (Merck), ethyleneglycol (Acros), dichloromethane (Merck), benzene (Merck), and CDCl_3 (Deutero GmbH) were used as received. Dichlorodimethylsilane (Merck) and 1,2-dichlorotetramethyldisilane (Aldrich) were distilled before use. THF and diethyl ether (both Merck) for organometallic synthesis were distilled over sodium benzophenone ketyl. Toluene, n-hexane, and n-octane (all Merck) for organometallic synthesis as well as CDCl_3 and CD_2Cl_2 (both Deutero GmbH) for NMR analysis of air- and moisture-sensitive compounds were dried over molecular sieves 4A (Acros) and flashed by dry argon before use. 1,1-Dichlorosilolane was obtained from 1,4-dibromobutane (Acros), magnesium turnings (Acros), and silicon tetrachloride (Merck) as described in [Mironov, V. F.; Nepomnina, V. V. *Izv. Akad. Nauk SSSR, Ser. Khim.*, 1959, 1231].

Tetrahydro-*as*-indacene Ligand Synthesis:

20 Example 1: Synthesis of 2,2,7-Trimethyl-1,2,3,6-tetrahydro-*as*-indacene
2-Methyl-3-(2-methyl-1-oxo-2,3-dihydro-1*H*-inden-4-yl)propanoic acid




In a three-necked round-bottom flask, 46.0 g (2.0 mol) of sodium metal was dissolved in 1100 ml of dry ethanol. To the resulting solution 348.5 g (2.0 mol) of diethyl methylmalonate was added. This mixture was stirred for 15 min., then 264 g (1.0 mol) of 1,2-bis(bromomethyl)benzene was added in several portions to maintain a gentle reflux. This mixture was refluxed for an additional 3 h and then cooled to room temperature. A solution of 411 g of KOH in 1200 ml of water was added. The resulting mixture was refluxed for 6 h to saponify the ester formed. Ethanol and water were distilled off until temperature reached

95°C, and 4 L of water and then 12 M HCl (to pH 1) were added to the residue. The precipitated acid was filtered off, washed with 3 x 500 ml of cold water, and then decarboxylated at 200°C to give 3,3'-(1,2-phenylene)bis(2-methylpropanoic acid).

¹H NMR (CDCl₃): δ 11.4 (bs, 2H), 7.16 (s, 4H), 3.20-3.11 (m, 2H), 2.79-2.63 (m, 4H), 1.2 (d, 6H, *J* = 6.6 Hz). ¹³C{¹H} NMR (CDCl₃): δ 182.78, 137.29, 129.92, 129.85, 126.61, 40.66, 40.62, 35.66, 16.63, 16.57.

A mixture of this acid and 511 ml of thionyl chloride was stirred at room temperature for 24 h. An excess of thionyl chloride was distilled off, the residue was dried in vacuum to give crude 3,3'-(1,2-phenylene)bis(2-methylpropanoyl chloride) which was further used without an additional purification. To a stirred suspension of 166.5 g (1.25 mol) of AlCl₃ in 1200 ml of dichloromethane cooled to 0°C, a solution of 3,3'-(1,2-phenylene)bis(2-methylpropanoyl chloride) in 200 ml of dichloromethane was added dropwise with vigorous stirring. This mixture was stirred overnight at room temperature and then poured on 2 kg of ice. The organic layer was separated, and the aqueous layer was additionally extracted with 3 x 250 ml of dichloromethane. The combined organic extract was evaporated to dryness, and the residue was dissolved in a cold solution of 100 g KOH in 1200 ml water. The obtained mixture was extracted with 2 x 200 ml of ether, then, acidified with 12 M HCl to pH 1. The resulting mixture was extracted with 3 x 400 ml of dichloromethane. The combined organic extract was passed through a short pad of silica gel 60 (40-63 μm), and the obtained filtrate was evaporated to dryness to give 147.5 g (63.5% yield) of a mixture of diastereomers of 2-methyl-3-(2-methyl-1-oxo-2,3-dihydro-1*H*-inden-4-yl)propanoic acid, a yellow oil which was further used without an additional purification.


¹H NMR (CDCl₃): δ 10.2 (br.s, 1H), 7.65 (d, *J* = 7.6 Hz, 1H), 7.43 (d, *J* = 7.6 Hz, 1H), 7.33 (t, *J* = 7.6 Hz, 1H), 3.45-3.30 (m, 1H), 3.19-3.08 (m, 1H), 2.90-2.79 (m, 1H), 2.79-2.59 (m, 3H), 1.32 (d, *J* = 7.3 Hz, 3H), 1.31 (d, *J* = 7.3 Hz, 3H), 1.25 (d, *J* = 6.8 Hz, 3H). ¹³C{¹H} NMR (CDCl₃): δ 209.79, 181.54, 181.50, 152.27, 136.86, 136.46, 134.93, 127.76, 122.35, 41.87, 39.84, 35.23, 33.60, 16.86, 16.29.

Methyl 2-methyl-3-(2-methyl-1-oxo-2,3-dihydro-1H-inden-4-yl)propanoate

To a solution of 408 g (1.76 mol) of 2-methyl-3-(2-methyl-1-oxo-2,3-dihydro-1H-inden-4-yl)propanoic acid in 1400 ml of methanol cooled to 0°C 154 ml (251 g, 2.11 mol, 1.2 equiv) of thionyl chloride was added dropwise for 2 h. This mixture was allowed to reach room temperature and then refluxed for 0.5 h. The obtained mixture was evaporated on Rotavapor, the residue was dissolved in 1000 ml of dichloromethane. This solution was washed with aqueous K₂CO₃, dried over K₂CO₃, and then evaporated to dryness to give a yellowish oil. This oil was rectified in vacuum to give 335 g (78% yield) of a mixture of two diastereomers of methyl 2-methyl-3-(2-methyl-1-oxo-2,3-dihydro-1H-inden-4-yl)propanoate as a yellowish oil, b.p. 162°C/3 mm Hg.

Anal. calc. for C₁₅H₁₈O₃: C, 73.15; H, 7.37. Found: C, 73.56; H, 7.61

¹H NMR (CDCl₃): δ 7.62 (d, *J* = 7.6 Hz, 1H), 7.39 (d, *J* = 7.6 Hz, 1H), 7.31 (t, *J* = 7.6 Hz, 1H), 3.63 (s, 3H), 3.42-3.32 (m, 1H), 3.12-3.07 (m, 1H), 2.86-2.61 (m, 4H), 1.32 (2d, *J* = 6.6 Hz, 3H), 1.21 (2d, *J* = 6.6 Hz, 3H). ¹³C{¹H} NMR (CDCl₃): δ 209.37, 176.14, 152.12, 137.15, 136.52, 134.81, 127.67, 122.20, 51.66, 41.92, 41.88, 40.00, 39.97, 35.64, 33.62, 17.11, 17.08, 16.31, 16.27.


3-(2,2-Dimethyl-1-oxo-2,3-dihydro-1H-inden-4-yl)-2-methylpropanoic acid

To a mixture of 335 g (1.36 mol) of methyl 2-methyl-3-(2-methyl-1-oxo-2,3-dihydro-1H-inden-4-yl)propanoate and 232 g (1.63 mol, 1.2 equiv) of methyl iodide cooled to 0°C, a solution of 183 g (1.63 mol, 1.2 equiv) of *t*BuOK in 1200 ml of THF was added dropwise for 4 h, and the reaction mixture was then stirred overnight at room temperature. Further on, this mixture was evaporated on Rotavapor. To the residue a solution of 150 g of KOH in a mixture of 800 ml of water and 250 ml of methanol was added. The resulting mixture was refluxed for 4 h to saponify the ester. Further on, methanol and water were distilled off

until temperature reached 95°C, and 3 L of water and then 12 M HCl (to pH 1) were added to the residue. Crude product was extracted with 500 ml of dichloromethane. The aqueous phase was additionally extracted with 3 x 250 ml of dichloromethane. The combined organic extract was evaporated to dryness, and the residue was re-crystallized from a ca. 5:1 (vol.) mixture of hexane and benzene to give 296 g (88% yield) of 3-(2,2-dimethyl-1-oxo-2,3-dihydro-1*H*-inden-4-yl)-2-methylpropanoic acid.

¹H NMR (CDCl₃): δ 10.5 (br.s, 1H), 7.66 (d, *J* = 7.6 Hz, 1H), 7.44 (d, *J* = 7.6 Hz, 1H), 7.34 (t, *J* = 7.6 Hz, 1H), 3.12 (dd, *J* = 13.6 Hz, *J* = 6.8 Hz, 1H), 3.03-2.89 (m, 2H), 2.83 (m, 1H), 2.72 (dd, *J* = 13.6 Hz, *J* = 7.8 Hz, 1H), 1.25 (d, *J* = 6.8 Hz, 3H), 1.25 (s, 3H), 1.24 (s, 3H). ¹³C{¹H} NMR (CDCl₃): δ 211.67, 181.80, 150.98, 136.87, 135.44, 135.06, 127.84, 122.83, 45.45, 41.54, 39.92, 35.22, 25.27, 16.86.

3-(2,2-Dimethyl-2,3-dihydro-1*H*-inden-4-yl)-2-methylpropionyl chloride



To a solution of 296 g (1.2 mol) of 3-(2,2-dimethyl-1-oxo-2,3-dihydro-1*H*-inden-4-yl)-2-methylpropanoic acid in a mixture of 260 g (~4.6 mol) of KOH and 2500 ml of ethylene glycol, 252 ml of hydrazine hydrate was added. The reaction mixture was refluxed for 5 h. Then, the reflux condenser was replaced by a Claisen distillation head with a Liebig condenser, and a mixture of water, hydrazine hydrate, and ethylene glycol was slowly distilled off until the distillation temperature reached 195°C. The residue was then allowed to cool to room temperature, poured into 5 L of water, acidified with 12 M HCl to pH=1, and crude product was extracted with 1 liter of dichloromethane. The aqueous phase was additionally extracted with 2 x 500 ml of dichloromethane. The combined organic extract was washed with 1 L of water and evaporated to dryness to give 3-(2,2-dimethyl-2,3-dihydro-1*H*-inden-4-yl)-2-methylpropanoic acid as a red viscous oil.


¹H NMR (CDCl₃): δ 11.0 (br.s, 1H), 7.1-7.0 (m, 2H), 6.94 (d, *J* = 7.1 Hz, 1H), 3.02 (dd, *J* = 13.5 Hz, *J* = 6.2 Hz, 1H), 2.79-2.64 (m, 5H), 2.59 (dd, *J* = 13.5 Hz, *J* = 8.4 Hz, 1H), 1.17 (d, *J* = 7.1 Hz, 3H), 1.14 (s, 6H). ¹³C{¹H} NMR (CDCl₃): δ 182.86, 143.75, 142.33, 135.09, 126.71, 126.27, 122.92, 47.86, 46.18, 40.27, 39.71, 36.76, 28.83, 16.49.

A mixture of the above-obtained acid and 307 ml (501 g, 4.21 mol) of thionyl chloride was stirred for 24 h at room temperature. An excess of thionyl chloride was distilled off, the

residue was distilled in vacuum to give 270 g [90% yield from 3-(2,2-dimethyl-1-oxo-2,3-dihydro-1*H*-inden-4-yl)-2-methylpropanoic acid] of 3-(2,2-dimethyl-2,3-dihydro-1*H*-inden-4-yl)-2-methylpropionyl chloride, b.p. 138-150°C/2 mm Hg.

¹H NMR (CDCl₃): δ 7.15-7.0 (m, 2H), 6.93 (d, *J* = 7.1 Hz, 1H), 3.19-3.06 (m, 2H), 2.77-2.6 (m, 5H), 1.27 (d, *J* = 7.07 Hz, 3H), 1.16 (s, 3H), 1.15 (s, 3H). ¹³C{¹H} NMR (CDCl₃): δ 177.19, 144.04, 142.31, 133.64, 126.75, 126.49, 123.39, 52.25, 47.80, 46.19, 39.84, 36.71, 28.80, 16.59.

2,7,7-Trimethyl-1,6,7,8-tetrahydro-*as*-indacen-3(2*H*)-one




To a suspension of 173 g (1.29 mol, 1.2 eq.) of AlCl₃ in 1000 ml of dichloromethane cooled to 0°C, a solution of 270 g (1.08 mol) of 3-(2,2-dimethyl-2,3-dihydro-1*H*-inden-4-yl)-2-methylpropionyl chloride in 2500 ml of dichloromethane was added for 1 h. The cooling bath was then removed, and the solution was stirred overnight at room temperature. The reaction mixture was poured into 2 kg of crushed ice, the organic phase was separated, and the aqueous phase was extracted by 3 x 500 ml of dichloromethane. The combined organic extract was washed with aqueous K₂CO₃, dried over K₂CO₃, passed through a short pad of silica gel 60 (40-63 μm), and the elute was evaporated to dryness. The residue was rectified in vacuum to give 223 g (97% yield) of 2,7,7-trimethyl-1,6,7,8-tetrahydro-*as*-indacen-3(2*H*)-one as a yellowish oil which crystallizes at room temperature, b.p. 137°C-138°C/1 mm Hg.

Anal. calc. for C₁₅H₁₈O: C, 84.07; H, 8.47. Found: C, 84.42; H, 8.69.

¹H NMR (CDCl₃): δ 7.57 (d, *J* = 7.6 Hz, 1H), 7.18 (d, *J* = 7.6 Hz, 1H), 3.24 (dd, *J* = 17.2 Hz, *J* = 7.8 Hz, 1H), 2.80 (s, 2H), 2.71 (s, 2H), 2.75-2.65 (m, 1H), 2.56 (dd, *J* = 17.2 Hz, *J* = 3.5 Hz, 1H), 1.31 (d, *J* = 7.6 Hz, 3H), 1.20 (s, 3H), 1.18 (s, 3H). ¹³C{¹H} NMR (CDCl₃): δ 209.31, 151.10, 149.82, 140.60, 134.81, 123.97, 122.22, 48.12, 44.86, 42.13, 40.34, 33.48, 28.90, 16.46.

2,2,7-Trimethyl-1,2,3,6-tetrahydro-*as*-indacene (illustrated as the 2,2,7-trimethyl-1,2,3,8-tetrahydro-*as*-indacene isomer)




To a solution of 94.9 g (442.8 mmol) of 2,7,7-trimethyl-1,6,7,8-tetrahydro-*as*-indacen-3(2*H*)-one in 440 ml of THF cooled to 5°C 25.1 g (664 mmol) of NaBH₄ was added. Further on, 220 ml of methanol was added dropwise to this vigorously stirred mixture for ca. 5 h at 5°C. The resulting mixture was stirred for 3 h at room temperature, then evaporated to dryness, and the residue was partitioned between 500 ml of dichloromethane and 500 ml of 2 M HCl. The organic layer was separated, and the aqueous layer was additionally extracted with 100 ml of dichloromethane. The combined organic extract was evaporated to dryness. To a solution of the residue in 900 ml of toluene 1 g of TsOH was added, and this mixture was refluxed with Dean-Stark head for 20 min., then cooled to room temperature using a water bath. The resulting solution was washed by 10% Na₂CO₃. The organic layer was separated, and the aqueous layer was extracted with 2 x 100 ml of dichloromethane. The combined organic extract was dried over K₂CO₃ and then passed through a short pad of silica gel 60 (40-63 µm). The silica gel pad was additionally washed by 100 ml of dichloromethane. The combined organic elute was evaporated to dryness. Crude product was rectified in vacuum to give 79.6 g (91% yield) of 2,2,7-trimethyl-1,2,3,6-tetrahydro-*as*-indacene as yellowish oil which crystallizes rapidly at room temperature, b.p. 119°C-125°C/2 mm Hg.

Anal. calc. for C₁₅H₁₈: C, 90.85; H, 9.15. Found: C, 90.76; H, 9.24.

¹H NMR (CDCl₃): δ 7.06-6.99 (m, 2H), 6.45 (br.s, 1H), 3.13 (s, 2H), 2.74 (s, 2H), 2.67 (s, 2H), 2.13 (s, 3H), 1.16 (s, 6H). ¹³C{¹H} NMR (CDCl₃): δ 144.40, 144.10, 139.37, 139.08, 138.18, 127.32, 122.41, 117.62, 47.66, 45.87, 41.19, 40.26, 29.09, 16.77.

Example 2: Synthesis of 2,2,7-Triethyl-1,2,3,6-tetrahydro-*as*-indacene

2-[(2-Ethyl-1-oxo-2,3-dihydro-1*H*-inden-4-yl)methyl]butanoic acid



In a three-necked round-bottom flask, 36.0 g (1.57 mol) of sodium metal was dissolved in 700 ml of dry ethanol. To the resulting solution, 500 g (3.12 mol) of diethyl malonate was added. This mixture was stirred for 15 min., then 206 g (0.78 mol) of 1,2-bis(bromomethyl)benzene was added in several portions to maintain a gentle reflux. This mixture was refluxed for an additional 3 h and then cooled to room temperature. Ethanol was distilled off, and 1000 ml of water was added to the residue at room temperature. The separated oil was extracted with 1000 ml of dichloromethane. The extract was evaporated on a Rotavapor, and an excess of diethyl malonate as well as by-product, i.e. diethyl 1,3-dihydro-2*H*-indene-2,2-dicarboxylate, were distilled off in vacuum ($<180^\circ\text{C}/3$ mm Hg). The residual tetraethyl 2,2'-[1,2-phenylenedi(methylene)]dimalonate was further used without an additional purification.

^1H NMR (CDCl_3): δ 7.17-7.11 (m), 4.16 (q, $J = 7.3$ Hz), 4.15 (q, $J = 7.3$ Hz), 3.69 (t, $J = 7.8$ Hz), 3.29 (d, $J = 7.8$ Hz), 1.20 (t, $J = 7.3$ Hz).


To a solution of sodium ethoxide (obtained from 33.4 g (1.45 mol) of sodium metal and 750 ml of dry ethanol), tetraethyl 2,2'-[1,2-phenylenedi(methylene)]dimalonate (as prepared above) was added. The formed mixture was stirred for 15 min., and then 158 g (1.45 mol) of bromoethane was added. The resulting mixture was refluxed for 7 h and then cooled to room temperature. A solution of 312 g of KOH in 850 ml of water was added. This mixture was refluxed for 5 h to saponify the ester. Ethanol and water were distilled off until vapor temperature reached 95°C , and 3000 ml of water and then 12 M HCl (to pH~1) were added to the residue. Crude 2,2'-[1,2-phenylenedi(methylene)]bis(ethylmalonic acid) was extracted with ether, the extract was evaporated to dryness, and the formed solid material was then decarboxylated at 160°C - 180°C to form 2,2'-[1,2-phenylenedi(methylene)]dibutanoic acid as a yellowish oil which was further used without an additional purification.

^1H NMR (CDCl_3): δ 11.6 (br.s, 2H), 7.19-7.07 (m, 4H), 3.09-2.94 (m, 2H), 2.85-2.69 (m, 2H), 2.68-2.55 (m, 2H), 1.77-1.52 (m, 4H), 0.96 (t, $J = 7.4$ Hz, 6H).

A mixture of this acid and 240 ml (3.31 mol) of thionyl chloride was stirred for 24 h at room temperature. After evaporation of an excess of thionyl chloride, the residue was dried in vacuum to give crude 2,2'-[1,2-phenylenedi(methylene)]dibutanoyl chloride which was further used without an additional purification. To a stirred suspension of 80.0 g (0.6 mol) of AlCl_3 in 600 ml of dichloromethane cooled to 0°C , a solution of 2,2'-[1,2-phenylenedi(methylene)]dibutanoyl chloride in 200 ml of dichloromethane was added dropwise. This mixture was stirred overnight at room temperature and then poured on 1000 g of ice. The organic layer was separated, and the aqueous layer was additionally extracted with 350 ml of dichloromethane. The combined organic extract was evaporated to dryness, and the residue was dissolved in a cold solution of 54 g KOH in 700 ml water. The obtained solution was extracted with 2 x 200 of ether, then acidified with 12 M HCl to pH 1. The formed mixture was extracted with 3 x 250 ml of dichloromethane. The combined organic extract was passed through a short pad of silica gel 60 (40-63 μm), and the obtained filtrate was evaporated to dryness to give 136.5 g [67% yield from 1,2-bis(bromomethyl)benzene] of 2-[(2-ethyl-1-oxo-2,3-dihydro-1*H*-inden-4-yl)methyl]butanoic acid as a yellow oil which was further used without an additional purification.

^1H NMR (CDCl_3): δ 9.1 (br.s, 1H), 7.61 (d, $J = 7.6$ Hz, 1H), 7.43 (d, $J = 7.3$ Hz, 1H), 7.34-7.26 (m, 1H), 3.40-3.19 (m, 1H), 3.12-2.96 (m, 1H), 2.92-2.53 (m, 4H), 2.05-1.86 (m, 1H), 1.84-1.42 (m, 3H), 1.10-0.86 (m, 6H).

Ethyl 2-[(2-ethyl-1-oxo-2,3-dihydro-1*H*-inden-4-yl)methyl]butanoate




To a solution of 136.5 g (524 mmol) of 2-[(2-ethyl-1-oxo-2,3-dihydro-1*H*-inden-4-yl)methyl]butanoic acid in 400 ml of ethanol cooled to 0°C , 46 ml (634 mmol, 1.2 equiv) of thionyl chloride was added dropwise over 1 h. This mixture was allowed to reach room temperature and then refluxed for 2 h. The obtained mixture was evaporated on a Rotavapor, the residue was dissolved in 500 ml of dichloromethane. This solution was washed with aqueous K_2CO_3 , dried over K_2CO_3 , and then evaporated to dryness to give a yellow oil. This oil was rectified in vacuum to give 87.0 g (56% yield) of a mixture of two diastereomers of

ethyl 2-[(2-ethyl-1-oxo-2,3-dihydro-1*H*-inden-4-yl)methyl]butanoate as a yellowish oil, b.p. 195°C-210°C/7 mm Hg.

Anal. calc. for C₁₈H₂₄O₃: C, 74.97; H, 8.39. Found: C, 75.16; H, 8.50


¹H NMR (CDCl₃): δ 7.61 (d, *J* = 7.6 Hz, 1H), 7.40 (d, *J* = 7.3 Hz, 1H), 7.33-7.27 (m, 1H), 4.10-4.00 (m, 2H), 3.37-3.21 (m, 1H), 3.05-2.95 (m, 1H), 2.88-2.56 (m, 4H), 2.06-1.91 (m, 1H), 1.82-1.47 (m, 3H), 1.13 and 1.11 (two t, *J* = 7.3 Hz, 3H), 1.03 (t, *J* = 7.3 Hz, 3H), 0.97 (t, *J* = 7.3 Hz, 3H). ¹³C{¹H} NMR (CDCl₃): δ 208.91, 175.10, 152.42, 137.19, 136.95, 134.66, 127.48, 121.84, 60.14, 48.57, 48.54, 47.61, 47.51, 34.08, 34.05, 30.88, 30.84, 25.56, 25.51, 24.45, 24.37, 14.08, 14.06, 11.65, 11.49.

10 2-[(2,2-Diethyl-1-oxo-2,3-dihydro-1*H*-inden-4-yl)methyl]butanoic acid




To a solution of 87.0 g (301.7 mmol) of ethyl 2-[(2-ethyl-1-oxo-2,3-dihydro-1*H*-inden-4-yl)methyl]butanoate and 56.5 g (362.3 mmol, 1.2 eq.) of ethyl iodide in 100 ml of THF cooled to 0°C, a solution of 44.0 g (392.1 mmol, 1.3 eq.) of *t*BuOK in 400 ml of THF was added dropwise for 4 h, and the reaction mixture was then stirred overnight at room temperature. Further on, this mixture was evaporated on a Rotavapor. To the residue, a solution of 60 g of KOH in a mixture of 200 ml of water and 200 ml of methanol was added. The resulting mixture was refluxed for 4 h to saponify the ester. Further on, methanol and water were distilled off until temperature reached 95°C, and 1.5 L of water and then 12 M HCl (to pH 1) were added to the residue. Crude product was extracted with 300 ml of dichloromethane. The aqueous phase was additionally extracted with 3 x 150 ml of dichloromethane. The combined organic extract was evaporated to dryness to give 84 g (ca. 100% yield) of 2-[(2,2-diethyl-1-oxo-2,3-dihydro-1*H*-inden-4-yl)methyl]butanoic acid as a red viscous oil which was further used without an additional purification.

¹H NMR (CDCl₃): δ 11.7 (br.s, 1H), 7.60 (d, *J* = 7.6 Hz, 1H), 7.42 (d, *J* = 7.3 Hz, 1H), 7.33-7.25 (m, 1H), 3.11-2.78 (m, 4H), 2.78-2.65 (m, 1H), 1.84-1.52 (m, 6H), 1.01 (t, *J* = 7.3 Hz, 3H), 0.76 (t, *J* = 7.6 Hz, 3H), 0.74 (t, *J* = 7.6 Hz, 3H). ¹³C{¹H} NMR (CDCl₃): δ 211.80, 181.04, 152.16, 137.55, 136.70, 134.71, 127.61, 121.95, 53.40, 47.45, 35.47, 33.59, 29.86, 29.81, 25.22, 11.58, 8.59, 8.56.

2-[(2,2-Diethyl-1-oxo-2,3-dihydro-1*H*-inden-4-yl)methyl]butanoic acid

To a solution of 2-[(2,2-diethyl-1-oxo-2,3-dihydro-1*H*-inden-4-yl)methyl]butanoic acid (as prepared above) in a mixture of 66 g (1.18 mol) of KOH and 540 ml of ethylene glycol, 53 ml of hydrazine hydrate was added. The reaction mixture was refluxed for 6 h. Then, 66 g of KOH and 26 ml of hydrazine hydrate were added, and the reaction mixture was additionally refluxed for 5 h. Further on, the reflux condenser was replaced by a Claisen distillation head with Liebig condenser, and a mixture of water, NH_2NH_2 , and ethylene glycol was slowly distilled off until the distillation temperature reached 195°C (ca. half of the initial volume). The residue was then allowed to cool to room temperature, diluted with 2 L of water, acidified with 12 N HCl to pH=1, and crude product was extracted with 3 x 300 ml of dichloromethane. The combined organic extract was washed with 1 L of water, and then evaporated to dryness to give 80.8 g [98% yield from ethyl 2-[(2-ethyl-1-oxo-2,3-dihydro-1*H*-inden-4-yl)methyl]butanoate] of the title product as a red viscous oil which was further used without an additional purification.

^1H NMR (CDCl_3): δ 11.8 (br.s, 1H), 7.08-6.98 (m, 2H), 6.93 (d, $J = 7.1$ Hz, 1H), 2.92 (dd, $J = 13.4$ Hz, $J = 7.3$ Hz, 1H), 2.73 (s, 2H), 2.71-2.55 (m, 4H), 1.74-1.52 (m, 2H), 1.51-1.42 (m, 4H), 0.95 (t, $J = 7.3$ Hz, 3H), 0.84 (t, $J = 7.3$ Hz, 3H), 0.83 (t, $J = 7.3$ Hz, 3H). $^{13}\text{C}\{^1\text{H}\}$ NMR (CDCl_3): δ 182.34, 143.54, 142.03, 134.94, 126.48, 126.27, 122.70, 47.70, 45.94, 43.93, 42.30, 35.18, 30.56, 24.82, 11.71, 9.00.


2,7,7-Triethyl-1,6,7,8-tetrahydro-*as*-indacen-3(2*H*)-one

A mixture of the above-obtained 2-[(2,2-diethyl-2,3-dihydro-1*H*-inden-4-yl)methyl]butanoic acid (80.8 g, 295 mmol) and 150 ml (246 g, 2.07 mol) of thionyl chloride was stirred for 24 h at room temperature. An excess of thionyl chloride was distilled off, and

the residue was dried in vacuum. The obtained 2-[(2,2-Diethyl-2,3-dihydro-1*H*-inden-4-yl)methyl]butanoyl chloride was further used without an additional purification. To a suspension of 47.2 g (354 mmol, 1.2 eq.) of AlCl₃ in 300 ml of dichloromethane cooled to 0°C, a solution of 2-[(2,2-diethyl-2,3-dihydro-1*H*-inden-4-yl)methyl]butanoyl chloride in 150 ml of dichloromethane was added over 1 h. The cooling bath was then removed, and the solution was stirred overnight at room temperature. The reaction mixture was poured into 500 g of crushed ice, the organic phase was separated, and the aqueous phase was extracted by 200 ml of dichloromethane. The combined organic extract was washed with aqueous K₂CO₃, dried over K₂CO₃, passed through a short pad of silica gel 60 (40-63 μm), and the elute was evaporated to dryness to give 73.7 g (98% yield) of 2,7,7-triethyl-1,6,7,8-tetrahydro-*as*-indacen-3(2*H*)-one as a red oil which was further used without an additional purification.

¹H NMR (CDCl₃): δ 7.55 (d, *J* = 7.6 Hz, 1H), 7.16 (d, *J* = 7.6 Hz, 1H), 3.16 (dd, *J* = 17.2 Hz, *J* = 7.6 Hz, 1H), 2.80 (s, 2H), 2.71 (s, 2H), 2.69-2.55 (m, 2H), 2.06-1.91 (m, 1H), 1.59-1.43 (m, 5H), 1.01 (t, *J* = 7.3 Hz, 3H), 0.87 (t, *J* = 7.3 Hz, 3H), 0.86 (t, *J* = 7.3 Hz, 3H).
¹³C{¹H} NMR (CDCl₃): δ 208.70, 150.90, 150.05, 140.44, 135.43, 123.77, 122.06, 49.04, 46.68, 44.29, 41.03, 30.90, 30.78, 30.71, 24.58, 11.66, 8.98, 8.94.

2,2,7-Triethyl-1,2,3,6-tetrahydro-*as*-indacene (illustrated as the 2,2,7-Triethyl-1,2,3,8-tetrahydro-*as*-indacene isomer)



To a solution of 73.7 g (288 mmol) of 2,7,7-triethyl-1,6,7,8-tetrahydro-*as*-indacen-3(2*H*)-one in 300 ml of THF cooled to 5°C, 16.3 g (431 mmol) of NaBH₄ was added. Further on, 150 ml of methanol was added dropwise to this vigorously stirred mixture for ca. 5 h at 5°C. The resulting mixture was stirred for 3 h at room temperature, then evaporated to dryness, and the residue was partitioned between 500 ml of dichloromethane and 500 ml of 2 M HCl. The organic layer was separated, and the aqueous layer was additionally extracted with 100 ml of dichloromethane. The combined organic extract was evaporated to dryness. To a solution of the residue in 500 ml of toluene, 1 g of TsOH was added, and this mixture was refluxed with a Dean-Stark head for 20 min., then cooled to room temperature using a water bath. The resulting solution was washed by 10% Na₂CO₃. The organic layer was

separated, and the aqueous layer was extracted with 2 x 100 ml of dichloromethane. The combined organic extract was dried over K₂CO₃ and then passed through a short pad of silica gel 60 (40-63 μ m). The silica gel pad was additionally washed by 100 ml of dichloromethane. The combined organic elute was evaporated to dryness. This crude product was rectified in vacuum to give 51.3 g (74% yield) of 2,2,7-triethyl-1,2,3,6-tetrahydro-*as*-indacene as a yellowish oil, b.p. 134°C-137°C/5 mm Hg.


Anal. calc. for C₁₈H₂₄: C, 89.94; H, 10.06. Found: C, 90.23; H, 10.36

¹H NMR (CDCl₃): δ 7.05 (d, J = 7.6 Hz, 1H), 7.01 (d, J = 7.6 Hz, 1H), 6.47 (s, 1H), 3.16 (s, 2H), 2.75 (s, 2H), 2.67 (s, 2H), 2.49 (q, J = 7.3 Hz, 2H), 1.49 (q, J = 7.3 Hz, 4H), 1.20 (q, J = 7.3 Hz, 3H), 0.84 (q, J = 7.3 Hz, 6H). ¹³C{¹H} NMR (CDCl₃): δ 150.82, 143.83, 139.24, 138.63, 138.08, 125.36, 122.27, 117.81, 46.63, 43.76, 41.96, 39.41, 30.68, 24.36, 13.43, 9.05.

Pre-catalyst Synthesis:

Example 3: Synthesis of *rac*-dimethylsilanediyl-bis[η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]zirconium dichloride (pre-catalyst A)

Bis(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)(dimethyl)silane




To a solution of 19.8 g (100 mmol) of 2,2,7-trimethyl-1,2,3,8-tetrahydro-*as*-indacene in a mixture of 200 ml of toluene and 10 ml of THF, 40.0 ml (100.0 mmol) of 2.5 M ⁿBuLi in hexanes was added in one portion at room temperature. This mixture was refluxed for 1 h, then the resulting light yellow solution with a large amount of white precipitate was cooled to 0°C, and 6.45 g (50.0 mmol) of dichlorodimethylsilane was added in one portion. Further on, this mixture was stirred overnight at ambient temperature. Then, the obtained mixture was quenched with 20 ml of water, the organic layer was separated, and the aqueous layer was

extracted with 2 x 60 ml of toluene. The combined organic extract was filtered through a pad of silica gel 60 (40-63 μ m) which was additionally washed by 2 x 10 ml of toluene. The combined filtrate was evaporated under a reduced pressure to give a white solid mass. The latter was triturated with 750 ml of n-hexane, the precipitate was filtered through a glass frit (G4) and then dried in vacuo. This procedure gave 16.6 g (73% yield) of bis(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)(dimethyl)silane as a white powder (approx. 3:2 mixture of two stereoisomers).

Anal. calc. for $C_{32}H_{40}Si$: C, 84.89; H, 8.91. Found: C, 85.27; H, 9.30

^1H NMR ($CDCl_3$): δ 7.30 (d, J = 7.6 Hz), 7.15 (d, J = 7.6 Hz), 6.95-6.85 (m), 6.53 (s), 3.70 (s), 3.68 (s), 2.85-2.69 (m), 2.23 (s), 2.17 (s), 1.20 (s), 1.19 (s), 1.17 (s), 1.16 (s), -0.31 (s), -0.33 (s). $^{13}C\{^1H\}$ NMR ($CDCl_3$): δ 147.44, 147.31, 142.79, 142.73, 141.60, 141.53, 140.45, 134.48, 124.95, 124.87, 120.94, 119.07, 119.00, 47.80, 47.09, 47.01, 46.05, 40.40, 29.08, 18.00, -5.87, -5.96, -6.16.

Rac-dimethylsilanediyl-bis[η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]zirconium dichloride (pre-catalyst A)



To a suspension of 4.53 g (10.0 mmol) of bis(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)(dimethyl)silane in 200 ml of ether cooled to $-50^\circ C$, 8.0 ml (20.0 mmol) of 2.5 M $nBuLi$ in hexanes was added in one portion. This mixture was stirred overnight at room temperature, then the resulting yellow suspension was cooled to $-50^\circ C$, and 3.78 g (10.02 mmol) of $ZrCl_4(THF)_2$ was added. The reaction mixture was stirred for 24 h at room temperature to give orange suspension. This mixture was evaporated to dryness. The residue was heated with 200 ml of toluene, and the formed suspension was filtered while hot through a glass frit (G4). The filtrate was evaporated to 80 ml and then heated to dissolve the


precipitate. Orange crystals precipitated from this solution within 2 h at room temperature and were collected, washed with 10 ml of n-hexane, and dried in vacuum. This procedure gave 1.98 g of pure *rac*-zirconocene. The mother liquor was evaporated to ca. 15 ml. Orange crystals precipitated from this solution overnight at room temperature and were collected and then dried in vacuum. This procedure gave 0.26 g of *rac*-zirconocene. Thus, the total yield of *rac*-dimethylsilanediyl-bis[η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]zirconium dichloride isolated in this synthesis was 2.24 g (36% yield).

Anal. calc. for $C_{32}H_{38}Cl_2SiZr$: C, 62.71; H, 6.25. Found: C, 62.95; H, 6.33

^1H NMR (CD_2Cl_2): δ 7.50 (d, J = 8.85 Hz, 2H), 6.92 (d, J = 8.85 Hz, 2H), 6.55 (s, 2H), 2.94 (d, J = 15.9 Hz, 2H), 2.78 (d, J = 15.9 Hz, 2H), 2.72 (s, 4H), 2.20 (s, 6H), 1.28 (s, 6H), 1.27 (s, 6H), 1.15 (s, 6H). ^1H NMR ($CDCl_3$): δ 7.48 (d, J = 8.7 Hz, 2H), 6.92 (d, J = 8.7 Hz, 2H), 6.58 (s, 2H), 2.98 (d, J = 16.1 Hz, 2H), 2.82 (d, J = 16.5 Hz, 2H), 2.77 (d, J = 16.5 Hz, 2H), 2.70 (d, J = 16.1 Hz, 2H), 2.22 (s, 6H), 1.28 (s, 12H), 1.16 (s, 6H). $^{13}C\{^1H\}$ NMR ($CDCl_3$): δ 141.42, 138.46, 135.13, 131.13, 126.53, 123.84, 123.34, 119.53, 83.42, 48.62, 46.96, 39.64, 29.93, 29.78, 18.60, 2.59.

Example 4: Synthesis of *rac*-dimethylsilanediyl-bis[η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]zirconium dimethyl (pre-catalyst B)

Rac-dimethylsilanediyl-bis[η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]zirconium dimethyl (pre-catalyst B)



20

To a suspension of 919 mg (1.5 mmol) of *rac*-dimethylsilanediyl-bis[η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]zirconium dichloride in a mixture of 25 ml of toluene and 5 ml of ether, 3.0 ml (6.33 mmol) of 2.11 M MeMgBr in ether was added. The resulting heterogeneous mixture was stirred overnight at room temperature and, then, additionally refluxed for 10 min. The reaction mixture was evaporated to ca. 25 ml, heated and filtered while hot through a glass frit (G3) to remove insoluble magnesium salts. The

25

filtrate was evaporated to ca. 20 ml, heated and again filtered while hot through a glass frit (G3). Yellow crystalline material precipitated from the obtained filtrate overnight at room temperature and was collected, washed with 5 ml of n-hexane, and dried in vacuum. This procedure gave 0.60 g of the title complex. The mother liquor was evaporated to ca. 3 ml.


- 5 Yellow solid precipitated from this solution overnight at room temperature was filtered off and dried in vacuum. This procedure gave 0.15 g of the same complex. Thus, total yield of the title *rac*-complex isolated in this synthesis was 0.75 g (87% yield).

Anal. calc. for C₃₄H₄₄SiZr: C, 71.39; H, 7.75. Found: C, 71.19; H, 7.64

- ¹H NMR (CDCl₃): δ 7.28 (d, *J* = 8.84 Hz, 2H), 6.75 (d, *J* = 8.84 Hz, 2H), 6.49 (s, 2H),
10 2.84 (d, *J* = 15.9 Hz, 2H), 2.76 (d, *J* = 16.2 Hz, 2H), 2.70 (d, *J* = 16.2 Hz, 2H), 2.65 (d, *J* = 15.9 Hz, 2H), 2.00 (s, 6H), 1.18 (s, 6H), 1.11 (s, 6H), 0.99 (s, 6H), -1.42 (s, 6H). ¹³C{¹H} NMR (CDCl₃): δ 138.25, 137.47, 134.28, 127.19, 127.00, 123.48, 121.68, 113.24, 79.19, 48.51, 47.35, 39.63, 34.78, 29.98, 18.10, 2.70.

- Example 5: Synthesis of *rac*-dimethylsilanediyl-bis[η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]hafnium dichloride (pre-catalyst C)

Rac-dimethylsilanediyl-bis[η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]hafnium dichloride (pre-catalyst C)



- To a suspension of 11.9 g (26.3 mmol) of bis(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-
20 indacen-3-yl)(dimethyl)silane in 450 ml of ether cooled to -78°C, 21.1 ml (52.75 mmol) of 2.5 M *n*-BuLi in hexanes was added in one portion. This mixture was stirred overnight at room temperature, then the resulting light orange suspension was cooled to -50°C, and 12.2 g (26.3 mmol) of HfCl₄(THF)₂ was added. The reaction mixture was stirred for 24 h at room temperature and then evaporated to dryness. The residue was heated with 300 ml of toluene,

and the formed suspension was filtered while hot through a glass frit (G4). The filtrate was evaporated to 150 ml and heated to dissolve the precipitate. Yellow crystals precipitated from this solution overnight at room temperature and were collected and dried in vacuum. This procedure gave 5.95 g of pure *rac*-hafnocene. The mother liquor was evaporated to ca. 40 ml.


- 5 Yellow crystals precipitated from this solution overnight at -30°C and were collected and then dried in vacuum. This procedure gave 0.63 g of *rac*-hafnocene. Thus, the total yield of *rac*-dimethylsilanediyl-bis[η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]hafnium dichloride isolated in this synthesis was 6.58 g (36% yield).

Anal. calc. for C₃₂H₃₈Cl₂SiZr: C, 62.71; H, 6.25. Found: C, 62.92; H, 6.49

- 10 ¹H NMR (CDCl₃): δ 7.51 (d, *J* = 8.84 Hz, 2H), 6.88 (d, *J* = 8.84 Hz, 2H), 6.47 (s, 2H), 3.01 (d, *J* = 15.9 Hz, 2H), 2.81 (d, *J* = 15.9 Hz, 2H), 2.78 (d, *J* = 16.2 Hz, 2H), 2.68 (d, *J* = 16.2 Hz, 2H), 2.30 (s, 6H), 1.26 (s, 6H), 1.25 (s, 6H), 1.15 (s, 6H). ¹³C{¹H} NMR (CDCl₃): δ 141.20, 138.03, 132.51, 130.71, 124.90, 123.54, 123.34, 117.64, 84.50, 48.59, 46.99, 39.63, 29.93, 29.81, 18.45, 2.57.

- 15 Example 6: Synthesis of *rac*-dimethylsilanediyl-bis[η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl] hafnium dimethyl (pre-catalyst D)

Rac-dimethylsilanediyl-bis[η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl] hafnium dimethyl (pre-catalyst D)



- 20 To a suspension of 1.40 g (2.0 mmol) of *rac*-dimethylsilanediyl-bis[η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]hafnium dichloride in 40 ml of toluene, 3.80 ml (8.02 mmol) of 2.11 M MeMgBr in ether was added. The resulting heterogeneous mixture was stirred overnight at room temperature and then additionally refluxed for 10 min. The reaction mixture was evaporated to ca. 25 ml, heated and filtered while hot through a glass
- 25 frit (G3) to remove insoluble magnesium salts. The filtrate was evaporated to ca. 20 ml, heated and again filtered while hot through a glass frit (G4). Yellow crystalline material precipitated from the obtained filtrate overnight at -30°C and was collected, washed with 5 ml


of n-hexane, and dried in vacuum. This procedure gave 1.06 g (80% yield) of pure target complex.

Anal. calc. for $C_{34}H_{44}HfSi$: C, 61.94; H, 6.73. Found: C, 61.80; H, 6.91

^1H NMR ($CDCl_3$): δ 7.4 (d, J = 8.84 Hz, 2H), 6.82 (d, J = 8.84 Hz, 2H), 6.47 (s, 2H),
 5 2.94 (d, J = 16.0 Hz, 2H), 2.82 (d, J = 11.6 Hz, 2H), 2.78 (d, J = 11.6 Hz, 2H), 2.71 (d, J =
 16.0 Hz, 2H), 2.12 (s, 6H), 1.25 (s, 6H), 1.18 (s, 6H), 1.08 (s, 6H), -1.54 (s, 6H). $^{13}C\{^1H\}$
 NMR ($CDCl_3$): δ 138.31, 137.18, 132.75, 127.19, 126.36, 123.45, 121.73, 112.26, 81.28,
 48.54, 47.41, 40.38, 39.61, 30.00 (two resonances), 17.94, 2.66.

Example 7: Synthesis of 1,1-silolanediyl-bis(η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-
 10 *indacen*-3-yl)hafnium dichloride (pre-catalyst E)

1,1-Bis(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)silolane




To a solution of 14.9 g (75.0 mmol) of 2,2,7-trimethyl-1,2,3,8-tetrahydro-*as*-indacene
 in 250 ml of ether, 30.0 ml (75.0 mmol) of 2.5 M n BuLi in hexanes was added in one portion
 15 at $-50^\circ C$. This mixture was stirred overnight at room temperature. Then, the obtained white
 suspension was cooled to $-40^\circ C$, and 1.0 g (11.2 mmol) of CuCN was added. The resulting
 mixture was stirred for 30 min. at $-25^\circ C$, and then 5.82 g (37.53 mmol) of 1,1-
 dichlorosilolane was added in one portion. This mixture was stirred for 3 h at ambient
 temperature, then filtered through a pad of silica gel 60 (40-63 μm) which was additionally
 20 washed by 2 x 50 ml of dichloromethane. The combined filtrate was evaporated under
 reduced pressure, and the product was isolated by flash-chromatography using 200 ml of
 silica gel 60 (40-63 μm ; eluent: hexanes-dichloromethane = 10:1, vol.). This procedure gave
 15.25 g (85% yield) of 1,1-bis(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)silolane
 (approx. 3:2 mixture of two isomers) as a slightly yellowish glass.

Anal. calc. for C₃₄H₄₂Si: C, 85.29; H, 8.84. Found: C, 85.53; H, 9.10

¹H NMR (CDCl₃): δ 7.14 (d, *J* = 7.3 Hz), 6.97 (d, *J* = 7.3 Hz), 6.88 (d, *J* = 7.3 Hz), 6.84 (d, *J* = 7.3 Hz), 6.48 (s), 6.36 (s), 3.31 (s), 2.88-2.55 (m), 2.10 (s), 2.00 (s), 0.93-0.32 (m).

- 5 1,1-Silolanediyl-bis(η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)hafnium dichloride (pre-catalyst E)




- To a solution of 15.25 g (31.9 mmol) of 1,1-bis(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)silolane in 400 ml of ether cooled to -50°C, 25.5 ml (63.8 mmol) of 2.5 M ⁿBuLi in hexanes was added in one portion. This mixture was stirred overnight at room temperature, then the resulting red solution was cooled to -50°C, and 14.8 g (31.9 mmol) of HfCl₄(THF)₂ was added. The reaction mixture was stirred for 24 h at room temperature to give orange suspension. This mixture was evaporated to dryness. The residue was heated with 200 ml of toluene, and the formed suspension was filtered while hot through a glass frit (G4).
- 15 The filtrate was evaporated to ca. 80 ml. Yellow crystals precipitated from this solution overnight at -30°C and were collected, washed with 15 ml of cold n-hexane, and dried in vacuum. This procedure gave 5.30 g (23%) of pure *rac*-1,1-silolanediyl-bis(η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)hafnium dichloride. The mother liquor was evaporated to ca. 40 ml, and to this solution 20 ml of n-hexane was added. Yellow crystalline
- 20 material precipitated from this solution overnight at -30°C was collected and dried in vacuum. This procedure gave 4.20 g (18% yield) of a ca. 60 to 40 mixture of *rac*- and *meso*-hafnocenes. Thus, the total yield of *rac*- and *meso*-1,1-silolanediyl-bis(η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)hafnium dichloride isolated in this synthesis was 9.50 g (41% yield).

Anal. calc. for C₃₄H₄₀Cl₂HfSi: C, 56.24; H, 5.55. Found: C, 56.21; H, 5.68

¹H NMR (CDCl₃): δ 7.44 (d, *J* = 8.8 Hz), 6.88 (d, *J* = 8.8 Hz), 6.46 (s), 3.02 (d, *J* = 16.2 Hz), 2.84 (s), 2.80 (s), 2.76 (s), 2.68 (d, *J* = 16.2 Hz), 2.29 (s), 2.18-2.06 (m), 2.01-1.91 (m), 1.91-1.81 (m), 1.27 (s), 1.15 (s). ¹³C{¹H} NMR (CDCl₃): δ 141.34, 138.02, 132.44, 130.89, 124.08, 123.28, 123.20, 116.43, 84.15, 48.59, 46.98, 39.63, 29.91, 29.77, 26.86, 18.20, 14.59.

Example 8: Synthesis of tetramethyldisilanediy-bis[η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]zirconium dichloride (pre-catalyst F (rac) and G (meso))

1,1,2,2-Tetramethyl-1,2-bis(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)disilane



10

To a solution of 14.9 g (75.0 mmol) of 2,2,7-trimethyl-1,2,3,8-tetrahydro-*as*-indacene in 250 ml of ether, 30.0 ml (75.0 mmol) of 2.5 M ⁿBuLi in hexanes was added in one portion at -50°C. This mixture was stirred overnight at room temperature. Then, the resulting white suspension was cooled to -40°C, and 1.0 g (11.2 mmol) of CuCN was added. The obtained mixture was stirred for 30 min. at -25°C, and then 7.02 g (37.5 mmol) of 1,2-dichloro-1,1,2,2-tetramethyldisilane was added in one portion. This mixture was stirred for 3 h at ambient temperature, then filtered through a pad of silica gel 60 (40-63 μm) which was additionally washed by 2 x 50 ml of dichloromethane. The combined filtrate was evaporated under reduced pressure, and the residue was dissolved in 60 ml of n-hexane. White solid precipitated overnight at -30°C was collected and dried in vacuum. This procedure gave 10.27 g of 1,1,2,2-tetramethyl-1,2-bis(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)disilane. Additional amount of the product was isolated by flash-chromatography (from the residue after evaporation of the mother liquor) using 350 ml of silica gel 60 (40-63 μm; eluent:

15

20

hexanes-dichloromethane = 10:1, vol.). This procedure gave extra 4.25 g of the title product. Thus, the total yield of 1,1,2,2-tetramethyl-1,2-bis(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)disilane isolated in this synthesis was 14.52 g (76% yield).

Anal. calc. for C₃₄H₄₆Si₂: C, 79.93; H, 9.08. Found: C, 80.23; H, 9.37


5 Major isomer:

¹H NMR (CDCl₃): δ 7.04 (d, *J* = 7.6 Hz, 2H), 6.86 (d, *J* = 7.6 Hz, 2H), 6.36 (s, 2H), 3.09 (s, 2H), 2.81-2.67 (m, 8H), 2.02 (s, 6H), 1.18 (s, 6H), 1.13 (s, 6H), 0.1 (s, 6H), -0.35 (s, 6H). ¹³C{¹H} NMR (CDCl₃): δ 148.42, 143.48, 140.94, 140.20, 134.25, 123.82, 120.78, 118.82, 49.23, 47.79, 46.03, 40.41, 29.01, 29.00, 17.85, -1.05, -2.01.

10 Minor isomer:

¹H NMR (CDCl₃): δ 6.95 (d, *J* = 7.6 Hz, 2H), 6.82 (d, *J* = 7.6 Hz, 2H), 6.42 (s, 2H), 3.14 (s, 2H), 2.81-2.67 (m, 8H), 2.11 (s, 6H), 1.18 (s, 6H), 1.14 (s, 6H), -0.04 (s, 6H), -0.28 (s, 6H). ¹³C{¹H} NMR (CDCl₃): δ 148.37, 143.41, 140.84, 140.24, 134.19, 123.90, 120.84, 118.87, 49.17, 47.79, 46.05, 40.43, 29.02, 29.00, 17.97, -1.22, -2.05.

15 Tetramethyldisilanediy1-bis[η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]zirconium dichloride (pre-catalyst F (rac) and G (meso))



To a solution of 5.11 g (10.0 mmol) of 1,1,2,2-tetramethyl-1,2-bis(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)disilane in 150 ml of ether cooled to -78°C, 8.0 ml (20.0 mmol) of 2.5 M ⁿBuLi in hexanes was added in one portion. This mixture was stirred overnight at room temperature, then the resulting yellowish suspension was cooled to -30°C, and 3.77 g (10.0 mmol) of ZrCl₄(THF)₂ was added. The reaction mixture was stirred for 24 h at room temperature to give orange suspension. This mixture was evaporated to dryness. The residue was heated with 200 ml of toluene, and the formed suspension was filtered while hot

through a glass frit (G4) to give a filtrate including on the evidence of NMR spectroscopy a ca. 2 to 1 mixture of *rac*- and *meso*-zirconocenes. Pure isomeric complexes were obtained using multiple crystallizations of this mixture from toluene-n-octane. This procedure gave 1.50 g (22% yield) and 0.57 g (9% yield) of *rac*- and *meso*-complexes, respectively.

5 *Rac*-zirconocene

Anal. calc. for C₃₄H₄₄Cl₂Si₂Zr: C, 60.86; H, 6.61. Found: C, 60.75; H, 6.82

¹H NMR (CDCl₃): δ 7.47 (d, *J* = 8.6 Hz, 2H), 7.02 (d, *J* = 8.6 Hz, 2H), 6.33 (s, 2H), 2.99 (d, *J* = 15.9 Hz, 2H), 2.92 (d, *J* = 16.4 Hz, 2H), 2.78 (d, *J* = 15.9 Hz, 2H), 2.67 (d, *J* = 16.4 Hz, 2H), 2.04 (s, 6H), 1.28 (s, 6H), 1.13 (s, 6H), 0.85 (s, 6H), 0.54 (s, 6H). ¹³C{¹H} NMR (CDCl₃): δ 140.79, 138.88, 138.63, 133.55, 125.74, 123.12, 122.03, 116.69, 108.14, 48.64, 47.29, 39.52, 30.12, 29.81, 18.28, -0.05, -0.33.


Meso-zirconocene

Anal. calc. for C₃₄H₄₄Cl₂Si₂Zr: C, 60.86; H, 6.61. Found: C, 61.09; H, 6.78.

¹H NMR (CDCl₃): δ 7.45 (d, *J* = 8.6 Hz, 2H), 6.82 (d, *J* = 8.6 Hz, 2H), 6.29 (s, 2H), 2.96 (d, *J* = 16.2 Hz, 2H), 2.61 (s, 4H), 2.58 (d, *J* = 16.2 Hz, 2H), 2.42 (s, 6H), 1.07 (s, 6H), 1.05 (s, 6H), 0.74 (s, 6H), 0.62 (s, 6H). ¹³C{¹H} NMR (CDCl₃): δ 144.36, 139.46, 137.87, 132.76, 128.51, 123.66, 121.71, 113.09, 108.19, 48.52, 47.17, 39.63, 29.68, 29.62, 20.12, 0.46, -0.48.

20 Example 9: Synthesis of tetramethyldisilanediy-bis[η⁵-2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]hafnium dichloride (pre-catalyst H (*rac*) and I (*meso*))

Tetramethyldisilanediy-bis[η⁵-2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]hafnium dichloride (pre-catalyst H (*rac*) and I (*meso*))



To a solution of 9.33 g (18.3 mmol) of 1,1,2,2-tetramethyl-1,2-bis(2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)disilane in 250 ml of ether cooled to -78°C, 14.6 ml (36.5 mmol) of 2.5 M ⁿBuLi in hexanes was added in one portion. This mixture was stirred overnight at room temperature, then the resulting slightly yellowish suspension was cooled to -30°C, and 8.48 g (18.0 mmol) of HfCl₄(THF)₂ was added. The reaction mixture was stirred for 24 h at room temperature to give orange suspension. This mixture was evaporated to dryness. The residue was heated with 200 ml of toluene, and the formed suspension was filtered while hot through a glass frit (G4). The filtrate was evaporated to 30 ml and heated to dissolve the precipitate. Yellowish crystals precipitated from this solution over 3 days at room temperature were collected and dried in vacuum. This procedure gave 2.60 g (19% yield) of pure *rac*-hafnocene. The mother liquor was evaporated to dryness, and the residue was dissolved in 70 ml of hot n-octane. Solid precipitated from this solution overnight at room temperature was filtered and discarded. Yellow crystals precipitated from the filtrate overnight at -30°C were collected and dried in vacuum. This procedure gave 0.7 g (5% yield) of pure *meso*-hafnocene.

Rac-hafnocene.

Anal. calc. for C₃₄H₄₄Cl₂HfSi₂: C, 53.85; H, 5.85. Found: C, 54.16; H, 6.03

¹H NMR (CDCl₃): δ 7.46 (d, *J* = 8.6 Hz, 2H), 6.98 (d, *J* = 8.6 Hz, 2H), 6.21 (s, 2H), 3.03 (d, *J* = 15.8 Hz, 2H), 2.88 (d, *J* = 16.2 Hz, 2H), 2.83 (d, *J* = 15.8 Hz, 2H), 2.67 (d, *J* = 16.2 Hz, 2H), 2.11 (s, 6H), 1.27 (s, 6H), 1.14 (s, 6H), 0.84 (s, 6H), 0.54 (s, 6H). ¹³C{¹H} NMR (CDCl₃): δ 140.60, 138.47, 137.08, 133.23, 124.40, 122.78, 122.27, 114.61, 105.86, 48.58, 47.30, 39.52, 30.09, 29.83, 18.11, 0.02, -0.33.


Meso-hafnocene.

Anal. calc. for C₃₄H₄₄Cl₂HfSi₂: C, 53.85; H, 5.85. Found: C, 54.87; H, 5.98

¹H NMR (CDCl₃): δ 7.46 (d, *J* = 8.6 Hz, 2H), 6.78 (d, *J* = 8.6 Hz, 2H), 6.17 (s, 2H), 2.93 (d, *J* = 16.4 Hz, 2H), 2.72-2.62 (m, 4H), 2.58 (d, *J* = 16.4 Hz, 2H), 2.51 (s, 6H), 1.08 (s, 6H), 1.04 (s, 6H), 0.74 (s, 6H), 0.61 (s, 6H). ¹³C{¹H} NMR (CDCl₃): δ 143.80, 139.24, 137.53, 132.30, 127.26, 124.00, 121.43, 110.64, 104.92, 48.47, 47.23, 39.61, 29.65, 29.63, 20.02, 0.51, -0.47.

Example 10: Synthesis of *rac*-tetramethyldisilanediy-bis[η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]hafnium dimethyl (pre-catalyst J)

Rac-tetramethyldisilanediy-bis[η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]hafnium dimethyl (pre-catalyst J)



5

To a solution of 1.14 g (1.5 mmol) of *rac*-tetramethyldisilanediy-bis[η^5 -2,7,7-trimethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]hafnium dichloride in 30 ml of toluene, 3.0 ml (6.33 mmol) of 2.11 M MeMgBr in ether was added. The resulting mixture was stirred overnight at room temperature and then additionally refluxed for 10 min. The reaction mixture was evaporated to ca. 20 ml, heated, and filtered while hot through a glass frit (G3) to remove insoluble magnesium salts. The filtrate was evaporated to dryness, 20 ml of n-hexane was added, and the resulting mixture was heated again and filtered while hot through a glass frit (G4). The filtrate was evaporated to ca. 10 ml and heated to dissolve the precipitate. Crystalline material precipitated from this solution overnight at room temperature was collected and dried in vacuum. This procedure gave 0.58 g (54% yield) of the target complex.

10

15


Anal. calc. for $C_{36}H_{50}HfSi_2$: C, 60.27; H, 7.02. Found: C, 60.12; H, 7.35

^1H NMR ($CDCl_3$): δ 7.32 (d, J = 8.6 Hz, 2H), 6.91 (d, J = 8.6 Hz, 2H), 6.32 (s, 2H), 3.00-2.71 (m, 8H), 2.07 (s, 6H), 1.25 (s, 6H), 1.19 (s, 6H), 0.64 (s, 6H), 0.63 (s, 6H), -1.48 (s, 6H). $^{13}C\{^1H\}$ NMR ($CDCl_3$): δ 137.83, 137.27, 133.56, 128.10, 126.63, 122.64, 121.44, 110.68, 100.42, 48.52, 47.65, 41.38, 39.59, 29.99, 17.64, 0.03.

20

Example 11: Synthesis of *rac*-dimethylsilanediyl-bis[η^5 -2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]zirconium dichloride (pre-catalyst K)

dimethylbis(2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)silane




5 To a solution of 16.0 g (66.6 mmol) of 2,2,7-triethyl-1,2,3,8-tetrahydro-*as*-indacene in a mixture of 250 ml of toluene and 12.5 ml of THF, 26.6 ml (66.5 mmol) of 2.5 M n BuLi in hexanes was added in one portion at room temperature. This mixture was refluxed for 2 h, then the resulting light yellow solution was cooled to room temperature, and 4.30 g (33.3 mmol) of dichlorodimethylsilane was added in one portion. Further on, this mixture was
10 refluxed for 3 h and then cooled to room temperature. This mixture was quenched with 1 ml of water, filtered through a pad of silica gel 60 (40-63 μ m) which was additionally washed by 3 x 50 ml of dichloromethane. The combined filtrate was evaporated under reduced pressure to give a yellowish oil. The product was isolated by flash-chromatography using 200 ml of silica gel 60 (40-63 μ m; eluent: hexane-dichloromethane = 10:1, vol.). This procedure gave
15 15.6 g (87% yield) of 1,1-bis(2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)silolane (approx. 4:3 mixture of isomers) as a yellowish oil.

Anal. calc. for $C_{38}H_{52}Si$: C, 85.01; H, 9.76. Found: C, 85.47; H, 9.94

^1H NMR ($CDCl_3$): δ 7.33 (d, $J=7.6$ Hz), 7.16 (d, $J=7.6$ Hz), 6.96-6.87 (m), 6.63-6.57 (m), 3.79 (s), 3.74 (s), 2.91-2.73 (m), 2.73-2.36 (m), 1.63-1.47 (m), 1.35-1.18 (m), 0.96-0.83
20 (m), -0.29 (s), -0.33 (s), -0.34 (s).

rac-Dimethylsilanediyl-bis[η^5 -2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]zirconium dichloride (pre-catalyst K)



To a solution of 15.6 g (29.06 mmol) of bis(2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)(dimethyl)silane in 300 ml of ether cooled to -50°C , 23.3 ml (58.3 mmol) of 2.5 M $n\text{-BuLi}$ in hexanes was added in one portion. This mixture was stirred overnight at room temperature, then the resulting yellow suspension was cooled to -50°C , and 11.0 g (29.1 mmol) of $\text{ZrCl}_4(\text{THF})_2$ was added. The reaction mixture was stirred for 24 h at room temperature to give bright orange suspension. This mixture was evaporated to dryness. The residue was heated with 200 ml of toluene, and the formed suspension was filtered while hot through a glass frit (G4). The filtrate was evaporated to 80 ml, and 20 ml of *n*-octane was added to this warm solution. Orange crystals precipitated from the formed solution overnight at room temperature and were collected and dried in vacuum. This procedure gave 4.40 g of pure *rac*-zirconocene. The mother liquor was evaporated to ca. 60 ml, heated almost to reflux, and 40 ml of *n*-octane was added. Orange powder precipitated from this solution overnight at room temperature was collected and dried in vacuum. This procedure gave 1.45 g of *rac*-zirconocene. Thus, the total yield of *rac*-dimethylsilanediyl-bis[η^5 -2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl]zirconium dichloride isolated in this synthesis was 5.85 g (29% yield).


Anal. calc. for $\text{C}_{38}\text{H}_{50}\text{Cl}_2\text{SiZr}$: C, 65.48; H, 7.23. Found: C, 65.63; H, 7.20

^1H NMR (CDCl_3): δ 7.45 (d, $J = 8.8$ Hz, 2H), 6.90 (d, $J = 8.8$ Hz, 2H), 6.62 (s, 2H), 2.97 (d, $J = 16.3$ Hz, 2H), 2.82-2.65 (m, 8H), 2.44-2.31 (m, 2H), 1.66-1.54 (m, 4H), 1.46 (q, $J = 7.3$ Hz, 4H), 1.27 (s, 6H), 1.10 (t, $J = 7.3$ Hz, 6H), 0.88 (t, $J = 7.3$ Hz, 6H), 0.80 (t, $J = 7.3$ Hz, 6H). $^{13}\text{C}\{^1\text{H}\}$ NMR (CDCl_3): δ 142.27, 141.12, 138.43, 131.14, 126.59, 123.78, 123.33,

117.06, 82.35, 46.04, 44.51, 43.17, 31.44, 31.09, 25.97, 16.96, 9.18, 8.83, 2.92.

Example 12: Synthesis of rac-1,1-silolanediy-bis(η^5 -2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)hafnium dichloride (pre-catalyst L)

1,1-Bis(2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)silolane



5

To a solution of 18.1 g (75.3 mmol) of 2,2,7-triethyl-1,2,3,8-tetrahydro-*as*-indacene in 300 ml of ether, 30.1 ml (75.3 mmol) of 2.5 M n -BuLi in hexanes was added in one portion at -50°C. This mixture was stirred overnight at room temperature. Then, the resulting yellowish precipitate was cooled to -60°C, and 1.69 g (18.9 mmol, 25 mol%) of CuCN was added. The resulting mixture was stirred for 30 min. at -25°C, and then 5.84 g (37.7 mmol) of 1,1-dichlorosilolane was added in one portion. This mixture was stirred overnight at ambient temperature, then filtered through a pad of silica gel 60 (40-63 μ m) which was additionally washed by 2 x 50 ml of dichloromethane. The combined filtrate was evaporated under reduced pressure, and the product was isolated by flash-chromatography on silica gel 60 (40-63 μ m; eluent: hexanes-dichloromethane = 10:1, vol.). This procedure gave 17.64 g (83% yield) of 1,1-bis(2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)silolane (approx. 3:2 mixture of isomers) as a slightly yellowish oil.

10


15

Anal. calc. for $C_{40}H_{54}Si$: C, 85.34; H, 9.67. Found: C, 85.69; H, 9.80

^1H NMR ($CDCl_3$): δ 7.13 (d, J = 7.6 Hz), 6.98 (d, J = 7.6 Hz), 6.88 (d, J = 7.6 Hz), 6.84 (d, J = 7.6 Hz), 6.51 (s), 6.37 (s), 3.36 (s), 2.85-2.69 (m), 2.58-2.12 (m), 1.57-1.42 (m), 1.41-0.98 (m), 1.13 (t, J = 7.4 Hz), 1.11 (t, J = 7.4 Hz), 0.89-0.80 (m), 0.54 (t, J = 7.2 Hz), 0.32 (t, J = 7.2 Hz).

20

rac-1,1-Silolanediyl-bis(η^5 -2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)hafnium dichloride (pre-catalyst L)



To a solution of 17.6 g (31.3 mmol) of 1,1-bis(2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)silolane in 300 ml of ether cooled to -50°C , 25.1 ml (62.8 mmol) of 2.5 M $n\text{-BuLi}$ in hexanes was added in one portion. This mixture was stirred overnight at room temperature, then the resulting orange solution was cooled to -50°C , and 10.04 g (31.35 mmol) of HfCl_4 was added. The reaction mixture was stirred for 24 h at room temperature to give orange-red solution. This mixture was evaporated to dryness. The residue was heated with 200 ml of toluene, and the formed suspension was filtered while hot through a glass frit (G4). The filtrate was evaporated to dryness, and the residue was dissolved in 50 ml of warm *n*-hexane. Yellow crystals precipitated from this solution for a week at room temperature and were collected and dried in vacuum. This procedure gave 5.14 g (20% yield) of pure *rac*-1,1-silolanediyl-bis(η^5 -2,7,7-triethyl-3,6,7,8-tetrahydro-*as*-indacen-3-yl)hafnium dichloride.

15 Anal. calc. for $\text{C}_{40}\text{H}_{52}\text{Cl}_2\text{HfSi}$: C, 59.29; H, 6.47. Found: C, 59.51; H, 6.62

^1H NMR (CDCl_3): δ 7.41 (d, $J = 8.8$ Hz, 2H), 6.86 (d, $J = 8.8$ Hz, 2H), 6.50 (s, 2H), 3.01 (d, $J = 16.3$ Hz, 2H), 2.87-2.63 (m, 8H), 2.48-2.35 (m, 2H), 2.20-2.08 (m, 2H), 1.99-1.79 (m, 6H), 1.67-1.51 (m, 4H), 1.46 (q, $J = 7.4$ Hz, 4H), 1.10 (t, $J = 7.4$ Hz, 6H), 0.88 (t, $J = 7.4$ Hz, 6H), 0.80 (t, $J = 7.4$ Hz, 6H). $^{13}\text{C}\{^1\text{H}\}$ NMR (CDCl_3): δ 141.01, 139.50, 138.03, 130.84, 124.10, 123.24, 123.19, 114.3.

Polymerization Examples

Solutions of the pre-catalysts were made using toluene (ExxonMobil Chemical anhydrous, stored under N_2) (98%). Pre-catalyst solutions were typically 0.5 mmol/L.

Solvents, polymerization grade toluene and/or isohexanes were supplied by ExxonMobil Chemical Co. and are purified by passing through a series of columns: two 500 cc Oxyclear cylinders in series from Labclear (Oakland, Calif.), followed by two 500 cc columns in series packed with dried 3 Å mole sieves (8-12 mesh; Aldrich Chemical Company), and two 500 cc columns in series packed with dried 5 Å mole sieves (8-12 mesh; Aldrich Chemical Company).

1-octene (C8; 98%, Aldrich Chemical Company) was dried by stirring over NaK overnight followed by filtration through basic alumina (Aldrich Chemical Company, Brockman Basic 1).

10 Polymerization grade ethylene (C2) was used and further purified by passing it through a series of columns: 500 cc Oxyclear cylinder from Labclear (Oakland, Calif.) followed by a 500 cc column packed with dried 3 Å mole sieves (8-12 mesh; Aldrich Chemical Company), and a 500 cc column packed with dried 5 Å mole sieves (8-12 mesh; Aldrich Chemical Company).

15 Polymerization grade propylene (C3) was used and further purified by passing it through a series of columns: 2250 cc Oxyclear cylinder from Labclear followed by a 2250 cc column packed with 3 Å mole sieves (8-12 mesh; Aldrich Chemical Company), then two 500 cc columns in series packed with 5 Å mole sieves (8-12 mesh; Aldrich Chemical Company), then a 500 cc column packed with Selexsorb CD (BASF), and finally a 500 cc column packed with Selexsorb COS (BASF).

20 Activation of the pre-catalysts was either by methylalumoxane (MAO, 10 wt% in toluene, Albemarle Corp.; Act ID=1), dimethylanilinium tetrakis(perfluorophenyl)borate (Boulder Scientific or Albemarle Corp; Act ID=2) or dimethylanilinium tetrakis(perfluoronaphthyl)borate (Albemarle Corp; Act ID=3). MAO was used as a 0.5 wt % or 1.0 wt % in toluene solution. Micromoles of MAO reported in the experimental section are based on the micromoles of aluminum in MAO. The formula weight of MAO is 58.0 grams/mole. Dimethylanilinium tetrakis(perfluorophenyl)borate and dimethylanilinium tetrakis(perfluoronaphthyl)borate were typically used as a 5 mmol/L solution in toluene.

25 For polymerization runs using dimethylanilinium tetrakis(perfluorophenyl)borate or dimethylanilinium tetrakis(perfluoronaphthyl)borate, tri-n-octylaluminum (TnOAl, Neat, AkzoNobel) was also used as a scavenger prior to introduction of the activator and pre-catalyst into the reactor. TnOAl was typically used as a 5 mmol/L solution in toluene.

Reactor Description and Preparation:

Polymerizations were conducted in an inert atmosphere (N₂) drybox using autoclaves equipped with an external heater for temperature control, glass inserts (internal volume of reactor=23.5 mL for C2 and C2/C8; 22.5 mL for C3 and C2/C3 runs), septum inlets, regulated supply of nitrogen, ethylene and propylene, and equipped with disposable PEEK mechanical stirrers (800 RPM). The autoclaves were prepared by purging with dry nitrogen at 110°C or 115°C for 5 hours and then at 25°C for 5 hours.

Ethylene Polymerization (PE) or Ethylene/1-octene Copolymerization (EO):

The reactor was prepared as described above, and then purged with ethylene. For MAO (Act ID=1) activated runs, toluene, 1-octene (100 µL when used), and activator (MAO) were added via syringe at room temperature and atmospheric pressure. The reactor was then brought to process temperature (80°C) and charged with ethylene to process pressure (75 psig=618.5 kPa or 200 psig=1480.3 kPa) while stirring at 800 RPM. The pre-catalyst solution was then added via syringe to the reactor at process conditions. For dimethylanilinium tetrakis(perfluorophenyl)borate (Act ID=2) activated runs, toluene, 1-octene (100 µL when used) and scavenger (TnOAl, 0.5 µmol) were added via syringe at room temperature and atmospheric pressure. The reactor was then brought to process temperature (80°C) and charged with ethylene to process pressure (75 psig=618.5 kPa or 200 psig=1480.3 kPa) while stirring at 800 RPM. The activator solution, followed by the pre-catalyst solution, was injected via syringe to the reactor at process conditions. Ethylene was allowed to enter (through the use of computer controlled solenoid valves) the autoclaves during polymerization to maintain reactor gauge pressure (+/-2 psig). Reactor temperature was monitored and typically maintained within +/-1°C. Polymerizations were halted by addition of approximately 50 psi O₂/Ar (5 mole % O₂) gas mixture to the autoclave for approximately 30 seconds. The polymerizations were quenched after a predetermined cumulative amount of ethylene had been added (maximum quench value in psid) or for a maximum of 30 minutes polymerization time. Afterwards, the reactors were cooled and vented. Polymers were isolated after the solvent was removed in-vacuo. Yields reported include total weight of polymer and residual catalyst. Catalyst activity is reported as grams of polymer per mmol transition metal compound per hour of reaction time (g/mmol•hr). Ethylene homopolymerization runs are summarized in Table 1, and ethylene/1-octene copolymerization runs are summarized in Table 2.

Propylene Polymerization (PP):

The reactor was prepared as described above, then heated to 40°C, and then purged with propylene gas at atmospheric pressure. For MAO activated runs, toluene or isohexane, MAO, and liquid propylene (1.0 mL) were added via syringe. The reactor was then heated to process temperature (70°C or 100°C) while stirring at 800 RPM. The pre-catalyst solution was added via syringe with the reactor at process conditions. For dimethylanilinium tetrakis(perfluorophenyl)borate or dimethylanilinium tetrakis(perfluoronaphthyl)borate activated runs, isohexanes, liquid propylene (1.0 mL) and scavenger (TnOAl, 0.5 µmol) were added via syringe. The reactor was then brought to process temperature (70 or 100°C) while stirring at 800 RPM. The activator solution, followed by the pre-catalyst solution, were injected via syringe to the reactor at process conditions. Reactor temperature was monitored and typically maintained within $\pm 1^\circ\text{C}$. Polymerizations were halted by addition of approximately 50 psi O₂/Ar (5 mole % O₂) gas mixture to the autoclaves for approximately 30 seconds. The polymerizations were quenched based on a predetermined pressure loss (maximum quench value) or for a maximum of 30 min. The reactors were cooled and vented. The polymers were isolated after the solvent was removed in-vacuo. The actual quench time (s) is reported as quench time (s). Yields reported include total weight of polymer and residual catalyst. Catalyst activity is reported as grams of polymer per mmol transition metal compound per hour of reaction time (g/mmol•hr). Propylene homopolymerization examples are reported in Table 3 with additional characterization in Table 4.

Propylene Polymerization and Ethylene-Propylene Copolymerization (EP):

The reactor was prepared as described above, then heated to 40°C and then purged with ethylene gas at atmospheric pressure for reactors using ethylene. The listed ethylene pressure (10, 20, 40, 60, or 80 psid) was then added to the reactor. Isohexanes and scavenger (TnOAl, 0.5 µmol) were added via syringe. The stirrers were then started and maintained at 800 RPM. Liquid propylene (1.0 ml) was then injected into the reactor. The reactor was then brought to process temperature (70°C). The activator solution, followed by the pre-catalyst solution, was injected via syringe to the reactor at process conditions. Reactor temperature was monitored and typically maintained within $\pm 1^\circ\text{C}$. Polymerizations were halted by addition of approximately 50 psi O₂/Ar (5 mole % O₂) gas mixture to the autoclaves for approximately 30 seconds. The polymerizations were quenched based on a predetermined pressure loss (quench value) of approximately 12 psid pressure loss or for a maximum of 45 minutes polymerization time. The reactors were cooled and vented. The polymer was

isolated after the solvent was removed in-vacuo. The quench times are reported in Table 5 for each run. Yields reported include total weight of polymer and residual catalyst. Catalyst activity is reported as grams of polymer per mmol transition metal compound per hour of reaction time (g/mmol•hr). Propylene polymerization examples and ethylene/propylene
5 copolymerization examples are collected in Table 5.

Polymer Characterization

For analytical testing, polymer sample solutions were prepared by dissolving polymer in 1,2,4-trichlorobenzene (TCB, 99+% purity from Sigma-Aldrich) containing 2,6-di-tert-butyl-4-methylphenol (BHT, 99% from Aldrich) at 165°C in a shaker oven for approximately
10 3 hours. The typical concentration of polymer in solution was between 0.1 to 0.9 mg/mL with a BHT concentration of 1.25 mg BHT/mL of TCB. Samples were cooled to 135°C for testing.

High temperature size exclusion chromatography was performed using an automated “Rapid GPC” system as described in US 6,491,816; US 6,491,823; US 6,475,391; US
15 6,461,515; US 6,436,292; US 6,406,632; US 6,175,409; US 6,454,947; US 6,260,407; and US 6,294,388; each of which is incorporated herein by reference. Molecular weights (weight average molecular weight (Mw) and number average molecular weight (Mn)) and molecular weight distribution (MWD = Mw/Mn), which is also sometimes referred to as the polydispersity (PDI) of the polymer, were measured by Gel Permeation Chromatography
20 using a Symyx Technology GPC equipped with evaporative light scattering detector (ELSD) and calibrated using polystyrene standards (Polymer Laboratories: Polystyrene Calibration Kit S-M-10: Mp (peak Mw) between 5000 and 3,390,000). Alternatively, samples were measured by Gel Permeation Chromatography using a Symyx Technology GPC equipped with dual wavelength infrared detector and calibrated using polystyrene standards (Polymer
25 Laboratories: Polystyrene Calibration Kit S-M-10: Mp (peak Mw) between 580 and 3,039,000). Samples (250 µL of a polymer solution in TCB were injected into the system) were run at an eluent flow rate of 2.0 mL/minute (135°C sample temperatures, 165°C oven/columns) using three Polymer Laboratories: PLgel 10µm Mixed-B 300 x 7.5mm columns in series. No column spreading corrections were employed. Numerical analyses
30 were performed using Epoch® software available from Symyx Technologies or Automation Studio software available from Freeslate. The molecular weights obtained are relative to linear polystyrene standards. Molecular weight data is reported in Tables 1, 2, 3 and 5 under the headings Mn, Mw and PDI as defined above. PDI values marked with an “^” indicate that

the dual wavelength infrared detector was used; no additional marking indicates that the ELSD was used.

Differential Scanning Calorimetry (DSC) measurements were performed on a TA-Q100 instrument to determine the melting point of the polymers. Samples were pre-annealed at 220°C for 15 minutes and then allowed to cool to room temperature overnight. The samples were then heated to 220°C at a rate of 100°C/minute and then cooled at a rate of 50°C/minute. Melting points were collected during the heating period. The results are reported in the Tables 1, 2, 3, and 5 under the heading, T_m (°C).

Samples for infrared analysis were prepared by depositing the stabilized polymer solution onto a silanized wafer (Part number S10860, Symyx). By this method, approximately between 0.12 and 0.24 mg of polymer is deposited on the wafer cell. The samples were subsequently analyzed on a Bruker Equinox 55 FTIR spectrometer equipped with Pike's MappIR specular reflectance sample accessory. Spectra, covering a spectral range of 5000 cm⁻¹ to 500 cm⁻¹, were collected at a 2 cm⁻¹ resolution with 32 scans.

For ethylene-1-octene copolymers, the wt% octene in the copolymer was determined via measurement of the methyl deformation band at ~1375 cm⁻¹. The peak height of this band was normalized by the combination and overtone band at ~4321 cm⁻¹, which corrects for path length differences. The normalized peak height was correlated to individual calibration curves from ¹H NMR data to predict the wt% octene content within a concentration range of ~2 to 35 wt% for octene. Typically, R² correlations of 0.98 or greater are achieved. These numbers are reported in Table 2 under the heading C8 (wt%).

For ethylene-propylene copolymers, the wt% ethylene is determined via measurement of the methylene rocking band (~770 cm⁻¹ to 700 cm⁻¹). The peak area of this band is normalized by sum of the band areas of the combination and overtone bands in the 4500 cm⁻¹ to 4000 cm⁻¹ range. The normalized band area is then correlated to a calibration curve from ¹³C NMR data to predict the wt.% ethylene within a concentration range of ~5 to 50 wt.%. Typically, R² correlations of 0.98 or greater are achieved. These numbers are reported in Table 5 under the heading C2 (wt%).

For some samples, polymer end-group analysis was determined by ¹H NMR using a Varian Unity+400 MHz instrument run with a single 30° flip angle, RF pulse. 120 pulses with a delay of 8 seconds between pulses were signal averaged. The polymer sample was dissolved in heated d₂-1,1,2,2-tetrachloroethane and signal collection took place at 120° C. Vinylenes were measured as the number of vinylenes per 1000 carbon atoms using the resonances

between 5.55-5.31 ppm. Trisubstituted end-groups ("trisubs") were measured as the number of trisubstituted groups per 1000 carbon atoms using the resonances between 5.30-5.11 ppm, by difference from vinyls. Vinyl end-groups were measured as the number of vinyls per 1000 carbon atoms using the resonances between 5.9-5.65 and between 5.13-4.98 ppm. Vinylidene end-groups were measured as the number of vinylidenes per 1000 carbon atoms using the resonances between 4.88-4.69 ppm. The values reported in Table 4 are % vinylene, % trisubstituted (% trisub), % vinyl and % vinylidene where the percentage is relative to the total olefinic unsaturation per 1000 carbon atoms.

¹³C NMR spectroscopy was used to characterize some polypropylene polymer samples produced in experiments collected in Table 3. This data is collected in Table 5. Unless otherwise indicated the polymer samples for ¹³C NMR spectroscopy were dissolved in d₂-1,1,2,2-tetrachloroethane and the samples were recorded at 125°C using a NMR spectrometer with a ¹³C NMR frequency of 150 MHz. Polymer resonance peaks are referenced to mmmm=21.8 ppm. Calculations involved in the characterization of polymers by NMR follow the work of F. A. Bovey in "Polymer Conformation and Configuration," Academic Press, New York 1969 and J. Randall in "Polymer Sequence Determination, Carbon-13 NMR Method," Academic Press, New York, 1977.

The stereo defects measured as "stereo defects/10,000 monomer units" are calculated from the sum of the intensities of mmrr, mmrm+rrmr, and rrmr resonance peaks times 5000. The intensities used in the calculations are normalized to the total number of monomers in the sample. Methods for measuring 2,1 regio defects/10,000 monomers and 1,3 regio defects/10,000 monomers follow standard methods. Additional references include Grassi, A. et al. *Macromolecules*, 1988, 21, 617-622 and Busico et al. *Macromolecules*, 1994, 27, 7538-7543. The average meso run length = 10000/[(stereo defects/10000 C) + (2,1-regio defects/10000 C) + (1,3-regio-defects/10000 C)].

Polymerization results are collected in Tables 1, 2, 3, 4, and 5 below. "Ex#" stands for example number. Under the Ex# column heading, the following abbreviations are defined: PE = polyethylene, EO = ethylene-1-octene copolymer, PP = polypropylene, EP=ethylene-propylene copolymer, CPE = comparative polyethylene, CEO = comparative ethylene-1-octene copolymer, CPP = comparative polypropylene, and CEP = comparative ethylene-propylene copolymer. Examples starting with a "C" as in CPP and CPE are comparative examples. "Cat ID" identifies the pre-catalyst used in the experiment. Corresponding letters identifying the pre-catalyst are located in the synthetic experimental

section or below for comparative pre-catalysts. "Cat (μmol)" is the amount of pre-catalyst added to the reactor. For all experiments using dimethylanilinium tetrakis(perfluorophenyl)borate (Act ID=2) or dimethylanilinium tetrakis(perfluoronaphthyl)borate (Act ID=3), the molar ratio of activator/pre-catalyst was 1.1.

5 For all experiments using MAO (Act ID=1) as the activator, a 500 Al/M molar ratio was used. T($^{\circ}\text{C}$) is the polymerization temperature which was typically maintained within $\pm 1^{\circ}\text{C}$. "Yield" is polymer yield, and is not corrected for catalyst residue. "Quench time (s)" is the actual duration of the polymerization run in seconds. "Quench Value (psid)" for ethylene based polymerization runs (no propylene) is the set maximum amount of ethylene uptake

10 (conversion) for the experiment. If a polymerization quench time is less than the maximum time set, then the polymerization ran until the set maximum value of ethylene uptake was reached. For propylene homopolymerization runs and ethylene-propylene copolymerization runs, quench value indicates the maximum set pressure loss (conversion) of propylene (for PP runs) or ethylene and propylene combined (for EP runs) during the polymerization. Activity is

15 reported at grams polymer per mmol of catalyst per hour.

Comparative catalysts for polymerization runs include:

- rac-Me₂Si[2,4-Me₂Ind]₂ZrCl₂ – comparative pre-catalyst C-1 (Cat ID = C-1);
 - rac-Me₂Si(2-Me-4-EtInd)₂ZrCl₂ – comparative pre-catalyst C-2 (Cat ID = C-2);
 - rac-Me₂Si(2,4-Me₂Ind)₂HfCl₂ – comparative pre-catalyst C-3 (Cat ID = C-3);
 - 20 rac-Me₂Si(2-Me-4-EtInd)₂HfCl₂ – comparative pre-catalyst C-4 (Cat ID = C-4);
 - rac-(CH₂)₄Si[2,4-Me₂Ind]₂HfCl₂ – comparative pre-catalyst C-5 (Cat ID = C-5);
 - rac-(CH₂)₄Si[2-Me-4-EtInd]₂HfCl₂ – comparative pre-catalyst C-6 (Cat ID = C-6);
 - rac-Me₂Si[2-MeInd]₂ZrCl₂ – comparative pre-catalyst C-7 (Cat ID = C-7);
 - rac-Me₂Si[2-MeInd]₂ZrMe₂ – comparative pre-catalyst C-8 (Cat ID = C-8);
 - 25 rac-(CH₂)₄Si[2-Et-4-MeInd]₂HfCl₂ – comparative pre-catalyst C-9 (Cat ID = C-9); and
 - rac-(CH₂)₄Si[2,4-Et₂Ind]₂HfCl₂ – comparative pre-catalyst C-10 (Cat ID = C-10);
- where Ind is inden-1-yl and (CH₂)₄Si is silolanediyl (also called cyclotetramethylenesilylene).

Polydispersity index (PDI) is defined to be Mw/Mn.

Table 1: Ethylene polymerization examples

Ex#	Cat ID	Act ID	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	Tm (°C)
PE-1	A	1	14	0.0774	813,547	325,462	535,075	1.64	135.9
PE-2	A	1	63	0.0941	216,806	352,585	586,832	1.66	134.1
PE-3	A	1	64	0.0958	217,247	407,129	646,034	1.59	133.6
PE-4	B	2	54	0.1009	269,566	315,978	562,136	1.78	135.7
PE-5	B	2	70	0.0962	199,321	333,501	590,895	1.77	135.2
PE-6	B	2	59	0.0940	228,649	411,942	672,628	1.63	135.4
PE-7	B	1	91	0.0989	156,846	332,543	544,471	1.64	133.8
PE-8	B	1	75	0.0975	187,952	384,321	698,852	1.82	134.9
PE-9	B	1	69	0.0955	200,466	331,997	555,096	1.67	134.2
PE-10	C	1	238	0.0847	51,333	825,734	1,458,366	1.77	134.7
PE-11	C	1	283	0.0861	43,842				
PE-12	C	1	153	0.0828	78,134	875,659	1,538,837	1.76	134.4
PE-13	D	2	59	0.0904	221,765	759,705	2,490,105	3.28	135.8
PE-14	D	2	77	0.0869	161,884	1,134,775	2,087,024	1.84	133.3
PE-15	D	2	65	0.0935	207,458	1,169,367	2,142,344	1.83	135.3
PE-16	D	1	143	0.0914	91,911	616,009	1,175,848	1.91	141.7
PE-17	D	1	272	0.0907	48,053	703,568	1,279,609	1.82	133.9
PE-18	D	1	252	0.0923	52,764	720,328	1,282,451	1.78	134.7
PE-19	E	1	148	0.1005	97,652	617,808	1,156,018	1.87	135.9
PE-20	E	1	309	0.0895	41,655	760,749	1,490,739	1.96	134.9
PE-21	E	1	255	0.0914	51,553	657,812	1,234,986	1.88	135.6
PE-22	F	1	274	0.0841	44,279	454,535	792,712	1.74	136.1
PE-23	F	1	233	0.0798	49,425	463,924	808,167	1.74	136.9
PE-24	F	1	207	0.0796	55,267				
PE-25	G	1	850	0.0313	5,301	137,172	1,496,705	10.91	134.3
PE-26	G	1	931	0.0325	5,026	132,676	1,581,538	11.92	134.1
PE-27	G	1	745	0.0312	6,030	123,526	1,519,633	12.30	134.3
PE-28	H	1	146	0.0858	84,857				
PE-29	H	1	197	0.0891	65,060	275,641	548,103	1.99	137.4
PE-30	H	1	136	0.0847	89,485				
PE-31	I	1	386	0.0332	12,373	151,795	569,163	3.75	134.5
PE-32	I	1	454	0.0332	10,537	141,673	551,944	3.90	133.7
PE-33	I	1	376	0.0327	12,530	151,763	572,743	3.77	134.6

Ex#	Cat ID	Act ID	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	Tm (°C)
PE-34	J	2	77	0.0825	154,286	195,565	531,085	2.72	135.4
PE-35	J	2	83	0.0808	140,183	69,412	555,118	8.00	137.8
PE-36	J	2	74	0.0821	158,903	194,052	531,692	2.74	135.7
PE-37	J	1	85	0.0823	140,085	297,837	521,056	1.75	133.4
PE-38	J	1	84	0.0816	140,723	323,365	563,313	1.74	136.1
PE-39	J	1	97	0.0834	123,683	323,349	540,937	1.67	133.6
PE-40	K*	2	153	0.0926	86,926	668,752	953,293	1.43	135.6
PE-41	K*	2	146	0.0845	83,571	523,709	798,243	1.52	134.3
PE-42	K*	2	177	0.0869	70,658	603,439	930,122	1.54	136.5
PE-43	K	1	102	0.1051	147,797	514,968	957,928	1.86	134.8
PE-44	K	1	112	0.0982	126,823	469,186	946,840	2.02	134.1
PE-45	K	1	96	0.1065	159,418	492,576	1,004,014	2.04	134.7
PE-46	L*	2	81	0.0863	158,127	1,330,594	2,445,401	1.84	135.8
PE-47	L*	2	57	0.0866	226,840	1,222,485	2,235,291	1.83	134.2
PE-48	L*	2	43	0.0879	301,335	1,181,677	2,096,612	1.77	135.6
PE-49	L	1	231	0.0828	53,281	585,251	1,174,374	2.01^	134.8
PE-50	L	1	232	0.0853	54,630	682,245	1,252,199	1.84^	135.1
PE-51	L	1	247	0.0850	51,138	657,496	1,238,802	1.88^	134.2

Total solvent volume: 5.0 ml toluene; 0.025 μ mol pre-catalyst for examples PE-1 through PE-46; 0.024 μ mol pre-catalyst for examples PE-46 through PE-51; Quench Value was set at 20 psid ethylene uptake.

*Pre-catalysts were pre-alkylated with 0.5 μ mol of triisobutyl aluminum prior to injection into the reactor.

5

^GPC data from dual wavelength infrared detector used with Automation Studio software.

Table 2: Ethylene-1-octene copolymerization examples

Ex#	Cat ID	Act ID	Pressure (psig)	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	C8 (wt%)	Tm (°C)
EO-1	A	1	75	41	0.1052	374,044	193,791	333,558	1.72	20.6	102.0
EO-2	A	1	75	48	0.1149	343,270	172,913	320,715	1.85	20.3	108.9
EO-3	A	1	75	49	0.4140	1,219,141	172,459	323,262	1.87	21.3	109.5
EO-4	A	1	200	36	0.1959	783,600	212,901	359,220	1.69	7.4	121.5
EO-5	A	1	200	45	0.2006	643,350	215,835	389,440	1.80	8.0	120.9
EO-6	A	1	200	43	0.2063	695,719	197,190	349,667	1.77	10.3	120.7
EO-7	B	1	75	45	0.1183	375,225	159,648	309,349	1.94	23.3	108.2
EO-8	B	1	75	44	0.1229	400,398	160,750	314,095	1.95	21.0	108.3
EO-9	B	1	75	43	0.1164	389,805	156,159	309,900	1.98	20.8	107.8
EO-10	B	1	200	37	0.2053	803,348	191,162	331,733	1.74	9.2	120.7
EO-11	B	1	200	37	0.2027	788,886	200,830	340,123	1.69	9.0	120.6
EO-12	B	1	200	36	0.2018	809,448	197,929	337,435	1.70	9.3	120.7
EO-13	B	2	75	41	0.1144	405,754	131,835	264,289	2.00	21.4	109.5
EO-14	B	2	75	40	0.1166	422,932	137,620	267,195	1.94	21.9	108.4
EO-15	B	2	75	38	0.1185	453,830	127,688	266,936	2.09	21.8	110.2
EO-16	B	2	200	27	0.1915	1,040,604	172,971	293,025	1.69	7.3	122.2
EO-17	B	2	200	37	0.2045	802,398	177,924	297,958	1.67	7.0	121.7
EO-18	B	2	200	34	0.2018	852,176	173,428	290,375	1.67	7.7	121.8
EO-19	C	1	75	116	0.0750	93,345	428,305	760,892	1.78	17.0	109.2
EO-21	C	1	75	118	0.0814	99,000	424,104	747,317	1.76	18.6	108.2

Ex#	Cat ID	Act ID	Pressure (psig)	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	C8 (wt%)	Tm (°C)
EO-22	C	1	200	125	0.1831	210,426	353,003	752,818	2.13	13.6	116.4
EO-23	C	1	200	114	0.1843	233,209	385,833	818,606	2.12	12.3	116.8
EO-24	C	1	200	110	0.1809	235,957	395,743	848,736	2.14	12.0	116.2
EO-25	D	1	75	136	0.0621	65,850	390,784	672,716	1.72	17.3	108.7
EO-26	D	1	75	134	0.0966	104,042	368,016	677,095	1.84	20.3	109.1
EO-27	D	1	75	105	0.0899	123,881	381,342	695,131	1.82	21.1	109.4
EO-28	D	1	200	93	0.1845	287,222	326,354	637,179	1.95	9.3	118.6
EO-29	D	1	200	127	0.1928	218,093	333,835	735,238	2.20	12.6	117.3
EO-30	D	1	200	128	0.2025	227,457	324,842	714,491	2.20	12.6	118.2
EO-31	D	2	75	146	0.1413	139,556	101,830	748,129	7.35	33.3	108.5
EO-32	D	2	75	167	0.1467	126,723	116,718	543,345	4.66	36.3**	101.8
EO-33	D	2	75	102	0.1375	194,882	109,411	701,351	6.41	32.8	107.6
EO-34	D	2	200	41	0.2161	753,472	68,447	1,079,001	15.76	21.6	100.1
EO-35	D	2	200	38	0.2219	852,096	58,226	986,781	16.95	22.6	99.8
EO-36	E	1	75	122	0.0636	75,007	436,418	719,009	1.65	11.2	110.4
EO-37	E	1	75	145	0.1027	102,274	351,200	711,031	2.02	21.5	107.2
EO-38	E	1	75	110	0.0783	102,876	420,857	700,468	1.66	13.7	109.4
EO-39	E	1	200	107	0.1838	247,126	370,293	748,712	2.02	8.1	118.1
EO-40	E	1	200	130	0.1930	213,456	307,148	842,951	2.74	12.8	116.2
EO-41	E	1	200	133	0.1901	206,599	330,605	787,487	2.38	9.5	117.0
EO-42	F	1	75	71	0.0866	175,887	238,315	473,537	1.99	8.4	113.3

Ex#	Cat ID	Act ID	Pressure (psig)	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	C8 (wt%)	Tm (°C)
EO-43	F	1	75	68	0.0845	178,678	241,929	460,146	1.90	8.9	113.2
EO-44	F	1	75	76	0.0883	167,085	232,102	466,510	2.01	9.2	113.9
EO-45	F	1	200	97	0.1776	262,841	224,333	607,992	2.71	6.4	121.4
EO-46	F	1	200	105	0.1756	241,744	238,660	595,437	2.49	6.9	121.3
EO-47	F	1	200	104	0.1750	243,478					
EO-48	G	1	75	261	0.0334	18,421	103,015	189,351	1.84	8.0	113.6
EO-49	G	1	75	368	0.0352	13,774	87,238	183,316	2.10	8.1	113.3
EO-50	G	1	75	231	0.0321	19,976	103,287	186,866	1.81	9.0	112.8
EO-51	G	1	200	79	0.0433	79,328	196,785	389,660	1.98	4.6	122.8
EO-52	G	1	200	86	0.0463	77,979	205,313	403,146	1.96	4.5	122.5
EO-53	G	1	200	81	0.0431	76,246	198,888	390,929	1.97	4.0	122.8
EO-54	H	1	75	64	0.0869	194,613	134,375	252,272	1.88	19.3	85.7
EO-55	H	1	75	60	0.0764	182,448	154,414	258,243	1.67	18.3	88.2
EO-56	H	1	75	54	0.0810	214,412					
EO-57	H	1	200	180	0.1908	152,895	125,188	398,280	3.18	14.3	106.5
EO-58	H	1	200	156	0.1979	182,443	84,470	384,898	4.56	13.8	108.3
EO-59	H	1	200	156	0.1648	151,734	48,359	176,309	3.65	19.2	105.9
EO-60	I	1	75	701	0.0349	7,165	73,955	137,813	1.86	12.2	110.2
EO-61	I	1	75	611	0.0360	8,490	71,881	241,910	3.37	12.1	110.4
EO-62	I	1	75	643	0.0352	7,882	68,513	227,939	3.33	12.1	111.3
EO-63	I	1	200	136	0.0439	46,482	212,809	393,502	1.85	5.8	118.6

Ex#	Cat ID	Act ID	Pressure (psig)	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	C8 (wt%)	Tm (°C)
EO-64	I	1	200	156	0.0445	40,972	201,650	482,275	2.39	5.8	119.4
EO-65	I	1	200	116	0.0413	51,181	198,929	442,800	2.23	6.5	118.7
EO-66	J	1	75	61	0.0870	204,039	127,730	219,381	1.72	19.9	85.4
EO-67	J	1	75	60	0.0844	201,552	138,064	227,995	1.65	19.8	86.4
EO-68	J	1	75	58	0.0880	218,107	130,502	225,577	1.73	20.2	84.8
EO-69	J	1	200	156	0.2073	190,987	297,003	606,149	2.04	12.1	109.7
EO-70	J	1	200	148	0.1991	193,197	83,350	355,471	4.26	13.7	107.5
EO-71	J	1	200	143	0.2015	203,193	79,211	346,478	4.37	14.6	108.0
EO-72	J	2	75	43	0.1055	354,126	48,896	135,384	2.77	25.0	85.6
EO-73	J	2	75	44	0.1089	354,787	51,311	146,735	2.86	22.4	86.3
EO-74	J	2	75	44	0.1107	359,027	49,634	154,012	3.10	22.0	84.7
EO-75	J	2	200	99	0.2006	293,263	25,289	484,587	19.16	13.6	111.1
EO-76	J	2	200	100	0.1958	282,234	36,948	510,452	13.82	14.2	110.8
EO-77	J	2	200	95	0.1938	292,835	222,803	550,149	2.47	14.4	110.9
EO-78	K	1	75	72	0.1278	257,028	155,379	452,281	2.91	30.3	104.5
EO-79	K	1	75	89	0.1224	197,375	126,721	453,729	3.58	27.3	106.4
EO-80	K	1	75	89	0.1303	211,536	103,684	380,130	3.67	34.6	104.8
EO-81	K	1	200	51	0.2123	599,435	125,238	531,427	4.24	12.7	116.9
EO-82	K	1	200	58	0.1639	408,332	100,848	483,989	4.80	14.6	116.3
EO-83	K	1	200	55	0.1983	522,989	114,143	530,861	4.65	13.1	117.1
EO-84	K*	2	75	54	0.1008	269,799	238,859	371,814	1.56	21.2	99.4

Ex#	Cat ID	Act ID	Pressure (psig)	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	C8 (wt%)	Tm (°C)
EO-85	K*	2	75	76	0.0943	177,971	303,826	461,470	1.52	17.6	102.7
EO-86	K*	2	75	74	0.0939	182,232	308,678	453,374	1.47	16.2	104.3
EO-87	K*	2	200	114	0.1850	233,071	291,119	465,357	1.60	11.5	117.6
EO-88	K*	2	200	122	0.1868	221,393	306,238	482,540	1.58	10.4	117.8
EO-89	K*	2	200	118	0.1957	238,618	280,052	460,833	1.65	11.6	118.1
EO-90	L	1	75	152	0.0606	59,200	478,005	817,488	1.71^	13.8	105.5
EO-91	L	1	75	146	0.0590	59,960	422,444	757,024	1.79^	14.3	105.1
EO-92	L	1	75	150	0.0588	58,245	463,583	824,663	1.78^	15.3	105.1
EO-93	L	1	200	153	0.1667	162,105	449,047	873,852	1.95^	9.7	113.7
EO-94	L	1	200	143	0.1637	170,797	457,542	871,130	1.90^	9.7	114.1
EO-95	L	1	200	140	0.1671	177,329	421,602	844,930	2.00^	10.6	114.4
EO-96	L*	2	75	249	0.1246	74,331	248,820	512,382	2.06	34.4	100.3
EO-97	L*	2	75	164	0.1227	111,655	252,341	520,920	2.06	32.4	
EO-98	L*	2	75	224	0.1213	80,604	297,124	586,696	1.97	31.0	99.7
EO-99	L*	2	200	87	0.2022	344,602	305,672	927,970	3.04	21.9	111.8
EO-100	L*	2	200	96	0.1941	301,762	204,422	646,982	3.16	23.3	110.7
EO-101	L*	2	200	87	0.1933	330,191	268,116	723,459	2.70	21.7	110.9

Total solvent volume: 4.9 ml toluene; 0.025 μ mol pre-catalyst for examples EO-1 through EO-89; 0.024 μ mol pre-catalyst for examples EO-90 through EO-101; Quench Value was set at 20 psid ethylene uptake if 75 psid ethylene pressure was used, or 15 psid ethylene uptake if 200 psid ethylene pressure was used

*Pre-catalysts were pre-alkylated with 0.5 μ mol of trisobutyl aluminum prior to injection into the reactor

^GPC data from dual wavelength infrared detector used with Automation Studio software

**Outside calibration range

Table 3: Propylene polymerization examples

Ex#	Cat ID	Act ID	Cat (μmol)	Isohexane (uL)	Toluene (uL)	T (C)	Quench value (psi)	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	Tm (°C)
PP-1	A	1	0.040	3841	258	70	20	109	0.2222	184,313	52,101	89,804	1.72	151.0
PP-2	A	1	0.040	3841	258	70	20	120	0.3208	240,600	51,152	90,217	1.76	151.2
PP-3	A	1	0.040	3841	258	70	20	113	0.3072	244,240	55,793	95,130	1.71	151.5
PP-4	A	1	0.025	3882	217	70	15	144	0.2365	236,172	73,447	123,855	1.69	152.4
PP-5	A	1	0.025	3882	217	70	15	154	0.2515	235,322	70,881	118,539	1.67	150.9
PP-6	A	1	0.025	3882	217	70	15	149	0.2442	236,323	68,263	115,775	1.70	151.9
PP-7	A	1	0.040	3841	258	100	20	91	0.2633	261,268	18,656	33,646	1.80	143.6
PP-8	A	1	0.040	3841	258	100	20	89	0.2390	242,503	17,895	32,404	1.81	143.5
PP-9	A	1	0.040	3841	258	100	20	93	0.2382	229,775	18,236	32,576	1.79	143.6
PP-10	A	1	0.025	3882	217	100	15	135	0.1912	203,645	26,221	42,028	1.60	145.4
PP-11	A	1	0.025	3882	217	100	15	156	0.1766	162,807	24,460	39,109	1.60	144.3
PP-12	A	1	0.025	3882	217	100	15	125	0.1848	213,060	27,573	44,858	1.63	145.0
PP-13	B	1	0.040	3841	258	70	20	114	0.2950	232,487	58,122	98,129	1.69	151.8
PP-14	B	1	0.040	3841	258	70	20	128	0.3129	219,493	53,957	94,821	1.76	151.3
PP-15	B	1	0.040	3841	258	70	20	131	0.2315	159,046	50,352	91,141	1.81	151.0
PP-16	B	1	0.025	3882	217	70	15	135	0.2226	237,440	69,534	116,726	1.68	151.6
PP-17	B	1	0.025	3882	217	70	15	143	0.2418	244,174	65,840	112,580	1.71	152.0
PP-18	B	1	0.025	3882	217	70	15	154	0.2635	246,390	65,167	112,986	1.73	152.6
PP-19	B	1	0.040	3841	258	100	20	92	0.1952	191,164	19,120	34,416	1.80	143.5
PP-20	B	1	0.040	3841	258	100	20	97	0.2577	239,103	18,313	33,695	1.84	143.6
PP-21	B	1	0.040	3841	258	100	20	88	0.2322	238,562	19,764	34,915	1.77	143.6
PP-22	B	1	0.025	3882	217	100	15	145	0.1839	182,632	27,965	44,103	1.58	144.9

Ex#	Cat ID	Act ID	Cat (μmol)	Isohexane (uL)	Toluene (uL)	T (C)	Quench value (psi)	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	Tm (°C)
PP-23	B	1	0.025	3882	217	100	15	135	0.1826	194,773	28,340	46,043	1.62	146.1
PP-24	B	1	0.025	3882	217	100	15	159	0.1666	150,978	31,064	47,987	1.54	146.1
PP-25	B	2	0.040	3832	268	70	15	53	0.3093	528,216	24,210	53,428	2.21	149.4
PP-26	B	2	0.040	3832	268	70	15	51	0.3518	624,497	19,024	49,192	2.59	149.3
PP-27	B	2	0.040	3832	268	70	15	42	0.2988	643,349	20,741	49,957	2.41	148.7
PP-28	B	2	0.040	3832	268	70	15	45	0.2899	582,388	19,983	51,210	2.56	148.6
PP-29	B	2	0.040	3832	268	70	15	43	0.3644	760,928	20,703	50,095	2.42	148.6
PP-30	B	2	0.040	3832	268	100	15	64	0.2334	329,765	9,839	19,203	1.95	141.8
PP-31	B	2	0.040	3832	268	100	15	49	0.2637	483,360	7,010	15,692	2.24	139.1
PP-32	B	2	0.040	3832	268	100	15	51	0.2626	466,154	8,785	17,972	2.05	140.3
PP-33	B	2	0.040	3832	268	100	15	51	0.2762	483,619	7,943	16,360	2.06	140.8
PP-34	B	2	0.040	3832	268	100	15	52	0.2588	452,272	7,958	16,752	2.11	140.3
PP-35	C	1	0.040	3841	258	70	20	1534	0.1743	10,229	140,365	238,564	1.70	155.8
PP-36	C	1	0.040	3841	258	70	20	1371	0.1788	11,739	130,479	219,647	1.68	157.1
PP-37	C	1	0.040	3841	258	70	20	1671	0.1787	9,624	139,454	232,168	1.66	156.4
PP-38	C	1	0.040	3841	258	100	20	794	0.1452	16,461	33,798	54,318	1.61	148.8
PP-39	C	1	0.040	3841	258	100	20	820	0.1508	16,543	31,327	50,410	1.61	149.1
PP-40	C	1	0.040	3841	258	100	20	1007	0.1400	12,519	30,639	49,987	1.63	148.1
PP-41	D	1	0.040	3841	258	70	20	1801	0.1345	6,720	132,051	222,181	1.68	156.7
PP-42	D	1	0.040	3841	258	70	20	1311	0.1746	11,991	140,413	224,113	1.60	157.1
PP-43	D	1	0.040	3841	258	70	20	1507	0.1731	10,339	129,064	216,542	1.68	157.4
PP-44	D	1	0.040	3841	258	100	20	768	0.1350	15,820	31,078	49,172	1.58	149.3
PP-45	D	1	0.040	3841	258	100	20	859	0.1228	12,869	27,928	44,269	1.59	147.6

Ex#	Cat ID	Act ID	Cat (μmol)	Isohexane (uL)	Toluene (uL)	T (C)	Quench value (psi)	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	Tm (°C)
PP-46	D	1	0.040	3841	258	100	20	892	0.1361	13,727	32,830	53,208	1.62	149.9
PP-47	D	2	0.040	3832	268	70	15	33	0.2860	784,756	12,590	52,397	4.16	145.4
PP-48	D	2	0.040	3832	268	70	15	73	0.3326	411,747	30,928	77,319	2.50	150.0
PP-49	D	2	0.040	3832	268	70	15	48	0.3202	599,127	28,117	74,382	2.65	149.2
PP-50	D	2	0.040	3832	268	70	15	35	0.3216	831,724	13,004	53,321	4.10	145.8
PP-51	D	2	0.040	3832	268	70	15	37	0.2422	584,397	17,385	66,765	3.84	147.6
PP-52	D	2	0.040	3832	268	70	15	41	0.3325	733,456	15,497	63,594	4.10	147.3
PP-53	D	2	0.040	3832	268	100	15	73	0.1940	240,165	13,929	27,321	1.96	143.1
PP-54	D	2	0.040	3832	268	100	15	1802	0.0000					
PP-55	D	2	0.040	3832	268	100	15	24	0.2676	1,024,851	6,029	17,041	2.83	137.2
PP-56	D	2	0.040	3832	268	100	15	27	0.3185	1,065,613	5,905	17,710	3.00	138.1
PP-57	D	2	0.040	3832	268	100	15	24	0.3047	1,152,227	7,951	20,891	2.63	139.8
PP-58	D	2	0.040	3832	268	100	15	25	0.3005	1,073,214	5,740	15,302	2.67	137.0
PP-59	E	1	0.040	0	4099	70	15	586	0.1320	20,266	117,061	193,977	1.66	156.4
PP-60	E	1	0.040	0	4099	70	15	649	0.1319	18,302	121,768	202,573	1.66	156.4
PP-61	E	1	0.040	0	4099	70	15	535	0.1281	21,541	124,933	207,468	1.66	156.9
PP-62	E	1	0.040	0	4099	100	15	530	0.1052	17,854	29,729	48,263	1.62	148.6
PP-63	E	1	0.040	0	4099	100	15	747	0.1079	13,005	30,558	49,866	1.63	148.8
PP-64	E	1	0.040	0	4099	100	15	743	0.0989	11,988	28,482	45,997	1.61	148.6
PP-65	F	1	0.040	3841	258	70	20	1802	0.0468	2,337	6,910	10,345	1.50	143.8
PP-66	F	1	0.040	3841	258	70	20	1800	0.0563	2,814	8,845	13,614	1.54	145.7
PP-67	F	1	0.040	3841	258	70	20	1802	0.0550	2,746	9,033	13,868	1.54	145.7
PP-68	F	1	0.080	0	4098	70	15	1800	0.0862	2,155	6,178	9,855	1.60	143.5

Ex#	Cat ID	Act ID	Cat (μmol)	Isohexane (uL)	Toluene (uL)	T (C)	Quench value (psi)	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	Tm (°C)
PP-69	F	1	0.080	0	4098	70	15	1802	0.0866	2,162	6,102	9,744	1.60	143.5
PP-70	F	1	0.080	0	4098	70	15	1800	0.0879	2,197	6,081	9,674	1.59	142.8
PP-71	F	1	0.040	3841	258	100	20	1801	0.0714	3,567	2,010	2,393	1.19	120.7
PP-72	F	1	0.040	3841	258	100	20	1802	0.0720	3,597	1,976	2,349	1.19	120.3
PP-73	F	1	0.040	3841	258	100	20	1802	0.0712	3,556	1,946	2,293	1.18	118.0
PP-74	F	1	0.080	0	4098	100	15	1332	0.0885	2,990	1,608	1,878	1.17	111.4
PP-75	F	1	0.080	0	4098	100	15	1317	0.0714	2,440	1,570	1,791	1.14	136.2
PP-76	F	1	0.080	0	4098	100	15	1360	0.0900	2,978	1,651	1,951	1.18	112.1
PP-77	G	1	0.040	3841	258	70	20	1802	0.0422	2,108	2,791	3,661	1.31	
PP-78	G	1	0.040	3841	258	70	20	1801	0.0466	2,329	3,135	4,209	1.34	
PP-79	G	1	0.040	3841	258	70	20	1802	0.0458	2,288	2,942	3,901	1.33	
PP-80	G	1	0.040	3841	258	100	20	1801	0.0246	1,229				
PP-81	G	1	0.040	3841	258	100	20	1802	0.0221	1,104	1,414	1,498	1.06	
PP-82	G	1	0.040	3841	258	100	20	1801	0.0181	905	1,414	1,488	1.05	
PP-83	H	1	0.040	3841	258	70	20	1800	0.1187	5,935	9,723	15,762	1.62	147.6
PP-84	H	1	0.040	3841	258	70	20	1801	0.0858	4,287	11,437	17,130	1.50	148.0
PP-85	H	1	0.040	3841	258	70	20	1803	0.1129	5,636	9,885	16,118	1.63	148.5
PP-86	H	1	0.080	0	4098	70	15	518	0.1333	11,573	5,976	9,642	1.61	145.6
PP-87	H	1	0.080	0	4098	70	15	531	0.1360	11,534	6,361	10,302	1.62	144.8
PP-88	H	1	0.080	0	4098	70	15	613	0.1358	9,964	6,212	9,963	1.60	145.0
PP-89	H	1	0.040	3841	258	100	20	1801	0.0885	4,422	2,142	2,679	1.25	127.7
PP-90	H	1	0.040	3841	258	100	20	1801	0.0838	4,188	2,045	2,528	1.24	123.4
PP-91	H	1	0.040	3841	258	100	20	1802	0.0983	4,910				

Ex#	Cat ID	Act ID	Cat (μmol)	Isohexane (uL)	Toluene (uL)	T (C)	Quench value (psi)	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	Tm (°C)
PP-92	H	1	0.080	0	4098	100	15	425	0.1069	11,313	1,718	2,052	1.19	119.0
PP-93	H	1	0.080	0	4098	100	15	432	0.1055	10,987	1,755	2,087	1.19	119.5
PP-94	H	1	0.080	0	4098	100	15	415	0.1031	11,171	1,682	1,986	1.18	108.9
PP-95	I	1	0.040	3841	258	70	15	1803	0.0282	1,408	9,903	81,880	8.27	142.0
PP-96	I	1	0.040	3841	258	70	15	1800	0.0093	465				
PP-97	I	1	0.040	3841	258	70	15	1802	0.0087	435				
PP-98	I	1	0.040	3841	258	100	15	1802	0.0324	1,618	11,185	19,621	1.75	138.2
PP-99	I	1	0.040	3841	258	100	15	1800	0.0091	455				
PP-100	I	1	0.040	3841	258	100	15	1802	0.0057	285				
PP-101	J	1	0.040	3841	258	70	15	1802	0.0876	4,376	11,172	17,637	1.58	149.6
PP-102	J	1	0.040	3841	258	70	15	1801	0.1058	5,288	9,842	16,125	1.64	148.5
PP-103	J	1	0.040	3841	258	70	15	1801	0.0952	4,758	10,158	16,399	1.61	149.5
PP-104	J	1	0.040	3841	258	100	15	1800	0.0688	3,440	1,999	2,429	1.21	124.4
PP-105	J	1	0.040	3841	258	100	15	1729	0.0629	3,274	1,963	2,353	1.20	121.8
PP-106	J	1	0.040	3841	258	100	15	1802	0.0857	4,281	2,149	2,675	1.24	126.9
PP-107	J	2	0.040	3832	268	70	15	1800	0.0103	515	7,038	11,251	1.60	144.5
PP-108	J	2	0.080	3664	436	70	15	525	0.1474	12,632	5,345	8,913	1.67	141.1
PP-109	J	2	0.080	3664	436	70	15	566	0.1575	12,513	7,276	11,334	1.56	143.4
PP-110	J	2	0.080	3664	436	70	15	540	0.1580	13,169	6,389	10,621	1.66	142.3
PP-111	J	2	0.040	3832	268	100	15	1800	0.0814	4,069	1,686	2,003	1.19	
PP-112	J	2	0.040	3832	268	100	15	1002	0.0988	8,876	1,682	1,978	1.18	133.1
PP-113	J	2	0.040	3832	268	100	15	952	0.0997	9,429	1,635	1,927	1.18	115.1
PP-114	J	2	0.080	3664	436	100	15	460	0.1185	11,597	1,792	2,070	1.16	114.1

Ex#	Cat ID	Act ID	Cat (μmol)	Isohexane (uL)	Toluene (uL)	T (C)	Quench value (psi)	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	Tm (°C)
PP-115	J	2	0.080	3664	436	100	15	539	0.1163	9,717	1,776	2,058	1.16	114.1
PP-116	J	2	0.080	3664	436	100	15	472	0.1129	10,773	1,775	2,031	1.14	112.0
PP-117	K	1	0.025	0	4099	70	7.5	81	0.1950	348,387	83,658	127,890	1.53	154.4
PP-118	K	1	0.025	0	4099	70	7.5	104	0.1759	244,258	115,599	168,124	1.45	155.0
PP-119	K	1	0.025	0	4099	70	7.5	81	0.2335	416,654	88,240	136,224	1.54	154.5
PP-120	K	1	0.025	0	4099	100	7.5	83	0.1424	248,553	34,662	52,822	1.52	149.1
PP-121	K	1	0.025	0	4099	100	7.5	70	0.1592	327,966	31,889	49,196	1.54	148.0
PP-122	K	1	0.025	0	4099	100	7.5	68	0.1500	318,584	30,527	46,978	1.54	149.6
PP-123	L	1	0.077	0	4098	70	8	178	0.0970	25,365	92,027	139,402	1.51	156.0
PP-124	L	1	0.077	0	4098	70	8	181	0.1065	27,387	87,291	134,431	1.54	156.7
PP-125	L	1	0.077	0	4098	70	8	173	0.0961	25,857	89,890	138,573	1.54	155.6
PP-126	L	1	0.077	0	4098	70	8	163	0.1199	34,169	77,478	167,316	2.16 [^]	157.4
PP-127	L	1	0.077	0	4098	70	8	178	0.1211	31,659	78,594	171,709	2.18 [^]	157.4
PP-128	L	1	0.077	0	4098	70	8	161	0.1205	34,740	76,762	167,676	2.18 [^]	157.6
PP-129	L	1	0.077	0	4098	70	8	144	0.1266	40,820	80,609	172,695	2.14 [^]	156.4
PP-130	L	1	0.077	0	4098	70	8	159	0.1331	38,823	80,457	171,710	2.13 [^]	157.4
PP-131	L	1	0.077	0	4098	70	8	144	0.1297	41,877	77,938	168,273	2.16 [^]	156.6
PP-132	L	1	0.077	0	4098	100	8	151	0.1097	33,890	22,885	34,583	1.51	147.0
PP-134	L	1	0.077	0	4098	100	8	133	0.1056	36,805	23,378	35,340	1.51	147.4
PP-135	L	1	0.077	0	4098	100	8	160	0.1087	31,627	23,562	35,511	1.51	148.2
PP-136	L	1	0.077	0	4098	100	8	117	0.1191	47,471	22,461	43,702	1.95 [^]	147.6
PP-137	L	1	0.077	0	4098	100	8	123	0.1239	46,698	19,006	37,862	1.99 [^]	147.6
PP-138	L	1	0.077	0	4098	100	8	129	0.1178	42,372	20,636	40,109	1.94 [^]	147.8

Ex#	Cat ID	Act ID	Cat (μmol)	Isohexane (uL)	Toluene (uL)	T (C)	Quench value (psi)	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	Tm (°C)
PP-139	L	1	0.077	0	4098	100	8	114	0.1190	48,406	20,735	41,134	1.98 [^]	147.1
PP-140	L	1	0.077	0	4098	100	8	109	0.1166	49,965	19,406	38,727	2.00 [^]	148.3
PP-141	L	1	0.077	0	4098	100	8	117	0.1255	50,000	21,330	38,028	1.78 [^]	147.1
PP-142	D	2	0.020	3916	184	70	12	46.3	0.3091	1,201,685	29,459	71,088	2.41	145.9
PP-143	D	2	0.020	3916	184	70	12	43.4	0.3312	1,373,641	32,006	73,455	2.30	147.1
PP-144	D	2	0.020	3916	184	70	12	46	0.3296	1,289,739	27,672	69,298	2.50	146.9
PP-145	D	2	0.020	3916	184	100	12	40.4	0.2235	995,792	10,700	22,322	2.09	141.6
PP-146	D	2	0.020	3916	184	100	12	35.4	0.2611	1,327,627	9,133	20,571	2.25	138.0
PP-147	D	2	0.020	3916	184	100	12	32.8	0.2422	1,329,146	10,152	20,931	2.06	139.6
PP-148	D	3	0.020	3916	184	70	12	52.6	0.3099	1,060,494	49,650	117,199	2.36	150.2
PP-149	D	3	0.020	3916	184	70	12	58.5	0.3327	1,023,692	49,850	119,464	2.40	150.8
PP-150	D	3	0.020	3916	184	70	12	59.1	0.3412	1,039,188	47,150	114,711	2.43	151.3
PP-151	D	3	0.020	3916	184	100	12	45.2	0.2444	973,274	16,226	33,137	2.04	142.6
PP-152	D	3	0.020	3916	184	100	12	45	0.2087	834,800	18,082	34,617	1.91	143.3
PP-153	D	3	0.020	3916	184	100	12	49	0.2354	864,735	16,147	35,116	2.17	143.5
CPP-1	C-1	1	0.080	0	265	70	5	301	0.0521	7,783	66,393	110,301	1.66	138.5
CPP-2	C-1	1	0.080	0	265	70	5	324	0.0527	7,315	63,094	106,092	1.68	138.6
CPP-3	C-1	1	0.100	0	331	70	5	240	0.0624	9,353	64,138	112,805	1.76	134.9
CPP-4	C-1	1	0.100	0	331	70	5	222	0.0560	9,062	63,788	105,815	1.66	133.3
CPP-5	C-2	1	0.025	0	4099	70	7.5	162	0.0831	74,095	72,417	103,663	1.43	143.5
CPP-6	C-2	1	0.025	0	4099	70	7.5	176	0.1075	88,205	72,911	107,306	1.47	143.3
CPP-7	C-2	1	0.025	0	4099	70	7.5	154	0.0871	81,233	72,449	104,518	1.44	143.3
CPP-8	C-2	1	0.025	0	4099	100	7.5	125	0.0716	82,814	18,609	26,172	1.41	134.0

Ex#	Cat ID	Act ID	Cat (μmol)	Isohexane (uL)	Toluene (uL)	T (C)	Quench value (psi)	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	Tm (°C)
CPP-9	C-2	1	0.025	0	4099	100	7.5	134	0.0712	76,743	17,468	25,677	1.47	134.6
CPP-10	C-2	1	0.025	0	4099	100	7.5	139	0.0757	78,310	18,241	25,266	1.39	133.6
CPP-11	C-3	1	0.040	0	4099	70	8	1023	0.0608	5,348	55,738	81,650	1.46	151.8
CPP-12	C-3	1	0.040	0	4099	70	8	1162	0.0658	5,096	53,737	79,557	1.48	151.9
CPP-13	C-3	1	0.040	0	4099	70	8	1159	0.0611	4,744	57,491	83,420	1.45	152.1
CPP-14	C-3	1	0.040	0	4099	100	8	864	0.0549	5,720	13,601	19,878	1.46	145.1
CPP-15	C-3	1	0.040	0	4099	100	8	677	0.0449	5,973	11,373	16,861	1.48	142.4
CPP-16	C-3	1	0.040	0	4099	100	8	800	0.0541	6,088	13,248	19,370	1.46	143.5
CPP-17	C-4	1	0.025	0	4099	70	7.5	1801	0.0434	3,470	52,296	82,094	1.57	148.6
CPP-18	C-4	1	0.025	0	4099	70	7.5	1802	0.0488	3,900	61,091	90,275	1.48	148.6
CPP-19	C-4	1	0.025	0	4099	70	7.5	1800	0.0442	3,536	59,086	88,825	1.50	148.6
CPP-20	C-4	1	0.025	0	4099	100	7.5	1801	0.0390	3,118	15,807	22,904	1.45	140.2
CPP-21	C-4	1	0.025	0	4099	100	7.5	1800	0.0430	3,440	13,695	20,340	1.49	140.5
CPP-22	C-4	1	0.025	0	4099	100	7.5	1801	0.0257	2,055	12,323	18,027	1.46	138.7
CPP-23	C-5	1	0.050	0	4099	70	8	835	0.0617	5,321	50,959	76,581	1.50	149.5
CPP-24	C-5	1	0.050	0	4099	70	8	892	0.0612	4,941	52,441	79,829	1.52	149.9
CPP-25	C-5	1	0.050	0	4099	70	8	944	0.0650	4,959	56,232	84,346	1.50	150.0
CPP-26	C-5	1	0.050	0	4099	100	8	574	0.0544	6,821	13,376	20,509	1.53	141.6
CPP-27	C-5	1	0.050	0	4099	100	8	591	0.0525	6,400	12,253	19,016	1.55	141.2
CPP-28	C-5	1	0.050	0	4099	100	8	692	0.0520	5,408	11,035	17,207	1.56	140.3
CPP-29	C-6	1	0.080	0	4098	70	8	473	0.0755	7,180	38,184	55,893	1.46	148.5
CPP-30	C-6	1	0.080	0	4098	70	8	472	0.0712	6,788	42,195	62,468	1.48	148.9
CPP-31	C-6	1	0.080	0	4098	70	8	514	0.0701	6,136	44,454	65,482	1.47	148.9

Ex#	Cat ID	Act ID	Cat (μmol)	Isohexane (uL)	Toluene (uL)	T (C)	Quench value (psi)	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	Tm (°C)
CPP-32	C-6	1	0.080	0	4098	100	8	315	0.0689	9,830	10,219	15,820	1.55	139.9
CPP-33	C-6	1	0.080	0	4098	100	8	318	0.0680	9,629	10,457	16,104	1.54	140.3
CPP-34	C-6	1	0.080	0	4098	100	8	306	0.0686	10,088	10,129	15,608	1.54	139.9
CPP-35	C-7	1	0.025	3882	217	70	20	408	0.1750	61,765	62,517	97,293	1.56	140.5
CPP-36	C-7	1	0.025	3882	217	70	20	431	0.1740	58,175	69,889	108,627	1.55	141.2
CPP-37	C-7	1	0.025	3882	217	70	20	432	0.1907	63,640	61,091	97,955	1.60	140.8
CPP-38	C-7	1	0.025	3882	217	100	20	415	0.1515	52,632	18,730	29,690	1.59	125.4
CPP-39	C-7	1	0.025	3882	217	100	20	370	0.1541	59,909	18,572	29,223	1.57	126.1
CPP-40	C-7	1	0.025	3882	217	100	20	356	0.1456	58,944	17,362	27,869	1.61	124.0
CPP-41	C-8	1	0.025	3882	217	70	20	364	0.1904	75,406	60,930	94,347	1.55	141.5
CPP-42	C-8	1	0.025	3882	217	70	20	380	0.1988	75,256	57,535	91,377	1.59	140.8
CPP-43	C-8	1	0.025	3882	217	70	20	358	0.1979	79,647	57,913	86,184	1.49	140.8
CPP-44	C-8	1	0.025	3882	217	100	20	383	0.1593	59,925	17,058	25,017	1.47	123.7
CPP-45	C-8	1	0.025	3882	217	100	20	436	0.1557	51,459	17,111	23,752	1.39	123.8
CPP-46	C-8	1	0.025	3882	217	100	20	467	0.1560	48,092	17,179	24,443	1.42	124.6
CPP-47	C-8	2	0.025	3895	205	70	15	55	0.2504	653,217	21,157	38,868	1.84	134.2
CPP-48	C-8	2	0.025	3895	205	70	15	61	0.2475	580,456	19,457	38,646	1.99	134.1
CPP-49	C-8	2	0.025	3895	205	70	15	59	0.2017	495,645	21,606	39,801	1.84	134.2
CPP-50	C-8	2	0.025	3895	205	100	15	144	0.1442	144,200	8,239	13,042	1.58	107.4
CPP-51	C-8	2	0.025	3895	205	100	15	197	0.1303	95,487	8,824	13,934	1.58	109.9
CPP-52	C-8	2	0.025	3895	205	100	15	102	0.1615	228,224	7,313	11,542	1.58	105.8
CPP-53	C-9	1	0.060	0	4099	70	10	1209	0.0778	3860	22818	43504	1.91^	150.9
CPP-54	C-9	1	0.060	0	4099	70	10	1409	0.0816	3475	27311	46621	1.71^	150.9

Ex#	Cat ID	Act ID	Cat (μ mol)	Isohexane (uL)	Toluene (uL)	T (C)	Quench value (psi)	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	Tm (°C)
CPP-55	C-9	1	0.060	0	4099	70	10	1374	0.0860	3755	24520	43853	1.79 [^]	150.9
CPP-56	C-9	1	0.060	0	4099	100	10	672	0.0693	6184	12335	100674	8.16 [^]	138.0
CPP-57	C-9	1	0.060	0	4099	100	10	723	0.0671	5570	5963	11233	1.88 [^]	138.5
CPP-58	C-9	1	0.060	0	4099	100	10	785	0.0676	5165	6905	11643	1.69 [^]	138.5
CPP-59	C-10	1	0.040	0	4099	70	8	1800	0.0261	1305	25078	43204	1.72 [^]	142.9
CPP-60	C-10	1	0.040	0	4099	70	8	1801	0.0299	1494	30110	46402	1.54 [^]	145.1
CPP-61	C-10	1	0.040	0	4099	70	8	1801	0.0339	1694	28609	49665	1.74 [^]	142.3
CPP-62	C-10	1	0.040	0	4099	100	8	1663	0.0498	2695	7424	13757	1.85 [^]	135.8
CPP-63	C-10	1	0.040	0	4099	100	8	1745	0.0486	2507	8065	13287	1.65 [^]	137.8

Total solvent volume: 4.1 ml

[^]GPC data from dual wavelength infrared detector used with Automation Studio software

Table 4: ¹³C NMR data for select polypropylene examples

Ex#	Cat ID	Act ID	T (C)	m	r	mmmm	mmmr	mmmr	mmmr	mmmr + mrrr	mmmm	mmrr	rrrr	mrrr	mrrm	stereo defects/10000 monomer	2,1-regio (ee) defects/10000 monomer	1,3 regio defects/10000 monomer	ave. meso run length
PP-5	A	1	70	0.961	0.039	0.9013	0.0421	0.0031	0.0146	0.0105	0.0029	0.0053	0.0029	0.0029	0.0172	140.4	21.9	0.0	61.6
PP-10	A	1	100	0.970	0.030	0.9142	0.0333	0.0091	0.0170	0.0055	0.0034	0.0062	0.0062	0.0006	0.0108	129.2	0.0	34.5	61.1
PP-17	B	1	70	0.980	0.020	0.9316	0.0223	0.0136	0.0119	0.0014	0.0126	0.0031	0.0002	0.0002	0.0034	129.3	23.1	11.1	61.2
PP-22	B	1	100	0.961	0.039	0.8845	0.0504	0.0060	0.0247	0.0045	0.0105	0.0075	0.0045	0.0045	0.0075	198.6	0.0	58.9	38.8
PP-28	B	2	70	0.972	0.028	0.8972	0.0516	0.0115	0.0180	0.0026	0.0026	0.0103	0.0000	0.0000	0.0064	115.4	0.0	56.0	58.3
PP-33	B	2	100	0.955	0.045	0.8286	0.0935	0.0062	0.0463	0.0005	0.0062	0.0021	0.0005	0.0005	0.0161	265.2	0.0	64.1	30.4
PP-51	D	2	70	0.948	0.052	0.8631	0.0476	0.0144	0.0364	0.0049	0.0039	0.0112	0.0020	0.0164	0.0164	226.6	0.0	36.8	38.0
PP-57	D	2	100	0.860	0.140	0.6603	0.0985	0.0374	0.0699	0.0066	0.0517	0.0285	0.0022	0.0449	0.0449	640.9	0.0	49.8	14.5
PP-59-61	E	1	70	0.979	0.021	0.9526	0.0208	0.0017	0.0069	0.0000	0.0002	0.0017	0.0001	0.0158	0.0158	35.8	10.4	12.7	169.7
PP-62-64	E	1	100	0.934	0.066	0.8788	0.0258	0.0146	0.0176	0.0047	0.0070	0.0035	0.0012	0.0468	0.0468	146.4	0.0	29.0	57.0
PP-68-70	F	1	70	0.922	0.078	0.8213	0.0582	0.0161	0.0198	0.0190	0.0136	0.0149	0.0097	0.0273	0.0273	262.3	0.0	0.0	38.1
PP-74-76	F	1	100	0.837	0.163	0.5675	0.1698	0.0211	0.0732	0.0662	0.0168	0.0212	0.0021	0.0620	0.0620	781.4	0.0	27.0	12.4
PP-87	H	1	70	0.962	0.038	0.8926	0.0465	0.0060	0.0226	0.0023	0.0090	0.0128	0.0023	0.0060	0.0060	169.3	0.0	52.0	45.2
PP-92-94	H	1	100	0.806	0.194	0.5440	0.1468	0.0225	0.0069	0.0561	0.1226	0.0181	0.0484	0.0345	0.0345	928.5	0.0	0.0	10.8
PP-101-103	J	1	70	0.981	0.019	0.9552	0.0160	0.0011	0.0142	0.0028	0.0014	0.0008	0.0013	0.0073	0.0073	92.3	0.0	0.0	108.4
PP-104-106	J	1	100	0.934	0.066	0.8453	0.0527	0.0038	0.0401	0.0144	0.0094	0.0056	0.0038	0.0249	0.0249	319.6	0.0	0.0	31.3
PP-109	J	2	70	0.960	0.040	0.8603	0.0750	0.0055	0.0273	0.0068	0.0041	0.0095	0.0000	0.0116	0.0116	190.9	0.0	0.0	52.4
PP-114	J	2	100	0.851	0.149	0.5859	0.1820	0.0068	0.0785	0.0563	0.0171	0.0205	0.0051	0.0478	0.0478	759.6	0.0	0.0	13.2
PP-118	K	1	70	0.990	0.010	0.9753	0.0096	0.0012	0.0058	0.0011	0.0015	0.0012	0.0016	0.0027	0.0027	42.0	16.1	5.6	157.0
PP-120	K	1	100	0.971	0.029	0.9362	0.0161	0.0028	0.0208	0.0076	0.0038	0.0076	0.0005	0.0047	0.0047	160.6	0.0	0.0	62.3
PP-123-125	L	1	70	0.988	0.012	0.9275	0.0480	0.0059	0.0101	0.0022	0.0012	0.0010	0.0005	0.0036	0.0036	67.0	7.2	6.2	124.4

	Ex#	Cat ID	Act ID	T (C)	m	r	mmmm	mmmr	mmrr	mmrr	mmrm+mmr	mmrm	rrrr	mmrr	mmrm	stereo defects/ 10000 monomer	2,1-regio (ee) defects/ 10000 monomer	ave. meso run length
	PP-132-135	L	1	100	0.970	0.030	0.8639	0.0765	0.0126	0.0261	0.0040	0.0043	0.0015	0.0009	0.0101	170.0	0.0	53.1
	PP-142	D	2	70	0.971	0.029	0.9265	0.0275	0.0026	0.0268	0.0002	0.0021	0.0014	0.0005	0.0126	143.1	0	61.8
	PP-145	D	2	100	0.934	0.066	0.8141	0.0699	0.0164	0.0541	0.0021	0.0109	0.0024	0.0009	0.0292	319.7	0	27.3
	PP-150	D	3	70	0.983	0.017	0.9533	0.0184	0.0021	0.0172	0.0000	0.0015	0.0000	0.0000	0.0074	92.5	0	89.1
	PP-151	D	3	100	0.958	0.042	0.8762	0.0499	0.0111	0.0333	0.0000	0.0092	0.0037	0.0018	0.0148	204.6	0	40.1
	CPP-5-7	C-2	1	70	0.755	0.245	0.5060	0.0788	0.0397	0.0714	0.1244	0.0651	0.0260	0.0534	0.0352	1293.7	41.2	7.5
	CPP-8-10	C-2	1	100	0.777	0.223	0.5385	0.0905	0.0353	0.0633	0.1082	0.0537	0.0280	0.0457	0.0369	1125.8	0.0	8.9
	CPP-11-13	C-3	1	70	0.955	0.045	0.8857	0.0406	0.0105	0.0023	0.0192	0.0142	0.0067	0.0091	0.0118	176.4	15.8	48.2
	CPP-23-25	C-5	1	70	0.930	0.070	0.8320	0.0312	0.0363	0.0153	0.0341	0.0125	0.0086	0.0155	0.0146	306.4	10.3	30.4
	CPP-26-28	C-5	1	100	0.923	0.077	0.7939	0.0632	0.0303	0.0216	0.0289	0.0205	0.0092	0.0159	0.0164	352.7	0.0	27.2
	CPP-29-31	C-6	1	70	0.968	0.032	0.8505	0.0871	0.0128	0.0236	0.0080	0.0038	0.0023	0.0015	0.0105	174.5	18.5	47.0
	CPP-32-34	C-6	1	100	0.947	0.053	0.7862	0.1146	0.0174	0.0399	0.0071	0.0101	0.0041	0.0023	0.0183	277.7	0.0	31.3
	CPP-53-55	C-9	1	70	0.936	0.064	0.8746	0.0357	0.0113	0.0205	0.0018	0.0057	0.0074	0.0005	0.0425	138.2	0.0	65.1
	CPP-56-58	C-9	1	100	0.911	0.089	0.8106	0.0557	0.0157	0.0419	0.0046	0.0119	0.0080	0.0009	0.0506	284.0	0.0	32.2

***The following polymer samples were mixed for ^{13}C NMR analysis:

PPP-59,60,61; PP-62,63,64; PP-68,69,70; PP-74,75,76; P-92,93,94; PP-101,102,103; PP-104,105,106; PP-123,124,125; P-132,133,134; CPP-5,6,7; CPP-8,9,10; CPP-11,12,13; CPP-23,24,25; CPP-26,27,28; CPP-29,30,31; CPP-32,33,34; CPP-53,54,55; CPP-56,57,58.

Table 5. Propylene polymerization examples and ethylene-propylene copolymerization examples

Ex#	Cat ID	Act ID	Cat (μmol)	C2 (psid)	Isohexane (uL)	Toluene (uL)	quench time (s)	yield (g)	Activity (g P/mmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	C2 (wt%)	Tm (°C)	% vinylene	% trisub	% vinyl	% vinylidene
PP-154	B	2	0.020	0	3895	205	65	0.2586	715,023	46,062	82,621	1.79	0.0	150.6				
PP-155	B	2	0.020	0	3895	205	83	0.2752	596,819	39,302	76,844	1.96	0.0	149.5	5.3	24.1	25.6	45.1
PP-156	B	2	0.020	0	3895	205	2700	0.0046	307									
PP-157	B	2	0.020	0	3895	205	59	0.2770	849,404	34,546	68,297	1.98	0.0	150.2	6.8	30.6	27.2	35.4
EP-1	B	2	0.020	10	3875	205	26	0.3095	2,159,302	21,447	55,205	2.57	5.8	119.8				
EP-2	B	2	0.020	10	3875	205	2703	0.0092	613									
EP-3	B	2	0.020	10	3875	205	36	0.3245	1,645,352	22,171	61,185	2.76	6.1	127.5	2.8	6.9	18.6	71.7
EP-4	B	2	0.020	10	3875	205	35	0.3183	1,636,971	26,017	67,172	2.58	6.9	118.5	2.3	5.3	18.8	73.7
EP-5	B	2	0.020	20	3855	205	26	0.3405	2,375,581	16,265	50,898	3.13	8.2	125.3	0.6	4.8	20.8	73.8
EP-6	B	2	0.020	20	3855	205	80	0.2123	475,299						4.0	20.0	17.0	59.0
EP-7	B	2	0.020	20	3855	205	45	0.2801	1,115,442	36,877	75,986	2.06	7.2	108.4				
EP-8	B	2	0.020	20	3855	205	38	0.3024	1,417,500	29,962	69,797	2.33	9.3	110.2				
EP-9	B	2	0.020	40	3835	205	24	0.3484	2,646,076	14,649	45,724	3.12	12.4	113.2				
EP-10	B	2	0.020	40	3835	205	23	0.3417	2,685,852	16,536	50,094	3.03	12.9	111.6	4.9	25.6	25.6	43.8
EP-11	B	2	0.020	40	3835	205	32	0.2937	1,672,975	25,256	61,842	2.45	14.0	98.7	7.9	34.2	25.0	32.9
EP-12	B	2	0.020	40	3835	205	25	0.3140	2,233,992	20,846	58,122	2.79	13.8	101.0				
EP-13	B	2	0.020	60	3815	205	14	0.3670	4,652,113	10,774	43,719	4.06	16.4	109.4	1.4	7.7	23.9	67.1
EP-14	B	2	0.020	60	3815	205	17	0.3771	3,923,584	10,519	39,635	3.77	9.1	113.1				
EP-15	B	2	0.020	60	3815	205	18	0.3575	3,535,714	13,639	48,900	3.59	11.7	105.1	1.1	4.9	22.7	71.4
EP-16	B	2	0.020	60	3815	205	22	0.3346	2,788,333	18,515	56,927	3.07	19.0	96.4				
EP-17	B	2	0.020	80	3795	205	14	0.3527	4,439,580	9,386	17,399	1.85	22.1	95.2				
EP-18	B	2	0.020	80	3795	205	17	0.3979	4,263,214	7,554	14,342	1.90	17.1	110.6	1.5	3.1	22.9	72.5

Ex#	Cat ID	Act ID	Cat (μmol)	C2 (psid)	Isohexane (uL)	Toluene (uL)	quench time (s)	yield (g)	Activity (g P/μmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	C2 (wt%)	Tm (°C)	% vinylene	% trisub	% vinyl	% vinylidene
EP-19	B	2	0.020	80	3795	205	19	0.3275	3,054,404	15,229	52,278	3.43	22.6		2.3	5.1	19.8	72.9
EP-20	B	2	0.020	80	3795	205	2700	0.0105	700	127,605	206,693	1.62	47.5					
PP-158	D	2	0.025	0	3869	231	38	0.3595	1,362,316	18,266	63,815	3.49	0.0	147.6				
PP-159	D	2	0.025	0	3869	231	56	0.2441	632,201	33,752	78,482	2.33	0.0	149.7				
PP-160	D	2	0.025	0	3869	231	44.8	0.2994	962,357	23,262	66,799	2.87	0.0	148.1	4.9	16.7	54.2	24.3
PP-161	D	2	0.025	0	3869	231	35.5	0.3364	1,364,552	14,140	57,752	4.08	0.0	144.6	2.0	11.2	62.5	24.3
EP-21	D	2	0.025	10	3849	231	2703	0	0									
EP-22	D	2	0.025	10	3849	231	37	0.3332	1,303,826	19,688	60,891	3.09	4.6*	113.9	3.3	9.0	54.9	32.8
EP-24	D	2	0.025	10	3849	231	22.6	0.3838	2,445,451	9,860	41,152	4.17	5.1*	105.2	0.5	5.4	64.5	29.6
EP-25	D	2	0.025	20	3829	231	27	0.3580	1,916,431	16,025	54,534	3.40	7.3	101.9				
EP-26	D	2	0.025	20	3829	231	24	0.3785	2,233,770	15,055	57,503	3.82	7.2	103.9	1.2	3.5	63.5	31.8
EP-27	D	2	0.025	20	3829	231	44.2	0.3127	1,018,751	26,928	71,551	2.66	7.1	102.8	2.0	6.9	52.0	39.2
EP-28	D	2	0.025	20	3829	231	22.2	0.3782	2,453,189	13,332	53,053	3.98	4.3*	100.3				
EP-29	D	2	0.025	40	3809	231	30	0.3248	1,585,464	22,187	64,761	2.92	9.1	85.9				
EP-30	D	2	0.025	40	3809	231	16	0.3750	3,375,000	12,568	55,488	4.41	11.4		0.9	5.5	65.4	28.1
EP-31	D	2	0.025	40	3809	231	28.7	0.3441	1,726,495	22,990	69,600	3.03	11.0					
EP-32	D	2	0.025	40	3809	231	17.5	0.3797	3,124,389	13,145	58,264	4.43	12.2		1.0	6.8	66.5	25.7
EP-33	D	2	0.025	60	3789	231	19	0.3609	2,794,065	13,721	56,519	4.12	11.1					
EP-34	D	2	0.025	60	3789	231	15.6	0.4186	3,864,000	13,964	61,405	4.40	11.4		0.5	4.3	64.6	30.6
EP-35	D	2	0.025	60	3789	231	23.1	0.4037	2,516,571	17,450	65,640	3.76	9.6					
EP-36	D	2	0.025	60	3789	231	15	0.4528	4,346,880	10,805	56,199	5.20	11.4		0.7	3.0	67.5	28.7
EP-37	D	2	0.025	80	3769	231	16	0.4306	3,827,556	10,100	51,849	5.13	17.7		0.4	5.6	65.6	28.4
EP-38	D	2	0.025	80	3769	231	10.6	0.4466	6,067,019	11,714	57,180	4.88	16.5		0.9	5.2	64.3	29.6
EP-39	D	2	0.025	80	3769	231	1409.3	0.0146	1,492	12,040	34,026	2.83	11.5					

Ex#	Cat ID	Act ID	Cat (μmol)	C2 (psid)	Isohexane (uL)	Toluene (uL)	quench time (s)	yield (g)	Activity (g P/nnmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	C2 (wt%)	Tm ($^{\circ}\text{C}$)	% vinylene	% trisub	% vinyl	% vinylidene
PP-162	E	1	0.040	0	0	4099	569.4	0.1013	16,012	116,598	180,818	1.55	0.0	155.5				
PP-163	E	1	0.040	0	0	4099	510.6	0.1038	18,296	132,895	208,482	1.57	0.0	155.3	9.4	15.6	46.9	28.1
PP-164	E	1	0.040	0	0	4099	607.6	0.1028	15,227	131,661	206,607	1.57	0.0	155.1	0.0	15.6	53.1	31.3
PP-165	E	1	0.040	0	0	4099	608.1	0.0967	14,312	131,702	208,146	1.58	0.0	155.2				
EP-40	E	1	0.040	10	0	4079	199.5	0.0979	44,165	136,095	199,229	1.46	8.0	107.2				
EP-41	E	1	0.040	10	0	4079	254.8	0.1000	35,322	124,306	192,436	1.55	7.8	106.9	1.5	1.5	16.7	80.3
EP-42	E	1	0.040	10	0	4079	267.1	0.0970	32,684	123,579	191,592	1.55	8.3	111.7				
EP-43	E	1	0.040	10	0	4079	320.8	0.0942	26,428	124,542	191,762	1.54	8.3	109.0	0.0	5.8	14.5	79.7
EP-44	E	1	0.040	20	0	4059	144.5	0.0990	61,661	127,569	196,404	1.54	14.4					
EP-45	E	1	0.040	20	0	4059	185.8	0.1007	48,778	129,960	200,749	1.54	12.7		3.4	5.1	16.9	74.6
EP-46	E	1	0.040	20	0	4059	238.8	0.1094	41,231	125,210	195,432	1.56	12.1	103.9				
EP-47	E	1	0.040	20	0	4059	233.5	0.0925	35,653	128,356	201,150	1.57	18.1		1.6	11.1	14.3	73.0
EP-48	E	1	0.040	40	0	4039	134.5	0.0917	61,361	141,798	214,561	1.51	25.3					
EP-49	E	1	0.040	40	0	4039	121.5	0.1099	81,407	127,118	199,200	1.57	23.9					
EP-50	E	1	0.040	40	0	4039	120.9	0.1072	79,801	128,520	199,860	1.56	23.9		6.7	5.0	13.3	75.0
EP-51	E	1	0.040	40	0	4039	145.1	0.0905	56,134	139,287	215,039	1.54	27.2		0.0	2.0	12.0	86.0
EP-52	E	1	0.040	60	0	4019	75.5	0.1154	137,563	148,160	228,351	1.54	32.1		2.0	0.0	20.0	78.0
EP-53	E	1	0.040	60	0	4019	92.9	0.1062	102,885	145,174	226,315	1.56	29.2					
EP-54	E	1	0.040	60	0	4019	101.9	0.0933	82,404	158,085	239,433	1.51	28.2		7.4	5.6	18.5	68.5
EP-55	E	1	0.040	60	0	4019	107.8	0.1072	89,499	152,359	237,910	1.56	37.1					
EP-56	E	1	0.040	80	0	3999	67	0.1089	146,284	160,566	248,466	1.55	38.9		0.0	0.0	16.2	83.8
EP-57	E	1	0.040	80	0	3999	62.7	0.1261	181,005	155,625	245,882	1.58	42.7					
EP-58	E	1	0.040	80	0	3999	69.6	0.1145	148,060	159,207	250,112	1.57	40.1					
EP-59	E	1	0.040	80	0	3999	82.6	0.1017	110,811	155,812	245,004	1.57	34.4		0.0	0.0	15.4	84.6

Ex#	Cat ID	Act ID	Cat (μmol)	C2 (psid)	Isohexane (uL)	Toluene (uL)	quench time (s)	yield (g)	Activity (g P/μmol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	C2 (wt%)	Tm (°C)	% vinylene	% trisub	% vinyl	% vinylidene
PP-166	J	2	0.080	0	3664	436	388.2	0.1230	14,258	7,175	11,664	1.63	0.0	143.2				
PP-167	J	2	0.080	0	3664	436	395.3	0.1237	14,082	6,584	10,527	1.60	0.0	142.1	0.6	1.5	19.7	78.2
PP-168	J	2	0.080	0	3664	436	420.5	0.1230	13,163	6,510	10,593	1.63	0.0	143.0				
PP-169	J	2	0.080	0	3664	436	397.6	0.1307	14,793	7,482	12,126	1.62	0.0	143.7	1.3	1.6	19.5	77.6
EP-60	J	2	0.040	10	3812	268	249.6	0.1068	38,510	11,683	19,202	1.64	14.2					
EP-61	J	2	0.040	10	3812	268	263.1	0.1051	35,952	12,046	19,644	1.63	14.1					
EP-62	J	2	0.040	10	3812	268	244.4	0.1153	42,459	12,490	20,413	1.63	14.7		0.0	1.6	22.2	76.2
EP-63	J	2	0.040	10	3812	268	253.6	0.1088	38,612	10,994	17,886	1.63	14.4		0.9	2.3	22.1	74.8
EP-64	J	2	0.040	20	3792	268	161.1	0.1091	60,950	13,665	22,799	1.67	20.2					
EP-65	J	2	0.040	20	3792	268	225.8	0.1162	46,315	14,878	24,324	1.63	19.0		0.0	0.0	22.8	77.2
EP-66	J	2	0.040	20	3792	268	224.2	0.1149	46,124	12,859	21,396	1.66	19.9					
EP-67	J	2	0.040	20	3792	268	190	0.1171	55,468	13,303	22,489	1.69	18.7		0.0	0.0	22.4	77.6
EP-68	J	2	0.040	40	3772	268	132.3	0.1275	86,735	18,949	32,273	1.70	31.5					
EP-69	J	2	0.040	40	3772	268	119.5	0.1314	98,962	18,937	32,981	1.74	28.8		0.0	0.0	23.8	76.2
EP-70	J	2	0.040	40	3772	268	105.4	0.1276	108,956	21,114	36,049	1.71	29.1		0.8	0.8	24.4	74.0
EP-71	J	2	0.040	40	3772	268	100.5	0.1154	103,343	21,721	35,704	1.64	32.2					
EP-72	J	2	0.040	60	3752	268	97.3	0.1311	121,264	20,069	34,874	1.74	30.9		0.0	0.0	23.8	76.2
EP-73	J	2	0.040	60	3752	268	82.6	0.1465	159,625	24,377	43,447	1.78	31.9		0.0	1.0	24.8	74.3
EP-74	J	2	0.040	60	3752	268	73.3	0.1423	174,720	24,661	44,107	1.79	37.1					
EP-75	J	2	0.040	60	3752	268	69.8	0.1406	181,289	23,773	42,399	1.78	39.5					
EP-76	J	2	0.040	80	3732	268	66.4	0.1605	217,545	28,148	51,590	1.83	42.5					
EP-77	J	2	0.040	80	3732	268	73	0.1597	196,890	26,648	49,844	1.87	42.2		0.0	0.0	24.2	75.8
EP-78	J	2	0.040	80	3732	268	83.5	0.1375	148,204	34,280	59,282	1.73	38.1					
EP-79	J	2	0.040	80	3732	268	81.2	0.1656	183,547	20,629	38,534	1.87	33.9		0.0	0.0	22.9	77.1

Ex#	Cat ID	Act ID	Cat (μmol)	C2 (psid)	Isohexane (uL)	Toluene (uL)	quench time (s)	yield (g)	Activity (g P/immol cat.hr)	Mn (g/mol)	Mw (g/mol)	PDI	C2 (wt%)	Tm ($^{\circ}\text{C}$)	% vinylene	% trisub	% vinyl	% vinylidene
CPP-64	C-8	2	0.015	0	3843	257	85	0.2873	815,035	26,061	43,859	1.68	0.0	134.3				
CPP-65	C-8	2	0.015	0	3843	257	88	0.2919	799,726	27,409	46,039	1.68	0.0	134.9	4.3	1.1	9.8	84.8
CEP-1	C-8	2	0.015	40	3803	257	30	0.2602	2,081,600	16,445	33,304	2.03	23.6					
CEP-2	C-8	2	0.015	40	3803	257	34	0.2851	1,989,070	18,702	34,664	1.85	23.1		0.0	9.7	17.0	73.3
CEP-3	C-8	2	0.015	80	3763	257	22	0.2651	2,931,982	16,025	47,570	2.97	36.8					
CEP-4	C-8	2	0.015	80	3763	257	24	0.2957	2,920,494	15,199	44,512	2.93	33.6		1.7	2.2	17.2	78.9
CPP-66	C-8	2	0.015	0	3843	257	85	0.3107	874,185	28,148	45,267	1.61	0.0	134.5				
CPP-67	C-8	2	0.015	0	3843	257	98	0.3015	739,122	22,346	41,469	1.86	0.0	134.2	0.0	9.0	13.0	78.0
CEP-5	C-8	2	0.015	40	3803	257	35	0.2867	1,971,576	15,564	32,020	2.06	19.5					
CEP-6	C-8	2	0.015	40	3803	257	38	0.2733	1,735,238	15,568	32,767	2.10	19.2		2.9	19.5	18.0	59.5
CEP-7	C-8	2	0.015	80	3763	257	22	0.3145	3,446,575	16,230	47,215	2.91	37.3					
CEP-8	C-8	2	0.015	80	3763	257	24	0.3080	3,092,887	17,002	47,432	2.79	35.7		2.4	7.3	20.0	70.2
CPP-68	C-8	1	0.015	0	3925	175	811	0.1744	51,642	67,135	103,027	1.53	0.0	141.4				
CPP-69	C-8	1	0.015	0	3925	175	925	0.1881	48,804	72,137	107,978	1.50	0.0	142.0	0.0	11.8	19.7	68.4
CEP-9	C-8	1	0.015	40	3885	175	88	0.1757	478,638	69,630	105,159	1.51	46.5	148.2				
CEP-10	C-8	1	0.015	40	3885	175	87	0.1715	472,560	73,012	109,924	1.51	47.3	150.3	2.9	10.1	14.5	72.5
CEP-11	C-8	1	0.015	80	3845	175	52	0.2023	928,337	83,382	132,653	1.59	54.2	126.8				
CEP-12	C-8	1	0.015	80	3845	175	59	0.2175	880,270	83,683	131,961	1.58	54.6		6.3	35.9	25.0	32.8
CPP-70	C-8	1	0.015	0	3925	175	876	0.1736	47,578	76,575	113,564	1.48	0.0	142.1				
CPP-71	C-8	1	0.015	0	3925	175	974	0.1708	42,108	69,302	103,118	1.49	0.0	142.0	3.3	37.4	22.0	37.4
CEP-13	C-8	1	0.015	40	3885	175	91	0.1564	412,031	72,009	107,954	1.50	46.6	136.3				
CEP-14	C-8	1	0.015	40	3885	175	79	0.1600	489,172	76,087	112,919	1.48	46.9		1.6	6.3	12.7	79.4
CEP-15	C-8	1	0.015	80	3845	175	48	0.1923	953,554	93,396	139,551	1.49	54.8*					
CEP-16	C-8	1	0.015	80	3845	175	55	0.2071	900,435	86,827	133,620	1.54	53.4	103.1	6.1	18.4	20.4	55.1


Total solvent 4.1 ml, *outside calibration range.

All documents described herein are incorporated by reference herein, including any priority documents and/or testing procedures to the extent they are not inconsistent with this text. As is apparent from the foregoing general description and the specific embodiments, while forms of the invention have been illustrated and described, various modifications can
5 be made without departing from the spirit and scope of the invention. Accordingly, it is not intended that the invention be limited thereby. Likewise, the term "comprising" is considered synonymous with the term "including." Likewise whenever a composition, an element or a group of elements is preceded with the transitional phrase "comprising", it is understood that we also contemplate the same composition or group of elements with transitional phrases
10 "consisting essentially of," "consisting of", "selected from the group of consisting of," or "is" preceding the recitation of the composition, element, or elements and vice versa. Likewise, the terms "comprising," "consisting essentially of," "consisting of" also include the product of the combinations of elements listed after the term.

Claims:

What is claimed is:

1. A compound represented by the formula: $T_y L A M X_{n-2}$
 wherein: A is a substituted or unsubstituted tetrahydro-*as*-indacenyl group bonded to M;
 5 L is substituted or unsubstituted monocyclic or polycyclic arenyl ligand or monocyclic or polycyclic heteroarenyl ligand bonded to M;
 M is a group 3, 4, 5, or 6 transition metal;
 T is a bridging group bonded to L and A;
 y is 0 or 1, indicating the absence or presence of T;
 10 X is a leaving group, typically a univalent anionic ligand, or two Xs are joined and bound to the metal atom to form a metallocycle ring, or two Xs are joined to form a chelating ligand, a diene ligand, or an alkylidene;
 n is the oxidation state of M and is 3, 4, 5, or 6.
- 15 2. The compound of claim 1 wherein the compound is represented by the formula 2:




wherein

- M is a group 3, 4, 5, or 6 transition metal;
 B is the oxidation state of M and is 3, 4, 5, or 6;
 20 C is B-2;
 T is a bridging group;
 y is 1 or 0 indicating the presence of absence of T;
 X is a leaving group;
 L is a substituted or unsubstituted monocyclic or polycyclic arenyl ligand or monocyclic or
 25 polycyclic heteroarenyl ligand bonded to M;
 each R^1 , R^2 , R^4 , and R^5 is independently hydrogen, or a C_1 - C_{50} substituted or unsubstituted hydrocarbyl, halocarbyl or silylcarbyl; and

each R^a , R^b , and R^c is independently C_1 - C_{10} alkyl, or hydrogen.

3. A compound represented by the formula (3):



5 wherein

M is a group 3, 4, 5, or 6 transition metal;

B is the oxidation state of M and is 3, 4, 5, or 6;

C is $B-2$;

T is a bridging group;

10 y is 1 or 0 indicating the presence of absence of T ;

X is a leaving group;

L is a substituted or unsubstituted monocyclic or polycyclic arenyl ligand or monocyclic or polycyclic heteroarenyl ligand bonded to M ;

15 each R^1 , R^2 , R^4 , and R^5 is independently hydrogen, or a C_1 - C_{50} substituted or unsubstituted hydrocarbyl, halocarbyl or silylcarbyl; and

each R^a , R^b , and R^c is independently C_1 - C_{10} alkyl, or hydrogen.



4. The compound of claim 1, 2, or 3 wherein M is a group 4 transition metal.

20 5. The compound of claim 1, 2, or 3 wherein M is zirconium or hafnium.

6. The compound of claim 2 or 3, wherein B is 4.

7. The compound of claim 1, 2, or 3 wherein each X is independently a halide, a hydride,
25 an alkyl group, an alkenyl group or an arylalkyl group.

8. The compound of claim 2, wherein y is 1 and T is selected from $(\text{CR}^8\text{R}^9)_x$, $(\text{SiR}^{10}\text{R}^{11})_x$, $\text{CR}^8\text{R}^9\text{SiR}^{10}\text{R}^{11}$, $\text{GeR}^{10}\text{R}^{11}$, BR^{12} , NR^{12} , PR^{12} , O or S where x is 1 or 2, R^8 and R^9 are independently selected from hydrogen, substituted or unsubstituted hydrocarbyl, halocarbyl, silylcarbyl, R^{10} , R^{11} and R^{12} are independently selected from substituted or unsubstituted hydrocarbyl, halocarbyl, silylcarbyl and any two or more adjacent R^8 , R^9 , R^{10} or R^{11} may optionally be bonded together to form a ring structure.
9. The compound of claim 2, wherein each R^a , R^b , R^c , R^1 , R^2 , R^4 and R^5 is independently hydrogen or a $\text{C}_1\text{-C}_{10}$ alkyl.
10. The compound of claim 2 or 3, wherein R^b and/or R^2 is independently a $\text{C}_1\text{-C}_{10}$ alkyl and each R^a , R^c , R^1 , R^4 and R^5 are hydrogen.
11. The compound of claim 2 or 3, wherein each R^2 is independently hydrogen, methyl, ethyl, propyl, butyl, pentyl or hexyl.
12. The compound of claim 2 or 3, wherein R^a and R^c are independently hydrogen, methyl or ethyl.
13. The compound of claim 2 or 3, wherein each R^b are independently hydrogen, methyl or ethyl.
14. The compound of claim 2 or 3, wherein each R^b and R^2 is independently methyl or ethyl and each R^a , R^c , R^1 , R^4 and R^5 is hydrogen.
15. The compound of claim 2 or 3, wherein each R^2 is methyl or ethyl.
16. A tetrahydro-*as*-indacenyl ligand wherein the ligand is derived from tetrahydro-*as*-indacene isomers represented by the formula 4a or 4b:



wherein R^3 is hydrogen or $\text{C}_1\text{-C}_{50}$ substituted or unsubstituted hydrocarbyl;

each R¹, R², R⁴, and R⁵ is independently hydrogen, or a C₁-C₅₀ substituted or unsubstituted hydrocarbyl, halocarbyl or silylcarbyl; and

each R^a, R^b, and R^c is independently C₁-C₅₀ substituted or unsubstituted hydrocarbyl, or hydrogen.

5

17. A catalyst system comprising the compound of any of claims 1 to 16, and an activator.

18. The catalyst system of claim 17, wherein the activator comprises a non-coordinating anion activator and / or an alumoxane.

10

19. The catalyst system of claim 17 or 18, where the catalyst system is supported.

20. A process to produce olefin polymer comprising contacting olefin monomer with the catalyst system of claim 17, 18 or 19.

15

21. The process of claim 20 wherein the monomer comprises ethylene and/or propylene.

22. The process of claim 20 or 21 wherein the catalyst system comprises one catalyst compound.

20

23. The process of claim 20, 21, or 22 wherein the process occurs at a temperature of from about 0°C to about 300°C, at a pressure in the range of from about 0.35 MPa to about 16 MPa, and at a time up to 300 minutes.

25

24. The process of claim 20, 21, 22 or 23 wherein the monomer comprises two or more of ethylene, propylene, butene, pentene, hexene, heptene, octene, nonene, decene, undecene, or dodecene.

25. The process of claim 20, 21, 22 or 23 wherein the monomer comprises ethylene, propylene and 5-ethylidene-2-norbornene.

30




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US2017/025400**A. CLASSIFICATION OF SUBJECT MATTER****C08F 4/6592(2006.01)i, C08F 4/642(2006.01)i, C08F 10/02(2006.01)i, C08F 10/04(2006.01)i, C08F 210/02(2006.01)i, C08F 10/06(2006.01)i, C08F 2/38(2006.01)i**

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C08F 4/6592; C07F 17/00; C08F 4/64; C07F 7/10; B01J 31/00; C08F 4/44; C08F 4/642; C08F 10/02; C08F 10/04; C08F 210/02; C08F 10/06; C08F 2/38

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Korean utility models and applications for utility models

Japanese utility models and applications for utility models

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKOMPASS(KIPO internal), STN(Registry, Caplus), Google & keywords: tetrahydro-as-indacene, catalyst, ligand, transition metal, activator, support, olefin

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2007-0015657 A1 (RIEGER, B. et al.) 18 January 2007 See claims 1-4; and formulas (I), (II), (IV).	1,2,4-16
A		3
A	KR 10-2015-0066484 A (LG CHEMICAL CO., LTD.) 16 June 2015 See claim 1; and formulas 1, 2a.	1-16
A	US 2005-0261510 A1 (GRAF, D. D. et al.) 24 November 2005 See claim 1; and formula (I).	1-16
A	US 2001-0014725 A1 (BECKE, S. et al.) 16 August 2001 See claim 1; and formula (I).	1-16
PX	US 2016-0244535 A1 (EXXONMOBIL CHEMICAL PATENTS INC.) 25 August 2016 See paragraph [0377]; and claim 3.	16



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

14 July 2017 (14.07.2017)

Date of mailing of the international search report

14 July 2017 (14.07.2017)

Name and mailing address of the ISA/KR

International Application Division

Korean Intellectual Property Office

189 Cheongsa-ro, Seo-gu, Daejeon, 35208, Republic of Korea



Facsimile No. +82-42-481-8578

Authorized officer

PARK, Jung Min

Telephone No. +82-42-481-3516



INTERNATIONAL SEARCH REPORT

International application No.

PCT/US2017/025400**Box No. II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)**

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☒ Claims Nos.: 18,21
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
Claims 18 and 21 are unclear because they refer to multiple dependent claims which do not comply with PCT Rule 6.4(a).
3. ☒ Claims Nos.: 17,19,20,22-25
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box No. III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fees, this Authority did not invite payment of any additional fees.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest and, where applicable, the payment of a protest fee.
- ☐ The additional search fees were accompanied by the applicant's protest but the applicable protest fee was not paid within the time limit specified in the invitation.
- ☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2017/025400

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2007-0015657 A1	18/01/2007	CA 2514645 A1 CN 100457784 C CN 101029102 A CN 1753914 A DE 10303225 A1 EP 1590376 A2 HK 1090935 A1 JP 2006-517991 A NO 20053659 A US 7381679 B2 WO 2004-067581 A2 WO 2004-067581 A3	12/08/2004 04/02/2009 05/09/2007 29/03/2006 05/08/2004 02/11/2005 12/06/2009 03/08/2006 28/10/2005 03/06/2008 12/08/2004 09/12/2004
KR 10-2015-0066484 A	16/06/2015	KR 10-2017-0076642 A	04/07/2017
US 2005-0261510 A1	24/11/2005	AT 399787 T AU 2003-233648 A1 BR 0313087 A BR 0313087 B1 CA 2492952 A1 CA 2492952 C CN 1309726 C CN 1671720 A EP 1529051 A1 EP 1529051 B1 ES 2305461 T3 JP 2005-534695 A JP 4482448 B2 NO 20050092 A US 7087773 B2 WO 2004-013149 A1	15/07/2008 23/02/2004 28/06/2005 16/04/2013 12/02/2004 16/10/2012 11/04/2007 21/09/2005 11/05/2005 02/07/2008 01/11/2008 17/11/2005 16/06/2010 16/02/2005 08/08/2006 12/02/2004
US 2001-0014725 A1	16/08/2001	CA 2332165 A1 DE 10003581 A1 EP 1120424 A2 EP 1120424 A3 JP 2001-253895 A US 6613713 B2	28/07/2001 02/08/2001 01/08/2001 16/10/2002 18/09/2001 02/09/2003
US 2016-0244535 A1	25/08/2016	WO 2016-114914 A1 WO 2016-114915 A1 WO 2016-114916 A1 WO 2016-171807 A1 WO 2016-171808 A1 WO 2016-172099 A1	21/07/2016 21/07/2016 21/07/2016 27/10/2016 27/10/2016 27/10/2016