

(19) DANMARK

(10) DK/EP 3930686 T3



(12)

Oversættelse af
europæisk patentskrift

Patent- og
Varemærkestyrelsen

(51) Int.Cl.: **A 61 K 9/00 (2006.01)** **A 61 K 9/06 (2006.01)** **A 61 K 33/26 (2006.01)**
A 61 K 47/02 (2006.01) **A 61 P 7/08 (2006.01)** **A 61 P 13/12 (2006.01)**

(45) Oversættelsen bekendtgjort den: **2023-09-11**

(80) Dato for Den Europæiske Patentmyndigheds
bekendtgørelse om meddelelse af patentet: **2023-05-31**

(86) Europæisk ansøgning nr.: **20717359.2**

(86) Europæisk indleveringsdag: **2020-02-28**

(87) Den europæiske ansøgnings publiceringsdag: **2022-01-05**

(86) International ansøgning nr.: **US2020020517**

(87) Internationalt publikationsnr.: **WO2020176894**

(30) Prioritet: **2019-02-28 US 201962812028 P**

(84) Designerede stater: **AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR**

(73) Patenthaver: **Renibus Therapeutics, Inc., 206 Grand Avenue, Suite 225, Southlake, TX 76092, USA**

(72) Opfinder: **GUILLEM, Alvaro F., 727 Lathrop Street, Lantana, Texas 76226, USA**
ZAGER, Richard A., 1100 Fairview Avenue, J2-302, Seattle, Washington 98109, USA
KEYSER, Donald Jeffrey, 1216 Wyndham Hill Lane, Southlake, Texas 76092, USA

(74) Fuldmægtig i Danmark: **AWA Denmark A/S, Strandgade 56, 1401 København K, Danmark**

(54) Benævnelse: **HIDTIL UKENDT JERNSAMMENSÆTNING OG FREMGANGSMÅDER TIL FREMSTILLING OG
ANVENDELSE HERAF**

(56) Fremdragne publikationer:
WO-A1-2018/148217
DE-A1- 19 547 356
DE-C- 862 482
US-A1- 2005 209 187

DK/EP 3930686 T3

DESCRIPTION

[0001] This application claims priority to provisional application no. 62/812,028, filed February 28, 2019, entitled Novel Iron Compositions and Methods of Marking and Using the Same.


BACKGROUND OF THE INVENTION

[0002] The intravenous (IV) iron agents are colloids that consist of spheroidal iron-carbohydrate nanoparticles as shown in Fig. 1. At the core of each particle is an iron-oxyhydroxide gel and the core is surrounded by a shell of carbohydrate that stabilizes the iron-oxyhydroxide (the main function of the ligand is to stabilize the complex and to protect it against further polynuclearization).


[0003] Iron carbohydrate complexes behave as prodrugs, since the iron has to be released from the iron(III)-hydroxide core. According to the proposed mechanism, after administration, the stable (Type 1) complexes such as ferric carboxymaltose and iron dextran are taken up by endocytosis by macrophages of the reticuloendothelial system (RES). See Danielson, J. Structure, chemistry, and pharmacokinetics of intravenous iron agents. Am. Soc. Nephrol. 2004, 15, S93-S98.

[0004] In the case of less stable iron(III)-carbohydrates (Type 2), significant amounts of labile iron from the complex can be released and lead to saturation of transferrin and, thus, to significant amounts of non-transferrin bound iron (NTBI), particularly if high doses are administered. This weakly bound Fe³⁺ is readily taken up in an unregulated way by cells and can induce oxidative stress. Evans, R.W.; Rafique, R.; Zarea, A.; Rapisarda, C.; Cammack, R.; Evans, P.J.; Porter, J.B.; Hider, R.C. Nature of non-transferrin-bound iron: studies on iron citrate complexes and the thalassemic era. J. Biol. Inorg. Chem. 2008, 13, 57-74.

[0005] There are five types of injectable iron-carbohydrate products currently approved by the FDA (1) INFeD®/ Dexferrum® (Iron dextran), Ferahem® (ferumoxytol), Injectafel® (ferric carboxymaltose), Venofer® (iron sucrose), Ferrlecit® (Sodium ferric gluconate complex). Iron sucrose, sold under the name Venofer®, is formulated as a colloidal suspension having a molecular weight (M_w) of about 34,000-60,000 Daltons and a molecular formula as follows:



where n is the degree of iron polymerization and m is the number of sucrose molecules (C₁₂H₂₂O₁₁) in complex with the poly-nuclear polymerized iron core:



[0006] Each mL contains 20 mg elemental iron as iron sucrose in water for injection. Venofer® is available in 5mL single dose vials (100 mg elemental iron per 5 mL) and 10 mL single dose vials (200 mg elemental iron per 10 mL). The drug product contains approximately 30% sucrose w/v (300 mg/mL) and has a pH of 10.5-11.1. The product contains no preservatives. The osmolarity of the injection is 1,250 mOsmo/L.

[0007] Methods for synthesizing iron carbohydrates are described in WO 97/11711 (1997) by Lawrence et al, which disclosed Ferric oxyhydroxide-dextran compositions for treating iron deficiency having ellipsoidal particles with a preferred molecular weight range of about 250,000 to 300,000 daltons.

[0008] Recently, iron sucrose has been used in combination with tin protoporphyrin (SnPP) to induce acquired cytoresistance without causing injury to the organ. See U.S. Pat. No. 9,844,563 to Zager et al. The present inventors have found a need for an iron sucrose formulation that can be easily combined with tin protoporphyrin (SnPP), that is stable, and can be injected into a patient to treat iron deficiency or for its renal protective effects either alone or in combination with another agent such as SnPP.

[0009] German patent number DE862482 discloses a process to prepare stable injectable solutions of salt of trivalent iron. US patent application publication no. US 2005/309187 discloses a process for preparing an iron sucrose complex, substantially free of excipients, for providing an iron sucrose complex co-precipitated with sucrose, and for providing iron sucrose complexes in aqueous solution. German patent number DE19547356 discloses an adsorbent for phosphate from an aqueous medium, in particular for inorganic or nutrient-bound phosphate from body fluids or nutrients. The adsorbent contains polynuclear beta-iron hydroxide stabilised by carbohydrates and/or humic acid. PCT publication number WO2018148217A1 discloses compositions, kits, and methods to protect organs by inducing acquired cytoresistance without causing injury to the organ. The compositions, kits, and methods utilize Me-porphyrin complexes, heme proteins, iron containing molecules, and/or vitamin B12 and, optionally, agents that impact heme protein metabolism.

SUMMARY OF THE INVENTION

[0010] The disclosure relates to aqueous iron sucrose compositions having desirable properties. In one aspect of the disclosure, the aqueous iron sucrose composition comprises iron sucrose and bicarbonate. In one aspect, the invention relates to an aqueous iron pharmaceutical composition comprising: iron sucrose; bicarbonate; and a pharmaceutically acceptable aqueous carrier. In another aspect, the invention relates to an aqueous iron composition comprises iron sucrose and bicarbonate for use in a method for prevention or treatment of a kidney disease or disorder comprising intravenously administering an aqueous iron composition in a therapeutically effective amount, wherein the aqueous iron composition comprises iron sucrose and bicarbonate.

DESCRIPTION OF THE FIGURES

[0011]

Fig. 1 shows the structure of an iron carbohydrate.

Fig. 2 is a Western blot of kidney at 18 hours post administration of aqueous iron compositions.

Fig. 3 shows GPC chromatograms of three S1 preparations.

Fig. 4 shows a zoom view of Fig. 3.

Fig. 5 shows GPC chromatograms of three S1 preparations.

Fig. 6 shows a zoom view of Fig. 5.

Fig. 7 shows GPC chromatograms of three S1 preparations.

Fig. 8 shows a zoom view of Fig. 7

Fig. 9 shows a comparison of GPC for S1, S2, and S3.

Fig. 10 shows an AFM top and side view for S1.

Fig. 11 shows S1, particles size analysis at location 1.

Fig. 12 shows S1, manual section analysis of three particles.

Fig. 13 shows FTIR spectra of S1 and the best library match, sucrose.

Fig. 14 shows FTIR spectra of S2 and the best library match, sucrose.

Fig. 15 shows FTIR spectra of S3 and the best library match, dextran.

Fig. 16 shows 1H NMR spectra of S1-preparation 1

FIG. 17 shows 1H NMR spectra of S2-preparation 1

FIG. 18 shows 1H NMR spectra of S3-preparation 1

FIG. 19 shows 13C NMR spectra of S1-preparation 1

FIG. 20 shows 13C NMR spectra of S2-preparation 1

FIG. 21 shows 13C NMR spectra of S3-preparation 1

FIG. 22 shows Raw data comparison for the three samples (lyophilized)

FIG. 23 shows Offset overlay of the data from all three samples (two replicates for S3)

Fig. 24 shows TGA thermogram of S1, S2 and S3 under nitrogen purge condition.

Fig. 25 shows DSC thermograms of S1, S2 and S3.

DETAILED DESCRIPTION OF THE INVENTION

[0012] In one aspect, the present disclosure involves an aqueous iron sucrose (FeS) and bicarbonate (FeS-bicarb) composition. The present inventors have found that this composition has beneficial properties. In one respect, the FeS-bicarb composition of the present disclosure can be utilized as a renal protective agent. The inventors have discovered that the FeS-bicarb composition according to aspects of the disclosure is preferentially absorbed in the kidney compared to commercially available forms of FeS. Further, the inventors have found that FeS-bicarb results in preferential upregulation of kidney protective molecule(s) relative to FeS alone. In another aspect, the FeS-bicarb composition of the present disclosure may be advantageously combined with other renal protective agents such as tin protoporphyrin (SnPP) to readily form injectable renal protective agents.

[0013] One advantage of using the FeS-bicarb is that this composition results in elevated renal protective effects. Specifically, the inventors found that FeS-bicarb preferentially upregulated kidney protective molecules relative to FeS alone. While not wishing to be bound by theory, the present inventors have proposed that the bicarb in addition to FeS may alter the relative levels of Fe(III) and Fe(II) present. Because of the observed redness in the FeS-bicarb product, the inventors have proposed that the compositions of the disclosure may include elevated levels of Fe(II). This could explain the elevated renal protective effects, given the higher reactivity of Fe(II) relative to Fe(III).

[0014] One advantage of using the FeS-bicarb is that the bicarb has a buffering effect. When using a tin protoporphyrin composition this can be advantageous since SnPP is best stored at low pH to prevent unwanted dimerization during storage. According to the present disclosure, the SnPP composition may be combined with the FeS-bicarb composition in a ratio of less than or equal to about 1:1 SnPP:FeS, such as about 1:2, about 1:4, about 1:8, about 1:10, about 1:20, about 1:50, about 1:100, about 1:1000, about 1:10,000, about 1:100,000, about 1:1,000,000.

[0015] In one aspect, the composition has a molecular weight measured using GPC as described in Example 1. The Mp is preferably within the range of between 25,000 and 35,000 Daltons, more preferably between 28,000 and 32,000 Daltons, and most preferably about 29,000 Daltons. The Mw is preferably within the range of between 25,000 and 45,000 Daltons, more preferably between 30,000 and 40,000 Daltons, even more preferably between 33,000 and 38,000 Daltons, and most preferably about 34,000 Daltons. The Mn is preferably within the range of between 15,000 and 30,000 Daltons, more preferably between 20,000 and 25,000 Daltons, and most preferably about 24,000 Daltons. The polydispersity (PDI) is preferably within the range of 1.35 to 1.60, more preferably within the range of 1.38 and 1.5, even more preferably within the range 1.40 and 1.48, and most preferably about 1.4.

[0016] In one aspect, the composition has a stable zeta potential of -3.0 mV or less, more preferably -7.0 mV or less, and most preferably around -10mV. In one aspect, the composition has a total organic carbon of less than 8.5%, preferably less than 8.0%, and most preferably about 7.7%. In one aspect, the osmolality as measured in accordance with Example 1 is within the range of 550 and 1600 mOsm/kg, preferably within the range of 1500 and 1580 mOsm/kg, and most preferably about 1540 mOsm/kg.

[0017] Any examples falling outside the scope of the claims are provided for comparative purposes only.

EXAMPLE 1

[0018] The present disclosure involves a composition that is prepared by dissolving enough iron sucrose complex in water (ca 3.5L) to give a 12 mg/mL (expressed as iron) solution when diluted to 6.0 L. The amount of iron sucrose needed was calculated for the final volume of liquid, 6100 mL (6.1L) so that the final concentration is 12 mg/mL. This requires 73.2 g of iron. The use potency of iron sucrose is 0.0550. Thus, 73.2 g / 0.0550 or 1331 g \pm 1 g of iron sucrose is needed. Iron sucrose, 1331 g \pm 1 g, was weighed directly into a 6.0 L Erlenmeyer flask. Approximately 3-3.5 L of water is added to the Erlenmeyer flask, and the contents of the flask are stirred.

[0019] Sodium bicarbonate is added in an amount such that the final sodium bicarbonate concentration is 10mg/mL when diluted to 6.0L. Sodium bicarbonate, 109.8 \pm 0.1g, is weighed and added to the 6.0 L flask.

[0020] Sodium chloride is added in an amount such that the final sodium chloride concentration is 9.0 mg/mL upon dilution. Sodium chloride, 54.9 \pm 0.1, is weighed and added to the 6.0 L flask. The suspension is stirred for 30-120 minutes to give a black opaque solution.

[0021] The pH of the solution is monitored with a pH meter while 1M sodium hydroxide is added in small portions until pH 10.30 is reached and remains stable. Sodium hydroxide, 40.0 \pm 0.1 g, was added to a 1.0 L Erlenmeyer flask. 1.0 \pm 0.1 L of water is added to the 1.0 L Erlenmeyer flask and stirred until all of the sodium hydroxide dissolved. A pH probe is affixed to monitor the pH of the 6.0 L Erlenmeyer flask and the sodium hydroxide is added in < 100 mL portions until the pH = 10.3 \pm 0.1. The solution is then stirred for 10 minutes. The pH is checked again after 10 minutes and if necessary adjusted to within pH = 10.3 \pm 0.1.

[0022] The solution is then transferred to a volumetrically accurate flask and diluted to 6.1L with water. A 2 L volumetric flask is used twice to transfer exactly 4L of the 10.3 pH solution to a 6L Erlenmeyer flask. The remaining 10.3 pH solution is diluted to 2 L in a volumetric flask and added to the 6L Erlenmeyer flask. The 100 mL graduated cylinder is used to add 100 \pm 0.1 mL to the 6.0 L Erlenmeyer, and the resulting solution is stirred for 10 minutes.

[0023] The resulting product solution appears dark red to brown. Two isotopes of iron are present in the sample preparation in a ratio consistent with that of the standard preparation. The resulting material had a pH of 10.3, which is within the preferred limits of 10.1-10.4. The resultant material had 11.5 / 11.6 parts per thousand (mg/mL) iron according to SOP 174472, which determines iron through inductively coupled plasma-mass spectroscopy.

[0024] Additional properties of the resultant composition are found in Table 1 below:

Table 1: Properties of the Composition of Example 1			
Test	Observation / Results	Specification	Reference to Test Method
Description	Brown to dark brown powder	Brown to dark brown powder	In house
Solubility	Freely soluble in water. Practically insoluble in methanol	Freely soluble in water. Practically insoluble in methanol	
Identification			
Iron	Red color discharge	Red color should discharge	USP38 Monographs of Iron sucrose Injection
Sucrose	Complies	The retention time of major peak in chromatogram of Assay Preparation corresponds to that in chromatogram of Standard Preparation, as obtained in the assay for sucrose.	USP38 Monographs of Iron sucrose injection.
Molecular Weight			
Mw	52149 Da	Between 34000 and 60000 Da	USP 38 Monographs of Iron sucrose Injection_Method Validate
Mn	35897 Da	Not Less Than 24000 Da	
Mw/Mn	1.453	Not more than 1.70	
pH	11.04	Between 10.50 and 11.0	USP38<791>Monograph of Iron sucrose injection
Specific Gravity	1.156	Between 1.135 and 1.165 at 20°C	USP38<841> Monograph of Iron sucrose injection

Molecular Weight			
Turbidity	At 4.67 pH	pH Between 4.40 and 5.30	USP38 Monograph of Iron Sucrose Injection
Alkalinity	0.68 mL	Between 0.5 mL and 0.8 mL of 0.1 N Hydrochloric Acid consumed per mL.	USP38 Monograph of Iron Sucrose Injection
Limit of Iron (II)	0.16 % w/v	Not more than 0.40% w/v	USP38 Monograph of Iron Sucrose Injection
Low Molecular Weight Fe(II) and Fe(III) complexes	No additional peaks in polarograms of Limit of Iron (II) observed	No additional peaks in polarograms of Limit of Iron (II) should be observed	USP38 Monograph of Iron Sucrose Injection
Content of Chloride	0.013 % w/w	Between 0.012 % w/w and 0.025 % w/w	USP 38 Monographs of Iron sucrose Injection_Method Validate
Assay of Sucrose (by HPLC)	85.21 % w/w	Between 80.00% (w/w) and 90.00% (w/w) on a dried basis	USP 38 Monographs of Iron sucrose Injection_Method Validate
Total Iron (III) Assay (by AAS)	5.66% w/w	Between 5.00% w/w and 6.00% w/w/ on a dried basis.	USP 38 Monographs of Iron sucrose Injection
Loss on Drying	1.24% w/w	Not More Than 5.00% w/w	USP38
Heavy Metals			
Arsenic	Less than 2.0 ppm	Not more than 2.0 ppm	In House
Copper	Less than 20 ppm	Not more than 20 ppm	In House
Lead	Less than 20 ppm	Not more than 20 ppm	In House
Residual Solvents	Methanol: 2624.41 ppm Acetone: 366 ppm	Methanol: NMT 3000 ppm Acetone: NMT 5000 ppm	USP 38<467> USP 38<467>
Osmolarity	1220 mOsmol/Lit	Between 1150 and 1350 mOsmol/Lit.	USP38<785> Monographs of Iron Sucrose Injection
Particulate Matter	54.66 1.66	≤10 µm 6000 per container ≤25 µm 600 per container	USP38<785> Monographs of Iron Sucrose Injection USP38<785> Monographs of Iron Sucrose Injection
Bacterial Endotoxin	Less Than 3.70 EU/mg of Iron	Not More Than 3.7 EU/mg of Iron	USP38<785> Monographs of Iron Sucrose Injection
Microbial Limit			
Total Aerobic Bacteria	20 CFU/g	Not More Than 100 CFU/g	USP38<61>
Total Yeast & Mold	Less Than 10 CFU/g	Not More Than 10 CFU/g	
Enterobacteriaceae count	Less Than 10 CFU/g	Not More Than 10 CFU/g	
Total E. Coli	Absent	Should be Absent	
Staph. Aureus	Absent	Should be Absent	
Pseudomonas Aeruginosa	Absent	Should be Absent	
Salmonella	Absent	Should be Absent	

[0025] The resulting FeS-bicarb composition has the following stoichiometry and physical constants are shown in Table 2 below:

Table 2: Stoichiometry and Physical Constants

Reagent	MW	Percentage Active	Nominal Amount
Iron Sucrose	736	5.5	1331 g
Sodium Bicarbonate	84	100	110 g
Sodium Chloride	58	100	55 g
Sodium Hydroxide	40	100	39 g
Water	46.07	1000	6.1 L

EXAMPLE 2

[0026] The intravenous administration of the iron sucrose (FeS) bicarb composition of Example 1 was conducted for 4 hours and resulted in elevated renal heme oxygenase 1 (HO-1) relative to commercially available iron sucrose (FeS) composition sold under the brand name, Venofer®. The results are shown in Table 3 below.

Table 3:

Kidney mRNA			
HO-1 / GAPDH			
Run #	Control	4hr IV FeS, Venofer®	4hr IV FeS-bicarb
1	0.22	1.52	3.2
2	0.04	1.23	2.01
3	0.06	1.11	1.99
4	0.07	2.23	2.23
5		1.86	1.86
Average	0.1	1.59	2.34
Std. Err	0.04	0.21	0.23

[0027] The elevated level of HO-1 observed in the kidney was not observed in the liver. Instead, the level of HO-1 was not observed to be increased for FeS-bicarb relative to what was observed for Venofer®. The results are shown in Table 4 below.

Table 4:

Liver mRNA			
HO-1 / GAPDH			
Run #	Control	4hr IV FeS, Venofer®	4hr IV FeS-bicarb
1	0.09	0.99	0.49
2	0.13	1.06	0.36
3	0.11	0.51	0.93
4	0.08	1.24	0.92
5		1.07	0.49
Average	0.1	0.97	0.64
Std. Err	0.01	0.12	0.12

[0028] The plasma BUN and Creatinine were similar for both FeS, Venofer® and FeS-bicarb as shown in Tables 5 and 6 below.

Table 5:

BUN - Plasma			
Run #	Control	4hr IV FeS, Venofer®	4hr IV FeS-bicarb
1	28	20	23
2	22	18	23
3	23	22	22
4	35	25	24
5		25	28
Average	27	22	24

Table 6:

Creatinine - Plasma			
Run #	Control	4hr IV FeS, Venofer®	4hr IV FeS-bicarb
1	0.32	0.27	0.34
2	0.31	0.29	0.31
3	0.31	0.28	0.31
4	0.31	0.25	0.32
5		0.32	0.30
Average	0.31	0.28	0.32

Example 3

[0029] FeS-bicarb composition of Example 1 was filtered and placed in a vial and had a FeS concentration of 12 mg/mL (CoreRx Lot #111002-18011). The osmolarity of this 12 mg/mL solution was 831 mOsm. For Venofer® Iron Sucrose Injection 20 mg/mL, American Regent, Lot # 8243A, the osmolarity was 1742 mOsm. These osmolarity measurements were made without dilution.

Example 4

[0030] A Western blot of kidney at 18 hours post administration of aqueous iron compositions is shown in Fig. 2 and Table 7:

TABLE 7

Kidney	Normal	Venofer	RBT3
HO-1 mRNA	0.1 ± 0.04	1.59 ± 0.21 <0.001	2.34 ± 0.23 <0.001 (<0.05)
Ftn LC mRNA	1.10 ± 0.06	1.36 ± 0.04 <0.01	1.47 ± 0.09 <0.02 (NS)
Ftn HC mRNA	1.38 ± 0.01	1.38 ± 0.03 NS	1.49 ± 0.06 NS (<0.05)*
<hr/>			
Liver	Normal	Venofer	RBT3
HO-1 mRNA	0.10 ± 0.01	0.97 ± 0.012 <0.001	0.64 ± 0.12 <0.01 (0.085)
Ftn LC mRNA	3.65 ± 0.15	4.02 ± 0.1 NS	3.63 ± 0.13 NS
Ftn HC mRNA	1.71 ± 0.11	1.82 ± 0.1 NS	1.71 ± 0.14 NS

[0031] On the left, is a heavy chain specific Western blot of kidney at 18 hr post SnPP, FeS (Venofer) or Fe+ SnPP. N= normal control. Glyc is glycerol, used as a positive H chain ferritin control. N= normal samples (controls). As is apparent, Fe induces an increase in heavy chain in kidney.

EXAMPLE 5

[0032] A patient suffering from chronic kidney disease is treated by intravenous injection using the aqueous iron composition of iron sucrose and bicarbonate of Example 1.

EXAMPLE 6

[0033] A patient undergoing organ transplantation is treated by intravenous injection using the aqueous iron composition of iron sucrose and bicarbonate of Example 1.

EXAMPLE 7

[0034] A patient undergoing organ transplantation is treated by intravenous injection using the aqueous iron composition of iron sucrose and bicarbonate of Example 1, in combination with tin protoporphyrin.

EXAMPLE 8

[0035] Three samples of iron-sucrose (S1, S2) and iron-dextran (S3) were characterized by a variety of analytical techniques. S1 was prepared in accordance with Example 1 above. S2 is the commercially available product, Venofer® (iron sucrose injection). S3 is the commercially available product INFeD® (iron dextran injection). The results are summarized in Table 8 below.

TABLE 8: Comparison of Example 1 to Venofer® and INFeD®

ANALYSIS	S1 FeS STERILE LIQUID 5mL UNLABELED VIAL (6R) Lot: AK2087	S2 VENOFER (IRON SUCROSE INJECTION, USP) (20 mg/mL) Lot: 9043	S3 INFeD (IRON DEXTRAN INJECTION, USP) (50 mg/mL) Lot: 18W11A	
	M _w	29,239	35,709	83,090
GPC	M _w	34,355	50,855	92,838

M _w	23,881	31,345	70,640
PDI	1.44	1.62	1.31
DLS	Z average PDI	15.30 nm 0.32	15.41 nm 0.31
	Zeta Potential	-10.16 mV	-2.61 mV
Zeta	Zeta Potential	25.0 °C	25.0 °C

Potenti al	Temp.	-- --		No stable reading obtained		-- --	
	pH	10.70		10.23		22.2 °C	
	pH Temp.	25.0 °C					
AFM	Location	1	2	1	2	1	2
	Mean Height	2.38 nm	2.43 nm	3.88 nm	3.49 nm	4.20 nm	3.73 nm
	Min Height	1.34 nm	1.16 nm	0.99 nm	1.20 nm	1.19 nm	0.91 nm
	Max Height	3.62 nm	3.73 nm	8.35 nm	7.76 nm	10.19 nm	7.23 nm
	σ	0.61	0.73	1.53	1.33	1.46	1.47
	# Particles	21	29	84	52	117	49
TOC		7.69%		12.14%		8.69%	
Osmolality		1540 mOsm/kg		1681 mOsm/kg		529 mOsm/kg	
Fe ³⁺ vs Fe ²⁺	Fe(II)	0.41 mg/mL		3.16 mg/mL		0.44 mg/mL	
	Fe(III)	11.43 mg/mL		16.90 mg/mL		50.90 mg/mL	
	Total Fe	11.87 mg/mL		20.02 mg/mL		51.33 mg/mL	
% Fe(II)		3.4%		15.8%		0.8%	
ICP-OES	Total Fe	1.07 wt%		1.77 wt%		4.51 wt%	
	Total Na	1.26 wt%		0.50 wt%		0.42 wt%	
ICP-MS Screen for Additional Elements	Summary	No element found >50 ppm, see report body for more		No elements found >80 ppm, see report body for		No elements found >30 ppm, see report body for more	
	Highest Conc. Element	Si, 50 ppm		Si, 80 ppm		Si, 30 ppm	
Chemical Family by FT-IR	Sucrose	Sucrose		Dextran			

TABLE 8: Comparison of Example 1 to Venofer® and INFeD®(cont'd)

ANALYSIS	S1 FES STERILE LIQUID 5ML UNLABELED VIAL (6R) Lot: AK2087	S2 VENDER (IRON SUCROSE INJECTION, USP) (20 mg/mL) Lot: 9043	S3 INFeD (IRON DEXTRAN INJECTION, USP) (50 mg/mL) Lot: 18W11A
----------	---	---	---

NMR Spectroscopy	~ NMR	Broad peaks observed, chemical shifts are consistent with dextran	Very broad peaks observed, chemical shifts are consistent with sucrose	Broad peaks observed, chemical shifts are consistent with dextran	
	13C NMR	Peaks are consistent with sucrose	Peaks are consistent with sucrose, though slightly more broad than S1	Peaks are consistent with dextran	
XRD (lyophilized material)	Phases Detected	wt%	Phases Detected	wt%	
	Na ₂ FeO ₄ – Sodium Iron Oxide Monoclinic, SG: P21/n (14) PDF# 04-013-8809	5.2	Fe ₂ Fe ₃ O ₄ – Sucrose Monoclinic, SG: P21 (4) PDF# 02-063-8998	42.9	
XRD (material purified with MWCO to remove sugars)	Amorphous materials	94.8	Amorphous materials	57.1	
	Phases Detected	wt%	Phases Detected	wt%	
	Fe ₂ Fe ₃ O ₄ – Magnetite Cubic, SG: P4322 (212) PDF# [04-021-3968]	81.0	Fe ₂ Fe ₃ O ₄ – Magnetite Cubic, SG: P4322 (212) PDF# [04-021-3968]	89.9	
	FeOOH – Iron Oxide Orthorhombic PDF# [04-003-2900]	19.0	FeOOH – Iron Oxide Orthorhombic PDF# [04-003-2900]	10.1	
Acid Degradation for Labile Iron (III)	1.48%		2.27%		
TGA	Temp.	Cond.	Weight Loss (%)		
	RT to	Nit.	3.4	1.1	3.7
	100°	Air	2.5	0.9	4.7
	100° to	Nit.	42.7	45.0	8.2
	245°	Air	43.2	43.0	7.8
	245° to	Nit.	30.2	35.4	47.1
	530°	Air	37.4	45.1	63.0
	245° to 530°	Nit.	11.8	8.7	20.8
	530°	Air	5.7	0.7	3.0
	Residu e at 800°C	Nit.	12.0	9.8	20.0
		Air	11.2	10.3	21.4
Thermal Transitions Observed					
	Texo ₁ (°C)	33.8	29.2	39.2	

Δ Hexo ₁ (J/g)	88.0	47.6	99.9
Texo ₂ (°C)	154.9	144.6	N/A
Onset Texo ₂ (°C)	141.0	127.1	N/A
Δ Hexo ₂ (J/g)	171.7	148	N/A

[0036] Finally, the as-received sample S1 was titrated in triplicate with dilute HCl to determine the hydroxide value in iron-sucrose injectable solution. The end points of the titrations were pH = 7.0. Using the assumption that all basic species titrated were from the hydroxide associated with the ferric oxyhydroxide cores, the total number of moles of H⁺ used in the titration was assumed to be equal to the number of moles of OH⁻. Considering TOC, and Mw (or Mn) by GPC, the molecular formula of iron sucrose in S1 was calculated as below:

[0037] Mw based calculation: [Na₆Fe₅O₈(OH)₅ · 3H₂O]13 · 73(C₁₂H₂₂O₁₁) Mn based calculation: [Na₆Fe₅O₈(OH)₅ · 3H₂O]9 · 51(C₁₂H₂₂O₁₁). Table 9 below shows details of the sample preparation and identification.

TABLE 9: Sample Preparation and identification		
SAMPLE NUMBER	DESCRIPTION	DATE RECEIVED
S1	FeS Sterile Liquid 5mL Unlabeled Vial (6R)	11 Jul 2019
	Lot: AK2087	
	Quantity: 15	
S2	Venofer (Iron Sucrose Injection, USP)	11 Jul 2019
	100mg Elemental Iron per 5mL (20mg/mL)	
	Lot: 9043	
	Exp: FEB 21 (2 Each of 10 x 5mL)	
S3	INFeD (Iron Dextran Injection, USP)	11 Jul 2019
	100mg Elemental Iron/2mL (50mg/mL)	
	Exp: 10/2021	
	Lot: 18W11A (4 Each of 10 x 2mL)	

[0038] Sample preparation:

The samples were lyophilized to a dried residue prior to analysis unless otherwise stated.

[0039] Gel Permeation Chromatography (GPC):

GPC is used to determine the molecular weight distribution of polymers. In GPC analysis, a solution of the polymer is passed through a column packed with a porous gel. The sample is separated based on molecular size with larger molecules eluting quicker than smaller molecules. The retention time of each component is detected and compared to a calibration curve, and the resulting data is then used to calculate the molecular weight distribution for the sample.

[0040] A distribution of molecular weights rather than a unique molecular weight is characteristic of all types of synthetic polymers. To characterize this distribution, statistical averages are used. The most common of these averages are the "number average molecular weight" (Mn) and the "weight average molecular weight" (Mw).

[0041] The number average molecular weight is similar to the standard arithmetic mean associated with a group of numbers. When applied to polymers, the number-average molecular weight refers to the average molecular weight of the molecules in the polymer. The number average molecular weight is figured giving the same amount of significance to each molecule regardless of its individual molecular weight. The number average molecular weight is figured by the following formula where N_i is the number of molecules with a molar mass equal to M_i.

$$\bar{M}_n = \frac{\sum N_i M_i}{\sum N_i}$$

[0042] Slightly different in calculation and much different in meaning is the weight average molecular weight, Mw. The weight average molecular weight is another statistical descriptor of the molecular weight distribution that provides more significance of larger molecules than the smaller molecules in the distribution. The formula below shows the statistical calculation of the weight average molecular weight.

$$\bar{M}_w = \frac{\sum N_i M_i^2}{\sum N_i M_i}$$

[0043] For GPC, the samples were prepared by diluting in phosphate buffer (per USP monograph method) and analyzed to determine the molecular weight distributions in each sample. The results are summarized below in Tables 10-12. Representative chromatograms from the analysis are presented in Figs. 3-9.

[0044] There are two general reasons for the weight average molecular weight. First, if comparing, for example toughness, the longer molecules influence the toughness of the polymer distribution more so than the shorter molecules do. The weight average molecular weight calculation gives emphasis to these longer molecules, and provides a comparative number that can describe the relative contribution of the long molecules present in a molecular weight distribution. The weight average molecular weight is also a number that is directly correlated to the molecular weight determination of polymers by light scattering, small angle neutron scattering (SANS), and sedimentation velocity.

[0045] Secondly, the weight average molecular weight provides insight to the shape of a molecular weight distribution. This value, in connection with the

number average molecular weight, provides a ratio determination of the broadness of the molecular weight distribution referred to as the polydispersity index or PI. The PI is defined as the ratio of M_w/M_n . The larger the PI, the more disperse the distribution is. The lowest value that a PI can be is 1. This represents a monodispersed sample - a polymer with all of the molecules in the distribution being the same molecular weight.

[0046] Not as commonly referred to, but also provided is the "z-average molecular weight" (M_z). This molecular weight average is a value that further describes the molecular weight distribution. This value can be readily determined from sedimentation equilibrium.

[0047] Also sometimes included is the peak molecular weight, M_p . The peak molecular weight value is defined as the mode of the molecular weight distribution. It signifies the molecular weight that is most abundant in the distribution. This value also gives insight to the molecular weight distribution.

[0048] Most GPC measurements are made relative to a different polymer standard (usually polystyrene). The accuracy of the results depends on how closely the characteristics of the polymer being analyzed match those of the standard used. The expected error in reproducibility between different series of determinations, calibrated separately, is ca. 5-10% and is characteristic to the limited precision of GPC determinations. Therefore, GPC results are most useful when a comparison between the molecular weight distribution of different samples is made during the same series of determinations.

[0049] GPC Precisions and bias are based on statistical data such as an average of measurements, standard deviation, relative percent difference, and/or percent relative standard deviation. For quantitative analyses, the amounts listed in the tables above were referenced to a known amount of standard and are quantitative. Calibration curves were prepared, and relative standard deviation and relative percent difference information are referenced in the report above. For semi-quantitative typical reproducibility as determined by statistical process control of the measurement system is estimated at about 10% (at 95% confidence level, $k \sim 2$). This reproducibility is an estimate of the uncertainty of a single standard measurement over time, and the uncertainty in a specific measurement must be determined on a case by case basis. For qualitative analyses, analytical reference standards were not analyzed to confirm the presence of the individual components. In such cases it is not possible to assign a numerical value to the "uncertainty" of the matches provided.

[0050] Note that samples S1 and S2 contained two peaks with unique molecular weight distributions while sample S3 contained three peaks. Also note that a M_p could not be calculated for "Peak 2" (small molecule peak, likely sucrose) because the peak saturated the detector; samples were analyzed at a concentration which was appropriate for characterization of the higher molecular weight species, with the expense of saturating the detector with the lower molecular weight species of lesser interest.

TABLE 10: Summary of GPC data for sample S1

SAMPLE DESCRIPTION	PREPARATION	INJECTION	M_p	M_n	M_w	M_z	PD	
S1 Peak 1	1	1	28,558	23,158	33,501	49,457	1.45	
		2	28,558	22,954	34,613	52,469	1.51	
	2	1	29,137	24,149	33,976	47,218	1.41	
		2	29,727	24,329	34,908	51,148	1.44	
	3	1	29,727	24,188	34,658	48,687	1.43	
		2	29,727	24,510	34,471	47,718	1.41	
	Average		29,239	23,881	34,355	49,450	1.44	
	Standard Deviation		575	655	520	2,028	0.04	
	% RSD		2.0	2.7	1.5	4.1	2.6	
			saturated detector; peak max not available ¹	256	281	306	1.10	
	S1 Peak 2	1		256	281	306	1.10	
		2		249	278	307	1.12	
	2	1		249	278	307	1.12	
		2		251	279	306	1.11	
	3	1		251	279	306	1.11	
		2		251	279	306	1.11	
	Average			252	279	306	1.11	
	Standard Deviation			N/A	3	1	0.01	
	% RSD			N/A	1.3	0.5	0.2	

TABLE 11: Summary of GPC data for sample S2

SAMPLE DESCRIPTION	PREPARATION	INJECTION	M_p	M_n	M_w	M_z	PD
S2 Peak 1	1	1	35,587	30,778	51,407	91,042	1.67
		2	34,884	31,180	50,455	83,903	1.62
	2	1	35,587	31,206	51,080	86,265	1.64
		2	35,587	31,442	50,835	84,143	1.62
	3	1	36,303	31,997	50,985	82,454	1.59
		2	36,303	31,469	50,368	80,420	1.60
	Average		35,709	31,345	50,855	84,705	1.62
	Standard Deviation		535	404	392	3,660	0.03
	% RSD		1.5	1.3	0.8	4.3	1.7
			saturated detector ; peak max not	242	286	327	1.18
	S2 Peak 2	1		243	286	328	1.18

TABLE 11: Summary of GPC data for sample S2

SAMPLE DESCRIPTION	PREPARATION	INJECTION	M _P	M _n	M _w	M _z	PD
	2	1		241	287	331	1.19
		2		240	287	331	1.20
	3	1		245	286	326	1.17
		2		243	288	332	1.19
	Average		N/A	242	287	329	1.18
	Standard Deviation		N/A	2	1	2	0.01
	% RSD		N/A	0.7	0.3	0.8	0.9

TABLE 12: Summary of GPC data for sample S3

SAMPLE DESCRIPTION	PREPARATION	INJECTION	M _P	M _n	M _w	M _z	PD
S3 Peak 1	1	1	83,090	71,378	93,965	124,983	1.32
		2	83,090	70,426	92,618	121,641	1.32
	2	1	83,090	70,660	92,582	121,443	1.31
		2	83,090	70,030	92,525	123,025	1.32
	3	1	83,090	70,719	92,723	121,912	1.31
		2	83,090	70,627	92,615	121,900	1.31
	Average		83,090	70,640	92,838	122,484	1.31
	Standard Deviation		0	440	556	1,342	0.00
	% RSD ¹		0.0	0.6	0.6	1.1	0.3
	S3 Peak 2	1	6,749	4,235	6,558	9,203	1.55
		2	6,607	4,209	6,503	9,096	1.55
	2	1	6,607	4,179	6,492	9,135	1.55
		2	6,607	4,156	6,434	8,988	1.55
	3	1	6,607	4,175	6,496	9,143	1.56
		2	6,607	4,162	6,488	9,140	1.56
	Average		6,631	4,186	6,495	9,118	1.55
	Standard Deviation		58	30	40	72	0.01
	% RSD ¹		0.9	0.7	0.6	0.8	0.3
S3 Peak 3	1	1	373	305	331	353	1.09
		2	373	310	334	355	1.08
	2	1	373	334	353	367	1.06
		2	373	342	359	373	1.05
	3	1	373	342	360	374	1.05
		2	373	344	361	375	1.05
	Average		373	330	350	366	1.06
	Standard Deviation		0	17	14	10	0.02
	% RSD ¹		0.0	5.3	3.9	2.7	1.4

Dynamic Light Scattering

[0051] PSD analysis was conducted with a laser diffractor. The measurement calculates a volume distribution from the laser diffraction pattern of a cloud of particles. This raw scatter data is then processed with an algorithm and presented on the basis of equivalent spherical diameter. The results have been summarized on a volume (mass) basis in a histogram giving the differential volume percent less and greater than the indicated size.

[0052] The particle size analysis was conducted on a Malvern® Zetasizer Nano ZS dynamic light scattering (DLS) instrument. DLS is an ensemble technique that analyzes the light scattered by particles moving in Brownian motion and generates a particle size distribution based on the particle's rate of diffusion. The raw scatter data are processed using a complex algorithm and presented on the basis of an intensity-weighted HYDRODYNAMIC DIAMETER. The analytical technique is summarized in ISO 22412:2008 Particle Size Analysis - Dynamic Light Scattering (DLS) as well as ASTM E2490-09(2015) Standard Guide for Measurement of Particle Size Distribution of Nanomaterials in Suspension by Photon Correlation Spectroscopy (PCS).

[0053] The as received samples were water for injection (WFI) and analyzed by DLS to give the overall physical dimension of the particles. The intensity- and volume-weighted results from the analysis are presented in Table 13 and Table 14, respectively.

TABLE 13: Summary of DLS results (intensity weighted)

SAMPLE ID	REPLICATE	CUMULANT RESULTS		NNLS RESULTS ¹					
		Z-AVERAGE ²	PDI ₃	PEAK 1 (nm)	PEAK 1 WIDTH (nm)	PEAK 2 (nm)	PEAK 2 WIDTH (nm)	PEAK 3 (nm)	PEAK 3 WIDTH (nm)
S1	Replicate 1	13.55	0.30	17.12	10.45	2419	1460	no peak	no peak
	Replicate 2	14.72	0.35	14.48	6.11	522.4	218.3	4668	838.3
	Replicate 3	17.64	0.30	16.22	6.91	705.5	425.1	4527	959.1
	Average	15.30	0.32	15.94	7.82	1215.6	701.1	4598	898.7
S2	Replicate 1	15.76	0.32	18.79	10.60	3271	1497	no peak	no peak
	Replicate 2	15.69	0.35	16.39	7.83	1017	574.5	4213	977.6
	Replicate 3	14.79	0.27	18.33	11.76	4037	1136	672.2	377.2
	Average	15.41	0.31	17.84	10.06	2775	1069.2	2442.6	677.4
S3	Replicate 1	17.35	0.22	20.9	11.18	3726	1240	379.5	232.3
	Replicate 2	16.17	0.20	18.43	8.10	3444	1425	no peak	no peak
	Replicate 3	17.13	0.22	20.27	9.95	3466	1276	812.4	370.1
	Average	16.88	0.21	19.87	9.74	3545.3	1313.7	596.0	301.2

¹NNLS = non-negative least squares data; ²Z-average = average particle size distribution; ³PDI = polydispersity index

TABLE 14: Summary of DLS results (volume weighted)

SAMPLE ID	REPLICATE	CUMULANT RESULTS		NNLS RESULTS ¹					
		Z-AVERAGE ²	PDI ₃	PEAK 1 (nm)	PEAK 1 WIDTH (nm)	PEAK 2 (nm)	PEAK 2 WIDTH (nm)	PEAK 3 (nm)	PEAK 3 WIDTH (nm)
S1	Replicate 1	13.55	0.30	7.94	3.89	1354	455.9	no peak	no peak
	Replicate 2	14.72	0.35	2.89	0.65	9.292	3.711	714.3	317.9
	Replicate 3	17.64	0.30	10.70	4.11	970.4	413.9	4904	993.8
	Average	15.30	0.32	7.18	2.88	777.9	291.2	2809	655.9
	Replicate 1	15.76	0.32	8.55	4.46	1398	406.3	4450	1157
	Replicate 2	15.69	0.35	8.19	4.39	1138	406.7	no peak	no peak
	Replicate 3	14.79	0.27	8.88	4.21	no peak	no peak	no peak	no peak
	Average	15.41	0.31	8.54	4.35	1268.0	406.5	4450	1157.0
S3	Replicate 1	17.35	0.22	11.66	5.03	no peak	no peak	no peak	no peak
	Replicate 2	16.17	0.20	11.61	4.62	4511	1135	no peak	no peak
	Replicate 3	17.13	0.22	11.66	5.03	1210	430.7	no peak	no peak
	Average	16.88	0.21	11.64	4.89	2860.5	782.9	no peak	no peak

¹NNLS = non-negative least squares data; ²Z-average = average particle size distribution; ³PDI = polydispersity index

ZETA POTENTIAL

[0054] The samples were prepared for zeta potential by diluting in buffer (instrument could not achieve stable readings when diluted in 10 mM NaCl per Nanomaterials 2018, 8, 25). The pH and temperature were recorded at the time of the zeta potential analysis. The results are summarized in Table 6 through Table 8 below. A stable reading could not be obtained for S2. The results for zeta potential testing are reported in Tables 15-17.

TABLE 15: Zeta potential data for sample S1

SAMPLE ID	ALIQUOT	REP.	ZETA POTENTIAL (mV)	AVG. ZETA POTENTIAL (mV)	ZETA POTENTIAL TEMP (°C)	PH	PH TEMP (°C)	CONDUCTIVITY (mS/cm)	AVG. CONDUCTIVITY (mS/cm)	CONDUCTIVITY TEMP (°C)
V1KCJ405 S1	1	1	-8.77	-10.42	25	10.7	25	10.0	11.2	25
		2	-8.87					11.1		
		3	-12.2					11.6		
		4	-9.08					11.7		
		5	-13.2					11.8		
	2	1	-10.1	-9.90	25	25	10.6	10.1	11.4	25
		2	-8.86					11.4		
		3	-8.25					11.7		
		4	-11.4					11.8		
		5	-10.9					11.9		

TABLE 16: Zeta potential data for sample S2 (stable reading could not be reached)										
SAMPLE ID	ALIQUOT	REP.	ZETA POTENTIAL (mV)	AVG. ZETA POTENTIAL (mV)	ZETA POTENTIAL TEMP (°C)	PH	PH TEMP (°C)	CONDUCTIVITY (mS/cm)	AVG. CONDUCTIVITY (mS/cm)	CONDUCTIVITY TEMP (°C)
V1KCJ405 S2	1	1	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
		2	N/A					N/A		
		3	N/A					N/A		
		4	N/A					N/A		
		5	N/A					N/A		
	2	1	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
		2	N/A					N/A		
		3	N/A					N/A		
		4	N/A					N/A		
		5	N/A					N/A		

TABLE 17: Zeta potential data for sample S3

SAMPLE ID	ALIQUOT	REP.	ZETA POTENTIAL (mV)	AVG. ZETA POTENTIAL (mV)	ZETA POTENTIAL TEMP (°C)	PH	PH TEMP (°C)	CONDUCTIVITY (mS/cm)	AVG. CONDUCTIVITY (mS/cm)	CONDUCTIVITY TEMP (°C)
V1KCJ405 S3	1	1	-3.35	-2.972	25	10.2	22.0	7.15	7.828	25
		2	-2.23					7.80		
		3	-2.13					8.00		
		4	-3.41					8.08		
		5	-3.74					8.11		
	2	1	-1.78	-2.254	25	10.2	22.4	7.32	8.012	25
		2	-3.07					7.99		
		3	-0.37					8.19		
		4	-2.53					8.27		
		5	-3.52					8.29		

ATOMIC FORCE MICROSCOPY (AFM)

[0055] The as received samples were diluted 50x using MilliQ filtered water (18.2 MΩ/cm, 4ppb TOC). About 10 µL of these diluted solutions were deposited onto freshly cleaved pieces of mica and allowed to incubate for about a minute. The samples were then rinsed 5x with MilliQ water and dried with nitrogen. Two 1 µm x 1 µm areas were imaged on each sample. The topography differences of these images are presented in colors where the brown is low and the white is high. The z ranges are noted on the vertical scale bar on the right side of the images. Perspective (3-D) views of these surfaces are also included with vertical exaggerations noted in the captions.

[0056] Particle size analyses were performed to characterize the heights of the particles present within each area. A height threshold of 0.5 nm was used to identify the particles of interest while excluding non-representative features. The maximum height, minimum height, and mean height results are summarized in Table 18.

TABLE 18: Particle Size Analysis Results						
SAMPLE ID	LOCATION	MEAN HEIGHT (nm)	MINIMUM HEIGHT (nm)	MAXIMUM HEIGHT (nm)	σ	# OF PARTICLES
S1	1	2.38	1.34	3.62	0.61	21
	2	2.43	1.16	3.73	0.73	29
S2	1	3.88	0.99	8.35	1.53	84
	2	3.49	1.20	7.76	1.33	52
S3	1	4.20	1.19	10.19	1.46	117
	2	3.23	0.91	7.23	1.47	49
Blank	1	n/a	n/a	n/a	n/a	0

[0057] Section analyses were performed to manually measure the heights of representative particles. The Sectional analysis for S1 at location 1 is shown in Figs. 10, 11, and 12. The results are summarized in Table 19 for each of S1, S2, and S3.

TABLE 19: Particle Size Analysis Results				
SAMPLE ID	LOCATION	PARTICLE 1 HEIGHT (nm)	PARTICLE 2 HEIGHT (nm)	PARTICLE 3 HEIGHT (nm)
S1	1	3.50	3.35	2.63
	2	3.67	2.67	2.44
S2	1	4.96	2.68	4.77
	2	3.51	3.95	6.48

TABLE 19: Particle Size Analysis Results

SAMPLE ID	LOCATION	PARTICLE 1 HEIGHT (nm)	PARTICLE 2 HEIGHT (nm)	PARTICLE 3 HEIGHT (nm)
S3	1	3.75	6.81	3.89
	2	4.37	4.27	3.81

TOTAL ORGANIC CARBON (TOC)

[0058] The total organic carbon (TOC) in the samples was calculated by subtracting the inorganic carbon from the total carbon (determined using combustion carbon analyzer). The results are summarized in Table 20 below.

TABLE 20: Calculations for total organic carbon (TOC)

SAMPLE ID	REPLICATE	TOTAL CARBON (wt%) ¹	AVERAGE TOTAL CARBON	%RSD	TOTAL INORGANIC CARBON	AVERAGE TOTAL CARBON	%RSD ₂	AVERAGE TOTAL ORGANIC CARBON (wt%) ¹
S1	Rep 1	8.07	7.92	1.8%	0.23%	0.23	0.0%	7.69
	Rep 2	7.89			0.23%			
	Rep 3	7.79			0.23%			
S2	Rep 1	12.27	12.17	0.8%	0.03%	0.03	0.0%	12.14
	Rep 2	12.15			0.03%			
	Rep 3	12.08			0.03%			
S3	Rep 1	8.56	8.69	2.5%	< 0.03%	< 0.03	-	8.69
	Rep 2	8.57			< 0.03%			
	Rep 3	8.94			< 0.03%			

¹ wt% = weight percent, ² %RSD = relative Standard Deviation

OSMOLALITY

[0059] The osmolality of the samples was measured using vapor pressure method. The vapor pressure method determines osmolality at room temperature with the sample in natural equilibrium. The results of the osmolality test are summarized in Table 21.

TABLE 21: Summary of Osmolality Results

SAMPLE ID	REPLICATE	OSMOLALITY (mOsm/kg)	AVERAGE OSMOLALITY (mOsm/kg)	%RSD ¹
S1	Replicate 1	1539	1540	0.1%
	Replicate 2	1541		
	Replicate 3	1539		
S2	Replicate 1	1677	1681	0.2%
	Replicate 2	1682		
	Replicate 3	1683		
S3	Replicate 1	533	529	0.7%
	Replicate 2	527		
	Replicate 3	526		

Fe⁺³ vs Fe⁺²

[0060] An aliquot of each sample was diluted into concentrated hydrochloric acid as per the method reference provided by the client, Gupta et al.¹ The samples were then analyzed in accordance with the method outlined by Stokey.² The results are shown in Table 22.

TABLE 22: Summary of iron speciation

SAMPLE ID	REPLICATE	Fe (II) (mg/mL)	AVERAGE Fe (II) (mg/mL)	%RSD	Fe (III) (mg/mL)	AVERAGE Fe (III) (mg/mL)	%RSD	Fe (REDUCED) (TOTAL IRON, mg/mL)	AVERAGE Fe (III) (mg/mL)	%RSD	%Fe (II)
S1	Replicate 1	0.43	0.41	4.3%	11.20	11.43	1.8%	11.70	11.87	1.3%	3.4%
	Replicate 2	0.41			11.60			12.00			
	Replicate 3	0.39			11.50			11.90			
S2	Replicate 1	3.16	3.16	1.6%	16.80	16.90	1.0%	19.90	20.03	1.2%	15.8%
	Replicate 2	3.21			17.10			20.30			
	Replicate 3	3.11			16.80			19.90			

TABLE 22: Summary of iron speciation

SAMPLE ID	REPLICATE	Fe (II) (mg/mL)	AVERAGE Fe (II) (mg/mL)	%RSD	Fe (III) (mg/mL)	AVERAGE Fe (III) (mg/mL)	%RSD	Fe (REDUCED) (TOTAL IRON, mg/mL)	AVERAGE Fe (III) (mg/mL)	%RSD	%Fe (II)
S3	Replicate 1	0.45	0.44	2.0%	51.70	50.90	1.7%	52.20	51.33	1.8%	0.8%
	Replicate 2	0.43			51.00			51.40			
	Replicate 3	0.43			50.00			50.40			

%RSD = Relative Standard Deviation

ELEMENTAL SCREEN BY INDUCTIVELY COUPLED PLASMA/MASS SPECTROMETRY (ICP/MS) AND TOTAL IRON AND SODIUM CONTENT BY INDUCTIVELY COUPLED PLASMA/OPTICAL EMISSION SPECTROSCOPY (ICP/OES)

[0061] ICP/OES is a spectroscopic technique used to identify and quantify components by element. In ICP, inductive coupling transfers high-frequency energy to a flow of inert gas, which contains the sample as an aerosol. The energy causes the aerosol to vaporize, while exciting the resulting free atoms so that they emit light. The intensity of this light is then related to the concentration of the emitting atoms. This technique requires calibration of the instrument and a second-source calibration verification before, during, and after completion of the analytical run sequence. In addition, instrument blanks follow each check verification standard. This ensures no carry over during the analytical sequence. Concentration measurements of major elements done by ICP have an uncertainty typically in the range from 3 to 5% (at the 95% confidence level). The uncertainty in the concentrations of trace elements might be significantly higher.

[0062] Samples S1 through S3 were analyzed by ICP-MS for metals and /or other elements. The samples were also analyzed by ICP-OES to determine total iron and sodium content. Samples were analyzed as received in triplicate. The results are summarized in Table 23-25.

TABLE 23: Summary of the elements detected by ICP in S1

ELEM ENT	S1 CONCENTRATION (ppm wt%) ¹ REPLICATE 1	S1 CONCENTRATION (ppm wt%) ¹ REPLICATE 2	S1 CONCENTRATION (ppm wt%) ¹ REPLICATE 3	S1 AVERAGE CONCENTRATION (ppm wt%)
Li	< 0.1	< 0.1	< 0.1	< 0.1
Be	< 0.1	< 0.1	< 0.1	< 0.1

B	4.2	4.1	4.1	4.1
Na ²	1.27%	1.25%	1.25%	1.26%
Mg	0.9	0.9	0.9	0.9
Al	6.9	6.8	7.0	6.9
Si	50	49	51	50
P	2.3	2.5	2.5	2.4
K	10	10	10	10
Ca	2	1	< 1	< 2
Sc	< 0.1	< 0.1	< 0.1	< 0.1
Ti	0.2	0.2	0.2	0.2
V	0.4	0.4	0.4	0.4
Cr	4.6	4.4	4.6	4.5
Mn	8.4	8.5	8.7	8.5
Fe ²⁺	1.07%	1.07%	1.07%	1.07%
Co	< 0.1	< 0.1	< 0.1	< 0.1
Ni	1.1	1.1	1.1	1.1
Cu	0.3	0.3	0.3	0.3
Zn	1.2	1.2	1.2	1.2
Ga	< 0.1	< 0.1	< 0.1	< 0.1
Ge	< 0.1	< 0.1	< 0.1	< 0.1
As	0.2	0.2	0.2	0.2
Se	< 0.1	< 0.1	< 0.1	< 0.1
Rb	< 0.1	< 0.1	< 0.1	< 0.1
Sr	< 0.1	< 0.1	< 0.1	< 0.1
Y	< 0.1	< 0.1	< 0.1	< 0.1
Zr	< 0.1	< 0.1	< 0.1	< 0.1
Nb	0.2	0.2	0.2	0.2
Mo	0.6	0.6	0.6	0.6
Ru	< 0.1	< 0.1	< 0.1	< 0.1
Rh	< 0.1	< 0.1	< 0.1	< 0.1
Pd	< 0.1	< 0.1	< 0.1	< 0.1
Ag	< 0.1	< 0.1	< 0.1	< 0.1

TABLE 23: Summary of the elements detected by ICP in S1 (cont'd)

ELEM ENT	S1 CONCENTRATION (ppm wt%) ¹ REPLICATE 1	S1 CONCENTRATION (ppm wt%) ¹ REPLICATE 2	S1 CONCENTRATION (ppm wt%) ¹ REPLICATE 3	S1 AVERAGE CONCENTRATION (ppm wt%)
----------	--	--	--	------------------------------------

Cd	< 0.1	< 0.1	< 0.1	< 0.1
In	< 0.1	< 0.1	< 0.1	< 0.1
Sn	0.2	0.1	0.1	0.1

Sb	< 0.1	< 0.1	< 0.1	·0.1
Te	< 0.1	< 0.1	< 0.1	·0.1
Cs	< 0.1	< 0.1	< 0.1	·0.1
Ba	< 0.1	< 0.1	< 0.1	·0.1
La	< 0.1	< 0.1	< 0.1	·0.1
Ce	< 0.1	< 0.1	< 0.1	·0.1
Pr	< 0.1	< 0.1	< 0.1	·0.1
Nd	< 0.1	< 0.1	< 0.1	·0.1
Sm	< 0.1	< 0.1	< 0.1	·0.1
Eu	< 0.1	< 0.1	< 0.1	·0.1
Gd	< 0.1	< 0.1	< 0.1	·0.1
Tb	< 0.1	< 0.1	< 0.1	·0.1
Dy	< 0.1	< 0.1	< 0.1	·0.1
Ho	< 0.1	< 0.1	< 0.1	·0.1
Er	< 0.1	< 0.1	< 0.1	·0.1
Tm	< 0.1	< 0.1	< 0.1	·0.1
Yb	< 0.1	< 0.1	< 0.1	·0.1
Lu	< 0.1	< 0.1	< 0.1	·0.1
Hf	< 0.1	< 0.1	< 0.1	·0.1
Ta	< 0.1	< 0.1	< 0.1	·0.1
W	< 0.1	< 0.1	< 0.1	·0.1
Re	< 0.1	< 0.1	< 0.1	·0.1
Os	< 0.1	< 0.1	< 0.1	·0.1
Ir	< 0.1	< 0.1	< 0.1	·0.1
Pt	< 0.1	< 0.1	< 0.1	·0.1
Au	< 0.1	< 0.1	< 0.1	·0.1
Hg	< 0.1	< 0.1	< 0.1	·0.1
Tl	< 0.1	< 0.1	< 0.1	·0.1
Pb	< 0.1	< 0.1	< 0.1	·0.1
Bi	< 0.1	< 0.1	< 0.1	·0.1
Th	< 0.1	< 0.1	< 0.1	·0.1
U	< 0.1	< 0.1	< 0.1	·0.1

TABLE 24: Summary of the elements detected by ICP in S2				
ELEMENT	S2 CONCENTRATION (ppm wt%) ¹ REPLICATE 1	S2 CONCENTRATION (ppm wt%) ¹ REPLICATE 2	S2 CONCENTRATION (ppm wt%) ¹ REPLICATE 3	S2 AVERAGE CONCENTRATION (ppm wt%) ¹
Li	< 0.1	< 0.1	< 0.1	< 0.1
Be	< 0.1	< 0.1	< 0.1	< 0.1
B	6.8	6.8	6.8	6.8
Na ²	0.50%	0.50%	0.50%	0.50%
Mg	1.9	1.9	1.9	1.9
Al	5.6	5.8	5.7	5.7
Si	78	80	79	78.5
P	1	1	1	1
K	10	10	10	10
Ca	11	12	12	11.7
Sc	< 0.1	< 0.1	< 0.1	< 0.1
Ti	1.0	1.0	1.0	1
V	< 0.1	< 0.1	< 0.1	< 0.1
Cr	< 0.1	< 0.1	< 0.1	< 0.1
Mn	< 0.1	< 0.1	< 0.1	< 0.1
Fe ²	1.77%	1.76%	1.77%	1.77%
Co	< 0.1	< 0.1	< 0.1	< 0.1
Ni	0.1	0.1	0.1	0.1
Cu	< 0.1	< 0.1	< 0.1	< 0.1
Zn	< 0.1	< 0.1	< 0.1	< 0.1
Ga	< 0.1	< 0.1	< 0.1	< 0.1
Ge	< 0.1	< 0.1	< 0.1	< 0.1
As	< 0.1	< 0.1	< 0.1	< 0.1
Se	< 0.1	< 0.1	< 0.1	< 0.1
Rb	< 0.1	< 0.1	< 0.1	< 0.1
Sr	0.2	0.2	0.2	0.2
Y	< 0.1	< 0.1	< 0.1	< 0.1
Zr	< 0.1	< 0.1	< 0.1	< 0.1
Nb	< 0.1	< 0.1	< 0.1	< 0.1
Mo	< 0.1	< 0.1	< 0.1	< 0.1
Ru	< 0.1	< 0.1	< 0.1	< 0.1
Rh	< 0.1	< 0.1	< 0.1	< 0.1
Pd	< 0.1	< 0.1	< 0.1	< 0.1
Ag	< 0.1	< 0.1	< 0.1	< 0.1
Cd	< 0.1	< 0.1	< 0.1	< 0.1
In	< 0.1	< 0.1	< 0.1	< 0.1
Sn	0.4	0.4	0.4	0.4
Sb	< 0.1	< 0.1	< 0.1	< 0.1
Te	< 0.1	< 0.1	< 0.1	< 0.1
Cs	< 0.1	< 0.1	< 0.1	< 0.1

TABLE 24: Summary of the elements detected by ICP in S2 (cont'd)

ELEMENT	S2 CONCENTRATION (ppm wt%) ¹ REPLICATE 1	S2 CONCENTRATION (ppm wt%) ¹ REPLICATE 2	S2 CONCENTRATION (ppm wt%) ¹ REPLICATE 3	S2 AVERAGE CONCENTRATION (ppm wt%) ¹
Ba	3.7	3.7	3.6	3.7
La	< 0.1	< 0.1	< 0.1	< 0.1
Ce	< 0.1	< 0.1	< 0.1	< 0.1
Pr	< 0.1	< 0.1	< 0.1	< 0.1
Nd	< 0.1	< 0.1	< 0.1	< 0.1
Sm	< 0.1	< 0.1	< 0.1	< 0.1
Eu	< 0.1	< 0.1	< 0.1	< 0.1
Gd	< 0.1	< 0.1	< 0.1	< 0.1
Tb	< 0.1	< 0.1	< 0.1	< 0.1
Dy	< 0.1	< 0.1	< 0.1	< 0.1
Ho	< 0.1	< 0.1	< 0.1	< 0.1
Er	< 0.1	< 0.1	< 0.1	< 0.1
Tm	< 0.1	< 0.1	< 0.1	< 0.1
Yb	< 0.1	< 0.1	< 0.1	< 0.1
Lu	< 0.1	< 0.1	< 0.1	< 0.1
Hf	< 0.1	< 0.1	< 0.1	< 0.1
Ta	< 0.1	< 0.1	< 0.1	< 0.1
W	< 0.1	< 0.1	< 0.1	< 0.1
Re	< 0.1	< 0.1	< 0.1	< 0.1
Os	< 0.1	< 0.1	< 0.1	< 0.1
Ir	< 0.1	< 0.1	< 0.1	< 0.1
Pt	< 0.1	< 0.1	< 0.1	< 0.1
Au	< 0.1	< 0.1	< 0.1	< 0.1
Hg	< 0.1	< 0.1	< 0.1	< 0.1
Tl	< 0.1	< 0.1	< 0.1	< 0.1
Pb	< 0.1	< 0.1	< 0.1	< 0.1
Bi	< 0.1	< 0.1	< 0.1	< 0.1
Th	< 0.1	< 0.1	< 0.1	< 0.1
U	< 0.1	< 0.1	< 0.1	< 0.1

TABLE 25: Summary of the elements detected by ICP in S3

ELEMENT	S3 CONCENTRATION (ppm wt%) ¹ REPLICATE 1	S3 CONCENTRATION (ppm wt%) ¹ REPLICATE 2	S3 CONCENTRATION (ppm wt%) ¹ REPLICATE 3	S3 AVERAGE CONCENTRATION (ppm wt%) ¹
Li	< 0.1	< 0.1	< 0.1	< 0.1
Be	< 0.1	< 0.1	< 0.1	< 0.1
B	1.0	0.9	0.9	0.9
Na ²	0.42%	0.42%	0.42%	0.42%
Mg	1.5	1.6	1.5	1.5
Al	1.0	1.1	1.0	1.1

TABLE 25: Summary of the elements detected by ICP in S3 (cont'd)

ELEMENT	S3 CONCENTRATION (ppm wt%) ¹ REPLICATE 1	S3 CONCENTRATION (ppm wt%) ¹ REPLICATE 2	S3 CONCENTRATION (ppm wt%) ¹ REPLICATE 3	S3 AVERAGE CONCENTRATION (ppm wt%) ¹
Si	30	30	30	30.0
P	3	3	3	3.0
K	3	4	3	3.3
Ca	3	4	3	3.3
Sc	< 0.1	< 0.1	< 0.1	< 0.1
Ti	0.4	0.4	0.4	0.4
V	0.1	0.1	0.1	0.1
Cr	0.3	0.2	0.2	0.2
Mn	< 0.1	< 0.1	< 0.1	< 0.1
Fe ²⁺	4.50%	4.52%	4.52%	4.51%
Co	< 0.1	< 0.1	< 0.1	< 0.1
Ni	0.7	0.5	0.5	0.6
Cu	< 0.1	< 0.1	< 0.1	< 0.1
Zn	0.6	0.7	0.5	0.6
Ga	0.2	0.2	0.2	0.2
Ge	< 0.1	< 0.1	< 0.1	< 0.1
As	< 0.1	< 0.1	< 0.1	< 0.1
Se	< 0.1	< 0.1	< 0.1	< 0.1
Rb	< 0.1	< 0.1	< 0.1	< 0.1
Sr	0.1	0.1	0.1	0.1
Y	< 0.1	< 0.1	< 0.1	< 0.1

Zr	< 0.1	< 0.1	< 0.1	< 0.1
Nb	< 0.1	< 0.1	< 0.1	< 0.1
Mo	0.5	0.5	0.5	0.5
Ru	< 0.1	< 0.1	< 0.1	< 0.1
Rh	< 0.1	< 0.1	< 0.1	< 0.1
Pd	< 0.1	< 0.1	< 0.1	< 0.1
Ag	< 0.1	< 0.1	< 0.1	< 0.1
Cd	< 0.1	< 0.1	< 0.1	< 0.1
In	< 0.1	< 0.1	< 0.1	< 0.1
Sn	2.0	1.9	1.9	1.9

Sb	< 0.1	< 0.1	< 0.1	< 0.1
Te	< 0.1	< 0.1	< 0.1	< 0.1
Cs	< 0.1	< 0.1	< 0.1	< 0.1
Ba	0.5	0.5	0.5	0.5
La	< 0.1	< 0.1	< 0.1	< 0.1
Ce	< 0.1	< 0.1	< 0.1	< 0.1
Pr	< 0.1	< 0.1	< 0.1	< 0.1
Nd	< 0.1	< 0.1	< 0.1	< 0.1
Sm	< 0.1	< 0.1	< 0.1	< 0.1
Eu	< 0.1	< 0.1	< 0.1	< 0.1

TABLE 25: Summary of the elements detected by ICP in S3 (cont'd)

ELEMENT	S3 CONCENTRATION (ppm wt%) ¹ REPLICATE 1	S3 CONCENTRATION (ppm wt%) ¹ REPLICATE 2	S3 CONCENTRATION (ppm wt%) ¹ REPLICATE 3	S3 AVERAGE CONCENTRATION (ppm wt%) ¹
Gd	< 0.1	< 0.1	< 0.1	0.1
Tb	< 0.1	< 0.1	< 0.1	0.1
Dy	< 0.1	< 0.1	< 0.1	0.1
Ho	< 0.1	< 0.1	< 0.1	0.1
Er	< 0.1	< 0.1	< 0.1	0.1
Tm	< 0.1	< 0.1	< 0.1	0.1
Yb	< 0.1	< 0.1	< 0.1	0.1
Lu	< 0.1	< 0.1	< 0.1	0.1
Hf	< 0.1	< 0.1	< 0.1	0.1
Ta	< 0.1	< 0.1	< 0.1	0.1
W	< 0.1	< 0.1	< 0.1	0.1
Re	< 0.1	< 0.1	< 0.1	0.1
Os	< 0.1	< 0.1	< 0.1	0.1
Ir	< 0.1	< 0.1	< 0.1	0.1
Pt	< 0.1	< 0.1	< 0.1	0.1
Au	< 0.1	< 0.1	< 0.1	0.1

Hg	< 0.1	< 0.1	< 0.1	0.1
Tl	< 0.1	< 0.1	< 0.1	0.1
Pb	< 0.1	< 0.1	< 0.1	0.1
Bi	< 0.1	< 0.1	< 0.1	0.1
Th	< 0.1	< 0.1	< 0.1	0.1
U	< 0.1	< 0.1	< 0.1	0.1

FOURIER TRANSFORM INFRARED SPECTROSCOPY (FT-IR)

[0063] Fourier Transform Infrared Spectroscopy (FT-IR) is a tool of choice for identification of materials. In FT-IR, the infrared absorption bands are assigned to characteristic functional groups. Based on the presence of a number of such bands, a material under consideration can be identified. Availability of spectra of known compounds increases the probability of making a positive identification. The lyophilized samples were analyzed by Horizontal Attenuated Total Reflectance (HATR), based on the internal reflection of infrared radiation (IR). The FT-IR spectrum of S1 with a spectral library match is presented in Fig. 13 below. The data suggests the material is consistent with sucrose. The FT-IR spectra of S2 and S3 are presented in Fig. 14 and Fig. 15. The assignment of the absorption against functional groups are shown in Table 26 -Table 28.

TABLE 26: Characteristic IR Absorption Band Assignments for sucrose in lyophilized S1 preparations

SUCROSE ³	LYOPHILIZED S1P1 WAVENUMBERS (cm ⁻¹)	LYOPHILIZED S1P2 WAVENUMBERS (cm ⁻¹)	LYOPHILIZED S1P3 WAVENUMBERS (cm ⁻¹)
OH stretching 3,566-3,263 cm ⁻¹	3,301 cm ⁻¹	3,315 cm ⁻¹	3,319 cm ⁻¹
C-H stretching 3,014 cm ⁻¹	Not detected	Not detected	Not detected
CH ₂ stretching 2,995-2,914 cm ⁻¹	2,923 cm ⁻¹	2,907 cm ⁻¹	2,918 cm ⁻¹
CH stretching 2,896-2,847 cm ⁻¹	Not detected	Not detected	Not detected
CH ₂ deformation, wagging 1,477-1,391 cm ⁻¹	Not detected	Not detected	Not detected
OH symmetric stretching 1,386 cm ⁻¹	1,372 cm ⁻¹	1,375 cm ⁻¹	1,371 cm ⁻¹
CH rocking 1,366-1,280 cm ⁻¹	Not detected	Not detected	Not detected
OH deformation 1,238-1,209, 1,161 cm ⁻¹	Not detected	Not detected	Not detected
C-C stretching 1,171, 1,073, 1,069, 943, 921 cm ⁻¹	924 cm ⁻¹	926 cm ⁻¹	926 cm ⁻¹
CO stretching 1,138-1,087, 1,053-991, 914, 909, 868 cm ⁻¹	1,135, 1,050, 993 cm ⁻¹	1,135, 1,050, 993 cm ⁻¹	1,135, 1,050, 993 cm ⁻¹
CH ₂ twisting 850 cm ⁻¹	832 cm ⁻¹	831 cm ⁻¹	833 cm ⁻¹

TABLE 26: Characteristic IR Absorption Band Assignments for sucrose in lyophilized S1 preparations

SUCROSE ³	LYOPHILIZED S1P1 WAVENUMBERS (cm ⁻¹)	LYOPHILIZED S1P2 WAVENUMBERS (cm ⁻¹)	LYOPHILIZED S1P3 WAVENUMBERS (cm ⁻¹)
C-O stretching 734 cm ⁻¹	Not detected	Not detected	Not detected

TABLE 27: Characteristic IR Absorption Band Assignments for sucrose in lyophilized S2 preparations

SUCROSE ³	LYOPHILIZED S2P1 WAVENUMBERS (cm ⁻¹)	LYOPHILIZED S2P2 WAVENUMBERS (cm ⁻¹)	LYOPHILIZED S2P3 WAVENUMBERS (cm ⁻¹)
OH stretching 3,566-3,263 cm ⁻¹	3,560 cm ⁻¹	3,562, 3,386, 3,337 cm ⁻¹	3,619, 3,338 cm ⁻¹
C-H stretching 3,014 cm ⁻¹	Not detected	Not detected	Not detected
CH ₂ stretching 2,995-2,914 cm ⁻¹	Not detected	2,941 cm ⁻¹	2,926 cm ⁻¹
CH stretching 2,896-2,847 cm ⁻¹	Not detected	2,891 cm ⁻¹	2,891 cm ⁻¹
CH ₂ deformation, wagging 1,477-1,391 cm ⁻¹	1,450, 1,404 cm ⁻¹	1,476, 1,432, 1,406 cm ⁻¹	1,463, 1,450, 1,435 cm ⁻¹
OH symmetric stretching 1,386 cm ⁻¹	Not detected	Not detected	Not detected
CH rocking 1,366-1,280 cm ⁻¹	1,343, 1,320, 1,279 cm ⁻¹	1,344, 1,322, 1,279 cm ⁻¹	1,344, 1,320, 1,278 cm ⁻¹
OH deformation 1,238-1,209, 1,161 cm ⁻¹	1,237, 1,205, 1,161 cm ⁻¹	1,238, 1,207 cm ⁻¹	1,236, 1,208 cm ⁻¹
C-C stretching 1,171, 1,073, 1,069, 943, 921 cm ⁻¹	1,116, 1,066, 921 cm ⁻¹	1,170, 1,116, 1,067, 943 cm ⁻¹	1,116, 1,067, 942 cm ⁻¹
CO stretching 1,138-1,087, 1,053-991, 914, 909, 868 cm ⁻¹	1,050, 990 cm ⁻¹	1,052, 1,013, 1,004, 989, 909 cm ⁻¹	1,051, 1,013, 1,004, 989, 910 cm ⁻¹
CH ₂ twisting 850 cm ⁻¹	867, 850 cm ⁻¹	868, 850 cm ⁻¹	867, 849 cm ⁻¹
C-O stretching 734 cm ⁻¹	Not detected	731 cm ⁻¹	Not detected


TABLE 28: Characteristic IR Absorption Band Assignments for sucrose in lyophilized S3 preparations

DEXTRAN ⁴	LYOPHILIZED S3P1 WAVENUMBERS (cm ⁻¹)	LYOPHILIZED S3P2 WAVENUMBERS (cm ⁻¹)	LYOPHILIZED S3P3 WAVENUMBERS (cm ⁻¹)
OH stretching ² 3,566-3,263 cm ⁻¹	3,304 cm ⁻¹	3,353 cm ⁻¹	3,340 cm ⁻¹
Exocyclic CO stretching 1,150 cm ⁻¹	1,154 cm ⁻¹	1,153 cm ⁻¹	1,153 cm ⁻¹
CO stretching + C-C deformation 1,107 cm ⁻¹	1,106 cm ⁻¹	1,105 cm ⁻¹	1,107 cm ⁻¹
C-O-C stretching 1,080 cm ⁻¹	1,075 cm ⁻¹	1,075 cm ⁻¹	1,079 cm ⁻¹
CH stretching 1,018 cm ⁻¹	1,016 cm ⁻¹	1,016 cm ⁻¹	1,015 cm ⁻¹

1H NUCLEAR MAGNETIC RESONANCE SPECTROSCOPY (NMR)


[0064] NMR Spectroscopy is an extremely useful method for material characterization. NMR is a physical phenomenon based upon the magnetic property of an atom's nucleus. NMR studies a magnetic nucleus (most commonly that of a hydrogen atom), by aligning it with a very powerful external magnetic field and perturbing this alignment using an electromagnetic pulse. The response to the perturbation is recorded, with each individual nucleus giving a response specific to its chemical, electronic, and spatial environment.

[0065] The lyophilized samples were reconstituted in deuterium oxide (D₂O) and analyzed by ¹H NMR spectroscopy.



[0066] The structure for sucrose is shown above with hydrogen annotation of Formula (I). The ^1H NMR for S1 is shown in Table 29 below:

ASSIGNMENT TS	CHEMICAL SHIFT (6 ppm)			
	SUCROSE	S1P1	S1P2	S1P3
A	5.418	5.43	5.43	5.43
B	4.219	4.22	4.22	4.22
C	4.055	4.06	4.07	4.06
D	3.89	3.83 (broad)	3.83 (broad)	3.83 (broad)
E	3.86			
F	3.826			
G	3.817			
J	3.762			
K	3.679	3.69	3.69	3.69
L	3.563	3.58	3.58	3.57
M	3.476	3.49	3.49	3.48



[0067] The structure of dextran is shown above with hydrogen annotation of formula (II). The following Table 30 shows the ^1H NMR for S3.

ASSIGNMENT S	CHEMICAL SHIFT (6 ppm)			
	DEXTRAN	S3P1	S3P2	S3P3
1	4.99	5.01 (shoulder)	5.01 (shoulder)	5.00 (shoulder)
2	3.58	3.60 (broad)	3.61 (broad)	3.60 (broad)
4	3.52			
3	3.74	3.77 (broad)	3.78 (broad)	3.77 (broad)
5	3.92	3.97 (broad)	3.97 (broad)	3.97 (broad)
6	3.99			

[0068] The NMR spectra of the prepared samples are presented in Figs. 16-18. Where possible, tentative assignments for the major chemical shifts observed in the NMR spectra were based on reference spectra of related compounds available in literature.

[0069] The data indicates that sucrose is present in sample S1, and the chemical shifts match well with those reported in the literature. However, no peak splitting patterns were observed, which could be due to multiple reasons such as the presence of nanoparticles or the paramagnetic iron itself.


[0070] The ^1H NMR spectra for sample S2 show a significant amount of peak broadening. It is unknown whether this is due to particulates which create an increased number of chemical environments, or if the nature of the iron in the sample could be responsible for the lack of resolution. Because of the extent of the broadening, no peak assignments could be made. However, the general peak intensities and chemical shifts are consistent with those observed for sucrose, as a large broad response was observed from chemical shift 2.5-4.2 ppm, with a slight shoulder visible on the solvent peak near 5.5 ppm.

13C NUCLEAR MAGNETIC RESONANCE SPECTROSCOPY (NMR)

[0071] The lyophilized samples were reconstituted in deuterium oxide (D₂O) and analyzed by ^{13}C NMR spectroscopy.

[0072] The results are summarized in Tables 28-30. The NMR spectra of the prepared samples are presented in Figs. 19-21. Where possible, tentative assignments for the major chemical shifts observed in the NMR spectra were based on reference spectra of related compounds available in literature.

[0073] The data indicates that sucrose is present in sample S1 and S2, and the chemical shifts match well with those reported in the literature. Note that like the proton spectra, sample S2 seemed to have broadening to a greater extent than sample S1. Finally, the peaks observed in sample S3 match well with literature values for dextran, indicating that it is present in the sample.




[0074] The structure of sucrose is shown above with carbon annotation. The results of ^{13}C NMR are shown in Tables 31 below:

Table 31: ^{13}C NMR assignments of sucrose and S1 in D_2O

ASSIGNMENT S	CHEMICAL SHIFT (6 ppm)			
	SUCROSE	S1P1	S1P2	S3P3
1	104.71	102.23	102.24	103.58
2	93.20	90.73	90.73	92.07
3	82.42	79.90	79.90	81.25
4	77.51	74.98	74.98	76.33
5	75.09	72.55	72.55	73.89
6	73.68	71.10	71.10	72.45
7	73.44	70.95	70.95	72.30
8	72.14	69.61	69.61	70.97
9	70.31	67.76	67.76	69.11
10	63.44	60.94	60.94	62.29
11	62.46	59.89	59.89	61.23
12	61.24	58.67	58.66	60.01

Table 32. ^{13}C NMR assignments of sucrose and S2 in D_2O

ASSIGNMENT S	CHEMICAL SHIFT (6 ppm)			
	SUCROSE	S2P1	S2P2	S2P3
1	104.71	103.53	103.71	103.69
2	93.20	91.97	92.19	92.23
3	82.42	81.15	81.42	81.38
4	77.51	76.17	76.41	76.28
5	75.09	73.75	73.98	74.01
6	73.68			
7	73.44			
8	72.14	70.93	70.97	70.97
9	70.31	68.99	69.38	69.14
10	63.44	62.06	62.34	62.29
11	62.46	61.07	61.36	61.16
12	61.24	59.85	60.11	59.98



[0075] The structure of dextran is shown above with carbon annotations of formula (III). The following Table 33 shows ^{13}C NMR for dextran of S3 in D_2O :

Table 33. ^{13}C NMR assignments of dextran and S3 in D_2O

ASSIGNMENTS S	CHEMICAL SHIFT (δ ppm)			
	DEXTRAN	S3P1	S3P2	S3P3
1	98.76	97.65	97.64	97.65

Table 33. ^{13}C NMR assignments of dextran and S3 in D_2O

ASSIGNMENTS S	DEXTRAN	CHEMICAL SHIFT (δ ppm)		
		S3P1	S3P2	S3P3
2	74.52	73.34	73.33	73.32
3	72.51	71.35	71.33	71.33
4	71.21	70.13	70.11	70.10
5	70.75	69.49	69.46	69.47
6	66.69	65.50	65.48	65.49

X-RAY DIFFRACTION (XRD) ANALYSIS (LYOPHILIZED MATERIAL)

[0076] XRD Analysis is a method by which a crystalline inorganic sample is irradiated with monoenergetic x-rays. The interaction of the lattice structure of the sample with these x-rays is recorded and provides information about the crystalline structure being irradiated. The resulting characteristic "fingerprint" allows for the identification of the crystalline compounds present in the sample. Using a whole-pattern fitting analysis (the Rietveld Refinement), it is possible to perform quantitative analyses on samples containing more than one crystalline compound.

[0077] The lyophilized samples were analyzed by XRD to characterize the chemical structure and phases present in the samples. The results from the analysis are presented in Table 34. Note that this sample preparation method resulted in sticky samples for S1 and S2 specifically (S3 was less sticky). For S1 and S2, a drop of methanol was added to the sample and the material was spread flat into the sample holder. Sample S3 was ground in a mortar and pestle.

Table 34: XRD phase identification and quantitative analysis for lyophilized samples

SAMPLE ID	PHASES IDENTIFIED	CONCENTRATION wt% ¹
S1	$\text{Na}_4\text{Fe}_2\text{O}_5$ -Sodium Iron Oxide	5.2
	Monoclinic, SG: P21/n (14)	
	PDF# 04-013-8809	
	Amorphous materials	
S2	$\text{C}_{12}\text{H}_{22}\text{O}_{11}$ - Sucrose	42.9
	Monoclinic, S.G.: P21 (4)	
	PDF# 02-063-8998	
	Amorphous materials	
S3	$\text{Na}_4\text{Fe}_2\text{O}_5$ -Sodium Iron Oxide	18.8
	Monoclinic, SG: P21/n (14)	
	PDF# 04-013-8809	
	Amorphous materials	

[0078] Fig. 22 overlays the XRD raw data from the three samples with small offsets for clarity. Sample S2 is different from the other two samples in terms of overall intensities, peak positions as well as peak shape. The broad peak shapes in samples S1 and S3 indicates that these samples consist of a mixture of nano-crystalline and amorphous materials.

[0079] Using best matches obtained by comparing the background modelled experimental data to the ICDD/CSD diffraction database for sample S1, S2, and S3, respectively, Sample S1 and S3 were determined to contain a mixture of amorphous and nano-crystalline materials. The sodium iron oxide reference pattern was superimposed on these experimental data. The markers indicate the location of expected diffraction peaks for each phase and the marker heights indicate the relative peak intensities for a fine-grained, randomly oriented material. Unlike the other two samples, sample S3 is primarily composed of sucrose and amorphous materials.

[0080] Semi-quantitative analysis was performed using WPF (whole pattern fitting), which is a subset of Rietveld Refinement that accounts for all areas above the background curve. This technique requires that either the structure factors and atomic locations or the reference intensity ratio (a way of comparing the diffracting power of different phases) are known for all phases identified. During this process, structure factor (which relates to concentration), lattice parameters (which relate to peak position), peak width and peak shape are refined for each phase to minimize the R value - an estimate of the agreement between the model and the experimental data over the entire pattern.

[0081] To obtain quantitative results from the sample that contains measurable amounts of amorphous material, the density of the amorphous has to be assigned in order to determine how much amorphous material is present. As a result, the concentration of amorphous material is uncertain. The locations of the amorphous peaks in these samples are assumed to be from the amorphous sucrose which has a density of approximately 1.59 g/cm³. Since WPF attempts to account for everything in the sample, any error in the amorphous concentration will result in errors in the crystalline phases as well. This means that the relative concentrations of the crystalline phases are correct, but the absolute values will be in error by amounts proportional to the error in amorphous concentration.

X-RAY DIFFRACTION (XRD) ANALYSIS (SUGAR-FREE MATERIAL)

[0082] The as received samples were diluted in water and placed in a 10000 Da molecular weight cutoff (MWCO) filter and centrifuged to remove the small molecules in the formulation (sugars) which caused amorphous material in the previous XRD analysis. The samples were then washed five more times with water to remove residual small molecules. The resulting material (in capable of passing through the filter) was lyophilized and analyzed by XRD to characterize the chemical structure and phases present in the samples. Note that sample S3 contained two distinct layers following centrifugation, a thick viscous layer and a thinner top layer. These layers were separated and lyophilized separately and analyzed as two samples. The results were averaged to afford the values seen in Table 35, but individual replicates of each layer are presented in the below figures. The results from the analysis are presented in Table 35.

Table 35: XRD phase identification and quantitative analysis for samples purified using MWCO filters, then lyophilized

SAMPLE ID	PHASES IDENTIFIED	CONCENTRATION wt% ¹
S1 (S1 ≡ S22)	Fe _{2.67} O ₄ - Maghemite	81.0
	Cubic, SG: P4332 (212)	
	PDF# [04-021-3968]	
	FeOOH - Iron Oxide Hydroxide	19.0
	Orthorhombic	
	PDF# [04-003-2900]	
S2 (S2 ≡ S23)	Fe _{2.67} O ₄ - Maghemite	89.9
	Cubic, SG: P4332 (212)	
	PDF# [04-021-3968]	
	FeOOH - Iron Oxide Hydroxide	10.1
	Orthorhombic	
	PDF# [04-003-2900]	
S3 ² (S3 ≡ S24 and S25)	Fe _{2.67} O ₄ - Maghemite	74.0
	Cubic, SG: P4332 (212)	
	PDF# [04-021-3968]	
	FeOOH - Iron Oxide Hydroxide	26.0
	Orthorhombic	
	PDF# [04-003-2900]	

wt% = weight percent, ±5%; 2 average of duplicate preparations (two layers observed)

[0083] An overlay of the XRD patterns from all four samples (two replicates for S3) is shown in Fig. 23. The patterns are offset for clarity. The phase identification was performed by comparing the best matches between the background-modelled experimental XRD data to the ICDD/ICSD diffraction database for the sample. The reference markers for the phase show where in two-theta the expected experimental peaks should be located and the height of the markers indicates the expected intensity of the experimental peaks, if the sample is fine-grained and randomly oriented. Note that XRD is sensitive to crystal structure but relatively insensitive to elemental or chemical state composition. The phase identification for these samples was difficult due the nanocrystalline nature of the samples which significantly broadens peak in the XRD patterns.

[0084] The best matches to the peaks present in all four samples are an iron oxide phase known as maghemite and an iron oxide hydroxide phase. The iron oxide hydroxide phase is atypical as it is formed from the heating of beta phase iron oxide hydroxide to about 300°C. Unfortunately, this reference card does not have the reference intensity ratio (RIR) included which is needed for semi-quantitative analysis. But as the symmetry and compositions are similar to that of the iron oxide hydroxide mineral goethite (alpha - FeOOH), the average RIR of goethite was used for the iron oxide hydroxide for semi-quantitative analysis.

[0085] Semi-quantitative analysis was performed using WPF (whole pattern fitting), which is a subset of Rietveld Refinement that accounts for all intensity above the background curve. This technique requires that either the structure factors and atomic locations or the reference intensity ratio (a way of comparing the diffracting power of different phases) are known for all phases identified. During this process, structure factor (which relates to concentration), lattice parameters (which relate to peak position), peak width and peak shape are refined for each phase to minimize the R value - an estimate of the agreement between the model and the experimental data over the entire pattern.

ACID DEGRADATION FOR LABILE IRON (III) USING UV-VISIBLE SPECTROSCOPY

[0086] UV/Vis Spectroscopy is used to determine analyte concentration either at one time or often over a desired time period. The technique measures the absorption of light across the ultraviolet and visible light wavelengths through a liquid sample. Samples are dispensed into a small vial and placed between the path of a UV/Vis light and a detector. According to Beer-Lambert's law, with a constant light path length and known absorption coefficient dependent upon wavelength, concentration of a compound in question can be determined from the light absorbed by the sample at that wavelength.

[0087] Samples were analyzed using the method adapted from B. S. Barot et al. (2014) which determines the amount of labile iron (III) in the samples using UV-Visible spectroscopy. The results are summarized in Table 36 below.

Table 36: Summary of determination of labile iron (III)

SAMPLE	REPLICATE	LABILE IRON (III) (%)	AVG LABILE IRON (III) (%)	% RSD ¹
S1	1	1.32%	1.48%	10.2%
	2	1.52%		

Table 36: Summary of determination of labile iron (III)

SAMPLE	REPLICATE	LABILE IRON (III) (%)	AVG LABILE IRON (III) (%)	% RSD ¹
	3	1.61%		
S2	1	2.14%	2.27%	5.3%
	2	2.38%		
	3	2.30%		
S3	1	1.40%	1.34%	3.7%
	2	1.33%		
	3	1.30%		

THERMOGRAVIMETRIC ANALYSIS (TGA)

[0088] TGA consists of measuring the weight change of a material as a function of temperature in a controlled atmosphere. The technique requires precise measurements of weight, temperature, and temperature change. The resulting thermogram generated from the analysis can determine the content of ingredient classes (e.g., solvents, polymers, inorganic fillers, etc.) and thermal stability of polymers. Precision and bias typical of TGA measurements are discussed under ASTM E2040.

[0089] The lyophilized samples were analyzed by Thermogravimetric Analysis (TGA) under nitrogen purge and air purge. Thermal decomposition of the samples occur in three distinct steps as shown in Fig. 24. The results of these steps are summarized in Table 37.

Table 37: Thermogravimetric analysis of S1, S2 and S3

ATMOSPHERIC CONDITION	SPECIMEN ANALYZED	% WEIGHT Loss AMBIENT TO 100°C	% WEIGHT Loss 100°C TO 245°C	% WEIGHT Loss 245°C TO 530°C	% WEIGHT Loss 530°C TO 800°C	% RESIDUE AT 800°C
Nitrogen	S1 Specimen	3.3	43.6	17.7	21.9	13.5
	S1 Specimen	3.3	42.3	36.4	6.6	11.4
	S1 Specimen	3.6	42.1	36.4	6.9	11.0
Method: Ramp 10.00°C/min to 800.00°C (N2 purge)	Average	3.4	42.7	30.2	11.8	12.0
	S2 Specimen	1.1	44.9	33.1	11.2	9.7
	S2 Specimen	1.0	45.3	36.3	7.6	9.8
	S2 Specimen	1.1	44.7	36.8	7.4	10.0
Isothermal for 2.00 min (N2 purge)	Average	1.1	45.0	35.4	8.7	9.8
	S3 Specimen	2.4	8.9	42.8	23.4	22.4
	S3 Specimen	4.8	7.7	56.0	15.7	15.6
	S3 Specimen	4.0	8.1	42.4	23.4	22.0
	Average	3.7	8.2	47.1	20.8	20.0
Air	S1 Specimen	3.0	42.8	37.5	5.8	11.0
	S1 Specimen	1.9	43.8	37.2	6.0	11.0
	S1 Specimen	2.5	42.9	37.6	5.4	11.5
	Average	2.5	43.2	37.4	5.7	11.2
Method: Ramp 10.00°C/min to 800.00°C (Air purge)	S2 Specimen	1.1	42.8	45.0	0.6	10.5
	S2 Specimen	0.7	43.4	45.0	0.7	10.2
	S2 Specimen	0.8	42.9	45.3	0.8	10.1
Isothermal for 2.00 min (Air purge)	Average	0.9	43.0	45.1	0.7	10.3
	S3 Specimen	4.2	8.2	63.1	2.9	21.6
	S3 Specimen	4.8	7.8	63.7	2.9	20.8
	S3 Specimen	5.2	7.4	62.3	3.1	21.9
	Average	4.7	7.8	63.0	3.0	21.4

DIFFERENTIAL SCANNING CALORIMETRY (DSC) AND DIFFERENTIAL THERMAL ANALYSIS (DTA)

[0090] The lyophilized samples were analyzed by Differential Scanning Calorimetry (DSC) under argon purge. Differential Scanning Calorimetry (DSC) measures the difference in the heat flows associated with transitions between a sample and an inert reference as a function of temperature and time. Such measurements provide quantitative and qualitative information about physical and chemical changes that involve endothermic or exothermic processes, or changes in heat capacity. See Fig. 25 for DSC thermograms. The summary of DTA is presented in Table 38 below.

Table 38: Summary of DTA results


Atmospheric Condition	Specimen Analyzed	Texo ₁ (°C)	AHexo ₁ (J/g)	Texo ₂ (°C)	Onset Texo ₂ (°C)	AHexo ₂ (J/g)
Ramp 10.00°C/min to 200.00°C (N2 purge)	S1 Specimen 1	33.2	63.8	155.8	138.2	187
	S1 Specimen 2	33.2	69.3	153.1	137.6	169
	S1 Specimen 3	35.1	130.9	155.9	147.3	159
	Average	33.8	88.0	154.9	141.0	171.7
	S2 Specimen 1	29.2	47.6	143.5	127.1	148
	S2 Specimen 2	n/a	n/a	142.8	* ₂	*
	S2 Specimen 3	n/a	n/a	147.6	*	*
	Average	29.2	47.6	127.1	127.1	148
	S3 Specimen 1	38.8	117.7	n/a	n/a	n/a
	S3 Specimen 2	44	45.6	n/a	n/a	n/a
	S3 Specimen 3	34.8	136.3	n/a	n/a	n/a
	Average	39.2	99.9	n/a	n/a	n/a

n/a=not observed; 2 *Possible overlapping transitions

HYDROXIDE VALUE BY TITRATION AND DETERMINATION OF MOLECULAR FORMULA

[0091] The as-received sample S1 was titrated in triplicate with 0.00998N HCl to determine the hydroxide value in iron-sucrose injectable solution. The end points of the titrations were pH = 7.0. Table 39 summarizes the results of this titration in S1.

[0092] Using the assumption that all basic species titrated were from the hydroxide associated with the ferric oxyhydroxide cores, the total number of moles of H⁺ used in the titration was assumed to be equal to the number of moles of OH⁻. Considering TOC, and Mw by GPC, the molecular formula of iron sucrose in S1 was calculated as below:



[0093] If Mn is considered for this calculation, the molecular formula is:




Table 39: Summary of the titration of S1 with 0.01N HCl

SAMPLE	REPLICATE	MASS OF S1 USED (g)	VOLUME OF 0.00998N HCl (mL) used to reach pH = 7.0	%RSD ¹
S1	1	1.0020	20.87	2.1%
	2	1.0007	21.21	
	3	1.0038	20.35	
	Average	1.0022	20.81	

[0094] Other embodiments and uses of the invention will be apparent to those skilled in the art from consideration of the specification and practice of the invention disclosed herein.

REFERENCES CITED IN THE DESCRIPTION

Cited references

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- WO2012028A [00011]
- WO971171A [00027]
- US200416503B [00028]

- DE882482 [0008]
- US2005309157A [0009]
- DE19547355 [0009]
- WO2018148217A1 [0009]

Non-patent literature cited in the description

- DANIELSONJ. Structure, chemistry, and pharmacokinetics of intravenous iron agentsAm. Soc. Nephrol., 2004, vol. 15, S93-S98 [0003]
- EVANS, R.W.RAFIQUE, R.ZAREA, A.RAPISARDA, C.CAMMACK, R.EVANS, P.J.PORTER, J.B.HIDER, R.C.Nature of non-transferrin-bound iron: studies on iron citrate complexes and the thalassemic era.J. Biol. Inorg. Chem., 2008, vol. 13, 57-74 [0004]

P A T E N T K R A V

1. Vandig jernsammensætning, der omfatter jernsaccharose og bicarbonat til anvendelse i en fremgangsmåde til forebyggelse eller behandling af en nyresygdom eller -lidelse, hvilken fremgangsmåde omfatter intravenøs administration af den vandige jernsammensætning i en terapeutisk effektiv mængde.
- 5 2. Vandig jernsammensætning til anvendelse ifølge krav 1, hvor sammensætningen har en pH-værdi, der er større end 9.
3. Vandig jernsammensætning til anvendelse ifølge krav 1 eller 2, hvor sammensætningen har en pH-værdi i intervallet fra ca. 10,5 til ca. 11,5.
4. Vandig jernsammensætning til anvendelse ifølge krav 1-3, hvor sammensætningen har en massefylde mellem 1,135 og 1,165 ved 20 °C.
- 10 5. Vandig jernsammensætning til anvendelse ifølge krav 1-4, hvor sammensætningen har en Mw ifølge GPC på mellem 30.000 og 40.000 dalton.
6. Vandig jernsammensætning til anvendelse ifølge krav 1-5, hvor sammensætningen har en Mw ifølge GPC på mellem 33.000 og 38.000 dalton.
- 15 7. Vandig jernsammensætning til anvendelse ifølge krav 1-6, hvor sammensætningen har en maksimal koncentration af jern (II) på 0,40 vægt/vol-%.
8. Vandig jernsammensætning til anvendelse ifølge krav 1-7, hvor sammensætningen har en koncentration af jern (II) på 0,05 vægt/vol-% til 0,40 vægt/vol-%.
9. Vandig jernsammensætning til anvendelse ifølge krav 1-8, hvor sammensætningen har en koncentraton af jern (II) på 0,10 vægt/vol-% til 0,20 vægt/vol-%.
- 20 10. Vandig jernsammensætning til anvendelse ifølge krav 1-9, hvor fremgangsmåden yderligere omfatter administration af en protoporphyrin.
11. Vandig jernsammensætning til anvendelse ifølge krav 1-10, hvor fremgangsmåden yderligere omfatter administration af tinprotoporphyrin.
- 25 12. Vandig jernsammensætning til anvendelse ifølge krav 1-11, hvor sygdommen eller lidelsen er kronisk nyresygdom, eller hvor sygdommen eller lidelsen er organtransplantatafstødning.
13. Vandig farmaceutisk jernsammensætning, der omfatter:
jernsaccharose;
bicarbonat; og
- 30 et farmaceutisk acceptabelt vandigt bærestof,
hvor jernsaccharosen forekommer i en farmaceutisk effektiv mængde til tilvejebringelse af en beskyttende virkning for en patients nyre, idet den farmaceutiske sammensætning har en pH-værdi i intervallet fra ca. 10,5 til ca. 11,5, en koncentration af jern (II) på 0,05 vægt/vol-% til 0,40 vægt/vol-%, og en Mw ifølge GPC er mellem 30.000 og 40.000 dalton.
- 35 14. Vandig jernsammensætning ifølge krav 13, hvor sammensætningen har en massefylde mellem 1,135 og 1,165 ved 20 °C; og/eller hvor Mw-værdien ifølge GPC er mellem 33.000 og 38.000 dalton.
15. Vandig jernsammensætning ifølge et hvilket som helst af kravene 13 eller 14, hvor sammensætningen har en koncentration af jern (II) på 0,10 vægt/vol-% til 0,20 vægt/vol-%.

DRAWINGS




Fig. 1




Fig. 2




Fig. 3:




Fig. 4





Fig. 5



୬୦




Fig. 7




Fig. 8




Fig. 9




Fig. 10




Fig. 1.1




FIG. 12




FIG. 13








FIG. 14



四百一十五

FIG. 16: ¹H NMR spectra of S1-preparation 1

FIG. 17: ¹H NMR spectra of S2-preparation 1

FIG. 18: ^1H NMR spectra of S3-preparation 1




FIG. 19: ¹³C NMR spectra of S1-preparation 1




FIG. 20: ^{13}C NMR spectra of S2-preparation 1




FIG. 21: ¹³C NMR spectra of S3-preparation 1




FIG. 22: Raw data comparison for the three samples (lyophilized)




FIG. 23: Offset overlay of the data from all three samples (two replicates for S33)




Fig. 24: TGA thermogram of S1, S2 and S3 under nitrogen purge condition




Fig. 25: DSC thermograms of S1, S2 and S3