

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
20 January 2005 (20.01.2005)

PCT

(10) International Publication Number
WO 2005/005674 A1

(51) International Patent Classification⁷: **C22B 19/04**,
19/34, 5/10, 5/12, 5/16, 13/02

(21) International Application Number:
PCT/EP2004/006238

(22) International Filing Date: 8 June 2004 (08.06.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
03077120.8 4 July 2003 (04.07.2003) EP
60/484,648 7 July 2003 (07.07.2003) US

(71) Applicant (for all designated States except US): **UMI-CORE** [BE/BE]; Rue du Marais 31, B-1000 Brussels (BE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **VAN CAMP, Maurits** [BE/BE]; Pansgatelaan 40, B-2640 Mortsel (BE). **AERTS, Jonathan** [BE/BE]; Duifhuisstraat 32, B-2300 Turnhout (BE). **JANSSENS, Benedict** [BE/BE]; Galgeveld 18, B-2200 Herentals (BE).

(74) Common Representative: **KNOCKAERT, Guy** et al.; Umicore, Kasteelstraat 7, B-2250 Olen (BE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declaration under Rule 4.17:

— of inventorship (Rule 4.17(iv)) for US only

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: RECOVERY OF NON-FERROUS METALS FROM ZINC RESIDUES

(57) Abstract: The invention relates to a process for the separation and recovery of non-ferrous metals from zinc-bearing residues, in particular from residues produced by the zinc manufacturing industry. The process allows for the valorisation of metal values in a Zn-, Fe- and Pb-bearing residue, and comprises the steps of: -subjecting the residue to a direct reduction step, thereby producing a metallic Fe-bearing phase and Zn- and Pb-bearing first fumes; - extracting the Zn- and Pb-bearing first fumes and valorising Zn and Pb; - subjecting the metallic Fe-bearing phase to an oxidising smelting step, thereby producing an Fe-bearing slag and second metals-bearing fumes; - extracting the second metals-bearing fumes and valorising at least part of their metallic content. The main advantage of this process is that an environmentally acceptable output for Fe is obtained.



WO 2005/005674 A1

Recovery of non-ferrous metals from zinc residues

This invention relates to the recovery of non-ferrous metals from zinc-bearing residues, in particular from residues produced by the zinc manufacturing industry.

Blende, which is an impure ZnS ore, is the main starting material for the production of Zn. The typical industrial practice encompasses an oxidative roasting step, producing ZnO together with sulphates or oxides of the impurities. In subsequent steps, the ZnO in roasted blende is brought into solution by leaching in neutral conditions or in weak acidic conditions, thereby producing Zn-depleted residues, respectively referred to as neutral leach residue and as weak acid leach residue in this description. However, during roasting, part of the Zn reacts with Fe, a typical impurity present in blende, and forms relatively insoluble zinc ferrite. The leach residues therefore contain, besides lead sulphate, calcium sulphate and other impurities, a sizeable fraction of Zn in the form of ferrite. According to present practice, the recovery of the Zn from ferrite requires a specific hydro-metallurgical residue treatment using high acid concentrations of 50 to 200 g/l H₂SO₄. In US 4,415,540 a process of this type is illustrated.

A disadvantage of this acidic treatment is that besides Zn, almost all the Fe and also other impurities such as As, Cu, Cd, Ni, Co, Tl, Sb are dissolved. As even low concentrations of these elements interfere with the subsequent electrowinning of Zn, they must be removed from the zinc sulphate solution. While Cu, Cd, Co, Ni and Tl are precipitated by addition of Zn powder, Fe is typically discarded as hematite, jarosite or goethite through hydrolysis. Due to the danger of washout of heavy metals, these Fe-bearing residues have to be disposed off in a well-controlled landfill. Land-filling of such residues has however come under heavy environmental pressure, rendering the sustainability of the process questionable. Another drawback of the above treatment is the loss of metals such as In, Ge, Ag and Zn in the Fe-bearing residue.

An alternative treatment of the ferrite bearing residues is applied in some plants, using Waelz kilns, which produce a slag and a Zn and Pb containing fume. Similarly, a rotary flame-fired furnace of the Dorschel type can be used in a batch process. In still another approach, the leach residue is processed, using coke as fuel, in a half shaft blast furnace, producing a Zn and Pb containing fume,

matte and slag. These pyro-metallurgical treatments generally result in an excellent recovery of Zn and Pb, and, for some of them, in a significant recovery of Ag, Ge and In.

- 5 These processes are however inadequate for modern zinc smelters, as they cannot be scaled up to large single-vessel operations. By this fact, they are not a cost efficient solution for today's Zn smelters.

10 A smelting reactor process is described in 'Smelting Reactor for Recovering Zinc from Industrial Low Zinc Bearing Residues', in Erzmetall 53 (2000) Nr. 6, p. 373-384. In this process, zinc and lead are flash-volatilised by means of the carbon contained in the residues as reduction agent and as fuel. Constituents such as iron oxide, silica and alumina form a slag which is further exhausted in
15 zinc and lead using a mixture of natural gas and oxygen blown on its surface. Iron oxide is however never reduced to the metallic state. The smelting reactor is operated at high temperatures, thereby using pure oxygen, making the economics of this process questionable.

- 20 Although numerous Zn fuming processes have been described, recent literature concentrates on the treatment of Zn-containing Fe-based secondary residues, such as EAF dusts. In this respect, the production of DRI (Direct Reduced Iron) by the direct reduction process, allows for the reduction of metals in the solid phase, thus
25 avoiding the extreme temperatures needed to produce a melt. Processing Fe-rich residues commonly aims at the recovery of pure metallic Fe. This process is well suited for treating an Fe-rich feed such as EAF dust, but fails to produce a good quality DRI from the low-Fe, highly contaminated residues which are the subject of this
30 invention. In such a case, the produced DRI indeed locks metals such as Cu, Ag and Ge and is therefore unsuitable for further processing by the steel industry.

One example of a process for treating Fe-rich residues is the Primus®
35 process, as described in 'Recycling of Zinc-Bearing Residues with the Primus® Process', in Iron Steelmaker I and SM, Vol. 30, Nr 4, p. 55-60. This two-stage process combines a multiple-hearth DRI furnace with an electric furnace for converting the reduced iron in a form usable in the ferrous industry, such as cast pig iron. In the second
40 step of this process, the DRI undergoes a final reduction, desulphurisation and carburization. It is intentionally avoided to re-oxidise any iron to the slag.

The primary aim of the invention is to provide for a process for the separation and recovery of a wide range of non-ferrous metals like Cu, Ag, Ge and Zn from residues of the Zn manufacturing industry; moreover, the process must ensure an environmentally acceptable output for Fe. The actual valorisation of Fe is however unimportant due to its relatively low concentration in the contemplated residues and to its rather low intrinsic value. These aims are achieved by a process for the valorisation of metal values in a Zn-, Fe- and Pb-bearing residue, comprising the steps of:

- 5 - subjecting the residue to a direct reduction step, thereby producing a metallic Fe-bearing phase and Zn- and Pb-bearing first fumes;
- extracting the Zn- and Pb-bearing first fumes and valorising Zn and Pb;
- 15 - subjecting the metallic Fe-bearing phase to an oxidising smelting step, thereby producing an Fe-bearing slag and second metals-bearing fumes;
- extracting the second metals-bearing fumes and valorising at least part of their metallic content.

20 In one embodiment of the invention, in the direct reduction step, a metallic Fe-bearing phase containing at least 50%, and preferably at least 90% of the Fe contained in the Zn-, Fe- and Pb-bearing residue is obtained; in another embodiment, during the oxidising step, Fe in the metallic Fe-bearing phase is oxidised to mainly FeO in the slag, and preferably at least 50%, or even at least 90% of the Fe in the metallic Fe-bearing phase is oxidised to FeO.

30 The Zn-, Fe- and Pb-bearing residue may be a neutral leach residue or a weak acid leach residue. The fluidity of the slag can be enhanced by avoiding massive formation of Fe_2O_3 , thus limiting the oxidation to the formation of mainly FeO. The presence of suitable amounts of an acidic flux such as sand and preferably, of a mixture of an acidic and a basic flux such as lime, limestone or dolomite, also enhances the slag fluidity, thus allowing for a lower working temperature.

40 If present, the major part of the Cu and Ag from the metallic Fe-bearing phase may be collected in a separate Cu-bearing phase during the oxidising smelting step.

If the Zn-, Fe- and Pb-bearing residue also contains Ge, the fraction of the Ge present in the first fumes, produced in the direct reduction step, may be separated and forwarded to the oxidising

smelting step. This separation of Ge is preferably performed by co-precipitation with Fe hydroxide or by addition of tannic acid. The same principles apply for In.

- 5 The first fumes may advantageously be oxidised in the reactor used for the direct reduction step.

The reactor used for the direct reduction step can be a multiple hearth furnace; the reactor for the oxidising smelting step can be a
10 submerged lance furnace.

The details of the invention are now discussed. The first step consists of the reduction of the residue, after addition of reductants such as natural gas, coal or cokes, and possibly fluxes
15 such as limestone (CaCO_3) to avoid sintering of the load, thereby producing Zn- and Pb-bearing fumes and a DRI-bearing phase containing, besides Fe, valuable metals such as Cu and Ag. Through leaching of these fumes, Zn and Pb can be separated in a Pb-
containing residue and a Zn-containing leaching liquor. Ge, if
20 present, is also dissolved in the leaching liquor, and can be precipitated as a Ge-containing residue and fed to the oxidising furnace, further enhancing the global Ge-recovery.

The DRI-bearing phase is smelted and oxidised in a second furnace,
25 preferably after addition of limestone and sand. The oxidation of Fe to FeO, and possibly to Fe_2O_3 , is particularly exothermic and brings in all the needed enthalpy. The process remains autogenous, even when e.g. 10% of the total feed consists of Ge-containing residues with
moisture content of around 25%. However, if more than 50% of the Fe
30 is oxidised to Fe_2O_3 instead of to FeO, the rise in liquidus temperature of the slag entails disadvantages such as increased lining wear and higher energy demands. The fact that Fe is slagged instead of being recovered as a metal, is a small price to pay for achieving an excellent separation and recovery of the non-ferrous
35 metals. The slag appears to be environmentally acceptable and can even be upgraded as gravel substitute in concrete. Next to this slag, two other streams can be recovered in this operation: fumes, typically containing Ge and In, and a Cu-bearing phase containing
precious metals such as Ag. This phase can be refined in a classical
40 Cu or precious metals flowsheet, separating the Cu and Ag in a Cu-rich and a Ag-rich stream. The fumes can be leached and used as feedstock for the production of Ge.

Useful reactor types such as multiple hearth furnaces and submerged lance furnaces lend themselves to the large single-vessel operations described in this invention. The overall process is energy efficient, bears low operational costs and ensures a high metal value recovery.

5 The invention thus provides for an essentially waste-free process that can compete economically with hydro-metallurgical Zn residue treatments.

The following example illustrates the separation of different non-ferrous metals contained in a roasted and subsequently leached blende. The analysis of the different feeds and productions are given in Table 1, together with the material balance.

10.000 g of weak acid leach residue, which mainly consists of zinc ferrite ($\text{ZnO} \cdot \text{Fe}_2\text{O}_3$), lead sulphate (PbSO_4), calcium sulphate (CaSO_4), zinc sulphate (ZnSO_4) and impurities like CaO , SiO_2 , MgO , Al_2O_3 , Cu_2O , SnO , is dried and thoroughly mixed with 3.000 g cokes, having a purity of >85% C. The amount of cokes is calculated in order to reduce Fe and the other metals in the DRI, and fume Zn and the other metals in the fumes, with an excess of around 5% to handle fluctuations in the feed composition. The metal content of the leach residue is given in Table 1, where "Others" refers to the impurities summed up above and to the bound oxygen and sulphur. For the cokes, "Others" refers to its ash content. No flux was added in this experiment.

The mixture is then loaded in a direct reduction furnace with an internal diameter of 454 mm and a height of 470 mm. Two arms are perpendicularly attached to a central shaft. The shaft is rotating at 2 rpm. Four teeth are located on each arm, which continuously stir the load. The teeth are positioned in such a way that one arm pushes the load towards the central shaft, while the other arm pushes in the opposite direction, resulting in a continuous stirring of the load without piling up at the furnace periphery. The atmosphere in the furnace is controlled by using a separate combustion chamber, where a mixture of air and natural gas is combusted. The nominal gas flow is 6 Nm^3/hr natural gas and 47 Nm^3/hr air, leading to a lambda value of 1. During 2 hours, the mixture is gradually heated until the temperature of the furnace atmosphere reaches 1100 °C; this temperature is maintained for approximately 4 hours. Fumes are collected using a cartridge filter, which is emptied every hour. The analysis of the fumes shown in Table 1 is the mean analysis of the hourly collected samples. These fumes are rich in Zn and Pb, present

as ZnO and PbO/PbSO₄. "Others" in Table 1 mainly consists of oxygen and sulphur bound to the fumed metals, together with some carry-over.

At the end of the reduction step, the DRI is removed from the furnace and sampled for analysis. The DRI obtained contains 88% of the Ag, 99% of the Cu, 70 % of the Ge, 7% of the Zn and 98% of the Fe when related to the feed. The low amount of Fe in the DRI (41,9%) is caused by the dilution with cokes remnants and light-metal oxides such as CaO, SiO₂, Al₂O₃ and MgO from the residue. This differentiates the obtained DRI from classic DRI's, which typically contain 80 to 90% Fe.

In a second step, sand and limestone are added to the DRI and the resulting mixture is loaded in an oxidising furnace. It is melted under N₂-atmosphere in a crucible and maintained at 1200 °C for about 3 hours, while air is bubbled through the molten bath, resulting in the burning of the remaining C from the cokes and in the oxidation of Fe to FeO. The amount of air needed for oxidation of the Fe to FeO is calculated based on the analysis of the DRI given in Table 1. Production of Fe₂O₃ is avoided to obtain a slag with as low a liquidus temperature as possible. The burning of cokes and the conversion of Fe to FeO generate enough energy to operate the furnace without any O₂ enrichment.

After the oxidative smelting step, three separate phases were recovered: fumes, slag and a Cu-bearing phase. The fumes are collected in a cartridge filter. Table 1 shows that these fumes are again rich in Zn and Pb. Thanks to the low total amount of fumes, elements like Ge and In, but also impurities like As, Sn, Bi and Sb, undergo a substantial concentration when related to the feed.

The environmental stability of the slag was tested on the slag as such and after formation of concrete containing 30% slag and 10% cement. The tests were performed according to European norm NEN 7343, whereby the material is broken to a PSD of less than 4 mm and percolated with acidified water. The leachability was assessed according to the VLAREA ("Vlaams reglement voor afvalvoorkoming") norm for non-ferro metallurgical slags. The leachability of both the slag and the slag-containing concrete proved to be well below the limits applicable to products intended for the building industry.

The Cu-bearing phase and the slag are separated by decantation, sampled and analysed. The slag analysis shows minimal amounts of

leachable heavy metals, such as Pb, ensuring that an environmentally clean slag is obtained. The high percentage of "Others" in the slag is attributable to CaO, SiO₂, MgO and Al₂O₃.

- 5 The Cu-alloy contains 89% of the Ag and 80% of the Cu in the feed, together with some impurities, mainly Fe, As, Sb, Sn.

Table 1: Material balance and metal recovery per produced phase

Feed to reduction step										
Component	Mass (g)	Composition (wt.%)								
		Ag	Pb	Cu	Zn	Fe	S	Ge	C	Others
Residue	10000	0,04	4,7	2,2	27,0	23,0	4,4	0,008		38,7
Cokes	3000					0,2	0,4		89	10,4

10

Products of reduction step										
Component	Mass (g)	Composition (wt.%)								
		Ag	Pb	Cu	Zn	Fe	S	Ge	C	Others
Impure DRI	5440	0,07	0,64	4,0	3,8	41,9	2,9	0,011	10	36,7
First fumes	4670	0,01	9,3	0,04	53,4	0,60	6,3	0,005		30,3

Feed to oxidising smelting step										
Component	Mass (g)	Composition (wt.%)								
		Ag	Pb	Cu	Zn	Fe	S	Ge	C	Others
Impure DRI	5440	0,07	0,64	4,0	3,8	41,9	2,9	0,011	10	36,7
Sand	1220									100
Limestone	800									100

Products of oxidising smelting step										
Component	Mass (g)	Composition (wt.%)								
		Ag	Pb	Cu	Zn	Fe	S	Ge	C	Others
Fe-slag	6780	<0,01	0,10	0,6	2,2	33,4	1,5	<0,001	<0,05	62,2
Cu-alloy	207	1,8	<0,1	85	<0,1	5,0	2,0	<0,001	<0,05	6,23
Second fumes	186	<0,01	15,2	1,0	32,4	1,0	2,35	0,32		47,7

(Table 1 continued)

Component	Fraction (wt.%)	Recovery (%)						
		Ag	Pb	Cu	Zn	Fe	S	Ge
Fe-slag	52		1	18	5	98	23	
Cu-alloy	2	89		80			1	
First fumes	36	11	93	1	92	1	65	30
Second fumes	1		6	1	2		11	70

- 5 The invented process thus achieves the separation of the metals as follows:
- Zn, Pb and a minor part of the Ge in first fumes which can be treated by known means for separation of Pb and Ge in different residues, and of Zn in a leach liquor;
 - 10 - Cu and Ag in an alloy which can be refined using a classical Cu and precious metals flowsheet;
 - Ge in second fumes that are greatly Ge-enriched and from which Ge can be refined cost-effectively;
 - Fe in an inert and environmentally clean slag, reusable as e.g.
 - 15 gravel substitute in concrete.

CLAIMS

1. Process for the valorisation of metal values in a Zn-, Fe- and Pb-
5 bearing residue, comprising the steps of:
- subjecting the residue to a direct reduction step, thereby
producing a metallic Fe-bearing phase and Zn- and Pb-bearing first
fumes;
 - extracting the Zn- and Pb-bearing first fumes and valorising Zn and
10 Pb;
 - subjecting the metallic Fe-bearing phase to an oxidising smelting
step, thereby producing an Fe-bearing slag and second metals-bearing
fumes;
 - extracting the second metals-bearing fumes and valorising at least
15 part of their metallic content.
2. Process according to claim 1, whereby in the direct reduction
step, a metallic Fe-bearing phase containing at least 50%, and
preferably at least 90% of the Fe contained in the Zn-, Fe- and Pb-
20 bearing residue is obtained.
3. Process according to claims 1 or 2, characterised in that during
the oxidising step, Fe in the metallic Fe-bearing phase is oxidised
to mainly FeO in the slag.
25
4. Process according to claim 3, whereby in the oxidising smelting
step, at least 50%, and preferably at least 90% of the Fe in the
metallic Fe-bearing phase is oxidised to FeO.
- 30 5. Process according to any one of claims 1 to 4, wherein the Zn-,
Fe- and Pb-bearing residue is a neutral leach residue or a weak acid
leach residue.
6. Process according to claims 3 or 4, characterised in that an
35 acidic flux and preferably, a mixture of an acidic and a basic flux
are present in the oxidising smelting step.
7. Process according to any one of claims 1 to 6, characterised in
that the Zn-, Fe- and Pb-bearing residue contains Cu and Ag, and
40 that, during the oxidising smelting step, a separate Cu-alloy phase
is produced containing a major part of the Cu and Ag.

8. Process according to any one of claims 1 to 7, characterised in that the Zn-, Fe- and Pb-bearing residue contains Ge, and that, after the direct reduction step, the fraction of the Ge present in the first fumes is separated and forwarded to the oxidising smelting
5 step.

9. Process according to claim 8, whereby the separation of Ge is performed by co-precipitation with Fe hydroxide or by addition of tannic acid.

10

10. Process according to any one of claims 1 to 9, whereby the first fumes are oxidised in the reactor used for the direct reduction step.

11. Process according to any one of claims 1 to 10, whereby the reactor used for the direct reduction step is a multiple hearth
15 furnace.

12. Process according to any one of claims 1 to 11, whereby the reactor used for the oxidising smelting step is a submerged lance
20 furnace.

INTERNATIONAL SEARCH REPORT

National Application No
PCT/EP2004/006238

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C22B19/04 C22B19/34 C22B5/10 C22B5/12 C22B5/16
C22B13/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C22B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, COMPENDEX

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	HEARD R ET AL.: "Recycling of Zinc-Bearing Residues with the PRIMUS Process" IRON STEELMAKER I AND SM, vol. 30, no. 4, April 2003 (2003-04), pages 55-60, XP009020220 the whole document	1-12
A	ESNA-ASHARI M ET AL: "SMELTING REACTOR FOR RECOVERING ZINC FROM INDUSTRIAL LOW ZINC BEARING RESIDUES" ERZMETALL, RIEDERER VERLAG GMBH. STUTTGART, DE, vol. 53, no. 6, 2000, pages 373-384, XP000959985 ISSN: 0044-2658 * Figure 1; pages 374-375 *	1-12

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

15 September 2004

Date of mailing of the international search report

23/09/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Bjoerk, P

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2004/006238

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 98/36102 A (BUCKETT GRAHAM ALAN ;BUKA TECH PTY LTD (AU); FOUNTAIN CHRISTOPHER) 20 August 1998 (1998-08-20) * page 20, lines 13-29 *	6
A	----- DATABASE COMPENDEX 'Online! ENGINEERING INFORMATION, INC., NEW YORK, NY, US; DE SCHEPPER A: "Liquid-liquid extraction of germanium by LIX-63" XP002260042 Database accession no. EIX78110005759 abstract & CHLORIDE HYDROMETALL, INT SYMP, PROC, 26 September 1977 (1977-09-26), - 28 September 1977 (1977-09-28) pages 357-384, Brussels, Belgium	7
A	----- GB 2 094 772 A (SAMIM SOC AZIONARIA MINERO MET) 22 September 1982 (1982-09-22) * page 1; lines 78-97 *	1-12
A	----- US 6 379 421 B1 (GUERRA-REYES MARIA TERESA ET AL) 30 April 2002 (2002-04-30) * Figure 1; column 3, lines 34-56 *	1-12
A	----- US 4 415 540 A (WILKOMIRSKY IGOR A E ET AL) 15 November 1983 (1983-11-15) cited in the application the whole document	1-12

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/EP2004/006238

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9836102	A	20-08-1998	AU 5974398 A WO 9836102 A1 ZA 9801286 A	08-09-1998 20-08-1998 17-08-1999
GB 2094772	A	22-09-1982	IT 1137505 B BE 892470 A1 CS 235010 B2 DE 3207026 A1 DK 99782 A FR 2501723 A1 GR 75875 A1 IE 52611 B1 LU 83997 A1 NL 8201028 A SE 462978 B SE 8201569 A YU 54482 A1	10-09-1986 13-09-1982 16-04-1985 16-09-1982 14-09-1982 17-09-1982 02-08-1984 23-12-1987 22-02-1983 01-10-1982 24-09-1990 14-09-1982 20-03-1985
US 6379421	B1	30-04-2002	AU 3317600 A EP 1165845 A2 ES 2200665 A1 WO 0050649 A2	14-09-2000 02-01-2002 01-03-2004 31-08-2000
US 4415540	A	15-11-1983	CA 1121605 A1 AU 526363 B2 AU 4608479 A BE 876054 A1 DE 2914823 A1 FI 791433 A ,B, FR 2424962 A1 GB 2020261 A ,B IE 48112 B1 JP 1456140 C JP 54147102 A JP 63000494 B US 4317803 A US 4619814 A US 4224122 A ZA 7901583 A	13-04-1982 06-01-1983 08-11-1979 03-09-1979 15-11-1979 06-11-1979 30-11-1979 14-11-1979 03-10-1984 09-09-1988 17-11-1979 07-01-1988 02-03-1982 28-10-1986 23-09-1980 28-05-1980