



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B32B 27/08, A61F 5/44, B32B 27/40		A1	(11) International Publication Number: WO 95/08440 (43) International Publication Date: 30 March 1995 (30.03.95)
<p>(21) International Application Number: PCT/US94/09682</p> <p>(22) International Filing Date: 26 August 1994 (26.08.94)</p> <p>(30) Priority Data: 08/123,270 20 September 1993 (20.09.93) US</p> <p>(71) Applicant: THE DOW CHEMICAL COMPANY [US/US]; 2030 Dow Center, Abbott Road, Midland, MI 48640 (US).</p> <p>(72) Inventors: ALLEN, Scott, I.; 570 Dogwood Drive, Newark, OH 43055 (US). FOYE, Duane, F.; 5327 South Pine, Beaverton, MI 48612 (US). FERGUSON, Michael; 222 Pembrroke Lane, Granville, OH 43023 (US).</p> <p>(74) Agent: HILL, Stanley, K.; The Dow Chemical Company, Patent Dept., P.O. Box 1967, Midland, MI 48641-1967 (US).</p>		<p>(81) Designated States: AU, CA, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report.</i></p>	
<p>(54) Title: MULTILAYER BARRIER FILM FOR OSTOMY APPLICATIONS</p> <p>(57) Abstract</p> <p>An oxygen and moisture impermeable multilayer barrier film was provided including a barrier layer comprising a homopolymer of vinylidene chloride or a copolymer of vinylidene chloride and vinyl chloride or methyl methacrylate. The barrier layer may be coated onto or coextruded with a water soluble film layer comprising a blend of a water soluble polymer such as polyvinyl alcohol, polycaprolactone, or polyethyloxazoline and a thermoplastic polyurethane. The multilayer film may be used for reusable or disposable ostomy bags and for heat sealable bags used in packaging agricultural chemicals, detergents, and other household chemicals.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

MULTILAYER BARRIER FILM FOR OSTOMY APPLICATIONS

The present invention relates to an oxygen and moisture impermeable coextruded or coated multilayer barrier film, and to articles produced therefrom including 5 ostomy bags and heat sealable bags for packaging a variety of materials.

Plastic film laminates having oxygen and moisture vapor barrier properties were desirable for current packaging requirements, as well as for use in medical applications such as the fabrication of ostomy bags. Such films have been provided through the use of multi-ply film laminates where at least one of the plies was oxygen and moisture vapor impermeable. 10 Typically, the films comprise chlorinated polyethylene films or plasticized polyvinyl chloride films, polyvinylidene chloride copolymer films, or multilayered structures such as ethylene vinyl acetate - polyvinylidene chloride/ethylene vinyl acetate combination films. Such constructions adequately meet the needs of oxygen and moisture barrier properties, but in use were often difficult to dispose of in a manner convenient to the user, such as by flushing the bag down a 15 toilet.

Martini et al, U.S. Patent No. 4,906,495, relate to a laminated film used for ostomy applications. The barrier and water soluble layers must be glued together using an additional adhesive layer. Such additional layers not only add to materials and manufacturing costs, but also result in a thicker film laminate having greater stiffness.

20 Both Brooks et al, U.S. Patent No. 4,772,279, and Coombes, U.S. Patent No. 4,917,689, relate to disposable ostomy bags having an outer water soluble layer of polyvinyl alcohol and an inner relatively insoluble layer of polyvinylidene chloride. Likewise, United Kingdom Patent Nos. 2,083,762 and 2,193,925 both show disposable ostomy bags which include a water soluble layer and a barrier layer.

25 However, many of the current prior art multilayer films do not have heat sealable surfaces, and thus, require complex processes for the fabrication of bags, such as positioning the barrier layer on only a portion of the film. Moreover, many require adhesives to laminate the layers so that they hold together. Accordingly, the need still exists for multilayer barrier films which may be produced by simpler and less expensive conventional processes without the 30 need for additional adhesive layers and lamination steps and for films which were impermeable to moisture and oxygen, provide odor barrier, and which have a heat sealable surface for forming bags or the like.

The present invention meets that need by providing an oxygen and moisture impermeable multilayer barrier film which may be produced by coextrusion or coating 35 techniques without the need for separate adhesive layers to secure the other layers together. The film provides excellent adhesion between layers, odor barrier characteristics, and a heat sealable surface for fabrication of bags.

According to one aspect of the present invention, an oxygen and moisture impermeable multilayer barrier film having a heat seal strength of at least 1.0 lb/inch of film width, and preferably greater than 1.5 lb/inch of film width was provided. By "oxygen impermeable", it was meant that the film has an oxygen transmission rate of equal to or less than 90 cc/m²/day atm. By "moisture impermeable", it was meant that the film has a water vapor transmission rate of equal to or less than 5 gm/m²/day.

In one embodiment of the invention, for use in ostomy applications, the film comprises a barrier layer of a homopolymer or copolymer of vinylidene chloride which was coextruded with or coated onto a water soluble film layer. The water soluble layer preferably 10 comprises a blend of a water soluble polymer such as polyvinyl alcohol, polycaprolactone, or polyethyloxazoline and a thermoplastic polyurethane. Preferably, the water soluble layer was thicker than the barrier layer and comprises from 1 to 50% by weight of the thermoplastic polyurethane, and more preferably from 10 to 25% by weight of the thermoplastic polyurethane. The water soluble film may be a monolayer or may include two or more layers 15 with the first layer comprising the water soluble polymer and thermoplastic polyurethane blend and the second layer comprising the same or different water soluble polymer to enhance the water solubility of the film.

Furthermore, the adhesion between the water soluble and barrier layers may be enhanced by a number of means. These include coating or coextruding a thermoplastic 20 polyurethane layer to the water soluble layer or blending an adhesion-enhancing amount of a thermoplastic polyurethane with the barrier layer. The resulting film has an oxygen transmission rate of less than 90 cc/m²/day atm. The barrier layer was formulated to heat seal to itself to form a disposable bag with the barrier film facing inward.

In an alternative form of this embodiment of the invention, the barrier film may 25 further comprise an optional heat sealable skin layer of a suitable adhesive resin including such as a thermoplastic polyurethane on the side opposite the water soluble layer. Such a layer provides enhanced heat seal properties to the film.

It has been found that the multilayer barrier films of the present invention have a sufficient bond between the layers to permit coextrusion or coating without the use of 30 additional adhesive layers and without the need for a lamination of the layers. Further, the resulting barrier film possesses properties which render the film suitable for use as disposable or reusable ostomy pouches, as well as packages for agricultural chemicals, detergents, and other household chemicals.

Accordingly, it was a feature of the present invention to provide an oxygen and 35 moisture permeable multilayer barrier film which may be produced using coextrusion or coating processes. Further features of the invention include odor barrier characteristics and the capability to form heat sealable bags and pouches from the film.

Fig. 1 was a schematic cross-section of one embodiment of the multilayer barrier film of the present invention useful as a disposable ostomy pouch including a water soluble layer; and

Fig. 2 was a front elevational view of an ostomy bag or pouch formed from the 5 multilayer barrier film of Fig. 1 of the present invention.

The multilayer barrier film of the present invention provides greater adhesion between layers than prior art laminated films without the need for separate adhesive or glue layers and the attendant cost associated with the extra manufacturing step involved with 10 lamination. This allows the films to be produced by a coating process in which the barrier film material was coated onto a water soluble film layer. The resulting multilayer films possess low oxygen and moisture vapor transmission rates, as well as having the odor barrier properties needed for ostomy applications. The practice of the present invention makes it possible to achieve these properties without the use of additional adhesive layers through the proper 15 selection and blending of the components of each layer of the film.

Referring now to Fig. 1, where the layer thicknesses were not to scale, one embodiment of the invention for ostomy applications was illustrated in which multilayer film 10-comprises a barrier layer 14 of a homopolymer or copolymer of vinylidene chloride with vinyl chloride or methyl methacrylate which was coextruded with or coated onto a water 20 soluble film layer 12. The water soluble layer 12 preferably comprises a blend of a water soluble polymer such as, for example, polyvinyl alcohol, polycaprolactone, or polyethyloxazoline and a thermoplastic polyurethane. Typically, water soluble layer 11 comprises from 1 to 50- by weight of the thermoplastic polyurethane, and more preferably from 10 to 25- by weight of the thermoplastic polyurethane. If desired, additional thermoplastic 25 polyurethane may be added to the blend to enhance the adhesion of the coating to the barrier layer. However, caution must be used as the water solubility of the film was adversely affected as the amount of thermoplastic polyurethane was increased. While the water soluble film may comprise a single monolayer of the blend, it was also possible to coextrude this blend with another water soluble polymer resin to produce a bi-layer film having enhanced water 30 solubility.

An example of a suitable barrier material includes a copolymer of vinyl chloride (15-20 percent by weight) and vinylidene chloride (80-85 percent by weight) commercially available from The Dow Chemical Company under the trademark Saran® F279. As the water soluble film layer, a water soluble polyvinyl alcohol resin such as Vinex® 5030 resin, 35 commercially available from Air Products and Chemicals, Inc. may be used. Where a bi-layer film having enhanced water solubility was desired, other water soluble polyvinyl alcohol resins such as Vinex® 2144 may be used. The two or more layers may be coextruded. If coextruded, the relative thickness of the two layers may be controlled, giving the advantage of being able to control the water solubility

characteristics of the film. For example, the unmodified water soluble polymer resin layer may comprise up to 75 percent or more of the bi-layer film to provide enhanced water solubility.

As previously discussed, from 1 to 50 percent of a thermoplastic polyurethane may be blended with the polyvinyl alcohol or other water soluble polymer layer. Suitable 5 thermoplastic polyurethanes include those based on the reaction of a polyisocyanate (aromatic or aliphatic) with polyester, polyether, or polycaprolactone polyols. Chain extenders such as diols and diamines may also be used in the reaction. Such thermoplastic polyurethanes were commercially available from the B.F. Goodrich Co. under the trademark Estane® and from The Dow Chemical Company under the trademark Pellethane®. A preferred thermoplastic 10 polyurethane composition was Pellethane® 2355-95AE.

As shown, an optional thermoplastic polyurethane skin 16 may be coextruded with or coated on the surface of water soluble layer 12. Skin layer 16, and/or the thermoplastic polyurethane blended into water soluble layer 12, acts as to enhance the adhesion of barrier layer 14 to water soluble layer 12. The resulting film should have an oxygen transmission rate 15 of less than 90 cc/m²/day/atm (6 cc/100 in²/day/atm). This higher oxygen transmission rate was acceptable for a barrier film which was designed to be disposable. As shown, the multilayer film may include an optional skin layer 18 of a heat sealable material such as, for example, a thermoplastic polyurethane or other suitable adhesive resin on the side of the film opposite water soluble layer 12 to provide enhanced heat seal properties for the film when folded to 20 form a bag or pouch.

Fig. 2 illustrates a typical disposable ostomy bag 20 including an opening 22 formed from the multilayer barrier film of Fig. 1. The bag may be formed by folding and heat sealing the edges of multilayer film 10. The film was preferably folded and sealed such that the barrier and heat sealable skin layers provide the inner surfaces of the bag or pouch 20. The 25 barrier film of the present invention provides an easily disposable ostomy pouch with the moisture resistance and odor and oxygen barrier properties needed. As will be appreciated by those skilled in the art, the barrier films of the present invention may also find use in other packaging applications where moisture and oxygen barrier properties were required.

The multilayer film of the present invention may be produced using conventional 30 extrusion or coating techniques. When using a coextrusion device, the configuration of the extrusion die can be varied and can be such as to reduce the thickness and dimensions of each individual layer. Thus, the thickness of the multilayer film may be controlled. Suitable coating devices include rotogravure coaters.

When coextruding a preferred embodiment of the water soluble film, advantages 35 were obtained when the adhesion-enhancing properties of the thermoplastic polyurethane were combined with the superior water solubility properties of the polyvinyl alcohol resin. In such a coextrusion, it was preferable to make the water soluble polyvinyl alcohol layer the thicker layer, comprising 75 percent or more of the overall film thickness. Typically, the water soluble

layer will be between 1 to 3 mils thick, while the barrier layer will have a thickness of between 0.1 to 0.2 mils.

However, it should be appreciated that many different layer combinations were possible. For example, the film may comprise a first layer of the water soluble 5 polymer/thermoplastic polyurethane blend, a second layer of a thermoplastic polyurethane, and a barrier layer comprising a vinylidene chloride homopolymer or copolymer. Another possible combination comprises the water soluble polymer/thermoplastic polyurethane blend and a barrier layer comprising a vinylidene chloride/ thermoplastic polyurethane blend. Still another combination was a coextruded three layer film comprising the water soluble 10 polymer/thermoplastic polyurethane blend and a layer of thermoplastic polyurethane, and a third layer comprising the polyvinylidene chloride/thermoplastic polyurethane blend. Still another possible combination includes a first layer comprising the water soluble polymer/thermoplastic polyurethane blend, a second layer comprising thermoplastic polyurethane, a third layer of a vinylidene chloride homopolymer or copolymer, and a fourth 15 layer of the thermoplastic polyurethane.

In order that the invention may be more readily understood, reference was made to the following examples, which were intended to be illustrative of the invention, but were not intended to be limiting in scope.

Example 1

20 A multilayer film was produced in accordance with the present invention by first dissolving 5- by weight of a thermoplastic polyurethane (Pellethane® 2354-80A5) in tetrahydrofuran at 45-50°C. The coating was applied to the surface of an extruded 2.0 mil thick polyvinyl alcohol film (Vinex® 5030 from Air Products and Chemicals, Inc.) containing 10 percent by weight thermoplastic polyurethane (Pellethane® 2355-95AE) at a coating weight of 25 2 gm/m², to yield a thickness of 0.05 mil. The coated film was then placed in an oven to dry for 1 1/2 minutes at 120°C.

A coating of the barrier material was then prepared by dissolving Saran® F279 resin in a mixture comprising 65 percent by weight tetrahydrofuran and 35 percent by weight toluene. The final lacquer contained approximately 18 percent by weight Saran®. The coating 30 was applied to the surface of the coated water soluble film at a coating weight of 4 gm/m² (approximately 0.1 mil thick) and dried at 110°C for two minutes to drive off the solvents and to crystallize the coating. The resulting multilayer barrier film had a heat seal strength of 7.7 N (1.73 lb) at 300°F, 30 psi, 1 sec dwell, and an oxygen transmission rate of 13.9 cc/m²/day:atm.

Example 2

35 A multilayer film was prepared as in Example 1 except that the water soluble film comprised 85 percent Vinex® 5030 and 15 percent Pellethane® 2355-95AE. The resulting film had a heat seal strength of 9.9 N (2.22 lb) at 300°F, 30 psi, 1 sec dwell, and an oxygen transmission rate of 8.4 cc/m² day:atm.

Example 3

A multilayer film was produced in accordance with the present invention by first dissolving 5 percent by weight thermoplastic polyurethane (Pellethane® 2354-80AI) in tetrahydrofuran at 45-50°C. The lacquer was applied to the surface of an extruded 2.0 mil thick 5 polyvinyl alcohol resin (Vinex® 5030 from Air Products and Chemicals, Inc.) containing 15 percent by weight Pellethane® 2355-95AE resin at a coating weight of 2 gm/m², to yield a thickness of 0.05 mil. The coated film was placed in an oven to dry for 1 1/2 minutes at 120°C.

A coating of the barrier material was prepared by dissolving Saran® F279 resin and Pellethane® 2354-80AI in a mixture comprising 65 percent by weight tetrahydrofuran and 10 35 percent by weight toluene so that the final lacquer contained approximately 18 percent by weight Saran® and 5 percent Pellethane®. The coating was applied to the surface of the coated water soluble film at a coating weight of 4 gm/m² (approximately 0.1 mil thick) and dried at 110°C for two minutes to drive off the solvents and crystalize the coating. The resulting film had a heat seal strength of 96.3 N (1.41 lb) at 300°F, 30 psi, 1 sec dwell, and an oxygen 15 transmission rate of 13.1 cc/m²/day/atm.

While certain representative embodiments and details have been shown for purposes of illustrating the invention, it will be apparent to those skilled in the art that various changes in the methods and apparatus disclosed herein may be made without departing from the scope of the invention, which was defined in the appended Claims.

20

25

30

35

1. A multilayer barrier film having a heat seal strength of 3t least 1.0 lb/inch width of said film, said film Comprising a barrier layer of a homopolymer of vinylidene chloride or a copolymer of vinylidene chloride with vinyl chloride or methyl methacrylate, said barrier 5 layer being coextruded with or coated onto a water soluble film layer, said water soluble layer comprising a blend of a water soluble polymer and a thermoplastic polyurethane.

2. The multilayer barrier film of Claim 1 in which said water soluble polymer was polyvinyl alcohol, polycaprolactone, or polyethyloxazoline.

3. The multilayer barrier film of Claim 1 in which said barrier layer includes 10 blended therein or coated on the surface thereof in contact with said water soluble film layer in adhesion enhancing amount of a thermoplastic polyurethane.

4. The multilayer barrier film of Claim 1 wherein said film has an oxygen transmission rate of less than 90 cc/m²/day/atm.

5. The multilayer barrier film of Claim 1 wherein said barrier layer further 15 comprises a layer of an adhesive polymer resin on the side opposite said water soluble layer.

6. The multilayer barrier film of Claim 5 in which said adhesive polymer resin was a thermoplastic polyurethane.

7. The multilayer barrier film of Claim 1 wherein said water soluble film layer comprises from 10-15 percent by weight of said thermoplastic polyurethane.

8. The multilayer barrier film of Claim 1 wherein said water soluble film layer 20 comprises from 10-15 percent by weight of said thermoplastic polyurethane.

9. The multilayer barrier film of Claim 1 wherein said water soluble film layer comprises two layers, the first layer comprising said blend of a water soluble polymer and a thermoplastic polyurethane and said second layer comprising a water soluble polymer.

10. The multilayer barrier film of Claim 1 wherein said water soluble layer was 25 thicker than said barrier layer.

11. The multilayer barrier film of Claim 1 wherein said moisture barrier layer and said thermoplastic polyurethane were heat sealed along their edges to form a bag or pouch.

30 12. A multilayer water soluble film comprising an inner layer of a thermoplastic polyurethane and outer layers of a water soluble film comprising a blend of a polyvinyl alcohol and a thermoplastic polyurethane.

FIG.1





FIG.2



INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 94/09682A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 B32B27/08 A61F5/44 B32B27/40

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 A61F B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 388 924 (E.R.SQUIBB & SONS) 26 September 1990	1,4,7,8
Y	see page 2, line 49 - page 4, line 50; claims 1,2,6; example 1 ---	1-5,9-11
Y	GB,A,1 384 791 (W.R.GRACE & CO.) 19 February 1975 see page 2, line 30-111; claims 1,5,6,10,13 ---	1-4
Y	DATABASE WPI Week 9414, Derwent Publications Ltd., London, GB; AN 94-114867 & JP,A,6 064 118 (KURARAY) see abstract ----	1,9 -/-

 Further documents are listed in the continuation of box C. Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

2 Date of the actual completion of the international search

Date of mailing of the international search report

13 October 1994

28.10.94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentiaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Derz, T

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 94/09682

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	GB,A,1 413 332 (UNILEVER) 12 November 1975 see page 2, line 27-89; claims 1,2; examples ---	5,6
Y	GB,A,2 212 167 (CRAIG MEDICAL PRODUCTS) 19 July 1989 see page 2, line 23 - page 3, line 6; claims 1,2,4,15,16 ---	1,5,6,11
A	GB,A,2 211 196 (NICHIGO FILM K.K.) 28 June 1989 see page 10, line 24 - page 11, line 9; claims 1-4; figures 2,3 ---	1,5,6
Y	EP,A,0 273 611 (W.R.GRACE & CO) 6 July 1988 cited in the application see column 5, line 31-44; claims 1,6,9,10,12,13,16; figure 2 see column 6, line 7-14 ---	1,4,5, 10,11
Y	EP,A,0 518 519 (SMITHS INDUSTRIES PLC) 16 December 1992 see column 1, line 55 - column 3, line 44; claims 1-5,7; figure 3 see column 4, line 18 - column 5, line 3 -----	1,10,11

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 94/09682

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
EP-A-0388924	26-09-90	US-A-	5009648	23-04-91
		CA-A-	2012010	22-09-90
		JP-A-	2280748	16-11-90
GB-A-1384791	19-02-75	AU-B-	471950	06-05-76
		AU-A-	5489373	31-10-74
		BE-A-	798778	16-08-73
		CA-A-	988828	11-05-76
		DE-A-	2321066	08-11-73
		FR-A-	2182164	07-12-73
		NL-A-	7305691	30-10-73
GB-A-1413332	12-11-75	DE-A-	2153854	17-05-73
		AT-B-	322865	10-06-75
		AU-B-	469001	29-01-76
		AU-A-	4817372	16-05-74
		BE-A-	790680	27-04-73
		CA-A-	973788	02-09-75
		CH-A-	560100	27-03-75
		FR-A,B	2158030	08-06-73
		JP-A-	48072289	29-09-73
		LU-A-	66379	03-05-73
		NL-A-	7214460	02-05-73
		SE-B-	401906	05-06-78
GB-A-2212167	19-07-89	NONE		
GB-A-2211196	28-06-89	JP-A-	1160550	23-06-89
		DE-A-	3842323	29-06-89
		FR-A-	2624728	23-06-89
		US-A-	4946720	07-08-90
EP-A-0273611	06-07-88	AU-B-	606109	31-01-91
		AU-A-	8300487	30-06-88
		CA-A-	1320324	20-07-93
		JP-A-	63168347	12-07-88
		US-A-	4906495	06-03-90
		US-A-	5110390	05-05-92
		ZA-A-	8709620	23-06-88

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 94/09682

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
EP-A-0518519	16-12-92	GB-A-	2257056	06-01-93